



US007116391B2

(12) **United States Patent**
Kim

(10) **Patent No.:** **US 7,116,391 B2**
(45) **Date of Patent:** **Oct. 3, 2006**

(54) **LIQUID CRYSTAL DISPLAY AND METHOD
FOR MANUFACTURING THE SAME
HAVING PARTICULAR PAD UNIT**

(75) Inventor: **Dong-Gyu Kim**, Suwon-si (KR)

(73) Assignee: **Samsung Electronics Co., Ltd.**, Suwon
(KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **11/208,781**

(22) Filed: **Aug. 23, 2005**

(65) **Prior Publication Data**

US 2006/0017873 A1 Jan. 26, 2006

Related U.S. Application Data

(63) Continuation of application No. 10/062,465, filed on
Feb. 5, 2002, now Pat. No. 6,937,314.

(30) **Foreign Application Priority Data**

Feb. 7, 2001 (KR) 2001-005967

(51) **Int. Cl.**
G02F 1/1345 (2006.01)

(52) **U.S. Cl.** 349/149; 349/151; 349/152

(58) **Field of Classification Search** 349/158,
349/139, 143, 149-152, 43, 113
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,295,711 A 10/1981 Tanaka et al. 349/149

5,066,106 A * 11/1991 Sakamoto et al. 349/54
5,352,318 A 10/1994 Takabayashi et al. 156/272.6
5,636,329 A * 6/1997 Sukegawa et al. 349/149
6,204,081 B1 * 3/2001 Kim et al. 438/30
6,690,185 B1 * 2/2004 Khandros et al. 324/758
6,697,040 B1 2/2004 Imajo et al. 345/98

FOREIGN PATENT DOCUMENTS

KR 10-1997-0018395 3/1999
KR 10-2000-0059471 10/2000
KR 10-2000-0066398 11/2000

* cited by examiner

Primary Examiner—Andrew Schechter
Assistant Examiner—Mike Qi

(57) **ABSTRACT**

Disclosed are a liquid crystal display (LCD) and a method for manufacturing the same, in which connection stability is improved when connecting a COG, a COF, or an FPC to a driving circuit. A substrate of the LCD has a display region and a non-display region at a peripheral area thereof. Terminals are provided to electrically connect an external circuit and a circuit of the display region to ends of signal lines extended from the display region and the non-display region. A flat protective layer is formed on the terminals. A plurality of pads are respectively formed of a first contact region and a flat second contact region, and each of the pads contacts a corresponding terminal, which is formed through a pad contact hole formed on the protective layer, at the first contact region, and each of the pads is electrically connected through an anisotropic conductive resin to a terminal of the external circuit by a pressing process at the flat second contact region.

10 Claims, 25 Drawing Sheets




FIG. 1A
(PRIOR ART)




FIG. 1B
(PRIOR ART)




FIG. 2A
(PRIOR ART)




FIG. 2B
(PRIOR ART)




FIG. 3A
(PRIOR ART)




FIG. 3B
(PRIOR ART)




FIG. 4




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13A




FIG. 13B




FIG. 14A




FIG. 14B




FIG. 15




FIG. 16A




FIG. 16B




FIG. 16C





FIG. 16D



LIQUID CRYSTAL DISPLAY AND METHOD FOR MANUFACTURING THE SAME HAVING PARTICULAR PAD UNIT

CROSS REFERENCE TO RELATED PATENT APPLICATION

This application is a continuation of prior U.S. patent application Ser. No. 10/062,465 filed on Feb. 5, 2002, now issued as U.S. Pat. No. 6,937,314, which claims priority to and the benefit of Korean Patent Application No. 2001-005967, filed on Feb. 7, 2001, which are hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a liquid crystal display and a manufacturing method thereof, and more specifically to a liquid crystal display and a manufacturing method thereof, in which connection stability is improved when connecting a COG (Chip On Glass), a COF (Chip On Film), or an FPC (Flexible Printed Circuit film) to a driving circuit.

2. Description of the Related Art

In an information-oriented society these days, the role of an electronic display is getting more important. The electronic displays of all kinds are widely used in various industrial fields. As techniques of the electronic display field are continuously developed, various electronic displays having new functions are provided corresponding to diverse requirements of the information-oriented society.

Generally, the electronic display is an apparatus for visually transmitting information to a person. That is, an electric information signal output from various electronic equipments is converted into a visually recognizable optical information signal in the electronic display. Therefore, the electronic display serves as a bridge for connecting the person and the electronic equipments.

The electronic display is classified into an emissive display that displays the optical information signal by emitting lights, and a non-emissive display that displays the signal by optical modulation such as light-reflecting, dispersing and interference, etc. The emissive display is called an active display. Examples are a CRT (Cathode Ray Tube), a PDP (Plasma Display Panel), an LED (Light Emitting Diode) and an ELD (Electroluminescent Display), etc. The non-emissive display is called a passive display. The examples are an LCD (Liquid Crystal Display) and an EPID (Electrophoretic Image Display), etc.

The CRT has been used for image display such as in a television and a monitor, etc., over the longest period of time. The CRT has enjoyed the highest market share because of high display quality and low costs. However, it also has much disadvantage such as heavy weight, large volume and high power consumption.

Meanwhile, due to rapid development of semiconductor technologies, various kinds of electronic devices are driven at lower voltage and consuming less power, rendering the electronic equipments much slimmer and lighter. Therefore, a flat panel type display of slimmer and lighter property as well as the less driving voltage and lower power consumption property is required according to the new environment.

An LCD, among various flat panel type displays, is much slimmer and lighter than any other displays. It can be driven at a lower voltage and consume less power. It also shows high display quality similar to the CRT. Therefore, the LCD is widely used in various electronic equipments. Further,

since the LCD can be facily manufactured, its application is getting wider. The LCD is classified into a backlight LCD that displays an image using an external light source and a reflective LCD that displays the image using ambient light instead of the external light source. Methods of manufacturing the backlight LCD and the reflective LCD are disclosed in Korean Patent Laid-Open Publication Nos. 1999-18395 entitled "Method of manufacturing polycrystalline silicon thin film transistor", 2000-66398 entitled "Method of manufacturing TFT-LCD panel" and 2000-59471 entitled "Reflective type LCD and manufacturing method thereof".

FIGS. 1A, 1B, and 1C are cross-sectional views disclosing a conventional method of manufacturing the LCD.

Referring to FIG. 1A, a metallic material such as Al and Cr, etc., is deposited on a substrate **10** of an insulating material, and then patterned to form a gate electrode **15** and a gate terminal **20**. Continuously, a gate insulating layer **25** is formed on the entire surface of the substrate **10**, where the gate electrode and terminal **15, 20** are formed, by a PCVD (plasma chemical vapor deposition) process.

Thereafter, an in-situ doped n⁺ type amorphous silicon film is deposited on the gate insulating layer **25** and then patterned to form an amorphous silicon layer **30** and an ohmic contact layer **35** on the gate electrode **15**.

The metallic material such as Mo, Al, Cr or W, etc., is further stacked on the gate electrode **15** and then patterned to form a source electrode **40** and a drain electrode **45**. At this time, in a pad area **70** of the substrate **10**, there is formed a data input terminal (not shown). Thus, in an active region **50** of the substrate **10** except the pad area **70**, is formed a thin film transistor **60** including the gate electrode **15**, the amorphous silicon layer **30**, the ohmic contact layer **35**, the source electrode **40** and the drain electrode **45**.

Referring to FIG. 1B, an organic photoresist layer is stacked on the entire surface of the active region **50** and the pad region **70** of the substrate **10** to form a protective layer **75**. Thus, the lower substrate **10** is completed.

Referring to FIG. 1C, in order to form a contact hole **80**, **81**, a mask (not shown) is positioned on an upper portion of the protective layer **75**. Then, the contact hole **80, 81** is formed on the protective layer **75** by an exposing and developing process so as to partially expose the drain electrode **45** and the gate terminal **20**.

Afterwards, the metallic material such as Al or Ni, having a high reflectivity, is deposited in an inner portion of the contact hole **80, 81** and on the organic insulating layer (protective layer) **75**. The deposited metallic material is patterned in the form of a desired pixel to form a reflective electrode **85** and a pad **86**. Then, an alignment layer is formed thereon. An upper substrate (not shown) including a color filter, a transparent electrode and the alignment layer is formed facing the lower substrate **10**.

The upper substrates and the lower substrate are put together with spacers interposed therebetween. A liquid crystal layer is formed at a space between the upper substrate and the lower substrate to complete the LCD.

The completed LCD is connected to a connecting device such as a COG, a COF or an FPC, etc., so as to apply a driving signal through the pad **86** from an outside.

However, in the above-mentioned conventional method of manufacturing the LCD, since the organic insulating layer or other thick layer is used as the protective layer of the thin film transistor, a step difference is generated between a pad portion under which the metal layer is formed and a remaining portion. Therefore, there is a problem that a pressing

failure occurs due to the step difference, when connecting a bump, etc., of the COG, the COF or the FPC to the pad portion.

FIG. 2A is a plan view of a conventional pad structure having the step difference by opening the contacts according to each terminal, and FIG. 2B is a cross sectional view taken along a line A—A when connecting the bump by a pressing process.

Referring to FIGS. 2A and 2B, in the conventional individual terminal opening type pad structure, a pad contact hole **102** having a little smaller surface area than that of a lower terminal **100** is formed in a protective layer **106**. Then, a pad **104** having an area a little wider than the surface area of the terminal **100**, is formed in order to electrically connect the terminal **100** and the pad **104**.

As a result, the protective layer is thickly formed in a thickness of about 5 μm , the terminal of the pad contact hole **102** is formed about 3–4 μm high. An adhesive resin (ACF: anisotropic conductive film) **108a** containing a conductive ball **108b** is coated thereon. A bump **110** connected to a terminal part of a driver IC is pressed on the ACF **108a**. Therefore, the pad **104** and the bump **110** are electrically connected to each other by the conductive ball **108b** compressed therebetween.

As shown in FIG. 2B, however, since only a peripheral region of the pad contact hole is electrically connected by the step difference of the pad contact hole **102**, and the conductive ball **108b** is not fully compressed at the center of the pad **104**, an electrical connection may fail. Therefore, a contact resistance generally increases, thereby lowering electrical properties.

In addition, if a misalignment between the bump and the pad occurs, the contact resistance further increases. The high contact resistance at the contact portion generates a large amount of resistance heat. As the result, the contact is cut off and thus the reliability of the device is lowered.

Therefore, in order to solve the above problem, there has been provided a terminal batch opening method. FIG. 3A shows a plan view of a conventional flat pad structure formed by collectively opening the terminals and FIG. 3B shows a cross sectional view of the flat pad structure when connecting a bump by a pressing process.

Referring to FIGS. 3A and 3B, an opening **112** including the whole terminals is formed on the protective layer to open the plurality of terminals. After depositing a pad conductive material thereon, a photolithography process is performed to form a pad pattern every terminal. Therefore, a flat pad **104** without a contact step difference is formed on the terminal **100**. In this method, all of the conductive balls **108b** is fully compressed between the bump **110** and the pad **104**, thereby improving the contact capability there between.

However, as shown in FIG. 3B, if the bump **110** is misaligned, the protective layer between the terminals **100** is removed due to the opening **112**, and thus the conductive ball **108b** is compressed at a portion in which the bump **110** is overlapped with an adjacent terminal, as shown in an “X” portion of FIG. 3B. Therefore, two terminals are electrically connected with one bump at the same time, causing contact failures.

Further, as shown in a “Y” portion of the FIG. 3B, when the opening **112** is formed where a data input terminal is formed, an under-cut portion is formed at an insulating layer of a lower portion of the terminal **100**. Therefore, the terminal **100** tends to peel off, or the adhesive resin **108a** is not sufficiently coated under the under-cut portion, exposing the under-cut portion to the outside. Also, moisture or contaminant infiltrates through the exposed portion and

electrochemically reacts with a metal portion of the terminal to cause corrosion of the metal portion.

SUMMARY OF THE INVENTION

Therefore, it is an object of the present invention to provide an LCD capable of securing connection stability when connecting a COG, a COF and FPC, etc with an LCD panel.

It is another object of the present invention to provide a method that is suitable for manufacturing the above LCD.

To achieve the aforementioned object of the present invention, there is provided an LCD comprising: a substrate; a pixel array formed on a display region of the substrate in a matrix configuration; a plurality of first terminals which are formed at a non-display region of the substrate, the first terminals having a contact region and applying an electrical signal to a plurality of column lines and row lines of the pixel array; a protective layer in which contact holes are formed corresponding to the contact region of each of the terminals, and which covers the pixel array and the first terminals; and a plurality of first pads formed on the protective layer to be overlapped with each of the first terminals with a surface area greater than the contact region, the first pads electrically connected through the contact holes to each of the first terminals and substantially electrically connected to an external circuit at a region other than the contact region.

Preferably, the terminals are aligned in zigzag of two rows. Each of first inner terminals arranged along an inside portion of the first row among the first terminals, has a first contact region at an inner portion thereof and a second contact region at an outer portion thereof and each of first outer terminals arranged along an outside portion of the first row among the first terminals has a first contact region at an outer portion thereof and a second contact region at an inner portion thereof.

Further, output terminals of at least one or more IC device are bonded at the area except the contact region of the first pads by a bump bonding method.

According to one embodiment of the present invention, a plurality of second pads are formed on the protective layer to be aligned along an edge portion of the substrate in one row, and input terminals of the IC device are respectively bonded to one side of each second pad.

Preferably, the other side of each second pad is boned to terminals of a flexible printed circuit board, and the plurality of second pads are respectively electrically connected through at least one or more contact hole to a plurality of second terminals which is formed at a lower portion of the protective layer.

Preferably, an entire surface area of at least one or more contact region of each second terminal is one third and below of an entire surface area of each terminal.

The second terminals may respectively have the contact regions that are aligned at both ends of the second terminals in a length direct, or the plurality of contact regions that are aligned at regular intervals in the length direction, or the elongated contact regions which are aligned at both ends of the second terminals in width direction.

The first pads may be aligned in one row, and connected through other area except the contact region to terminals of a TCP, a COF or an FPC.

A reflective type LCD according to another embodiment of the present invention comprises a first substrate in which a plurality of pixels are formed into a matrix configuration at a center portion thereof, and a plurality of terminal parts

for applying an electrical signal to the pixels is formed at an edge portion thereof; a second substrate which is formed to be opposite to the first substrate; a liquid crystal layer which is formed between the first and second substrates; a reflective electrode which is formed at the center portion of the first substrate to have an irregular portion; a protective layer which is formed from a first area to a second area between the first substrate and the reflective electrode to have an opening for exposing each contact region of the plurality of terminals, the protective layer having the same surface structure as the reflective electrode at the first area and a flat surface structure at the second area; and a plurality of pads which is formed on the protective layer to include the opening and have a surface area greater than the opening, and connected through other area except the opening to a terminal part of an external circuit.

Further, an LCD according to the present invention comprises a first substrate having a pixel array circuit in which a plurality of pixels are formed into a matrix configuration at a center portion thereof, a plurality of data pads formed at a first peripheral region to apply a data signal through each data line to the plurality of pixels, and a plurality of gate pads formed at a second peripheral region to apply a gate signal through each data line to the pixels; a second substrate in which a color filter array is formed corresponding to the center portion of the first substrate and a transparent common electrode is formed thereon; a liquid crystal layer interposed between the first and second substrates.

The device further comprises at least one or more data driving IC chip which is bump-bonded to the data pads at the first peripheral region by a COG mounting way; and a gate driving IC chip bonded to the gate pads at the second peripheral region by a COF mounting way, wherein the data pads respectively have a surface area greater than that of a contact region contacted with the data line and are bonded to each terminal of the data driving IC chip at an area except the contact region, and the gate pads respectively have a surface area greater than that of a contact region contacted with the gate line and are bonded to each terminal of the gate driving IC chip at the area except the contact region.

To achieve the aforementioned second object of the present invention, there is provided a method of manufacturing an LCD comprising the steps of depositing and photo-etching a first conductive material on a substrate to form a gate pattern including a gate electrode, a gate line, and a gate terminal part; covering the gate pattern with a gate insulating layer; depositing and photo-etching a semiconductor material and a second conductive material on the gate insulating layer to form a data pattern including an active pattern, source and drain electrodes, a data line and a data terminal part; covering a resultant material with a protective layer; photo-etching the protective layer to open a contact region of the source electrode, the gate terminal part and the data terminal part; depositing and photo-etching a conductive material on the protective layer to a pixel electrode and a bonding pad, the bonding pad having a surface area greater than the contact region; and bonding a terminal part of a driving IC device at an area except the contact region of the bonding pad.

The protective layer has an irregular surface, and the pixel electrode is formed of a reflective metallic material selected from a group consisting of Al, an Al alloy, Ag and an Ag alloy. The driving IC device is mounted by a TCP, COF or COG method.

According to the present invention, the pad is formed on the thick protective layer in its longitudinal direction to have twice or more surface area as large as the first contact region.

The remaining flat area except the first contact region is provided as the second area for contacting with an external circuit terminal. Therefore, even if the misalignment between the external circuit terminal and the pad is generated, a preferred contact property can be maintained.

BRIEF DESCRIPTION OF THE DRAWINGS

The above objects and other advantages of the present invention will become more apparent by describing in detail the preferred embodiments thereof with reference to the attached drawings in which:

FIGS. 1A and 1B are cross-sectional views of a conventional manufacturing method of an LCD;

FIGS. 2A and 2B are a plan view of a conventional pad structure having a contact step difference by opening contacts according to each terminal, and a cross-sectional view of the conventional pad structure when connecting a bump by a pressing process;

FIG. 3A is a plan view of a conventional flat pad structure formed by collectively opening terminals and FIG. 3B is a cross sectional view of the flat pad structure when connecting a bump by a pressing operation;

FIG. 4 is a plan view of a data COG mounting LCD according to one embodiment of the present invention;

FIG. 5 is a cross-sectional view taken along the line C-C' of FIG. 4;

FIG. 6 is a plan view of a pad structure which is arranged in zigzag according to other embodiment of the present invention;

FIG. 7 is a cross-sectional view taken along the line D-D' of FIG. 6;

FIG. 8 is a cross-sectional view taken along the line C-C' of FIG. 6;

FIGS. 9, 10, and 11 are plan views of the pad structures which are aligned in one row according to embodiments of the present invention;

FIG. 12 is a plan view of a modified pad structure according to another embodiment of the present invention; and

FIGS. 13A, 13B, 14A, 14B, 15, 16A, 16B, 16C and 16D are sectional views showing a manufacturing method of the LCD according to one embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Now, preferred embodiments of the present invention will be described in detail with reference to the annexed drawings.

FIG. 4 is a plan view of an LCD according to one embodiment of the present invention.

Referring to FIG. 4, an LCD panel according to the present invention includes a TFT substrate 200 and a color filter substrate 300. The color filter substrate 300 is formed with a color filter and a transparent common electrode. The TFT substrate 200 is disposed facing the color filter substrate 300. Liquid crystal is injected into a space between the TFT substrate 200 and the color filter substrate 300, and then sealed. The color filter substrate 300 has a surface area smaller than the TFT substrate 200. A portion in which the TFT substrate 200 is overlapped with the color filter substrate 300 corresponds to a display region 212, and a peripheral region which is the remaining area of the TFT substrate 200, corresponds to a non-display region 214.

On the non-display region **214**, there are formed signal lines extended from the display region **212** to the non-display region **214**, gate lines and pads connected to each end of data lines.

Further, in the non-display region **214**, one end of a COG IC **210** as a data driving IC is connected to data line pads (not shown) by a bump bonding method, and the other end of the COG IC **210** is connected to a film cable or an FPC (flexible printed circuit) **220** to be connected through a circuit pattern formed at the peripheral area to an external integrated circuit board (not shown). The gate lines (not shown) are connected to a COF **230** as a flexible printed circuit having a gate driving IC device mounted thereon.

FIG. 5 is a cross-sectional view taken along the line C-C' of FIG. 4. On a substrate **200** are formed a plurality of first terminals **201**, a plurality of second terminals **202a** and a plurality of third terminals **202b**. The second terminals **202a** and the third terminals **202b** are connected to each other through a metal line. The first, second and third terminals are covered by a protective layer **203**. On the protective layer **203**, there are formed pad contact holes **203a**, **203b**, **203c** corresponding to each of the first, second and third terminals **201**, **202a**, **202b**. First, second and third pads **204**, **205**, **206** are formed on the protective layer **203**.

The first, second and third pads **204**, **205**, **206** are respectively formed with first contact regions **204a**, **205a**, **206a** and second contact regions **204b**, **205b**, **206b**. The second contact regions **204b**, **205b**, **206b** of each pad have a flat plane on the protective layer **203**. The first, second and third pads **204**, **205**, **206** are respectively coated by anisotropic conductive adhesive resin **207**. The anisotropic conductive adhesive resin **207** contains a plurality of conductive balls **208**.

Bumps **211**, **212** of the COG IC **210** are aligned with the second contact region **204b**, **205b** of the first and second pads **204**. Then, the COG IC **210** is pressed to compress the conductive balls **208** between the bumps **211**, **212** and the second contact regions **204b**, **205b**. Thus, the bumps **211**, **212** are electrically connected with the first pad **204** and the second pad **205**, respectively. The bump **211** is an output terminal of the COG IC **210**, and the bump **212** is an input terminal of the COG IC **210**.

Further, an output terminal **222** of the FPC **220** is aligned with the second contact region **206b** of the third pad **206** and then pressed on the second contact region **206b**. The conductive balls **208** are compressed between the output terminal **222** and the second contact region **206b**, so that the output terminal **222** of the FPC **210** is electrically connected with the third pad **206**.

FIG. 6 is a plan view of a pad structure of the LCD according to one embodiment of the present invention.

Referring to FIG. 6, since a plurality of first terminals **201** formed at an extended portion of a data line have a very narrow pitch, the first terminals **201** are aligned alternately in a zigzag fashion. Each of first inner terminals **201a** which are arranged along an inside portion of the first row among the first terminals **201**, has a first contact region **204a1** at an inner portion thereof and a second contact region **204b1** at an outer portion thereof. Each of first outer terminals **201b** that are arranged along an outside portion of the first row among the first terminals **201**, has a first contact region **204a2** at an outer portion thereof and a second contact region **204b2** at an inner portion thereof. The bumps **211** as output terminals of the COG IC **210** are also aligned in two rows of zigzag type. The bumps of a first row are disposed such that they respectively correspond to the second contact regions of pads of the first row. The bumps of a second row

are disposed such that they respectively correspond to the second contact regions of the pads of the second row.

FIG. 7 shows a cross-sectional view taken along the line D-D' of FIG. 6. As shown in FIG. 7, the bump **211** is misaligned at the second contact region of the pad to be slightly shifted to a left side. However, since the bump **211** is pressed on a thick protective layer **203**, it is not possible that the bump **211** may be shorted to an adjacent terminal.

FIG. 8 shows a cross-sectional structure taken along the line E-E' of FIG. 6. As shown in FIG. 8, a surface of a pad **204** is not flat at a first contact region **204a** due to a step coverage of a pad contact hole **203a**.

According to the present invention, as described above, on the protective layer **203** is formed a pad of which a surface area is twice as large as that of a pad contact hole, and a flat contact region except the first contact region contacts the terminal of an external circuit or a driving IC device, thereby reducing the contact defect.

As shown in FIGS. 9, 10 and 11, since a second terminal **250** and a third terminal **256** have a pitch greater than the first terminals. Thus, the second terminal and the third terminal are aligned in one row. Pads aligned in one row are appropriate for a TCP, COF or FPC type OLB (out lead bonding) method. Since a length of the pad aligned in one row is long, a distance between a first contact region and a second contact region increases, generating a resistance difference. In this case, it is preferred to form a plurality of pad contact holes on each terminal. Particularly, ITO or IZO can be used as a pad material in a transparent type LCD.

FIGS. 9, 10 and 11 are plan views of the pad structure aligned in one row according to the present invention.

As shown in FIG. 9, at both ends of a terminal **250** on a protective layer, there is formed each pad contact hole **252**, **254**. A pad **256** is then formed thereon.

Further, as shown in FIG. 10, a plurality of pad contact holes **258** are formed in a protective layer in a length direction respectively apart from each other at regular intervals. The pad **256** is then formed thereon.

As shown in FIG. 11, at both ends of the terminal **250** in a wide direction, there are formed each elongated contact hole **260**, **262**. Then, the pad **256** is formed thereon. In this case, a second contact region between the elongated contact holes **260**, **262** is designed to sufficiently have their surface areas. This embodiment is useful when forming a pad corresponding to a gate terminal that is formed under a gate insulating layer.

As described above, in case the plurality of pad contact holes are formed on each terminal, it is preferred that the first contact region is designed to have one third and below of a surface area of the second contact region. By forming the pad in this way, in which the plurality of pad contact holes are formed on each terminal, the non-uniform resistance generated by the misalignment of a probe is reduced in a full probing test which is performed before a bonding process. Also, although the pads are partially damaged or cut during the test process by the probe, the electrical connection is maintained by other contacts.

FIG. 12 shows a plan view of a modified pad structure according to the present invention.

As shown in FIG. 12, a surface area of a pad **274** may be twice or more as large as that of a terminal **270**. In this case, a pad contact hole **272** has preferably a little smaller surface area than the terminal **270**. And a first contact region **274a** of pad **274** is a half or smaller size of a second contact region **274b**.

FIGS. 13A through 16D are cross-sectional views and plan views showing manufacturing processes of an LCD according to the present invention.

FIGS. 13A and 13B are a cross-sectional view and a plan view showing a state that a gate electrode and a gate input pad are formed on a first substrate.

Referring to FIGS. 13A and 13B, after a metallic material such as Al, Mo, Cr, Ta, Ti, Cu or W, etc., is deposited on a first substrate 400 which is formed of a non-conductive material such as glass or ceramic, the deposited metallic material is patterned so as to form a gate line 415 aligned at a desired interval in a lateral direction of the first substrate 100, a gate electrode 405 branched from the gate line 415, and a gate input terminal 410 extended to an outer wall of the first substrate 400. At this time, the gate input terminal 410 is formed to have a surface area greater than the gate electrode 405 and the gate line 415 in order to avoid a possible misalignment when forming a pad contact hole.

In addition, the gate electrode 405, the gate input terminal 410 and the gate line 415 may be respectively formed of an Al—Cu alloy or an Al—Si—Cu alloy.

FIGS. 14A and 14B are a cross-sectional view and a plan view showing a state that a data line and a data input terminal are formed.

Referring to 14A and 14B, on the entire surface of the first substrate 400 on which the gate electrode 405, the gate input terminal 410 and the gate line 415 are formed, a silicon nitride (Si_3N_4) film is stacked by PCVD (plasma chemical vapor deposition). The stacked silicon nitride film is patterned to form a gate insulating layer 420.

Sequentially, a silicon material as a semiconductor material is deposited on the gate insulating layer 420. And an amorphous silicon film and an insitu doped n^+ type amorphous silicon film are stacked in order by the PCVD. Then, a metallic layer formed of Al, Mo, Ta, Ti, Cr, W or Cu is stacked on the semiconductor layer formed of the semiconductor material.

The amorphous silicon film and the insitu doped n^+ type amorphous silicon film are patterned to form a semiconductor layer 430 and an ohmic contact layer 435 on a portion of the gate insulating layer 420, under which the gate electrode 405 is positioned. The metallic layer is also patterned to form a data line 460 orthogonal to the gate line 420, a source electrode 440 and a drain electrode 445 branched from the data line 460, and a data input terminal 450 at a side of the data line 460. Thus, a TFT transistor 455 including the gate electrode 405, the semiconductor layer 430, the ohmic layer 435, the source electrode 440 and the drain electrode 445 is completed at a center portion of the first substrate 400 as a device forming area. The gate input terminal 410 and the data input terminal 450 are formed at an edge portion of the first substrate 400. In this case, the gate insulating layer 420 is interposed between the data line and the gate line to prevent an electrical short therebetween.

FIG. 15 is a cross-sectional view showing a state that an organic insulating film as a protective film is formed on the first substrate.

Referring to FIG. 15, a photosensitive organic photoresist is coated on the device forming area, on which the TFT transistor 455 is formed, and a pad area 480, which is formed at the edge side of the first substrate 400, in a thickness of about 3~4 μm by a spin coating method to form an organic insulating layer 465.

In a reflective or semi-transparent LCD, in order to form a concavo-convex (prominence/recess) structure at a reflective electrode, the organic insulating layer is exposed and developed to form the concavo-convex structure at the

organic insulating layer. A reflective electrode is stacked on the organic insulating layer on which the concavo-convex structure is formed. There are provided a method of fully exposing a double layer or a method of partially exposing or slit-exposing a single layer, in order to form the concavo-convex structure at the organic insulating layer.

FIGS. 16A through 16D are cross-sectional views taken along the line F—F' and G—G' of FIG. 14B and show a process of forming the organic insulating layer.

Referring to FIG. 16A, after the gate input terminal 410, the data input pad 450 (not shown) and a first mask 185 for exposing a peripheral region of the gate input terminal and the data input pad are positioned at an upper portion of the organic insulating layer 465 of the first substrate 400, an exposure process is performed with a desired light amount. Then, a contact hole 475 for exposing the drain electrode 445 of the TFT transistor 455 and a pad contact hole 476 of the data and gate input terminal 450, 410 are formed on the organic insulating layer 465 by a developing process.

Referring to FIG. 16B, a second mask 200 is positioned on an upper portion of the organic insulating layer 465. Then a partial exposing or slit exposing process and a developing process are performed to form a plurality of concavo-convex structures 505 as micro lenses on the organic insulating layer 465 of a device area 470 of the first substrate 400.

Referring to FIG. 16C, a metallic material such as Al, Ni, Cr or Ag having an excellent reflectivity is deposited at the pad area 480, an inside portion of the contact hole 475 for exposing the source electrode 445 and an upper portion of the organic insulating layer 465 on which the concavo-convex structure 505 is formed. The deposited metal is patterned in the form of a desired pixel and pad to form the reflective electrode 510 and the pad 512. Therefore, the plurality of concavo-convex structures are formed on the reflective electrode 510, which is formed on the device area 470 of the first substrate 400, according to a shape of the organic insulating layer 465. At this time, the pad 512 is formed on the data input terminal 450 and the gate input terminal 410. The pad 512 is formed to include a first contact region 512a and a second contact region 512b. The second contact region 512b is formed on a flat surface of the organic insulating layer 465.

FIG. 16D is a cross-sectional view of a completed LCD according to the embodiment of the present invention. A first alignment layer 300 is formed on the resultant structure. Then, a second substrate 305 including a color filter 310, a common electrode 315, a second alignment layer 320, a phase difference plate 325 and a polarizing plate 330 is disposed on the first substrate 400.

A plurality of spacers 335, 336 are interposed between the first substrate 400 and the second substrate 305 to form a liquid crystal layer 230 at a space between the first and second substrate 400, 305, thereby forming the reflective or semi-transparent LCD.

Thereafter, an anisotropic resin layer 490 including a conductive ball 492 is disposed on a second contact region 512b of an input pad 512 that is formed on a pad portion 480 of the first substrate. A bump 494 is pressed on the anisotropic resin layer 490 of the second contact region 512b to complete a module of the reflective or semi-transparent LCD.

According to the present invention, the pad is formed on the thick protective layer in its longitudinal direction to have twice or more surface area as large as the first contact region. The remaining flat area except the first contact region is provided as the second area for contacting an external circuit terminal. Therefore, even if the external circuit terminal and

11

the pad are misaligned, a preferred contact property can be maintained. Further, as the pad is aligned in a zigzag fashion of two rows, the adjacent pads are not shorted.

While the present invention has been described in detail, it should be understood that various changes, substitutions and alterations can be made hereto without departing from the spirit and scope of the invention as defined by the appended claims. 5

For example, in case of the backlight LCD, the concavo-convex structure is not formed on the protective layer, and a transparent conductive material such as ITO and IZO is used as the reflective electrode and pad material. 10

What is claimed is:

1. An array substrate comprising:

a substrate including a display region and a non-display region; 15

a pixel array arranged in the display region to display an image; and

a pad unit arranged in the non-display region to electrically connect an external circuit to the pixel array, the pad unit comprising: 20

a first contact region having a contact hole;

a second contact region adjacent to the first contact region;

a first metal layer arranged over the first contact region and the second contact region; 25

an insulating layer on the first metal layer, the insulating layer having a plurality of contact holes; and

12

a second metal layer arranged over the insulating layer and electrically connected to the first metal layer through contact holes, wherein the bump located in the second contact region, contacts a second metal layer through a plurality of conductive balls.

2. The array substrate of claim 1, wherein the contact holes are arranged along a longitudinal direction of the pad unit.

3. The array substrate of claim 2, wherein the contact holes are spaced apart from each other by a substantially same distance.

4. The array substrate of claim 1, further comprising an organic layer formed on the insulating layer.

5. The array substrate of claim 1, wherein the contact holes are formed at both end portions of the pad unit.

6. The array substrate of claim 1, wherein the pixel array includes a gate line and a data line.

7. The array substrate of claim 6, wherein the pad unit is electrically connected to the gate line or the data line.

8. The array substrate of claim 1, wherein the second metal layer is larger than the first metal layer.

9. The array substrate of claim 1, wherein the first contact region is located at both end portions of the pad unit.

10. The array substrate of claim 1, wherein the material of said second metal layer is ITO or IZO.

* * * * *

专利名称(译)	液晶显示器及其制造方法，具有特定的垫单元		
公开(公告)号	US7116391	公开(公告)日	2006-10-03
申请号	US11/208781	申请日	2005-08-23
[标]申请(专利权)人(译)	金东GYU		
申请(专利权)人(译)	金东GYU		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD.		
[标]发明人	KIM DONG GYU		
发明人	KIM, DONG-GYU		
IPC分类号	G02F1/1345 G02F1/13 G02F1/1362 G09F9/00 G09F9/30 G09F9/35 H01L21/60 H01L29/786		
CPC分类号	G02F1/13452 G02F1/13458 H05K3/361 H05K1/114 H05K1/117 H01L2224/16225 H05K2201/09436 G02F2001/133357 G02F2001/133388 H05K3/323 H01L2924/00014 H01L2224/0401		
优先权	1020010005967 2001-02-07 KR		
其他公开文献	US20060017873A1		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种液晶显示器 (LCD) 及其制造方法，其中当将COG，COF或FPC连接到驱动电路时改善了连接稳定性。LCD的基板在其外围区域具有显示区域和非显示区域。提供端子以将外部电路和显示区域的电路电连接到从显示区域和非显示区域延伸的信号线的末端。在端子上形成平坦的保护层。多个焊盘分别由第一接触区和平坦的第二接触区形成，并且每个焊盘在第一接触区处接触相应的端子，该端子通过形成在保护层上的焊盘接触孔形成，并且每个焊盘通过各向异性导电树脂通过在平坦的第二接触区域处的压制工艺电连接到外部电路的端子。

