

(19)



(11)

EP 2 019 432 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
17.09.2014 Bulletin 2014/38

(51) Int Cl.:
H01L 27/32^(2006.01)

(21) Application number: **08158487.2**

(22) Date of filing: **18.06.2008**

(54) Organic light emitting display and method of manufacturing the same

Organische lichtemittierende Anzeige und Verfahren zu ihrer Herstellung

Affichage électroluminescent organique et son procédé de fabrication

(84) Designated Contracting States:
DE FR GB HU

(30) Priority: **23.07.2007 KR 20070073385**

(43) Date of publication of application:
28.01.2009 Bulletin 2009/05

(73) Proprietor: **Samsung Display Co., Ltd.**
Yongin-City, Gyeonggi-Do, 446-711 (KR)

(72) Inventors:
• **Kwak, Won-Kyu**
c/o Legal & IP Team Samsung SDI Co., Ltd
Gyeonggi-do (KR)

• **Chun, Hae-jin**
c/o Legal & IP Team Samsung SDI Co., Ltd
Gyeonggi-do (KR)

(74) Representative: **Walaski, Jan Filip et al**
Venner Shipley LLP
200 Aldersgate
London
EC1A 4HD (GB)

(56) References cited:
WO-A1-01/81649 JP-A- 2003 271 075
JP-A- 2007 157 470 US-A- 5 760 855
US-A1- 2003 094 615

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 019 432 B1

Description

[0001] The present invention relates to an organic light emitting display and a method of manufacturing the same, and, more particularly, to an organic light emitting display capable of protecting a driving circuit from electrostatic discharge (ESD) and a method of manufacturing the same.

[0002] An organic light emitting display is a self-emission display that has a wider view angle, a higher contrast, a faster response speed, and a lower power consumption as compared to that of a liquid crystal display (LCD). Because a back light is not required, the organic light emitting display can be made to be light and thin.

[0003] The organic light emitting display includes a first substrate having a pixel (or display) region and a non-pixel (or non-display) region and a container (or a second substrate) provided to face the first substrate for encapsulation and to be attached to the first substrate by a sealant such as epoxy.

[0004] In the pixel region, a plurality of organic light emitting diodes (OLEDs) are coupled between scan lines and data lines in a matrix to form pixels. Each OLED includes an anode electrode, a cathode electrode, and an organic thin layer formed between the anode electrode and the cathode electrode, wherein the organic thin layer includes a hole transport layer, an organic light emitting layer, and an electron transport layer.

[0005] In the non-pixel region, the scan lines and data lines are extended from the scan lines and the data lines of the pixel region, power source supply lines are disposed for operating the OLEDs, and a scan driver and a data driver are disposed for processing signals supplied from an external source through an input pad to supply the processed signals to the scan lines and the data lines. The scan driver and the data driver include a driving circuit for converting the signals supplied from the external source into scan signals and data signals to selectively drive the pixels. The scan driver and the data driver can be formed in a process of manufacturing the OLEDs or can be manufactured as an additional integrated circuit chip to be mounted on a substrate of the organic light emitting display. Since the substrate of the organic light emitting display is formed of glass, a large electrostatic discharge (ESD) can be generated during manufacturing or when the organic light emitting display is being used. In particular, because the driving circuit is composed of thin film transistors (TFTs) which are operated at high speed, a low voltage is formed in a peripheral part of the organic light emitting display, thereby causing the driving circuit to directly receive the ESD. When the ESD is received, the channels and the gate insulating layers of the TFTs may be damaged, erroneous operations may be generated by the short between the gate electrodes and wiring lines, and/or the driving circuit may be damaged due to the electric influence. The driving circuit is more severely damaged by the ESD as the driving circuit is highly integrated (or minimized).

[0006] In order to prevent (or protect) the driving circuit from being damaged by the ESD, an additional protecting element or a protecting circuit capable of discharging a high voltage may be added. However, the element or the protecting circuit is designed to discharge the ESD generated during the manufacturing processes and its effectiveness in preventing (or reducing) the damage generated during the use of the organic light emitting display is limited.

[0007] JP2007 157470 and US2003/094615 disclose organic light emitting displays having shielding layers in the non-pixel region. US5760855 discloses formation of a guard ring to address the problem of electrostatic discharge in an active matrix LCD display.

[0008] Aspects of the present invention are directed toward an organic light emitting display capable of protecting a driving circuit against electrostatic discharge (ESD) and a method of manufacturing the same. Other aspects of the present invention are directed toward an organic light emitting display capable of preventing (or reducing) damage caused by the ESD without adding an additional protecting element (or an ESD protecting circuit) and a method of manufacturing the same.

[0009] According to the invention, there is provided an organic light emitting display according to claim 1.

[0010] The present invention provides a method of manufacturing an organic light emitting display as disclosed in claim 8.

[0011] The accompanying drawings, together with the specification, illustrate exemplary embodiments of the present invention, and, together with the description, serve to explain the principles of the present invention.

FIG. 1 is a plan view schematically illustrating an organic light emitting display according to an embodiment of the present invention;

FIG. 2 is a sectional view schematically illustrating the organic light emitting diode (OLED) illustrated in FIG. 1;

FIGs. 3A and 3B are sectional views schematically illustrating organic light emitting displays according to embodiments of the present invention;

FIG. 4 is a sectional view schematically illustrating an organic light emitting display according to a first embodiment of the present invention;

FIG. 5 is a sectional view schematically illustrating an organic light emitting display according to a second embodiment of the present invention;

FIG. 6 is a sectional view schematically illustrating an organic light emitting display according to a third embodiment of the present invention; and

FIGs. 7A, 7B, 7C, and 7D are sectional views schematically illustrating a method of manufacturing an organic light emitting display according to an embodiment of the present invention.

[0012] In the following detailed description, only certain exemplary embodiments of the present invention are

shown and described, by way of illustration. As those skilled in the art would recognize, the invention may be embodied in many different forms and should not be construed as being limited to the embodiments set forth herein. Also, when a first element is referred to as being "on" a second element, it can be directly on the second element or be indirectly on the second element with one or more intervening elements interposed therebetween. In addition, when a first element is described as being "coupled to" a second element, the first element may be not only directly coupled to the second element but may also be indirectly coupled to the second element via one or more intervening elements. Further, elements that are not essential to the complete understanding of the invention may be omitted for clarity. Like reference numerals designate like elements throughout the specification.

[0013] FIG. 1 is a plan view schematically illustrating an organic light emitting display according to an embodiment of the present invention.

[0014] As shown in FIG. 1, a substrate 100 includes a pixel region 140 and a non-pixel region 160. The non-pixel region 160 can be the region surrounding the pixel region 140 and/or the remaining region excluding the pixel region 140. In the pixel region 140, a plurality of organic light emitting diodes (OLEDs) 180 are coupled between scan lines 104b and data lines 106c in a matrix on the substrate 100. Referring to FIG. 2, each OLED 180 includes an anode electrode 108a, a cathode electrode 111, and an organic thin layer 110 formed between the anode electrode 108a and the cathode electrode 111. The organic thin layer 110 includes a structure in which a hole transport layer, an organic light emitting layer, and an electron transport layer are laminated with each other, and a hole injection layer and an electron injection layer may also be included.

[0015] In a passive matrix type, the OLEDs 180 having the above structure are coupled between the scan lines 104b and the data lines 106c in a matrix.

[0016] In an active matrix type, the OLEDs 180 are coupled between the scan lines 104b and the data lines 106c in the matrix. Here, the TFTs for controlling the operations of the OLEDs 180 and capacitors for maintaining signals are further included.

Each TFT includes a source, a drain, and a gate. In FIG. 2, a semiconductor layer 102 provides source and drain regions and a channel region. Source and drain electrodes 106a and 106b are coupled to the source and drain regions, and a gate electrode 104a insulated from the semiconductor layer 102 by a gate insulating layer 103 is formed on the channel region.

[0017] In the non-pixel region 160 shown in FIG. 1, the scan lines 104b and the data lines 106c are extended from the scan lines 104b and the data lines 106c of the pixel region 140, power source supply lines 106d and 106e are disposed for operating the OLEDs 180, and a scan driver 220 and a data driver 240 are disposed for processing signals supplied from an external source through a pad 120 to supply the processed signals to the

scan lines 104b and the data lines 106c are formed on the substrate 100.

[0018] The scan driver 220 and the data driver 240 include a circuit for converting signals supplied from the external source through the pad 120 into scan signals and data signals to selectively drive the pixels. The scan driver 220 and the data driver 240 can be formed in a process of manufacturing the OLEDs or can be manufactured as an additional integrated circuit chip to be mounted on the substrate 100. In FIG. 1, only the scan driver 220 and the data driver 240 are illustrated. However, a driving circuit unit such as an emission driver and a DC demultiplexer can be further included in accordance with a driving type, or the structure of a circuit and the positions of the scan driver 220 and the data driver 240 can be changed.

[0019] In addition, a guard ring 106f is formed at the edge (or edge portion) of the substrate 100 (and in the non-pixel region 160) to surround the driving circuit (or the driving circuit unit). A shielding layer 108c is formed in the non-pixel region 160 and on the driving circuit, and is insulated from the driving circuit by an insulating layer. Here, the shielding layer 108c can be coupled to an electrical ground or earth, such as a ground power source (for example, ELVSS) through the power source supply line 106d or 106e.

[0020] Referring to FIG. 3A, in one embodiment, a sealing substrate 400 is provided on the substrate 100 (where the OLEDs 180 are formed to face the sealing substrate 400), and the pixel region 140 is sealed up by a sealing material 300 interposed between the substrate 100 and the sealing substrate 400. Referring to FIG. 3B, in another embodiment, a sealing layer 420 having a multilayer structure of an organic layer 420a and an inorganic layer 420b is formed on the substrate 100.

[0021] A film-shaped flexible printed circuit (FPC) is electrically coupled to the pad 120 of the organic light emitting display having the above structure, and signals, such as power source voltages ELVDD and ELVSS and data, are input from the external source through the FPC. When the signals are input through the pad 120 to the power source supply lines 106d and 106e, the scan driver 220, and the data driver 240, the scan driver 220 and the data driver 240 supply scan signals and data signals to the scan lines 104b and the data lines 106c. Therefore, the OLEDs 180 of the pixels selected by the scan signals emit light components corresponding to the data signals. In the organic light emitting display according to an embodiment of the present invention, the non-pixel region 160 in which the driving circuit unit such as the scan driver 220, the data driver 240, the emission driver, and the DC demultiplexer formed of the TFTs is covered with the shielding layer 108c. Since the shielding layer 108c is coupled to the ground power source through the power source supply line 106d or 106e, it is possible to effectively protect the driving circuit unit against the ESD received through the peripheral part.

[0022] FIG. 4 is a sectional view schematically illus-

trating an organic light emitting display according to a first embodiment of the present invention and is a sectional view taken along the I1-I2 of FIG. 1.

[0023] A buffer layer 101 is formed on the substrate 100 in both the pixel region 140 and the non-pixel region 160. A semiconductor layer 102 that provides an active layer is formed on the buffer layer 101. The semiconductor layer 102 formed in the pixel region 140 provides the active layer of a TFT for driving the OLED 180, and the semiconductor layer 102 formed in the non-pixel region 160 provides the active layer of a TFT that constitutes the driving circuit unit.

[0024] The gate insulating layer 103 is formed in the pixel region 140 and the non-pixel region 160 and on the semiconductor layer 102, and the gate electrode 104a is formed on the gate insulating layer 103 on the semiconductor layer 102. Here, the scan line 104b coupled to the gate electrode 104a is formed in the pixel region 140, and the scan line 104b (extended from the scan line 104b of the pixel region 140) and the pad 120 for receiving signals from the external source are formed in the non-pixel region 160.

[0025] An interlayer insulating layer 105 is formed in the pixel region 140 and on the gate electrode 104a, and is also formed in the non-pixel region 160. Contact holes are formed in the interlayer insulating layer 105 and the gate insulating layer 103 to expose parts (or predetermined parts) of the semiconductor layer 102. The source and drain electrodes 106 and 106b are formed to be coupled to the semiconductor layer 102 through the contact holes. Here, the data line 106c coupled to the source and drain electrodes 106a and 106b is formed in the pixel region 140. The data line 106c extended from the data line 106c of the pixel region 140, the power source supply lines 106d and 106e, the guard ring 106f, and the pad 120 for receiving signals from the outside are all formed in the non-pixel region 160.

[0026] A protecting layer 107a and a planarizing layer 107b are formed in the pixel region 140 and the non-pixel region 160. A via hole is formed in the planarizing layer 107b and the protecting layer 107a of the pixel region 140 to expose a part (or a predetermined part) of the source or drain electrode 106a or 106b. Also, via holes are formed in the planarizing layer 107b and the protecting layer 107a of the non-pixel region 160 so that a part (or a predetermined part) of the power source supply line 106d or 106e and a part (or a predetermined part) of the guard ring 106f are exposed. Then, the anode electrode 108a coupled to the source or drain electrode 106a or 106b through via hole in the pixel region 140 is formed in the pixel region 140, and the shielding layer 108c is formed in the non-pixel region 160. Here, the shielding layer 108c is formed in the non-pixel region 160 and on the driving circuit unit to be coupled to the power source supply line 106d or 106e and the guard ring 106f through the via holes in the non-pixel region 160. In FIG. 4, a pattern 108b coupled to the power source supply line 106e increases the surface area of the power source

supply line 106e so that electric resistance is reduced and can be formed together with the anode electrode 108a.

[0027] A pixel defining layer 109 is formed in the pixel region 140, and an opening is formed in the pixel defining layer 109 to expose a partial region (emission region) of the anode electrode 108a. The organic thin layer 110 is formed on the exposed anode electrode 109a, and the cathode electrode 111 is formed in the pixel region 140 and on the organic thin layer 110 to be coupled to the power source supply line 106d or 106e.

[0028] FIG. 5 is a sectional view schematically illustrating an organic light emitting display according to a second embodiment of the present invention and is a sectional view taken along the line I1-I2 of FIG. 1.

[0029] The organic light emitting display according to the second embodiment of the present invention has substantially the same structure as the organic light emitting display according to the first embodiment. However, the shielding layer 108c of the non-pixel region 160 is covered with a protecting layer 109 formed of an organic layer.

[0030] As described in the first embodiment, when the shielding layer 108c is formed on the planarizing layer 107b formed of acryl, the attachment state between the planarizing layer 107b and the shielding layer 108c may deteriorate due to the weak layer structure of acryl. Therefore, the shielding layer 108c is covered with the protecting layer 109 so that the attachment state between the planarizing layer 107b and the shielding layer 108c can be maintained so that the shielding layer 108c can be protected.

[0031] Therefore, according to the first embodiment, the pixel defining layer 109 is formed only in the pixel region 140. However, according to the second embodiment, the pixel defining layer 109 is formed on the pixel region 140 and the non-pixel region 160 as the protecting layer 109. In addition, an opening is formed in the pixel defining layer 109 of the pixel region 140 to expose a partial region (emission region) of the anode electrode 108a, and an opening is formed in the pixel defining layer 109 of the non-pixel region 160 to expose a part (or a predetermined part) of the power source supply line 106d or 106e. The organic thin layer 110 is formed on the exposed anode electrode 109a, and the cathode electrode 111 coupled to the power source supply line 106d or 106e through the opening is formed in the pixel region 140 and on the organic thin layer 110.

[0032] FIG. 6 is a sectional view schematically illustrating an organic light emitting display according to a third embodiment of the present invention and is taken along the line I1-I2 of FIG. 1.

The organic light emitting display according to the third embodiment of the present invention has substantially the same structure as the structure of the organic light emitting display according to the first embodiment. However, the cathode electrode 111 is extended to the top of the shielding layer 108c (or is extended to be on the

shielding layer 108c). Here, the pixel defining layer 109 can reside between the cathode electrode 111 and the shielding layer 108c in the remaining part excluding the contacting part between the cathode electrode 111 and the shielding layer 108c. The cathode electrode 111 is extended to the top of the shielding layer 108c (or is extended to be on the shielding layer 108c) to form an electric contact in the overlapping part between the cathode electrode 111 and the shielding layer 108c to reduce the size of the contacting part (opening) between the cathode electrode 111 and the power source supply line 106d or 106e. As a result, a dead space of the substrate 100 can be effectively reduced.

[0033] A method of manufacturing an organic light emitting display according to an embodiment of the present invention having the above structure will be described in more detail with reference to FIGs. 7A to 7D.

[0034] Referring to FIG. 7A, first, the substrate 100 in which the pixel region 140 and the non-pixel region 160 are defined is provided. The buffer layer 101 is formed on the substrate 100 in both the pixel region 140 and the non-pixel region 160 of SiO₂ and SiNx, and the semiconductor layer 102 is formed on the buffer layer 101. The semiconductor layer 102 is an active layer for providing the source and drain regions and the channel region of the TFT. The semiconductor layer 102 formed on the pixel region 140 provides the active layer of the TFT for driving the OLED 180, and the semiconductor layer 102 formed in the non-pixel region 160 provides the active layer of the TFT that constitutes the driving circuit (or the driving circuit unit). Therefore, the number of semiconductor layers 102 formed in the pixel region 140 and the non-pixel region 160 corresponds to the number of TFTs required for constituting the pixel circuit and the driving circuit. Referring to FIG. 7B, the gate insulating layer 103 is formed in the pixel region 140 and the non-pixel region 160 and on the semiconductor layer 102, and the gate electrode 104a is formed on the gate insulating layer 103 on the semiconductor layer 102. Here, the scan line 104b coupled to the gate electrode 104a is formed in the pixel region 140, and the scan line 104b extended from the scan line 104b of the pixel region 140 and the pad for receiving signals from the outside are formed in the non-pixel region 160. The gate electrode 104a, the scan line 104b, and the pad 120 are formed of metals (such as Mo, W, Ti, and Al), an alloy of the above metals, or a laminated structure (e.g., a laminated structure of the above metals).

[0035] The interlayer insulating layer 105 is formed in the pixel region 140 and the non-pixel region 160 and on the gate electrode 104a. The interlayer insulating layer 105 and the gate insulating layer 103 are patterned to form the contact holes so that parts (or predetermined parts) of the semiconductor layer 102 are exposed and the source and drain electrodes 106a and 106b are formed to be coupled to the semiconductor layer 102 through the contact holes. Here, in the pixel region 140, the data line 106c coupled to the source and drain elec-

trodes 106a and 106b is formed. Also, in the non-pixel region 160, the data line 106c extended from the data line 106c of the pixel region 140, the power source supply lines 106d and 106e, the guard ring 106f, and the pad 120 for receiving the signals from the external source are formed. The source and drain electrodes 106a and 106b, the data line 106c, the power source supply lines 106d and 106e, the guard ring 106f, and the pad 120 are formed of the metals (such as Mo, W, Ti, and Al), an alloy of the above metals, or a laminated structure (e.g., a laminated structure of the above metals). Referring to FIG. 7C, after the protecting layer 107a is formed in the pixel region 140 and the non-pixel region 160 of SiN, the planarizing layer 107b is formed on the protecting layer 107a of acryl to planarize the surface. The planarizing layer 107b and the protecting layer 107a are patterned to form a via hole in the pixel region 140 to expose a part (or a predetermined part) of the source or drain electrode 106a or 106b. Also, the planarizing layer 107b and the protecting layer 107a are patterned to form via holes in the non-pixel region 160 so that a part (or a predetermined part) of the power source supply line 106d or 106e and a part (or a predetermined part) of the guard ring 106f are exposed.

[0036] According to the present embodiment, the protecting layer 107a and the planarizing layer 107b are sequentially formed, and then the planarizing layer 107b and the protecting layer 107a are patterned. However, the present invention is not thereby limited. That is, for example, after the protecting layer 107a is formed and patterned, the planarizing layer 107b can then be formed and patterned.

[0037] Then, the anode electrode 108a coupled to the source or drain electrode 106a or 106b through the via hole in the pixel region 140 is formed in the pixel region 140, and the shielding layer 108c is formed in the non-pixel region 160. The shielding layer 108c is formed in the non-pixel region 160 and on the driving circuit unit to be coupled to the power source supply line 106d or 106e and the guard ring 106f through the via holes in the non-pixel region 160.

[0038] Here, the peripheral circuit unit and the shielding layer 108c are electrically insulated from each other by an insulating layer formed of the protecting layer 107a and the planarizing layer 107b. Here, in order to minimize (or reduce) parasitic capacitance between the peripheral circuit unit and the shielding layer 108c, the protecting layer 107a and the planarizing layer 107b are formed to be relatively thick.

[0039] In addition, according to the present embodiment, in order not to add additional process and mask, the shielding layer 108c is formed in a process of forming the anode electrode 108a. However, the present invention is not thereby limited, and the anode electrode 108a and the shielding layer 108c can be formed by the separate (or respective) processes. In one embodiment, when the anode electrode 108a and the shielding layer 108c are formed in the same process with a same anode

electrode material, the anode electrode 108a and the shielding layer 108c are electrically separated from each other.

[0040] In the case of a front emission type, the anode electrode material can be formed of an opaque inorganic material or an alloy of inorganic materials. In the case of a rear emission method, the anode electrode material can be formed of a transparent inorganic material or an alloy of inorganic materials. The opaque inorganic material or the alloy of the inorganic materials can be ACX (an Al alloy), Ag, or Au. The transparent inorganic material or the alloy of the inorganic materials can be ITO, IZO, or ITZO.

[0041] Referring to FIG. 7D, the pixel defining layer 109 is formed in the pixel region 140, and the pixel defining layer 109 is patterned to have an opening so that a partial region (emission region) of the anode electrode 108a is exposed. Then, the organic thin layer 110 is formed on the anode electrode 109a exposed through the opening and the cathode electrode 111 is formed in the pixel region 140 and on the organic thin layer 110 to be coupled to the power source supply line 106d or 106e (refer to FIG. 4).

[0042] According to another embodiment, the pixel defining layer 109 is formed in both the pixel region 140 and the non-pixel region 160, and the pixel defining layer 109 is patterned to form an opening in the pixel region 140 so that a partial region (emission region) of the anode electrode 108a is exposed. In addition, the pixel defining layer 109 is also patterned to form an opening in the non-pixel region 160 so that a part (or a predetermined part) of the power source supply line 106d or 106e is exposed. Then, the organic thin layer 110 is formed on the anode electrode 108a exposed through the opening, and the cathode electrode 111 coupled to the power source supply line 106d or 106e through the opening is formed in the pixel region 140 and on the organic thin layer 110 (refer to FIG. 5).

[0043] According to another embodiment, in a process of forming the cathode electrode 111, the cathode electrode 111 is extended to the top of the shielding layer 108c (or is extended to be on the shielding layer 108c) and is electrically coupled to each other in the overlapping part of the cathode electrode 111 and the shielding layer 108c (refer to FIG. 6).

[0044] Referring to FIG. 3A, a sealing substrate 400 is provided on the substrate 100 (where the OLEDs 180 are formed to face the substrate 100), and the substrate 100 and the sealing substrate 400 are attached to each other by the sealing material 300 formed at the edge portions of the substrate 100 and the sealing substrate 400 to seal the pixel region 140. In another embodiment, referring to FIG. 3B, the sealing substrate 420 formed of a multilayer structure of the organic layer 420a and the inorganic layer 420b is formed on the substrate 100 to seal the pixel region 140. As described above, in an embodiment of the present invention, the shielding layer coupled to the ground power source is formed in the non-

pixel region and on the driving circuit so that the driving circuit is effectively protected against the ESD.

[0045] According to the conventional organic light emitting display, the driving circuit is damaged by the ESD of 2kV. However, according to the organic light emitting display of an embodiment of the present invention, the driving circuit can be protected against the ESD of about 15kV.

[0046] In addition, according to an embodiment of the present invention, the shielding layer is formed in the process of forming the anode electrode so that it is possible to prevent (or protect) the organic light emitting display from being damaged without adding an additional masking process, an additional mask, an additional protecting element, and/or an additional ESD protecting circuit to thereby reduce manufacturing cost.

Claims

1. An organic light emitting display comprising:

a substrate having a pixel region (140) and a non-pixel region (160);
an organic light emitting diode OLED (180) in the pixel region and including a first electrode (108a), an organic thin layer (110), and a second electrode (111);
a driving circuit (220, 240) in the non-pixel region for driving the OLED;
a shielding layer (108c) in the non-pixel region (160) and on the driving circuit (220, 240);
an insulating layer (107b) interposed between the driving circuit (220, 240) and the shielding layer (108c);
a guard ring (106f) at an edge portion of the non-pixel region to surround the driving circuit and electrically coupled to the shielding layer (108c); and
a power source supply line (106e),
wherein the shielding layer (108c) is electrically grounded through the power source supply line (106e) and covers completely the driving circuit (220, 240) between the power source supply line and the guard ring (106f).

2. The organic light emitting display as claimed in claim 1, further comprising a protecting layer (107a) on the shielding layer, wherein the protecting layer may comprise an organic material.

3. The organic light emitting display as claimed in claim 1 or 2, wherein the shielding layer and the first electrode both comprise the same electrode material.

4. The organic light emitting display as claimed in any one of the preceding claims, wherein the second electrode is electrically grounded through the power

source supply line.

5. The organic light emitting display as claimed in any one of the preceding claims, wherein the second electrode extends onto the shielding layer.
6. The organic light emitting display as claimed in any one of the preceding claims, wherein the driving circuit comprises a scan driver (220) and a data driver (240).
7. The organic light emitting display as claimed in any one of the preceding claims, further comprising a sealing substrate on and attached to the substrate by a sealing material to seal the pixel region or a sealing layer having a multilayer structure of an organic layer and an inorganic layer on the substrate to seal the pixel region.

8. A method of manufacturing an organic light emitting display according to any one of the preceding claims, the method comprising:

providing a substrate having a pixel region and a non-pixel region;
forming a first thin film transistor TFT comprising a gate electrode and source and drain electrodes on the substrate in the pixel region and a second TFT on the substrate in the non-pixel region;
forming an insulating layer in the pixel region and the non-pixel region and on the first TFT and the second TFT;
forming a via hole in the insulating layer to expose the source or drain electrode of the first TFT in the pixel region;
forming a first electrode coupled to the source or drain electrode through the via hole in the pixel region;
forming a shielding layer in the non-pixel region;
forming a pixel defining layer in the pixel region;
forming an opening in the pixel defining layer so that a part of the first electrode is exposed;
forming an organic thin layer on the first electrode in the opening; and
forming a second electrode in the pixel region.

9. The method as claimed in claim 8, wherein forming the first TFT comprises forming the source and drain electrodes of the first TFT in the pixel region and forming the power source supply line and the guard ring on the substrate in the non-pixel region.
10. The method as claimed in claim 9, wherein forming the via hole in the insulating layer comprises forming a first via hole in the insulating layer to expose the source or drain electrode of first TFT in the pixel region and forming second via holes in the insulating

layer to expose the power source supply line and the guard ring in the non-pixel region.

11. The method as claimed in claim 9 or 10, wherein the pixel defining layer is formed in the pixel region and the non-pixel region, and wherein openings are formed in the pixel defining layer so that the first electrode and the power source supply line are exposed.
12. The method as claimed in claim 11, wherein the second electrode is coupled to the exposed power source supply line.
13. The method as claimed in any one of claims 8 to 12, wherein the second electrode is formed to be extended onto the shielding layer.
14. The method as claimed in any one of claims 8 to 13, further comprising providing a sealing substrate on the substrate and attaching the sealing substrate to the substrate by utilizing a sealing material to seal the pixel region, or forming a sealing layer having a multilayer structure of an organic layer and an inorganic layer on the substrate to seal the pixel region.

Patentansprüche

1. Organische Leuchtanzeige, umfassend:

eine Trägerschicht mit einer Pixelregion (140) und einer Nicht-Pixelregion (160);
eine organische Leuchtdiode OLED (180) in der Pixelregion und eine erste Elektrode (108a), eine organische Dünnschicht (110) und eine zweite Elektrode (111) enthaltend;
eine Ansteuerschaltung (220, 240) in der Nicht-Pixelregion zum Ansteuern der OLED;
eine Abschirmschicht (108c) in der Nicht-Pixelregion (160) und auf der Ansteuerschaltung (220, 240);
eine Isolierschicht (107b), die zwischen der Ansteuerschaltung (220, 240) und der Abschirmschicht (108c) eingesetzt ist;
einen Schutzring (106f) an einem Randabschnitt der Nicht-Pixelregion, der die Ansteuerschaltung umgibt und elektrisch an die Abschirmschicht (108c) gekoppelt ist; und
eine Stromquellenversorgungsleitung (106e), wobei die Abschirmschicht (108c) durch die Stromquellenversorgungsleitung (106e) elektrisch geerdet ist und die Ansteuerschaltung (220, 240) vollständig zwischen der Stromquellenversorgungsleitung und dem Schutzring (106f) bedeckt.

2. Organische Leuchtanzeige nach Anspruch 1, des

Weiteren umfassend eine Schutzschicht (107a) auf der Abschirmschicht, wobei die Schutzschicht ein organisches Material umfassen kann.

3. Organische Leuchtanzeige nach Anspruch 1 oder 2, wobei die Abschirmschicht und die erste Elektrode beide dasselbe Elektrodenmaterial umfassen. 5
4. Organische Leuchtanzeige nach einem der vorangehenden Ansprüche, wobei die zweite Elektrode durch die Stromquellenversorgungsleitung elektrisch geerdet ist. 10
5. Organische Leuchtanzeige nach einem der vorangehenden Ansprüche, wobei sich die zweite Elektrode in die Abschirmschicht erstreckt. 15
6. Organische Leuchtanzeige nach einem der vorangehenden Ansprüche, wobei die Ansteuerschaltung einen Abtastreiber (220) und einen Datentreiber (240) umfasst. 20
7. Organische Leuchtanzeige nach einem der vorangehenden Ansprüche, des Weiteren umfassend eine Dichtungsträgerschicht, die sich auf der Trägerschicht befindet und an dieser durch ein Dichtungsmaterial befestigt ist, um die Pixelregion abzudichten, oder eine Dichtungsschicht mit einer mehrschichtigen Struktur aus einer organischen Schicht und einer anorganischen Schicht auf der Trägerschicht, um die Pixelregion abzudichten. 25 30
8. Verfahren zur Herstellung einer organischen Leuchtanzeige nach einem der vorangehenden Ansprüche, wobei das Verfahren umfasst: 35
 - Bereitstellen einer Trägerschicht mit einer Pixelregion und einer Nicht-Pixelregion;
 - Bilden eines ersten Dünnschichttransistors TFT, umfassend eine Gate-Elektrode und Source- und Drain-Elektroden, auf der Trägerschicht in der Pixelregion und eines zweiten TFT auf der Trägerschicht in der Nicht-Pixelregion;
 - Bilden einer Isolierschicht in der Pixelregion und der Nicht-Pixelregion und auf dem ersten TFT und dem zweiten TFT;
 - Bilden eines Durchkontaktierungslochs in der Isolierschicht, um die Source- oder Drain-Elektrode des ersten TFT in der Pixelregion freizulegen;
 - Bilden einer ersten Elektrode, die an die Source- oder Drain-Elektrode durch das erste Durchkontaktierungsloch in der Pixelregion gekoppelt ist;
 - Bilden einer Abschirmschicht in der zweiten Nicht-Pixelregion;
 - Bilden einer Pixeldefinierungsschicht in der Pixelregion;
 - Bilden einer Öffnung in der Pixeldefinierungs-

schicht, so dass ein Teil der ersten Elektrode freiliegt;
 Bilden einer organischen Dünnschicht auf der ersten Elektrode in der Öffnung; und
 Bilden einer zweiten Elektrode in der Pixelregion.

9. Verfahren nach Anspruch 8, wobei das Bilden des ersten TFT das Bilden der Source- und Drain-Elektroden des ersten TFT in der Pixelregion und das Bilden einer Stromquellenversorgungsleitung und des Schutzrings auf der Trägerschicht in der Nicht-Pixelregion umfasst.
10. Verfahren nach Anspruch 9, wobei das Bilden des Durchkontaktierungslochs in der Isolierschicht das Bilden eines ersten Durchkontaktierungslochs in der Isolierschicht zum Freilegen der Source- oder Drain-Elektrode des ersten TFT in der Pixelregion und das Bilden zweiter Durchkontaktierungslöcher zum Freilegen der Stromquellenversorgungsleitung und des Schutzrings in der Nicht-Pixelregion umfasst.
11. Verfahren nach Anspruch 9 oder 10, wobei die Pixeldefinierungsschicht in der Pixelregion und der Nicht-Pixelregion gebildet ist und wobei Öffnungen in der Pixeldefinierungsschicht so gebildet sind, dass die erste Elektrode und die Stromquellenversorgungsleitung freiliegen.
12. Verfahren nach Anspruch 11, wobei die zweite Elektrode an die freiliegende Stromquellenversorgungsleitung gekoppelt ist.
13. Verfahren nach einem der Ansprüche 8 bis 12, wobei die zweite Elektrode so gebildet ist, dass sie auf die Abschirmschicht verlängert ist.
14. Verfahren nach einem der Ansprüche 8 bis 13, des Weiteren umfassend ein Bereitstellen einer Dichtungsträgerschicht auf der Trägerschicht und Befestigen der Dichtungsträgerschicht an der Trägerschicht unter Verwendung eines Dichtungsmaterials, um die Pixelregion abzudichten, oder ein Bilden einer Dichtungsschicht mit einer mehrschichtigen Struktur aus einer organischen Schicht und einer anorganischen Schicht auf der Trägerschicht, um die Pixelregion abzudichten.

Revendications

1. Dispositif d'affichage électroluminescent organique comprenant :
 - un substrat présentant une région de pixel (140) et une région sans pixel (160) ;
 - une diode électroluminescente organique

- OLED (180) dans la région de pixel et comportant une première électrode (108a), une couche mince organique (110), et une deuxième électrode (111) ;
 un circuit d'attaque (220, 240) dans la région sans pixel pour attaquer l'OLED ;
 une couche de blindage (108c) dans la région sans pixel (160) et sur le circuit d'attaque (220, 240) ;
 une couche isolante (107b) interposée entre le circuit d'attaque (220, 240) et la couche de blindage (108c) ;
 un anneau de garde (106f) au niveau d'une partie de bord de la région sans pixel pour entourer le circuit d'attaque et couplé électriquement à la couche de protection (108c) ; et
 une ligne d'alimentation en énergie (106e), la couche de protection (108c) étant électriquement mise à la masse par l'intermédiaire de la ligne d'alimentation en énergie (106e) et couvrant complètement le circuit d'attaque (220, 240) entre la ligne d'alimentation en énergie (106f) et l'anneau de garde.
2. Dispositif d'affichage électroluminescent organique tel que revendiqué dans la revendication 1, comprenant en outre une couche de protection (107a) sur la couche de blindage, dans lequel la couche de protection peut comprendre un matériau organique.
3. Dispositif d'affichage électroluminescent organique tel que revendiqué dans la revendication 1 ou 2, dans lequel la couche de blindage et la première électrode comprennent toutes deux le même matériau d'électrode.
4. Dispositif d'affichage électroluminescent organique tel que revendiqué dans l'une quelconque des revendications précédentes, dans lequel la deuxième électrode est électriquement mise à la masse par l'intermédiaire de la ligne d'alimentation en énergie.
5. Dispositif d'affichage électroluminescent organique tel que revendiqué dans l'une quelconque des revendications précédentes, dans lequel la deuxième électrode s'étend sur la couche de blindage.
6. Dispositif d'affichage électroluminescent organique tel que revendiqué dans l'une quelconque des revendications précédentes, dans lequel le circuit d'attaque comprend un pilote de balayage (220) et un pilote de données (240).
7. Dispositif d'affichage électroluminescent organique tel que revendiqué dans l'une quelconque des revendications précédentes, comprenant en outre un substrat d'étanchéité sur le substrat et fixé à celui-ci par un matériau d'étanchéité pour assurer l'étanchéité de la région de pixel ou une couche d'étanchéité présentant une structure multicouche d'une couche organique et d'une couche inorganique sur le substrat pour assurer l'étanchéité de la région de pixel.
8. Procédé de fabrication d'un dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications précédentes, le procédé comprenant le fait :
- de fournir un substrat présentant une région de pixel et une région sans pixel ;
 de former un premier transistor à couches minces TFT comprenant une électrode de grille et des électrodes de source et de drain sur le substrat dans la région de pixel et un deuxième transistor TFT sur le substrat dans la région sans pixel ;
 de former une couche isolante dans la région de pixel et dans la région sans pixel et sur le premier transistor TFT et le deuxième transistor TFT ;
 de former un trou d'interconnexion dans la couche isolante pour exposer l'électrode de source ou de drain du premier transistor TFT dans la région de pixel ;
 de former une première électrode couplée à l'électrode de source ou de drain à travers le trou d'interconnexion dans la région de pixel ;
 de former une couche de blindage dans la région sans pixel ;
 de former une couche de définition de pixel dans la région de pixel ;
 de former une ouverture dans la couche de définition de pixel de sorte qu'une partie de la première électrode soit exposée ;
 de former une couche mince organique sur la première électrode dans l'ouverture ; et
 de former une deuxième électrode dans la région de pixel.
9. Procédé tel que revendiqué dans la revendication 8, dans lequel la formation du premier transistor TFT comprend le fait de former des électrodes de source et de drain du premier transistor TFT dans la région de pixel et de former la ligne d'alimentation en énergie et l'anneau de garde sur le substrat dans la région sans pixel.
10. Procédé tel que revendiqué dans la revendication 9, dans lequel la formation du trou d'interconnexion dans la couche isolante comprend le fait de former un premier trou d'interconnexion dans la couche isolante pour exposer l'électrode de source ou de drain du premier transistor TFT dans la région de pixel et de former un deuxième trou d'interconnexion dans la couche isolante pour exposer la ligne d'alimenta-

tion en énergie et l'anneau de garde dans la région sans pixel.

11. Procédé tel que revendiqué dans la revendication 9 ou 10, 5
 dans lequel la couche de définition de pixel est formée dans la région de pixel et dans la région sans pixel, et
 dans lequel des ouvertures sont formées dans la couche de définition de pixel de sorte que la première électrode et la ligne d'alimentation en énergie soient exposées. 10
12. Procédé tel que revendiqué dans la revendication 11, dans lequel la deuxième électrode est couplée à la ligne d'alimentation en énergie exposée. 15
13. Procédé tel que revendiqué dans l'une quelconque des revendications 8 à 12, dans lequel la deuxième électrode est formée de manière à s'étendre sur la couche de blindage. 20
14. Procédé tel que revendiqué dans l'une quelconque des revendications 8 à 13, comprenant en outre le fait de fournir un substrat d'étanchéité sur le substrat et de fixer le substrat d'étanchéité au substrat en utilisant un matériau d'étanchéité pour assurer l'étanchéité de la région de pixel, ou de former une couche d'étanchéité présentant une structure multicouche d'une couche organique et d'une couche inorganique sur le substrat pour assurer l'étanchéité de la région de pixel. 25 30

35

40

45

50

55

FIG. 1




FIG. 2




FIG. 3A




FIG. 3B




FIG. 4




FIG. 5




FIG. 6




FIG. 7A




FIG. 7B




FIG. 7C





FIG. 7D



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2007157470 A [0007]
- US 2003094615 A [0007]
- US 5760855 A [0007]

专利名称(译)	有机发光显示器及其制造方法		
公开(公告)号	EP2019432B1	公开(公告)日	2014-09-17
申请号	EP2008158487	申请日	2008-06-18
[标]申请(专利权)人(译)	三星斯笛爱股份有限公司		
申请(专利权)人(译)	三星SDI CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KWAK WON KYU C O LEGAL & IP TEAM SAMSUNG SDI CO LTD CHUN HAE JIN C O LEGAL & IP TEAM SAMSUNG SDI CO LTD		
发明人	KWAK, WON-KYU C/O LEGAL & IP TEAM SAMSUNG SDI CO., LTD CHUN, HAE-JIN C/O LEGAL & IP TEAM SAMSUNG SDI CO., LTD		
IPC分类号	H01L27/32		
CPC分类号	H01L27/3272 H01L27/3276		
优先权	1020070073385 2007-07-23 KR		
其他公开文献	EP2019432A3 EP2019432A2		
外部链接	Espacenet		

摘要(译)

有机发光显示器及其制造方法。发光显示器包括具有像素区域 (140) 和非像素区域 (160) 的基板;像素区域中的有机发光二极管 (OLED) (180) , 包括第一电极 (108a) , 有机薄层 (110) 和第二电极 (111) ;非像素区域中的驱动电路单元 (220,240) , 用于驱动OLED;在非像素区域和驱动电路上的屏蔽层 (108c) , 屏蔽层电接地;绝缘层介于驱动电路和屏蔽层之间。屏蔽层有效地保护非像素区域中的驱动电路形成静电放电 (ESD) 。而且, 发光显示器可以包括在非像素区域的边缘部分处的保护环 (106f) 并且电耦合到屏蔽层以进一步保护驱动电路免受ESD。

