



(11) **EP 3 525 253 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
14.08.2019 Bulletin 2019/33

(51) Int Cl.:
H01L 51/00 (2006.01)

(21) Application number: **19156553.0**

(22) Date of filing: **11.02.2019**

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**
Designated Extension States:
BA ME
Designated Validation States:
KH MA MD TN

(72) Inventors:
• **SEO, Jihyun**
Gyeonggi-do (KR)
• **KIM, Mikyung**
Gyeonggi-do (KR)
• **YANG, Seunggak**
Gyeonggi-do (KR)
• **LEE, Kwanhee**
Gyeonggi-do (KR)

(30) Priority: **13.02.2018 KR 20180018060**
28.09.2018 KR 20180116586

(74) Representative: **Shearman, James Ward
Marks & Clerk LLP**
15 Fetter Lane
London EC4A 1BW (GB)


(71) Applicant: **Samsung Display Co., Ltd**
Gyeonggi-do (KR)

(54) **ORGANIC LIGHT-EMITTING DEVICE AND DISPLAY APPARATUS INCLUDING ORGANIC LIGHT-EMITTING DEVICE**

(57) An organic light-emitting device and a display apparatus including the organic light-emitting device includes a light emitting layer having one or more host materials having unexpectedly low driving voltage, high efficiency and a long life span.

FIG. 1

10



EP 3 525 253 A1

Description

BACKGROUND

5 FIELD

[0001] Embodiments of the invention relate generally to an organic light-emitting device for use in display apparatus and, more particularly, to the light emission layer of the organic light-emitting device.

10 Discussion of the Background

[0002] Organic light-emitting devices (OLEDs) are self-emission devices that, as compared with conventional devices, have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of brightness, driving voltage, and response speed.

15 **[0003]** OLEDs may include a first electrode on a substrate, and may include a hole transport region, an emission layer, an electron transport region, and a second electrode sequentially stacked on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region. Electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, may recombine in the emission layer to produce excitons. These excitons transit from an excited state
20 to a ground state to thereby generate light.

[0004] The above information disclosed in this Background section is only for understanding of the background of the inventive concepts, and, therefore, it may contain information that does not constitute prior art.

SUMMARY

25 **[0005]** Emission layers for organic light-emitting devices constructed according to embodiments of the invention have one or more host materials providing surprisingly low-driving voltage, high efficiency, and a long lifespan. In particular, emission layers having one or more host materials constructed according to the principles and embodiments of the invention have life spans unexpectedly higher than those provided with conventional host materials.

30 **[0006]** One or more embodiments of the invention include an organic light-emitting device and a display apparatus including the organic light emitting device.

[0007] Additional features of the inventive concepts will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the inventive concepts.

35 **[0008]** According to one or more embodiments, an organic light-emitting device includes a first electrode; a second electrode; and an emission layer disposed between the first electrode and the second electrode, wherein the emission layer includes a host material and wherein the organic light-emitting device satisfies Equation 1:

$$F_{CB} > 2.8 \qquad \text{Equation 1}$$

40 **[0009]** wherein F_{CB} is defined by Equation 2:


$$F_{CB} = V_{EOD} \text{ (at } 10 \text{ mA/cm}^2\text{)} / V_{HOD} \text{ (at } 10 \text{ mA/cm}^2\text{)} \qquad \text{Equation 2}$$

45 **[0010]** V_{HOD} (at 10 mA/cm²) is a driving voltage (volts, V) at a current density of 10 mA/cm² of a hole-only device having a structure of ITO (1,500 Angstroms (Å))/ HT211 :NDP9 (1 percent by weight (wt%)) (100 Å)/ HT211 (1,500 Å)/ the host material (400 Å)/ L101 (100 Å)/ Yb (13 Å)/ Mg:Ag (10 wt%)(600 Å), and

50 V_{EOD} (at 10 mA/cm²) is a driving voltage (V) at a current density of 10 mA/cm² of an electron-only device having a structure of ITO (1,500 Å)/ LiQ (100 Å)/ the host material (400 Å)/ TPBi:LiQ (50 wt%) (360 Å)/ Yb (13 Å)/ Mg:Ag (10 wt%) (600 Å):


55

5




HT211

10




NDP9



L101


15

20



TPBi

25



LiQ

[0011] According to one or more embodiments, a display apparatus includes a thin-film transistor including a source electrode, a drain electrode, and an active layer; and the organic light-emitting device, wherein the first electrode of the organic light-emitting device is electrically connected to the source electrode or the drain electrode of the thin-film transistor.


30

[0012] The host material may include at least one compound selected from a compound represented by Formula 1 and a compound represented by Formula 2:

35

<Formula 1>


40



45

<Formula 2>

50



wherein, in Formulae 1 and 2,

Ar_{10} is a C_1 - C_{60} heterocyclic group including at least one π electron-depleted nitrogen-containing ring,

55

L_{10} , L_{20} , L_{30} , and L_{40} are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted

divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a₁₀, a₂₀, a₃₀, and a₄₀ are each independently an integer from 0 to 5,

when a₁₀ is 2 or greater, at least two L₁₀(s) are identical to or different from each other,

when a₂₀ is 2 or greater, at least two L₂₀(s) are identical to or different from each other,

when a₃₀ is 2 or greater, at least two L₃₀(s) are identical to or different from each other,

when a₄₀ is 2 or greater, at least two L₄₀(s) are identical to or different from each other,

R₁₀, R₂₀, R₃₀, R₄₀, and R₅₀ are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl

group, a cyano group, a nitro group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted

C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀

alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ hetero-

cycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀

heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀

aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl

group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted

monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁)(Q₂)(Q₃), -N(Q₁)(Q₂), -B(Q₁)(Q₂),

-C(=O)(Q₁), -S(=O)₂(Q₁), and -P(=O)(Q₁)(Q₂),

b₁₀, b₂₀, b₃₀, b₄₀, and b₅₀ are each independently an integer from 1 to 10,

when b₁₀ is 2 or greater, at least two R₁₀(s) are identical to or different from each other,

when b₂₀ is 2 or greater, at least two R₂₀(s) are identical to or different from each other,

when b₃₀ is 2 or greater, at least two R₃₀(s) are identical to or different from each other,

when b₄₀ is 2 or greater, at least two R₄₀(s) are identical to or different from each other,

when b₅₀ is 2 or greater, at least two R₅₀(s) are identical to or different from each other,

c₄₀ is an integer from 1 to 4,

when c₄₀ is 2 or greater, at least two -[(L₄₀)_{a40}-(R₄₀)_{b40}](s) are identical to or different from each other, and

at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene

group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the sub-

stituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic

condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted

C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀

alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted

C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the

substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group,

the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic

condensed heteropolycyclic group is selected from:

deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁₁)(Q₁₂)(Q₁₃), -N(Q₁₁)(Q₁₂), -B(Q₁₁)(Q₁₂), -C(=O)(Q₁₁), -S(=O)₂(Q₁₁), and -P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;


a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from

deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀


heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, $-\text{Si}(\text{Q}_{21})(\text{Q}_{22})(\text{Q}_{23})$, $-\text{N}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{B}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{C}(=\text{O})(\text{Q}_{21})$, $-\text{S}(=\text{O})_2(\text{Q}_{21})$, and $-\text{P}(=\text{O})(\text{Q}_{21})(\text{Q}_{22})$; and
 $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$,

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , Q_{31} to Q_{33} , and Q_{41} to Q_{43} are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.


[0013] At least one selected from R_{10} , R_{20} , and R_{30} and at least one selected from R_{40} and R_{50} may each independently comprise a partial structure represented by one of Formulae 4-1 to 4-15:




4-1




4-2




4-3




4-4




4-5




4-6




4-7




4-8




4-9




4-10




4-11




4-12



4-13



4-14



4-15

wherein, in Formulae 4-1 to 4-15,

Y_{11} is selected from $\text{C}(\text{R}_1)(\text{R}_2)$, $\text{N}(\text{R}_1)$, O, and S,

Y_{12} is selected from $\text{C}(\text{R}_3)(\text{R}_4)$, $\text{N}(\text{R}_3)$, O, and S,


R_1 to R_4 are each independently selected from a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, and -I; a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a quinolinyl group, an


isoquinolinyl group, a quinoxaliny group, a quinazoliny group, a benzofuopyridiny group, a benzothienopyridiny group, a benzofuopyrimidiny group, and a benzothienopyrimidiny group; and
 a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridiny group, a pyrimidiny group, a quinoliny group, an
 5 isoquinolinyl group, a quinoxaliny group, a quinazoliny group, a benzofuopyridiny group, a benzothienopyridiny group, a benzofuopyrimidiny group, and a benzothienopyrimidiny group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a methoxy group, an ethoxy group, an n-propoxy group, an iso-propoxy group, an n-butoxy group, an iso-butoxy group, a sec-butoxy group, a tert-butoxy group, a
 10 phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridiny group, a pyrimidiny group, a quinoliny group, an isoquinolinyl group, a quinoxaliny group, a quinazoliny group, a benzofuopyridiny group, a benzothienopyridiny group, a benzofuopyrimidiny group, and a benzothienopyrimidiny group, and
 15 any carbon atom or any nitrogen atom in the partial structure represented by any one of Formulae 4-1 to 4-15 is a binding site to an adjacent atom.

[0014] The compound represented by Formula 1 may be a compound represented by Formula 3A, 3B, or 3C, and the compound represented by Formula 2 may be a compound represented by Formula 4:


<Formula 3A>




<Formula 3B>



<Formula 3C>



<Formula 4>



wherein, in Formulae 3A, 3B, 3C, and 4,

A₁₀, A₂₀, and A₄₀ are each independently selected from a benzene group, a naphthalene group, a fluorene group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, an indoline group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a dibenzofuran group, and a dibenzothiophene group,

Y₂₁ is selected from -O-, -S-, -N(R₂₁)-, -C(R₂₁)(R₂₂)-, and -Si(R₂₁)(R₂₂)-,

X₁₁, X₁₂, X₁₃, and X₁₄ are each independently N or C(R₁₃),

X₂₁, X₂₂, X₂₃, and X₂₄ are each independently N or C(R₂₄),

X₄₁, X₄₂, X₄₃, and X₄₄ are each independently N or C(R₄₂),

X₅₁, X₅₂, X₅₃, X₅₄, and X₅₅ are each independently N or C(R₅₁),

at least one selected from X₅₁, X₅₂, X₅₃, X₅₄, and X₅₅ is N,

L₁₁ is defined the same as L₁₀ described above,

L₂₁ is defined the same as L₂₀ described above,

L₄₁ is defined the same as L₄₀ described above,

a₁₁ is an integer from 0 to 5,

a₂₁ is an integer from 0 to 5,

a₄₁ is an integer from 0 to 5,

R₁₁, R₁₂, and R₁₃ are each defined the same as R₁₀ described above,

R₂₁, R₂₂, R₂₃, and R₂₄ are each defined the same as R₂₀ described above,

R₃₁ is defined the same as R₃₀ described above,

R₄₁ and R₄₂ are each defined the same as R₄₀ described above,

R₅₁ is defined the same as R₅₀ described above, and

b₁₂, b₂₃, and b₄₁ are each independently an integer from 1 to 8.

[0015] At least some of the above and other features of the invention are set out in the claims.

[0016] It is to be understood that both the foregoing general description and the following detailed description are explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention, and together with the description serve to explain the inventive concepts.

FIG. 1 is a schematic cross-sectional view of an embodiment of an organic light-emitting device constructed according to the principles of the invention.

FIG. 2 is a schematic cross-sectional view of an embodiment of an organic light-emitting device constructed according to the principles of the invention.

FIG. 3 is a schematic cross-sectional view of an embodiment of an organic light-emitting device constructed according to the principles of the invention.

FIG. 4 is a schematic cross-sectional view of an embodiment of an organic light-emitting device constructed according to the principles of the invention.

DETAILED DESCRIPTION

[0018] In the following description, for the purposes of explanation, numerous specific details are set forth in order to provide a thorough understanding of various embodiments of the invention. As used herein "embodiments" are non-limiting examples of devices employing one or more of the inventive concepts disclosed herein. It is apparent, however, that various embodiments may be practiced without these specific details or with one or more equivalent arrangements. In other instances, well-known structures and devices are shown in block diagram form in order to avoid unnecessarily obscuring various embodiments. Further, various embodiments may be different, but do not have to be exclusive. For example, specific shapes, configurations, and characteristics of an embodiment may be used or implemented in another embodiment without departing from the inventive concepts.

[0019] Unless otherwise specified, the illustrated embodiments are to be understood as providing features of varying detail of some ways in which the inventive concepts may be implemented in practice. Therefore, unless otherwise specified, the features, components, modules, layers, films, panels, regions, and/or aspects, etc. (hereinafter individually or collectively referred to as "elements"), of the various embodiments may be otherwise combined, separated, interchanged, and/or rearranged without departing from the inventive concepts.

[0020] In the accompanying drawings, the size and relative sizes of elements may be exaggerated for clarity and/or descriptive purposes. When an embodiment may be implemented differently, a specific process order may be performed differently from the described order. For example, two consecutively described processes may be performed substantially at the same time or performed in an order opposite to the described order. Also, like reference numerals denote like elements.

[0021] When an element, such as a layer, is referred to as being "on," "connected to," or "coupled to" another element or layer, it may be directly on, connected to, or coupled to the other element or layer or intervening elements or layers may be present. When, however, an element or layer is referred to as being "directly on," "directly connected to," or "directly coupled to" another element or layer, there are no intervening elements or layers present. To this end, the term "connected" may refer to physical, electrical, and/or fluid connection, with or without intervening elements. For the purposes of this disclosure, "at least one of X, Y, and Z," "at least one selected from the group consisting of X, Y, and Z," "at least one selected from X, Y, and Z" and "at least one element selected from X, Y, and Z" may be construed as X only, Y only, Z only, or any combination of two or more of X, Y, and Z, such as, for instance, XYZ, XYY, YZ, and ZZ. As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items. However, the phrases "A, B, and C are each independently selected from X, Y, and Z," "A, B, and C are each independently selected from elements represented by X, Y, and Z," "A, B, and C are each independently X, Y, or Z," may be construed to mean that A may be X only, Y only, or Z only, B may be X only, Y only, or Z only, and C may be X only, Y only, or Z only.

[0022] Although the terms "first," "second," etc. may be used herein to describe various types of elements, these elements should not be limited by these terms. These terms are used to distinguish one element from another element. Thus, a first element discussed below could be termed a second element without departing from the teachings of the disclosure.

[0023] Spatially relative terms, such as "beneath," "below," "under," "lower," "above," "upper," "over," "higher," "side" (e.g., as in "sidewall"), and the like, may be used herein for descriptive purposes, and, thereby, to describe one elements relationship to another element(s) as illustrated in the drawings. Spatially relative terms are intended to encompass different orientations of an apparatus in use, operation, and/or manufacture in addition to the orientation depicted in the drawings. For example, if the apparatus in the drawings is turned over, elements described as "below" or "beneath" other elements or features would then be oriented "above" the other elements or features. Thus, the term "below" can encompass both an orientation of above and below. Furthermore, the apparatus may be otherwise oriented (e.g., rotated

90 degrees or at other orientations), and, as such, the spatially relative descriptors used herein interpreted accordingly.

[0024] The terminology used herein is for the purpose of describing particular embodiments and is not intended to be limiting. As used herein, the singular forms, "a," "an," and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. Moreover, the terms "comprises," "comprising," "includes," and/or "including," when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof. It is also noted that, as used herein, the terms "substantially," "about," and other similar terms, are used as terms of approximation and not as terms of degree, and, as such, are utilized to account for inherent deviations in measured, calculated, and/or provided values that would be recognized by one of ordinary skill in the art.

[0025] Various embodiments are described herein with reference to sectional and/or exploded illustrations that are schematic illustrations of idealized embodiments and/or intermediate structures. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments disclosed herein should not necessarily be construed as limited to the particular illustrated shapes of regions, but are to include deviations in shapes that result from, for instance, manufacturing. In this manner, regions illustrated in the drawings may be schematic in nature and the shapes of these regions may not reflect actual shapes of regions of a device and, as such, are not necessarily intended to be limiting.

[0026] Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure is a part. Terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and should not be interpreted in an idealized or overly formal sense, unless expressly so defined herein.

[0027] An organic light-emitting device includes a first electrode, a second electrode, and an emission layer between the first electrode and the second electrode.

[0028] The first electrode may be an anode. The second electrode may be a cathode. Descriptions for the first electrode and the second electrode may be understood by referring to the descriptions for those provided herein.

[0029] The emission layer includes a host material. The host material may be understood by referring to the descriptions for those provided herein.

[0030] The organic light-emitting device satisfies Equation 1:

$$F_{CB} > 2.8 \qquad \text{Equation 1}$$

[0031] F_{CB} is defined by Equation 2:


$$F_{CB} = V_{EOD} \text{ (at } 10 \text{ mA/cm}^2\text{)} / V_{HOD} \text{ (at } 10 \text{ mA/cm}^2\text{)} \qquad \text{Equation 2}$$

wherein, in Equation 2,


V_{HOD} (at 10 mA/cm²) is a driving voltage (volts, V) at a current density of 10 mA/cm² of a hole-only device having a structure of ITO (1,500 Angstroms (Å))/ HT211 :NDP9 (1 percent by weight (wt%)) (100 Å)/ HT211 (1,500 Å)/ the host material (400 Å)/ L101 (100 Å)/ Yb (13 Å)/ Mg:Ag (10 wt%)(600 Å), and

V_{EOD} (at 10 mA/cm²) may be a driving voltage (V) at a current density of 10 mA/cm² of an electron-only device having a structure of ITO (1,500 Å)/ LiQ (100 Å)/ the host material (400 Å)/ TPBi:LiQ (50 wt%) (360 Å)/ Yb (13 Å)/ Mg:Ag (10 wt%) (600 Å):


5



HT211



NDP9




L101


10

15

20



TPBI



LiQ

25

[0032] V_{HOD} and V_{EOD} may be measured by using, for example, a Keithley Source Measure Unit 2635A.

[0033] According to an embodiment, the organic light-emitting device may satisfy Equation 3-1:

30

$$2.9 \leq F_{CB} \leq 50 \quad \text{Equation 3-1}$$

[0034] According to an embodiment, the organic light-emitting device may satisfy Equation 3-2:

35

$$2.9 \leq F_{CB} \leq 15 \quad \text{Equation 3-2}$$

[0035] According to an embodiment, the organic light-emitting device may satisfy Equation 3-3:

40

$$2.9 \leq F_{CB} \leq 10 \quad \text{Equation 3-3}$$

[0036] According to an embodiment, the organic light-emitting device may satisfy Equation 3-4:

45

$$2.9 \leq F_{CB} \leq 5.0 \quad \text{Equation 3-4}$$

[0037] According to an embodiment, the organic light-emitting device may satisfy Equation 3-5:

50

$$3.0 \leq F_{CB} \leq 4.0 \quad \text{Equation 3-5}$$

[0038] According to an embodiment, the organic light-emitting device may satisfy Equation 3-6:

55

$$3.0 \leq F_{CB} \leq 3.8 \quad \text{Equation 3-6}$$

[0039] When the host material in the emission layer of the organic light-emitting device satisfies Equation 2, in the emission layer, electrons and holes may be balanced, and thus, the efficiency and lifespan characteristics of the organic light-emitting device may improve.

[0040] According to an embodiment, the host material may include one type of host or a combination of at least two types of host.

[0041] In some embodiments, the host material may include one type of compound or a mixture of at least two types of compound at a given ratio.

[0042] In some embodiments, the host material may include at least one host selected from a hole transporting host, an electron transporting host, and a bipolar host. The hole transporting host may be an amine-based compound containing a hole transporting unit, the electron transporting host may contain an electron transporting unit, and the bipolar host may contain the hole transporting unit and the electron transporting unit.

[0043] In some embodiments, the host material may include the hole transporting host and the bipolar host.


[0044] In some embodiments, the hole transporting unit may be selected from a fluorene group, a carbazole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, a dibenzosilole group, an indenocarbazole group, an indolocarbazole group, a benzoindolocarbazole group, a benzofurocarbazole group, a benzothienocarbazole group, and a benzosilolocarbazole group.

[0045] In some embodiments, the electron transporting unit may be selected from an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group.


[0046] In some embodiments, the hole transporting unit may be selected from a fluorene group, a carbazole group, a dibenzofuran group, a dibenzothiophene group, a dibenzocarbazole group, an indenocarbazole group, an indolocarbazole group, and a benzoindolocarbazole group.

[0047] In some embodiments, the electron transporting unit may be selected from a pyridine group, a pyrimidine group, a quinoline group, a quinazoline group, an isoquinoline group, a benzimidazole group, and a triazine group.

[0048] According to an embodiment, the host material may include at least one compound selected from a compound represented by Formula 1 and a compound represented by Formula 2:



Formula 1



Formula 2

wherein, in Formulae 1 and 2,

Ar_{10} is a C_1 - C_{60} heterocyclic group including at least one π electron-depleted nitrogen-containing ring,

L_{10} , L_{20} , L_{30} , and L_{40} are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{32}) arylene group, a substituted or unsubstituted C_1 - C_{60} (e.g. C_1 - C_{20}) heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a_{10} , a_{20} , a_{30} , and a_{40} are each independently an integer from 0 to 5,

when a_{10} is 2 or greater, at least two L_{10} (s) are identical to or different from each other,

when a_{20} is 2 or greater, at least two L_{20} (s) are identical to or different from each other,

when a_{30} is 2 or greater, at least two L_{30} (s) are identical to or different from each other,

when a_{40} is 2 or greater, at least two L_{40} (s) are identical to or different from each other,

R_{10} , R_{20} , R_{30} , R_{40} , and R_{50} are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl

group, a cyano group, a nitro group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁)(Q₂)(Q₃), -N(Q₁)(Q₂), -B(Q₁)(Q₂), -C(=O)(Q₁), -S(=O)₂(Q₁), and -P(=O)(Q₁)(Q₂),

b₁₀, b₂₀, b₃₀, b₄₀, and b₅₀ are each independently an integer from 1 to 10,

when b₁₀ is 2 or greater, at least two R₁₀(s) are identical to or different from each other,

when b₂₀ is 2 or greater, at least two R₂₀(s) are identical to or different from each other,

when b₃₀ is 2 or greater, at least two R₃₀(s) are identical to or different from each other,

when b₄₀ is 2 or greater, at least two R₄₀(s) are identical to or different from each other,

when b₅₀ is 2 or greater, at least two R₅₀(s) are identical to or different from each other,

c₄₀ is an integer from 1 to 4,

when c₄₀ is 2 or greater, at least two -(L₄₀)_{a40}-(R₄₀)_{b40}(s) are identical to or different from each other, and

at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ (e.g. C₆-C₃₀) arylene group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) heteroarylene group, the substituted

divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, the substituted C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, the substituted C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, the substituted

C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, the substituted C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, the substituted C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted

monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, and a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group;

a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, and a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group,

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁₁)(Q₁₂)(Q₁₃), -N(Q₁₁)(Q₁₂), -B(Q₁₁)(Q₁₂), -C(=O)(Q₁₁), -S(=O)₂(Q₁₁), and -P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group,

-Si(Q₂₁)(Q₂₂)(Q₂₃), -N(Q₂₁)(Q₂₂), -B(Q₂₁)(Q₂₂), -C(=O)(Q₂₁), -S(=O)₂(Q₂₁), and -P(=O)(Q₂₁)(Q₂₂); and -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂),

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , Q_{31} to Q_{33} , and Q_{41} to Q_{43} are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} (e.g. C_1 - C_{20}) alkyl group, a C_2 - C_{60} (e.g. C_2 - C_{20}) alkenyl group, a C_2 - C_{60} (e.g. C_2 - C_{20}) alkynyl group, a C_1 - C_{60} (e.g. C_1 - C_{20}) alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} (e.g. C_6 - C_{30}) aryl group, a C_1 - C_{60} (e.g. C_1 - C_{20}) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0049] In some embodiments, i) when the compound represented by Formula 1 includes a biscarbazole group, the compound represented by Formula 2 may not include a biscarbazole group, and ii) when the compound represented by Formula 2 includes a biscarbazole group, the compound represented by Formula 1 may not include a biscarbazole group, and the compound represented by Formula 2 may not include a substituted or unsubstituted amino group.

[0050] In some embodiments, the compound represented by Formula 1 may not include a biscarbazole group, and the compound represented by Formula 2 may not include a substituted or unsubstituted amino group.

[0051] In Formula 2, Ar_{10} is a C_1 - C_{60} heterocyclic group including at least one π electron-depleted nitrogen-containing ring. For example, in Formula 2, Ar_{10} may be a C_1 - C_{50} , a C_1 - C_{40} , a C_1 - C_{30} , a C_1 - C_{20} or a C_1 - C_{12} heterocyclic group including at least one π electron-depleted nitrogen-containing ring.

[0052] The term " π electron-depleted nitrogen-containing ring" as used herein refers to a C_1 - C_{60} (e.g. C_1 - C_{30}) heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

[0053] For example, the " π electron-depleted nitrogen-containing ring" may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which at least two 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*$ moiety, are condensed, or iii) a heteropolycyclic group in which at least one of a 5-membered to 7-membered heteromonocyclic group, each having at least one $*-N=*$ moiety, is condensed with at least one C_5 - C_{60} carbocyclic group.

[0054] In some embodiments, in Formula 2, Ar_{10} may be selected from an imidazole ring, a pyrazole ring, a thiazole ring, an isothiazole ring, an oxazole ring, an isoxazole ring, a pyridine ring, a pyrazine ring, a pyrimidine ring, a pyridazine ring, an indazole ring, a purine ring, a quinoline ring, an isoquinoline ring, a benzoquinoline ring, a phthalazine ring, a naphthyridine ring, a quinoxaline ring, a quinazoline ring, a cinnoline ring, a phenanthridine ring, an acridine ring, a phenanthroline ring, a phenazine ring, a benzimidazole ring, an iso-benzothiazole ring, a benzoxazole ring, an isobenzoxazole ring, a triazole ring, a tetrazole ring, an oxadiazole ring, a triazine ring, a thiadiazole ring, an imidazopyridine ring, an imidazopyrimidine ring, and an azacarbazole ring.

[0055] In some embodiments, in Formula 2, Ar_{10} may be selected from a pyrimidine ring, a quinazoline ring, and a triazine ring.

[0056] In some embodiments, in Formulae 1 and 2, L_{10} , L_{20} , L_{30} , and L_{40} may each independently be selected from:


a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, an indoloindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, an indolocarbazolylenylene group, a biscarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, an indoloindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, an indolocarbazolylenylene group, a biscarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl


group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with -F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, an indoloindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an indolocarbazolyl group, a biscarbazolyl group, a dibenzosilolyl group, a pyridinyl group, -Si(Q₃₁)(Q₃₂)(Q₃₃), and -N(Q₃₁)(Q₃₂).

wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


[0057] In some embodiments, in Formulae 1 and 2, L₁₀, L₂₀, L₃₀, and L₄₀ may each independently be selected from groups represented by Formulae 3-1 to 3-43:




5




3-15



3-16




3-17




3-18


10




3-19



3-20



3-21




3-22


15

20


25




3-23




3-24



3-25




3-26




3-27

30


35




3-28




3-29




3-30



3-31




3-32




3-33

40


45




3-34




3-35




3-36



3-37




3-38




3-39

50


55




3-40



3-41



3-42



wherein, in Formulae 3-1 to 3-43,

Y_1 is O, S, $C(Z_5)(Z_6)$, $N(Z_7)$, or $Si(Z_8)(Z_9)$,

Z_1 to Z_9 are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, a triazinyl group, - $Si(Q_{31})(Q_{32})(Q_{33})$, - $N(Q_{31})(Q_{32})$, - $B(Q_{31})(Q_{32})$, - $C(=O)(Q_{31})$, - $S(=O)_2(Q_{31})$, and - $P(=O)(Q_{31})(Q_{32})$,

wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

d_2 is an integer selected from 1 and 2,

d_3 is an integer from 1 to 3,

d_4 is an integer from 1 to 4,

d_5 is an integer from 1 to 5,

d_6 is an integer from 1 to 6,

d_8 is an integer from 1 to 8, and

* and ** each indicate a binding site to an adjacent atom.

[0058] In some embodiments, in Formulae 1 and 2, L_{10} , L_{20} , L_{30} , and L_{40} may be selected from groups represented by Formulae 3-1, 3-2, 3-20, 3-23, 3-24, and 3-40 to 3-43, but embodiments are not limited thereto:

In one embodiment, in Formulae 1 and 2, L_{10} , L_{20} , L_{30} , and L_{40} may each independently be selected from:

a phenylene group, a carbazolyene group, an indoloindolyene group, a dibenzofuranylene group, and an indolo-carbazolyene group; and

a phenylene group, a carbazolyene group, an indoloindolyene group, a dibenzofuranylene group, and an indolo-carbazolyene group, each substituted with at least one selected from a phenyl group, a carbazolyl group substituted with a phenyl group, and - $N(Q_{31})(Q_{32})$,

wherein Q_{31} and Q_{32} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0059] In one or more embodiments, in Formulae 1 and 2,

L_{10} , L_{20} , L_{30} , and L_{40} may not include a biscarbazolyene group, but embodiments are not limited thereto.

[0060] In one embodiment, in Formula 2, L_{40} may be selected from

a phenylene group, a pentalenyne group, an indenylene group, a naphthylene group, an azulenyne group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenyne group, a furanylene group, a carbazolyene group, an indolyene group, an isoindolyene group, an indoloindolyene group, a benzofuranylene group, a benzothiophenyne group, a dibenzofuranylene group, a dibenzothiophenyne group, a benzocarbazolyene group, a dibenzocarbazolyene group, an indolocarbazolyene group, a biscarbazolyene group, a dibenzosilolyene group, and a pyridinyne group; and

a phenylene group, a pentalenyne group, an indenylene group, a naphthylene group, an azulenyne group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group,

a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylylene group, a phenanthrenylylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylylylene group, a pyrenylylene group, a chrysenylylene group, a naphthacenylylene group, a picenenylylene group, a perylenylylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenenylylene group, a rubicenenylylene group, a coronenylylene group, an ovalenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, an indoloindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, an indolocarbazolylylene group, a biscarbazolylylene group, a dibenzosilolylylene group, and a pyridinylylene group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with -F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenylyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylylyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, an indoloindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzocarbazolyl group, an indolocarbazolyl group, a biscarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and -Si(Q₃₁)(Q₃₂)(Q₃₃),

wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0061] In some embodiments, in Formula 2, L₄₀ may be selected from:

a phenylene group, a carbazolylylene group, an indolocarbazolylylene group, and a biscarbazolylylene group; and a phenylene group, a carbazolylylene group, an indolocarbazolylylene group, and a biscarbazolylylene group each substituted with at least one selected from a phenyl group and a carbazolyl group, but embodiments are not limited thereto.

[0062] In Formulae 1 and 2, a₁₀, a₂₀, a₃₀, and a₄₀ each indicate the number of L₁₀(s), L₂₀(s), L₃₀(s), and L₄₀(s). a₁₀, a₂₀, a₃₀, and a₄₀ are each independently an integer from 0 to 5; and when a₁₀ is 2 or greater, at least two L₁₀(s) are identical to or different from each other, when a₂₀ is 2 or greater, at least two L₂₀(s) are identical to or different from each other, when a₃₀ is 2 or greater, at least two L₃₀(s) are identical to or different from each other, and when a₄₀ is 2 or greater, at least two L₄₀(s) are identical to or different from each other.

[0063] In Formulae 1 and 2, when a₁₀ is 0, $^{*}-(L_{10})_{a_{10}}-^{*}$ is a single bond, when a₂₀ is 0, $^{*}-(L_{20})_{a_{20}}-^{*}$ is a single bond, when a₃₀ is 0, $^{*}-(L_{30})_{a_{30}}-^{*}$ is a single bond, and when a₄₀ is 0, $^{*}-(L_{40})_{a_{40}}-^{*}$ is a single bond.

[0064] In one embodiment, in Formulae 1 and 2, a₁₀, a₂₀, a₃₀, and a₄₀ may each independently be 0, 1, 2, or 3.

[0065] In Formulae 1 and 2, R₁₀, R₂₀, R₃₀, R₄₀ and R₅₀ are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁)(Q₂)(Q₃), -N(Q₁)(Q₂), -B(Q₁)(Q₂), -C(=O)(Q₁), -S(=O)₂(Q₁), and -P(=O)(Q₁)(Q₂).

[0066] For example, in Formulae 1 and 2, R₁₀, R₂₀, R₃₀, R₄₀ and R₅₀ may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substituted or unsubstituted C₂-C₂₀ alkenyl group, a substituted or unsubstituted C₂-C₂₀ alkynyl group, a substituted or unsubstituted C₁-C₂₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, a substituted or unsubstituted C₁-C₂₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁)(Q₂)(Q₃), -N(Q₁)(Q₂), -B(Q₁)(Q₂), -C(=O)(Q₁), -S(=O)₂(Q₁), and -P(=O)(Q₁)(Q₂).

[0067] In some embodiments, in Formulae 1 and 2, R₁₀, R₂₀, R₃₀, R₄₀, and R₅₀ may each independently be selected

from:


hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;


a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂); and -Si(Q₁)(Q₂)(Q₃), -C(=O)(Q₁), -S(=O)₂(Q₁), and -P(=O)(Q₁)(Q₂),

wherein Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.


[0068] In one embodiment, in Formulae 1 and 2, R₁₀, R₂₀, R₃₀, R₄₀, and R₅₀ may each independently be selected from groups represented by Formulae 5-1 to 5-47 and 6-1 to 6-27, but embodiments are not limited thereto:




5-1




5-2










5-3




5-4









wherein, in Formulae 5-1 to 5-47 and 6-1 to 6-27,

Y_{31} and Y_{32} are each independently selected from O, S, $C(Z_{34})(Z_{35})$, $N(Z_{36})$, and $Si(Z_{37})(Z_{38})$.

Z_{31} to Z_{38} are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, a pyridinyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a carbazolyl group substituted with a phenyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$,

wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, and a pyridinyl group,

e_2 is an integer from 0 to 2,

e_3 is an integer from 0 to 3,

e_4 is an integer from 0 to 4,

e_5 is an integer from 0 to 5,


e_6 is an integer from 0 to 6,


e_7 is an integer from 0 to 7,

e_9 is an integer from 0 to 9, and


* indicates a binding site to an adjacent atom.

[0069] In some embodiments, in Formulae 1 and 2, R_{10} , R_{20} , R_{30} , R_{40} , and R_{50} may each independently be selected from groups represented by Formulae 9-1 to 9-100 and 10-1 to 10-27, but embodiments are not limited thereto:







5




9-53



9-54




9-55




9-56


10




9-57



9-58




9-59




9-60

15


20




9-61



9-62




9-63




9-64

25


30




9-65



9-66




9-67




9-68

35


40




9-69



9-70



9-71




9-72

45


50

55


5
10
15
20
25
30
35
40
45
50
55




9-73




9-74




9-75




9-76




9-77




9-78




9-79




9-80




9-81




9-82




9-83




9-84




9-85




9-86




9-87




9-88




9-89



9-90










9-91



9-92

5
10
15
20
25
30
35
40
45
50
55





35 wherein, in Formulae 9-1 to 9-100 and 10-1 to 10-27, "Ph" represents a phenyl group, and * indicates a binding site to an adjacent atom.

[0070] In some embodiments, in Formulae 1 and 2, R_{10} , R_{20} , R_{30} , and R_{50} may be selected from Formulae 9-1, 9-11, 9-16, 9-37, 9-41, 9-54, 9-65, 9-90, 9-91, 10-18 to 10-20, and 10-23 to 10-25, and in Formula 2, R_{40} may be selected from Formulae 9-1, 9-20, 9-28, 10-16, 10-18, 10-22, 10-26, and 10-27, but embodiments are not limited thereto.

[0071] In one embodiment, in Formulae 1 and 2, R_{10} , R_{20} , R_{30} , R_{40} , and R_{50} may each independently be selected from a phenyl group, a biphenyl group, a fluorenyl group, a chrysenyl group, a quinoliny group, an isoquinoliny group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a biphenyl group, a fluorenyl group, a chrysenyl group, a quinoliny group, an isoquinoliny group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a fluorenyl group, a chrysenyl group, a quinoliny group, an isoquinoliny group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-N(Q_{31})(Q_{32})$,

wherein Q_{31} to Q_{32} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0072] In one or more embodiments, in Formulae 1 and 2, R_{10} , R_{20} , R_{30} , R_{40} , and R_{50} may not include a biscarbazolyl group, and R_{10} , R_{20} , and R_{30} may not include at least two carbazolyl groups, but embodiments are not limited thereto.


[0073] In one or more embodiments, in Formula 2, R_{40} may be selected from:

a phenyl group, a biphenyl group, a fluorenyl group, a chrysenyl group, a quinoliny group, an isoquinoliny group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;


a phenyl group, a biphenyl group, a fluorenyl group, a chrysenyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a fluorenyl group, a chrysenyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, an indoloindolyl group, an indolocarbazolyl group, a benzothienocarbazolyl group, a benzothienobenzocarbazolyl group, an indenocarbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

wherein Q₃₁ to Q₃₂ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.


[0074] According to another embodiment, at least one selected from R₁₀, R₂₀, and R₃₀ and at least one selected from R₄₀ and R₅₀ may each independently include a partial structure represented by any one of Formulae 4-1 to 4-15:




4-1




4-2




4-3




4-4




4-5




4-6




4-7




4-8




4-9




4-10




4-11




4-12



4-13



4-14



4-15

wherein, in Formulae 4-1 to 4-15,

Y₁₁ is selected from C(R₁)(R₂), N(R₁), O, and S,

Y₁₂ is selected from C(R₃)(R₄), N(R₃), O, and S,

R₁ to R₄ are each independently selected from a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, and -I;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalanyl group, a quinazolanyl group, a benzofuopyridinyl group, a benzothienopyridinyl

group, a benzofuopyrimidinyl group, and a benzothienopyrimidinyl group; and a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalanyl group, a quinazolanyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a benzofuopyrimidinyl group, and a benzothienopyrimidinyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a methoxy group, an ethoxy group, an n-propoxy group, an iso-propoxy group, an n-butoxy group, an iso-butoxy group, a sec-butoxy group, a tert-butoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalanyl group, a quinazolanyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a benzofuopyrimidinyl group, and a benzothienopyrimidinyl group, and any carbon atom or any nitrogen atom in the partial structure represented by any one of Formulae 4-1 to 4-15 is a binding site to an adjacent atom.

[0075] The expression, a compound "including a partial structure represented by" and/or a compound "including a partial structure", as used herein, may be construed as meaning that the compound includes a substituent including the partial structure (e.g., a monovalent substituent or a divalent substituent), and also that the partial structure may further include an additional substituent.

[0076] In Formula 2, c40 indicates the number of $-(L_{40})_{a40}-(R_{40})_{b40}(s)$. c40 is an integer from 1 to 4; and when c40 is 2 or greater, at least two $-(L_{40})_{a40}-(R_{40})_{b40}(s)$ are identical to or different from each other.

[0077] In some embodiments, i) when the compound represented by Formula 1 includes a biscarbazole group, the compound represented by Formula 2 may not include a biscarbazole group, and ii) when the compound represented by Formula 2 includes a biscarbazole group, the compound represented by Formula 1 may not include a biscarbazole group.

[0078] The term "biscarbazole group", as used herein, refers to a group in which at least two carbazole groups are linked via a single bond. For example, the biscarbazole group may be a biscarbazolyl group or a biscarbazolylene group.

[0079] In some embodiments, the compound represented by Formula 1 may not include a biscarbazole group, but embodiments are not limited thereto.

[0080] In one or more embodiments, the compound represented by Formula 2 may not include a substituted or unsubstituted amino group.

[0081] The term "amino group", as used herein, refers to a group having at least one amine group. For example, the amino group may be monoamine, diamine, or triamine.

[0082] A substituted amino group may include at least one substituent that may be selected from:

deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, and a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group;

a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, and a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁₁)(Q₁₂)(Q₁₃), -N(Q₁₁)(Q₁₂), -B(Q₁₁)(Q₁₂), -C(=O)(Q₁₁), -S(=O)₂(Q₁₁), and -P(=O)(Q₁₁)(Q₁₂);


a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl


group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, -Si(Q₂₁)(Q₂₂)(Q₂₃), -N(Q₂₁)(Q₂₂), -B(Q₂₁)(Q₂₂), -C(=O)(Q₂₁), -S(=O)₂(Q₂₁), and -P(=O)(Q₂₁)(Q₂₂); and

-Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂), wherein Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, Q₃₁ to Q₃₃, and Q₄₁ to Q₄₃ may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.


[0083] According to an embodiment, the host material may include at least one compound selected from a compound represented by Formula 3A, Formula 3B, or Formula 3C and a compound represented by Formula 4. In some embodiments, the compound represented by Formula 1 may be the compound represented by Formula 3A, Formula 3B, or Formula 3C, and the compound represented by Formula 2 may be the compound represented by Formula 4:




Formula 3A



Formula 3B



Formula 3C



Formula 4

wherein, in Formulae 3A, 3B, 3C, and 4,

15 A_{10} , A_{20} , and A_{40} are each independently selected from a benzene group, a naphthalene group, a fluorene group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, an indoline group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a dibenzofuran group, and a dibenzothiophene group,

20 Y_{21} is selected from -O-, -S-, -N(R_{21})-, -C(R_{21})(R_{22})-, and -Si(R_{21})(R_{22})-,

X_{11} , X_{12} , X_{13} , and X_{14} are each independently N or C(R_{13}),

25 X_{21} , X_{22} , X_{23} , and X_{24} are each independently N or C(R_{24}),

X_{41} , X_{42} , X_{43} , and X_{44} are each independently N or C(R_{42}),

X_{51} , X_{52} , X_{53} , X_{54} , and X_{55} are each independently N or C(R_{51}),

at least one selected from X_{51} , X_{52} , X_{53} , X_{54} , and X_{55} is N,

L_{11} may be understood by referring to the descriptions for L_{10} provided herein,

25 L_{21} may be understood by referring to the descriptions for L_{20} provided herein,

L_{41} may be understood by referring to the descriptions for L_{40} provided herein,

a_{11} is an integer from 0 to 5,

a_{21} is an integer from 0 to 5,

30 a_{41} is an integer from 0 to 5,

R_{11} , R_{12} , and R_{13} may each be understood by referring to the descriptions for R_{10} provided herein,

R_{21} , R_{22} , R_{23} , and R_{24} may each be understood by referring to the descriptions for R_{20} provided herein,

R_{31} may be understood by referring to the descriptions for R_{30} provided herein,


R_{41} and R_{42} may each be understood by referring to the descriptions for R_{40} provided herein,

35 R_{51} may be understood by referring to the descriptions for R_{50} provided herein, and


b_{12} , b_{23} , and b_{41} are each independently an integer from 1 to 8.

[0084] In one or more embodiments, the compound represented by Formula 1 may be one of Compounds 1-1 to 1-14, and the compound represented by Formula 2 may be one of Compounds 2-1 to 2-8:


40




5



1-4




1-5




1-6

10


15



1-7



1-8




1-9


20

25

30



1-10




1-11

35

40

45




1-12

1-13


1-14

50


55




2-1




2-2




2-3




2-4




2-5



2-6



2-7



2-8

[0085] In Formula 1, any combination of L_{10} , L_{20} , L_{30} , a_{10} , a_{20} , a_{30} , R_{10} , R_{20} , R_{30} , b_{10} , b_{20} , and b_{30} may be possible within the scope described herein.

[0086] In Formula 2, any combination of Ar_{10} , c_{40} , L_{40} , a_{40} , R_{40} , R_{50} , b_{40} , and b_{50} may be possible within the scope described herein.

[0087] In some embodiments, a host material included in the emission layer of the organic light-emitting device may include at least one of the compound represented by Formula 1 or at least one of the compound represented by Formula 2.

[0088] In some embodiments, a host material included in the emission layer of the organic light-emitting device may include at least one of the compound represented by Formula 1 and at least one of the compound represented by Formula 2.

[0089] The term "at least one", as used herein, refers to one or more, for example, two or more. In one embodiment, when a host material included in the emission layer of the organic light-emitting device includes at least two compounds represented by Formula 1, the at least two compounds represented by Formula 1 may be identical to or different from each other; and when the host material included in the emission layer of the organic light-emitting device includes at least two compounds represented by Formula 2, the at least two compounds represented by Formula 2 may be identical to or different from each other.

[0090] The compound represented by Formula 1 may be a hole transporting host, and the compound represented by Formula 2 may be an electron transporting host or a bipolar host.

[0091] In an organic light-emitting device, when at least one selected from the compound represented by Formula 1 and the compound represented by Formula 2 is used as host materials, while satisfying Equation 1, injection of electrons and holes an emission layer may be facilitated. Thus, relatively low-voltage driving may be achieved, and maintaining balance may be possible due to widespread excitons within the emission layer. Thus, the organic light-emitting device may have relatively high efficiency.

[0092] In some embodiments, the emission layer may further include a dopant material, and a content of the host material may be greater than that of the dopant material.

[0093] In some embodiments, the dopant material may be a phosphorescent dopant.

[0094] In some embodiments, the emission layer may be a phosphorescent emission layer and may further include a phosphorescent dopant.

[0095] The organic light-emitting device may include at least one of the compound represented by Formula 1, at least one of the compound represented by Formula 2, and a phosphorescent dopant in the emission layer, and thus the organic light-emitting device may have a low driving voltage, high efficiency, and a long lifespan.

[0096] In one embodiment, in the emission layer, a sum of a content of the compound represented by Formula 1 and a content of the compound represented by Formula 2 may be greater than that of the phosphorescent dopant.

[0097] In some embodiments, in the emission layer, the compound represented by Formula 1 and the compound represented by Formula 2 may serve as hosts, and the phosphorescent dopant may serve as a dopant.

[0098] The emission layer may further include, in addition to the compound represented by Formula 1, the compound represented by Formula 2, and a phosphorescent dopant, any host or any dopant.

[0099] In one embodiment, the first electrode may be an anode, and the second electrode may be a cathode.

[0100] The organic light-emitting device may further include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode.

[0101] In one embodiment, the hole transport region may include at least one selected from a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer, and the electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

[0102] In one embodiment, the hole transport region may include at least one selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer, and the electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron transport layer, and an electron injection layer.

[0103] In one embodiment, the hole transport region may include a hole transporting host, and the electron transport region may include an electron transporting host.

[0104] In one embodiment, the hole transport region may include a hole transport layer and an emission auxiliary layer between the hole transport layer and the emission layer, wherein the emission auxiliary layer may include an amine-based compound. The amine-based compound included in the emission auxiliary layer may also include a hole transporting unit, as the hole transporting host may be. In some embodiments, the amine-based compound may be a compound different from the hole transporting host.

[0105] In some embodiments, the emission auxiliary layer may be in direct contact with the emission layer.

[0106] In some embodiments, the electron injection layer may include Li, Na, K, Rb, Cs, Mg, Ca, Er, Tm, Yb, or any combination thereof, but embodiments are not limited thereto.

[0107] In one or more embodiments, the hole transport region may include a p-dopant, wherein the lowest unoccupied molecular orbital (LUMO) energy level of the p-dopant may be -3.5 electron Volts (eV) or less.

[0108] For example, the p-dopant may include a cyano group-containing compound, but embodiments are not limited thereto.

[0109] In one or more embodiments, in the organic light-emitting device, the emission layer may be a first color light-emitting layer emitting first color light, the organic light-emitting device may further include i) at least one second color light-emitting layer emitting second color light between the first electrode and the second electrode or ii) at least one second color light-emitting layer emitting second color light and at least one third color light-emitting layer emitting third color light between the first electrode and the second electrode,

a maximum emission wavelength of the first color light and a maximum emission wavelength of the second color light may be identical to or different from each other or a maximum emission wavelength of the first color light, a maximum emission wavelength of the second color light, and a maximum emission wavelength of the third color light may be identical to or different from each other, and

the first color light and the second color light may be emitted in the form of mixed light, or the first color light, the second color light, and the third color light may be emitted in the form of mixed light.

[0110] FIG. 1 illustrates a schematic cross-sectional view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 includes a first electrode 110, an organic layer 150, and a second electrode 190.

[0111] Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIG. 1.

[0112] In FIG. 1, a substrate may be additionally located under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal

stability, transparency, surface smoothness, ease of handling, and water resistance.

[0113] The first electrode 110 may be formed by depositing or sputtering, onto the substrate, a material for forming the first electrode 110. When the first electrode 110 is an anode, the material for forming the first electrode 110 may be selected from materials with a high work function that facilitate hole injection.

[0114] The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming the first electrode 110 may be at least one selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), and zinc oxide (ZnO), but embodiments are not limited thereto. In some embodiments, when the first electrode 110 is a semi-transmissive electrode or a reflective electrode, a material for forming the first electrode 110 may be at least one of magnesium (Mg), silver (Ag), aluminium (Al), aluminium-lithium (Al-Li), calcium (Ca), magnesium-indium (Mg-In), and magnesium-silver (Mg-Ag), may be used, but embodiments are not limited thereto.

[0115] The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. In some embodiments, the first electrode 110 may have a triple-layered structure of ITO/Ag/ITO, but embodiments are not limited thereto.

[0116] The organic layer 150 may be on the first electrode 110. The organic layer 150 may include an emission layer.


[0117] The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer and an electron transport region between the emission layer and the second electrode 190.




[0118] The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0119] The hole transport region may include at least one selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer.


[0120] For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials or a multi-layered structure, e.g., a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein layers of each structure are sequentially stacked on the first electrode 110 in each stated order, but embodiments are not limited thereto.

[0121] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPD), β-NPB, TPD, spiro-TPD, spiro-NPB, methylated-NPB, TAPC, HMTDP, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:





Formula 201



Formula 202

wherein, in Formulae 201 and 202,

L_{201} to L_{204} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{32}) arylene group, a substituted or unsubstituted C_1 - C_{60} (e.g. C_1 - C_{20}) heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

L_{205} maybe selected from $^*O^*$, $^*S^*$, $^*N(Q_{201})^*$, a substituted or unsubstituted C_1 - C_{20} alkylene group, a substituted or unsubstituted C_2 - C_{20} alkenylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{32}) arylene group, a substituted or unsubstituted C_1 - C_{60} (e.g. C_1 - C_{20}) heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

xa_1 to xa_4 may each independently be an integer from 0 to 3,

xa_5 may be an integer from 1 to 10, and

R_{201} to R_{204} and Q_{201} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{32}) aryl group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{32}) aryloxy group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{32}) arylthio group, a substituted or unsubstituted C_1 - C_{60} (e.g. C_1 - C_{20}) heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0122] In some embodiments, in Formula 202, R_{201} and R_{202} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R_{203} and R_{204} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group.

[0123] In one embodiment, in Formulae 201 and 202,

5 L_{201} to L_{205} may each independently be selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group,
10 an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group,
15 a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group,
20 an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group,
25 a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with -F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenylenylene group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, $-Si(Q_{31})(Q_{32})(Q_{33})$, and $-N(Q_{31})(Q_{32})$,
30 wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

40 **[0124]** In one or more embodiments, xa_1 to xa_4 may each independently be 0, 1, or 2.

[0125] In one or more embodiments, xa_5 may be 1, 2, 3, or 4.

[0126] In one or more embodiments, R_{201} to R_{204} and Q_{201} may each independently be selected from a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenylenylene group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenylenylene group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with -F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, -Si(Q₃₁)(Q₃₂)(Q₃₃), and -N(Q₃₁)(Q₃₂),

wherein Q₃₁ to Q₃₃ may be understood by referring to the descriptions for those provided herein.

[0127] In one or more embodiments, in Formula 201, at least one selected from R₂₀₁ to R₂₀₃ may each independently be selected from:

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with -F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, but embodiments are not limited thereto.


[0128] In one or more embodiments, in Formula 202, i) R₂₀₁ may be linked to R₂₀₂ via a single bond, and/or ii) R₂₀₃ may be linked to R₂₀₄ via a single bond.

[0129] In one or more embodiments, in Formula 202, at least one of R₂₀₁ to R₂₀₄ may be selected from:

a carbazolyl group; and

a carbazolyl group substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with -F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, but embodiments are not limited thereto.

[0130] The compound represented by Formula 201 may be represented by Formula 201A:




Formula 201A.

[0131] In some embodiments, the compound represented by Formula 201 may be represented by Formula 201A(1), but embodiments are not limited thereto:

5

10

15



Formula 201A(1).


20

[0132] In some embodiments, the compound represented by Formula 201 may be represented by Formula 201A-1, but embodiments are not limited thereto:

25

30

35




Formula 201A-1.

40

[0133] In some embodiments, the compound represented by Formula 202 may be represented by Formula 202A:

45


50



Formula 202A.

55

[0134] In some embodiments, the compound represented by Formula 202 may be represented by Formula 202A-1:









[0135] In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,

15 L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ may each be understood by referring to the descriptions for those provided herein,


R₂₁₁ and R₂₁₂ may each be understood by referring to the descriptions for R₂₀₃ provided herein, and

20 R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with -F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.


30 [0136] The hole transport region may include at least one compound selected from Compounds HT1 to HT39, but embodiments are not limited thereto:




5



HT7




HT8




HT9

10


15



HT10



HT11




HT12


20

25


30



HT13




HT14




HT15

35


40



HT16



HT17




HT18

45


50

55


5



HT19




HT20




HT21

10


15



HT22




HT23




HT24

20


25



HT25




HT26




HT27

30


35



HT28




HT29




HT30

40


45



HT31



HT32




HT33

50


55

5




HT34

10




HT35




HT36

15




HT37

20



HT38



HT39

25

[0137] The thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, and in some embodiments, about 100 Å to about 7000 Å, about 100 Å to about 5000 Å, about 100 Å to about 3000 Å, or about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, and in some embodiments, about 100 Å to about 7,000 Å, about 100 Å to about 5,000 Å, about 100 Å to about 3,000 Å, about 100 Å to about 2,000 Å or about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and in some embodiments, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within any of these ranges, excellent hole transport characteristics may be obtained without a substantial increase in driving voltage.

30

[0138] The emission auxiliary layer may increase light emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer. The electron blocking layer may reduce or eliminate the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the aforementioned materials.

35

[0139] The hole transport region may include a charge generating material as well as the aforementioned materials, to improve conductive properties of the hole transport region. The charge generating material may be substantially homogeneously or non-homogeneously dispersed in the hole transport region.

40

[0140] The charge generating material may include, for example, a p-dopant.

[0141] In some embodiments, the LUMO of the p-dopant may be about -3.5 eV or less.

[0142] The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments are not limited thereto.

[0143] In some embodiments, the p-dopant may include at least one selected from:

45

a quinone derivative, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

a metal oxide, such as tungsten oxide or molybdenum oxide;

1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and



50

a compound represented by Formula 221, but embodiments are not limited thereto:


<HAT-CN>

<F4-TCNQ>

55



Formula 221



wherein, in Formula 221,

R₂₂₁ to R₂₂₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ (e.g. C₆-C₃₂) aryl group, a substituted or unsubstituted C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, provided that at least one selected from R₂₂₁ to R₂₂₃ may include at least one substituent selected from a cyano group, -F, -Cl, -Br, -I, a C₁-C₂₀ alkyl group substituted with -F, a C₁-C₂₀ alkyl group substituted with -Cl, a C₁-C₂₀ alkyl group substituted with -Br, and a C₁-C₂₀ alkyl group substituted with -I.

[0144] When the organic light-emitting device 10 is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer may have a stacked structure. The stacked structure may include two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer. The two or more layers may be in direct contact with each other. In some embodiments, the two or more layers may be separated from each other. In one or more embodiments, the emission layer may include two or more materials. The two or more materials may include a red light-emitting material, a green light-emitting material, or a blue light-emitting material. The two or more materials may be mixed with each other in a single layer. The two or more materials mixed with each other in the single layer may emit white light.

[0145] The emission layer may include a host and a dopant. The dopant may include a phosphorescent dopant.

[0146] The amount of the dopant in the emission layer may be, in general, in a range of about 0.01 parts to about 15 parts by weight based on 100 parts by weight of the host, but embodiments are not limited thereto.


[0147] The thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, and in some embodiments, about 100 Å to about 800 Å, about 150 Å to about 800 Å, about 150 Å to about 700 Å, about 150 Å to about 650 Å, about 200 Å to about 600 Å or about 300 Å to about 500 Å. When the thickness of the emission layer is within any of these ranges, improved luminescence characteristics may be obtained without a substantial increase in driving voltage.

[0148] A host in the emission layer may be understood by referring to the descriptions for the host material provided herein. In some embodiments, the host material may include at least one host selected from a hole transporting host, an electron transporting host, and a bipolar host.

[0149] For example, the host material may include at least one selected from the compound represented by Formula 1 and the compound represented by Formula 2.

[0150] When a combination of the compound represented by Formula 1 and the compound represented by Formula 2 is used as the host material, a weight ratio of the compound represented by Formula 1 to the compound represented by Formula 2 may be in a range of about 10:90 to about 90:10, for example, about 30:70 to about 70:30. In some embodiments, a weight ratio of the compound represented by Formula 1 to the compound represented by Formula 2 may be 30:70, but embodiments are not limited thereto. When the weight ratio of the compound represented by Formula 1 to the compound represented by Formula 2 is within any of these ranges, the hole-electron transport balance in the emission layer may be effective.

[0151] In some embodiments, the host may further include a compound represented by Formula 301:



wherein, in Formula 301,

Ar_{301} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

$\text{xb}11$ may be 1, 2, or 3,

L_{301} may be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

$\text{xb}1$ may be an integer from 0 to 5,

R_{301} may be selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ alkyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{60}$ alkenyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{60}$ alkynyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ alkoxy group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{301})(\text{Q}_{302})(\text{Q}_{303})$, $-\text{N}(\text{Q}_{301})(\text{Q}_{302})$, $-\text{B}(\text{Q}_{301})(\text{Q}_{302})$, $-\text{C}(=\text{O})(\text{Q}_{301})$, $-\text{S}(=\text{O})_2(\text{Q}_{301})$, and $-\text{P}(=\text{O})(\text{Q}_{301})(\text{Q}_{302})$, and

$\text{xb}21$ may be an integer from 1 to 5,

wherein Q_{301} to Q_{303} may each independently be selected from a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0152] For example, Ar_{301} may be a substituted or unsubstituted $\text{C}_6\text{-C}_{32}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{12}$ heterocyclic group, but embodiments are not limited thereto.

[0153] In some embodiments, Ar_{301} in Formula 301 may be selected from:



a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group; and

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$.

wherein Q_{31} to Q_{33} may each independently be selected from a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0154] When $\text{xb}11$ in Formula 301 is 2 or greater, at least two $\text{Ar}_{301}(\text{s})$ may be linked via a single bond.

[0155] In one or more embodiments, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:



wherein, in Formulae 301-1 to 301-2,

25 A₃₀₁ to A₃₀₄ may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran group, a dinaphthofuran group, a thiophene group, a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, and a dinaphthothiophene group,

30 X₃₀₁ may be O, S, or N-[(L₃₀₄)_{xb4}-R₃₀₄],

35 R₃₁₁ to R₃₁₄ may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂),

xb₂₂ and xb₂₃ may each independently be 0, 1, or 2,

L₃₀₁, xb₁, R₃₀₁, and Q₃₁ to Q₃₃ may each be understood by referring to the descriptions for those provided herein,

L₃₀₂ to L₃₀₄ may each be understood by referring to the descriptions for L₃₀₁ provided herein,

xb₂ to xb₄ may each be understood by referring to the descriptions for xb₁ provided herein, and

40 R₃₀₂ to R₃₀₄ may each be understood by referring to the descriptions for R₃₀₁ provided herein.

45 **[0156]** For example, L₃₀₁ to L₃₀₄ in Formulae 301, 301-1, and 301-2 may each independently be selected from: a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₃₀ arylene group, a substituted or unsubstituted C₁-C₂₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group, but embodiments are not limited thereto.

50 **[0157]** In some embodiments, in Formulae 301, 301-1, and 301-2, L₃₀₁ to L₃₀₄ may each independently be selected from:

55 a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilylylylene group, a pyridinylylene group, an imidazolylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylylene group, an oxadiazolylylene

group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂), wherein Q₃₁ to Q₃₃ may each be understood by referring to the descriptions for those provided herein.

[0158] As another example, R₃₀₁ to R₃₀₄ in Formulae 301, 301-1, and 301-2 may each independently be selected from: deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ (e.g. C₁-C₁₀) alkyl group, a substituted or unsubstituted C₂-C₆₀ (e.g. C₂-C₁₀) alkenyl group, a substituted or unsubstituted C₂-C₆₀ (e.g. C₂-C₁₀) alkynyl group, a substituted or unsubstituted C₁-C₆₀ (e.g. C₁-C₁₀) alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, a substituted or unsubstituted C₁-C₂₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃), -N(Q₃₀₁)(Q₃₀₂), -B(Q₃₀₁)(Q₃₀₂), -C(=O)(Q₃₀₁), -S(=O)₂(Q₃₀₁), and -P(=O)(Q₃₀₁)(Q₃₀₂), but embodiments are not limited thereto.

[0159] In some embodiments, in Formulae 301, 301-1, and 301-2, R₃₀₁ to R₃₀₄ may each independently be selected from a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group,


a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂),


wherein Q₃₁ to Q₃₃ may each be understood by referring to the descriptions for those provided herein.

[0160] In some embodiments, the host may include an alkaline earth metal complex. For example, the host may include a beryllium (Be) complex, e.g., Compound H55, a magnesium (Mg) complex, or a zinc (Zn) complex.


[0161] The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds HI to H55, but embodiments are not limited thereto:




H1




H2




H3




H4




H5



H6




H7




H8


5




H9



H10




H11




H12


10




H13



H14




H15




H16


15




H17



H18




H19




H20

20


25




H21



H22




H23




H24

30


35




H25



H26



H27




H28


40

45


50




H29



H30




H31




H32

55


5



H33




H34




H35


10




H36



H37




H38




H39

15


20




H40



H41



H42




H43

25


30

35


40




H44



H45




H46




H47


45



H48




H49




H50

50


55




H51




H52





H53



H54



[0162] The phosphorescent dopant may include an organometallic complex represented by Formula 401:



Formula 402

wherein, in Formulae 401 and 402,

M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

L_{401} may be selected from ligands represented by Formula 402, $xc1$ may be an integer from 1 to 3; and when $xc1$ is 2 or greater, at least two $L_{401}(s)$ may be identical to or different from each other,

L_{402} may be an organic ligand, $xc2$ may be an integer from 0 to 4; and when $xc2$ is 2 or greater, at least two $L_{402}(s)$ may be identical to or different from each other,

X_{401} to X_{404} may each independently be N or C,

X_{401} and X_{403} may be linked via a single bond or a double bond, X_{402} and X_{404} may be linked via a single bond or a double bond,

A_{401} and A_{402} may each independently be a C_5 - C_{60} (e.g. C_5 - C_{30}) carbocyclic group or a C_1 - C_{60} (e.g. C_1 - C_{20}) heterocyclic group,

X_{405} may be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{411})-*$, $*-C(Q_{411})(Q_{412})-*$, $*-C(Q_{411})=C(Q_{412})-*$, $*-C(Q_{411})=*$, or $*=C=*$, wherein Q_{411} and Q_{412} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

X_{406} may be a single bond, O, or S,

R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{30}) aryl group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{30}) aryloxy group, a substituted or unsubstituted C_6 - C_{60} (e.g. C_6 - C_{30}) arylthio group, a substituted or unsubstituted C_1 - C_{60} (e.g. C_1 - C_{20}) heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(Q_{401})(Q_{402})(Q_{403})$, $-\text{N}(Q_{401})(Q_{402})$, $-\text{B}(Q_{401})(Q_{402})$, $-\text{C}(=O)(Q_{401})$, $-\text{S}(=O)_2(Q_{401})$, and $-\text{P}(=O)(Q_{401})(Q_{402})$, wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group, $xc11$ and $xc12$ may each independently be an integer from 0 to 10, and

* and ** in Formula 402 each indicate a binding site to M in Formula 401.

[0163] In some embodiments, in Formula 402, A_{401} and A_{402} may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

[0164] In one or more embodiments, in Formula 402, i) X_{401} may be nitrogen, and X_{402} may be carbon, or ii) X_{401} and X_{402} may each be nitrogen.

[0165] In one or more embodiments, in Formula 402, R_{401} and R_{402} may each independently be selected from:

hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, and a norbornenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;


a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and


$-\text{Si}(\text{Q}_{401})(\text{Q}_{402})(\text{Q}_{403})$, $-\text{N}(\text{Q}_{401})(\text{Q}_{402})$, $-\text{B}(\text{Q}_{401})(\text{Q}_{402})$, $-\text{C}(=\text{O})(\text{Q}_{401})$, $-\text{S}(=\text{O})_2(\text{Q}_{401})$, and $-\text{P}(=\text{O})(\text{Q}_{401})(\text{Q}_{402})$, wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0166] In one or more embodiments, when xc1 in Formula 401 is 2 or greater, two A_{401} (s) of at least two L_{401} (s) may optionally be linked via X_{407} as a linking group; or two A_{402} (s) may optionally be linked via X_{408} as a linking group (see Compounds PD1 to PD4 and PD7). X_{407} and X_{408} may each independently be selected from a single bond, $^*-\text{O}-^*$, $^*-\text{S}-^*$, $^*-\text{C}(=\text{O})-^*$, $^*-\text{N}(\text{Q}_{413})-^*$, $^*-\text{C}(\text{Q}_{413})(\text{Q}_{414})-^*$, and $^*-\text{C}(\text{Q}_{413})=\text{C}(\text{Q}_{414})-^*$, wherein Q_{413} and Q_{414} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, but embodiments are not limited thereto.

[0167] L_{402} in Formula 401 may be any suitable monovalent, divalent, or trivalent organic ligand. For example, L_{402} may be selected from halogen, diketone (e.g., acetylacetonate), a carboxylic acid (e.g., picolinate), $-\text{C}(=\text{O})$, isonitrile, $-\text{CN}$, and phosphorus (e.g., phosphine or phosphite), but embodiments are not limited thereto.

[0168] In some embodiments, the phosphorescent dopant may include, for example, at least one selected from Compounds PD1 to PD25, but embodiments are not limited thereto:





[0169] The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers, each having a plurality of different materials.

[0170] The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer, but embodiments are not limited thereto.

[0171] In some embodiments, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein layers of each structure are sequentially stacked on the emission layer in each stated order, but embodiments are not limited thereto.

[0172] The electron transport region, e.g., a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region, may include a metal-free compound. The metal-free compound may include at least one π electron-depleted nitrogen-containing ring.


[0173] The term " π electron-depleted nitrogen-containing ring" as used herein refers to a C_1 - C_{60} (e.g. a C_1 - C_{30}) heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

[0174] For example, the " π electron-depleted nitrogen-containing ring" may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which at least two 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*$ moiety, are condensed, or iii) a heteropolycyclic group in which at least one of a 5-membered to 7-membered heteromonocyclic group, each having at least one $*-N=*$ moiety, is condensed with at least one C_5 - C_{60} (e.g. a C_5 - C_{30}) carbocyclic group.

[0175] Examples of the π electron-depleted nitrogen-containing ring may include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline,

a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an iso-benzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, a thiadiazole, an imidazopyridine, an imidazopyrimidine, and an azacarbazole, but embodiments are not limited thereto.

[0176] In some embodiments, the electron transport region may include a compound represented by Formula 601:



wherein, in Formula 601,

Ar_{601} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

$\text{xe}11$ may be 1, 2, or 3,

L_{601} may be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

$\text{xe}1$ may be an integer from 0 to 5,

R_{601} may be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{601})(\text{Q}_{602})(\text{Q}_{603})$,

$-\text{C}(=\text{O})(\text{Q}_{601})$, $-\text{S}(=\text{O})_2(\text{Q}_{601})$, and $-\text{P}(=\text{O})(\text{Q}_{601})(\text{Q}_{602})$,

wherein Q_{601} to Q_{603} may each independently be a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and

$\text{xe}21$ may be an integer from 1 to 5.

[0177] In one embodiment, at least one of $\text{Ar}_{601}(\text{s})$ in the number of $\text{xe}11$ and $\text{R}_{601}(\text{s})$ in the number of $\text{xe}21$ may include the π electron-depleted nitrogen-containing ring.

[0178] For example, Ar_{601} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{30}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{20}$ heterocyclic group, but embodiments are not limited thereto.

[0179] In some embodiments, Ar_{601} in Formula 601 may be selected from:

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and


a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a

hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, -Si(Q₃₁)(Q₃₂)(Q₃₃), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂), wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0180] When xe11 in Formula 601 is 2 or greater, at least two Ar₆₀₁(s) may be linked via a single bond.

[0181] In one or more embodiments, Ar₆₀₁ in Formula 601 may be an anthracene group.

[0182] In some embodiments, the compound represented by Formula 601 may be represented by Formula 601-1:



wherein, in Formula 601-1,

X₆₁₄ may be N or C(R₆₁₄), X₆₁₅ may be N or C(R₆₁₅), X₆₁₆ may be N or C(R₆₁₆), and at least one selected from X₆₁₄ to X₆₁₆ may be N,

L₆₁₁ to L₆₁₃ may each be understood by referring to the descriptions for L₆₀₁ provided herein,

xe611 to xe613 may each be understood by referring to the descriptions for xe1 provided herein,

R₆₁₁ to R₆₁₃ may each be understood by referring to the descriptions for R₆₀₁ provided herein, and

R₆₁₄ to R₆₁₆ may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0183] For example, L₆₀₁ and L₆₁₁ to L₆₁₃ in Formulae 601 and 601-1 may each independently be selected from: a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₃₀ arylene group, a substituted or unsubstituted C₁-C₂₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group, but embodiments are not limited thereto.

[0184] In one embodiment, in Formulae 601 and 601-1, L₆₀₁ and L₆₁₁ to L₆₁₃ may each independently be selected from a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylene group, a dibenzofuranylenylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylene group, a dibenzofuranylenylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a

pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, but embodiments are not limited thereto.

[0185] In one or more embodiments, in Formulae 601 and 601-1, xe1 and xe611 to xe613, may each independently be 0, 1, or 2.

[0186] For example, R₆₀₁ and R₆₁₁ to R₆₁₃ in Formulae 601 and 601-1 may each independently be selected from: a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, a substituted or unsubstituted C₁-C₂₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₆₀₁)(Q₆₀₂)(Q₆₀₃), -C(=O)(Q₆₀₁), -S(=O)₂(Q₆₀₁), and -P(=O)(Q₆₀₁)(Q₆₀₂).

[0187] In one or more embodiments, in Formulae 601 and 601-1, R₆₀₁ and R₆₁₁ to R₆₁₃ may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;


a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano

group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexaceny group, a pentaceny group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


-S(=O)₂(Q₆₀₁) and -P(=O)(Q₆₀₁)(Q₆₀₂),

wherein Q₆₀₁ and Q₆₀₂ may each be understood by referring to the descriptions for those provided herein.


[0188] The electron transport region may include at least one compound selected from Compounds ET1 to ET36, but embodiments are not limited thereto:




ET1




ET2




ET3



ET4




ET5




ET6

5




ET7

10




ET8

15




ET9

20




ET10

25




ET11

30




ET12

35




ET13

40



ET14

45




ET15


50

55


5



ET16



ET17




ET18

15


20

25


30



ET19



ET20




ET21


35

40


45



ET22



ET23




ET24


50

55


5



ET25




ET26




ET27


15



ET28



ET29



ET30


20

25


30

35


40



ET31




ET32




ET33

45


50



ET34




ET35



ET36

55 **[0189]** In some embodiments, the electron transport region may include at least one compound selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAlq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ:




20 [0190] The thicknesses of the buffer layer, the hole blocking layer, or the electron control layer may each independently be in a range of about 20 Å to about 1,000 Å, and in some embodiments, about 20 Å to about 700 Å, about 20 Å to about 500 Å, about 20 Å to about 400 Å, about 30 Å to about 400 Å or about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer or the electron control layer are within any of these ranges, excellent hole blocking characteristics or excellent electron controlling characteristics may be obtained without a substantial increase in driving voltage.

25 [0191] The thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, and in some embodiments, about 100 Å to about 700 Å, about 100 Å to about 600 Å, about 150 Å to about 600 Å, about 150 Å to about 500 Å or about 300 Å to about 400 Å. When the thickness of the electron transport layer is within any of these ranges, excellent electron transport characteristics may be obtained without a substantial increase in driving voltage.

30 [0192] The electron transport region (e.g., the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a material including metal.

35 [0193] The material including metal may include at least one selected from an alkali metal complex and an alkaline earth metal complex. The alkali metal complex may include a metal ion selected from a lithium (Li) ion, a sodium (Na) ion, a potassium (K) ion, a rubidium (Rb) ion, and a cesium (Cs) ion. The alkaline earth metal complex may include a metal ion selected from a beryllium (Be) ion, a magnesium (Mg) ion, a calcium (Ca) ion, an strontium (Sr) ion, and a barium (Ba) ion. Each ligand coordinated with the metal ion of the alkali metal complex and the alkaline earth metal complex may independently be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyloxazole, a hydroxyphenylthiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenyl thiadiazole, a hydroxyphenyl pyridine, a hydroxyphenyl benzimidazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments are not limited thereto.

40 [0194] For example, the material including metal may include a Li complex. The Li complex may include, e.g., Compound ET-D1 (lithium 8-hydroxyquinolate, LiQ) or Compound ET-D2:



[0195] The electron transport region may include an electron injection layer that facilitates injection of electrons from

the second electrode 190. The electron injection layer may be in direct contact with the second electrode 190.

[0196] The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers, each including a plurality of different materials.

[0197] The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth metal complex, a rare earth metal complex, or a combination thereof.

[0198] The alkali metal may be selected from Li, Na, K, Rb, and Cs. In one embodiment, the alkali metal may be Li, Na, or Cs. In one or more embodiments, the alkali metal may be Li or Cs, but embodiments are not limited thereto.

[0199] The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

[0200] The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

[0201] The alkali metal compound, the alkaline earth metal compound, and the rare earth metal compound may each independently be selected from oxides and halides (e.g., fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth metal, and the rare earth metal, respectively.

[0202] The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, KI, or RbI. In one embodiment, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, and KI, but embodiments are not limited thereto.

[0203] The alkaline earth metal compound may be selected from alkaline earth metal compounds such as BaO, SrO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ (where $0 < x < 1$), and $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ (where $0 < x < 1$). In one embodiment, the alkaline earth metal compound may be selected from BaO, SrO, and CaO, but embodiments are not limited thereto.

[0204] The rare earth metal compound may be selected from YbF_3 , ScF_3 , Sc_2O_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one embodiment, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 , but embodiments are not limited thereto.

[0205] The alkali metal complex, the alkaline earth metal complex, and the rare earth metal complex may each include ions of the above-described alkali metal, alkaline earth metal, and rare earth metal. Each ligand coordinated with the metal ion of the alkali metal complex, the alkaline earth metal complex, and the rare earth metal complex may independently be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyl oxazole, a hydroxyphenyl thiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenyl thiadiazole, a hydroxyphenyl pyridine, a hydroxyphenyl benzimidazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments are not limited thereto.

[0206] The electron injection layer may consist of an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth metal complex, a rare earth metal complex, or a combination thereof, as described above. In some embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, the alkali metal, the alkaline earth metal, the rare earth metal, the alkali metal compound, the alkaline earth metal compound, the rare earth metal compound, the alkali metal complex, the alkaline earth metal complex, the rare earth metal complex, or a combination thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

[0207] The thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, and in some embodiments, about 3 Å to about 90 Å or about 3 Å to about 20 Å. When the thickness of the electron injection layer is within any of these ranges, excellent electron injection characteristics may be obtained without a substantial increase in driving voltage.

[0208] The second electrode 190 may be on the organic layer 150. In an embodiment, the second electrode 190 may be a cathode that is an electron injection electrode. In this embodiment, a material for forming the second electrode 190 may be a material having a low work function, for example, a metal, an alloy, an electrically conductive compound, or a combination thereof.

[0209] The second electrode 190 may include at least one selected from lithium (Li), silver (Ag), magnesium (Mg), aluminium (Al), aluminium-lithium (Al-Li), calcium (Ca), magnesium-indium (Mg-In), magnesium-silver (Mg-Ag), ITO, and IZO, but embodiments are not limited thereto. The second electrode 190 may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

[0210] The second electrode 190 may have a single-layered structure, or a multi-layered structure including two or more layers.

[0211] Referring to FIG. 2, an organic light-emitting device 20 has a first capping layer 210, the first electrode 110, the organic layer 150, and the second electrode 190 structure, wherein the layers are sequentially stacked in this stated order. Referring to FIG. 3, an organic light-emitting device 30 has the first electrode 110, the organic layer 150, the second electrode 190, and a second capping layer 220 structure, wherein the layers are sequentially stacked in this stated order. Referring to FIG. 4, an organic light-emitting device 40 has the first capping layer 210, the first electrode 110, the organic layer 150, the second electrode 190, and the second capping layer 220 structure, wherein the layers

are stacked in this stated order.

[0212] The first electrode 110, the organic layer 150, and the second electrode 190 illustrated in FIGS. 2 to 4 may be substantially the same as those illustrated in FIG. 1.

[0213] In the organic light-emitting devices 20 and 40, light emitted from the emission layer in the organic layer 150 may pass through the first electrode 110 (which may be a semi-transmissive electrode or a transmissive electrode) and through the first capping layer 210 to the outside. In the organic light-emitting devices 30 and 40, light emitted from the emission layer in the organic layer 150 may pass through the second electrode 190 (which may be a semi-transmissive electrode or a transmissive electrode) and through the second capping layer 220 to the outside.


[0214] The first capping layer 210 and the second capping layer 220 may improve the external luminescence efficiency based on the principle of constructive interference.

[0215] The first capping layer 210 and the second capping layer 220 may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

[0216] The first capping layer 210, the second capping layer 220, or both may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphine derivatives, phthalocyanine derivatives, naphthalocyanine derivatives, alkali metal complexes, and alkaline earth metal complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may optionally be substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one embodiment, at least one of the first capping layer 210 and the second capping layer 220 may each independently include an amine-based compound.

[0217] In one or more embodiments, at least one of the first capping layer 210 and the second capping layer 220 may each independently include a compound represented by Formula 201 or a compound represented by 202.

[0218] In one or more embodiments, at least one of the first capping layer 210 and the second capping layer 220 may each independently include a compound selected from Compounds HT28 to HT33 and Compound CP1 to CP5, but embodiments are not limited thereto:



[0219] Hereinbefore, the organic light-emitting device has been described with reference to FIGS. 1 to 4, but embodiments are not limited thereto.

[0220] The layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region may be formed in a specific region by using one or more suitable methods such as vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser printing, and laser-induced thermal imaging.

[0221] When the layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region are each formed by vacuum deposition, the vacuum deposition may be performed at a deposition temperature in a range of about 100°C to about 500°C at a vacuum degree in a range of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition rate in a range of about 0.01 Angstroms per second (Å/sec) to about 100 Å/sec, depending on

the material to be included in each layer and the structure of each layer to be formed.

[0222] When the layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region are each formed by spin coating, the spin coating may be performed at a coating rate of about 2,000 revolutions per minute (rpm) to about 5,000 rpm and at a heat treatment temperature of about 80°C to about 200°C, depending on the material to be included in each layer and the structure of each layer to be formed.

[0223] The term "C₁-C₆₀ alkyl group" as used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term "C₁-C₆₀ alkylene group" as used herein refers to a divalent group having substantially the same structure as the C₁-C₆₀ alkyl group. Corresponding definitions apply to other ranges given for the number of carbon atoms in an alkyl/alkylene group.

[0224] The term "C₂-C₆₀ alkenyl group" as used herein refers to a hydrocarbon group having at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group. Examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term "C₂-C₆₀ alkenylene group" as used herein refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkenyl group. Corresponding definitions apply to other ranges given for the number of carbon atoms in an alkenyl/alkenylene group.

[0225] The term "C₂-C₆₀ alkynyl group" as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group. Examples thereof include an ethynyl group and a propynyl group. The term "C₂-C₆₀ alkynylene group" as used herein refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkynyl group. Corresponding definitions apply to other ranges given for the number of carbon atoms in an alkynyl/alkynylene group.

[0226] The term "C₁-C₆₀ alkoxy group" as used herein refers to a monovalent group represented by -OA₁₀₁ (wherein A₁₀₁ is a C₁-C₆₀ alkyl group). Examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group. Corresponding definitions apply to other ranges given for the number of carbon atoms in an alkoxy group.

[0227] The term "C₃-C₁₀ cycloalkyl group" as used herein refers to a monovalent saturated hydrocarbon monocyclic group including 3 to 10 carbon atoms. Examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term "C₃-C₁₀ cycloalkylene group" as used herein refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkyl group.

[0228] The term "C₁-C₁₀ heterocycloalkyl group" as used herein refers to a monovalent monocyclic group including at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms. Examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuranyl group, and a tetrahydrothiophenyl group. The term "C₁-C₁₀ heterocycloalkylene group" as used herein refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkyl group.

[0229] The term "C₃-C₁₀ cycloalkenyl group" as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in its ring, and is not aromatic. Examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term "C₃-C₁₀ cycloalkenylene group" as used herein refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkenyl group.

[0230] The term "C₁-C₁₀ heterocycloalkenyl group" as used herein refers to a monovalent monocyclic group including at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Examples of the C₁-C₁₀ heterocycloalkenyl group include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranyl group, and a 2,3-dihydrothiophenyl group. The term "C₁-C₁₀ heterocycloalkylene group" as used herein refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0231] The term "C₆-C₆₀ aryl group" as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. The term "C₆-C₆₀ arylene group" as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each independently include two or more rings, the respective rings may be fused. Corresponding definitions apply to other ranges given for the number of carbon atoms in an aryl/arylene group.

[0232] The term "C₁-C₆₀ heteroaryl group" as used herein refers to a monovalent group having a heterocyclic aromatic system having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 60 carbon atoms. The term "C₁-C₆₀ heteroarylene group" as used herein refers to a divalent group having a heterocyclic aromatic system having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 60 carbon atoms. Examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each independently include two or more rings, the respective rings may be fused. Corresponding definitions apply to other ranges given for the number of carbon atoms in an heteroaryl/heteroarylene group.

[0233] The term "C₆-C₆₀ aryloxy group" as used herein refers to a group represented by -OA₁₀₂ (where A₁₀₂ is a C₆-C₆₀ aryl group). The term "C₆-C₆₀ arylthio group" as used herein refers to a group represented by -SA₁₀₃ (where A₁₀₃ is a

C₆-C₆₀ aryl group). Corresponding definitions apply to other ranges given for the number of carbon atoms in an aryloxy group and an arylthio group.

[0234] The term "monovalent non-aromatic condensed polycyclic group" as used herein refers to a monovalent group that has two or more rings condensed and only carbon atoms as ring forming atoms (e.g., 8 to 60 carbon atoms), wherein the entire molecular structure is non-aromatic. An example of the monovalent non-aromatic condensed polycyclic group may be a fluorenyl group. The term "divalent non-aromatic condensed polycyclic group" as used herein refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed polycyclic group.

[0235] The term "monovalent non-aromatic condensed heteropolycyclic group" as used herein refers to a monovalent group that has two or more condensed rings and at least one heteroatom selected from N, O, Si, P, and S, in addition to carbon atoms (e.g., 1 to 60 carbon atoms), as a ring-forming atom, wherein the entire molecular structure is non-aromatic. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. The term "divalent non-aromatic condensed heteropolycyclic group" as used herein refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0236] The term "C₅-C₆₀ carbocyclic group" as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms only as ring-forming atoms. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The term "C₅-C₆₀ carbocyclic group" as used herein refers to a ring (e.g., a benzene group), a monovalent group (e.g., a phenyl group), or a divalent group (e.g., a phenylene group). In one or more embodiments, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group. Corresponding definitions apply to other ranges given for the number of carbon atoms in a carbocyclic group.

[0237] The term "C₁-C₆₀ heterocyclic group" as used herein refers to a group having substantially the same structure as the C₅-C₆₀ carbocyclic group, except that at least one heteroatom selected from N, O, Si, P, and S is used as a ring-forming atom, in addition to carbon atoms (e.g., 1 to 60 carbon atoms). Corresponding definitions apply to other ranges given for the number of carbon atoms in a heterocyclic group.

[0238] In the present specification, at least one substituent of the substituted C₅-C₆₀ (e.g. C₆-C₃₀) carbocyclic group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ (e.g. C₆-C₃₂) arylene group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, the substituted C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, the substituted C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, the substituted C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, the substituted C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, the substituted C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, and a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group;

a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, and a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁₁)(Q₁₂)(Q₁₃), -N(Q₁₁)(Q₁₂), -B(Q₁₁)(Q₁₂), -C(=O)(Q₁₁), -S(=O)₂(Q₁₁), and -P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, a

C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryloxy group, a C₆-C₆₀ (e.g. C₆-C₃₀) arylthio group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₂₁)(Q₂₂)(Q₂₃), -N(Q₂₁)(Q₂₂), -B(Q₂₁)(Q₂₂), -C(=O)(Q₂₁), -S(=O)₂(Q₂₁), and -P(=O)(Q₂₁)(Q₂₂); and -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂), wherein Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkenyl group, a C₂-C₆₀ (e.g. C₂-C₂₀) alkynyl group, a C₁-C₆₀ (e.g. C₁-C₂₀) alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ (e.g. C₆-C₃₀) aryl group, a C₁-C₆₀ (e.g. C₁-C₂₀) heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0239] The term "Ph" as used herein represents a phenyl group. The term "Me" as used herein represents a methyl group. The term "Et" as used herein represents an ethyl group. The term "ter-Bu" or "Bu" as used herein represents a tert-butyl group. The term "OMe" as used herein represents a methoxy group.

[0240] The term "biphenyl group" as used herein refers to a phenyl group substituted with a phenyl group. In other words, the "biphenyl group" may be a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

[0241] The term "terphenyl group" as used herein refers to a phenyl group substituted with a biphenyl group. In other words, the "terphenyl group" may be a substituted phenyl group having a C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group as a substituent.

[0242] The symbols * and ** as used herein, unless defined otherwise, refer to a binding site to an adjacent atom in a corresponding formula.

[0243] Hereinafter the compound and the organic light-emitting device according to an embodiment will be described in detail with reference to Examples. The wording "B was used instead of A" used herein refers to that an identical number of molar equivalents of B was used in place of A.


Example 1

[0244] As for a substrate and an anode, a Corning 15 Ohms per square centimeter (Ω/cm^2) (120 nanometers (nm)) ITO glass substrate was cut to a size of 50 millimeters (mm)×50 mm×0.5 mm, sonicated by using acetone, isopropyl alcohol, and deionized water for 5 minutes, respectively, and cleaned by exposure to ultraviolet rays with ozone for 10 minutes. Then, the glass substrate was mounted on a vacuum deposition device.


[0245] Compound 301 was vacuum-deposited on the ITO anode to form a hole injection layer having a thickness of 600 Å, and 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (hereinafter, referred as "NPB") was deposited on the hole injection layer to form a hole transport layer having a thickness of 600 Å.

[0246] Compound A was deposited on the hole transport layer to a thickness of 550 Å to form an emission auxiliary layer.

[0247] Compounds 1-12 and 2-7 and a phosphorescent dopant (Ir(mppy)₂(acac)) were co-vacuum-deposited (at a weight ratio of 3%) on the emission auxiliary layer to form an emission layer having a thickness of 400 Å. Subsequently, Compound 101 and LiQ were deposited (at a ratio of 50:50) on the emission layer to form an electron transport layer having a thickness of 360 Å, LiQ was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Mg and Ag were co-vacuum-deposited (at a weight ratio of 10%) on the electron injection layer to form a cathode having a thickness of 130 Å, thereby completing the manufacture of an organic light-emitting device.




5



1-13


10



1-14


15

20



2-7


25




2-8

30

35

Ir(mppy)₂(acac)

40



101


45

Examples 2 and 3 and Comparative Examples 1 to 3

[0248] Organic light-emitting devices were manufactured in substantially the same manner as in Example 1, except that the compounds shown in Table 1 were used instead of Compound 1-12 and 2-7 as hosts in the formation of an emission layer.

55


5



10

Comparative Compound 1-1.


15



20

Comparative Compound 1-2.


25



30

Comparative Compound 1-3.

35



40

Comparative Compound 1-4.

Evaluation Example 1

45

[0249] The driving voltage, luminance, current efficiency, color-coordinate, emission color, and lifespan of the organic light-emitting devices of Examples 1 to 3 and Comparative Examples 1 to 3 were measured by using a Keithley 236 source-measure unit (SMU) and a PR650 spectroscan source measurement unit (available from PhotoResearch). The evaluation results are shown in Table 1.

50

55

Table 1

	Host material	Driving voltage (V)	Luminance (Cd/m ²)	Efficiency (Cd/A)	CIE color-coordinate		Emission color	Lifespan (T ₉₇) (hr)
					x	y		
Example 1	Compound 1-12	4.4	5000	19	0.223	0.725	green	330
Example 2	Compound 1-13	4.5	5000	18	0.224	0.724	green	450
Example 3	Compound 1-14	4.4	5000	20	0.223	0.725	green	350
Comparative Example 1	Comparative Compound 1-1	4.7	5000	16	0.224	0.724	green	50
Comparative Example 2	Comparative Compound 1-1	4.6	5000	17	0.223	0.725	green	130
Comparative Example 3	Comparative Compound 1-4	4.7	5000	17	0.224	0.725	green	150

[0250] According to Table 1, the organic light-emitting devices of Examples 1 to 3 were found to have a low-driving voltage, high efficiency, and a long lifespan, as compared with the organic light-emitting devices of Comparative Examples 1 to 3.

5 Evaluation Example 2

[0251] By using the host materials of each of Examples 1 to 3 and Comparative Examples 1 to 3, hole-only devices (HODs) 1 to 6 having a structure of ITO (1,500 Å)/ HT211 :NDP9 (1 wt%) (100 Å)/ HT211 (1,500 Å)/ host material (400 Å)/ L101 (100 Å)/ Yb (13 Å)/ Mg:Ag (10 wt%) (600 Å) and electron-only devices (EODs) 1 to 6 having a structure of ITO (1,500 Å)/ LiQ (100 Å)/ host material (400 Å)/ TPBi:LiQ (50 wt%) (360 Å)/ Yb (13 Å)/ Mg:Ag (10 wt%) (600 Å) were manufactured.

[0252] The compositions of the hosts in the HODs 1 to 6 and the EODs 1 to 6 are shown in Table 2.

[0253] Subsequently, V_{HOD} (at 10 mA/cm²) which is a driving voltage value (V) at a current density of 10 mA/cm² of HODs 1 to 3 and V_{EOD} (at 10 mA/cm²) which is a driving voltage value (V) at a current density of 10 mA/cm² of EODs 1 to 3 were measured by using current voltmeter (Keithley 2400). On the basis of the results, F_{CB} values were calculated, which are shown in Table 2.

Table 2

	Host material		Volumetric ratio in of the hosts	$V_{HOD}(@ 10 \text{ mA/cm}^2)$	$V_{EOD}(@ 10 \text{ mA/cm}^2)$	F_{CB}	Lifespan (T_{97}) (hours)
Example 1	Compound 1-12	Compound 2-7	8:2	(HOD 1) 1.05	(EOD 1) 4.00	3.8	330
Example 2	Compound 1-13	Compound 2-7	7:3	(HOD 2) 1.11	(EOD 2) 4.10	3.7	450
Example 3	Compound 1-14	Compound 2-8	7:3	(HOD 3) 1.30	(EOD 3) 3.90	3.0	350
Comparative Example 1	Comparative Compound 1-1	Comparative Compound 1-2	7:3	(HOD 4) 1.30	(EOD 4) 1.60	1.2	50
Comparative Example 2	Comparative Compound 1-1	Comparative Compound 1-3	7:3	(HOD 5) 1.05	(EOD 5) 3.00	2.8	130
Comparative Example 3	Comparative Compound 1-4	Comparative Compound 1-2	8:2	(HOD 6) 1.40	(EOD 6) 2.70	1.9	150

[0254] According to Table 2, it was found that the organic light-emitting devices of Examples 1 to 3 that satisfy Equation 1 have unexpected and surprisingly excellent lifespan characteristics, as compared with the organic light-emitting devices of Comparative Examples 1 to 3.

[0255] As described above, the organic light-emitting device according to embodiments of the invention may have a low-driving voltage, improved efficiency, and a long lifespan.

[0256] Although certain embodiments and implementations have been described herein, other embodiments and modifications will be apparent from this description. Accordingly, the inventive concepts are not limited to such embodiments, but rather to the broader scope of the appended claims and various obvious modifications and equivalent arrangements as would be apparent to a person of ordinary skill in the art.

50 **Claims**

1. An organic light-emitting device comprising:

a first electrode;

a second electrode; and

an emission layer disposed between the first electrode and the second electrode, wherein the emission layer comprises a host material, wherein the organic light-emitting device satisfies Equation 1:

<Equation 1>

$$F_{CB} > 2.8$$

wherein F_{CB} is defined by Equation 2:


<Equation 2>

$$F_{CB} = V_{EOD} \text{ (at } 10 \text{ mA/cm}^2\text{)} / V_{HOD} \text{ (at } 10 \text{ mA/cm}^2\text{)}$$


wherein, in Formula 2,

V_{HOD} (at 10 mA/cm²) is a driving voltage (volts, V) at a current density of 10 mA/cm² of a hole-only device having a structure of ITO (1,500 Angstroms (Å))/ HT211:NDP9 (1 percent by weight (wt%)) (100 Å)/ HT211 (1,500 Å)/ the host material (400 Å)/ L101 (100 Å)/ Yb(13 Å)/ Mg:Ag (10 wt%)(600 Å), and


V_{EOD} (at 10 mA/cm²) is a driving voltage (V) at a current density of 10 mA/cm² of an electron-only device having a structure of ITO (1,500 Å)/ LiQ (100 Å)/ the host material (400 Å)/ TPBi:LiQ (50 wt%) (360 Å)/ Yb (13 Å)/ Mg:Ag (10 wt%) (600 Å):




HT211




NDP9



L101



TPBi



LiQ

2. An organic light-emitting device according to claim 1, wherein the organic light-emitting device satisfies Equation 3-1:

<Equation 3-1>


$$2.9 \leq F_{CB} \leq 50.$$

3. An organic light-emitting device according to claim 1 or claim 2, wherein the host material comprises one type of host or a combination of at least two types of host.
4. An organic light-emitting device according to any one of claims 1 to 3, wherein the host material comprises at least one host selected from a hole transporting host, an electron transporting host, and a bipolar host,


wherein the hole transporting host is an amine-based compound comprising a hole transporting unit,
 wherein the electron transporting host comprises an electron transporting unit, and
 wherein the bipolar host comprises the hole transporting unit and the electron transporting unit.

- 5 5. An organic light-emitting device according to claim 4, wherein the hole transporting unit is selected from a fluorene group, a carbazole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, a dibenzosilole group, an indenocarbazole group, an indolocarbazole group, a benzoindolocarbazole group, a benzofurocarbazole group, a benzothienocarbazole group, and a benzosilolocarbazole group, and
 10 wherein the electron transporting unit is selected from an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group.
- 15 6. An organic light-emitting device according to any one of claims 1 to 5, wherein the host material comprises at least one compound selected from a compound represented by Formula 1 and a compound represented by Formula 2:

20 <Formula 1>



30 <Formula 2>



wherein, in Formulae 1 and 2,

Ar₁₀ is a C₁-C₆₀ heterocyclic group comprising at least one π electron-depleted nitrogen-containing ring,
 L₁₀, L₂₀, L₃₀, and L₄₀ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a₁₀, a₂₀, a₃₀, and a₄₀ are each independently an integer from 0 to 5,

when a₁₀ is 2 or greater, at least two L₁₀(s) are identical to or different from each other,

when a₂₀ is 2 or greater, at least two L₂₀(s) are identical to or different from each other,

when a₃₀ is 2 or greater, at least two L₃₀(s) are identical to or different from each other,

when a₄₀ is 2 or greater, at least two L₄₀(s) are identical to or different from each other,

R₁₀, R₂₀, R₃₀, R₄₀, and R₅₀ are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

-Si(Q₁)(Q₂)(Q₃), -N(Q₁)(Q₂), -B(Q₁)(Q₂), -C(=O)(Q₁), -S(=O)₂(Q₁), and -P(=O)(Q₁)(Q₂),
 b₁₀, b₂₀, b₃₀, b₄₀, and b₅₀ are each independently an integer from 1 to 10,
 when b₁₀ is 2 or greater, at least two R₁₀(s) are identical to or different from each other,
 when b₂₀ is 2 or greater, at least two R₂₀(s) are identical to or different from each other,
 when b₃₀ is 2 or greater, at least two R₃₀(s) are identical to or different from each other,
 when b₄₀ is 2 or greater, at least two R₄₀(s) are identical to or different from each other,
 when b₅₀ is 2 or greater, at least two R₅₀(s) are identical to or different from each other,
 c₄₀ is an integer from 1 to 4,

when c₄₀ is 2 or greater, at least two -(L₄₀)_{a40}-(R₄₀)_{b40}(s) are identical to or different from each other, and
 at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene
 group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the
 substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-
 aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group,
 the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group,
 the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocy-
 cloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the
 substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the
 substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and
 the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino
 group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a
 C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each
 substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a
 nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀
 heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl
 group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-
 aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group,

-Si(Q₁₁)(Q₁₂)(Q₁₃), -N(Q₁₁)(Q₁₂), -B(Q₁₁)(Q₁₂), -C(=O)(Q₁₁), -S(=O)₂(Q₁₁), and -P(=O)(Q₁₁)(Q₁₂);


a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ hete-
 rocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀
 heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic
 condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ hete-
 rocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀
 heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic
 condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least
 one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino
 group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀
 alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀
 cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a
 C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group,
 a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group,


-Si(Q₂₁)(Q₂₂)(Q₂₃), -N(Q₂₁)(Q₂₂), -B(Q₂₁)(Q₂₂), -C(=O)(Q₂₁), -S(=O)₂(Q₂₁), and -P(=O)(Q₂₁)(Q₂₂); and
 -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂),

wherein Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, Q₃₁ to Q₃₃, and Q₄₁ to Q₄₃ are each independently selected from
 hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a
 hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a
 C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group,
 a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic
 condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group,
 and a terphenyl group.


7. An organic light-emitting device according to claim 6, wherein at least one selected from R₁₀, R₂₀, and R₃₀ and at
 least one selected from R₄₀ and R₅₀ each independently comprise a partial structure represented by one of Formulae
 4-1 to 4-15:




4-1




4-2




4-3




4-4



4-5




4-6




4-7




4-8




4-9




4-10




4-11




4-12



4-13



4-14



4-15

wherein, in Formulae 4-1 to 4-15,

Y_{11} is selected from $C(R_1)(R_2)$, $N(R_1)$, O, and S,

Y_{12} is selected from $C(R_3)(R_4)$, $N(R_3)$, O, and S,

R_1 to R_4 are each independently selected from a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, and -I;


a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a benzofuopyrimidinyl group, and a benzothienopyrimidinyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a benzofuopyrimidinyl group, and a benzothienopyrimidinyl group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a methoxy group, an ethoxy group, an n-propoxy group, an iso-propoxy group, an n-butoxy group, an iso-butoxy group, a sec-butoxy group, a tert-butoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a benzofuopyrimidinyl group, and a benzothienopyrimidinyl group, and any carbon atom or any nitrogen atom in the partial structure represented by any one of Formulae 4-1 to 4-15


is a binding site to an adjacent atom.

8. An organic light-emitting device according to claim 6 or claim 7, wherein the compound represented by Formula 1 is a compound represented by Formula 3A, 3B, or 3C, and the compound represented by Formula 2 is a compound represented by Formula 4:


<Formula 3A>



<Formula 3B>




<Formula 3C>



<Formula 4>

5

10



15

wherein, in Formulae 3A, 3B, 3C, and 4,

A₁₀, A₂₀, and A₄₀ are each independently selected from a benzene group, a naphthalene group, a fluorene group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, an indoline group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a dibenzofuran group, and a dibenzothiophene group,

20

Y₂₁ is selected from -O-, -S-, -N(R₂₁)-, -C(R₂₁)(R₂₂)-, and -Si(R₂₁)(R₂₂)-,

X₁₁, X₁₂, X₁₃, and X₁₄ are each independently N or C(R₁₃),

X₂₁, X₂₂, X₂₃, and X₂₄ are each independently N or C(R₂₄),

X₄₁, X₄₂, X₄₃, and X₄₄ are each independently N or C(R₄₂),

25

X₅₁, X₅₂, X₅₃, X₅₄, and X₅₅ are each independently N or C(R₅₁),

at least one selected from X₅₁, X₅₂, X₅₃, X₅₄, and X₅₅ is N,

L₁₁ is defined the same as L₁₀ in claim 6,

L₂₁ is defined the same as L₂₀ in claim 6,

L₄₁ is defined the same as L₄₀ in claim 6,

a₁₁ is an integer from 0 to 5,

30

a₂₁ is an integer from 0 to 5,

a₄₁ is an integer from 0 to 5,

R₁₁, R₁₂, and R₁₃ are each defined the same as R₁₀ in claim 6,

R₂₁, R₂₂, R₂₃, and R₂₄ are each defined the same as R₂₀ in claim 6,

R₃₁ is defined the same as R₃₀ in claim 6,

35

R₄₁ and R₄₂ are each defined the same as R₄₀ in claim 6,


R₅₁ is defined the same as R₅₀ in claim 6, and

b₁₂, b₂₃, and b₄₁ are each independently an integer from 1 to 8.

9. An organic light-emitting device according to any one of claims 1 to 8, wherein the emission layer further comprises a dopant material, and a content of the host material is greater than that of the dopant material, wherein the emission layer is preferably a phosphorescent emission layer and further comprises a phosphorescent dopant, wherein the dopant material is preferably represented by Formula 401:

40

<Formula 401>



45

<Formula 402>


50

55

5

10

15



20

25

30

35

40

45

wherein, in Formulae 401 and 402,

M is selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

L_{401} is selected from ligands represented by Formula 402, xc1 is an integer from 1 to 3; and when xc1 is 2 or greater, at least two $L_{401}(s)$ are identical to or different from each other,

L_{402} is an organic ligand, xc2 is an integer from 0 to 4; and when xc2 is 2 or greater, at least two $L_{402}(s)$ are identical to or different from each other,

X_{401} to X_{404} are each independently N or C,

X_{401} and X_{403} are linked via a single bond or a double bond, X_{402} and X_{404} are linked via a single bond or a double bond,

A_{401} and A_{402} are each independently a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

X_{405} is a single bond, $^*-O-^*$, $^*-S-^*$, $^*-C(=O)-^*$, $^*-N(Q_{411})-^*$, $^*-C(Q_{411})(Q_{412})-^*$, $^*-C(Q_{411})=C(Q_{412})-^*$, $^*-C(Q_{411})=^*$, or $^*=C=^*$, wherein Q_{411} and Q_{412} are each independently selected from hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

X_{406} is a single bond, O, or S,

R_{401} and R_{402} are each independently selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$, wherein Q_{401} to Q_{403} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group, xc11 and xc12 are each independently an integer from 0 to 10,

* and ** in X_{405} each indicate a binding site to either X_{404} or X_{403} in Formula 402, and

* in Formula 402 indicates a binding site to M in Formula 401.

10. An organic light-emitting device according to any one of claims 1 to 9, wherein the first electrode is an anode, wherein the second electrode is a cathode, wherein the organic light-emitting device comprises a hole transport region between the first electrode and the emission layer; and an electron transport region between the emission layer and the second electrode, wherein the hole transport region comprises at least one selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer, and wherein the electron transport region comprises at least one selected from a buffer layer, a hole blocking layer, an electron transport layer, and an electron injection layer.
11. An organic light-emitting device according to claim 10, wherein the hole transport region comprises a hole transporting host, and the electron transport region comprises an electron transporting host.

- 5
12. An organic light-emitting device according to claim 10 or claim 11, wherein the hole transport region comprises the hole transport layer and the emission auxiliary layer, wherein the emission auxiliary layer is between the hole transport layer and the emission layer, wherein the emission auxiliary layer comprises an amine-based compound, and wherein the emission auxiliary layer is preferably in direct contact with the emission layer.
- 10
13. An organic light-emitting device according to any one of claims 10 to 12, wherein the electron transport region further comprises a metal-containing material.
- 15
14. An organic light-emitting device according to any one of claims 10 to 13, wherein the electron transport region comprises the electron injection layer, and the electron injection layer is in direct contact with the second electrode, wherein the electron transport region preferably comprises the electron injection layer, and the electron injection layer comprises at least one of an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth metal complex, and a rare earth metal complex.
- 20
15. An organic light-emitting device according to any one of claims 1 to 14, wherein the emission layer is a first color light-emitting layer emitting first color light, wherein the organic light-emitting device further comprises at least one second color light-emitting layer emitting second color light between the first electrode and the second electrode, wherein a maximum emission wavelength of the first color light and a maximum emission wavelength of the second color light are identical to or different from each other, and wherein the first color light and the second color light are emitted in the form of mixed light.
- 25
16. An organic light-emitting device according to any one of claims 1 to 15, wherein the emission layer is a first color light-emitting layer emitting first color light, wherein the organic light-emitting device further comprises at least one second color light-emitting layer emitting second color light and at least one third color light-emitting layer emitting third color light between the first electrode and the second electrode, wherein a maximum emission wavelength of the first color light, a maximum emission wavelength of the second color light, and a maximum emission wavelength of the third color light are identical to or different from each other, and wherein the first color light, the second color light, and the third color light are emitted in the form of mixed light.
- 30
17. A display apparatus comprising a thin-film transistor comprising a source electrode, a drain electrode, and an active layer; and the organic light-emitting device according to any one of claims 1 to 16, wherein the first electrode of the organic light-emitting device is electrically connected to the source electrode or the drain electrode of the thin-film transistor.
- 35
- 40
- 45
- 50
- 55

FIG. 1

10

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3

30

220
190
150
110

FIG. 4

40

220
190
150
110
210



EUROPEAN SEARCH REPORT

Application Number
EP 19 15 6553

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	EP 3 185 325 A1 (SAMSUNG DISPLAY CO LTD [KR]) 28 June 2017 (2017-06-28) * page 51 - page 50 * * paragraph [0243] - paragraph [0258]; claim 15; table 7 * * paragraph [0137] - paragraph [0144] * -----	1-17	INV. H01L51/00
X	WO 2017/183859 A1 (ROHM & HAAS ELECT MATERIALS KOREA LTD [KR]) 26 October 2017 (2017-10-26) * paragraph [0061] - paragraph [0249]; tables 1-3 * -----	1-17	
X	WO 2015/178732 A1 (ROHM & HAAS ELECT MATERIALS [KR]) 26 November 2015 (2015-11-26) * paragraph [0022] - paragraph [0254]; tables 1,2 * -----	1-17	
			TECHNICAL FIELDS SEARCHED (IPC)
			H01L
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 13 June 2019	Examiner Konráðsson, Ásgeir
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

1
EPO FORM 1503 03/02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 19 15 6553

5 This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-06-2019

10	Patent document cited in search report	Publication date	Patent family member(s)	Publication date
15	EP 3185325 A1	28-06-2017	CN 106905955 A EP 3185325 A1 KR 20170075118 A US 2017179401 A1	30-06-2017 28-06-2017 03-07-2017 22-06-2017

	WO 2017183859 A1	26-10-2017	NONE	

20	WO 2015178732 A1	26-11-2015	NONE	

25				
30				
35				
40				
45				
50				
55				

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

专利名称(译)	有机发光装置和包括有机发光装置的显示装置		
公开(公告)号	EP3525253A1	公开(公告)日	2019-08-14
申请号	EP2019156553	申请日	2019-02-11
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SEO JIHYUN KIM MIKYUNG YANG SEUNGGAK LEE KWANHEE		
发明人	SEO, JIHYUN KIM, MIKYUNG YANG, SEUNGGAK LEE, KWANHEE		
IPC分类号	H01L51/00		
CPC分类号	H01L27/3244 H01L51/0052 H01L51/0058 H01L51/0059 H01L51/006 H01L51/0072 H01L51/5012 H01L51/5024 H01L51/0067 H01L51/5016 H01L2251/5384		
优先权	1020180018060 2018-02-13 KR 1020180116586 2018-09-28 KR		
外部链接	Espacenet		

摘要(译)

有机发光装置和包括该有机发光装置的显示装置包括发光层，该发光层具有一种或多种具有出乎意料的低驱动电压，高效率 and 长寿命的主体材料。

FIG. 1

10

190
150
110