



(11)

EP 1 821 354 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
09.11.2016 Bulletin 2016/45

(51) Int Cl.:
H01L 27/32 (2006.01) **H01L 51/52 (2006.01)**
H01L 51/00 (2006.01) **H01L 51/56 (2006.01)**

(21) Application number: **07250691.8**(22) Date of filing: **20.02.2007**(54) **Organic light emitting display and method of fabricating the same**

Organische lichtemittierende Anzeigevorrichtung und Verfahren zu ihrer Herstellung

Dispositif d'affichage électroluminescent organique et son procédé de fabrication

(84) Designated Contracting States:
DE ES FR GB HU IT

- Song, Seung Yong,**
c/o Samsung SDI Co., Ltd
Yongin-si
Gyeonggi-do (KR)
- Choi, Young Seo,**
c/o Samsung SDI Co., Ltd
Yongin-si
Gyeonggi-do (KR)

(30) Priority: **20.02.2006 KR 20060016480**
19.04.2006 KR 20060035456

(74) Representative: **Mounteney, Simon James**
Marks & Clerk LLP
90 Long Acre
London
WC2E 9RA (GB)

(43) Date of publication of application:
22.08.2007 Bulletin 2007/34

(56) References cited:
JP-A- 2001 118 680 **JP-A- 2004 280 759**
JP-A- 2006 031 256 **US-A- 4 192 060**
US-A1- 2001 013 756 **US-A1- 2003 107 315**
US-A1- 2004 207 314 **US-A1- 2005 046 338**

(73) Proprietor: **Samsung Display Co., Ltd.**
Gyeonggi-do (KR)

(72) Inventors:

- Zu, Young Cheol,**
c/o Samsung SDI Co., Ltd
Yongin-si
Gyeonggi-do (KR)
- Park, Jin-Woo,**
c/o Samsung SDI Co., Ltd
Suwon-si
Gyeonggi-do (KR)
- Lee, Jae Sun,**
c/o Samsung SDI Co., Ltd
Yongin-si
Gyeonggi-do (KR)

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**BACKGROUND OF THE INVENTION****1. Field of the Invention**

[0001] The present invention relates to an organic light emitting display and a method of fabricating the same, and more particularly, to an organic light emitting display in which differential pressure is controlled to prevent Newton's rings from being generated and a method of fabricating the same.

2. Description of the Related Technology

[0002] Recently, organic light emitting displays have been widely used due to their relatively simple structure. The organic light emitting display is a self-emission display in which an organic layer is used as an emission layer. Since the organic light emitting display does not need a back-light for emitting light unlike a liquid crystal display (LCD), the thickness and weight of the organic light emitting display are small. Therefore, the organic light emitting display has been actively developed as a display panel for portable electronic devices such as portable computers, mobile telephones, portable game apparatus, and electronic books.

[0003] In an organic light emitting display, one or more organic layers including an emission layer are interposed between first electrodes and second electrodes. The first electrodes are formed on a substrate and function as anodes for injecting holes. The organic layers are formed on the first electrodes. Second electrodes that function as cathodes for injecting electrons are formed on the organic layers to face the first electrodes.

[0004] When moisture and oxygen are permeated from the outside to organic light emitting diodes (OLED) in the organic light emitting display, the electrodes are oxidized and separated from each other. In such a case, the life of the OLEDs is reduced, and emission efficiency deteriorates. In addition, emission colors may change.

[0005] Therefore, in the fabrication of the organic light emitting display, a sealing process for protecting the OLEDs from the outside may be performed. In one method, a polymer such as polyethyleneteraphthalate (PET) may be laminated on the cathodes of the OLEDs. In another method, a cover or a cap formed of a metal or glass includes an absorbent. In addition, a nitrogen gas may be filled in the cover or the cap. The edges of the cover or the cap may be capsule sealed by a sealant such as an epoxy resin.

[0006] However, since it is not possible to completely prevent moisture and oxygen from permeating into the OLEDs from the outside by the above-described methods, the OLEDs may deteriorate and change.

[0007] In order to solve the above problem, a capsule sealing up method has been proposed in which a frit is used as a sealing material in order to improve a moisture-

proof property between an element substrate and a cap. In this vein, U.S. Patent Publication No. 20040207314 discloses coating a glass substrate with a frit to seal up an OLED. Since a gap between a first substrate and a second substrate is completely sealed up using the frit, it is possible to protect the OLED effectively in the disclosed structures.

[0008] In such structures where the OLED is sealed up using a sealing substrate coated with the frit, the distance between the substrate and the sealing substrate is smaller than the distance between the substrate and the sealing substrate in a structure where an absorbent is used. Also, in manufacturing an organic light emitting display sealed with frit, a plurality of display panels are simultaneously fabricated on a mother substrate. In such a case, the mother substrate is typically cut into individual unit display panels. The center of the substrate curves down due to the weight of the substrate.

[0009] In such an OLED, light incident on the substrate from the outside generates optical interference to form concentric rings at connection points of the sealing substrate. These concentric rings are referred to as Newton's rings. The phenomenon of Newton's rings is an interference pattern caused by the reflection of light between two surfaces: a spherical surface and an adjacent flat surface. It appears as a series of concentric, alternating light and dark rings centered at the point of contact between the two surfaces. The Newton's rings deteriorate the quality of an image during the operation of OLEDs.

[0010] Documents US 2001/013756, US 4 192 060 A, JP 2001 118680 A, US 2005/046338 A1, US 2003/107315 A1, JP 2006 031256 A, JP 2004 280759 A and US 2004/207314 A1 disclose displays bent outward or related to the problem of Newton's rings.

SUMMARY OF CERTAIN INVENTIVE ASPECTS

[0011] The present invention sets out to solve the above problems and accordingly provides an organic light emitting display device as set out in claim 1 and a method of making an organic light emitting display device as set out in claim 8.

[0012] Preferred features of the invention are set out in claims 2 to 7 and 9 to 13.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] Embodiments of the invention will be described by way of example and with reference to the accompanying drawings in which:

FIG. 1 is a schematic cross-sectional view illustrating an organic light emitting display according to a first embodiment of the invention;

FIGs. 2A to 2E are schematic cross-sectional views illustrating a method of fabricating the organic light emitting display of FIG. 1;

FIG. 3 is a schematic cross-sectional view illustrating

the angle of the curvature of the second substrate according to the first embodiment;

FIG. 4 is a schematic cross-sectional view illustrating an organic light emitting display according to a second embodiment not forming part of the present invention;

FIGS. 5A to 5E are schematic cross-sectional views illustrating a method of fabricating the organic light emitting display of FIG. 4;

FIG. 6 is a schematic cross-sectional view illustrating the angle of the curvature of the second substrate according to the second embodiment;

FIG. 7A is a schematic exploded view of a passive matrix type organic light emitting display device;

FIG. 7B is a schematic exploded view of an active matrix type organic light emitting display device;

FIG. 7C is a schematic top plan view of an organic light emitting display device;

FIG. 7D is a cross-sectional view of the organic light emitting display device of FIG. 7C, taken along the line d-d; and

FIG. 7E is a schematic perspective view illustrating mass production of organic light emitting devices.

DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

[0014] An organic light emitting display (OLED) is a display device comprising an array of organic light emitting diodes. Organic light emitting diodes are solid state devices which include an organic material and are adapted to generate and emit light when appropriate electrical potentials are applied.

[0015] OLEDs can be generally grouped into two basic types dependent on the arrangement with which the stimulating electrical current is provided. Fig. 7A schematically illustrates an exploded view of a simplified structure of a passive matrix type OLED 1000. Fig. 7B schematically illustrates a simplified structure of an active matrix type OLED 1001. In both configurations, the OLED 1000, 1001 includes OLED pixels built over a substrate 1002, and the OLED pixels include an anode 1004, a cathode 1006 and an organic layer 1010. When an appropriate electrical current is applied to the anode 1004, electric current flows through the pixels and visible light is emitted from the organic layer.

[0016] Referring to Fig. 7A, the passive matrix OLED (PMOLED) design includes elongate strips of anode 1004 arranged generally perpendicular to elongate strips of cathode 1006 with organic layers interposed therebetween. The intersections of the strips of cathode 1006 and anode 1004 define individual OLED pixels where light is generated and emitted upon appropriate excitation of the corresponding strips of anode 1004 and cathode 1006. PMOLEDs provide the advantage of relatively simple fabrication.

[0017] Referring to Fig. 7B, the active matrix OLED (AMOLED) includes driving circuits 1012 arranged be-

tween the substrate 1002 and an array of OLED pixels. An individual pixel of AMOLEDs is defined between the common cathode 1006 and an anode 1004, which is electrically isolated from other anodes. Each driving circuit 5 1012 is coupled with an anode 1004 of the OLED pixels and further coupled with a data line 1016 and a scan line 1018. The scan lines 1018 supply scan signals that select rows of the driving circuits, and the data lines 1016 supply data signals for particular driving circuits. The data signals and scan signals stimulate the local driving circuits 1012, which excite the anodes 1004 so as to emit light 10 from their corresponding pixels.

[0018] In the illustrated AMOLED, the local driving circuits 1012, the data lines 1016 and scan lines 1018 are 15 buried in a planarization layer 1014, which is interposed between the pixel array and the substrate 1002. The planarization layer 1014 provides a planar top surface on which the organic light emitting pixel array is formed. The planarization layer 1014 may be formed of organic 20 or inorganic materials, and formed of two or more layers although shown as a single layer. The local driving circuits 1012 are typically formed with thin film transistors (TFT) and arranged in a grid or array under the OLED pixel array. The local driving circuits 1012 may be at least 25 partly made of organic materials, including organic TFT. AMOLEDs have the advantage of fast response time improving their desirability for use in displaying data signals. Also, AMOLEDs have the advantages of consuming less power than passive matrix OLEDs.

[0019] Referring to common features of the PMOLED and AMOLED designs, the substrate 1002 provides structural support for the OLED pixels and circuits. The substrate 1002 can comprise rigid or flexible materials 30 as well as opaque or transparent materials, such as plastic, glass, and/or foil. As noted above, each OLED pixel or diode is formed with the anode 1004, cathode 1006 and organic layer 1010 interposed therebetween. When an appropriate electrical current is applied to the anode 1004, the cathode 1006 injects electrons and the anode 40 1004 injects holes. In certain cases, the anode 1004 and cathode 1006 are inverted; i.e., the cathode is formed on the substrate 1002 and the anode is opposingly arranged.

[0020] Interposed between the cathode 1006 and anode 1004 are one or more organic layers. More specifically, at least one emissive or light emitting layer is interposed between the cathode 1006 and anode 1004. The light emitting layer may comprise one or more light emitting organic compounds. Typically, the light emitting layer 50 is configured to emit visible light in a single color such as blue, green, red or white. In the illustrated st, one organic layer 1010 is formed between the cathode 1006 and anode 1004 and acts as a light emitting layer. Additional layers, which can be formed between the anode 1004 and cathode 1006, can include a hole transporting layer, a hole injection layer, an electron transporting layer and an electron injection layer.

[0021] Hole transporting and/or injection layers can be

interposed between the light emitting layer 1010 and the anode 1004. Electron transporting and/or injecting layers can be interposed between the cathode 1006 and the light emitting layer 1010. The electron injection layer facilitates injection of electrons from the cathode 1006 toward the light emitting layer 1010 by reducing the work function for injecting electrons from the cathode 1006. Similarly, the hole injection layer facilitates injection of holes from the anode 1004 toward the light emitting layer 1010. The hole and electron transporting layers facilitate movement of the carriers injected from the respective electrodes toward the light emitting layer.

[0022] In some cases, a single layer may serve both electron injection and transportation functions or both hole injection and transportation functions. In some cases, one or more of these layers are lacking. In some structures, one or more organic layers are doped with one or more materials that help injection and/or transportation of the carriers. In structures where only one organic layer is formed between the cathode and anode, the organic layer may include not only an organic light emitting compound but also certain functional materials that help injection or transportation of carriers within that layer.

[0023] There are numerous organic materials that have been developed for use in these layers including the light emitting layer. Also, numerous other organic materials for use in these layers are being developed. In some cases, these organic materials may be macromolecules including oligomers and polymers. In some cases, the organic materials for these layers may be relatively small molecules. The skilled artisan will be able to select appropriate materials for each of these layers in view of the desired functions of the individual layers and the materials for the neighboring layers in particular designs.

[0024] In operation, an electrical circuit provides appropriate potential between the cathode 1006 and anode 1004. This results in an electrical current flowing from the anode 1004 to the cathode 1006 via the interposed organic layer(s). The cathode 1006 provides electrons to the adjacent organic layer 1010. The anode 1004 injects holes to the organic layer 1010. The holes and electrons recombine in the organic layer 1010 and generate energy particles called "excitons." The excitons transfer their energy to the organic light emitting material in the organic layer 1010, and the energy is used to emit visible light from the organic light emitting material. The spectral characteristics of light generated and emitted by the OLED 1000, 1001 depend on the nature and composition of organic molecules in the organic layer(s). The composition of the one or more organic layers can be selected to suit the needs of a particular application by one of ordinary skill in the art.

[0025] OLED devices can also be categorized based on the direction of the light emission. In one type referred to as "top emission" type, OLED devices emit light and display images through the cathode or top electrode 1006. In these devices, the cathode 1006 is made of a material transparent or at least partially transparent with

respect to visible light. In certain cases, to avoid losing any light that can pass through the anode or bottom electrode 1004, the anode may be made of a material substantially reflective of the visible light. A second type of

5 OLED devices emits light through the anode or bottom electrode 1004 and is called "bottom emission" type. In the bottom emission type OLED devices, the anode 1004 is made of a material which is at least partially transparent with respect to visible light. Often, in bottom emission 10 type OLED devices, the cathode 1006 is made of a material substantially reflective of the visible light. A third type of OLED devices emits light in two directions, e.g. 15 through both anode 1004 and cathode 1006. Depending upon the direction(s) of the light emission, the substrate may be formed of a material which is transparent, opaque or reflective of visible light.

[0026] Typically an OLED pixel array 1021 comprising a plurality of organic light emitting pixels is arranged over a substrate 1002 as shown in Fig. 7C. The pixels in the 20 array 1021 are controlled to be turned on and off by a driving circuit (not shown), and the plurality of the pixels as a whole displays information or image on the array 1021. In certain cases, the OLED pixel array 1021 is arranged with respect to other components, such as drive 25 and control electronics to define a display region and a non-display region. In these devices, the display region refers to the area of the substrate 1002 where OLED pixel array 1021 is formed. The non-display region refers to the remaining areas of the substrate 1002. The non- 30 display region can contain logic and/or power supply circuitry. It will be understood that there will be at least portions of control/drive circuit elements arranged within the display region. For example, in PMOLEDs, conductive components will extend into the display region to provide appropriate potential to the anode and cathodes. In 35 AMOLEDs, local driving circuits and data/scan lines coupled with the driving circuits will extend into the display region to drive and control the individual pixels of the AMOLEDs.

[0027] One design and fabrication consideration in 40 OLED devices is that certain organic material layers of OLED devices can suffer damage or accelerated deterioration from exposure to water, oxygen or other harmful gases. Accordingly, it is generally understood that OLED

45 devices be sealed or encapsulated to inhibit exposure to moisture and oxygen or other harmful gases found in a manufacturing or operational environment. Fig. 7D schematically illustrates a cross-section of an encapsulated 50 OLED device 1011 having a layout of Fig. 7C and taken along the line d-d of Fig. 7C. In this structure, a generally planar top plate or substrate 1061 engages with a seal 1071 which further engages with a bottom plate or substrate 1002 to enclose or encapsulate the OLED pixel array 1021. In other cases, one or more layers are formed 55 on the top plate 1061 or bottom plate 1002, and the seal 1071 is coupled with the bottom or top substrate 1002, 1061 via such a layer. In the illustrated device, the seal 1071 extends along the periphery of the OLED pixel array

1021 or the bottom or top plate 1002, 1061.

[0028] The seal 1071 is made of a frit material as will be further discussed below. In various structures, the top and bottom plates 1061, 1002 comprise materials such as plastics, glass and/or metal foils which can provide a barrier to passage of oxygen and/or water to thereby protect the OLED pixel array 1021 from exposure to these substances. At least one of the top plate 1061 and the bottom plate 1002 are formed of a substantially transparent material.

[0029] To lengthen the life time of OLED devices 1011, it is generally desired that seal 1071 and the top and bottom plates 1061, 1002 provide a substantially non-permeable seal to oxygen and water vapor and provide a substantially hermetically enclosed space 1081. In certain applications, it is indicated that the seal 1071 of a frit material in combination with the top and bottom plates 1061, 1002 provide a barrier to oxygen of less than approximately 10^{-3} cc/m²-day and to water of less than 10^{-6} g/m²-day. Given that some oxygen and moisture can permeate into the enclosed space 1081, in some cases, a material that can take up oxygen and/or moisture is formed within the enclosed space 1081.

[0030] The seal 1071 has a width W, which is its thickness in a direction parallel to a surface of the top or bottom substrate 1061, 1002 as shown in Fig. 7D. The width varies among devices and ranges from about 300 μ m to about 3000 μ m, optionally from about 500 μ m to about 1500 μ m. Also, the width may vary at different positions of the seal 1071. In some devices, the width of the seal 1071 may be the largest where the seal 1071 contacts one of the bottom and top substrate 1002, 1061 or a layer formed thereon. The width may be the smallest where the seal 1071 contacts the other. The width variation in a single cross-section of the seal 1071 relates to the cross-sectional shape of the seal 1071 and other design parameters.

[0031] The seal 1071 has a height H, which is its thickness in a direction perpendicular to a surface of the top or bottom substrate 1061, 1002 as shown in Fig. 7D. The height varies among structures and ranges from about 2 μ m to about 30 μ m, optionally from about 10 μ m to about 15 μ m. Generally, the height does not significantly vary at different positions of the seal 1071. However, in certain cases, the height of the seal 1071 may vary at different positions thereof.

[0032] In the illustrated device, the seal 1071 has a generally rectangular cross-section. In other structures, however, the seal 1071 can have other various cross-sectional shapes such as a generally square cross-section, a generally trapezoidal cross-section, a cross-section with one or more rounded edges, or other configuration as indicated by the needs of a given application. To improve hermeticity, it is generally desired to increase the interfacial area where the seal 1071 directly contacts the bottom or top substrate 1002, 1061 or a layer formed thereon. The shape of the seal can be designed such that the interfacial area can be increased.

[0033] The seal 1071 can be arranged immediately adjacent the OLED array 1021, and in other cases, the seal 1071 is spaced some distance from the OLED array 1021. In certain cases, the seal 1071 comprises generally

5 linear segments that are connected together to surround the OLED array 1021. Such linear segments of the seal 1071 can extend, in certain cases, generally parallel to respective boundaries of the OLED array 1021. In other cases, one or more of the linear segments of the seal 1071 are arranged in a non-parallel relationship with respective boundaries of the OLED array 1021. In yet other cases, at least part of the seal 1071 extends between the top plate 1061 and bottom plate 1002 in a curvilinear manner.

[0034] As noted above, in certain cases, the seal 1071 is formed using a frit material or simply "frit" or glass frit," which includes fine glass particles. The frit particles includes one or more of magnesium oxide (MgO), calcium oxide (CaO), barium oxide (BaO), lithium oxide (Li₂O)

20 sodium oxide (Na₂O) potassium oxide (K₂O) boron oxide (B₂O₃), vanadium oxide (V₂O₅), zinc oxide (ZnO), tellurium oxide (TeO₂) aluminum oxide (Al₂O₃), silicon dioxide (SiO₂), lead oxide (PbO), tin oxide (SnO), phosphorous oxide (P₂O₅), ruthenium oxide (Ru₂O), rubidium oxide (Rb₂O), rhodium oxide (Rh₂O), ferrite oxide (Fe₂O₃), copper oxide (CuO), titanium oxide (TiO₂), tungsten oxide (WO₃), bismuth oxide (Bi₂O₃), antimony oxide (Sb₂O₃), lead-borate glass, tin-phosphate glass, vanadate glass, and borosilicate, etc. These particles range in size from about 2 μ m to about 30 μ m, optionally about 5 μ m to about 10 μ m, although not limited only thereto.

The particles can be as large as about the distance between the top and bottom substrates 1061, 1002 or any layers formed on these substrates where the frit seal 1071 contacts.

[0035] The frit material used to form the seal 1071 can also include one or more filler or additive materials. The filler or additive materials can be provided to adjust an overall thermal expansion characteristic of the seal 1071 and/or to adjust the absorption characteristics of the seal 1071 for selected frequencies of incident radiant energy. The filler or additive material(s) can also include inversion and/or additive fillers to adjust a coefficient of thermal expansion of the frit. For example, the filler or additive

40 materials can include transition metals, such as chromium (Cr), iron (Fe), manganese (Mn), cobalt (Co), copper (Cu), and/or vanadium. Additional materials for the filler or additives include ZnSiO₄, PbTiO₃, ZrO₂, eucryptite.

[0036] Typically, a frit material as a dry composition 50 contains glass particles from about 20 to 90 about wt%, and the remaining includes fillers and/or additives. In some cases, the frit paste contains about 10-30 wt% organic materials and about 70-90% inorganic materials. In some cases, the frit paste contains about 20 wt% organic materials and about 80 wt% inorganic materials. In some cases, the organic materials may include about 0-30 wt% binder(s) and about 70-100 wt% solvent(s). In some cases, about 10 wt% is binder(s) and about 90 wt%

is solvent(s) among the organic materials. In some cases, the inorganic materials may include about 0-10 wt% additives, about 20-40 wt% fillers and about 50-80 wt% glass powder. In some cases, about 0-5 wt% is additive(s), about 25-30 wt% is filler(s) and about 65-75 wt% is the glass powder among the inorganic materials.

[0037] In forming a frit seal, a liquid material is added to the dry frit material to form a frit paste. Any organic or inorganic solvent with or without additives can be used as the liquid material. The solvent may include one or more organic compounds. For example, applicable organic compounds are ethyl cellulose, nitro cellulose, hydroxyl propyl cellulose, butyl carbitol acetate, terpineol, butyl cellulose, acrylate compounds. Then, the thus formed frit paste can be applied to form a shape of the seal 1071 on the top and/or bottom plate 1061, 1002.

[0038] Typically, a shape of the seal 1071 is initially formed from the frit paste and interposed between the top plate 1061 and the bottom plate 1002. The seal 1071 can in certain cases be pre-cured or pre-sintered to one of the top plate and bottom plate 1061, 1002. Following assembly of the top plate 1061 and the bottom plate 1002 with the seal 1071 interposed therebetween, portions of the seal 1071 are selectively heated such that the frit material forming the seal 1071 at least partially melts. The seal 1071 is then allowed to resolidify to form a secure joint between the top plate 1061 and the bottom plate 1002 to thereby inhibit exposure of the enclosed OLED pixel array 1021 to oxygen or water.

[0039] The selective heating of the frit seal is carried out by irradiation of light, such as a laser or directed infrared lamp. As previously noted, the frit material forming the seal 1071 can be combined with one or more additives or filler such as species selected for improved absorption of the irradiated light to facilitate heating and melting of the frit material to form the seal 1071.

[0040] In some cases, OLED devices 1011 are mass produced. In an arrangement illustrated in Fig. 7E, a plurality of separate OLED arrays 1021 is formed on a common bottom substrate 1101. Each OLED array 1021 is surrounded by a shaped frit to form the seal 1071. Common top substrate (not shown) is placed over the common bottom substrate 1101 and the structures formed thereon such that the OLED arrays 1021 and the shaped frit paste are interposed between the common bottom substrate 1101 and the common top substrate. The OLED arrays 1021 are encapsulated and sealed, such as via the previously described enclosure process for a single OLED display device. The resulting product includes a plurality of OLED devices kept together by the common bottom and top substrates. Then, the resulting product is cut into a plurality of pieces, each of which constitutes an OLED device 1011 of Fig. 7D. In certain cases, the individual OLED devices 1011 then further undergo additional packaging operations to further improve the sealing formed by the frit seal 1071 and the top and bottom substrates 1061, 1002.

[0041] A light emitting display (OLED) device includes

a first substrate comprising a first outer surface and a first inner surface and a second substrate generally opposing the first substrate. The second substrate has a second outer surface and a second inner surface. The

5 OLED device also includes an array of organic light emitting pixels interposed between the first and second substrates. The OLED further includes a frit seal interposed between the first and second substrates while surrounding the array. The frit seal, the first substrate, and the second substrate in combination define an enclosed space in which the array is located.

[0042] The second substrate has a curvature with a radius of the curvature. The curvature may be formed across the entire 15 second substrate. In other embodiments, the curvature may be formed in a portion of the second substrate. The second substrate has a curvature sufficient to substantially reduce Newton's rings on the second substrate compared to when there is no curvature in the second substrate.

[0043] The radius of the curvature ranges from 0.2m to 100m. The radius of the curvature may be selected from 25 0.2m, 0.3m, 0.4m, 0.5m, 0.75m, 1m, 1.25m, 1.5m, 1.75m, 2m, 2.25m, 2.5m, 2.75m, 3m, 3.25m, 3.5m, 3.75m, 4m, 4.25m, 4.5m, 4.75m, 5m, 5.25m, 5.5m, 5.75m, 6m, 6.25m, 6.5m, 6.75m, 7m, 7.25m, 7.5m, 7.75m, 8m, 8.25m, 8.5m, 8.75m, 9m, 9.25m, 9.5m, 9.75m, 10m, 15m, 20m, 25m, 30m, 35m, 40m, 45m, 50m, 55m, 60m, 65m, 70m, 75m, 80m, 85m, 90m, 95m, 100m. A skilled artisan will appreciate that the radius of the curvature may vary depending on the size and configuration of the OLED device.

[0044] FIG. 1 is a cross-sectional view illustrating an 35 organic light emitting display according to a first embodiment. Referring to FIG. 1, an organic light emitting display 100 includes a first substrate 110, a second substrate 150, and a frit 130. The first substrate 110 includes a pixel region 120a in which at least one organic light emitting diode (OLED) is formed and a non-pixel region 120b. The second substrate 150 is placed over the pixel region 120a and at least a portion of the non-pixel region 120b of the first substrate 110. The frit 130 is provided between the non-pixel region 120b of the first substrate 40 110 and the second substrate 150. The second substrate 150 forms an outwardly convex curve. In alternative embodiments, the first substrate 110 forms such a curve.

[0045] The substrate 110 includes the pixel region 120a and the non-pixel region 120b. The pixel region 50 120a may include at least one OLED having a first electrode, an organic layer, and a second electrode. The non-pixel region 120b surrounds the pixel region 120a. The pixel region 120a refers to a region which displays an image. The non-pixel region 120b refers to the substantially all the region outside the pixel region 120a.

[0046] The frit 130 is provided between the non-pixel region 120b of the first substrate 110 and the second substrate 150 to adhere the first substrate 110 and the

second substrate 150 to each other. The term "frit" may refer to powder type glass. In the context of this document, a frit may also refer to gel or paste type glass that may be obtained by adding an organic material to the powder type glass or a solid glass that may be obtained by radiating laser onto the powder type glass so that the powder type glass is hardened.

[0047] A sealant 140 is formed on the outermost peripheries of the second substrate 150 outside the frit 130. The sealant 140 is formed outside the frit 130 to improve adhesive strength between the first substrate 110 and the second substrate 150. In other embodiments, the sealant 140 may be formed inside the frit 130.

[0048] The external center of the second substrate 150 is convex, as shown in FIG. 1. Since the external center of the second substrate 150 is convex, the distance between the center of the first substrate 110 and the center of the second substrate 150 is larger than the height of the frit 130 or the sealant 140. In the present invention the reflectance of the first substrate 110 is 60 to 70% (LTPS glass) and the reflectance of the second substrate 150 is 4% (bare glass), the distance between the first substrate 110 and the second substrate 150 maintained to be no less than 10 μ m. This configuration prevents Newton's rings from being generated. The second substrate 150 may be formed of edge glass or bare glass. When the second substrate 150 is formed of the edge glass, the distance between the first substrate 110 and the second substrate 150 is no less than several tens μ m along the edge region. Thus, optical interference intensity may be reduced.

[0049] FIGs. 2A to 2E are cross-sections illustrating a method of fabricating the organic light emitting display according to the first embodiment. FIG. 3 is a cross-sectional view illustrating the angle of the curvature of the second substrate according to the first embodiment.

[0050] Referring to FIG. 2A, the substrate 110 includes the pixel region 120a in which at least one OLED including a first electrode, an organic layer, and a second electrode is formed, and the non-pixel region 120b surrounding the pixel region 120a. The second substrate 150 for sealing the first substrate 110 is positioned under the first substrate 110.

[0051] Referring to FIG. 2B, a frit 130 is applied to one region of the second substrate 150 that corresponds to the non-pixel region 120b. The frit 130 may include, as additives, a filler (not shown) for controlling a thermal expansion coefficient and an absorbent (not shown) that absorbs laser or infrared rays. In one embodiment, the frit may include a powder type glass and an oxide powder. The temperature of a glass material is rapidly dropped so that the powder type glass is obtained. An organic material may be added to the frit so that gel type paste is obtained. Then, when the frit 130 is annealed at a pre-determined temperature, the organic material is removed and the gel type frit paste is hardened so that the solid frit 130 is obtained. The temperature at which the frit 130 is annealed may be in the range of about 300°C to about

700°C.

[0052] Referring to FIG. 2C, the sealant 140 may be formed on the outermost peripheries of the second substrate 150, outside the frit 130. The sealant 140 is formed outside the frit 130 to improve the adhesive strength between the first substrate 110 and the second substrate 150. The sealant 140 may be formed by a bar coating method using sputtering or a roller.

[0053] Referring to FIG. 2D, the first substrate 110 and the second substrate 150 are placed into a vacuum chamber (not shown). After placing the first substrate 110 and the second substrate 150 into the vacuum chamber, the pressure in the vacuum chamber may be reduced to negative pressure that is lower than the atmospheric pressure (760torr) using pressure controlling means. In this embodiment, the pressure in the vacuum chamber is maintained to be higher than the pressure P1 between the first substrate and the second substrate that are not attached to each other in order to maintain the pressure between the first substrate 110 and the second substrate 120 that are attached to each other at the atmospheric pressure 760torr. When it is assumed that $P_1 * V_1 = P_2 * V_2$, a value obtained by multiplying the pressure and the volume between the first substrate and the second substrate that are not attached to each other is equal to a value obtained by multiplying the pressure and the volume between the first substrate and the second substrate that are attached to each other. The pressure P1 can be represented by EQUATION 1.

EQUATION 1

$$P_1 = 760 * V_2 / V_1$$

[0054] wherein, P_1 , V_1 , P_2 , and V_2 denote the pressure between the first substrate and the second substrate that are not attached to each other, the volume between the first substrate and the second substrate that are not attached to each other, the pressure between the first substrate and the second substrate that are attached to each other, and the volume between the first substrate and the second substrate that are attached to each other, respectively.

[0055] The EQUATION 1 represents the Boyle's law in which the pressure of a gas is in inverse proportion to the volume of the gas at a constant temperature. That is, when the pressure is applied from the outside to reduce the volume of the gas to 1/2, the density of the gas doubles and the number of collision of the gas per unit time doubles so that the pressure doubles. To the contrary, when the pressure from the outside is reduced, the gas expands so that the volume of the gas increases. Therefore, the volume of a uniform gas is in inverse proportion to the pressure at a uniform temperature.

[0056] Then, the first substrate 110 and the second substrate 150 are attached to each other by a physical force. Therefore, the pressure of the gas molecules be-

tween the first substrate 110 and the second substrate 150 is maintained to be higher than the pressure P1.

[0057] Referring to FIG. 2E, the vacuum of the vacuum chamber is broken or the first substrate 110 and the second substrate 120 that are attached to each other are exposed to the atmospheric pressure. When the first substrate 110 and the second substrate 150 that are attached to each other are exposed to the atmospheric pressure, due to a difference in pressure (differential pressure) between the pressure between the first substrate 110 and the second substrate 150 that are attached to each other and the atmospheric pressure, the volume of the gas molecules that exist between the first substrate 110 and the second substrate 150 increases by the amount of the differential pressure. Therefore, the first substrate 110 and the second substrate 150 expand outward.

[0058] The angles of the first substrate and the second substrate are represented by EQUATION 2 (refer to FIG. 3).

EQUATION 2

$$h > 10 \mu\text{m}$$

$$\tan \alpha = h/a$$

$$h = a * \tan \alpha > 10 \mu\text{m}$$

Therefore, $\alpha > \tan^{-1}(10/a)$

wherein $\alpha < 45^\circ$ and the value of β is not limited.

[0059] In the EQUATION 2, α , β , h , a , and b represent the angle corresponding to the distance between the first substrate and the second substrate, the angle that is formed by the curvature of the second substrate that expands and the peak between the two ends of the second substrate, the height of the frit provided between the first substrate and the second substrate, 1/2 of the length of the second substrate, and the height of the peak of the curvature of the second substrate, respectively.

[0060] At least one of the first substrate 110 and the second substrate 150 may be provided with a vacuum pump or suction in order to prevent sliding of the substrates due to the difference in pressure. For example, a plurality of inlets (not shown) for inhaling the air are provided on one surface of the first substrate 110. The inlets are connected to an air inhaling device such as a vacuum pump (not shown) that is positioned on one side of the first substrate 110 through outlets. Therefore, the air that is inhaled to the inside of the first substrate 110 through the inlets is discharged to the air inhaling device such as the vacuum pump through the outlets. One of the first substrate 110 and the second substrate 150 is fixed using a vacuum suction plate under the first substrate 110 so as to prevent the sliding of the first substrate 110 and the second substrate 150 and to change the shape of a desired substrate.

[0061] In one embodiment, the first substrate 110 is fixed to the plate by the above method so that only the second substrate 150 expands to become convex. Since the center of the second substrate 150 expands to become convex, the distance between the centers of the first substrate 110 and the second substrate 150 that are attached to each other is maintained to be larger than the height of the frit 130 or the sealant 140.

[0062] Then, laser or infrared rays may be radiated onto the frit 130 to melt the frit 130. Therefore, the first substrate 110 and the second substrate 150 are interconnected to each other.

[0063] FIG. 4 is a sectional view illustrating an organic light emitting display according to a second embodiment not forming part of the present invention. Referring to FIG. 4, the organic light emitting display includes a first substrate 210 including a pixel region 220a in which at least one organic light emitting diode (OLED) is formed and a non-pixel region 220b that is formed outside the pixel region 220a, a second substrate 250 that is attached to one region including the pixel region 220a of the first substrate 210, and a frit 230 that is provided between the non-pixel region 220b of the first substrate 210 and the second substrate 250. The second substrate is 250 is formed to be outwardly concave. In alternative embodiments, the first substrate 210 is formed to be outwardly concave.

[0064] In order to avoid redundancy, description of the first substrate 210, the frit 230, and the sealant 240 that are the same elements as those of the above-described first embodiment will be omitted.

[0065] The second substrate 250 is formed to be outwardly concave, which is caused by reduction in pressure, that is, difference in pressure between the pressure between the first substrate 210 and the second substrate 250 that are not attached and the pressure between the first substrate 210 and the second substrate 250 that are attached to each other. For example, when the reflectance of the first substrate 210 is about 60 to about 70% (LTPS glass) and the reflectance of the second substrate 250 is about 4% (bare glass), it is possible to prevent the distance between the first substrate 210 and the second substrate 250 from being reduced to be less than 10 μm and to thus prevent Newton's rings from being generated.

[0066] FIGS. 5A to 5E are schematic cross-sections illustrating a method of fabricating the organic light emitting display according to the second embodiment. FIG. 6 is a sectional view illustrating the angle of the curvature of the second substrate according to the second embodiment.

[0067] Referring to FIG. 5A, the substrate 210 includes the pixel region 220a in which at least one OLED including a first electrode, an organic layer, and a second electrode is formed and the non-pixel region 220b that is formed outside the pixel region 220a. The second substrate 250 for sealing up the first substrate 210 is positioned under the first substrate 210.

[0068] Referring to FIG. 5B, one region of the second

substrate 250 that corresponds to the non-pixel region 220b is coated with the frit 230 so that the pixel region 220a of the first substrate 210 is sealed up. Referring to FIG. 5C, the sealant 240 is formed on the outermost periphery of the second substrate 250, that is, outside of the frit 230.

[0069] Referring to FIG. 5D, the first substrate 210 and the second substrate 250 are placed in a vacuum chamber (not shown). After placing the first substrate 210 and the second substrate 250 into the vacuum chamber, the pressure in the vacuum chamber is reduced to negative pressure that is lower than the atmospheric pressure (760torr) using pressure controlling means. At this time, the pressure in the vacuum chamber is maintained to be lower than the pressure P_1 between the first substrate and the second substrate that are not attached to each other in order to maintain the pressure between the first substrate 210 and the second substrate 220 that are attached to each other as the air pressure 760torr. When it is assumed that $P_1 * V_1 = P_2 * V_2$, since the value that is obtained by multiplying the pressure and the volume between the first substrate and the second substrate that are not attached to each other by each other must be equal to the value that is obtained by multiplying the pressure and the volume between the first substrate and the second substrate that are attached to each other, the pressure P_1 can be represented by EQUATION 3.

EQUATION 3

$$P_1 = 760 * V_2 / V_1$$

In Equation 3, P_1 , V_1 , P_2 , and V_2 denote the pressure between the first substrate and the second substrate that are not attached to each other, the volume between the first substrate and the second substrate that are not attached to each other, the pressure between the first substrate and the second substrate that are attached to each other, and the volume between the first substrate and the second substrate that are attached to each other, respectively.

[0070] The EQUATION 3 represents the Boyle's law in which the pressure of a gas is in inverse proportion to the volume of the gas at a uniform temperature. That is, when the pressure is applied from the outside to reduce the volume of the gas to 1/2, the density of the gas doubles and the number of time of collision of the gas per a unit time doubles so that the pressure doubles. To the contrary, when the pressure from the outside is reduced, the gas expands so that the volume of the gas increases. Therefore, the volume of a uniform gas is in inverse proportion to the pressure at a uniform temperature.

[0071] Then, the first substrate 210 and the second substrate 250 are attached to each other by physical force. Therefore, the pressure of the gas molecules between the first substrate 210 and the second substrate 250 is maintained to be lower than the pressure P_1 .

[0072] Referring to FIG. 5E, the vacuum of the vacuum chamber is broken or the first substrate 210 and the second substrate 220 that are attached to each other are exposed to the atmospheric pressure. When the first substrate 210 and the second substrate 250 that are attached to each other under the negative pressure that is lower than the pressure P_1 are exposed to the atmospheric pressure, due to difference in pressure (differential pressure) between the pressure between the first substrate 210 and the second substrate 250 that are attached to each other and the air pressure, the volume of the gas molecules that exist between the first substrate 210 and the second substrate 250 is reduced. Therefore, the first substrate 210 and the second substrate 250 contract inward.

[0073] The angles of the first substrate and the second substrate are represented by EQUATION 4 (refer to FIG. 6).

EQUATION 4

$$h' - b' > 10 \mu\text{m}$$

$$\tan \alpha' = h'/a', \tan \beta' = b'/a'$$

Therefore, $h' = a' * \tan \alpha'$ and $b' = a' * \tan \beta'$

$$a' * (\tan \alpha' - \tan \beta') > 10 \mu\text{m}$$

$$\tan \beta' < (\tan \alpha' - 10 \mu\text{m}/a'), \text{ where } a' > 0 \text{ and } \alpha', \beta' < 45^\circ$$

[0074] In the EQUATION 4, α' , β' , h' , a' , and b' represent the angle corresponding to the distance between the first substrate and the second substrate, the angle that is formed by the curvature of the second substrate that expands and the peak between the two ends of the second substrate, the height of the frit provided between the first substrate and the second substrate, 1/2 of the length of the second substrate, and the height of the peak of the curvature of the second substrate, respectively.

[0075] In one embodiment, at least one of the first substrate 210 and the second substrate 250 includes a vacuum pump or suction in order to prevent sliding of the substrates due to the difference in pressure. For example, a plurality of inlets (not shown) for inhaling the air are provided to one surface of the first substrate 210. The inlets are connected to an air inhaling device such as a vacuum pump (not shown) that is positioned on one side of the first substrate 210 through outlets. Therefore, the air that is inhaled to the inside of the first substrate 210 through the inlets is discharged to the air inhaling device such as the vacuum pump through the outlets. One of the first substrate 210 and the second substrate 250 is fixed using a vacuum suction plate under the first substrate 210 so as to prevent the sliding of the first substrate 210 and the second substrate 250 and to change the shape of a desired substrate.

[0076] In one embodiment, the first substrate 210 is

fixed to the plate by the above method so that the center of the second substrate 250 deforms to become concave. A predetermined pressure is maintained between the first substrate 210 and the second substrate 250 so that it is possible to prevent the second substrate 250 from sagging.

[0076] Then, laser or infrared rays are radiated onto the frit 230 to melt the frit 230. Therefore, the first substrate 210 and the second substrate 250 are adhered to each other.

[0077] Although a few embodiments of the invention have been shown and described, it would be appreciated by those skilled in the art that changes might be made in this embodiment without departing from the scope of the appended claims.

Claims

1. An organic light emitting display (OLED) device, comprising:
 a first substrate (110) comprising a first outer surface and a first inner surface;
 a second substrate (150) generally opposing the first substrate, the second substrate comprising a second outer surface and a second inner surface;
 an array of organic light emitting pixels interposed between the first and second substrates; and
 a frit (130) interposed between the first and second substrates while surrounding the array, wherein the frit seal, the first substrate, and the second substrate in combination define an enclosed space in which the array is located;
 wherein the second substrate bends outward and has a curvature sufficient to substantially reduce Newton's rings on the second substrate compared to when there is no curvature in the second substrate, **characterized in that** the radius of the curvature ranges from 0.2 meters to 100 meters, a distance between the first and second inner surfaces is greater than about 10 μ m and the first substrate has a reflectance of from 60% to 70%, and the second substrate has a reflectance of 4%.
2. A device according to any preceding claim, wherein the second substrate is more flexible than the first substrate.
3. A device according to any preceding claim, wherein the enclosed space has a gas pressure the same as the atmospheric pressure.
4. A device according to any preceding claim, wherein the second substrate comprises a material selected from the group consisting of bare glass and edge glass.
5. A device according to any preceding claim, further comprising another sealing structure (140) interposed between the first and second substrates, wherein the other sealing structure surrounds the frit seal.
6. A device according to Claim 5, wherein the other sealing structure and the frit seal forms a gap therebetween.
7. A device according to any preceding claim, wherein the frit seal comprises one or more materials selected from the group consisting of magnesium oxide (MgO), calcium oxide (CaO), barium oxide (BaO), lithium oxide (Li₂O), sodium oxide (Na₂O), potassium oxide (K₂O), boron oxide (B₂O₃), vanadium oxide (V₂O₅), zinc oxide (ZnO), tellurium oxide (TeO₂), aluminum oxide (Al₂O₃), silicon dioxide (SiO₂), lead oxide (PbO), tin oxide (SnO), phosphorous oxide (P₂O₅), ruthenium oxide (Ru₂O), rubidium oxide (Rb₂O), rhodium oxide (Rh₂O), ferrite oxide (Fe₂O₃), copper oxide (CuO), titanium oxide (TiO₂), tungsten oxide (WO₃), bismuth oxide (Bi₂O₃), antimony oxide (Sb₂O₃), lead-borate glass, tin-phosphate glass, vanadate glass, and borosilicate.
8. A method of making an organic light emitting display (OLED) device, the method comprising:
 providing a first substrate (110);
 placing a second substrate (150) over the first substrate so as to interpose an array of light emitting pixels between the first and second substrates;
 interposing, under a predetermined gas pressure, a frit (130) between the first and second substrates while surrounding the array, wherein the frit, the first substrate, and the second substrate in combination define an enclosed space in which the array is located, the predetermined gas pressure is substantially higher than the atmospheric pressure;
 melting and re-solidifying the frit to the first and second substrates so as to substantially hermetically seal the enclosed space; and
 subjecting the device to the atmospheric pressure so as to form a curvature in the second substrate sufficient to substantially reduce Newton's rings on the second substrate compared to when there is no curvature in the second substrate, wherein the second substrate generally bends outward after subjecting the device to the atmospheric pressure, **characterized in that** the radius of the curvature ranges from 0.2 meters to 100 meters.

meters to 100 meters, a distance between the first and second inner surfaces is greater than 10 μ m and the first substrate has a reflectance of from 60% to 70%, and the second substrate has a reflectance of 4%. 5

9. A method according to Claim 8, wherein after forming the curvature, the gas pressure within the enclosed space is equal to the atmospheric pressure outside the enclosed space. 10
10. A method according to Claims 8 or 9 wherein during melting and re-solidifying, the predetermined gas pressure is maintained. 15
11. A method according to any one of Claims 8 to 10 wherein the second substrate is more flexible than the first substrate. 20
12. A method according to one of Claims 8 to 11, further comprising providing a second seal (140) between the first and second substrates, wherein the second seal surrounds the frit (130) before subjecting the device to the atmospheric pressure. 25
13. A method according to one of Claims 8 to 12, further comprising holding one of outer surfaces of the first and second substrates by suction during interposing the frit. 30

Patentansprüche

1. Organische lichtemittierende Anzeigevorrichtung (OLED), umfassend:

ein erstes Substrat (110) umfassend eine erste Außenfläche und einer erste Innenfläche; ein zweites Substrat (150), welches generell dem ersten Substrat gegenübersteht, wobei das zweite Substrat eine zweite Außenfläche und eine zweite Innenfläche umfasst; eine Anordnung organischer lichtemittierender Pixel, welche zwischen dem ersten und dem zweiten Substrat angeordnet sind; und eine Fritte (130), welche zwischen dem ersten und dem zweiten Substrat angeordnet ist, während sie die Anordnung umschließt, wobei die Frittendichtung, das erste Substrat, und das zweite Substrat zusammen einen geschlossenen Raum definieren, in welchem die Anordnung angeordnet ist; wobei das zweite Substrat sich nach außen biegt und eine Krümmung aufweist, welche ausreicht, um die Newtonschen Ringe auf dem zweiten Substrat im Wesentli- 40

chen zu verringern, im Vergleich zum Fall, in dem das zweite Substrat keine Krümmung aufweist, **dadurch gekennzeichnet, dass** der Krümmungsradius zwischen 0,2 m und 100 m liegt, wobei der Abstand zwischen der ersten und der zweiten Innenfläche größer als 10 μ m ist und das erste Substrat ein Reflexionsvermögen von 60% bis 70% aufweist und das zweite Substrat ein Reflexionsvermögen von 4% aufweist. 5

2. Vorrichtung nach einem der vorhergehenden Ansprüche, wobei das zweite Substrat flexibler als das erste Substrat ist. 10
3. Vorrichtung nach einem der vorhergehenden Ansprüche, wobei der geschlossene Raum einen Gasdruck aufweist, welcher dem atmosphärischen Druck entspricht. 15
4. Vorrichtung nach einem der vorhergehenden Ansprüche, wobei das zweite Substrat ein Material umfasst, welches aus der Gruppe, bestehend aus blankem Glass und Kantenglass ausgewählt ist. 20
5. Vorrichtung nach einem der vorhergehenden Ansprüche, ferner umfassend eine weitere Dichtungsstruktur (140), welche zwischen dem ersten und dem zweiten Substrat eingebracht ist, wobei die weitere Dichtungsstruktur die Frittendichtung umschließt. 25
6. Vorrichtung nach Anspruch 5, wobei die weitere Dichtungsstruktur und die Frittendichtung zwischen einander einen Spalt bilden. 30
7. Vorrichtung nach einem der vorhergehenden Ansprüche, wobei die Frittendichtung ein oder mehrere Materialien, ausgewählt aus der Gruppe, bestehend aus Magnesiumoxid (MgO), Calciumoxid (CaO), Bariumoxid (BaO), Lithiumoxid (Li₂O), Natriumoxid (Na₂O), Kaliumoxid (K₂O), Boroxid (B₂O₃), Vanadiumoxid (V₂O₅), Zinkoxid (ZnO), Telluroxid (TeO₂), Aluminiumoxid (Al₂O₃), Siliziumdioxid (SiO₂), Bleioxid (PbO), Zinnoxid (SnO), Phosphoroxid (P₂O₅), Rutheniumoxid (Ru₂O), Rubidiumoxid (Rb₂O), Rhodiumoxid (Rh₂O), Ferritoxid (Fe₂O₃), Kupferoxid (CuO), Titanoxid (TiO₂), Wolframoxid (WO₃), Wismutoxid (Bi₂O₃), Antimonoxid (Sb₂O₃), Blei-Boratglas, Zinn-Phosphat-Glas, Vanadat-Glas und Borosilikat umfasst. 45
8. Verfahren zur Herstellung einer organischen lichtemittierenden Anzeigevorrichtung (OLED), wobei das Verfahren umfasst: 50

Bereitstellen eines ersten Substrats (110); Anordnen eines zweiten Substrats (150) über dem ersten Substrat, sodass eine Anordnung

von lichtemittierenden Pixeln zwischen dem ersten und dem zweiten Substrat eingebracht wird; Einbringen, unter einem vorbestimmten Gasdruck, einer Fritte (130) zwischen das erste und das zweite Substrat, während sie die Anordnung umschließt, wobei die Fritte, das erste Substrat und das zweite Substrat zusammen einen geschlossenen Raum definieren, in dem die Anordnung angeordnet ist, wobei der vorbestimmte Gasdruck wesentlich höher ist als der atmosphärische Druck; 10 Schmelzen und Wiederverfestigen der Fritte auf dem ersten und zweiten Substrat, um den geschlossenen Raum im Wesentlichen hermetisch abzudichten; und 15 Aussetzen der Vorrichtung gegenüber dem atmosphärischen Druck, um eine Krümmung im zweiten Substrat zu bilden, welche ausreichend ist, um die Newtonschen Ringe auf dem zweiten Substrat zu verringern, im Vergleich zum Fall, in dem das zweite Substrat keine Krümmung aufweist, wobei das zweite Substrat sich generell nach außen krümmt, nachdem die Vorrichtung dem atmosphärischen Druck ausgesetzt worden ist, **dadurch gekennzeichnet, dass** 20 der Krümmungsradius zwischen 0,2 m und 100 m liegt, der Abstand zwischen der ersten und zweiten Innenfläche größer als 10 μm ist und das erste Substrat ein Reflexionsvermögen zwischen 60% und 70% aufweist, und das zweite Substrat ein Reflexionsvermögen von 4% aufweist. 25

9. Verfahren nach Anspruch 8, wobei nach dem Bilden der Krümmung der Gasdruck innerhalb des geschlossenen Raums dem atmosphärischen Druck außerhalb des geschlossenen Raums entspricht.
10. Verfahren nach Anspruch 8 oder 9, wobei während des Schmelzens und der Wiederverfestigung der vorbestimmte Gasdruck beibehalten wird. 40
11. Verfahren nach einem der Ansprüche 8 bis 10, wobei das zweite Substrat flexibler als das erste Substrat ist. 45
12. Verfahren nach einem der Ansprüche 8 bis 11, ferner umfassend das Bereitstellen einer zweiten Dichtung (140) zwischen dem ersten und dem zweiten Substrat, wobei die zweite Dichtung die Fritte (130) umschließt, bevor die Vorrichtung dem atmosphärischen Druck ausgesetzt wird. 50
13. Verfahren nach einem der Ansprüche 8 bis 12, ferner umfassend das Halten, durch Saugwirkung, während des Einbringens der Fritte, einer der Außenflächen des ersten und des zweiten Substrats.

Revendications

1. Dispositif d'affichage électroluminescent organique (Organic Light Emitting Display, OLED), comprenant : un premier substrat (110) comprenant une première surface extérieure et une première surface intérieure, un second substrat (150) globalement opposé au premier substrat, le second substrat comprenant une seconde surface extérieure et une seconde surface intérieure, un réseau de pixels électroluminescents organiques interposé entre les premier et second substrats, et une fritte (130) interposée entre les premier et second substrats tout en entourant le réseau, le joint de fritte, le premier substrat et le second substrat définissant conjointement un espace clos dans lequel se situe le réseau ; le second substrat étant fléchi vers l'extérieur et présentant une courbure suffisante pour réduire sensiblement les anneaux de Newton sur le second substrat en comparaison au cas d'une absence de courbure dans le second substrat, **caractérisé en ce que** le rayon de la courbure est compris dans la plage allant de 0,2 mètre à 100 mètres, une distance séparant les première et seconde surfaces intérieures est supérieure à 10 μm et le premier substrat présente un facteur de réflexion allant de 60 % à 70 %, et le second substrat présente un facteur de réflexion de 4 %. 35
2. Dispositif selon l'une quelconque des revendications précédentes, dans lequel le second substrat est plus souple que le premier substrat. 40
3. Dispositif selon l'une quelconque des revendications précédentes, dans lequel l'espace clos présente une pression de gaz identique à la pression atmosphérique. 45
4. Dispositif selon l'une quelconque des revendications précédentes, dans lequel le second substrat comprend un matériau choisi dans le groupe constitué par le verre nu et le verre de bord. 50
5. Dispositif selon l'une quelconque des revendications précédentes, comprenant en outre une autre structure de joint (140) interposée entre les premier et second substrats, l'autre structure de joint entourant le joint de fritte. 55
6. Dispositif selon la revendication 5, dans lequel l'autre structure de joint et le joint de fritte définissent un écart entre eux.

7. Dispositif selon l'une quelconque des revendications précédentes, dans lequel le joint de fritte comprend un ou plusieurs matériaux choisis dans le groupe constitué par l'oxyde de magnésium (MgO), l'oxyde de calcium (CaO), l'oxyde de baryum (BaO), l'oxyde de lithium (Li₂O), l'oxyde de sodium (Na₂O), l'oxyde de potassium (K₂O₃), l'oxyde de bore (B₂O₃), l'oxyde de vanadium (V₂O₅), l'oxyde de zinc (ZnO), l'oxyde de tellurium (TeO₂), l'oxyde d'aluminium (Al₂O₃), le dioxyde de silicium (SiO₂), l'oxyde de plomb (PbO), l'oxyde d'étain (SnO), l'oxyde de phosphore (P₂O₅), l'oxyde de ruthénium (Ru₂O), l'oxyde de rubidium (Rb₂O), l'oxyde de rhodium (Rh₂O), l'oxyde de ferrite 15 l'oxyde de cuivre (CuO), l'oxyde de titane (TiO₂), l'oxyde de tungstène (WO₃), l'oxyde de bismuth (Bi₂O₃), l'oxyde d'antimoine (Sb₂O₃), le verre au borate de plomb, le verre au phosphate d'étain, le verre de vanadate et le borosilicate.

8. Procédé de fabrication d'un dispositif d'affichage électroluminescent organique (Organic Light Emitting Display, OLED), le procédé comprenant :

la mise à disposition d'un premier substrat (110) ; 25

la mise en place d'un second substrat (150) sur le premier substrat de manière à interposer un réseau de pixels électroluminescents entre les premier et second substrats ; 30

l'interposition, sous une pression de gaz prédéterminée, d'une fritte (130) entre les premier et second substrats en entourant également le réseau, la fritte, le premier substrat et le second substrat définissant conjointement un espace clos dans lequel se situe le réseau, la pression de gaz prédéterminée étant sensiblement supérieure à la pression atmosphérique ; 35

la fonte et la resolidification de la fritte sur les premier et second substrats de manière à fermer l'espace clos de façon sensiblement hermétique ; et 40

l'exposition du dispositif à la pression atmosphérique de manière à produire une courbure dans le second substrat qui soit suffisante pour réduire sensiblement les anneaux de Newton sur le second substrat en comparaison au cas d'une absence de courbure dans le second substrat, le second substrat fléchissant globalement vers l'extérieur après avoir exposé le dispositif à la pression atmosphérique, **caractérisé en ce que** le rayon de la courbure est compris dans la plage allant de 0,2 mètre à 100 mètres, la distance séparant les première et seconde surfaces intérieures est supérieure à 10 µm, et le premier substrat présente un facteur de réflexion allant de 60 % à 70 %, et le second substrat présente un facteur de réflexion de 4 %. 45 50 55

9. Procédé selon la revendication 8, dans lequel, après la production de la courbure, la pression de gaz au sein de l'espace clos est égale à la pression atmosphérique régnant hors de l'espace clos. 5

10. Procédé selon les revendications 8 ou 9, dans lequel, pendant la fonte et la ressolidification, la pression de gaz prédéterminée est maintenue.

11. Procédé selon l'une quelconque des revendications 8 à 10, dans lequel le second substrat est plus souple que le premier substrat.

12. Procédé selon l'une des revendications 8 à 11, comprenant en outre la mise à disposition d'un second joint (140) entre les premier et second substrats, le second joint entourant la fritte (130) avant l'exposition du dispositif à la pression atmosphérique.

13. Procédé selon l'une des revendications 8 à 12, comprenant en outre le maintien d'une des surfaces extérieures des premier et second substrats par effet de ventouse pendant l'interposition de la fritte.

FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 3




FIG. 4

200




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D



FIG. 5E

200




FIG. 6




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D





FIG. 7E



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 20040207314 A [0007]
- US 2001013756 A [0010]
- US 4192060 A [0010]
- JP 2001118680 A [0010]
- US 2005046338 A1 [0010]
- US 2003107315 A1 [0010]
- JP 2006031256 A [0010]
- JP 2004280759 A [0010]
- US 2004207314 A1 [0010]

| | | | |
|----------------|---|---------|------------|
| 专利名称(译) | 有机发光显示器及其制造方法 | | |
| 公开(公告)号 | EP1821354B1 | 公开(公告)日 | 2016-11-09 |
| 申请号 | EP2007250691 | 申请日 | 2007-02-20 |
| [标]申请(专利权)人(译) | 三星斯笛爱股份有限公司 | | |
| 申请(专利权)人(译) | 三星SDI CO. , LTD. | | |
| 当前申请(专利权)人(译) | 三星DISPLAY CO. , LTD. | | |
| 发明人 | ZU, YOUNG CHEOL, C/O SAMSUNG SDI CO., LTD PARK, JIN-WOO, C/O SAMSUNG SDI CO., LTD LEE, JAE SUN, C/O SAMSUNG SDI CO., LTD SONG, SEUNG YONG, C/O SAMSUNG SDI CO., LTD CHOI, YOUNG SEO, C/O SAMSUNG SDI CO., LTD | | |
| IPC分类号 | H01L27/32 H01L51/52 H01L51/00 H01L51/56 | | |
| CPC分类号 | H01L51/5246 H01L27/3244 H01L27/3281 H01L51/0097 H01L51/56 | | |
| 优先权 | 1020060016480 2006-02-20 KR 1020060035456 2006-04-19 KR | | |
| 其他公开文献 | EP1821354A3 EP1821354A2 | | |
| 外部链接 | Espacenet | | |

摘要(译)

一种有机发光显示器，其中控制压差以防止产生牛顿环，以及制造该有机发光显示器的方法。有机发光显示器包括：第一基板，包括：像素区域，其中形成有至少一个有机发光二极管(OLED)；以及非像素区域；第二基板，附接到包括第一基板的像素区域的一个区域，以及在第一基板的非像素区域和第二基板之间提供的玻璃料。第一基板和第二基板中的至少一个形成为向外凸出或凹入。

EQUATION 1

$$P_1 = 760 * V_2 / V_1$$