

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
3 August 2006 (03.08.2006)

PCT

(10) International Publication Number
WO 2006/080644 A1

(51) International Patent Classification:
C09K 11/06 (2006.01)

[KR/KR]; 3-507 Lg Chemistry Dormitory, Doryong-dong,
Yuseong-gu., Daejeon Metropolitan City 305-340 (KR).

(21) International Application Number:
PCT/KR2005/003177

(74) Agent: **HAN YANG PATENT FIRM**; 9F Keungil
Tower, 677-25 Yeoksam-dong, Gangnam-gu., Seoul
135-914 (KR).

(22) International Filing Date:
23 September 2005 (23.09.2005)

(25) Filing Language: Korean

(26) Publication Language: English

(30) Priority Data:
10-2004-0077245
24 September 2004 (24.09.2004) KR

(71) Applicant (for all designated States except US): **LG
CHEM. LTD.** [KR/KR]; 20, Yoido-dong, Young-
dungpo-gu., Seoul 150-721 (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CHO, Wook Dong**
[KR/KR]; 107-1006 Expo Apt., 15/3 464-1, Jeonmin-dong,
Yuseong-gu., Daejeon Metropolitan City 305-761 (KR).
KIM, Ji Eun [KR/KR]; 7-403 Lg Chemistry Apt., 381-42,
Doryong-dong, Yuseong-gu., Daejeon Metropolitan City
305-340 (KR). **JEON, Byung Sun** [KR/KR]; 1006, Taey-
oung Apt., Sillim 5-dong, Gwanak-gu., Seoul 151-708
(KR). **JANG, Jun Gi** [KR/KR]; 7-401 Lg Chemistry Apt.,
Doryong-dong, Yuseong-gu., Daejeon Metropolitan City
305-340 (KR). **YOON, Seok Hee** [KR/KR]; 302-904
Songgang Green Apt., Songgang-dong, Yuseong-gu., Dae-
jeon Metropolitan City 305-756 (KR). **MOON, Jae Min**

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KP, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA,
MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ,
OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL,
SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC,
VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: NEW COMPOUND AND ORGANIC LIGHT EMITTING DEVICE USING THE SAME(5)

(57) Abstract: Disclosed is an organic light emitting device. The organic light emitting device comprises a first electrode, organic material layer(s) comprising a light emitting layer, and a second electrode. The first electrode, the organic material layer(s), and the second electrode form layered structure and at least one layer of the organic material layer(s) include the compound of Formula 1 or the compound of Formula 1 into which a thermosetting or photo-crosslinkable functional group is introduced.



WO 2006/080644 A1

Description

NEW COMPOUND AND ORGANIC LIGHT EMITTING DEVICE USING THE SAME (5)

Technical Field

- [1] The present invention relates to an organic light emitting device which comprises a fluorene derivative capable of significantly improving a lifespan, efficiency, and electrochemical and thermal stabilities thereof.

[2]

Background Art

- [3] An organic light emission phenomenon is an example of a conversion of current into visible rays through an internal process of a specific organic molecule. The organic light emission phenomenon is based on the following mechanism. When organic material layers are interposed between an anode and a cathode, if voltage is applied between the two electrodes, electrons and holes are injected from the cathode and the anode into the organic material layer. The electrons and the holes which are injected into the organic material layer are recombined to form an exciton, and the exciton is reduced to a bottom state to emit light. An organic light emitting device which is based on the above mechanism typically comprises a cathode, an anode, and organic material layer(s), for example, organic material layers including a hole injection layer, a hole transport layer, a light emitting layer, and an electron transport layer, interposed therebetween.
- [4] The materials used in the organic light emitting device are mostly pure organic materials or complexes of organic material and metal. The material used in the organic light emitting device may be classified as a hole injection material, a hole transport material, a light emitting material, an electron transport material, or an electron injection material, according to its use. In connection with this, an organic material having a p-type property, which is easily oxidized and is electrochemically stable when it is oxidized, is mostly used as the hole injection material or the hole transport material. Meanwhile, an organic material having an n-type property, which is easily reduced and is electrochemically stable when it is reduced, is used as the electron injection material or the electron transport material. As the light emitting layer material, an organic material having both p-type and n-type properties is preferable, which is stable when it is oxidized and when it is reduced. Also a material having high light emission efficiency for conversion of the exciton into light when the exciton is formed is preferable.
- [5] In addition, it is preferable that the material used in the organic light emitting device

further have the following properties.

- [6] First, it is preferable that the material used in the organic light emitting device have excellent thermal stability. The reason is that joule heat is generated by movement of electric charges in the organic light emitting device. NPB, which has recently been used as the hole transport layer material, has a glass transition temperature of 100°C or lower, thus it is difficult to apply to an organic light emitting device requiring a high current.
- [7] Second, in order to produce an organic light emitting device that is capable of being actuated at low voltage and has high efficiency, holes and electrons which are injected into the organic light emitting device must be smoothly transported to a light emitting layer, and must not be released out of the light emitting layer. To achieve this, a material used in the organic light emitting device must have a proper band gap and a proper HOMO and LUMO energy levels. A LUMO energy level of PEDOT:PSS, which is currently used as a hole transport material of an organic light emitting device produced using a solution coating method, is lower than that of an organic material used as a light emitting layer material, thus it is difficult to produce an organic light emitting device having high efficiency and a long lifespan.
- [8] Moreover, the material used in the organic light emitting device must have excellent chemical stability, electric charge mobility, and interfacial characteristic with an electrode or an adjacent layer. That is to say, the material used in the organic light emitting device must be little deformed by moisture or oxygen. Furthermore, proper hole or electron mobility must be assured so as to balance densities of the holes and of the electrons in the light emitting layer of the organic light emitting device to maximize the formation of excitons. Additionally, it has to be able to have a good interface with an electrode including metal or metal oxides so as to assure stability of the device.
- [9] Accordingly, there is a need to develop an organic light emitting device including an organic material having the above-mentioned requirements in the art.

[10]

Disclosure of Invention

Technical Problem

- [11] Therefore, the object of the present inventions is to provide an organic light emitting device which is capable of satisfying conditions required of a material usable for an organic light emitting device, for example, a proper energy level, electrochemical stability, and thermal stability, and which includes a fluorene derivative having a chemical structure capable of playing various roles required in the organic light emitting device, depending on a substituent group.


[12]

Technical Solution

[13] The present invention provides an organic light emitting device which comprises a first electrode, organic material layer(s) comprising a light emitting layer, and a second electrode, wherein the first electrode, the organic material layer(s), and the second electrode form a layered structure and at least one layer of the organic material layer(s) includes a compound of the following Formula 1 or a compound of Formula 1 into which a thermosetting or photo-crosslinkable functional group is introduced:

[14] [Formula 1]


[15]



[16]

[17] In Formula 1, X is C or Si,

[18] A is



, and

[19] a is zero or positive integer.

[20] Y is a bond; bivalent aromatic hydrocarbons; bivalent aromatic hydrocarbons which are substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino groups; a bivalent heterocyclic group; or a bivalent heterocyclic group which is substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino groups.


[21] Y1 and Y2 are each bivalent aromatic hydrocarbons; bivalent aromatic hydrocarbons which are substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino groups; a bivalent

heterocyclic group; or a bivalent heterocyclic group which is substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino groups.

- [22] Z1 to Z4 are each independently hydrogen; aliphatic hydrocarbons having a carbon number of 1 - 20; aromatic hydrocarbons; aromatic hydrocarbons which are substituted with at least one substituent group selected from the group consisting of the nitro, nitrile, halogen, alkyl, alkoxy, amino, aromatic hydrocarbon, and heterocyclic groups; a silicon group substituted with aromatic hydrocarbons; a heterocyclic group; a heterocyclic group which is substituted with at least one substituent group selected from the group consisting of the nitro, nitrile, halogen, alkyl, alkoxy, amino, aromatic hydrocarbon, and heterocyclic groups; a thiophenyl group which is substituted with hydrocarbons having a carbon number of 1 - 20 or aromatic hydrocarbons having a carbon number of 6 - 20; or a boron group which is substituted with aromatic hydrocarbons.
- [23] R1 to R11 are each independently hydrogen, a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkoxy group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted arylamine group, a substituted or unsubstituted heterocyclic group, an amino group, a nitrile group, a nitro group, a halogen group, an amide group, or an ester group. R1 to R11 may form aliphatic or hetero condensation rings along with adjacent groups.
- [24] R12 to R15 are each independently hydrogen, a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkoxy group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted heterocyclic group, an amino group, a nitrile group, a nitro group, a halogen group, an amide group, or an ester group. R12 to R15 may form aliphatic or hetero condensation rings along with adjacent groups.
- [25] R7 and R8 may be directly connected to each other, or may form a condensation ring along with a group selected from the group consisting of O, S, NR, PR, C=O, CRR', and SiRR', R and R' independently or collectively being hydrogen, a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkoxy group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted arylamine group, a substituted or unsubstituted heterocyclic group, a nitrile group, an amide group, or an ester group. R7 and R8 may form a condensation ring to form a spiro compound.
- [26] A detailed description will be given of the substituent groups of Formula 1.
- [27] In Z1 to Z4 as the substituent groups of Formula 1, the aromatic hydrocarbons are exemplified by monocyclic aromatic rings, such as phenyl, biphenyl, and terphenyl, and multicyclic aromatic rings, such as naphthyl, anthracenyl, pyrenyl, and perylenyl.

The heterocyclic group is exemplified by thiophene, furan, pyrrole, imidazole, thiazole, oxazole, oxadiazole, thiadiazole, triazole, pyridyl, pyridazyl, pyrazine, quinoline, and isoquinoline.

- [28] Examples of aliphatic hydrocarbons having a carbon number of 1 - 20 include straight chain aliphatic hydrocarbons, branched chain aliphatic hydrocarbons, saturated aliphatic hydrocarbons, and unsaturated aliphatic hydrocarbons. They are exemplified by an alkyl group, such as a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a ter-butyl group, a pentyl group, and a hexyl group; an alkenyl group having a double bond, such as styryl; and an alkynyl group having a triple bond, such as an acetylene group.
- [29] The carbon number of the alkyl, alkoxy, and alkenyl groups of R1 to R15 of Formula 1 is not limited, but is preferably 1 - 20.
- [30] The length of the alkyl group contained in the compound does not affect the conjugate length of the compound, but may affect the method of applying the compound to the organic light emitting device, for example, a vacuum deposition method or a solution coating method.
- [31] Illustrative, but non-limiting, examples of the aryl group of R1 to R15 of Formula 1 include monocyclic aromatic rings, such as a phenyl group, a biphenyl group, a terphenyl group, and a stilbene group, and multicyclic aromatic rings, such as a naphthyl group, an anthracenyl group, a phenanthrene group, a pyrenyl group, and a perylenyl group.
- [32] Illustrative, but non-limiting, examples of the arylamine group of R1 to R11 of Formula 1 include a diphenylamine group, a dinaphthylamine group, a dibiphenylamine group, a phenylnaphthylamine group, a phenyldiphenylamine group, a ditolylamine group, a phenyltolylamine group, a carbazolyl group, and a triphenylamine group.
- [33] Illustrative, but non-limiting, examples of the heterocyclic group of R1 to R15 of Formula 1 include a thiophenyl group, a furan group, a pyrrolyl group, an imidazolyl group, a thiazolyl group, an oxazolyl group, an oxadiazolyl group, a triazolyl group, a pyridyl group, a pyridazine group, a quinolinyl group, an isoquinoline group, and an acridyl group.
- [34] In addition, illustrative, but non-limiting, examples of the alkenyl, aryl, arylamine, and heterocyclic groups of R1 to R15 of Formula 1 include compounds shown in the following Formulae.
- [35]




- [36] In the above Formulae, Z is a group selected from the group consisting of hydrogen, aliphatic hydrocarbons having a carbon number of 1 - 20, an alkoxy group, an arylamine group, an aryl group, a heterocyclic group, a nitrile group, and an acetylene group. Examples of the arylamine, aryl, and heterocyclic groups of Z are as shown in the above-mentioned substituent groups of R1 to R15.
- [37] According to a preferred embodiment of the present invention, X of Formula 1 is C, and R7 and R8 are directly connected to each other, or form a condensation ring along with a group selected from the group consisting of O, S, NR, PR, C=O, CRR', and SiRR' (R and R' are as defined in Formula 1).


[38] According to another preferred embodiment of the present invention, X of Formula 1 is Si, and R7 and R8 may be directly connected to each other, or form a condensation ring along with a group selected from the group consisting of O, S, NR, PR, CRR', and SiRR' (R and R' are as defined in Formula 1).

[39] According to still another preferred embodiment of the present invention, the compound of Formula 1 is any one of compounds of the following Formulae 2 to 5.

[40]




[Formula 2]




[Formula 3]

[41]



[Formula 4]





[Formula 5]



[42] In the above Formulae, A is as defined in Formula 1.


[43] Illustrative, but non-limiting, examples of a group A of Formula 1 are as follows.

[44]




[45]







[46]




[47]




[48]




[49]







[50]








[51]





[52]













[53]




[54]





[55]




[56]












[57]















[58]





[59]

**218****219****220****221****222****223****224****225****226**


[60]

**227****228****229****230****231****232****233****234****235****236****237****238**







261




262




263




264




265



266




267




268


[62]




269



270





271













272

[63]




















[64]
















**286****287****288****289****290****291****292****293****294**














[65]









**295****296****297****298**




















[66]






374







388




389




390




391




392




393




394




395




396




397
















398




399



















400






[68]






[70]



[71]



[72]

Brief Description of the Drawings

[73] FIG. 1 illustrates an organic light emitting device comprising a substrate 1, an anode 2, a light emitting layer 3, and a cathode 4; and

[74] FIG. 2 illustrates an organic light emitting device comprising a substrate 1, an anode 2, a hole injection layer 5, a hole transport layer 6, a light emitting layer 7, an electron transport layer 8, and a cathode 4.

[75]

Best Mode for Carrying Out the Invention


[76] Hereinafter, a detailed description will be given of the present invention.

[77] Various substituent groups are introduced into a core structure shown in Formula 1,

in detail, the core structure in which a fluorene group is bonded to a combination of an acridine group and a carbazolyl group to form a spiro structure, thereby the compound of Formula 1 has characteristics suitable for application to an organic material layer used in an organic light emitting device. This will be described in detail, below.

[78] The steric core structure of the compound of Formula 1, for convenience of explanation, can be divided into two portions, A and B, as shown in the following Formula.

[79]



[80] The compound of Formula 1 has the steric core structure in which a plane A meets with a plane B at right angles around X, and conjugation does not occur between the A and B portions around X. Furthermore, since one nitrogen atom is positioned among three aryl groups in the plane B, conjugation is limited in the plane B.

[81] The conjugation length of the compound has a close relationship with an energy band gap. In detail, the energy band gap is reduced as the conjugation length of the compound increases. As described above, since a conjugation structure is limited in the core structure of the compound of Formula 1, the core structure has a large energy band gap.

[82] As described above, in the present invention, various substituent groups are introduced to R1 to R15 positions and Z1 to Z2 positions of the core structure having the large energy band gap so as to produce compounds having various energy band gaps. Generally, it is easy to control the energy band gap by introducing substituent groups into a core structure having a large energy band gap, but it is difficult to significantly control the energy band gap by introducing substituent groups into a core structure having a small energy band gap. Furthermore, in the present invention, it is possible to control HOMO and LUMO energy levels of the compound by introducing various substituent groups into the R1 to R15 positions and the Z1 to Z4 positions of the core structure.

- [83] Additionally, by introducing various substituent groups into the core structure, compounds having intrinsic characteristics of the substituent groups can be synthesized. For example, substituent groups, which are frequently applied to hole injection layer materials, hole transport layer materials, light emitting layer materials, and electron transport layer materials which are used during the production of the organic light emitting device, are introduced into the core structure so as to produce substances capable of satisfying requirements of each organic material layer. For example, since the core structure of the compound of Formula 1 includes the arylamine structure, it has an energy level suitable for the hole injection and/or hole transport materials in the organic light emitting device. In the present invention, the compound having the proper energy level is selected depending on the substituent group among the compounds represented by Formula 1 to be used in the organic light emitting device, thereby it is possible to realize a device having a low actuating voltage and a high light efficiency.
- [84] Furthermore, various substituent groups are asymmetrically introduced into the core structure (A is located at one side of the core structure) so as to precisely control the energy band gap, improve interfacial characteristics with organic materials, and apply the compound to various fields.
- [85] As well, if the number of amine contained in the substituent group A is set to 2 or more (if Z1 and Z2 are hetero aromatic amine compounds, the number of nitrogen contained in them is not counted), it is possible to precisely control the HOMO and LUMO energy levels and the energy band gap, and on the other hand interfacial characteristics with the organic materials is improved and thereby make it possible to apply the compound to various fields.
- [86] Additionally, various substituent groups are introduced into the steric structure of the compound of Formula 1 using spiro bonding to control the three-dimensional structure of the organic material so as to minimize π - π interaction in the organic material, thereby formation of excimers is prevented.
- [87] With respect to the energy band gap and the energy level, for example, since the compound of Formula 2-2, in which arylamine is introduced into the hole transport material or the hole injection material of the structure of Formula 1, has HOMO of 5.31 eV, it has an energy level suitable for the hole injection layer or the hole transport layer. Meanwhile, the compound of Formula 2-1 has the band gap of 2.99 eV, which is still larger than that of NPB, typically used as the hole transport layer material, thus it has a LUMO value of about 2.32 eV, which is considered to be very high. If a compound having a high LUMO value is used as the hole transport layer, it increases the energy wall of LUMO of the material constituting the light emitting layer to prevent the movement of electrons from the light emitting layer to the hole transport

layer. Accordingly, the above-mentioned compound improves the light emission efficiency of the organic light emitting device so that efficiency is higher than that of conventionally used NPB (HOMO 5.4 eV, LUMO 2.3 eV, and energy band gap 3.1 eV). In the present invention, the energy band gap is calculated by a typical method using a UV-VIS spectrum.

[88] As well, the compound of Formula 1 has stable redox characteristics. Redox stability is estimated using a CV (cyclovoltammetry) method. For example, if oxidation voltage is repeatedly applied to the compound of Formula 2-1, oxidation repeatedly occurs at the same voltage and the current amount is the same. This means that the compound has excellent stability to oxidation.

[89] Meanwhile, since the compound of Formula 1 has a high glass transition temperature (T_g), it has excellent thermal stability. For example, the glass transition temperature of the compound of Formula 2-1 is 150°C, which is still higher than that of conventionally used NPB (T_g: 96°C). Such increase in thermal stability is an important factor providing actuating stability to the device.

[90] Furthermore, the compound of Formula 1 may be used to form the organic material layer using a vacuum deposition process or a solution coating process during the production of the organic light emitting device. In connection with this, illustrative, but non-limiting, examples of the solution coating process include a spin coating process, a dip coating process, an inkjet printing process, a screen printing process, a spray process, and a roll coating process.

[91] Tertiary alcohol, which is produced by a reaction of a lithiated aryl and keto group, is heated in the presence of an acid catalyst to form a hexagonal cyclic structure while water is removed, thereby producing the compound having a spiro structure according to the present invention. The above-mentioned procedure for producing the compound is well known in the art, and those skilled in the art can change the production conditions during the production of the compound of Formula 1. The production will be described in detail in the preparation examples later.

[92] The organic light emitting device of the present invention can be produced using known materials through a known process, modified only in that at least one layer of organic material layer(s) include the compound of the present invention, that is, the compound of Formula 1.

[93] The organic material layer(s) of the organic light emitting device according to the present invention may have a single layer structure, or alternatively, a multilayered structure in which two or more organic material layers are layered. For example, the organic light emitting device of the present invention may comprise a hole injection layer, a hole transport layer, a light emitting layer, an electron transport layer, and an electron injection layer as the organic material layer(s). However, the structure of the

organic light emitting device is not limited to this, but may comprise a smaller number of organic material layers.

[94] Furthermore, the organic light emitting device of the present invention may be produced, for example, by sequentially layering a first electrode, organic material layer(s), and a second electrode on a substrate. In connection with this, a physical vapor deposition (PVD) method, such as a sputtering method or an e-beam evaporation method, may be used, but the method is not limited to these.

[95] A method of producing the compound of Formula 1 and the production of the organic light emitting device using the same will be described in detail in the following preparation examples and examples. However, the following preparation examples and examples are set forth to illustrate, but are not to be construed to limit the present invention.


[96]

Mode for the Invention


[97] A better understanding of a method of producing an organic compound represented by Formula 1 and the production of an organic light emitting device using the same may be obtained in light of the following preparation examples and examples which are set forth to illustrate, but are not to be construed to limit the present invention.

[98] In order to produce the compound represented by Formula 1, any one of the compounds of the following Formulae, a to c, may be used as a starting material.


[99]



[formula a]



[formula b]



[formula c]

[100] PREPARATION EXAMPLE 1: Preparation of a starting material represented by Formula a

[101]

[102] Carbazole (1.672 g, 10 mmol), 1-bromo-2-iodobenzene (1.5 ml, 12 mmol), potassium carbonate (K_2CO_3 , 2.7646 g, 20 mmol), copper iodide (CuI, 95 mg, 0.5 mmol), and 25 ml of xylene were refluxed in a nitrogen atmosphere. After cooling to normal temperature, a product was extracted with ethyl acetate, water was removed

with anhydrous magnesium sulfate (MgSO_4), and the solvent was removed at a reduced pressure. The resulting product was passed through a silica gel column using a hexane solvent to produce a compound, the solvent was removed at a reduced pressure, and vacuum drying was conducted to produce the resulting white solid compound (800 mg, 25 % yield). MS: $[\text{M}+\text{H}]^+ = 323$.

[103]

[104] PREPARATION EXAMPLE 2: Preparation of a starting material represented by Formula b

[105]

[106] 4.19 g of starting material represented by Formula a (13 mmol) were dissolved in 50 ml of purified THF, and 4.8 ml of n-BuLi (2.5 M in hexane, 12 mmol) were slowly dropped thereon at -78°C . Stirring was conducted at the same temperature for 45 min, and 2.59 g of 2-bromo-9-fluorenone (10.0 mmol) were added thereto. After stirring at the same temperature for 1 hour, the temperature was raised to normal temperature, stirring was carried out for an additional 2 hours, and the reaction was completed in a NH_4Cl aqueous solution. An organic material was extracted with ethyl ether, water was removed therefrom, and an organic solvent was removed to produce yellow solid. The produced solid was dispersed in ethanol, stirred, filtered, and vacuum dried to obtain 4.5 g of intermediate material. The intermediate solid was dispersed in 40 ml of acetic acid, 12 drops of concentrated sulfuric acid were added thereto, and reflux was conducted for 3 hours. After cooling to normal temperature, the resulting solid was filtered, washed with ethanol, and vacuum dried to create 3.98 g of product (82.2 % yield). MS: $[\text{M}+\text{H}]^+ = 484$.

[107]

[108] PREPARATION EXAMPLE 3: Preparation of a starting material represented by Formula c

[109]

[110] The starting material represented by Formula c (5.0 g, 10.32 mmol) was completely dissolved in 40 ml of THF, 4-chloro-phenylboronic acid (2.42 g, 15.48 mmol), 2M potassium carbonate solution, tetrakis(triphenylphosphine)palladium(0) (0.31 mmol, 0.36 g), and 10 ml of ethanol were added thereto, and reflux was conducted for 24 hours. After the reaction was completed, cooling to normal temperature was conducted, and filtration was conducted. Washing was conducted with water and ethanol, several times. Recrystallization was conducted with ethanol, and vacuum drying was conducted to produce a compound (4.97 g, yield 93 %). MS: $[\text{M}+\text{H}]^+ = 515$.

[111]

[112] EXAMPLE 1: Preparation of the compound represented by Formula 2-2

[113]

[114] 1) Synthesis of arylamine (4-(N-phenyl-N-phenylamino)phenyl-1-naphthylamine) to produce the compound represented by Formula 2-2: 15.0 g of 4-bromophenyl-N-phenyl-N-phenylamine (46.3 mmol) and 7.29 g of 1-naphthylamine (50.9 mmol) were dissolved in 200 ml of toluene, 13.34 g of sodium-tert-butoxide (138.8 mmol), 0.53 g of bis(dibenzylidene acetone)palladium(0) (0.93 mmol), and 0.56 ml of 50 wt% tri-tert-butylphosphine toluene solution (1.39 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. A column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (13 g, yield 73 %). MS: $[M+H]^+ = 386$.

[115] 2) 5.00 g of compound of Formula b (10.3 mmol) and 4.78 g of 4-(N-phenyl-N-phenylamino)phenyl-1-naphthylamine (12.4 mmol) were dissolved in 50 ml of toluene, 5.89 g of sodium-tert-butoxide (61.3 mmol), 0.12 g of bis(dibenzylidene acetone)dipalladium(0) (0.21 mmol), and 0.15 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.31 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. A column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 4:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-2 (4.3 g, yield 53 %). MS: $[M+H]^+ = 789$.

[116]

[117] EXAMPLE 2: Preparation of the compound represented by Formula 2-256

[118]

[119] 1) Synthesis of arylamine (4-(N,N-diphenylamino)-biphenyl-N-phenylamine) to produce the compound represented by Formula 2-256: 4.00 g of 4-chlorobiphenyl-N,N-diphenylamine (11.2 mmol) and 1.13 ml of aniline (12.4 mmol) were dissolved in 100 ml of toluene, 2.70 g of sodium-tert-butoxide (28.1 mmol), 0.13 g of bis(dibenzylidene acetone)palladium(0) (0.23 mmol), and 0.17 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.34 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 5 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (3.8 g, yield 81 %). MS: $[M+H]^+ = 413$.

[120] 2) 3.62 g of compound of Formula b (7.47 mmol) and 3.4 g of 4-(N,N-diphenylamino)-biphenyl-N-phenylamine (8.2 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.09 g of bis(dibenzylidene acetone)palladium(0) (0.16 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-256 (3.5 g, yield 53 %). MS: $[M+H]^+ = 817$.

[121]

[122] EXAMPLE 3: Preparation of the compound represented by Formula 2-257

[123]

[124] 1) Synthesis of arylamine (4-(N,N-diphenylamino)-biphenyl-N-naphthylamine) to produce the compound represented by Formula 2-257: 8.80 g of 4-chlorobiphenyl-N,N-diphenylamine (24.7 mmol) and 5.31 g of 1-naphthylamine (37.1 mmol) were dissolved in 200 ml of toluene, 5.94 g of sodium-tert-butoxide (61.8 mmol), 0.43 g of bis(dibenzylidene acetone)palladium(0) (0.74 mmol), and 0.61 ml of 50 wt% tri-tert-butylphosphine toluene solution (1.24 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 5 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (7.0 g, yield 61 %). MS: $[M+H]^+ = 413$.

[125] 2) 3.62 g of compound of Formula b (7.47 mmol) and 3.8 g of 4-(N,N-diphenylamino)-biphenyl-N-naphthylamine (8.2 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.09 g of bis(dibenzylidene acetone)palladium(0) (0.16 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-257 (3.5 g, yield 54 %). MS: $[M+H]^+ = 867$.

[126]

[127] EXAMPLE 4: Preparation of the compound represented by Formula 2-259

[128]

[129] 1) Synthesis of arylamine (4-(N,N-diphenylamino)-biphenyl-N-biphenylamine) to produce the compound represented by Formula 2-259: 8.80 g of 4-chlorobiphenyl-N,N-diphenylamine (24.7 mmol) and 6.28 g of 4-aminobiphenyl (37.1 mmol) were dissolved in 200 ml of toluene, 5.94 g of sodium-tert-butoxide (61.8 mmol), 0.43 g of bis(dibenzylidene acetone)palladium(0) (0.74 mmol), and 0.61 ml of 50 wt% tri-tert-butylphosphine toluene solution (1.24 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 5 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (7.0 g, yield 58 %). MS: $[M+H]^+ = 489$.

[130] 2) 3.62 g of compound of Formula b (7.47 mmol) and 4.0 g of 4-(N,N-diphenylamino)-biphenyl-N-biphenylamine (8.2 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.09 g of bis(dibenzylidene acetone)palladium(0) (0.16 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-259 (3.5 g, yield 53 %). MS: $[M+H]^+ = 893$.

[131]

[132] EXAMPLE 5: Preparation of the compound represented by Formula 2-273

[133]

[134] 1) Synthesis of arylamine (4-(N-phenyl-N-naphthylamino)-biphenyl-N-phenylamine) to produce the compound represented by Formula 2-273: 4.08 g of 4-chlorobiphenyl-N-phenyl-N-naphthylamine (10.1 mmol) and 1.38 ml of aniline (15.1 mmol) were dissolved in 100 ml of toluene, 2.90 g of sodium-tert-butoxide (30.2 mmol), 0.17 g of bis(dibenzylidene acetone)palladium(0) (0.30 mmol), and 0.26 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.53 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 7 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (3.8 g, yield 82 %). MS: $[M+H]^+ = 463$.

[135] 2) 3.13 g of compound of Formula b (6.47 mmol) and 3.3 g of

4-(N-phenyl-N-naphthylamino)-biphenyl-N-phenylamine (7.1 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.08 g of bis(dibenzylidene acetone)palladium(0) (0.14 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-273 (2.5 g, yield 45 %). MS: $[M+H]^+ = 867$.

[136]

[137] EXAMPLE 6: Preparation of the compound represented by Formula 2-274

[138]

[139] 1) Synthesis of arylamine

(4-(N-phenyl-N-naphthylamino)-biphenyl-N-naphthylamine) to produce the compound represented by Formula 274: 4.08 g of 4-chlorobiphenyl-N-phenyl-N-naphthylamine (10.1 mmol) and 2.16 g of 1-naphthylamine (15.1 mmol) were dissolved in 100 ml of toluene, 2.90 g of sodium-tert-butoxide (30.2 mmol), 0.17 g of bis(dibenzylidene acetone)palladium(0) (0.30 mmol), and 0.26 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.53 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 7 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (3.8 g, yield 74 %). MS: $[M+H]^+ = 513$.

[140]

2) 3.62 g of compound of Formula b (7.47 mmol) and 3.8 g of 4-(N-phenyl-N-naphthylamino)-biphenyl-N-naphthylamine (7.4 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.089 g of bis(dibenzylidene acetone)palladium(0) (0.16 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-274 (3.0 g, yield 44 %). MS: $[M+H]^+ = 917$.

[141]

[142] EXAMPLE 7: Preparation of the compound represented by Formula 2-276

[143]

[144] 1) Synthesis of arylamine

(4-(N-phenyl-N-naphthylamino)-biphenyl-N'-biphenylamine) to produce the compound represented by Formula 276: 4.08 g of 4-chlorobiphenyl-N-phenyl-N-naphthylamine (10.1 mmol) and 2.55 g of 4-aminobiphenyl (15.1 mmol) were dissolved in 100 ml of toluene, 2.90 g of sodium-tert-butoxide (30.2 mmol), 0.17 g of bis(dibenzylidene acetone)palladium(0) (0.30 mmol), and 0.26 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.53 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 7 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (3.8 g, yield 70 %). MS: $[M+H]^+ = 539$.

[145]

2) 3.13 g of compound of Formula b (6.47 mmol) and 3.8 g of 4-(N-phenyl-N-naphthylamino)-biphenyl-N'-biphenylamine (7.1 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.081 g of bis(dibenzylidene acetone)palladium(0) (0.14 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-276 (2.5 g, yield 41 %). MS: $[M+H]^+ = 943$.

[146]

[147] EXAMPLE 8: Preparation of the compound represented by Formula 2-307

[148]

[149] 1) Synthesis of arylamine

(4-(N-phenyl-N-biphenylamino)-biphenyl-N'-phenylamine) to produce the compound represented by Formula 307: 4.86 g of 4-chlorobiphenyl-N-phenyl-N-biphenylamine (11.2 mmol) and 1.13 ml of aniline (12.4 mmol) were dissolved in 100 ml of toluene, 2.70 g of sodium-tert-butoxide (28.1 mmol), 0.13 g of bis(dibenzylidene acetone)palladium(0) (0.23 mmol), and 0.17 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.34 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 7 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of

10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (3.8 g, yield 69 %). MS: $[M+H]^+ = 489$.

- [150] 2) 3.13 g of compound of Formula b (6.47 mmol) and 3.5 g of 4-(N-phenyl-N-biphenylamino)-biphenyl-N'-phenylamine (7.1 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.081 g of bis(dibenzylidene acetone)palladium(0) (0.14 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-307 (2.6 g, yield 45 %). MS: $[M+H]^+ = 893$.

[151]

[152] EXAMPLE 9: Preparation of the compound represented by Formula 2-308

[153]

[154] 1) Synthesis of arylamine

(4-(N-phenyl-N-biphenylamino)-biphenyl-N'-naphthylamine) to produce the compound represented by Formula 308: 4.86 g of 4-chlorobiphenyl-N-phenyl-N-biphenylamine (11.2 mmol) and 1.78 ml of 1-naphthylamine (12.4 mmol) were dissolved in 100 ml of toluene, 2.70 g of sodium-tert-butoxide (28.1 mmol), 0.13 g of bis(dibenzylidene acetone)palladium(0) (0.23 mmol), and 0.17 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.34 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 7 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (4.0 g, yield 69 %). MS: $[M+H]^+ = 539$.

- [155] 2) 3.13 g of compound of Formula b (6.47 mmol) and 3.8 g of 4-(N-phenyl-N-biphenylamino)-biphenyl-N'-naphthylamine (7.1 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.081 g of bis(dibenzylidene acetone)palladium(0) (0.14 mmol), and 0.11 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.22 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and

vacuum drying was conducted to produce the compound of Formula 2-308 (3.1 g, yield 51 %). MS: $[M+H]^+ = 943$.

[156]

[157] EXAMPLE 10: Preparation of the compound represented by Formula 2-310

[158]

[159] 1) Synthesis of arylamine

(4-(N-phenyl-N-biphenylamino)-biphenyl-N'-biphenylamine) to produce the compound represented by Formula 310: 4.86 g of 4-chlorobiphenyl-N-phenyl-N-biphenylamine (11.2 mmol) and 2.09 ml of 4-aminobiphenyl (12.4 mmol) were dissolved in 100 ml of toluene, 2.70 g of sodium-tert-butoxide (28.1 mmol), 0.13 g of bis(dibenzylidene acetone)palladium(0) (0.23 mmol), and 0.17 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.34 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 5 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 10:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce an arylamine connection group (3.6 g, yield 56 %). MS: $[M+H]^+ = 565$.

[160]

2) 2.92 g of compound of Formula b (6.02 mmol) and 3.57 g of 4-(N-phenyl-N-biphenylamino)-biphenyl-N'-biphenylamine (6.32 mmol) were dissolved in 40 ml of toluene, 1.94 g of sodium-tert-butoxide (22.4 mmol), 0.073 g of bis(dibenzylidene acetone)palladium(0) (0.13 mmol), and 0.10 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.19 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. After a column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 8:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 2-310 (2.5 g, yield 43 %). MS: $[M+H]^+ = 969$.

[161]

[162] EXAMPLE 11: Preparation of the compound represented by Formula 3-2

[163]

[164] 1) Synthesis of arylamine (4-(N-phenyl-N-phenylamino)phenyl-1-naphthylamine) to produce the compound represented by Formula 3-2: Synthesis was conducted through the same procedure as in synthesis of the arylamine connection group of Formula 2-2.

[165]

2) 4.97 g of compound of Formula c (9.63 mmol) and 5.58 g of 4-(N-phenyl-N-phenylamino)phenyl-1-naphthylamine (12.4 mmol) were dissolved in

50 ml of toluene, 1.85 g of sodium-tert-butoxide (19.3 mmol), 0.11 g of bis(dibenzylidene acetone)palladium(0) (0.19 mmol), and 0.14 ml of 50 wt% tri-tert-butylphosphine toluene solution (0.29 mmol) were added thereto, and reflux was conducted in a nitrogen atmosphere for 2 hours. Distilled water was added to the reaction solution to complete the reaction, and the organic layer was extracted. A column separation process was conducted using a solvent of n-hexane and tetrahydrofuran at a ratio of 4:1, stirring was conducted using petroleum ether, and vacuum drying was conducted to produce the compound of Formula 3-2 (4.5 g, yield 54 %). MS: $[M+H]^+ = 865$.

[166]


[167] EXAMPLE 12: Production of an organic light emitting device

[168]

[169] Hexanitrile hexaazatriphenylene (hereinafter, referred to as "HAT") of the following Formula was vacuum deposited to a thickness of 500 Å by heating on a transparent ITO electrode, which was prepared through the above procedure, so as to form an anode including an ITO conductive layer and an N-type organic material.

[170]


[HAT]



[171] The compound of Formula 2-2 (400 Å) was vacuum deposited thereon to form a hole transport layer. Alq3 was vacuum deposited to a thickness of 300 Å on the hole transport layer to form a light emitting layer. An electron transport layer material of the following Formula was deposited to a thickness of 200 Å on the light emitting layer to form an electron transport layer.

[172]

Electron transport layer
material



[173] Lithium fluoride (LiF) having a thickness of 12 Å and aluminum having a thickness of 2000 Å were sequentially deposited on the electron transport layer to form a cathode.

[174] In the above procedure, the deposition speed of an organic material was maintained at 0.3 - 0.8 Å/sec. Furthermore, lithium fluoride and aluminum were deposited at speeds of 0.3 Å/sec and 1.5 - 2.5 Å/sec, respectively, on the cathode. During the deposition, a vacuum was maintained at $1 - 3 \times 10^{-7}$.

[175] The resulting device had an electric field of 7.44 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 1.69 lm/W. The operation and light emission of the device at the above-mentioned actuating voltage mean that the compound of Formula 2-2, which formed the layer between the hole injection layer and the light emitting layer, functions to transport holes.

[176]

[177] EXAMPLE 13: Production of an organic light emitting device

[178]

[179] HAT was deposited on an ITO substrate, which was prepared through the procedure of example 12, to a thickness of 80 Å to form a thin film. The thin film can improve the characteristics of an interface of the substrate and a hole injection layer. Subsequently, the compound of Formula 2-2 was deposited on the thin film to a thickness of 800 Å to form the hole injection layer.

[180] NPB was deposited on the hole injection layer to a thickness of 300 Å so as to form a hole transport layer, and Alq3 was then deposited thereon to a thickness of 300 Å to form a light emitting layer. An electron transport layer and a cathode were formed on the light emitting layer through the same procedure as example 14.

[181] In the present example, deposition speeds of an organic material and the cathode were the same as those of example 12.

[182] The resulting device had an electric field of 9.36 V at a forward current density of

100 mA/cm², and a spectrum having a light efficiency of 2.38 lm/W. The operation and light emission of the device at the above-mentioned actuating voltage mean that the compound of Formula 2-2, which formed the layer between the thin film on the substrate and the hole transport layer, functions to inject holes.

[183]

[184] EXAMPLE 14: Production of an organic light emitting device

[185]

[186] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-256 was used as the hole transport layer instead of the compound of Formula 2-2.

[187] The resulting device had an electric field of 8.05 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.01 lm/W.

[188]

[189] EXAMPLE 15: Production of an organic light emitting device

[190]

[191] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-257 was used as the hole transport layer instead of the compound of Formula 2-2.

[192] The resulting device had an electric field of 8.08 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.37 lm/W.

[193]

[194] EXAMPLE 16: Production of an organic light emitting device

[195]

[196] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-259 was used as the hole transport layer instead of the compound of Formula 2-2.

[197] The resulting device had an electric field of 8.00 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.23 lm/W.

[198]

[199] EXAMPLE 17: Production of an organic light emitting device

[200]

[201] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-273 was used as the hole transport layer instead of the compound of Formula 2-2.

[202] The resulting device had an electric field of 8.02 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.16 lm/W.

[203]

[204] EXAMPLE 18: Production of an organic light emitting device

[205]

[206] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-274 was used as the hole transport layer instead of the compound of Formula 2-2.

[207] The resulting device had an electric field of 4.43 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.24 lm/W.

[208]

[209] EXAMPLE 19: Production of an organic light emitting device

[210]

[211] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-276 was used as the hole transport layer instead of the compound of Formula 2-2.

[212] The resulting device had an electric field of 8.13 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.32 lm/W.

[213]

[214] EXAMPLE 20: Production of an organic light emitting device

[215]

[216] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-307 was used as the hole transport layer instead of the compound of Formula 2-2.

[217] The resulting device had an electric field of 8.05 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.03 lm/W.

[218]

[219] EXAMPLE 21: Production of an organic light emitting device

[220]

[221] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-308 was used as the hole transport layer instead of the compound of Formula 2-2.

[222] The resulting device had an electric field of 8.07 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.23 lm/W.

[223]

[224] EXAMPLE 22: Production of an organic light emitting device

[225]

[226] The procedure of example 12 was repeated to produce a device except that the compound of Formula 2-310 was used as the hole transport layer instead of the compound of Formula 2-2.

[227] The resulting device had an electric field of 8.01 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 2.19 lm/W.

[228]

[229] EXAMPLE 23: Production of an organic light emitting device

[230]

[231] The procedure of example 12 was repeated to produce a device except that the compound of Formula 3-2 was used as the hole transport layer instead of the compound of Formula 2-2.

[232] The resulting device had an electric field of 7.34 V at a forward current density of 100 mA/cm², and a spectrum having a light efficiency of 1.73 lm/W.

[233]


Industrial Applicability

[234] The compound of the present invention can be used as an organic material layer material, particularly, hole injection and/or transport materials in an organic light emitting device, and when applied to an organic light emitting device it is possible to reduce the actuating voltage of the device, to improve the light efficiency thereof, and to improve the lifespan of the device through the thermal stability of the compound.

Claims


- [1] An organic light emitting device, comprising:
 a first electrode;
 organic material layer(s) comprising a light emitting layer, wherein at least one layer of the organic material layer(s) includes the compound of Formula 1 or a compound of Formula 1 into which a thermosetting or photo-crosslinkable functional group is introduced; and
 a second electrode;
 wherein the first electrode, the organic material layer(s), and the second electrode form layered structure.

[Formula 1]



wherein X is C or Si;

A is



;

a is zero or positive integer;

Y is a bond; bivalent aromatic hydrocarbons; bivalent aromatic hydrocarbons which are substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino groups; a bivalent heterocyclic group; or a bivalent heterocyclic group which is substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino groups;

Y1 and Y2 are each bivalent aromatic hydrocarbons; bivalent aromatic hydrocarbons which are substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino

groups; a bivalent heterocyclic group; or a bivalent heterocyclic group which is substituted with at least one substituent group selected from the group consisting of nitro, nitrile, halogen, alkyl, alkoxy, and amino groups;

Z1 to Z4 are each independently hydrogen; aliphatic hydrocarbons having a carbon number of 1 - 20; aromatic hydrocarbons; aromatic hydrocarbons which are substituted with at least one substituent group selected from the group consisting of the nitro, nitrile, halogen, alkyl, alkoxy, amino, aromatic hydrocarbon, and heterocyclic groups; a silicon group substituted with aromatic hydrocarbons; a heterocyclic group; a heterocyclic group which is substituted with at least one substituent group selected from the group consisting of the nitro, nitrile, halogen, alkyl, alkoxy, amino, aromatic hydrocarbon, and heterocyclic groups; a thiophenyl group which is substituted with hydrocarbons having a carbon number of 1 - 20 or aromatic hydrocarbons having a carbon number of 6 - 20; or a boron group which is substituted with aromatic hydrocarbons;


R1 to R11 are each independently hydrogen, a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkoxy group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted arylamine group, a substituted or unsubstituted heterocyclic group, an amino group, a nitrile group, a nitro group, a halogen group, an amide group, or an ester group, R1 to R11 may form aliphatic or hetero condensation rings along with adjacent groups;

R12 to R15 are each independently hydrogen, a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkoxy group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted heterocyclic group, an amino group, a nitrile group, a nitro group, a halogen group, an amide group, or an ester group, R12 to R15 may form aliphatic or hetero condensation rings along with adjacent groups; and


R7 and R8 may be directly connected to each other, or may form a condensation ring along with a group selected from the group consisting of O, S, NR, PR, C=O, CRR', and SiRR', wherein R and R' each independently or collectively are hydrogen, a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkoxy group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted arylamine group, a substituted or unsubstituted heterocyclic group, a nitrile group, an amide group, or an ester group, and may form a condensation ring to form a spiro compound.

- [2] The organic light emitting device as set forth in claim 1, wherein R7 and R8 of Formula 1 form a condensation ring along with a group selected from the group

[3] The organic light emitting device as set forth in claim 1, wherein the compound of Formula 1 is any one of compounds of Formulae 2 to 5:






















































[Formula 3]





【Formula 5】


[4] The organic light emitting device as set forth in claim 1, wherein A of Formula 1 is any one of following groups:


**1****2****3****4****5****6****7****8****9****10****11****12****13****14****15****16****17****18****19****20****21****22**


























































































**218****219****220****221****222****223****224****225****226****227****228****229****230****231****232****233****234****235****236****237****238**
















**261****262****263****264****265****266****267****268****269****270****271****272**






















































388




389




390




391




392




393




394




395




396




397
















398


















399

















400
















- [5] The organic light emitting device as set forth in claim 1, wherein the organic material layer(s) comprise a hole transport layer, and the hole transport layer includes the compound of Formula 1 or the compound of Formula 1 into which the thermosetting or photo-crosslinkable functional group is introduced.
- [6] The organic light emitting device as set forth in claim 1, wherein the organic material layer(s) comprise a hole injection layer, and the hole injection layer includes the compound of Formula 1 or the compound of Formula 1 into which the thermosetting or photo-crosslinkable functional group is introduced.
- [7] The organic light emitting device as set forth in claim 1, wherein the organic material layer(s) comprise a layer which both injects and transports holes and

which includes the compound of Formula 1 or the compound of Formula 1 into which the thermosetting or photo-crosslinkable functional group is introduced.

[Fig. 1]



[Fig. 2]



INTERNATIONAL SEARCH REPORT

International application No.

PCT/KR2005/003177

A. CLASSIFICATION OF SUBJECT MATTER***C09K 11/06(2006.01)i***

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC8: C09K 11/06, C07D209/86, H05B 33/14, H05B33/20, C08F130/08, H05B33/12

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

KR, JP: classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

JPA, NPS, ESPACENET, USPTO, STN

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO9309074 1993.05.13 Dow Chemical Co., see the whole document	1
A	Chemische Berichte (1984), 117 (8), 2703-13 Tritschler, et al., see the whole document	1
A	US06613454 2003/09/02 TDK Corporation see the whole document	1-7
P, A	US2004/0219386 2004.11.04 Canon Kabushiki Kaisha see the whole document	1-7
A	US06630254 2003/10/07 National Research Council of Canada see the whole document	1-7
A	US06605373 2003/08/12 Dow Global Technologies Inc see the whole document	1-7
A	EP01310539 2003/05/14 Sumitomo Chemical Company, Limited see the whole document	1-7

☐

Further documents are listed in the continuation of Box C.

☐

See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

03 JANUARY 2006 (03.01.2006)

Date of mailing of the international search report

05 JANUARY 2006 (05.01.2006)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

SHIN, JU CHEOL

Telephone No. 82-42-481-8156



INTERNATIONAL SEARCH REPORT

International application No.

PCT/KR2005/003177

A. CLASSIFICATION OF SUBJECT MATTER***C09K 11/06(2006.01)i***

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC8: C09K 11/06, C07D209/86, H05B 33/14, H05B33/20, C08F130/08, H05B33/12

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

KR, JP: classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

JPA, NPS, ESPACENET, USPTO, STN

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO9309074 1993.05.13 Dow Chemical Co., see the whole document	1
A	Chemische Berichte (1984), 117 (8), 2703-13 Tritschler, et al., see the whole document	1
A	US06613454 2003/09/02 TDK Corporation see the whole document	1-7
P, A	US2004/0219386 2004.11.04 Canon Kabushiki Kaisha see the whole document	1-7
A	US06630254 2003/10/07 National Research Council of Canada see the whole document	1-7
A	US06605373 2003/08/12 Dow Global Technologies Inc see the whole document	1-7
A	EP01310539 2003/05/14 Sumitomo Chemical Company, Limited see the whole document	1-7



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

03 JANUARY 2006 (03.01.2006)

Date of mailing of the international search report

05 JANUARY 2006 (05.01.2006)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

SHIN, JU CHEOL

Telephone No. 82-42-481-8156



专利名称(译)	新型化合物及使用其的有机发光装置 (5)		
公开(公告)号	EP1791929A1	公开(公告)日	2007-06-06
申请号	EP2005856362	申请日	2005-09-23
[标]申请(专利权)人(译)	乐金化学股份有限公司		
申请(专利权)人(译)	LG化学有限公司.		
当前申请(专利权)人(译)	LG化学有限公司.		
[标]发明人	JEON BYUNG SUN JANG JUN GI YOON SEOK HEE 302 904 SONGGANG GREEN APT MOON JAE MIN 3 507 LG CHEM DORMITORY		
发明人	CHO, WOOK DONG, 107-1006 EXPO APT., 15/3 464-1 KIM, JI EUN, 7-403 LG CHEMISTRY APT., 381-42 JEON, BYUNG SUN JANG, JUN GI YOON, SEOK HEE, 302-904 SONGGANG GREEN APT. MOON, JAE MIN, 3-507 LG CHEMISTRY DORMITORY		
IPC分类号	C09K11/06 H01L51/54 H05B33/14		
CPC分类号	H01L51/006 C07D221/20 C09K11/06 C09K2211/1022 C09K2211/1029 C09K2211/1458 C09K2211/1466 H01L51/0058 H01L51/0061 H01L51/0072 H01L51/5012 H01L51/5048 H01L51/5088 H05B33/14 Y10S428/917		
优先权	1020040077245 2004-09-24 KR		
其他公开文献	EP1791929A4 EP1791929B1		
外部链接	Espacenet		

摘要(译)

公开了一种有机发光器件。有机发光装置包括第一电极，包括发光层的有机材料层和第二电极。第一电极，有机材料层和第二电极形成层状结构，并且至少一层有机材料层包括式1的化合物或式1的化合物，其中热固性或光固化 - 引入了可交联的功能组。