



(11)

EP 3 336 077 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

11.09.2019 Bulletin 2019/37

(51) Int Cl.:

C09K 11/06 ^(2006.01) **H01L 51/50** ^(2006.01)
C07D 209/86 ^(2006.01) **C07D 209/88** ^(2006.01)
H01L 51/00 ^(2006.01)

(21) Application number: **16848864.1**

(86) International application number:

PCT/KR2016/010351

(22) Date of filing: **13.09.2016**

(87) International publication number:

WO 2017/052138 (30.03.2017 Gazette 2017/13)

(54) **AMINE-BASED COMPOUND AND ORGANIC LIGHT-EMITTING ELEMENT COMPRISING SAME**
AMINBASIERTE VERBINDUNG UND ORGANISCHES LICHEMITTIERENDES ELEMENT DAMIT
COMPOSÉ À BASE D'AMINE ET ÉLÉMENT ÉLECTROLUMINESCENT ORGANIQUE
COMPRENANT CELUI-CI

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

• **KIM, Jin Joo**

Daejeon 34122 (KR)

(30) Priority: **25.09.2015 KR 20150137124**

(74) Representative: **Hoffmann Eitle**

**Patent- und Rechtsanwälte PartmbB
Arabellastraße 30
81925 München (DE)**

(43) Date of publication of application:

20.06.2018 Bulletin 2018/25

(56) References cited:

**WO-A1-2012/039534 WO-A2-2012/091428
JP-A- 2008 195 841 KR-A- 20140 130 297
KR-A- 20150 010 016 US-A1- 2013 207 092
US-A1- 2013 256 649 US-A1- 2015 179 950
US-A1- 2015 179 956**

(73) Proprietor: **LG Chem, Ltd.**
Seoul 07336 (KR)

(72) Inventors:

- **CHA, Yongbum**
Daejeon 34122 (KR)
- **HONG, Sung Kil**
Daejeon 34122 (KR)
- **KIM, Jungbum**
Daejeon 34122 (KR)

Remarks:

The file contains technical information submitted after
the application was filed and not included in this
specification

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[Technical Field]

5 **[0001]** The present specification relates to an amine-based compound and an organic light emitting device comprising the same.

[Background Art]

10 **[0002]** In general, an organic light emitting phenomenon refers to a phenomenon in which electric energy is converted into light energy by using an organic material. An organic light emitting device using the organic light emitting phenomenon usually has a structure including a positive electrode, a negative electrode, and an organic material layer interposed therebetween. Here, the organic material layer may have a multi-layered structure composed of different materials in order to improve the efficiency and stability of an organic light emitting device in many cases, and for example, may be
 15 composed of a hole injection layer, a hole transport layer, a light emitting layer, an electron transport layer, an electron injection layer, and the like. In the structure of the organic light emitting device, if a voltage is applied between two electrodes, holes are injected from a positive electrode into the organic material layer and electrons are injected from a negative electrode into the organic material layer, and when the injected holes and electrons meet each other, an exciton is formed, and light is emitted when the exciton falls down again to a ground state. Amine-based compounds used in
 20 organic light emitting devices have been already disclosed in US 2013/207092, US 2013/256649, JP 2008 195841, KR 2014 0130297, US 2015/179950 and US 2015/179956.

[0003] There is a continuous need for developing a new material for the aforementioned organic light emitting device.

[Disclosure]

25

[Technical Problem]


[0004] The present specification describes an amine-based compound and an organic light emitting device comprising the same.

30

[Technical Solution]

[0005] The present specification provides a compound represented by the following Chemical Formula 1:

35




40

45


Chemical Formula 1

50 in Chemical Formula 1,


55



Y is



Z is



Ar1 is a substituted or unsubstituted aryl group,

L is a direct bond; or a substituted or unsubstituted arylene group,

R1 is hydrogen; deuterium; or a substituted or unsubstituted alkyl group,

R2 and R3 are the same as or different from each other, and are each independently hydrogen; a substituted or unsubstituted alkyl group; or a substituted or unsubstituted aryl group,

a is an integer of 0 to 5,

b is an integer of 0 to 7,

c is an integer of 0 to 11, and when a is 2 or more, R1's are the same as or different from each other,

when b is 2 or more, R2's are the same as or different from each other, and

when c is 2 or more, R3's are the same as or different from each other.

[0006] Further, an exemplary embodiment of the present specification provides an organic light emitting device including: a first electrode; a second electrode provided to face the first electrode; and one or more organic material layers provided between the first electrode and the second electrode, in which one or more layers of the organic material layers include the compound of Chemical Formula 1.

[Advantageous Effects]

[0007] The compound described in the present specification may be used as a material for an organic material layer of an organic light emitting device. The compound according to at least one exemplary embodiment may improve the efficiency, achieve low driving voltage and/or improve lifetime characteristics in the organic light emitting device. In particular, the compound described in the present specification may be used as a material for hole injection, hole transport, hole injection and hole transport, electron blocking, light emission, hole inhibition, electron transport, or electron injection.

[Description of Drawings]

[0008]

FIG. 1 illustrates an example of an organic light emitting device composed of a substrate (1), a positive electrode (2), a light emitting layer (3), and a negative electrode (4).

FIG. 2 illustrates an example of an organic light emitting device composed of a substrate (1), a positive electrode (2), a hole injection layer (5), a hole transport layer (6), a light emitting layer (3), an electron transport layer (7), and a negative electrode (4).


- 1: Substrate
- 2: Positive electrode
- 3: Light emitting layer
- 4: Negative electrode
- 5: Hole injection layer
- 6: Hole transport layer
- 7: Electron transport layer

[Mode for Invention]

Hereinafter, the present specification will be described in more detail.

The present specification provides the compound represented by Chemical Formula 1.

In the present specification,




mean a moiety linked to another substituent.

The term "substituted or unsubstituted" means being unsubstituted or substituted with one or more substituents selected from the group consisting of deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amino group; a phosphine oxide group; an alkoxy group; an aryloxy group; an alkylthioxy group; an arylthioxy group; an alkylsulfoxy group; an arylsulfoxy group; a silyl group; a boron group; a germanium group; an alkyl group; a cycloalkyl group; an alkenyl group; an aryl group; an aralkyl group; an aralkenyl group; an alkylaryl group; an alkylamine group; an aralkylamine group; a heteroarylamine group; an arylamine group; an arylphosphine group; and a heterocyclic group, or being unsubstituted or substituted with a substituent to which two or more substituents among the substituents exemplified above are linked. For example, "the substituent to which two or more substituents are linked" may be a biphenyl group. That is, the biphenyl group may also be an aryl group, and may be interpreted as a substituent to which two phenyl groups are linked.


In the present specification, examples of a halogen group include fluorine, chlorine, bromine or iodine.

In the present specification, the number of carbon atoms of a carbonyl group is not particularly limited, but is preferably 1 to 40. Specifically, the carbonyl group may be a compound having the following structures, but is not limited thereto.




In the present specification, for an ester group, the oxygen of the ester group may be substituted with a straight-

chained, branch-chained, or cyclic alkyl group having 1 to 40 carbon atoms, or an aryl group having 6 to 30 carbon atoms. Specifically, the ester group may be a compound having the following structural formulae, but is not limited thereto.



15 **[0016]** In the present specification, the number of carbon atoms of an imide group is not particularly limited, but is preferably 1 to 25. Specifically, the imide group may be a compound having the following structures, but is not limited thereto.



35 **[0017]** In the present specification, a silyl group may be represented by a chemical formula of $-\text{SiR}_a\text{R}_b\text{R}_c$, and R_a , R_b , and R_c may be each hydrogen; a substituted or unsubstituted alkyl group; or a substituted or unsubstituted aryl group. Specific examples of the silyl group include a trimethylsilyl group, a triethylsilyl group, a t-butyldimethylsilyl group, a vinyl dimethylsilyl group, a propyldimethylsilyl group, a triphenylsilyl group, a diphenylsilyl group, a phenylsilyl group, and the like, but are not limited thereto.

40 **[0018]** In the present specification, a boron group may be represented by a chemical formula of $-\text{BR}_a\text{R}_b$, and R_a and R_b may be each hydrogen; a substituted or unsubstituted alkyl group; or a substituted or unsubstituted aryl group. Specific examples of the boron group include a trimethylboron group, a triethylboron group, a t-butyldimethylboron group, a triphenylboron group, a phenylboron group, and the like, but are not limited thereto.

45 **[0019]** In the present specification, the alkyl group may be straight-chained or branch-chained, and the number of carbon atoms thereof is not particularly limited, but is preferably 1 to 40. According to an exemplary embodiment, the number of carbon atoms of the alkyl group is 1 to 20. According to another exemplary embodiment, the number of carbon atoms of the alkyl group is 1 to 10. According to still another exemplary embodiment, the number of carbon atoms of the alkyl group is 1 to 6. Specific examples of the alkyl group include a methyl group, an ethyl group, a propyl group, an n-propyl group, an isopropyl group, a butyl group, an n-butyl group, an isobutyl group, a tert-butyl group, a sec-butyl group, a 1-methyl-butyl group, an 1-ethyl-butyl group, a pentyl group, an n-pentyl group, an isopentyl group, a neopentyl group, a tert-pentyl group, a hexyl group, an n-hexyl group, a 1-methylpentyl group, a 2-methylpentyl group, a 4-methyl-
50 2-pentyl group, a 3,3-dimethylbutyl group, a 2-ethylbutyl group, a heptyl group, an n-heptyl group, a 1-methylhexyl group, a cyclopentylmethyl group, a cyclohexylmethyl group, an octyl group, an n-octyl group, a tert-octyl group, a 1-methylheptyl group, a 2-ethylhexyl group, a 2-propylpentyl group, an n-nonyl group, a 2,2-dimethylheptyl group, a 1-ethyl-propyl group, a 1,1-dimethyl-propyl group, an isohexyl group, a 4-methylhexyl group, a 5-methylhexyl group, and the like, but are not limited thereto.

55 **[0020]** In the present specification, the alkoxy group may be straight-chained, branch-chained, or cyclic. The number of carbon atoms of the alkoxy group is not particularly limited, but is preferably 1 to 40. Specific examples thereof include methoxy, ethoxy, n-propoxy, isopropoxy, i-propyloxy, n-butoxy, isobutoxy, tert-butoxy, sec-butoxy, n-pentyloxy, neopentyloxy, isopentyloxy, n-hexyloxy, 3,3-dimethylbutyloxy, 2-ethylbutyloxy, n-octyloxy, n-nonyloxy, n-decyloxy, benzy-

loxy, p-methylbenzyloxy, and the like, but are not limited thereto.

[0021] A substituent including an alkyl group, an alkoxy group, and other alkyl group moieties described in the present specification includes both a straight-chained form and a branch-chained form.

[0022] In the present specification, the alkenyl group may be straight-chained or branch-chained, and the number of carbon atoms thereof is not particularly limited, but is preferably 2 to 40. According to an exemplary embodiment, the number of carbon atoms of the alkenyl group is 2 to 20. According to another exemplary embodiment, the number of carbon atoms of the alkenyl group is 2 to 10. According to still another exemplary embodiment, the number of carbon atoms of the alkenyl group is 2 to 6. Specific examples thereof include vinyl, 1-propenyl, isopropenyl, 1-butenyl, 2-butenyl, 3-butenyl, 1-pentenyl, 2-pentenyl, 3-pentenyl, 3-methyl-1-butenyl, 1,3-butadienyl, allyl, 1-phenylvinyl-1-yl, 2-phenylvinyl-1-yl, 2,2-diphenylvinyl-1-yl, 2-phenyl-2-(naphthyl-1-yl)vinyl-1-yl, 2,2-bis(diphenyl-1-yl)vinyl-1-yl, a stilbenyl group, a styrenyl group, and the like, but are not limited thereto.

[0023] In the present specification, a cycloalkyl group is not particularly limited, but has preferably 3 to 60 carbon atoms, and according to an exemplary embodiment, the number of carbon atoms of the cycloalkyl group is 3 to 40. According to another exemplary embodiment, the number of carbon atoms of the cycloalkyl group is 3 to 20. According to still another exemplary embodiment, the number of carbon atoms of the cycloalkyl group is 3 to 6. Specific examples thereof include cyclopropyl, cyclobutyl, cyclopentyl, 3-methylcyclopentyl, 2,3-dimethylcyclopentyl, cyclohexyl, 3-methylcyclohexyl, 4-methylcyclohexyl, 2,3-dimethylcyclohexyl, 3,4,5-trimethylcyclohexyl, 4-tert-butylcyclohexyl, cycloheptyl, cyclooctyl, and the like, but are not limited thereto.

[0024] In the present specification, the number of carbon atoms of an alkylamine group is not particularly limited, but is preferably 1 to 40. Specific examples of the alkylamine group include a methylamine group, a dimethylamine group, an ethylamine group, a diethylamine group, a phenylamine group, a naphthylamine group, a biphenylamine group, an anthracenylamine group, a 9-methyl-anthracenylamine group, a diphenylamine group, a phenyl-naphthylamine group, a ditolylamine group, a phenyltolylamine group, a triphenylamine group, and the like, but are not limited thereto.

[0025] In the present specification, examples of an arylamine group include a substituted or unsubstituted monoarylamine group, a substituted or unsubstituted diarylamine group, or a substituted or unsubstituted triarylamine group. The aryl group in the arylamine group may be a monocyclic aryl group or a polycyclic aryl group. The arylamine group including two or more aryl groups may include a monocyclic aryl group, a polycyclic aryl group, or both a monocyclic aryl group and a polycyclic aryl group.

[0026] Specific examples of the arylamine group include phenylamine, naphthylamine, biphenylamine, anthracenylamine, 3-methyl-phenylamine, 4-methyl-naphthylamine, 2-methyl-biphenylamine, 9-methyl-anthracenylamine, a diphenylamine group, a phenyl-naphthylamine group, a ditolylamine group, a phenyltolylamine group, carbazole, a triphenylamine group, and the like, but are not limited thereto.


[0027] In the present specification, examples of a heteroarylamine group include a substituted or unsubstituted mono-heteroarylamine group, a substituted or unsubstituted diheteroarylamine group, or a substituted or unsubstituted tri-heteroarylamine group. The heteroaryl group in the heteroarylamine group may be a monocyclic heterocyclic group or a polycyclic heterocyclic group. The heteroarylamine group including two or more heterocyclic groups may include a monocyclic heterocyclic group, a polycyclic heterocyclic group, or both a monocyclic heterocyclic group and a polycyclic heterocyclic group.

[0028] In the present specification, examples of an arylphosphine group include a substituted or unsubstituted monoarylphosphine group, a substituted or unsubstituted diarylphosphine group, or a substituted or unsubstituted tri-arylphosphine group. The aryl group in the arylphosphine group may be a monocyclic aryl group, and may be a polycyclic aryl group. The arylphosphine group including two or more aryl groups may include a monocyclic aryl group, a polycyclic aryl group, or both a monocyclic aryl group and a polycyclic aryl group.


[0029] In the present specification, an aryl group is not particularly limited, but has preferably 6 to 60 carbon atoms, and may be a monocyclic aryl group or a polycyclic aryl group. According to an exemplary embodiment, the number of carbon atoms of the aryl group is 6 to 30. According to an exemplary embodiment, the number of carbon atoms of the aryl group is 6 to 20. When the aryl group is a monocyclic aryl group, examples of the monocyclic aryl group include a phenyl group, a biphenyl group, a terphenyl group, and the like, but are not limited thereto. Examples of the polycyclic aryl group include a naphthyl group, an anthracenyl group, a phenanthryl group, a pyrenyl group, a perylenyl group, a triphenyl group, a chrysenyl group, a fluorenyl group, and the like, but are not limited thereto.

[0030] In the present specification, a fluorenyl group may be substituted, and two substituents may combine with each other to form a spiro structure.

[0031] When the fluorenyl group is substituted, the fluorenyl group may be a spiro fluorenyl group such as



and a substituted fluorenyl group such as



15 (a 9,9-dimethylfluorenyl group) and



(a 9,9-diphenylfluorenyl group). However, the fluorenyl group is not limited thereto.

25 **[0032]** In the present specification, a heterocyclic group is a heterocyclic group including one or more of N, O, P, S, Si, and Se as a hetero atom, and the number of carbon atoms thereof is not particularly limited, but is preferably 1 to 60. According to an exemplary embodiment, the number of carbon atoms of the heterocyclic group is 1 to 30. Examples of the heterocyclic group include a pyridyl group, a pyrrole group, a pyrimidyl group, a pyridazinyl group, a furanyl group, a thiophenyl group, an imidazole group, a pyrazole group, an oxazole group, an isooxazole group, a thiazole group, an isothiazole group, a triazole group, an oxadiazole group, a thiadiazole group, a dithiazole group, a tetrazole group, a pyranlyl group, a thiopyranlyl group, a pyrazinyl group, an oxazinyl group, a thiazinyl group, a dioxynyl group, a triazinyl group, a tetrazinyl group, a quinolinyl group, an isoquinolinyl group, a quinolyl group, a quinazolinyl group, a quinoxalinyl group, a naphthyridinyl group, an acrydyl group, a xanthenyl group, a phenanthridinyl group, a diaza naphthalenyl group, a triazaindenyl group, an indole group, an indolynyl group, an indolizinyl group, a phthalizinyl group, a pyrido pyrimidinyl group, a pyrido pyrazinyl group, a pyrazino pyrazinyl group, a benzothiazole group, a benzoxazole group, a benzimidazole group, a benzothiophene group, a benzofuranyl group, a dibenzothiophenyl group, a dibenzofuranyl group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, an indolocarbazole group, an indenocarbazole group, a phenazinyl group, an imidazopyridine group, a phenoxazinyl group, a phenanthridine group, a phenanthroline group, a phenothiazine group, an imidazopyridine group, an imidazophenanthridine group, a benzoimidazoquinazoline group, or a benzoimidazophenanthridine group, and the like, but are not limited thereto.

40 **[0033]** In the present specification, the above-described description on the heterocyclic group may be applied to a heteroaryl group except for an aromatic heteroaryl group.

[0034] In the present specification, the above-described description on the aryl group may be applied to an aryl group in an aryloxy group, an arylthioxy group, an arylsulfoxy group, an arylphosphine group, an aralkyl group, an aralkylamine group, an aralkenyl group, an alkylaryl group, an arylamine group, and an arylheteroarylamine group.

45 **[0035]** In the present specification, the above-described description on the alkyl group may be applied to an alkyl group in an alkylthioxy group, an alkylsulfoxy group, an aralkyl group, an aralkylamine group, an alkylaryl group, and an alkylamine group.

[0036] In the present specification, the above-described description on the heterocyclic group may be applied to a heteroaryl group in a heteroaryl group, a heteroarylamine group, and an arylheteroarylamine group.

[0037] In the present specification, a germanium group may be represented by a chemical formula of $-\text{GeR}_a\text{R}_b\text{R}_c$, and R_a , R_b , and R_c may be each hydrogen; a substituted or unsubstituted alkyl group; or a substituted or unsubstituted aryl group. Specific examples of the germanium group include a trimethylgermanium group, a triethylgermanium group, a t-butylidimethylgermanium group, and the like, but are not limited thereto.

55 **[0038]** In the present specification, the above-described description on the alkenyl group may be applied to an alkenyl group in an aralkenyl group.

[0039] In the present specification, the above-described description on the aryl group may be applied to arylene except for a divalent arylene group.

[0040] In the present specification, the above-described description on the heteroaryl group may be applied to heteroarylene except for a divalent heteroarylene group.

[0041] In the present specification, the meaning of combining with an adjacent group to form a ring means combining with an adjacent group to form a substituted or unsubstituted aliphatic hydrocarbon ring; a substituted or unsubstituted aromatic hydrocarbon ring; a substituted or unsubstituted aliphatic hetero ring; a substituted or unsubstituted aromatic hetero ring; or a fused ring thereof.

[0042] In the present specification, the aliphatic hydrocarbon ring means a ring composed only of carbon and hydrogen atoms as a ring which is not an aromatic group. Specifically, examples of the aliphatic hydrocarbon ring include cyclopropane, cyclobutane, cyclobutene, cyclopentane, cyclopentene, cyclohexane, cyclohexene, 1,4-cyclohexadiene, cycloheptane, cycloheptene, cyclooctane, cyclooctene, and the like, but are not limited thereto.

[0043] In the present specification, an aromatic hydrocarbon ring means an aromatic ring composed only of carbon and hydrogen atoms. Specifically, examples of the aromatic hydrocarbon ring include benzene, naphthalene, anthracene, phenanthrene, perylene, fluoranthene, triphenylene, phenalene, pyrene, tetracene, chrysene, pentacene, fluorene, indene, acenaphthylene, benzofluorene, spirofluorene, and the like, but are not limited thereto.


[0044] In the present specification, the aliphatic hetero ring means an aliphatic ring including one or more of hetero atoms. Specifically, examples of the aliphatic hetero ring include oxirane, tetrahydrofuran, 1,4-dioxane, pyrrolidine, piperidine, morpholine, oxepane, azocane, thiocane, and the like, but are not limited thereto.

[0045] In the present specification, the aromatic hetero ring means an aromatic ring including one or more of hetero atoms. Specifically, examples of the aromatic hetero ring include pyridine, pyrrole, pyrimidine, pyridazine, furan, thiophene, imidazole, pyrazole, oxazole, isoxazole, thiazole, isothiazole, triazole, oxadiazole, thiadiazole, dithiazole, tetrazole, pyran, thiopyran, diazine, oxazine, thiazine, dioxine, triazine, tetrazine, isoquinoline, quinoline, quinol, quinazoline, quinoxaline, naphthyridine, acridine, phenanthridine, diaza naphthalene, triazaindene, indole, indolizine, benzothiazole, benzoxazole, benzoimidazole, benzothiophene, benzofuran, dibenzothiophene, dibenzofuran, carbazole, benzocarbazole, dibenzocarbazole, phenazine, imidazopyridine, phenoxazine, phenanthridine, indolocarbazole, indenocarbazole, and the like, but are not limited thereto.


[0046] In the present specification, the aliphatic hydrocarbon ring, the aromatic hydrocarbon ring, the aliphatic hetero ring, and the aromatic hetero ring may be monocyclic or polycyclic.

[0047] According to an exemplary embodiment of the present specification, the compound represented by Chemical Formula 1 may be represented by the following Chemical Formula 2 or Chemical Formula 3.

[Chemical Formula 2]




[Chemical Formula 3]




[0048] In Chemical Formula 2 and Chemical Formula 3, the definitions of Ar1, L, R1, R3, a and c are each the same as those in Chemical Formula 1.

[0049] According to an exemplary embodiment of the present specification, the compound represented by Chemical Formula 1 may be represented by the following Chemical Formula 4 or Chemical Formula 5.

[Chemical Formula 4]



[Chemical Formula 5]




[0050] In Chemical Formula 4 and Chemical Formula 5, the definitions of Ar1, L, R1, and a are each the same as those in Chemical Formula 1.

[0051] According to an exemplary embodiment of the present invention, Ar1 is a substituted or unsubstituted monocyclic or polycyclic aryl group having 6 to 30 carbon atoms.

[0052] In an exemplary embodiment of the present invention, Ar1 is a substituted or unsubstituted phenyl group; a substituted or unsubstituted biphenyl group; a substituted or unsubstituted terphenyl group; a substituted or unsubstituted naphthyl group; a substituted or unsubstituted anthracenyl group; a substituted or unsubstituted phenanthryl group; a substituted or unsubstituted pyrenyl group; a substituted or unsubstituted perylenyl group; a substituted or unsubstituted chrysenyl group; or a substituted or unsubstituted fluorenyl group.

[0053] In an exemplary embodiment of the present invention, Ar1 is a substituted or unsubstituted phenyl group; a substituted or unsubstituted biphenyl group; a substituted or unsubstituted terphenyl group; a substituted or unsubstituted naphthyl group; a substituted or unsubstituted fluorenyl group; a substituted or unsubstituted phenanthrenyl group; or a substituted or unsubstituted triphenylenyl group.

[0054] According to an exemplary embodiment of the present specification, Ar1 may be any one selected from the following structures, and the following structures may be additionally substituted.




[0055] Specifically, the structures may be unsubstituted or substituted with one or more substituents selected from the group consisting of deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amine group; a phosphine oxide group, an alkoxy group; an aryloxy group; an alkylthioxy group; an arylthioxy group; an alkylsulfoxy group; an arylsulfoxy group; a silyl group; a boron group; an alkyl group; a cycloalkyl group; an alkenyl group; an aryl group; an aralkyl group; an aralkenyl group; an alkylaryl group; an alkylamine group; an aralkylamine group; a heteroarylamine group; an arylamine group; an arylheteroarylamine group; an arylphosphine group; and a heterocyclic group. More specifically, the structures may be unsubstituted or substituted with deuterium; an alkyl group; or an aryl group.

[0056] In an exemplary embodiment of the present invention, L is a direct bond; or a substituted or unsubstituted monocyclic or polycyclic arylene group having 6 to 30 carbon atoms.

[0057] In an exemplary embodiment of the present invention, L is a direct bond; a substituted or unsubstituted phenylene group; a substituted or unsubstituted biphenylene group; a substituted or unsubstituted terphenylene group; a substituted or unsubstituted naphthylene group; a substituted or unsubstituted anthracenylene group; a substituted or unsubstituted fluorenylene group; a substituted or unsubstituted phenanthrenylene group; or a substituted or unsubstituted triphenylenylene group.

[0058] In an exemplary embodiment of the present invention, L is a direct bond; or a substituted or unsubstituted phenylene group.

[0059] According to an exemplary embodiment of the present specification, L may be a direct bond; or any one selected from the following structures, and the following structures may be additionally substituted.



[0060] Specifically, the structures may be unsubstituted or substituted with one or more substituents selected from the group consisting of deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group;

an ester group; an imide group; an amine group; a phosphine oxide group; an alkoxy group; an aryloxy group; an alkylthio group; an arylthio group; an alkylsulfoxy group; an arylsulfoxy group; a silyl group; a boron group; an alkyl group; a cycloalkyl group; an alkenyl group; an aryl group; an aralkyl group; an aralkenyl group; an alkylaryl group; an alkylamine group; an aralkylamine group; a heteroarylamine group; an arylamine group; an arylheteroarylamine group; an arylphosphine group; and a heterocyclic group. More specifically, the structures may be unsubstituted or substituted with deuterium; an alkyl group; or an aryl group.


[0061] In an exemplary embodiment of the present invention, R1 is hydrogen; deuterium; or a substituted or unsubstituted alkyl group having 1 to 40 carbon atoms.
















[0062] In an exemplary embodiment of the present invention, R1 is hydrogen; deuterium; a substituted or unsubstituted methyl group; a substituted or unsubstituted ethyl group; a substituted or unsubstituted propyl group; a substituted or unsubstituted n-propyl group; a substituted or unsubstituted isopropyl group; a substituted or unsubstituted butyl group; a substituted or unsubstituted n-butyl group; a substituted or unsubstituted isobutyl group; a substituted or unsubstituted tert-butyl group; a substituted or unsubstituted sec-butyl group; a substituted or unsubstituted 1-methyl-butyl group; a substituted or unsubstituted 1-ethyl-butyl group; a substituted or unsubstituted pentyl group; a substituted or unsubstituted n-pentyl group; a substituted or unsubstituted isopentyl group; a substituted or unsubstituted neopentyl group; a substituted or unsubstituted tert-pentyl group; a substituted or unsubstituted hexyl group; a substituted or unsubstituted n-hexyl group; a substituted or unsubstituted 1-methylpentyl group; a substituted or unsubstituted 2-methylpentyl group; a substituted or unsubstituted 4-methyl-2-pentyl group; a substituted or unsubstituted 3,3-dimethylbutyl group; a substituted or unsubstituted 2-ethylbutyl group; a substituted or unsubstituted heptyl group; a substituted or unsubstituted n-heptyl group; a substituted or unsubstituted 1-methylhexyl group; a substituted or unsubstituted cyclopentylmethyl group; a substituted or unsubstituted cyclohexylmethyl group; a substituted or unsubstituted octyl group; a substituted or unsubstituted n-octyl group; a substituted or unsubstituted tert-octyl group; a substituted or unsubstituted 1-methylheptyl group; a substituted or unsubstituted 2-ethylhexyl group; a substituted or unsubstituted 2-propylpentyl group; a substituted or unsubstituted n-nonyl group; a substituted or unsubstituted 2,2-dimethylheptyl group; a substituted or unsubstituted 1-ethyl-propyl group; a substituted or unsubstituted 1,1-dimethyl-propyl group; a substituted or unsubstituted isohexyl group; a substituted or unsubstituted 4-methylhexyl group; or a substituted or unsubstituted 5-methylhexyl group.
















[0063] In an exemplary embodiment of the present invention, R1 is hydrogen; deuterium; a substituted or unsubstituted methyl group; or a substituted or unsubstituted t-butyl group.
















[0064] In an exemplary embodiment of the present invention, R1 is hydrogen; deuterium; a methyl group; or a t-butyl group.


[0065] In an exemplary embodiment of the present invention, the compound of Chemical Formula 1 may be any one selected from the following compounds.




**7****8****9****10****11****12****13****14****15****16****17****18****19****20****21**




**37****38****39****40****41****42****43****44****45****46****47****48****49****50****51**




52




53




54




55




56




57




58




59




60




61




62




63















64



65






66






5

10






15

20



25




30



35


40

45



50


55



[0066] The compound of Chemical Formula 1 may be synthesized by a general reaction formula to be described below, but is not limited thereto.



<Reaction Formula A> Synthesis of Intermediate A

[0067]






<Reaction Formula B> Synthesis of Intermediate B

[0068]



[0069] Further, the compound of Chemical Formula 1 may be synthesized by using the following C to J as an intermediate instead of Intermediate A or B in Reaction Formula A or B.





[0070] The conjugation length and energy bandgap of the compound are closely associated with each other. Specifically, the longer the conjugation length of the compound is, the smaller the bandgap is.

[0071] In the present invention, various substituents may be introduced into the positions of Ar1 and R1 having the core structure as described above to synthesize compounds having various energy bandgaps. A substituent is usually introduced into a core structure having a large energy bandgap to easily adjust the energy bandgap, but when the core structure has a small energy bandgap, it is difficult to significantly adjust the energy bandgap by introducing a substituent. Further, in the present invention, various substituents may also be introduced into the positions of Ar1 and R1 having the core structure as described above to adjust the HOMO and LUMO energy levels of a compound.

[0072] In addition, various substituents may be introduced into the core structure having the structure as described above to synthesize a compound having inherent characteristics of the introduced substituent. For example, a substituent usually used for a hole injection layer material, a material for transporting holes, a light emitting layer material, and an electron transport layer material, which are used for manufacturing an organic light emitting device, may be introduced into the core structure to synthesize a material which satisfies conditions required for each organic material layer.

[0073] Furthermore, an organic light emitting device according to the present invention is an organic light emitting device comprising a first electrode, a second electrode, and one or more organic material layers disposed between the first electrode and the second electrode, in which one or more layers of the organic material layers comprise the compound.

[0074] The organic light emitting device of the present invention may be manufactured by typical preparation methods and materials of an organic light emitting device, except that the above-described compound is used to form one or more organic material layers.

[0075] The compound may be formed as an organic material layer by not only a vacuum deposition method, but also a solution application method when an organic light emitting device is manufactured. Here, the solution application method means spin coating, dip coating, inkjet printing, screen printing, a spray method, roll coating, and the like, but is not limited thereto.

[0076] The organic material layer of the organic light emitting device of the present invention may also be composed of a single-layered structure, but may be composed of a multi-layered structure in which two or more organic material layers are stacked. For example, the organic light emitting device of the present invention may have a structure including a hole injection layer, an electron blocking layer, a hole transport layer, a light emitting layer, an electron transport layer, an electron injection layer, and the like as organic material layers. However, the structure of the organic light emitting device is not limited thereto, and may include a fewer number of organic material layers.

[0077] Accordingly, in the organic light emitting device of the present invention, the organic material layer may comprise one or more layers of a hole injection layer, an electron blocking layer, a hole transport layer, and a layer which injects and transports holes simultaneously, and one or more layers of the layers may comprise the compound represented by Chemical Formula 1.

[0078] In an exemplary embodiment, the organic material layer comprises an electron blocking layer, and the electron blocking layer comprises the compound represented by Chemical Formula 1.

[0079] In another exemplary embodiment, the organic material layer includes a hole transport layer, and the hole transport layer includes the compound represented by Chemical Formula 1.

[0080] In still another exemplary embodiment, the organic material layer comprises a light emitting layer, and the light emitting layer comprises the compound represented by Chemical Formula 1. As an example, the compound represented by Chemical Formula 1 may be included as a host of the light emitting layer. As another example, the compound represented by Chemical Formula 1 may be included as a phosphorescent host of the light emitting layer.

[0081] As still another example, the organic material layer comprising the compound represented by Chemical Formula 1 may comprise the compound represented by Chemical Formula 1 as a host, and may comprise another organic compound, a metal or a metal compound as a dopant.

[0082] As yet another example, the organic material layer comprising the compound represented by Chemical Formula

1 may comprise the compound represented by Chemical Formula 1 as a host, and may use an iridium (Ir)-based dopant together.


[0083] Further, the organic material layer may comprise one or more layers of an electron transport layer, an electron injection layer, and a layer which transports and injects electrons simultaneously, and one or more layers of the layers may comprise the compound.

[0084] In another exemplary embodiment, the organic material layer of the organic electronic light emitting comprises a hole transport layer, and the hole transport layer comprises the compound represented by Chemical Formula 1.

[0085] In the organic material layer having the multi-layered structure, the compound may be included in a light emitting layer, a layer which injects holes/ transports holes and emits light simultaneously, a layer which transports holes and emits light simultaneously, or a layer which transports electrons and emits light simultaneously, and the like.

[0086] In an exemplary embodiment of the present specification, the organic material layer comprises a light emitting layer, and the light emitting layer comprises a compound represented by the following Chemical Formula 6.

[Chemical Formula 6]



[0087] In Chemical Formula 6,

Ar2 is a substituted or unsubstituted monovalent or more benzofluorene group; a substituted or unsubstituted monovalent or more fluoranthene group; a substituted or unsubstituted monovalent or more pyrene group; or a substituted or unsubstituted monovalent or more chrysene group,

L1 is a direct bond; a substituted or unsubstituted arylene group; or a substituted or unsubstituted heteroarylene group, Ar3 and Ar4 are the same as or different from each other, and are each independently a substituted or unsubstituted aryl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted aralkyl group; or a substituted or unsubstituted heteroaryl group, or may combine with each other to form a substituted or unsubstituted ring,

r is an integer of 1 or more, and

when r is 2 or more, the substituents in the parenthesis are the same as or different from each other.

[0088] According to an exemplary embodiment of the present specification, the organic material layer comprises a light emitting layer, and the light emitting layer comprises the compound represented by Chemical Formula 6 as a dopant of the light emitting layer.

[0089] In an exemplary embodiment of the present specification, L1 is a direct bond.

[0090] According to an exemplary embodiment of the present specification, r is 2.

[0091] In an exemplary embodiment of the present specification, Ar2 is a substituted or unsubstituted divalent pyrene group.

[0092] In another exemplary embodiment, Ar2 is a divalent pyrene group which is unsubstituted or substituted with a methyl group, an ethyl group, a t-butyl group or an isopropyl group.

[0093] In still another exemplary embodiment, Ar2 is a divalent pyrene group.


[0094] In an exemplary embodiment of the present specification, Ar3 and Ar4 are the same as or different from each other, and are each independently a substituted or unsubstituted aryl group having 6 to 30 carbon atoms; a substituted or unsubstituted alkyl group having 1 to 30 carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 30 carbon atoms.

[0095] According to an exemplary embodiment of the present specification, Ar3 and Ar4 are the same as or different from each other, and are each independently a substituted or unsubstituted aryl group having 6 to 30 carbon atoms.

[0096] According to an exemplary embodiment of the present specification, Ar3 and Ar4 are the same as or different from each other, and are each independently an aryl group having 6 to 30 carbon atoms, which is substituted or unsubstituted with a germanium group substituted with an alkyl group.


[0097] In an exemplary embodiment of the present specification, Ar3 and Ar4 are a phenyl group which is unsubstituted or substituted with a trimethylgermanium group.

[0098] According to an exemplary embodiment of the present specification, Chemical Formula 6 may be represented by the following compound.




[0099] In an exemplary embodiment of the present specification, the organic material layer comprises a light emitting layer, and the light emitting layer comprises a compound represented by the following Chemical Formula 7.

[Chemical Formula 7]



[0100] In Chemical Formula 7,

X1 is a 1-naphthyl group, a 2-naphthyl group, a 1-anthryl group, a 2-anthryl group, a 1-phenanthryl group, a 2-phenanthryl group, a 3-phenanthryl group, a 4-phenanthryl group, a 9-phenanthryl group, a 1-naphthacenyl group, a 2-naphthacenyl group, a 9-naphthacenyl group, a 1-pyrenyl group, a 2-pyrenyl group, a 4-pyrenyl group, a 3-methyl-2-naphthyl group, a 4-methyl-1-naphthyl group, or the following Chemical Formula



X3 is a phenyl group, a 1-naphthyl group, a 2-naphthyl group, a 1-anthryl group, a 2-anthryl group, a 1-phenanthryl group, a 2-phenanthryl group, a 3-phenanthryl group, a 4-phenanthryl group, a 9-phenanthryl group, a 1-naphthacenyl group, a 2-naphthacenyl group, a 9-naphthacenyl group, a 1-pyrenyl group, a 2-pyrenyl group, a 4-pyrenyl group, a 2-biphenyl group, a 2-biphenyl group, a 3-biphenyl group, a 4-biphenyl group, a p-terphenyl-4-yl group, a p-terphenyl-3-yl group, a p-terphenyl-2-yl group, an m-terphenyl-4-yl group, an m-terphenyl-3-yl group, an m-terphenyl-2-yl group, an o-tolyl group, an m-tolyl group, a p-tolyl group, a p-t-butylphenyl group, a p-(2-phenylpropyl)phenyl group, a 3-methyl-2-naphthyl group, a 4-methyl-1-naphthyl group, a 4-methyl-1-anthryl group, a 4'-methylbiphenyl group, a 4'-t-butyl-p-terphenyl-4-yl group, or a 3-fluoranthenyl group,

X2 and X4 are the same as or different from each other, and are each independently hydrogen; a substituted or unsubstituted alkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryl group; or a substituted or unsubstituted heteroaryl group,

p2 is an integer of 1 to 5,

p1 and p3 are each an integer of 1 to 4, and

when p1 to p3 are each 2 or more, the substituents in the parenthesis are the same as or different from each other.


[0101] According to an exemplary embodiment of the present specification, the organic material layer comprises a light emitting layer, and the light emitting layer comprises the compound represented by Chemical Formula 7 as a host of the light emitting layer.

[0102] In an exemplary embodiment of the present specification, X1 is a 1-naphthyl group.

[0103] In an exemplary embodiment of the present specification, X3 is a 2-naphthyl group, and p2 is 1.

[0104] In an exemplary embodiment of the present specification, X2 and X4 are hydrogen.

[0105] According to an exemplary embodiment of the present specification, Chemical Formula 7 may be represented by the following compound.



[0106] For example, the structure of the organic light emitting device of the present invention may have a structure as illustrated in FIGS. 1 and 2, but is not limited thereto.

[0107] FIG. 1 illustrates the structure of an organic light emitting device in which a positive electrode (2), a light emitting layer (3), and a negative electrode (4) are sequentially stacked on a substrate (1). In the structure as described above, the compound may be included in the light emitting layer (3).

[0108] FIG. 2 illustrates the structure of an organic light emitting device in which a positive electrode (2), a hole injection layer (5), a hole transport layer (6), a light emitting layer (3), an electron transport layer (7), and a negative electrode (4) are sequentially stacked on a substrate (1). In the structure as described above, the compound may be included in the hole injection layer (5), the hole transport layer (6), the light emitting layer (3), or the electron transport layer (7).

[0109] For example, the organic light emitting device according to the present invention may be manufactured by depositing a metal or a metal oxide having conductivity, or an alloy thereof on a substrate to form a positive electrode, forming an organic material layer including a hole injection layer, a hole transport layer, a light emitting layer, and an electron transport layer thereon, and then depositing a material, which may be used as a negative electrode, thereon, by using a physical vapor deposition (PVD) method such as sputtering or e-beam evaporation. In addition to the method as described above, an organic light emitting device may also be made by sequentially depositing a negative electrode material, an organic material layer, and a positive electrode material on a substrate.

[0110] The organic material layer may have a multi-layered structure comprising a hole injection layer, a hole transport layer, a light emitting layer, and an electron transport layer, and the like, but is not limited thereto and may have a single-layered structure. Further, the organic material layer may be manufactured with a fewer number of layers by a method such as a solvent process, for example, spin coating, dip coating, doctor blading, a screen printing, inkjet printing, or a thermal transfer method using various polymers, instead of a deposition method.

[0111] As the positive electrode material, a material having a large work function is usually preferred so as to smoothly inject holes into an organic material layer. Specific examples of the positive electrode material which may be used in the present invention include: a metal, such as vanadium, chromium, copper, zinc, and gold, or alloys thereof; a metal oxide, such as zinc oxide, indium oxide, indium tin oxide (ITO), and indium zinc oxide (IZO); a combination of metal and oxide, such as ZnO : Al or SnO₂ : Sb; an electrically conductive polymer, such as poly(3-methyl compound), poly[3,4-(ethylene-1,2-dioxy)compound] (PEDT), polypyrrole, and polyaniline, and the like, but are not limited thereto.

[0112] As the negative electrode material, a material having a small work function is usually preferred so as to smoothly inject electrons into an organic material layer. Specific examples of the negative electrode material include: a metal, such as magnesium, calcium, sodium, potassium, titanium, indium, yttrium, lithium, gadolinium, aluminum, silver, tin, and lead, or alloys thereof; a multi-layered structural material, such as LiF/Al or LiO₂/Al, and the like, but are not limited thereto.

[0113] The hole injection material is a material which may receive well holes injected from the positive electrode at low voltage, and it is preferred that the highest occupied molecular orbital (HOMO) of the hole injection material is between the work function of the positive electrode material and the HOMO of the peripheral organic material layer. Specific examples of the hole injection material include metal porphyrin, oligothiophene, an arylamine-based organic material, a hexanitride hexaazatriphenylene-based organic material, a quinacridone-based organic material, a perylene-based organic material, anthraquinone, a polyaniline and polycompound-based electrically conductive polymer, and the like, but are not limited thereto.

















[0114] The hole transport material is a material which may receive holes transported from a positive electrode or a hole injection layer and transfer the holes to a light emitting layer, and is suitably a material having a large mobility for holes. Specific examples thereof include an arylamine-based organic material, an electrically conductive polymer, a block copolymer in which a conjugate portion and a non-conjugate portion are present together, and the like, but are not limited thereto.


[0115] The light emitting material is a material which may receive holes and electrons from a hole transport layer and

an electron transport layer, respectively, and combine the holes and the electrons to emit light in a visible ray region, and is preferably a material having good quantum efficiency to fluorescence or phosphorescence. Specific examples thereof include: an 8-hydroxy-quinoline aluminum complex (Alq_3); a carbazole-based compound; a dimerized styryl compound; BAlq; a 10-hydroxybenzoquinoline-metal compound; a benzoxazole, benzthiazole and benzimidazole-based compound; a poly(p-phenylenevinylene) (PPV)-based polymer; a spiro compound; polyfluorene, lubrene, and the like, but are not limited thereto.

[0116] The organic material layer comprising the compound represented by Chemical Formula 1 may comprise the compound represented by Chemical Formula 1 as a host, and may use an iridium (Ir)-based dopant together.

[0117] The iridium-based complex used as a dopant is as follows.





[0118] The electron transport material is a material which may receive well electrons injected from a negative electrode and transfer the electrons to a light emitting layer, and is suitably a material having a large mobility for electrons. Specific examples thereof include: an Al complex of 8-hydroxyquinoline; a complex including Alq₃; an organic radical compound; a hydroxyflavone-metal complex, and the like, but are not limited thereto.


[0119] The organic light emitting device according to the present invention may be a top emission type, a bottom emission type, or a dual emission type according to the material to be used.

[0120] The compound according to the present invention may be operated by a principle which is similar to the principle applied to an organic light emitting device, even in an organic electronic device including an organic solar cell, an organic photoconductor, an organic transistor, and the like.

[0121] The preparation method of the compound of Chemical Formula 1 and the manufacture of an organic light emitting device using the same will be specifically described in the following Examples. However, the following Examples are provided for exemplifying the present invention, and the scope of the present invention is not limited thereby.

<Preparation Example 1> Synthesis of Compound 1

[0122]



[0123] Compound A (12.0 g, 37.62 mmol) and 2-bromo-9-phenyl-9H-carbazole (10.98 g, 34.21 mmol) were completely dissolved in 240 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put therein, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 12 to prepare Compound 1 (16.54 g, yield: 78%).


MS[M+H]⁺ = 561

<Preparation Example 2> Synthesis of Compound 3

[0124]

[Compound A]

[Compound 3]



[0125] Compound A (12.0 g, 37.62 mmol) and 9-([1,1'-biphenyl]-4-yl)-2-bromo-9H-carbazole (13.58 g, 34.21 mmol) were completely dissolved in 280 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereto, and then the resulting mixture was heated and stirred for 4 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was recrystallized with 300 ml of ethyl acetate to prepare Compound 3 (21.33 g, yield: 89%).


MS[M+H]⁺ = 637

<Preparation Example 3> Synthesis of Compound 9

[0126]

[Compound A]

[Compound 9]



[0127] Compound A (12.0 g, 37.62 mmol) and 2-bromo-9-(9,9-dimethyl-9H-fluoren-2-yl)-9H-carbazole (14.95 g, 34.21 mmol) were completely dissolved in 240 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereto, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 16 to prepare Compound 9 (19.77 g, yield: 77%).


MS[M+H]⁺ = 677

<Preparation Example 4> Synthesis of Compound 5

[0128]

[Compound A]

[Compound 5]




[0129] Compound A (12.0 g, 37.62 mmol) and 2-bromo-9-(naphthalen-2-yl)-9H-carbazole (12.69 g, 34.21 mmol) were completely dissolved in 180 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereto, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 16 to prepare Compound 5 (16.92 g, yield: 74%).
MS[M+H]⁺ = 611

<Preparation Example 5> Synthesis of Compound 10

[0130]

[Compound A]

[Compound 10]




[0131] Compound A (12.0 g, 37.62 mmol) and 9-([1,1'-biphenyl]-2-yl)-2-bromo-9H-carbazole (13.58 g, 34.21 mmol) were completely dissolved in 280 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereto, and then the resulting mixture was heated and stirred for 4 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was recrystallized with 220 ml of ethyl acetate to prepare Compound 10 (17.07 g, yield: 71%).
MS[M+H]⁺ = 637

<Preparation Example 6> Synthesis of Compound 89

[0132]

[Compound A]

[Compound 89]




[0133] Compound A (12.0 g, 37.62 mmol) and 9-([1,1':4',1''-terphenyl]-4-yl)-2-bromo-9H-carbazole (16.18 g, 34.21 mmol) were completely dissolved in 240 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereto, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 12 to prepare Compound 89 (23.08 g, yield: 86%).
 $\text{MS}[\text{M}+\text{H}]^+ = 713$

<Preparation Example 7> Synthesis of Compound 7

[0134]

[Compound A]

[Compound 7]




[0135] Compound A (12.0 g, 37.62 mmol) and 9-([1,1'-biphenyl]-3-yl)-2-bromo-9H-carbazole (13.58 g, 34.21 mmol) were completely dissolved in 280 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereto, and then the resulting mixture was heated and stirred for 4 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was recrystallized with 260 ml of ethyl acetate to prepare Compound 7 (15.36 g, yield: 64%).
 $\text{MS}[\text{M}+\text{H}]^+ = 637$

<Preparation Example 8> Synthesis of Compound 90

[0136]

[Compound A]

[Compound 90]



[0137] Compound A (12.0 g, 37.62 mmol) and 2-bromo-9-(phenyl-d5)-9H-carbazole (10.98 g, 34.21 mmol) were completely dissolved in 240 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereinto, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 12 to prepare Compound 90 (17.35 g, yield: 82%).


MS[M+H]⁺ = 561

<Preparation Example 9> Synthesis of Compound 17

[0138]

[Compound A]

[Compound 17]



[0139] Compound A (12.0 g, 37.62 mmol) and 2-bromo-9-(9,9-dimethyl-9H-fluoren-3-yl)-9H-carbazole (14.95 g, 34.21 mmol) were completely dissolved in 240 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereinto, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 15 to prepare Compound 17 (17.78 g, yield: 69%).


MS[M+H]⁺ = 677

<Preparation Example 10> Synthesis of Compound 23

[0140]

[Compound A]


[Compound 23]




[0141] Compound A (12.0 g, 37.62 mmol) and 2-bromo-9-(4-(naphthalen-2-yl)phenyl)-9H-carbazole (16.18 g, 34.21 mmol) were completely dissolved in 240 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.27 g, 44.46 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.17 g, 0.34 mmol) was put thereto, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 12 to prepare Compound 23 (21.16 g, yield: 82%).
MS[M+H]⁺ = 687




<Preparation Example 11> Synthesis of Compounds 61, 63 to 67, 71, and 91 to 94

[0142]




[0143] The following compounds were prepared in the same manner as in Preparation Examples 1 to 10, except that Compound B was used instead of Compound A as a starting material.





40 <Preparation Example 12> Synthesis of Compound 29

[0144]



[0145] Compound C (12.0 g, 36.04 mmol) and 2-bromo-9-phenyl-9H-carbazole (10.52 g, 32.76 mmol) were completely dissolved in 230 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.09 g, 42.59 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.16 g, 0.33 mmol) was put thereto, and then the resulting mixture was heated and stirred for 2 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was purified by column chromatography at a ratio of tetrahydrofuran : hexane = 1 : 12 to prepare Compound 29 (13.92 g, yield: 67%).


MS[M+H]⁺ = 575

<Preparation Example 13> Synthesis of Compound 37

[0146]

[Compound D]

[Compound 37]



[0147] Compound D (12.0 g, 32.0 mmol) and 2-bromo-9-phenyl-9H-carbazole (9.34 g, 29.09 mmol) were completely dissolved in 240 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (3.63 g, 37.82 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.15 g, 0.29 mmol) was put thereto, and then the resulting mixture was heated and stirred for 5 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was recrystallized with 240 ml of ethyl acetate to prepare Compound 37 (15.01 g, yield: 76%).


MS[M+H]⁺ = 617

<Preparation Example 14> Synthesis of Compound 55

[0148]

[Compound F]

[Compound 55]



[0149] Compound F (12.0 g, 35.40 mmol) and 9-([1,1'-biphenyl]-4-yl)-2-bromo-9H-carbazole (10.33 g, 32.18 mmol) were completely dissolved in 280 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.02 g, 41.83 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.16 g, 0.32 mmol)

was put thereinto, and then the resulting mixture was heated and stirred for 4 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was recrystallized with 210 ml of ethyl acetate to prepare Compound 55 (18.85 g, yield: 83%).


MS[M+H]⁺ = 642

<Preparation Example 15> Synthesis of Compound 94

[0150]

[Compound J]

[Compound 94]



[0151] Compound J (12.0 g, 35.40 mmol) and 9-([1,1'-biphenyl]-4-yl)-2-bromo-9H-carbazole (10.33 g, 32.18 mmol) were completely dissolved in 280 ml of xylene in a 500 ml round bottom flask under nitrogen atmosphere, and then sodium tert-butoxide (4.02 g, 41.83 mol) was added thereto, bis(tri-tert-butylphosphine) palladium(0) (0.16 g, 0.32 mmol) was put thereinto, and then the resulting mixture was heated and stirred for 4 hours. The temperature of the mixture was lowered to room temperature, the resulting mixture was filtered to remove the salt, and then xylene was concentrated under reduced pressure, and the residue was recrystallized with 210 ml of ethyl acetate to prepare Compound 94 (18.85 g, yield: 83%).

MS[M+H]⁺ = 642


<Experimental Examples>

<Experimental Example 1-1>

[0152] A glass substrate thinly coated with indium tin oxide (ITO) to have a thickness of 1,000 Å was put into distilled water in which a detergent was dissolved, and ultrasonically washed. In this case, a product manufactured by Fischer Co., was used as the detergent, and distilled water twice filtered using a filter manufactured by Millipore Co., was used as the distilled water. After the ITO was washed for 30 minutes, ultrasonic washing was conducted twice repeatedly using distilled water for 10 minutes. After the washing using distilled water was completed, ultrasonic washing was conducted using isopropyl alcohol, acetone, and methanol solvents, and drying was conducted, and then the substrate was transferred to a plasma cleaner. In addition, the substrate was cleaned using oxygen plasma for 5 minutes, and then transferred to a vacuum evaporator.


[0153] Hexanitrihexaazatriphenylene (HAT) of the following Chemical Formula was thermally vacuum deposited to have a thickness of 500 Å on the transparent ITO electrode, which was thus prepared, thereby forming a hole injection layer.

[HAT]




[0154] The following compound N-([1,1'-biphenyl]-4-yl)-9,9-dimethyl-N-(4-(9-phenyl-9H-carbazol-3-yl)phenyl)-H-fluoren-2-amine (HTL 1) (300 Å) being a material for transporting holes was vacuum deposited on the hole injection layer, thereby forming a hole transport layer.

[HTL 1]




[0155] Subsequently, the following Compound 1 was vacuum deposited to have a film thickness of 100 Å on the hole transport layer, thereby forming an electron blocking layer.

[Compound 1]




[0156] Subsequently, the following BH and BD were vacuum deposited at a weight ratio of 25:1 to have a film thickness of 300 Å on the electron blocking layer, thereby forming a light emitting layer.


[BH]




[BD]



[ET1]



[LiQ]



[0157] Compound ET1 and Compound LiQ (lithium quinolate) were vacuum deposited at a weight ratio of 1:1 on the light emitting layer, thereby forming an electron injection and transport layer having a thickness of 300 Å. Lithium fluoride (LiF) and aluminum were sequentially deposited to have a thickness of 12 Å and 2,000 Å, respectively, on the electron injection and transport layer, thereby forming a negative electrode.

[0158] The deposition rate of the organic material was maintained at 0.4 to 0.7 Å/sec, the deposition rates of lithium fluoride and aluminum of the negative electrode were maintained at 0.3 Å/sec and at 2 Å/sec, respectively, and the degree of vacuum during the deposition was maintained at 2×10^{-7} to 5×10^{-6} torr, thereby manufacturing an organic light emitting device.

<Experimental Example 1-2>

[0159] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 3 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-3>

[0160] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 9 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-4>

[0161] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 5 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-5>

[0162] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 10 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-6>

[0163] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 89 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-7>

[0164] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 90 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-8>

[0165] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 64 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-9>

[0166] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 61 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-10>

[0167] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 91 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-11>

[0168] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 92 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-12>

[0169] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 29 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-13>

[0170] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 37 was used instead of Compound 1 in Experimental Example 1-1.

<Experimental Example 1-14>

[0171] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 55 was used instead of Compound 1 in Experimental Example 1-1.


<Experimental Example 1-15>

[0172] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that Compound 94 was used instead of Compound 1 in Experimental Example 1-1.

<Comparative Example 1-1>

[0173] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that EB 1 was used instead of Compound 1 in Experimental Example 1-1.


[EB 1]



<Comparative Example 1-2>

[0174] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that EB 2 was used instead of Compound 1 in Experimental Example 1-1.


[EB 2]



<Comparative Example 1-3>

[0175] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that EB 3 was used instead of Compound 1 in Experimental Example 1-1.


[EB 3]



<Comparative Example 1-4>

[0176] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that EB 4 was used instead of Compound 1 in Experimental Example 1-1.


[EB 4]



<Comparative Example 1-5>

[0177] An organic light emitting device was manufactured in the same manner as in Experimental Example 1-1, except that EB 5 was used instead of Compound 1 in Experimental Example 1-1.

[EB 5]



[0178] When current was applied to the organic light emitting devices manufactured in Experimental Examples 1-1 to 1-15 and Comparative Examples 1-1 to 1-5, the results of Table 1 were obtained.

[Table 1]

	Compound (Electron blocking layer)	Voltage (V@10mA/cm ²)	Efficiency (cd/A@10mA/cm ²)	Color coordinate (x, y)
Experimental Example 1-1	Compound 1	3.55	5.85	(0.139, 0.122)
Experimental Example 1-2	Compound 3	3.52	5.88	(0.138, 0.126)
Experimental Example 1-3	Compound 9	3.61	5.71	(0.138, 0.127)
Experimental Example 1-4	Compound 5	3.62	5.72	(0.137, 0.125)
Experimental Example 1-5	Compound 10	3.64	5.73	(0.136, 0.125)
Experimental Example 1-6	Compound 89	3.66	5.77	(0.136, 0.127)
Experimental Example 1-7	Compound 90	3.68	5.78	(0.136, 0.125)
Experimental Example 1-8	Compound 64	3.74	5.61	(0.137, 0.125)
Experimental Example 1-9	Compound 61	3.73	5.68	(0.138, 0.125)
Experimental Example 1-10	Compound 91	3.78	5.62	(0.136, 0.125)
Experimental Example 1-11	Compound 92	3.79	5.57	(0.137, 0.125)
Experimental Example 1-12	Compound 29	3.75	5.55	(0.136, 0.125)
Experimental Example 1-13	Compound 37	3.82	5.58	(0.138, 0.126)
Experimental Example 1-14	Compound 55	3.87	5.51	(0.137, 0.125)

(continued)

	Compound (Electron blocking layer)	Voltage (V@10mA/cm ²)	Efficiency (cd/A@10mA/cm ²)	Color coordinate (x, y)
Experimental Example 1-15	Compound 94	3.80	5.42	(0.136, 0.127)
Comparative Example 1-1	EB 1	4.56	4.73	(0.138, 0.127)
Comparative Example 1-2	EB 2	4.61	4.52	(0.139, 0.125)
Comparative Example 1-3	EB 3	4.79	4.36	(0.139, 0.126)
Comparative Example 1-4	EB 4	4.26	5.05	(0.139, 0.127)
Comparative Example 1-5	EB 5	4.33	4.94	(0.139, 0.127)

[0179] As observed in Table 1, it can be seen that the compounds in Experimental Examples 1-1 to 1-15 exhibit lower voltage and higher efficiency characteristics in an organic light emitting device than those in Comparative Examples 1-1 to 1-5.

[0180] When an N atom is linked to No. 3 or 4 of a carbazole group as in Comparative Example 1-1 or Comparative Example 1-2, the voltage was relatively high, and the efficiency thereof was also low. The case where a fluorenyl group or a dibenzothiophene group is used instead of a carbazole group (Comparative Example 1-3 and Comparative Example 1-4) and the case where a carbazole group is linked to an N atom through a linking group being an arylene group (Comparative Example 1-5) also exhibited similar characteristics.

[0181] It could be confirmed that the compound according to the present invention, which is linked to an N atom at the No. 2 position of the carbazole without a linking group, has excellent electron blocking ability, and thus exhibits low voltage and high efficiency characteristics, and can be applied to an organic light emitting device.

<Experimental Example 2>


<Experimental Example 2-1> to <Experimental Example 2-15>

[0182] An experiment was performed in the same manner as in Experimental Example 1-1, except that EB 1 (TCTA) was used as the electron blocking layer, and the compounds in Experimental Examples 1-1 to 1-15 were used instead of HTL 1 as the hole transport layer.

<Comparative Example 2-1>

[0183] An organic light emitting device was manufactured in the same manner as in Experimental Example 2-1, except that HT 1 was used instead of Compound 1.


[HT 1]



<Comparative Example 2-2>

[0184] An organic light emitting device was manufactured in the same manner as in Experimental Example 2-1, except that HT 2 was used instead of Compound 1.


[HT 2]



<Comparative Example 2-3>

[0185] An organic light emitting device was manufactured in the same manner as in Experimental Example 2-1, except that HT 3 was used instead of Compound 1.


[HT 3]



<Comparative Example 2-4>

[0186] An organic light emitting device was manufactured in the same manner as in Experimental Example 2-1, except that HT 4 was used instead of Compound 1.


[HT 4]



<Comparative Example 2-5>

[0187] An organic light emitting device was manufactured in the same manner as in Experimental Example 2-1, except that HT 5 was used instead of Compound 1.

[HT 5]



[0188] When current was applied to the organic light emitting devices manufactured in Experimental Examples 2-1 to 2-15 and Comparative Examples 2-1 to 2-5, the results of Table 2 were obtained.

[Table 2]

	Compound (Hole transport layer)	Voltage (V@10mA/cm ²)	Efficiency (cd/A@10mA/cm ²)	Color coordinate (x, y)
Experimental Example 2-1	Compound 1	3.72	6.35	(0.139, 0.122)
Experimental Example 2-2	Compound 3	3.79	6.28	(0.138, 0.126)
Experimental Example 2-3	Compound 9	3.75	6.31	(0.138, 0.127)
Experimental Example 2-4	Compound 5	3.85	6.24	(0.137, 0.125)
Experimental Example 2-5	Compound 10	3.86	6.22	(0.136, 0.125)
Experimental Example 2-6	Compound 89	3.84	6.13	(0.136, 0.127)
Experimental Example 2-7	Compound 90	3.89	6.11	(0.136, 0.125)
Experimental Example 2-8	Compound 64	3.95	6.02	(0.137, 0.125)
Experimental Example 2-9	Compound 61	3.93	6.01	(0.138, 0.125)
Experimental Example 2-10	Compound 91	3.98	5.92	(0.136, 0.125)
Experimental Example 2-11	Compound 92	3.93	5.95	(0.137, 0.125)
Experimental Example 2-12	Compound 29	4.05	5.95	(0.136, 0.125)
Experimental Example 2-13	Compound 37	4.06	5.82	(0.138, 0.126)
Experimental Example 2-14	Compound 55	4.10	5.76	(0.137, 0.125)

(continued)

	Compound (Hole transport layer)	Voltage (V@10mA/cm ²)	Efficiency (cd/A@10mA/cm ²)	Color coordinate (x, y)
Experimental Example 2-15	Compound 94	4.15	5.74	(0.136, 0.127)
Comparative Example 2-1	HT 1	4.51	4.72	(0.135, 0.127)
Comparative Example 2-2	HT 2	4.64	4.65	(0.138, 0.127)
Comparative Example 2-3	HT 3	4.48	4.86	(0.137, 0.125)
Comparative Example 2-4	HT 4	4.60	4.34	(0.139, 0.126)
Comparative Example 2-5	HT 5	4.65	4.40	(0.139, 0.127)


[0189] As observed in Table 2, it can be seen that the compounds in Experimental Examples 2-1 to 2-15 exhibit lower voltage and higher efficiency characteristics than those in Comparative Examples 2-1 to 2-5 when the compounds in Experimental Examples 2-1 to 2-15 are used for an organic light emitting device.

[0190] When an N atom is linked to No. 3 or 4 position of a carbazole group as in Comparative Example 2-1 or Comparative Example 2-2, the driving voltage of the organic light emitting device was relatively high, and the efficiency thereof was also low. The case where a fluorenyl group or a dibenzothiophene group is used instead of a carbazole group (Comparative Example 2-3 and Comparative Example 2-4) and the case where a carbazole group is linked to an N atom through a linking group being an arylene group (Comparative Example 2-5) also exhibited similar characteristics. It could be confirmed that the compound according to the present invention, which is linked to an N atom at the No. 2 position of the carbazole without a linking group, also has excellent hole transport ability, and thus exhibits low voltage and high efficiency characteristics, and can be applied to an organic light emitting device.

[0191] Although the preferred exemplary embodiments (an electron blocking layer and a hole transport layer) of the present invention have been described above, the present invention is not limited thereto, and various modifications can be made and carried out within the scope of the claims in view of the description of the invention, and also fall within the scope of the invention.

Claims


1. A compound represented by the following Chemical Formula 1:




Chemical Formula 1

in Chemical Formula 1,


X is



Y is



Z is



Ar1 is a substituted or unsubstituted aryl group,

L is a direct bond; or a substituted or unsubstituted arylene group,

R1 is hydrogen; deuterium; or a substituted or unsubstituted alkyl group,

R2 and R3 are the same as or different from each other, and are each independently hydrogen; a substituted or unsubstituted alkyl group; or a substituted or unsubstituted aryl group,

a is an integer of 0 to 5,

b is an integer of 0 to 7,

c is an integer of 0 to 11, and when a is 2 or more, R1's are the same as or different from each other,


when b is 2 or more, R2's are the same as or different from each other, and

when c is 2 or more, R3's are the same as or different from each other,


wherein the term "substituted or unsubstituted" means being unsubstituted or substituted with one or more substituents selected from the group consisting of deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amino group; a phosphine oxide group; an alkoxy group; an aryloxy group; an alkylthioxy group; an arylthioxy group; an alkylsulfoxy group; an arylsulfoxy group; a silyl group; a boron group; a germanium group; an alkyl group; a cycloalkyl group; an alkenyl group; an aryl group; an aralkyl group; an aralkenyl group; an alkylaryl group; an alkylamine group; an aralkylamine group; a heteroarylamine group; an arylamine group; an arylphosphine group; and a heterocyclic group, or being unsubstituted or substituted with a substituent to which two or more substituents among the preceding substituents are linked.

2. The compound of claim 1, wherein Chemical Formula 1 is represented by the following Chemical Formula 2 or 3:

[Chemical Formula 2]




[Chemical Formula 3]




in Chemical Formula 2 and Chemical Formula 3, the definitions of Ar1, L, R1, R3, a, and c are each the same as those in Chemical Formula 1.

3. The compound of claim 1, wherein Chemical Formula 1 is represented by the following Chemical Formula 4 or 5:

[Chemical Formula 4]




[Chemical Formula 5]




in Chemical Formula 4 and Chemical Formula 5, the definitions of Ar1, L, R1, and a are each the same as those in Chemical Formula 1.
















4. The compound of claim 1, wherein Ar1 is a substituted or unsubstituted phenyl group; a substituted or unsubstituted biphenyl group; a substituted or unsubstituted terphenyl group; a substituted or unsubstituted naphthyl group; a substituted or unsubstituted fluorenyl group; a substituted or unsubstituted phenanthrenyl group; or a substituted or unsubstituted triphenylenyl group.
5. The compound of claim 1, wherein Ar1 is any one selected from the following structures:




the structures are optionally substituted or unsubstituted with deuterium; an alkyl group; or an aryl group.


6. The compound of claim 1, wherein the compound of Chemical Formula 1 is any one selected from the following structural formulae:









19




20




21




22




23




24




25




26




27




28




29




30


















31






























32




33












76




77




78




79




80




81




82




83




84




85



86



87



7. An organic light emitting device comprising:

a first electrode;
a second electrode; and
one or more organic material layers disposed between the first electrode and the second electrode,
wherein one or more layers of the organic material layers comprise the compound of any one of claims 1 to 6.

8. The organic light emitting device of claim 7, wherein the organic material layer comprises one or more layers of an electron transport layer, an electron injection layer, and a layer which transports and injects electrons simultaneously, and one or more layers of the layers comprise the compound.

9. The organic light emitting device of claim 7, wherein the organic material layer comprises a light emitting layer, and the light emitting layer comprises the compound as a host of the light emitting layer.


10. The organic light emitting device of claim 7, wherein the organic material layer comprises one or more layers of a hole injection layer, an electron blocking layer, a hole transport layer, and a layer which injects and transports holes

simultaneously, and one or more layers of the layers comprise the compound.

11. The organic light emitting device of claim 7, wherein the organic material layer comprises the compound as a host, and comprises another organic compound, a metal, or a metal compound as a dopant.

12. The organic light emitting device of claim 7, wherein the organic material layer comprises a light emitting layer, and the light emitting layer comprises a compound represented by the following Chemical Formula 6:

[Chemical Formula 6]



in Chemical Formula 6,

Ar2 is a substituted or unsubstituted monovalent or more benzofluorene group; a substituted or unsubstituted monovalent or more fluoranthene group; a substituted or unsubstituted monovalent or more pyrene group; or a substituted or unsubstituted monovalent or more chrysene group,

L1 is a direct bond; a substituted or unsubstituted arylene group; or a substituted or unsubstituted heteroarylene group,


Ar3 and Ar4 are the same as or different from each other, and are each independently a substituted or unsubstituted aryl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted aralkyl group; or a substituted or unsubstituted heteroaryl group, or optionally combine with each other to form a substituted or unsubstituted ring,

r is an integer of 1 or more, and

when r is 2 or more, the substituents in the parenthesis are the same as or different from each other, wherein the term "substituted or unsubstituted" means being unsubstituted or substituted with one or more substituents selected from the group consisting of deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amino group; a phosphine oxide group; an alkoxy group; an aryloxy group; an alkylthioxy group; an arylthioxy group; an alkylsulfoxy group; an arylsulfoxy group; a silyl group; a boron group; a germanium group; an alkyl group; a cycloalkyl group; an alkenyl group; an aryl group; an aralkyl group; an aralkenyl group; an alkylaryl group; an alkylamine group; an aralkylamine group; a heteroarylamine group; an arylamine group; an arylphosphine group; and a heterocyclic group, or being unsubstituted or substituted with a substituent to which two or more substituents among the preceding substituents are linked.


13. The organic light emitting device of claim 7, wherein the organic material layer comprises a light emitting layer, and the light emitting layer comprises a compound represented by the following Chemical Formula 7:

[Chemical Formula 7]



in Chemical Formula 7,

X1 is a 1-naphthyl group, a 2-naphthyl group, a 1-anthryl group, a 2-anthryl group, a 1-phenanthryl group, a 2-phenanthryl group, a 3-phenanthryl group, a 4-phenanthryl group, a 9-phenanthryl group, a 1-naphthacenyl group, a 2-naphthacenyl group, a 9-naphthacenyl group, a 1-pyrenyl group, a 2-pyrenyl group, a 4-pyrenyl group, a 3-methyl-2-naphthyl group, a 4-methyl-1-naphthyl group, or the following Chemical Formula



X3 is a phenyl group, a 1-naphthyl group, a 2-naphthyl group, a 1-anthryl group, a 2-anthryl group, a 1-phenanthryl group, a 2-phenanthryl group, a 3-phenanthryl group, a 4-phenanthryl group, a 9-phenanthryl group, a 1-naphthacenyl group, a 2-naphthacenyl group, a 9-naphthacenyl group, a 1-pyrenyl group, a 2-pyrenyl group, a 4-pyrenyl group, a 2-biphenyl group, a 3-biphenyl group, a 4-biphenyl group, a p-terphenyl-4-yl group, a p-terphenyl-3-yl group, a p-terphenyl-2-yl group, an m-terphenyl-4-yl group, an m-terphenyl-3-yl group, an m-terphenyl-2-yl group, an o-tolyl group, an m-tolyl group, a p-tolyl group, a p-t-butylphenyl group, a p-(2-phenyl-propyl)phenyl group, a 3-methyl-2-naphthyl group, a 4-methyl-1-naphthyl group, a 4-methyl-1-anthryl group, a 4'-methylbiphenyl group, a 4"-t-butyl-p-terphenyl-4-yl group, or a 3-fluoranthenyl group,

X2 and X4 are the same as or different from each other, and are each independently hydrogen; a substituted or unsubstituted alkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryl group; or a substituted or unsubstituted heteroaryl group,

p2 is an integer of 1 to 5,


p1 and p3 are each an integer of 1 to 4, and

when p1 to p3 are each 2 or more, the substituents in the parenthesis are the same as or different from each other, wherein the term "substituted or unsubstituted" means being unsubstituted or substituted with one or more substituents selected from the group consisting of deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amino group; a phosphine oxide group; an alkoxy group; an aryloxy group; an alkylthio group; an arylthio group; an alkylsulfoxy group; an arylsulfoxy group; a silyl group; a boron group; a germanium group; an alkyl group; a cycloalkyl group; an alkenyl group; an aryl group; an aralkyl group; an aralkenyl group; an alkylaryl group; an alkylamine group; an aralkylamine group; a heteroarylamine group; an arylamine group; an arylphosphine group; and a heterocyclic group, or being unsubstituted or substituted with a substituent to which two or more substituents among the preceding substituents are linked.

14. The organic light emitting device of claim 13, wherein X1 is a 1-naphthyl group, and X3 is a 2-naphthyl group.


15. The organic light emitting device of claim 12, wherein the light emitting layer comprises a compound represented by the following Chemical Formula 7:

[Chemical Formula 7]



in Chemical Formula 7,


X1 is a 1-naphthyl group, a 2-naphthyl group, a 1-anthryl group, a 2-anthryl group, a 1-phenanthryl group, a 2-phenanthryl group, a 3-phenanthryl group, a 4-phenanthryl group, a 9-phenanthryl group, a 1-naphthacenyl group, a 2-naphthacenyl group, a 9-naphthacenyl group, a 1-pyrenyl group, a 2-pyrenyl group, a 4-pyrenyl group, a 3-methyl-2-naphthyl group, a 4-methyl-1-naphthyl group, or the following Chemical Formula



X3 is a phenyl group, a 1-naphthyl group, a 2-naphthyl group, a 1-anthryl group, a 2-anthryl group, a 1-phenanthryl group, a 2-phenanthryl group, a 3-phenanthryl group, a 4-phenanthryl group, a 9-phenanthryl group, a 1-naphthacenyl group, a 2-naphthacenyl group, a 9-naphthacenyl group, a 1-pyrenyl group, a 2-pyrenyl group, a 4-pyrenyl group, a 2-biphenyl group, a 3-biphenyl group, a 4-biphenyl group, a p-terphenyl-4-yl group, a p-terphenyl-3-yl group, a p-terphenyl-2-yl group, an m-terphenyl-4-yl group, an m-terphenyl-3-yl group, an m-terphenyl-2-yl group, an o-tolyl group, an m-tolyl group, a p-tolyl group, a p-t-butylphenyl group, a p-(2-phenylpropyl)phenyl group, a 3-methyl-2-naphthyl group, a 4-methyl-1-naphthyl group, a 4-methyl-1-anthryl group, a 4'-methylbiphenyl group, a 4"-t-butyl-p-terphenyl-4-yl group, or a 3-fluoranthryl group, X2 and X4 are the same as or different from each other, and are each independently hydrogen; a substituted or unsubstituted alkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryl group; or a substituted or unsubstituted heteroaryl group, p2 is an integer of 1 to 5, p1 and p3 are each an integer of 1 to 4, and when p1 to p3 are each 2 or more, the substituents in the parenthesis are the same as or different from each other.

Patentansprüche


1. Verbindung, die durch die folgende chemische Formel 1 dargestellt ist:




chemische Formel 1

worin in der chemischen Formel 1,


X



ist,
Y



ist,
Z



ist,

Ar1 eine substituierte oder unsubstituierte Arylgruppe ist,

L eine direkte Bindung; oder eine substituierte oder unsubstituierte Arylgruppe ist,

R1 Wasserstoff; Deuterium; oder eine substituierte oder unsubstituierte Alkylgruppe ist,

R2 und R3 gleich oder voneinander verschieden sind und unabhängig voneinander Wasserstoff; eine substituierte oder unsubstituierte Alkylgruppe; oder eine substituierte oder unsubstituierte Arylgruppe ist,

a eine Zahl von 0 bis 5 ist,

b eine Zahl von 0 bis 7 ist,

c eine Zahl von 0 bis 11 ist, und

R1 gleich oder voneinander verschieden sind, wenn a 2 oder größer ist,


R2 gleich oder voneinander verschieden sind, wenn b 2 oder größer ist und

R3 gleich oder voneinander verschieden sind, wenn c 2 oder größer ist,


worin der Ausdruck "substituiert oder unsubstituiert" bedeutet, unsubstituiert oder mit einem oder mehreren Substituenten substituiert zu sein, ausgewählt aus der Gruppe bestehend aus Deuterium; einer Halogengruppe; einer Nitrilgruppe; einer Nitrogruppe; einer Hydroxygruppe; einer Carbonylgruppe; einer Estergruppe; einer Imidgruppe; einer Aminogruppe; einer Phosphinoxidgruppe; einer Alkoxygruppe; einer Aryloxygruppe; einer Alkylthioxygruppe; einer Arylthioxygruppe; einer Alkylsulfoxygruppe; einer Arylsulfoxygruppe; einer Silylgruppe; einer Borgruppe; einer Germaniumgruppe; einer Alkylgruppe; einer Cycloalkylgruppe; einer Alkenylgruppe; einer Arylgruppe; einer Aralkylgruppe; einer Aralkenylgruppe; einer Alkylarylgruppe; einer Alkylamingruppe; einer Aralkylamingruppe; einer Heteroarylamingruppe; einer Arylamingruppe; einer Arylphosphingruppe; und einer heterocyclischen Gruppe, oder unsubstituiert oder mit einem Substituenten substituiert zu sein, mit welchem zwei oder mehrere Substituenten unter den vorangegangenen Substituenten verbunden sind.

2. Verbindung gemäß Anspruch 1, worin die chemische Formel 1 durch die folgende chemische Formel 2 oder 3 dargestellt ist:

[chemische Formel 2]




[chemische Formel 3]




worin die Definitionen von Ar1, L, R1, R3, a und c in der chemischen Formel 2 und der chemischen Formel 3 die gleichen wie in der chemischen Formel 1 sind.

3. Verbindung gemäß Anspruch 1, worin die chemische Formel 1 durch die folgende chemische Formel 4 oder 5 dargestellt ist:

[chemische Formel 4]




[chemische Formel 5]



worin die Definitionen von Ar1, L, R1 und a in der chemischen Formel 4 und der chemischen Formel 4 die gleichen wie in der chemischen Formel 1 sind.

4. Verbindung gemäß Anspruch 1, worin Ar1 eine substituierte oder unsubstituierte Phenylgruppe; eine substituierte oder unsubstituierte Biphenylgruppe; eine substituierte oder unsubstituierte Terphenylgruppe; eine substituierte oder unsubstituierte Naphthylgruppe; eine substituierte oder unsubstituierte Fluorenylgruppe; eine substituierte oder unsubstituierte Phenanthrenylgruppe; oder eine substituierte oder unsubstituierte Triphenylenylgruppe ist.

5. Verbindung gemäß Anspruch 1, worin Ar1 irgendeines ist, ausgewählt aus den folgenden Strukturen:




worin die Strukturen gegebenenfalls substituiert oder unsubstituiert mit Deuterium; einer Alkylgruppe; oder einer Arylgruppe sind.



6. Verbindung gemäß Anspruch 1, worin die Verbindung der chemischen Formel 1 irgendeine ist, ausgewählt aus den

folgenden Strukturformeln:


5

**1**



10

**2****3**


15

**4**



20

**5****6**


25

**7**



30

**8****9**


35

**10**


40

**11****12**


45
















**13**

50


**14**

55



**15**




5

**31**



10

**32****33**


15

**34**



20

**35****36**


25

**37**



30

**38****39**


35

**40**



40

**41****42**
















45

**43**

50




**44****45**

55






5

10






15

20



25




30



35

40


45



50


55

5




73

10




74




75

15




76

20




77




78

25




79

30




80

35




81

40




82

45













83

50



84

55




7. Organische lichtemittierende Vorrichtung, umfassend:

eine erste Elektrode;
eine zweite Elektrode; und

eine oder mehrere Schichten aus organischem Material, die zwischen der ersten Elektrode und der zweiten Elektrode angeordnet sind,
 worin eine oder mehrere Schichten der Schichten aus organischem Material die Verbindung gemäß mindestens einem der Ansprüche 1 bis 6 umfassen.

8. Organische lichtemittierende Vorrichtung gemäß Anspruch 7, worin die Schicht aus organischem Material eine oder mehrere Schichten einer Elektronenübertragungsschicht, einer Elektroneninjectionsschicht und einer Schicht umfasst, die gleichzeitig Elektronen überträgt und injiziert, und eine oder mehrere Schichten der Schichten die Verbindung umfassen.
9. Organische lichtemittierende Vorrichtung gemäß Anspruch 7, worin die Schicht aus organischem Material eine lichtemittierende Schicht umfasst und die lichtemittierende Schicht die Verbindung als Wirt der lichtemittierenden Schicht umfasst.
10. Organische lichtemittierende Vorrichtung gemäß Anspruch 7, worin die Schicht aus organischem Material eine oder mehrere Schichten einer Lochinjectionsschicht, einer Elektronenblockierschicht, einer Lochübertragungsschicht und einer Schicht umfasst, die gleichzeitig Löcher injiziert und überträgt und eine oder mehrere Schichten der Schichten die Verbindung umfassen.
11. Organische lichtemittierende Vorrichtung gemäß Anspruch 7, worin die Schicht aus organischem Material die Verbindung als Wirt umfasst und eine weitere organische Verbindung, ein Metall oder eine Metallverbindung als Dotierstoff umfasst.
12. Organische lichtemittierende Vorrichtung gemäß Anspruch 7, worin die Schicht aus organischem Material eine lichtemittierende Schicht umfasst und die lichtemittierende Schicht eine Verbindung umfasst, die durch die folgende chemische Formel 6 dargestellt ist:



worin in der chemischen Formel 6

Ar2 eine substituierte oder unsubstituierte, ein- oder mehrwertige Benzofluorengruppe; eine substituierte oder unsubstituierte, ein- oder mehrwertige Fluoranthengruppe; eine substituierte oder unsubstituierte, ein- oder mehrwertige Pyrenggruppe; oder eine substituierte oder unsubstituierte, ein- oder mehrwertige Chrysegruppe ist,

L1 eine direkte Bindung; eine substituierte oder unsubstituierte Arylengruppe; oder eine substituierte oder unsubstituierte Heteroarylengruppe ist,

Ar3 und Ar4 gleich oder voneinander verschieden sind und jeweils unabhängig voneinander eine substituierte oder unsubstituierte Arylgruppe; eine substituierte oder unsubstituierte Silylgruppe; eine substituierte oder unsubstituierte Alkylgruppe; eine substituierte oder unsubstituierte Aralkylgruppe; oder eine substituierte oder unsubstituierte Heteroarylgruppe sind oder gegebenenfalls miteinander verbunden sind, um einen substituierten oder unsubstituierten Ring zu bilden,


r eine Zahl von 1 oder größer ist und

die Substituenten in den Klammern gleich oder voneinander verschieden sind, wenn r 2 oder größer ist, worin der Ausdruck "substituiert oder unsubstituiert" bedeutet, unsubstituiert oder mit einem oder mehreren Substituenten substituiert zu sein, ausgewählt aus der Gruppe bestehend aus Deuterium; einer Halogengruppe; einer Nitrilgruppe; einer Nitrogruppe; einer Hydroxygruppe; einer Carbonylgruppe; einer Estergruppe; einer Imidgruppe; einer Aminogruppe; einer Phosphinoxidgruppe; einer Alkoxygruppe; einer Aryloxygruppe; einer Alkylthioxygruppe; einer Arylthioxygruppe; einer Alkylsulfoxygruppe; einer Arylsulfoxygruppe; einer Silylgruppe; einer Borgruppe; einer Germaniumgruppe; einer Alkylgruppe; einer Cycloalkylgruppe; einer Alkenylgruppe; einer Arylgruppe; einer Aralkylgruppe; einer Aralkenylgruppe; einer Alkylarylgruppe; einer Alkylaminogruppe; einer Aralkylaminogruppe; einer Heteroarylaminogruppe; einer Arylaminogruppe; einer Arylphosphingruppe; und

einer heterocyclischen Gruppe, oder unsubstituiert oder mit einem Substituenten substituiert zu sein, mit welchem zwei oder mehrere Substituenten unter den vorangegangenen Substituenten verbunden sind.


13. Organische lichtemittierende Vorrichtung gemäß Anspruch 7, worin die Schicht aus organischem Material eine lichtemittierende Schicht umfasst und die lichtemittierende Schicht eine Verbindung umfasst, die durch die folgende chemische Formel 7 dargestellt ist:

[chemische Formel 7]



worin in der chemischen Formel 7

X1 eine 1-Naphthylgruppe, eine 2-Naphthylgruppe, eine 1-Anthrylgruppe, eine 2-Anthrylgruppe, eine 1-Phenanthrylgruppe, eine 2-Phenanthrylgruppe, eine 3-Phenanthrylgruppe, eine 4-Phenanthrylgruppe, eine 9-Phenanthrylgruppe, eine 1-Naphthacenylgruppe, eine 2-Naphthacenylgruppe, eine 9-Naphthacenylgruppe, eine 1-Pyrenylgruppe, eine 2-Pyrenylgruppe, eine 4-Pyrenylgruppe, eine 3-Methyl-2-naphthylgruppe, eine 4-Methyl-1-naphthylgruppe oder die folgende chemische Formel ist



X3 eine Phenylgruppe, eine 1-Naphthylgruppe, eine 2-Naphthylgruppe, eine 1-Anthrylgruppe, eine 2-Anthrylgruppe, eine 1-Phenanthrylgruppe, eine 2-Phenanthrylgruppe, eine 3-Phenanthrylgruppe, eine 4-Phenanthrylgruppe, eine 9-Phenanthrylgruppe, eine 1-Naphthacenylgruppe, eine 2-Naphthacenylgruppe, eine 9-Naphthacenylgruppe, eine 1-Pyrenylgruppe, eine 2-Pyrenylgruppe, eine 4-Pyrenylgruppe, eine 2-Biphenylgruppe, eine 3-Biphenylgruppe, eine 4-Biphenylgruppe, eine p-Terphenyl-4-ylgruppe, eine p-Terphenyl-3-ylgruppe, eine p-Terphenyl-2-ylgruppe, eine m-Terphenyl-4-ylgruppe, eine m-Terphenyl-3-ylgruppe, eine m-Terphenyl-2-ylgruppe, eine o-Tolylgruppe, eine m-Tolylgruppe, eine p-Tolylgruppe, eine p-t-Butylphenylgruppe, eine p-(2-Phenylpropyl)phenylgruppe, eine 3-Methyl-2-naphthylgruppe, eine 4-Methyl-1-naphthylgruppe, eine 4-Methyl-1-anthrylgruppe, eine 4'-Methylbiphenylgruppe, eine 4"-t-Butyl-p-terphenyl-4-ylgruppe oder eine 3-Fluoranthrylgruppe ist,

X2 und X4 gleich oder voneinander verschieden sind und jeweils unabhängig voneinander Wasserstoff; eine substituierte oder unsubstituierte Alkylgruppe; eine substituierte oder unsubstituierte Alkoxygruppe; eine substituierte oder unsubstituierte Arylgruppe; oder eine substituierte oder unsubstituierte Heteroarylgruppe sind, p2 eine Zahl von 1 bis 5 ist,

p1 und p3 jeweils eine Zahl von 1 bis 4 sind und

die Substituenten in den Klammern gleich oder voneinander verschieden sind, wenn p1 bis p3 jeweils 2 oder größer sind,


worin der Ausdruck "substituiert oder unsubstituiert" bedeutet, unsubstituiert oder mit einem oder mehreren Substituenten substituiert zu sein, ausgewählt aus der Gruppe bestehend aus Deuterium; einer Halogengruppe; einer Nitrilgruppe; einer Nitrogruppe; einer Hydroxygruppe; einer Carbonylgruppe; einer Estergruppe; einer

Imidgruppe; einer Aminogruppe; einer Phosphinoxidgruppe; einer Alkoxygruppe; einer Aryloxygruppe; einer Alkylthioxygruppe; einer Arylthioxygruppe; einer Alkylsulfoxygruppe; einer Arylsulfoxygruppe; einer Silylgruppe; einer Borgruppe; einer Germaniumgruppe; einer Alkylgruppe; einer Cycloalkylgruppe; einer Alkenylgruppe; einer Arylgruppe; einer Aralkylgruppe; einer Aralkenylgruppe; einer Alkylarylgruppe; einer Alkylamingruppe; einer Aralkylamingruppe; einer Heteroarylamingruppe; einer Arylamingruppe; einer Arylphosphingruppe; und einer heterocyclischen Gruppe, oder unsubstituiert oder mit einem Substituenten substituiert zu sein, mit welchem zwei oder mehrere Substituenten unter den vorangegangenen Substituenten verbunden sind.

14. Organische lichtemittierende Vorrichtung gemäß Anspruch 13, worin X1 eine 1-Naphthylgruppe ist und X3 eine 2-Naphthylgruppe ist.


15. Organische lichtemittierende Vorrichtung gemäß Anspruch 12, worin die lichtemittierende Schicht eine Verbindung umfasst, die durch die folgende chemische Formel 7 dargestellt ist:

[chemische Formel 7]



worin in der chemischen Formel 7

X1 eine 1-Naphthylgruppe, eine 2-Naphthylgruppe, eine 1-Anthrylgruppe, eine 2-Anthrylgruppe, eine 1-Phenanthrylgruppe, eine 2-Phenanthrylgruppe, eine 3-Phenanthrylgruppe, eine 4-Phenanthrylgruppe, eine 9-Phenanthrylgruppe, eine 1-Naphthacenylgruppe, eine 2-Naphthacenylgruppe, eine 9-Naphthacenylgruppe, eine 1-Pyrenylgruppe, eine 2-Pyrenylgruppe, eine 4-Pyrenylgruppe, eine 3-Methyl-2-naphthylgruppe, eine 4-Methyl-1-naphthylgruppe oder die folgende chemische Formel ist



X3 eine Phenylgruppe, eine 1-Naphtylgruppe, eine 2-Naphtylgruppe, eine 1-Anthrylgruppe, eine 2-Anthrylgruppe, eine 1-Phenanthrylgruppe, eine 2-Phenanthrylgruppe, eine 3-Phenanthrylgruppe, eine 4-Phenanthrylgruppe, eine 9-Phenanthrylgruppe, eine 1-Naphthacenylgruppe, eine 2-Naphthacenylgruppe, eine 9-Naphthacenylgruppe, eine 1-Pyrenylgruppe, eine 2-Pyrenylgruppe, eine 4-Pyrenylgruppe, eine 2-Biphenylgruppe, eine 2-Biphenylgruppe, eine 3-Biphenylgruppe, eine 4-Biphenylgruppe, eine p-Terphenyl-4-ylgruppe, eine p-Terphenyl-3-ylgruppe, eine p-Terphenyl-2-ylgruppe, eine m-Terphenyl-4-ylgruppe, eine m-Terphenyl-3-ylgruppe, eine m-Terphenyl-2-ylgruppe, eine o-Tolylgruppe, eine m-Tolylgruppe, eine p-Tolylgruppe, eine p-t-Butylphenylgruppe, eine p-(2-Phenylpropyl)phenylgruppe, eine 3-Methyl-2-naphthylgruppe, eine 4-Methyl-1-naphthylgruppe, eine 4-Methyl-1-anthrylgruppe, eine 4'-Methylbiphenylgruppe, eine 4"-t-Butyl-p-terphenyl-4-ylgruppe oder eine 3-Fluoranthenylgruppe ist,

X2 und X4 gleich oder voneinander verschieden sind und unabhängig voneinander Wasserstoff; eine substituierte oder unsubstituierte Alkylgruppe; eine substituierte oder unsubstituierte Alkoxygruppe; eine substituierte oder unsubstituierte Arylgruppe; oder eine substituierte oder unsubstituierte Heteroarylgruppe ist,


p2 eine Zahl von 1 bis 5 ist,

p1 und p3 jeweils eine Zahl von 1 bis 4 sind und

die Substituenten in den Klammern gleich oder verschieden voneinander sind, wenn p1 bis p3 jeweils 2 oder größer sind.

Revendications


1. Composé représenté par la formule chimique 1 suivante :




[Formule chimique 1]

dans la formule chimique 1,


X est



Y est



Z est



Ar1 est un groupe aryle substitué ou non substitué,

L est une liaison directe ; ou un groupe arylène substitué ou non substitué,

R1 est de l'hydrogène ; du deutérium ; ou un groupe alkyle substitué ou non substitué,

R2 et R3 sont identiques ou différents l'un de l'autre, et représentent chacun indépendamment de l'hydrogène ; un groupe alkyle substitué ou non substitué ; ou un groupe aryle substitué ou non substitué,

a est un entier de 0 à 5,

b est un entier de 0 à 7,

c est un entier de 0 à 11, et quand a vaut 2 ou plus, les R1 sont identiques ou différents les uns des autres,


lorsque b vaut 2 ou plus, les R2 sont identiques ou différents l'un de l'autre, et

quand c vaut 2 ou plus, les R3 sont identiques ou différents les uns des autres,


dans lequel l'expression « substitué ou non substitué » signifie être non substitué ou substitué par un ou plusieurs substituants choisis dans le groupe constitué par le deutérium ; un groupe halogène ; un groupe nitrile ; un groupe nitro ; un groupe hydroxy ; un groupe carbonyle ; un groupe ester ; un groupe imide ; un groupe amino ; un groupe oxyde de phosphine ; un groupe alcoxy ; un groupe aryloxy ; un groupe alkylthioxy ; un groupe arylthioxy ; un groupe alkylsulfoxy ; un groupe arylsulfoxy ; un groupe silyle ; un groupe bore ; un groupe germanium ; un groupe alkyle ; un groupe cycloalkyle ; un groupe alcényle ; un groupe aryle ; un groupe aralkyle ; un groupe aralcényle ; un groupe alkylaryle ; un groupe alkylamine ; un groupe aralkylamine ; un groupe hétéroarylamine ; un groupe arylamine ; un groupe arylphosphine ; et un groupe hétérocyclique, ou être non substitué ou substitué par un substituant auquel deux substituants ou plus parmi les substituants précédents sont liés.

2. Composé selon la revendication 1, dans lequel la formule chimique 1 est représentée par les formules chimiques 2 ou 3 suivantes :

[Formule chimique 2]




[Formule chimique 3]




dans les formules chimiques 2 et 3, les définitions de Ar1, L, R1, R3, a et c sont chacune identiques à celles de la formule chimique 1.

3. Composé selon la revendication 1, dans lequel la formule chimique 1 est représentée par les formules chimiques 4 ou 5 suivantes :

[Formule chimique 4]





[Formule chimique 5]



dans les formules chimiques 4 et 5, les définitions de Ar1, L, R1 et a sont chacune identiques à celles de la formule chimique 1.




4. Composé selon la revendication 1, dans lequel Ar1 est un groupe phényle substitué ou non substitué ; un groupe biphenyle substitué ou non substitué ; un groupe terphenyle substitué ou non substitué ; un groupe naphthyle substitué ou non substitué ; un groupe fluorényle substitué ou non substitué ; un groupe phénanthrényle substitué ou non substitué ; ou un groupe triphénylényle substitué ou non substitué.
















5. Composé selon la revendication 1, dans lequel Ar1 est une quelconque choisie parmi les structures suivantes :









les structures sont facultativement substituées ou non substituées par du deutérium ; un groupe alkyle ; ou un groupe aryle.

6. Composé selon la revendication 1, dans lequel le composé de formule chimique 1 est un quelconque choisi parmi les formules structurales suivantes :












40




41




42




43




44




45




46




47




48




49




50




51


















52



























53




54









7. Dispositif électroluminescent organique comprenant :

une première électrode ;
 une seconde électrode ; et
 une ou plusieurs couches de matériau organique disposées entre la première électrode et la seconde électrode,
 dans lequel une ou plusieurs couches des couches de matériau organique comprennent le composé de l'une
 quelconque des revendications 1 à 6.

8. Dispositif électroluminescent organique selon la revendication 7, dans lequel la couche de matériau organique
 comprend une ou plusieurs couches parmi une couche de transport d'électrons, une couche d'injection d'électrons
 et une couche qui transporte et injecte des électrons simultanément, et une ou plusieurs couches parmi les couches
 comprennent le composé.


9. Dispositif électroluminescent organique selon la revendication 7, dans lequel la couche de matériau organique
 comprend une couche électroluminescente, et la couche électroluminescente comprend le composé en tant qu'hôte
 de la couche électroluminescente.

10. Dispositif électroluminescent organique selon la revendication 7, dans lequel la couche de matériau organique
 comprend une ou plusieurs couches d'une couche d'injection de trous, d'une couche de blocage d'électrons, d'une
 couche de transport de trous et d'une couche qui injecte et transporte des trous simultanément, et une ou plusieurs
 couches parmi les couches comprennent le composé.

11. Dispositif électroluminescent organique selon la revendication 7, dans lequel la couche de matériau organique
 comprend le composé en tant qu'hôte, et comprend un autre composé organique, un métal, ou un composé métallique
 en tant que dopant.

12. Dispositif électroluminescent organique selon la revendication 7, dans lequel la couche de matériau organique
 comprend une couche électroluminescente, et la couche électroluminescente comprend un composé représenté
 par la formule chimique 6 suivante :

[Formule chimique 6]



dans une formule chimique 6,

Ar2 est un groupe benzofluorène monovalent ou plus substitué ou non substitué ; un groupe fluoranthène
 monovalent ou plus substitué ou non substitué ; un groupe pyrène monovalent ou plus substitué ou non substitué ;
 ou un groupe chrysène monovalent ou plus substitué ou non substitué,

L1 est une liaison directe ; un groupe arylène substitué ou non substitué ; ou un groupe hétéroarylène substitué ou non substitué,


Ar3 et Ar4 sont identiques ou différents l'un de l'autre, et sont chacun indépendamment un groupe aryle substitué ou non substitué ; un groupe silyle substitué ou non substitué ; un groupe alkyle substitué ou non substitué ; un groupe aralkyle substitué ou non substitué ; ou un groupe hétéroaryle substitué ou non substitué, ou sont facultativement combinés l'un avec l'autre pour former un cycle substitué ou non substitué,

r est un entier égal à 1 ou plus, et

lorsque r vaut 2 ou plus, les substituants entre parenthèses sont identiques ou différents les uns des autres, dans lequel l'expression « substitué ou non substitué » signifie être non substitué ou substitué par un ou plusieurs substituants choisis dans le groupe constitué par le deutérium ; un groupe halogène ; un groupe nitrile ; un groupe nitro ; un groupe hydroxy ; un groupe carbonyle ; un groupe ester ; un groupe imide ; un groupe amino ; un groupe oxyde de phosphine ; un groupe alcoxy ; un groupe aryloxy ; un groupe alkylthioxy ; un groupe arylthioxy ; un groupe alkylsulfoxy ; un groupe arylsulfoxy ; un groupe silyle ; un groupe bore ; un groupe germanium ; un groupe alkyle ; un groupe cycloalkyle ; un groupe alcényle ; un groupe aryle ; un groupe aralkyle ; un groupe aralcényle ; un groupe alkylaryle ; un groupe alkylamine ; un groupe aralkylamine ; un groupe hétéroarylamine ; un groupe arylamine ; un groupe arylphosphine ; et un groupe hétérocyclique, ou être non substitué ou substitué par un substituant auquel deux substituants ou plus parmi les substituants précédents sont liés.


13. Dispositif électroluminescent organique selon la revendication 7, dans lequel la couche de matériau organique comprend une couche électroluminescente, et la couche électroluminescente comprend un composé représenté par la formule chimique 7 suivante :

[Formule chimique 7]



dans une formule chimique 7,

X1 est un groupe 1-naphtyle, un groupe 2-naphtyle, un groupe 1-anthryle, un groupe 2-anthryle, un groupe 1-phénanthryle, un groupe 2-phénanthryle, un groupe 3-phénanthryle, un groupe 4-phénanthryle, un groupe 9-phénanthryle, un groupe 1-naphthacényle, un groupe 2-naphthacényle, un groupe 9-naphthacényle, un groupe 1-pyrényle, un groupe 2-pyrényle, un groupe 4-pyrényle, un groupe 3-méthyl-2-naphtyle, un groupe 4-méthyl-1-naphtyle, ou la formule chimique suivante



X3 est un groupe phényle, un groupe 1-naphtyle, un groupe 2-naphtyle, un groupe 1-anthryle, un groupe 2-anthryle, un groupe 1-phénanthryle, un groupe 2-phénanthryle, un groupe 3-phénanthryle, un groupe 4-phénanthryle, un groupe 9-phénanthryle, un groupe 1-naphthacényle, un groupe 2-naphthacényle, un groupe 9-naphthacényle, un groupe 1-pyrényle, un groupe 2-pyrényle, un groupe 4-pyrényle, un groupe 2-biphényllyle, un groupe 3-biphényllyle, un groupe 4-biphényllyle, un groupe p-terphényl-4-yle, un groupe p-terphényl-3-yle, un groupe p-terphényl-2-yle, un groupe m-terphényl-4-yle, un groupe m-terphényl-3-yle, un groupe m-terphényl-

2-yle, un groupe o-tolyle, un groupe m-tolyle, un groupe p-tolyle, un groupe p-t-butylphényle, un groupe p-(2-phénylpropyl)phényle, un groupe 3-méthyl-2-naphtyle, un groupe 4-méthyl-1-naphtyle, un groupe 4-méthyl-1-anthryle, un groupe 4'-méthylbiphénylyle, un groupe 4"-t-butyl-p-terphényl-4-yle, ou un groupe 3-fluoranthényle, X2 et X4 sont identiques ou différents l'un de l'autre et représentent chacun indépendamment de l'hydrogène;

un groupe alkyle substitué ou non substitué; un groupe alcoxy substitué ou non substitué; un groupe aryle substitué ou non substitué; ou un groupe hétéroaryle substitué ou non substitué,

p2 est un entier de 1 à 5,

p1 et p3 sont chacun un entier de 1 à 4, et


lorsque p1 à p3 sont chacun 2 ou plus, les substituants entre parenthèses sont identiques ou différents les uns des autres,

dans lequel l'expression « substitué ou non substitué » signifie être non substitué ou substitué par un ou plusieurs substituants choisis dans le groupe constitué par le deutérium; un groupe halogène; un groupe nitrile; un groupe nitro; un groupe hydroxy; un groupe carbonyle; un groupe ester; un groupe imide; un groupe amino; un groupe oxyde de phosphine; un groupe alcoxy; un groupe aryloxy; un groupe alkylthioxy; un groupe arylthioxy; un groupe alkylsulfoxy; un groupe arylsulfoxy; un groupe silyle; un groupe bore; un groupe germanium; un groupe alkyle; un groupe cycloalkyle; un groupe alcényle; un groupe aryle; un groupe aralkyle; un groupe aralcényle; un groupe alkylaryle; un groupe alkylamine; un groupe aralkylamine; un groupe hétéroarylamine; un groupe arylamine; un groupe arylphosphine; et un groupe hétérocyclique, ou être non substitué ou substitué par un substituant auquel deux substituants ou plus parmi les substituants précédents sont liés.

14. Dispositif électroluminescent organique selon la revendication 13, dans lequel X1 est un groupe 1-naphtyle et X3 est un groupe 2-naphtyle.


15. Dispositif électroluminescent organique selon la revendication 12, dans lequel la couche électroluminescente comprend un composé représenté par la formule chimique 7 suivante :

[Formule chimique 7]



dans la formule chimique 7,

X1 est un groupe 1-naphtyle, un groupe 2-naphtyle, un groupe 1-anthryle, un groupe 2-anthryle, un groupe 1-phénanthryle, un groupe 2-phénanthryle, un groupe 3-phénanthryle, un groupe 4-phénanthryle, un groupe 9-phénanthryle, un groupe 1-naphthacényle, un groupe 2-naphthacényle, un groupe 9-naphthacényle, un groupe 1-pyrényle, un groupe 2-pyrényle, un groupe 4-pyrényle, un groupe 3-méthyl-2-naphtyle, un groupe 4-méthyl-1-naphtyle, ou la formule chimique suivante



X3 est un groupe phényle, un groupe 1-naphtyle, un groupe 2-naphtyle, un groupe 1-anthryle, un groupe 2-anthryle, un groupe 1-phénanthryle, un groupe 2-phénanthryle, un groupe 3-phénanthryle, un groupe 4-phénanthryle, un groupe 9-phénanthryle, un groupe 1-naphthacényle, un groupe 2-naphthacényle, un groupe 9-naphthacényle, un groupe 1-pyrényle, un groupe 2-pyrényle, un groupe 4-pyrényle, un groupe 2-biphénylyle, un groupe 3-biphénylyle, un groupe 4-biphénylyle, un groupe p-terphényl-4-yle, un groupe p-terphényl-3-yle, un groupe p-terphényl-2-yle, un groupe m-terphényl-4-yle, un groupe m-terphényl-3-yle, un groupe m-terphényl-2-yle, un groupe o-tolyle, un groupe m-tolyle, un groupe p-tolyle, un groupe p-t-butylphényle, un groupe p-(2-phénylpropyl)phényle, un groupe 3-méthyl-2-naphtyle, un groupe 4-méthyl-1-naphtyle, un groupe 4-méthyl-1-anthryle, un groupe 4'-méthylbiphénylyle, un groupe 4"-t-butyl-p-terphényl-4-yle, ou un groupe 3-fluoranthényle,

X2 et X4 sont identiques ou différents l'un de l'autre et représentent chacun indépendamment de l'hydrogène; un groupe alkyle substitué ou non substitué; un groupe alcoxy substitué ou non substitué ; un groupe aryle substitué ou non substitué ; ou un groupe hétéroaryle substitué ou non substitué,

p2 est un entier de 1 à 5,

p1 et p3 sont chacun un entier de 1 à 4, et

lorsque p1 à p3 sont chacun 2 ou plus, les substituants entre parenthèses sont identiques ou différents les uns des autres.

[Figure 1]

4
3
2
1

[Figure 2]

4
7
3
6
5
2
1

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.


Patent documents cited in the description

- US 2013207092 A [0002]
- US 2013256649 A [0002]
- JP 2008195841 A [0002]
- KR 20140130297 [0002]
- US 2015179950 A [0002]
- US 2015179956 A [0002]

专利名称(译)	胺类化合物和包含其的有机发光元件		
公开(公告)号	EP3336077B1	公开(公告)日	2019-09-11
申请号	EP2016848864	申请日	2016-09-13
[标]申请(专利权)人(译)	乐金化学股份有限公司		
申请(专利权)人(译)	LG化学有限公司.		
当前申请(专利权)人(译)	LG化学有限公司.		
[标]发明人	CHA YONGBUM HONG SUNG KIL KIM JUNGBUM KIM JIN JOO		
发明人	CHA, YONGBUM HONG, SUNG KIL KIM, JUNGBUM KIM, JIN JOO		
IPC分类号	C09K11/06 H01L51/50 C07D209/86 C07D209/88 H01L51/00		
CPC分类号	C07D209/86 C07D209/88 C09K11/06 H01L51/50 C07C211/54 C07D209/82 C09K2211/1029 C09K2211/1018 H01L51/0054 H01L51/0058 H01L51/006 H01L51/0061 H01L51/0072 H01L51/5016 H01L51/5056 H01L51/5072 H01L51/5088 H01L51/5092 H01L51/5096		
优先权	1020150137124 2015-09-25 KR		
其他公开文献	EP3336077A4 EP3336077A2		
外部链接	Espacenet		

摘要(译)

本说明书提供胺类化合物和包含其的有机发光器件。



Chemical Formula 1