



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**22.08.2018 Bulletin 2018/34**

(51) Int Cl.:  
**H01L 51/54<sup>(2006.01)</sup> H01L 27/32<sup>(2006.01)</sup>**

(21) Application number: **17156902.3**

(22) Date of filing: **20.02.2017**

(84) Designated Contracting States:  
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**  
Designated Extension States:  
**BA ME**  
Designated Validation States:  
**MA MD**

• **HUMMERT, Markus Dr.**  
**01307 Dresden (DE)**

(74) Representative: **Bittner, Thomas L.**  
**Boehmert & Boehmert**  
**Anwaltpartnerschaft mbB**  
**Pettenkoferstrasse 22**  
**80336 München (DE)**

(71) Applicant: **Novaled GmbH**  
**01307 Dresden (DE)**

Remarks:  
Amended claims in accordance with Rule 137(2) EPC.

(72) Inventors:  
• **HEGGEMANN, Ulrich**  
**01307 Dresden (DE)**

(54) **ACTIVE OLED DISPLAY, METHOD FOR PREPARING AN ACTIVE OLED DISPLAY AND COMPOUND**

(57) The present invention relates to a display device comprising

- a plurality of OLED pixels comprising at least two OLED pixels, the OLED pixels comprising an anode, a cathode, and a stack of organic layers, wherein the stack of organic layers

- is arranged between and in contact with the cathode and the anode, and

- comprises a first electron transport layer, a first hole transport layer, and a first light emitting layer provided between the first hole transport layer and the first electron transport layer, and

- a driving circuit configured to separately driving the pixels of the plurality of OLED pixels, wherein, for the plurality of OLED pixels, the first hole transport layer is provided in the stack of organic layers as a common hole transport layer shared by the plurality of OLED pixels, and the first hole transport layer comprises

(i) at least one first hole transport matrix compound consisting of covalently bound atoms and

(ii) at least one electrical p-dopant selected from metal salts and from electrically neutral metal complexes comprising a metal cation and at least one anion and/or at least one anionic ligand consisting of at least 4 covalently bound atoms,

wherein the metal cation of the electrical p-dopant is selected from alkali metals; alkaline earth metals, Pb, Mn,

Fe, Co, Ni, Zn, Cd; rare earth metals in oxidation state (II) or (III); Al, Ga, In; and from Sn, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo and W in oxidation state (IV) or less, a method for preparing the display device and a chemical compound for use therein.




Fig 1

**Description**

**[0001]** The disclosure relates to an active OLED display having a plurality of OLED pixels and comprising a non-oxidizing p-dopant in a hole injection and/or hole transport layer shared by at least two pixels, a method of preparing the active OLED display and to a compound particularly suitable for the display.

Background

**[0002]** With respect to active OLED displays, comprising a plurality of OLED pixels sharing a common hole transport layer, challenging requirements are put on semiconducting materials used in layers arranged between the anode and the emitting layer and shared by the plurality of pixels. On one hand, the materials shall enable individual driving of individual pixels at operational voltages which are as low as possible. On the other hand, so called electrical crosstalk between neighbour pixels should be avoided. The application WO2016/050834 which is herein incorporated by the reference teaches that these contradictory requirements can be fulfilled by p-doped layers having electrical conductivity in the range  $1 \times 10^{-3} \text{ S} \cdot \text{m}^{-1}$  and  $1 \times 10^{-8} \text{ S} \cdot \text{m}^{-1}$ , most favourably between  $1 \times 10^{-5} \text{ S} \cdot \text{m}^{-1}$  and  $1 \times 10^{-6} \text{ S} \cdot \text{m}^{-1}$ . Such low-conductivity p-doped hole transport layers are achievable by use of usual state-of-art redox dopants, like strongly electron accepting radialene compounds, in matrices which are poorly dopable in terms of their deep HOMO level. There is, however, continuing demand for p-dopants fulfilling these criteria and improved in other parameters, e.g. from the viewpoint of processability and device stability.

Summary

**[0003]** It is an object to provide improved active OLED displays and improved materials enabling this improvement. In one aspect, electrical crosstalk between neighbor pixels of the active OLED display shall be reduced. In another aspect, the improved materials should enable robust display manufacturing, e.g. in terms of improved device stability during any processing step which comprises a treatment of the device or its particular layer at an elevated temperature.

**[0004]** The object is achieved through a display device comprising

- a plurality of OLED pixels comprising at least two OLED pixels, the OLED pixels comprising an anode, a cathode, and a stack of organic layers, wherein the stack of organic layers
  - is arranged between and in contact with the cathode and the anode, and
  - comprises a first electron transport layer, a first hole transport layer, and a first light emitting layer provided between the first hole transport layer and the first electron transport layer, and
- a driving circuit configured to separately driving the pixels of the plurality of OLED pixels,

wherein, for the plurality of OLED pixels, the first hole transport layer is provided in the stack of organic layers as a common hole transport layer shared by the plurality of OLED pixels, and the first hole transport layer comprises

- (i) at least one first hole transport matrix compound consisting of covalently bound atoms and
- (ii) at least one electrical p-dopant selected from metal salts and from electrically neutral metal complexes comprising a metal cation and at least one anion and/or at least one anionic ligand consisting of at least 4 covalently bound atoms,

wherein the metal cation of the electrical p-dopant is selected from alkali metals; alkaline earth metals, Pb, Mn, Fe, Co, Ni, Zn, Cd; rare earth metals in oxidation state (II) or (III); Al, Ga, In; and from Sn, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo and W in oxidation state (IV) or less.

**[0005]** In one embodiment, the anion and/or the anionic ligand is bound to the metal cation of the p-dopant through an oxygen atom, preferably through two oxygen atoms.

**[0006]** It is to be understood that the term "bound" encompasses structures of the p-dopant, wherein the distance between the metal cation and the oxygen atom/atoms is shorter than the distance between the metal cation and any other atom of the anion and/or of the anionic ligand.

**[0007]** In an embodiment, the oxygen atom of the anion and/or of the anionic ligand which is in the metal salt and/or in the metal complex bound to the metal cation has in dichloroethane lower basicity than at least one non-oxygen atoms of the anion and/or of the anionic ligand.

**[0008]** Analogously, in another embodiment, each of the oxygen atoms of the anion and/or of the anionic ligand which are in the metal salt and/or in the metal complex bound to the metal cation has in dichloroethane lower basicity than at

least one non-oxygen atom of the anion and/or of the anionic ligand. It is to be understood that the basicity of an atom in the anion and/or in the anionic ligand in an environment, e.g. in 1,2-dichloroethane, is inversely proportional to the acidity of a corresponding tautomeric form of the electrically neutral conjugated acid formed by addition of one or more protons in the same environment. Measurement of the acidity in 1,2-dichloroethane as a versatile tool for comparison of various acids is described in Journal of Organic Chemistry (2011), 76(2), 391-395. It is understood that if the basicity of a particular atom in an anion and/or anionic ligand has to be assessed, the "corresponding tautomeric form" of the electrically neutral conjugated acid is the acid formed by proton addition to the particular atom.

**[0009]** In one embodiment, the anion and/or the anionic ligand consists of at least 5, preferably at least 6, more preferably at least 7, even more preferably at least 8, most preferably at least 9 covalently bound atoms.

**[0010]** In one embodiment, the anion and/or the anionic ligand comprises at least one atom selected from B, C, N.

**[0011]** In one embodiment, the anion and/or the anionic ligand comprises at least two atoms selected from B, C and N which are bound to each other by a covalent bond.

**[0012]** In one embodiment, the anion and/or the anionic ligand comprises at least one peripheral atom selected from H, N, O, F, Cl, Br and I. Under "peripheral atom", it is to be understood an atom which is covalently bound to only one atom of the anion and/or of the anionic ligand. Oppositely, atoms covalently bound to at least two other atoms of the anion and/or of the anionic ligand are assigned as inner atoms.

**[0013]** Under covalent bond, it is to be understood any bonding interaction which involves electron density sharing between the two assessed atoms, wherein the bonding is stronger than van der Waals dispersive interactions; for the sake of simplicity, binding energy 10 kJ/mol may be taken as an arbitrary lower limit. In this sense, the term includes also coordination bonds or hydrogen bonds. Anions and/or anionic ligands comprising hydrogen bonds, however, are not particularly preferred.

**[0014]** In one embodiment, the anion and/or the anionic ligand comprises at least one electron withdrawing group selected from halogenated alkyl, halogenated (hetero)aryl, halogenated (hetero)arylalkyl, halogenated alkylsulfonyl, halogenated (hetero)arylsulfonyl, halogenated (hetero)arylalkylsulfonyl, cyano. It is to be understood that for the sake of brevity, halogenated (hetero)aryl means "halogenated aryl or halogenated heteroaryl", halogenated (hetero)arylalkyl means "halogenated heteroarylalkyl or halogenated arylalkyl", halogenated (hetero)arylsulfonyl means "halogenated heteroarylsulfonyl or halogenated arylsulfonyl" and halogenated (hetero)arylalkylsulfonyl means "halogenated heteroarylalkylsulfonyl or halogenated arylalkylsulfonyl".

**[0015]** In one embodiment, the electron withdrawing group is a perhalogenated group. It is to be understood that the term "halogenated" means that at least one hydrogen atom of a group comprising peripheral or inner hydrogen atoms is replaced with an atom selected from F, Cl, Br and I. It is further understood that in a perhalogenated group, all hydrogen atoms comprised in the unsubstituted group are replaced with atoms independently selected from F, Cl, Br and I. Accordingly, under perfluorinated group, it is to be understood a perhalogenated group, wherein all halogen atoms replacing hydrogen atoms are fluorine atoms.

**[0016]** In one embodiment, the metal cation of the p-dopant is selected from Li(I), Na(I), K(I), Rb(I), Cs(I); Mg(II), Ca(II), Sr(II), Ba(II), Sn(II), Pb(II), Mn(II), Fe(II), Co(II), Ni(II), Zn(II), Cd(II), Al(III); rare earth metal in oxidation state (III), V(III), Nb(III), Ta(III), Cr(III), Mo(III), W(III), Ga(III), In(III) and from Ti(IV), Zr(IV), Hf(IV), Sn(IV).

**[0017]** In one embodiment, in the p-dopant molecule, the atom of the anion and/or of the anionic ligand which is closest to the metal cation is a C or a N atom.

**[0018]** In one embodiment, the acidity of the electrically neutral conjugated acid formed from the anion and/or anionic ligand by addition of one or more protons in 1,2-dichloroethane is higher than that of HCl, preferably higher than that of HBr, more preferably higher than that of HI, even more preferably higher than that of fluorosulfuric acid, and most preferably higher than that of perchloric acid.

**[0019]** In one embodiment, the electrical p-dopant has energy level of its highest unoccupied molecular orbital computed by standard quantum chemical method and expressed in absolute vacuum scale at least 0.5 eV, preferably at least 0.6 eV, more preferably at least 0.8 eV, even more preferably at least 1.0 eV, most preferably at least 1.2 eV above the energy level of the highest occupied orbital of the covalent hole transport compound computed by the standard quantum chemical method.

**[0020]** The standard quantum chemical method may be the software package TURBOMOLE using DFT functional B<sub>3</sub>LYP with the basis set def2-TZVP.

**[0021]** In one embodiment, the first hole transport matrix compound is an organic compound, preferably an organic compound comprising a conjugated system of at least 6, more preferably at least 10 delocalized electrons; also preferably, the first hole transport matrix compound comprises at least one triaryl amine structural moiety, more preferably, the first hole transport matrix compound comprises at least two triaryl amine structural moieties.

**[0022]** The object is further achieved by method for preparing the display device according to any of the preceding embodiments, the method comprising at least one step wherein the hole transport matrix compound and the electrical p-dopant are in mutual contact exposed to a temperature above 50 °C.

**[0023]** In one embodiment, the method may comprise the steps, wherein


- (i) the p-dopant and the first hole transport matrix compound are dispersed in a solvent,
- (ii) the dispersion is deposited on a substrate and
- (iii) the solvent is evaporated at an elevated temperature.

**[0024]** The method may further comprise at least one step wherein the p-dopant is evaporated at a reduced pressure, preferably at a pressure below  $1 \times 10^{-2}$  Pa and at a temperature above 50 °C, more preferably at a pressure below  $5 \times 10^{-2}$  Pa and at a temperature above 80 °C, even more preferably at a pressure below  $1 \times 10^{-3}$  Pa and at a temperature above 120 °C, most preferably at a pressure below  $5 \times 10^{-4}$  Pa and at a temperature above 150 °C.

**[0025]** In one embodiment, the p-dopant may be used in form of a solid hydrate.

**[0026]** In another embodiment, the p-dopant may be used as an anhydrous solid comprising less than 0.10 wt% water, preferably less than 0.05 wt% water.

**[0027]** The object is further achieved by compound having formula (I)



wherein

$M^{x+}$  is a x-valent cation of a metal selected from alkali metals, alkaline earth metals, rare earth metals and Al, Ga, In, Sn, Pb, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Fe, Co, Ni, Zn and Cd;

x is 1 for M selected from alkali metals; 2 for M selected from alkaline earth metals, Pb, Mn, Fe, Co, Ni, Zn and Cd; 2 or 3 for M selected from rare earth metals; 3 for Al, Ga, In; 2, 3 or 4 for Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W; and 2 or 4 for Sn; B<sup>1</sup> and B<sup>2</sup> is independently selected from perhalogenated C<sub>3</sub> to C<sub>20</sub> alkyl, C<sub>3</sub> to C<sub>20</sub> cycloalkyl or C<sub>3</sub> to C<sub>20</sub> arylalkyl;

with the proviso that the compound having formula (I), wherein

- a) M is selected from alkali metals, Mg, Ca and Zn and B<sup>1</sup> and B<sup>2</sup> are independently selected from perfluorinated straight-chain primary alkyl, or
- b) M is Li and B<sup>1</sup> and B<sup>2</sup> is perfluorinated isopropyl,

is excluded.

**[0028]** In one embodiment, M is selected from Mg(II), Mn(II) and Zn(II).

**[0029]** In one embodiment, the compound according to formula (I) is provided in a solid form, preferably in a solid form comprising less than 0.10 wt % water, more preferably in a solid form comprising less than 0.05 wt % water, most preferably in a solid crystalline form comprising less than 0.05 wt % water.

**[0030]** In another embodiment, the compound according to formula (I) is provided in form of a solid crystalline hydrate, preferably in form of a solid crystalline hydrate which has water content in the range

(i) from 30.33 to 36.33 mol%, preferably from 31.00 to 35.66 mol%, more preferably from 31.00 to 35.66 mol%, even more preferably from 31.66 to 35.00 mol%, even more preferably from 32.33 to 34.33 mol%, most preferably from 33.00 to 33.66 mol%; or

(ii) from 18.20 to 21.80 mol%, preferably from 18.60 to 21.40 mol%, more preferably from 19.00 to 21.00 mol%, even more preferably from 19.40 to 20.60 mol%, most preferably from 19.80 to 20.20 mol%.

#### Effect of the invention



**[0031]** An important property of materials comprised in organic semi-conducting devices is their conductivity. In a display device having a structured anode and at least two pixels sharing at least one hole transport and/or hole injection

layer, as described in WO2016/050834, a limited conductivity of the shared layer may be favourable for achieving a low level of the undesired electrical crosstalk in the display. On the other hand, very low conductivity of the shared layer may increase the operational voltage of the display. WO2016/050834 teaches a conductivity range which represents a trade-off between these contradictory requirements.

**[0032]** The authors of the present application, however, surprisingly found that electrical p-dopants based on certain metal salts and metal complexes enable, under certain conditions, preparing p-doped materials and/or p-doped layers providing stable hole injection state-of-art anodes into state-of-art hole transport matrices, without substantially increasing the concentration of the free charge carriers above the level which corresponds to conductivities observed in a neat matrix.


**[0033]** This surprising finding offered an opportunity to build the displays of WO2016/050834, operating at fully comparable voltages, even though the hole transport and/or hole injection layers shared by the multiplicity of pixels have conductivities below the optimum range between  $1 \times 10^{-5} \text{ S} \cdot \text{m}^{-1}$  and  $1 \times 10^{-6} \text{ S} \cdot \text{m}^{-1}$  as disclosed in WO2016/050834. The dopants of the present application enable efficient operation of display devices of WO2016/050834 at the level of electrical conductivity in p-doped layers shared by the multiplicity of pixels which is near to the detection limit of the available measuring procedure or below it. Thus, the dopants of the present application enable further suppressing the electrical crosstalk in OLED displays and offer new opportunities for designing efficient OLED displays exhibiting very low level of electrical crosstalk. These observations made by the authors will be further described in more detail.

**[0034]** In a previous application EP15181385 filed by the applicant, herein incorporated by the reference, some of the authors described successful use of some metal amides like



as hole injection materials in organic electronic devices.

**[0035]** Parallel with further investigation of analogous metal amide compounds, the authors surprisingly found that also some structurally quite different compounds, namely metal borate complexes like



are utilizable in an analogous way.

**[0036]** Most surprisingly, the authors found that all these structurally different compounds analogously exhibit two different modes in their p-doping activity, depending on the process conditions during preparation of the doped material and/or layer.

**[0037]** In the first mode, semiconducting materials and/or layers doped with these compounds (which can be generalized as metal salts and/or electrically neutral metal complexes with an anionic ligand) exhibit well-measurable electrical conductivities which are only slightly lower in comparison with materials and/or layers doped with typical redox p-dopants. It appears that this mode occurs if the doped material and/or layer is exposed to oxygen, even though only in trace amounts.

**[0038]** In the second mode, the semiconducting materials and/or layers doped with the disclosed metal salts and/or electrically neutral metal complexes comprising an anionic ligand exhibit hardly measurable electrical conductivities. This mode occurs if the oxygen access to the doped material and/or layer is strictly avoided throughout processing thereof. The authors found that despite the extremely low conductivity of materials and/or layers doped in the second mode, devices comprising such materials and/or layers particularly as hole transporting or hole injecting layers still exhibit electrical behavior corresponding to an excellent hole injection.

**[0039]** The existence of the two above described modes of p-doping activity provides the disclosed p-dopants with a unique versatility in their use in organic electronic devices, and particularly in displays comprising an anode structured into a multiplicity of pixels sharing a common hole transport layer. The conductivity of the common p-doped layer can be either set in the limits taught in WO2016/050834 by exploiting the first doping mode, or set below these limits, exploiting the second doping mode.

**[0040]** Furthermore, recent investigations made by the authors provided hints that the materials and/or layers doped with the presented metal salts and/or metal complexes may exhibit favourable thermal stability, particularly in materials provided according to the above described second mode of the p-doping action. These properties may be again particularly suitable for the use of the disclosed p-dopants in AMOLED displays, because the necessity of structuring such displays into separate pixels often requires a thermal treatment of p-doped layers or using another treatment which may result in an unavoidable heating of a previously deposited p-doped layer.

**[0041]** In a specific embodiment of the invention, the authors provided new amide compounds comprising bulkier fluorinated side chains in comparison with the compounds tested in EP15181385. This change resulted in favourable storage properties of the new compounds, which are substantially non-hygroscopic and remain solid even at high air humidity, whereas LiTFSI and analogous TFSI salts have tendency to deliquesce.

#### Detailed description

**[0042]** The electrical conductivity of a thin layer sample can be measured by, for example, the so called two-point method. At this, a voltage is applied to the thin layer and the current flowing through the layer is measured. The resistance, respectively the electrical conductivity, results by considering the geometry of the contacts and the thickness of the layer of the sample. The experimental setup for conductivity measurement used by the authors of the present application enables deposition of p-doped layers as well as conductivity measurement under controlled conditions, especially with regard to contact of deposited layers with an atmosphere comprising oxygen. In this regard, the whole deposition-measurement sequence may be carried out either in a glove-box or in a chamber comprising a controlled atmosphere, using solution processing techniques, or completely in a vacuum chamber, using vacuum thermal evaporation (VTE) as the method of choice, especially suitable for materials and/or layers doped in the second mode.

**[0043]** The electrical conductivity of the first hole transport layer may be lower than  $1 \times 10^{-6} \text{ S} \cdot \text{m}^{-1}$ , preferably lower than  $1 \times 10^{-7} \text{ S} \cdot \text{m}^{-1}$ , more preferably lower than  $1 \times 10^{-8} \text{ S} \cdot \text{m}^{-1}$ . Alternatively, provided that the detection limit of the used conductivity measurement method is lower than  $1 \times 10^{-6} \text{ S} \cdot \text{m}^{-1}$ , it is preferred that the conductivity of the first hole transport layer is lower than the detection limit.

**[0044]** The first hole transport layer (HTL) may be formed for the plurality of OLED pixels in the OLED display. In one embodiment, the first HTL may extend over all pixels of the plurality of pixels in the OLED display. Similarly, the cathode may be formed as a common cathode for the plurality of pixels. The common cathode may extend over all pixels of the plurality of pixels in the OLED display. Every individual pixel may have its own anode that may not touch anodes of other individual pixels.

**[0045]** Optionally, for one or more of the plurality of OLED pixels, following organic layers may be provided: a hole blocking layer, an electron injection layer, and/or an electron blocking layer.

**[0046]** Further, the active OLED display has driving circuit configured to separately drive the individual pixels of the plurality of pixels provided in the OLED display. In one embodiment, a step of separately driving may comprise separate control of the driving current applied the individual pixels.

**[0047]** The first HTL is made of a hole transport matrix (HTM) material electrically doped with the p-dopant. The hole transport matrix material may be electrically doped with more than one p-dopant. It is to be understood that the HTM material may consist of one or more HTM compounds, whereas the term hole transport material is a broader term used throughout this application for all semiconducting materials comprising at least one hole transport matrix compound. The hole transport matrix material is not particularly limited. Generally, it is any material consisting of covalently bound atoms which allows embedding the p-dopant. In this sense, infinite inorganic crystals having predominantly covalent bonds like silicon or germanium, or extremely crosslinked inorganic glasses like silicate glass, do not fall in the scope of the definition of the hole transport matrix material. Preferably, the hole transport matrix material may consist of one or more organic compounds.

**[0048]** The first hole transport layer may have a thickness of less than 50 nm, less than 40 nm, less than 30 nm, less than 20 nm, or less than 15 nm.

**[0049]** The first hole transport layer may have a thickness of more than 3 nm, more than 5 nm, more than 8 nm, or more than 10 nm.

**[0050]** The anode may be made of a transparent conductive oxide (TCO), like indium tin oxide (ITO) or aluminium zinc oxide (AZO). Alternatively, the anode may be made of one or more thin metallic layers leading to a semitransparent anode. In another embodiment, the anode may be made of a thick metallic layer which is not transparent to visible light.

**[0051]** The OLED pixel(s) may comprise an electron blocking layer (EBL) provided between the first hole transport layer and the light emitting layer. The EBL may be in direct contact with the first HTL and the EML. The electron blocking layer may be an electrically undoped layer (in other words, it may be free of an electrical dopant) made of an organic hole transport matrix material. The composition of the organic hole transport matrix material of the first hole transport layer may be the same as the composition of the organic hole transport matrix material of the electron blocking layer. In another embodiment of the invention, the composition of both hole transport matrix materials may be different.

**[0052]** The EBL may have a layer thickness of more than 30 nm, more than 50 nm, more than 70 nm, more than 100 nm, or more than 110 nm.

**[0053]** The thickness of the EBL may be less than 200 nm, less than 170 nm, less than 140 nm, or less than 130 nm. Compared to the EBL, the common HTL may be thinner by about one order of magnitude.

**[0054]** Each compound forming the electron blocking layer may have a highest occupied molecular orbital (HOMO) energy level, expressed in the absolute scale referring to vacuum energy level being zero, higher than a HOMO level of any compound forming the hole transport matrix material of the common hole transport layer.

**[0055]** The organic matrix material of the electron blocking layer may have a hole mobility which is equal to or higher than the hole mobility of the matrix material of the hole transport layer.

**[0056]** The hole transport matrix (HTM) material of the common HTL and/or of the EBL may be selected from compounds comprising a conjugated system of delocalized electrons, the conjugated system comprising lone electron pairs of at least two tertiary amine nitrogen atoms.

**[0057]** Suitable compounds for the hole transport matrix material of the doped hole transport layer and / or the common hole transport layer may be selected from the known hole transport matrices (HTMs), e.g. from triaryl amine compounds. HTMs for the doped hole transport material maybe compounds comprising a conjugated system of delocalized electrons, wherein the conjugated system comprises lone electron pairs of at least two tertiary amine nitrogen atoms. Examples are N4,N4'-di(naphthalen-1-yl)-N4,N4'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (HT1), and N4,N4, N4",N4"-tetra([1,1'-biphenyl]-4-yl)-[1,1':4',1"-terphenyl]-4,4"-diamine (HT4). The synthesis of terphenyldiamine HTMs is described e.g. in WO 2011/134458 A1, US 2012/223296 A1 or WO 2013/135237 A1; 1,3-phenylenediamine matrices are described e.g. in WO 2014/060526 A1. These documents are herein incorporated by reference. Many triaryl amine HTMs are commercially available.

**[0058]** The light emitting layer of the OLED display may comprise a plurality of sub-regions, each of the sub-regions

being assigned to one of the pixels from the plurality of pixels. The light emitting layer of an individual pixel, corresponding to a sub-region of the emitting layer of the display, preferably does not touch light emitting layers of neighbor pixels. In the display manufacturing process, the organic layer comprising EMLs of individual pixels may be patterned by known methods, for example, by fine-metal masking (FMM), laser induced thermal imaging (LITI), and / or ink-jet printing (IJP) in either top emission, bottom emission or bottom emission micro cavity (see, for example, Chung et al. (2006), 70.1: Invited Paper: Large-Sized Full Color AMOLED TV: Advancements and Issues. SID Symposium Digest of Technical Papers, 37: 1958-1963. doi: 10.1889/1.2451418; Lee et al. (2009), 53.4: Development of 31-Inch Full-HD AMOLED TV Using LTPS-TFT and RGB FMM. SID Symposium Digest of Technical Papers, 40: 802-804. doi: 10.1889/1.3256911). A RGB layout may be provided.

**[0059]** For the plurality of OLED pixels, a common electron transport layer may be formed by the electron transport layers provided in the stack of organic layers of the plurality of OLED pixels.

**[0060]** The common electron transport layer may comprise an organic electron transport matrix (ETM) material. Further, the common electron transport layer may comprise one or more n-dopants. Suitable compounds for the ETM contain aromatic or heteroaromatic structural moieties, as disclosed e.g. in documents EP 1970 371 A1 or WO 2013/079217 A1.

**[0061]** The cathode can be made of a metal or a metal alloy with a low work function. Transparent cathodes made of a TCO are also well-known in the art.

**[0062]** The stack of organic layers may be made of organic compounds having a molecular weight of less than 2000 g/mol. In an alternative embodiment, the organic compounds may have a molecular weight of less than 1000 g/mol.

#### Description of embodiments

**[0063]** In the following, further embodiments will be described in further detail, by way of example, with reference to figures. In the figures show:

Fig. 1 a schematic representation of an active OLED display, the display having a plurality of OLED pixels,

**[0064]** Fig. 1 shows a schematic representation of an active OLED display 1 having a plurality of OLED pixels 2, 3, 4 provided in an OLED display 1. In the OLED display 1, each pixel 2, 3, 4 is provided with an anode 2a, 3a, 4a being connected to a driving circuit (not shown). Various equipment able to serve as a driving circuit for an active matrix display is known in the art. In one embodiment, the anodes 2a, 3a, 4a are made of a TCO, for example of ITO.


**[0065]** A cathode 6 is provided on top of an organic stack comprising an electrically doped hole transport layer (HTL) 7, an electron blocking layer (EBL) 5, a light emitting layer (EML) having sub-regions 2b, 3b, 4b assigned to the pixels 2, 3, 4 and being provided separately in an electron transport layer (ETL) 9. For example, the sub-regions 2b, 3b, 4b can provide an RGB combination for a color display (R - red, G - green, B - blue). By applying individual drive currents to the pixels 2, 3, 4 via the anodes 2a, 3a, 4a and the cathode 6, the display pixels 2, 3, 4 are operated independently.

#### Synthesis examples


##### LiPFPI

**[0066]**





Chemical Formula:  $C_{24}HF_{20}NO_2P_2$   
Molecular Weight: 777,19




Chemical Formula:  $C_{24}F_{20}LiNO_2P_2$   
Molecular Weight: 783,12


**[0067]** 1.0 g (1.29 mmol) N-(bis(perfluorophenyl)phosphoryl)-P,P-bis(perfluorophenyl)phosphinic amide is dissolved in 20 mL dry toluene and cooled to 0 °C. 10 mg (12.9 mmol, 1.0 eq) lithium hydride are added. The mixture is heated to reflux for 2 h. After cooling to room temperature, the product is precipitated with 20 mL n-hexane, filtered off, washed with n-hexane (2 × 10 mL). 0.62 g (61 %) product is obtained as a white solid after drying in high vacuum.

#### ZnPFPI

**[0068]**



Chemical Formula:  $C_{24}HF_{20}NO_2P_2$   
Molecular Weight: 777,19




Chemical Formula:  $C_{48}F_{40}N_2O_4P_4Zn$   
Molecular Weight: 1617,75

**[0069]** 2.0 g (2.57 mmol) N-(bis(perfluorophenyl)phosphoryl)-P,P-bis(perfluorophenyl)phosphinic amide are dissolved in 50 mL dry toluene and cooled to 0 °C. 1.6 mL (1.40 mmol, 0.55 eq) 0.9 M diethylzinc solution in hexane are added. The mixture is heated to reflux for 2 h. After cooling to room temperature, the product is precipitated with 50 mL n-hexane, filtered off, washed with n-hexane (2 × 10 mL). 1.05 g (51 %) product is obtained as a white solid after drying in high vacuum.

#### Lithium bis((perfluorohexyl)sulfonyl)amide

Step 1: lithium bis((perfluorohexyl)sulfonyl)amide


**[0070]**



**[0071]** 10.25 g (25.7 mmol) perfluorohexyl sulfonyl amide is dissolved in a dried Schlenk flask in 100 mL dry THF. 0.51 g (64.2 mmol, 2.5 eq) lithium hydride is added under Ar counter-flow to the ice-cooled solution. 10.33 g (25.7 mmol, 1.0 eq) perfluorohexylsulfonyl fluoride is added dropwise to the resulting slurry. The mixture is heated to 60 °C for ca 18 h. The mixture is cooled to room temperature, filtered and the solvent is removed under reduced pressure. The residue is treated with 50 mL toluene and concentrated again. The crude product is slurry-washed with 50 mL hexane, the solid is filtered-off and dried in vacuum. The 13.49g (67 %) product is obtained as a pale yellow powder.

Step 2: lithium bis((perfluorohexyl)sulfonyl)amine


**[0072]**



**[0073]** 5.0 g (6.35 mmol) bis((perfluorohexyl)sulfonyl)amine is dissolved in 100 mL diethyl ether and 40 mL 25% aqueous sulfuric acid is cautiously added under ice cooling. The mixture is stirred vigorously for 15 min. The organic phase is separated, dried over magnesium sulfate, 5 mL toluene is added to avoid foaming and the solvent is evaporated under reduced pressure. The residue is purified using a bulb-to-bulb-distillation apparatus at a temperature about 140 °C and a pressure about 4 Pa. 3.70 g (75 %) product is obtained as a yellowish, waxy solid.

Step 3: lithium bis((perfluorohexyl)sulfonyl)amine

**[0074]**




**[0075]** 1.0 g (1.28 mmol) bis((perfluorohexyl)sulfonyl)amine is dissolved in 5 mL dry methyl-tert-butylether (MTBE). 12 mg (1.24 mmol, 1.0 eq) LiH are added under Ar counter-flow. The reaction mixture is stirred overnight and the solvent subsequently removed under reduced pressure. The pale pink solid residue is dried at 60 °C in vacuum. 0.89 g (88%) product are obtained as an off-white solid.


**[0076]** Mass spectroscopy with electrospray ionization (MS-ESI) confirmed the expected synthesis outcome by the dominant presence of  $m/z$  780 (anion  $C_{12}F_{26}NO_4S_2$ ) in the intermediate bis((perfluorohexyl)sulfonyl)amine as well as in the Li salt.

**Zinc bis((perfluorohexyl)sulfonyl)namide**

**[0077]**

Chemical Formula:  $C_{12}HF_{26}NO_4S_2$ 


Molecular Weight: 781,22

Chemical Formula:  $C_{24}F_{52}N_2O_8S_4Zn$ 


Molecular Weight: 1625,81

**[0078]** 1.0 g (1.28 mmol) bis((perfluorohexyl)sulfonyl)amine is dissolved in 6 mL dry MTBE. 0.71 mL (0.64 mmol, 0.5 eq) diethyl zinc solution in hexane are added dropwise. The reaction mixture is stirred overnight and the solvent removed under reduced pressure. 0.794g (78 %) pale pink solid are obtained after drying at 60 °C in vacuum.

#### Zinc bis((perfluoropropan-2-yl)sulfonyl)amide

**[0079]**Chemical Formula:  $C_6HF_{14}NO_4S_2$ 


Molecular Weight: 481,17

Chemical Formula:  $C_{12}F_{28}N_2O_8S_4Zn$ 


Molecular Weight: 1025,71

**[0080]** 0.5 g (1.04 mmol) bis((perfluoropropan-2-yl)sulfonyl)amine is dissolved in 10 mL dry MTBE, 0.47 mL (0.52 mmol, 0.5 eq) diethyl zinc solution in hexane are added dropwise and the mixture is stirred overnight at room temperature. 10 mL hexane are added and the resulting solid precipitate is filtered off and dried in high vacuum. 0.34 g (33 %) product are obtained as a white powder.

#### Magnesium bis((perfluoropropan-2-yl)sulfonyl)amide

**[0081]**Chemical Formula:  $C_6HF_{14}NO_4S_2$ 

Molecular Weight: 481,17

Chemical Formula:  $C_{12}F_{28}MgN_2O_8S_4$ 

Molecular Weight: 984,64


**[0082]** 0.5g (1.04 mmol) bis((perfluoropropan-2-yl)sulfonyl)amine is dissolved in 10 mL dry MTBE, 0.52 mL (0.52 mmol, 0.5 eq) dibutyl magnesium solution in heptane are added dropwise and the mixture is stirred overnight at room temperature. The solvent is removed under reduced pressure and the residue is dried in high vacuum. 0.38 g (74 %) product are obtained as a white powder.

product are obtained as a white powder.

**Lithium tris(4,5,6,7-tetrafluoro-3-(trifluoromethyl)-1H-indazol-1-yl)hydroborate (PB-1)**

**Step 1: 4,5,6,7-tetrafluoro-3-(trifluoromethyl)-1H-indazole**

[0083]




[0084] 11.09 g (45.1 mmol) perfluoroacetophenone is dissolved in 100 mL toluene. The solution is cooled with an ice bath and 2.3 mL (2.37 g, 47.3 mmol, 1.05 eq) hydrazine-monohydrate is added dropwise. The mixture is heated to reflux for 3 days. After cooling to room temperature, the mixture is washed two times with 100 mL saturated aqueous sodium hydrogen carbonate solution and two times with 100 mL water, dried over magnesium sulfate and the solvent is removed under reduced pressure. The yellow, oily residue is distilled from bulb to bulb at a temperature about 140 °C and pressure about 12 Pa. The crude product is dissolved in hot hexane and the solution stored at -18 °C. The precipitated solid is filtered off and the slurry washed two times in 10 mL hexane. 5.0 g (43 %) product are obtained as a slightly yellow solid.


[0085] GCMS: confirms the expected M/z (mass/charge) ratio 258

Step 2: lithium tris(4,5,6,7-tetrafluoro-3-(trifluoromethyl)-1H-indazol-1-yl)hydroborate

[0086]




[0087] 5.1 g (19.8 mmol) 4,5,6,7-tetrafluoro-3-(trifluoromethyl)-1H-indazole is added under Ar counter-flow to an out-baked Schlenk flask and treated with 3 mL toluene. Freshly pulverized lithium borohydride is added to the starting material. The mixture is heated to 100 °C, until hydrogen formed ceases (ca. 4h). After slight cooling, 15 mL hexane are added, the mixture is heated to reflux for 10 min and cooled to room temperature. The precipitated solid is filtered off, washed with 10 mL hot hexane and dried in high vacuum. 2.55g (49 %) product is obtained as an off-white solid.

**Lithium tris(3,5-bis(trifluoromethyl)-1H-pyrazol-1-yl)hydroborate (PB-2)****[0088]**

**[0089]** 2.0 g (9.8 mmol, 5 eq) 3,5-bis(trifluoromethyl)pyrazole in a baked-out Schlenk flask is dissolved in 5 mL dry toluene. 43 mg (1.96 mmol, 1 eq) freshly pulverized lithium borohydride is added under Ar counter-flow and the mixture is heated to reflux for 3 days. The solvent and the excessive starting material are removed by distillation under reduced pressure and the residue is crystallized from n-chlorohexane. 0.25 g (20 %) product is obtained as a white solid.

**Lithium tris(4,5,6,7-tetrafluoro-3-(perfluorophenyl)-1H-indazol-1-yl)hydroborate (PB-3)**

Step 1: 4,5,6,7-tetrafluoro-3-(perfluorophenyl)-1H-indazole


**[0090]**

**[0091]** 20.0 g (54.8 mmol) perfluorobenzophenone are dissolved in 200 mL toluene. 4.0 mL (4.11 g, 82.1 mmol, ca. 1.5 eq) hydrazine-monohydrate is added dropwise to the ice-cooled solution. 40 g sodium sulfate are added and the mixture is heated to reflux for 2 days. After cooling, 10 mL acetone are added to the reaction mixture and the resulting slurry is stirred for 1 h at room temperature. The solid is filtered off, thoroughly washed with 4×50 mL toluene, organic fractions are combined and washed two times with saturated aqueous sodium hydrogen carbonate. The solvent is removed under reduced pressure and the residue purified by column chromatography. 7.92 g (41 %) product are obtained as a pale yellow solid.

**[0092]** GC-MS: confirms the expected M/z (mass/charge) ratio 356

Step 2: lithium tris(4,5,6,7-tetrafluoro-3-(perfluorophenyl)-1H-indazol-1-yl)hydroborate


**[0093]**



[0094] 1.02 g (2.86 mmol), 3.0 eq) 4,5,6,7-tetrafluoro-3-(perfluorophenyl)-1H-indazole are dissolved in 5 mL chlorobenzene in a baked-out Schlenk flask. Freshly pulverized lithium borohydride (21 mg, 0.95 mmol, 1.0 eq) is added under Ar counter-flow. The mixture is heated to 150 °C for 2 days and cooled to room temperature. The solvent is removed under reduced pressure and the residue dried in high vacuum. The crude is further purified by drying in a bulb to bulb apparatus at a temperature about 150 °C and a pressure about 12 Pa. 0.57 g (70 %) product is obtained as an off-white solid.

#### Lithium tris(3-cyano-5,6-difluoro-1H-indazol-1-yl)hydroborate (PB-4)


[0095]




[0096] Freshly pulverized lithium borohydride (15 mg, 0.7 mmol, 1.0 eq) is placed in a baked-out pressure tube, 0.5 g (2.79 mmol, 4.0 eq) 5,6-difluoro-1H-indazole-3-carbonitrile are added under Ar counter-flow and washed down with 1 mL toluene. The pressure tube is closed and heated to a temperature about 160 °C for ca 21 h. After cooling to room temperature, the mixture is treated with 5 mL hexane in an ultra-sonic bath for ca 30 min. The precipitated solid is filtered off and washed with hexane (20 mL in total). After drying, 0.48 g yellowish solid is obtained.

#### Zinc(II) tris(3,5-bis(trifluoromethyl)-1H-pyrazol-1-yl)hydroborate (PB-5)

[0097]



Chemical Formula:  $C_{15}H_4BF_{18}LiN_6$   
Molecular Weight: 627,96



Chemical Formula:  $C_{30}H_8B_2F_{36}N_{12}Zn$   
Molecular Weight: 1307,42

**[0098]** 0.57g (0.91 mmol) lithium tris(3,5-bis(trifluoromethyl)-1H-pyrazol-1-yl)hydroborate is dissolved in 6 mL N,N-dimethyl formamide. An aqueous solution of 62 mg zinc dichloride in 1 mL water is added dropwise. 20 mL water is further added and the mixture is treated in an ultra-sonic bath for 2 h. The precipitate is filtered off and dried in high vacuum. 0.485 g (82 %) product is obtained as a white solid.

#### Device examples

##### Example 1 (tandem OLED, model for bottom emitting white OLED pixel)

**[0099]** On a glass substrate provided with an ITO anode having thickness 90 nm, there were subsequently deposited 10 nm hole injection layer made of F1 doped with 8 wt% PD-2; 140 nm thick undoped hole transport layer made of neat F1; 20 nm thick first emitting layer formed of ABH113 doped with 3 wt% BD200 (both supplied by SFC, Korea); 25 nm thick first electron transport layer made of neat F2; 10 nm thick electron-generating part of the charge-generating layer (n-CGL) made of F3 doped with 5 wt% Yb; 2 nm thick interlayer made of F4; 30 nm thick hole-generating part of the charge-generating layer (p-CGL) made of PB-1; 10 nm thick second hole transport layer made of neat F1; 20 nm second emitting layer of the same thickness and composition as the first emitting layer; 25 nm thick first electron transport layer made of neat F2; 10 nm thick electron injection layer (EIL) made of F3 doped with 5 wt% Yb; 100 nm Al cathode.

**[0100]** All layers were deposited by vacuum thermal evaporation (VTE).

**[0101]** At the current density 10 mA/cm<sup>2</sup>, the operational voltage of the device 8 V was well comparable with the same device comprising a commercial state-of-art p-dopant instead of PB-1. Exact calibration of measuring equipment necessary for luminance/efficiency comparison was not made in this experiment.






##### Example 2 (bottom emitting blue OLED pixel)

**[0102]** On the same glass substrate provided with an ITO anode as in the Example 1, following layers were subsequently deposited by VTE: 10 nm hole injection layer made of the compound PB-1; 120 nm thick HTL made of neat F1; 20 nm EML made of ABH113 doped with 3 wt% NUBD370 (both supplied by SFC, Korea), 36 nm EIL/ETL made of F2 doped with 50 wt% LiQ; 100 nm Al cathode.

**[0103]** Comparative device comprised the HIL made of the compound CN-HAT (CAS 105598-27-4) instead of PB-1.



**[0104]** The inventive device achieved current density 15 mA/cm<sup>2</sup> and external quantum efficiency (EQE) 5.4 % at an operational voltage 5.2 V, whereas the comparative device exhibited the same current density at a significantly higher voltage 5.4 V and with a significantly lower EQE 4.9 %.

Table 1 auxiliary materials

Compound	Structure
<p>F1 (CAS 1242056-42-3)</p>	
<p>F2 (CAS 1440545-225-1)</p>	
<p>F3 (CAS 597578-38-6)</p>	
<p>F4 (CAS 1207671-22-4)</p>	
<p>PD2 2,2',2''-(cyclopropane-1,2,3-triylidene)-tris[2-(4-cyanoperfluorophenyl)-acetonitrile] (CAS1224447-88-4)</p>	



(continued)

Compound	Structure
5 LiQ 8-Hydroxyquinolato lithium (CAS 850918-68-2)	
10 CN-HAT (CAS 105598-27-4)	15 20 

25 **[0105]** The features disclosed in the foregoing description and in the dependent claims may, both separately and in any combination thereof, be material for realizing the aspects of the disclosure made in the independent claims, in diverse forms thereof.

**[0106]** Key symbols and abbreviations used throughout the application:

CV	cyclic voltammetry
DSC	differential scanning calorimetry
EBL	electron blocking layer
EIL	electron injecting layer
EML	emitting layer
eq.	equivalent
ETL	electron transport layer
ETM	electron transport matrix
Fc	ferrocene
Fc <sup>+</sup>	ferricenium
HBL	hole blocking layer
HIL	hole injecting layer
HOMO	highest occupied molecular orbital
HPLC	high performance liquid chromatography
HTL	hole transport layer
p-HTL	p-doped hole transport layer
HTM	hole transport matrix
ITO	indium tin oxide
LUMO	lowest unoccupied molecular orbital
mol%	molar percent
NMR	nuclear magnetic resonance
OLED	organic light emitting diode
OPV	organic photovoltaics
QE	quantum efficiency
R <sub>f</sub>	retardation factor in TLC
RGB	red-green-blue
TCO	transparent conductive oxide
TFT	thin film transistor
T <sub>g</sub>	glass transition temperature
TLC	thin layer chromatography

wt% weight percent

## Claims

### 1. Display device comprising

- a plurality of OLED pixels comprising at least two OLED pixels, the OLED pixels comprising an anode, a cathode, and a stack of organic layers, wherein the stack of organic layers

- is arranged between and in contact with the cathode and the anode, and  
- comprises a first electron transport layer, a first hole transport layer, and a first light emitting layer provided between the first hole transport layer and the first electron transport layer, and

- a driving circuit configured to separately driving the pixels of the plurality of OLED pixels, wherein, for the plurality of OLED pixels, the first hole transport layer is provided in the stack of organic layers as a common hole transport layer shared by the plurality of OLED pixels, and the first hole transport layer comprises

(i) at least one first hole transport matrix compound consisting of covalently bound atoms and  
(ii) at least one electrical p-dopant selected from metal salts and from electrically neutral metal complexes comprising a metal cation and at least one anion and/or at least one anionic ligand consisting of at least 4 covalently bound atoms,

wherein the metal cation of the electrical p-dopant is selected from alkali metals;

alkaline earth metals, Pb, Mn, Fe, Co, Ni, Zn, Cd; rare earth metals in oxidation state (II) or (III); Al, Ga, In; and from Sn, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo and W in oxidation state (IV) or less.

2. Display device according to claim 1, wherein the anion and/or the anionic ligand is bound to the metal cation of the p-dopant through an oxygen atom, preferably through two oxygen atoms.

3. Display device according to claim 2, wherein the oxygen atom/atoms of the anion and/or of the anionic ligand which is/are in the metal salt and/or in the metal complex bound to the metal cation has/have in 1,2-dichloroethane lower basicity than at least one non-oxygen atoms of the anion and/or of the anionic ligand; preferably, the basicity of the non-oxygen atom is higher than the basicity of any oxygen atom comprised in the anion and/or of the anionic ligand.

4. Display device according to claim 1 or 2, wherein the anion and/or the anionic ligand consists of at least 5, preferably at least 6, more preferably at least 7, even more preferably at least 8, most preferably at least 9 covalently bound atoms.

5. Display device according to claim 1 or 2 or 3, wherein the anion and/or anionic ligand comprises at least one atom selected from B, C, N.

6. Display device according to any of the preceding claims, wherein the anion and/or anionic ligand comprises at least two atoms selected from B, C and N which are bound to each other by a covalent bond.


7. Display device according to any of the preceding claims, wherein the anion and/or anionic ligand comprises at least one peripheral atom selected from H, N, O, F, Cl, Br and I.

8. Display device according to any of the preceding claims, wherein the anion and/or anionic ligand comprises at least one electron withdrawing group selected from halogenated alkyl, halogenated (hetero)aryl, halogenated (hetero)arylalkyl, halogenated alkylsulfonyl, halogenated (hetero)arylsulfonyl, halogenated (hetero)arylalkylsulfonyl, cyano.

9. Display device according to claim 8, wherein the electron withdrawing group is a perhalogenated group.

10. Display device according to claim 9, wherein the perhalogenated electron withdrawing group is a perfluorinated group.

11. Display device according to any of the preceding claims, wherein the metal cation of the p-dopant is selected from Li(I), Na(I), K(I), Rb(I), Cs(I); Mg(II), Ca(II), Sr(II), Ba(II), Sn(II), Pb(II), Mn(II), Fe(II), Co(II), Ni(II), Zn(II), Cd(II), Al(III); rare earth metal in oxidation state (III), V(III), Nb(III), Ta(III), Cr(III), Mo(III), W(III) Ga(III), In(III) and from Ti(IV), Zr(IV), Hf(IV), Sn(IV).
12. Display device according to any of the preceding claims 5-11, wherein in the p-dopant molecule, the atom of the anion and/or of the anionic ligand which is closest to the metal cation is a C or a N atom.
13. Display device according to any of the preceding claims, wherein the acidity of the electrically neutral conjugated acid formed from the anion and/or anionic ligand by addition of one or more protons in 1,2-dichloroethane is higher than that of HCl, preferably higher than that of HBr, more preferably higher than that of HI, even more preferably higher than that of fluorosulfuric acid, and most preferably higher than that of perchloric acid.
14. Display device according to any of the preceding claims, wherein the electrical p-dopant has energy level of its highest unoccupied molecular orbital computed by standard quantum chemical method and expressed in absolute vacuum scale at least 0.5 eV, preferably at least 0.6 eV, more preferably at least 0.8 eV, even more preferably at least 1.0 eV, most preferably at least 1.2 eV above the energy level of the highest occupied orbital of the covalent hole transport compound computed by the standard quantum chemical method.
15. Display device according to any of the preceding claims, wherein the first hole transport matrix compound is an organic compound, preferably an organic compound comprising a conjugated system of at least 6, more preferably at least 10 delocalized electrons; also preferably, the first hole transport matrix compound comprises at least one triaryl amine structural moiety, more preferably, the first hole transport matrix compound comprises at least two triaryl amine structural moieties.
16. Method for preparing the display device according to any of the preceding claims, the method comprising at least one step wherein the hole transport matrix compound and the electrical p-dopant are in mutual contact exposed to a temperature above 50 °C.
17. Method according to claim 16, wherein
- (i) the p-dopant and the first hole transport matrix compound are dispersed in a solvent,
  - (ii) the dispersion is deposited on a substrate and
  - (iii) the solvent is evaporated at an elevated temperature.
18. Method according to claim 16, further comprising at least one step wherein the p-dopant is evaporated at a reduced pressure, preferably at a pressure below  $1 \times 10^{-2}$  Pa and at a temperature above 50 °C, more preferably at a pressure below  $5 \times 10^{-2}$  Pa and at a temperature above 80 °C, even more preferably at a pressure below  $1 \times 10^{-3}$  Pa and at a temperature above 120 °C, most preferably at a pressure below  $5 \times 10^{-4}$  Pa and at a temperature above 150 °C.
19. Method according to claim 16 or 17 or 18, wherein the p-dopant is used in form of a solid hydrate.
20. Method according to claim 18, wherein the p-dopant is used as an anhydrous solid comprising less than 0.10 wt % water, preferably less than 0.05 wt % water.
21. Compound having formula (I)



wherein

$M^{x\oplus}$  is a x-valent cation of a metal selected from alkali metals, alkaline earth metals, rare earth metals and Al, Ga, In, Sn, Pb, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Fe, Co, Ni, Zn and Cd;

x is 1 for M selected from alkali metals; 2 for M selected from alkaline earth metals, Pb, Mn, Fe, Co, Ni, Zn and Cd; 2 or 3 for M selected from rare earth metals; 3 for Al, Ga, In; 2, 3 or 4 for Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W; and 2 or 4 for Sn;

Bland  $B^2$  is independently selected from perhalogenated  $C_3$  to  $C_{20}$  alkyl,  $C_3$  to  $C_{20}$  cycloalkyl or  $C_3$  to  $C_{20}$  arylalkyl; with the proviso that the compound having formula (I), wherein

a) M is selected from alkali metals, Mg, Ca and Zn and  $B^1$  and  $B^2$  are independently selected from perfluorinated straight-chain primary alkyl, or

b) M is Li and  $B^1$  and  $B^2$  is perfluorinated isopropyl,

is excluded.

**22.** Compound according to claim 20, wherein M is selected from Mg(II), Mn(II) and Zn(II).

**23.** Compound according to claim 20 or 21 in a solid form, preferably in a solid form comprising less than 0.10 wt % water, more preferably in a solid form comprising less than 0.05 wt % water, most preferably in a solid crystalline form comprising less than 0.05 wt % water.

**24.** Compound according to claim 20 or 21 in form of a solid crystalline hydrate, preferably in form of a solid crystalline hydrate which has water content in the range

(i) from 30.33 to 36.33 mol%, preferably from 31.00 to 35.66 mol%, more preferably from 31.00 to 35.66 mol%, even more preferably from 31.66 to 35.00 mol%, even more preferably from 32.33 to 34.33 mol%, most preferably from 33.00 to 33.66 mol%; or

(ii) from 18.20 to 21.80 mol%, preferably from 18.60 to 21.40 mol%, more preferably from 19.00 to 21.00 mol%, even more preferably from 19.40 to 20.60 mol%, most preferably from 19.80 to 20.20 mol%.

#### Amended claims in accordance with Rule 137(2) EPC.

**1.** Display device comprising

- a plurality of OLED pixels comprising at least two OLED pixels, the OLED pixels comprising an anode, a cathode, and a stack of organic layers, wherein the stack of organic layers

- is arranged between and in contact with the cathode and the anode, and

- comprises a first electron transport layer, a first hole transport layer, and a first light emitting layer provided between the first hole transport layer and the first electron transport layer, and

- a driving circuit configured to separately driving the pixels of the plurality of OLED pixels,

wherein, for the plurality of OLED pixels, the first hole transport layer is provided in the stack of organic layers as a common hole transport layer shared by the plurality of OLED pixels, and the first hole transport layer comprises

(i) at least one first hole transport matrix compound consisting of covalently bound atoms and

(ii) at least one electrical p-dopant selected from metal salts and from electrically neutral metal complexes comprising a metal cation and at least one anion and/or at least one anionic ligand consisting of at least 4 covalently bound atoms,

wherein the metal cation of the electrical p-dopant is selected from alkali metals; alkaline earth metals, Pb, Mn, Fe, Co, Ni, Zn, Cd; rare earth metals in oxidation state (II) or (III); Al, Ga, In; and from Sn, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo and W in oxidation state (IV) or less.

**2.** Display device according to claim 1, wherein the anion and/or the anionic ligand consists of at least 5, preferably at

least 6, more preferably at least 7, even more preferably at least 8, most preferably at least 9 covalently bound atoms.


3. Display device according to claim 1 or 2, wherein the anion and/or anionic ligand comprises at least one atom selected from B, C, N.
4. Display device according to any of the preceding claims, wherein the anion and/or anionic ligand comprises at least two atoms selected from B, C and N which are bound to each other by a covalent bond.
5. Display device according to any of the preceding claims, wherein the anion and/or anionic ligand comprises at least one peripheral atom selected from H, N, O, F, Cl, Br and I.
6. Display device according to any of the preceding claims, wherein the anion and/or anionic ligand comprises at least one electron withdrawing group selected from halogenated alkyl, halogenated (hetero)aryl, halogenated (hetero)arylalkyl, halogenated alkylsulfonyl, halogenated (hetero)arylsulfonyl, halogenated (hetero)arylalkylsulfonyl, cyano.
7. Display device according to claim 6, wherein the electron withdrawing group is a perhalogenated group.
8. Display device according to claim 7, wherein the perhalogenated electron withdrawing group is a perfluorinated group.
9. Display device according to any of the preceding claims, wherein the metal cation of the p-dopant is selected from Li(I), Na(I), K(I), Rb(I), Cs(I); Mg(II), Ca(II), Sr(II), Ba(II), Sn(II), Pb(II), Mn(II), Fe(II), Co(II), Ni(II), Zn(II), Cd(II), Al(III); rare earth metal in oxidation state (III), V(III), Nb(III), Ta(III), Cr(III), Mo(III), W(III) Ga(III), In(III) and from Ti(IV), Zr(IV), Hf(IV), Sn(IV).
10. Display device according to any of the preceding claims 3-9, wherein in the p-dopant molecule, the atom of the anion and/or of the anionic ligand which is closest to the metal cation is a C or a N atom.
11. Display device according to any of the preceding claims, wherein the acidity of the electrically neutral conjugated acid formed from the anion and/or anionic ligand by addition of one or more protons in 1,2-dichloroethane is higher than that of HCl, preferably higher than that of HBr, more preferably higher than that of HI, even more preferably higher than that of fluorosulfuric acid, and most preferably higher than that of perchloric acid, wherein the measurement of the acidity in 1,2-dichloroethane is performed in line with the disclosure of Journal of Organic Chemistry (2011), 76(2), 391-395.
12. Display device according to any of the preceding claims, wherein the electrical p-dopant has energy level of its highest unoccupied molecular orbital computed by standard quantum chemical method and expressed in absolute vacuum scale at least 0.5 eV, preferably at least 0.6 eV, more preferably at least 0.8 eV, even more preferably at least 1.0 eV, most preferably at least 1.2 eV above the energy level of the highest occupied orbital of the first hole transport matrix compound computed by the standard quantum chemical method, wherein the standard quantum chemical method uses the software package TURBOMOLE using DFT functional B3LYP with the basis set def2-TZVP.
13. Display device according to any of the preceding claims, wherein the first hole transport matrix compound is an organic compound, preferably an organic compound comprising a conjugated system of at least 6, more preferably at least 10 delocalized electrons; also preferably, the first hole transport matrix compound comprises at least one triaryl amine structural moiety, more preferably, the first hole transport matrix compound comprises at least two triaryl amine structural moieties.
14. Method for preparing the display device according to any of the preceding claims, the method comprising at least one step wherein the first hole transport matrix compound and the electrical p-dopant are in mutual contact exposed to a temperature above 50°C.
15. Method according to claim 14, wherein
  - (i) the p-dopant and the first hole transport matrix compound are dispersed in a solvent,
  - (ii) the dispersion is deposited on a substrate and
  - (iii) the solvent is evaporated at an elevated temperature.

16. Method according to claim 14, further comprising at least one step wherein the p-dopant is evaporated at a reduced pressure, preferably at a pressure below  $1 \times 10^{-2}$  Pa and at a temperature above  $50^{\circ}\text{C}$ , more preferably at a pressure below  $5 \times 10^{-2}$  Pa and at a temperature above  $80^{\circ}\text{C}$ , even more preferably at a pressure below  $1 \times 10^{-3}$  Pa and at a temperature above  $120^{\circ}\text{C}$ , most preferably at a pressure below  $5 \times 10^{-4}$  Pa and at a temperature above  $150^{\circ}\text{C}$ .

17. Method according to claim 14 to 16, wherein the p-dopant is used in form of a solid hydrate.

18. Method according to claim 16, wherein the p-dopant is used as an anhydrous solid comprising less than 0.10 wt % water, preferably less than 0.05 wt % water.

19. Compound having formula (I)



wherein

$\text{M}^{x\oplus}$  is a x-valent cation of a metal selected from alkali metals, alkaline earth metals, rare earth metals and Al, Ga, In, Sn, Pb, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Fe, Co, Ni, Zn and Cd;

x is 1 for M selected from alkali metals; 2 for M selected from alkaline earth metals, Pb, Mn, Fe, Co, Ni, Zn and Cd; 2 or 3 for M selected from rare earth metals; 3 for Al, Ga, In; 2, 3 or 4 for Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W; and 2 or 4 for Sn;

$\text{B}^1$  and  $\text{B}^2$  is independently selected from perhalogenated  $\text{C}_3$  to  $\text{C}_{20}$  alkyl,  $\text{C}_3$  to  $\text{C}_{20}$  cycloalkyl or  $\text{C}_3$  to  $\text{C}_{20}$  arylalkyl;

with the proviso that the compound having formula (I), wherein

- a) M is selected from alkali metals, Mg, Ca and Zn and  $\text{B}^1$  and  $\text{B}^2$  are independently selected from perfluorinated straight-chain primary alkyl, or
- b) M is Li and  $\text{B}^1$  and  $\text{B}^2$  is perfluorinated isopropyl,

is excluded.

20. Compound according to claim 18, wherein M is selected from Mg(II), Mn(II) and Zn(II).

21. Compound according to claim 18 or 19 in a solid form, preferably in a solid form comprising less than 0.10 wt % water, more preferably in a solid form comprising less than 0.05 wt % water, most preferably in a solid crystalline form comprising less than 0.05 wt % water.

22. Compound according to claim 18 or 19 in form of a solid crystalline hydrate, preferably in form of a solid crystalline hydrate which has water content in the range

(i) from 30.33 to 36.33 mol%, preferably from 31.00 to 35.66 mol%, more preferably from 31.00 to 35.66 mol%, even more preferably from 31.66 to 35.00 mol%, even more preferably from 32.33 to 34.33 mol%, most preferably from 33.00 to 33.66 mol%; or

(ii) from 18.20 to 21.80 mol%, preferably from 18.60 to 21.40 mol%, more preferably from 19.00 to 21.00 mol%, even more preferably from 19.40 to 20.60 mol%, most preferably from 19.80 to 20.20 mol%.




Fig 1



## EUROPEAN SEARCH REPORT

 Application Number  
 EP 17 15 6902

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
Y	US 2014/264295 A1 (SIM JOONG-WON [KR] ET AL) 18 September 2014 (2014-09-18) * paragraph [0058]; figures 4-6 *	1-20	INV. H01L51/54 H01L27/32
Y	W0 2017/014946 A1 (SOLVAY USA INC [US]) 26 January 2017 (2017-01-26) * page 2, line 21 - page 3, lines 16,18-21 * * page 17, lines 12-13 * * page 18, lines 6-7 * * page 54, lines 27-28; figures 1-6 *	1-20	
Y	US 2013/330632 A1 (BURSCHKA JULIAN [CH] ET AL) 12 December 2013 (2013-12-12) * paragraphs [0003], [0193] - [0195], [0237]; figures 1,2; compound complex 2 *	1-20	
Y	EP 3 002 797 A1 (NOVALED GMBH [DE]) 6 April 2016 (2016-04-06) * example working example 1 *	1-20	
E	EP 3 133 663 A1 (NOVALED GMBH [DE]) 22 February 2017 (2017-02-22) * page 26 - page 27; compounds D10-D24 *	21,22	
E	EP 3 133 664 A1 (NOVALED GMBH [DE]) 22 February 2017 (2017-02-22) * page 33 - page 34; compounds D10-D24 *	21,22	H01L
		-/--	
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
The Hague		2 August 2017	Fratiloiu, Silvia
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03.82 (P04C01)





## EUROPEAN SEARCH REPORT

 Application Number  
 EP 17 15 6902

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	SLAWOMIR PITULA ET AL: "Synthesis, Structure, and Physico-optical Properties of Manganate(II)-Based Ionic Liquids", CHEMISTRY - A EUROPEAN JOURNAL, vol. 16, no. 11, 15 March 2010 (2010-03-15), pages 3355-3365, XP055358644, ISSN: 0947-6539, DOI: 10.1002/chem.200802660 * page 3356, column 1, line 49; compound Mn(Tf2N2)2 * -----	21-24	
			TECHNICAL FIELDS SEARCHED (IPC)
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 2 August 2017	Examiner Fratiloiu, Silvia
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

 2  
 EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 17 15 6902

5

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

02-08-2017

10

15

20

25

30

35

40

45

50

55

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2014264295 A1	18-09-2014	KR 20140111839 A	22-09-2014
		US 2014264295 A1	18-09-2014
-----			
WO 2017014946 A1	26-01-2017	TW 201714984 A	01-05-2017
		TW 201714985 A	01-05-2017
		WO 2017014946 A1	26-01-2017
-----			
US 2013330632 A1	12-12-2013	CN 103492401 A	01-01-2014
		EP 2678346 A1	01-01-2014
		JP 2014517807 A	24-07-2014
		KR 20140015398 A	06-02-2014
		US 2013330632 A1	12-12-2013
		WO 2012114316 A1	30-08-2012
-----			
EP 3002797 A1	06-04-2016	EP 3002797 A1	06-04-2016
		EP 3201961 A1	09-08-2017
		KR 20170062522 A	07-06-2017
		WO 2016050834 A1	07-04-2016
-----			
EP 3133663 A1	22-02-2017	EP 3133663 A1	22-02-2017
		WO 2017029370 A1	23-02-2017
-----			
EP 3133664 A1	22-02-2017	EP 3133664 A1	22-02-2017
		WO 2017029366 A1	23-02-2017
-----			

## REFERENCES CITED IN THE DESCRIPTION

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

### Patent documents cited in the description

- WO 2016050834 A [0002] [0031] [0033] [0039]
- EP 15181385 A [0034] [0041]
- WO 2011134458 A1 [0057]
- US 2012223296 A1 [0057]
- WO 2013135237 A1 [0057]
- WO 2014060526 A1 [0057]
- EP 1970371 A1 [0060]
- WO 2013079217 A1 [0060]

### Non-patent literature cited in the description

- *Journal of Organic Chemistry*, 2011, vol. 76 (2), 391-395 [0008]
- **CHUNG et al.** 70.1: Invited Paper: Large-Sized Full Color AMOLED TV: Advancements and Issues. *SID Symposium Digest of Technical Papers*, 2006, vol. 37, 1958-1963 [0058]
- **LEE et al.** 53.4: Development of 31-Inch Full-HD AMOLED TV Using LTPS-TFT and RGB FMM. *SID Symposium Digest of Technical Papers*, 2009, vol. 40, 802-804 [0058]

专利名称(译)	有源OLED显示器，制备有源OLED显示器的方法和化合物		
公开(公告)号	<a href="#">EP3364476A1</a>	公开(公告)日	2018-08-22
申请号	EP2017156902	申请日	2017-02-20
[标]申请(专利权)人(译)	诺瓦莱德公开股份有限公司		
申请(专利权)人(译)	Novaled公司GMBH		
当前申请(专利权)人(译)	Novaled公司GMBH		
[标]发明人	HEGGEMANN ULRICH HUMMERT MARKUS DR		
发明人	HEGGEMANN, ULRICH HUMMERT, MARKUS DR.		
IPC分类号	H01L51/54 H01L27/32		
CPC分类号	H01L27/3211 H01L51/008 H01L51/0092 H01L51/506		
外部链接	<a href="#">Espacenet</a>		

#### 摘要(译)

显示装置技术领域本发明涉及一种显示装置，包括：- 多个OLED像素，包括至少两个OLED像素，所述OLED像素包括阳极，阴极和有机层堆叠，其中所述有机层堆叠- 布置在与阴极和阳极接触，和- 包括第一电子传输层，第一空穴传输层和设置在第一空穴传输层和第一电子传输层之间的第一发光层，和- 配置的驱动电路分别驱动多个OLED像素的像素，其中，对于多个OLED像素，第一空穴传输层设置在有机层堆叠中作为共用的共用空穴传输层所述多个OLED像素和所述第一空穴传输层包含 (i) 至少一种由共价键合的原子组成的第一空穴传输基质化合物和 (ii) 至少一种选自金属盐和电中性金属配合物的电p-掺杂剂包含金属阳离子和至少一种阴离子和/或至少一种阴离子配体，其由至少4个共价键合的原子组成，其中电p-掺杂剂的金属阳离子选自碱金属；碱土金属，Pb，Mn，Fe，Co，Ni，Zn，Cd；氧化态 (II) 或 (III) 的稀土金属；Al，Ga，In；从氧化态 (IV) 以下的Sn，Ti，Zr，Hf，V，Nb，Ta，Cr，Mo和W，制备显示装置的方法和使用的化合物在其中。




Fig. 1