

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 October 2008 (02.10.2008)

PCT

(10) International Publication Number
WO 2008/117976 A1

(51) International Patent Classification:
C09K 11/06 (2006.01)

8-dong, Gangseo-gu, Seoul 157-886 (KR). **YOON, Seung Soo** [KR/KR]; 405-1409, Samik Apt., Suseo-dong, Gangnam-gu, Seoul 135-884 (KR).

(21) International Application Number:
PCT/KR2008/001659

(74) Agents: **KWON, Oh-Sig** et al.; 4f, Joeeunleaderstel, 921 Dunsan-dong, Seo-gu, Daejeon 302-120 (KR).

(22) International Filing Date: 25 March 2008 (25.03.2008)

(25) Filing Language: Korean

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(26) Publication Language: English

(30) Priority Data:
10-2007-0030315 28 March 2007 (28.03.2007) KR

(71) Applicant (for all designated States except US): **GRACEL DISPLAY INC.** [KR/KR]; 5 Floor, Samyang Techno Town, 284-25, Seongsoo-dong 2ga, Seongdong-gu, Seoul 133-833 (KR).

(72) Inventors; and


(75) Inventors/Applicants (for US only): **LEE, Mi Ae** [KR/KR]; 112-202, Deokhyeon Apt., Gyomun-dong, Guri-si, Gyeonggi-do 471-020 (KR). **KWON, Hyuck Joo** [KR/KR]; 224-2001, Samsung Raemian 2 cha Apt., Jangan-dong, Dongdaemun-gu, Seoul 130-100 (KR). **KIM, Bong Ok** [KR/KR]; 101-1108, Hansol Apt., 4, Samseong-dong, Gangnam-gu, Seoul 135-090 (KR). **KIM, Sung Min** [KR/KR]; 102, Salemhouse, 392-27, Hwagok

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: THIAZOLE SYSTEM ORGANIC ELECTROLUMINESCENT COMPOUNDS AND ORGANIC LIGHT EMITTING DIODE USING THE SAME

【Figure 3】



(57) Abstract: The present invention relates to novel thiazole system organic electroluminescent compounds and organic light emitting diodes comprising the same. Since the thiazole system organic electroluminescent compounds according to the invention have good luminous efficiency and life property, OLED's having very good operation lifetime can be produced.

WO 2008/117976 A1



Published:

— *with international search report*

THIAZOLE SYSTEM ORGANIC ELECTROLUMINESCENT COMPOUNDS AND
ORGANIC LIGHT EMITTING DIODE USING THE SAME

【Technical Field】

5 The present invention relates to novel thiazole system organic electroluminescent compounds and organic light emitting diodes comprising the same.

【Background Art】

10 As the modern society comes into information-oriented age, the importance of a display, which plays a role of interface between the electronic information device and human being, increases. As a novel planar display technique, OLED's have been actively investigated
15 all over the world, since OLED's show excellent display property as self-luminescent device, and the manufacture is easy because of simple device structure, and enable manufacturing of ultra-thin and ultra-light weight displays.

20 OLED device usually consists of a plurality of thin layers of organic compound between the cathode and anode made of metal. Electrons and holes injected through the cathode and anode are transmitted to an electroluminescent layer via an electron injection layer

and an electron transportation layer, a hole injection layer and a hole transportation layer to form excitons, which degrade into stable state to emit light. In particular, the properties of an OLED largely depend on
5 the properties of the organic electroluminescent compound employed. Accordingly studies on core organic materials having enhanced performances have been actively achieved.

The core organic materials are classified into electroluminescent materials, carrier injection and
10 transportation materials. The electroluminescent materials can be classified into host materials and dopant materials. Usually, as the device structure with most excellent EL properties, structures comprising a core organic thin film layer employing host-dopant doping
15 system have been known.


Recently, small size displays are practically used, so that development of OLED's with high efficiency and long life is raising as an urgent subject. This would be an important milestone in the field of practical use of
20 medium to large size OLED panels. Thus, development of core organic materials having more excellent properties as compared to conventional core organic materials is urgently required. From this point of view, development

of host materials, carrier injection and transportation materials is one of the important subjects to be solved.


Desirable properties for host material as solid state solvent and energy deliverer or material for carrier injection or delivery in an OLED are high purity and appropriate molecular weight to enable vacuum vapor deposition. In addition, they should ensure thermal stability with high glass transition temperature and thermal decomposition temperature, and they should have high electrochemical stability for long life of the product, and easily form an amorphous thin layer. Particularly, it is very important for them to have good adhesion with the material of other adjacent layers, along with difficulties in interlayer migration.

Representatives for conventional electron delivery material include aluminum complexes such as tris(8-hydroxyquinoline)aluminum (III) (Alq), which has been used prior to the multilayer thin film OLED's disclosed by Kodak in 1987; and beryllium complexes such as bis(10-hydroxybenzo-[h]quinolinato)beryllium (Bebq), which was reported in the middle of 1990's in Japan [T. Sato et al., *J. Mater. Chem.* 10 (2000) 1151]. However, the limitation of the materials has come to the fore as OLED's have been practically used after 2002. Thereafter, many electron

delivery materials of high performance have been investigated and reported to approach their practical use.




Alq




Bebq


5 In the meanwhile, non-metal complex election delivery materials of good features which have been reported up to the present include spiro-PBD [N. Jahansson et al. *Adv. Mater.* 10 (1998) 1136], PyPySPyPy [M. Uchida et al. *Chem. Mater.* 13 (2001) 2680] and TPBI
 10 [Y. -T. Tao et al. *Appl. Phys. Lett.* 77 (2000) 1575] of Kodak. However, there remain various needs for improvement in terms of electroluminescent properties and lifetime.



spiro-PBD



PyPySPyPy



Particularly noticeable is that conventional electron delivery materials have only slightly improved operation voltage as compared to what was reported, or show the problem of considerable reduction of device operation lifetime. In addition the materials exhibit adverse effects such as deviation in device lifetime for each color and deterioration of thermal stability. Up to the present, those adverse effects are in the way to achieve the objects such as reasonable power consumption and increased luminance, which have been the issues in manufacturing large-size OLED panels.

15 **【Disclosure】**

【Technical Problem】


The object of the present invention is to solve the problems described above, and to provide thiazole system organic electroluminescent compounds with improved


electroluminescent properties, excellent power efficiency property and operation lifetime, as compared to that from conventional electron transportation materials. Another object of the present invention is to provide organic light emitting diode comprising said thiazole system organic electroluminescent compound.

【Technical Solution】

The present invention relates to thiazole system organic electroluminescent compounds represented by Chemical Formula (1) and organic light emitting diodes comprising the same. Since the thiazole system organic electroluminescent compounds according to the present invention have excellent luminous efficiency, power efficiency and life property, OLED's having very good operation lifetime can be produced.

[Chemical Formula 1]




wherein, A is a chemical bond or  ;

if m is 0, Ar₁ is hydrogen, phenyl, 1-naphthyl or 2-


naphthyl;

if m is 1 or 2, Ar₁ is selected from following structures;




5

Ar₂ is selected from following structures;



10

Ar₃ is selected from following structures;



R₁ independently represents hydrogen, a C₁₋₂₀ alkyl
 5 group with or without halogen substituent(s), a C₁₋₂₀
 alkylsilyl group, a C₆₋₂₀ arylsilyl group or a C₆₋₂₀ aryl
 group;

R₁₁ and R₁₂ independently represent hydrogen, or a
 C₁₋₂₀ alkyl group with or without halogen substituent(s);

10 R₁₃ through R₁₈ independently represent hydrogen, a
 C₁₋₂₀ alkyl group with or without halogen substituent(s),
 a C₁₋₂₀ alkylsilyl group, a C₆₋₂₀ arylsilyl group or a C₆₋₂₀
 aryl group;

n is 1 or 2; and


15 the aryl group of R₁ and R₁₃ through R₁₈ may further
 comprise C₁₋₂₀ alkyl group(s) or halogen substituent(s).

If there is no element in A of the Chemical Formulas
 of the present invention, but Ar₁ or Ar₃ is simply bonded
 to the carbon of 2-position of thiazole is referred to as


'a chemical bond'.

The thiazole system organic electroluminescent compounds of Chemical Formula (1) according to the present invention are exemplified by compounds of
 5 Chemical Formulas (2) to (4):

[Chemical Formula 2]




[Chemical Formula 3]



10

[Chemical Formula 4]







In Chemical Formulas (2) to (4), A, Ar₁, Ar₃, R₁, R₁₃, R₁₄, R₁₅, R₁₆, R₁₇, R₁₈, m and n are defined as for

Chemical Formula (1).


In Chemical Formulas (1) to (4), R_1 and R_{13} through R_{18} are independently selected from hydrogen, methyl, ethyl, n-propyl, i-propyl, i-butyl, t-butyl, n-pentyl, i-
 5 amyl, n-hexyl, n-heptyl, n-octyl, 2-ethylhexyl, n-nonyl, decyl, dodecyl, hexadecyl, trifluoromethyl, pentafluoroethyl, trimethylsilyl, tripropylsilyl, tri(t-butyl)silyl, t-butyl dimethylsilyl, triphenylsilyl, phenyldimethylsilyl, phenyl, benzyl, tolyl, 2-
 10 fluorophenyl, 4-fluorophenyl, biphenyl, naphthyl, anthryl, phenanthryl, naphthacenyl, fluorenyl, 9,9-dimethylfluoren-2-yl, pyrenyl, phenylenyl and fluoranthenyl.

The thiazole system organic electroluminescent
 15 compounds according to the present invention may be specifically exemplified by following compounds, but not restricted thereto.







103




104




105




106




107




108




109




110




111




112




113




114




115




116




117




118




119




120




121




122




123




124




125




126




127




128




129




130




131




132




133




134




135









136




137




138







145




146




147




148




149




150




151




152




153




154






155



156




157



5 The thiazole system organic electroluminescent

compounds according to the present invention can be prepared through the reaction route illustrated by Reaction Scheme (1):

[Reaction Scheme 1]




5

wherein, A, Ar₁, Ar₂, Ar₃, R₁, R₁₃, R₁₄, R₁₅, R₁₆, R₁₇, R₁₈, m and n are defined as for Chemical Formula (1) above.

Among the bromo compounds employed in Reaction Scheme (1) as the starting material, a reaction route for 9,10-bis(2-bromophenyl)anthracene, for instance, is illustrated by Reaction Scheme (2), but it is not restricted thereto.

[Reaction Scheme 2]




15

The starting material, dione or mono-one compound,

for preparing the bromo compound in Reaction Scheme (2) may have further halogen atom(s) such as bromine. The reaction route for preparing a thiazole system organic electroluminescent compound according to the present invention starting from the dione or mono-one compound having halogen substituent(s) can be illustrated by Reaction Scheme (3), but it is not restricted thereto.

[Reaction Scheme 3]



10

【Description of Drawings】

Fig. 1 is a cross-sectional view of an OLED;

Fig. 2 shows luminous efficiency curve of Alq:C545T

as a conventional electroluminescent material;

Fig. 3 shows luminous efficiency curve of Example 10 (Compound 109);

Fig. 4 shows luminance-voltage curve comparing
5 Example 10 (Compound 109) and Comparative Example 1; and

Fig. 5 shows power efficiency-luminance curve comparing Example 10 (Compound 109) and Comparative Example 1.

10 <Description of symbols of significant parts of the drawings>

1: Glass

2: Transparent electrode

3: Hole injection layer

15 4: Hole transportation layer

5: Electroluminescent layer

6: Electron transportation layer

7: Electron injection layer

8: Al cathode

20

【Best Mode】

The present invention is further described with respect to the novel thiazole system organic electroluminescent compounds according to the present

invention, processes for preparing the same and the electroluminescent properties of the device employing the same, by referring to Preparation Examples and Examples, which are provided for illustration only but are not
5 intended to be limiting in any way.

[Preparation Examples]

[Preparation Example 1] Preparation of Compound
(100)

10 Under nitrogen atmosphere, 1,2-dibromobenzene (56.7 g, 240.1 mmol) was dissolved in tetrahydrofuran (500 mL), and n-butyllithium (2.5M solution in n-hexane) (115.3 mL, 288.2 mmol) was slowly added thereto at -78°C. After stirring the mixture for 2 hours, anthracene-9,10-dione
15 (20.0 g, 96.1 mmol) was added thereto, and the resultant mixture was slowly warmed to room temperature, and stirred for 16 hours. Then the reaction mixture was extracted with water and ethyl acetate. The extract was dried under reduced pressure, and recrystallized from
20 ethyl acetate (300 mL) and n-hexane (500 mL) to obtain 9,10-bis(2-bromophenyl)-9,10-dihydroanthracene-9,10-diol (35.1 g, 67.2 mmol).

The compound, 9,10-bis(2-bromophenyl)-9,10-dihydroanthracene-9,10-diol (35.1 g, 67.2 mmol) thus

obtained, potassium iodide (44.7 g, 268.9 mmol) and sodium hydrophosphite (57.0 g, 537.9 mmol) were dissolved in acetic acid (500 mL), and the solution was stirred at 100°C under reflux for 18 hours. After cooling the
5 reaction mixture to room temperature, water (150 mL) was slowly added thereto to quench the reaction. The reaction was extracted with dichloromethane, and the extract was dried under reduced pressure. Recrystallization from methanol (300 mL) and ethyl
10 acetate (100 mL) gave 9,10-bis(2-bromophenyl)anthracene (29.5 g, 60.5 mmol).

Under nitrogen atmosphere, 9,10-bis(2-bromophenyl)anthracene (29.5 g, 60.5 mmol) was dissolved in tetrahydrofuran (400 mL), and n-buthyllithium (2.5M
15 solution in n-hexane) (16.8 mL, 181.7 mmol) was slowly added thereto at -78°C, and the mixture was stirred for 2 hours. While maintaining the temperature, 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-oxaborolane (49.4 mL, 24.2 mmol) was added thereto. After warming to room
20 temperature, the reaction mixture was stirred for 2 hours. The reaction mixture was extracted with ethyl acetate (300 mL) and dried under reduced pressure. Recrystallization from ethyl acetate (300 mL) and n-hexane (500 mL) gave 4,4,5,5-tetramethyl-2-(2-(10-(2-

(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)anthracen-9-yl)phenyl)-1,3,2-dioxaborolane (17.6 g, 30.3 mmol).

The compound, 4,4,5,5-tetramethyl-2-(2-(10-(2-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)anthracen-9-yl)phenyl)-1,3,2-dioxaborolane (17.6 g, 30.3 mmol), 2-chlorobenzo[d]thiazole (15.2 mL, 121.0 mmol), Aliquat 336 (6.9 mL, 15.1 mmol), tetrakis(triphenylphosphine)palladium (0) (Pd(PPh₃)₄) (17.5 g, 15.1 mmol), and 2M potassium carbonate (16.7 g, 121.0 mmol) were dissolved in toluene (300 mL), and the solution was stirred under reflux at 120°C for 6 hours. After cooling the reaction mixture to room temperature, water was slowly added thereto to quench the reaction. The solid produced was filtered and washed with acetone to obtain the objective compound (100) (13.4 g, 22.5mmol, overall yield: 23.4%).

¹H NMR (200MHz, CDCl₃): δ 7.28-7.32(m, 8H), 7.54-7.55(m, 8H), 7.67(d, 4H), 8.12(d, 2H), 8.23(s, 2H)

MS/FAB: 596.14(found), 596.76(calculated)

[Preparation Example 2] Preparation of Compound (101)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 1,3-dibromobenzene (56.7 g, 240.1 mmol) and 2-chlorobenzo[d]thiazole (16.7 mL, 133.3 mmol), obtained
5 was Compound (101) (15.5 g, 26.0 mmol, overall yield: 27.1%).

^1H NMR (200MHz, CDCl_3): δ 7.32-7.44(m, 10H), 7.55(t, 4H), 7.67-7.70(m, 10H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 596.14(found), 596.76(calculated)

10

[Preparation Example 3] Preparation of Compound (102)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1
15 mmol), 1,3,5-tribromobenzene (75.6 g, 240.2 mmol) and 2-chlorobenzo[d]thiazole(23.7 mL, 188.9 mmol), obtained was the objective compound (102) (17.3 g, 20.1 mmol, overall yield: 20.9%).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 4H), 7.55(t, 8H),
20 7.66-7.67(m, 10H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 862.14(found), 863.1(calculated)

[Preparation Example 4] Preparation of Compound (103)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 1,4-dibromonaphthalene (68.7 g, 240.1 mmol) and 2-chlorobenzo[d]thiazole (13.0 mL, 103.7 mmol), obtained
5 was the objective compound (103) (13.6 g, 19.5 mmol, overall yield: 20.0%).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 8H), 7.55(t, 4H), 7.60(s, 4H) 7.67(m, 8H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 696.17(found), 696.88(calculated)

10

[Preparation Example 5] Preparation of Compound (104)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1
15 mmol), 2,6-dibromonaphthalene (68.7 g, 240.1 mmol) and 2-chlorobenzo[d]thiazole (13.3 mL, 105.5 mmol), obtained was the objective compound (104) (14.2 g, 20.3 mmol, overall yield: 21.1%).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 4H), 7.54-7.55(m, 8H), 7.67(m, 4H), 7.73(d, 4H), 7.89(s, 4H), 8.12(d, 2H),
20 8.23(d, 2H)

MS/FAB: 696.17(found), 696.88(calculated)

[Preparation Example 6] Preparation of Compound (105)

In toluene (100 mL), dissolved were 2-chlorobenzo[d]thiazole (10.0 g, 59.0 mmol), 4-chlorophenylboronic acid (11.1 g, 70.7 mmol), and trans-dichlorobis(triphenylphosphine)palladium (II) (Pd(PPh₃)₂Cl₂ (4.2 g, 5.9 mmol). To the solution, added was 2M sodium carbonate solution (87 mL), and the resultant mixture was stirred under reflux for 3 hours.

After the reaction was completed, the reaction mixture was cooled to room temperature, and extracted with ethyl acetate (300 mL). The extract was dried under reduced pressure and recrystallized from dichloromethane (100 mL) and hexane (100 mL) to obtain 2-(4-chlorophenyl)benzo[d]thiazole (13.0 g, 53.1 mmol, yield: 90%).

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 1,2-dibromobenzene (56.7 g, 240.1 mmol) and 2-(4-chlorophenyl)benzo[d]thiazole (29.7 g, 120.9 mmol), obtained was the objective compound (105) (13.1 g, 17.5 mmol, overall yield: 18.2%).

¹H NMR (200MHz, CDCl₃): δ 7.28-7.32(m, 8H), 7.54-7.55(m, 16H), 7.67(m, 4H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 748.20(found), 748.95(calculated)

[Preparation Example 7] Preparation of Compound
(106)

5 According to the same procedure as in Preparation
Example 1 but using anthracene-9,10-dione (20.0 g, 96.1
mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and 2-(4-
chlorophenyl)benzo[d]thiazole (25.3 g, 103.0 mmol),
obtained was the objective compound (106) (14.5 g, 19.4
10 mmol, overall yield: 20.2%).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 4H), 7.54-7.55(m,
20H), 7.67(m, 4H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 748.20(found), 748.95(calculated)

15 [Preparation Example 8] Preparation of Compound
(107)

According to the same procedure as in Preparation
Example 1 but using anthracene-9,10-dione (20.0 g, 96.1
mmol), 1,3-dibromobenzene (56.7 g, 240.1 mmol) and 2-(4-
20 chlorophenyl)benzo[d]thiazole (32.7 g, 133.3 mmol),
obtained was the objective compound (107) (13.8 g, 18.4
mmol, overall yield: 19.2%).

^1H NMR (200MHz, CDCl_3): δ 7.32-7.44(m, 10H), 7.54-
7.55(m, 12H), 7.67-7.70(m, 6H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 748.20 (found), 748.95 (calculated)

[Preparation Example 9] Preparation of Compound
(108)

5 According to the same procedure as in Preparation
Example 1 but using 2-bromoanthracene-9,10-dione (27.6 g,
96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and
2-chlorobenzo[d]thiazole (19.8 ml, 103.4 mmol), obtained
was 2-(4-(9-(4-(benzo[d]thiazol-2-yl)phenyl)-2-
10 bromoanthracen-10-yl)phenyl)benzo[d]thiazole (15.5 g,
22.9 mmol).

In a mixture of toluene (300 mL) and ethanol (150
mL), dissolved were 2-(4-(9-(4-(benzo[d]thiazol-2-
yl)phenyl)-2-bromoanthracen-10-yl)phenyl)benzo[d]thiazole
15 (15.5 g, 22.9 mmol), phenylboronic acid (3.4 g, 27.5
mmol) and tetrakis(triphenylphosphine)palladium (0)
(Pd(PPh₃)₄) (2.6 g, 2.3 mmol). Aqueous solution of
sodium carbonate (2M Na₂CO₃) (250 mL) was added thereto,
and the resultant mixture was stirred under reflux for 6
20 hours. After cooling to room temperature, water was
slowly added to the reaction mixture to quench the
reaction. The reaction mixture was extracted with
dichloromethane (300 mL), and the extract was dried under
reduced pressure, and recrystallized from ethyl acetate

(200 mL) and methanol (100 mL) to obtain the objective compound (108) (13.9 g, 20.6 mmol, overall yield: 21.4%).

^1H NMR (200MHz, CDCl_3): δ 7.22-7.32(m, 5H), 7.48-7.55(m, 15H), 7.67-7.73(m, 3H), 7.89(s, 1H) 8.12(d, 2H),
5 8.23(d, 2H)

MS/FAB: 672.17(found), 672.86(calculated)

[Preparation Example 10] Preparation of Compound (109)

10 According to the same procedure as in Preparation Example 9 but using 2-(4-(9-(4-(benzo[d]thiazol-2-yl)phenyl)-2-bromo-anthracen-10-yl)phenyl)benzo[d]thiazole (15.5 g, 22.9 mmol), 2-naphthaleneboronic acid (5.9 g, 34.4 mmol),
15 tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$) (2.6 g, 2.3 mmol), 2M sodium carbonate (Na_2CO_3) (12.1 g, 114.5 mmol) and toluene (300 mL), obtained was the objective compound (109) (13.2 g, 18.3 mmol, overall yield: 19.0%).

20 ^1H NMR (200MHz, CDCl_3): δ 7.32(m, 4H), 7.54-7.55(m, 14H), 7.67(m, 4H), 7.73(d, 2H), 7.89(s, 2H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 722.19(found), 722.92(calculated)

[Preparation Example 11] Preparation of Compound
(110)

In tetrahydrofuran (300 mL), dissolved was 2-(4-(9-(4-(benzo[d]thiazol-2-yl)phenyl)-2-bromoanthracen-10-
5 yl)phenyl)benzo[d]thiazole (15.5 g, 22.9 mmol) under
nitrogen atmosphere, and the solution was chilled to -
78°C. After slowly adding n-butyllithium (2.5M solution
in n-hexane) (6.4 mL, 68.9 mmol) thereto, the mixture was
stirred for one hour. While maintaining the temperature,
10 chlorotrimethyl silane (7.5 g, 68.8 mmol) was added
thereto. The reaction mixture was slowly warmed to room
temperature, and stirred for 24 hours. Then sodium
chloride solution (50 mL) was added thereto to quench the
reaction, and the resultant mixture was extracted with
15 ethyl acetate (300 mL). The extract was dried under
reduced pressure and recrystallized from ethyl acetate
(200 mL) and methanol (100 mL) to obtain the objective
compound (110) (6.9 g, 10.3 mmol, overall yield: 10.7%).

¹H NMR (200MHz, CDCl₃): δ 0.66(s, 9H), 7.32(m, 2H),
20 7.54-7.55(m, 13H), 7.65-7.67(m, 3H), 7.89(s, 1H), 8.12(d,
2H), 8.23(d, 2H)

MS/FAB: 668.12(found), 668.94(calculated)

[Preparation Example 12] Preparation of Compound (111)

According to the same procedure as in Preparation Example 11 but using 2-(4-(9-(4-(benzo[d]thiazol-2-yl)phenyl)-2-bromo-anthracen-10-yl)phenyl)benzo[d]thiazole (15.5 g, 22.9 mmol), chlorotriphenylsilane (10.1 g, 34.3 mmol), n-butyllithium (2.5M solution in n-hexane) (6.4 mL, 68.9 mmol) and tetrahydrofuran (300 mL), obtained was the objective compound (111) (7.8 g, 9.1 mmol, overall yield: 9.5%).

^1H NMR (200MHz, CDCl_3): δ 7.32-7.36(m, 11H), 7.54-7.55(m, 18H), 7.60-7.67(m, 3H), 7.77(d, 1H), 7.94(s, 1H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 854.22(found), 855.15(calculated)

15

[Preparation Example 13] Preparation of Compound (112)

According to the same procedure as in Preparation Example 1 but using 2-methylanthraquinone (21.4 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and 2-chlorobenzo[d]thiazole (19.8 mL, 103.4 mmol), obtained was the objective compound (112) (14.0 g, 22.9 mmol, overall yield: 23.8%).

¹H NMR (200MHz, CDCl₃): δ 2.46(s, 3H), 7.18(d, 1H),
7.32(m, 2H), 7.46(s, 1H), 7.54-7.67(m, 15H), 8.12(d, 2H),
8.23(d, 2H)

MS/FAB: 610.15(found), 610.79(calculated)

5

[Preparation Example 14] Preparation of Compound
(113)

According to the same procedure as in Preparation
Example 1 but using 2,3-dimethylantracene-9,10-dione
10 (22.7 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1
mmol) and 2-chlorobenzo[d]thiazole (19.8 mL, 103.4 mmol),
obtained was the objective compound (113) (13.1 g, 21.0
mmol, overall yield: 21.9%).

¹H NMR (200MHz, CDCl₃): δ 2.46(s, 6H), 7.32(m, 2H),
15 7.40(s, 2H), 7.54-7.55(m, 12H), 7.67(m, 2H), 8.12(d, 2H),
8.23(d, 2H)

MS/FAB: 624.17(found), 624.82(calculated)

[Preparation Example 15] Preparation of Compound
20 (114)

According to the same procedure as in Preparation
Example 1 but using 2-tert-butylantracene-9,10-dione
(25.4 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1
mmol) and 2-chlorobenzo[d]thiazole (19.8 mL, 103.4 mmol),

obtained was the objective compound (114) (12.2 g, 18.7 mmol, overall yield: 19.5%).

^1H NMR (200MHz, CDCl_3): δ 1.40(s, 9H), 7.18(d, 1H), 7.32(m, 2H), 7.46(s, 1H), 7.54-7.55(m, 12H), 7.61-7.67(m, 3H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 652.2(found), 652.87(calculated)

[Preparation Example 16] Preparation of Compound (115)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and 2-chloro-6-(trimethylsilyl)benzo[d]thiazole (24.9 g, 103.0 mmol), obtained was the objective compound (115) (3.8 g, 5.2 mmol, overall yield: 5.4%).

^1H NMR (200MHz, CDCl_3): δ 0.66(s, 9H), 7.32(m, 4H), 7.54(s, 8H), 7.67(m, 4H), 7.77(d, 2H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 740.22(found), 741.12(calculated)

[Preparation Example 17] Preparation of Compound (116)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1

mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and 2-chloro-6-(trifluoromethyl)benzo[d]thiazole (24.5 g, 103.0 mmol), obtained was the objective compound (116) (8.2 g, 11.2 mmol, overall yield: 11.6%).

5 ^1H NMR (200MHz, CDCl_3): δ 7.32(m, 4H), 7.54(s, 8H), 7.67(m, 4H), 7.74(d, 2H), 8.16(d, 2H), 8.31(s, 2H)

MS/FAB: 732.11(found), 732.76(calculated)

[Preparation Example 18] Preparation of Compound
10 (117)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and 2-chloro-6-phenylbenzo[d]thiazole (25.3 g, 103.0 mmol),
15 obtained was the objective compound (117) (15.1 g, 20.1 mmol, overall yield: 20.9%).

^1H NMR (200MHz, CDCl_3): δ 7.22-7.32(m, 10H), 7.48(d, 4H), 7.54(s, 8H), 7.67(m, 4H), 7.77(s, 2H), 8.29(d, 2H), 8.34(s, 2H)

20 MS/FAB: 748.20(found), 748.95(calculated)

[Preparation Example 19] Preparation of Compound
(118)

According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 2,7-dibromo-9,9-dimethyl-9H-fluorene (84.5 g, 240.1 mmol) and 2-chlorobenzo[d]thiazole (8.2 mL, 65.2 mmol), obtained was the objective compound (118) (9.5 g, 11.4 mmol, overall yield: 11.9%).

^1H NMR (200MHz, CDCl_3): δ 1.67(s, 12H), 7.32(m, 4H), 7.55-7.67(m, 12H), 7.77(s, 4H), 7.90(d, 4H), 8.12(t, 2H), 8.23(t, 2H)

10 MS/FAB: 828.26(found), 829.08(calculated)

[Preparation Example 20] Preparation of Compound (119)

According to the same procedure as in Preparation Example 1 but using 9-(10-oxoanthracen-9(10H)-ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.3 mmol) and 2-chlorobenzo[d]thiazole (13.0 mL, 103.2 mmol), obtained was the objective compound (119) (15.0 g, 19.4 mmol, overall yield: 20.2%).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 12H), 7.54-7.55(m, 12H), 7.67(t, 8H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 772.2(found), 772.98(calculated)

[Preparation Example 21] Preparation of Compound
(120)

According to the same procedure as in Preparation
Example 1 but using 9-(10-oxoanthracen-9(10H)-
5 ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,3-
dibromobenzene (56.7 g, 240.1 mmol) and 2-
chlorobenzo[d]thiazole (16.7 mL, 133.3 mmol), obtained
was the objective compound (120) (20.1 g, 26.0 mmol,
overall yield: 27.1%).

10 $^1\text{H NMR}$ (200MHz, CDCl_3): δ 7.32-7.44(m, 14H), 7.55(t,
4H), 7.67-7.70(m, 10H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 772.2(found), 772.98(calculated)

[Preparation Example 22] Preparation of Compound
15 (121)

According to the same procedure as in Preparation
Example 1 but using 9-(10-oxoanthracen-9(10H)-
ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,3,5-
tribromobenzene (75.6 g, 240.2 mmol) and 2-
20 chlorobenzo[d]thiazole (23.7 mL, 188.9 mmol), obtained
was the objective compound (121) (20.9 g, 20.1 mmol,
overall yield: 20.9%).

$^1\text{H NMR}$ (200MHz, CDCl_3): δ 7.32(m, 8H), 7.55(m, 8H),
7.66-7.67(m, 14H), 8.12(d, 4H), 8.23(d, 4H)

MS/FAB: 1038.2(found), 1039.32(calculated)

[Preparation Example 23] Preparation of Compound
(122)

5 According to the same procedure as in Preparation
Example 1 but using 9-(10-oxoanthracen-9(10H)-
ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,2-
dibromobenzene (56.7 g, 240.1 mmol) and 2-(4-
chlorophenyl)benzo[d]thiazole (13.3 mL, 105.5 mmol),
10 obtained was the objective compound (122) (17.7 g, 20.3
mmol, overall yield: 21.1%).

^1H NMR (200MHz, CDCl_3): δ 7.28-7.32(m, 12H), 7.54-
7.55(m, 16H), 7.67(m, 8H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 924.26(found), 925.17(calculated)

15

[Preparation Example 24] Preparation of Compound
(123)

According to the same procedure as in Preparation
Example 1 but using 9-(10-oxoanthracen-9(10H)-
20 ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 2,6-
dibromonaphthalene (68.7 g, 240.1 mmol) and 2-
chlorobenzo[d]thiazole (13.3 mL, 105.5 mmol), obtained
was the objective compound (123) (17.7 g, 20.3 mmol,
overall yield: 21.1%).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 8H), 7.54-7.55(m, 8H), 7.67-7.73(m, 12H), 7.89(s, 4H), 8.12(d, 2H), 8.23(d, 2H)

MS/FAB: 872.23(found), 873.09(calculated)

5

[Preparation Example 25] Preparation of Compound (124)

According to the same procedure as in Preparation Example 1 but using 9-(10-oxoanthracen-9(10H)-ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.3 mmol) and 2-chloro-6-(trifluoromethyl)benzo[d]thiazole (24.5 g, 103.2 mmol), obtained was the objective compound (124) (17.6 g, 19.4 mmol, overall yield: 20.2%).

15 ^1H NMR (200MHz, CDCl_3): δ 7.32(m, 8H), 7.54(s, 8H), 7.67(m, 8H), 7.74(d, 2H), 8.16(d, 2H), 8.31(s, 2H)

MS/FAB: 908.18(found), 908.97(calculated)

20 [Preparation Example 26] Preparation of Compound (125)

According to the same procedure as in Preparation Example 1 but using 9-(10-oxoanthracen-9(10H)-ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.3 mmol) and 2-chloro-6-

(trimethylsilyl)benzo[d]thiazole (25.0 g, 103.2 mmol),
obtained was the objective compound (125) (16.7 g, 18.2
mmol, overall yield: 18.9%).

¹H NMR (200MHz, CDCl₃): δ 0.66(s, 18H), 7.32(m, 8H),
5 7.54(s, 8H), 7.67(m, 8H), 7.77(d, 2H), 8.21(d, 2H),
8.34(s, 2H)

MS/FAB: 916.28(found), 917.34(calculated)

[Preparation Example 27] Preparation of Compound
10 (126)

According to the same procedure as in Preparation
Example 1 but using 9-(10-oxoanthracen-9(10H)-
ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,4-
dibromobenzene (56.7 g, 240.3 mmol) and 2-chloro-6-
15 phenylbenzo[d]thiazole (25.3 g, 103.0 mmol), obtained was
the objective compound (126) (10.4 g, 11.2 mmol, overall
yield: 11.6%).

¹H NMR (200MHz, CDCl₃): δ 7.32(m, 14H), 7.48(d, 4H),
7.54(s, 8H), 7.67(m, 8H), 7.77(d, 2H), 8.29(d, 2H),
20 8.34(s, 2H)

MS/FAB: 924.26(found), 925.17(calculated)

[Preparation Example 28] Preparation of Compound
(127)

According to the same procedure as in Preparation Example 1 but using 9-(10-oxoanthracen-9(10H)-ylidene)anthracen-10(9H)-one (36.9 g, 96.1 mmol), 1,3-dibromobenzene (56.7 g, 240.1 mmol) and 2-chloro-6-(trimethylsilyl)benzo[d]thiazole (25.0 g, 103.4 mmol),
5 obtained was the objective compound (127) (16.7 g, 18.2 mmol, overall yield: 18.9%).

^1H NMR (200MHz, CDCl_3): δ 0.66(s, 18H), 7.30-7.38(m, 10H), 7.42-7.45(m, 4H), 7.65-7.68(m, 10H), 8.21-8.12(m,
10 2H), 8.34(s, 2H)

MS/FAB: 916.28(found), 917.34(calculated)

[Preparation Example 29] Preparation of Compound (128)

15 According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 1,3-dibromobenzene (56.7 g, 240.1 mmol) and 2-chloro-6-(trimethylsilyl)benzo[d]thiazole (32.2 g, 133.2 mmol), obtained was the objective compound (128) (13.8 g,
20 18.6 mmol, overall yield: 7.7%).

^1H NMR (200MHz, CDCl_3): δ 0.66(s, 18H), 7.32-7.38(m, 6H), 7.42-7.46(m, 4H), 7.67-7.70(m, 6H), 7.77(d, 2H), 8.21(d, 2H), 8.34(s, 2H)

MS/FAB: 740.22(found), 741.12(calculated)

[Preparation Example 30] Preparation of Compound
(129)

According to the same procedure as in Preparation
Example 1 but using 2-methylanthraquinone (21.4 g, 96.1
5 mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and 2-
chloro-6-(trimethylsilyl)benzo[d]thiazole (25.1 g, 103.8
mmol), obtained was the objective compound (129) (14.0 g,
19.8 mmol, overall yield: 23.8%).

¹H NMR (200MHz, CDCl₃): δ 0.67(s, 18H), 2.43(s, 3H),
10 7.20-7.29(m, 3H), 7.45(s, 1H), 7.53-7.56(m, 8H), 7.61-
7.65(m, 3H), 7.75-7.77(d, 2H), 8.19-8.21(d, 2H), 8.32(d,
2H)

MS/FAB: 754.23(found), 755.15(calculated)

15 [Preparation Example 31] Preparation of Compound
(130)

According to the same procedure as in Preparation
Example 1 but using 2-tert-butylanthracene-9,10-dione
(25.4 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1
20 mmol) and 2-chloro-6-(trimethylsilyl)benzo[d]thiazole
(25.0 g, 103.4 mmol), obtained was the objective compound
(130) (12.2 g, 15.3 mmol, overall yield: 19.5%).

¹H NMR (200MHz, CDCl₃): δ 0.65(s, 18H), 1.42(m, 3H),
7.16-7.28(m, 3H), 7.45(s, 1H), 7.50-7.54(m, 8H), 7.62-

7.66(m, 3H), 7.74-7.77(d, 2H), 8.19-8.21(d, 2H), 8.34(d, 2H)

MS/FAB: 796.28(found), 797.23(calculated)

5 [Preparation Example 32] Preparation of Compound (131)

According to the same procedure as in Preparation Example 1 but using 2,3-dimethylantracene-9,10-dione (22.7 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1
10 mmol) and 2-chloro-6-(trimethylsilyl)benzo[d]thiazole (24.4 g, 100.9 mmol), obtained was the objective compound (131) (13.1 g, 17.1 mmol, overall yield: 21.9%).

¹H NMR (200MHz, CDCl₃): δ 0.67(s, 18H), 2.47(s, 6H), 7.31(d, 2H), 7.41(m, 2H), 7.56(d, 8H), 7.66(m, 2H),
15 8.21(d, 2H), 8.34(d, 2H)

MS/FAB: 768.25(found), 769.18(calculated)

[Preparation Example 33] Preparation of Compound (132)

20 According to the same procedure as in Preparation Example 1 but using anthracene-9,10-dione (20.0 g, 96.1 mmol), 1,4-dibromobenzene (56.7 g, 240.1 mmol) and 2-chlorobenzo[d]thiazole (17.5 mL, 103.0 mmol), obtained

was the objective compound (132) (8.2 g, 11.2 mmol, overall yield: 11.6%).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 4H), 7.54-7.55(m, 12H), 7.67(m, 4H), 8.12(d, 2H), 8.23(d, 2H)

5 MS/FAB: 597.74(found), 596.14(calculated)

[Preparation Example 34] Preparation of Compound (133)

Under nitrogen atmosphere, 9-bromoanthracene (20.0 g, 77.8 mmol) was dissolved in tetrahydrofuran (200 mL), and
10 the solution was chilled to -78°C . To the solution, n-butyllithium (n-BuLi, 2.5M in hexane) (37.4 mL, 93.4 mmol) was slowly added dropwise. After 30 minutes, trimethylborate (17.7 mL, 155.6 mmol) was added dropwise
15 thereto. The temperature was slowly raised, and the mixture was further stirred at room temperature for one day. To the mixture, 1N aqueous hydrochloric acid (200 mL) was added, and the resultant mixture was stirred for 30 minutes, and extracted with water (300 mL) and
20 dichloromethane (200 mL). The extract was dried under reduced pressure and recrystallized from ethyl acetate (30 mL) and hexane (500 mL) to obtain 9-anthraceneboronic acid (9.3 g, 41.9 mmol).

To a mixture of toluene (200 mL) and ethanol (100 mL), dissolved were 9-anthraceneboronic acid (9.3 g, 41.9 mmol), 2-(4-chlorophenyl)benzo[d]thiazole (29.7 g, 120.9 mmol) and tetrakis(triphenylphosphine)palladium (0) (Pd(PPh₃)₄) (2.1 g, 1.8 mmol). To the solution, added
5 was aqueous 2M sodium carbonate solution (100 mL), and the mixture was stirred at 120°C under reflux for 12 hours. Then, the temperature was lowered to 25°C, and the reaction was quenched by adding distilled water (100
10 mL). The reaction mixture was extracted with ethyl acetate (100 mL), and the extract was dried under reduced pressure. Recrystallization from tetrahydrofuran (20 mL) and methanol (300 mL) gave 2-(4-anthracen-10-yl)phenyl)benzo[d]thiazole (6.5 g, 15.1 mmol).

Under nitrogen atmosphere, 2-(4-anthracen-10-yl)phenyl) benzo[d]thiazole (6.5 g, 15.1 mmol) and N-bromosuccinimide (3.0 g, 16.6 mmol) were dissolved in dichloromethane (200 mL), and the solution was stirred at 25°C for one day. After quenching the reaction by adding
20 distilled water (200 mL), the reaction mixture was extracted with dichloromethane (100 mL). The extract was dried under reduced pressure, and recrystallized from tetrahydrofuran (20 mL) and methanol (200 mL) to obtain

2-(4-(10-bromoanthracen-9-yl)phenyl)benzo[d]thiazole (6.9 g, 13.5 mmol).

In a mixture of toluene (150 mL) and ethanol (70 mL), dissolved were 2-(4-(10-bromoanthracen-9-yl)phenyl)benzo[d]thiazole (6.9 g, 13.5 mmol), 2-naphthylboronic acid (2.0 g, 16.2 mmol) and tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$) (1.6 g, 1.4 mmol). Then, aqueous 2M sodium carbonate solution (70 mL) was added thereto, and the resultant mixture was stirred at 120°C under reflux for 6 hours. After cooling the mixture to 25°C, the reaction was quenched by adding distilled water (100 mL). The reaction mixture was extracted with ethyl acetate (100 mL), and the extract was dried under reduced pressure. Recrystallization from tetrahydrofuran (20 mL) and methanol (200 mL) gave the objective compound (133) (5.8 g, 11.4 mmol).

^1H NMR (200MHz, CDCl_3): δ 7.32(m, 6H), 7.54-7.55(m, 7H), 7.67-7.73(m, 7H), 7.89(d, 2H), 8.12-8.23(m, 2H)

MS/FAB: 514.16(found), 513.16(calculated)

[Preparation Example 35] Preparation of Compound (134)

Under nitrogen atmosphere, 2-(4-chlorophenyl)benzo[d]thiazole (20.0 g, 68.9 mmol) was dissolved in tetrahydrofuran (THF) (700 mL), and the solution was chilled to -78°C. To the solution, n-buthyllithium (2.5M solution in n-hexane) (33.0 mL, 82.7 mmol) was slowly added, and the mixture was stirred for one hour. While maintaining the temperature at -78°C, trimethylborate (10.7 g, 103.3 mmol) was added thereto. Then the temperature was slowly raised, and the mixture was stirred at room temperature for 18 hours. Water (700 mL) was added thereto, and the resultant mixture was stirred for one hour, and extracted with ethyl acetate. The extract was dried under reduced pressure, and recrystallized from n-hexane (300 mL) to obtain 4-(benzo[d]thiazol-2-yl)phenylboronic acid (17.0 g, 66.6 mmol).

A solution of 2-chloroanthraquinone (6.8 g, 27.8 mmol), 4-(benzo[d]thiazol-2-yl)phenylboronic acid (10.6 g, 41.7 mmol) and tetrakis(triphenylphosphine)palladium (0) (Pd(PPh₃)₄) (3.2 g, 2.8 mmol) dissolved in 2M potassium carbonate (K₂CO₃) (150 mL), ethylene glycol dimethyl ether (DME) (300 mL) and ethanol (150 mL) was stirred under reflux for 20 hours. After cooling to room temperature, water (200 mL) was added to the reaction

mixture, and the resultant mixture was stirred and extracted with ethyl acetate (300 mL). The extract was dried under reduced pressure, and recrystallized from n-hexane (300 mL) to obtain 2-(4-(benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (11.6 g, 27.7 mmol).

According to the same procedure as in Preparation Example 1 but using 2-bromonaphthalene (19.8 g, 95.8 mmol) and 2-(4-(benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (10.0 g, 24.0 mmol) under nitrogen atmosphere, obtained was the objective compound (134) (5.5 g, 8.5 mmol, overall yield: 42.5%).

^1H NMR (200MHz, CDCl_3): δ 7.34-7.36 (m, 6H), 7.55-7.58 (m, 9H), 7.67-7.73 (m, 9H), 7.86-7.89 (m, 3H), 8.14 (d, 1H), 8.26 (d, 1H)

MS/FAB: 640.21(found), 639.80(calculated)

[Preparation Example 36] Preparation of Compound (135)

According to the same procedure as in Preparation Example 1 but using 2-bromo-9,9-dimethylfluorene (13.7 g, 50.3 mmol) and 2-(4-(benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (7.0 g, 16.7 mmol), obtained was the objective compound (135) (5.0 g, overall yield: 30.2%).

¹H NMR (200MHz, CDCl₃): δ 1.63 (d, 12H), 7.30-7.38 (m, 6H), 7.53-7.55 (m, 5H), 7.55-7.57 (m, 4H), 7.58-7.60 (m, 2H), 7.62-7.65 (m, 2H), 7.70-7.74 (m, 3H), 7.84-7.89 (m, 5H), 8.13 (d, 1H), 8.24 (d, 1H)

5 MS/FAB: 772.30(found), 772.01(calculated)

[Preparation Example 37] Preparation of Compound (136)

According to the same procedure as in Preparation
10 Example 1 but using 4-bromobiphenyl (11.7 g, 50.3 mmol) and 2-(4-(benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (7.0 g, 16.7 mmol), obtained was the objective compound (136) (6.0 g, overall yield: 20.3%).

¹H NMR (200MHz, CDCl₃): δ 7.20-7.21 (m, 2H), 7.31-
15 7.33 (m, 8H), 7.47-7.54 (m, 19H), 7.68-7.72 (m, 3H), 7.89-7.91 (d, 1H), 8.11 (d, 1H), 8.21 (d, 1H)

MS/FAB: 692.24(found), 691.88(calculated)

[Preparation Example 38] Preparation of Compound
20 (137)

According to the same procedure as in Preparation Example 1 but using 2-bromobiphenyl (11.7 g, 50.3 mmol) and 2-(4-(benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-

dione (7.0 g, 16.7 mmol), obtained was the objective compound (137) (3.8 g, overall yield: 15.3%).

^1H NMR (200MHz, CDCl_3): δ 7.25-7.31 (m, 8H), 7.46-7.51 (m, 4H), 7.52-7.60 (m, 11H), 7.68-7.73 (m, 3H), 7.87
5 (d, 1H), 8.12 (d, 1H), 8.23 (d, 1H)

MS/FAB: 691.23(found), 691.88(calculated)

[Preparation Example 39] Preparation of Compound (138)

10 A reaction vessel was charged with 1,3,5-tribromobenzene (20.0 g, 63.5 mmol), phenyl boronic acid (16.2 g, 133.4 mmol) and trans-dichlorobis(triphenylphosphine)palladium (II) ($\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$) (4.4 g, 6.3 mmol), and toluene (600 mL)
15 and 2M sodium carbonate (Na_2CO_3) (200 mL), and the mixture was stirred at 90°C . After 4 hours, the temperature was lowered to room temperature, and water (200 mL) was added to quench the reaction. The reaction mixture was extracted with dichloromethane (300 mL), and
20 the extract was dried under reduced pressure. Purification via column chromatography (eluent: n-hexane) gave 1-bromo-3,5-diphenylbenzene (9.6 g, 31.0 mmol).

According to the same procedure as in Preparation Example 1 but using 1-bromo-3,5-diphenylbenzene (9.6 g,

31.0 mmol), 2-(4-(benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (7.0 g, 16.7 mmol), obtained was the objective compound (138) (5.0 g, overall yield: 32.8%).

^1H NMR (200MHz, CDCl_3): δ 7.19-7.22 (m, 4H), 7.24-
5 7.31 (m, 10H), 7.48-7.58 (m, 15H), 7.62-7.65 (m, 8H),
7.66-7.70 (m, 3H), 7.87 (d, 1H), 8.11(d, 1H), 8.21 (d,
1H)

MS/FAB: 843.30(found), 844.07(calculated)

10 [Preparation Example 40] Preparation of Compound
(139)

A reaction vessel was charged with 1,2-
dibromobenzene (20.0 g, 84.8 mmol), 2-naphthalene boronic
acid (16.0 g, 93.3 mmol), and trans-
15 dichlorobis(triphenylphosphine)palladium (II)
($\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$) (5.9 g, 8.4 mmol), and the mixture was
stirred under reflux in 2M sodium carbonate (Na_2CO_3) (150
mL) and toluene (500 mL). After two hours, the reaction
mixture was extracted with dichloromethane (500 mL), and
20 the extract was filtered under reduced pressure.
Recrystallization from methanol (300 mL) gave 2-(2-
bromophenyl)naphthalene (20.0 g, 70.6 mmol).

According to the same procedure as in Preparation
Example 1 but using 2-(2-bromophenyl)naphthalene (14.24 g,

50.3 mmol) and 2-(4-(benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (7.0 g, 16.7 mmol), obtained was the objective compound (139) (5.0 g, overall yield: 21.7%).

5 ^1H NMR (200MHz, CDCl_3): δ 7.22-7.38 (m, 10H), 7.48-7.51 (m, 13H), 7.61-7.67 (m, 6H), 7.70-7.74 (d, 3H), 7.89-7.90 (s, 3H), 8.12 (d, 1H), 8.23 (d, 1H)

MS/FAB: 791.26(found), 792.0(calculated)

10 [Preparation Example 41] Preparation of Compound (140)

According to the same procedure as in Preparation Example 35 but using 2,7-bromo-9,9-dimethylfluorene (100.0 g, 284.0 mmol), tetrahydrofuran (800 mL), n-
15 butyllithium (2.5M solution in n-hexane) (124.9 mL, 312.4 mmol), N,N-dimethylformaldehyde (41.5 g, 568.0 mmol) and 2-aminophenol (13.7 g, 109.5 mmol) under nitrogen atmosphere, obtained was 7-(benzo[d]thiazol-2-yl)-9,9-dimethyl-9H-fluoren-2-yl-2-boronic acid (19.0 g,
20 51.18 mmol).

According to the same procedure as in Preparation Example 35 but using 2-chloroanthraquinone (7.8 g, 32.3 mmol), 7-(benzo[d]thiazol-2-yl)-9,9-dimethyl-9H-fluoren-2-yl-2-boronic acid (18.0 g, 48.4 mmol),

tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$)
(3.7 g, 3.2 mmol) and 2M potassium carbonate (K_2CO_3) (150
mL), obtained was 2-(2-benzo[d]thiazol-2-yl)-9,9-
dimethyl-9H-fluoren-7-yl)anthracene-9,10-dione (16.3 g,
5 30.7 mmol).

According to the same procedure as in Preparation
Example 1 but using 2-bromonaphthalene (8.15 g, 39.35
mmol) and 2-(2-benzo[d]thiazol-2-yl)-9,9-dimethyl-9H-
fluoren-7-yl)anthracene-9,10-dione (7.0 g, 13.1 mmol)
10 under nitrogen atmosphere, obtained was the objective
compound (140) (5.2 g, overall yield: 31.5%).

^1H NMR (200MHz, CDCl_3): δ 1.67 (s, 6H), 7.35-7.39 (m,
6H), 7.51-7.63 (m, 7H), 7.64-7.70 (m, 6H), 7.72-7.81 (m,
5H), 7.91-7.94 (m, 5H), 8.11 (d, 1H), 8.21 (d, 1H)

15 MS/FAB: 756.27(found), 755.96(calculated)

[Preparation Example 42] Preparation of Compound
(141)

According to the same procedure as in Preparation
20 Example 1 but using 2-bromo-9,9-dimethylfluorene (3.58 g,
39.36 mmol) and 2-(2-benzo[d]thiazol-2-yl)-9,9-dimethyl-
9H-fluoren-7-yl)anthracene-9,10-dione (7.0 g, 13.12 mmol),
obtained was the objective compound (141) (6.64 g,
overall yield: 32.5%).

^1H NMR (200MHz, CDCl_3): δ 1.67 (s, 18H), 7.25-7.38 (m, 6H), 7.51-7.90 (m, 22H), 8.14 (d, 1H), 8.22 (d, 1H)

MS/FAB: 887.36 (found), 888.17 (calculated)

5 [Preparation Example 43] Preparation of Compound (142)

According to the same procedure as in Preparation Example 1 but using 4-bromobiphenyl (9.17 g, 39.3 mmol) and 2-(2-benzo[d]thiazol-2-yl)-9,9-dimethyl-9H-fluoren-7-yl)anthracene-9,10-dione (7.0 g, 13.1 mmol), obtained was
10 the objective compound (142) (5.69 g, overall yield: 36.2%).

^1H NMR (200MHz, CDCl_3): δ 1.66 (d, 6H), 7.21-7.28 (m, 2H), 7.31-7.37 (m, 6H), 7.47-7.51 (m, 4H), 7.52-7.63 (m, 13H), 7.65-7.69 (m, 2H), 7.72-7.79 (m, 3H), 7.90-7.92 (m, 3H), 8.13 (d, 1H), 8.24 (d, 1H)

MS/FAB: 807.30 (found), 808.04 (calculated)

20 [Preparation Example 44] Preparation of Compound (143)

According to the same procedure as in Preparation Example 1 but using 2-bromobiphenyl (9.17 g, 39.36 mmol) and 2-(2-benzo[d]thiazol-2-yl)-9,9-dimethyl-9H-fluoren-7-yl)anthracene-9,10-dione (7.0 g, 13.1 mmol), obtained was

the objective compound (143) (3.63 g, overall yield: 23.9%).

^1H NMR (200MHz, CDCl_3): δ 1.64 (s, 6H), 7.19-7.34 (m, 12H), 7.49-7.51 (d, 4H), 7.52-7.62 (m, 9H), 7.68-7.72 (m, 3H), 7.73-7.78 (m, 2H), 7.88-7.91 (m, 3H), 8.11 (d, 1H), 8.25 (d, 1H)

MS/FAB: 807.30(found), 808.04(calculated)

[Preparation Example 45] Preparation of Compound (144)

According to the same procedure as in Preparation Example 1 but using 1-bromo-3,5-diphenylbenzene (12.1 g, 39.3 mmol) and 2-(2-benzo[d]thiazol-2-yl)-9,9-dimethyl-9H-fluoren-7-yl)anthracene-9,10-dione (7.0 g, 13.12 mmol), obtained was the objective compound (144) (7.42 g, overall yield: 43.3%).

^1H NMR (200MHz, CDCl_3): δ 1.66 (s, 6H), 7.21-7.27 (m, 4H), 7.29-7.34 (m, 10H), 7.48-7.50 (d, 8H), 7.51-7.64 (m, 5H), 7.65-7.71 (m, 8H), 7.71-7.76 (m, 3H), 7.89-7.91 (m, 3H), 8.13 (d, 1H), 8.24 (d, 1H)

MS/FAB: 959.36(found), 960.23(calculated)

[Preparation Example 46] Preparation of Compound (145)

According to the same procedure as in Preparation Example 1 but using 2-(2-bromophenyl)naphthalene (11.15 g, 39.36 mmol) and 2-(2-benzo[d]thiazol-2-yl)-9,9-dimethyl-9H-fluoren-7-yl)anthracene-9,10-dione (7.0 g, 13.12 mmol),
5 obtained was the objective compound (145) (3.82 g, overall yield: 23.5%).

^1H NMR (200MHz, CDCl_3): δ 1.65 (d, 6H), 7.22-7.30 (m, 10H), 7.51-7.65 (m, 11H), 7.67-7.78 (m, 11H), 7.89-7.92 (m, 5H), 8.12 (d, 1H), 8.22 (d, 1H)

10 MS/FAB: 907.23(found), 908.16(calculated)

[Preparation Example 47] Preparation of Compound (146)

According to the same procedure as in Preparation Example 35 but using 2,6-dibromonaphthalene (100.0 g, 349.69 mmol), n-buthyllithium (2.5M solution in n-hexane) (153.87 mL, 384.67 mmol), N,N-dimethylformaldehyde (51.13 g, 699.38 mmol), 2-aminophenol (17.57 g, 140.38 mmol) and trimethylborate (18.36 g, 176.34 mmol) under nitrogen
20 atmosphere, obtained was 6-(benzo[d]thiazol-2-yl)naphthalen-2-yl-2-boronic acid (24.62 g, 80.68 mmol).

According to the same procedure as in Preparation Example 35 but using 2-chloroanthraquinone (10.0 g, 41.21 mmol), 6-(benzo[d]thiazol-2-yl) naphthalen-2-yl-2-boronic

acid (15.09 g, 49.45 mmol), tetrakis palladium (II) triphenylphosphine ($\text{Pd}(\text{PPh}_3)_4$) (4.76 g, 4.12 mmol) and 2M potassium carbonate (K_2CO_3) (200 mL) in ethylene glycol dimethyl ether (DME) (500 mL) and ethanol (200 mL),
5 obtained was 2-(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-dione (18.11 g, 38.74 mmol).

According to the same procedure as in Preparation Example 1 but using 2-bromonaphthalene (13.29 g, 64.17 mmol) and 2-(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-dione (10.0 g, 21.39 mmol) under
10 nitrogen atmosphere, obtained was the objective compound (146) (8.02 g, overall yield: 36.2%).

^1H NMR (200MHz, CDCl_3): δ 7.30-7.32 (m, 4H), 7.34-7.36 (d, 2H), 7.53-7.56 (m, 7H), 7.64-7.67 (d, 6H), 7.71-7.73 (m, 5H), 7.86-7.88 (s, 5H), 8.12 (d, 1H), 8.21 (d, 1H)
15

MS/FAB: 689.22(found), 689.86(calculated)

[Preparation Example 48] Preparation of Compound
20 (147)

According to the same procedure as in Preparation Example 1 but using 2-bromo-9,9-dimethylfluorene (17.53 g, 64.17 mmol) and 2-(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-dione (10.0 g, 21.39 mmol), obtained

was the objective compound (147) (9.06 g, overall yield: 21.3%).

^1H NMR (200MHz, CDCl_3): δ 1.66 (s, 12H), 7.31-7.37 (m, 6H), 7.51-7.56 (m, 8H), 7.62-7.37 (m, 4H), 7.73-7.77 (m, 4H), 7.83-7.91 (m, 6H), 8.06 (s, 1H), 8.11 (d, 1H) 8.22 (d, 1H)

MS/FAB: 821.31(found), 822.07(calculated)

[Preparation Example 49] Preparation of Compound (148)

According to the same procedure as in Preparation Example 1 but using 4-bromobiphenyl (14.94 g, 64.08 mmol) and 2-(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-dione (10.0 g, 21.39 mmol), obtained was the objective compound (148) (7.79 g, overall yield: 52.5%).

^1H NMR (200MHz, CDCl_3): δ 7.21-7.23 (m, 2H), 7.30-7.33 (m, 6H), 7.46-7.49 (m, 4H), 7.51-7.54 (m, 12H), 7.67-7.66 (m, 2H), 7.72-7.74 (d, 3H), 8.12 (d, 1H), 8.23 (d, 1H)

MS/FAB: 741.25(found), 741.94(calculated)

[Preparation Example 50] Preparation of Compound (149)

According to the same procedure as in Preparation Example 35 but using 1,4-dibromonaphthalene (100.0 g, 349.69 mmol), n-buthyllithium (2.5M solution in n-hexane) (153.87 mL, 384.67 mmol), N,N-dimethylformaldehyde (51.13 g, 699.38 mmol) and 2-aminophenol (17.57 g, 140.38 mmol) under nitrogen atmosphere, obtained was 2-(1-bromonaphthalen-4-yl)benzo[d]thiazole (31.26 g, 91.89 mmol).

According to the same procedure as in Preparation Example 35 but using 2-(1-bromonaphthalen-4-yl)benzo[d]thiazole (30.0 g, 88.17 mmol), n-buthyllithium (2.5M solution in n-hexane) (38.79 mL, 96.99 mmol) and trimethylborate (18.36 g, 176.34 mmol) under nitrogen atmosphere, obtained was 4-(benzo[d]thiazol-2-yl)naphthalen-1-yl-1-boronic acid (18.57 g, 80.68 mmol).

According to the same procedure as in Preparation Example 35 but using 2-chloroanthraquinone (10.0 g, 41.21 mmol), 4-(benzo[d]thiazol-2-yl)naphthalen-1-yl-1-boronic acid (15.09 g, 49.45 mmol), tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$) (4.76 g, 4.12 mmol) and 2M potassium carbonate (K_2CO_3) (200 mL) dissolved in ethylene glycol dimethyl ether (DME) (500 mL) and ethanol (200 mL), obtained was 2-(1-

benzo[d]thiazol-2-yl)naphthalen-4-yl)anthracene-9,10-dione (16.74 g, 35.81 mmol).

According to the same procedure as in Preparation Example 1 but using 2-bromonaphthalene (13.29 g, 64.17
5 mmol) and 2-(1-benzo[d]thiazol-2-yl)naphthalen-4-yl)anthracene-9,10-dione (10.0 g, 21.39 mmol) under nitrogen atmosphere, obtained was the objective compound (149) (6.65 g, overall yield: 26.5%).

^1H NMR (200MHz, CDCl_3): δ 7.31-7.34 (m, 8H), 7.55-
10 7.58 (m, 5H), 7.61-7.64 (m, 2H), 7.67-7.70 (m, 8H), 7.73-7.75 (m, 3H), 7.87-7.89 (s, 3H), 8.11 (d, 1H), 8.21 (d, 1H)

MS/FAB: 690.22(found), 689.86(calculated)

15 [Preparation Example 51] Preparation of Compound (150)

According to the same procedure as in Preparation Example 35 but using 4,4-dibromobiphenyl (100.0 g, 320.51 mmol), n-buthyllithium (2.5M solution in n-hexane)
20 (141.03 mL, 352.56 mmol), N,N-dimethylformaldehyde (46.86 g, 641.02 mmol), 2-aminophenol (15.82 g, 126.38 mmol), n-buthyllithium (2.5M solution in n-hexane) (36.04 mL, 90.09 mmol) and trimethylborate (12.796 g, 122.86 mmol) under nitrogen atmosphere, obtained was 4-

(benzo[d]thiazol-2-yl)biphenyl-4-yl-4'-boronic acid
(20.07 g, 80.68 mmol).

According to the same procedure as in Preparation
Example 35 but using 2-chloroanthraquinone (10.0 g, 41.21
5 mmol), 4-(benzo[d]thiazol-2-yl)biphenyl-4-yl-4-boronic
acid (20.47 g, 61.82 mmol),
tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$)
(4.76 g, 4.12 mmol) and 2M potassium carbonate (K_2CO_3)
(200 mL) dissolved in ethylene glycol dimethyl ether
10 (DME) (500 mL) and ethanol (200 mL), obtained was 2-(4-
benzo[d]thiazol-2-yl)biphenyl-4-yl)anthracene-9,10-dione
(17.82 g, 36.09 mmol).

According to the same procedure as in Preparation
Example 1 but using 2-bromonaphthalene (12.59 g, 60.78
15 mmol) and 2-(4-benzo[d]thiazol-2-yl)biphenyl-4-
yl)anthracene-9,10-dione (10.0 g, 20.26 mmol) under
nitrogen atmosphere, obtained was the objective compound
(150) (6.03 g, 49.8%).

^1H NMR (200MHz, CDCl_3): δ 7.30-7.32 (m, 6H), 7.49-
20 7.52 (m, 13H), 7.65-7.67 (m, 6H), 7.71-7.72 (d, 3H),
7.91-7.92 (d, 3H), 8.13 (d, 1H), 8.23 (d, 1H)

MS/FAB: 716.24(found), 715.9(calculated)

[Preparation Example 52]

Under nitrogen atmosphere, an excess amount of 10N potassium hydroxide (KOH) solution (24.1 g, 430 mmol) was added to 5-amino-6-methylbenzothiazole (20.0 g, 143.68 mmol), and ethylene glycol solvent (20 mL) was added thereto. After stirring the mixture at 125°C for 15 hours, the temperature was lowered to room temperature, and conc. hydrochloric acid (HCl) (5.0 g) was added to the reaction mixture. The reaction was quenched by extraction with ethyl acetate (500 mL) and washing with water (1000 mL). Purification via column chromatography (eluent: dichloromethane/n-hexane) gave 2-amino-4-methylbenzenethiazole (17.78 g, 127.73 mmol).

According to the same procedure as in Preparation Example 35 but using 2-amino-4-methylbenzethiazole (20.0 g, 143.68 mmol), 4-bromobenzaldehyde (26.58 g, 143.68 mmol) and n-buthyllithium (2.5M solution in n-hexane) (21.04 mL, 52.6 mmol) and trimethylborate (10.31 g, 98.63 mmol), obtained was 4-(6-methylbenzo[d]thiazol-2-yl)phenylboronic acid (15.27 g, 56.74 mmol).

According to the same procedure as in Preparation Example 35 but using 2-chloroanthraquinone (10.0 g, 41.21 mmol), 4-(6-methylbenzo[d]thiazol-2-yl)phenylboronic acid (14.42 g, 53.57 mmol), tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$)

(4.76 g, 4.12 mmol) and 2M potassium carbonate (K_2CO_3) (200 mL) dissolved in ethylene glycol dimethyl ether (DME) (500 mL) and ethanol (200 mL), obtained was 2-(4-(6-methylbenzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (12.25 g, 38.33 mmol).

According to the same procedure as in Preparation Example 1 but using 2-bromonaphthalene (14.39 g, 69.52 mmol) and 2-(4-(6-methylbenzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (10.0 g, 23.17 mmol) under nitrogen atmosphere, obtained was the objective compound (151) (7.45 g, overall yield: 32.1%).

1H NMR (200MHz, $CDCl_3$): δ 2.35 (s, 3H), 7.29-7.34 (m, 7H), 7.54-7.57 (m, 7H), 7.69-7.71 (m, 6H), 7.73-7.75 (m, 3H), 7.89-7.91 (m, 4H), 8.12 (d, 1H)

MS/FAB: 716.24(found), 715.9(calculated)

[Preparation Example 53] Preparation of Compound (152)

According to the same procedure as in Preparation Example 52 but using 2-amino-6-bromobenzothiazole (15.0 g, 65.47 mmol) and 10N potassium hydroxide (KOH) (10 g, 180 mmol), obtained was 2-amino-5-bromobenzenethiol (11.6 g, 56.84 mmol).

A solution of 2-amino-5-bromobenzenethiol (10.0 g, 48.99 mmol), phenylboronic acid (7.15 g, 58.68 mmol) and tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$) (5.65 g, 4.89 mmol) dissolved in 2M sodium carbonate (5) (Na_2CO_3) (150 mL), ethylene glycol dimethyl ether (DME) (500 mL) and ethanol (200 mL) was stirred under reflux for 20 hours. After cooling to room temperature, water (300 mL) was added to the reaction mixture, and the resultant mixture was stirred and extracted with ethyl 10 acetate (600 mL). The extract was distilled under reduced pressure, and recrystallized from n-hexane (300 mL) to obtain 2-amino-5-phenylbenzenethiol (8.77 g, 43.45 mmol).

According to the same procedure as in Preparation 15 Example 35 but using 2-amino-5-phenylbenzenethiol (8.77 g, 43.35 mmol), 4-bromobenzaldehyde (8.04 g, 43.45 mmol), dimethylsulfoxide (DMSO) (40 mL), n-butyllithium (2.5M solution in n-hexane) (8.74 mL, 21.84 mmol), trimethylborate (3.69 g, 35.49 mmol), obtained was 4-(6- 20 phenylbenzo[d]thiazol-2-yl)phenylboronic acid (6.06 g, 18.29 mmol).

According to the same procedure as in Preparation Example 35 but using 2-chloroanthraquinone (10.0 g, 41.21 mmol), 4-(6-phenylbenzo[d]thiazol-2-yl)phenylboronic acid

(20.47 g, 61.82 mmol) and tetrakis(triphenylphosphine)palladium (O) ($\text{Pd}(\text{PPh}_3)_4$) (4.76 g, 4.12 mmol) dissolved in 2M potassium carbonate (K_2CO_3) (200 mL), ethylene glycol dimethyl ether (DME) (500 mL) and ethanol (200 mL), obtained was 2-(4-(6-phenylbenzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (18.92 g, 38.33 mmol).

According to the same procedure as in Preparation Example 1 but using 2-bromonaphthalene (12.59 g, 60.78 mmol) and 2-(4-(6-phenylbenzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (10.0 g, 20.26 mmol) under nitrogen atmosphere, obtained was the objective compound (152) (6.88 g, overall yield: 51.7%).

^1H NMR (200MHz, CDCl_3): δ 7.24-7.26 (m, 1H), 7.30-7.34 (m, 8H), 7.49-7.51 (m, 2H), 7.51-7.52 (m, 7H), 7.69-7.72 (m, 6H), 7.72-7.84 (m, 4H), 7.90-7.92 (s, 3H), 8.29 (d, 1H), 8.34 (d, 1H)

MS/FAB: 716.24(found), 715.9(calculated)

[Preparation Example 54] Preparation of Compound (153)

According to the same procedure as in Preparation Example 35 but using 2-bromobenzaldehyde (59.10 g, 319.51 mmol), 2-aminophenol (40.0 g, 319.51 mmol),

dimethylsulfoxide (400 mL), n-butyllithium (2.5M solution in n-hexane) (24.81 mL, 62.03 mmol) and trimethylborate (10.76 g, 103.35 mmol), obtained was 2-(benzo[d]thiazol-2-yl)phenylboronic acid (8.3 g, 32.53 mmol).

5 According to the same procedure as in Preparation Example 35 but using 2-chloroanthraquinone (5.26 g, 21.69 mmol), 2-(benzo[d]thiazol-2-yl)phenylboronic acid (8.3 g, 32.53 mmol) and tetrakis(triphenylphosphine)palladium (0) (Pd(PPh₃)₄) (2.51 g, 2.17 mmol) dissolved in 2M potassium
10 carbonate (K₂CO₃) (80 mL), ethylene glycol dimethyl ether (DME) (200 mL) and ethanol (800 mL), obtained was 2-(2-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (8.69 g, 20.82 mmol).

 According to the same procedure as in Preparation
15 Example 1 but using 2-bromonaphthalene (19.83 g, 95.8 mmol) and 2-(2-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (10.0 g, 23.95 mmol) under nitrogen atmosphere, obtained was the objective compound (153) (6.50 g, 10.17 mmol, overall yield: 51.4%).

20 ¹H NMR (200MHz, CDCl₃): δ 7.25-7.32 (m, 8H), 7.51-7.58 (m, 7H), 7.62-7.66 (m, 6H), 7.66-7.73 (m, 3H), 8.91-7.92 (s, 3H), 8.15 (d, 1H), 8.25 (d, 1H)

 MS/FAB: 639.21(found), 639.80(calculated)

[Preparation Example 55] Preparation of Compound (154)

According to the same procedure as in Preparation Example 35 but using 3-bromobenzaldehyde (59.10 g, 319.51 mmol), 2-aminophenol (40.0 g, 319.51 mmol), n-butyllithium (2.5M solution in n-hexane) (24.81 mL, 62.03 mmol) and trimethylborate (10.76 g, 103.35 mmol), obtained was 3-(benzo [d]thiazol-2-yl)phenylboronic acid (12.61 g, 49.42 mmol).

10 According to the same procedure as in Preparation Example 35 but using 2-chloroanthraquinone (7.99 g, 32.95 mmol), 3-(benzo[d]thiazol-2-yl)phenylboronic acid (12.61 g, 49.42 mmol) and tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$) (3.80 g, 3.29 mmol) dissolved in 2M
15 potassium carbonate (K_2CO_3) (100 mL), ethylene glycol dimethyl ether (DME) (300 mL) and ethanol (100 mL), obtained was 2-(3-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (11.17 g, 26.76 mmol).

According to the same procedure as in Preparation
20 Example 1 but using 2-bromonaphthalene (19.83 g, 95.8 mmol) and 2-(3-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (10.0 g, 23.95 mmol) under nitrogen atmosphere, obtained was the objective compound (154) (7.61 g, 11.89 mmol, overall yield: 55.4%).

^1H NMR (200MHz, CDCl_3): δ 7.29-7.47 (m, 9H), 7.48-7.57 (m, 5H), 7.61-7.72 (m, 10H), 7.88-7.91 (s, 3H), 8.09-7.12 (m, 1H), 8.18-8.22 (m, 1H)

MS/FAB: 640.21(found), 639.80(calculated)

5

[Preparation Example 56] Preparation of Compound (155)

A reaction vessel was charged with copper bromide (101.0 g, 0.45 mmol), tert-butyl nitrate (58.34 mL, 0.49 mmol) and acetonitrile (800 mL), and the mixture was stirred at 70°C. After 1 hour, 2,6-diaminoanthraquinone (45.0 g, 0.19 mmol) was added thereto, and the resultant mixture was stirred at 85°C. After 48 hours, 20% hydrochloric acid (1 L) was added thereto, and the mixture was stirred for 1 hours. The precipitate produced was filtered and washed several times with water and methanol. Washing again with acetone and dichloromethane twice each gave 2,6-dibromoanthracene-9,10-dione (50.0 g, 54.65 mmol).

20 A solution of 2,6-dibromoanthracene-9,10-dione (10.0 g, 27.32 mmol), 4-benzo[d]thiazol-2-yl)phenylboronic acid (17.42 g, 68.31 mmol) and tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$) (3.15 g, 2.73 mmol) dissolved in 2M potassium carbonate

(K₂CO₃) (100 mL), ethylene glycol dimethyl ether (DME) (300 mL) and ethanol (100 mL) was stirred under reflux for 20 hours. After cooling to room temperature, water (200 mL) was added to the reaction mixture, and the
5 resultant mixture was stirred, and extracted with ethyl acetate solvent (300 mL). The extract was dried under reduced pressure, and recrystallized from n-hexane (300 mL) to obtain 2,6-bis(4-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (14.79 g, 23.60 mmol).

10 According to the same procedure as in Preparation Example 1 but using 2-bromonaphthalene (9.91 g, 47.88 mmol) and 2,6-bis(4-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (10.0 g, 15.96 mmol) under nitrogen atmosphere, obtained was the objective
15 compound (155) (8.0 g, 9.18 mmol, overall yield: 62.4%).

¹H NMR (200MHz, CDCl₃): δ 7.25-7.31 (m, 4H), 7.50-7.56 (m, 16H), 7.62-7.69 (m, 4H), 7.70-7.72 (d, 4H), 7.89-7.91 (s, 4H), 8.08-8.12 (m, 2H), 8.20-8.23 (m, 2H)

MS/FAB: 848.23(found), 849.07(calculated)

20

[Preparation Example 57] Preparation of Compound (156)

According to the same procedure as in Preparation Example 1 but using 2-bromo-9,9-dimethylfluorene (13.08 g,

47.87 mmol), 2,6-bis(4-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-dione (10.0 g, 15.96 mmol), obtained was the objective compound (156) (7.01 g, 54.7%).

¹H NMR (200MHz, CDCl₃): δ 1.68 (s, 12H), 7.24-7.29 (t, 2H), 7.31-7.39 (t, 2H), 7.50-7.64 (m, 18H), 7.72-7.78 (m, 4H), 7.80-7.82 (d, 2H), 7.87-7.90 (m, 4H), 8.11-8.13 (m, 2H), 8.19-8.21 (m, 2H)

MS/FAB: 982.33(found), 981.27(calculated)

10 [Preparation Example 58] Preparation of Compound (157)

According to the same procedure as in Preparation Example 1 but using 4-bromobiphenyl (11.16 g, 47.87 mmol), 2,6-bis(4-benzo[d]thiazol-2-yl)phenyl)anthracene-9,10-
15 dione (10.0 g, 15.96 mmol), obtained was the objective compound (157) (6.59 g, 54.9%).

¹H NMR (200MHz, CDCl₃): δ 7.16-7.21 (m, 2H), 7.23-7.31 (m, 4H), 7.45-7.50 (m, 4H), 7.50-7.57(s, 22H), 7.71-7.73 (d, 2H), 8.89-8.90 (s, 2H), 8.07-8.12 (m, 2H), 8.19-
20 8.23 (m, 2H)

MS/FAB: 902.27(found), 901.15(calculated)

[Preparation Example 59] Preparation of Compound (158)

According to the same procedure as in Preparation Example 56 but using 2,6-dibromoanthracene-9,10-dione (10.0 g, 27.32 mmol), 6-(benzo[d]thiazol-2-yl)naphthalen-2-yl-2-boronic acid (20.0 g, 54.64 mmol) and
5 tetrakis(triphenylphosphine)palladium (0) ($\text{Pd}(\text{PPh}_3)_4$) (6.31 g, 5.46 mmol) dissolved in 2M potassium carbonate (K_2CO_3) (200 mL), ethylene glycol dimethyl ether (DME) (500 mL) and ethanol (200 mL), obtained was 2,6-bis(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-
10 dione (28.83 g, 39.67 mmol).

According to the same procedure as in Preparation Example 1 but using 2-bromonaphthalene (8.55 g, 41.27 mmol) and 2,6-bis(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-dione (10.0 g, 13.76 mmol) under
15 nitrogen atmosphere, obtained was the objective compound (158) (6.05 g, 6.37 mmol, overall yield: 67.4%).

^1H NMR (200MHz, CDCl_3): δ 7.25-7.32 (m, 4H), 7.51-7.58 (m, 12H), 7.62-7.68 (m, 4H), 7.69-7.72 (m, 8H), 7.88-7.90 (s, 8H), 8.12-8.14 (m, 2H), 8.23-8.25 (m, 2H)

20 MS/FAB: 848.23(found), 849.07(calculated)

[Preparation Example 60] Preparation of Compound (159)

According to the same procedure as in Preparation Example 1 but using 2-bromo-9,9-dimethylfluorene (11.27 g, 41.27 mmol) and 2,6-bis(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-dione (10.0 g, 13.76 mmol), obtained was the objective compound (159) (6.09 g, 57.4%).

^1H NMR (200MHz, CDCl_3): δ 1.65 (s, 12H), 7.21-7.28 (t, 2H), 7.30-7.37 (t, 2H), 7.50-7.61 (m, 14H), 7.70-7.78 (m, 8H), 7.82-7.91 (m, 10H), 8.08-8.10 (m, 2H), 8.22-8.24 (m, 2H)

MS/FAB: 1080.36(found), 1081.39(calculated)

[Preparation Example 61] Preparation of Compound (160)

According to the same procedure as in Preparation Example 1 but using 4-bromobiphenyl (11.16 g, 47.87 mmol) and 2,6-bis(2-benzo[d]thiazol-2-yl)naphthalen-6-yl)anthracene-9,10-dione (10.0 g, 13.76 mmol), obtained was the objective compound (160) (6.59 g, 54.9%).

^1H NMR (200MHz, CDCl_3): δ 7.14-7.22 (m, 2H), 7.24-7.32 (m, 4H), 7.47-7.49 (m, 4H), 7.49-7.56 (m, 18H), 7.71-7.76 (d, 6H), 7.88-7.90 (s, 6H), 8.11-8.13 (m, 2H), 8.24-8.26 (m, 2H)


MS/FAB: 902.27(found), 901.15(calculated)

[Example 1-61] Manufacture of OLED's using the compounds according to the present invention

OLED's were manufactured as illustrated in Fig. 1 by using the electron transportation materials according to
5 the present invention.


First, a transparent electrode ITO thin film (2) (15 Ω/\square) obtained from glass (1) for OLED was subjected to ultrasonic washing with trichloroethylene, acetone, ethanol and distilled water, subsequently, and stored in
10 isopronanol before use.

Then, an ITO substrate was equipped in a substrate folder of a vacuum vapor-deposit device, and 4,4',4"-tris(N,N-(2-naphthyl)-phenylamino)triphenylamine (2-TNATA, having the structure shown below) was placed in a cell of
15 the vacuum vapor-deposit device, which was then vented to reach 10^{-6} torr of vacuum in the chamber. Electric current was applied to the cell to evaporate 2-TNATA to vapor-deposit a hole injection layer (3) with 60 nm of thickness on the ITO substrate.



2-TNATA


Then, another cell of the vacuum vapor-deposit device was charged with N,N'-bis(α -naphthyl)-N,N'-diphenyl-4,4'-diamine (NPB), and electric current was applied to the cell to evaporate NPB to vapor-deposit a hole transportation layer (4) with 20 nm of thickness on the hole injection layer.




NPB

After formation of the hole injection layer and hole transportation layer, an electroluminescent layer was vapor-deposited as follows. One cell of the vacuum deposition device was charged with tris(8-hydroxyquinoline)aluminum (III) (Alq) as an

electroluminescent host material, while another cell of said device was charged with coumarin 545T (C545T), respectively. Two substances were doped by evaporating with different rates to vapor-deposit an electroluminescent layer (5) with a thickness of 30 nm on the hole transportation layer. The doping concentration was preferably 2 to 5 mol% on the basis of Alq.




Alq



C545T

Then, one of the compounds prepared according to Preparation Examples 1 to 61 (for example, Compound 109) was vapor-deposited with a thickness of 20 nm, as an electron transportation layer (6), followed by lithium quinolate (Liq) with a thickness of from 1 to 2 nm as an electron injection layer (7). Thereafter, an Al cathode (8) was vapor-deposited with a thickness of 150 nm by using another vacuum vapor-deposit device to manufacture an OLED.




[Comparative Example 1] Manufacture of an OLED using conventional EL material

5 A hole injection layer (3), a hole transportation layer (4) and an electroluminescent layer (5) were formed according to the same procedure as described in Example 1 to 61, and Alq (tris(8-hydroxyquinoline)-aluminum (III) having the structure shown below was vapor-deposited with

10 20 nm of thickness as an electron transportation layer (6), followed by lithium quinolate (Liq) with 1~2 nm of thickness as an electron injection layer (7). An Al cathode (8) was vapor-deposited by using another vacuum vapor-deposit device with a thickness of 150 nm, to

15 manufacture an OLED.



[Experimental Example 1] Examination of properties of OLED

Current luminous efficiencies and power efficiencies of OLED's comprising the thiazole system organic electroluminescent compound according to the present invention prepared from Example 1 to 61 and the conventional electroluminescent compound were measured at 1000 cd/m², of which the results are shown in Table 1.

10 [Table 1]

	Electron transportat ion layer material	Operatio n voltage (V) @1000cd/m ²	Luminous efficien cy (cd/A) @1000cd/m ²	Power efficien cy (lm/W) @1000cd/m ²	Color coordin ate (x,y)
Ex.1	Comp.100	5	11.7	7.3	0.29, 0.65
Ex.10	Comp.109	4	13.1	10.3	0.29,

					0.65
Ex.12	Comp.111	4	12.2	9.6	0.28, 0.64
Ex.19	Comp.118	4.5	12.8	8.9	0.28, 0.64
Ex.22	Comp.121	4	12.5	9.8	0.28, 0.64
Ex.26	Comp.125	3.5	11.0	9.9	0.30, 0.65
Ex.31	Comp.130	4	12.7	9.9	0.29, 0.65
Ex.35	Comp.134	4.5	13	9.1	0.29, 0.64
Ex.39	Comp.138	4.5	12.9	9.0	0.29, 0.64
Ex.42	Comp.141	4.5	13.1	9.1	0.28, 0.64
Ex.46	Comp.145	4.5	13.4	9.3	0.28, 0.64
Ex.54	Comp.153	4	12.8	10.0	0.28, 0.65
Ex.57	Comp.156	4	12.0	9.4	0.30, 0.64
Comp.	Alq ₃	6	11.6	6.1	0.30,

Ex. 1					0.65
-------	--	--	--	--	------

As can be seen from Table 1, Compound (109) as the electron transportation material (Example 10) showed highest power efficiency. In particular, Compound (109) of Example 10 and Compound (153) of Example 54 showed about 70% enhancement of power efficiency as compared to the conventional material, Alq, as the electron transportation layer.

Fig. 2 is a luminous efficiency curve of the conventional electroluminescent material, Alq:C545T, while Fig. 3 is a luminous efficiency curve of Compound (109) employed as the electron transportation material. Fig. 4 and Fig. 5 are luminance-voltage and power efficiency-luminance curves, respectively, which compare Compound (109) according to the present invention and Alq employed as the electron transportation layer.

From Table 1 showing the properties of the compounds developed by the present invention employed as an electron transportation layer, it is confirmed that the compounds developed by the present invention show excellent properties as compared to conventional substances in view of the performances.

It is analyzed that this results come from

appropriate combination of thiazole system functional group and anthracene skeletal as new concept of the present invention. The thiazole system functional group comprises heteroatoms such as N and S, so that electron
5 density of the aromatic ring is reduced to give excellent electron transportation property. In addition, anthracene is bipolar in its property, thereby maximizing the ability of carrier delivery.

The combination of both properties as mentioned
10 above is an inherent concept which is looking to the enhancement of carrier delivery property and the role of a host, not only directing to improvement of electroluminescent property of the molecule itself. Consistently, good electroluminescent properties were
15 confirmed in an OLED according to the present invention.

In the meanwhile, in addition to the concept as described above, the present invention designed a molecular structure to have highest electric properties as organic semiconductor in thin film by appropriately
20 combining the position of functional groups, steric hindrance, or the like. It is found that these results contribute to improvement of ability of electron transportation in the present invention.

Particularly, it is found that the improvement of

power consumption due to lowered operation voltage in an OLED employing the material according to the invention comes from improvement of current properties, not from simple improvement of luminous efficiency.

5

【Industrial Applicability】

The compounds according to the present invention for an electron transportation layer are advantageous in that they can substantially improve the power efficiency by noticeably lowering the operational voltage and increasing the current efficiency. Thus, it is expected that the material can greatly contribute to reduce the power consumption of an OLED.


10


【CLAIMS】

【Claim 1】

A thiazole system organic electroluminescent compound represented by Chemical Formula (1):


5 [Chemical Formula 1]




wherein, A is a chemical bond or  ;

if m is 0, Ar₁ is hydrogen, phenyl, 1-naphthyl or 2-
10 naphthyl;

if m is 1 or 2, Ar₁ is selected from following structures;




15 Ar₂ is selected from following structures;



5

Ar₃ is selected from following structures;



R₁ independently represents hydrogen, a C₁₋₂₀ alkyl group with or without halogen substituent(s), a C₁₋₂₀ alkylsilyl group, a C₆₋₂₀ arylsilyl group or a C₆₋₂₀ aryl

group;

R_{11} and R_{12} independently represent hydrogen, a C_{1-20} alkyl group with or without halogen substituent(s);

R_{13} through R_{18} independently represent hydrogen, a C_{1-20} alkyl group with or without halogen substituent(s),
 5 C_{1-20} alkylsilyl group, a C_{6-20} arylsilyl group or a C_{6-20} aryl group;


n is 1 or 2; and

the aryl group of R_1 and R_{13} through R_{18} may further
 10 comprise C_{1-20} alkyl group(s) or halogen substituent(s).


【Claim 2】

A thiazole system organic electroluminescent compound according to claim 1, which is selected from the
 15 compounds represented by one of Chemical Formulas (2) to (4):


[Chemical Formula 2]



[Chemical Formula 3]



[Chemical Formula 4]



5 wherein, A, Ar₁, Ar₃, R₁, R₁₃, R₁₄, R₁₅, R₁₆, R₁₇, R₁₈,
 m and n are defined for Chemical Formula (1) in claim 1.


【Claim 3】










A thiazole system organic electroluminescent
 10 compound according to claim 2, wherein R₁ and R₁₃ through
 R₁₈ are independently selected from hydrogen, methyl,
 ethyl, n-propyl, i-propyl, i-butyl, t-butyl, n-pentyl, i-
 amyl, n-hexyl, n-heptyl, n-octyl, 2-ethylhexyl, n-nonyl,
 decyl, dodecyl, hexadecyl, trifluoromethyl,
 15 pentafluoroethyl, trimethylsilyl, tripropylsilyl, tri(t-
 butyl)silyl, t-butyldimethylsilyl, triphenylsilyl,
 phenyldimethylsilyl, phenyl, benzyl, tolyl, 2-
 fluorophenyl, 4-fluorophenyl, biphenyl, naphthyl, anthryl,

phenanthryl, naphthacenyl, fluorenyl, 9,9-dimethylfluoren-2-yl, pyrenyl, phenylenyl and fluoranthenyl.


5 **【Claim 4】**








A thiazole system organic electroluminescent compound according to claim 3, which is selected from following compounds:












5















5




















5













**【Claim 5】**


5 An organic light emitting diode comprising a thiazole system organic electroluminescent compound according to any one of claims 1 to 4.

【DRAWINGS】


【Figure 1】




【Figure 2】




【Figure 3】



【Figure 4】





【Figure 5】



INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR2008/001659

A. CLASSIFICATION OF SUBJECT MATTER		
<i>C09K 11/06(2006.01)i</i>		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) IPC 8 : C09K, H05B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) eKIPASS (KIPO internal), USPAT, PAJ, REGISTRY and CAPLUS (STN)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	KR 10-2003-0067773 A (LG CHEM, LTD.) 19.08.2003 See chemical formula 1 (especially, 1-6, 1-7, 1-8 and 1-9).	1-5
A	US 6171715 B1 (SATO et al.) 09.01.2001 See abstract.	1-5
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
<p>* Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>		
Date of the actual completion of the international search 30 APRIL 2008 (30.04.2008)		Date of mailing of the international search report 30 APRIL 2008 (30.04.2008)
Name and mailing address of the ISA/KR  Korean Intellectual Property Office Government Complex-Daejeon, 139 Seonsa-ro, Seo-gu, Daejeon 302-701, Republic of Korea Facsimile No. 82-42-472-7140		Authorized officer OH, Se Zu Telephone No. 82-42-481-8156 

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR2008/001659

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
KR 10-2003-0067773 A	19.08.2003	AU2003215914A1	30.07.2003
		CN1625552A	08.06.2005
		EP1465874A2	13.10.2004
		JP2005515233A	26.05.2005
		US2003165715A1	04.09.2003
		US6878469BB	12.04.2005
		W02003060956A3	13.11.2003
US 6171715 B1	09.01.2001	JP11345686 A	14.12.1999

专利名称(译)	噻唑系机电致发光化合物和使用它的有机发光二极管		
公开(公告)号	EP2129738A1	公开(公告)日	2009-12-09
申请号	EP2008723695	申请日	2008-03-25
申请(专利权)人(译)	GRACEL显示增量.		
当前申请(专利权)人(译)	GRACEL显示增量.		
[标]发明人	LEE MI AE KWON HYUCK JOO KIM BONG OK KIM SUNG MIN YOON SEUNG SOO		
发明人	LEE, MI AE KWON, HYUCK JOO KIM, BONG OK KIM, SUNG MIN YOON, SEUNG SOO		
IPC分类号	C09K11/06		
CPC分类号	C09K11/06 C07D277/22 C09K2211/1007 C09K2211/1011 C09K2211/1037 H01L51/0058 H01L51/0064 H01L51/0071 H01L51/0077 H01L51/0081 H01L51/5012 H05B33/14		
优先权	1020070030315 2007-03-28 KR		
其他公开文献	EP2129738A4		
外部链接	Espacenet		

摘要(译)

本发明涉及新型噻唑系机电致发光化合物和包含该化合物的有机发光二极管。由于根据本发明的噻唑系机电致发光化合物具有良好的发光效率和寿命特性，因此可以生产具有非常好的工作寿命的OLED。