



(11)

EP 2 175 490 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
26.03.2014 Bulletin 2014/13

(51) Int Cl.:
H01L 27/32 (2006.01) H01L 51/50 (2006.01)
H01L 51/52 (2006.01) H01L 51/00 (2006.01)

(21) Application number: 09172511.9

(22) Date of filing: 08.10.2009

(54) Organic el display apparatus

Organische elektrolumineszente Anzeigevorrichtung
Dispositif organique électroluminescent d'affichage

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL
PT RO SE SI SK SM TR

(30) Priority: 10.10.2008 JP 2008264193
28.09.2009 JP 2009222634

(43) Date of publication of application:
14.04.2010 Bulletin 2010/15

(73) Proprietor: Canon Kabushiki Kaisha
Tokyo 146-8501 (JP)

(72) Inventors:

- Mori, Toshifumi
Tokyo Tokyo 146-8501 (JP)
- Suzuki, Koichi
Tokyo Tokyo 146-8501 (JP)
- Tsuboyama, Akira
Tokyo Tokyo 146-8501 (JP)
- Shiobara, Satoru
Tokyo Tokyo 146-8501 (JP)
- Ikari, Kenichi
Tokyo Tokyo 146-8501 (JP)

(74) Representative: TBK
Bavariaring 4-6
80336 München (DE)

(56) References cited:
EP-A1- 1 862 524 WO-A1-2005/054404
US-A1- 2003 034 722 US-A1- 2006 207 649

- "IUPAC Compendium of Chemical Terminology, 2nd Edition; Delayed Fluorescence" In: "IUPAC Compendium of Chemical Terminology, 2nd Edition; Delayed Fluorescence", 1 January 1997 (1997-01-01), COMPENDIUM OF CHEMICAL TERMINOLOGY. INTERNATIONAL UNION OF PURE & APPLIED CHEMISTRY (IUPAC), XP55022700, * the whole document *
- GIEBINK N C ET AL: "Transient analysis of triplet exciton dynamics in amorphous organic semiconductor thin films", ORGANIC ELECTRONICS, ELSEVIER, AMSTERDAM, NL, vol. 7, no. 5, 1 October 2006 (2006-10-01) , pages 375-386, XP024972796, ISSN: 1566-1199, DOI: 10.1016/J.ORGEL.2006.04.007 [retrieved on 2006-10-01]
- AKIRA TSUBOYAMA ET AL: "Photophysical Properties of Highly Luminescent Copper(I) Halide Complexes Chelated with 1,2-Bis (diphenylphosphino)benzene", INORGANIC CHEMISTRY, AMERICAN CHEMICAL SOCIETY, EASTON, US, vol. 46, no. 6, 27 February 2007 (2007-02-27), pages 1992-2001, XP002626460, ISSN: 0020-1669, DOI: 10.1021/IC0608086 [retrieved on 2007-02-27]

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**BACKGROUND OF THE INVENTION****Field of the Invention**

[0001] The present invention relates to an organic EL display apparatus having an organic EL device containing a delayed fluorescence material and a soaking member.

Description of the Related Art

[0002] Recently, research and development of an organic EL display apparatus using an organic EL device have actively been conducted.

[0003] The organic EL display apparatus has a plurality of red organic EL devices, green organic EL devices, and blue organic EL devices, each of which independently performs light emission and non-light emission as a pixel to display a full-color image.

[0004] The organic EL device has a pair of electrodes and a light-emitting layer that is disposed between the electrodes and formed of an organic compound.

[0005] A plurality of wirings are connected to the organic EL device. The wirings include a wiring transmitting gradation information for each wire, a wiring transmitting emission timing, and the like.

[0006] Also, a plurality of organic EL devices are connected to one wiring. One of the wirings serves to supply a current, and, when the plurality of organic EL devices are connected to the wiring, a large current flows to the organic EL device close to a power source to generate Joule heat which causes an increase in temperature. Also, depending on the position of the power source, the organic EL device close to the power source receives heat from the power source as compared to the organic EL device distant from the organic EL device. As a result, a temperature difference is caused between the plurality of organic EL devices disposed in a pixel region. Thus, emission luminance is varied between the organic EL devices even when identical information is so supplied as to achieve light emission of identical emission luminance. Therefore, uneven luminance is generated when pixels are compared to one another.

[0007] While fluorescence materials and phosphorescence materials have been developed, use of a delayed fluorescence material having high internal quantum efficiency for the organic EL device is disclosed in Japanese Patent Application No. 2004-241374.

[0008] Though Japanese Patent Application No. 2004-241374 discloses the organic EL device having the delayed fluorescence material, an organic EL display apparatus provided with red organic EL devices, green organic EL devices, and blue organic EL devices as pixels is not described nor suggested. Also, though the delayed fluorescence material is the one with which strong delayed fluorescence spectrum and phosphorescence

spectrum are observed within a range of 520 to 750 nm, the emission wavelength actually shown in drawings has a maximum emission wavelength that is formed of a peak exceeding 550 nm and a peak exceeding 600 nm. In short, the disclosed delayed fluorescence material is not a light-emitting material that is capable of emitting any elementary color such as green and blue in terms of its color purity.

[0009] Prior art which is related to this field of technology can be found in e.g. document EP 1 862 524 A1 disclosing an organic light emitting device and a flat panel display device comprising the same, in document US 2006 0207649 A1 disclosing an organic electroluminescent device, in non-patent literature IUPAC Compendium of Chemical Terminology, 2nd Edition (1997), disclosing delayed fluorescence, and in non-patent literature Giebink N. C. et al., Organic Electronics, 7, 2006, pages 375-386, disclosing a transient analysis of triplet exciton dynamics in amorphous organic semiconductor thin films, in document WO 2005/054404 A1 disclosing a luminescent device, in non-patent literature Akira Tsuboyama et al., Inorganic Chemistry, vol. 46, no. 6, 2007, pages 1992-2001 disclosing photophysical properties of highly luminescent copper (I) halide complexes chelated with 1,2-bis(diphenylphosphino)benzene, and in document US 2003/0034722 A1 disclosing a light emitting device and a display unit which make use of porphyrin derivative compound.

30 SUMMARY OF THE INVENTION

[0010] An object of the present invention is to provide an organic EL display apparatus that is free from uneven luminance even when an organic EL device having a phosphorescence material with high internal quantum yield and an organic EL device having a delayed fluorescence material with high internal quantum yield are provided on the same plane.

[0011] Thus, the present invention provides an organic EL display apparatus according to the appended claims.

[0012] According to the present invention, it is possible to provide an organic EL display apparatus that is free from uneven luminance even when an organic EL device having a phosphorescence material and an organic EL device having a delayed fluorescence material are provided on the same plane. Further features of the present invention will become apparent from the following description of exemplary embodiments with reference to the attached drawings.

50

BRIEF DESCRIPTION OF THE DRAWINGS

[0013]

55 FIG. 1 is a diagram showing a light emission mechanism of delayed fluorescence.

FIG. 2 is a diagram showing comparison between light emission mechanisms of delayed fluorescence

and phosphorescence.

FIG. 3 is a block diagram schematically showing a structure of an organic EL display apparatus and disposition of RGB pixels.

FIG. 4 is a block diagram showing a structure of an organic EL device.

FIG. 5 is a diagram showing heat conductivities of substances.

FIG. 6 is a diagram showing a correlation between emission quantum yield of a delayed fluorescence material and a temperature.

FIG. 7 is a block diagram in which a pixel region of an organic EL display apparatus is divided.

FIG. 8 is a block diagram schematically showing a structure of an organic EL display apparatus of Example 6 and disposition of RGB pixels thereof.

DESCRIPTION OF THE EMBODIMENTS

[0014] The organic EL display apparatus according to the present invention is defined by the claims.

[0015] Due to the soaking that is achieved even when the organic EL device having the delayed fluorescence material and the organic EL device having the phosphorescence material are disposed on the same plane, uneven emission luminance is prevented.

[0016] Shown in FIG. 1 is a light emission mechanism in the case of using a delayed fluorescence material for a light-emitting layer of an organic EL device. Of excitons generated by recombination of holes and electrons in the light-emitting layer, 25% of the excitons are brought into an excited singlet state (S_1), and 75% of the excitons are brought into an excited triplet state (T_1) depending on the spin multiplicity. Since delayed fluorescence is thermally excited from T_1 to S_1 to emit light by electron transition from S_1 to S_0 , it is possible to extract all of the excitons of S_1 and T_1 generated in the light-emitting layer as light. Therefore, in principle, it is possible to set an upper limit of internal quantum yield to 100% as in the case of phosphorescence.

[0017] The above-described delayed fluorescence utilizes thermal excitation from T_1 to S_1 . Therefore, the delayed fluorescence in the present invention is a thermal excitation type delayed fluorescence.


[0018] Hereinafter, with reference to FIG. 2 schematically showing energy levels when the delayed fluorescence and the phosphorescence have identical emission wavelengths, the energy levels are compared to one another. In FIG. 2, the energy level T_1 shown on the left and the energy level S_1 shown on the right are at the same level. This is for the purpose of the comparison between the delayed fluorescence and phosphorescence having the identical emission wavelengths. Focusing on an energy difference between S_1 and S_0 and an energy difference between T_1 and S_0 of each of the energy levels, the delayed fluorescence has the smaller energy differences than the phosphorescence. That is, it is understood that the delayed fluorescence has a

smaller bandgap as compared to the case of the phosphorescence when the emission wavelengths are identical to each other.


[0019] Hereinafter, a case of using a light-emitting material having a small bandgap in the organic EL device will be described. The organic EL device has a single layer- or multilayer- organic layer that is disposed between an anode and a cathode. When holes are injected from the anode while injecting electrons from the cathode, due to an injection barrier from the electrode to the organic layer, the drive voltage strongly depends on the injection barrier. In the case where a plurality of organic layers are used, also, an injection barrier between the organic layers is likewise problematic. In the case of using a light-emitting material having a small bandgap, it is possible to reduce the injection barrier. As a result, holes are smoothly injected into the organic layer from the anode, and electrons are smoothly injected from the cathode to the organic layer. Therefore, it is possible to reduce the drive voltage of the organic EL device, thereby improving the power efficiency (lm/W) in accordance with the drive voltage reduction.

[0020] Examples of the delayed fluorescence material include a copper complex, a platinum complex, a palladium complex, and the like. The examples of the delayed materials are shown in <Formula 1> to <Formula 3>.

[0021] <Formula 1> Delayed Fluorescence Material




[0022] <Formula 2> Delayed Fluorescence Material



X=I, Br, Cl

[0023] <Formula 3> Delayed Fluorescence Material

55



[0024] In the delayed fluorescence material to be used in the present invention, a light emission process can be specified to be delayed fluorescence by its light-emitting characteristics. The light emission of the delayed fluorescence material to be used in the present invention has the following properties.

1. An emission lifetime at room temperature (298 K) is at an order of microsecond.
2. An emission wavelength at room temperature (298 K) is shorter than an emission wavelength at a low temperature (77 K).
3. The emission lifetime at room temperature (298 K) is greatly shorter than an emission lifetime at a low temperature (77 K).
4. Emission intensity is increased by an increase in temperature.

[0025] In a comparison between an emission wavelength at room temperature and an emission wavelength at a low temperature of ordinary fluorescence and phosphorescence, the wavelengths are identical or the wavelength at the low temperature is shortened. In contrast, in the delayed fluorescence, the emission wavelength at a low temperature is lengthened. Such wavelength lengthening is caused since light emission is caused from an energy level of a triplet state which is lower than a singlet state although light emission from a singlet state is observed at room temperature. As used herein, the emission wavelength means a maximum emission wavelength or an emission start wavelength.

[0026] Also, the ordinary fluorescence has an emission lifetime at an order of nanosecond since the fluorescence is light emission from a singlet state, while the phosphorescence of which a triplet state is involved in light emission has an emission lifetime which is at an order of microsecond. Likewise, the delayed fluorescence has an emission lifetime at an order of microsecond since a triplet state is involved in light emission. The emission lifetime of a light-emitting material to be used in the present invention may preferably be 0.1 microsecond or more and less than one millisecond in a solid state or a solution state.

[0027] The emission lifetime of each of the delayed fluorescence and phosphorescence is at the order of microsecond. However, as the properties of the delayed fluorescence, the emission lifetime at a low temperature

becomes greatly longer with respect to the emission lifetime at room temperature. For example, in the case of a phosphorescent compound having quantum yield of 0.1 at room temperature, the emission life time under an assumption that non-radiation deactivation is suppressed at the low temperature is 10 times the emission lifetime at room temperature at the maximum. In the case of the delayed fluorescence, since light emissions at low temperature and room temperature are caused from different excitation states, the emission lifetime strongly depends on the temperature. Since light emission is caused from the triplet state at the low temperature though the light emission is caused from the singlet state at room temperature, the emission lifetime at low temperature is more

5 than 10 times the emission lifetime at room temperature and sometimes increased by two digits depending on the compound. The emission lifetime of the light-emitting material to be used in the present invention may preferably be 10 times or more, more preferably 50 times or more, 10 further preferably 100 times or more, of the emission lifetime at room temperature in a solid state or a solution state. The foregoing is a method for discriminating the delayed fluorescence.

[0028] In the case of the delayed fluorescence, the 25 light-emitting characteristics strongly depend on a temperature. For example, as shown in FIG. 6, the emission intensity (emission quantum yield) is increased with an increase in temperature. Unlike the phosphorescent material and the fluorescent material, the delayed fluorescence material shows strong temperature characteristics 30 due to the emission mechanism that involves thermal excitation.

[0029] In contrast, in the case of phosphorescence, the 35 temperature dependency of the light-emitting characteristics is smaller than the delayed fluorescence material. However, since the non-radiation deactivation rate is increased with an increase in temperature, the emission intensity tends to be reduced with an increase in temperature.

[0030] In short, in an organic EL display apparatus in 40 which an organic EL device having a delayed fluorescence material and an organic EL device having a phosphorescent material are provided on the same substrate, the emission intensity of one of the devices is increased 45 with an increase in temperature, while the emission intensity of the other device is reduced with the increase in temperature. Therefore, the present inventors have found that it is important to prevent the temperature increase in the organic EL display apparatus in which the 50 organic EL device having the delayed fluorescence material and the organic EL device having the phosphorescent material are provided on the same substrate. More specifically, a device for soaking of a display surface by means of a soaking unit is provided.

[0031] In the present invention, at least one of the red 55 organic EL device, the green organic EL device, and the blue organic EL device has a delayed fluorescence material in the light-emitting layer. At least one of the other

devices has a phosphorescent material in the light-emitting layer. Each of the red organic EL device, the green organic EL device, and the blue organic EL device may independently have either one of the delayed fluorescence material or the phosphorescent material in the light-emitting layer, but one of the red organic EL device, the green organic EL device, and the blue organic EL device may have a fluorescent material.

[0032] Hereinafter, the organic EL display apparatus will be described in detail. As shown in FIG. 3, the organic EL display apparatus of **an example useful for understanding** the present invention is provided with pixels arranged in a matrix pattern, a data signal line driver 302 for driving a data signal line wired for each of pixel rows, and a scanning signal line driver 301 for driving a scanning signal line wired for each of pixel lines. In the figure, R, G, and B indicate a red-light-emitting pixel, green-light-emitting pixel, and blue-light-emitting pixel, respectively. Each of the pixels has an organic EL device corresponding to the color. Furthermore, each of the pixels has a TFT device for controlling luminance of the organic EL device. As shown in the figure, the pixels are connected by row and by line each by way of a common wiring. Each of the wirings is connected to the data signal line driver 302 or the scanning signal line driver 301.

[0033] The pixels of R, G, and B (RGB pixels) may be arranged in various orders without limitation instead of the order shown in FIG. 3.

[0034] FIG. 7 is a diagram showing the pixel region which is divided for the brevity of explanation. In FIG. 7, the RGB pixels are not indicated, however, the pixel region is divided into 9 regions, and numbers 1 to 9 are respectively indicated in the regions. The regions 1 to 3 are regions close to the data signal line driver. The regions 1, 4, and 7 are the regions close to the scanning signal line driver. The temperature of each of the pixel regions in the present invention means an average temperature of the pixels existing in four corners in each of the regions of the pixel regions 1 to 9. Here, the pixel region 1, for example, is the most subject to temperature increase (referred to as high temperature pixel region, and the temperature thereof being indicated as TH) as compared to other pixel regions, while the pixel region 9 is the least subject to temperature increase (referred to as low temperature pixel region, and the temperature thereof being indicated as TL). In the case where TH-TL is large, uneven luminance of the organic EL display apparatus as a whole is prominent due to the temperature difference.

[0035] Also, as described above, the delayed fluorescence material is increased in emission intensity with an increase in temperature, while the phosphorescence material has the temperature characteristics that the emission intensity is lowered or kept constant along with an increase in temperature. Therefore, in the organic EL display apparatus including the organic EL device having the delayed fluorescence material and the organic EL device having the phosphorescent material, uneven lu-

minance as the whole display apparatus is increased with an increase in TH-TL.

[0036] FIG. 4 is a block diagram showing the organic EL device having the soaking unit. In FIG. 4, in the organic EL device 601, an organic function layer 602 in which organic compound layers are stacked, an upper electrode (reflective electrode 603) serving as the cathode, and a lower electrode (transparent electrode 607) serving as the anode are stacked. The reflective electrode and the transparent electrode are opposed to each other.

[0037] The organic function layer 602 has a hole transport layer 606, a light-emitting layer 605, and an electron transport layer 604.

[0038] The organic EL device 601 further has a protective film 608, and a radiating member 609 is provided on the protective film 608.

[0039] The organic EL display apparatus according to **examples useful for understanding** the present invention has a plurality of the organic EL devices shown in FIG. 4. Namely, the radiating member 609 is disposed on all of the pixel regions.

[0040] Here, examples of the soaking unit in the present invention and **examples useful for understanding the present invention** include the following two types.

1. **(example)** The radiating member is provided in all of the pixel regions of the display apparatus to achieve soaking by heat radiation. Since heat transfer from the high temperature side pixels to the low temperature side pixels is also caused, the soaking reduces the temperature difference in the whole pixel regions. Furthermore, the radiating member may be locally provided on the pixel regions of the display apparatus for radiating heat to achieve soaking of the whole pixel regions.

2. **(embodiment)** The wiring pattern of the display apparatus is devised to prevent local concentration of heat, thereby achieving soaking in such a manner that the temperature difference in the whole pixel regions is reduced.

[0041] The radiating member of (1) specifically is the soaking achieved by the provision of a member having high heat conductivity in the whole pixel regions of the display apparatus. The radiating member may preferably have high heat conductivity. FIG. 5 is a diagram showing heat conductivities of substances. The shape of the radiating member is not particularly limited, and the radiating member may not necessarily be in the form of a plate or a sheet. In order to enhance the effect of heat conduction, a surface area may be increased by forming an unevenness structure on the member. Also, the radiating member may be provided at a plurality of parts. In the organic EL device shown in FIG. 4, the reflective electrode 603 is the upper electrode, and the transparent electrode 607 is the lower electrode. In short, light is extracted toward a lower side in the drawing in FIG. 4. The

radiating member 609 is disposed on a rear side of the reflective electrode. A substrate (not shown) supporting the organic EL device of FIG. 4 may be provided outside the radiating member of the organic EL device 601 or may be provided at a lower electrode side.

[0042] Also, the RGB pixels have the same positional relationship of the reflective electrode and the transparent electrode. That is, when the reflective electrode is provided in an upper part of the drawing with the transparent electrode being provided in a lower part of the drawing in one organic EL device as shown in FIG. 4, such positional relationship is established between the reflective electrode and the transparent electrode in each of the other organic EL devices.

[0043] When the organic EL display apparatus is of the top emission type, i.e. the type of externally discharging light without transmitting the substrate, the radiating member may be provided on both of front and rear sides of the support substrate disposed at a reflective electrode side. Also, the thickness of the radiating member is not limited insofar as the thickness allows satisfactory confirmation of the heat radiation effect. The thickness may preferably be about 500 nm or more and about 3 mm or less.

[0044] Furthermore, in the case of soaking the whole pixel regions by locally allowing heat radiation by providing the radiating member only at a part in which heat generation amount is large, the type, shape, and thickness of the radiating member may be the same as those described above. In order to further enhance the soaking effect, a plurality of types of radiating members may be provided, for example, in such a manner that a radiating member of which a type may be the same or different from the aforementioned radiating member is locally provided in addition to the radiating member that is provided in the whole pixel regions.

[0045] One of specific examples of the soaking unit (2) is a zigzag wiring. By the zigzag wiring, in the case of connecting a wiring pattern to a display apparatus in which the data signal line drivers are disposed at upper and lower edges as shown in FIG. 8, data signal lines of odd numbers (i.e., 1st, 3rd, 5th, ...) in the column direction are connected to the upper data signal line driver, and the data signal lines of even numbers (i.e., 2nd, 4th, 6th, ...) are connected to the lower data signal line driver. By such wiring, it is possible to supply display data to the pixels from the data signal line drivers at the upper and lower edges. The wiring is disposed outside the organic EL device, specifically at a side opposite to a light extraction side of the organic EL device, more specifically at a side opposite to the light reflection surface of the reflective electrode of the organic EL device.

[0046] Likewise, in the case of connecting a wiring pattern to a display apparatus in which the scanning signal line drivers are disposed at left and right edges, scanning signal lines of odd numbers in the row direction may be connected to the left scanning signal line driver, and the scanning signal lines at even numbers may be connected

to the right scanning signal line driver.

[0047] Thus, it is possible to prevent local concentration of heat since the heat is easily transmitted to adjacent pixels as compared to the case wherein display data are supplied to the pixels in one direction from one of the signal line drivers. As a result, it is possible to soak the whole pixel regions of the display apparatus. In the case of (2), it is unnecessary to provide the radiating member of (1).

[0048] Also, an organic EL display apparatus having both of the above-described two soaking units may be created. Thus, the soaking effect is further enhanced to make it possible to further suppress the uneven luminance between the pixel regions.


[0049] The organic function layer 602 may be formed only of the light-emitting layer. Alternatively, for the purpose of achieving high efficiency, the organic function layer 602 may be formed of a plurality of layers such as a carrier blocking layer and an exciton blocking layer that are to be disposed adjacent to the light-emitting layer. For the organic function layer 602 to be used for the organic EL devices, the layer structure for each of the colors is formed by combining layers that are appropriately selected from an electron transport layer, a light-emitting layer, a hole transport layer, a carrier blocking layer, and an exciton blocking layer.

[0050] Each of the organic EL devices of the RGB pixels has any one of the delayed fluorescence material, the phosphorescent material, and the fluorescent material. It is possible to independently select the material to be used for the light emission of each of the colors.

[0051] As the transparent electrode indicated by the lower electrode 607 as the cathode, it is possible to use an oxide conductive film, more specifically, a compound film ITO (Indium Tin Oxide) of indium oxide and tin oxide, an indium oxide/zinc oxide-based amorphous material (Indium Zinc Oxide: IZO), and the like. These are transparent electrodes. As a method for forming the transparent electrode, a sputtering method, a vacuum evaporation method, an ion plating method, or the like may be employed, and the thickness is not particularly limited.


[0052] Examples of the hole transport layer 606 provided on the lower electrode 607 which is indicated as the anode include, for example, α -NPD (Formula 4). The hole transport layer may be a material other than α -NPD. Specific examples of the material include a conductive polymer or the like, such as an arylamine derivative, a carbazole derivative, and a poly(ethylenedioxythiophene) (PEDOT-PSS).

[0053] <Formula 4> α -NOD



[0054] Examples of a host material of the light-emitting layer include, for example, CBP (Formula 5). Other materials may be used without particular limitation insofar as the material has a bandgap that is higher than emission energy of the light-emitting material (guest material) of each of the colors.

[0055] <Formula 5> CBP




CBP

[0056] As the guest material of the light-emitting layer, for each of the organic EL devices other than the organic EL device having the delayed fluorescence material, an organic compound that is appropriate for the emission color may be selected. For example, a phosphorescent material such as Btp₂Ir(acac) (red), Ir(ppy)₃ (green), FIr6 (blue) may be used, or a fluorescent material such as BPPC (red), Bebq₂ (green), DPVBi (blue), and Spiro-TAD may be used.

[0057] As used herein, the host material in the light-emitting layer is the organic compound having a relatively large weight ratio of a plurality of organic compounds forming the light-emitting layer. The organic compound having a relatively small weight ratio is referred to as a guest material.

[0058] Examples of the electron transport layer include BCP (Formula 6) which has an electron-accepting property, but materials other than BCP may be used. For example, it is possible to use Bphen, BAQ, a metal complex of quinolinol derivative, and the like.

[0059] <Formula 6> BCP



[0060] The cathode indicated as the upper electrode 603 is provided on the electron transport layer 604. For the upper electrode, a metal or an alloy having a small work function is used. For example, a metal such as silver, aluminum, and chromium, alloys thereof, and the like are used.

[0061] As described above, in the present embodiment, the anode is the transparent electrode that transmits light, and the cathode is the reflective electrode that reflects light. In the organic EL device according to the present invention, the anode may be the reflective electrode, while the cathode may be the transparent electrode.

[0062] As the protective film 60 to be provided on the upper electrode 603, a ceramic film such as of silicon oxynitride, silicon nitride, and the like may be used. Other materials may be used without particular limitation insofar as the material protects the organic function layer 602 from adverse influences of moisture (water vapor) and oxygen. The thickness thereof is not particularly limited and may preferably be 500 nm or more and 1 μ m or less. In the present embodiment, the radiating member is provided on the protective film. When light is extracted via the protective film, the protective film needs to be transparent.

[0063] (Example 1)

[0064] The present example is an organic EL display apparatus having a structure in which a green organic EL device has a delayed fluorescence material in a light-emitting layer; a red organic light-emitting device and a blue organic light-emitting device have a phosphorescent material in light-emitting layers; and light emitted from the organic EL devices is extracted via a substrate having the organic EL devices.

[0065] As shown in FIGS. 3 and 4, the organic EL display apparatus having the organic EL devices emitting three colors of RGB was produced by a method described below. The organic EL display apparatus had a structure that RGB pixels are arranged in the matrix pattern as shown in FIG. 3.


[0066] A panel which was produced to serve as a pixel region was 42 inches in width across corners, and had 1080 pixels in a vertical direction, 1920 pixels in a horizontal direction, and an aperture ratio of RGB pixels of 40%. The term "aperture ratio" herein employed refers to a ratio of an area occupied by all the pixels to an area of a region in which the pixels are provided. A region which is not occupied by the pixels of the pixel region is a gap region between adjacent pixels.

[0067] On a glass (glass substrate) serving as a support member which is a substrate, TFT drive circuits made from low temperature polysilicon were formed, and a planarizing film made from an acrylic resin was formed on the TFT circuits. On the planarizing film, 120 nm of ITO to be used as a transparent electrode was formed by a sputtering method, followed by patterning to form an anode. Furthermore, a pixel separation film was formed by using an acrylic resin to produce an anode

side transparent electrode substrate. The anode side transparent electrode substrate was subjected to ultrasonic cleaning with isopropyl alcohol (IPA), followed by washing with boiled IPA and drying. After that, UV/O₃ cleaning was performed, and a hole transport layer, organic light-emitting layers corresponding to RGB pixels, an electron transport layer, an electron injection layer, and a cathode material were sequentially formed by vacuum evaporation.

[0068] As the hole transport layer, a film of 24 nm in thickness was formed by performing vacuum evaporation of α -NOD shown in (Formula 4) under the condition of a vacuum degree of 3.0×10^{-5} Pa. After that, the organic light-emitting layers corresponding to RGB pixels were coated on the same substrate by using a mask corresponding to an emission pattern. At that time, for the light-emitting layer for the R pixel, CBP shown in (Formula 5) was used as a host material, and the phosphorescence material Ir(piq)₃ (Formula 7) shown below was used as a guest material. The ratio of the guest material to the host material was set to 5.0 mass% by concentration, and the light-emitting layer of 20 nm in thickness was formed by the co-evaporation method under the condition of a vacuum degree of 3.0×10^{-5} Pa.

[0069] <Formula 7> Phosphorescence material Ir(piq)₃: 5.0 mass%



[0070] The G pixel was formed in the same manner as in the case of the R pixel except for forming the light-emitting-layer by using the delayed fluorescence material (Formula 1) as the guest material and setting the ratio thereof to the host material to 5.0 mass% by concentration. The B pixel was formed in the same manner as in the case of the R pixel except for forming the light-emitting layer by using Flrpic (Formula 8) which is the phosphorescent material as the guest material.

<Formula 8> Phosphorescent Material Flrpic: 5.0 mass%

5

10

15

20

25

30

35

40

45

50

55

55

60

65

70


75

80

85

90

95



10

15

20

25

30

35

40

45

50

55

60

65

70

75

80

85

90

95

100

105

110

115

120

125

130

135

140

145

150

155

160

165

170

175

180

185

190

195

200

205

210

215

220

225

230

235

240

245

250

255

260

265

270

275

280

285

290

295

300

305

310

315

320

325

330

335

340

345

350

355

360

365

370

375

380

385

390

395

400

405

410

415

420

425

430

435

440

445

450

455

460

465

470

475

480

485

490

495

500

505

510

515

520

525

530

535

540

545

550

555

560

565

570

575

580

585

590

595

600

605

610

615

620

625

630

635

640

645

650

655

660

665

670

675

680

685

690

695

700

705

710

715

720

725

730

735

740

745

750

755

760

765

770

775

780

785

790

795

800

805

810

815

820

825

830

835

840

845

850

855

860

865

870

875

880

885

890

895

900

905

910

915

920

925

930

935

940

945

950

955

960

965

970

975

980

985

990

995

1000

1005

1010

1015

1020

1025

1030

1035

1040

1045

1050

1055

1060

1065

1070

1075

1080

1085

1090

1095

1100

1105

1110

1115

1120

1125

1130

1135

1140

1145

1150

1155

1160

1165

1170

1175

1180

1185

1190

1195

1200

1205

1210

1215

1220

1225

1230

1235

1240

1245

1250

1255

1260

1265

1270

1275

1280

1285

1290

1295

1300

1305

1310

1315

1320

1325

1330

1335

1340

1345

1350

1355

1360

1365

1370

1375

1380

1385

1390

1395

1400

1405

1410

1415

in which $TH-TL=30^{\circ}\text{C}$ was measured ($TH=74^{\circ}\text{C}$, $TL=44^{\circ}\text{C}$). Also, as the front surface luminance, 1200 cd/m^2 was measured in TH , and 1060 cd/m^2 was measured in TL .

[0078] (Example 2)

[0079] The present example is an organic EL display apparatus having a structure in which a green organic EL device and a red organic EL device have a delayed fluorescence material in light-emitting layers; and the blue organic light-emitting device has a phosphorescent material in a light-emitting layer; and light emitted from the organic EL devices is extracted outside via a substrate having the organic EL devices. In terms of the organic EL device formation, the organic EL display apparatus was produced by following the same procedure as in Example 1 except for forming the light-emitting layer of the R pixel by using the delayed fluorescence material (Formula 3) as the guest material and setting the ratio of the guest material to the host material to 5.0 mass% by concentration.

[0080] The thus-produced organic EL display apparatus was caused to display continuously under the same conditions as those of Example 1, and then a display apparatus rear side temperature and front surface luminance of each of the pixel regions shown in FIG. 7 were measured. The region 1 was TH , and the region 9 was TL , in which $TH-TL=5^{\circ}\text{C}$ was measured ($TH=43^{\circ}\text{C}$, $TL=38^{\circ}\text{C}$). Also, as the front surface luminance, 1060 cd/m^2 was measured in TH , and 1040 cd/m^2 was measured in TL .

[0081] (Comparative Example 2)

[0082] An organic EL display apparatus was produced by following the same procedure as in Example 2 except for omitting the sheet-like graphite provided above the protective film in the organic EL display apparatus production of Example 2.

[0083] The thus-produced organic EL display apparatus was caused to display continuously under the same conditions as those of Example 1, and then a display apparatus rear side temperature and front surface luminance of each of the pixel regions shown in FIG. 7 were measured. The region 1 was TH , and the region 9 was TL , in which $TH-TL=31^{\circ}\text{C}$ was measured ($TH=78^{\circ}\text{C}$, $TL=47^{\circ}\text{C}$). Also, as the front surface luminance, 1250 cd/m^2 was measured in TH , and 1060 cd/m^2 was measured in TL .

[0084] (Example 3)

[0085] The present example is an organic EL display apparatus having a structure in which a green organic EL device has a delayed fluorescence material in a light-emitting layer; and a red organic light-emitting device and a blue organic light-emitting device have a phosphorescent material in light-emitting layers; and light emitted from the organic EL devices is extracted outside without transmitting a substrate having the organic EL devices.

[0086] The organic EL display apparatus formed of three colors of RGB having the structure shown in FIGS. 3 and 4 was produced by a method described below. The

display apparatus had a structure that RGB pixels are arranged in a matrix pattern as shown in FIG. 3 as is the case in Example 1.

[0087] A panel was so produced as to be 42 inches in width across corners and to have 1080 pixels in a vertical direction, 1920 pixels in a horizontal direction, and an aperture ratio of 70%.

[0088] On a glass substrate serving as a support member, sheet-like graphite serving as the radiating member and having a thickness of 0.5 mm was disposed. TFT drive circuits made from low temperature polysilicon were formed on the sheet-like graphite, and a planarizing film made from an acrylic resin was formed on the TFT drive circuits. Above the planarizing film, a film having a thickness of 100 nm to be used as a reflective electrode was formed by sputtering a silver alloy (AgCuNd) by a sputtering method, followed by patterning, and an anode serving as a lower electrode was formed by forming a film having a thickness of 30 nm by sputtering IZO by a sputtering method, followed by patterning. That is, the radiating member was disposed on a side opposite to a reflective side of the reflective electrode.

[0089] Furthermore, a pixel separation film was formed by using an acrylic resin to produce an anode side electrode substrate. The anode side electrode substrate was subjected to ultrasonic cleaning with IPA, followed by washing with boiled IPA and drying. After that, UV/O_3 cleaning was performed, and organic function layers corresponding to RGB pixels were provided in accordance with the procedure described below.

[0090] The organic function layers corresponding to RGB pixels were differently coated by performing evaporation on the same substrate by using a mask corresponding to an emission pattern. A hole transport layer of 24 nm in thickness was formed by depositing α -NPD shown in (Formula 4) by the vacuum evaporation under the condition of a vacuum degree of $3.0 \times 10^{-5} \text{ Pa}$.

[0091] Subsequently, as the light-emitting layers, different coatings were performed for the light-emitting layers corresponding to the RGB pixels. The combination of the host material and the guest material for each of the colors of the organic EL devices was the same as that of Example 1. The thicknesses of the light-emitting layers were different from those of Example 1. For the R pixel, CBP shown in (Formula 5) was used as the host material, and the delayed fluorescent material shown in (Formula 3) was used as the guest material. The ratio of the guest material to the host material was set to 5.0 vol% by concentration, and the light-emitting layer of 70 nm in thickness was formed by a co-evaporation method under the condition of a vacuum degree of $3.0 \times 10^{-5} \text{ Pa}$. The G pixel was formed by using CBP shown in (Formula 5) as the host material and using the delayed fluorescent material shown in (Formula 1) as the guest material. The ratio of the guest material to the host material was set to 5.0 vol% by concentration, and the light-emitting layer of 65 nm in thickness was formed by a co-evaporation method under the condition of a vacuum degree of $3.0 \times 10^{-5} \text{ Pa}$.

Pa.

[0092] The B pixel was formed by using CBP shown in (Formula 5) as the host material and using the phosphorescent material FIrpic shown in (Formula 8) as the guest material. The ratio of the guest material to the host material was set to 5.0 vol% by concentration, and the light-emitting layer of 40 nm in thickness was formed by a co-evaporation method under the condition of a vacuum degree of 3.0×10^{-5} Pa.

[0093] Next, as the electron transport layer, a film of 10 nm in thickness was formed by depositing BCP (Formula 6) by a vacuum evaporation method under the condition of a vacuum degree of 3.0×10^{-5} Pa. Furthermore, as another electron transport layer, a film of 14 nm in thickness was formed by co-evaporation of BCP and Cs_2CO_3 (weight ratio: 9:1) under the condition of a vacuum degree of 2.0×10^{-4} Pa. As cathode, a film of 15 nm in thickness was formed by depositing silver (Ag) by a vacuum evaporation method under the condition of a vacuum degree of 2.0×10^{-4} Pa. This cathode was used as the transparent electrode. Furthermore, as the protective film, a film of 700 nm in thickness of silicon nitride was formed to perform sealing, thereby obtaining the organic EL display apparatus. In each of the organic EL devices, the reflective electrode is disposed at a position close to the substrate, and the transparent electrode opposed to the reflective electrode is disposed at a position distant from the substrate as compared to the reflective electrode. Light emitted from the light-emitting layers include the light that directly exits through the transparent electrode, and the light that exits after being reflected by the reflective electrode.

[0094] The thus-produced organic EL display apparatus was caused to display continuously under the same conditions as those of Example 1, and then a display apparatus rear side temperature and front surface luminance of each of the pixel regions shown in FIG. 7 were measured.

[0095] The region 1 was TH, and the region 9 was TL, in which $\text{TH-TL}=4^\circ\text{C}$ was measured ($\text{TH}=44^\circ\text{C}$, $\text{TL}=40^\circ\text{C}$). Also, as the front surface luminance, 1070 cd/m^2 was measured in TH, and 1050 cd/m^2 was measured in TL.

[0096] (Comparative Example 3)

[0097] An organic EL display apparatus was produced by following the same procedure as in Example 3 except for omitting the sheet-like graphite in the organic EL display apparatus production of Example 3.

[0098] The thus-produced organic EL display apparatus was caused to display continuously under the same conditions as those of Example 1, and then a display apparatus rear side temperature and front surface luminance of each of the pixel regions shown in FIG. 7 were measured. The region 1 was TH, and the region 9 was TL, in which $\text{TH-TL}=31^\circ\text{C}$ was measured ($\text{TH}=77^\circ\text{C}$, $\text{TL}=46^\circ\text{C}$). Also, as the front surface luminance, 1240 cd/m^2 was measured in TH, and 1070 cd/m^2 was measured in TL.

[0099] (Example 4)

[0100] An organic EL display apparatus was produced by following the same procedure as in Example 3 except for providing sheet-like graphite having a thickness of 0.5 mm on each of both sides of the glass substrate serving as the support.

[0101] The thus-produced organic EL display apparatus was caused to display continuously under the same conditions as those of Example 1, and then a display apparatus rear side temperature and front surface luminance of each of the pixel regions shown in FIG. 7 were measured.

[0102] The region 1 was TH, and the region 9 was TL, in which $\text{TH-TL}=2^\circ\text{C}$ was measured ($\text{TH}=38^\circ\text{C}$, $\text{TL}=36^\circ\text{C}$). Also, as the front surface luminance, 1030 cd/m^2 was measured in TH, and 1020 cd/m^2 was measured in TL. Therefore, it was confirmed that uneven luminance due to the temperature difference between pixel regions was suppressed as compared to Example 3.

[0103] (Example 5)

[0104] An organic EL display apparatus was produced by following the same procedure as in Example 4 except for providing a copper plate having a thickness of 3 mm at a part corresponding to the pixel regions 1, 4, and 7 of FIG. 7 on a side from which the light does not exit.

[0105] The thus-produced organic EL display apparatus was caused to display continuously under the same conditions as those of Example 1, and then a display apparatus rear side temperature and front surface luminance of each of the pixel regions shown in FIG. 7 were measured.

[0106] The region 1 was TH, and the region 9 was TL, in which $\text{TH-TL}=1^\circ\text{C}$ was measured ($\text{TH}=37^\circ\text{C}$, $\text{TL}=36^\circ\text{C}$). Also, as the front surface luminance, 1025 cd/m^2 was measured in TH, and 1020 cd/m^2 was measured in TL. Therefore, it was confirmed that uneven luminance due to the temperature difference between pixel regions was suppressed as compared to Example 4.

[0107] (Example 6)

[0108] The present example has a structure in which light is extracted without transmitting a substrate. Radiating members were provided at both sides of the substrate, and the wiring was arranged as shown in FIG. 8. The RGB pixel arrangement, panel size, number of pixels in the display apparatus, and the aperture ratio of RGB pixels were the same as those of Example 4.

[0109] In the case of connecting the wiring pattern to the display apparatus in which the data signal line drivers are disposed both of upper and lower ends as shown in FIG. 8, the data signal lines of odd numbers were connected to the upper data signal line driver, and the data signal lines of even numbers were connected to the lower data signal line drivers.

[0110] The thus-produced organic EL display apparatus was caused to display continuously under the same conditions as those of Example 1, and then a display apparatus rear side temperature and front surface luminance of each of the pixel regions (same as the regions

1 to 9 shown in FIG. 7) were measured.

[0111] The region 1 was TH, and the region 9 was TL, in which $TH-TL=2^{\circ}\text{C}$ was measured ($TH=43^{\circ}\text{C}$, $TL=41^{\circ}\text{C}$). Also, as the front surface luminance, 1060 cd/m^2 was measured in TH, and 1055 cd/m^2 was measured in TL.

[0112] While the present invention has been described with reference to exemplary embodiments and examples useful for understanding the invention, it is to be understood that the invention is not limited to the disclosed exemplary embodiments, but only limited to the scope of the following claims.

Provided is an organic EL display apparatus including an organic EL device having a delayed fluorescence material which has good internal quantum efficiency and an organic EL device having a phosphorescent material. A soaking unit is provided in a plane in which the organic EL devices are provided.

Claims

1. An organic EL display apparatus comprising:

a plurality of pixels arranged in columns in an array on a substrate,

the plurality of pixels including a red-light-emitting pixel, a green-light-emitting pixel, and a blue-light-emitting pixel, and the red-light-emitting pixel, the green-light-emitting pixel, and the blue-light-emitting pixel having a red organic EL device, a green organic EL device, and a blue organic EL device, respectively,

each of the red organic EL device, the green organic EL device, and the blue organic EL device having a reflective electrode (603), a transparent electrode (607) opposed to the reflective electrode, and a light-emitting layer (605) disposed between the reflective electrode and the transparent electrode, and.

the reflective electrode in each of the red organic EL device, the green organic EL device, and the blue organic EL device being disposed distant from or close to the substrate as compared to the transparent electrode,

characterized in that

at least one of the red organic EL device, the green organic EL device, and the blue organic EL device has a thermal excitation-type delayed fluorescence material in the light-emitting layer; at least one of the other devices has a phosphorescence material in the light-emitting layer; the organic display apparatus comprises an upper data signal line driver at an upper edge of the array and a lower data signal line driver at a lower edge of the array;

each of the pixels is electrically connected to one of the upper data signal line driver and the

lower data signal line driver; and

if a first pixel in a first column of the pixels is connected to the upper, data signal line driver, a second pixel in a second column of the pixels neighbored to the first column is connected to the lower data signal line driver.

2. The organic EL display apparatus according to claim 1, wherein

the plurality of pixels is arranged in rows in the array; the organic display apparatus comprises a left scanning signal line driver at a left edge of the array and a right scanning signal line driver at a right edge of the array;

each of the pixels is electrically connected to one of the left scanning signal line driver and the right scanning signal line driver; and

if a third pixel in a first row of the pixels is connected to the left scanning signal line driver, a fourth pixel in a second row of the pixels neighbored to the first row is connected to the right scanning signal line driver.

Patentansprüche

1. Organische EL-Anzeigevorrichtung mit einer Vielzahl von Pixeln, die in Spalten in einer Anordnung auf einem Substrat angeordnet sind, wobei die Vielzahl von Pixeln einen rotes Licht emittierenden Pixel, einen grünes Licht emittierenden Pixel und einen blauen Licht emittierenden Pixel aufweist und der rotes Licht emittierende Pixel, der grünes Licht emittierende Pixel und der blaues Licht emittierende Pixel eine rote organische EL-Einrichtung, eine grüne organische EL-Einrichtung bzw. eine blaue organische EL-Einrichtung haben, jede der roten organischen EL-Einrichtung, der grünen organischen EL-Einrichtung und der blauen organischen EL-Einrichtung eine reflektierende Elektrode (603), eine transparente Elektrode (607), die der reflektierenden Elektrode gegenüber angeordnet ist, und eine lichtemittierende Schicht (605), die zwischen der reflektierenden Elektrode und der transparenten Elektrode angeordnet ist, aufweist, und

die reflektierende Elektrode in jeder der roten organischen EL-Einrichtung, der grünen organischen EL-Einrichtung und der blauen organischen EL-Einrichtung verglichen mit der transparenten Elektrode entfernt von oder nahe an dem Substrat ist,

dadurch gekennzeichnet, dass

zumindest eine der roten organischen EL-Einrichtung, der grünen organischen EL-Einrichtung und der blauen organischen EL-Einrichtung ein Fluoreszenzmaterial eines verzögerten thermischen Anregungstyps in der lichtemittierenden Schicht hat; zumindest eine der anderen Einrichtungen ein Phos-

phoreszenzmaterial in der lichtemittierenden Schicht hat; die organische Anzeigevorrichtung eine obere Datensignaltreiberleitung an einer oberen Kante der Anordnung und eine untere Datensignaltreiberleitung an einer unteren Kante der Anordnung aufweist; jeder der Pixel elektrisch mit einer der oberen Datensignaltreiberleitung und der unteren Datensignaltreiberleitung verbunden ist; und wenn ein erster Pixel in einer ersten Spalte der Pixel mit der oberen Datensignaltreiberleitung verbunden ist, ist ein zweiter Pixel in einer zweiten Spalte der Pixel, die der ersten Spalte benachbart ist, mit der unteren Datensignaltreiberleitung verbunden.

5

10

15

2. Organische EL-Anzeigevorrichtung nach Anspruch 1, wobei die Vielzahl von Pixeln in Zeilen in der Anordnung angeordnet ist; die organische Anzeigevorrichtung eine linke Abtastsignaltreiberleitung an einer linken Kante der Anordnung und eine rechte Abtastsignaltreiberleitung an einer rechten Kante der Anordnung aufweist; jeder der Pixel elektrisch mit einer der linken Abtastsignaltreiberleitung und der rechten Abtastsignaltreiberleitung verbunden ist; und wenn ein dritter Pixel in einer ersten Zeile der Pixel mit der linken Abtastsignaltreiberleitung verbunden ist, ist ein vierter Pixel in einer zweiten Zeile der Pixel, die benachbart zu der ersten Zeile ist, mit der rechten Abtastsignaltreiberleitung verbunden.

20

25

30

Revendications

1. Appareil électroluminescent (EL) organique d'affichage comprenant :

une pluralité de pixels disposés en colonnes dans un réseau sur un substrat, la pluralité de pixels comprenant un pixel émettant de la lumière rouge, un pixel émettant de la lumière verte et un pixel émettant de la lumière bleue, et le pixel émettant de la lumière rouge, le pixel émettant de la lumière verte et le pixel émettant de la lumière bleue comprenant un dispositif EL organique rouge, un dispositif EL organique vert et un dispositif EL organique bleu, respectivement, chacun du dispositif EL organique rouge, du dispositif EL organique vert et du dispositif EL organique bleu comprenant une électrode réfléchissante (603), une électrode transparente (607) à l'opposé de l'électrode réfléchissante et une couche photoémettrice (605) disposée entre l'électrode réfléchissante et l'électrode transparente, et l'électrode réfléchissante dans chacun du dis-

positif EL organique rouge, du dispositif EL organique vert et du dispositif EL organique bleu étant disposée à distance ou à proximité du substrat, comparativement à l'électrode transparente,

caractérisé en ce que

au moins un dispositif EL organique rouge, du dispositif EL organique vert et du dispositif EL organique bleu comporte une matière à fluorescence retardée du type à excitation thermique dans la couche photoémettrice ; au moins un des autres dispositifs comporte une matière phosphorescente dans la couche photoémettrice ; l'appareil d'affichage organique comprend un circuit supérieur d'attaque de ligne de signaux de données à un bord supérieur du réseau et un circuit inférieur d'attaque de ligne de signaux de données à un bord inférieur du réseau ; chacun des pixels est connecté électriquement à un du circuit supérieur d'attaque de ligne de signaux de données et du circuit inférieur d'attaque de ligne de signaux de données ; et si un premier pixel dans une première colonne des pixels est connecté au circuit supérieur d'attaque de ligne de signaux de données, un second pixel dans une seconde colonne des pixels proche de la première colonne est connecté au circuit inférieur d'attaque de ligne de signaux de données.

2. Appareil d'affichage EL organique suivant la revendication 1, dans lequel

la pluralité de pixels est disposée en rangées dans le réseau ;

l'appareil organique d'affichage comprend un circuit gauche d'attaque de lignes de signaux de balayage à un bord gauche du réseau et un circuit droit d'attaque de lignes de signaux de balayage à un bord droit du réseau ;

chacun des pixels est connecté électriquement à un du circuit gauche d'attaque de lignes de signaux de balayage et du circuit droit d'attaque de lignes de signaux de balayage ; et

si un troisième pixel dans une première rangée des pixels est connecté au circuit gauche d'attaque de lignes de signaux de balayage, un quatrième pixel dans une seconde rangée des pixels proche de la première rangée est connecté au circuit droit d'attaque de lignes de signaux de balayage.

35

40

45

50

55

55

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

MATERIAL	THERMAL CONDUCTIVITY [W/(m·K)]
GRAPHITE	800
SILVER	422
COPPER	395
ALUMINIUM	240

FIG. 6




FIG. 7





FIG. 8



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2004241374 A [0007] [0008]
- EP 1862524 A1 [0009]
- US 20060207649 A1 [0009]
- WO 2005054404 A1 [0009]
- US 20030034722 A1 [0009]

Non-patent literature cited in the description

- IUPAC Compendium of Chemical Terminology. 1997 [0009]
- GIEBINK N. C. et al. *Organic Electronics*, 2006, vol. 7, 375-386 [0009]
- AKIRA TSUBOYAMA et al. *Inorganic Chemistry*, 2007, vol. 46 (6), 1992-2001 [0009]

专利名称(译)	有机EL显示装置		
公开(公告)号	EP2175490B1	公开(公告)日	2014-03-26
申请号	EP2009172511	申请日	2009-10-08
[标]申请(专利权)人(译)	佳能株式会社		
申请(专利权)人(译)	佳能株式会社		
当前申请(专利权)人(译)	佳能株式会社		
[标]发明人	MORI TOSHIKUMI SUZUKI KOICHI TSUBOYAMA AKIRA SHIOBARA SATORU IKARI KENICHI		
发明人	MORI, TOSHIKUMI SUZUKI, KOICHI TSUBOYAMA, AKIRA SHIOBARA, SATORU IKARI, KENICHI		
IPC分类号	H01L27/32 H01L51/50 H01L51/52 H01L51/00		
CPC分类号	H01L51/529 H01L27/3211 H01L51/0085 H01L51/009 H01L51/0091 H01L51/5012 H01L51/5016		
代理机构(译)	TBK		
优先权	2008264193 2008-10-10 JP 2009222634 2009-09-28 JP		
其他公开文献	EP2175490A3 EP2175490A2		
外部链接	Espacenet		

摘要(译)

本发明提供一种有机EL显示装置，其包括具有延迟荧光材料的有机EL器件和具有磷光材料的有机EL器件，所述有机EL器件具有良好的内量子效率。浸泡单元设置在其中设置有机EL器件的平面中。

