



(11) **EP 3 647 392 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 153(4) EPC

(43) Date of publication:
06.05.2020 Bulletin 2020/19

(21) Application number: **18824986.6**

(22) Date of filing: **27.06.2018**

(51) Int Cl.:
C09K 11/06 ^(2006.01) **C07C 255/58** ^(2006.01)
C07D 209/88 ^(2006.01) **C07D 405/14** ^(2006.01)
H01L 51/50 ^(2006.01)

(86) International application number:
PCT/JP2018/024302

(87) International publication number:
WO 2019/004254 (03.01.2019 Gazette 2019/01)

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
KH MA MD TN

(30) Priority: **27.06.2017 JP 2017124947**
15.06.2018 JP 2018114758

(71) Applicant: **Kyulux, Inc.**
Fukuoka-shi, Fukuoka 819-0388 (JP)

(72) Inventors:
• **NOTSUKA Naoto**
Fukuoka-shi
Fukuoka 819-0388 (JP)
• **YANG YuSeok**
Fukuoka-shi
Fukuoka 819-0388 (JP)
• **YOSHIZAKI Asuka**
Fukuoka-shi
Fukuoka 819-0388 (JP)

(74) Representative: **Zimmermann & Partner**
Patentanwälte mbB
Postfach 330 920
80069 München (DE)

(54) **LIGHT-EMITTING MATERIAL, COMPOUND, LONG-PERSISTENT PHOSPHOR AND LIGHT-EMITTING ELEMENT**

(57) A compound represented by the following general formula is an excellent light-emitting material. R¹ to R⁵ each independently represent a hydrogen atom or a substituent, and one of R¹ to R⁵ is a cyano group, one

to three of R¹ to R⁵ each are an aryl group Ar optionally substituted with an alkyl group or an aryl group, and one to three of R¹ to R⁵ each are a donor group D (but excepting one that corresponds to Ar).

EP 3 647 392 A1

Description

Technical Field


5 **[0001]** The present invention relates to a compound useful as a light-emitting material and to a light-emitting device using the compound. The invention also relates to a delayed fluorescent material that emits delayed fluorescence.

Background Art

10 **[0002]** Studies for enhancing the light emission efficiency of organic light-emitting devices such as organic electroluminescent devices (organic EL devices) are being made actively. In particular, various kinds of efforts have been made for increasing light emission efficiency by newly developing and combining an electron transfer material, a hole transfer material, a light-emitting material and others to constitute an organic electroluminescent device. Among them, there is known a study relating to an organic electroluminescent device that utilizes a delayed fluorescent material.

15 **[0003]** A delayed fluorescent material is a compound which, in an excited state, after having undergone reverse intersystem crossing from an excited triplet state to an excited singlet state, emits fluorescence when returning back from the excited singlet state to a ground state thereof. Fluorescence through the route is observed later than fluorescence from the excited singlet state directly occurring from the ground state (ordinary fluorescence), and is therefore referred to as delayed fluorescence. Here, for example, in the case where a light-emitting compound is excited through carrier injection thereinto, the occurring probability of the excited singlet state to the excited triplet state is statistically 25%/75%, and therefore improvement of light emission efficiency by the fluorescence alone from the directly occurring excited singlet state is limited. On the other hand, in a delayed fluorescent material, not only the excited singlet state thereof but also the excited triplet state can be utilized for fluorescent emission through the route via the above-mentioned reverse intersystem crossing, and therefore as compared with an ordinary fluorescent material, a delayed fluorescent material can realize a higher emission efficiency.

20 **[0004]** After such principles have been revealed, various delayed fluorescent materials have been invented by various studies. However, any and all materials capable of emitting delayed fluorescence could not be directly said to be useful as a light-emitting material. Among delayed fluorescent materials, some could relatively hardly undergo reverse intersystem crossing, and some others may have a long delayed fluorescence lifetime. Further, still some others may suffer from emission efficiency reduction owing to accumulation of excitons in a high-current density region, and may therefore rapidly degrade in continuous long-term driving. Accordingly, in fact, most delayed fluorescent materials are still desired to be further improved in point of practical use thereof. Consequently, even cyanobenzene derivatives known as a delayed fluorescent material are pointed out to have problems to be solved. For example, 2CzPN having the following structure is a material that emits delayed fluorescence, but has a problem in that its emission efficiency is not high and the emission efficiency thereof in a high-current density region is great (see NPL 1).



Citation List

50 Non-Patent Literature

[0005] NPL 1: Organic Electronics 14 (2013)2721-2726

Summary of Invention

55

Technical Problem

[0006] Though delayed fluorescent materials are pointed out to have such problems, the relation between chemical

structures of delayed fluorescent materials and properties thereof could not be said to have been sufficiently clarified. Consequently, at present, it is difficult to generalize the chemical structure of a compound useful as a light emitting material, and there are many unclear points.


[0007] Given the situation, the present inventors have made assiduous studies for the purpose of providing a compound more useful as a light-emitting material for light-emitting devices. With that, the present inventors have further made assiduous studies for the purpose of deriving a general formula of a compound more useful as a light-emitting material and generalizing such a compound.

Solution to Problem

[0008] As a result of assiduous studies made for the purpose of attaining the above-mentioned object, the present inventors have found that a compound a dicyanobenzene derivative substituted with a donor group and further substituted with a specific aryl group is useful as a material for light-emitting devices. The present invention has been proposed on the basis of such findings, and specifically has the following constitution.

[1] A light-emitting material containing a compound represented by the following general formula (1):

General Formula (1)



In the general formula (1), R^1 to R^5 each independently represent a hydrogen atom or a substituent; one of R^1 to R^5 is a cyano group,

one to three of R^1 to R^5 each are an aryl group Ar optionally substituted with an alkyl group or an aryl group (in which the benzene ring to constitute the aryl group Ar may be condensed with a ring that may optionally contain an oxygen atom or a sulfur atom in addition to carbon atoms as a ring skeleton-constituting atom, but is not condensed with a ring containing any other hetero atom than an oxygen atom and a sulfur atom as a ring skeleton-constituting atom), and when two or more of R^1 to R^5 are Ar's, these Ar's may be the same as or different from each other,


one to three of R^1 to R^5 each are a donor group D (but excepting one that corresponds to Ar), and when two or more of R^1 to R^5 are D's, these D's may be the same as or different from each other.

[2] The light-emitting material according to [1], wherein R^1 to R^5 each independently represent a cyano group, Ar or D.

[3] The light-emitting material according to [1] or [2], wherein D contains a substituted amino group.

[4] The light-emitting material according to [3], wherein D is a group represented by the following general formula (2a):

General Formula (2a)




In the general formula (2a), R^{11} and R^{12} each independently represent a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, or a substituted or unsubstituted

tuted heteroaryl group; L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; * indicates a bonding position to the carbon atom (C) constituting a ring skeleton of the benzene ring in the general formula (1); and R¹¹ and R¹² may bond to each other to form a cyclic structure.
 [5] The light-emitting material according to [3], wherein D is a group represented by the following general formula (2b):

5

General Formula (2b)

10



15

20

In the general formula (2b), R²¹ to R²⁸ each independently represent a hydrogen atom or a substituent; L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; R²¹ and R²², R²² and R²³, R²³ and R²⁴, R²⁴ and R²⁵, R²⁶ and R²⁷, and R²⁷ and R²⁸ each may bond to each other to form a linking group necessary for forming a cyclic structure; and R²⁵ and R²⁶ may bond to each other to form a single bond or a linking group.


25

[6] The light-emitting material according to [3], wherein D is a group represented by the following general formula (2c):

30

General Formula (2c)

35



40

45

In the general formula (2c), R³¹ to R⁴⁰ each independently represent a hydrogen atom or a substituent; L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; R³¹ and R³², R³² and R³³, R³³ and R³⁴, R³⁴ and R³⁵, R³⁶ and R³⁷, R³⁷ and R³⁸, R³⁸ and R³⁹, and R³⁹ and R⁴⁰ each may bond to each other to form a linking group necessary for forming a cyclic structure; and R³⁵ and R³⁶ may bond to each other to form a single bond or a linking group; and * indicates a bonding position to the carbon atom (C) constituting the ring skeleton of the benzene ring in the general formula (1).

50

[7] The light-emitting material according to any one of [4] to [6], wherein L is a single bond.


[8] The light-emitting material according to any one of [4] to [6], wherein R³ is a cyano group, and L is a substituted or unsubstituted phenylene group.

55

[9] The light-emitting material according to any one of [4] to [8], wherein D is a group represented by any of the following general formulae (3) to (6):

General Formula (3)

5




10

15

General Formula (4)

20




25

30

General Formula (5)

35




40

45

50

55

General Formula (6)



20 In the general formulae (3) to (6), R^{41} to R^{46} , R^{51} to R^{60} , R^{61} to R^{68} , and R^{71} to R^{78} each independently represent a hydrogen atom or a substituent; L^{11} to L^{14} each independently represent a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group. In the general formula (6), X represents an oxygen atom, a sulfur atom, a substituted or unsubstituted nitrogen atom, a substituted or unsubstituted carbon atom, a substituted or unsubstituted silicon atom or a carbonyl group, which is divalent and which has a linking chain length of one atom, or represents a substituted or unsubstituted ethylene group, a substituted or unsubstituted vinylene group, a substituted or unsubstituted o-arylene group or a substituted or unsubstituted o-heteroarylene group, which is divalent and which has a bonding chain length of two atoms.

25 [10] A compound represented by the general formula (1).

[11] A delayed fluorescent material containing a compound represented by the general formula (1).

[12] A light-emitting device containing a compound represented by the general formula (1).

[13] The light-emitting device according to [12], which emits delayed fluorescence.

30 [14] The light-emitting device according to [12] or [13], wherein the light-emitting device has a light-emitting layer and the light emitting layer contains the compound and a host material.

[15] The light-emitting device according to any one of [12] to [14], wherein the light-emitting device has a light-emitting layer and the light-emitting layer contains the compound and a light-emitting material.

Advantageous Effects of Invention

35 **[0009]** The compound of the present invention is useful as a light-emitting material. The compound of the present invention includes compounds capable of emitting delayed fluorescence and capable of effectively utilizing the excited triplet energy thereof for light emission. Accordingly, an organic light-emitting device using the compound of the present invention as a light-emitting material therein can realize high emission efficiency.

Brief Description of Drawings

[0010]

45 [Fig. 1] This is a schematic cross-sectional view showing a layer configuration example of an organic electroluminescent device.

[Fig. 2] This shows a fluorescence spectrum and a phosphorescence spectrum of a compound 6-1 of the invention of Example 1.

[Fig. 3] This is a transient decay curve of a thin film of a compound 6-1 alone of the invention of Example 1.

50 [Fig. 4] This is a transient decay curve of a doped thin film with a compound 6-1 of the invention of Example 2.

[Fig. 5] This is a transient decay curve of a doped thin film with a comparative compound 6-1 of Comparative Example 2.

Description of Embodiments


55 **[0011]** The contents of the invention will be described in detail below. The constitutional elements may be described below with reference to representative embodiments and specific examples of the invention, but the invention is not limited to the embodiments and the examples. In the description herein, a numerical range expressed as "to" means a

range that includes the upper limit and/or the lower limit. In the invention, the hydrogen atom that is present in the compound used in the invention is not particularly limited in isotope species, and for example, all the hydrogen atoms in the molecule may be ^1H , and all or a part of them may be ^2H (deuterium (D)). The matters described in Japanese Patent Application 2018-114758, especially Tables 1 to 5 in the specification of the patent application are incorporated herein by reference.

[Compound represented by General Formula (1)]

[0012]

General Formula (1)



[0013] In the general formula (1), R¹ to R⁵ each represent a hydrogen atom or a substituent.

[0014] One alone of R¹ to R³ is a cyano group. The substituent that represents a cyano group may be R¹, or R², or R³.

[0015] One to three of R¹ to R⁵ in the general formula (1) each are an aryl group Ar optionally substituted with an alkyl group or an aryl group. Among R¹ to R⁵, the number of the substituents each representing an aryl group Ar may be one to three, but is preferably one or two. The benzene ring that has a bond of Ar may be a single ring or a part of a condensed ring. In the case where a ring is further condensed with a benzene ring, the condensed ring may be a ring composed of carbon atoms alone as the ring skeleton-constituting atoms, or may contain an oxygen atom or a sulfur atom as a ring skeleton-constituting atom. However, in the case where a ring is further condensed with a benzene ring, the condensed ring is not a ring that contains any other hetero atom than an oxygen atom and a sulfur atom as a ring skeleton-constituting atom. Examples of the ring that may be condensed with a benzene ring having a bond of Ar include a benzene ring, a furan ring, a thiophene ring, a cyclopentene ring, a cyclopentadiene ring, a cyclohexene ring, a cyclohexadiene ring, a cycloheptene ring, a cycloheptadiene ring, and a cycloheptatriene ring. The benzene ring having a bond of Ar may be condensed with one ring, or may be condensed with two or more rings. A ring may be further condensed with the ring condensed with the benzene ring having a bond of Ar. Even in such a case where multiple rings are condensed, the resultant condensed ring is a ring where ring skeleton-constituting atoms are carbon atoms alone or is a ring that contains an oxygen atom or a sulfur atom as a ring skeleton-constituting atom. In the case where two or more rings are condensed, these two or more rings may be the same as or different from each other.

[0016] The benzene ring having a bond of Ar or the condensed ring containing the benzene ring as a part thereof may be substituted with at least one substituent of an alkyl group and an aryl group. The substituent as referred to herein means a monovalent group capable of substituting for a hydrogen atom, and is not a concept to include condensation.

[0017] The "alkyl group" to be a substituent as referred to herein may be any of a linear, branched or cyclic one. The group may have two or more kinds of a linear moiety, a cyclic moiety and a branched moiety as combined. The carbon number of the alkyl group may be, for example, 1 or more, 2 or more, or 4 or more. The carbon number may be 30 or less, 20 or less, 10 or less, 6 or less, or 4 or less. Specific examples of the alkyl group include a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, an n-hexyl group, an isohexyl group, a 2-ethylhexyl group, an n-heptyl group, an isoheptyl group, an n-octyl group, an isooctyl group, an n-nonyl group, an isononyl group, an n-decanyl group, an isodecanyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The alkyl group to be a substituent may be further substituted with an aryl group.

[0018] The "aryl group" to be a substituent as referred to herein may be a group composed of one aromatic hydrocarbon ring alone, or may be a group of an aromatic hydrocarbon ring further condensed with one or more rings. The group of an aromatic hydrocarbon ring further condensed with one or more rings for use herein may be a group of an aromatic hydrocarbon ring further condensed with one or more of an aromatic hydrocarbon ring, an aliphatic hydrocarbon ring and a non-aromatic heterocyclic ring. The carbon number of the aryl group may be, for example, 6 or more, or 10 or



more. The carbon number may be 30 or less, 18 or less, 14 or less, or 10 or less. Specific examples of the aryl group include a phenyl group, a 1-naphthyl group, a 2-naphthyl group, a 1-anthracenyl group, a 2-anthracenyl group, and a 9-anthracenyl group. The aryl group to be a substituent may be further substituted with an alkyl group and an aryl group.

[0019] In the case where the benzene ring having a bond of Ar has a substituent, the substitution position of the substituent is preferably any of 3- to 5-positions. For example, preferred examples include a case having a substituent at the 3-position, a case having a substituent at the 4-position, a case having a substituent at the 3-position and the 5-position, and a case having a substituent at the 3-position, the 4-position and the 5-position.


[0020] The total carbon number of the group represented by Ar is preferably 6 to 50, more preferably 6 to 30, even more preferably 6 to 18, and further more preferably 6 to 12.

[0021] A preferred group of Ar includes a phenyl group, a phenyl group substituted with an alkyl group, a phenyl group substituted with a phenyl group, a phenyl group substituted with an alkyl group and a phenyl group, a naphthyl group, a naphthyl group substituted with an alkyl group, a naphthyl group substituted with a phenyl group, a naphthyl group substituted with an alkyl group and a phenyl group, a dibenzofuryl group, a dibenzofuryl group substituted with an alkyl group, a dibenzofuryl group substituted with an alkyl group and a phenyl group, a dibenzothiophenyl group, a dibenzothiophenyl group substituted with an alkyl group, a dibenzothiophenyl group substituted with an alkyl group and a phenyl group, a fluorenyl group, a fluorenyl group substituted with an alkyl group, a fluorenyl group substituted with a phenyl group, and a fluorenyl group substituted with an alkyl group and a phenyl group. Another preferred group of Ar includes a phenyl group, a monoalkylphenyl group, a dialkylphenyl group, a trialkylphenyl group, a tetraalkylphenyl group, a pentaalkylphenyl group, a monophenylphenyl group, a diphenylphenyl group, a naphthyl group, a monoalkylnaphthyl group, a dialkylnaphthyl group, a trialkylnaphthyl group, a tetraalkylnaphthyl group, a pentaalkylnaphthyl group, a monophenylnaphthyl group, a dibenzofuryl group, a monoalkyldibenzofuryl group, a dialkyldibenzofuryl group, trialkyldibenzofuryl group, a tetraalkyldibenzofuryl group, a pentaalkyldibenzofuryl group, a monophenyldibenzofuryl group, a dibenzothiophenyl group, a monoalkyldibenzothiophenyl group, a dialkyldibenzothiophenyl group, a trialkyldibenzothiophenyl group, a tetraalkyldibenzothiophenyl group, a pentaalkyldibenzothiophenyl group, a monophenylalkyldibenzothiophenyl group, a monoalkylfluorenyl group, a dialkylfluorenyl group, a trialkylfluorenyl group, a tetraalkylfluorenyl group, an octaalkylfluorenyl group, a monophenylfluorenyl group, a diphenylfluorenyl group, a triphenylfluorenyl group, and a tetraphenylfluorenyl group.


[0022] Specific examples of the group represented by Ar are mentioned below, but Ar that can be employed in the present invention should not be limitatively interpreted by these specific examples.




5



Ar 9




Ar 10




Ar 11


10



Ar 12




Ar 13




Ar 14

15


20



Ar 15




Ar 16




Ar 17

25


30



Ar 18




Ar 19




Ar 20

35


40



Ar 21




Ar 22




Ar 23

45


50



Ar 24




Ar 25



Ar 26

55



[0023] In the general formula (1), one to three of R¹ to R⁵ each represent a donor group D. However, the donor group D does not include one that corresponds to Ar.

[0024] The "donor group" as referred to in this description is a group having a negative Hammett's σ_p value. Here, "Hammett's σ_p value" is one propounded by L. P. Hammett, and is one to quantify the influence of a substituent on the reaction rate or the equilibrium of a para-substituted benzene derivative. Specifically, the value is a constant (σ_p) peculiar to the substituent in the following equation that is established between a substituent and a reaction rate constant or an equilibrium constant in a para-substituted benzene derivative:

$$\log(k/k_0) = \rho\sigma_p$$

or

$$\log(K/K_0) = \rho\sigma_p$$

[0025] In the above equations, k represents a rate constant of a benzene derivative not having a substituent; k₀ represents a rate constant of a benzene derivative substituted with a substituent; K represents an equilibrium constant of a benzene derivative not having a substituent; K₀ represents an equilibrium constant of a benzene derivative substituted with a substituent; ρ represents a reaction constant to be determined by the kind and the condition of reaction. Regarding the description relating to the "Hammett's σ_p value" and the numerical value of each substituent, reference may be made to the description relating to σ_p value in Hansch, C. et. al., Chem. Rev., 91, 165-195 (1991). A group having a negative Hammett's σ_p value tends to exhibit electron-donating performance (donor-like performance) and a group having a positive Hammett's σ_p value tends to exhibit electron-accepting performance (acceptor-like performance).

[0026] In the general formula (1), D is preferably a group containing a substituted amino group. The substituent that

bonds to the nitrogen atom of the amino group is preferably a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, or a substituted or unsubstituted heteroaryl group, and is more preferably a substituted or unsubstituted aryl group, or a substituted or unsubstituted heteroaryl group. In particular, the substituent is preferably a substituted or unsubstituted diarylamino group, or a substituted or unsubstituted diheteroaryl amino group. In the general formula (1), D may be a group bonding at the nitrogen atom of a substituted amino group, or may also be a group bonding at a group to which a substituted amino group bonds. The group to which a substituted amino group bonds is preferably a π -conjugated group.


[0027] Here, for the "alkyl group" to be a substituent, reference may be made to the corresponding description of the alkyl group to be a substituent for Ar in the general formula (1).

[0028] Here, the "alkenyl group" to be a substituent may be any of a linear, branched or cyclic one. The group may have two or more kinds of a linear moiety, a cyclic moiety and a branched moiety as combined. The carbon number of the alkenyl group may be, for example, 2 or more, or 4 or more. The carbon number may be 30 or less, 20 or less, 10 or less, 6 or less, or 4 or less. Specific examples of the alkenyl group include an ethenyl group, an n-propenyl group, an isopropenyl group, an n-butenyl group, an isobutenyl group, an n-pentenyl group, an isopentenyl group, an n-hexenyl group, an isohexenyl group, and a 2-ethylhexenyl group. The alkenyl group to be a substituent may be further substituted with a substituent.

[0029] The "aryl group" and the "heteroaryl group" to substituents as referred to herein each may be a single ring or may be a condensed ring of two or more rings condensed with each other. In the case of a condensed ring, the number of condensed rings is preferably selected from 2 to 6, more preferably 2 to 4. Specific examples of the ring include a benzene ring, a pyridine ring, a pyrimidine ring, a triazine ring, a naphthalene ring, an anthracene ring, a phenanthrene ring, a triphenylene ring, a quinoline ring, a pyrazine ring, a quinoxaline ring, and a naphthyridine ring. Specific examples of the arylene group and the heteroarylene group include a phenyl group, a 1-naphthyl group, a 2-naphthyl group, a 1-anthracenyl group, a 2-anthracenyl group, a 9-anthracenyl group, a 2-pyridyl group, a 3-pyridyl group, and a 4-pyridyl group. The arylene group and the heteroarylene group each may have a substituent or may be unsubstituted. In the case where the group has 2 or more substituents, the multiple substituents may be the same as or different from each other. The substituent includes a hydroxy group, a halogen atom, an alkyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an alkylthio group having 1 to 20 carbon atoms, an alkyl-substituted amino group having 1 to 20 carbon atoms, an aryl-substituted amino group having 1 to 26 carbon atoms, an aryl group having 6 to 40 carbon atoms, a heteroaryl group having 3 to 40 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, an alkynyl group having 2 to 10 carbon atoms, an alkylamide group having 2 to 20 carbon atoms, an arylamide group having 7 to 21 carbon atoms, and a trialkylsilyl group having 3 to 20 carbon atoms. Of these specific examples, those further substitutable with any substituent may be substituted. More preferred substituents include an alkyl group having 1 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an alkylthio group having 1 to 20 carbon atoms, an alkyl-substituted amino group having 1 to 26 carbon atoms, an aryl-substituted amino group having 1 to 20 carbon atoms, an aryl group having 6 to 40 carbon atoms, and a heteroaryl group having 3 to 40 carbon atoms.

[0030] The donor group D in the general formula (1) is, for example, preferably a group represented by the following general formula (2a).

General Formula (2a)




[0031] In the general formula (2a), R^{11} and R^{12} each independently represent a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, or a substituted or unsubstituted heteroaryl group. R^{11} and R^{12} may bond to each other to form a cyclic structure. L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group. The substituent that may be introduced into the arylene group or the heteroarylene group of L may be a group represented by the general formula (1), or a group represented by any of the general formulae (2a), (2b), (2c), and (3) to (6) to be mentioned hereinunder. The groups represented by these (1) to (6) may be introduced into L up to the largest number of substituents that can be introduced thereinto. In the case where multiple groups of the general formulae (1) to (6) are introduced, these substituents may be the same as or different from each other. * indicates a bonding position to the carbon atom (C) constituting a ring skeleton of the benzene ring in the general formula (1).

[0032] In the general formula (2a), R¹¹ and R¹² may bond to each other to form a cyclic structure along with the nitrogen atom in the general formula (2a).

[0033] For the aryl group or the heteroaryl group represented by R¹¹ and R¹², reference may be made to the description of the aryl group or the heteroaryl group to be a substituent that bonds to the nitrogen atom of the amino group mentioned hereinabove.

[0034] The substituent represented by the general formula (2a) is preferably a substituent represented by the following general formula (2b).




[0035] In the general formula (2b), R²¹ to R²⁸ each independently represent a hydrogen atom or a substituent. L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group. R²¹ and R²², R²² and R²³, R²³ and R²⁴, R²⁴ and R²⁵, R²⁶ and R²⁷, and R²⁷ and R²⁸ each may bond to each other to form a linking group necessary for forming a cyclic structure. R²⁵ and R²⁶ may bond to each other to form a single bond or a linking group. For example, when R²⁵ and R²⁶ bond to each other to form a single bond, the compound represented by the general formula (2b) includes a carbazole ring. * indicates a bonding position to the carbon atom (C) that constitutes the ring skeleton of the benzene ring in the general formula (1). Regarding specific examples and preferred range of the substituents that R²¹ to R²⁸ may have, reference may be made to the description of the arylene group or the heteroarylene group to be a substituent for Ar in the general formula (1).

[0036] The cyclic structure to be formed by R²¹ and R²², R²² and R²³, R²³ and R²⁴, R²⁴ and R²⁵, R²⁵ and R²⁶, R²⁶ and R²⁷, and R²⁷ and R²⁸ each bonding to each other may be an aromatic ring or an aliphatic ring, and may contain a hetero atom, and further, the cyclic structure may be a condensed ring of 2 or more rings. Here, the hetero atom is preferably one selected from the group consisting of a nitrogen atom, an oxygen atom and a sulfur atom. Examples of the cyclic structure to be formed include a benzene ring, a naphthalene ring, a pyridine ring, a pyridazine ring, a pyrimidine ring, a pyrazine ring, a pyrrole ring, an imidazole ring, a pyrazole ring, an imidazoline ring, an oxazole ring, an isoxazole ring, a thiazole ring, an isothiazole ring, a cyclohexadiene ring, a cyclohexene ring, a cyclopentaene ring, a cycloheptatriene ring, a cycloheptadiene ring, a cycloheptaene ring, a furan ring, a thiophene ring, a naphthyridine ring, a quinoxaline ring, and a quinoline ring.

[0037] The substituent represented by the general formula (2a) is preferably a substituent represented by the following general formula (2c).

General Formula (2c)



[0038] In the general formula (2c), R^{31} to R^{40} each independently represent a hydrogen atom or a substituent. L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group. R^{31} and R^{32} , R^{32} and R^{33} , R^{33} and R^{34} , R^{34} and R^{35} , R^{35} and R^{36} , R^{36} and R^{37} , R^{37} and R^{38} , R^{38} and R^{39} , and R^{39} and R^{40} each may bond to each other to form a linking group necessary for forming a cyclic structure. R^{35} and R^{36} may bond to each other to form a single bond or a linking group. * indicates a bonding position to the carbon atom (C) constituting the ring skeleton of the benzene ring in the general formula (1). For specific examples and preferred ranges of the substituents that R^{31} to R^{40} may have, reference may be made to the description of the arylene group or the heteroarylene group to be a substituent for Ar in the general formula (1).

[0039] Regarding the cyclic structure to be formed by R^{31} and R^{32} , R^{32} and R^{33} , R^{33} and R^{34} , R^{34} and R^{35} , R^{35} and R^{36} , R^{36} and R^{37} , R^{37} and R^{38} , R^{38} and R^{39} , and R^{39} and R^{40} each bonding to each other, reference may be made to the corresponding description of the cyclic structure that R^{21} and R^{22} in the general formula (2a) form.

[0040] In the general formulae (2a) to (2c), L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group. Preferably, L is a single bond, or a substituted or unsubstituted arylene group.

[0041] The aromatic ring to constitute the arylene group represented by L may be a single ring or a condensed ring of two or more condensed aromatic rings. In the case of where two or more aromatic rings are condensed, they may link linearly or in a branched form. The carbon number of the aromatic ring to constitute the arylene group represented by L is preferably 6 to 22, more preferably 6 to 18, even more preferably 6 to 14, and further more preferably 6 to 10. Specific examples of the arylene group include a phenylene group, a naphthalenediyl group, and a biphenylene group.


[0042] The hetero ring to constitute the heteroarylene group represented by L may be a single ring, or a condensed ring of one or more hetero rings condensed with an aromatic ring or a hetero ring, or a linking ring of one or more hetero rings linking to an aromatic ring or a hetero ring. The carbon number of the hetero ring is preferably 5 to 22, more preferably 5 to 18, even more preferably 5 to 14, and further more preferably 5 to 10. Preferably, the hetero atom to constitute the hetero ring is a nitrogen atom. Specific examples of the hetero ring include a pyridine ring, a pyridazine ring, a pyrimidine ring, a triazole ring, and a benzotriazole ring.

[0043] A more preferred group represented by L is a phenylene group. When L is a phenylene group, the phenylene group may be any of a 1,2-phenylene group, a 1,3-phenylene group, or a 1,4-phenylene group, but is preferably a 1,4-phenylene group. L may be substituted with a substituent. The number of the substituents for L and the substitution position thereof are not specifically limited. Regarding the description and preferred ranges of the substituents that may be introduced into L, reference may be made to the description and the preferred ranges of the substituents that R^{11} and R^{12} mentioned above may have. The substituent that may be introduced into the arylene group or the heteroarylene group of L may be a group represented by any of the general formulae (1), (2a), (2b) and (2c), and may also be a group represented by any of the general formulae (3) to (6) to be mentioned hereinunder. The groups represented by these (1) to (6) may be introduced into L up to the largest number of substituents that can be introduced thereinto. In the case where multiple groups of the general formulae (1) to (6) are introduced, these substituents may be the same as or different from each other.

[0044] In the case where L has a substituent, the substituent may form a cyclic structure along with R^{11} and R^{12} in (2a), or R^{21} and R^{28} in (2b), or R^{31} and R^{40} in (2c).

[0045] The substituent represented by the general formulae (2a) to (2c) is preferably a substituent represented by any of the following general formulae (3) to (6). Above all, groups represented by the general formulae (3) to (5) are preferred, and groups represented by the general formula (5) are more preferred.

General Formula (3)




General Formula (4)

5

10

15




General Formula (5)

20

25

30




General Formula (6)

35

40

45



[0046] In the general formulae (3) to (6), R^{41} to R^{46} , R^{51} to R^{60} , R^{61} to R^{68} , and R^{71} to R^{78} each independently represent a hydrogen atom or a substituent. Regarding the description and preferred ranges of the substituent as referred to herein, reference may be made to the description of the arylene group or the heteroarylene group of a substituent for Ar in the general formula (1). Preferably, R^{41} to R^{46} , R^{51} to R^{60} , R^{61} to R^{68} , and R^{71} to R^{78} each independently represent a group represented by any of the above-mentioned general formulae (3) to (6). The number of the substituents in the general formulae (3) to (6) is not specifically limited. Also preferred is a case where all are unsubstituted (that is, all are hydrogen atoms). In the case where the general formulae (3) to (6) each have two or more substituents, those substituents may be the same as or different from each other. In the case where the general formulae (3) to (6) each have a substituent, the substituent is preferably any of R^{42} to R^{46} , and more preferably at least one of R^{45} and R^{46} . In the general formula (4), preferably, any of R^{52} to R^{59} is a substituent; in the general formula (5), preferably, any of R^{62} to R^{67} is a substituent;

and in the general formula (6), preferably, any of R⁷² to R⁷⁷ is a substituent.


[0047] In the general formulae (3) to (6), R⁴¹ and R⁴², R⁴² and R⁴³, R⁴³ and R⁴⁴, R⁴⁵ and R⁴⁶, R⁵¹ and R⁵², R⁵² and R⁵³, R⁵³ and R⁵⁴, R⁵⁴ and R⁵⁵, R⁵⁵ and R⁵⁶, R⁵⁶ and R⁵⁷, R⁵⁷ and R⁵⁸, R⁵⁸ and R⁵⁹, R⁵⁹ and R⁶⁰, R⁶¹ and R⁶², R⁶² and R⁶³, R⁶³ and R⁶⁴, R⁶⁵ and R⁶⁶, R⁶⁶ and R⁶⁷, R⁶⁷ and R⁶⁸, R⁷¹ and R⁷², R⁷² and R⁷³, R⁷³ and R⁷⁴, R⁷⁵ and R⁷⁶, R⁷⁶ and R⁷⁷, and R⁷⁷ and R⁷⁸ each may bond to each other to form a cyclic structure. Regarding the description and preferred examples of the cyclic structure, reference may be made to the description and the preferred examples of the cyclic structure that is formed by R²¹ and R²² and the like in the general formula (2b) each bonding to each other.


[0048] In the general formula (6), X represents an oxygen atom, a sulfur atom, a substituted or unsubstituted nitrogen atom, a substituted or unsubstituted carbon atom, a substituted or unsubstituted silicon atom or a carbonyl group, which is divalent and which has a linking chain length of one atom, or represents a substituted or unsubstituted ethylene group, a substituted or unsubstituted vinylene group, a substituted or unsubstituted o-arylene group or a substituted or unsubstituted o-heteroarylene group, which is divalent and which has a bonding chain length of two atoms. Regarding specific examples and preferred ranges of the substituent, reference may be made to the corresponding description of the substituent for the arylene group or the heteroarylene group represented by R¹¹ in the general formula (2a).


[0049] In the general formulae (3) to (6), L¹¹ to L¹⁴ each independently represent a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group. Here, the substituent for the arylene group or the heteroarylene group may be a group represented by any of the general formulae (1) to (6). The groups represented by the general formulae (1) to (6) may be introduced into L¹¹ to L¹⁴ up to the largest number of substituents that can be introduced thereinto. In the case where multiple groups of the general formulae (1) to (6) are introduced, these substituents may be the same as or different from each other.

[0050] * indicates a bonding position to the carbon atom (C) constituting a ring skeleton of the benzene ring in the general formula (1). Regarding the description and preferred ranges of the arylene group or the heteroarylene group represented by L¹¹ to L¹⁴ and those of the substituents that may be introduced into these groups, reference may be made to the description and the preferred ranges of the arylene group or the heteroarylene group represented by L and those of the substituents that may be introduced into the group. Preferably, L¹¹ to L¹⁴ each are a single bond, or a substituted or unsubstituted arylene group.

[0051] Specific examples of the substituted amino group are shown below; however, the substituted amino group employable in the present invention should not be limitatively interpreted by these specific examples. * indicates a bonding position to the linking group (L) in the general formulae (2a) to (2c).








[0052] When two or more of R¹ to R⁵ in the general formula (1) are D's, these multiple D's may be the same as or


different from each other.

[0053] In the case where D's are different, preferably, two D's each have an aromatic ring, and the aromatic ring is common between the two D's, but the two differ from each other in point of at least one condition of the number of the substituents on the aromatic ring, the substitution site of the aromatic ring substituted with the substituent, and the structure of the substituent on the aromatic ring.


[0054] Specific examples of the group represented by D are shown below; however, D that is employable in the present invention should not be limitatively interpreted by these specific examples.




D1




D2




D3




D4




D5




D6




D7




D8




D9



D10




D11




D12


5



D13




D14




D15

10


15



D16



D17




D18


20

25

30



D19




D20


35

40


45



D21




D22




D23

50


55




D24




D25



D26



D27



D28

[0055] In the general formula (1), at least any one of R¹ to R⁵ is a cyano group and at least one is Ar, and at least one is D. The remaining two may be hydrogen atoms, or may be Ar's or D's, or may also be any other substituent than Ar and D (but excepting a cyano group). Preferably, the remaining two are selected from a hydrogen atom, Ar and D, and is more preferably selected from Ar and D. For example, one of the remaining two may be Ar and the other may be D.

[0056] The general formula (1) may be a symmetric compound or may also be an asymmetric compound.

[0057] The compound represented by the general formula (1) is preferably such that the energy difference ΔE_{ST} between the lowest excited singlet energy level (E_{si}) and the lowest excited triplet energy level (E_{T1}) thereof is 0.9 or less as a relative value based on ΔE_{ST} , 1, of a reference compound prepared by removing Ar from the compound, more preferably 0.8 or less, even more preferably 0.7 or less, still more preferably 0.6 or less, further more preferably 0.5 or less, and especially preferably 0.4 or less. The compound having such a smaller ΔE_{ST} than that of a reference compound can more readily undergo reverse intersystem crossing from the excited triplet state to the excited singlet state among delayed fluorescent materials and tends to have a shorter lifetime of delayed fluorescence. When a light-emitting material having a short delayed fluorescence lifetime is used in an electroluminescent device, the device can be free from a problem of emission efficiency reduction owing to exciton accumulation in a high-current density region and a problem of device degradation in long-term driving, and the device performance can be improved.

[0058] ΔE_{ST} of the compound can be determined from the fluorescence spectrum and the phosphorescence spectrum thereof, and can also be calculated according to computational chemistry. The relative value (based on ΔE_{ST} of a reference compound, 1) determined according to these methods well dovetails with each other. Regarding the computational method for ΔE_{ST} of from a fluorescence spectrum and a phosphorescence spectrum and the computational method for ΔE_{ST} according to computational chemistry, reference may be made to the description in the section of Examples given hereinunder.

[0059] The compound represented by the general formula (1) has a wide variation of emission colors among cyanobenzene derivatives. Consequently, the present invention can provide useful compounds even in a blue region.

[0060] Specific examples of the compound represented by the general formula (1) are shown below. However, the compound represented by the general formula (1) employable in the present invention should not be limitatively interpreted by the following specific examples.

EP 3 647 392 A1

[Table 1]

5
10
15
20
25
30
35
40
45
50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
1	D1	D1	CN	D1	Ar1
2	D1	D1	CN	Ar1	Ar1
3	D1	Ar1	CN	D1	Ar1
4	Ar1	D1	CN	D1	Ar1
5	D1	Ar1	CN	Ar1	Ar1
6	D1	D1	CN	H	Ar1
7	D1	H	CN	D1	Ar1
8	D1	H	CN	Ar1	D1
9	D1	H	CN	Ar1	Ar1
10	D1	Ar1	CN	H	Ar1
11	D1	Ar1	CN	Ar1	H
12	D1	H	CN	H	Ar1
13	D1	H	CN	Ar1	H
14	D1	Ar1	CN	H	H
15	CN	D1	D1	D1	Ar1
16	CN	D1	D1	Ar1	D1
17	CN	D1	D1	Ar1	Ar1
18	CN	D1	Ar1	D1	Ar1
19	CN	Ar1	D1	D1	Ar1
20	CN	D1	Ar1	Ar1	Ar1
21	CN	Ar1	D1	Ar1	Ar1
22	CN	D1	H	Ar1	D1
23	CN	D1	H	D1	Ar1
24	CN	D1	Ar1	D1	H
25	CN	D1	D1	Ar1	H
26	CN	H	D1	D1	Ar1
27	CN	D1	H	Ar1	Ar1
28	CN	D1	Ar1	H	Ar1
29	CN	H	Ar1	D1	Ar1
30	CN	Ar1	D1	H	Ar1
31	CN	D1	Ar1	Ar1	H
32	CN	Ar1	D1	H	H
33	CN	Ar1	H	D1	H
34	CN	D1	H	Ar1	H
35	CN	H	D1	Ar1	H
36	CN	D1	H	H	Ar1
37	CN	D1	Ar1	Ar1	D1
38	D1	CN	D1	D1	Ar1

EP 3 647 392 A1

(continued)

5
10
15
20
25
30
35
40
45
50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
39	D1	CN	D1	Ar1	D1
40	Ar1	CN	D1	D1	D1
41	D1	CN	D1	Ar1	Ar1
42	D1	CN	Ar1	D1	Ar1
43	Ar1	CN	D1	D1	Ar1
44	Ar1	CN	D1	Ar1	D1
45	D1	CN	Ar1	Ar1	Ar1
46	Ar1	CN	D1	Ar1	Ar1
47	Ar1	CN	Ar1	D1	Ar1
48	D1	CN	D1	H	Ar1
49	D1	CN	H	D1	Ar1
50	H	CN	D1	D1	Ar1
51	Ar1	CN	D1	D1	H
52	H	CN	D1	Ar1	D1
53	Ar1	CN	D1	H	D1
54	Ar1	CN	Ar1	H	D1
55	Ar1	CN	H	Ar1	D1
56	H	CN	Ar1	Ar1	D1
57	D1	CN	Ar1	Ar1	H
58	H	CN	Ar1	D1	Ar1
59	D1	CN	Ar1	H	Ar1
60	H	CN	H	D1	Ar1
61	H	CN	D1	H	Ar1
62	D1	CN	H	H	Ar1
63	Ar1	CN	H	H	D1
64	D1	CN	H	Ar1	H
65	Ar1	CN	H	D1	H
66	D1	Ar2	CN	D1	Ar2
67	D1	Ar3	CN	D1	Ar3
68	D1	Ar4	CN	D1	Ar4
69	D1	Ar5	CN	D1	Ar5
70	D1	Ar6	CN	D1	Ar6
71	D1	Ar7	CN	D1	Ar7
72	D1	Ar8	CN	D1	Ar8
73	D1	Ar9	CN	D1	Ar9
74	D1	Ar10	CN	D1	Ar10
75	D1	Ar11	CN	D1	Ar11
76	D1	Ar12	CN	D1	Ar12

EP 3 647 392 A1

(continued)

5
10
15
20

No	R ¹	R ²	R ³	R ⁴	R ⁵
77	D1	Ar13	CN	D1	Ar13
78	D1	Ar14	CN	D1	Ar14
79	D1	Ar15	CN	D1	Ar15
80	D1	Ar16	CN	D1	Ar16
81	D1	Ar17	CN	D1	Ar17
82	D1	Ar18	CN	D1	Ar18
83	D1	Ar19	CN	D1	Ar19
84	D1	Ar20	CN	D1	Ar20
85	D1	Ar21	CN	D1	Ar21
86	D1	Ar22	CN	D1	Ar22
87	D1	Ar23	CN	D1	Ar23
88	D1	Ar24	CN	D1	Ar24

[Table 2]

25
30
35
40
45
50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
89	D1	Ar25	CN	D1	Ar25
90	D1	Ar26	CN	D1	Ar26
91	D1	Ar27	CN	D1	Ar27
92	D1	Ar28	CN	D1	Ar28
93	D1	Ar29	CN	D1	Ar29
94	D1	Ar30	CN	D1	Ar30
95	D1	Ar31	CN	D1	Ar31
96	D1	Ar32	CN	D1	Ar32
97	D1	Ar33	CN	D1	Ar33
98	D2	Ar1	CN	D2	Ar1
99	D3	Ar1	CN	D3	Ar1
100	D4	Ar1	CN	D4	Ar1
101	D5	Ar1	CN	D5	Ar1
102	D6	Ar1	CN	D6	Ar1
103	D7	Ar1	CN	D7	Ar1
104	D8	Ar1	CN	D8	Ar1
105	D9	Ar1	CN	D9	Ar1
106	D10	Ar1	CN	D10	Ar1
107	D11	Ar1	CN	D11	Ar1
108	D12	Ar1	CN	D12	Ar1
109	D13	Ar1	CN	D13	Ar1
110	D14	Ar1	CN	D14	Ar1

EP 3 647 392 A1

(continued)

5
10
15
20
25
30
35
40
45
50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
111	D15	Ar1	CN	D15	Ar1
112	D16	Ar1	CN	D16	Ar1
113	D17	Ar1	CN	D17	Ar1
114	D18	Ar1	CN	D18	Ar1
115	D19	Ar1	CN	D19	Ar1
116	D20	Ar1	CN	D20	Ar1
117	D21	Ar1	CN	D21	Ar1
118	D22	Ar1	CN	D22	Ar1
119	D23	Ar1	CN	D23	Ar1
120	D24	Ar1	CN	D24	Ar1
121	D25	Ar1	CN	D25	Ar1
122	D26	Ar1	CN	D26	Ar1
123	D27	Ar1	CN	D27	Ar1
124	D28	Ar1	CN	D28	Ar1
125	D1	CN	Ar2	D1	Ar2
126	D1	CN	Ar3	D1	Ar3
127	D1	CN	Ar4	D1	Ar4
128	D1	CN	Ar5	D1	Ar5
129	D1	CN	Ar6	D1	Ar6
130	D1	CN	Ar7	D1	Ar7
131	D1	CN	Ar8	D1	Ar8
132	D1	CN	Ar9	D1	Ar9
133	D1	CN	Ar10	D1	Ar10
134	D1	CN	Ar11	D1	Ar11
135	D1	CN	Ar12	D1	Ar12
136	D1	CN	Ar13	D1	Ar13
137	D1	CN	Ar14	D1	Ar14
138	D1	CN	Ar15	D1	Ar15
139	D1	CN	Ar16	D1	Ar16
140	D1	CN	Ar17	D1	Ar17
141	D1	CN	Ar18	D1	Ar18
142	D1	CN	Ar19	D1	Ar19
143	D1	CN	Ar20	D1	Ar20
144	D1	CN	Ar21	D1	Ar21
145	D1	CN	Ar22	D1	Ar22
146	D1	CN	Ar23	D1	Ar23
147	D1	CN	Ar24	D1	Ar24
148	D1	CN	Ar25	D1	Ar25

EP 3 647 392 A1

(continued)

5
10
15
20
25
30
35
40
45

No	R ¹	R ²	R ³	R ⁴	R ⁵
149	D1	CN	Ar26	D1	Ar26
150	D1	CN	Ar27	D1	Ar27
151	D1	CN	Ar28	D1	Ar28
152	D1	CN	Ar29	D1	Ar29
153	D1	CN	Ar30	D1	Ar30
154	D1	CN	Ar31	D1	Ar31
155	D1	CN	Ar32	D1	Ar32
156	D1	CN	Ar33	D1	Ar33
157	D2	CN	Ar1	D2	Ar1
158	D3	CN	Ar1	D3	Ar1
159	D4	CN	Ar1	D4	Ar1
160	D5	CN	Ar1	D5	Ar1
161	D6	CN	Ar1	D6	Ar1
162	D7	CN	Ar1	D7	Ar1
163	D8	CN	Ar1	D8	Ar1
164	D9	CN	Ar1	D9	Ar1
165	D10	CN	Ar1	D10	Ar1
166	D11	CN	Ar1	D11	Ar1
167	D12	CN	Ar1	D12	Ar1
168	D13	CN	Ar1	D13	Ar1
169	D14	CN	Ar1	D14	Ar1
170	D15	CN	Ar1	D15	Ar1
171	D16	CN	Ar1	D16	Ar1
172	D17	CN	Ar1	D17	Ar1
173	D18	CN	Ar1	D18	Ar1
174	D19	CN	Ar1	D19	Ar1
175	D20	CN	Ar1	D20	Ar1
176	D21	CN	Ar1	D21	Ar1

[Table 3

50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
177	D22	CN	Ar1	D22	Ar1
178	D23	CN	Ar1	D23	Ar1
179	D24	CN	Ar1	D24	Ar1
180	D25	CN	Ar1	D25	Ar1
181	D26	CN	Ar1	D26	Ar1
182	D27	CN	Ar1	D27	Ar1

EP 3 647 392 A1

(continued)

5

10

15

20

25

30

35

40

45

50

55

No	R ¹	R ²	R ³	R ⁴	R ⁵
183	D28	CN	Ar1	D28	Ar1
184	Ar2	CN	D1	Ar2	D1
185	Ar3	CN	D1	Ar3	D1
186	Ar4	CN	D1	Ar4	D1
187	Ar5	CN	D1	Ar5	D1
188	Ar6	CN	D1	Ar6	D1
189	Ar7	CN	D1	Ar7	D1
190	Ar8	CN	D1	Ar8	D1
191	Ar9	CN	D1	Ar9	D1
192	Ar10	CN	D1	Ar10	D1
193	Ar11	CN	D1	Ar11	D1
194	Ar12	CN	D1	Ar12	D1
195	Ar13	CN	D1	Ar13	D1
196	Ar14	CN	D1	Ar14	D1
197	Ar15	CN	D1	Ar15	D1
198	Ar16	CN	D1	Ar16	D1
199	Ar17	CN	D1	Ar17	D1
200	Ar18	CN	D1	Ar18	D1
201	Ar19	CN	D1	Ar19	D1
202	Ar20	CN	D1	Ar20	D1
203	Ar21	CN	D1	Ar21	D1
204	Ar22	CN	D1	Ar22	D1
205	Ar23	CN	D1	Ar23	D1
206	Ar24	CN	D1	Ar24	D1
207	Ar25	CN	D1	Ar25	D1
208	Ar26	CN	D1	Ar26	D1
209	Ar27	CN	D1	Ar27	D1
210	Ar28	CN	D1	Ar28	D1
211	Ar29	CN	D1	Ar29	D1
212	Ar30	CN	D1	Ar30	D1
213	Ar31	CN	D1	Ar31	D1
214	Ar32	CN	D1	Ar32	D1
215	Ar33	CN	D1	Ar33	D1
216	Ar1	CN	D2	Ar1	D2
217	Ar1	CN	D3	Ar1	D3
218	Ar1	CN	D4	Ar1	D4
219	Ar1	CN	D5	Ar1	D5
220	Ar1	CN	D6	Ar1	D6

EP 3 647 392 A1

(continued)

5

10

15

20

25

30

35

40

45

50

55

No	R ¹	R ²	R ³	R ⁴	R ⁵
221	Ar1	CN	D7	Ar1	D7
222	Ar1	CN	D8	Ar1	D8
223	Ar1	CN	D9	Ar1	D9
224	Ar1	CN	D10	Ar1	D10
225	Ar1	CN	D11	Ar1	D11
226	Ar1	CN	D12	Ar1	D12
227	A1	CN	D13	Ar1	D13
228	Ar1	CN	D14	Ar1	D14
229	Ar1	CN	D15	Ar1	D15
230	Ar1	CN	D16	Ar1	D16
231	Ar1	CN	D17	Ar1	D17
232	Ar1	CN	D18	Ar1	D18
233	Ar1	CN	D19	Ar1	D19
234	Ar1	CN	D20	Ar1	D20
235	Ar1	CN	D21	Ar1	D21
236	Ar1	CN	D22	Ar1	D22
237	Ar1	CN	D23	Ar1	D23
238	Ar1	CN	D24	Ar1	D24
239	Ar1	CN	D25	Ar1	D25
240	Ar1	CN	D26	Ar1	D26
241	Ar1	CN	D27	Ar1	D27
242	Ar1	CN	D28	Ar1	D28
243	D1	CN	D1	Ar2	D1
244	D1	CN	D1	Ar3	D1
245	D1	CN	D1	Ar4	D1
246	D1	CN	D1	Ar5	D1
247	D1	CN	D1	Ar6	D1
248	D1	CN	D1	Ar7	D1
249	D1	CN	D1	Ar8	D1
250	D1	CN	D1	Ar9	D1
251	D1	CN	D1	Ar10	D1
252	D1	CN	D1	Ar11	D1
253	D1	CN	D1	Ar12	D1
254	D1	CN	D1	Ar13	D1
255	D1	CN	D1	Ar14	D1
256	D1	CN	D1	Ar15	D1
257	D1	CN	D1	Ar16	D1
258	D1	CN	D1	Ar17	D1

EP 3 647 392 A1

(continued)

5

No	R ¹	R ²	R ³	R ⁴	R ⁵
259	D1	CN	D1	Ar18	D1
260	D1	CN	D1	Ar19	D1
261	D1	CN	D1	Ar20	D1
262	D1	CN	D1	Ar21	D1
263	D1	CN	D1	Ar22	D1
264	D1	CN	D1	Ar23	D1

10

15

Table 4

No	R ¹	R ²	R ³	R ⁴	R ⁵
265	D1	CN	D1	Ar24	D1
266	D1	CN	D1	Ar25	D1
267	D1	CN	D1	Ar26	D1
268	D1	CN	D1	Ar27	D1
269	D1	CN	D1	Ar28	D1
270	D1	CN	D1	Ar29	D1
271	D1	CN	D1	Ar30	D1
272	D1	CN	D1	Ar31	D1
273	D1	CN	D1	Ar32	D1
274	D1	CN	D1	Ar33	D1
275	D2	CN	D2	Ar1	D2
276	D3	CN	D3	Ar1	D3
277	D4	CN	D4	Ar1	D4
278	D5	CN	D5	Ar1	D5
279	D6	CN	D6	Ar1	D6
280	D7	CN	D7	Ar1	D7
281	D8	CN	D8	Ar1	D8
282	D9	CN	D9	Ar1	D9
283	D10	CN	D10	Ar1	D10
284	D11	CN	D11	Ar1	D11
285	D12	CN	D12	Ar1	D12
286	D13	CN	D13	Ar1	D13
287	D14	CN	D14	Ar1	D14
288	D15	CN	D15	Ar1	D15
289	D16	CN	D16	Ar1	D16
290	D17	CN	D17	Ar1	D17
291	D18	CN	D18	Ar1	D18
292	D19	CN	D19	Ar1	D19

20

25

30

35

40

45

50

55

EP 3 647 392 A1

(continued)

5
10
15
20
25
30
35
40
45
50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
293	D20	CN	D20	Ar1	D20
294	D21	CN	D21	Ar1	D21
295	D22	CN	D22	Ar1	D22
296	D23	CN	D23	Ar1	D23
297	D24	CN	D24	Ar1	D24
298	D25	CN	D25	Ar1	D25
299	D26	CN	D26	Ar1	D26
300	D27	CN	D27	Ar1	D27
301	D28	CN	D28	Ar1	D28
302	Ar2	CN	D1	D1	D1
303	Ar3	CN	D1	D1	D1
304	Ar4	CN	D1	D1	D1
305	Ar5	CN	D1	D1	D1
306	Ar6	CN	D1	D1	D1
307	Ar7	CN	D1	D1	D1
308	Ar8	CN	D1	D1	D1
309	Ar9	CN	D1	D1	D1
310	Ar10	CN	D1	D1	D1
311	Ar11	CN	D1	D1	D1
312	Ar12	CN	D1	D1	D1
313	Ar13	CN	D1	D1	D1
314	Ar14	CN	D1	D1	D1
315	Ar15	CN	D1	D1	D1
316	Ar16	CN	D1	D1	D1
317	Ar17	CN	D1	D1	D1
318	Ar18	CN	D1	D1	D1
319	Ar19	CN	D1	D1	D1
320	Ar20	CN	D1	D1	D1
321	Ar21	CN	D1	D1	D1
322	Ar22	CN	D1	D1	D1
323	Ar23	CN	D1	D1	D1
324	Ar24	CN	D1	D1	D1
325	Ar25	CN	D1	D1	D1
326	Ar26	CN	D1	D1	D1
327	Ar27	CN	D1	D1	D1
328	Ar28	CN	D1	D1	D1
329	Ar29	CN	D1	D1	D1
330	Ar30	CN	D1	D1	D1

EP 3 647 392 A1

(continued)

5
10
15
20
25
30
35

No	R ¹	R ²	R ³	R ⁴	R ⁵
331	Ar31	CN	D1	D1	D1
332	Ar32	CN	D1	D1	D1
333	Ar33	CN	D1	D1	D1
334	Ar1	CN	D2	D2	D2
335	Ar1	CN	D3	D3	D3
336	Ar1	CN	D4	D4	D4
337	Ar1	CN	D5	D5	D5
338	Ar1	CN	D6	D6	D6
339	Ar1	CN	D7	D7	D7
340	Ar1	CN	D8	D8	D8
341	Ar1	CN	D9	D9	D9
342	Ar1	CN	D10	D10	D10
343	Ar1	CN	D11	D11	D11
344	Ar1	CN	D12	D12	D12
345	Ar1	CN	D13	D13	D13
346	Ar1	CN	D14	D14	D14
347	Ar1	CN	D15	D15	D15
348	Ar1	CN	D16	D16	D16
349	Ar1	CN	D17	D17	D17
350	Ar1	CN	D18	D18	D18
351	Ar1	CN	D19	D19	D19
352	Ar1	CN	D20	D20	D20

[Table 5]

40
45
50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
353	Ar1	CN	D21	D21	D21
354	Ar1	CN	D22	D22	D22
355	Ar1	CN	D23	D23	D23
356	Ar1	CN	D24	D24	D24
357	Ar1	CN	D25	D25	D25
358	Ar1	CN	D26	D26	D26
359	Ar1	CN	D27	D27	D27
360	Ar1	CN	D28	D28	D28
361	D1	Ar1	CN	D1	Ar2
362	D1	Ar1	CN	D1	Ar3
363	D1	Ar1	CN	D1	Ar4
364	D1	Ar1	CN	D1	Ar5

EP 3 647 392 A1

(continued)

5
10
15
20
25
30
35
40
45
50
55

No	R ¹	R ²	R ³	R ⁴	R ⁵
365	D1	Ar1	CN	D1	Ar6
366	D1	Ar1	CN	D1	Ar7
367	D1	Ar1	CN	D1	Ar8
368	D1	Ar1	CN	D1	Ar9
369	D1	Ar1	CN	D1	Ar10
370	D1	Ar1	CN	D1	Ar11
371	D1	Ar1	CN	D1	Ar12
372	D1	Ar1	CN	D1	Ar13
373	D1	Ar1	CN	D1	Ar14
374	D1	Ar1	CN	D1	Ar15
375	D1	Ar1	CN	D1	Ar16
376	D1	Ar1	CN	D1	Ar17
377	D1	Ar1	CN	D1	Ar18
378	D1	Ar1	CN	D1	Ar19
379	D1	Ar1	CN	D1	Ar20
380	D1	Ar1	CN	D1	Ar21
381	D1	Ar1	CN	D1	Ar22
382	D1	Ar1	CN	D1	Ar23
383	D1	Ar1	CN	D1	Ar24
384	D1	Ar1	CN	D1	Ar25
385	D1	Ar1	CN	D1	Ar26
386	D1	Ar1	CN	D1	Ar27
387	D1	Ar1	CN	D1	Ar28
388	D1	Ar1	CN	D1	Ar29
389	D1	Ar1	CN	D1	Ar30
390	D1	Ar1	CN	D1	Ar31
391	D1	Ar1	CN	D1	Ar32
392	D1	Ar1	CN	D1	Ar33
393	D1	Ar1	CN	D2	Ar1
394	D1	Ar1	CN	D3	Ar1
395	D1	Ar1	CN	D4	Ar1
396	D1	Ar1	CN	D5	Ar1
397	D1	Ar1	CN	D6	Ar1
398	D1	Ar1	CN	D7	Ar1
399	D1	Ar1	CN	D8	Ar1
400	D1	Ar1	CN	D9	Ar1
401	D1	Ar1	CN	D10	Ar1
402	D1	Ar1	CN	D11	Ar1

EP 3 647 392 A1

(continued)

5
10
15
20
25
30
35
40
45
50

No	R ¹	R ²	R ³	R ⁴	R ⁵
403	D1	Ar1	CN	D12	Ar1
404	D1	Ar1	CN	D13	Ar1
405	D1	Ar1	CN	D14	Ar1
406	D1	Ar1	CN	D15	Ar1
407	D1	Ar1	CN	D16	Ar1
408	D1	Ar1	CN	D17	Ar1
409	D1	Ar1	CN	D18	Ar1
410	D1	Ar1	CN	D19	Ar1
411	D1	Ar1	CN	D20	Ar1
412	D1	Ar1	CN	D21	Ar1
413	D1	Ar1	CN	D22	Ar1
414	D1	Ar1	CN	D23	Ar1
415	D1	Ar1	CN	D24	Ar1
416	D1	Ar1	CN	D25	Ar1
417	D1	Ar1	CN	D26	Ar1
418	D1	Ar1	CN	D27	Ar1
419	D1	Ar1	CN	D28	Ar1
420	D7	Ar1	CN	D8	Ar1
421	D7	Ar1	CN	D9	Ar1
422	D7	Ar1	CN	D10	Ar1
423	D7	Ar1	CN	D11	Ar1
424	D7	Ar1	CN	D12	Ar1
425	D13	Ar1	CN	D14	Ar1
426	D13	Ar1	CN	D15	Ar1
427	D13	Ar1	CN	D16	Ar1
428	D13	Ar1	CN	D17	Ar1
429	D13	Ar1	CN	D18	Ar1
430	D13	Ar1	CN	D19	Ar1
431	D13	Ar1	CN	D20	Ar1
432	D17	Ar1	CN	D18	Ar1
433	D17	Ar1	CN	D19	Ar1
434	D17	Ar1	CN	D20	Ar1

[0061] The molecular weight of the compound represented by the general formula (1) is, for example, in the case where an organic layer containing the compound represented by the general formula (1) is intended to be formed according to a vapor deposition method and used in devices, preferably 1500 or less, more preferably 1200 or less, even more preferably 1000 or less, and further more preferably 900 or less. The lower limit of the molecular weight is the smallest molecular weight that the general formula (1) can take.

[0062] Irrespective of the molecular weight thereof, the compound represented by the general formula (1) may be formed into a film according to a coating method. When a coating method is employed, even a compound having a


relatively large molecular weight can be formed into a film. The compound represented by the general formula (1) has an advantage that, among cyanobenzene compounds, it can readily dissolve in an organic solvent. Consequently, the compound represented by the general formula (1) is applicable to a coating method and, in addition, it can be readily purified to have an increased purity.

[0063] Applying the present invention, it is considered to use a compound containing plural structures represented by the general formula (1) in the molecule as a light-emitting material.


[0064] For example, it is considered that a polymerizable group is previously introduced into a structure represented by the general formula (1) and the polymerizable group is polymerized to give a polymer, and the polymer is used as a light-emitting material. Specifically, a monomer containing a polymerizable functional group in any of R¹ to R⁵ in the general formula (1) is prepared, and this is homo-polymerized or copolymerized with any other monomer to give a polymer having a recurring unit, and the polymer can be used as a material for a light-emitting material. Alternatively, compounds each having a structure represented by the general formula (1) are coupled to give a dimer or a trimer, and it can be used as a light-emitting material.

[0065] Examples of the polymer having a recurring unit containing a structure represented by the general formula (1) include polymers containing a structure represented by the following general formula (3) or (4).

General Formula (3)



General Formula (4)




[0066] In the general formula (3) or (4), Q represents a group containing a structure represented by the general formula (1), and L¹ and L² each represent a linking group. The carbon number of the linking group is preferably 0 to 20, more preferably 1 to 15, even more preferably 2 to 10. Preferably, the linking group has a structure represented by -X¹¹-L¹¹-. Here, X¹¹ represents an oxygen atom or a sulfur atom and is preferably an oxygen atom. L¹¹ represents a linking group, and is preferably a substituted or unsubstituted alkylene group, or a substituted or unsubstituted arylene group, more preferably a substituted or unsubstituted alkylene group having 1 to 10 carbon atoms, or a substituted or unsubstituted phenylene group.

[0067] In the general formula (3) or (4), R¹⁰¹, R¹⁰², R¹⁰³ and R¹⁰⁴ each independently represent a substituent. Preferably, the substituent is a substituted or unsubstituted alkyl group having 1 to 6 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 6 carbon atoms, or a halogen atom, more preferably an unsubstituted alkyl group having 1 to 3 carbon atoms, an unsubstituted alkoxy group having 1 to 3 carbon atoms, a fluorine atom, or a chlorine atom, and even more preferably an unsubstituted alkyl group having 1 to 3 carbon atoms, or an unsubstituted alkoxy group having 1 to 3 carbon atoms.


[0068] The linking group represented by L¹ and L² may bond to any of R¹ to R⁵ in the structure of the general formula (1) constituting Q. Two or more linking groups may bond to one Q to form a crosslinked structure or a network structure.

[0069] Specific examples of the structure of the recurring unit include structures represented by the following general formulae (5) to (8).


Formula (5)




Formula (6)





Formula (7)



Formula (8)



[0070] The polymer having the recurring unit containing the structure represented by any of the general formulae (5) to (8) may be synthesized in such a manner that a hydroxyl group is introduced to any of R¹ to R⁵ in the structure represented by the general formula (1), and the hydroxyl group as a linker is reacted with the following compound to introduce a polymerizable group thereinto, followed by polymerizing the polymerizable group.



[0071] The polymer containing the structure represented by the general formula (1) in the molecule may be a polymer containing only a recurring unit having the structure represented by the general formula (1), or a polymer further containing a recurring unit having another structure. The recurring unit having the structure represented by the general formula (1) contained in the polymer may be only one kind or two or more kinds. Examples of the recurring unit that does not have the structure represented by the general formula (1) include a recurring unit derived from a monomer that is used for ordinary copolymerization. Examples of the recurring unit include a recurring unit derived from a monomer having an ethylenic unsaturated bond, such as ethylene and styrene.

[Synthesis Method for Compound represented by General Formula (1)]

[0072] The compound represented by the general formula (1) is a novel compound.

[0073] The compound represented by the general formula (1) can be synthesized by combining known reactions. For example, a tetrahalogenodicyanobenzene is used as a starting substance, and is reacted with a carbazole in the presence of NaH to give a dicyanobenzene derivative having a donor group of a carbazolyl group introduced thereinto in place of a part of halogen atoms. The resultant dicyanobenzene derivative is reacted with a tributylphenyl stannane in the presence of a catalyst to thereby substitute the halogen atom with a phenyl group to give a dicyanobenzene derivative having a carbazolyl group and a phenyl group and represented by the general formula (1). Regarding the specific conditions for the reaction and the reaction scheme, Synthesis Examples to be given hereinafter may be referred to. The other compounds represented by the general formula (1) can be synthesized using the same process or a known synthesis method.

[Organic Light-Emitting Device]

[0074] The compound represented by the general formula (1) of the present invention is useful as a light-emitting material for organic light-emitting devices. Accordingly, the compound represented by the general formula (1) of the

present invention can be effectively used as a light-emitting material in a light-emitting layer of an organic light-emitting device. In addition, the compound represented by the general formula (1) of the present invention can also be used as a host or assist dopant.

5 [0075] The compound represented by the general formula (1) include a delayed fluorescent material that emits delayed fluorescence. Specifically, the present invention includes an invention of a delayed fluorescent material having a structure represented by the general formula (1), an invention of using the compound represented by the general formula (1) as a delayed fluorescent material, and an invention of a method of using the compound represented by the general formula (1) for emitting delayed fluorescence. An organic light-emitting device using such a compound as a light-emitting material is characterized that it emits delayed fluorescence and has a high emission efficiency. The principle will be described below with reference to an organic electroluminescent device taken as an example.

10 [0076] In an organic electroluminescent device, carriers are injected from an anode and a cathode to a light-emitting material to form an excited state for the light-emitting material, with which light is emitted. In the case of a carrier injection type organic electroluminescent device, in general, excitons that are excited to the excited singlet state are 25% of the total excitons generated, and the remaining 75% thereof are excited to the excited triplet state. Accordingly, the use of phosphorescence, which is light emission from the excited triplet state, provides a high energy utilization. However, the excited triplet state has a long lifetime and thus causes saturation of the excited state and deactivation of energy through mutual action with the excitons in the excited triplet state, and therefore the quantum yield of phosphorescence may generally be often not high. A delayed fluorescent material emits fluorescent light through the mechanism that the energy of excitons transits to the excited triplet state through intersystem crossing or the like, and then transits to the excited singlet state through reverse intersystem crossing due to triplet-triplet annihilation or absorption of thermal energy, thereby emitting fluorescent light. It is considered that among the materials, a thermal activation type delayed fluorescent material emitting light through absorption of thermal energy is particularly useful for an organic electroluminescent device. In the case where a delayed fluorescent material is used in an organic electroluminescent device, the excitons in the excited singlet state normally emit fluorescent light. On the other hand, the excitons in the excited triplet state emit fluorescent light through intersystem crossing to the excited singlet state by absorbing the heat generated by the device. At this time, the light emitted through reverse intersystem crossing from the excited triplet state to the excited singlet state has the same wavelength as fluorescent light since it is light emission from the excited singlet state, but has a longer lifetime (light emission lifetime) than the normal fluorescent light, and thus the light is observed as fluorescent light that is delayed from the normal fluorescent light. The light may be defined as delayed fluorescent light. The use of the thermal activation type reverse intersystem crossing mechanism may raise the proportion of the compound in the excited singlet state, which is generally formed in a proportion only of 25%, to 25% or more through the absorption of the thermal energy after the carrier injection. A compound that emits strong fluorescent light and delayed fluorescent light at a low temperature of lower than 100°C undergoes the intersystem crossing from the excited triplet state to the excited singlet state sufficiently with the heat of the device, thereby emitting delayed fluorescent light, and thus the use of the compound may drastically enhance the light emission efficiency.

25 [0077] Using the compound represented by the general formula (1) of the present invention as a light-emitting material in a light-emitting layer, excellent organic light-emitting devices such as an organic photoluminescent device (organic PL device) and an organic electroluminescent device (organic EL device) can be provided. An organic photoluminescent device has a structure where at least a light-emitting layer is formed on a substrate. An organic electroluminescent device has a structure including at least an anode, a cathode and an organic layer formed between the anode and the cathode. The organic layer contains at least a light-emitting layer, and may be formed of a light-emitting layer alone, or may has one or more other organic layers in addition to a light-emitting layer. The other organic layers include a hole transport layer, a hole injection layer, an electron blocking layer, a hole blocking layer, an electron injection layer, an electron transport layer, and an exciton blocking layer. The hole transport layer may be a hole injection transport layer having a hole injection function, and the electron transport layer may be an electron injection transport layer having an electron injection function. A configuration example of an organic electroluminescent device is shown in Fig. 1. In Fig. 1, 1 is a substrate, 2 is an anode, 3 is a hole injection layer, 4 is a hole transport layer, 5 is a light-emitting layer, 6 is an electron transport layer, and 7 is a cathode.

30 [0078] In the following, the constituent members and the layers of the organic electroluminescent device are described. The description of the substrate and the light-emitting layer given below may apply to the substrate and the light-emitting layer of an organic photoluminescent device.

(Substrate)

35 [0079] The organic electroluminescent device of the invention is preferably supported by a substrate. The substrate is not particularly limited and may be those that have been commonly used in an organic electroluminescent device, and examples thereof used include those formed of glass, transparent plastics, quartz and silicon.

(Anode)

[0080] The anode of the organic electroluminescent device used is preferably formed of, as an electrode material, a metal, an alloy, or an electroconductive compound each having a large work function (4 eV or more), or a mixture thereof. Specific examples of the electrode material include a metal, such as Au, and an electroconductive transparent material, such as CuI, indium tin oxide (ITO), SnO₂ and ZnO. A material that is amorphous and is capable of forming a transparent electroconductive film, such as IDIXO (In₂O₃-ZnO), may also be used. The anode may be formed in such a manner that the electrode material is formed into a thin film by such a method as vapor deposition or sputtering, and the film is patterned into a desired pattern by a photolithography method, or in the case where the pattern may not require high accuracy (for example, approximately 100 μm or more), the pattern may be formed with a mask having a desired shape on vapor deposition or sputtering of the electrode material. In alternative, in the case where a material capable of being coated, such as an organic electroconductive compound, is used, a wet film forming method, such as a printing method and a coating method, may be used. In the case where emitted light is to be taken out through the anode, the anode preferably has a transmittance of more than 10%, and the anode preferably has a sheet resistance of several hundred Ω/sq (ohm per square) or less. The thickness of the anode may be generally selected from a range of from 10 to 1,000 nm, and preferably from 10 to 200 nm, while depending on the material used.

(Cathode)

[0081] The cathode is preferably formed of as an electrode material a metal (which is referred to as an electron injection metal), an alloy, or an electroconductive compound, having a small work function (4 eV or less), or a mixture thereof. Specific examples of the electrode material include sodium, a sodium-potassium alloy, magnesium, lithium, a magnesium-copper mixture, a magnesium-silver mixture, a magnesium-aluminum mixture, a magnesium-indium mixture, an aluminum-aluminum oxide (Al₂O₃) mixture, indium, a lithium-aluminum mixture, and a rare earth metal. Among these, a mixture of an electron injection metal and a second metal that is a stable metal having a larger work function than the electron injection metal, for example, a magnesium-silver mixture, a magnesium-aluminum mixture, a magnesium-indium mixture, an aluminum-aluminum oxide (Al₂O₃) mixture, a lithium-aluminum mixture, and aluminum, is preferred from the standpoint of the electron injection property and the durability against oxidation and the like. The cathode may be produced by forming the electrode material into a thin film by such a method as vapor deposition or sputtering. The cathode preferably has a sheet resistance of several hundred Ω/sq (ohm per square) or less, and the thickness thereof may be generally selected from a range of from 10 nm to 5 μm, and preferably from 50 to 200 nm. For transmitting the emitted light, any one of the anode and the cathode of the organic electroluminescent device is preferably transparent or translucent, thereby enhancing the light emission luminance.

[0082] The cathode may be formed with the electroconductive transparent materials described for the anode, thereby forming a transparent or translucent cathode, and by applying the cathode, a device having an anode and a cathode, both of which have transmittance, may be produced.

(Light-emitting Layer)

[0083] The light-emitting layer is a layer in which holes and electrons injected from an anode and a cathode are recombined to give excitons for light emission. A light-emitting material may be used singly in the light-emitting layer, but preferably, the layer contains a light-emitting material and a host material. As the light-emitting material, one or more selected from a group of the compounds of the present invention represented by the general formula (1) can be used. In order that the organic electroluminescent device and the organic photoluminescent device of the present invention can express a high light emission efficiency, it is important to confine the singlet exciton and the triplet exciton formed in the light-emitting material to the light-emitting material. Accordingly, preferably, a host material is used in addition to the light-emitting material in the light-emitting layer. As the host material, an organic compound, of which at least any one of the excited singlet energy and the excited triplet energy is higher than that of the light-emitting material of the present invention, may be used. As a result, the singlet exciton and the triplet exciton formed in the light-emitting material of the present invention can be confined to the molecule of the light-emitting material of the present invention to sufficiently derive the light emission efficiency thereof. Needless-to-say, there may be a case where a high light emission efficiency could be attained even though the singlet exciton and the triplet exciton could not be sufficiently confined, and therefore, any host material capable of realizing a high light emission efficiency can be used in the present invention with no specific limitation. In the organic light-emitting device or the organic electroluminescent device of the present invention, light emission occurs from the light-emitting material of the present invention contained in the light-emitting layer. The light emission contains both of fluorescent emission and delayed fluorescent emission. In addition, a part of light emission may be partially from a host material.

[0084] The content of the compound represented by the general formula (1) in the light-emitting layer is preferably

less than 50% by weight. Further, the upper limit of the content of the compound represented by the general formula (1) is preferably less than 30% by weight, and the upper limit of the content may be, for example, less than 20% by weight, less than 10% by weight, less than 5% by weight, less than 3% by weight, less than 1% by weight, or less than 0.5% by weight. Preferably, the lower limit is 0.001% by weight or more, and may be, for example, more than 0.01% by weight, more than 0.1% by weight, more than 0.5% by weight, or more than 1% by weight.

[0085] The host material in the light-emitting layer is preferably an organic compound having hole transport competence and electron transport competence, capable of preventing prolongation of emission wavelength and having a high glass transition temperature.

[0086] The compound represented by the general formula (1) can be used as a host material in the light-emitting layer.

(Injection Layer)

[0087] The injection layer is a layer that is provided between the electrode and the organic layer, for decreasing the driving voltage and enhancing the light emission luminance, and includes a hole injection layer and an electron injection layer, which may be provided between the anode and the light-emitting layer or the hole transport layer and between the cathode and the light emitting layer or the electron transport layer. The injection layer may be provided depending on necessity.

(Blocking Layer)

[0088] The blocking layer is a layer that is capable of inhibiting charges (electrons or holes) and/or excitons present in the light-emitting layer from being diffused outside the light-emitting layer. The electron blocking layer may be disposed between the light-emitting layer and the hole transport layer, and inhibits electrons from passing through the light-emitting layer toward the hole transport layer. Similarly, the hole blocking layer may be disposed between the light-emitting layer and the electron transport layer, and inhibits holes from passing through the light-emitting layer toward the electron transport layer. The blocking layer may also be used for inhibiting excitons from being diffused outside the light-emitting layer. Thus, the electron blocking layer and the hole blocking layer each may also have a function as an exciton blocking layer. The term "the electron blocking layer" or "the exciton blocking layer" referred to herein is intended to include a layer that has both the functions of an electron blocking layer and an exciton blocking layer by one layer.

(Hole Blocking Layer)

[0089] The hole blocking layer has the function of an electron transport layer in a broad sense. The hole blocking layer has a function of inhibiting holes from reaching the electron transport layer while transporting electrons, and thereby enhances the recombination probability of electrons and holes in the light-emitting layer. As the material for the hole blocking layer, the material for the electron transport layer to be mentioned below may be used optionally.

(Electron Blocking Layer)

[0090] The electron blocking layer has the function of transporting holes in a broad sense. The electron blocking layer has a function of inhibiting electrons from reaching the hole transport layer while transporting holes, and thereby enhances the recombination probability of electrons and holes in the light-emitting layer.

(Exciton Blocking Layer)

[0091] The exciton blocking layer is a layer for inhibiting excitons generated through recombination of holes and electrons in the light-emitting layer from being diffused to the charge transporting layer, and the use of the layer inserted enables effective confinement of excitons in the light-emitting layer, and thereby enhances the light emission efficiency of the device. The exciton blocking layer may be inserted adjacent to the light-emitting layer on any of the side of the anode and the side of the cathode, and on both the sides. Specifically, in the case where the exciton blocking layer is present on the side of the anode, the layer may be inserted between the hole transport layer and the light-emitting layer and adjacent to the light-emitting layer, and in the case where the layer is inserted on the side of the cathode, the layer may be inserted between the light-emitting layer and the cathode and adjacent to the light-emitting layer. Between the anode and the exciton blocking layer that is adjacent to the light-emitting layer on the side of the anode, a hole injection layer, an electron blocking layer and the like may be provided, and between the cathode and the exciton blocking layer that is adjacent to the light-emitting layer on the side of the cathode, an electron injection layer, an electron transport layer, a hole blocking layer and the like may be provided. In the case where the blocking layer is provided, preferably, at least one of the excited singlet energy and the excited triplet energy of the material used as the blocking layer is higher

than the excited singlet energy and the excited triplet energy of the light-emitting layer, respectively, of the light-emitting material.

(Hole Transport Layer)

[0092] The hole transport layer is formed of a hole transport material having a function of transporting holes, and the hole transport layer may be provided as a single layer or plural layers.

[0093] The hole transport material has one of injection or transporting property of holes and blocking property of electrons, and may be any of an organic material and an inorganic material. Examples of known hole transport materials that may be used herein include a triazole derivative, an oxadiazole derivative, an imidazole derivative, a carbazole derivative, an indolocarbazole derivative, a polyaryalkane derivative, a pyrazoline derivative, a pyrazolone derivative, a phenylenediamine derivative, an arylamine derivative, an amino-substituted chalcone derivative, an oxazole derivative, a styrylanthracene derivative, a fluorenone derivative, a hydrazone derivative, a stilbene derivative, a silazane derivative, an aniline copolymer and an electroconductive polymer oligomer, particularly a thiophene oligomer. Among these, a porphyrin compound, an aromatic tertiary amine compound and a styrylamine compound are preferably used, and an aromatic tertiary amine compound is more preferably used.

(Electron Transport Layer)


[0094] The electron transport layer is formed of a material having a function of transporting electrons, and the electron transport layer may be a single layer or may be formed of plural layers.

[0095] The electron transport material (often also acting as a hole blocking material) may have a function of transmitting the electrons injected from a cathode to a light-emitting layer. The electron transport layer usable here includes, for example, nitro-substituted fluorene derivatives, diphenylquinone derivatives, thiopyran dioxide derivatives, carbodiimides, fluorenylidene methane derivatives, anthraquinodimethane and anthrone derivatives, oxadiazole derivatives, etc. Further, thiadiazole derivatives derived from the above-mentioned oxadiazole derivatives by substituting the oxygen atom in the oxadiazole ring with a sulfur atom, and quinoxaline derivatives having a quinoxaline ring known as an electron-attractive group are also usable as the electron transport material. Further, polymer materials prepared by introducing these materials into the polymer chain, or having these material in the polymer main chain are also usable.



[0096] In producing the organic electroluminescent device, the compound represented by the general formula (1) may be used not only in one organic layer (for example, an electron transport layer) but also in multiple organic layers. In so doing, the compounds represented by the general formula (1) used in different organic layers may be the same as or different from each other. For example, the compound represented by the general formula (1) may be used in the above-mentioned injection layer, the blocking layer, the hole blocking layer, the electron blocking layer, the exciton blocking layer and the hole transport layer, in addition to the electron transport layer and the light-emitting layer. The method for forming these layers is not specifically limited, and the layers may be formed according to any of a dry process or a wet process.

[0097] Preferred materials for use for the organic electroluminescent device are concretely exemplified below. However, the materials for use in the present invention are not limitatively interpreted by the following exemplary compounds. Compounds, even though exemplified as materials having a specific function, can also be used as other materials having any other function.



[0098] First, preferred compounds for use as a host material in a light-emitting layer are mentioned below.





5



10





15




20

25





30

35





40

45




50


55




5




10




15



20




25





30

35




40




45

$R_2 - R_7 = \text{H or substituent}$
 $L = \text{ligand}$


50




55



5




10




15

20




25

30



35

40





45

50

55

5





R = alkyl, aryl

R = alkyl, aryl


10

15



20



25



30

[0099] Next, preferred compounds for use as a hole injection material are mentioned below.


35




40

45



50





55



5





10




15

20





25



30


[0100] Next, preferred compounds for use as a hole transport material are mentioned below.

35



40


45




50

55

5



10




15

20

25

30


35



40

R = alkyl, aryl, alkoxy, aryloxy,
9,9'-dialkylfluorene


45



50

55

5




10

15

20


25



30


35

40




45

50




55

5




10




15


20




25



30




35




40

45




50




55


5




10




15




20




25



30



35



40

45

50

55

5



10

15

20

25

30




[0101] Next, preferred compounds for use as an electron blocking material are mentioned below.

35


40

45



50

55






5

10

15




20



[0102] Next, preferred compounds for use as a hole blocking material are mentioned below.

25



30



35




40

45




50

55



5


10




15

[0103] Next, preferred compounds for use as an electron transport material are mentioned below.

20




25




30

35



40

45




R = H, alkyl, aryl,
heteroaryl


50

55

5




10




15

20




25

30



35

40




45

50


55

5




10


15






20






25



30



35







40

[0104] Next, preferred compounds for use as an electron injection material are mentioned below.

45 LiF, CsF

[0105]




50



55



[0106] Further, preferred compounds for use as additional materials are mentioned below. For example, these are considered to be added as a stabilization material.

5



10

15



20

[0107] The organic electroluminescent device thus produced by the aforementioned method emits light on application of an electric field between the anode and the cathode of the device. In this case, when the light emission is caused by the excited singlet energy, light having a wavelength that corresponds to the energy level thereof may be confirmed as fluorescent light and delayed fluorescent light. When the light emission is caused by the excited triplet energy, light having a wavelength that corresponds to the energy level thereof may be confirmed as phosphorescent light. The normal fluorescent light has a shorter light emission lifetime than the delayed fluorescent light, and thus the light emission lifetime may be distinguished between the fluorescent light and the delayed fluorescent light.

25

[0108] On the other hand, the phosphorescent light may substantially not be observed with an ordinary organic compound such as the compound of the present invention at room temperature since the excited triplet energy thereof is unstable, and the rate constant of thermal deactivation of the compound is large while the rate constant of light emission is small, and therefore the compound immediately deactivates. The excited triplet energy of an ordinary organic compound may be measured by observing light emission under an extremely low temperature condition.

30

[0109] The organic electroluminescent device of the invention may be applied to any of a single device, a structure with plural devices disposed in an array, and a structure having anodes and cathodes disposed in an X-Y matrix. According to the present invention using the compound represented by the general formula (1) in a light-emitting layer, an organic light-emitting device having a markedly improved light emission efficiency can be obtained. The organic light-emitting device such as the organic electroluminescent device of the present invention may be applied to a further wide range of purposes. For example, an organic electroluminescent display apparatus may be produced with the organic electroluminescent device of the invention, and for the details thereof, reference may be made to S. Tokito, C. Adachi and H. Murata, "Yuki EL Display" (Organic EL Display) (Ohmsha, Ltd.). In particular, the organic electroluminescent device of the invention may be applied to organic electroluminescent illumination and backlight which are highly demanded.

35

40

45

Examples

[0110] The features of the present invention will be described more specifically with reference to Synthesis Examples and Examples given below. The materials, processes, procedures and the like shown below may be appropriately modified unless they deviate from the substance of the invention. Accordingly, the scope of the invention is not construed as being limited to the specific examples shown below.

50

[0111] Hereinunder the light emission characteristics were evaluated using Source Meter (available from Keithley Instruments Corporation: 2400 series), a semiconductor parameter analyzer (available from Agilent Corporation, E5273A), an optical power meter device (available from Newport Corporation, 1930C), an optical spectroscope (available from Ocean Optics Corporation, USB2000), a spectroradiometer (available from Topcon Corporation, SR-3), a nitrogen gas laser (available from USHO Inc., excitation wavelength 337 nm) and a streak camera (available from Hamamatsu Photonics K.K., Model C4334).

55

EP 3 647 392 A1

[Measurement of difference ΔE_{ST} between lowest excited singlet energy level (E_{S1}) and lowest excited triplet energy level (E_{T1})]

5 **[0112]** A difference ΔE_{ST} between a lowest excited singlet energy level (E_{S1}) and a lowest excited triplet energy level (E_{T1}) of a compound was determined by calculating the lowest excited singlet energy level (E_{S1}) and the lowest excited triplet energy level (E_{T1}) from the fluorescence spectrum and the phosphorescence spectrum of the compound, according to an equation, $\Delta E_{ST} = E_{S1} - E_{T1}$.

10 (1) Lowest excited singlet energy level (E_{S1})

15 **[0113]** A thin film or a toluene solution (concentration: 10^{-5} mol/L) of the compound to be analyzed was prepared as a measurement sample, and the fluorescent spectrum of the sample was measured at room temperature (300 K). For the fluorescent spectrum, the emission intensity was on the vertical axis and the wavelength was on the horizontal axis. A tangent line was drawn to the rising of the emission spectrum on the short wavelength side, and the wavelength value λ_{edge} [nm] at the intersection between the tangent line and the horizontal axis was read. The wavelength value was converted into an energy value according to the following conversion expression to calculate E_{S1} .
Conversion Expression:

$$20 \quad E_{S1} [\text{eV}] = 1239.85/\lambda_{edge}$$

25 **[0114]** For the measurement of the emission spectrum, an LED light source (available from Thorlabs Corporation, M340L4) was used as an excitation light source along with a detector (available from Hamamatsu Photonics K.K., PMA-50).

(2) Lowest excited triplet energy level (E_{T1})

30 **[0115]** The same sample as that for measurement of the lowest excited singlet energy level (E_{S1}) was cooled to 77 [K] with liquid nitrogen, and the sample for phosphorescence measurement was irradiated with excitation light (340 nm), and using a detector, the phosphorescence thereof was measured. The emission after 100 milliseconds from irradiation with the excitation light was drawn as a phosphorescent spectrum. A tangent line was drawn to the rising of the phosphorescent spectrum on the short wavelength side, and the wavelength value λ_{edge} [nm] at the intersection between the tangent line and the horizontal axis was read. The wavelength value was converted into an energy value according to the following conversion expression to calculate E_{T1} .

35 Conversion Expression:

$$40 \quad E_{T1} [\text{eV}] = 1239.85/\lambda_{edge}$$

45 **[0116]** The tangent line to the rising of the phosphorescent spectrum on the short wavelength side was drawn as follows. While moving on the spectral curve from the short wavelength side of the phosphorescent spectrum toward the maximum value on the shortest wavelength side among the maximum values of the spectrum, a tangent line at each point on the curve toward the long wavelength side was taken into consideration. With rising thereof (that is, with increase in the vertical axis), the inclination of the tangent line increases. The tangent line drawn at the point at which the inclination value has a maximum value was referred to as the tangent line to the rising on the short wavelength side of the phosphorescent spectrum.

50 **[0117]** The maximum point having a peak intensity of 10% or less of the maximum peak intensity of the spectrum was not included in the maximum value on the above-mentioned shortest wavelength side, and the tangent line drawn at the point which is closest to the maximum value on the shortest wavelength side and at which the inclination value has a maximum value was referred to as the tangent line to the rising on the short wavelength side of the phosphorescent spectrum.


55 [Calculation of difference ΔE_{ST} between lowest excited singlet energy level (E_{S1}) and lowest excited triplet energy level (E_{T1}) according to computational chemistry]

[0118] In this Example, the difference ΔE_{ST} between a lowest excited singlet energy level (E_{S1}) and a lowest excited triplet energy level (E_{T1}) of a compound was calculated according to computational chemistry. For computational chem-


istry, Gaussian 09 and Gaussian 16 programs by Gaussian Corporation were used. Here, for optimization of the molecular structure in a ground singlet state S_0 and for calculation of an electron state, a B3LYP/6-31G (d) method was used; and for calculation of a lowest excited singlet energy level (E_{S1}) and a lowest excited triplet energy level (E_{T1}), a time-dependent density-functional calculation method (TD-DFT) was used. From the resultant data of a lowest excited singlet energy level (E_{S1}) and a lowest excited triplet energy level (E_{T1}), ΔE_{ST} was calculated according to $\Delta E_{ST} = E_{S1} - E_{T1}$.

[Compounds used in Examples]


[0119] Structures of the compounds of the invention and the comparative compounds used in Examples, and mCBP used as a host in a doped film are shown below.




Comparative Compound 1-1




Invention Compound 1-1




Comparative Compound 2-1



Invention Compound 2-1




Comparative Compound 3-1




Invention Compound 3-1


5
10
15
20
25
30
35
40
45
50
55




Invention Compound 3-2




Invention Compound 3-3




Invention Compound 3-4



Invention Compound 3-5




Comparative Compound 4-1




Invention Compound 4-1

5



Comparative Compound 5-1


10



Invention Compound 5-1


15

20



Comparative Compound 6-1


25



Invention Compound 6-1


30

35



Invention Compound 6-2


40



Invention Compound 6-3

45


50



Invention Compound 6-4


55

5




Comparative Compound 7-1

10




Invention Compound 7-1

15




Comparative Compound 8-1

20




Invention Compound 8-1

25




Invention Compound 8-2

30




Invention Compound 8-3

35



Invention Compound 8-4

45




Invention Compound 8-5


50

55

5




Comparative Compound 9-1




Invention Compound 9-1

10

15




Invention Compound 9-2




Invention Compound 9-3

20

25




Invention Compound 9-4




Invention Compound 9-5

30

35




Comparative Compound 10-1



Invention Compound 10-1

40

45




Invention Compound 10-2

50

55

5

10



mCBP

[A] Synthesis of Compounds

15


(Synthesis Example 1) Synthesis of invention compound 6-1

(1) Synthesis of intermediate 1

20

[0120]

25



30

Intermediate 1

35

[0121] 0.94 mg (23.5 mmol) of 60% sodium hydride was put into a 300-mL three-neck flask, the sodium hydride was dried, then the flask was purged with nitrogen, and 200 mL of tetrahydrofuran (dewatered solvent) was added and stirred. 3.14 g (18.8 mmol) of 9H-carbazole was added to the mixture, and in a nitrogen stream atmosphere, this was stirred at room temperature for 60 minutes. After stirring, 2.50 g (9.40 mmol) of tetrachloroterephthalonitrile was added to the mixture, and the mixture was stirred at room temperature in a nitrogen atmosphere for 12 hours. After stirring, water was added to the mixture and stirred, and the precipitate was filtered out. After filtration, the mixture was purified through silica gel column chromatography. In column chromatography, a mixed solvent of toluene/hexane was used as a developing solvent. The resultant fraction was concentrated to give a solid, which was then recrystallized with a mixed solvent of acetone and hexane to give a yellow powdery solid in a yield amount of 2.01 g and a yield of 40.3%.

40


$^1\text{H NMR}$ (500 Hz, CDCl_3 , δ): 8.21(d, $J=10$ Hz, 2H), 7.54(td, $J=7.5$ Hz, $J=1$ Hz, 2H), 7.45(td, $J=7.5$ Hz, $J=1$ Hz, 2H), 7.15(d, $J=8.5$ Hz, 2H)

45

Mass Spectroscopy Analysis: 526.0

50

55




(2) Synthesis of invention compound 6-1

15

[0122] 1.55 g (2.93 mmol) of the intermediate 1, 3.2 g (8.8 mmol) of tributylphenyl stannane, 0.10 g (0.093 mmol) of tris(dibenzylideneacetone)dipalladium(0) and 0.26 g (0.88 mmol) of tri(o-tolyl) phosphine were put into a 200-mL three-neck flask, and the flask was purged with nitrogen. 70 mL of toluene was added to the mixture, and in a nitrogen atmosphere, this was stirred at 100°C for 24 hours. The mixture was purified through silica gel column chromatography. In column chromatography, a mixed solvent of ethyl acetate/hexane = 1/9 was used as a developing solvent. The resultant fraction was concentrated to give a solid, which was then recrystallized with a mixed solvent of acetone and hexane to give a yellow powdery solid in a yield amount of 0.36 g and a yield of 20.2%.
¹H NMR (500 Hz, CDCl₃, δ): 8.03(d, J=7.9 Hz, 4H), 7.42(t, J=8.0 Hz, 4H), 7.28(t, J=7.9 Hz, 4H), 7.19(d, J=8.1 Hz, 4H), 7.14(d, J=7.0 Hz, 4H), 7.09(t, J=7.9 Hz, 2H), 7.42(t, J=7.7 Hz, 4H)
 20
 25 Mass Spectroscopy Analysis: 610.10

(Synthesis Example 2) Synthesis of invention compound 8-1

(1) Synthesis of intermediate 2




45

[0124] 0.26 g (1.0 mmol) of tetrachloroterephthalonitrile, 0.81 g (2.2 mmol) of tributylphenyl stannane, 0.03 g (0.03 mmol) of tris(dibenzylideneacetone)dipalladium(0) and 0.09 g (0.3 mmol) of tri(o-tolyl) phosphine were put into a flask, the flask was purged with nitrogen, then 20 mL of toluene was added, and stirred at 120°C in a nitrogen atmosphere for 24 hours. After stirring, the mixture was restored to room temperature, and purified through silica gel column chromatography. Toluene and hexane were used as a developing solvent in column chromatography. The resultant fraction was concentrated to give a solid, which was then recrystallized with dichloromethane and hexane to give an intermediate 2 in a yield amount of 0.070 g and a yield of 20%.
 50
 Mass Spectroscopy Analysis: 347.98

(2) Synthesis of invention compound 8-1

55

[0125]



20 **[0126]** 0.17 g (0.5 mmol) of the intermediate 2, 0.31 g (1.1 mmol) of 4-(9H-carbazolyl)phenylboronic acid and 15 mL of dewatered toluene were put into a 15-mL Schlenk tube. 0.11 g (0.1 mmol) of tetrakis(triphenylphosphine)palladium(0), and 6 mL of an aqueous solution of 2 M potassium carbonate were added to the mixture and stirred at 80°C for 72 hours. After stirring, the mixture was restored to room temperature, and the precipitate in the mixture was taken out through filtration. The precipitate was washed with water, hexane and methanol in that order to give an invention compound 8-1.

25 Calculation of ΔE_{ST} according to computational chemistry

30 **[0127]** The above-mentioned invention compounds and comparative compounds were analyzed according to computational chemistry to determine the lowest excited singlet energy level (E_{S1}) and the lowest excited triplet energy level (E_{T1}) thereof, and the energy difference ΔE_{ST} therebetween was calculated and shown in Tables 6 to 15. "Relative value" of the invention compound in each Table is a relative value of ΔE_{ST} of each compound as calculated on the basis of ΔE_{ST} , 1.00, of the corresponding comparative compound (comparative compound shown in the same Table).

[Table 6]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 1-1	2.842	2.501	0.341	1.00
Invention Compound 1-1	2.627	2.473	0.154	0.45

40 [Table 7]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 2-1	2.665	2.489	0.176	1.00
Invention Compound 2-1	2.598	2.553	0.045	0.25

45 [Table 8]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 3-1	2.806	2.601	0.205	1.00
Invention Compound 3-1	2.584	2.524	0.061	0.30
Invention Compound 3-2	2.629	2.570	0.059	0.29
Invention Compound 3-3	2.651	2.591	0.061	0.29
Invention Compound 3-4	2.657	2.596	0.061	0.30
Invention Compound 3-5	2.662	2.604	0.059	0.29

EP 3 647 392 A1

[Table 9]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 4-1	2.704	2.599	0.105	1.00
Invention Compound 4-1	2.719	2.663	0.055	0.53

[Table 10]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 5-1	2.684	2.568	0.116	1.00
Invention Compound 5-1	2.487	2.449	0.039	0.33

[Table 11]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 6-1	2.477	2.294	0.183	1.00
Invention Compound 6-1	2.498	2.420	0.079	0.43
Invention Compound 6-2	2.509	2.426	0.084	0.46
Invention Compound 6-3	2.493	2.415	0.078	0.42
Invention Compound 6-4	2.477	2.414	0.063	0.35

[Table 12]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 7-1	2.531	2.097	0.434	1.00
Invention Compound 7-1	2.379	2.133	0.246	0.57

[Table 13]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 8-1	2.577	2.419	0.158	1.00
Invention Compound 8-1	2.706	2.642	0.064	0.40
Invention Compound 8-2	2.566	2.516	0.050	0.32
Invention Compound 8-3	2.554	2.515	0.039	0.24
Invention Compound 8-4	2.452	2.375	0.077	0.49
Invention Compound 8-5	2.586	2.574	0.012	0.08

[Table 14]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 9-1	2.586	2.336	0.250	1.00
Invention Compound 9-1	2.746	2.525	0.221	0.88
Invention Compound 9-2	2.800	2.618	0.182	0.73

(continued)

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Invention Compound 9-3	2.755	2.560	0.196	0.78
Invention Compound 9-4	2.766	2.761	0.004	0.02
Invention Compound 9-5	2.778	2.776	0.003	0.01

[Table 15]

	E_{S1} (eV)	E_{T1} (eV)	ΔE_{ST} (eV)	Relative Value
Comparative Compound 10-1	2.517	2.236	0.281	1.00
Invention Compound 10-1	2.534	2.434	0.100	0.35
Invention Compound 10-2	2.452	2.375	0.077	0.27

[0128] As shown in these Tables, the invention compounds having a cyano group, an aryl group and a donor group had a smaller ΔE_{ST} value as compared with the corresponding comparative compounds (comparative compounds not having an aryl group Ar)

[C] Production and evaluation of thin film

(Example 1) Production and evaluation of thin film of invention compound 6-1 alone

[0129] According to a vacuum evaporation method, the invention compound 6-1 was vapor-deposited on a quartz substrate under a condition of a vacuum degree of less than 1×10^{-3} Pa to form thereon a thin film of the invention compound 6-1 alone in a thickness of 70 nm.

[0130] Using a 337 nm excitation light, the resultant thin film was analyzed to observe the emission spectrum thereof, and the peak wavelength (λ_{max}) of the film was 530 nm. Fig. 2 shows a fluorescence spectrum and a phosphorescence spectrum of the film. Fig. 3 shows a transient decay curve in emission of the thin film observed using a 337 nm excitation light. The lifetime (τ_d) of delayed fluorescence was 5.62 μ s (microseconds). ΔE_{ST} was calculated and was 0.123 eV. Further, using a 300 nm excitation light, the photoluminescence quantum yield (PLQY) of the film was measured, and was 36.0% in air and 39.9% in nitrogen.

(Example 2) Production and evaluation of doped thin film with invention compound 6-1

[0131] According to a vacuum evaporation method, the invention compound 6-1 and mCBP were vapor-deposited from different evaporation sources on a quartz substrate under a condition of a vacuum degree of less than 1×10^{-3} Pa to form thereon a thin film having a thickness of 100 nm and having a concentration of the invention compound 6-1 of 20% by weight.

[0132] Using a 337 nm excitation light, the resultant thin film was analyzed to observe the emission spectrum thereof, and the peak wavelength (λ_{max}) of the film was 518 nm. Fig. 4 shows a transient decay curve in emission of the thin film observed using a 337 nm excitation light. The lifetime (τ_d) of delayed fluorescence was 9.16 μ s (microseconds). Further, using a 300 nm excitation light, the photoluminescence quantum yield (PLQY) of the film was measured, and was 65.7% in nitrogen.

(Comparative Example 1) Production and evaluation of thin film of comparative compound 6-1 alone

[0133] In the same manner as in Example 1 except that the comparative compound 6-1 was used in place of the invention compound 6-1, a thin film of the comparative compound 6-1 alone was formed in a thickness of 70 nm.

[0134] ΔE_{ST} of the resultant thin film was measured and was 0.213 eV.

(Comparative Example 2) Production and evaluation of doped thin film with comparative compound 6-1

[0135] In the same manner as in Example 2 except that the comparative compound 6-1 was used in place of the invention compound 6-1, a thin film having a thickness of 100 nm and having a concentration of the comparative compound

6-1 of 20% by weight was formed.

[0136] Fig. 5 shows a transient decay curve in emission of the resultant thin film observed using a 337 nm excitation light. In addition, the transient decay curve in emission in Example 4 shown in Fig. 4 is additionally shown in Fig. 5 by changing the scale of the horizontal axis and the vertical axis. The lifetime (τ_d) of delayed fluorescence of the thin film of Comparative Example 2 was 76.8 μ s (microseconds).


[0137] The measured results of Example 1 and Comparative Example 1 are compared. ΔE_{ST} of the thin film of the invention compound 6-1 produced in Example 1 was about 0.58 times ΔE_{ST} of the thin film of the comparative compound 6-1 produced in Comparative Example 1. The computational results in Table 11 are referred to. ΔE_{ST} of the invention compound 6-1 is about 0.43 times ΔE_{ST} of the thin film of the comparative compound 6-1. From these, it is confirmed that the computational results of ΔE_{ST} well correspond to the tendency of the measured value thereof. The lifetime (τ_d) of delayed fluorescence of the thin film of Example 2 is about 0.12 times the lifetime (τ_d) of delayed fluorescence of the thin film of Comparative Example 2, that is, τ_d of the invention compound 6-1 is far shorter than τ_d of the comparative compound 6-1. This is because the invention compound 6-1 has a small value of ΔE_{ST} and therefore can readily undergo reverse intersystem crossing from the excited triplet state to the excited singlet state.

[0138] The above-mentioned measurement results and computational results show that the invention compounds employed in these Examples all have a smaller value ΔE_{ST} than the corresponding comparative compounds, and accordingly, it is known that the invention compounds can readily undergo reverse intersystem crossing, that is, the invention compounds have a short delayed fluorescence lifetime. The electroluminescent devices using such a compound that has a short emission lifetime are relieved from emission efficiency reduction owing to accumulation of excitons in a high-current density region and from degradation of devices in long-term driving, and therefore exhibit excellent device performance. From these results, it is known that the compound represented by the general formula (1) can significantly contribute toward realization of such excellent light-emitting devices.

Claims

1. A light-emitting material comprising a compound represented by the following general formula (1):

General Formula (1)



wherein R^1 to R^5 each independently represent a hydrogen atom or a substituent;

one of R^1 to R^5 is a cyano group,

one to three of R^1 to R^5 each are an aryl group Ar optionally substituted with an alkyl group or an aryl group (in which the benzene ring to constitute the aryl group Ar may be condensed with a ring that may optionally contain an oxygen atom or a sulfur atom in addition to carbon atoms as a ring skeleton-constituting atom, but is not condensed with a ring containing any other hetero atom than an oxygen atom and a sulfur atom as a ring skeleton-constituting atom), and when two or more of R^1 to R^5 are Ar's, these Ar's may be the same as or different from each other,

one to three of R^1 to R^5 each are a donor group D (but excepting one that corresponds to Ar), and when two or more of R^1 to R^5 are D's, these D's may be the same as or different from each other.


2. The light-emitting material according to claim 1, wherein R^1 to R^5 each independently represent a cyano group, Ar or D.
3. The light-emitting material according to claim 1 or 2, wherein D contains a substituted amino group.
4. The light-emitting material according to claim 3, wherein D is a group represented by the following general formula

(2a):

General Formula (2a)

5

10



15

wherein R^{11} and R^{12} each independently represent a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted aryl group, or a substituted or unsubstituted heteroaryl group; L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; R^{11} and R^{12} may bond to each other to form a cyclic structure; * indicates a bonding position to the carbon atom (C) constituting a ring skeleton of the benzene ring in the general formula (1).

20


5. The light-emitting material according to claim 3, wherein D is a group represented by the following general formula (2b):

General Formula (2b)

25

30

35



40

wherein R^{21} to R^{28} each independently represent a hydrogen atom or a substituent; L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; R^{21} and R^{22} , R^{22} and R^{23} , R^{23} and R^{24} , R^{24} and R^{25} , R^{26} and R^{27} , and R^{27} and R^{28} each may bond to each other to form a linking group necessary for forming a cyclic structure; and R^{25} and R^{26} may bond to each other to form a single bond or a linking group.

45

6. The light-emitting material according to claim 3, wherein D is a group represented by the following general formula (2c):

50


55

General Formula (2c)

5

10

15



20

wherein R^{31} to R^{40} each independently represent a hydrogen atom or a substituent; L represents a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; R^{31} and R^{32} , R^{32} and R^{33} , R^{33} and R^{34} , R^{34} and R^{35} , R^{36} and R^{37} , R^{37} and R^{38} , R^{38} and R^{39} , and R^{39} and R^{40} each may bond to each other to form a linking group necessary for forming a cyclic structure; R^{35} and R^{36} may bond to each other to form a single bond or a linking group; and * indicates a bonding position to the carbon atom (C) constituting the ring skeleton of the benzene ring in the general formula (1).

25

7. The light-emitting material according to any one of claims 4 to 6, wherein L is a single bond.

8. The light-emitting material according to any one of claims 4 to 6, wherein R^3 is a cyano group, and L is a substituted or unsubstituted phenylene group.

30

9. The light-emitting material according to any one of claims 4 to 8, wherein D is a group represented by any of the following general formulae (3) to (6):

General Formula (3)


35

40

45

50

55




General Formula (4)

5

10

15




General Formula (5)

20

25

30




General Formula (6)

35

40

45




50

55

wherein R^{41} to R^{46} , R^{51} to R^{60} , R^{61} to R^{68} , and R^{71} to R^{78} each independently represent a hydrogen atom or a substituent; L^{11} to L^{14} each independently represent a single bond, a substituted or unsubstituted arylene group, or a substituted or unsubstituted heteroarylene group; X in the general formula (6) represents an oxygen atom, a sulfur atom, a substituted or unsubstituted nitrogen atom, a substituted or unsubstituted carbon atom, a substituted or unsubstituted silicon atom or a carbonyl group, which is divalent and which has a linking chain length of one atom, or represents a substituted or unsubstituted ethylene group, a substituted or unsubstituted vinylene group, a substituted or unsubstituted o-arylene group or a substituted or unsubstituted o-heteroarylene group, which is divalent and which has a bonding chain length of two atoms.

10. A compound represented by the following general formula (1):


General Formula (1)



15 wherein R^1 to R^5 each independently represent a hydrogen atom or a substituent;
 one of R^1 to R^5 is a cyano group,
 one to three of R^1 to R^5 each are an aryl group Ar optionally substituted with an alkyl group or an aryl group (in
 20 which the benzene ring to constitute the aryl group Ar may be condensed with a ring that may optionally contain
 an oxygen atom or a sulfur atom in addition to carbon atoms as a ring skeleton-constituting atom, but is not
 condensed with a ring containing any other hetero atom than an oxygen atom and a sulfur atom as a ring
 skeleton-constituting atom), and when two or more of R^1 to R^5 are Ar's, these Ar's may be the same as or
 different from each other,
 one to three of R^1 to R^5 each are a donor group D (but excepting one that corresponds to Ar), and when two
 25 or more of R^1 to R^5 are D's, these D's may be the same as or different from each other.

11. A delayed fluorescent material comprising a compound represented by the following general formula (1):


General Formula (1)



45 wherein R^1 to R^5 each independently represent a hydrogen atom or a substituent;
 one of R^1 to R^5 is a cyano group,
 one to three of R^1 to R^5 each are an aryl group Ar optionally substituted with an alkyl group or an aryl group (in
 which the benzene ring to constitute the aryl group Ar may be condensed with a ring that may optionally contain
 an oxygen atom or a sulfur atom in addition to carbon atoms as a ring skeleton-constituting atom, but is not
 condensed with a ring containing any other hetero atom than an oxygen atom and a sulfur atom as a ring
 skeleton-constituting atom), and when two or more of R^1 to R^5 are Ar's, these Ar's may be the same as or
 different from each other,
 50 one to three of R^1 to R^5 each are a donor group D (but excepting one that corresponds to Ar), and when two
 or more of R^1 to R^5 are D's, these D's may be the same as or different from each other.

12. A light-emitting device comprising a compound represented by the following general formula (1):

General Formula (1)



wherein R^1 to R^5 each independently represent a hydrogen atom or a substituent;
one of R^1 to R^5 is a cyano group,
one to three of R^1 to R^5 each are an aryl group Ar optionally substituted with an alkyl group or an aryl group (in which the benzene ring to constitute the aryl group Ar may be condensed with a ring that may optionally contain an oxygen atom or a sulfur atom in addition to carbon atoms as a ring skeleton-constituting atom, but is not condensed with a ring containing any other hetero atom than an oxygen atom and a sulfur atom as a ring skeleton-constituting atom), and when two or more of R^1 to R^5 are Ar's, these Ar's may be the same as or different from each other,
one to three of R^1 to R^5 each are a donor group D (but excepting one that corresponds to Ar), and when two or more of R^1 to R^5 are D's, these D's may be the same as or different from each other.

13. The light-emitting device according to claim 12, which emits delayed fluorescence.
14. The light-emitting device according to claim 12 or 13, wherein the light-emitting device has a light-emitting layer and the light-emitting layer contains the compound and a host material.
15. The light-emitting device according to any one of claims 12 to 14, wherein the light-emitting device has a light-emitting layer and the light-emitting layer contains the compound and a light-emitting material.

FIG. 1




FIG. 2




FIG. 3




FIG. 4





FIG. 5



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2018/024302

5	A. CLASSIFICATION OF SUBJECT MATTER Int.Cl. C09K11/06(2006.01)i, C07C255/58(2006.01)i, C07D209/88(2006.01)i, C07D405/14(2006.01)i, H01L51/50(2006.01)i According to International Patent Classification (IPC) or to both national classification and IPC													
10	B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int.Cl. C09K11/06, C07C255/58, C07D209/88, C07D405/14, H01L51/50 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Published examined utility model applications of Japan 1922-1996 Published unexamined utility model applications of Japan 1971-2018 Registered utility model specifications of Japan 1996-2018 Published registered utility model applications of Japan 1994-2018													
15	Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) CAPLUS/REGISTRY (STN), JSTPlus/JMEDPlus/JST7580 (JDreamIII)													
20	C. DOCUMENTS CONSIDERED TO BE RELEVANT													
	<table border="1"> <thead> <tr> <th>Category*</th> <th>Citation of document, with indication, where appropriate, of the relevant passages</th> <th>Relevant to claim No.</th> </tr> </thead> <tbody> <tr> <td>25</td> <td> X WO 2015/080183 A1 (KYUSHU UNIVERSITY) 04 June 2015, claims, paragraphs [0104]-[0113], examples, particularly, examples 6-8, etc. & US 2016/0380205 A1, claims, paragraphs [0193]-[0201], examples 6-8 & EP 3093326 A1 & KR 10-2016-0095014 A & CN 106029829 A </td> <td>1-15</td> </tr> <tr> <td>30</td> <td> A WO 2016/208240 A1 (KANEKA CORPORATION) 29 December 2016, claims, examples, etc. & EP 3316328 A1, claims, examples </td> <td>1-15</td> </tr> </tbody> </table>	Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.	25	X WO 2015/080183 A1 (KYUSHU UNIVERSITY) 04 June 2015, claims, paragraphs [0104]-[0113], examples, particularly, examples 6-8, etc. & US 2016/0380205 A1, claims, paragraphs [0193]-[0201], examples 6-8 & EP 3093326 A1 & KR 10-2016-0095014 A & CN 106029829 A	1-15	30	A WO 2016/208240 A1 (KANEKA CORPORATION) 29 December 2016, claims, examples, etc. & EP 3316328 A1, claims, examples	1-15				
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.												
25	X WO 2015/080183 A1 (KYUSHU UNIVERSITY) 04 June 2015, claims, paragraphs [0104]-[0113], examples, particularly, examples 6-8, etc. & US 2016/0380205 A1, claims, paragraphs [0193]-[0201], examples 6-8 & EP 3093326 A1 & KR 10-2016-0095014 A & CN 106029829 A	1-15												
30	A WO 2016/208240 A1 (KANEKA CORPORATION) 29 December 2016, claims, examples, etc. & EP 3316328 A1, claims, examples	1-15												
35	<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.													
40	<table border="0"> <tr> <td>* Special categories of cited documents:</td> <td>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>"A" document defining the general state of the art which is not considered to be of particular relevance</td> <td>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>"E" earlier application or patent but published on or after the international filing date</td> <td>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>"&" document member of the same patent family</td> </tr> <tr> <td>"O" document referring to an oral disclosure, use, exhibition or other means</td> <td></td> </tr> <tr> <td>"P" document published prior to the international filing date but later than the priority date claimed</td> <td></td> </tr> </table>		* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family	"O" document referring to an oral disclosure, use, exhibition or other means		"P" document published prior to the international filing date but later than the priority date claimed	
* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention													
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone													
"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art													
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family													
"O" document referring to an oral disclosure, use, exhibition or other means														
"P" document published prior to the international filing date but later than the priority date claimed														
45	Date of the actual completion of the international search 28.08.2018	Date of mailing of the international search report 11.09.2018												
50	Name and mailing address of the ISA/ Japan Patent Office 3-4-3, Kasumigaseki, Chiyoda-ku, Tokyo 100-8915, Japan	Authorized officer Telephone No.												
55														

INTERNATIONAL SEARCH REPORT

International application No.
PCT/JP2018/024302

5
10
15
20
25
30
35
40
45
50
55

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2016/181772 A1 (KONICA MINOLTA, INC.) 17 November 2016, claims, examples, etc. (Family: none)	1-15
A	JP 2011-176250 A (FUJIFILM CORPORATION) 08 September 2011, claims, examples, etc. & KR 10-2011-0088457 A	1-15
A	WO 2016/124704 A1 (TECHNISCHE UNIVERSITAET DRESDEN) 11 August 2016, claims, examples, etc. & US 2018/0016493 A1, claims, examples & JP 2018-507849 A & KR 10-2017-0113646 A & CN 107454897 A	1-15

Form PCT/ISA/210 (continuation of second sheet) (January 2015)

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2018114758 A [0011]

Non-patent literature cited in the description

- *Organic Electronics*, 2013, vol. 14, 2721-2726 [0005]
- HANSCH, C. *Chem. Rev.*, 1991, vol. 91, 165-195 [0025]

专利名称(译)	发光材料，连接件，永久荧光和发光元件		
公开(公告)号	EP3647392A1	公开(公告)日	2020-05-06
申请号	EP2018824986	申请日	2018-06-27
申请(专利权)人(译)	KYULUX, INC.		
当前申请(专利权)人(译)	KYULUX, INC.		
[标]发明人	NOTSUKA NAOTO YANG YUSEOK YOSHIZAKI ASUKA		
发明人	NOTSUKA NAOTO YANG YUSEOK YOSHIZAKI ASUKA		
IPC分类号	C09K11/06 C07C255/58 C07D209/88 C07D405/14 H01L51/50		
CPC分类号	C09K11/06 C09K2211/1007 C09K2211/1029 C07C255/58 C07D209/88 C07D405/14 H01L51/50 C07C255/42 C07D209/86 C09K2211/1014 C09K2211/1018 H01L51/0058 H01L51/0059 H01L51/0072 H01L51/0073 H01L51/5012 H01L51/5016		
优先权	2017124947 2017-06-27 JP 2018114758 2018-06-15 JP		
其他公开文献	EP3647392A4		
外部链接	Espacenet		

摘要(译)

由以下通式表示的化合物是优异的发光材料。R₁~R₅各自独立地表示氢原子或取代基，R₁~R₅的一个为氰基，R₁~R₅的1~3为任选被烷基或芳基取代的芳基Ar。R₁至R₅中的3至3中的每一个是供体基团D（但对应于Ar的一个除外）。

