



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
16.02.2005 Bulletin 2005/07

(51) Int Cl.⁷: **H05B 33/14**, C09K 11/06,
H01S 3/00, H01L 31/00

(21) Application number: **03253437.2**

(22) Date of filing: **02.06.2003**

(54) **Organic photoluminescent polymers with improved stability**

Organische elektrolumineszente Polymere mit verbesserter Stabilität

Polymers organiques électroluminescentes avec une stabilité améliorée

(84) Designated Contracting States:
DE GB

(30) Priority: **04.06.2002 US 160057**

(43) Date of publication of application:
17.12.2003 Bulletin 2003/51

(73) Proprietor: **CANON KABUSHIKI KAISHA**
Tokyo (JP)

(72) Inventors:
• **Li, Xiao-Chang,**
Canon Development Americas, Inc.
San Jose, California 95134 (US)
• **Ueno, Kazunori,**
Canon Development Americas, Inc.
San Jose, California 95134 (US)
• **Hsieh, Bing R.,**
Canon Development Americas, Inc.
San Jose, California 95134 (US)

(74) Representative:
Beresford, Keith Denis Lewis et al
BERESFORD & Co.
16 High Holborn
London WC1V 6BX (GB)

(56) References cited:
WO-A-02/47440

- **HALLS J J M ET AL: "EXCITON DIFFUSION AND DISSOCIATION IN A POLY(P-PHENYLENEVINYLENE)/C60 HETEROJUNCTION PHOTOVOLTAIC CELL" APPLIED PHYSICS LETTERS, AMERICAN INSTITUTE OF PHYSICS. NEW YORK, US, vol. 68, no. 22, 27 May 1996 (1996-05-27), pages 3120-3122, XP000599510 ISSN: 0003-6951**
- **JOON LEE G ET AL: "Mechanism of one- and two-photon absorption induced photoluminescence in PPV type, electroluminescent polymer" OPTICS COMMUNICATIONS, NORTH-HOLLAND PUBLISHING CO. AMSTERDAM, NL, vol. 203, no. 1-2, 1 March 2002 (2002-03-01), pages 151-157, XP004343757 ISSN: 0030-4018**
- **RUGHOOPTH S D ET AL: "Polymers for electronics and communications" AFRICON, 1999 IEEE CAPE TOWN, SOUTH AFRICA 28 SEPT.-1 OCT. 1999, PISCATAWAY, NJ, USA, IEEE, US, 28 September 1999 (1999-09-28), pages 55-60, XP010367170 ISBN: 0-7803-5546-6**
- **J.H. SIMPSON ET AL.: "Solid-state 2H quadrupole echo NMR characterisation of vinylene-deuterated poly(p-phenylenevinylene) films" MACROMOLECULES, vol. 25, 1992, pages 3068-3074, XP002254212**
- **M.D. MCGEHEE, A.J. HEEGER: "Semiconducting (conjugated) polymers as material for solid-state lasers" ADVANCED MATERIALS, vol. 12, no. 22, 2000, pages 1655-1668, XP002254213**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**BACKGROUND OF THE INVENTION**

5 Field of the Invention

[0001] The present invention relates to luminescent polymers suitable for use in organic light-emitting devices (OLEDs), organic solid-state lasers, photovoltaic cells, and electrochromic displays. The invention further relates to a method of producing the luminescent polymers, and of producing OLEDs, organic solid state lasers, photovoltaic cells and electrochromic displays employing such luminescent polymers in an active layer.

Description of the Related Art

15 [0002] Conjugated polymer semi-conductors have attracted attention for optoelectronic applications that traditionally have been the domains of inorganic semi-conductors. The structural flexibility, the very low cost for processing, and the flexible thin film features of conjugated polymers make organic semi-conductive polymer devices competitive with the inorganic semiconductors. Most conjugated polymers are highly luminescent, and they have attracted great attention in light-emitting device applications and for use in organic solid-state lasers.

20 [0003] Recent improvements in performance characteristics of organic/polymer LEDs have led to renewed interest in organic lasers. Laser emission in general relies on two key ingredients: first, the active material must exhibit strong stimulated emission. Second, there has to be an optical feedback mechanism. The first requirement is fulfilled for a variety of state-of the-art conjugated polymers. The observation of gain narrowing via amplification of spontaneous emission (ASE) in planar conjugated polymer wave guides has proven that conjugated polymers can exhibit high optical gain comparable to the best inorganic semiconductor laser materials. (M. D. McGehee and A. Heeger, *Adv. Mater.*, 2000, 12(22), 1655-1668). The second important condition for lasing, namely an optical feedback, has to be accomplished by a suitable resonator geometry which is dependent on physical device configuration. Recent realization of the first organic solid state injection laser pumped by electrical charge injection reveals that the current is at the level of more than 1000 A/cm² for an electrically pumped organic solid state laser. (J.H. Schon, et al, *Science*, 2000, 289, 599-601). This is considerably much more than a normal OLED which is operated at a level of 10-100 mA/cm² (for a brightness between 100-1000 cd/m²). The prospect of compact electrically pumped polymer lasers using their semiconductor properties is exciting. However, there is indeed a need to develop highly luminescent and highly stabilized polymers.

25 [0004] Luminescent conjugated polymers are generally known in the art and include substituted and unsubstituted poly(phenylene vinylene)s and polyphenylenes. They are widely used in active layers which can be incorporated into a variety of OLED, organic solid-state laser, photovoltaic cell and electrochromic display structures. For all the above applications, polymers are either subject to electrical field, charge injection, or light irradiation conditions. Besides having the luminescence property, the other key parameter for these applications is the stability of the material under conditions of use, including high UV irradiation and high currents. Thus, the materials must maintain a high level of photoluminescent properties in use, as well as maintain their structural integrity.


30 [0005] Efforts to use these conjugated polymers commercially have focused on improving stability. It has been found that stability can be improved by the introduction of highly hindered aromatic rings, such as diphenyl-substituted poly(phenylene vinylene)s and phenyl-substituted poly(phenylene vinylene)s. (USP 5,945,502). Even with these improvements, however, stability is still unsatisfactory for use under certain conditions including high UV irradiation and high currents, both of which are normal conditions in OLEDs, organic solid state lasers, photovoltaic cells, and electrochromic displays.

SUMMARY OF THE INVENTION

35 [0006] It is an object of the present invention to provide luminescent polymers with improved stability, particularly against UV irradiation and high currents, and suitable for use in organic solid state lasers, OLEDs, photovoltaic cells, and electrochromic displays.

40 [0007] Accordingly, in one aspect the invention is a poly(phenylene vinylene) with a highly sterically hindered aromatic or heteroaromatic ring substitution on the phenylene portion, and deuterium substitution on the vinylene portion, as shown in the following structure:

55



wherein Ar_1 and Ar_2 are aromatic or heteroaromatic rings, such as phenyl, biphenyl, fluorene, thiophene, pyridyl, or their substituted aromatic or heteroaromatic rings with or without deuterium. R_1 and R_2 are independently each selected from the group consisting of hydrogen, deuterium, substituted or unsubstituted alkyl, alkoxy, aryl and heteroaryl, or halogen such as chlorine, fluorine, bromine etc. D represents deuterium, and n is an integer greater than 3.

15 **[0008]** In preferred embodiments, R_1 and R_2 are the same and are selected from the group consisting of substituted or unsubstituted alkyl, alkoxy, aryl and heteroaryl. Most preferably, Ar_1 and Ar_2 are phenyl or pyridyl or substituted phenyl or pyridyl.

[0009] In particularly preferred embodiments, the luminescent polymers are:

20

25

30


35

40


45

50


55




Formula 1




Formula 2




Formula 3



Formula 4



Formula 5



Formula 6

50 **[0010]** In the above formulas X, Y=F, Cl, Br, CN, NO₂, OR₁, SR₁, phenyl, pyridyl, thiophene R₁, R₂=H, alkyl (1-20), alkoxy (1-20), F, Cl, Br.

55 **[0011]** The above-described luminescent polymers exhibit good stability, particularly under UV irradiation and high current injection. The polymers are soluble, with well-controlled microstructure and, as a consequence, are suitable for formation into the active layer of OLEDs, organic solid state lasers, photovoltaic cells and electrochromic displays. Preferred embodiments are particularly well-suited for formation of such layers by solution processing, such as spin-coating and printing processes.

[0012] In a further aspect, the present invention is an organic light emitting device, an organic solid state laser, and

a method for producing such devices, comprising a transparent electrode; a cathode; and an active layer containing a luminescent polymer having the structure of formula (I).

[0013] In a still further aspect, the present invention is a photovoltaic cell, and a method for producing such a cell, comprising an active layer containing a luminescent polymer having the structure of formula (I).

[0014] In another aspect, the present invention is an electrochromic display, and a method for producing such a display, comprising an active layer containing a luminescent polymer having the structure of formula (I).

[0015] In a related aspect, the invention is a method of making a luminescent polymer having a structure as set out in formula (I), comprising the steps of deuteration of the monomers, and the 1,6-dehalogenation polymerization reaction.

[0016] This brief summary has been provided so that the nature of the invention may be understood quickly. A more complete understanding of the invention can be obtained by reference to the following detailed description of the preferred embodiments thereof in connection with the attached drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] Fig. 1 is a graphical comparison of the UV-visible and photoluminescent spectral characteristics of DP-PPV (Blue) with DP-PPV-d2 (Red).

[0018] Fig. 2 is a graph showing the cyclic voltametric curve of normal DP-PPV and deuterated DP-PPV-d2.

[0019] Fig. 3 is an illustration of a UV irradiation experiment set-up.

[0020] Fig. 4 is a three-dimensional illustration of a DP-PPV-d2 polymer.

[0021] Fig. 5 is a schematic diagram of an organic solid state laser (OSL) device showing the pump beam focused onto the surface of the polymer film.

DETAILED DESCRIPTION OF THE INVENTION

[0022] The present invention provides conjugated luminescent polymers or copolymers which present better stability against current and against UV light irradiation. Amongst various conjugated polymers, poly(phenylene vinylene) (PPV) and its derivatives remain as the most important conjugated polymers for the use in opto-electronic applications. This is because PPVs can be molecularly engineered to provide various derivatives with different emissive colors, such as red, green, yellow and bluish green, by changing the side substituted groups of the polymer. PPVs with extremely high molecular weight can also be easily achieved (with Mw higher than 10^6). Many applications of conjugated PPVs in the area of photovoltaic cells, light-emitting devices, electrochromic displays, and organic lasing etc, have been reported. For almost all the above applications, the paramount important requirement is the improvement of material stability.


[0023] Di-phenyl substituted poly(phenylene vinylene) has been developed as a good green luminescent polymer. It has a better stability against photo-irradiation than some other derivatives, such as 2-methoxy-5-(2'-ethyl-hexyl)-poly(1,4-phenylenevinylene) (MEH-PPV).

[0024] In order to further enhance the stability of the vinyl bonds along the conjugated polymer chain, deuterium substituted polymer has been explored. The difference between hydrogen and deuterium has fairly small chemical effects; however, there are important physical effects because of the mass difference between the isotopes, with deuterium having double the mass of hydrogen. It is known that the C-D bond is shorter than the C-H as a result of anharmonicity of the bond stretching potential. This means the carbon-deuterium chemical bond is stronger, more stable, and reacts more slowly than the carbon-hydrogen chemical bond, so that the deuterium organic system has better thermal stability, and a longer lifetime in opto-electronic devices. Deuterium is found to act as an apparent electron-donating inductive substituent relative to hydrogen. The isotope effects may be applied in the design of new luminescent material with enhanced charge-injection ability.

[0025] Various PPV-based luminescent materials containing deuterium have been prepared to investigate their suitability for use in OLEDs.

EXAMPLE 1


[0026] Synthesis of a soluble green luminescent diphenyl-substituted PPV with deuterium substitution has been carried out as described in Scheme 1.



Scheme 1. Preparation of DP-PPV-d2

25

30 [0027] The deuterium reaction mechanism is illustrated in Scheme 2. As is shown, it is possible to obtain the deuterium DP-PPV with the readily available starting material LiAlD₄.



Scheme 2. Deuterium reaction mechanism

45

50 [0028] The resulting polymer has a melting point around 285 °C. Due to the diphenyl steric effect, combined with the stabilization effect of deuterium, the green luminescent DP-PPV-d2 has a better stability against light irradiation and against thermal curing than the non-deuterated polymer.

[0029] The three dimensional features of a DP-PPV-d2 polymer are illustrated in Fig. 4.

55 [0030] Compared with the normal DP-PPV, the deuterated DP-PPV-d2 has similar optical and electronic absorption properties, as can be seen from Figure 1.

EXAMPLE 2. Cyclic voltametric analysis

[0031] From a cyclic voltametric analysis, the band gap of the polymer can be estimated as, $E_g = 2.8$ eV; and the energy level for the highest occupied molecular orbitals (HOMO) being $=5.9$ eV, and for the lowest occupied molecular orbitals being (LUMO) = 3.1 eV. The reduction position and the cyclic voltametric features for both normal DP-PPV and DP-PPV-d2 are similar. However, the oxidation position and features of the two polymers are different, as illustrated in Figure 2. The deuterated DP-PPV-d2 shows a better hole injection as indicated by the larger oxidation peak area in Figure 2.

EXAMPLE 3. UV stability comparison

[0032] A DP-PPV polymer sample and a DP-PPV-d2 polymer sample were coated on quartz glass substrates respectively, and subjected to UV irradiation under nitrogen as illustrated in Figure 3.

[0033] After 100 minutes UV irradiation (290 W, 366 nm) under nitrogen atmosphere, the normal DP-PPV sample showed photoluminescence of 80% of its original intensity due to photo-degradation. The DP-PPV-d2 deuterium sample, however, showed 95% of its original photoluminescence intensity.

EXAMPLE 4. OLED property comparison

[0034] A solution of a DP-PPV-d2 polymer (where $X = Y = H$, $R_1 = H$ and $R_2 = C_{10}H_{21}$ (40 mg dissolved in 2 mL chloroform) is prepared and filtered through a filter with a pore size of less than 0.45 microns. A polymer thin film of PEDOT (Baytron®) is formed by spin-coating an aqueous solution of PEDOT on a pre-coated ITO glass substrate (1.5x1.0 inch, resistivity less than 50 ohm/in²) at 2000 rpm and at room temperature for a spin-time of 1.5 minutes. The thin film of PEDOT is used as a hole injection layer. The deuterium polymer is spin-coated on top of the PEDOT film by similar spin-coating techniques to form an emissive layer. The emissive layer has a uniform thickness of about 100 nm. A layer of calcium, with a thickness of 60 nm, is deposited on top of the polymer film by vacuum thermal evaporation at a rate of 0.2-2.2 nm/sec. A layer of Al with a thickness of 150 nm is deposited on top of the Ca layer at a rate of 2.2-12 nm/sec. The formed OLED device ITO/PEDOT/DP-PPV-d2/Ca-Al is encapsulated by gluing a cover glass substrate on top of the aluminum cathode. The metal evaporation and encapsulation of the device are carried out in a dry box under an argon atmosphere. Stable and uniform green light emission is achieved at a forward bias of 5 volts.

[0035] For comparison, a similar device of ITO/PEDOT/DP-PPV/Ca-Al was also fabricated using a normal DP-PPV (without deuterium, where $X=Y=H$, $R_1=H$ and $R_2=C_{10}H_{21}$) as the emissive layer. Green electroluminescence can be observed at a forward bias of 4 volts, but after 2 weeks storage the "normal" DP-PPV polymer produced less stable light emission than the deuterium containing polymer.

[0036] Luminescent polymers according to the present invention can be used in optically pumped laser devices. Optically pumped laser devices can be made having a variety of structures, including the following:

1. A vertical microcavity - luminescent polymer layer using a polymer according to the present invention can be coated onto a commercially available Diffraction Bragg Resonance (DBR) mirror. A silver mirror is then deposited on top of the polymer layer;
2. A polymer selected from among the polymers of the present invention can be coated in the shape of a disk, ring or sphere onto a plate or rod-shaped material, as known in the art. Such materials include aluminum and copper;
3. An in-plane Fabry-Perot polymer is selected from among those of the present invention and is coated on a cladding material. The cladding has a higher index of refraction than the polymer, but an index of refraction less than about 1.8. Such cladding materials are selected to be resistant to typical organic solvents and polymers. Examples of such materials include TiO_2 and SiO_2 . The cladding materials are usually coated onto semiconductor materials, such as Si or InP by known sputtering deposition techniques; and
4. A distributed feedback (DFB) polymer selected from among the polymers of the present invention is coated on top of a specially designed distributed feedback plate, which is typically an insulator material such as rubber or ceramics, etc. Such a feedback plate is designed to have periodic modulation of either the refractive index or the gain coefficient.

[0037] The above mentioned devices can be pumped by a laser source with wavelengths of 300-550 nm. Various laser sources within these wavelengths are commercially available. For instance, one can employ a frequency doubled output of a regeneratively amplified femtosecond (fs) Ti:sapphire laser. This laser source can produce a pulse duration of less than 150 fs at a wavelength of 400 nm with a pulse energy of 0.1 nJ to 5000 nJ. The pump beam is focused onto a spot with a diameter of approximately 20-2000 μm , more preferably around 200 μm .


EXAMPLE 5. Optically pumped laser device

[0038] A polished InP substrate is pre-coated with a 2- μm -thick layer of SiO_2 (deposited by plasma enhanced chemical vapor deposition). The polymer (DP-PPV-d) is coated on the surface (100) of the SiO_2 by spin coating. The polymer film (refractive index $n=1.8$) forms a slab optical wave guide with the SiO_2 cladding layer ($n=1.46$) on one side, and air ($n=1$) on the other. The thickness of the organic film was chosen in order to form a single mode slab wave guide confining the optical field in the gain region. The OSL is optically pumped with 500 ps pulses generated at a 50 Hz repetition rate by a nitrogen laser at $\lambda=337$ nm. The pump beam was focused onto a 50- μm -wide stripe on the surface of the organic film forming the gain region. At pump level above threshold (4nJ), a well defined green laser beam is clearly observed emerging from the edges of the film (Figure 5).

[0039] An organic laser device can also be constructed in accordance with the present invention. Such a device would have a cathode with a low work function of less than 4.5 eV and an anode with a higher work function of more than 4.8 eV, together with an active layer containing a luminescent polymer according to the present invention.

Claims

1. A luminescent polymer having a structure



wherein Ar_1 and Ar_2 are aromatic or heteroaromatic rings, and R_1 and R_2 are independently each selected from the group consisting of hydrogen, deuterium, substituted or unsubstituted alkyl, alkoxy, aryl and heteroaryl, or halogen;

wherein D represents deuterium; and


wherein n is an integer greater than 3.

2. The luminescent polymer according to claim 1, wherein Ar_1 and Ar_2 are phenyl, biphenyl, fluorene, thiophene, pyridyl, or their substituted aromatic or heteroaromatic rings with or without deuterium.


3. The luminescent polymer according to claim 1, wherein R_1 and R_2 are the same and are selected from the group consisting of substituted or unsubstituted alkyl, alkoxy, aryl and heteroaryl.

4. The luminescent polymer according to claim 3, wherein Ar_1 and Ar_2 are phenyl or pyridyl or substituted phenyl or pyridyl.


5. The luminescent polymer according to claim 1, selected from the group consisting of:




Formula 1




Formula 2




Formula 3



Formula 4



Formula 5



Formula 6

50 where X and Y are selected from the group consisting of F, Cl, Br, CN, NO₂, OR₁, SR₁, phenyl, pyridyl or thiophene; and R₁, R₂ may be H, alkyl C₁-C₂₀, C₁-C₂₀ alkoxy, F, Cl or Br.

55 6. An organic light emitting device comprising:

- (a) a transparent electrode;
- (b) a cathode; and
- (c) an active layer containing the luminescent polymer according to any one of claims 1-5.

7. An optically pumped laser device comprising:

- (a) a substrate coated with a cladding layer having an index of refraction less than about 1.8;
 (b) a luminescent polymer according to any one of claims 1-5 coated on top of the substrate; and
 (c) a laser pumping light with a wavelength between about 300 nm and 550 nm.

8. An organic laser device comprising:

- (a) a cathode with a low work function of less than 4.5 eV;
 (b) an anode with a higher work function of more than 4.8 eV; and
 (c) an active layer containing a luminescent polymer according to any one of claims 1-5.

9. A method for making the organic light emitting device of claim 6 comprising the step of placing the luminescent polymer as the emissive layer between two electrodes.

10. A photovoltaic cell comprising an active layer containing a luminescent polymer according to any one of claims 1-5.

11. A method for making the photovoltaic cell of claim 10 comprising the step of placing the luminescent polymer as the active layer between two electrodes.


12. An electrochromic display device comprising an active layer containing a luminescent polymer according to any one of claims 1-5.

13. A method for making the electrochromic display device of claim 12 comprising the step of placing the luminescent polymer as the active layer between two electrodes.

14. A method of making a luminescent polymer according to any one of claims 1-5 comprising the steps of using LiAlD_4 as the deuterium source to include deuterium on a vinyl group of the polymer.

Patentansprüche

1. Lumineszentes Polymer mit einer Struktur



wobei Ar_1 und Ar_2 aromatische oder heteroaromatische Ringe sind, und R_1 und R_2 unabhängig jeweils gewählt sind aus der Gruppe bestehend aus Wasserstoff, Deuterium, substituiertem oder unsubstituiertem Alkyl, Alkoxy, Aryl und Heteroaryl, oder Halogen;
 wobei D darstellt Deuterium; und
 wobei n eine ganze Zahl grösser als 3 ist.

2. Lumineszentes Polymer nach Anspruch 1, wobei Ar_1 und Ar_2 Phenyl, Biphenyl, Fluoren, Thiophen, Pyridyl, oder deren substituierte aromatische oder heteroaromatische Ringe mit oder ohne Deuterium sind.

3. Lumineszentes Polymer nach Anspruch 1, wobei R_1 und R_2 gleich sind und gewählt sind aus der Gruppe bestehend aus substituiertem oder unsubstituiertem Alkyl, Alkoxy, Aryl und Heteroaryl.


4. Lumineszentes Polymer nach Anspruch 3, wobei Ar_1 und Ar_2 Phenyl oder Pyridyl oder substituiertes Phenyl oder Pyridyl sind.

5. Lumineszentes Polymer nach Anspruch 1, gewählt aus der Gruppe bestehend aus:


5

10

15



Formel 1




Formel 2


20

25

30



Formel 3




Formel 4


35

40

45



Formel 5



Formel 6

50

wobei X und Y gewählt sind aus der Gruppe bestehend aus F, Cl, Br, CN, NO₂, OR₁, SR₁, Phenyl, Pyridyl oder Thiophen; und R₁, R₂ sein können H, C₁-C₂₀ Alkyl, C₁-C₂₀ Alkoxy, F, Cl oder Br.

55

6. Organische Licht-emittierende Vorrichtung mit:

(a) einer transparenten Elektrode;

- (b) einer Kathode; und
 (c) einer aktiven Schicht, welche das lumineszente Polymer nach einem der Ansprüche 1-5 enthält.

7. Optisch gepumpte Laser-Vorrichtung mit:

- (a) einem Substrat, das beschichtet ist mit einer Überzugsschicht mit einem Brechungsindex von weniger als etwa 1,8;
 (b) einem lumineszenten Polymer nach einem der Ansprüche 1-5, das auf dem Substrat aufgetragen ist; und
 (c) einem Laser-pumpenden Licht mit einer Wellenlänge zwischen etwa 300 nm und 550 nm.

8. Organische Laser-Vorrichtung mit:

- (a) einer Kathode mit einer niedrigen Austrittsarbeit von weniger als 4,5 eV;
 (b) einer Anode mit einer höheren Austrittsarbeit von mehr als 4,8 eV; und
 (c) einer aktiven Schicht, welche ein lumineszentes Polymer nach einem der Ansprüche 1-5 enthält.

9. Verfahren zum Herstellen der organischen Lichtemittierenden Vorrichtung nach Anspruch 6 mit dem Schritt des Anordnens des lumineszenten Polymers als die Emissionsschicht zwischen zwei Elektroden.

10. Photovoltaische Zelle mit einer aktiven Schicht, welche ein lumineszentes Polymer nach einem der Ansprüche 1-5 enthält.

11. Verfahren zum Herstellen der photovoltaischen Zelle nach Anspruch 10 mit dem Schritt des Anordnens des lumineszenten Polymers als die aktive Schicht zwischen zwei Elektroden.


12. Elektrochromieanzeige-Vorrichtung mit einer aktiven Schicht, welche ein lumineszentes Polymer nach einem der Ansprüche 1-5 enthält.

13. Verfahren zum Herstellen der Elektrochromieanzeige-Vorrichtung nach Anspruch 12 mit dem Schritt des Anordnens des lumineszenten Polymers als die aktive Schicht zwischen zwei Elektroden.

14. Verfahren zum Herstellen eines lumineszenten Polymers nach einem der Ansprüche 1-5 mit dem Schritt des Verwendens von LiAlD_4 als Deuterium-Quelle, um Deuterium bei einer Vinylgruppe des Polymers einzufügen.

Revendications

1. Polymère luminescent ayant une structure



dans laquelle Ar_1 et Ar_2 représentent des noyaux aromatiques ou hétéroaromatiques, et R_1 et R_2 sont choisis chacun indépendamment dans le groupe consistant en un atome d'hydrogène, un atome de deutérium, des groupes alkyle, alkoyle, aryle et hétéroaryle substitués ou non substitués, ou un atome d'halogène ; et

D représente un atome de deutérium ; et

n représente un nombre entier supérieur à 3.


2. Polymère luminescent suivant la revendication 1, dans lequel Ar_1 et Ar_2 représentent des groupes phényle, bi-phényle, fluorène, thiophène ou pyridyle, ou leurs noyaux aromatiques ou hétéroaromatiques substitués, avec ou

sans deutérium.


3. Polymère luminescent suivant la revendication 1, dans lequel R_1 et R_2 sont identiques et sont choisis dans le groupe consistant en des groupes alkyle, alkoyle, aryle et hétéroaryle substitués ou non substitués.

4. Polymère luminescent suivant la revendication 3, dans lequel Ar_1 et Ar_2 représentent des groupes phényle ou pyridyle ou des groupes phényle ou pyridyle substitués.


5. Polymère luminescent suivant la revendication 1, choisi dans le groupe consistant en :




Formule 1




Formule 2




Formule 3



Formule 4



Formule 5



Formule 6

dans lesquelles X et Y sont choisis dans le groupe consistant en F, Cl, Br, CN, NO₂, OR₁, SR₁, phényle, pyridyle ou thiophène ; et R₁ et R₂ peuvent représenter H, des groupes alkyle en C₁ à C₂₀, alkoxy en C₁ à C₂₀, F, Cl ou Br.

6. Dispositif photoémetteur organique, comprenant :

- (a) une électrode transparente ;
- (b) une cathode ; et
- (c) une couche active contenant le polymère luminescent suivant l'une quelconque des revendications 1 à 5.

7. Dispositif laser à pompage optique, comprenant :

- (a) un substrat revêtu avec une couche de gainage ayant un indice de réfraction inférieur à environ 1,8 ;
- (b) un polymère luminescent suivant l'une quelconque des revendications 1 à 5, appliqué sous forme de revêtement sur le substrat ; et
- (c) une lumière de pompage laser ayant une longueur d'onde comprise dans l'intervalle d'environ 300 nm à 550 nm.

8. Dispositif laser organique comprenant :

- (a) une cathode ayant un faible travail d'extraction, inférieur à 4,5 eV ;
- (b) une anode ayant un travail d'extraction plus élevé, supérieur à 4,8 eV ; et
- (c) une couche active contenant un polymère luminescent suivant l'une quelconque des revendications 1 à 5.

9. Procédé pour la préparation du dispositif photoémetteur organique de la revendication 6, comprenant l'étape consistant à placer le polymère luminescent comme couche émissive entre deux électrodes.

10. Cellule photovoltaïque comprenant une couche active contenant un polymère luminescent suivant l'une quelconque des revendications 1 à 5.

11. Procédé pour la préparation de la cellule photovoltaïque de la revendication 10, comprenant l'étape consistant à placer le polymère luminescent comme couche active entre deux électrodes.

12. Dispositif d'affichage électrochromique, comprenant une couche active contenant un polymère luminescent suivant l'une quelconque des revendications 1 à 5.

13. Procédé pour la préparation du dispositif d'affichage électrochromique de la revendication 12, comprenant l'étape

EP 1 372 360 B1

consistant à placer le polymère luminescent comme couche active entre deux électrodes.

14. Procédé pour la préparation d'un polymère luminescent suivant l'une quelconque des revendications 1 à 5, comprenant les étapes d'utilisation de LiAlD_4 comme source de deutérium pour inclure du deutérium sur un groupe vinyle du polymère.

5

10

15

20

25

30

35

40

45

50

55

FIGURE 1




Figure 1. UV-Vis and PL spectral comparison of DP-PPV (Blue) with DP-PPV-d2

FIGURE 2




Figure 2. Cyclic voltammetric curve of normal DP-PPV (dotted line in blue) and d2-terminated DP-PPV-d2 (solid line).

FIGURE 3




Fig. 3. Illustration of UV irradiation experiment set up

FIGURE 4




Fig. 4. 3D illustration of the DP-PPV-d2 polymer

FIG. 5




Figure 5. Schematic diagram of an organic solid state laser (OSL) device with surface-emitting planar Fabry-Perot resonator showing the pump beam focused onto the surface of the polymer film, and the OSL output beam emerging from the film edge.

专利名称(译)	有机光致发光聚合物，具有改善的稳定性		
公开(公告)号	EP1372360B1	公开(公告)日	2005-02-16
申请号	EP2003253437	申请日	2003-06-02
[标]申请(专利权)人(译)	佳能株式会社		
申请(专利权)人(译)	佳能株式会社		
当前申请(专利权)人(译)	佳能株式会社		
发明人	LI, XIAO-CHANG, CANON DEVELOPMENT AMERICAS, INC. UENO, KAZUNORI, CANON DEVELOPMENT AMERICAS, INC. HSIEH, BING R., CANON DEVELOPMENT AMERICAS, INC.		
IPC分类号	H01L51/50 C07C15/52 C08G61/02 C09K11/06 H01L51/30 H01L51/42 H01S3/16 H05B33/14 H01S3/00 H01L31/00		
CPC分类号	H05B33/14 C08G61/02 C09K11/06 C09K2211/1416 C09K2211/1425 C09K2211/1466 H01L51/0038 H01L51/42 H01L51/5012 Y02E10/549 Y02P70/521 Y10S428/917		
代理机构(译)	贝雷斯福德KEITH DENIS LEWIS		
优先权	10/160057 2002-06-04 US		
其他公开文献	EP1372360A1		
外部链接	Espacenet		

摘要(译)

一种发光聚合物，适用于有机发光器件的有源层，有机固态激光器，光伏电池或电致变色显示器，具有良好的稳定性和微观结构控制，其结构中Ar1和Ar2是芳香族或杂芳环，例如苯基，联苯基，苄基，噻吩基，吡啶基，或它们的取代的芳族或杂芳族环，有或没有氘，R1和R2各自独立地选自氢，氘，取代或未取代的烷基，烷氧基芳基和杂芳基，或卤素，其中D代表氘，n是大于3的整数。还描述了使用这些发光聚合物的电子器件及其制备方法。

