

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 November 2003 (27.11.2003)

PCT

(10) International Publication Number
WO 03/098716 A1

- (51) International Patent Classification⁷: H01L 51/20, 51/40
- (21) International Application Number: PCT/NL03/00371
- (22) International Filing Date: 20 May 2003 (20.05.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
1020635 21 May 2002 (21.05.2002) NL
- (71) Applicant (for all designated States except US): OTB GROUP B.V. [NL/NL]; Luchthavenweg 10, NL-5657 EB Eindhoven (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): DINGS, Franciscus, Cornelius [NL/NL]; Kapelstraat-noord 129, NL-5502 CC Veldhoven (NL). BIJKER, Martin, Dinant [NL/NL]; Betuwehof 64, NL-5709 KR Helmond (NL). EVERS, Marinus, Franciscus, Johanus [NL/NL]; Ginderover 33, NL-5591 JM Heeze (NL).
- (74) Agent: PRINS, A.W.; Nieuwe Parklaan 97, NL-2587 BN DEN HAAG (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK (utility model), SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- with international search report
 - before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 03/098716 A1

(54) Title: METHOD FOR MANUFACTURING A POLYMER OLED

(57) Abstract: A method for manufacturing a polymer OLED, wherein after the application of a number of active layers onto a substrate to form the OLED, these active layers are encapsulated with at least one sealing, wherein prior to the application of the sealing, the OLED is heated for some time, as a result of which volatile substances present in the active layers evaporate from the OLED, and subsequently the respective sealing is applied. Optionally independently of the heating of the OLED prior to the application of the sealing, the sealing can be formed by at least a UV-setting resist layer which is applied with one of the following techniques: printing, such as inkjet printing, screen printing, tampon printing, offset printing and the like, or a mechanical coating technique, such as spray coating, curtain coating, spin coating and the like.

Title: Method for manufacturing a polymer OLED

This invention relates to a method for manufacturing a polymer OLED, wherein after the application of a number of active layers onto a substrate to form the OLED, these active layers are encapsulated with at least one sealing.

5 In the known polymer OLEDs, such as described, for instance, in WO99/03122, the content of which is to be understood to be incorporated herein by reference, the OLED is sandwiched between two plates which are sealed together. The plates therefore form a housing in which the OLED is accommodated. Also known, from practice, is an OLED where the OLED on
10 one side has been formed on a glass substrate plate and on the other side is covered with the aid of a small metal box which is glued onto the glass substrate plate. In the box, a getter material is included. A problem of this practical embodiment is that the manufacture thereof is difficult to automate.

15 The problem one is faced with is that it should be possible to rapidly manufacture an OLED having a long lifetime. It is to be taken into account here that the active layers, such as, for instance, a PEDOT layer and a PPV layer, of the OLED are highly sensitive to moisture and oxygen. Minor exposure to one of these substances leads to a considerably shorter lifetime.
20 When such exposure does not occur, however, lifetimes of 35,000 hours can be achieved. The glued joint between the metal box and the glass substrate plate or the seal between the two plates from the above-mentioned PCT publication should therefore be particularly gas- and moisture-tight. Even when that condition is met, it is found that also the active polymer layers
25 contain moisture, which evaporates when the OLED is switched on. In the conventional OLEDs, as described, for instance, in the publication mentioned, a getter material may be included in the housing bounded by the two plates. US-B-6,268,695, the content of which is to be understood to be

incorporated herein by reference, discloses an OLED sealing method which utilizes a PECVD process for applying sealing layers. In the use of this method it is not possible to provide getter material under the sealing layer. Accordingly, when the sealing is formed by a vacuum deposition process, the lifetime of the OLED is limited by the release of moisture from the active layers of the OLED during use. It may even happen that the sealing layers after switch-on of the OLED break up under the influence of water vapor released through evaporation, leading to bubble formation under the sealing layers.

10 The invention contemplates a solution to these problems and to that end provides a method of the type mentioned in the opening paragraph hereof that is characterized in that prior to the application of the sealing, the OLED is heated for some time, as a result of which volatile substances present in the active layers evaporate from the OLED, and subsequently the
15 respective sealing is applied.

 As a result of the heating, the volatile substances present in the active layers, such as water vapor, will be released. All volatile substances released during the heating cannot damage the OLED during use anymore, so that the lifetime of an OLED manufactured with the present method is
20 extended.

 According to a further elaboration of the invention, it is particularly favorable when the heating of the not yet encapsulated OLED takes place while the OLED is in a reduced pressure area, so that volatile substances can easily escape from the layers.

25 Accordingly, heating can take place, for instance, in the process chamber in which subsequently the sealing layer or the sealing housing is provided on the OLED.

 The reduced pressure is preferably lower than $1 \cdot 10^{-1}$ mbar.

According to a further elaboration of the invention, heating can be done by an external heating source, such as, for instance, an IR lamp or a resistance heating element.

However, according to an alternative further elaboration of the invention, it is also possible to have the heating take place by switching the OLED on for some time.

This last procedure moreover has the advantage that before the application of the sealing layers, the OLED, and specifically the active layers thereof, enters a stable condition fairly soon after it has been switched on for the first time, in which stable condition the OLED will remain for the greater part of its lifetime. It has been found that OLEDs perish specifically in this initial start period. When the OLED survives this initial start period, however, the chances that the OLED attains its expected lifetime are high. Accordingly, drying out the OLED at the same time constitutes a good test of the correct functioning of the OLED.

According to a further elaboration of the invention, the time during which the OLED is switched on is long enough to obtain a stable light emittance.

As already indicated above, the invention envisages a fast method for the manufacture of OLEDs. To that end, the invention provides a method of the type mentioned in the opening paragraph hereof that is characterized in that the sealing comprises at least a UV-setting resist layer which is applied with one of the following techniques: printing, such as inkjet printing, screen printing, tampon printing, offset printing and the like, or a mechanical coating technique, such as spray coating, curtain coating, spin coating and the like.

Such a manner of applying a UV-setting resist layer has the advantage that application can proceed at high speed whilst forming a considerable layer thickness. Moreover, a very good levelling of the relief structure of the OLED can be accomplished. US-B-6,268,695, mentioned

earlier, shows the application of a polymer layer by a vacuum deposition. With such techniques, only much thinner layers can be applied and moreover the extent of levelling of the relief structure of the OLED is much less. The thus applied UV-setting resist layer therefore affords better protection from a mechanical loading of the OLED, a better levelling of the relief structure of the OLED and, by virtue of its considerable thickness, an excellent barrier against moisture and oxygen. Compared with the application of a polymer layer by vacuum deposition, a layer of UV-setting resist that is applied by one of the techniques mentioned can be formed faster by a factor of 20 to 30. The fabrication process is thus considerably shortened in time. Specifically in the case of inkjet printing, a thick UV-setting resist layer can be rapidly applied selectively at desired positions in a particularly efficient and flexible manner, that is, without the use of special masks. The coating techniques generally do require the use of masks. Over against the slightly lesser flexibility in these coating techniques, however, there are the higher rates of application. This last also applies to printing techniques such as screen printing and offset printing.

According to a further elaboration of the invention, the UV-setting resist layer can be provided with fillers which enlarge the diffusion path length in the layer. Such fillers can comprise, for instance, mica sheets. The mica sheets will align substantially parallel in the resist layer, and moisture or oxygen tending to penetrate through the resist layer will have to find a way around these mica sheets. Thus the moisture or the oxygen must traverse a longer path length through the layer, which considerably reduces the chance of complete penetration through the layer.

According to a further elaboration of the invention, a getter material can be included in the UV-setting resist layer. Such a getter material can ensure that moisture or like volatile gases that are released from the OLED during use are absorbed directly into the getter material and not into the active layers of the OLED. As already indicated hereinbefore, moisture

constitutes a great threat to the useful life of the OLED by attacking the active layers thereof. A suitable getter material comprises, for instance, zeolite and/or silicates.

It is naturally preferred when the method for drying out the active layers prior to application of the sealing is combined with the application of a UV-setting resist layer by printing or a mechanical coating technique.

According to a further elaboration of the invention, the sealing can comprise at least a nitride layer, a metal layer, an oxide layer, or a combination of one or more of these layers, and these layers are applied with a PECVD process.

It is here preferred that after the application of at least a top layer of the active layers, which active layers comprise, for instance, a sputtered barium layer and a sputtered aluminum layer, there is applied directly, i.e. without removing the substrate from the reduced pressure area, at least one sealing layer, such as, for instance, an SiNx layer.

This can be accomplished, according to a further elaboration of the invention, in that the process chamber for applying at least a number of the active layers at the same time constitutes the process chamber for applying at least one sealing layer.

According to an alternative further elaboration, the non-removal from the reduced pressure area can be effected by transporting the substrate from the process chamber for applying at least a number of the active layers, via a conveyor arranged in a vacuum space, to a process chamber for applying at least one sealing layer.

Printing, such as inkjet printing, screen printing, tampon printing, offset printing and the like, or mechanical coating techniques, such as spray coating, curtain coating, spin coating and the like are techniques known per se in the subject technical field, not requiring further description here.

The method for applying sealing layers, such as for instance the SiNx layer that is applied with the aid of a PECVD process after the last active

layers of the OLED, such as, for instance, barium and aluminum, have been applied with the aid of, for instance, a sputter process, can be carried out, for instance, in an apparatus as described in applicant's earlier patent application WO 02/04697. After the first sealing layers have been applied in
5 the reduced pressure environment, subsequently the thus sealed OLED can be removed from the reduced pressure environment and with one of the techniques mentioned the relatively thick and mechanically strong UV-setting resist layer can be applied.

CLAIMS

1. A method for manufacturing a polymer OLED, wherein after the application of a number of active layers onto a substrate to form the OLED, these active layers are encapsulated with at least one sealing, characterized in that prior to the application of the sealing, the OLED is heated for some
5 time, as a result of which volatile substances present in the active layers evaporate from the OLED, and subsequently the respective sealing is provided.
2. A method according to claim 1, wherein the heating of the not yet encapsulated OLED is done while the OLED is situated in a reduced
10 pressure area, such that volatile substances can easily escape from the layers.
3. A method according to claim 2, wherein the reduced pressure is lower than 1.10^{-1} mbar.
4. A method according to any one of the preceding claims, wherein the
15 heating is done by an external heating source, such as, for instance, an IR lamp or a resistance heating element.
5. A method according to any one of claims 1-3, wherein the heating is done by switching the OLED on for some time.
6. A method according to claim 5, wherein the said time is long enough
20 to obtain a stable light emittance.
7. A method for manufacturing a polymer OLED, wherein after the application of a number of active layers onto a substrate to form the OLED, these active layers are encapsulated by a sealing, the sealing comprising at least a UV-setting resist layer which is applied with one of the following
25 techniques: printing, such as inkjet printing, screen printing, tampon printing, offset printing and the like, or a mechanical coating technique, such as spray coating, curtain coating, spin coating and the like.

8. A method according to claim 7, wherein the UV-setting resist layer is provided with fillers which enlarge the diffusion path length in the layer.

9. A method according to claim 8, wherein the fillers comprise mica sheets.

5 10. A method according to any one of claims 7-9, wherein a getter material is included in the UV-setting layer.

11. A method according to claim 10, wherein the getter material comprises zeolite and/or silicates.

12. A method for manufacturing a polymer OLED, comprising the method
10 steps of at least one of claims 1-6 in combination with the method steps of at least one of claims 7-11.

13. A method according to any one of the preceding claims, wherein the sealing comprises at least a nitride layer, a metal layer, an oxide layer or a combination of one or more of these layers, these layers being applied with
15 the aid of a PECVD process.

14. A method according to claim 13, wherein after application of at least a top layer of the active layers, which active layers comprise, for instance, a sputtered barium layer and a sputtered aluminum layer, there is applied directly, i.e. without removing the substrate from the reduced pressure area,
20 at least one sealing layer, such as, for instance, an SiNx layer.

15. A method according to claim 14, wherein the process chamber for applying at least a number of the active layers at the same time constitutes the process chamber for applying at least one sealing layer.

16. A method according to claim 14, wherein the substrate is conveyed
25 from the process chamber for applying at least a number of the active layers, via a conveyor arranged in a vacuum space, to a process chamber for applying at least one sealing layer .

INTERNATIONAL SEARCH REPORT

Intern Application No
PCT/NL 03/00371

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 H01L51/20 H01L51/40		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) IPC 7 H01L H05B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, PAJ, WPI Data		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 08, 6 October 2000 (2000-10-06) -& JP 2000 150147 A (TORAY IND INC), 30 May 2000 (2000-05-30)	1,2
A	abstract	3,4,7, 10-14
X	US 2001/050532 A1 (EIDA MITSURU ET AL) 13 December 2001 (2001-12-13)	1-4
A	page 11, column 1, paragraph 245 - page 15, column 1, paragraph 338	14-16
	-/--	
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
° Special categories of cited documents:		
A document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed		*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family
Date of the actual completion of the international search 1 October 2003		Date of mailing of the international search report 09/10/2003
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer De Laere, A.

INTERNATIONAL SEARCH REPORT

Inter Application No

PCT/NL 03/00371

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 196 03 746 A (BOSCH GMBH ROBERT) 24 April 1997 (1997-04-24)	7
A	column 4, lines 20-42	10,11
A	WO 98 59528 A (FED CORP) 30 December 1998 (1998-12-30) page 11, line 25 - page 13, line 15	7,10,13, 14
A	WO 00 76276 A (KONINKL PHILIPS ELECTRONICS NV) 14 December 2000 (2000-12-14) page 3, lines 17-26	8
A	PATENT ABSTRACTS OF JAPAN vol. 016, no. 038 (E-1161), 30 January 1992 (1992-01-30) -& JP 03 246883 A (SHARP CORP), 5 November 1991 (1991-11-05) abstract	1
A	PATENT ABSTRACTS OF JAPAN vol. 013, no. 493 (E-842), 8 November 1989 (1989-11-08) -& JP 01 197992 A (YASUO SUZUKI), 9 August 1989 (1989-08-09) abstract	1,5
A	US 6 198 220 B1 (JONES GARY W ET AL) 6 March 2001 (2001-03-06) column 5, lines 8-51	13

INTERNATIONAL SEARCH REPORT

 Interr Application No
 PCT/NL 03/00371

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 2000150147	A	30-05-2000	NONE	
US 2001050532	A1	13-12-2001	CN 1358404 T EP 1176850 A1 WO 0158221 A1	10-07-2002 30-01-2002 09-08-2001
DE 19603746	A	24-04-1997	DE 19603746 A1 WO 9716053 A1	24-04-1997 01-05-1997
WO 9859528	A	30-12-1998	US 5920080 A CN 1265261 T EP 1016327 A1 JP 2002508108 T WO 9859528 A1	06-07-1999 30-08-2000 05-07-2000 12-03-2002 30-12-1998
WO 0076276	A	14-12-2000	WO 0076276 A1 EP 1114569 A1 JP 2003501792 T US 6489719 B1	14-12-2000 11-07-2001 14-01-2003 03-12-2002
JP 03246883	A	05-11-1991	NONE	
JP 01197992	A	09-08-1989	JP 2030531 C JP 7054747 B	19-03-1996 07-06-1995
US 6198220	B1	06-03-2001	EP 1021255 A1 WO 9902277 A1	26-07-2000 21-01-1999

专利名称(译)	制造聚合物OLED的方法		
公开(公告)号	EP1514317A1	公开(公告)日	2005-03-16
申请号	EP2003752949	申请日	2003-05-20
[标]申请(专利权)人(译)	欧提比集团有限公司		
申请(专利权)人(译)	OTB集团B.V.		
当前申请(专利权)人(译)	OTB集团B.V.		
[标]发明人	DINGS FRANCISCUS CORNELIUS BIJKER MARTIN DINANT EVERS MARINUS FRANCISCUS JOHANUS		
发明人	DINGS, FRANCISCUS, CORNELIUS BIJKER, MARTIN, DINANT EVERS, MARINUS, FRANCISCUS, JOHANUS		
IPC分类号	H01L51/50 H01L51/40 H01L51/52 H01L51/20		
CPC分类号	H01L51/0002 H01L51/5253 H01L51/5259		
优先权	1020635 2002-05-21 NL		
外部链接	Espacenet		

摘要(译)

一种制造聚合物OLED的方法，其中在将多个有源层施加到基板上以形成OLED之后，用至少一个密封封装这些有源层，其中在施加密封之前，OLED被加热一段时间之后，由此存在于活性层中的挥发性物质从OLED蒸发，并且随后施加相应的密封。可选地，独立于在施加密封之前OLED的加热，密封可以通过至少UV固化抗蚀剂层形成，该抗蚀剂层施加有以下技术之一：印刷，例如喷墨印刷，丝网印刷，棉塞印刷，胶版印刷等，或机械涂布技术，例如喷涂，幕涂，旋涂等。