

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 489 155 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

22.12.2004 Bulletin 2004/52

(51) Int Cl.⁷: **C09K 11/06**, H05B 33/14,

H05B 33/22

(21) Application number: **03712758.6**

(86) International application number:

PCT/JP2003/003329

(22) Date of filing: **19.03.2003**

(87) International publication number:

WO 2003/080760 (02.10.2003 Gazette 2003/40)

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT SE SI SK TR**

(30) Priority: **22.03.2002 JP 2002081234**

15.10.2002 JP 2002299810

(71) Applicant: **IDEMITSU KOSAN CO., LTD.**

Tokyo 100-8321 (JP)

(72) Inventors:

- **IWAKUMA, Toshihiro**
Sodegaura-shi, Chiba 299-0205 (JP)
- **YAMAMOTO, Hiroshi**
Sodegaura-shi, Chiba 299-0205 (JP)

• **HIRONAKA, Yoshio**

Sodegaura-shi, Chiba 299-0205 (JP)

• **IKEDA, Hidetsugu**

Sodegaura-shi, Chiba 299-0205 (JP)

• **HOSOKAWA, Chishio**

Sodegaura-shi, Chiba 299-0205 (JP)

• **TOMITA, Seiji**

Sodegaura-shi, Chiba 299-0205 (JP)

• **ARAKANE, Takashi**

Sodegaura-shi, Chiba 299-0205 (JP)

(74) Representative:

Gille Hrabal Struck Neidlein Prop Roos
Patentanwälte,
Brucknerstrasse 20
40593 Düsseldorf (DE)

(54) **MATERIAL FOR ORGANIC ELECTROLUMINESCENT DEVICES AND ORGANIC
ELECTROLUMINESCENT DEVICES MADE BY USING THE SAME**

(57) A material for organic electroluminescence devices comprising a compound in which a heterocyclic group having nitrogen is bonded to an arylcarbazolyl group or a carbazolylalkylene group and an organic electroluminescence device comprising an anode, a cathode and an organic thin film layer comprising at least one layer and disposed between the anode and

the cathode, wherein at least one layer in the organic thin film layer comprises the material for organic electroluminescence devices described above. The material can provide an organic electro-luminescence device emitting bluish light with a high purity of color. The organic electroluminescence device uses the material.

EP 1 489 155 A1

DescriptionTECHNICAL FIELD

[0001] The present invention relates to a material for organic electro-luminescence devices (organic EL devices) and an organic EL device using the material and, more particularly, to an organic EL device emitting bluish light with a high purity of color.

BACKGROUND ART

[0002] Organic EL devices which utilize organic substances are expected to be useful for application as an inexpensive full color display device of the solid light emission type having a great size and various developments on the organic EL devices are being conducted. In general, an organic EL device has a construction comprising a light emitting layer and a pair of electrodes disposed at both sides of the light emitting layer.

[0003] The light emission of the organic EL device is a phenomenon in which, when an electric field is applied between the two electrodes, electrons are injected from the cathode side and holes are injected from the anode side, the electrons are recombined with the holes in the light emitting layer to form an excited state, and energy generated when the excited state returns to the ground state is emitted as light.

[0004] As the light emitting material, chelate complexes such as tris(8-quinolinolato)aluminum, coumarine derivatives, tetraphenylbutadiene derivatives, bisstyrylarylene derivatives and oxadiazole derivatives are known. It has been reported that these light emitting materials emit light in the visible region of blue to red and it is expected that color display devices can be obtained by using these light emitting materials (for example, Japanese Patent Application Laid-Open Nos. Heisei 8(1996)-239655, Heisei 7(1995)-138561 and Heisei 3(1991)-200289).

[0005] Although the practical use of displays using organic EL devices recently started, the full color display device is still under development. In particular, an organic EL device which emits bluish light with excellent purity of color and efficiency of light emission has been desired.

[0006] As the device as the attempt to satisfy the above desire, for example, a device using a phenylanthracene derivative as the material emitting blue light is disclosed in Japanese Patent Application Laid-Open No. Heisei 8(1996)-12600. The phenylanthracene derivative is used as the material emitting blue light and, in general, used as a laminate composed of a layer of the material emitting blue light and a layer of a complex of tris(8-quinolinolato)aluminum (Alq). However, the efficiency of light emission, the life and the purity of blue light are insufficient for the practical application. In Japanese Patent Application Laid-Open No. 2001-288462, a device emitting blue light in which an amine-based aromatic compound is used for the light emitting layer is disclosed. However, the efficiency of light emission of this device is as insufficient as 2 to 4 cd/A. In Japanese Patent Application Laid-Open No. 2001-160489, a device in which an azafluoranthene compound is added to the light emitting layer is disclosed. However, this device emits light of yellow to green and cannot emit blue light having a sufficiently high purity of color.

DISCLOSURE OF THE INVENTION

[0007] The present invention is made to overcome the above problems and has an object of providing a material for organic EL devices which emits bluish light with excellent purity of color and an organic EL device utilizing the material.

[0008] As the result of extensive studies by the present inventors, it was found that an organic EL device exhibiting excellent purity of blue color could be obtained by using a compound having a heterocyclic group having nitrogen bonded to an arylcarbazolyl group or a carbazolylalkylene group as the host material. The present invention has been completed based on this knowledge.

[0009] The present invention provides a material for organic electroluminescence devices which comprises a compound represented by following general formula (1) or (2):



wherein Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group, A represents a group represented by following general formula (A):



wherein M and M' each independently represent a heteroaromatic ring having 2 to 40 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, M and M' may represent a same ring or different rings, L represents a single bond, a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms, a substituted or unsubstituted cycloalkylene group having 5 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms, p represents an integer of 0 to 2, q represents an integer of 1 or 2, r represents an integer of 0 to 2, and **p+r** represents an integer of 1 or greater; and

n and **m** each represent an integer of 1 to 3.

[0010] The present invention also provides an organic electroluminescence device comprising an anode, a cathode and an organic thin film layer comprising at least one layer and disposed between the anode and the cathode, wherein at least one layer in the organic thin film layer comprises a material for organic electroluminescence devices described above. Among the above organic thin film layers, the light emitting layer, the electron transporting layer or the hole transporting layer may comprise the above material for organic EL devices.

THE MOST PREFERRED EMBODIMENT TO CARRY OUT THE INVENTION

[0011] The material for organic electroluminescence devices of the present invention comprises a compound represented by following general formula (1) or (2):



[0012] In the above formulae, Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group and n and m each represent an integer of 1 to 3.

[0013] It is preferable that the aryl group in the arylcarbazolyl group has 6 to 30 carbon atoms. Examples of the aryl group include phenyl group, naphthyl group, anthryl group, phenanthryl group, naphthacenyl group, pyrenyl group, fluorenyl group, biphenyl group and terphenyl group. Among these groups, phenyl group, naphthyl group, biphenyl group and terphenyl group are preferable.

[0014] It is preferable that the alkylene group in the carbazolylalkylene group has 1 to 10 carbon atoms. Examples of the alkylene group include methylene group, ethylene group, propylene group, isopropylene group, n-butylene group, s-butylene group, isobutylene group, t-butylene group, n-pentylene group, n-hexylene group, n-heptylene group, n-octylene group, hydroxymethylene group, chloromethylene group and aminomethylene group. Among these groups, methylene group, ethylene group, propylene group, isopropylene group, n-butylene group, t-butylene group and n-pentylene group are preferable.

[0015] In general formulae (1) and (2), A represents a group represented by the following general formula (A):



[0016] M and M' each independently represent a heteroaromatic ring having 2 to 40 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, and M and M' may represent the same ring or different rings.

[0017] Examples of the heteroaromatic ring having nitrogen atom include rings of pyridine, pyrimidine, pyrazine, triazine, aziridine, azaindolindine, indolidine, imidazole, indole, isoindole, indazole, purine, puteridine, β -carboline, naphthylidine, quinoxaline, terpyridine, bipyridine, acridine, phenanthroline, phenazine and imidazopyridine. Among these rings, rings of pyridine, terpyridine, pyrimidine, imidazopyridine and triazine are preferable.

[0018] L represents a single bond, a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms, a substituted or unsubstituted cycloalkylene group having 5 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.

[0019] **p** represents an integer of 0 to 2, **q** represents an integer of 1 or 2, **r** represents an integer of 0 to 2, and **p+r** represents an integer of 1 or greater.

[0020] Examples of the aryl group having 6 to 30 carbon atoms include phenyl group, biphenyl group, terphenyl group, naphthyl group, anthranyl group, phenanthryl group, pyrenyl group, chrysenyl group, fluoranthenyl group and

perfluoroaryl groups. Among these groups, phenyl group, biphenyl groups, terphenyl group and perfluoroaryl groups are preferable.

[0021] Examples of the arylene group having 6 to 30 carbon atoms include phenylene group, biphenylene group, terphenylene group, naphthylene group, anthranylene group, phenanthrylene group, pyrenylene group, chrysenylene group, fluoranthylene group and perfluoroarylene groups. Among these groups, phenylene group, biphenylene group, terphenylene group and perfluoroarylene groups are preferable.

[0022] Examples of the cycloalkylene group having 5 to 30 carbon atoms include cyclopentylene group, cyclohexylene group and cycloheptylene group. Among these groups, cyclohexylene group is preferable.

[0023] Examples of the heteroaromatic group having 2 to 30 carbon atoms include 1-pyrrolyl group, 2-pyrrolyl group, 3-pyrrolyl group, pyridinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 2-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxanyl group, 5-quinoxanyl group, 6-quinoxanyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group, 1-phenanthrydinyl group, 2-phenanthrydinyl group, 3-phenanthrydinyl group, 4-phenanthrydinyl group, 6-phenanthrydinyl group, 7-phenanthrydinyl group, 8-phenanthrydinyl group, 9-phenanthrydinyl group, 10-phenanthrydinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthrolin-2-yl group, 1,7-phenanthrolin-3-yl group, 1,7-phenanthrolin-4-yl group, 1,7-phenanthrolin-5-yl group, 1,7-phenanthrolin-6-yl group, 1,7-phenanthrolin-8-yl group, 1,7-phenanthrolin-9-yl group, 1,7-phenanthrolin-10-yl group, 1,8-phenanthrolin-2-yl group, 1,8-phenanthrolin-3-yl group, 1,8-phenanthrolin-4-yl group, 1,8-phenanthrolin-5-yl group, 1,8-phenanthrolin-6-yl group, 1,8-phenanthrolin-7-yl group, 1,8-phenanthrolin-9-yl group, 1,8-phenanthrolin-10-yl group, 1,9-phenanthrolin-2-yl group, 1,9-phenanthrolin-3-yl group, 1,9-phenanthrolin-4-yl group, 1,9-phenanthrolin-5-yl group, 1,9-phenanthrolin-6-yl group, 1,9-phenanthrolin-7-yl group, 1,9-phenanthrolin-8-yl group, 1,9-phenanthrolin-10-yl group, 1,10-phenanthrolin-2-yl group, 1,10-phenanthrolin-3-yl group, 1,10-phenanthrolin-4-yl group, 1,10-phenanthrolin-5-yl group, 2,9-phenanthrolin-1-yl group, 2,9-phenanthrolin-3-yl group, 2,9-phenanthrolin-4-yl group, 2,9-phenanthrolin-5-yl group, 2,9-phenanthrolin-6-yl group, 2,9-phenanthrolin-7-yl group, 2,9-phenanthrolin-8-yl group, 2,9-phenanthrolin-10-yl group, 2,8-phenanthrolin-1-yl group, 2,8-phenanthrolin-3-yl group, 2,8-phenanthrolin-4-yl group, 2,8-phenanthrolin-5-yl group, 2,8-phenanthrolin-6-yl group, 2,8-phenanthrolin-7-yl group, 2,8-phenanthrolin-9-yl group, 2,8-phenanthrolin-10-yl group, 2,7-phenanthrolin-1-yl group, 2,7-phenanthrolin-3-yl group, 2,7-phenanthrolin-4-yl group, 2,7-phenanthrolin-5-yl group, 2,7-phenanthrolin-6-yl group, 2,7-phenanthrolin-8-yl group, 2,7-phenanthrolin-9-yl group, 2,7-phenanthrolin-10-yl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrol-1-yl group, 2-methylpyrrol-3-yl group, 2-methylpyrrol-4-yl group, 2-methylpyrrol-5-yl group, 3-methylpyrrol-1-yl group, 3-methylpyrrol-2-yl group, 3-methylpyrrol-4-yl group, 3-methylpyrrol-5-yl group, 2-t-butylpyrrol-4-yl group, 3-(2-phenylpropyl)pyrrol-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group and 4-t-butyl-3-indolyl group. Among these groups, pyridinyl group and quinolyl group are preferable.

[0024] Examples of the substituent in the group represented by Cz, M or M' in general formulae (1), (2) and (A) include halogen atoms such as chlorine atom, bromine atom and fluorine atom, carbazole group, hydroxyl group, substituted or unsubstituted amino groups, nitro group, cyano group, silyl group, trifluoromethyl group, carbonyl group, carboxyl group, substituted or unsubstituted alkyl groups, substituted or unsubstituted alkenyl groups, substituted or unsubstituted arylalkyl groups, substituted or unsubstituted aromatic groups, substituted or unsubstituted heteroaromatic heterocyclic groups, substituted or unsubstituted aralkyl groups, substituted or unsubstituted aryloxy groups and substituted or unsubstituted alkyloxy groups. Among these groups, fluorine atom, methyl group, perfluorophenylene group, phenyl group, naphthyl group, pyridyl group, pyrazyl group, pyrimidyl group, adamantyl group, benzyl group, cyano group and silyl group are preferable.

[0025] The bonding mode of the compound represented by general formula (1) or (2) described above is shown in Table 1 in the following in accordance with the numbers represented by n and m.

Table 1

$n=m=1$	$n=2$	$n=3$	$m=2$	$m=3$
Cz-A	Cz-A-Cz	Cz-A-Cz Cz	A-Cz-A	A-Cz-A A

[0026] The bonding mode of the group represented by general formula (A) described above is shown in Table 2 in the following in accordance with the numbers represented by **p**, **q** and **r**.


Table 2

No	p	q	r	The bonding mode
[1]	0	1	1	$L-M'$
[2]	0	1	2	$L-M'-M', M'-L-M'$
[3]	0	2	1	$L-L-M', L-M'-L$
[4]	0	2	2	$L-L-M'-M', M'-L-L-M',$ $L-M'-M'-L, M'-L-M', L-M-L$ $\begin{array}{ccc} \text{L} & \text{L} & \text{L} \\ & & \\ & & M' \end{array}$
[5]	1	1	0	The same as [1] except that M' is replaced with M .
[6]	1	1	1	$M-L-M'$
[7]	1	1	2	$M-L-M'-M',$ $\begin{array}{c} M-L-M' \\ \\ M' \end{array}$
[8]	1	2	0	The same as [3] except that M' is replaced with M .
[9]	1	2	1	$M-L-L-M', L-M-L-M', M-L-M'-L$
[10]	1	2	2	$M-L-L-M'-M', M'-L-M-L-M',$ $M'-M'-L-M-L,$ $\begin{array}{ccccccc} M-L-L & M-L-L-M' & L-L-M-M' & L-M-L-M' & M-L-L \\ & & & & \\ M' & M' & M' & M & M' \end{array}$
[11]	2	1	0	The same as [2] except that M' is replaced with M .
[12]	2	1	1	The same as [7] except that M' is replaced with M and M is replaced with M' .
[13]	2	1	2	$M-M-L-M'-M',$ $\begin{array}{c} M' \\ \\ M-L-M' \\ \\ M' \end{array}, \begin{array}{c} M-L-M'-M' \\ \\ M \end{array}$
[14]	2	2	0	The same as [4] except that M' is replaced with M .
[15]	2	2	1	The same as [10] except that M' is replaced with M and M is replaced with M' .
[16]	2	2	2	$M-M-L-L-M'-M',$ $\begin{array}{c} M-M-L-M'-M' \\ \\ L \end{array}, \begin{array}{c} M-L-L-M'-M' \\ \\ M \end{array}, \begin{array}{c} M \\ \\ M-L-L \\ \quad \\ M' \quad M' \end{array},$ $\begin{array}{c} M-M-L-L-M' \\ \\ M' \end{array}, \begin{array}{c} M \\ \\ L-L-M'-M' \\ \\ M \end{array}, \begin{array}{c} M-L-L-M \\ \quad \\ M' \quad M' \end{array}$

[0027] The group represented by Cz which is bonded to the group represented by A may be bonded to any of the groups represented by M, L or M' in general formula (A) representing the group represented by A.

[0028] For example, when the group represented by A has the bonding mode [6] in Table 2 ($p=q=r=1$) in the compound represented by Cz-A in which $m=n=1$ in general formula (1) or (2), the bonding mode includes three bonding modes of Cz-M-L-M', M-L(Cz)-M' and M-L-M'-Cz.

[0029] When the group represented by A has the bonding mode [7] in Table 2 ($p=q=1$ and $r=2$) in the compound represented by Cz-A-Cz in which $n=2$ in general formula (1), the bonding mode includes bonding modes shown in the following:



[0030] With respect to the bonding mode of the group represented by general formula (1), (2) or (A) and the combination of the groups shown in the above as the examples, materials for organic EL devices comprising compounds shown in (i) to (iv) in the following are preferable.

(i) Materials for organic EL devices in which

$n=1$ in general formula (1) and $p=1$ and $r=0$ in general formula (A);
 in general formula (1), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group; and
 in general formula (A), M represents a heterocyclic six-membered or seven-membered ring having 4 or 5 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic five-membered ring having 2 to 4 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic ring having 8 to 11 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring or a substituted or unsubstituted imidazopyridinyl ring, and L represents a substituted or unsubstituted aryl group

or arylene group having 6 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.

(ii) Materials for organic EL devices in which

n=2 in general formula (1) and p=1 and r=0 in general formula (A);
 in general formula (1), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group; and
 in general formula (A), M represents a heterocyclic six-membered or seven-membered ring having 4 or 5 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic five-membered ring having 2 to 4 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic ring having 8 to 11 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring or a substituted or unsubstituted imidazopyridinyl ring, and L represents a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.

(iii) Materials for organic EL devices in which

n=1 in general formula (1) and p=2 and r=0 in general formula (A);
 in general formula (1), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group; and
 in general formula (A), M represents a heteroaromatic ring having 2 to 40 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, and L represents a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.

(iv) Materials for organic EL devices in which

m=2 in general formula (2) and p=q=1 in general formula (A);
 in general formula (2), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group; and
 in general formula (A), M and M' each independently represent a heteroaromatic ring having 2 to 40 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, and M and M' may represent a same ring or different rings, and L represents a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms, a substituted or unsubstituted cycloalkylene group having 5 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.

[0031] In the above general formulae (1) and (2), it is preferable that Cz represents a substituted or unsubstituted arylcarbazolyl group and, more preferably, phenylcarbazolyl group. It is preferable that the aryl portion of the arylcarbazolyl group is substituted with carbazolyl group.

[0032] Specific examples of the compound represented by general formula (1) are shown in the following. However, the compound represented by general formula (1) is not limited to these compounds.

5

10

15

20

25

30


35


40

45

50

55





5

10

15

20

25

30


35

40


45

50


55




(A58)




(A59)




(A60)




(A61)




(A62)




(A63)




(A64)




(A65)




(A66)




(A67)




(A68)













(A69)
























(A70)











(A71)














(A110)




(A111)



(A112)




(A113)



(A114)

[0033] Specific examples of the compound represented by general formula (2) are shown in the following. However, the compound represented by general formula (2) is not limited to these compounds.



[0034] It is preferable that the energy gap of the triplet state of a compound represented by general formula (1) or (2) is 2.5 to 3.3 eV and more preferably 2.5 to 3.2 eV.

It is preferable that the energy gap of the singlet state of a compound represented by general formula (1) or (2) is 2.8 to 3.8 eV and more preferably 2.9 to 3.7 eV.

[0035] The organic EL device of the present invention comprises an anode, a cathode and an organic thin film layer comprising at least one layer disposed between the anode and the cathode, wherein at least one layer in the organic thin film layer comprises the material for organic electroluminescence devices comprising the compound represented by the above general formula (1) or (2).

[0036] It is preferable that the organic EL device of the present invention comprises the material for organic electroluminescence devices comprising the compounds represented by the above general formula (1) or (2) in the light emitting layer, the electron transporting layer or the hole transporting layer.

[0037] The organic EL device of the present invention emits bluish light and the purity of color of the emitted light is as excellent as (0.12, 0.10) to (0.17, 0.20). This property is exhibited since the material for organic EL devices comprising the compound represented by general formula (1) or (2) of the present invention has a great energy gap.

[0038] It is preferable that the organic EL device of the present invention emits light by a multiplet excitation which is the excitation to the triplet state or higher.

[0039] It is preferable that the material for organic electroluminescence devices is a host material of the organic EL device. The host material is a material into which holes and electrons can be injected and which has the function of transporting holes and electrons and emitting fluorescent light by recombination of holes and electrons.

[0040] The compounds represented by general formulae (1) and (2) in the present invention are useful also as the organic host material for phosphorescence devices since the energy gap of the singlet state is as high as 2.8 to 3.8 eV and the energy gap of the triplet state is as high as 2.5 to 3.3 eV.

[0041] The phosphorescence device is the organic device which comprises a substance emitting light based on the transition from the energy level of the triplet state to the energy level of the ground singlet state with a stronger intensity than those emitted from other substances, i.e., a phosphorescent material such as organometallic complexes comprising at least one metal selected from Groups 7 to 11 of the Periodic Table, and emits light under an electric field utilizing the so-called phosphorescence.

[0042] In the light emitting layer of the organic EL device, in general, the singlet exciton and the triplet exciton are mixed in the formed excited molecules and it is said that the ratio of the amount of the singlet exciton to the amount of the triplet exciton is 1:3 and the triplet exciton is formed in a greater amount. In conventional organic EL devices using the phosphorescence, the exciton contributing to the light emission is the singlet exciton and the triplet exciton does not emit light. Therefore, the triplet exciton is ultimately consumed as heat and the light is emitted by the singlet exciton which is formed in a smaller amount. Therefore, in these organic EL devices, the energy transferred to the triplet exciton in the energy generated by the recombination of holes and electrons causes a great loss.

[0043] In contrast, it is considered that, by using the compound of the present invention for the phosphorescence device, the efficiency of light emission three times as great as that of a device using a fluorescence can be obtained since the triplet exciton can be used for emission of light. It is also considered that, when the compound of the present invention is used for the light emitting layer of the phosphorescence device, an excited triplet state having an energy state higher than the excited triplet state of a phosphorescent organometallic complex comprising a metal selected from the Group 7 to 11 of the Periodic Table is formed; the film having a more stable form is formed; the glass transition temperature is higher (T_g : 80 to 160°C); the holes and the electrons are efficiently transported; the compound is electrochemically and chemically stable; and the formation of impurities which may work as a trap or causes the loss in the light emission is suppressed during the preparation and the use.

[0044] The organic EL device of the present invention comprises, as described above, one or more organic thin film layers formed between the anode and the cathode. When the device comprises a single layer, a light emitting layer is formed between the anode and the cathode. The light emitting layer comprises a light emitting material and, further, a hole injecting material for transporting holes injected from the anode to the light emitting material or an electron injecting material for transporting electrons injected from the cathode to the light emitting material. It is preferable that the light emitting material exhibits a very excellent phosphorescent quantum efficiency, has a great ability of transporting both holes and electrons and forms a uniform thin layer. Examples of the organic EL device of the multi-layer type include organic EL device comprising a laminate having a multi-layer construction such as (the anode / the hole injecting layer / the light emitting layer / the cathode), (the anode / the light emitting layer / the electron injecting layer / the cathode) and (the anode / the hole injecting layer / the light emitting layer / the electron injecting layer).

[0045] For the light emitting layer, in addition to the compound represented by general formula (1) or (2) of the present invention, conventional host materials, light emitting materials, doping materials, hole injecting materials and electron injecting materials and combinations of these materials may be used, where necessary. By using a multi-layer structure for the organic EL device, decreases in the luminance and the life due to quenching can be prevented and the luminance of emitted light and the efficiency of light emission can be improved with other doping materials. By using other doping materials contributing to the light emission of the phosphorescence in combination, the luminance of emitted light and the efficiency of light emission can be improved in comparison with conventional devices.


[0046] In the organic EL device of the present invention, the hole injecting layer, the light emitting layer and the electron injecting layer may each have a multi-layer structure. When the hole injecting layer has a multi-layer structure,

the layer into which holes are injected from the electrode is called the hole injecting layer and the layer which receives holes from the hole injecting layer and transports holes to the light emitting layer is called the hole transporting layer. Similarly, when the electron injecting layer has a multi-layer structure, the layer into which electron are injected from the electrode is called the electron injecting layer and the layer which receives electrons from the electron injecting layer and transports electrons to the light emitting layer is called the electron transporting layer. The layers are selected in accordance with the energy levels of the material, heat resistance and adhesion with the organic thin film layers or the metal electrodes.

[0047] In the organic EL device of the present invention, the electron transporting layer and/or the hole transporting layer may comprise the material for organic EL devices of the present invention which comprises any of the compounds represented by general formulae (1) and (2). The hole injecting layer, the electron injecting layer and the hole barrier layer may comprise the material for organic EL devices of the present invention. A phosphorescent light emitting compound and the material for organic EL materials of the present invention may be used as a mixture.

[0048] Examples of the light emitting material and the host material which can be used for the organic thin film layer in combination with the compound represented by general formula (1) or (2) include anthracene, naphthalene, phenanthrene, pyrene, tetracene, coronen, chrysene, fluoresceine, perylene, phthaloperylene, naphthaloperylene, perynone, phthaloperynone, naphthaloperynone, diphenylbutadiene, tetraphenylbutadiene, coumarine, oxadiazole, al-dazine, bisbenzoxazoline, bisstyryl, pyrazine, cyclopentadiene, metal complexes of quinoline, metal complexes of aminoquinoline, metal complexes of benzoquinoline, imines, diphenylethylene, vinylanthracene, diaminoanthracene, diaminocarbazole, pyrane, thiopyrane, polymethine, melocyanine, oxinoid compounds chelated with imidazole, quinacridone, rubrene, stilbene-based derivatives and phosphorescent pigments. However, the light emitting material and the host material are not limited to the compounds described above.

[0049] As the light emitting material, phosphorescent organometallic complexes are preferable since the external quantum efficiency of the device can be improved. Examples of the metal in the phosphorescent organometallic complex include ruthenium, rhodium, palladium, silver, rhenium, osmium, iridium, platinum and gold. It is preferable that the organometallic complex is an organometallic compound represented by the following general formula (3):



[0050] In the above general formula, A¹ represents a substituted or unsubstituted aromatic hydrocarbon cyclic group or aromatic heterocyclic group which is preferably phenyl group, biphenyl group, naphthyl group, anthryl group, thienyl group, pyridyl group, quinolyl group or isoquinolyl group. Examples of the substituent include halogen atoms such as fluorine atom; alkyl groups having 1 to 30 carbon atoms such as methyl group and ethyl group; alkenyl groups such as vinyl group; alkoxy carbonyl groups having 1 to 30 carbon atoms such as methoxycarbonyl group and ethoxycarbonyl group; alkoxy groups having 1 to 30 carbon atoms such as methoxy group and ethoxy group; aryloxy groups such as phenoxy group and benzyloxy group; dialkylamino groups such as dimethylamino group and diethylamino group; acyl groups such as acetyl group; haloalkyl groups such as trifluoromethyl group; and cyano group.

[0051] A² represents a substituted or unsubstituted aromatic heterocyclic group having nitrogen atom as the atom forming the heterocyclic ring, which is preferably pyridyl group, pirimidyl group, pyrazine group, triazine group, benzo-thiazole group, benzoxazole group, benzimidazole group, quinolyl group, isoquinolyl group, quinoxaline group or phenanthridine group. Examples of the substituent include the substituents described as the examples of the substituent for the group represented by A¹.

[0052] The ring having the group represented by A¹ and the ring having the group represented by A² may form one condensed ring. Examples of the condensed ring include 7,8-benzoquinoline group.


[0053] Q represents a metal selected from metals of Groups 7 to 11 of the Periodic Table, which is preferably ruthenium, rhodium, palladium, silver, rhenium, osmium, iridium, platinum or gold.

[0054] L represents a bidentate ligand, which is preferably selected from ligands of the β-diketone type such as acetylacetonates and pyromellitic acid.


[0055] m and n each represent an integer. When Q represents a divalent metal, n=2 and m=0. When Q represents a trivalent metal, n=3 and m=0 or n=2 and m=1.

[0056] Specific examples of the organometallic complex represented by the above general formula (3) are shown in the following. However, the organometallic complex is not limited to these compounds.


(K-1)




(K-2)




(K-3)




(K-4)




(K-5)




(K-6)




(K-7)




(K-8)




(K-9)




(K-10)




(K-11)




(K-12)




(K-13)




(K-14)




(K-15)




(K-16)




(K-17)




(K-18)




(K-19)




(K-20)



(K-21)



(K-22)



[0057] As the hole injecting material, compounds which have the ability to transport holes, exhibits the excellent effect of receiving holes injected from the anode and the excellent effect of injecting holes to the light emitting layer or the light emitting material, prevents transfer of excitons formed in the light emitting layer to the electron injecting layer or the electron injecting material and has the excellent ability of forming a thin film, are preferable. Examples of the hole injecting compound include phthalocyanine derivatives, naphthalocyanine derivatives, porphyrin derivatives, oxazoles, oxadiazoles, triazoles, imidazoles, imidazolones, imidazolethiones, pyrazolones, pyrazolones, tetrahydroimidazoles, hydrazones, acylhydrazones, polyarylethanes, stilbene, butadiene, triphenylamine of the benzidine type, triphenylamine of the styrylamine type, triphenylamine of the diamine type, derivatives of the above compounds and macromolecular materials such as polyvinyl-carbazoles, polysilanes and electrically conductive macromolecules. However, the hole injecting material is not limited to these materials.

[0058] Among these hole injecting materials, the more effective hole injecting materials are aromatic tertiary amine derivatives and phthalocyanine derivatives. Examples of the aromatic tertiary amine derivative include triphenylamine, tritolylamine, tolyldiphenylamine, N,N'-diphenyl-N,N'-(3-methylphenyl)-1,1'-biphenyl-4,4'-diamine, N,N,N',N'-(4-methylphenyl)-1,1'-phenyl-4,4'-diamine, N,N,N',N'-(4-methylphenyl)-1,1'-biphenyl-4,4'-diamine, N,N'-diphenyl-N,N'-dinaphthyl-1,1'-biphenyl-4,4'-diamine, N,N'-(methylphenyl)-N,N'-(4-n-butylphenyl)-phenanthrene-9,10-diamine, N,N-bis(4-di-4-tolylaminophenyl)-4-phenylcyclohexane and oligomers and polymers having the skeleton structure of these aromatic tertiary amines. However, the aromatic tertiary amine is not limited to these compounds. Examples of the phthalocyanine (Pc) derivative include phthalocyanine derivatives and naphthalocyanine derivatives such as H₂Pc, CuPc, CoPc, NiPc, ZnPc, PdPc, FePc, MnPc, ClAlPc, ClGaPc, ClInPc, ClSnPc, Cl₂SiPc, (HO)AlPc, (HO)GaPc, VOPc, TiOPc, MoOPc and GaPc-O-GaPc. However the phthalocyanine derivative is not limited to these compounds.

[0059] As the electron injecting material, compounds which have the ability to transport electrons, exhibits the excellent effect of receiving electrons injected from the anode and the excellent effect of injecting electrons to the light emitting layer or the light emitting material, prevents transfer of excitons formed in the light emitting layer to the hole injecting layer and has the excellent ability of forming a thin film, are preferable. Examples of the electron injecting compound include fluorenone, anthraquinodimethane, diphenylquinone, thiopyrane dioxide, oxazoles, oxadiazoles, triazoles, imidazoles, perylenetetracarboxylic acid, quinoxaline, fluorenylidene methane, anthraquinodimethane, anthrone and derivatives of these compounds. However, the electron injecting material is not limited to these compounds.

[0060] Among these electron injecting materials, the more effective electron injecting materials are metal complex compounds and five-membered derivatives having nitrogen. Examples of the metal complex compound include 8-hydroxyquinolinatolithium, bis(8-hydroxyquinolinato)zinc, bis(8-hydroxyquinolinato)copper, bis(8-hydroxyquinolinato)manganese, tris(8-hydroxyquinolinato)aluminum, tris(2-methyl-8-hydroxyquinolinato)aluminum, tris(8-hydroxyquinolinato)-gallium, bis(10-hydroxybenzo[h]quinolinato)beryllium, bis(10-hydroxybenzo[h]quinolinato)zinc, bis(2-methyl-8-quinolinato)chlorogallium, bis(2-methyl-8-quinolinato)(o-cresolato)gallium, bis(2-methyl-8-quinolinato)(1-naphtholato)aluminum and bis(2-methyl-8-quinolinato)(2-naphtholato)-gallium. However the electron injecting material is not limited to these compounds.

[0061] As the five-membered derivative having nitrogen, oxazoles, thiazoles, oxadiazoles, thiadiazoles, triazoles and derivatives of these compounds are preferable. Examples of the five-membered derivative having nitrogen include bis(1-phenyl)-1,3,4-oxazole, dimethylPOPOP, 2,5-bis(1-phenyl)-1,3,4-thiazole, 2,5-bis(1-phenyl)-1,3,4-oxadiazole, 2-(4'-tert-butylphenyl)-5-(4"-biphenyl)-1,3,5-oxadiazole, 2,5-bis(1-naphthyl)-1,3,4-oxadiazole, 1,4-bis[2-(5-phenyloxadiazolyl)]benzene, 1,4-bis[2-(5-phenyloxadiazolyl)-4-tert-butylbenzene], 2-(4'-tert-butylphenyl)-5-(4"-biphenyl)-1,3,4-thiadiazole, 2,5-bis(1-naphthyl)-1,3,4-thiadiazole, 1,4-bis[2-(5-phenylthiadiazolyl)]benzene, 2-(4'-tert-butylphenyl)-5-(4"-biphenyl)-1,3,4-triazole, 2,5-bis(1-naphthyl)-1,3,4-triazole and 1,4-bis[2-(5-phenyltriazolyl)]benzene. However, the five-membered derivative having nitrogen is not limited to these compounds.

[0062] The property of charge injection can be improved by adding an electron-accepting compound to the hole injecting material and an electron-donating compound to the electron injecting material.

[0063] As the electrically conductive material used for the anode of the organic EL device of the present invention, a material having a work function greater than 4 eV is suitable and carbon, aluminum, vanadium, iron, cobalt, nickel, tungsten, silver, gold, platinum, palladium, alloys of these metals, metal oxides such as tin oxides and indium oxide used for ITO substrates and NESA substrates and organic electrically conductive resins such as polythiophene and polypyrrol are used. As the electrically conductive material used for the cathode, a material having a work function smaller than 4 eV is suitable and magnesium, calcium, tin, lead, titanium, yttrium, lithium, ruthenium, manganese, aluminum and alloys of these metals are used. However, the electrically conductive material used for the cathode is not limited to these materials. Typical examples of the alloy include magnesium/silver, magnesium/indium and lithium/aluminum. However, the alloy is not limited to these alloys. The composition of the alloy is controlled by the temperature of the source of vaporization, the atmosphere and the degree of vacuum and a suitable composition is selected. The anode and the cathode may be formed with a structure having two or more layers, where necessary.

[0064] The organic EL device of the present invention may comprise an inorganic compound layer between at least one of the electrodes and the above organic thin film layer. Examples of the inorganic compound used for the inorganic compound layer include various types of oxides, nitrides and oxide nitrides such as alkali metal oxides, alkaline earth metal oxides, rare earth oxides, alkali metal halides, alkaline earth metal halides, rare earth halides, SiO_x , AlO_x , SiN_x , SiON , AlON , GeO_x , LiO_x , LiON , TiO_x , TlON , TaO_x , TaON , TaN_x and C. In particular, as the component contacting the anode, SiO_x , AlO_x , SiN_x , SiON , AlON , GeO_x and C are preferable since a stable interface layer of injection is formed. As the component contacting the cathode, LiF, MgF_2 , CaF_2 and NaF are preferable.

[0065] In the organic EL device of the present invention, it is preferable that at least one face is sufficiently transparent in the region of the wavelength of the light emitted by the device so that the light emission is achieved efficiently. It is preferable that the substrate is also transparent.

[0066] For the transparent electrode, the conditions in the vapor deposition or the sputtering are set so that the prescribed transparency is surely obtained using the above electrically conductive material. It is preferable that the electrode of the light emitting face has a transmittance of light of 10% or greater. The substrate is not particularly limited as long as the substrate has the mechanical and thermal strength and is transparent. Examples of the substrate include glass substrates and transparent films of resins. Examples of the transparent film of a resin include films of polyethylene, ethylene-vinyl acetate copolymers, ethylene-vinyl alcohol copolymers, polystyrene, polymethyl methacrylate, polyvinyl chloride, polyvinyl alcohol, polyvinyl butyral, nylon, polyether ether ketones, polysulfones, polyether sulfones, tetrafluoroethylene-perfluoroalkyl vinyl ether copolymers, polyvinyl fluoride, tetrafluoro-ethylene-ethylene copolymers, tetrafluoroethylene-hexafluoropropylene copolymers, polychlorotrifluoroethylene, polyvinylidene fluoride, polyesters, polycarbonates, polyurethanes, polyether imides, polyimides and polypropylene.

[0067] In the organic EL device of the present invention, it is possible that a protective layer is formed on the surface of the device or the entire device is covered with a silicone oil or a resin so that stability to the temperature, the humidity and the atmosphere is improved.

[0068] For the formation of each layer of the organic EL device of the present invention, any of the dry processes of film formation such as the vacuum vapor deposition, the sputtering, the plasma plating and the ion plating and the wet processes of film formation such as the spin coating, the dipping and the flow coating, can be applied. The thickness of each film is not particularly limited. However, it is necessary that the thickness of the film be set at a suitable value. When the thickness is excessively great, application of a greater voltage is necessary to obtain the same output of the light and the efficiency of light emission decreases. When the thickness is excessively small, pin holes are formed and sufficient light emission cannot be obtained even when an electric field is applied. In general, a thickness in the range of 5 nm to 10 μm is suitable and a thickness in the range of 10 nm to 0.2 μm is preferable.

[0069] When the wet process of film formation is used, the material forming each layer is dissolved or suspended in a suitable solvent such as ethanol, chloroform, tetrahydrofuran and dioxane and a thin film is formed from the obtained solution or suspension. Any of the above solvents can be used. For any of the layers, suitable resins and additives may be used to improve the property for film formation and to prevent formation of pin holes in the film. Examples of the resin which can be used include insulating resins such as polystyrene, polycarbonates, polyarylates, polyesters, polyamides, polyurethanes, polysulfones, polymethyl methacrylate, polymethyl acrylate, cellulose and copolymers of these resins; photoconductive resins such as poly-N-vinylcarbazole and polysilanes; and electrically conductive resins such as polythiophene and polypyrrol. Examples of the additive include antioxidants, ultraviolet light absorbents and plasticizers.

[0070] As described above, by using the compound represented by general formula (1) or (2) for the organic thin film layer of the organic EL device of the present invention, the organic EL device emitting blue light with a high purity of color can be obtained. This organic EL device can be advantageously used for a photosensitive member for electronic photograph, a planar light emitting member such as a flat panel display of wall televisions, a back light of copiers, printers and liquid crystal displays, a light source for instruments, a display panel, a marking light and an accessory.

[0071] The present invention will be described more specifically with reference to examples in the following. However, the present invention is not limited to the examples.

[0072] The triplet energy gap and the singlet energy gap of a compound were measured in accordance with the following methods.

(1) Measurement of the triplet energy gap


[0073] The lowest excited triplet energy level T1 was measured. The phosphorescence spectrum of a sample was measured (10 μ moles/liter; an EPA (diethyl ether : isopentane : ethanol=5:5:2 by volume) solution; 77K; a quartz cell; FLUOROLOG II manufactured by SPEX Company). A tangent was drawn to the increasing line at the short wavelength side of the phosphorescence spectrum and the wavelength at the intersection of the tangent and the abscissa (the end of light emission) was obtained. The obtained wavelength was converted into the energy.

(2) Measurement of the singlet energy gap

[0074] The excited singlet energy gap was measured. Using a toluene solution (10⁻⁵ moles/liter) of a sample, the absorption spectrum was obtained by a spectrometer for absorption of ultraviolet and visible light manufactured by HITACHI Co. Ltd. A tangent was drawn to the increasing line at the long wavelength side of the spectrum and the wavelength at the intersection of the tangent and the abscissa (the end of absorption) was obtained. The obtained wavelength was converted into the energy.

Synthesis Example 1 (Synthesis of Compound (A5))

[0075] The route of synthesis of Compound (A5) is shown in the following.



(1) Synthesis of Intermediate Compound (A)

[0076] 2,4'-Dibromoacetophenone in an amount of 15 g (54 mmoles) was dissolved into 100 ml of ethanol. To the obtained solution, 7.0 g of sodium hydrogencarbonate and 5.2 g (55 mmoles) of 2-aminopyridine were added and the resultant mixture was heated for 9 hours under the refluxing condition. After the reaction was completed, the mixture was cooled at the room temperature. The formed crystals were separated by filtration and washed with water and ethanol and 12.5 g (the yield: 85%) of Intermediate Compound (A) was obtained.

(2) Synthesis of Compound (A5)

[0077] Into a reactor, 6.1 g (19 mmoles) of 3,6-diphenylcarbazole, 6.3 g (23 mmoles) of Intermediate Compound (A), 0.2 g of copper powder, 1.7 g of 18-crown-6 and 2.9 g (21 mmoles) of potassium carbonate were placed and 30 ml of o-dichlorobenzene was added as the solvent. The resultant mixture was heated at 200°C in a silicone oil bath under a nitrogen stream and the reaction was allowed to proceed for 48 hours. After the reaction was completed, the reaction mixture was filtered under suction before being cooled and the obtained filtrate was concentrated using an evaporator. To the obtained oily product, 30 ml of methanol was added. The formed solid substance was separated by filtration under a reduced pressure and a gray solid substance was obtained. The obtained solid substance was recrystallized from benzene and 3.0 g (the yield: 31%) of white crystals were obtained. It was confirmed by 90 MHz ¹H-NMR and FD-MS (the field desorption mass analysis) that the obtained crystals were the target substance (A5). The result of the measurement by FD-MS is shown in the following:

10

15

20



30

34

40

45


50

54

27

Synthesis Example 3 (Synthesis of Compound (A26))

[0084] The route of synthesis of Compound (A26) is shown in the following.



(1) Synthesis of Intermediate Compound (D)

[0085] Into a reactor, 33 g (0.20 moles) of carbazole, 68 g (0.24 moles) of p-bromoiodobenzene, 2.0 g of copper powder, 18 g of 18-crown-6 and 30 g (0.22 moles) of potassium carbonate were placed and 300 ml of o-dichlorobenzene was added as the solvent. The resultant mixture was heated at 200°C in a silicone oil bath under a nitrogen stream and the reaction was allowed to proceed for 24 hours. After the reaction was completed, the reaction mixture was filtered under suction using a Buchner funnel before being cooled and the obtained filtrate was concentrated using an evaporator. To the obtained oily product, 30 ml of methanol was added. The formed solid substance was separated by filtration under a reduced pressure and a gray solid substance was obtained. The obtained solid substance was recrystallized from benzene and 31 g (the yield: 49%) of white crystals were obtained.

(2) Synthesis of Compound (A26)


[0086] Into a reactor, 5.4 g (20 mmoles) of 2-biphenylindole, 7.7 g (24 mmoles) of Intermediate Compound (D), 0.2 g of copper powder, 1.8 g of 18-crown-6 and 3.0 g (22 mmoles) of potassium carbonate were placed and 30 ml of o-dichlorobenzene was added as the solvent. The resultant mixture was heated at 200°C in a silicone oil bath under a nitrogen stream and the reaction was allowed to proceed for 48 hours. After the reaction was completed, the reaction mixture was filtered under suction before being cooled and the obtained filtrate was concentrated using an evaporator. To the obtained oily product, 30 ml of methanol was added. The formed solid substance was separated by filtration under a reduced pressure and a gray solid substance was obtained. The obtained solid substance was recrystallized from benzene and 1.7 g (the yield: 17%) of white crystals were obtained. It was confirmed by 90 MHz ¹H-NMR and FD-MS that the obtained crystals were the target substance (A26). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for C₃₈H₂₆N₂=510; found: m/z=510 (M⁺, 100)

[0087] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 4 (Synthesis of Compound (A27))

[0088] The route of synthesis of Compound (A27) is shown in the following.




[0089] In accordance with the same procedures as those conducted in Synthesis Example 3 (2) except that 2-biphenyl-3-phenylindole was used in place of 2-biphenylindole, 2.2 g (the yield: 19%) of white crystals were obtained. It was confirmed by 90 MHz 1H -NMR and FD-MS that the obtained crystals were the target substance (A27). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $C_{44}H_{30}N_2=586$; found: $m/z=586$ (M^+ , 100)

[0090] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 5 (Synthesis of Compound (A11))

[0091] The route of synthesis of Compound (A11) is shown in the following.



(1) Synthesis of Intermediate Compound (E)

[0092] 3,6-Biphenyl-9-p-bromophenylcarbazole in an amount of 7.6 g (16 mmoles) was dissolved into 70 ml of ether. To the obtained solution, 12 ml of a hexane solution (1.6 M) of n-butyllithium was added at $-60^\circ C$. After the resultant solution was stirred at a temperature between $-60^\circ C$ and $0^\circ C$ for 2 hours, the solution was cooled at $-60^\circ C$ again and a solution obtained by diluting 8.8 g of triisopropyl borate with 10 ml of ether was added dropwise. After the resultant mixture was stirred at a temperature between $-60^\circ C$ and $0^\circ C$ for 2 hours, the reaction was quenched by adding a 5% aqueous solution of hydrochloric acid. The formed crystals were separated by filtration and washed with water and methanol and 4.0 g (the yield: 58%) of Intermediate Compound (E) was obtained.

(2) Synthesis of Compound (A11)

[0093] 2-(4'-Bromophenyl)imidazo[1,2-a]pyridine in an amount of 2.0 g (7.3 mmoles), 3.5 g (8.0 mmoles) of Intermediate Compound (E), 0.2 g of copper powder and 0.17 g of tetrakis(triphenylphosphine)palladium were dissolved into 30 ml of 1,2-dimethoxyethane. To the resultant solution, 12 ml of a 2.0 M aqueous solution of sodium carbonate was added and the obtained solution was heated for 8 hours under the refluxing condition. After the reaction was


completed, the formed solid substance was dissolved into dichloromethane, washed with water and dried with sodium sulfate. After the solvent was removed by distillation, the obtained product was washed with methanol and 2.0 g (the yield: 47%) of yellowish white solid substance was obtained. It was confirmed by 90 MHz $^1\text{H-NMR}$ and FD-MS that the obtained solid substance was the target substance (A11). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $\text{C}_{43}\text{H}_{29}\text{N}_3=587$; found: $m/z=587$ (M^+ , 100)

[0094] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 6 (Synthesis of Compound (A9))

[0095] The route of synthesis of Compound (A9) is shown in the following.




[0096] Intermediate Compound (C) obtained in Synthesis Example 2 in an amount of 2.0 g (5.2 mmoles), 1.7 g (5.8 mmoles) of 4-(9'-carbazolyl)-phenylboronic acid and 0.11 g of tetrakis(triphenylphosphine)palladium were dissolved into 20 ml of 1,2-dimethoxyethane. To the resultant solution, 9 ml of a 2.0 M aqueous solution of sodium carbonate was added and the obtained solution was heated for 8 hours under the refluxing condition. After the reaction was completed, the formed solid substance was dissolved into dichloromethane, washed with water and dried with sodium sulfate. After the solvent was removed by distillation, the obtained product was washed with methanol and 1.8 g (the yield: 62%) of yellowish white solid substance was obtained. It was confirmed by 90 MHz $^1\text{H-NMR}$ and FD-MS that the obtained solid substance was the target substance (A9). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $\text{C}_{39}\text{H}_{26}\text{N}_4=550$; found: $m/z=550$ (M^+ , 100)

[0097] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 7 (Synthesis of Compound (A43))

[0098] The route of synthesis of Compound (A43) is shown in the following.




15 **[0099]** Under a stream of argon, 2.33 g (10 mmoles) of 2,3-dicyano-5-(p-bromophenyl)-7-methyl-6H-1,4-diazepine, 2 g (12 mmoles) of carbazole, 0.14 g (1.5% by mole) of tris(dibenzylideneacetone)dipalladium, 0.06 g (3% by mole) of tri-*t*-butylphosphine, 2.0 g (22 mmoles) of sodium *t*-butoxide and 100 ml of dry toluene were placed into a 200 ml three-necked flask equipped with a condenser and the resultant mixture was heated at 100°C under stirring for one night. After the reaction was completed, the formed crystals were separated by filtration and washed with 100 ml of methanol and 1.2 g (3 mmoles) (the yield: 30%) of a light yellow powder was obtained. It was confirmed by the measurements of NMR, IR and FD-MS that the obtained powder was the target substance (A43). The result of the measurement by FD-MS is shown in the following:

20

25 FD-MS calcd. for $C_{26}H_{17}N_5=399$; found: $m/z=399$ (M^+ , 100)

Synthesis Example 8 (Synthesis of Compound (A45))

30 **[0100]** The route of synthesis of Compound (A45) is shown in the following.




45 **[0101]** Under a stream of argon, 4.5 g (10 mmole) of 2,3-dicyano-5,7-bis(p-bromophenyl)-6H-1,4-diazepine, 4 g (24 mmoles) of carbazole, 0.28 g (1.5% by mole) of tris(dibenzylideneacetone)dipalladium, 0.12 g (3% by mole) of tri-*t*-butylphosphine, 4.2 g (44.2 mmoles) of sodium *t*-butoxide and 160 ml of dry toluene were placed into a 200 ml three-necked flask equipped with a condenser and the resultant mixture was heated at 100°C under stirring for 18 hours. After the reaction was completed, the formed crystals were separated by filtration and washed with 100 ml of methanol and 1.8 g (2.9 mmoles) (the yield: 29%) of a white powder was obtained. It was confirmed by the measurements of NMR, IR and FD-MS that the obtained powder was the target substance (A45). The result of the measurement by FD-MS is shown in the following:

50

55 FD-MS calcd. for $C_{43}H_{26}N_6=626$; found: $m/z=626$ (M^+ , 100)

Synthesis Example 9 (Synthesis of Compound (B9))

[0102] The route of synthesis of Compound (B9) is shown in the following.




[0103] Under the atmosphere of argon, 11 g (32 mmole, 2.6 eq) of 4-(2'-phenyl-4'-pyridyl)pyrimidin-6'-ylphenylboric acid, 5 g (12 mmole) of 3,6-dibromo-9-phenylcarbazole and 0.55 g (0.48 mmole, 2% Pd) of tetrakis(triphenylphosphine)palladium(0) were suspended in 100 ml of 1,2-dimethoxyethane. To the resultant suspension, 10.2 g of a 2 M aqueous solution of sodium carbonate (96 mmole, 3 eq/50 ml) was added and the resultant mixture was heated for 10 hours under the refluxing condition. After the organic layer was separated and concentrated, the product was purified in accordance with the column chromatography and 8.5 g (the yield: 83%) of a white solid substance was obtained. It was confirmed by 90 MHz ¹H-NMR and FD-MS that the obtained solid substance was the target substance (B9). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for C₆₀H₃₉N₇=857; found: m/z=857 (M⁺, 100)

[0104] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 10 (Synthesis of Compound (B11))

[0105] The route of synthesis of Compound (B11) is shown in the following.




[0106] Under the atmosphere of argon, 7.6 g (32 mmole, 2.6 eq) of 4-(imidazopyridin-2'-yl)phenylboric acid, 5 g (12 mmole) of 3,6-dibromo-9-phenylcarbazole and 0.55 g (0.48 mmole, 2% Pd) of tetrakis(triphenylphosphine)palladium(0) were suspended in 100 ml of 1,2-dimethoxyethane. To the resultant suspension, 10.2 g of a 2 M aqueous solution of sodium carbonate (96 mmole, 3 eq/50 ml) was added and the resultant mixture was heated for 10 hours under the refluxing condition. After the organic layer was separated and concentrated, the product was purified in accordance with the column chromatography and 5.7 g (the yield: 76%) of a white solid substance was obtained. It was confirmed by 90 MHz ¹H-NMR and FD-MS that the obtained solid substance was the target substance (B11). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $C_{44}H_{29}N_5=627$; found: $m/z=627$ (M^+ , 100)

[0107] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 11 (Synthesis of Compound (A72))

[0108] The route of synthesis of Compound (A72) is shown in the following.



(1) Synthesis of Intermediate Compound (F)

[0109] In accordance with the same procedures as those conducted in Synthesis Example 2 (1) except that acetophenone was used in place of 2-acetylpyridine, 29.4 g (the yield: 84%) of Intermediate Compound (F) was obtained.

(2) Synthesis of Intermediate Compound (G)

[0110] Intermediate Compound (F) in an amount of 9.0 g (31 mmoles), 8.7 g (31 mmoles) of 1-phenylpyridinium bromide and 19.3 g (250 mmoles) of ammonium acetate were suspended into 27 ml of acetic acid and the resultant suspension was heated for 12 hours under the refluxing condition. The reaction solution was then cooled at the room temperature. Toluene and water were added and the resultant mixture was separated into two layers. The organic layer was washed with a 10% aqueous solution of sodium hydroxide and a saturated aqueous solution of sodium chloride, successively, and dried with anhydrous sodium sulfate. After the organic solvent was removed by distillation under a reduced pressure, 27 ml of ethanol was added. The formed crystals were separated by filtration and washed with ethanol and 10.6 g (the yield: 88%) of Intermediate Compound (G) was obtained.

(3) Synthesis of Compound (A72)


[0111] Intermediate Compound (G) in an amount of 3.5 g (9 mmoles), 1.7 g (10 mmoles) of carbazole, 0.09 g (0.5 mmoles) of copper iodide and 4.0 g (19 mmoles) of potassium phosphate were suspended into 18 ml of 1,4-dioxane. To the obtained suspension, 0.5 ml (4 mmoles) of trans-1,2-cyclohexanediamine was added. Under the atmosphere of argon, the resultant mixture was heated for 18 hours under the refluxing condition. The reaction solution was then cooled at the room temperature. Methylene chloride and water were added and the resultant mixture was separated into two layers. The organic layer was washed with a 5% aqueous solution of hydrochloric acid and water, successively, and dried with anhydrous sodium sulfate. After the organic solvent was removed by distillation, 15 ml of ethyl acetate was added. The formed crystals were separated by filtration and washed with ethyl acetate and 3.5 g (the yield: 83%) of yellowish white crystals were obtained. It was confirmed by 90 MHz 1H -NMR and FD-MS that the obtained crystals were the target substance (A72). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $C_{35}H_{24}N_2=472$; found: $m/z=472$ (M^+ , 100)

[0112] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 12 (Synthesis of Compound (A73))

[0113] The route of synthesis of Compound (A73) is shown in the following.



(1) Synthesis of Intermediate Compound (H)

[0114] In accordance with the same procedures as those conducted in Synthesis Example 2 (2) except that Intermediate Compound (F) obtained in Synthesis Example 11 was used in place of Intermediate Compound (B), 7.8 g (the yield: 61%) of Intermediate Compound (H) was obtained.


(2) Synthesis of Compound (A73)

[0115] In accordance with the same procedures as those conducted in Synthesis Example 11 (3) except that Intermediate Compound (H) was used in place of Intermediate Compound (G), 3.3 g (the yield: 76%) of yellowish white crystals were obtained. It was confirmed by 90 MHz ¹H-NMR and FD-MS that the obtained crystals were the target substance (A73). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for C₃₄H₂₃N₃=473; found: m/z=473 (M⁺, 100)

[0116] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3. Synthesis Example 13 (Synthesis of Compound (A113))

[0117] The route of synthesis of Compound (A113) is shown in the following.




[0118] In accordance with the same procedures as those conducted in Synthesis Example 11 (3) except that Intermediate Compound (C) obtained in Synthesis Example 2 was used in place of Intermediate Compound (G), 1.5 g (the yield: 50%) of yellowish white crystals were obtained. It was confirmed by 90 MHz ¹H-NMR and FD-MS that the obtained crystals were the target substance (A113). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $C_{33}H_{22}N_4=474$; found: $m/z=474$ (M^+ , 100)

[0119] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 14 (Synthesis of Compound (A98))

[0120] The route of synthesis of Compound (A98) is shown in the following.



(1) Synthesis of Intermediate Compound (J)

[0121] In accordance with the same procedures as those conducted in Synthesis Example 2 (1) except that 3,5-dibromobenzaldehyde was used in place of 4-bromobenzaldehyde and acetophenone was used in place of 2-acetylpyridine, 19.2 g (the yield: 92%) of Intermediate Compound (J) was obtained.

(2) Synthesis of Intermediate Compound (K)

[0122] In accordance with the same procedures as those conducted in Synthesis Example 2 (2) except that Intermediate Compound (J) was used in place of Intermediate Compound (B), 5.5 g (the yield: 45%) of Intermediate Compound (K) was obtained.

(3) Synthesis of Compound (A98)


[0123] Intermediate Compound (K) in an amount of 3.0 g (6 mmoles), 2.3 g (14 mmoles) of carbazole, 0.12 g (0.6 mmoles) of copper iodide and 4.2 g (20 mmoles) of potassium phosphate were suspended into 21 ml of 1,4-dioxane. To the obtained suspension, 0.8 ml (6 mmoles) of trans-1,2-cyclohexanediamine was added. Under the atmosphere of argon, the resultant mixture was heated for 18 hours under the refluxing condition. The reaction solution was then cooled at the room temperature. Methylene chloride and water were added and the resultant mixture was separated into two layers. The organic layer was washed with water and dried with anhydrous sodium sulfate. After the organic solvent was removed by distillation under a reduced pressure, the residue of distillation was suspended into 21 ml of dioxane. To the obtained suspension, 0.12 g (0.6 mmoles) of copper iodide, 2.9 g (14 mmoles) of potassium phosphate and 0.8 ml (6 mmoles) of trans-1,2-cyclohexanediamine were added. Under the atmosphere of argon, the resultant mixture was heated for 18 hours under the refluxing condition. The reaction solution was then cooled at the room temperature. Methylene chloride and water were added and the resultant mixture was separated into two layers. The organic layer was washed with water and dried with anhydrous sodium sulfate. After the organic solvent was removed by distillation under a reduced pressure, 30 ml of ethyl acetate was added. The formed crystals were separated by filtration and washed with ethyl acetate and 3.3 g (the yield: 80%) of yellowish white crystals were obtained. It was confirmed by 90 MHz 1H -NMR and FD-MS that the obtained crystals were the target substance (A98). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $C_{46}H_{30}N_4=638$; found: $m/z=638$ (M^+ , 100)

[0124] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 15 (Synthesis of Compound (A105))

[0125] The route of synthesis of Compound (A105) is shown in the following.



(1) Synthesis of Intermediate Compound (M)

[0126] In accordance with the same procedures as those conducted in Synthesis Example 11 (2) except that Intermediate Compound (J) obtained in Synthesis Example 14 (1) was used in place of Intermediate Compound (F), 10.0 g (the yield: 88%) of Intermediate Compound (M) was obtained.

(2) Synthesis of Compound (A105)


[0127] In accordance with the same procedures as those conducted in Synthesis Example 14 (3) except that Intermediate Compound (M) was used in place of Intermediate Compound (K), 2.9 g (the yield: 71%) of yellowish white crystals were obtained. It was confirmed by 90 MHz ¹H-NMR and FD-MS that the obtained crystals were the target substance (A105). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for C₄₇H₃₁N₃=637; found: m/z=637 (M⁺, 100)

[0128] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Synthesis Example 16 (Synthesis of Compound (A108))

[0129] The route of synthesis of Compound (A108) is shown in the following.



(1) Synthesis of Intermediate Compound (N)

[0130] 1,3,5-Tribromobenzene in an amount of 13.0 g (41 mmoles), 10.0 g (45 mmoles) of 3,5-diphenylpyrazole, 0.8 g (4 mmoles) of copper iodide and 11.9 g (86 mmoles) of potassium carbonate were suspended into 50 ml of 1,4-dioxane. To the obtained suspension, 4.9 ml (41 mmoles) of trans-1,2-cyclohexanediamine was added. Under the atmosphere of argon, the resultant mixture was heated for 18 hours under the refluxing condition. The reaction solution

was then cooled at the room temperature. Methylene chloride and water were added and the resultant mixture was separated into two layers. The organic layer was washed with water and dried with anhydrous sodium sulfate. After the organic solvent was removed by distillation under a reduced pressure, the remaining product was purified in accordance with the silica gel column chromatography and 2.0 g (the yield: 11%) of Intermediate Compound (N) was obtained.

(2) Synthesis of Compound (A108)

[0131] Intermediate Compound (N) in an amount of 2.0 g (4 mmoles), 1.4 g (8 mmoles) of carbazole, 0.08 g (0.4 mmoles) of copper iodide and 2.9 g (14 mmoles) of potassium phosphate were suspended into 15 ml of 1,4-dioxane. To the obtained suspension, 0.5 ml (4 mmoles) of trans-1,2-cyclohexanediamine was added. Under the atmosphere of argon, the resultant mixture was heated for 18 hours under the refluxing condition. The reaction solution was then cooled at the room temperature. Methylene chloride and water were added and the resultant mixture was separated into two layers. The organic layer was washed with water and dried with anhydrous sodium sulfate. After the organic solvent was removed by distillation, the residue of distillation was suspended into 15 ml of 1,4-dioxane. To the obtained suspension, 0.08 g (0.4 mmoles) of copper iodide, 2.9 g (14 mmoles) of potassium phosphate and 0.5 ml (4 mmoles) of trans-1,2-cyclohexanediamine were added. Under the atmosphere of argon, the resultant mixture was heated for 14 hours under the refluxing condition. The reaction solution was then cooled at the room temperature. Methylene chloride and water were added and the resultant mixture was separated into two layers. The organic layer was washed with water and dried with anhydrous sodium sulfate. After the organic solvent was removed by distillation under a reduced pressure, 5 ml of ethanol and 15 ml of ethyl acetate were added. The formed crystals were separated by filtration and washed with a mixed solvent containing ethyl acetate and ethanol in relative amounts by volume of 5:2 and 2.4 g (the yield: 87%) of yellowish white crystals were obtained. It was confirmed by 90 MHz $^1\text{H-NMR}$ and FD-MS that the obtained crystals were the target substance (A108). The result of the measurement by FD-MS is shown in the following:

FD-MS calcd. for $\text{C}_{45}\text{H}_{30}\text{N}_4=626$; found: $m/z=626$ (M^+ , 100)

[0132] The values of the energy gaps were obtained in accordance with the same methods as those in Synthesis Example 1 and the results are shown in Table 3.

Table 3


	Compound	Singlet energy gap (eV)	Triplet energy gap (eV)
Synthesis Example 1	A5	3.2	2.7
Synthesis Example 2	A3	3.1	2.7
Synthesis Example 3	A26	3.1	2.6
Synthesis Example 4	A27	3.0	2.6
Synthesis Example 5	A11	3.0	2.7
Synthesis Example 6	A9	3.1	2.5
Synthesis Example 9	B9	3.2	2.6
Synthesis Example 10	B11	3.2	2.7
Synthesis Example 11	A72	3.5	2.8
Synthesis Example 12	A73	3.3	2.8
Synthesis Example 13	A113	3.2	2.7
Synthesis Example 14	A98	3.5	2.9
Synthesis Example 15	A105	3.4	2.9
Synthesis Example 16	A108	3.7	3.0

Example 1

[0133] A glass substrate (manufactured by GEOMATEC Company) of 25 mm \times 75 mm \times 1.1 mm thickness having an ITO transparent electrode was cleaned by application of ultrasonic wave in isopropyl alcohol for 5 minutes and then

by exposure to ozone generated by ultraviolet light for 30 minutes. The glass substrate having the transparent electrode lines which had been cleaned was attached to a substrate holder of a vacuum vapor deposition apparatus. On the surface of the cleaned substrate at the side having the transparent electrode, a film of N,N'-bis(N,N'-diphenyl-4-aminophenyl)-N,N'-diphenyl-4,4'-diamino-1,1'-biphenyl (a film of TPD232) having a thickness of 60 nm was formed in a manner such that the formed film covered the transparent electrode. The formed film of TPD232 worked as the hole injecting layer. On the formed film of TPD232, a film of 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (a film of NPD) having a thickness of 20 nm was formed by vapor deposition. The formed film of NPD worked as the hole transporting layer. On the formed film of NPD, a film of the above Compound (A5) having a thickness of 40 nm was formed by vapor deposition. At the same time, Compound (D1) shown in the following was vapor deposited in an amount such that the ratio of the amounts by weight of Compound (A5) to Compound (D1) was 40:3. Compound (D1) is a light emitting compound having a singlet energy as low as 2.79 eV so that blue light is emitted. The formed mixed film of Compound (A5) and Compound (D1) worked as the light emitting layer. On the film formed above, a film of BAlq shown in the following (Me means methyl group) having a thickness of 20 nm was formed. The film of BAlq worked as the electron injecting layer. Thereafter, Li (the source of lithium: manufactured by SAES GETTERS Company) as the reducing dopant and Alq were binary vapor deposited and an Alq:Li film having a thickness of 10 nm was formed as the second electron injecting layer (the cathode). On the formed Alq:Li film, metallic aluminum was vapor deposited to form a metal cathode and an organic EL device was prepared.

[0134] When a direct current voltage of 5.0 V was applied to the organic EL device prepared above, blue light was emitted at a luminance of 150 cd/m² and an efficiency of the light emission of 6.3 cd/A. The chromatic coordinates were (0.14, 0.16) and the purity of color was excellent.




Examples 2 to 8

[0135] In accordance with the same procedures as those conducted in Example 1 except that compounds shown in Table 4 were used in place of Compound (A5), organic EL devices were prepared and the voltage of the direct current, the luminance of the emitted light, the efficiency of the light emission, the color of the emitted light and the purity of color were measured. The results are shown in Table 4.

Comparative Example 1


[0136] In accordance with the same procedures as those conducted in Example 1 except that a conventional compound BCz shown in the following was used in place of Compound (A5), an organic EL device was prepared and the voltage of the direct current, the luminance of the emitted light, the efficiency of the light emission, the color of the emitted light and the purity of color were measured. The results are shown in Table 4.



BCz

Comparative Example 2

[0137] In accordance with the same procedures as those conducted in Example 1 except that Compound (C2) shown in the following which is described in Japanese Patent Application Laid-Open No. 2001-288462 was used in place of Compound (A5), an organic EL device was prepared and the voltage of the direct current, the luminance of the emitted light, the efficiency of the light emission, the color of the emitted light and the purity of color were measured. The results are shown in Table 4.



(C2)

Table 4


	Organic host material of light emitting layer	Voltage	Luminance of emitted light	Efficiency of light emission	Color of emitted light	Chromatic coordinates
		(V)	(cd/m ²)	(cd/A)		
Example 1	A5	5.0	150	6.3	blue	(0.14,0.16)
Example 2	A3	5.8	160	5.8	blue	(0.15,0.17)
Example 3	A26	6.0	132	5.2	blue	(0.14, 0.16)
Example 4	A27	6.0	154	5.9	blue	(0.14, 0.16)
Example 5	All	5.2	180	6.3	blue	(0.15, 0.17)
Example 6	A9	6.2	145	5.1	blue	(0.15, 0.16)
Example 7	B9	5.7	151	5.7	blue	(0.15,0.17)
Example 8	B11	5.0	181	6.9	blue	(0.15, 0.17)
Comparative Example 1	BCz	8.5	70	2.4	blue	(0.14, 0.16)
Comparative Example 2	C2	6.5	65	2.6	blue	(0.14, 0.16)

[0138] As shown in Table 4, in comparison with the organic EL devices using conventional compounds BCz and (C2) in Comparative Examples 1 and 2, respectively, the organic EL devices using the compounds of the present invention could be driven at lower voltages and emitted blue light in higher efficiencies. Since the energy gap of the compounds of the present invention is great, light emitting molecules having a great energy gap could be mixed into the light emitting layer and used for the light emission.


Example 9

[0139] A glass substrate (manufactured by GEOMATEC Company) of 25 mm × 75 mm × 0.7 mm thickness having an ITO transparent electrode was cleaned by application of ultrasonic wave in isopropyl alcohol for 5 minutes and then by exposure to ozone generated by ultraviolet light for 30 minutes. The glass substrate having the transparent electrode lines which had been cleaned was attached to a substrate holder of a vacuum vapor deposition apparatus. On the surface of the cleaned substrate at the side having the transparent electrode, a film of copper phthalocyanine shown in the following (a film of CuPc) having a thickness of 10 nm was formed in a manner such that the formed film covered the transparent electrode. The formed film of CuPc worked as the hole injecting layer. On the formed film of CuPc, a film of 1,1'-bis[4-N,N-di(p-tolyl)aminophenyl]cyclohexane (a film of TPAC) having a thickness of 30 nm was formed. The formed film of TPAC worked as the hole transporting layer. On the formed film of TPAC, a film of the above Compound (A72) having a thickness of 30 nm was formed by vapor deposition and the light emitting layer was formed. At the same time, Ir bis[(4,6-difluorophenyl)pyridinato-N,C^{2'}] picolinate (Flrpic shown in the following) as the phosphorescent Ir metal complex was added. The concentration of Flrpic in the light emitting layer was set at 7% by weight. This layer worked as the light emitting layer. On the film formed above, a film of Alq having a thickness of 30 nm was formed. The film of Alq worked as the electron injecting layer. Thereafter, LiF as the alkali metal halide was vapor deposited in an amount such that the formed film had a thickness of 0.2 nm and, then, aluminum was vapor deposited in an amount such that the formed film had a thickness of 150 nm. The formed film of Alq:Li film worked as the cathode. Thus, an organic EL device was prepared.


[0140] When the obtained device was tested by passing the electric current, bluish green light having a luminance of 89 cd/m² was emitted at a voltage of 6.6 V and a current density of 0.59 mA/cm². The chromatic coordinates were (0.18, 0.39) and the efficiency of the light emission was 14.98 cd/A.



CuPc



TPAC



Flrpic

Examples 10 to 12

[0141] In accordance with the same procedures as those conducted in Example 9 except that compounds shown in


Table 5 were used in place of Compound (A72), organic EL devices were prepared and the voltage of the direct current, the current density, the luminance of the emitted light, the efficiency of the light emission, the color of the emitted light and the purity of color were measured. The results are shown in Table 5.

Comparative Example 3

[0142] In accordance with the same procedures as those conducted in Example 9 except that the conventional compound BCz was used in place of Compound (A72), an organic EL device was prepared and the voltage of the direct current, the current density, the luminance of the emitted light, the efficiency of the light emission, the color of the emitted light and the purity of color were measured. The results are shown in Table 5.

Comparative Example 4

[0143] In accordance with the same procedures as those conducted in Comparative Example 3 except that 4,4'-bis [N-(1-naphthyl)-N-phenylamino]biphenyl (α -NPD shown in the following) was used for the hole transporting layer in place of the compound TPAC and BAlq shown above was used for the electron transporting layer in place of the compound Alq, an organic EL device was prepared and the voltage of the direct current, the current density, the luminance of the emitted light, the efficiency of the light emission, the color of the emitted light and the purity of color were measured. The results are shown in Table 5.



α -NPD

Table 5

	Organic host material of light emitting layer	Voltage	Current density	Luminance of emitted light	Efficiency of light emission	Color of emitted light	Chromatic coordinates
		(V)	(mA/cm ²)	(cd/m ²)	(cd/A)		
Example 9	A72	6.6	0.59	89	14.98	bluish green	(0.18,0.39)
Example 10	A98	6.4	0.54	86	15.89	bluish green	(0.18,0.40)
Example 11	A105	6.9	0.84	99	11.76	bluish green	(0.17, 0.40)
Example 12	A73	6.0	1.00	99	9.91	bluish green	(0.16, 0.39)
Comparative Example 3	BCz	7.8	1.70	98	5.80	bluish green	(0.16, 0.37)
Comparative Example 4	BCz	7.6	1.09	99	9.15	bluish green	(0.17, 0.37)

[0144] As shown in Table 5, in comparison with the organic EL devices using the conventional compound BCz in Comparative Examples 3 and 4, the organic EL devices using the compounds of the present invention could be driven at a lower voltage and emit blue light at a higher efficiency. Since the energy gap of the compounds of the present invention is great, light emitting molecules having a great energy gap could be mixed into the light emitting layer and


used for the light emission.

INDUSTRIAL APPLICABILITY

[0145] As described above in detail, by utilizing the material for organic electroluminescence devices comprising the compound represented by general formula (1) or (2) of the present invention, the organic electroluminescence device emitting blue light with a high efficiency of light emission and an excellent purity of color can be obtained. Therefore, the organic electroluminescence device of the present invention is very useful as the light source for various electronic instruments.

Claims

1. A material for organic electroluminescence devices which comprises a compound represented by following general formula (1) or (2):



wherein Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group, A represents a group represented by following general formula (A):



wherein M and M' each independently represent a heteroaromatic ring having 2 to 40 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, M and M' may represent a same ring or different rings, L represents a single bond, a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms, a substituted or unsubstituted cycloalkylene group having 5 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms, **p** represents an integer of 0 to 2, **q** represents an integer of 1 or 2, **r** represents an integer of 0 to 2, and **p+r** represents an integer of 1 or greater; and n and m each represent an integer of 1 to 3.

2. A material for organic electroluminescence devices according to Claim 1, wherein
n=1 in general formula (1) and **p=1** and **r=0** in general formula (A);
 in general formula (1), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group; and
 in general formula (A), M represents a heterocyclic six-membered or seven-membered ring having 4 or 5 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic five-membered ring having 2 to 4 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic ring having 8 to 11 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring or a substituted or unsubstituted imidazopyridinyl ring, and L represents a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.
3. A material for organic electroluminescence devices according to Claim 1, wherein
n=2 in general formula (1) and **p=1** and **r=0** in general formula (A);
 in general formula (1), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolylalkylene group; and
 in general formula (A), M represents a heterocyclic six-membered or seven-membered ring having 4 or 5 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic five-membered ring having 2 to 4 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, a heterocyclic ring having 8 to 11 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring or a substituted or unsubstituted imidazopyridinyl ring, and L represents a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.

4. A material for organic electroluminescence devices according to Claim 1, wherein
 $n=1$ in general formula (1) and $p=2$ and $r=0$ in general formula (A);
in general formula (1), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolyllkylene group; and
in general formula (A), M represents a heteroaromatic ring having 2 to 40 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, and L represents a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.
5. A material for organic electroluminescence devices according to Claim 1, wherein
 $m=2$ in general formula (2) and $p=q=1$ in general formula (A);
in general formula (2), Cz represents a substituted or unsubstituted arylcarbazolyl group or carbazolyllkylene group; and
in general formula (A), M and M' each independently represent a heteroaromatic ring having 2 to 40 carbon atoms and nitrogen atom and forming a substituted or unsubstituted ring, and M and M' may represent a same ring or different rings, and L represents a substituted or unsubstituted aryl group or arylene group having 6 to 30 carbon atoms, a substituted or unsubstituted cycloalkylene group having 5 to 30 carbon atoms or a substituted or unsubstituted heteroaromatic ring having 2 to 30 carbon atoms.
6. A material for organic electroluminescence devices according to Claim 1, wherein Cz represents a substituted or unsubstituted arylcarbazolyl group.
7. A material for organic electroluminescence devices according to Claim 6, wherein Cz represents a substituted or unsubstituted phenylcarbazolyl group.
8. A material for organic electroluminescence devices according to Claim 6, wherein an aryl portion of the arylcarbazolyl group is substituted with carbazolyl group.
9. A material for organic electroluminescence devices according to Claim 1, wherein a triplet energy gap of a compound represented by general formula (1) or (2) is 2.5 to 3.3 eV.
10. A material for organic electroluminescence devices according to Claim 1, wherein a singlet energy gap of a compound represented by general formula (1) or (2) is 2.8 to 3.8 eV.
11. An organic electroluminescence device comprising an anode, a cathode and an organic thin film layer comprising at least one layer and disposed between the anode and the cathode, wherein at least one layer in the organic thin film layer comprises a material for organic electroluminescence devices described in Claim 1.
12. An organic electroluminescence device comprising an anode, a cathode and an organic thin film layer comprising at least one layer and disposed between the anode and the cathode, wherein a light emitting layer comprises a material for organic electroluminescence devices described in Claim 1.
13. An organic electroluminescence device comprising an anode, a cathode and an organic thin film layer comprising at least one layer and disposed between the anode and the cathode, wherein an electron transporting layer comprises a material for organic electroluminescence devices described in Claim 1.
14. An organic electroluminescence device comprising an anode, a cathode and an organic thin film layer comprising at least one layer disposed between the anode and the cathode, wherein a hole transporting layer comprises a material for organic electroluminescence devices described in Claim 1.
15. An organic electroluminescence device according to Claim 11, wherein the material for organic electroluminescence devices is an organic host material.
16. An organic electroluminescence device according to Claim 11, which comprises an inorganic compound layer disposed between at least one of the electrodes and the organic thin film layer.
17. An organic electroluminescence device according to Claim 11, which emits light by a multiplet excitation which is excitation to a triplet state or higher.

18. An organic electroluminescence device according to Claim 11, which emits bluish light.

5

10

15

20

25

30

35

40

45

50

55

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/03329

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl⁷ C09K11/06, H05B33/14, H05B33/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl⁷ C09K11/06, H05B33/14, H05B33/22

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CA (STN), REGISTRY (STN)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	JP 2001-247858 A (Fuji Photo Film Co., Ltd.), 14 September, 2001 (14.09.01), Claim 1; Par. Nos. [0039] to [0046]; example 1 (Family: none)	1, 2, 6, 7, 9-18 3, 4, 5, 8
X A	WO 01/72927 A1 (Idemitsu Kosan Co., Ltd.), 04 October, 2001 (04.10.01), & EP 1205527 A1 & US 2002/45061 A1	1, 5-7, 9-18 2-4, 8
X A	JP 2000-68059 A (Toyo Ink Manufacturing Co., Ltd.), 03 March, 2000 (03.03.00), Claims; page 5 (Family: none)	1-3, 6, 7, 9-18 4, 5, 8

☒ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:	"I" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search
30 May, 2003 (30.05.03)Date of mailing of the international search report
17 June, 2003 (17.06.03)Name and mailing address of the ISA/
Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

Form PCT/ISA/210 (second sheet) (July 1998)

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/03329

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	JP 2000-169448 A (Minolta Co., Ltd.), 20 June, 2000 (20.06.00), Claims; Par. Nos. [0032] to [0045] (Family: none)	1,2,6-18 3,4,5
X A	JP 11-111460 A (Toyo Ink Manufacturing Co., Ltd.), 23 April, 1999 (23.04.99), Claims; Par. Nos. [0035] to [0047] (Family: none)	1,8-18 2-7
X A	JP 2001-64640 A (Toyo Ink Manufacturing Co., Ltd.), 13 March, 2001 (13.03.01), Claims; Par. Nos. [0036] to [0041] (Family: none)	1,2,6,7,9-18 3-5,8
X A	JP 2001-192653 A (Fuji Photo Film Co., Ltd.), 17 July, 2001 (17.07.01), Claims; Par. Nos. [0089] to [0108] (Family: none)	1-3,6,7,9-18 4,5,8
X A	JP 2001-207167 A (Toyo Ink Manufacturing Co., Ltd.), 31 July, 2001 (31.07.01), Claims; Par. No. [0055] (Family: none)	1,6,9-18 2-5,7,8
X A	WO 01/019939 A1 (Ciba Specialty Chemicals Holding Inc.), 22 March, 2001 (22.03.01), & JP 2003-509441 A & US 6258954 A & EP 1216285 A1	1-3,6,7,9-18 4,5,8
X A	EP 926216 A1 (CHISSO CORP.), 30 June, 1999 (30.06.99), & JP 11-222590 A	1,3,6,7,9-18 2,4,5,8
P,X	EP 1202608 A2 (Kabushiki Kaisha Toyota Chuo Kenkyusho), 02 May, 2002 (02.05.02), & JP 2002-203683 A	1,6,7,9-18
P,X	JP 2003-31371 A (Mitsubishi Chemical Corp.), 31 January, 2003 (31.01.03), Claims; Par. Nos. [0047] to [0058] (Family: none)	1,6-18

Form PCT/ISA/210 (continuation of second sheet) (July 1998)

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/03329

Box I Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

The claim of this application includes two groups of inventions having the following matters as the "technical feature":

(I) a material for organic electroluminescent devices consisting of a compound of the general formula (1) or (2) wherein Cz is a substituted or unsubstituted arylcarbazole group, and

(II) a material for organic electroluminescent devices consisting of a compound of the general formula (1) or (2) wherein Cz is a substituted or unsubstituted carbazoylalkylene group.

The "technical feature" common to any two of the groups (I) and (II) is (continued to extra sheet)

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest ☐ The additional search fees were accompanied by the applicant's protest.
☒ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP03/03329

Continuation of Box No. II of continuation of first sheet (1)

a material for organic electroluminescent devices consisting of a compound having a structure wherein a group having carbazoyl skeleton and a substituent of the general formula (A) are bonded directly to each other, but such materials for organic electroluminescent devices are known (see Japanese Patent Laid-Open No. 2001-247858) and are therefore not considered as a "special technical feature" within the meaning of PCT Rule 13.2.

Thus, the groups (I) and (II) do not have any "special technical feature" in common.

专利名称(译)	用于有机电致发光器件的材料和使用其制造的有机电致发光器件		
公开(公告)号	EP1489155A1	公开(公告)日	2004-12-22
申请号	EP2003712758	申请日	2003-03-19
[标]申请(专利权)人(译)	出光兴产株式会社		
申请(专利权)人(译)	出光兴产股份有限公司.		
当前申请(专利权)人(译)	出光兴产股份有限公司.		
[标]发明人	IWAKUMA TOSHIHIRO YAMAMOTO HIROSHI HIRONAKA YOSHIO IKEDA HIDEITSUGU HOSOKAWA CHISHIO TOMITA SEIJI ARAKANE TAKASHI		
发明人	IWAKUMA, TOSHIHIRO YAMAMOTO, HIROSHI HIRONAKA, YOSHIO IKEDA, HIDEITSUGU HOSOKAWA, CHISHIO TOMITA, SEIJI ARAKANE, TAKASHI		
IPC分类号	C09K11/06 C07D401/10 C07D401/14 C07D403/10 C07D403/14 C07D471/04 C07F15/00 H01L51/00 H01L51/30 H01L51/50 H05B33/14 H05B33/22		
CPC分类号	C07D471/04 C07D401/10 C07D401/14 C07D403/10 C07D403/14 C07F15/0046 C09K11/06 C09K2211 /1007 C09K2211/1011 C09K2211/1014 C09K2211/1029 C09K2211/1044 C09K2211/1059 C09K2211 /185 H01L51/0059 H01L51/0067 H01L51/0072 H01L51/0081 H01L51/0085 H01L51/5012 H01L51/5016 H01L51/5048 H01L2251/308 H05B33/14		
代理机构(译)	GILLE HRABAL STRUCK NEIDLEIN PROP ROOS		
优先权	2002299810 2002-10-15 JP 2002081234 2002-03-22 JP		
其他公开文献	EP1489155A4		
外部链接	Espacenet		

摘要(译)

一种用于有机电致发光器件的材料，包括其中具有氮的杂环基与芳基吡啶基或吡啶基亚烷基键合的化合物和包含阳极，阴极和包含至少一层的有机薄膜层并配置的有机电致发光器件的有机电致发光器件在阳极和阴极之间，其中有机薄膜层中的至少一层包含上述用于有机电致发光器件的材料。该材料可以提供发出具有高纯度颜色的蓝色光的有机电致发光器件。有机电致发光器件使用该材料。

Table 1

n=m=1	n=2	n=3	m=2	m=3
Cz-A	Cz-A-Cz	Cz-A-Cz Cz	A-Cz-A	A-Cz-A A