



(11) **EP 2 418 707 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 153(4) EPC

(43) Date of publication:
15.02.2012 Bulletin 2012/07

(51) Int Cl.:
H01L 51/50 ^(2006.01) **C07C 13/62** ^(2006.01)
C09K 11/06 ^(2006.01) **C07F 15/00** ^(2006.01)

(21) Application number: **10761669.0**

(86) International application number:
PCT/JP2010/056166

(22) Date of filing: **05.04.2010**

(87) International publication number:
WO 2010/116970 (14.10.2010 Gazette 2010/41)

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

(30) Priority: **06.04.2009 JP 2009092523**

(71) Applicant: **Idemitsu Kosan Co., Ltd.**
Chiyoda-ku
Tokyo 100-8321 (JP)

(72) Inventors:
• **IWAKUMA, Toshihiro**
Sodegaura-shi
Chiba 299-0293 (JP)

• **TAKASHIMA, Yoriyuki**
Sodegaura-shi
Chiba 299-0293 (JP)
• **ITO, Mitsunori**
Sodegaura-shi
Chiba 299-0293 (JP)
• **OGIWARA, Toshinari**
Sodegaura-shi
Chiba 299-0293 (JP)

(74) Representative: **Prop, Gerrit**
Gille Hrabal
Patentanwälte
Brucknerstrasse 20
40593 Düsseldorf (DE)

(54) **ORGANIC ELECTROLUMINESCENT ELEMENT AND MATERIAL FOR ORGANIC ELECTROLUMINESCENT ELEMENT**

(57) An organic electroluminescence device includes: a cathode; an anode; and an organic thin-film layer including at least one layer and provided between the cathode and the anode. At least one layer of the organic thin-film layer includes: an organic-electroluminescence-device material represented by any one of the following formulae (1), (2) and (3); and at least one phosphorescent material, in which the organic-electroluminescence-device material may have a substituent. A or Ar may be substituted by a phenyl group or a naphthyl group.

EP 2 418 707 A1





FIG. 1



Description

TECHNICAL FIELD

5 **[0001]** The present invention relates to an organic electroluminescence device (hereinafter abbreviated as organic EL device as needed) and a material for the organic electroluminescence device. In particular, the present invention relates to an organic electroluminescence device including a red emitting layer and a material used for the organic electroluminescence device.

10 BACKGROUND ART

[0002] An organic EL device, which includes an organic thin-film layer (in which an emitting layer is included) between an anode and a cathode, has been known to emit light using exciton energy generated by a recombination of holes and electrons that have been injected into the emitting layer (e.g., see Patent Literature 1 to 19).

15 Such an organic EL device, which has the advantages as a self-emitting device, is expected to serve as an emitting device excellent in luminous efficiency, image quality, power consumption and thin design.

[0003] An example of a further improvement to be made in an organic EL device is an improvement in luminous efficiency.

20 In this respect, in order to enhance internal quantum efficiency, developments have been made on an emitting material (phosphorescent material) that emits light using triplet excitons. In recent years, there has been a report on a phosphorescent organic EL device.

Since the internal quantum efficiency can be enhanced up to 75% or more (up to approximately 100% in theory) by forming the emitting layer (phosphorescent-emitting layer) from such a phosphorescent material, an organic EL device having high efficiency and consuming less power can be obtained.

25 **[0004]** In forming the emitting layer, a doping method, according to which an emitting material (dopant) is doped to a host material, has been known as a usable method.

The emitting layer formed by the doping method can efficiently generate excitons from electric charges injected into the host material. With the exciton energy generated by the excitons being transferred to the dopant, the dopant can emit light with high efficiency.

30 In order to intermolecularly transfer the energy from the host material to the phosphorescent dopant, triplet energy E_{gH} of the host material is required to be larger than triplet energy E_{gD} of the phosphorescent dopant.

[0005] A known representative example of a material having effectively-large triplet energy has been CBP (4,4'-bis(N-carbazolyl)biphenyl). See, for instance, Patent Literature 1.

35 By using such CBP as the host material, energy can be transferred to a phosphorescent dopant for emitting light of a predetermined emitting wavelength (e.g., green, red), by which an organic EL device of high efficiency can be obtained. Alternatively, Patent Literature 2 discloses a technique according to which a fused-ring derivative containing a nitrogen-containing ring such as carbazole is used as the host material for a red-phosphorescent-emitting layer.

40 **[0006]** On the other hand, a variety of host materials (fluorescent hosts) for fluorescent dopants that generate fluorescent emission are known. Various proposals have been made on a host material capable of, with a combination of a fluorescent dopant, providing a fluorescent-emitting layer excellent in luminous efficiency and lifetime.

However, although a fluorescent host has larger excited singlet energy $E_g(S)$ than a fluorescent dopant, such a fluorescent host does not necessarily have larger triplet energy $E_g(T)$. Accordingly, it is not successful to simply apply the fluorescent host to the host material (phosphorescent host) for a phosphorescent-emitting layer.

[0007] A well-known example of such a fluorescent host is an anthracene derivative.

45 However, triplet energy $E_g(T)$ of an anthracene derivative is relatively small (approximately 1.9 eV). Thus, energy cannot be reliably transferred to a phosphorescent dopant for emitting light having a wavelength in a visible light range of 520 nm to 720 nm. In addition, excited triplet energy cannot be trapped within the emitting layer.

Accordingly, an anthracene derivative is not suitable for the phosphorescent host.

50 Further, derivatives such as a perylene derivative, a pyrene derivative and a naphthalene derivative are not preferable phosphorescent hosts for the same reason above.

[0008] Alternatively, an exemplary arrangement in which an aromatic hydrocarbon compound is used as the phosphorescent host has been known (Patent Literature 3). In the arrangement disclosed in Patent Literature 3, a compound in which two aromatic groups are bonded as substituents to a benzene central skeleton in meta positions is used as the phosphorescent host.

55 Patent Literature 4 to 9 disclose organic EL devices in which various aromatic hydrocarbon compounds are used.

[0009] Further, Patent Literature 10 exemplifies compounds in which fused aromatic hydrocarbon rings are arranged at right and left substituent positions of 2,7-naphthalene rings.

Patent Literature 11 exemplifies compounds in which phenanthroline rings (nitrogen-containing heterocycles) are arranged at right and left substituent positions of 2,7-naphthalene rings.

Patent Literature 12 exemplifies compounds in which aromatic substituent groups of which essential skeletons are anthracene rings are arranged at right and left substituent positions of 2,7-naphthalene rings.

5
[0010] Moreover, Patent Literature 13 and 14 disclose compounds having a structure in which four aromatic hydrocarbon rings are continuously coupled to one another and organic EL devices in which the compounds are used. Such an aromatic hydrocarbon compound is structured so that: the aromatic hydrocarbon ring at one terminal end is a fused polycyclic aromatic ring; the aromatic hydrocarbon ring adjoined and coupled to that aromatic hydrocarbon ring is a divalent benzene ring having a meta bonding; and the remaining two rings are fused aromatic rings. Patent Literature 13 and 14 further disclose that a device of which emitting layer uses both the aromatic hydrocarbon compound and a red-phosphorescent complex exhibits relatively high efficiency and relatively long device lifetime. Further, fluoranthene compounds related to this invention and organic EL devices in which the fluoranthene compounds are used are also disclosed in Patent Literature 15 to 19.

15
 CITATION LIST

PATENT LITERATURE

20
[0011]

- Patent Literature 1: US2002/0182441
- Patent Literature 2: WO2005/112519
- Patent Literature 3: JP-A-2003-142267
- 25 Patent Literature 4: WO2007/046658
- Patent Literature 5: JP-A-2006-151966
- Patent Literature 6: JP-A-2005-8588
- Patent Literature 7: JP-A-2005-19219
- Patent Literature 8: JP-A-2005-197262
- 30 Patent Literature 9: JP-A-2004-75567
- Patent Literature 10: US2008/0224603
- Patent Literature 11: JP-A-2004-281390
- Patent Literature 12: JP-A-2006-045503
- Patent Literature 13: WO2009/008215
- 35 Patent Literature 14: WO2009/008205
- Patent Literature 15: WO2002/20693
- Patent Literature 16: JP-A-2001-250690
- Patent Literature 17: JP-A-2001-244075
- Patent Literature 18: JP-A-2001-257074
- 40 Patent Literature 19: JP-A-10-189248

SUMMARY OF THE INVENTION

PROBLEMS TO BE SOLVED BY THE INVENTION

45
[0012] However, when applied with CBP as the host material, the organic EL device disclosed in Patent Literature 1 exhibits much higher luminous efficiency due to phosphorescent emission on one hand, but exhibits such a short lifetime as to be practically unusable on the other hand. Such a problem is considered to be attributed to considerable degradation of molecules by holes due to not-high oxidation stability that the molecular structure of CBP exhibits.

50 Although the organic EL device disclosed in Patent Literature 2 exhibits improvement in the luminous efficiency and lifetime, the improved luminous efficiency and lifetime may not be always sufficient for practical application. The aromatic hydrocarbon compound disclosed in Patent Literature 3 is molecularly structured such that the molecules extend from the benzene central skeleton in a manner symmetrical relative to the benzene central skeleton. Therefore, an emitting layer applied with the aromatic hydrocarbon compound tends to be easily crystallized. Accordingly, an organic EL device in which the aromatic hydrocarbon compound disclosed in Patent Literature 3 is used may require higher driving voltage.

55 Patent Literature 4 to 9 are totally silent on the effectivity of the aromatic hydrocarbon compounds used in organic EL devices as the phosphorescent hosts.

In the organic EL devices disclosed in Patent Literature 10 to 14, which require relatively high driving voltage, lifetime of the devices may not be sufficiently prolonged.

Further, Patent Literature 15 to 19 are totally silent on structures in which the fluoranthene compounds and phosphorescent materials are used together in organic EL devices.

[0013] An object of the invention is to provide a material for phosphorescent organic EL devices capable of reducing driving voltage and exhibiting high efficiency and long lifetime, and to provide an organic EL device in which the material is used.


MEANS FOR SOLVING THE PROBLEMS

[0014] After conducting concentrated studies in order to achieve such an object, the inventors have found that a phosphorescent organic EL device that requires less driving voltage and exhibits high efficiency and long lifetime can be provided by using a material for organic EL devices (hereinafter abbreviated as organic-EL-device material as needed) selected from structures respectively represented by any one of the following formulae (1), (2) and (3), and reached the invention.

[0015] Specifically, the organic EL device according to an aspect of the invention includes: a cathode; an anode; and an organic thin-film layer including at least one layer and provided between the cathode and the anode. At least one layer of the organic thin-film layer includes: an organic-EL-device material represented by any one of the following formulae (1), (2) and (3); and at least one phosphorescent material, in which the organic-EL-device material may have a substituent.

[0016]

[Chemical Formula 1]



[0017] where: A represents a group selected from a 3-fluoranthenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-benzo[g]chrysenyl group;

Ar represents a fused aromatic ring having 10 to 30 carbon atoms and having triplet energy of 2.10 eV or more.)

[0018] In this respect, similarly to the invention, Patent Literature 13 and 14 disclose general formulae for representing aromatic hydrocarbon compounds structured so that four aromatic hydrocarbon rings are continuously coupled to one another. However, Patent Literature 13 and 14 are silent on specific compounds represented by any one of the above formulae (1), (2) and (3) according to the aspect of the invention. The examples in Patent Literature 13 and 14 show that the organic EL devices of Patent Literature 13 and 14 require driving voltage of 4.1 to 4.7 V, based on which it can be said that there is still a room for improvement.

Among the various linkage structures of four rings linked in series disclosed in Patent Literature 13 and 14, an organic-EL-device material according to another aspect of the invention has the specific linkage structure represented by any one of the general formulae (1) to (3). Specifically, the organic-EL-device material according to the aspect of the invention

is structured such that: the middle divalent aromatic rings have a 2,6 naphthalene skeleton; and the fused aromatic ring at the terminal end is the specific aromatic ring. Accordingly, in an organic EL device containing the organic-EL-device material according to the aspect of the invention, considerable reduction in driving voltage of the organic EL device takes place, which is not disclosed in Patent Literature 13 or 14.

Since the conjugation length is elongated suitably for the molecular structure and the fused aromatic hydrocarbon ring contributing to reduction in voltage via the divalent aromatic hydrocarbon ring positioned in meta position is at the terminal end in the organic-EL-device material according to the aspect of the invention, an organic EL device exhibiting high luminous efficiency and excellent lifetime and requiring less driving voltage can be realized.

[0019] Moreover, the organic-EL-device material according to the aspect of the invention, which is represented by any one of the above formulae (1), (2) and (3), may have a substituent.

[0020] The aspect of the invention can provide a phosphorescent organic EL device that requires less driving voltage and exhibits high efficiency and long lifetime because of its use of the organic-EL-device material represented by any one of the formulae (1), (2) and (3), and also can provide the organic-EL-device material capable of realizing such an organic EL device.

BRIEF DESCRIPTION OF DRAWINGS

[0021]

Fig. 1 schematically shows an exemplary arrangement of an organic electroluminescence device according to an exemplary embodiment of the invention.

DESCRIPTION OF EXEMPLARY EMBODIMENTS

[0022] Exemplary embodiment(s) of the invention will be described below.

Arrangement of Organic EL Device

[0023] Arrangement(s) of an organic EL device according to the aspect of the invention will be described below.

The followings are representative arrangement examples of an organic EL device:

- (1) anode / emitting layer / cathode;
- (2) anode / hole injecting layer / emitting layer / cathode;
- (3) anode / emitting layer / electron injecting-transporting layer / cathode;
- (4) anode / hole injecting layer / emitting layer / electron injecting-transporting layer / cathode;
- (5) anode / organic semiconductor layer / emitting layer / cathode;
- (6) anode / organic semiconductor layer / electron blocking layer / emitting layer / cathode;
- (7) anode / organic semiconductor layer / emitting layer / adhesion improving layer / cathode;
- (8) anode / hole injecting-transporting layer / emitting layer / electron injecting-transporting layer / cathode;
- (9) anode / insulating layer / emitting layer / insulating layer / cathode;
- (10) anode / inorganic semiconductor layer / insulating layer / emitting layer / insulating layer / cathode;
- (11) anode / organic semiconductor layer / insulating layer / emitting layer / insulating layer / cathode;
- (12) anode / insulating layer / hole injecting-transporting layer / emitting layer / insulating layer / cathode; and
- (13) anode / insulating layer / hole injecting-transporting layer / emitting layer / electron injecting-transporting layer / cathode.

While the arrangement (8) is preferably used among the above, the arrangement of the invention is not limited to the above arrangements.

[0024] Fig. 1 schematically shows an exemplary arrangement of an organic EL device according to an exemplary embodiment of the invention.

An organic EL device 1 includes a transparent substrate 2, an anode 3, a cathode 4 and an organic thin-film layer 10 disposed between the anode 3 and the cathode 4.

The organic thin-film layer 10 includes a phosphorescent-emitting layer 5 containing a phosphorescent host and a phosphorescent dopant. A layer such as a hole injecting/transporting layer 6 may be provided between the phosphorescent-emitting layer 5 and the anode 3 while a layer such as an electron injecting/transporting layer 7 may be provided between the phosphorescent-emitting layer 5 and the cathode 4.

In addition, an electron blocking layer may be provided to the phosphorescent-emitting layer 5 adjacently to the anode 3 while a hole blocking layer may be provided to the phosphorescent-emitting layer 5 adjacently to the cathode 4.

With this arrangement, electrons and holes can be trapped in the phosphorescent-emitting layer 5, thereby enhancing probability of exciton generation in the phosphorescent-emitting layer 5.

[0025] It should be noted that a "fluorescent host" and a "phosphorescent host" herein respectively mean a host combined with a fluorescent dopant and a host combined with a phosphorescent dopant, and that a distinction between the fluorescent host and phosphorescent host is not unambiguously derived only from a molecular structure of the host in a limited manner.

In other words, the fluorescent host herein means a material for forming a fluorescent-emitting layer containing a fluorescent dopant, and does not mean a host that is only usable as a host of a fluorescent material.

Likewise, the phosphorescent host herein means a material for forming a phosphorescent-emitting layer containing a phosphorescent dopant, and does not mean a host that is only usable as a host of a phosphorescent material.

[0026] It should also be noted that the "hole injecting/transporting layer (or hole injecting-transporting layer)" herein means "at least one of hole injecting layer and hole transporting layer" while "electron injecting/transporting layer (or electron injecting-transporting layer)" herein means "at least one of electron injecting layer and electron transporting layer."

Light-Transmissive Substrate

[0027] The organic EL device according to the aspect of the invention is formed on a light-transmissive substrate. The light-transmissive plate, which supports the organic EL device, is preferably a smoothly-shaped substrate that transmits 50% or more of light in a visible region of 400nm to 700nm.

The light-transmissive plate is exemplarily a glass plate, a polymer plate or the like.

For the glass plate, materials such as soda-lime glass, barium/strontium-containing glass, lead glass, aluminosilicate glass, borosilicate glass, barium borosilicate glass and quartz can be used.

For the polymer plate, materials such as polycarbonate resins, acryl resins, polyethylene terephthalate resins, polyether sulfide resins and polysulfone resins can be used.

Anode and Cathode

[0028] The anode of the organic EL device is used for injecting holes into the hole injecting layer, the hole transporting layer or the emitting layer. It is effective that the anode has a work function of 4.5 eV or more.

Exemplary materials for the anode are alloys of indium-tin oxide (ITO), tin oxide (NESA), indium zinc oxide, gold, silver, platinum and copper.

The anode may be made by forming a thin film from these electrode materials through a method such as vapor deposition or sputtering.

When light from the emitting layer is to be emitted through the anode as in this embodiment, the anode preferably transmits more than 10% of the light in the visible region. Sheet resistance of the anode is preferably several hundreds Ω /square or lower. Although depending on the material of the anode, thickness of the anode is typically in a range of 10 nm to 1 μ m, and preferably in a range of 10 to 200 nm.

[0029] The cathode is preferably formed of a material with smaller work function in order to inject electrons into the electron injecting layer, the electron transporting layer or the emitting layer.

Although a material for the cathode is subject to no specific limitation, examples of the material are indium, aluminum, magnesium, alloy of magnesium and indium, alloy of magnesium and aluminum, alloy of aluminum and lithium, alloy of aluminum, scandium and lithium, alloy of magnesium and silver and the like.

Like the anode, the cathode may be made by forming a thin film from the above materials through a method such as vapor deposition or sputtering. In addition, the light may be emitted through the cathode.

Emitting Layer

[0030] The emitting layer of the organic EL device has functions as follows, namely:

(1) injecting function: a function for accepting, when an electrical field is applied, the holes injected by the anode or the hole injecting layer, or the electrons injected by the cathode or the electron injecting layer;

(2) transporting function: a function for transporting injected electric charges (the electrons and the holes) by the force of the electrical field; and

(3) emitting function: a function for providing a condition for recombination of the electrons and the holes to emit light.

[0031] Injectability of the holes may differ from that of the electrons and transporting capabilities of the hole and the

electrons (represented by mobilities of the holes and the electrons) may differ from each other.

[0032] As a method of forming the emitting layer, known methods such as vapor deposition, spin coating and an LB method may be employed.

The emitting layer is preferably a molecular deposit film.

The molecular deposit film means a thin film formed by depositing a material compound in gas phase or a film formed by solidifying a material compound in a solution state or in liquid phase. The molecular deposit film is typically distinguished from a thin film formed by the LB method (molecular accumulation film) by differences in aggregation structures, higher order structures and functional differences arising therefrom.

[0033] As disclosed in JP-A-57-51781, the emitting layer can be formed from a thin film formed by spin coating or the like, the thin film being formed from a solution prepared by dissolving a binder (e.g. a resin) and a material compound in a solvent.


The thickness of the emitting layer is preferably in a range of 5 to 50 nm, more preferably in a range of 7 to 50 nm and most preferably in a range of 10 to 50 nm. The thickness below 5 nm may cause difficulty in forming the emitting layer and in controlling chromaticity, while the thickness above 50 nm may increase driving voltage.

Organic-EL-Device Material

[0034] At least one layer of the organic thin-film layer according to the aspect of the invention contains: an organic-EL-device material represented by any one of the following formulae (1), (2) and (3); and at least one phosphorescent material. Here, the organic-EL-device material may have a substituent.

[0035]

[Chemical Formula 2]



[0036] where: A represents a group selected from a 3-fluoranthenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-benzo[g]chrysenyl group;

Ar represents a fused aromatic ring having 10 to 30 carbon atoms and having triplet energy of 2.10 eV or more.

When the organic-EL-device material according to the aspect of the invention has a substituent, at least one of A, Ar, a phenylene ring and a naphthylene ring in the formulae (1), (2) and (3) has a substituent.

The substituent which the organic-EL-device material according to the aspect of the invention may have is subjected to no specific limitation as long as the substituent provides advantages of the invention. Preferable examples of the substituent are an alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a cycloalkyl group having 3 to 18 carbon atoms, a silyl group having 3 to 20 carbon atoms, a cyano group or a halogen atom.

Examples of the alkyl group are a methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, 1-methylpropyl group and 1-propylbutyl group.

An example of the haloalkyl group is a 2,2,2-trifluoroethyl group.

Examples of the cycloalkyl group are a cyclopropyl group, cyclobutyl group, cyclopentyl group, cyclohexyl group and

cyclooctyl group.

Examples of the silyl group are a trimethylsilyl and triethylsilyl group.

Examples of the halogen atom are fluorine, chlorine, bromine and iodine.

The substituents may be provided in a manner to connect two aromatic hydrocarbon rings in A, Ar, the phenylene ring and the naphthylene ring.

In the organic-EL-device material according to the aspect of the invention, the A or the Ar may have a substituent. Specifically, the A or the Ar may be substituted by a phenyl group or a naphthyl group.

[0037] The fused aromatic ring having 10 to 30 carbon atoms and having triplet energy of 2.10 eV or more means that the triplet energy of the fused aromatic ring having 10 to 30 carbon atoms is 2.10 eV or more when the fused aromatic ring is structured in Ar-H structure. The level of the triplet energy is measurable in accordance with the later-described measuring method of triplet energy. The upper limit to the triplet energy of Ar may be suitably set within a range where the advantages of the invention are obtained. The triplet energy of Ar is preferably 2.8 eV or less.

Examples of the fused aromatic ring having 10 to 30 carbon atoms and having triplet energy of 2.1 eV or more are naphthalene, phenanthrene, fluoranthene, triphenylene, chrysene, picene, benzo[c]phenanthrene, dibenzo[c,g]phenanthrene, benzo[g]chrysene, and benzo[b]fluoranthene.

The fused aromatic ring having 10 to 30 carbon atoms of Ar means that the number of the carbon atoms forming the fused aromatic ring is 10 to 30.

[0038] At least one layer of the organic thin-film layer of the organic EL device according to the aspect of the invention may be the emitting layer. The emitting layer may contain: the organic-EL-device material represented by any one of the above formulae (1), (2) and (3); and at least one phosphorescent material.

Since having great triplet energy, the organic-EL-device material represented by any one of the above formulae (1), (2) and (3) according to the aspect of the invention is usable as a host for transferring energy to the phosphorescent dopant so that the phosphorescent dopant can emit light.

While an anthracene derivative, which is well-known as a fluorescent host, is not suitably applied as a host for red-emitting phosphorescent dopant, the organic-EL-device material according to the aspect of the invention, which has great triplet energy, is effectively applicable for the red-emitting phosphorescent dopant to emit light.

However, while CBP, which is a conventionally-known phosphorescent host, can serve as the host even for a phosphorescent dopant for emitting light of a shorter wavelength than green, the organic-EL-device material according to the aspect of the invention can be used for a green-emitting phosphorescent dopant but cannot be used for a phosphorescent dopant for emitting light of a shorter wavelength than green.

According to the aspect of the invention, since the skeleton of the organic-EL-device material has a polycyclic fused ring containing no nitrogen atom, molecular stability thereof can be enhanced and the lifetime of the device can be prolonged.

When the number of ring atoms (i.e., atoms for forming the ring) contained in the skeleton is too small, the molecular stability thereof is not sufficiently high. On the other hand, when the number of rings fused in the polycyclic fused ring for structuring the compound according to the aspect of the invention is too large, the conjugate is excessively lengthened and a HOMO-LUMO gap is so much narrowed that the triplet energy becomes insufficient for a useful emission wavelength. In this respect, since containing the suitable number of the ring atoms, the organic-EL-device material according to the aspect of the invention can be favorably applied as the phosphorescent host for a highly-stable phosphorescent-emitting layer that emits light of a useful wavelength.

Further, since the organic-EL-device material according to the aspect of the invention has the fused aromatic hydrocarbon having the specific structure for contributing to voltage reduction at its terminal end, the driving voltage of the organic EL device can be reduced.

[0039] Conventionally, a host material widely usable for phosphorescent dopants that emit light of wide wavelengths ranging from green to red has been selected for each phosphorescent dopant. Thus, a material having great triplet energy $E_g(T)$ such as CBP has been used as the host material.

However, it is true that CBP has great triplet energy $E_g(T)$, but lifetime is short.

In this respect, the organic-EL-device material according to the aspect of the invention is not applicable as a host for such a wide-gap phosphorescent dopant as to be comparable to a blue-emitting phosphorescent dopant, but is applicable as a host for a red-emitting or green-emitting phosphorescent dopant. Moreover, when the triplet energy $E_g(T)$ is great as in CBP, a difference in energy gap between the material and the red-emitting phosphorescent dopant is so large that the energy is not efficiently transferred intermolecularly. However, since the host according to the aspect of the invention has an excited energy value suitable for a red-emitting or green-emitting phosphorescent dopant, energy can be efficiently transferred from the excitons of the host to the phosphorescent dopant, thereby providing a phosphorescent emitting layer of considerably high efficiency. Even when the phosphorescent dopant is directly excited, the organic-EL-device material according to the aspect of the invention, which has sufficiently greater triplet energy than the phosphorescent dopant, can efficiently trap the energy within the emitting layer.

As described above, according to the aspect of the invention, a phosphorescent emitting layer having high efficiency

and long lifetime can be provided.

[0040] Triplet energy $E_g(T)$ of a material for forming an organic EL device may be exemplarily defined based on the phosphorescence spectrum. For instance, in the invention, the triplet energy $E_g(T)$ may be defined as follows.

Specifically, each material is dissolved in an EPA solvent (diethylether: isopentane: ethanol = 5: 5: 2 in volume ratio) with a concentration of 10 $\mu\text{mol/L}$, thereby forming a sample for phosphorescence measurement.

Then, the sample for phosphorescence measurement is put into a quartz cell, cooled to 77K and irradiated with exciting light, so that a wavelength of phosphorescence radiated therefrom is measured.

A tangent line is drawn to be tangent to a rising section adjacent to the short-wavelength side of the obtained phosphorescence spectrum, and a wavelength value at an intersection of the tangent line and a base line is converted into energy value. Then, the converted energy value is defined as the triplet energy gap $E_g(T)$.

For the measurement, for instance, a commercially-available FLUOROLOG II (manufactured by SPEX Corporation) may be used.

However, the triplet energy gap does not need to be defined by the above method, but may be defined by any other suitable method as long as compatible with the invention.

[0041] The organic-EL-device material represented by any one of the formulae (1), (2) and (3) according to the aspect of the invention preferably has triplet energy of 2.0 eV to 2.5 eV

When the triplet energy is 2.0 eV or more, energy can be transferred to a phosphorescent material that emits light in a range of 520 to 720nm. When the triplet energy exceeds 2.5eV, a difference in the triplet energy between the red dopant and the host material within the emitting layer may become so large that the driving voltage is increased.

The triplet energy of the organic-EL-device material according to the aspect of the invention is preferably in a range of 2.1 eV to 2.5 eV, more preferably in a range of 2.2 eV to 2.5 eV

[0042] In the organic-EL-device material represented by any one of the formulae (1), (2) and (3) according to the aspect of the invention, A preferably represents a group selected from unsubstituted 3-fluoranthenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl and 10-benzo[g]chrysenyl group.

Herein, "unsubstituted" means substitution by a hydrogen atom. The hydrogen atom of the compounds in the present specification includes light hydrogen and deuterium.

In addition, in the organic-EL-device material according to the aspect of the invention, Ar each preferably independently represents a group selected from a naphthyl group, fluoranthenyl group, phenanthrenyl group, benzophenanthrenyl group and benzo[g]chrysenyl group.


Further, in the organic-EL-device material according to the aspect of the invention, Ar preferably represents a group selected from a 2-naphthyl group, 3-fluoranthenyl group, 8-fluoranthenyl group, 9-phenanthrenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-benzo[g]chrysenyl group.

[0043] By adopting the groups having the specific structures as the groups represented by A and Ar of the organic-EL-device material according to the aspect of the invention in the above-described manner, the level of the triplet energy can be made suitable and the driving voltage can be reduced.

Examples of the organic-EL-device material represented by any one of the formulae (1), (2) and (3) are compounds shown below.

[0044]

[Chemical Formula 3]



[0045]

[Chemical Formula 4]

5

10

15

20

25

30


35

40

45

50

55



[0046]

5

10

15

20

25

30

35


40

45

50

55

[Chemical Formula 5]



[0047]

[Chemical Formula 6]


5

10

15

20

25



[0048]

30

[Chemical Formula 7]


35

40

45

50

55



Phosphorescent Material

50

[0049] The phosphorescent material used in the invention, which generates phosphorescent emission, preferably contains a metal complex. The metal complex is preferably a metal complex having: a metal atom selected from Ir, Pt, Os, Au, Re and Ru; and a ligand. Particularly, the ligand preferably has an ortho-metal bond.

55 The phosphorescent material is preferably a compound containing a metal selected from iridium (Ir), osmium (Os) and platinum (Pt) because such a compound, which exhibits high phosphorescence quantum yield, can further enhance external quantum efficiency of the emitting device. The phosphorescent material is more preferably a metal complex such as an iridium complex, an osmium complex or a platinum complex, among which an iridium complex and a platinum complex are more preferable and ortho metalation of an iridium complex is the most preferable.

Examples of the metal complex are shown below, among which metal complexes that emit green to red light are particularly preferable.


[0050]

5

[Chemical Formula 8]


10

15




20

25




30




35

40



45




50

[0051]


55

[Chemical Formula 9]



[0052]

[Chemical Formula 10]



[0053]


[Chemical Formula 11]

45


50

55

5




10




15

20




25

30




35

40



45

50



55

[0054] In the invention, at least one phosphorescent material contained in the emitting layer preferably emits light having the maximum wavelength of 520 to 720 nm, more preferably light having the maximum wavelength of 570 nm to 720 nm.

By doping the phosphorescent material (phosphorescent dopant) having such an emission wavelength to the specific host material usable for the invention so as to form the emitting layer, the organic EL device can exhibit high efficiency.

[0055] The organic EL device according to the aspect of the invention may include a hole transporting layer (hole injecting layer), and the hole transporting layer (hole injecting layer) may preferably contain the organic-EL-device material represented by any one of the formulae (1), (2) and (3).

The organic EL device according to the aspect of the invention may include an electron transporting layer (electron injecting layer), and the electron transporting layer (electron injecting layer) may preferably contain the organic-EL-device material represented by any one of the formulae (1), (2) and (3).

The organic EL device according to the aspect of the invention may include an electron blocking layer and a hole blocking layer, and the electron blocking layer and the hole blocking layer may preferably contain the organic-EL-device material represented by any one of the formulae (1), (2) and (3).

[0056] In the organic EL device according to the aspect of the invention, a reductive dopant may be preferably contained in an interfacial region between the cathode and the organic thin-film layer.

With this arrangement, the organic EL device can emit light with enhanced luminance intensity and have a longer lifetime. The reductive dopant may be at least one compound selected from an alkali metal, an alkali metal complex, an alkali metal compound, an alkali earth metal, an alkali earth metal complex, an alkali earth metal compound, a rare-earth metal, a rare-earth metal complex, a rare-earth metal compound and the like.

[0057] Examples of the alkali metal are Na (work function: 2.36 eV), K (work function: 2.28 eV), Rb (work function: 2.16 eV), Cs (work function: 1.95 eV) and the like, among which a substance having a work function of 2.9 eV or less is particularly preferable. Among the above, the reductive dopant is preferably K, Rb or Cs, more preferably Rb or Cs, the most preferably Cs.

Examples of the alkali earth metal are Ca (work function: 2.9 eV), Sr (work function: 2.0 to 2.5 eV), Ba (work function: 2.52 eV), and the like, among which a substance having a work function of 2.9 eV or less is particularly preferable.

Examples of the rare-earth metal are Sc, Y, Ce, Tb, Yb and the like, among which a substance having a work function of 2.9 eV or less is particularly preferable.

Since the above preferable metals have particularly high reducibility, addition of a relatively small amount of the metals to an electron injecting zone can enhance luminance intensity and lifetime of the organic EL device.

[0058] Examples of the alkali metal compound are an alkali oxide such as Li_2O , Cs_2O or K_2O , an alkali halogen compound such as LiF, NaF, CsF or KF and the like, among which LiF, Li_2O and NaF are preferable.

Examples of the alkali earth metal compound are BaO, SrO, CaO, a mixture thereof such as $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$) or $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$) and the like, among which BaO, SrO and CaO are preferable.

Examples of the rare-earth metal compound are YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , TbF_3 and the like, among which YbF_3 , ScF_3 and TbF_3 are preferable.

[0059] The alkali metal complex, the alkali earth metal complex and the rare-earth metal complex are not specifically limited, as long as at least one of alkali metal ion, alkali earth metal ion and rare-earth metal ion is contained therein as metal ion. The ligand for each of the complexes is preferably quinolinol, benzoquinolinol, acridinol, phenanthridinol, hydroxyphenyl oxazole, hydroxyphenyl thiazole, hydroxydiaryl oxadiazole, hydroxydiaryl thiadiazole, hydroxyphenyl pyridine, hydroxyphenyl benzoimidazole, hydroxybenzo triazole, hydroxy fluborane, bipyridyl, phenanthroline, phthalocyanine, porphyrin, cyclopentadiene, α -diketones, azomethines, or a derivative thereof, but the ligand is not limited thereto.

[0060] The reductive dopant is added to preferably form a layer or an island pattern in the interfacial region. The layer of the reductive dopant or the island pattern of the reductive dopant is preferably formed by depositing the reductive dopant by resistance heating deposition while an emitting material for forming the interfacial region or an organic substance as an electron-injecting material are simultaneously deposited, so that the reductive dopant is dispersed in the organic substance. Dispersion concentration at which the reductive dopant is dispersed in the organic substance is a mole ratio (organic substance to reductive dopant) of 100 : 1 to 1 : 100, preferably 5 : 1 to 1 : 5.

When the reductive dopant forms the layer, the emitting material or the electron injecting material for forming the organic layer of the interfacial region is initially layered, and the reductive dopant is subsequently deposited singularly thereon by resistance heating deposition to form a preferably 0.1 to 15 nm-thick layer.

When the reductive dopant forms the island pattern, the emitting material or the electron injecting material for forming the organic layer of the interfacial region is initially formed in an island shape, and the reductive dopant is subsequently deposited singularly thereon by resistance heating deposition to form a preferably 0.05 to 1 nm-thick island shape.

A ratio of the main component to the reductive dopant in the organic EL device according to the aspect of the invention is preferably a mole ratio (main component to reductive dopant) of 5:1 to 1:5, more preferably 2:1 to 1:2.

[0061] The organic EL device according to the aspect of the invention preferably includes the electron transporting

layer or the electron injecting layer between the emitting layer and the cathode, and the electron transporting layer or the electron injecting layer preferably contains the above organic-EL-device material. The electron transporting layer or the electron injecting layer more preferably contains the above organic-EL-device material as the main component. The electron injecting layer may serve also as the electron transporting layer.

It should be noted that "as the main component" means that the organic-EL-device material is contained in the electron injecting layer with a content of 50 mass% or more.


The electron injecting layer or the electron transporting layer, which aids injection of the electrons into the emitting layer, has a high electron mobility. The electron injecting layer is provided for adjusting energy level, by which, for instance, sudden changes of the energy level can be reduced.

A preferable example of an electron transporting material for forming the electron transporting layer or the electron injecting layer is an aromatic heterocyclic compound having in the molecule at least one heteroatom. Particularly, a nitrogen-containing cyclic derivative is preferable. The nitrogen-containing cyclic derivative is preferably an aromatic ring having a nitrogen-containing six-membered or five-membered ring skeleton, or a fused aromatic cyclic compound having a nitrogen-containing six-membered or five-membered ring skeleton.

[0062] A preferable example of the nitrogen-containing cyclic derivative is a nitrogen-containing cyclic metal chelate complex represented by the following formula (A).

[0063]

[Chemical Formula 12]



[0064] In the formula, R^2 to R^7 each independently represent a hydrogen atom, a halogen atom, an oxy group, an amino group, a hydrocarbon group having 1 to 40 carbon atoms, an alkoxy group, an aryloxy group, an alkoxy carbonyl group or a heterocyclic group. R^2 to R^7 may be substituted or unsubstituted.

Examples of the halogen atom are fluorine, chlorine, bromine and iodine. Examples of a substituted or unsubstituted amino group are an alkylamino group, an arylamino group and an aralkylamino group.

Examples of the hydrocarbon group having 1 to 40 carbon atoms are a substituted or unsubstituted alkyl group, an alkenyl group, a cycloalkyl group, an aryl group, an aralkyl group and the like.

[0065] Examples of the alkyl group are a methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, neo-pentyl group, 1-methylpentyl group, 2-methylpentyl group, 1-pentylhexyl group, 1-butylpentyl group, 1-heptyloctyl group, 3-methylpentyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-

triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 1,2-dinitroethyl group, 2,3-dinitro-t-butyl group and 1,2,3-trinitropropyl group.

[0066] Among the above, the alkyl group is preferably a methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, neo-pentyl group, 1-methylpentyl group, 1-pentylhexyl group, 1-butylpentyl group or 1-heptyloctyl group.

[0067] Examples of the alkenyl group are a vinyl group, allyl group, 1-butenyl group, 2-butenyl group, 3-butenyl group, 1,3-butanediethyl group, 1-methylvinyl group, styryl group, 2,2-diphenylvinyl group, 1,2-diphenylvinyl group, 1-methylallyl group, 1,1-dimethylallyl group, 2-methylallyl group, 1-phenylallyl group, 2-phenylallyl group, 3-phenylallyl group, 3,3-diphenylallyl group, 1,2-dimethylallyl group, 1-phenyl-1-butenyl group and 3-phenyl-1-butenyl group, among which a styryl group, 2,2-phenylvinyl group and 1,2-diphenylvinyl group are preferable.

[0068] Examples of the cycloalkyl group are a cyclopentyl group, cyclohexyl group, cyclooctyl group, and 3,5-tetramethylcyclohexyl group, among which cyclohexyl group, cyclooctyl group and 3,5-tetramethylcyclohexyl group are preferable.

The alkoxy group is a group represented by -OY. Examples of Y are the same as the examples described in relation to the alkyl group, and preferable examples of Y are also the same as those described in relation to the alkyl group.

[0069] Examples of non-fused aryl group are a phenyl group, biphenyl-2-yl group, biphenyl-3-yl group, biphenyl-4-yl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, o-cumenyl group, m-cumenyl group, p-cumenyl group, 2,3-xylyl group, 3,4-xylyl group, 2,5-xylyl group, mesityl group, m-quarter-phenyl group and the like.

[0070] Among the above, a phenyl group, biphenyl-2-yl group, biphenyl-3-yl group, biphenyl-4-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, p-tolyl group, 3,4-xylyl group, m-quarter-phenyl-2-yl group are preferable.

Examples of a fused aryl group are a 1-naphthyl group and 2-naphthyl group.

[0071] The heterocyclic group, which may be monocyclic or fused, preferably has 1 to 20 carbon atoms for forming the ring, more preferably 1 to 12 carbon atoms for forming the ring, further preferably 2 to 10 carbon atoms for forming the ring. The heterocyclic group is an aromatic heterocyclic group having at least one heteroatom selected from a nitrogen atom, oxygen atom, sulfur atom and selenium atom. Examples of the heterocyclic group are groups induced by pirrolidine, piperidine, piperazine, morpholine, thiophene, selenophene, furane, pyrrole, imidazole, pyrazole, pyridine, pyrazine, pyridazine, pyrimidine, triazole, triazine, indole, indazole, purine, thiazoline, thiazole, thiadiazole, oxazoline, oxazole, oxadiazole, quinoline, isoquinoline, phthalazine, naphthyridine, quinoxaline, quinazoline, cinnoline, pteridine, acridine, phenanthroline, phenazine, tetrazole, benzoimidazole, benzoxazole, benzothiazole, benzotriazole, tetra-aza indene, carbazole, azepine and the like, preferably groups induced by furane, thiophene, pyridine, pyrazine, pyrimidine, pyridazine, triazine, quinoline, phthalazine, naphthyridine, quinoxaline and quinazoline, further preferably groups induced by furane, thiophene, pyridine and quinoline, further more preferably a quinolinyl group.

[0072] Examples of the aralkyl group are a benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, 2-phenylisopropyl group, phenyl-t-butyl group, α -naphthylmethyl group, 1- α -naphthylethyl group, 2- α -naphthylethyl group, 1- α -naphthylisopropyl group, 2- α -naphthylisopropyl group, β -naphthylmethyl group, 1- β -naphthylethyl group, 2- β -naphthylethyl group, 1- β -naphthylisopropyl group, 2- β -naphthylisopropyl group, p-methylbenzyl group, m-methylbenzyl group, o-methylbenzyl group, p-chlorobenzyl group, m-chlorobenzyl group, o-chlorobenzyl group, p-bromobenzyl group, m-bromobenzyl group, o-bromobenzyl group, p-iodobenzyl group, m-iodobenzyl group, o-iodobenzyl group, p-hydroxybenzyl group, m-hydroxybenzyl group, o-hydroxybenzyl group, p-aminobenzyl group, m-aminobenzyl group, o-aminobenzyl group, p-nitrobenzyl group, m-nitrobenzyl group, o-nitrobenzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-hydroxy-2-phenylisopropyl group, 1-chloro-2-phenylisopropyl group and the like.

[0073] Among the above, a benzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group and 2-phenylisopropyl group are preferable.

[0074] The aryloxy group is represented by -OY'. Preferable examples of Y' are a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group,

3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group and the like.

[0075] Among the aryloxy group, the heteroaryloxy group is represented by -OZ'. Examples of Z' are a 2-pyroryl group, 3-pyroryl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalanyl group, 5-quinoxalanyl group, 6-quinoxalanyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthrydinyl group, 2-phenanthrydinyl group, 3-phenanthrydinyl group, 4-phenanthrydinyl group, 6-phenanthrydinyl group, 7-phenanthrydinyl group, 8-phenanthrydinyl group, 9-phenanthrydinyl group, 10-phenanthrydinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group and the like.

[0076] The alkoxycarbonyl group is represented by -COOY'. Examples of Y' are the same as the examples of the alkyl group.

[0077] The alkylamino group and the aralkylamino group are represented by -NQ¹Q². Examples for each of Q¹ and Q² are the same as the examples described in relation to the alkyl group and the aralkyl group, and preferable examples for each of Q¹ and Q² are also the same as those described in relation to the alkyl group and the aralkyl group. Either one of Q¹ and Q² may be a hydrogen atom.

The arylamino group is represented by -NAr¹Ar². Examples for each of Ar¹ and Ar² are the same as the examples described in relation to the non-fused aryl group and the fused aryl group. Either one of Ar¹ and Ar² may be a hydrogen atom.


[0078] M represents aluminum (Al), gallium (Ga) or indium (In), among which In is preferable.

L in the formula (A) represents a group represented by the following formula (A') or the following formula (A'').

[0079]


[Chemical Formula 13]

5



10

15



20

25

30

35 **[0080]** In the formula, R⁸ to R¹² each independently represent a hydrogen atom or a substituted or unsubstituted hydrocarbon group having 1 to 40 carbon atoms. Adjacent groups may form a cyclic structure. In the formula, R¹³ to R²⁷ each independently represent a hydrogen atom or a substituted or unsubstituted hydrocarbon group having 1 to 40 carbon atoms. Adjacent groups may form a cyclic structure.

40 **[0081]** Examples of the hydrocarbon group having 1 to 40 carbon atoms represented by each of R⁸ to R¹² and R¹³ to R²⁷ in the formulae (A') and (A'') are the same as those of R² to R⁷.

Examples of a divalent group formed when an adjacent set of R⁸ to R¹² and R¹³ to R²⁷ forms a cyclic structure are a tetramethylene group, a pentamethylene group, a hexamethylene group, a diphenylmethane-2,2'-diyl group, a diphenylethane-3,3'-diyl group, a diphenylpropane-4,4'-diyl group and the like.


45 **[0082]** Examples of the nitrogen-containing cyclic metal chelate complex represented by the formula (A) will be shown below. However, the nitrogen-containing cyclic metal chelate complex is not limited to the exemplary compounds shown below.

[0083]

50

[Chemical Formula 14]

55



[0084]

[Chemical Formula 15]

5

10

15

20

25

30

35



40

45



50

55

5





10





15

20





25





30

35





40



45

50



55

[0085]

[Chemical Formula 16]

5

10

15

20

25

30

35


40

45

50


55

5




10

15




20

25




30

35




40

45



50

55




[0086] According to the aspect of the invention, the electron injecting layer or the electron transporting layer preferably contains a nitrogen-containing heterocyclic derivative.

[0087] The electron injecting layer or the electron transporting layer, which aids injection of the electrons into the emitting layer, has a high electron mobility. The electron injecting layer is provided for adjusting energy level, by which, for instance, sudden changes of the energy level can be reduced. As a material for the electron injecting layer or the electron transporting layer, 8-hydroxyquinoline or a metal complex of its derivative, an oxadiazole derivative and a nitrogen-containing heterocyclic derivative are preferable. An example of the 8-hydroxyquinoline or the metal complex of its derivative is a metal chelate oxinoid compound containing a chelate of oxine (typically 8-quinolinol or 8-hydroxyquinoline). For instance, tris(8-quinolinol) aluminum can be used. Examples of the oxadiazole derivative are as follows.

[0088]

[Chemical Formula 17]




[0089] In the formula, Ar¹⁷, Ar¹⁸, Ar¹⁹, Ar²¹, Ar²² and Ar²⁵ each represent a substituted or unsubstituted arylene group. Ar¹⁷, Ar¹⁹ and Ar²² may be the same as or different from Ar¹⁸, Ar²¹ and Ar²⁵ respectively. Ar²⁰, Ar²³ and Ar²⁴ each represent a substituted or unsubstituted arylene group. Ar²³ and Ar²⁴ may be mutually the same or different.

Examples of the arylene group are a phenylene group, naphthylene group, biphenylene group, anthranylene group, perylenylene group and pyrenylene group. Examples of the substituent therefor are an alkyl group having 1 to 10 carbon atoms, alkoxy group having 1 to 10 carbon atoms and cyano group. Such an electron transport compound is preferably an electron transport compound that can be favorably formed into a thin film(s). Examples of the electron transport compounds are as follows.


[0090]

[Chemical Formula 18]

5




10




15

20




25



30



35



40

[0091] An example of the nitrogen-containing heterocyclic derivative is a nitrogen-containing heterocyclic derivative that is not a metal complex, the derivative being formed of an organic compound having the following structure. Examples of the nitrogen-containing heterocyclic derivative are five-membered ring or six-membered ring derivative having a skeleton represented by the formula (A) and a derivative having a structure represented by the formula (B).

45

[0092]

[Chemical Formula 19]

50


55

5



10

15



20

[0093] In the formula (B), X represents a carbon atom or a nitrogen atom. Z₁ and Z₂ each independently represent an atom group capable of forming a nitrogen-containing heterocycle.

[0094]

25

[Chemical Formula 20]

30

35



40

[0095] Preferably, the nitrogen-containing heterocyclic derivative is an organic compound having a nitrogen-containing aromatic polycyclic group having a five-membered ring or six-membered ring. When the nitrogen-containing heterocyclic derivative is such a nitrogen-containing aromatic polycyclic group that contains plural nitrogen atoms, the nitrogen-containing heterocyclic derivative may be a nitrogen-containing aromatic polycyclic organic compound having a skeleton formed by a combination of the skeletons respectively represented by the formulae (A) and (B), or by a combination of the skeletons respectively represented by the formulae (A) and (C).

45


[0096] A nitrogen-containing group of the nitrogen-containing organic compound is selected from nitrogen-containing heterocyclic groups respectively represented by the following.

[0097]

50

[Chemical Formula 21]

55



[0098] In the formulae: R represents an aryl group having 6 to 40 carbon atoms, heteroaryl group having 3 to 40 carbon atoms, alkyl group having 1 to 20 carbon atoms or alkoxy group having 1 to 20 carbon atoms; and n represents an integer in a range of 0 to 5. When n is an integer of 2 or more, plural R may be mutually the same or different.

[0099] A preferable specific compound is a nitrogen-containing heterocyclic derivative represented by the following formula.

[0100]

[Chemical Formula 22]


HAr-L¹-Ar¹-Ar²

[0101] In the formula, HAr represents a substituted or unsubstituted nitrogen-containing heterocycle having 3 to 40 carbon atoms; L¹ represents a single bond, substituted or unsubstituted arylene group having 6 to 40 carbon atoms or substituted or unsubstituted heteroarylene group having 3 to 40 carbon atoms; Ar¹ represents a substituted or unsubstituted divalent aromatic hydrocarbon group having 6 to 40 carbon atoms; and Ar² represents a substituted or unsubstituted aryl group having 6 to 40 carbon atoms or substituted or unsubstituted heteroaryl group having 3 to 40 carbon atoms.

[0102] HAr is exemplarily selected from the following group.

[0103]

[Chemical Formula 23]



[0104] L¹ is exemplarily selected from the following group.

[0105]

[Chemical Formula 24]

55

5


10 [0106] Ar² is exemplarily selected from the following group.

[0107]

15

[Chemical Formula 25]

20



25

30


35 [0108] Ar¹ is exemplarily selected from the following arylanthranil groups.

[0109]

40

[Chemical Formula 26]

45



50

[0110] In the formula, R¹ to R¹⁴ each independently represent a hydrogen atom, halogen atom, alkyl group having 1 to 20 carbon atoms, alkoxy group having 1 to 20 carbon atoms, aryloxy group having 6 to 40 carbon atoms, substituted or unsubstituted aryl group having 6 to 40 carbon atoms or heteroaryl group having 3 to 40 carbon atoms. Ar³ represents a substituted or unsubstituted aryl group having 6 to 40 carbon atoms or heteroaryl group having 3 to 40 carbon atoms. The nitrogen-containing heterocyclic derivative may be a nitrogen-containing heterocyclic derivative in which R¹ to R⁸ in the structure of Ar¹ represented by the above formula each represent a hydrogen atom.

55

[0111] Other than the above, the following compound (see JP-A-9-3448) can be favorably used.

[0112]


5

[Chemical Formula 27]

10

15

20



[0113] In the formula, R₁ to R₄ each independently represent a hydrogen atom, substituted or unsubstituted aliphatic group, substituted or unsubstituted alicyclic group, substituted or unsubstituted carbocyclic aromatic cyclic group or substituted or unsubstituted heterocyclic group. X₁ and X₂ each independently represent an oxygen atom, sulfur atom or dicyanomethylene group.

25

[0114] Alternatively, the following compound (see JP-A-2000-173774) can also be favorably used.


[0115]

30

[Chemical Formula 28]

35

40



[0116] In the formula, R¹, R², R³ and R⁴, which may be mutually the same or different, each represent an aryl group represented by the following formula.


45

[0117]

50

55

[Chemical Formula 29]



5

10

15

20

25

30

35

40

45

50

55




[0118] In the formula, R⁵, R⁶, R⁷, R⁸ and R⁹, which may be mutually the same or different, each represent a hydrogen atom, saturated or unsaturated alkoxy group, alkyl group, amino group or alkylamino group. At least one of R⁵, R⁶, R⁷, R⁸ and R⁹ represents a saturated or unsaturated alkoxy group, alkyl group, amino group or alkylamino group.

[0119] A polymer compound containing the nitrogen-containing heterocyclic group or a nitrogen-containing heterocyclic derivative may be used.

[0120] The electron transporting layer preferably contains at least one of nitrogen-containing heterocycle derivatives respectively represented by the following formulae (201) to (203).

[0121]

[Chemical Formula 30]



[0122] In the formulae (201) to (203): R represents a hydrogen atom, substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms; n represents an integer of 0 to 4; R¹ represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms or alkoxy group having 1 to 20 carbon atoms; R² and R³ each independently represent a hydrogen atom, substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms; L represents a substituted or unsubstituted arylene group having 6 to 60 carbon atoms, substituted or unsubstituted pyridinylene group, substituted or unsubstituted quinolinylene group or substituted or unsubstituted fluorenylene group; Ar¹ represents a substituted or unsubstituted arylene group having 6 to 60 carbon atoms, substituted or unsubstituted pyridinylene group or substituted or unsubstituted quinolinylene group; Ar² represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms.

Ar³ represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms,

substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms or a group represented by $-Ar^1-Ar^2$ (Ar^1 and Ar^2 may be the same as the above).

[0123] In the formulae (201) to (203), R represents a hydrogen atom, substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms.

[0124] The aryl group having 6 to 60 carbon atom is preferably an aryl group having 6 to 40 carbon atoms, more preferably an aryl group having 6 to 20 carbon atoms. Examples of such an aryl group are a phenyl group, naphthyl group, anthryl group, phenanthryl group, naphthacenyl group, chrysenyl group, pyrenyl group, biphenyl group, terphenyl group, tolyl group, t-butylphenyl group, (2-phenylpropyl) phenyl group, fluoranthenyl group, fluorenyl group, a monovalent group formed of spirobifluorene, perfluorophenyl group, perfluoronaphthyl group, perfluoroanthryl group, perfluorobiphenyl group, a monovalent group formed of 9-phenylanthracene, a monovalent group formed of 9-(1'-naphthyl) anthracene, a monovalent group formed of 9-(2'-naphthyl) anthracene, a monovalent group formed of 6-phenylchrysene, and a monovalent group formed of 9-[4-(diphenylamine) phenyl] anthracene, among which a phenyl group, naphthyl group, biphenyl group, terphenyl group, 9-(10-phenyl) anthryl group, 9-[10-(1'-naphthyl)] anthryl group and 9-[10-(2'-naphthyl)] anthryl group are preferable.

[0125] The alkyl group having 1 to 20 carbon atoms is preferably an alkyl group having 1 to 6 carbon atoms. Examples of such an alkyl group are a methyl group, ethyl group, propyl group, butyl group, pentyl group, hexyl group, and a haloalkyl group such as trifluoromethyl group. When such an alkyl group has 3 or more carbon atoms, the alkyl group may be linear, cyclic or branched.

The alkoxy group having 1 to 20 carbon atoms is preferably an alkoxy group having 1 to 6 carbon atoms. Examples of such an alkoxy group are a methoxy group, ethoxy group, propoxy group, butoxy group, pentyloxy group, and hexyloxy group. When such an alkoxy group has 3 or more carbon atoms, the alkoxy group may be linear, cyclic or branched.

[0126] Examples of a substituent for the group represented by R are a halogen atom, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 40 carbon atoms, a substituted or unsubstituted aryl group having 6 to 40 carbon atoms, or a substituted or unsubstituted heteroaryl group having 3 to 40 carbon atoms.

Examples of the halogen atom are fluorine, chlorine, bromine and iodine.

Examples for each of the alkyl group having 1 to 20 carbon atoms, the alkoxy group having 1 to 20 carbon atoms, and an aryl group having 6 to 40 carbon atoms may be the same as the above examples.

[0127] Examples of the aryloxy group having 6 to 40 carbon atoms are a phenoxy group and a biphenyloxy group.

Examples of the heteroaryl group having 3 to 40 carbon atoms are a pyroryl group, furyl group, thienyl group, silolyl group, pyridyl group, quinolyl group, isoquinolyl group, benzofuryl group, imidazolyl group, pyrimidyl group, carbazolyl group, selenophenyl group, oxadiazolyl group and triazolyl group.

n is an integer of 0 to 4, preferably 0 to 2.

[0128] In the formulae (201), R^1 represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, a substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, or an alkoxy group having 1 to 20 carbon atoms.

Examples for each of the groups, the preferable number of carbon atoms contained in each of the groups, and preferable examples of the substituent for each of the groups are the same as those described in relation to R.

[0129] In the formulae (202) and (203), R^2 and R^3 each independently represent a hydrogen atom, a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, a substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, or a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms.

Examples for each of the groups, the preferable number of carbon atoms contained in each of the groups, and preferable examples of the substituent for each of the groups are the same as those described in relation to R.


[0130] In the formulae (201) to (203), L represents a substituted or unsubstituted arylene group having 6 to 60 carbon atoms, a substituted or unsubstituted pyridinylene group, a substituted or unsubstituted quinolinylene group, or a substituted or unsubstituted fluorenylene group.

The arylene group having 6 to 60 carbon atoms is preferably an arylene group having 6 to 40 carbon atoms, more preferably an arylene group having 6 to 20 carbon atoms. An example of such an arylene group is a divalent group formed by removing one hydrogen atom from the aryl group having been described in relation to R. Examples of a substituent for the group represented by L are the same as those described in relation to R.

[0131] Alternatively, L is preferably a group selected from a group consisting of the following.

[0132]

[Chemical Formula 31]



[0133] In the formulae (201), Ar¹ represents a substituted or unsubstituted arylene group having 6 to 60 carbon atoms, a substituted or unsubstituted pyridinylene group, or a substituted or unsubstituted quinolinylene group. Examples of a substituent for the group represented by L are the same as those described in relation to R. Alternatively, Ar¹ is preferably selected from a group consisting of fused cyclic groups respectively represented by the following formulae (101) to (110).

[0134]

25

30

35


40

45

50

55

[Chemical Formula 32]




[0135] In the formulae (101) to (110), the fused rings each may be linked with a link group formed of a halogen atom, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 40 carbon atoms, a substituted or unsubstituted aryl group having 6 to 40 carbon atoms or a substituted or unsubstituted heteroaryl group having 3 to 40 carbon atoms. When the rings each are linked with plural link groups, the plural link groups may be mutually the same or different. Examples for each of the groups are the same as those described above.

In the formula (110), L' represents a single bond or a group selected from a group consisting of the following.


[0136]

[Chemical Formula 33]

5



10



15

20 **[0137]** The structure of Ar¹ represented by the formula (103) is preferably a fused cyclic group represented by any one of the following formulae (111) to (125).

[0138]

25

[Chemical Formula 34]

30

35


40

45


50

55

5




(111)



(112)




(113)




(114)

10


15



(115)



(116)




(117)




(118)

20


25



(119)



(120)



(121)




(122)


30

35


40



(123)



(124)



(125)

45

50

55

[0139] In the formulae (111) to (125), the fused rings each may be linked with a link group formed of a halogen atom, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 40 carbon atoms, a substituted or unsubstituted aryl group having 6 to 40 carbon atoms or a substituted or unsubstituted heteroaryl group having 3 to 40 carbon atoms. When the rings each are linked with plural link groups, the plural link groups may be mutually the same or different. Examples for each of the groups are the same as those described above.

[0140] In the formula (201), Ar² represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, a substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, or a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms. Examples for each of the groups, the preferable number of carbon atoms contained in each of the groups, and preferable

examples of the substituent for each of the groups are the same as those described in relation to R.


[0141] In the formulae (202) and (203), Ar³ represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, a substituted or unsubstituted pyridyl group, a substituted or unsubstituted quinolyl group, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, or a group represented by -Ar¹-Ar² (Ar¹ and Ar² may be the same as the above).

Examples for each of the groups, the preferable number of carbon atoms contained in each of the groups, and preferable examples of the substituent for each of the groups are the same as those described in relation to R.

Alternatively, Ar³ is preferably selected from fused cyclic groups respectively represented by the following formulae (126) to (135).

[0142]


[Chemical Formula 35]




(126)




(127)




(128)




(129)



(130)




(131)




(132)



(133)



(134)



(135)

[0143] In the formulae (126) to (135), the fused rings each may be linked with a link group formed of a halogen atom, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 40 carbon atoms, a substituted or unsubstituted aryl group having 6 to 40 carbon atoms or a substituted or unsubstituted heteroaryl group having 3 to

EP 2 418 707 A1

40 carbon atoms. When the rings each are linked with plural link groups, the plural link groups may be mutually the same or different. Examples for each of the groups are the same as those described above.

In the formula (135), L' represents the same as the above.

5 In the formulae (126) to (135), R' represents a hydrogen atom, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 40 carbon atoms, or substituted or unsubstituted heteroaryl group having 3 to 40 carbon atoms. Examples for each of the groups are the same as those described above.

A structure represented by the formula (128), which is an example of Ar³, is preferably a fused cyclic group represented by any one of the following formulae (136) to (158).

[0144]

10

[Chemical Formula 36]

15

20

25

30


35

40

45

50

55




[0145] In the formulae (136) to (158), the fused rings each may be linked with a link group formed of a halogen atom, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 40 carbon atoms, a substituted

or unsubstituted aryl group having 6 to 40 carbon atoms or a substituted or unsubstituted heteroaryl group having 3 to 40 carbon atoms. When the rings each are linked with plural link groups, the plural link groups may be mutually the same or different. Examples for each of the groups are the same as those described above. R' is the same as the above. Alternatively, Ar² and Ar³ each independently are preferably a group selected from a group consisting of the following.

[0146]

[Chemical Formula 37]




[0147] Examples of the nitrogen-containing heterocyclic derivative represented by any one of the general formulae (201) to (203) according to the aspect of the invention will be shown below. However, the invention is not limited to the exemplary compounds shown below.

In the chart shown below, HAr represents any one of structures represented by the formulae (201) to (203).

[0148]

[Chemical Formula 38]




[0149]

[Chemical Formula 39] HAr-L-Ar¹-Ar²


5
10
15
20
25
30
35
40
45
50
55

1-1
2
3
4
5
6
7
8
9
10
11



(continued)


[Chemical Formula 39] HAr-L-Ar¹-Ar²




20 [0150]

[Chemical Formula 40]


HAr-L-Ar¹-Ar²




(continued)



[0151]




(continued)



[0152]

[Chemical Formula 42]




(continued)




[0153]

[Chemical Formula 43]




(continued)




[0154]

[Chemical Formula 44]




(continued)



30 [0155]

[Chemical Formula 45]




(continued)



[0156]


[Chemical Formula 46]



(continued)



(continued)




10 [0157]

[Chemical Formula 47]




(continued)




[0158]

[Chemical Formula 48]




(continued)



[0159]

[Chemical Formula 49]




55

(continued)



[0160]



(continued)

	HAr	L	Ar ¹	Ar ²
5				
3				
10				
4				
15				
5				
20				
6				
25				
7				
30				
8				
35				
9				
40				
10				
45				
11				
50				
55				

[0161]

[Chemical Formula 51]

(continued)


HAr-L-Ar¹-Ar²




[0162]

45 [Chemical Formula 52]

HAr-L-Ar¹-Ar²




(continued)



[0163]

[Chemical Formula 53]



(continued)

	HAr	L	Ar ¹	Ar ²
5				
4		/		
10				
5		/		
15				
6		/		
20				
7		/		
25				
8		/		
30				
9		/		
35				
10		/		
40				
45				

[0164]

[Chemical Formula 54]


HAr-L-Ar¹-Ar²

55

(continued)

	HAr	L	Ar ¹	Ar ²
5	16-1			
10	2			
15				
20	3			
25				
30	4			
35				
40	5			
45				
50	6			
55				
	7			


(continued)




10

[0165]

[Chemical Formula 55]



(continued)



[0166] Among the above examples, examples (1-1), (1-5), (1-7), (2-1), (3-1), (4-2), (4-6), (7-2), (7-7), (7-8), (7-9), (9-1) and (9-7) are particularly preferred.

[0167] Although thickness of the electron injecting layer or the electron transporting layer is not specifically limited, the thickness is preferably 1 to 100 nm.

[0168] The electron injecting layer preferably contains an inorganic compound such as an insulator or a semiconductor in addition to the nitrogen-containing cyclic derivative. Such an insulator or a semiconductor, when contained in the electron injecting layer, can effectively prevent a current leak, thereby enhancing electron injectability of the electron injecting layer.

As the insulator, it is preferable to use at least one metal compound selected from a group consisting of an alkali metal chalcogenide, an alkali earth metal chalcogenide, a halogenide of alkali metal and a halogenide of alkali earth metal. By forming the electron injecting layer from the alkali metal chalcogenide or the like, the electron injecting capability can preferably be further enhanced. Specifically, preferable examples of the alkali metal chalcogenide are Li_2O , K_2O , Na_2S , Na_2Se and Na_2O while preferable example of the alkali earth metal chalcogenide are CaO , BaO , SrO , BeO , BaS and CaSe . Preferable examples of the halogenide of the alkali metal are LiF , NaF , KF , LiCl , KCl and NaCl . Preferable examples of the halogenide of the alkali earth metal are fluorides such as CaF_2 , BaF_2 , SrF_2 , MgF_2 and BeF_2 , and halogenides other than the fluoride.


Examples of the semiconductor are one of or a combination of two or more of an oxide, a nitride or an oxidized nitride containing at least one element selected from Ba, Ca, Sr, Yb, Al, Ga, In, Li, Na, Cd, Mg, Si, Ta, Sb and Zn. An inorganic compound for forming the electron injecting layer is preferably a microcrystalline or amorphous semiconductor film. When the electron injecting layer is formed of such semiconductor film, more uniform thin film can be formed, thereby reducing pixel defects such as a dark spot. Examples of such an inorganic compound are the above-described alkali metal chalcogenide, alkali earth metal chalcogenide, halogenide of the alkali metal and halogenide of the alkali earth metal.

When the electron injecting layer contains such an insulator or such a semiconductor, a thickness thereof is preferably in a range of approximately 0.1 to 15nm. The electron injecting layer according to the aspect of the invention may preferably contain the above-described reductive dopant.

[0169] The hole injecting layer or the hole transporting layer (including the hole injecting/transporting layer) may contain an aromatic amine compound such as an aromatic amine derivative represented by the following (I).

[0170]

[Chemical Formula 56]



[0171] In the above (I), Ar¹ to Ar⁴ each represent a substituted or unsubstituted aryl group having 6 to 50 carbon atoms for forming a ring or a substituted or unsubstituted heteroaryl group having 5 to 50 atoms for forming a ring.

[0172] Examples of the substituted or unsubstituted aryl group having 6 to 50 ring carbon atoms are a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, fluoranthenyl group, fluorenyl group and the like.

[0173] Examples of the substituted or unsubstituted heteroaryl group having 5 to 50 ring atoms are a 1-pyroryl group, 2-pyroryl group, 3-pyroryl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 2-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxaliny group, 5-quinoxaliny group, 6-quinoxaliny group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group, 1-phenanthrydiny group, 2-phenanthrydiny group, 3-phenanthrydiny group, 4-phenanthrydiny group, 6-phenanthrydiny group, 7-phenanthrydiny group, 8-phenanthrydiny group, 9-phenanthrydiny group, 10-phenanthrydiny group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-3-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-me-

thyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group and the like. Among the above, a phenyl group, a naphthyl group, biphenyl group, anthranil group, phenanthryl group, pyrenyl group, chrysenyl group, fluoranthryl group, fluorenyl group and the like are preferable.

[0174] L represents a link group. Specifically, L represents a substituted or unsubstituted arylene group having 6 to 50 carbon atoms forming a ring, a substituted or unsubstituted heteroarylene group having 5 to 50 atoms forming a ring, a divalent group formed by singly bonding, ether-bonding or thioether-bonding two or more arylene groups, a divalent group formed by bonding two or more arylene groups by alkylene group having 1 to 20 carbon atoms, alkenylene group having 2 to 20 carbon atoms or amino group, a divalent group formed by singly bonding, ether-bonding or thioether-bonding two or more heteroarylene groups, or a divalent group formed by bonding two or more heteroarylene groups by alkylene group having 1 to 20 carbon atoms, alkenylene group having 2 to 20 carbon atoms or amino group. Examples of the arylene group having 6 to 50 ring carbon atoms are a 1,4-phenylene group, 1,2-phenylene group, 1,3-phenylene group, 1,4-naphthylene group, 2,6-naphthylene group, 1,5-naphthylene group, 9,10-anthranylene group, 9,10-phenanthrenylene group, 3,6-phenanthrenylene group, 1,6-pyrenylene group, 2,7-pyrenylene group, 6,12-chrysenylene group, 4,4'-biphenylene group, 3,3'-biphenylene group, 2,2'-biphenylene group, 2,7-fluorenylene group and the like. Examples of the arylene group having 5 to 50 ring atoms are a 2,5-thiophenylene group, 2,5-silolylene group, 2,5-oxadiazolylene and the like. Among the above, a 1,4-phenylene group, 1,2-phenylene group, 1,3-phenylene group, 1,4-naphthylene group, 9,10-anthranylene group, 6,12-chrysenylene group, 4,4'-biphenylene group, 3,3'-biphenylene group, 2,2'-biphenylene group, and 2,7-fluorenylene group are preferable.

[0175] When L represents a link group formed of 2 or more arylene groups or 2 or more heteroarylene groups, adjacent arylene groups or adjacent heteroarylene groups may be bonded together via a divalent group to form a new ring. Examples of the divalent group for forming the ring are a tetramethylene group, a pentamethylene group, a hexamethylene group, a diphenylmethane-2,2'-diyl group, a diphenylethane-3,3'-diyl group, a diphenylpropane-4,4'-diyl group and the like.

[0176] Examples of a substituent for each of Ar¹ to Ar⁴ and L are an amino group, a halogen atom, a cyano group, a nitro group and a hydroxy group each of which is substituted by a substituted or unsubstituted aryl group having 6 to 50 carbon atoms forming a ring, a substituted or unsubstituted heteroaryl group having 5 to 50 atoms forming a ring, a substituted or unsubstituted alkyl group having 1 to 50 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 50 carbon atoms, a substituted or unsubstituted aralkyl group having 7 to 50 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 50 carbon atoms forming a ring, a substituted or unsubstituted heteroaryloxy group having 6 to 50 carbon atoms forming a ring, a substituted or unsubstituted arylthio group having 6 to 50 atoms forming a ring, a substituted or unsubstituted heteroarylthio group having 5 to 50 atoms forming a ring, a substituted or unsubstituted alkoxy carbonyl group having 2 to 50 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms forming a ring, or a substituted or unsubstituted heteroaryl group having 5 to 50 atoms forming a ring.

[0177] Examples of the substituted or unsubstituted aryl group having 6 to 50 ring carbon atoms are a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, fluoranthryl group, fluorenyl group and the like.

[0178] Examples of the substituted or unsubstituted heteroaryl group having 5 to 50 ring atoms are a 1-pyroryl group, 2-pyroryl group, 3-pyroryl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 2-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxaliny group, 5-quinoxaliny group, 6-quinoxaliny group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group, 1-phenanthrydiny group, 2-phenanthrydiny group, 3-phenanthrydiny group, 4-phenanthrydiny group, 6-phenanthrydiny group, 7-phenanthrydiny group, 8-phenanthrydiny group, 9-phenanthrydiny group, 10-phenanthrydiny group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenan-

throlin-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-3-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group and the like.

[0179] Examples of the substituted or unsubstituted alkyl group having 1 to 50 carbon atoms are a methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group and 1,2,3-trinitropropyl group.

[0180] Examples of the substituted or unsubstituted cycloalkyl group having 3 to 50 carbon atoms are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, a 4-methylcyclohexyl group, a 1-adamantyl group, a 2-adamantyl group, a 1-norbornyl group, a 2-norbornyl group and the like.

[0181] The substituted or unsubstituted alkoxy group having 1 to 50 carbon atoms is a group represented by -OY. Examples of the substituted or unsubstituted alkyl group having 1 to 50 carbon atoms are a methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group and 1,2,3-trinitropropyl group.

[0182] Examples of the substituted or unsubstituted aralkyl group having 7 to 50 carbon atoms are a benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, 2-phenylisopropyl group, phenyl-t-butyl group, α -naphthylmethyl group, 1- α -naphthylethyl group, 2- α -naphthylethyl group, 1- α -naphthylisopropyl group, 2- α -naphthylisopropyl group, β -naphthylmethyl group, 1- β -naphthylethyl group, 2- β -naphthylethyl group, 1- β -naphthylisopropyl group, 2- β -naphthylisopropyl group, 1-pyrorylmethyl group, 2-(1-pyroryl)ethyl group, p-methylbenzyl group, m-methylbenzyl group, o-methylbenzyl group, p-chlorobenzyl group, m-chlorobenzyl group, o-chlorobenzyl group, p-bromobenzyl group,

m-bromobenzyl group, o-bromobenzyl group, p-iodobenzyl group, m-iodobenzyl group, o-iodobenzyl group, p-hydroxybenzyl group, m-hydroxybenzyl group, o-hydroxybenzyl group, p-aminobenzyl group, m-aminobenzyl group, o-aminobenzyl group, p-nitrobenzyl group, m-nitrobenzyl group, o-nitrobenzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-hydroxy-2-phenylisopropyl group, 1-chloro-2-phenylisopropyl group and the like.

[0183] The substituted or unsubstituted aryloxy group having 6 to 50 ring carbon atoms is represented by -OY'. Examples of Y' are a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group and the like.

[0184] Among the aryloxy group, the heteroaryloxy group is represented by -OZ'. Examples of Z' are a 2-pyroryl group, 3-pyroryl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalanyl group, 5-quinoxalanyl group, 6-quinoxalanyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthrydiny group, 2-phenanthrydiny group, 3-phenanthrydiny group, 4-phenanthrydiny group, 6-phenanthrydiny group, 7-phenanthrydiny group, 8-phenanthrydiny group, 9-phenanthrydiny group, 10-phenanthrydiny group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group and the like.

[0185] The substituted or unsubstituted arylthio group having 6 to 50 ring carbon atoms is represented by -SY". Examples of Y" are a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group and the like.

[0186] The substituted or unsubstituted heteroarylthio group having 5 to 50 ring carbon atoms is represented by -SZ". Examples of Z" are a 2-pyroryl group, 3-pyroryl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-

furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxaliny group, 5-quinoxaliny group, 6-quinoxaliny group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthrydiny group, 2-phenanthrydiny group, 3-phenanthrydiny group, 4-phenanthrydiny group, 6-phenanthrydiny group, 7-phenanthrydiny group, 8-phenanthrydiny group, 9-phenanthrydiny group, 10-phenanthrydiny group, 1-acridiny group, 2-acridiny group, 3-acridiny group, 4-acridiny group, 9-acridiny group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-8-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenaziny group, 2-phenaziny group, 1-phenothiaziny group, 2-phenothiaziny group, 3-phenothiaziny group, 4-phenothiaziny group, 1-phenoxaziny group, 2-phenoxaziny group, 3-phenoxaziny group, 4-phenoxaziny group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group and the like.

[0187] Examples of the substituted or unsubstituted alkyoxycarbonyl group having 2 to 50 carbon atoms are a methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group and 1,2,3-trinitropropyl group.


[0188] The amino group substituted by the substituted or unsubstituted aryl group having 6 to 50 ring carbon atoms or the substituted or unsubstituted heteroaryl group having 5 to 50 ring atoms is represented by -NPQ. Examples of P and Q are a phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthaceny group, 2-naphthaceny group, 9-naphthaceny group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyly group, 3-biphenyly group, 4-biphenyly group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl) phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyly group, 4-Et-butyl-p-terphenyl-4-yl group, 2-pyroryl group, 3-pyroryl group, pyraziny group, 2-pyridiny group, 3-pyridiny group, 4-pyridiny group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group,

2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalanyl group, 5-quinoxalanyl group, 6-quinoxalanyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthrydiny group, 2-phenanthrydiny group, 3-phenanthrydiny group, 4-phenanthrydiny group, 6-phenanthrydiny group, 7-phenanthrydiny group, 8-phenanthrydiny group, 9-phenanthrydiny group, 10-phenanthrydiny group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group and the like.

[0189] Examples of the compound represented by the above (I) are shown below. However, the compound is not limited thereto.

[0190]

[Chemical Formula 57]



[0191] Aromatic amine represented by the following (II) can also be preferably used for forming the hole injecting layer or the hole transporting layer.


[0192]

55

[Chemical Formula 58]

5

10



15

[0193] In the above (II), Ar¹ to Ar³ each represent the same as those represented by Ar¹ to Ar⁴ of the above (I). Examples of the compound represented by the above (II) are shown below. However, the compound is not limited thereto.

[0194]

20

[Chemical Formula 59]

25

30


35

40

45

50

55




[0195]

[Chemical Formula 60]

50

55



[0196] It should be noted that the invention is not limited to the above description but may include any modification as long as such modification is compatible with the invention.

For instance, the following is a preferable example of such modification made to the invention.

40 According to the aspect of the invention, the emitting layer may also preferably contain an assistance substance for assisting injection of charges.

When the emitting layer is formed of a host material that exhibits a wide energy gap, a difference in ionization potential (I_p) between the host material and the hole injecting/transporting layer etc. becomes so large that the holes can hardly be injected into the emitting layer and that a driving voltage required for providing sufficient luminance may be raised.

45 **[0197]** In the above instance, introducing a hole-injectable or hole-transportable assistance substance for assisting injection of charges in the emitting layer can contribute to facilitation of the injection of the holes into the emitting layer and to reduction of the driving voltage.

As the assistance substance for assisting the injection of charges, for instance, a general hole injecting material, a general hole transporting material or the like can be used.

50 Examples of the material are a triazole derivative (see, for instance, the specification of US Patent No. 3,112,197), an oxadiazole derivative (see, for instance, the specification of US Patent No. 3,189,447), an imidazole derivative (see, for instance, JP-B-37-16096), a polyaryllalkane derivative (see, for instance, the specifications of US Patent No. 3,615,402, No.3,820,989 and No. 3,542,544, JP-B-45-555, JP-B-51-10983, JP-A-51-93224, JP-A-55-17105, JP-A-56-4148, JP-A-55-108667, JP-A-55-156953, and JP-A-56-36656), a pyrazoline derivative and a pyrazolone derivative (see, for instance, the specifications of US Patent No. 3,180,729 and No. 4,278,746, JP-A-55-88064, JP-A-55-88065, JP-49-105537, JP-A-55-51086, JP-A-56-80051, JP-A-56-88141, JP-A-57-45545, JP-A-54-112637 and JP-A-55-74546), a phenylenediamine derivative (see, for instance, the specification of US Patent No. 3,615,404, JP-B-51-10105, JP-B-46-3712, JP-B-47-25336, JP-A-54-53435, JP-A-54-110536 and JP-A-54-119925), an arylamine derivative (see, for instance, the

specifications of US Patent No. 3,567,450, No. 3,180,703, No. 3,240,597, No. 3,658,520, No. 4,232,103, No. 4,175,961 and No. 4,012,376, JP-B-49-35702, JP-B-39-27577, JP-A-55-144250, JP-A-56-119132 and JP-A-56-22437 and the specification of West Germany Patent No. 1,110,518), an amino-substituted chalcone derivative (see, for instance, the specification of US Patent No. 3,526,501), an oxazole derivative (disclosed in, for instance, the specification of US Patent No. 3,112,197, 257,203), a styrylanthracene derivative (see, for instance, JP-A-56-46234), a fluorenone derivative (see, for instance, JP-A-54-110837), a hydrazone derivative (see, for instance, the specification of US Patent No. 3,717,462 and JP-A-54-59143, JP-A-55-52063, JP-A-55-52064, JP-A-55-46760, JP-A-55-85495, JP-A-57-11350, JP-A-57-148749 and JP-A-02-311591), a stilbene derivative (see, for instance, JP-A-61-210363, JP-A-61-228451, JP-A-61-14642, JP-A-61-72255, JP-A-62-47646, JP-A-62-36674, JP-A-62-10652, JP-A-62-30255, JP-A-60-93455, JP-A-60-94462, JP-A-60-174749 and JP-A-60-175052), a silazane derivative (see the specification of US Patent No. 4,950,950), a polysilane type (see JP-A-02-204996), an aniline-based copolymer (see JP-A-02-282263), and a conductive polymer oligomer (particularly, thiophene oligomer) disclosed in JP-A-01-211399.

[0198] The hole-injectable material, examples of which are as listed above, is preferably a porphyrin compound (disclosed in JP-A-63-295695 etc.), an aromatic tertiary amine compound or a styrylamine compound (see, for instance, the specification of US Patent No. 4,127,412, JP-A-53-27033, JP-A-54-58445, JP-A-54-149634, JP-A-54-64299, JP-A-55-79450, JP-A-55-144250, JP-A-56-119132, JP-A-61-295558, JP-A-61-98353 or JP-A-63-295695), particularly preferably an aromatic tertiary amine compound.

[0199] In addition, 4,4'-bis(N-(1-naphthyl)-N-phenylamino)biphenyl (hereinafter, abbreviated as NPD) having in the molecule two fused aromatic rings disclosed in US Patent No. 5,061,569, 4,4'-tris(N-(3-methylphenyl)-N-phenylamino)triphenylamine (hereinafter, abbreviated as MTDATA) in which three triphenylamine units disclosed in JP-A-04-308688 are bonded in a starburst form and the like may also be used.

Further, a hexaazatriphenylene derivative disclosed in Japanese Patent No. 3614405 and No. 3571977 and US Patent No. 4,780,536 may also preferably be used as the hole-injectable material.

[0200] Alternatively, inorganic compounds such as p-type Si and p-type SiC can also be used as the hole-injectable material.

[0201] A method of forming each of the layers in the organic EL device according to the aspect of the invention is not particularly limited. A conventionally-known methods such as vacuum deposition or spin coating may be employed for forming the layers. The organic thin-film layer containing the compound represented by the formula (1), which is used in the organic EL device according to the aspect of the invention, may be formed by a conventional coating method such as vacuum deposition, molecular beam epitaxy (MBE method) and coating methods using a solution such as a dipping, spin coating, casting, bar coating, and roll coating.

Although the thickness of each organic layer of the organic EL device is not particularly limited, the thickness is generally preferably in a range of several nanometers to 1 μm because an excessively-thinned film likely entails defects such as a pin hole while an excessively-thickened film requires high voltage to be applied and deteriorates efficiency.


Examples

[0202] Next, the invention will be described in further detail by exemplifying Example(s) and Comparative(s). However, the invention is not limited by the description of Example(s).

Synthesis Example 1 (Synthesis of Compound (A1))

[0203]

[Chemical Formula 61]



[0204] Under an argon gas atmosphere, 7.33 g (18 mmol) of bromide 1-2, 6.70g (18 mmol) of boronic acid I-1, 420 mg (0.36 mmol) of tetrakis(triphenylphosphine)palladium(0), 80 mL of toluene, 80 mL of dimethoxyethane and 26 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized by toluene, such that 6.48 g of the compound (A1) was obtained at a yield of 55%.

20

25


FD mass analysis consequently showed that m/e was equal to 654 while a calculated molecular weight was 654.

Synthesis Example 2 (Synthesis of Compound (A3))

[0205]

30

[Chemical Formula 62]



[0206] Under an argon gas atmosphere, 7.33 g (18 mmol) of bromide 1-2, 5.37g (18 mmol) of boronic acid I-3, 420 mg (0.36 mmol) of tetrakis(triphenylphosphine)palladium(0), 80 mL of toluene, 80 mL of dimethoxyethane and 26 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized by toluene, such that 6.27g of the compound (A3) was obtained at a yield of 60%.

50


55

FD mass analysis consequently showed that m/e was equal to 580 while a calculated molecular weight was 580.

Synthesis Example 3 (Synthesis of Compound (A7))

[0207]

[Chemical Formula 63]




[0208] Under an argon gas atmosphere, 7.33 g (18 mmol) of bromide I-4, 5.37g (18 mmol) of boronic acid I-3, 420 mg (0.36 mmol) of tetrakis(triphenylphosphine)palladium(0), 80 mL of toluene, 80 mL of dimethoxyethane and 26 mL of 2M sodium carbonate solution were added together, and stirred for 14 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 5.02g of the compound (A7) was obtained at a yield of 48%.

FD mass analysis consequently showed that m/e was equal to 580 while a calculated molecular weight was 580.

Synthesis Example 4 (Synthesis of Compound (A9))

[0209]

[Chemical Formula 64]



[0210] Under an argon gas atmosphere, 5.36g (15 mmol) of bromide I-5, 5.58g (15 mmol) of boronic acid I-1, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 50 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 10 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and


subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 3.72g of the compound (A9) was obtained at a yield of 41 %.

FD mass analysis consequently showed that m/e was equal to 604 while a calculated molecular weight was 604.

5 Synthesis Example 5 (Synthesis of Compound (A11))

[0211]

10 [Chemical Formula 65]



30 [0212] Under an argon gas atmosphere, 5.36g (15 mmol) of bromide I-5, 4.47g (15 mmol) of boronic acid I-3, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 50 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 4.70g of the compound (A11) was obtained at a yield of 59%.

35 FD mass analysis consequently showed that m/e was equal to 530 while a calculated molecular weight was 530.


40 Synthesis Example 6 (Synthesis of Compound (A18))

[0213]

45 [Chemical Formula 66]

50

55



20 **[0214]** Under an argon gas atmosphere, 6.43g (18 mmol) of bromide I-5, 7.17g (18 mmol) of boronic acid I-6, 420 mg (0.36 mmol) of tetrakis(triphenylphosphine)palladium(0), 80 mL of toluene, 80 mL of dimethoxyethane and 26 mL of 2M sodium carbonate solution were added together, and stirred for 11 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 4.31g of the compound (A18) was obtained at a yield of 38%. FD mass analysis consequently showed that m/e was equal to 630 while a calculated molecular weight was 630.


25

30 Synthesis Example 7 (Synthesis of Compound (A20))

[0215]

[Chemical Formula 67]

35



55 **[0216]** Under an argon gas atmosphere, 6.43g (18 mmol) of bromide I-5, 8.07g (18 mmol) of boronic acid I-7, 420 mg (0.36 mmol) of tetrakis(triphenylphosphine)palladium(0), 80 mL of toluene, 80 mL of dimethoxyethane and 26 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the

organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 4.29g of the compound (A20) was obtained at a yield of 35%.

FD mass analysis consequently showed that m/e was equal to 680 while a calculated molecular weight was 680.

5


Synthesis Example 8 (Synthesis of Compound (A30))

[0217]

10

[Chemical Formula 68]

15



25

30

[0218] Under an argon gas atmosphere, 6.90g (18 mmol) of bromide I-8, 6.70g (18 mmol) of boronic acid I-1, 420 mg (0.36 mmol) of tetrakis(triphenylphosphine)palladium(0), 80 mL of toluene, 80 mL of dimethoxyethane and 26 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 3.18g of the compound (A30) was obtained at a yield of 28%.

35

FD mass analysis consequently showed that m/e was equal to 630 while a calculated molecular weight was 630.

40

Synthesis Example 9 (Synthesis of Compound (A32))


[0219]

45

[Chemical Formula 69]

50

55



20

25


[0220] Under an argon gas atmosphere, 5.75g (15 mmol) of bromide I-8, 4.47g (15 mmol) of boronic acid I-3, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 60 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 13 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 3.26g of the compound (A32) was obtained at a yield of 39%. FD mass analysis consequently showed that m/e was equal to 556 while a calculated molecular weight was 556.

Synthesis Example 10 (Synthesis of Compound (A37))

[0221]

30

[Chemical Formula 70]



55

[0222] Under an argon gas atmosphere, 6.50g (15 mmol) of bromide I-9, 5.97g (15 mmol) of boronic acid I-6, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 60 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times


by toluene, such that 4.77g of the compound (A37) was obtained at a yield of 45%.

FD mass analysis consequently showed that m/e was equal to 706 while a calculated molecular weight was 706.

Synthesis Example 11 (Synthesis of Compound (A42))

[0223]

[Chemical Formula 71]




[0224] Under an argon gas atmosphere, 6.50g (15 mmol) of bromide I-10, 5.58g (15 mmol) of boronic acid I-1, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 60 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 4.49g of the compound (A42) was obtained at a yield of 44%.

FD mass analysis consequently showed that m/e was equal to 680 while a calculated molecular weight was 680.

Synthesis Example 12 (Synthesis of Compound (A50))

[0225]

[Chemical Formula 72]




20 [0226] Under an argon gas atmosphere, 5.75g (15 mmol) of bromide I-11, 5.58g (15 mmol) of boronic acid I-1, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 60 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 13 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times

25 by toluene, such that 4.92g of the compound (A50) was obtained at a yield of 52%. FD mass analysis consequently showed that m/e was equal to 630 while a calculated molecular weight was 630.

Synthesis Example 13 (Synthesis of Compound (A52))

30 [0227]

[Chemical Formula 73]



55 [0228] Under an argon gas atmosphere, 5.75g (15 mmol) of bromide I-11, 4.47g (15 mmol) of boronic acid I-3, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 60 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 3.01g of the compound (A52) was obtained at a yield of 36%.

FD mass analysis consequently showed that m/e was equal to 556 while a calculated molecular weight was 556.

Synthesis Example 14 (Synthesis of Compound (A59))

5 [0229]

[Chemical Formula 74]


10

15

20

25

30



35

[0230] Under an argon gas atmosphere, 5.75g (15 mmol) of bromide I-11, 5.97g (15 mmol) of boronic acid I-6, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 60 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 4.53g of the compound (A59) was obtained at a yield of 46%.

FD mass analysis consequently showed that m/e was equal to 656 while a calculated molecular weight was 656.

40 Synthesis Example 15 (Synthesis of Compound (A62))


[0231]

45

[Chemical Formula 75]

50

55



[0232] Under an argon gas atmosphere, 6.50g (15 mmol) of bromide I-12, 4.47g (15 mmol) of boronic acid I-3, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 60 mL of toluene, 60 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 12 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized three times by toluene, such that 4.87g of the compound (A62) was obtained at a yield of 54%.

20


25

FD mass analysis consequently showed that m/e was equal to 556 while a calculated molecular weight was 556.

Synthesis Example 16 (Synthesis of Compound (A69))

[0233]

[Chemical Formula 76]



[0234] Under an argon gas atmosphere, 6.74g (15 mmol) of bromide I-13, 4.47g (15 mmol) of boronic acid I-3, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 70 mL of toluene, 70 mL of dimethoxyethane and 23 mL of 2M sodium carbonate solution were added together, and stirred for 14 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized by toluene, such that 4.80g of the compound (A69) was obtained at a yield of 51%.

55

FD mass analysis consequently showed that m/e was equal to 622 while a calculated molecular weight was 622.

Synthesis Example 17 (Synthesis of Compound (A79))

5 [0235]


[Chemical Formula 77]

10

15

20

25



30

35

[0236] Under an argon gas atmosphere, 8.33g (15 mmol) of bromide I-14, 5.58g (15 mmol) of boronic acid I-1, 350mg (0.30 mmol) of tetrakis(triphenylphosphine)palladium(0), 90 mL of toluene, 90 mL of dimethoxyethane and 22 mL of 2M sodium carbonate solution were added together, and stirred for 15 hours at 85 degrees C. Subsequently, the reaction mixture was cooled down to room temperature and added with water, and the aqueous phase was removed while the organic phase was condensed. Addition of nitrobenzene then followed, and the residue was thermally melted and subjected to filtration. Then, the residue was refined by silica-gel column chromatography and recrystallized by toluene,

such that 5.15g of the compound (A79) was obtained at a yield of 43%.
FD mass analysis consequently showed that m/e was equal to 803 while a calculated molecular weight was 803.

Example 1

40

Manufacturing of Organic EL Device

45

50

55

[0237] A glass substrate (size: 25 mm x 75 mm x 0.7 mm thick) having an ITO transparent electrode (manufactured by Asahi Glass Co., Ltd) was ultrasonic-cleaned in isopropyl alcohol for five minutes, and then UV/ozone-cleaned for 30 minutes. After the glass substrate having the transparent electrode line was cleaned, the glass substrate was mounted on a substrate holder of a vacuum deposition apparatus, so that 50-nm thick film of HT1 was initially formed on a surface of the glass substrate where the transparent electrode line was provided so as to cover the transparent electrode. The HT1 film serves as a hole injecting/transporting layer. Subsequently to the formation of the hole injecting/transporting layer, 40-nm thick film of the compound (A1) and film of Ir(piq)₃ as a phosphorescent dopant (phosphorescent material) were co-evaporated on the hole injecting/transporting layer by resistance heating so that Ir(piq)₃ was contained therein with a content of 10 mass%. The co-deposited film serves as an emitting layer (phosphorescent emitting layer). After the film of the emitting layer was formed, 40-nm thick film of ET1 was formed. The film of ET1 serves as an electron transporting layer. Then, 0.5-nm thick film of LiF was formed as an electron-injecting electrode (cathode) at a film-forming speed of 0.1 nm/min. Metal (A1) was vapor-deposited on the LiF film to form a 150-nm thick metal cathode, thereby providing the organic EL device.

Examples 2 to 17 and Comparatives 1 to 4

[0238] The organic EL devices according respectively to Examples 2 to 17 and Comparatives 1 to 4 were formed by

the same method as Example 1 except that compounds shown in Table 1 were respectively used in place of the compound (A1).

Evaluation on Emitting Performance of Organic EL Device

5

[0239] The organic EL devices according to Examples 1 to 17 and Comparatives 1 to 4 each were driven by direct-current electricity to emit light, so that voltage, luminous efficiency and time elapsed until the initial luminance intensity of 3000 cd/m² was reduced to the half (i.e., time until half-life) at a current density of 10 mA/cm² were measured for each organic EL device.

10

The phosphorescence spectrum of each sample was measured by the following method. Specifically, each material was dissolved in an EPA solvent (diethylether: isopentane: ethanol = 5: 5: 2 in volume ratio) with a concentration of 10 μmol/L, thereby forming a sample for phosphorescence measurement. Then, the sample for phosphorescence measurement was put into a quartz cell, cooled to 77K and irradiated with exciting light (with use of FLUOROLOG II manufactured by SPEX Corporation).

15

A tangent line was drawn to be tangent to a rising section adjacent to the short-wavelength side of the phosphorescence spectrum, and a wavelength (emission end) at an intersection of the tangent line and the abscissa axis was obtained. The obtained wavelength was converted into energy value so as to measure the triplet energy (Eg(T)) of the organic-EL-device material. The samples were all products purified by sublimation purification.

The results of the evaluation are shown in Table 1.

20

[0240]

[Chemical Formula 78]

25

30

35


40

45

50


55

5




Ir(piq)₃

10




HT1

15




CBP

20



ET1

25




BAlq

30

35


40



(P)

45

50



(Q)

55

[0241]

Table 1

	Compound	Eg(T)(eV) of Compound	Voltage (V)	Luminous Efficiency (cd/A)	Time until Half-life (hours)	
5	Example 1	A1	2.24	3.5	12.3	13000
	Example 2	A3	2.26	3.6	12.6	13900
10	Example 3	A7	2.27	3.6	13.0	12800
	Example 4	A9	2.22	3.5	12.0	13300
	Example 5	A11	2.27	3.4	12.6	14000
15	Example 6	A18	2.32	3.5	12.5	12800
	Example 7	A20	2.20	3.6	12.3	12500
	Example 8	A30	2.34	3.4	13.2	12700
	Example 9	A32	2.45	3.5	13.1	13300
20	Example 10	A37	2.40	3.5	12.8	12500
	Example 11	A42	2.32	3.5	12.4	13000
	Example 12	A50	2.36	3.4	14.0	13700
	Example 13	A52	2.44	3.4	12.6	13500
25	Example 14	A59	2.42	3.5	12.7	14100
	Example 15	A62	2.37	3.5	12.5	14700
	Example 16	A69	2.26	3.6	11.4	11900
30	Example 17	A79	2.33	3.4	12.0	12800
	Comparative 1	CBP	2.81	5.7	6.3	1200
	Comparative 2	BAIq	2.28	5.3	7.0	2300
	Comparative 3	P	2.47	4.3	12.3	12500
35	Comparative 4	Q	2.38	4.4	10.0	10500

[0242] As is clearly understandable from Table 1, with respect to luminous efficiency, the organic EL device according to each of Examples 1 to 17, which was formed of the organic-EL-device material according to the aspect of the invention, has been found to require low driving voltage, exhibit high external quantum efficiency and have considerably long lifetime. In contrast, the organic EL device according to each of Comparatives 1 and 2 required relatively high driving voltage, exhibited low luminous efficiency and had short lifetime. The organic EL device according to each of Comparatives 3 and 4 exhibited an approximately equal level of luminous efficiency, but required driving voltage higher by 0.7 to 1.0 V than those required by the devices of Examples 1 to 17.

[0243] When applied as the host material of an organic EL device, the material according to the aspect of the invention enables the luminous efficiency to be enhanced because the triplet energy of the host material and the triplet energy of the dopant are well-balanced, and enables the device to have a longer lifetime than a device provided by a conventionally-known combination of materials because the organic-EL-device material contains no nitrogen-containing ring or nitrogen atom in its molecular skeleton and thus exhibits high tolerance of holes and electrons. In addition, by selecting the specific partial structure and the specific molecular linkage structure, the driving voltage of the organic EL device can be dramatically reduced, and the power consumption by the organic EL device can be dramatically improved.

INDUSTRIAL APPLICABILITY

[0244] The invention is applicable to a phosphorescent organic EL device capable of reducing driving voltage and exhibiting high efficiency and long lifetime

EXPLANATION OF CODES

[0245]


- 5 1... organic EL device
 2... substrate
 3...anode
 4... cathode
 5... phosphorescent-emitting layer
 10 6...hole injecting/transporting layer
 7... electron injecting/transporting layer
 10... organic thin-film layer

15 **Claims**

1. An organic electroluminescence device, comprising:

20 a cathode;
 an anode; and
 an organic thin-film layer including at least one layer and provided between the cathode and the anode, wherein
 at least one layer of the organic thin-film layer comprises: an organic-electroluminescence-device material
 represented by any one of the following formulae (1), (2) and (3); and at least one phosphorescent material,
 wherein
 25 the organic-electroluminescence-device material is allowed to have a substituent,

[Chemical Formula 1]




45 where: A represents a group selected from a 3-fluoranthenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo
 [c]phenanthrenyl group and 10-benzo[g]chrysenyl group; and
 Ar represents a fused aromatic ring having 10 to 30 carbon atoms and having triplet energy of 2.10 eV or more.

- 50 2. The organic electroluminescence device according to claim 1, wherein the A or the Ar is allowed to be substituted
 by a phenyl group or a naphthyl group.
3. The organic electroluminescence device according to claim 1 or 2, wherein the A represents a group selected from
 an unsubstituted 3-fluoranthenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-
 55 benzo[g]chrysenyl group.
4. The organic electroluminescence device according to any one of claims 1 to 3, wherein the Ar each independently
 represent a group selected from a naphthyl group, fluoranthenyl group, phenanthrenyl group, benzophenanthrenyl

group and benzo[g]chrysenyl group.

- 5
- 10
- 15
- 20
- 25
- 30
- 35
- 40
- 45
- 50
- 55
5. The organic electroluminescence device according to claim 4, wherein the Ar represents a group selected from a 2-naphthyl group, 3-fluoranthenyl group, 8-fluoranthenyl group, 9-phenanthrenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-benzo[g]chrysenyl group.
 6. The organic electroluminescence device according to claim 5, wherein the organic-electroluminescence-device material is represented by the formula (1) and the Ar is a 2-naphtyl group.
 7. The organic electroluminescence device according to any one of claims 1 to 6, wherein triplet energy of the organic-electroluminescence-device material represented by any one of the formulae (1), (2) and (3) is in a range of 2.0 eV to 2.5 eV
 8. The organic electroluminescence device according to any one of claims 1 to 7, wherein the at least one layer of the organic thin-film layer is an emitting layer, and at least one layer of the emitting layer comprises: the organic-electroluminescence-device material represented by any one of the formulae (1), (2) and (3); and at least one phosphorescent material.
 9. The organic electroluminescence device according to claim 8, wherein the phosphorescent material contains a metal complex, the metal complex comprising: a metal atom selected from Ir, Pt, Os, Au, Re and Ru; and a ligand.
 10. The organic electroluminescence device according to claim 9, wherein the ligand has: a metal atom for forming a complex; and an ortho-metal bond.
 11. The organic electroluminescence device according to any one of claims 8 to 10, wherein a maximum wavelength of light emission of the at least one phosphorescent material contained in the emitting layer is in a range of 520 nm to 720 nm.
 12. The organic electroluminescence device according to any one of claims 1 to 11, wherein the organic thin-film layer comprises an electron transporting layer between the cathode and the emitting layer, the electron transporting layer comprising the organic-electroluminescence-device material.
 13. The organic electroluminescence device according to any one of claims 1 to 12, wherein the organic thin-film layer comprises an electron transporting layer or an electron injecting layer between the cathode and the emitting layer, and the electron transporting layer or the electron injecting layer comprises an aromatic ring having a nitrogen-containing six-membered or five-membered ring skeleton, or a fused aromatic cyclic compound having a nitrogen-containing six-membered or five-membered ring skeleton.
 14. The organic electroluminescence device according to any one of claims 1 to 13, wherein a reductive dopant is present at an interfacial region between the cathode and the organic thin-film layer.
 15. An organic-electroluminescence-device material that is represented by any one of the following formulae (1), (2) and (3) and is allowed to have a substituent,


[Chemical Formula 2]



25 where: A represents a group selected from a 3-fluoranthenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-benzo[g]chrysenyl group; and Ar represents a fused aromatic ring having 10 to 30 carbon atoms and having triplet energy of 2.10 eV or more.

- 30
- 35
- 40
- 45
- 50
- 55
16. The organic-electroluminescence-device material according to claim 15, wherein the A or the Ar is allowed to be substituted by a phenyl group or a naphthyl group.
 17. The organic-electroluminescence-device material according to claim 15 or 16, wherein the A represents a group selected from an unsubstituted 3-fluoranthenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-benzo[g]chrysenyl group.
 18. The organic-electroluminescence-device material according to any one of claims 15 to 17, wherein the Ar each independently represent a group selected from a naphthyl group, fluoranthenyl group, phenanthrenyl group, benzophenanthrenyl group and benzo[g]chrysenyl group.
 19. The organic-electroluminescence-device material according to claim 18, wherein the Ar represents a group selected from a 2-naphthyl group, 3-fluoranthenyl group, 8-fluoranthenyl group, 9-phenanthrenyl group, 5-benzo[c]phenanthrenyl group, 6-benzo[c]phenanthrenyl group and 10-benzo[g]chrysenyl group.
 20. The organic-electroluminescence-device material according to claim 19, wherein the organic-electroluminescence-device material is represented by the formula (1) and the Ar is a 2-naphthyl group.

FIG. 1



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2010/056166

<p>A. CLASSIFICATION OF SUBJECT MATTER <i>H01L51/50</i>(2006.01) <i>i</i>, <i>C07C13/62</i>(2006.01) <i>i</i>, <i>C09K11/06</i>(2006.01) <i>i</i>, <i>C07F15/00</i> (2006.01) <i>n</i></p> <p>According to International Patent Classification (IPC) or to both national classification and IPC</p>											
<p>B. FIELDS SEARCHED</p> <p>Minimum documentation searched (classification system followed by classification symbols) <i>H01L51/50</i>, <i>C07C13/62</i>, <i>C09K11/06</i>, <i>C07F15/00</i></p> <p>Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1922-1996 Jitsuyo Shinan Toroku Koho 1996-2010 Kokai Jitsuyo Shinan Koho 1971-2010 Toroku Jitsuyo Shinan Koho 1994-2010</p> <p>Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) CA/REGISTRY (STN)</p>											
<p>C. DOCUMENTS CONSIDERED TO BE RELEVANT</p> <table border="1"> <thead> <tr> <th>Category*</th> <th>Citation of document, with indication, where appropriate, of the relevant passages</th> <th>Relevant to claim No.</th> </tr> </thead> <tbody> <tr> <td>A</td> <td>WO 2009/008356 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0041], [0054], [0282] to [0283]; claims 1 to 17 & EP 2166591 A</td> <td>1-20</td> </tr> <tr> <td>A</td> <td>WO 2009/008199 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0012] to [0013], [0047] to [0048]; claims 1 to 14 & US 2009/0008605 A1 & US 2009/0008606 A1 & US 2009/0008607 A1 & EP 2166585 A & EP 2166586 A & EP 2166587 A</td> <td>1-20</td> </tr> </tbody> </table>			Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.	A	WO 2009/008356 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0041], [0054], [0282] to [0283]; claims 1 to 17 & EP 2166591 A	1-20	A	WO 2009/008199 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0012] to [0013], [0047] to [0048]; claims 1 to 14 & US 2009/0008605 A1 & US 2009/0008606 A1 & US 2009/0008607 A1 & EP 2166585 A & EP 2166586 A & EP 2166587 A	1-20
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.									
A	WO 2009/008356 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0041], [0054], [0282] to [0283]; claims 1 to 17 & EP 2166591 A	1-20									
A	WO 2009/008199 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0012] to [0013], [0047] to [0048]; claims 1 to 14 & US 2009/0008605 A1 & US 2009/0008606 A1 & US 2009/0008607 A1 & EP 2166585 A & EP 2166586 A & EP 2166587 A	1-20									
<p><input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.</p>											
<p>* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family</p>											
<p>Date of the actual completion of the international search 18 June, 2010 (18.06.10)</p>		<p>Date of mailing of the international search report 29 June, 2010 (29.06.10)</p>									
<p>Name and mailing address of the ISA/ Japanese Patent Office</p>		<p>Authorized officer</p>									
<p>Facsimile No.</p>		<p>Telephone No.</p>									

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2010/056166

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2009/008205 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0064] to [0065] & US 2009/0009065 A1 & US 2009/0009066 A1 & US 2009/0009067 A1 & EP 2166585 A & EP 2166586 A & EP 2166587 A	1-20
A	WO 2009/008215 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0226], [0229], [0232], [0238], [0247] & US 2009/0009065 A1 & US 2009/0009066 A1 & US 2009/0009067 A1 & EP 2166585 A & EP 2166586 A & EP 2166587 A	1-20
A	WO 2009/008200 A1 (Idemitsu Kosan Co., Ltd.), 15 January 2009 (15.01.2009), paragraphs [0012] to [0013], [0293] & US 2009/0008605 A1 & US 2009/0008606 A1 & US 2009/0008607 A1 & EP 2166585 A & EP 2166586 A & EP 2166587 A	1-20
A	JP 2009-504730 A (Gracel Display Inc.), 05 February 2009 (05.02.2009), claim 10; paragraph [0039] & US 2009/0128010 A1 & EP 1922382 A & WO 2007/021117 A1 & KR 10-2007-0021043 A & CN 101243157 A	1-20

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 20020182441 A [0011]
- WO 2005112519 A [0011]
- JP 2003142267 A [0011]
- WO 2007046658 A [0011]
- JP 2006151966 A [0011]
- JP 2005008588 A [0011]
- JP 2005019219 A [0011]
- JP 2005197262 A [0011]
- JP 2004075567 A [0011]
- US 20080224603 A [0011]
- JP 2004281390 A [0011]
- JP 2006045503 A [0011]
- WO 2009008215 A [0011]
- WO 2009008205 A [0011]
- WO 200220693 A [0011]
- JP 2001250690 A [0011]
- JP 2001244075 A [0011]
- JP 2001257074 A [0011]
- JP 10189248 A [0011]
- JP 57051781 A [0033]
- JP 9003448 A [0111]
- JP 2000173774 A [0114]
- US 3112197 A [0197]
- US 3189447 A [0197]
- JP 3716096 B [0197]
- US 3615402 A [0197]
- US 3820989 A [0197]
- US 3542544 A [0197]
- JP 45555 B [0197]
- JP 51010983 B [0197]
- JP 51093224 A [0197]
- JP 55017105 A [0197]
- JP 56004148 A [0197]
- JP 55108667 A [0197]
- JP 55156953 A [0197]
- JP 56036656 A [0197]
- US 3180729 A [0197]
- US 4278746 A [0197]
- JP 55088064 A [0197]
- JP 55088065 A [0197]
- JP 49105537 A [0197]
- JP 55051086 A [0197]
- JP 56080051 A [0197]
- JP 56088141 A [0197]
- JP 57045545 A [0197]
- JP 54112637 A [0197]
- JP 55074546 A [0197]
- US 3615404 A [0197]
- JP 51010105 B [0197]
- JP 46003712 B [0197]
- JP 47025336 B [0197]
- JP 54053435 A [0197]
- JP 54110536 A [0197]
- JP 54119925 A [0197]
- US 3567450 A [0197]
- US 3180703 A [0197]
- US 3240597 A [0197]
- US 3658520 A [0197]
- US 4232103 A [0197]
- US 4175961 A [0197]
- US 4012376 A [0197]
- JP 49035702 B [0197]
- JP 3927577 B [0197]
- JP 55144250 A [0197] [0198]
- JP 56119132 A [0197] [0198]
- JP 56022437 A [0197]
- DE 1110518 [0197]
- US 3526501 A [0197]
- US 257203 A [0197]
- JP 56046234 A [0197]
- JP 54110837 A [0197]
- US 3717462 A [0197]
- JP 54059143 A [0197]
- JP 55052063 A [0197]
- JP 55052064 A [0197]
- JP 55046760 A [0197]
- JP 55085495 A [0197]
- JP 57011350 A [0197]
- JP 57148749 A [0197]
- JP 2311591 A [0197]
- JP 61210363 A [0197]
- JP 61228451 A [0197]
- JP 61014642 A [0197]
- JP 61072255 A [0197]
- JP 62047646 A [0197]
- JP 62036674 A [0197]
- JP 62010652 A [0197]
- JP 62030255 A [0197]
- JP 60093455 A [0197]
- JP 60094462 A [0197]
- JP 60174749 A [0197]
- JP 60175052 A [0197]
- US 4950950 A [0197]
- JP 2204996 A [0197]
- JP 2282263 A [0197]
- JP 1211399 A [0197]
- JP 63295695 A [0198]
- US 4127412 A [0198]

EP 2 418 707 A1

- JP 53027033 A [0198]
- JP 54058445 A [0198]
- JP 54149634 A [0198]
- JP 54064299 A [0198]
- JP 55079450 A [0198]
- JP 61295558 A [0198]
- JP 61098353 A [0198]
- US 5061569 A [0199]
- JP 4308688 A [0199]
- JP 3614405 B [0199]
- JP 3571977 B [0199]
- US 4780536 A [0199]

专利名称(译)	有机电致发光元件和用于有机电致发光元件的材料		
公开(公告)号	EP2418707A4	公开(公告)日	2012-09-19
申请号	EP2010761669	申请日	2010-04-05
[标]申请(专利权)人(译)	出光兴产株式会社		
申请(专利权)人(译)	出光兴产股份有限公司.		
当前申请(专利权)人(译)	出光兴产股份有限公司.		
[标]发明人	IWAKUMA TOSHIHIRO TAKASHIMA YORIYUKI ITO MITSUNORI OGIWARA TOSHINARI		
发明人	IWAKUMA, TOSHIHIRO TAKASHIMA, YORIYUKI ITO, MITSUNORI OGIWARA, TOSHINARI		
IPC分类号	H01L51/50 C07C13/62 C09K11/06 C07F15/00 C07C13/66 H01L51/00 H05B33/14		
CPC分类号	C09K11/06 C07C13/66 C07C2603/40 C07C2603/42 C09K2211/1011 C09K2211/185 H01L51/0058 H01L51/006 H01L51/0081 H01L51/0085 H01L51/5016 H05B33/14		
代理机构(译)	PROP , GERRIT		
优先权	2009092523 2009-04-06 JP		
其他公开文献	EP2418707B1 EP2418707A1		
外部链接	Espacenet		

摘要(译)

一种有机电致发光器件，包括：阴极;阳极;和包括至少一层并设置在阴极和阳极之间的有机薄膜层。至少一层有机薄膜层包括：由下式(1)，(2)和(3)中任一表示的有机电致发光器件材料;和至少一种磷光材料，其中有机电致发光器件材料可以具有取代基。A或Ar可以被苯基或萘基取代。

