



(11) **EP 1 407 500 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
12.11.2008 Bulletin 2008/46

(51) Int Cl.:
H01L 51/50 *(2006.01)* **H01L 51/30** *(2006.01)*
H05B 33/14 *(2006.01)* **C09K 11/06** *(2006.01)*

(21) Application number: **02750024.8**

(86) International application number:
PCT/US2002/022308

(22) Date of filing: **10.07.2002**

(87) International publication number:
WO 2003/007395 (23.01.2003 Gazette 2003/04)

(54) **ELECTROACTIVE POLYMERS AND DEVICES MADE THEREFROM**

ELEKTROAKTIVE POLYMERE UND DARAUS HERGESTELLTE VORRICHTUNGEN

POLYMERES ELECTROACTIFS ET DISPOSITIFS FABRIQUES A PARTIR DE CEUX-CI

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR**

(30) Priority: **10.07.2001 US 304336 P**

(43) Date of publication of application:
14.04.2004 Bulletin 2004/16

(60) Divisional application:
08151070.3 / 1 921 688

(73) Proprietor: **DOW GLOBAL TECHNOLOGIES INC.
Midland MI 48674 (US)**

(72) Inventors:
• **WU, Weishi
Midland, MI 48642 (US)**

- **INBASEKARAN, Michael
Midland, MI 48642 (US)**
- **BERNIUS, Mark, T.
Midland, MI 48640 (US)**
- **O'BRIEN, James, J.
Midland, MI 48640 (US)**

(74) Representative: **Raynor, John et al
Beck Greener
Fulwood House,
12 Fulwood Place,
London WC1V 6HR (GB)**

(56) References cited:
EP-A- 1 149 827 WO-A-00/46321
WO-A-00/55927 WO-A-99/54385
US-A- 5 621 131

EP 1 407 500 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

FIELD OF THE INVENTION

5 **[0001]** The instant invention relates to electroactive polymers, particularly electroluminescent polymers, that are block polymers, and to processes for making such block polymers.

BACKGROUND OF THE INVENTION

10 **[0002]** Highly conjugated polymeric materials have been taught to be useful as semiconductors. See e.g. U.S. Patent 6,204,515. Burroughes et al. discovered that certain conjugated polymeric materials, specifically polyphenylene vinylene (PPV), were electroluminescent and thus could be used in light emitting diodes. Burroughes et al., "Light-emitting diodes used on conjugated polymers " Nature, vol. 347, pp. 539-541, October 1990.

15 **[0003]** Extensive work has occurred since this initial discovery. This work includes use of variations of PPV as well as other types of conjugated polymers - e.g. polythiophenes, polyfluorenes. See e.g. Fukuda, "Synthesis of Fusible and Soluble Conducting polyfluorene Derivatives and their Characteristics" J. of Poly. Sci., vol. 31, pp. 2465-2471, 1993, and U.S. Patent 5,708,130. Polymers containing more than one type of monomer unit have also been taught. See e.g. WO 00/46321. Finally, blends of conjugated polymers have been taught to be especially effective as they may allow adjustment of the overall composition to maximize various desired properties, such as emission wavelength, efficiency, lifetime, etc. Yu et al., "Enhanced electroluminescence from semiconducting polymer blends", Syn. Met. 72 (1995) pp. 249-252; Kim et al., "LED Characterization of an Alternating Copolymer and its Blends" SPIE vol. 3148, pp. 151-158; Tasch et al., "Efficient red- and orange-light emitting diodes realized by excitation energy transfer from blue-light-emitting conjugated polymers" Physical Review B, The American Physical Society, vol. 56, no. 8 (1997) pp. 4479-4483; and U.S. Patent 6,169,163.

25 **[0004]** While some work has been done using block copolymers, these block copolymers have included blocks that are not consistently conjugated along the backbone of the polymer (because at least part of the backbone of the polymer is saturated). See e.g. Heischkel et al. "Synthesis of ABC-triblock copolymers for light emitting diodes" Macromol. Chem. Phys., 199, 869-880 (1998) and Chen et al., "Improved efficiencies of light-emitting diodes through incorporation of charge transporting components in tri-block polymers", Syn. Met. 107 (1999) pp. 203-207 and U.S. Patent publication 2001/0024738A1.

30 **[0005]** Electroluminescent polymer devices can be made as layered systems. For example, a transparent layer of electrically conductive indium-tin oxide can be deposited on a pane of glass as the anode of the device. Then a "hole injection" layer of, for example, polyethylene dioxythiophene, (available under the tradename Baytron P from Bayer Corp.) can be formed on the anode. Then a layer of electroluminescent polymer can be formed on top of the hole injection layer. Then, a layer of an appropriate low work function metal, such as calcium, can be formed on top of the electroluminescent polymer layer as the cathode of the device. When an electrical potential is applied between the cathode and anode, holes or positive charge carriers are injected into the electroluminescent polymer layer from the hole injection layer while electrons or negative charge carriers are injected into the electroluminescent polymer layer from the cathode. The negative charge carriers can combine with the positive charge carriers in the electroluminescent polymer layer to generate light.

35 **[0006]** As disclosed in USP 6,204,515, semiconducting polymer field effect transistors can be prepared by forming a layer of an electrically insulating material on an electrically conducting gate layer. A layer of semiconducting polymer is formed on the layer of electrically insulating material, the layer of semiconducting polymer being in electrical contact with and between the source and drain of the transistor.

40 **[0007]** Towns et al., WO 00/55927, taught a copolymer for use in an electroluminescent device comprised of at least two or more regions along the length of the polymer backbone. The first region is for transporting negative charge carriers. The second region is for transporting positive charge carrier. The third region is for accepting and combining the positive and negative charge carriers to generate light. While mentioning at page 4, second paragraph that the components could be combined in the main chain, side chains, in block or random copolymer form, Towns teaches only how to make random copolymers and exemplifies only random copolymers and only polymers of two different monomers, See Example 5. Towns also indicates that the third component may be present as part of the copolymer or as a separate blended component and in Example 6 blends the random copolymer of Example 5 with another copolymer.

45 **[0008]** The various optimized polymers and polymer blends of Towns et al. are an advance in the art because they tend to optimize the energy levels and bandgap of the polymers and polymer blends. However, it would be a further advance in the art of electroluminescent polymers if the brightness, energy efficiency and lifetime of electroluminescent devices made from electroluminescent polymers could be further improved.

SUMMARY OF THE INVENTION

[0009] Applicants have found that certain specifically designed block polymers surprisingly function better in electroluminescent devices (better brightness, energy efficiency and lifetime) than: (a) random polymers of the same monomers; or (b) blends of random polymers of the same monomers.

[0010] More specifically, the instant invention is an organic block polymer useful in an electroluminescent polymer device, comprising: (a) an emissive polymer block that is consistently conjugated along the backbone of the emissive polymer block (e.g., a copolymer of 2,7-linked 9,9 dioctyl fluorene and 4,7-linked 2,1,3-benzothiadiazole); and at least one of the following: (b) a positive charge carrier polymer block that is consistently conjugated along the backbone of the positive charge carrier polymer block (e.g., a copolymer of 2,7-linked 9,9-dioctylfluorene and 4, 4'-linked N,N'-di(3-carbomethoxyphenyl)benzidine) for transporting positive charge carriers to the emissive polymer block so that the positive charge carriers can combine with negative charge carriers to generate light, (c) a negative charge carrier polymer block that is consistently conjugated along the backbone of the negative charge carrier polymer block for transporting negative charge carriers to the emissive polymer block so that the negative charge carriers can combine with positive charge carriers to generate light, and (d) a host polymer block that is consistently conjugated along the backbone of the host block for providing a matrix for emitter that affords Forster energy transfer and minimization of concentration quenching effects.

[0011] In another embodiment the instant invention is an improved electroluminescent polymer device that includes an anode, a cathode and an electroluminescent polymer positioned between the anode and the cathode, wherein the improvement comprises: the electroluminescent polymer being an organic block polymer comprising an emissive polymer block that is consistently conjugated along the backbone of the emissive polymer block and a positive charge carrier polymer block that is consistently conjugated along the backbone of the positive charge carrier polymer block.

[0012] In yet another embodiment, the instant invention is an improved semiconducting polymer field effect transistor that includes a semiconducting polymer positioned between and in electrical contact with a drain and a source, wherein the improvement comprises: the semiconducting polymer being an organic block polymer comprising an emissive polymer block that is consistently conjugated along the backbone of the emissive polymer block and a positive charge carrier polymer block that is consistently conjugated along the backbone of the positive charge carrier polymer block.

[0013] In yet another embodiment, this invention is a method of making the above copolymers by synthesizing the blocks sequentially in time or by separately synthesizing the blocks followed by combination and reaction of the blocks.

DETAILED DESCRIPTION OF THE INVENTION

[0014] In its broadest scope, the instant invention is an organic block polymer useful in an electroluminescent polymer device, comprising: (a) an emissive polymer block that is consistently conjugated along the backbone of the emissive polymer block for facilitating the recombination of the charge carriers forming the excited singlet state (exciton) and the subsequent relaxation of the excitons to the ground state with emission of light; and (b) a positive charge carrier polymer block that is consistently conjugated along the backbone of the positive charge carrier polymer block for transporting positive charge carriers to the emissive polymer block so that the positive charge carriers can combine with negative charge carriers to generate light. The term "block polymer" means a polymer whose backbone is made up of at least one section or block of one chemical composition connected to at least another section or block of a different chemical composition. Each such section or block can be comprised of one or more monomer groups. The term "consistently conjugated" means that there is essentially no monomer group in the backbone of the block that does not contain conjugated double bonds.

[0015] A "block polymer" is also defined herein by the process used to make it. The blocks of a block polymer are polymerized at different times or in different locations at the same time or at different times. In contrast, a random polymer, comprised of one or more monomer groups, is generally polymerized at one time and in one location.

[0016] The emissive polymer block of the instant invention comprises at least a first monomer group selected from those monomer groups known in the art for this function (see, for example WO00/55927, PCT/GB99/00741, USP 5,777,070, USP 6,169,163, USP 5,962,631 and USP 5,708,130 and includes substituted or unsubstituted aromatic or heteroaromatic groups, and more particularly polyarylene vinylenes, thiophenes and fluorenes, used alone or in combination. Particularly preferred are fluorene monomer groups and alternating or random copolymers of fluorene, such as a 2,7-linked dialkyl fluorene (e.g., 9,9-dioctyl fluorene or 9,9-dihexyl fluorene) with a second substituted or unsubstituted aromatic or heteroaromatic monomer group such as a polycyclic aromatic group (e.g., naphthalene or anthracene) or an aromatic or heteroaromatic diazine group fused to a benzene or thiophene group (e.g., a 2,7-linked 2,1,3-benzothiadiazole). When selecting such particularly preferred emissive blocks, the weight ratio of the first to the second monomer should be at least 1:99, more preferably at least 3:97, more preferably still at least 5:95, and most preferably at least 15:85. However, when selecting such particularly preferred emissive blocks, the weight ratio of the first to the second monomer should be no more than 50:50, more preferably no more than 40:60, and most preferably no more

than 30:70. The mole ratio for the first to second monomers is preferably at least 10:90, more preferably at least 20:80. The mole ratio for the first to second monomer is preferably less than 90:10, more preferably less than 80:20. In many instances, alternating copolymers function well as the emissive block.

[0017] The positive charge carrier polymer block of the instant invention comprises a third monomer selected from those monomer groups known in the art for this function (see, for example PCT/GB00/00911, PCT/GB99/00741, USP 5,777,070, USP 6,169,163, USP 5,962,631 and USP 5,708,130) and includes substituted or unsubstituted aromatic or heteroaromatic groups, and more particularly polyarylene vinylenes, thiophenes and fluorenes, used alone or in combination. Particularly preferred are fluorene monomer groups and alternating or random copolymers of fluorene, such as a 2,7-linked dialkyl fluorene (e.g., 9,9 dioctyl fluorene or 9,9 dihexyl fluorene) with a substituted or unsubstituted aromatic or heteroaromatic fourth monomer such as a 1,4-diene without electron-withdrawing substituents, tertiary amines, N,N,N',N'-tetraaryl-1,4-diaminobenzene, N,N,N',N'-tetraarylbenzidine, N-substituted-carbazoles, diarylsilanes, and thiophenes/furans/pyrroles without electron-withdrawing substituents. It may be desirable to substitute the third monomer group with a substituent selected from the group consisting of C₁₋₂₀ alkyls, C₆₋₂₀ aryls and alkylaryls optionally substituted with C₁₋₆ alkoxys and C₆₋₁₂ aryloxys. A preferred fourth monomer comprises a triarylamine group having the general formula -Ar₃N- wherein each Ar is the same or different and comprises a substituted or unsubstituted aromatic or heteroaromatic group. A preferred fourth monomer group is N,N'-di(3-carboxomethoxyphenyl)benzidine. Another preferred fourth monomer group is N,N'-di(4-methoxyphenyl)1,4-phenylenediamine. When selecting such particularly preferred positive charge carrier blocks, the weight ratio of the third to the fourth monomer should be at least 5:95, more preferably at least 10:90, and most preferably at least 15:85. However, when selecting such particularly preferred positive charge carrier blocks, the weight ratio of the third to the fourth monomer should be no more than 50:50, more preferably no more than 40:60, and most preferably no more than 20:80. The mole ratio for the third to fourth monomers is preferably at least 10:90, more preferably at least 20:80. The mole ratio for the third to fourth monomer is preferably less than 90:10, more preferably less than 80:20. In many instances, alternating copolymers function well as the positive charge carrier block.

[0018] In another embodiment of the instant invention the organic block polymer discussed above can further comprise a wide band gap host polymer block that is consistently conjugated along the backbone of the host polymer block. The host polymer block may perform one or more of the following functions: enable utilization of Forster energy transfer to the narrow band gap emissive polymer block, facilitate transport of charge carriers (electrons or holes), inhibit or limit concentration quenching (also known as dipole-dipole induced light quenching), facilitate charge injection from the adjacent layers (e.g. anode, cathode, hole transport layer, etc.), facilitate attaining a balance of holes and electrons, facilitate morphology control (e.g. glass transition temperature, T_g; phase separation, etc.), and enhance color tuning. The host polymer block of the instant invention comprises a fifth monomer selected from those monomer groups known in the art for this function (see, for example PCT/GB00/00911, PCT/GB99/00741, USP 5,777,070, USP 6,169,163, USP 5,962,631 and USP 5,708,130) and includes substituted or unsubstituted aromatic or heteroaromatic groups, and more particularly polyarylene vinylenes, thiophenes and fluorenes, used alone or in combination. Particularly preferred are fluorene monomer groups and alternating or random copolymers of fluorene, such as a 2,7-linked dialkyl fluorene (e.g., 9,9 dioctyl fluorene or 9,9 dihexyl fluorene) with a substituted or unsubstituted aromatic or heteroaromatic sixth monomer such as (when positive charge carrier properties are desired) a stilbene or 1,4-diene without electron-withdrawing substituents, tertiary amines, N,N,N',N'-tetraaryl-1,4-diaminobenzene, N,N,N',N'-tetraarylbenzidine, N-substituted-carbazoles, diarylsilanes, and thiophenes/furans/pyrroles without electron-withdrawing substituents. It may be desirable to substitute the sixth monomer group with a substituent selected from the group consisting of C₁₋₂₀ alkyls, C₆₋₂₀ aryls and alkylaryls optionally substituted with C₁₋₆ alkoxys and C₆₋₁₂ aryloxys. A preferred sixth monomer comprises a triarylamine group having the general formula -Ar₃N- wherein each Ar is the same or different and comprises a substituted or unsubstituted aromatic or heteroaromatic group. A preferred sixth monomer group is N,N'-di(3-carboxomethoxyphenyl)benzidine. Another preferred sixth monomer group is N,N'-di(4-methoxyphenyl)1,4-phenylenediamine. When selecting such particularly preferred host blocks, the weight ratio of the fifth to the sixth monomer should be at least 5:95, more preferably at least 10:90, and most preferably at least 15:85. However, when selecting such particularly preferred host blocks, the weight ratio of the fifth to the sixth monomer should be no more than 50:50, more preferably no more than 40:60, and most preferably no more than 20:80. The mole ratio for the fifth to sixth monomers is preferably at least 10:90, more preferably at least 20:80. The mole ratio for the fifth to sixth monomer is preferably less than 90:10, more preferably less than 80:20.

[0019] When negative charge carrier properties are desired, the host polymer block may instead have a sixth monomer with an electron withdrawing group or a negative charge carrying block comprising an electron withdrawing group may be used. Such electron withdrawing group can be selected from the group consisting of F, cyano, sulfonyl, carboxy; moieties containing an imine linkage, condensed polycyclic aromatics such as acenaphthene, phenanthrene, anthracene, fluoranthene, pyrene, perylene, rubrene, chrysene, and corene as well as five-membered heterocycles containing imine linkages include oxazoles/isoxazoles, N-substituted-imidazoles/pyrazoles, thiazole/isothiazole, oxadiazoles, and N-substituted-triazoles and six-membered heterocycles containing imine linkages such as pyridines, pyridazines, pyrimidines,

pyrazines, triazines, and tetrazenes as well as benzo-fused heterocycles containing imine linkages include benzoxazoles, benzothiazole, benzimidazoles, quinoline, isoquinolines, cinnolines, quinazolines, quinoxalines, phthalazines, benzothiadiazoles, benzotriazines, phenazines, phenanthridines, and, acridines.

[0020] Preferably, the monomer groups of the emissive block polymer of the instant invention are essentially not comprised of a stilbene or 1,4-diene without electron-withdrawing substituents, tertiary amines, N,N,N',N'-tetraaryl-1,4-diaminobenzene, N,N,N',N'-tetraarylbenzidine, N-substituted-carbazoles, diarylsilanes, and thiophenes/furans/pyrroles without electron-withdrawing substituents. Preferably, the monomer groups of the emissive polymer block are essentially not comprised of a triarylamine group having the general formula $-Ar_3N-$ wherein each Ar is the same or different and comprises a substituted or unsubstituted aromatic or heteroaromatic group such as N,N'-di(3-carboxomethoxyphenyl) benzidine or N,N'-di(4-methoxyphenyl)1,4-phenylenediamine. When selecting such particularly preferred negative charge carrier blocks, the weight ratio of the fifth to the sixth monomer should be at least 5:95, more preferably at least 10:90, and most preferably at least 15:85. However, when selecting such particularly preferred host blocks, the weight ratio of the fifth to the sixth monomer should be no more than 50:50, more preferably no more than 40:60, and most preferably no more than 20:80. The mole ratio for the fifth to sixth monomers is preferably at least 10:90, more preferably at least 20:80. The mole ratio for the first to second monomers is preferably at least 10:90, more preferably at least 20:80. The mole ratio for the first to second monomer is preferably less than 90:10, more preferably less than 80:20. The mole ratio for the first to second monomer is preferably less than 90:10, more preferably less than 80:20.

[0021] The weight ratio of the emissive block to the positive charge carrier block is preferably at least 5:95, more preferably at least 10:90 and most preferably at least 15:85. On the other hand, the weight ratio of the emissive block to the positive charge carrier block is preferably no more than 90:10, more preferably no more than 80:20 and most preferably no more than 70:30. The weight ratio of any host block used in the instant invention to the total weight of the block polymer is preferably at least 5:95, more preferably at least 10:90 and most preferably at least 15:85. On the other hand, the weight ratio of such host block to the total weight of the block polymer is preferably no more than 90:10, more preferably no more than 80:20 and most preferably no more than 70:30.


[0022] The host block, when used, preferably comprises at least 10, more preferably at least 30, and most preferably at least 40 mole% of the monomeric units in the copolymer. The host polymer preferably comprises less than 99, more preferably less than 90, more preferably still less than 80, and most preferably less than 70 mole% of the monomeric units of the block copolymer. Additional blocks, preferably comprise cumulatively not more than 89, more preferably not more than 50, most preferably not more than 30 mole% of the total moles of monomeric units in the copolymer.

[0023] The organic block polymers of the instant invention may be made by modifying any preparative method that is suitable for aromatic coupling polymerizations. Suzuki polymerization disclosed for example in U.S. Patent 5,777,070 is a preferred method for forming the block segments and block polymers of the instant invention. In this method, dibromo functionalized monomers are reacted with diboronate functional monomers in the presence of a base, a phase transfer catalyst, and a catalytic amount of a palladium complex. The blocks may be assembled either by first forming one block, then adding the monomers for the second block to the reaction mixture, followed by sequential addition of monomers for additional blocks if desired. Alternatively, each block may first be assembled separately and then reacted with other blocks prepared in the same manner to form the desired block polymer with two or more distinct block regions. In either of these processes, the averaged block length may be tuned by control of monomer stoichiometry, base addition, or acid addition.


[0024] The organic block polymers of the instant invention can be used in a polymeric light emitting diode, as the photoconverter in a photodiode or as the semiconductor in a polymer field effect transistor.

EXAMPLE 1 (DIBLOCK BLUE EMITTER)


[0025] To a stirred solution of 2,7-dibromo-9,9-dihexylfluorene (3.18 g, 6.46 mmol), 9,10-dibromoanthracene (114 mg, 0.34 mmol), and 9,9-dihexylfluorene-2,7-bisboronate (3.32 g, 7 mmol) in 60 mL of toluene under nitrogen is added Aliquat 336 (phase transfer catalyst, registered trademark of Henkel Corporation) (1.5 g), tetrakis(triphenylphosphine)palladium (8.6 mg) and 2M sodium carbonate (20 mL). After refluxing and stirring for 24 hours, another 50 mL of toluene was added and heated another 3 hours to obtain AN5 emitting block as a clear solution in toluene. The following formula is for the AN5 emitting block.



[0026] To the above solution was added compound of the formula




(at 1.162 g, 1.47 mmol), and compound of the formula



R_8 = methoxy

(at 1.091 g, 1.73 mmol) and 9,9-dihexylfluorene-2,7-bisboronate (1.518 g) along with Aliquat 336 (phase transfer catalyst) (0.6 g) and tetrakis(triphenylphosphine)palladium (8 mg) and the reaction continued for 13 hours. Di-bromo BFE has the formula:

[0027] The diblock polymer was end capped with 0.5 g of phenylboronic acid for 8 hours of refluxing and isolated as pale yellow fibers (6 g) by precipitating from 2L of methanol. Further purification and additional precipitation led to pure polymer which weighed 5.74 g and had an inherent viscosity of 2.04 dL/g (THF, 25 °C, 0.5 g/dL). The following formula is for the positive charge carrier block.




[0028] The above-described block polymer is used in a standardized polymer light emitting diode device prepared by depositing a layer of Baytron P polyethylene dioxythiophene on an indium-tin oxide coated pane of glass, followed by a layer of the block polymer as prepared in this Example, followed by a layer of calcium. The efficiency of the device at 100 Cd/meter² brightness is 1.3 Cd/Ampere. The half-life of the device is 50 hours at 100 Cd/meter². A maximum brightness of 2,170 Cd/meter² is obtained at 18 volts and at a current density of 400 mA/cm².

COMPARATIVE EXAMPLE 1 (RANDOM BLUE)


[0029] Example 1 is repeated except that all the monomers are reacted at one time for 36 hours. The resulting random co-polymer has an inherent viscosity of 0.85 dL/g. The random co-polymer is used in a standardized polymer light emitting diode device prepared by depositing a layer of polyethylene dioxythiophene on an indium-tin oxide coated pane of glass, followed by a layer of the block polymer, followed by a layer of calcium. The efficiency of the device at 100 Cd/meter² brightness is 0.4 Cd/Ampere. The half-life of the device is less than one minute at 100 Cd/meter². A maximum brightness of 1190 Cd/meter² is obtained at 15 volts and at a current density of 400 mA/cm².

EXAMPLE 2 (TRI-BLOCK GREEN)


[0030] To a stirred solution of 2,7-bis(1,3,2-dioxaborolan-2-yl)-9,9-dioctylfluorene (99.4%, 2.45 g, 4.59 mmol), 4,7-dibromo-2,1,3-benzothiadiazole (1.35 g, 4.59 mmol) in toluene (38 mL), under nitrogen is added Aliquat 336 (0.64 g), tetrakis(triphenylphosphine)palladium (6.0 mg, 5.2 micromol, 0.11 mol%) and aqueous sodium carbonate (2 M, 4.8 mL). The reaction is stirred and heated in an oil-bath at 95 °C for 16 hr. An orange, viscous solution of the emissive polymer block is obtained. The following formula is for the emitting block:



[0031] To the above solution was added 2,7-bis(1,3,2-dioxaborolan-2-yl)-9,9-dihexylfluorene (7.43 g, 15.57 mmol), 2,7-dibromo-9,9-dihexylfluorene (7.30 g, 14.83 mmol), 4,4'-dibromostilbene (0.25 g, 0.74 mmol), aqueous sodium carbonate (2 M, 32 mL), phase-transferrin reagent Aliquat 336 (2.2 g), and tetrakis(triphenylphosphine) palladium (9.0 mg, 7.8 micromol), and toluene (100 mL). The reaction was allowed to go for 8 hr. The formula of the host block is given as following.



[0032] To above is added with 2,7-bis(1,3,2-dioxaborolan-2-yl)-9,9-dioctylfluorene (99.4%, 2.01 g, 3.77 mmol), N,N'-di(4-bromophenyl)-N,N'-di(3-ethoxycarbonylphenyl)-benzidine (99.4%, 2.62 g, 3.30 mmol), aqueous sodium carbonate (2 M, 8 mL), phase-transferring reagent Aliquat 336 (0.6 g), and tetrakis(triphenylphosphine) palladium (3 mg, 0.0026), and toluene (25 mL). The reaction is allowed to go for 14 hr to add the positive charge carrier block to the host block as given below.



[0033] The tri-block polymer was end capped with 0.25 g of phenylboronic acid for 8 hours of refluxing and isolated as yellow fibers by precipitating from 4 L of methanol. Further purification and additional precipitation led to pure polymer, which weighed 11.4 g and had an inherent viscosity of 2.06 dL/g (THF, 25 °C, 0.5 g/dL).

[0034] The above-described block polymer is used in a standardized polymer light emitting diode device prepared by depositing a layer of polyethylene dioxythiophene on an indium-tin oxide coated pane of glass, followed by a layer of the block polymer, followed by a layer of calcium. The efficiency of the device at 200 Cd/meter² brightness is 5.0 Cd/Ampere.

EXAMPLE 3 (TRI-BLOCK GREEN)


[0035] To a 250 mL flask is charge with 2,7-bis(1,3,2-dioxaborolan-2-yl)-9,9-dioctylfluorene (99.4%, 2.45 g, 4.59 mmol), 4,7-dibromo-2,1,3-benzothiadiazole (1.35 g, 4.59 mmol), Aliquat 336 (0.6 g), tetrakis(triphenylphosphine)palladium (6.0 mg, 5.2 micromol), aqueous sodium carbonate (2 M, 4.6 mL) and toluene (40 mL). The reaction is stirred and heated in an oil-bath at 95 °C under nitrogen for 14 hours. A red-orange viscous solution was observed. The stirring is

then stopped, and the solution of emissive block polymer is kept at 50 °C under nitrogen.

[0036] To a separated 250 mL flask is charged with 2,7-bis(1,3,2-dioxaborolan-2-yl)-9,9-dioctylfluorene (BF9914, 99.4%, 1.76 g, 3.30 mmol), N,N'-di(4-bromophenyl)-N,N'-di(3-Ethoxycarbonylphenyl)-benzidine (99.4%, 2.62 g, 3.30 mmol), Aliquat 336 (0.5 g), tetrakis(triphenylphosphine) palladium (4.3 mg, 3.7 micromol), aqueous sodium carbonate (2 M, 3.3 mL) in toluene (30 mL) and toluene (30 mL). The reaction is stirred and heated in an oil-bath under nitrogen at 95 °C for 14 hours. A light-brown viscous solution of positive charge carrier block polymer is observed. The stirring is then stopped, and the solution is kept at 50 °C under nitrogen.

[0037] To a 500 mL flask is charged with 2,7-bis(1,3,2-dioxaborolan-2-yl)-9,9-dioctylfluorene (99.4%, 7.11 g, 13.33 mmol), 2,7-dibromo-9,9-dioctylfluorene (7.31 g, 13.33 mmol), aqueous sodium carbonate (2 M, 33 mL), Aliquat 336 (2.2 g), and tetrakis(triphenylphosphine) palladium (9.5 mg, 8.2 micromol) and toluene (90 mL). The reaction is allowed to proceed for 14 hours. A light-brown viscous solution of host polymer block is observed.

[0038] To the host polymer block flask above emissive block polymer solution and positive charge carrier block polymer solutions are transferred, each with 15 mL of toluene and more 2,7-bis(1,3,2-dioxaborolan-2-yl)-9,9-dioctylfluorene (99.4%, 0.23 g, 0.42 mmol) and tetrakis(triphenylphosphine) palladium (1.0 mg) are added. The reaction is allowed to proceed for 16 hours. After which phenylboronic acid (0.2 g) and toluene (50 mL) are added and the stirring is continued for another 8 hours. At the end of the reaction a very viscous orange-colored solution of tri-block polymer is observed. The product was isolated as yellow fibers by precipitating from 4 L of methanol. Further purification and additional precipitation led to pure polymer, which weighed 12.0 g. The formula of the tri-block polymer is given as following.



[0039] The above-described block polymer is used in a standardized polymer light emitting diode device prepared by depositing a layer of polyethylene dioxythiophene on an indium-tin oxide coated pane of glass, followed by a layer of the block polymer, followed by a layer of calcium. The efficiency of the device at 200 Cd/meter² brightness is 6.0 Cd/Ampere.

EXAMPLE 5 (DI-BLOCK GREEN)




[0040] The experiment of Example 2 is repeated except that the host and positive charge carrier monomers are charged together at the same time. The resulting di-block polymer is used in a standardized polymer light emitting diode device prepared by depositing a layer of polyethylene dioxythiophene on an indium-tin oxide coated pane of glass, followed by a layer of the block polymer, followed by a layer of calcium. The efficiency of the device at 200 Cd/meter² brightness is 6.5 Cd/Ampere.

COMPARATIVE EXAMPLE 2 (RANDOM GREEN)

[0041] The experiment of Example 2 is repeated except that all of the monomers are charged together at the same time. The resulting random polymer is used in a standardized polymer light emitting diode device prepared by depositing a layer of polyethylene dioxythiophene on an indium-tin oxide coated pane of glass, followed by a layer of the block polymer, followed by a layer of calcium.

EXAMPLE 6

[0042] Random and block copolymer red emitters were prepared from the following monomers: 9,9 alkyl substituted fluorenes.



R7 = methyl

[0043] While devices made with these polymers displayed similar initial luminescence values, the block copolymer was easier to process and displayed significant lifetime benefits over the random copolymer.

Claims

1. An electroluminescent organic block polymer useful in an electroluminescent polymer device, comprising:

(a) an emissive polymer block with essentially no monomer group that does not contain conjugated double bonds in the backbone of the block; and at least one of the following:

(b) a positive charge carrier polymer block with essentially no monomer group that does not contain conjugated double bonds in the backbone of the block, transporting positive charge carriers to the emissive polymer block so that the positive charge carriers can combine with negative charge carriers to generate light,

(c) a negative charge carrier polymer block with essentially no monomer group that does not contain conjugated double bonds in the backbone of the block, transporting negative charge carriers to the emissive polymer block so that the negative charge carriers can combine with positive charge carriers to generate light, and

(d) a host polymer block with essentially no monomer group that does not contain conjugated double bonds in the backbone of the block, providing a matrix for emitter that affords Forster energy transfer and minimization of concentration quenching effects.

2. The organic block polymer of Claim 1, wherein the emissive polymer block comprises a first monomer comprising a substituted or unsubstituted aromatic or heteroaromatic group.

3. The organic block polymer of Claim 2, wherein the first monomer comprises a substituted or unsubstituted fluorene group.

4. The organic block polymer of Claim 3, wherein the first monomer comprises a 2,7-linked dialkyl fluorene group.

5. The organic block polymer of Claim 4, wherein the 2,7-linked dialkyl fluorene group is selected from the group consisting of a 9,9-dioctyl fluorene group and a 9,9-dihexyl fluorene group.

6. The organic block polymer of Claims 2-5, wherein the emissive polymer block comprises a second monomer comprising a substituted or unsubstituted aromatic or heteroaromatic group.

7. The organic block polymer of Claim 6, wherein the second monomer comprises a substituted or unsubstituted polycyclic aromatic group.

8. The organic block polymer of Claim 7, wherein the substituted or unsubstituted polycyclic aromatic group is naphthalene or anthracene.

9. The organic block polymer of Claim 6, wherein the second monomer comprises an aromatic or heteroaromatic diazine group fused to a benzene or thiophene group.
- 5 10. The organic block polymer of Claim 9, wherein the aromatic or heteroaromatic diazine group fused to a benzene or thiophene group is a 2,7-linked 2,1,3 benzothiadiazole.
11. The organic block polymer of Claims 1-10, wherein the positive charge carrier polymer block (b) is present and comprises a third monomer comprising a substituted or unsubstituted aromatic or heteroaromatic group.
- 10 12. The organic block polymer of Claim 11, wherein the third monomer comprises a substituted or unsubstituted fluorene group.
13. The organic block polymer of Claim 12, wherein the third monomer comprises a 2, 7-linked dialkyl fluorene group.
- 15 14. The organic block polymer of Claim 13, wherein the 2,7-linked dialkyl fluorene group is selected from the group consisting of a 9,9-dioctyl fluorene group and a 9,9 dihexyl fluorene group.
15. The organic block polymer of Claims 11-14, wherein the positive charge carrier polymer block comprises a fourth monomer comprising a substituted or unsubstituted aromatic or heteroaromatic group.
- 20 16. The organic block polymer of Claim 15, wherein the fourth monomer comprises a stilbene or 1,4-diene without electron-withdrawing substituents, tertiary amines, N,N,N',N'-tetraaryl-1,4-diaminobenzene, N,N,N',N'-tetraarylbenzidine, N-substituted-carbazoles, diarylsilanes, and thiophenes/furans/pyrroles without electron-withdrawing substituents.
- 25 17. The organic block polymer of Claim 16, wherein the fourth monomer is substituted with a substituent selected from the group consisting of C₁₋₂₀ alkyls, C₆₋₂₀ aryls and alkylaryls optionally substituted with C₁₋₆ alkoxy and C₆₋₁₂ aryloxy.
- 30 18. The organic block polymer of Claim 15, wherein the fourth monomer comprises a triarylamine group having the general formula -Ar₃N- wherein each Ar is the same or different and comprises a substituted or unsubstituted aromatic or heteroaromatic group.
- 35 19. The organic block polymer of Claim 18, wherein the triarylamine group is N,N'-di-(3-carboxymethoxyphenyl) benzidine.
20. The organic block polymer of Claim 18, wherein the triarylamine group is N,N'-di-(3-oxymethoxyphenyl) benzidine.
- 40 21. The organic block polymer of Claims 1-20, wherein the host polymer block (d) is present.
22. The organic block polymer of Claim 21, wherein the host polymer block comprises a fifth monomer comprising a substituted or unsubstituted aromatic or heteroaromatic group.
- 45 23. The organic block polymer of Claim 22, wherein the fifth monomer comprises a 2,7-linked dialkyl fluorene group.
24. The organic block polymer of Claim 23, wherein the 2,7-linked dialkyl fluorene group is selected from the group consisting of a 9,9-dioctyl fluorene group and a 9,9 dihexyl fluorene group.
- 50 25. The organic block polymer of Claims 21-24, wherein the host polymer block comprises a sixth monomer comprising a substituted or unsubstituted aromatic or heteroaromatic group.
- 55 26. The organic block polymer of Claim 25, wherein the sixth monomer comprises a stilbene or 1,4-diene without electron-withdrawing substituents, tertiary amines, N,N,N',N'-tetraaryl-1,4-diaminobenzene, N,N,N',N'-tetraarylbenzidine, N-substituted-carbazoles, diarylsilanes, and thiophenes/furans/pyrroles without electron-withdrawing substituents.
27. The organic block polymer of Claim 26, wherein the sixth monomer is substituted with a substituent selected from the group consisting of C₁₋₂₀ alkyls, C₆₋₂₀ aryls and alkylaryls optionally substituted with C₁₋₆ alkoxy and C₆₋₁₂ aryloxy.

aryloxys.

28. The organic block polymer of Claim 26, wherein the sixth monomer comprises a triarylamine group having the general formula $-Ar_3N-$ wherein each Ar is the same or different and comprises a substituted or unsubstituted aromatic or heteroaromatic group.
29. The organic block polymer of Claim 28, wherein the triarylamine group is N,N'-di- (3-carboxymethoxyphenyl) benzidine.
30. The organic block polymer of Claim 28, wherein the triarylamine group is N,N'-di- (4-methoxyphenyl) phenylenediamine.
31. The organic block polymer of Claim 25, wherein the sixth monomer is substituted with an electron withdrawing group.
32. The organic block polymer of Claim 31, wherein the electron withdrawing group is selected from the group consisting of F, cyano, sulfonyl, carboxy; moieties containing an imine linkage, condensed polycyclic aromatics such as acenaphthene, phenanthrene, anthracene, fluoranthene, pyrene, perylene, rubrene, chrysene, and corene as well as five-membered heterocycles containing imine linkages including oxazoles/isoxazoles, N-substituted-imidazoles/pyrazoles, thiazole/isothiazole, oxadiazoles, and N-substituted-triazoles and six-membered heterocycles containing imine linkages such as pyridines, pyridazines, pyrimidines, pyrazines, triazines, and tetrazines as well as benzofused heterocycles containing imine linkages including benzoxazoles, benzothiazole, benzimidazoles, quinoline, isoquinolines, cinnolines, quinazolines, quinoxalines, phthalazines, benzothiadiazoles, benzotriazines, phenazines, phenanthridines, and, acridines.
33. The organic block polymer of Claims 1-10, wherein the monomer groups of the emissive polymer block are essentially not comprised of a stilbene or 1,4-diene without electron-withdrawing substituents, tertiary amines, N,N,N',N'-tetraaryl 1,4-diaminobenzene, N,N,N',N'-tetraarylbenzidine, N-substituted-carbazoles, diarylsilanes, and thiophenes/furans/pyrroles without electron-withdrawing substituents.
34. The organic block polymer of Claims 1-10, wherein the monomer groups of the emissive polymer block are essentially not comprised of a triarylamine group having the general formula $-Ar_3N-$ wherein each Ar is the same or different and comprises a substituted or unsubstituted aromatic or heteroaromatic group.
35. The organic block polymer of Claims 21-32, wherein the monomer groups of the emissive polymer block are essentially not comprised of a stilbene or 1,4-diene without electron-withdrawing substituents, tertiary amines, N,N,N',N'-tetraaryl 1,4-diaminobenzene, N,N,N',N'-tetraarylbenzidine, N-substituted-carbazoles, diarylsilanes, and thiophenes/furans/pyrroles without electron-withdrawing substituents.
36. The organic block polymer of Claims 21-32, wherein the monomer groups of the emissive polymer block are essentially not comprised of a triarylamine group having the general formula $-Ar_3N-$ wherein each Ar is the same or different and comprises a substituted or unsubstituted aromatic or heteroaromatic group.
37. An electroluminescent polymer device comprising an anode, a cathode and the electroluminescent organic block polymer of any of the preceding claims positioned between the anode and the cathode.
38. A polymer field effect transistor that includes the electroluminescent organic block polymer of any of claims 1-36 positioned between and in electrical contact with a drain and a source.
39. A process of making the block polymers of Claim 1 by reacting the monomers to build individual blocks separately and then combining and reacting the individual blocks to form a single component block polymer.
40. A process of making the block polymers of Claim 1 by reaction of a first set of monomers to form the first block, followed by sequentially adding and reacting additional sets of monomers for each subsequent block to form a single component block polymer.

Patentansprüche

1. Elektrolumineszentes organisches Blockpolymer, verwendbar in einer elektrolumineszenten Polymervorrichtung, umfassend:

(a) einen emittierenden Polymerblock, welcher im Wesentlichen keine Monomergruppe aufweist, die keine konjugierten Doppelbindungen im Gerüst des Blocks enthält; und mindestens eines der folgenden:

(b) einen Polymerblock mit positiven Ladungsträgern, welcher im Wesentlichen keine Monomergruppe aufweist, die keine konjugierten Doppelbindungen im Gerüst des Blocks enthält, und welcher positive Ladungsträger auf den emittierenden Polymerblock überträgt, so dass die positiven Ladungsträger mit negativen Ladungsträgern kombinieren können, um Licht zu erzeugen;

(c) einen Polymerblock mit negativen Ladungsträgern, welcher im Wesentlichen keine Monomergruppe aufweist, die keine konjugierten Doppelbindungen im Gerüst des Blocks enthält, und welcher negative Ladungsträger auf den emittierenden Polymerblock überträgt, so dass die negativen Ladungsträger mit positiven Ladungsträgern kombinieren können, um Licht zu erzeugen; und

(d) einen Wirtspolymerblock, welcher im Wesentlichen keine Monomergruppe aufweist, die keine konjugierten Doppelbindungen im Gerüst des Blocks enthält, und welcher eine Matrix für Emitter bereitstellt, die Foster-Energietransfer und Minimierung von Konzentrationsquenching-Effekten ermöglicht.

2. Organisches Blockpolymer gemäß Anspruch 1, wobei der emittierende Polymerblock ein erstes Monomer umfasst, umfassend einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest.

3. Organisches Blockpolymer gemäß Anspruch 2, wobei das erste Monomer einen substituierten oder unsubstituierten Fluorenrest umfasst.

4. Organisches Blockpolymer gemäß Anspruch 3, wobei das erste Monomer einen 2,7-verknüpften Dialkylfluorenrest umfasst.

5. Organisches Blockpolymer gemäß Anspruch 4, wobei der 2,7-verknüpfte Dialkylfluorenrest aus einer 9,9-Dioctylfluorengruppe und einer 9,9-Dihexylfluorengruppe ausgewählt ist.

6. Organisches Blockpolymer gemäß einem Ansprüche 2 bis 5, wobei der emittierende Polymerblock ein zweites Monomer umfasst, umfassend einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest.

7. Organisches Blockpolymer gemäß Anspruch 6, wobei das zweite Monomer einen substituierten oder unsubstituierten polycyclischen aromatischen Rest umfasst.

8. Organisches Blockpolymer gemäß Anspruch 7, wobei der substituierte oder unsubstituierte polycyclische aromatische Rest Naphthalin oder Anthrazin ist.

9. Organisches Blockpolymer gemäß Anspruch 6, wobei das zweite Monomer einen aromatischen oder heteroaromatischen Diazinrest, kondensiert an eine Benzoyl- oder Thiophengruppe, umfasst.

10. Organisches Blockpolymer gemäß Anspruch 9, wobei der aromatische oder heteroaromatische Diazinrest, kondensiert an einen Benzol- oder Thiophenrest, ein 2,7-verknüpftes 2,1,3-Benzothiadiazol ist.

11. Organisches Blockpolymer gemäß einem der Ansprüche 1 bis 10, wobei der Polymerblock mit positiven Ladungsträgern (b) vorhanden ist und ein drittes Monomer umfasst, umfassend einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest.

12. Organisches Blockpolymer gemäß Anspruch 11, wobei das dritte Monomer einen substituierten oder unsubstituierten Fluorenrest umfasst.

13. Organisches Blockpolymer gemäß Anspruch 12, wobei das dritte Monomer einen 2,7-verknüpften Dialkylfluorenrest umfasst.

14. Organisches Blockpolymer gemäß Anspruch 13, wobei der 2,7-verknüpfte Dialkylfluorenrest aus einer 9,9-Dioctyl-

fluorengruppe und einer 9,9-Dihexylfluorengruppe ausgewählt ist.

- 5 15. Organisches Blockpolymer gemäß einem der Ansprüche 11 bis 14, wobei der Polymerblock mit positiven Ladungsträgern ein viertes Monomer umfasst, umfassend einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest.
- 10 16. Organisches Blockpolymer gemäß Anspruch 15, wobei das vierte Monomer ein Stilben oder 1,4-Dien ohne elektronenziehende Substituenten, tertiäre Amine, N,N,N',N'-Tetraaryl-1,4-diaminobenzol, N,N,N',N'-Tetraarylbenzidin, N-substituierte Carbazole, Diarylsilane, und Thiophene/Furane/Pyrrole ohne elektronenziehende Substituenten umfasst.
- 15 17. Organisches Blockpolymer gemäß Anspruch 16, wobei das vierte Monomer mit einem Substituenten, ausgewählt aus C₁₋₂₀-Alkylresten, C₆₋₂₀-Arylresten und Alkylarylresten, gegebenenfalls substituiert mit C₁₋₆-Alkoxyresten und C₆₋₁₂-Aryloxyresten, substituiert ist.
- 20 18. Organisches Blockpolymer gemäß Anspruch 15, wobei das vierte Monomer einen Triarylaminrest der allgemeinen Formel -Ar₃N- umfasst, wobei Ar jeweils gleich oder verschieden ist und einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest umfasst.
- 25 19. Organisches Blockpolymer gemäß Anspruch 18, wobei der Triarylaminrest N,N'-Di-(3-carboxymethoxyphenyl)benzidin ist.
20. Organisches Blockpolymer gemäß Anspruch 18, wobei der Triarylaminrest N,N'-Di-(3-oxymethoxyphenyl)benzidin ist.
- 30 21. Organisches Blockpolymer gemäß einem der Ansprüche 1 bis 20, wobei der Wirtspolymerblock (d) vorhanden ist.
22. Organisches Blockpolymer gemäß Anspruch 21, wobei der Wirtspolymerblock ein fünftes Monomer umfasst, umfassend einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest.
- 35 23. Organisches Blockpolymer gemäß Anspruch 22, wobei das fünfte Monomer einen 2,7-verknüpften Dialkylfluorenrest umfasst.
24. Organisches Blockpolymer gemäß Anspruch 23, wobei der 2,7-verknüpfte Dialkylfluorenrest aus einer 9,9-Dioctylfluorengruppe und einer 9,9-Dihexylfluorengruppe ausgewählt ist.
- 40 25. Organisches Blockpolymer gemäß einem der Ansprüche 21 bis 24, wobei der Wirtspolymerblock ein sechstes Monomer umfasst, umfassend einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest.
- 45 26. Organisches Blockpolymer gemäß Anspruch 25, wobei das sechste Monomer ein Stilben oder 1,4-Dien ohne elektronenziehende Substituenten, tertiäre Amine, N,N,N',N'-Tetraaryl-1,4-diaminobenzol, N,N,N',N'-Tetraarylbenzidin, N-substituierte Carbazole, Diarylsilane, und Thiophene/Furane/Pyrrole ohne elektronenziehende Substituenten umfasst.
- 50 27. Organisches Blockpolymer gemäß Anspruch 26, wobei das sechste Monomer mit einem Substituenten, ausgewählt aus C₁₋₂₀-Alkylresten, C₆₋₂₀-Arylresten und Alkylarylresten, gegebenenfalls substituiert mit C₁₋₆-Alkoxyresten und C₆₋₁₂-Aryloxyresten, substituiert ist.
- 55 28. Organisches Blockpolymer gemäß Anspruch 26, wobei das sechste Monomer einen Triarylaminrest der allgemeinen Formel -Ar₃N- umfasst, wobei Ar jeweils gleich oder verschieden ist und einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest umfasst.
29. Organisches Blockpolymer gemäß Anspruch 28, wobei der Triarylaminrest N,N'-Di-(3-carboxymethoxyphenyl)benzidin ist.
30. Organisches Blockpolymer gemäß Anspruch 28, wobei der Triarylaminrest N,N'-Di-(4-methoxyphenyl)phenylen-diamin ist.

31. Organisches Blockpolymer gemäß Anspruch 25, wobei das sechste Monomer mit einem elektronenziehenden Rest substituiert ist.

32. Organisches Blockpolymer gemäß Anspruch 11, wobei der elektronenziehende Rest aus F, Cyano, Sulfonyl, Carboxy, eine Iminverknüpfung enthaltenden Gruppen, kondensierten polycyclischen Aromaten wie Acenaphthen, Phenanthren, Anthracen, Fluoranthren, Pyren, Perylen, Rubren, Chrysen und Coren, sowie fünfgliedrige Iminverknüpfungen enthaltenden Heterocyclen einschließlich Oxazole/Isoxazole, N-substituierte Imidazole/Pyrazole, Thiazol/Isothiazol, Oxadiazole, und N-substituierte Triazole, und sechsgliedrige Iminverknüpfungen enthaltenden Heterocyclen wie Pyridinen, Pyridazinen, Pyrimidinen, Pyrazinen, Triazinen und Tetrazinen, sowie benzokondensierte Iminverknüpfungen enthaltenden Heterocyclen einschließlich Benzoxazole, Benzothiazole, Benzimidazole, Chinolin, Isochinoline, Cinnoline, Chinazoline, Chinoxaline, Phthalazine, Benzothiadiazole, Benzotriazine, Phenazine, Phenanthridine und Acridine, ausgewählt ist.

33. Organisches Blockpolymer gemäß einem der Ansprüche 1 bis 10, wobei die Monomerreste des emittierenden Polymerblocks im Wesentlichen kein(e) Stilben oder 1,4-Dien ohne elektronenziehende Substituenten, tertiäre Amine, N,N,N',N'-Tetraaryl-1,4-diaminobenzol, N,N,N',N'-Tetraarylbenzidin, N-substituierten Carbazole, Diarylsilane, und Thiophene/Furane/Pyrrrole ohne elektronenziehende Substituenten umfassen.

34. Organisches Blockpolymer gemäß einem der Ansprüche 1 bis 10, wobei die Monomergruppen des emittierenden Polymerblocks im Wesentlichen keinen Triarylaminstoff der allgemeinen Formel $-Ar_3N-$ umfassen, wobei Ar jeweils gleich oder verschieden ist und einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest umfasst.

35. Organisches Blockpolymer gemäß einem der Ansprüche 21 bis 32, wobei die Monomergruppen des emittierenden Polymerblocks im Wesentlichen kein(e) Stilben oder 1,4-Dien ohne elektronenziehende Substituenten, tertiäre Amine, N,N,N',N"-Tetraaryl-1,4-diaminobenzol, N,N,N',N'-Tetraarylbenzidin, N-substituierten Carbazole, Diarylsilane, und Thiophene/Furane/Pyrrrole ohne elektronenziehende Substituenten umfassen.

36. Organisches Blockpolymer gemäß einem der Ansprüche 21 bis 32, wobei die Monomergruppen des emittierenden Polymerblocks im Wesentlichen keinen Triarylaminstoff der allgemeinen Formel $-Ar_3N-$ umfassen, wobei Ar jeweils gleich oder verschieden ist und einen substituierten oder unsubstituierten aromatischen oder heteroaromatischen Rest umfasst.

37. Elektrolumineszente Polymervorrichtung umfassend eine Anode, eine Kathode und das elektrolumineszente organische Blockpolymer gemäß einem der vorhergehenden Ansprüche, das zwischen der Anode und der Kathode angeordnet ist.

38. Polymerfeldeffekt-Transistor, welcher das elektrolumineszente organische Blockpolymer gemäß einem der Ansprüche 1 bis 36 angeordnet zwischen und in elektrischem Kontakt mit einer Ableitung und einer Quelle einschließt.

39. Verfahren zur Herstellung der Blockpolymere gemäß Anspruch 1 durch Umsetzen der Monomere, um individuelle Blöcke getrennt voneinander zu erzeugen, und anschließendes Kombinieren und Umsetzen der individuellen Blöcke, um ein Einzelkomponenten-Blockpolymer zu erzeugen.

40. Verfahren zur Herstellung der Blockpolymere gemäß Anspruch 1 durch Umsetzen eines ersten Satzes von Monomeren, um den ersten Block zu bilden, gefolgt von aufeinander folgendem Hinzufügen und Umsetzen zusätzlicher Sätze von Monomeren für jeden nachfolgenden Block, um einen Einzelkomponenten-Blockpolymer zu bilden.

Revendications

1. Polymère séquencé organique électroluminescent utile dans un dispositif de polymère électroluminescent, comprenant :

(a) une séquence de polymère émissif avec essentiellement aucun groupe monomère qui ne contient pas de double liaison conjuguée dans l'ossature de la séquence du polymère émissif ; et au moins l'un parmi les suivants ;

(b) une séquence de polymère porteur de charges positives avec essentiellement aucun groupe monomère

qui ne contient pas de double liaison conjuguée dans l'ossature de la séquence, transportant des porteurs de charges positives vers la séquence de polymère émissif de telle sorte que les porteurs de charges positives puissent se combiner aux porteurs de charges négatives afin de générer de la lumière

(c) une séquence de polymère porteur de charges négatives avec essentiellement aucun groupe monomère qui ne contient pas de double liaison conjuguée dans l'ossature de la séquence transportant des porteurs de charges négatives vers la séquence de polymère émissif de telle sorte que les porteurs de charges négatives puissent se combiner aux porteurs de charges positives afin de générer de la lumière, et

(d) une séquence de polymère hôte avec essentiellement aucun groupe monomère qui ne contient pas de double liaison conjuguée dans l'ossature de la séquence fournissant une matrice pour émetteur qui permet un transfert d'énergie par résonance et une minimisation des effets de neutralisation par concentration.

2. Polymère séquencé organique selon la revendication 1, dans lequel la séquence de polymère émissif comprend un premier monomère comprenant un groupe aromatique ou hétéroaromatique substitué ou non substitué.

3. Polymère séquencé organique selon la revendication 2, dans lequel le premier monomère comprend un groupe fluorène substitué ou non substitué.

4. Polymère séquencé organique selon la revendication 3, dans lequel le premier monomère comprend un groupe dialkylfluorène lié en 2,7.

5. Polymère séquencé organique selon la revendication 4, dans lequel le groupe dialkylfluorène lié en 2,7 est choisi dans le groupe constitué d'un groupe 9,9-dioctylfluorène et d'un groupe 9,9-dihexylfluorène.

6. Polymère séquencé organique selon les revendications 2 à 5, dans lequel la séquence de polymère émissif comprend un deuxième monomère comprenant un groupe aromatique ou hétéroaromatique substitué ou non substitué.

7. Polymère séquencé organique selon la revendication 6, dans lequel le deuxième monomère comprend un groupe aromatique polycyclique substitué ou non substitué.

8. Polymère séquencé organique selon la revendication 7, dans lequel le groupe aromatique polycyclique substitué ou non substitué est le naphthalène ou l'anthracène.

9. Polymère séquencé organique selon la revendication 6, dans lequel le deuxième monomère comprend un groupe diazine aromatique ou hétéroaromatique fusionné avec un groupe benzène ou thiophène.

10. Polymère séquencé organique selon la revendication 9, dans lequel le groupe diazine aromatique ou hétéroaromatique fusionné avec un groupe benzène ou thiophène est un 2,1,3-benzothiadiazole lié en 2,7.

11. Polymère séquencé organique selon les revendications 1 à 10, dans lequel une séquence de polymère porteur de charges positives (b) est présente et comprend un troisième monomère comprenant un groupe aromatique ou hétéroaromatique substitué ou non substitué.

12. Polymère séquencé organique selon la revendication 11, dans lequel le troisième monomère comprend un groupe fluorène substitué ou non substitué.

13. Polymère séquencé organique selon la revendication 12, dans lequel le troisième monomère comprend un groupe dialkylfluorène lié en 2,7.

14. Polymère séquencé organique selon la revendication 13, dans lequel le groupe dialkylfluorène lié en 2,7 est choisi dans le groupe constitué d'un groupe 9,9-dioctylfluorène et d'un groupe 9,9-dihexylfluorène.

15. Polymère séquencé organique selon les revendications 11 à 14, dans lequel la séquence de polymère porteur de charges positives comprend un quatrième monomère comprenant un groupe aromatique ou hétéroaromatique substitué ou non substitué.

16. Polymère séquencé organique selon la revendication 15, dans lequel le quatrième monomère comprend un stilbène ou un 1,4-diène ne comportant pas de substituant électroattracteur, des amines tertiaires, un N,N,N',N'-tétraaryl-1,4-diaminobenzène, une N,N,N',N'-tétraarylbenzidine, des carbazoles N-substitués, des diarylsilanes et des thio-

phènes/furannes/pyrroles ne comportant pas de substituants électroattracteurs.

- 5 17. Polymère séquencé organique selon la revendication 16, dans lequel le quatrième monomère est substitué par un substituant choisi dans le groupe constitué d'alkyles en C₁ à C₂₀, d'aryles et d'alkylaryles en C₆ à C₂₀ substitués de manière facultative par des alkoxyes en C₁ à C₆ et des aryloxyes en C₆ à C₁₂.
- 10 18. Polymère séquencé organique selon la revendication 15, dans lequel le quatrième monomère comprend un groupe triarylamine de formule générale -Ar₃N- dans lequel les groupes Ar sont identiques ou différents et comprennent un groupe aromatique ou hétéroaromatique substitué ou non substitué
- 15 19. Polymère séquencé organique selon la revendication 18, dans lequel le groupe triarylamine est la N,N'-di(3-carboxométhoxyphényl)benzidine.
- 20 20. Polymère séquencé organique selon la revendication 18, dans lequel le groupe triarylamine est la N,N'-di(3-oxythoxyphényl)benzidine.
- 25 21. Polymère séquencé organique selon les revendications 1 à 20, dans lequel la séquence de polymère hôte (d) est présente.
- 30 22. Polymère séquencé organique selon la revendication 21, dans lequel la séquence de polymère hôte comprend un cinquième monomère comprenant un groupe aromatique ou hétéroaromatique substitué ou non substitué.
- 35 23. Polymère séquencé organique selon la revendication 22, dans lequel le cinquième monomère comprend un groupe dialkylfluorène lié en 2, 7.
- 40 24. Polymère séquencé organique selon la revendication 23, dans lequel le groupe dialkylfluorène lié en 2,7 est choisi dans le groupe constitué d'un groupe 9,9-dioctylfluorène et d'un groupe 9,9-dihexylfluorène.
- 45 25. Polymère séquencé organique selon les revendications 21 à 24, dans lequel la séquence de polymère hôte comprend un sixième monomère comprenant un groupe aromatique ou hétéroaromatique substitué ou non substitué.
- 50 26. Polymère séquencé organique selon la revendication 25, dans lequel le sixième monomère comprend un stilbène ou un 1,4-diène ne comportant pas de substituant électroattracteur, des amines tertiaires, un N,N,N',N'-tétraaryl-1,4-diaminobenzène, une N,N,N',N'-tétraarylbenzidine, des carbazoles N-substitués, des diarylsilanes et des thio-
phènes/furannes/pyrroles ne comportant pas de substituants électroattracteurs.
- 55 27. Polymère séquencé organique selon la revendication 26, dans lequel le sixième monomère est substitué par un substituant choisi dans le groupe constitué d'alkyles en C₁ à C₂₀, d'aryles et d'alkylaryles en C₆ à C₂₀ substitués de manière facultative par des alkoxyes en C₁ à C₆ et des aryloxyes en C₆ à C₁₂.
28. Polymère séquencé organique selon la revendication 26, dans lequel le sixième monomère comprend un groupe triarylamine de formule générale -Ar₃N- dans lequel les groupes Ar sont identiques ou différents et comprennent un groupe aromatique ou hétéroaromatique substitué ou non substitué.
29. Polymère séquencé organique selon la revendication 28, dans lequel le groupe triarylamine est la N,N'-di(3-carboxométhoxyphényl)benzidine.
30. Polymère séquencé organique selon la revendication 28, dans lequel le groupe triarylamine est la N,N'-di(4-méthoxyphényl)phénylènediamine.
31. Polymère séquencé organique selon la revendication 25, dans lequel le sixième monomère est substitué par un groupe électroattracteur.
32. Polymère séquencé organique selon la revendication 31, dans lequel le groupe électroattracteur est choisi dans le groupe constitué de F, cyano, sulfonyl, carboxyle ; d'entités comportant un lien imine, d'aromatiques polycycliques condensés tels que l'acénaphthène, le phénanthrène, l'anthracène, le fluoranthène, le pyrène, le pérylène, le rubrène, le chrysène et le coronène ainsi que des hétérocycles à cinq éléments contenant des liens imines comprenant les oxazoles/isoxazoles, les imidazoles/pyrazoles N-substitués, le thiazole/isothiazole, les oxadiazoles et les triazoles

N-substitués et des hétérocycles à six éléments contenant des liens imines tels que des pyridines, des pyridazines, des pyrimidines, des pyrazines, des triazines et des tétrazènes ainsi que des hétérocycles à benzène fusionnés contenant des liens imines comprenant des benzoxazoles, des benzothiazole, des benzimidazoles, des quinoline, des isoquinolines, des cinnolines, des quinazolines, des quinoxalines, des phthalazines, des benzothiadiazoles, des benzotriazines, des phénazines, des phénanthridines et des acridines.

33. Polymère séquencé organique selon les revendications 1 à 10, dans lequel les groupes de monomères de la séquence de polymère émissif ne se composent essentiellement pas de stilbène ou d'un 1,4-diène ne comportant pas de substituant électroattracteur, d'amines tertiaires, d'un N,N,N',N'-tétraaryl-1,4-diaminobenzène, d'une N,N,N',N'-tétraarylbenzidine, de carbazoles N-substitués, de diarylsilanes et de thiophènes/furannes/pyrroles ne comportant pas de substituants électroattracteurs.
34. Polymère séquencé organique selon les revendications 1 à 10, dans lequel les groupes de monomère de la séquence de polymère émissif ne comprennent essentiellement pas un groupe triarylamine de formule générale -Ar₃N- dans lequel les groupes Ar sont identiques ou différents et comprennent un groupe aromatique ou hétéroaromatique substitué ou non substitué.
35. Polymère séquencé organique selon les revendications 21 à 32, dans lequel les groupes de monomère de la séquence de polymère émissif ne se composent essentiellement pas de stilbène ou d'un 1,4-diène ne comportant pas de substituant électroattracteur, d'amines tertiaires, d'un N,N,N',N'-tétraaryl-1,4-diaminobenzène, d'une N,N,N',N'-tétraarylbenzidine, de carbazoles N-substitués, de diarylsilanes et de thiophènes/furannes/pyrroles ne comportant pas de substituants électroattracteurs.
36. Polymère séquencé organique selon les revendications 21 à 32, dans lequel les groupes de monomère de la séquence de polymère émissif ne comprennent essentiellement pas un groupe triarylamine de formule générale -Ar₃N- dans lequel les groupes Ar sont identiques ou différents et comprennent un groupe aromatique ou hétéroaromatique substitué ou non substitué.
37. Dispositif en polymère électroluminescent comprenant une anode, une cathode et le polymère séquencé organique électroluminescent selon l'une quelconque des revendications précédentes positionné entre l'anode et la cathode.
38. Transistor à effet de champ en polymère comprenant un polymère séquencé organique électroluminescent selon l'une quelconque des revendications 1 à 36 positionné entre et en contact électrique avec un drain et une source.
39. Procédé de fabrication des polymères séquencés selon la revendication 1 consistant à faire réagir des monomères afin de construire des séquences individuelles séparément puis à combiner et à faire réagir les séquences individuelles afin de former un polymère séquencé mono-composant.
40. Procédé de fabrication de polymères séquencés selon la revendication 1 consistant à faire réagir un premier ensemble de monomères afin de former la première séquence, puis à ajouter et à faire réagir séquentiellement des ensembles de monomères supplémentaires pour chaque séquence subséquente afin de former un polymère séquencé mono-composant.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 6204515 B, Burroughes [0002]
- US 5708130 A [0003]
- WO 0046321 A [0003]
- US 6169163 B [0003]
- US 20010024738 A1 [0004]
- US P6204515 B [0006]
- WO 0055927 A, Towns [0007] [0016]
- GB 9900741 W [0016] [0017] [0018]
- US P5777070 A [0016] [0017] [0018]
- US P6169163 B [0016] [0017] [0018]
- US P5962631 A [0016] [0017] [0018]
- US P5708130 A [0016] [0017] [0018]
- GB 0000911 W [0017] [0018]
- US 5777070 A [0023]

Non-patent literature cited in the description

- **BURROUGHES et al.** Light-emitting diodes used on conjugated polymers. *Nature*, October 1990, vol. 347, 539-541 [0002]
- **FUKUDA.** Synthesis of Fusible and Soluble Conducting polyfluorene Derivatives and their Characteristics. *J. of Poly. Sci.*, 1993, vol. 31, 2465-2471 [0003]
- **YU et al.** Enhanced electroluminescence from semiconducting polymer blends. *Syn. Met.*, 1995, vol. 72, 249-252 [0003]
- **KIM et al.** LED Characterization of an Alternating Copolymer and its Blends. *SPIE*, vol. 3148, 151-158 [0003]
- Efficient red- and orange-light emitting diodes realized by excitation energy transfer from blue-light-emitting conjugated polymers. **TASCH et al.** *Physical Review B. The American Physical Society*, 1997, vol. 56, 4479-4483 [0003]
- **HEISCHKEL et al.** Synthesis of ABC-triblock copolymers for light emitting diodes. *Macromol. Chem. Phys.*, 1998, vol. 199, 869-880 [0004]
- **CHEN et al.** Improved efficiencies of light-emitting diodes through incorporation of charge transporting components in tri-block polymers. *Syn. Met.*, 1999, vol. 107, 203-207 [0004]

一种可用于电致发光聚合物流器件（或聚合物场效应晶体管）的有机嵌段聚合物，其包括沿着发光聚合物嵌段的主链始终共轭的发光聚合物嵌段（例如，2,7-连接的9的共聚物，9-二辛基芴和4,7-连接的2,1,3-苯并噻二唑）；和正电荷载体聚合物嵌段沿着正电荷载体聚合物嵌段的主链一致共轭（例如，2,7-连接的9,9-二辛基芴和4N，4N'-连接的N，N'-二己基的共聚物（3-羧基甲氧基苯基）联苯胺），用于将正电荷载体输送到发光聚合物嵌段，使得正电荷载体可以与负电荷载体结合产生光。

