



(11)

EP 1 744 598 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:

31.05.2017 Bulletin 2017/22

(21) Application number: 05734415.2

(22) Date of filing: 20.04.2005

(51) Int Cl.:

H05B 33/22 (2006.01) **C07F 9/53** (2006.01)
C09K 11/06 (2006.01) **H05B 33/10** (2006.01)
H05B 33/14 (2006.01) **H01L 51/00** (2006.01)
H01L 51/50 (2006.01) **H01L 51/56** (2006.01)

(86) International application number:
PCT/JP2005/007551

(87) International publication number:
WO 2005/104628 (03.11.2005 Gazette 2005/44)

(54) **ORGANIC ELECTROLUMINESCENT ELEMENT AND MANUFACTURING METHOD THEREOF, ORGANIC COMPOUND CONTAINING PHOSPHORUS AND MANUFACTURING METHOD THEREOF**

ORGANISCHES ELEKTROLUMINESZENZELEMENT UND HERSTELLUNGSVERFAHREN DAFÜR, PHOSPHORHALTIGE ORGANISCHE ZUSAMMENSETZUNG UND HERSTELLUNGSVERFAHREN DAFÜR

ÉLÉMENT ÉLECTROLUMINESCENT ORGANIQUE ET PROCÉDÉ DE FABRICATION DE CELUI-CI, COMPOSÉ ORGANIQUE CONTENANT DU PHOSPHORE ET PROCÉDÉ DE FABRICATION DE CELUI-CI

(84) Designated Contracting States:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU MC NL PL PT RO SE SI SK TR

(30) Priority: 20.04.2004 JP 2004124712

(43) Date of publication of application:

17.01.2007 Bulletin 2007/03

(73) Proprietors:

- Kyushu Electric Power Co., Inc.
Fukuoka-ken 810-8720 (JP)
- Daiden Co., Ltd.
Kurume-shi,
Fukuoka-ken, 830-8511 (JP)

(72) Inventors:

- GOTO, Yasuyuki,
c/o KYUSHU ELECTRIC POWER CO., INC.
Fukuoka-shi,
Fukuoka 810-8720 (JP)
- NOTO, Mitsuharu,
c/o DAIDEN CO., LTD.
Kurume-shi, Fukuoka 830-8511 (JP)

• HAYASHIDA, Tsuyoshi,
c/o DAIDEN CO., LTD.

Kurume-shi, Fukuoka 830-8511 (JP)

• ERA, Masanao

Saga-shi,
Saga 840-0027 (JP)

(74) Representative: Gevers & Orès

41 avenue de Friedland
75008 Paris (FR)

(56) References cited:

WO-A1-2005/073340	JP-A- 2002 063 989
JP-A- 2002 367 785	JP-A- 2003 292 587
JP-A- 2003 292 587	JP-A- 2003 317 965
JP-A- 2004 095 221	US-A- 3 895 074
US-A- 5 231 329	US-A1- 2001 012 572

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Technical Field

5 [0001] The present invention relates to an organic electroluminescent element and a manufacturing method thereof, and a novel phosphorus-containing organic compound used for the formation of an electron-transporting layer of the organic electroluminescent element and a manufacturing method thereof. According to the present invention, it is possible to form the electron-transporting layer of the organic electroluminescent element on an underlying organic film by a wet method without damaging the underlying organic film.

10 [0002] Organic electroluminescent elements that use an organic material as a luminescent material act to recombine holes injected from their anodes and electrons injected from their cathodes and to form excited molecules (excitons), which radiate energy to emit light when returning to a ground state.

15 [0003] In 1987, C.W. Tang et al. of the Eastman Kodak Company announced an organic electroluminescent element having organic films laminated between its anode and cathode, and thus realized emission of high luminance light at a low driving voltage (C.W.Tang et al., Applied Physics Letters, 1987, Vol.51, p.913: Nonpatent document 1).

20 [0004] Since the announcement by Tang et al., eager studies have been conducted of organic electroluminescent elements, that is, of their luminescence in three RGB primary colors, luminance improvement, stability, laminate structure and manufacturing method. The organic electroluminescent elements have already been in some practical use as a component of a display for the mobile telephone or car audio, and are regarded as promising as a component of a next-generation flat display which is an alternative to the liquid crystal display.

25 [0005] Many organic electroluminescent elements use an electron-transporting material in combination with a luminescent material.

[0006] The electron-transporting material is used for efficient transportation of electrons injected from the cathode to a luminescent layer and also for blocking of holes. Usable electron-transporting materials include an oxadiazole derivative and Alq₃ (tris(8-hydroxyquinoline)aluminum), which is widely used as a green-color luminescent material.

30 [0007] Methods for forming an organic film for an organic electroluminescent element are roughly classified into two categories: dry methods and wet methods. The dry methods include a vacuum deposition method and a CVD method, while the wet methods include a spin coating method and an inkjet method.

35 [0008] The dry methods have an advantage of facilitating formation of a multi-layered film due to vacuum deposition. When used for the manufacture of organic electroluminescent elements, the dry methods facilitate formation of a multi-layered film comprising a hole-injecting layer, an electron-injecting layer, a hole-blocking layer and the like, to achieve an injection balance between holes and electrons. Thus, organic electroluminescent elements manufactured by the dry methods realize high efficiency and luminance, and display devices using such organic electroluminescent elements have already been in practical use. The dry methods, however, have a disadvantage of requiring large-scale apparatuses for the manufacture of elements having a large area, which lowers the productivity.


40 [0009] On the other hand, the wet methods have an advantage of permitting formation of a coating film having a large area, all at a time, which facilitates the manufacture of elements having a large area and increases the productivity. In terms of productivity and costs, therefore, the wet methods are superior to the dry methods. Especially for polymer materials, with which it is often difficult to form a thin film by vacuum deposition, the wet methods are mainly employed.

45 [0010] Japanese Unexamined Patent Publication No. 2002-63989 (Patent document 1) discloses a luminescent element containing an organic fluorophor represented by the formula:



wherein R, the same or different from each other, are substituents such as an aryl group, at least one of R being a fluorescent skeleton.

50 [0011] Also, Japanese Unexamined Patent Publication No. 2004-204140 (Patent document 2) discloses a material for luminescent element represented by the formula:



55 wherein Ar, the same or different from each other, are an aryl group or a heteroaryl group, at least one of Ar being a naphthyl group linked at its α position, at least one of Ar containing either a fluorescent skeleton or a charge transport skeleton.

[0012] The above publication recites condensed rings such as phenanthryl, anthranyl, pyrenyl and perylenyl, as ex-

amples of fluorescent skeletons.

[0013] The structure of the phosphorus-containing organic compound of the present invention, however, is different from, though similar to, the structures of the organic fluophor and the material for luminescent element disclosed in the above publications, since it does not have a naphthyl group linked at its α position, a fluorescent skeleton or the like.

5

Patent document 1: Japanese Unexamined Patent Publication No. 2002-63989

Patent document 2: Japanese Unexamined Patent Publication No. 2004-204140

10

Nonpatent document 1: C.W.Tang et al., Applied Physics Letters, 1987, Vol.51, p.913 Japanese Patent Application No. JP 2002-063989 and JP 2004-095221 disclose a light emitting device in which the layers, including the electron-transporting layer, are manufactured by a dry method.

[0014] US Patent Application No. US 2001/012572 A1 discloses a light emitting device in which the electron-transporting layer is not made from a phosphorus-containing organic compound.

15

Disclosure of the Invention

Problem that the Invention is to Solve

20

[0015] However, conventional electron-transporting materials have the following problem when they are used for the manufacture of an organic film by a wet method.

25

[0016] With the wet methods that use a solution of an electron-transporting material in a solvent for film formation, the conventional electron-transporting materials permit the use of only limited solvents such as chloroform, toluene, THF (tetrahydrofuran) and the like. When a solvent other than the above is used, the electron-transporting material does not dissolve at all and a film itself cannot be formed or, even if it is formed, the electron-transporting material crystallizes after the film formation and the product obtained is not usable as an element

[0017] Accordingly, if the electron-transporting layer is formed by the wet method on an underlying organic film which is soluble in chloroform, toluene, THF and the like, the underlying organic film dissolves in, and is damaged by, the same solvent that is used for the formation of the electron-transporting layer, and as a result, the organic film has an ununiform quality and pin-holes, making it impossible to manufacture an excellent organic electroluminescent element

30

[0018] Since especially polymer materials used for the film formation by the wet method are soluble in only solvents such as chloroform, toluene, THF (tetrahydrofuran) and the like, it is impossible to form the electron-transporting layer on a film of a polymer material by the wet method.

(Object of the Invention)

35

[0019] It is an object of the present invention to provide a phosphorus-containing organic compound that can be used for formation of a smooth-surfaced electron-transporting layer of an organic electroluminescent element on an underlying organic film by a wet method without damaging the underlying organic film.

40

Means of Solving the Problem

45

[0020] The present inventors, as a result of eager studies to achieve the above object, have noted that, by using a specific phosphorus-containing organic compound as an electron-transporting material for an organic electroluminescent element, it is possible to form an electron-transporting layer on an underlying organic film by a wet method without damaging the underlying organic film, thereby completing the present invention.

50


[0021] In one aspect, the present invention provides an organic electroluminescent element comprising an anode, a cathode and a plurality of organic compound layers sandwiched between the anode and cathode, the organic compound layers including: a hole-transporting layer made of an organic compound insoluble in alcohols; and an electron-transporting layer formed on the hole-transporting layer by a wet method, the electron-transporting layer being made of a phosphorus-containing organic compound soluble in the alcohols.

55

[0022] In another aspect, the present invention provides a manufacturing method of an organic electroluminescent element including an anode, a cathode and a plurality of organic compound layers sandwiched between the anode and cathode, the method comprising the steps of: forming a hole-transporting layer using an organic compound insoluble in alcohols; and forming an electron-transporting layer on the hole-transporting layer by a wet method using as an electron transporting layer material a phosphorus-containing organic compound to be dissolved in an alcohol.

[0023] In still another aspect, the present invention provides a phosphorus-containing organic compound as a condensation product of a compound represented by the general formula (4):

5



10

wherein Ar¹¹, the same or different from each other, represent a phenyl group or naphthyl group optionally substituted with a halogen atom, a lower alkyl group, a lower alkoxy group or a phenyl group, and either a compound represented by the formula:

15


Ar¹²

wherein Ar¹² represents benzene substituted with three halogen atoms, or benzene or biphenyl substituted with two halogen atoms

or

20 a compound represented by the general formula (5):

25




30

wherein Ar¹³, the same or different from each other, are a phenyl group or biphenyl group optionally substituted with a halogen atom, at least two of Ar¹³ being a phenyl group or biphenyl group substituted with at least one halogen atom.

35 **[0024]** In yet another aspect, the present invention provides a phosphorus-containing organic compound having at least three partial structures represented by a diarylphosphine oxide skeleton, the diarylphosphine oxide skeleton represented by either the formula (9):

40




45

wherein Ar¹¹ has the same meaning as defined in the general formula (4) or the formula (10):

50

55

5



10

wherein Ar¹³', the same or different from each other, are a phenyl group or a biphenyl group, or a phenylene group or biphenylene group linked to the formula (9).

15 [0025] In a further aspect, the present invention provides a manufacturing method of a phosphorus-containing organic compound, comprising the step of condensing, in a solvent, in the presence of a condensing catalyst and a base, a compound of the general formula (4) with either a compound of the formula: Ar¹² or a compound of the general formula (5).

Effect of the Invention

20 [0026] According to the present invention, the organic electroluminescent element is manufactured by forming the electron-transporting layer on the hole-transporting layer of the organic compound insoluble in the alcohols, by the wet method, using the solution of the electron-transporting material in the alcohol. Since the underlying hole-transporting layer does not dissolve in the alcohol used for formation of the overlying electron-transporting layer, it is possible to form 25 the electron-transporting layer on the underlying organic film by the wet method without damaging the underlying organic film. As a result, the organic compound layer can have a uniform quality and can be free from pin-holes, making it possible to manufacture a long-life organic electroluminescent element that provides excellent luminescence at a low voltage.

30 [0027] The above-described phosphorus-containing organic compound has satisfactory properties in ionization potential, band gap, glass transition temperature and the like, and possesses good electron-transporting capability, hole-blocking capability and heat resistance. Accordingly, use of the above-described phosphorus-containing organic compound leads to a long-life organic electroluminescent element that provides excellent luminescence at a low voltage.

Brief Description of Drawings

35 [0028]

Fig. 1 is an explanatory view showing an organic electroluminescent element according to Example 1 of the present invention.

40 Fig. 2 is an explanatory view showing an organic electroluminescent element according to Comparative Example 1.

Fig. 3 is a characteristic view showing the voltage-luminance relationships of the elements according to Example 1 and Comparative Example 1.

45 Fig. 4 is a characteristic view showing the current-luminance relationships of the elements according to Example 1 and Comparative Example 1.

Fig. 5 is an explanatory view showing an organic electroluminescent element according to Example 2 of the present invention.

50 Fig. 6 is an explanatory view showing an organic electroluminescent element according to Comparative Example 2.

Fig. 7 is a characteristic view showing the voltage-luminance relationships of the elements according to Example 2 and Comparative Example 2.

Fig. 8 is a characteristic view showing the current-luminance relationships of the elements according to Example 2 and Comparative Example 2.

55 Fig. 9 is a characteristic view showing the voltage-vs.-EL-efficiency relationships of the elements according to Example 2 and Comparative Example 2.

Fig. 10 is a characteristic view showing the voltage-luminance relationships of the elements according to Example 3 and Comparative Example 3.

Fig. 11 is a characteristic view showing the current-luminance relationships of the elements according to Example 3 and Comparative Example 3.

Fig. 12 is a characteristic view showing the voltage-vs.-EL-efficiency relationships of the elements according to

Example 3 and Comparative Example 3.

Fig. 13 is a characteristic view showing the luminance-voltage relationships of the elements according to Example 19 and Comparative Example 4.

Fig. 14 is a characteristic view showing the luminance-voltage relationships of the elements according to Example 20 and Comparative Example 4.

Fig. 15 is a characteristic view showing the luminance-voltage relationships of the elements according to Example 21 and Comparative Example 4.

Fig. 16 is a characteristic view showing the luminance-voltage relationships of the elements according to Example 22 and Comparative Example 4.

Explanation of Reference Numerals

[0029]

- 15 1 Glass substrate having a transparent electrode
- 2 Hole-transporting and luminescent layer
- 3 Electron-transporting layer
- 4 Cathode
- 5 Hole-injecting layer


20 Best Mode for Carrying Out the Invention

[0030] The organic electroluminescent element of the present invention comprises an anode, a cathode and a plurality of organic compound layers sandwiched between the anode and cathode, the organic compound layers including: a hole-transporting layer made of an organic compound insoluble in alcohols; and an electron-transporting layer formed on the hole-transporting layer by a wet method, the electron-transporting layer being made of a phosphorus-containing organic compound soluble in the alcohols.

[0031] The term "soluble" in the present specification means soluble enough for the solution obtained to be actually used with a wet method for forming a film, the solubility being preferably 0.1 g per liter or higher, for example.

[0032] The material of the electron-transporting layer is an organic compound soluble in alcohols when it is used with a wet method, while when it is used with a dry method, it is an organic compound that has a capability of being vapor-deposited under 10^{-3} Pa or lower. It is preferably a nonionic organic compound, particularly preferably a phosphorus-containing organic compound.

[0033] Usable as the phosphorus-containing organic compound are compounds represented by the general formulae (1)-(3):




45 wherein Ar^1 - Ar^3 , the same or different from each other, represent an aromatic ring residue optionally containing a substituent.

5

10

15

(2)




wherein Ar¹-Ar⁶, the same or different from each other, represent an aromatic ring residue optionally containing a substituent; and Ar⁷-Ar⁹, the same or different from each other, represent an arylene group optionally containing a substituent.

25

30

35

40



wherein R¹ or R², the same or different from each other, represents a hydrogen atom, an alkyl group, a halogen atom, cyano group, nitro group, amino group, an aryl group or a diarylphosphinyl group, and R¹ and R² can form, together with a carbon atom of a benzene ring to which they are linked, a substituted or unsubstituted aromatic ring; and n is 1 or 2.

[0034] Examples of the "aromatic ring residue" in the general formulae (1) and (2) include monocyclic aromatic ring residues and heterocycles such as a benzene ring, a thiophene ring, a triazine ring, a furan ring, a pyrazine ring and a pyridine ring; condensed polycyclic aromatic ring residues and heterocycles such as a naphthalene ring, an anthracene ring, a thieno[3,2-b]thiophene ring, a phenanthrene ring, a fluorene ring and a furo[3,2-b]furan ring; ring-aggregated aromatic ring residues and heterocycles such as a biphenyl ring, a terphenyl ring, a bithiophene ring and a bifuran ring; and aromatic ring residues and heterocycles such as a acridine ring, an isoquinoline ring, an indole ring, a carbazole ring, a carboline ring, a quinoline ring, a dibenzofuran furan ring, a cinnoline ring, a thionaphthene ring, a 1,10-phenanthroline ring, a phenothiazine ring, a purine ring, a benzofuran ring and a silol ring.

[0035] Examples of the "arylene group" in the general formula (2) include aromatic hydrocarbon groups such as a phenylene group, a naphthylene group, a biphenylene group, a phenanthrene group, a terphenylene group and a pyrenylene group. These may be substituted or unsubstituted.

[0036] Examples of the "aryl group" in the general formula (3) include aromatic hydrocarbon groups such as a phenyl

group, a naphthyl group, a biphenyl group, a phenanthryl group, a terphenyl group and a pyrenyl group. These may be substituted or unsubstituted.

[0037] Examples of substituents in the "aryl group" and "aromatic ring residue" include an alkyl group, an alkoxy group, a halogen atom, cyano group, nitro group, amino group, an aryl group and a diarylphosphinyl group.

5 [0038] The phosphorus-containing organic compound of the present invention is preferably a nonionic organic compound which has a high electrochemical stability, is reluctant to crystallize and has a long life when used for the organic electroluminescent element.

10 [0039] The phosphorus-containing organic compound of the present invention preferably has a molecular weight of 300-5000, more preferably, in view of its solubility in alcohols and its capability of being vapor-deposited, 300-1500 when it is used with a wet method and 300-1200 when it is used with a dry method.

15 [0040] The present invention provides a manufacturing method of an organic electroluminescent element including an anode, a cathode and a plurality of organic compound layers sandwiched between the anode and cathode, comprising the steps of: forming a hole-transporting layer using an organic compound insoluble in alcohols; and forming an electron-transporting layer on the hole-transporting layer by a wet method using as an electron transporting layer material a phosphorus-containing organic compound to be dissolved in an alcohol.

[0041] The electron-transporting layer surface of the organic electroluminescent element manufactured by the method of the present invention preferably has a arithmetical mean roughness (Ra) of 10 nm or less, more preferably 1 nm or less in view of an improvement in the luminescence of the organic electroluminescent element.

20 [0042] The phosphorus-containing organic compounds represented by the general formulae (1)-(3) are used as an electron transporting layer material that is soluble in alcohols.

[0043] Examples of alcohols include linear or branched C₁-C₆ aliphatic alcohols such as methanol, ethanol, 1-propanol, 2-propanol, 1-butanol, 2-butanol, 2-methyl-1-propanol and 2-methyl-2-propanol; and glycol-type solvents such as ethylene glycol monomethyl ether and ethylene glycol monoethyl ether, among which preferable are the linear or branched C₁-C₆ aliphatic alcohols. These may be used in a combination of two or more.

25 [0044] Examples of the wet methods include a spin coating method, an inkjet method, an a spraying method, a dip coating method, a blade coating method, a wire bar coating method, a casting method, a roll coating method, and printing methods such as screen printing, gravure printing, offset printing and the like.

[0045] When the electron-transporting layer is formed by the wet method, the above-mentioned alcohols may be used in combination with a solvent other than the above-mentioned alcohols.

30 [0046] Other steps in the manufacture of the organic electroluminescent element are not particularly limited and may be performed with known methods.

[0047] Examples of the dry methods include a vacuum deposition method, a CVD method and the like.

[0048] There will be described the present organic electroluminescent element that uses the electron-transporting material.

35 [0049] The organic electroluminescent element has a layer structure exemplified as follows:

- (1) A substrate; an anode; a luminescent layer; and a cathode (rear electrode)
- (2) A substrate; an anode; a luminescent layer; one or more organic compound layers containing an electron-transporting material; and a cathode
- 40 (3) A substrate; an anode; one or more organic compound layers containing a hole-transporting material; a luminescent layer; and a cathode
- (4) A substrate; an anode; one or more organic compound layers containing a hole-transporting-material; a luminescent layer; one or more organic compound layers containing an electron-transporting material; and a cathode

45 [0050] Each of the above layer structures (1)-(4) may include a hole-injecting layer and/or an electron-injecting layer.

[0051] The choice of materials depends on whether it is the substrate side or the cathode side from which light is taken out. When light is taken out from the substrate side, the substrate and the anode are formed of a transparent material, while when light is taken out from the cathode side, the cathode is formed of a transparent material.

50 [0052] The organic electroluminescent element may further include a hole-blocking layer and/or an electron-injecting layer.

[0053] Further, the luminescent layer may contain either a hole-transporting material or an electron-transporting material, and may function either as a hole-transporting and luminescent layer or as an electron-transporting and luminescent layer.

55 [0054] In addition, the luminescent layer may be doped with a luminescent material at its hole-transporting layer side and/or at its electron-transporting layer side.

[0055] The material of the substrate is not particularly limited and may be a known material. Known materials include glass, plastic, a thin metal film, silicon, quartz and the like. Also, the substrate may have a fluorescent-color conversion filter film, a color filter film, a dielectric reflective film and the like, for control of the luminescent color.

[0056] The material of the anode is not particularly limited and may be a known material. Known materials include indium tin oxide (ITO), titanium oxide, tin oxide, metals such as gold, platinum, nickel, palladium, cobalt, selenium, vanadium and the like, and alloys thereof; and conductive polymers such as polyaniline, polypyrrol, polythiophene, polyphenylene sulfide and the like. These electrode materials may be used alone or in combination.

5 [0057] The method of forming the electrode is not particularly limited and may be a known method. Known methods include thin-film formation methods such as a vacuum deposition method, a sputtering method, a sol-gel method, a spin coating method, an inkjet method and the like.

10 [0058] The material of the cathode is not particularly limited and may be a known material. Known materials include metals such as lithium, aluminum, magnesium, sodium, potassium, calcium, indium, silver, lead, tin, chromium and the like, and alloys thereof; and metal oxides such as indium tin oxide (ITO) and the like.

[0059] The cathode may have a single-layered or multilayered structure.

[0060] The method of forming the electrode is not particularly limited and may be a known method.

15 [0061] The material of the hole-transporting layer is not particularly limited and may be a known material. When the hole-transporting layer is formed by a wet method, the material is selected from ones that do not dissolve in the alcohol used with the wet method for the formation of the electron-transporting layer.

[0062] Materials of the hole-transporting layer include conductive polymers, low-molecular organic semiconductors, and composite materials prepared by dispersing a low-molecular organic semiconductor in an insulative polymer such as poly(methyl acrylate), poly(butyl acrylate) or polycarbonate, as well as composite materials of two or more of these.


20 [0063] Examples of the conductive polymers include poly(diethyl-fluorene) (POF), polyvinyl carbazole (PVK), polyphenylene (PP), polyfluorene (PF), polythiophene (PT), polyparaphenylene vinylene (PPV) and polyacetylene (PA), as well as composite materials of two or more of these, derivatives and copolymers of these conductive polymers, and copolymers of one or more of these conductive polymers with a polyacene or with a fluorescent pigment.

[0064] Examples of the low-molecular organic semiconductors include phenylenediamine derivatives (e.g., N,N'-bis(3-methylphenyl)-N,N'-bis (phenyl)-benzidine(TPD) and the like), triphenylamine derivatives, carbazole derivatives and phenyl styrene derivatives, as well as composite materials of two or more of these.

[0065] The material of the hole-injecting layer is not particularly limited and may be a known material. Known materials include PEDT/PSS (polyethylenedioxythiophene/polystyrene sulfonic acid), copper phthalocyanine and the like.

30 [0066] The material of the electron-injecting layer is not particularly limited and may be a known material. Known materials include alkali metal fluorides such as lithium fluoride, cesium fluoride and the like; alkali earth metal fluorides such as magnesium fluoride, calcium fluoride and the like; lithium complexes such as acetylacetosodium, lithium quinolate and the like; and composite films of vasophenanthroline or bathocuproin doped with metal sodium or metal lithium.

[0067] The present invention provides a phosphorus-containing organic compound as a condensation product of a compound represented by the general formula (4):



wherein Ar^{11} , the same or different from each other, represent a phenyl group or naphthyl group optionally substituted with a halogen atom, a lower alkyl group, a lower alkoxy group or a phenyl group, and either a compound represented by the formula:




wherein Ar^{12} represents benzene substituted with three halogen atoms, benzene or biphenyl substituted with two halogen atoms

or

a compound represented by the general formula (5):

5




10

wherein Ar¹³, the same or different from each other, are a phenyl group or biphenyl group optionally substituted with a halogen atom, at least two of Ar¹³ being a phenyl group or biphenyl group substituted with at least one halogen atom.

15 [0068] Preferable examples of the above-mentioned condensation product include compounds represented by the following subformulae (6)-(8):

20




25

wherein Ar¹¹ has the same meaning as defined in the general formula (4); and Ar¹²' represents a phenylene group or biphenylene group when n=2 and a benzenetriyl group when n=3.

30

35




40

45

wherein Ar¹¹ has the same meaning as defined in the general formula (4); and Ar¹³', the same or different from each other, represent a phenylene group or a biphenylene group.

50

55



wherein Ar^{11} has the same meaning as defined in the general formula (4); $\text{Ar}^{13'}$, the same or different from each other, represent a phenylene group or a biphenylene group; and $\text{Ar}^{13''}$ represents a phenyl group or a biphenyl group.

[0069] $\text{Ar}^{11}, \text{Ar}^{12}, \text{Ar}^{12'}, \text{Ar}^{13}, \text{Ar}^{13'}$ and $\text{Ar}^{13''}$ in the subformulae (6)-(8) are substantially the same as, though partially different from, Ar^1-Ar^3 in the general formula (1) and Ar^1-Ar^9 in the general formulae (2) and (3).

[0070] Examples of the "halogen atom" in substituent Ar^{11} include fluorine, chlorine, bromine, iodine and the like.




[0071] Examples of the "lower alkyl group" in substituent Ar^{11} include methyl group, ethyl group, n-propyl group, iso-propyl group, n-butyl group, iso-butyl group, tert-butyl group (also referred to as t-butyl), and the like.

[0072] Examples of the "lower alkoxy group" in the substituent Ar^{11} include methoxy group, ethoxy group, propoxy group, butoxy group and the like.

[0073] Particularly preferable examples of the substituent Ar^{11} include an unsubstituted phenyl group; and a phenyl group, biphenyl or naphthyl group substituted with methyl group, t-butyl group or methoxy group.


[0074] In the case where the substituents Ar^{11} in the subformulae (6)-(8) include a phenyl group and a naphthyl group, the phenyl group and the naphthyl group may be linked to the same phosphorus atom.

[0075] Specific examples of the phosphorus-containing organic compound represented by the subformula (6) ($n=6$) include compounds represented by the following formulae. In the following formulae, only skeletons are illustrated, and substituents in substituted Ar^{11} are omitted.




55 [0076] Specific examples of the phosphorus-containing organic compounds represented by subformula (6) ($n=3$) include the following compounds:


5




10




15



20




25




30

[0077] Specific examples of the phosphorus-containing organic compounds represented by the subformula (7) include the following compounds:

35



40




45


50

55


5




10




15




25



30



35




45

[0078] Specific examples of the phosphorus-containing organic compounds represented by the subformula (8) include the following compounds:


50

55


5




10




15



20



25



30

35

[0079] Specific examples of phosphorus-containing organic compounds other than the above include the following compounds:


40

45


50

55

5




10




(0-2)

15




20



(0-4)

25



30


35

40


45

50

55




(0-6)




(0-7)

5




10




15

20




25




30

35



40




45


50

55


5




10



15




20



[0080] However, the above specific examples are merely for an illustrative purpose and the phosphorus-containing organic compound of the present invention is not limited to the above.

[0081] The phosphorus-containing organic compound of the present invention preferably has at least three partial structures represented by a diarylphosphine oxide skeleton, the diarylphosphine oxide skeleton represented by either the formula (9):


30



35

wherein Ar^{11} has the same meaning as defined in the general formula (4) or the formula (10):

40



45

50

wherein $\text{Ar}^{13'}$, the same or different from each other, are a phenyl group or a biphenyl group, or a phenylene group or biphenylene group linked to the formula (9).

[0082] The phosphorus-containing organic compound having said at least three partial structures has an excellent effect of transporting electrons, as the electron transporting layer material for the organic electroluminescent element.

55

[0083] The phosphorus-containing organic compound of the present invention may be synthesized by a known method.

[0084] The phosphorus-containing organic compound of the present invention can be manufactured by condensing (dehydrohalogenating), in a solvent, in the presence of a condensing catalyst and a base, a compound of the general formula (4) (compound 4) with either a compound of the formula: Ar^{12} or a compound of the general formula (5) (compound

5).

[0085] For example, the use amount of the compound 4 for manufacture of the compound of the subformula (6) (n=2) is about 2.0-4.5 moles with respect to one mole of the compound Ar¹².

[0086] The amount of the compound 4 to be used for manufacture of the compound of the subformula (6) (n=3) is about 3.0-7.5 moles with respect to one mole of the compound Ar¹².

[0087] The amount of the compound 4 to be used for manufacture of the compound of the subformula (7) is about 3.0-7.5 moles with respect to one mole of the compound 5.

[0088] The amount of the compound 4 to be used for manufacture of the compound of the subformula (8) is about 2.0-4.5 moles with respect to one mole of the compound 5.

[0089] Examples of the above solvent include dimethyl sulfoxide (DMSO), dimethylformamide (DMF), tetrahydrofuran (THF), dioxane, pyridine, benzene, toluene, xylene and the like, among which preferable is DMSO in terms of yield.

[0090] Examples of the above condensing catalyst include palladium acetate [Pd(OAc)₂], nickel acetate[Ni(OAc)₂], and complex compounds of elements belonging to the platinum family and bisphosphinoalkanes such as Pd(OAc)₂-1,3-bis(diphenylphosphino)propane[dppp], Pd(OAc)₂-1,2-bis(diphenylphosphino)ethane[dppb], Pd(OAc)₂-1,4-bis(diphenylphosphino)butane[dppb], Ni(OAc)₂-dppe and Ni(OAc)₂-dppp. Among these, preferable are Pd(OAc)₂, Pd(OAc)₂-dppp and Pd(OAc)₂-dppb in terms of yield.

[0091] The amount of the catalyst to be used is about 0.005-0.1 moles with respect to one mole of the compound 4.

[0092] The base has a function to capture hydrogen halide generated by the condensation.

[0093] Examples of the base include trialkylamines such as triethylamine, tripropylamine and tributylamine; aliphatic tertiary amines such as N-ethyldiisopropylamine[edpa]; and aromatic tertiary amines such as pyridine and N,N'-dimethylaminopyridine[DMAP]. Among these, preferable are edpa and DMAP in terms of boiling point

[0094] The amount of the base to be used is an amount sufficient to capture the theoretical amount of hydrogen halogenide generated. That is, it is about 1.0-1.2 moles with respect to one mole of the compound 4.

[0095] The reaction temperature in the condensation reaction according to the present invention is preferably 60-180 °C, more preferably 80-130 °C.

[0096] The reaction time depends on conditions such as reaction temperature, and typically a reaction time of 1-48 hours is sufficient.

[0097] After the reaction, the target compound is separated from the reaction solution obtained, by a known method. For example, the target compound is extracted with chloroform/distilled water from the reaction solution, and the chloroform phase is separated and concentrated. The target compound obtained may further be purified. For example, the remaining viscous liquid is dissolved in a small amount of chloroform, and the resulting solution is subjected to column chromatography that uses silica gel as a filler, to separate the target compound. After the separation, the target compound is recrystallized, and further purified by sublimation in a vacuum.

[0098] The phosphorus-containing organic compound thus obtained can be used as the electron-transporting material for the organic electroluminescent element


[0099] Among the aforementioned examples of the present phosphorus-containing organic compound, preferable as the electron-transporting material for the organic electroluminescent element are the following compounds:

Compounds of the subformula (6):


40

[0100]

45




(A)




(B)

50

55




(C)




(D)

Compounds of the subformula (7):


[0101]




(E)



(F)




(G)




(H)

50


55




(I)




(J)




(K)



(L)



(M)



(N)


50

55

5

10

15




20

25

30

(P)



[0103] The phosphorus-containing organic compound of the present invention is considered to have the same properties as those of organic semiconductors in general use, and its application to devices is expected. Examples of devices to which the compound of the present invention is expected to be applied include organophotoreceptors, organic thin film lasers, organic solar cells, organic field-effect transistors, organic volatile memories, organic nonvolatile memories, antistatic agents and the like. Examples of products to which these devices are expected to be applied include TFT substrates for liquid crystal display, TFT substrates for organic EL, organic integrated circuits, copying machines, facsimiles, mobile telephones, non-contact IC cards and tags, personal computers and the like.

[0104] The phosphorus-containing organic compound of the present invention has a partial structure represented by a diarylphosphine oxide skeleton, and is also referred to as a "triarylphosphine oxide compound" in the present specification.

[0105] Hereafter, the present invention will be described by way of Examples. However, the present invention should not be construed as being limited by these Examples.



45 (Example 1)

(1) Synthesis of 4,4',4''-tris(diphenylphosphinyl)-triphenylphosphine oxide (also referred to as "TPPO-Burst")

[0106] In Example 1, TPPO-Burst represented by the following formula was synthesized.

50

55



(1-1) Synthesis of triphenylphosphine oxide (intermediate 6)

55

[0108] A solution of 26.0 g (110 mmol) of 1,4-dibromobenzene in absolute THF was dripped onto 2.40 g (98.8 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant 6a). To the solution, a solution of 4.6 g (30 mmol) of phosphorus oxychloride (reactant 6b) in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 17 mL of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/ chloroform

from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was further recrystallized. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=515, (molecular weight)+2=517, and (molecular weight)+4=519, and that the crystals obtained were the target intermediate 6 (yield 5.21 g (10.1 mmol), 34%).

5 (1-2) Synthesis of diphenylphosphine oxide (intermediate 7)

10 [0109] A solution of 17.2 g (110 mmol) of bromobenzene in absolute THF was dripped onto 2.4 g (98.8 mmol) of a magnesium metal piece in an atmosphere of nitrogen while cooling the solution to prevent reflux of the solvent, to prepare a Grignard reagent (reactant 7a). To the solution, a solution of 5.18 g (37.5 mmol) of diethylphosphite (reactant 7b) in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 1 mol/l hydrochloric acid was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was further recrystallized. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=203, and that the crystals obtained were the target intermediate 7 (yield 3.57 g (17.7 mmol), 47%).

15 (1-3) Synthesis of TPPO-Burst as the product from the intermediate 6 and the intermediate 7

20 [0110] The intermediate 7 of 2.55 g (12.6 mmol) was reacted with 1.06 g (2.05 mmol) of triphenylphosphine oxide serving as an intermediate b, in 20 ml of DMSO serving a solvent at 100 °C in the presence of 93.3 mg (0.416 mmol) of Pd(OAc)₂, 257 mg (0.623 mmol) of dppp and 3.7 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized, and further purified by sublimation at a degree of vacuum of 2x10⁻⁴ Pa. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=879, and that the crystals obtained were the target TPPO-Burst (yield 1.39 g (1.58 mmol), 77%, T_m: 399 °C, T_g: 149 °C).

25 (2) Properties of the TPPO-Burst

30 (2-1) Ionization potential and band gap

35 [0111] The ionization potential of the TPPO-Burst was measured by an ultraviolet-ray electron spectrometer (AC-2) manufactured by RIKENKEIKI Co., Ltd. and found to be beyond 6.8 eV because the threshold was not detected up to the measurement limit of 6.8 eV. The band gap was 3.96 eV. Thus, it was noted that the TPPO-Burst had a higher ionization potential and a larger band gap than the ionization potential and band gap of bathocuproin which was in general use as an electron-transporting material, as an hole-blocking material and as an exciton-confining material (the ionization potential of bathocuproin: 6.8 eV, the band gap thereof: 3.7 eV). This indicates that TPPO-Burst has a high capability to block holes and a great effect of confining excitons and is promising as a hole-blocking material and as an exciton-confining material for a phosphorescent element

40 (2-2) Glass transition temperature

45 [0112] The T_g of the TPPO-Burst obtained was measured by DSC-6200 manufactured by Seiko Instruments & Electronics Ltd. according to differential thermal analysis, and found to be as high as 149 °C. The T_g of 149 °C is higher than the T_g (63 °C) of N,N'-bis(3-methylphenyl)-N,N'-bis(phenyl)-benzidine (TPD) which is in general use as a hole-transporting material. This indicates that TPPO-Burst has excellent heat resistance.

50 (3) Manufacture of an organic electroluminescent element using TPPO-Burst

55 [0113] Fig. 1 is an explanatory view showing an organic electroluminescent element according to Example 1. The element according to Example 1 was manufactured using TPPO-Burst as an electron-transporting material. The following are details of the constitution of the element (see Fig. 1).

[0114] transparent electrode (ITO)/ hole-transporting and luminescent layer (POF)/ electron-transporting layer (TPPO-Burst) / cathode (MgAg)

[0115] A glass substrate 1 having a transparent electrode (100 nm) of indium tin oxide (ITO) was cleaned ultrasonically sequentially with an alkaline detergent, distilled water, acetone, isopropyl alcohol (IPA) twice each, and dried.

[0116] POF (poly(diethyl-fluorene)) as a conductive polymer was dissolved in methylene chloride, to prepare a solution having a POF content of 10 mg per milliliter of methylene chloride. The solution was dripped onto the ITO electrode and spin-coated onto it at 4000 rpm for 30 seconds, to form a hole-transporting and luminescent layer 2. The POF film obtained had a thickness of 50 nm.

[0117] Next, TPPO-Burst as an electron-transporting material was dissolved in methanol to prepare a solution having a TPPO-Burst content of 16 mg per milliliter of methanol. The solution was dripped onto the hole-transporting and luminescent layer of POF and spin-coated onto it at 4000 rpm for 30 seconds, to form an electron-transporting layer 3. The underlying hole-transporting and luminescent layer showed no change in thickness before and after the spin-coating, and received no damage. The electron-transporting layer obtained had a thickness of 50nm.

[0118] Mg and Ag were co-deposited on the electron-transporting layer, to form a cathode 4 (Mg:Ag = 10:1). The MgAg electrode had a thickness of 100 nm.

(4) Manufacture of an organic electroluminescent element according to Comparative Example 1.

[0119] Fig. 2 is an explanatory view showing an organic electroluminescent element according to Comparative Example 1. The element according to Comparative Example 1 shown in Fig. 2 was manufactured in the same manner as used to obtain the element according to Example 1, except that no electron-transporting layer was formed on the hole-transporting and luminescent layer. However, in Comparative Example 1, the POF as the conductive polymer was dissolved in 16 mg per milliliter of the methylene chloride to prepare the spin-coating solution, and the POF film after the spin-coating had a thickness of 100 nm.

(5) Voltage-luminance characteristics and current-luminance characteristics of the organic electroluminescent elements

[0120] A voltage was applied to each of the elements according to Example 1 and Comparative Example 1, to evaluate their voltage-luminance characteristics and current-luminance characteristics.

[0121] Fig. 3 is a characteristic view showing the voltage-luminance relationships of the elements according to Example 1 and Comparative Example 1.

[0122] Fig. 4 is a characteristic view showing the current-luminance relationships of the elements according to Example 1 and Comparative Example 1.

[0123] As seen from the voltage-luminance characteristics shown in Fig. 3, the use of the TPPO-Burst as the electron-transporting material significantly decreased the driving voltage, presumably by promoting the injection of electrons from the MgAg electrode.

[0124] Also, as seen from the current-luminance characteristics shown in Fig. 4, the use of the TPPO-Burst as the electron-transporting material significantly improved the luminance of the element in relation to the current, presumably by improving the injection balance between electrons and holes due to the exciton-confining effect of the TPPO-Burst.

(Example 2)

(1) Manufacture of an organic electroluminescent element having a hole-injecting layer

[0125] Fig. 5 is an explanatory view showing an organic electroluminescent element according to Example 2 of the present invention.

[0126] The organic electroluminescent element according to Examle 2 shown in Fig. 5 was manufactured in the same manner as used to obtain the element according to Example 1, except that a hole-injecting layer 5 was formed between the transparent electrode and the hole-transporting and luminescent layer. The following are details of the constitution of the organic electroluminescent element according to Example 2.

transparent electrode (ITO)/ hole-injecting layer (PEDT/PSS)/
hole-transporting and luminescent layer (POF)/ electron-transporting layer
(TPPO-Burst)/ cathode (MgAg)

[0127] An aqueous solution of PEDT/PSS (polyethylene dioxythiophene/polystyrene sulfonic acid) manufactured by Bayer AG. was used as a hole-injecting material. The solution was dripped onto the transparent electrode and spin-coated onto it at 1000 rpm for 180 seconds to form the hole-injecting layer 5. Further, as in Example 1, the hole-transporting and luminescent layer, the electron-transporting layer and the cathode were sequentially laminated to manufacture the element. The hole-transporting and luminescent layer and the hole-injecting layer showed no change in thickness before and after the spin-coating conducted for the lamination of the electron-transporting layer on the hole-transporting and luminescent layer, and received no damage. This is attributable to the fact that the POF as the hole-injecting layer material and the PEDT/PSS as the luminescent layer material were insoluble in alcohols (in this Example, methanol).

(2) Manufacture of an organic electroluminescent element according to Comparative Example 2

[0128] Fig. 6 is an explanatory view showing an organic electroluminescent element according to Comparative Example 2.

[0129] The organic electroluminescent element according to Comparative Example 2 shown in Fig. 6 was manufactured in the same manner as used to obtain the element according to Example 1, except that no electron-transporting layer was formed on the hole-transporting and luminescent layer 2.

(3) Voltage-luminance characteristics and current-luminance characteristics of the organic electroluminescent elements

[0130] A voltage was applied to each of the elements of Example 2 and Comparative Example 2 to evaluate their voltage-luminance characteristics and current-luminance characteristics.

[0131] Fig. 7 is a characteristic view showing the voltage-luminance relationships of the elements according to Example 2 and Comparative Example 2.

[0132] Fig. 8 is a characteristic view showing the current-luminance relationships of the elements according to Example 2 and Comparative Example 2.

[0133] As seen from the voltage-luminance characteristics shown in Fig. 7, the use of TPPO-Burst as the electron-transporting material decreased the driving voltage by about 3V. Also, as seen from the current-luminance characteristics shown in Fig. 8, the elements according to Example 2 and Comparative Example 2 that had the hole-injecting layer of PEDT/PSS, unlike the element according to Example 1 that has no hole-injecting layer (see Fig. 4), were not subject to instability in current-luminance characteristics, presumably because the hole-injecting layer of PEDT/PSS increased the total thickness of the organic compound layers and as a result, prevented contact and electrical continuity between the transparent electrode (anode) and the rear electrode.

(4) Voltage-vs.-EL-efficiency characteristics of the organic electroluminescent elements

[0134] The voltage-vs.-EL-efficiency characteristics of the elements of Example 2 and Comparative Example 2 were evaluated. Fig. 9 is a characteristic view showing the voltage-vs.-EL-efficiency relationships of the elements according to Example 2 and Comparative Example 2.

[0135] As seen in Fig. 9, the lamination of the electron-transporting layer of TPPO-Burst improved the EL efficiency about fivefold.

(Example 3)

(1) Manufacture of an organic electroluminescent element

[0136] An organic electroluminescent element according to Example 3 was manufactured in the same manner as used to obtain the element according to Example 2 shown in Fig. 2, except that PVK (polyvinyl carbazole) and Ir(ppy)₃ (tris(2-phenylpyridine)iridium) were used as the materials of the hole-transporting and luminescent layer. The following are details of the constitution of the element

transparent electrode (ITO)/ hole-injecting layer (PEDT/PSS)/ hole-transporting and luminescent layer (PVK: Ir(ppy)₃)/ electron-transporting layer (TPPO-Burst) cathode (MgAg)

[0137] The hole-transporting and luminescent layer was formed as follows. First, a predetermined amount of PVK was fed into a vial, and next, 10 parts by weight of Ir(ppy)₃ with respect to 100 parts by weight of the PVK were fed into it. After that, the PVK and Ir(ppy)₃ were dissolved in 1 ml of THF serving as the solvent to prepare a solution having a PVK content of 14 mg per milliliter of THF serving as the solvent. The solution was dripped onto the hole-injecting layer and spin-coated onto it at 4000 rpm for 30 seconds to form the hole-transporting and luminescent layer. The hole-transporting and luminescent layer had a thickness of 60 nm.

[0138] As in Example 2, the electron-transporting layer and the cathode were sequentially laminated to manufacture the element. However, the electron-transporting layer had a thickness of 60 nm. As in Example 2, the hole-transporting and luminescent layer and the hole-injecting layer showed no change in thickness before and after the spin-coating conducted for the lamination of the electron-transporting layer on the hole-transporting and luminescent layer, and received no damage.

[0139] TPPO-Burst films were formed by a wet method and a dry method and the arithmetical mean roughnesses (Ra) of their surfaces were measured as follows. Methanol, ethanol, 2-propanol, 1-propanol, 1-butanol, 2-butanol, 2-methyl-1-propanol, and 2-methyl-2-propanol were used as solvents to dissolve the TPPO-Burst. Solutions with a TPPO-Burst content of 16 mg per milliliter of each solvent were spin-coated at 4000 rpm for 30 seconds to form thin films. Some of the thin films obtained were dried at room temperature and the other at 105 °C for 1 hour. Further, as contrasts, TPPO-Burst thin films were formed by a vacuum deposition method. The surface conditions of the thin films were observed through a scanning probe microscope (SPI4000N) manufactured by Seiko Instruments Inc. and an atomic force microscope (AFM), and quantitatively evaluated using the arithmetical mean roughness (Ra) as an indicator of the surface conditions.

[0140] The surface conditions of thin films were assumed to be subject to their underlying substrates, and two types of substrates were prepared: substrates of quartz and substrates comprising a transparent electrode (ITO)/ a hole-injecting layer (PEDT/PSS)/ a hole-transporting and luminescent layer (PVK: Ir(ppy)₃). Each of the substrates comprising the transparent electrode (ITO)/ the hole-injecting layer (PEDT/PSS)/ the hole-transporting and luminescent layer (PVK: Ir(ppy)₃) was produced as follows. An aqueous solution was prepared using PEDT/PSS (polyethylenedioxythiophene/polystyrene sulfonic acid) manufactured by Bayer AG. as the hole-injecting material. The solution was dripped onto the transparent electrode and spin-coated onto it at 1000 rpm for 180 seconds to form the hole-injecting layer (PEDT/PSS). After that, the hole-transporting and luminescent layer was formed as follows. First, a predetermined amount of PVK was fed into a vial and next, 10 parts by weight of Ir(ppy)₃ with respect to 100 parts by weight of the PVK were fed into it. Then, the PVK and Ir(ppy)₃ were dissolved in 1 ml of THF serving as a solvent to prepare a solution having a PVK content of 14 mg per milliliter of THF serving as the solvent. The solution was dripped onto the hole-injecting layer and spin-coated onto it at 4000 rpm for 30 seconds to form the hole-transporting and luminescent layer.

[0141] The tables below show the arithmetical mean roughnesses (Ra) obtained, together with: the drying conditions; the underlying substrates; and the solvents to dissolve the TPPO-Burst.

Table 1

Drying condition	Underlying substrate	Solvent to dissolve TPPO-Burst	Arithmetical mean roughness *1
			Unit: nm
No drying by heating	Quartz substrate	Methanol	0.35
No drying by heating	Quartz substrate	Ethanol	0.27
No drying by heating	Quartz substrate	2-propanol	0.39
No drying by heating	Quartz substrate	1-propanol	0.35
No drying by heating	Quartz substrate	1-butanol	0.37
No drying by heating	Quartz substrate	2-butanol	0.40
No drying by heating	Quartz substrate	2-methyl-1-propanol	0.39
No drying by heating	Quartz substrate	2-methyl-2-propanol	0.34
105°C,1h	Quartz substrate	Methanol	0.65
105°C,1h	Quartz substrate	Ethanol	0.79
105°C,1h	Quartz substrate	2-propanol	0.43
105°C,1h	Quartz substrate	1-propanol	0.55
105°C,1h	Quartz substrate	1-butanol	0.64
105°C,1h	Quartz substrate	2-butanol	0.61
105°C,1h	Quartz substrate	2-methyl-1-propanol	0.45
105°C,1h	Quartz substrate	2-methyl-2-propanol	0.46

(continued)

5	Drying condition	Underlying substrate	Solvent to dissolve TPPO-Burst	Arithmetical mean roughness *1
				Unit: nm
	-	Quartz substrate	(Film is made by vacuum deposition)	0.33

*1: Calculated for a length of about 15 nm on a line made in parallel to a scanning direction.

10

Table 2

15	Drying condition	Underlying condition	Solvent to dissolve TPPO-Burst	Arithmetical mean roughness *1
				Unit: nm
	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	Methanol	9.00
20	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	Ethanol	0.20
25	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	2-propanol	0.57
30	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	1-propanol	0.43
35	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	1-butanol	0.52
40	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	2-butanol	0.53
45	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	2-methyl-1-propanol	0.58
	No dryng by heating	ITO/PEDOT/PVK:Ir(ppy) ₃	2-methyl-2-propanol	0.64
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	Methanol	9.18
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	Ethanol	0.18
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	2-propanol	0.28
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	1-propanol	0.34
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	1-butanol	0.52
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	2-butanol	0.47
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	2-methyl-1-propanol	0.46
	105°C, 1h	ITO/PEDOT/PVK:Ir(ppy) ₃	2-methyl-2-propanol	0.52

*1: Calculated for a length of about 15 nm on a line made in parallel to a scanning direction.

50

[0142] Shown in the table below for reference are the properties of underlying substrate materials.

Table 3

Method/material	Drying Condition	Underlying substrate	Solvent to dissolve material	Arithmetical mean roughness *1 (Unit: nm)
Spin coating Method /(PEDT-PSS)	105°C, 1h	ITO glass	Water	1.05

(continued)

Method/material	Drying Condition	Underlying substrate	Solvent to dissolve material	Arithmetical mean roughness *1 (Unit: nm)
5 Spin coating Method /(PVK:Ir(ppy) ₃)	105°C, 1h	(ITO)/(PEDT/PSS)	THF	0.55

*1: Calculated for a length of about 15 nm on a line made in parallel to a scanning direction.

10 [0143] As shown in Table 1, the surfaces of the thin films formed on the quartz substrates by spin-coating the TPPO-Burst solutions in the alcohols had arithmetical mean roughnesses Ra of 1 nm or less, indicating that the surfaces of these films were smooth enough to permit manufacture of organic electroluminescent elements.

15 [0144] Table 2 shows the arithmetical mean roughnesses Ra of the thin films formed by spin-coating the TPPO-Burst solutions in the alcohols on the film of conductive polymer PVK: Ir(ppy)₃ which was actually used as the hole-transporting and luminescent layer of the organic electroluminescent element. It was noted that the Ra were 10 nm or less, indicating that the surfaces of the thin films were smooth enough to permit manufacture of organic electroluminescent elements. Also, it is noted that while the surfaces of thin films formed by spin-coating solutions in methanol had Ra of about 9 nm, the surfaces of the other thin films formed by spin-coating solutions in the other solvents had an Ra of 0.7 nm or less, about an order of magnitude smaller. This indicates that the solvents other than methanol are more suitable for spin-coating than methanol.

20 (3) Manufacture of an organic electroluminescent element according to Comparative Example 3

25 [0145] An element according to Comparative Example 3 was manufactured in the same manner as used to obtain the element according to Example 3, except that no electron-transporting layer was formed on the hole-transporting and luminescent layer. It is to be noted that the hole-transporting and luminescent layer was formed on the hole-injecting layer by spin-coating at 2000 rpm for 30 seconds the same PVK: Ir(ppy)₃ solution in THF as used in Example 3. The hole-transporting and luminescent layer had a thickness of 90 nm.

30 (4) Voltage-luminance characteristics and current-luminance characteristics of the organic electroluminescent elements

35 [0146] A voltage was applied to each of the elements of Example 3 and Comparative Example 3 to evaluate their voltage-luminance characteristics and current-luminance characteristics.

[0147] Fig. 10 is a characteristic view showing the voltage-luminance relationships of the elements according to Example 3 and Comparative Example 3.

[0148] Fig. 11 is a characteristic view showing the current-luminance relationships of the elements according to Example 3 and Comparative Example 3.

[0149] As seen from the voltage-luminance characteristics shown in Fig. 10, the use of the TPPO-Burst as the electron-transporting material decreased the driving voltage by about 6 V. Also, as seen from the current-luminance characteristics shown in Fig. 11, the use of the TPPO-Burst improved the luminance of the element in relation to the current.

40 (5) Voltage-vs.-EL-efficiency characteristics of the organic electroluminescent elements


[0150] The voltage-vs.-EL-efficiency characteristics of the elements according to Example 3 and Comparative Example 3 were evaluated. Fig. 12 is a characteristic view showing the voltage-vs.-EL-efficiency relationships of the elements according to Example 3 and Comparative Example 3.

[0151] As seen in Fig. 12, the lamination of the TPPO-Burst as the electron-transporting layer improved the EL efficiency about 3.8-fold.

50 (Example 4)

Synthesis of 4,4'-bis(diphenylphosphinyl)-triphenylphosphine oxide [TPPO-Trimer]

[0152] TPPO-Trimer was synthesized as shown in the following reaction scheme. First, phosphine oxide (intermediate) was synthesized and then, from this intermediate, the TPPO-Trimer was synthesized.



20

25

30

[0153] A solution of 29.3 g (124 mmol) of 1,4-dibromobenzene in absolute tetrahydrofuran (hereafter, referred to as THF) was dripped onto 2.54 g (105 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant 7b). To the solution, a solution of 6.99 g (35.9 mmol) of dichlorophenylphosphine oxide in absolute diethyl ether was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 14 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/ chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from cyclohexane. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=436, (molecular weight)+2=438, and (molecular weight)+4=440 and that the crystals obtained were the target intermediate (yield 4.93 g (11.30 mmol), 31.6%).

35

40

(Synthesis from the intermediate)

45

[0154] The intermediate of 2.42 g (5.55 mmol) was reacted with 4.48 g (22.1 mmol) of diphenylphosphine oxide serving as an intermediate 1, in 55.6 ml of dimethyl sulfoxide (hereafter, referred to as DMSO) serving as a solvent at 100 °C in the presence of 250 mg (1.11 mol) of palladium acetate (hereafter, referred to as Pd(OAc)₂), 688 mg (1.67 mmol) of 1,3-bis(diphenylphosphino) propane (hereafter, referred to as dppp), and 10 ml of N-ethyldiisopropylamine (edpa). The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. The target compound was recrystallized, and purified by sublimation in a vacuum at 330-340 °C, to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight) = 679 and that the crystals obtained were the target TPPO-Trimer (yield 2.12 g (3.12 mmol), 56%, Tm: 346 °C, Tg: 105 °C).

50


(Example 5)


45

Synthesis of 4,4',4''-tris-(di-p-tolyl-phosphinyl)- triphenylphosphine oxide [TPPO-(p-CH₃) Burst]

55

[0155] TPPO-(p-CH₃) Burst was synthesized as shown in the following reaction scheme. First, di-p-tolyl-phosphine oxide(intermediate a) was synthesized, and then from this intermediate a and the intermediate b, the TPPO-(p-CH₃) Burst was synthesized.





15 [0156] A solution of 25 g (145.9 mmol) of p-bromotoluene in absolute diethyl ether was dripped onto 3.0 g (123.5 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 8.64 g (62.59 mmol) of diethylphosphite in absolute diethyl ether was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 14 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from diethyl ether. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=231 and that the crystals obtained were the target intermediate a (yield 5.76 g (25.02 mmol), 40%)


30 (Synthesis from the intermediates a and b)


30 [0157] The intermediate a of 2.88 g (12.51 mmol) was reacted with 1.07 g (2.08 mmol) of triphenylphosphine oxide serving as the intermediate b, in 20.8 ml of DMSO serving as a solvent at 100 °C in the presence of 93.3 mg (0.416 mmol) of Pd(OAc)₂, 257 mg (0.624 mmol) of dppp, and 3.7 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from methanol/toluene, to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=963 and that the crystals obtained were the target TPPO-(p-CH₃)Burst (yield 1.17 g (1.22 mmol), 59%, Tm:335 °C, Tg:133 °C).

40 (Example 6)

Synthesis of 4,4',4"-tris-(di-o-tolyl-phosphinyl)-triphenylphosphine oxide[TPPO-(o-CH₃)Burst]

45 [0158] TPPO-(o-CH₃)Burst was synthesized as shown in the following reaction scheme. First, di-o-tolyl-phosphine oxide (intermediate a) was synthesized, and then from this intermediate a and the intermediate b, the TPPO-(o-CH₃)Burst was synthesized.





15 (Synthesis of the intermediate a)

[0159] A solution of 25 g (145.9 mmol) of o-bromotoluene in absolute diethyl ether is dripped onto 3.0 g (123.5 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 8.64 g (62.59 mmol) of diethylphosphite in absolute diethyl ether was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 14 ml of hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from diethyl ether. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=231 and that the crystals obtained were the target intermediate a (yield 6.67 g (29.0 mmol), 46%).


(Synthesis from the intermediates a and b)


[0160] The intermediate a of 2.89 g (12.6 mmol) was reacted with 1.07 g (2.08 mmol) of triphenylphosphine oxide serving as the intermediate b, in 20.8 ml of DMSO serving as a solvent at 100 °C in the presence of 93.3 mg (0.416 mmol) of $\text{Pd}(\text{OAc})_2$, 257 mg (0.624 mmol) of dppp, and 3.7 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=963, and that the crystals obtained were the target TPPO-(o-CH₃)Burst (yield 1.50 g (1.56 mmol), 75%, T_m: 310 °C, T_g:133 °C).


(Example 7)

Synthesis of 4,4',4"-tris-(di-m-tolyl-phosphinyl)-triphenylphosphine oxide[TPPO-(m-CH₃)Burst]

[0161] TPPO-(m-CH₃)Burst was synthesized as shown in the following reaction scheme. First, di-m-tolyl-phosphine oxide (intermediate a) was synthesized, and then from the intermediate a and the intermediate b, the TPPO-(m-CH₃)Burst was synthesized.







15 (Synthesis of the intermediate a)

[0165] A solution of 25.0 g (134 mmol) of p-bromoanisole in absolute THF was dripped onto 2.92 g (120.2 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 8.69 g (60.3 mmol) of diethylphosphite in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, a 14 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from cyclohexane. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=263, and that the crystals obtained were the target intermediate (yield 8.20 g (31.3 mmol), 52%).


(Synthesis from the intermediates a and b)


[0166] The intermediate a of 3.30 g (12.6 mmol) was reacted with 1.07 g (2.08 mmol) of triphenylphosphine oxide as the intermediate b, in 20.8 ml of DMSO serving as a solvent at 100 °C in the presence of 93.3 mg (0.624 mmol) of Pd(OAc)₂, 257 mg (0.416 mmol) of dppp, and 3.7 ml of edpa. The target compound was extracted with chloroform/distilled water from the solution, and the chloroform phase was separated and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from methanol/toluene to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=1059, and that the crystals obtained were the target TPPO-(p-OCH₃)Burst (yield 1.56 g (1.47 mmol), 71%, T_m: 378 °C, T_g: 127 °C).

40 (Example 9)

Synthesis of 4,4',4''-tris-(bis-(2-methoxy-phenyl)-phosphinyl)-triphenylphosphine oxide[TPPO-(o-OCH₃)₃Burst]

[0167] TPPO-(o-OCH₃)Burst was synthesized as shown in the following reaction scheme. First, di(2-methoxy-phenyl)phosphine oxide (intermediate a) was synthesized, and then from the intermediate a and the intermediate b, the TPPO-(o-OCH₃)Burst was synthesized.





[0168] A solution of 12.5 g (66.8 mmol) of o-bromoanisole in absolute THF was dripped onto 1.51 g (62.1 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 4.43 g (32.1mmol) of diethylphosphite in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 8 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from cyclohexane. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=263, and that the crystals obtained were the target intermediate (yield 4.38 g (16.7mmol), 52%).


(Synthesis from the intermediates a and b)


[0169] The intermediate a of 2.00 g (7.63 mmol) was reacted with 0.655 g (1.27 mmol) of triphenylphosphine oxide as the intermediate b, in 13.0 ml of DMSO serving as a solvent at 100 °C in the presence of 57.2 mg (0.254 mmol) of Pd(OAc)₂, 157 mg (0.381 mmol) of dppp, and 2.3 ml of edpa. The target compound was extracted with chloroform/distilled water from the solution, and the chloroform phase was separated and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from methanol/toluene to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=1059, and that the crystals obtained were the target TPPO-(o-OCH₃)Burst (yield 0.80 g (0.755 mmol, 56%).

(Example 10)

Synthesis of tris-(4'-diphenylphosphinyl-biphenyl-4-yl)-phosphine oxide [TBPO-(DPPO)Burst]

[0170] TBPO-(DPPO)Burst was synthesized as shown in the following reaction scheme. First, phosphine oxide (intermediate a) was synthesized, and then from the intermediate a, the TBPO-(DPPO)Burst was synthesized.





15 (Synthesis of the intermediate a)

[0171] A solution of 74.9 g (240 mmol) of 4,4'-dibromobiphenyl in absolute THF was dripped onto 4.8 g (197.5 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 10.2 g (66.6 mmol) of phosphoryl chloride (reactant) in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 50 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from cyclohexane. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=743, (molecular weight)+2=745, and (molecular weight)+4=747, and that the crystals obtained were the target intermediate a (yield 38.1 g (51.3 mmol), 77%).


30 (Synthesis from the intermediate a)

[0172] The intermediate a of 0.6 g (1.16 mmol) was reacted with 1.4 g (6.69 mmol) of diphenylphosphine oxide, in 11.6 ml DMSO serving as a solvent at 100 °C in the presence of 52.4 mg (0.233 mmol) of Pd(OAc)₂, 144 mg (0.349 mmol) of dppp, and 2.1 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from methanol/toluene. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=1107, and that the crystals obtained were the target TBPO-(DPPO)Burst (yield 0.618 g (0.70 mmol), 61%).


40 (Example 11)

Synthesis of 4,4',4"-tris-(1-naphthyl-phenyl-phosphinyl)-triphenylphosphine oxide[TPPO-(α -NPPO)Burst]

[0173] TPPO-(α -NPPO)Burst was synthesized as shown in the following reaction scheme. First, 1-naphthyl-phenyl-phosphine oxide (intermediate a) was synthesized, and from the intermediate a and the intermediate b, the TPPO-(α -NPPO)Burst was synthesized.



55



15

[0174] A solution of 28.35 g (137 mmol) of 1-bromonaphthalene in absolute THF was dripped onto 3.15 g (129.6 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 26.0 g (145 mmol) of dichlorophenylphosphine in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 21 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/ chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from cyclohexane. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=253, and that the crystals obtained were the target intermediate (yield 12.7 g (50.3 mmol), 36%).

20

25

30

35

40

(Synthesis from the intermediates a and b)

[0175] The intermediate a of 4.03 g (16.0mmol) was reacted with 1.17 g (2.28 mmol) of triphenylphosphine oxide as the intermediate b, in 22.8 ml of DMSO serving as a solvent at 100 °C in the presence of 144 mg (0.643 mmol) of Pd(OAc)₂, 377mg (0.915 mmol) of dppp, and 4.2 ml of edpa. The target compound was extracted with chloroform/distilled water from the solution, and the chloroform phase was separated and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from cyclohexane/toluene, to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=1029, and that the crystals obtained were the target TPPO-(α -NPPO)Burst (yield 1.75 g (1.70mmol), 75%).

45


50


55

(Example 12)

Synthesis of 4,4',4"-tris-(di-1-naphthyl-phosphinyl)-triphenylphosphine oxide[TPPO-(α -DNPO)Burst]

[0176] TPPO-(α -DNPO)Burst was synthesized as shown in the following reaction scheme. First, di-1-naphthylphosphine oxide(intermediate a) was synthesized, and then from the intermediate a and the intermediate b, TPPO-(α -DNPO)Burst was synthesized.





(Synthesis of the intermediate a)

[0177] A solution of 114 g (551 mmol) of 1-bromonaphthalene in absolute THF was dripped onto 12.6 g (519 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 34.0 g (246 mmol) of diethylphosphite in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was heated under reflux overnight. To the solution, 200 ml of a hydrochloric acid solution (concentration 18%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from ether. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=303, and that the crystals obtained were the target intermediate a (yield 52.8 g (175 mmol), 71%).


(Synthesis from the intermediates a and b)

[0178] The intermediate a of 13.59 g (45 mmol) was reacted with 3.86 g (7.5 mmol) of triphenylphosphine oxide serving as the intermediate b, in 75 ml of DMSO serving as a solvent at 100 °C in the presence of 338 mg (1.5 mmol) of Pd(OAc)2, 927 mg (2.25 mmol) of dppp, 13.5 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from methanol/toluene to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=1179, and that the crystals obtained were the target TPPO-(DNPO)Burst (yield 6.03 g (5.11 mmol), 68%).

(Example 13)

Synthesis of 1,3,5-tris(diphenylphosphinyl)benzene [referred to as TDPPOB]

[0179] TDPPOB was synthesized from 1,3,5-tribromobenzene (reactant 1a) and diphenylphosphine oxide (intermediate 1), as shown in the following reaction scheme.



[0180] Commercially available 1,3,5-Tribromobenzene (reactant 1a) of 0.63 g (2 mmol) was reacted with 1.21 g (6.0 mmol) of diphenylphosphine oxide (intermediate 1), in 20 ml of DMSO serving as a solvent at 100 °C in the presence of 93 mg (0.41 mmol) of Pd(OAc)2, 3.7 ml of edpa, and 261 mg (0.63 mmol) of dppp. The target compound was extracted


with chloroform/distilled water from the solution, and the chloroform phase was separated and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized, and purified by sublimation in a vacuum. The target compound obtained was subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=679, and that the crystals obtained were the target TDPPOB (product) (yield 0.64 g (0.94 mmol), 47%, Tg 79.7 °C).

(Example 14)

10 Synthesis of tris-(dibiphenyl-phosphinyl)triphenylphosphine oxide [TRIS-(DBPPO)-TPPO-Burst]

[0181] TRIS-(DBPPO)-TPPO-Burst was synthesized as shown in the following reaction scheme. First, OBPPO (intermediate a) was synthesized, and from the intermediate a and the intermediate b, the TRIS-(DBPPO)-TPPO-Burst was synthesized.

15



(Synthesis of the intermediate a)

40 [0182] A solution of 100.0 g (388.5 mmol) of 4-bromobiphenyl in absolute THF was dripped onto 10.4 g (428 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 29.5 g (213.6 mmol) of diethylphosphite in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 40 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from diethyl ether. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=355, and that the crystals obtained were the target intermediate a (yield 22.73g (64.2 mmol), 30%).

45 (Synthesis from the intermediates a and b)


50 [0183] The intermediate a of 18.5 g (52.3 mmol) was reacted with 3.9 g (7.6mmol) of triphenylphosphine oxide serving as the intermediate b, in DMSO serving as a solvent at 100 °C in the presence of 250 mg (1.1 mmol) of Pd(OAc)₂,460 mg (1.1 mmol)of dppp, and 7.7 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After

the separation, the target compound was recrystallized from cyclohexane, to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=1335, and that the crystals obtained were the target TRIS-(DBPPO)-TPPO-Burst (yield 2.8 g (2.1 mmol), 28%).

5 (Example 15)

Synthesis of bis-(dibiphenyl-phosphinyl)-biphenylene [BIS(OBPPO)-BP]

10 [0184] BIS(OBPPO)-BP was synthesized from OBPPO (intermediate a) and 4,4'-dibromobiphenyl, as shown in the following reaction scheme.




(Synthesis of the intermediate a and 4,4'-dibromobiphenyl)

25 [0185] The intermediate a of 18.49 g (52.2 mmol) was reacted with 3.61 g (11.6 mmol) of 4,4'-dibromobiphenyl, in DMSO serving as a solvent at 100 °C, in the presence of 250 mg (1.1 mmol) of Pd(OAc)₂, 460mg (1.1 mmol) of dppp, and 7.9 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the 30 target compound was recrystallized. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=858, and that the crystals obtained were the target BIS(OBPPO)-BP (yield 7.7 g (9.0 mmol), 77%).

(Example 16)


35 Synthesis of tris-(t-butyl-diphenyl-phosphinyl)triphenylphosphine oxide[TRIS-(t-Bu-DPPO)-TPPO-Burst]

40 [0186] TRIS-(t-Bu-DPPO)-TPPO-Burst was synthesized as shown in the following reaction scheme. First, t-Bu-DPPO (intermediate c) was synthesized, and then from the intermediate c and the intermediate b, the TRIS-(t-Bu-DPPO)-TPPO-Burst was synthesized.



50

55



[0187] A solution of 25.0g (117.3 mmol) of 4-t-butyl-bromobenzene in absolute THF was dripped onto 2.85 g (117.3 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant). To the solution, a solution of 8.10 g (58.66 mmol) of diethylphosphite in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 30 ml of a hydrochloric acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from diethyl ether. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=315, and that the crystals obtained were the target intermediate c (yield 8.65 g (18.4 mmol), 47%).


(Synthesis from the intermediates c and b)

[0188] The intermediate c of 15.5 g (49.4 mmol) was reacted with 4.2 g (8.2 mmol) of triphenylphosphine oxide serving as the intermediate b, in DMSO serving as a solvent at 100 °C in the presence of 270 mg (1.2 mmol) of Pd(OAc)₂, 510 mg (1.2 mmol) of dppp, and 8.4 ml of edpa. The target compound was extracted with distilled water/chloroform from the solution and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from toluene-chloroform, to obtain a white crystal. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=1215 and that the crystals obtained were the target TRIS-(t-Bu-DPPO)-TPPO-Burst (yield 1.5 g (1.2 mmol), 15%).

(Example 17)

Synthesis of 4,4'-bis(diphenylphosphinyl)-biphenyl [TPPO-Dimer]

[0189] TPPO-Dimer was synthesized as shown in the following reaction scheme. First, diphenylphosphine oxide as an intermediate 1 was synthesized, and then from the intermediate 1, the TPPO-Dimer was synthesized.



(Synthesis of the intermediate 1)

[0190] A solution of 17.2 g (110 mmol) of bromobenzene in absolute THF was dripped onto 2.4 g (98.8 mmol) of a magnesium metal piece in an atmosphere of nitrogen while cooling the solution to prevent reflux of the solvent, to prepare a Grignard reagent (reactant 1). To the solution, 5.18 g (37.5 mmol) of diethylphosphite (reactant 2) in absolute THF was slowly dropwise added. After completion of the addition, the resulting solution was stirred overnight. To the solution, 1 mol/l hydrochloric acid was added dropwise. The target compound was extracted with distilled water/chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from diethyl ether. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=203 and that the crystals obtained were the target intermediate 1 (yield 3.57 g (17.7 mmol), 47%).



(Synthesis from the intermediate 1)

[0191] The intermediate 1 of 4.04 g (20 mmol) was reacted with 3.12 g (10 mmol) of commercially available 4,4'-dibromobiphenyl (reactant 3), in DMSO serving as a solvent at 100 °C in the presence of 89.8 mg (0.4 mmol) of $\text{Pd}(\text{OAc})_2$, 247 mg (0.6 mmol) of dppp, and 9 ml of edpa. The target compound was extracted with chloroform/distilled water from the solution, and the chloroform phase was separated and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized, and purified by sublimation in a vacuum. The target compound obtained was subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=555, and that the crystals obtained were the target TPPO-Dimer (product) (yield 4.56 g (8.22 mmol), 82%).

(Example 18)

Synthesis of [4,4-bis[(1-naphthyl)-phenyl-phosphinyl]]-biphenyl[α -NPPOB]

[0192] α -NPPOB was synthesized as shown in the following reaction scheme. First, (1-naphthyl)-phenyl-phosphine oxide (intermediate 1d) was synthesized, and then from the intermediate 1d, the α -NPPOB was synthesized.



(Synthesis of the intermediate 1d)

[0193] A solution of 28.35 g (137 mmol) of 1-bromonaphthalene in absolute THF was dripped onto 3.15 g (129.6 mmol) of a magnesium metal piece in an atmosphere of nitrogen, to prepare a Grignard reagent (reactant 1d). The solution was slowly dropwise added to a solution of 26.0 g (145 mmol) of dichlorophenylphosphine (reactant 2d) in absolute THF. After completion of the addition, the resulting solution was stirred overnight. To the solution, 21 ml of a hydrochloric

acid solution (concentration 36%) was added dropwise. The target compound was extracted with distilled water/ chloroform from the solution, and the chloroform phase was separated, and concentrated by a rotary evaporator. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized from cyclohexane. The crystals obtained were subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)+1=253, and that the crystals obtained were the target intermediate 1d (yield 12.7 g (50.3 mmol), 36%).

(Synthesis from the intermediate 1d)

[0194] The intermediate 1 of 5.04 g (20 mmol) was reacted with 3.12 g (10 mmol) of commercially available 4,4'-dibromobiphenyl (reactant 3), in DMSO serving as a solvent at 100 °C in the presence of 89.8 mg (0.4mmol) of Pd(OAc)₂, 247 mg (0.6 mmol) of dppp, and 9 ml of edpa. The target compound was extracted with chloroform/ distilled water from the solution, and the chloroform phase was separated and concentrated. The remaining viscous liquid was dissolved in a small amount of chloroform, and the resulting solution was subjected to column chromatography that used silica gel as a filler, to separate the target compound. After the separation, the target compound was recrystallized, and purified by sublimation in a vacuum. The target compound obtained was subjected to FAB mass analysis, whereby it was confirmed that (molecular weight)=655, and that the crystals obtained were the target α -NPPOB (product) (yield 5.15 g (7.87 mmol), 79%).

(Example 19)

[0195] The TPPO-Dimer prepared in Example 17 was evaluated.

[Properties of the TPPO-Dimer]

(Ionization potential and band gap)

[0196] The ionization potential of the TPPO-Dimer obtained was measured by an ultraviolet-ray electron spectrometer (AC-2) manufactured by RIKENKEIKI Co., Ltd. and found to be beyond 6.8 eV because the threshold was not detected up to the measurement limit of 6.8 eV. The band gap was 4.07 eV. Thus, it was noted that the TPPO-Dimer had a higher ionization potential and a larger band gap than the ionization potential and band gap of bathocuproin which was in general use as an electron-transporting material, as an hole-blocking material and as an exciton-confining material (the ionization potential of bathocuproin: 6.8 eV, the band gap thereof: 3.7 eV). This indicates that TPPO-Dimer has a high capability to block holes and a great effect of confining excitons and is promising as a hole-blocking material and as an exciton-confining material for a phosphorescent element.

(Glass transition temperature)

[0197] The Tg of the TPPO-Dimer was measured by DSC-6200 manufactured by Seiko Instruments & Electronics Ltd. according to differential thermal analysis, and found to be as high as 90.8 °C. The Tg of 90.8 °C is higher than the Tg (63 °C) of N,N'-bis(3-methylphenyl)-N,N'-bis(phenyl)-benzidine (TPD) which is in general use as a hole-transporting material. This indicates that TPPO-Dimer has excellent heat resistance.

[Manufacture of an organic electroluminescent element using TPPO-Dimer]

[0198] An organic electroluminescent element was manufactured using TPPO-Dimer as an electron-transporting material. The following are details of the constitution of the element
transparent electrode (ITO)/ hole-transporting layer (TPD)/ luminescent layer (Alq₃)/ electron-transporting layer (TPPO-Dimer)/ cathode(MgAg)

[0199] More specifically, TPD was vacuum-deposited on a glass substrate having a transparent electrode (100 nm) of ITO, to form a hole-transporting layer thereon. The degree of vacuum was 2.0x10⁻⁴ Pa (ditto with Example 20 and later Examples), and the thickness of the hole-transporting layer was 55 nm. On the hole-transporting layer, Alq₃ was deposited to form a luminescent layer having a thickness of 20 nm. The deposition speed was 0.2 nm/ sec. On the luminescent layer, TPPO-Dimer was deposited to form an electron-transporting layer having a thickness of 30 nm. On the electron-transporting layer, Mg and Ag were deposited to a thickness of 100 nm to form a cathode.

(Comparative Example 4)

[0200] An element according to Comparative Example 4 was manufactured in the same manner as in Example 19, except that TPPO-Dimer was not employed as the electron-transporting material and that the luminescent layer (Alq_3) formed had a thickness of 50 nm.

[Luminance-voltage characteristics of the organic electroluminescent elements]

[0201] A voltage was applied to each of the elements according to Example 19 and Comparative Example 4, to evaluate their luminance-voltage characteristics.

[0202] Fig. 13 is a characteristic view showing the luminance-voltage relationships of the elements according to Example 19 and Comparative Example 4.

[0203] As seen in Fig. 13, the element according to Example 19 emitted light at a lower voltage than the element according to Comparative Example 4. This indicates that TPPO-Dimer has a high capability to transport electrons.

(Example 20)

[0204] The characteristics of the TDPPOB prepared in Example 13 were evaluated.

[Properties of the TDPPOB]

(Ionization potential and band gap)

[0205] The ionization potential of the TDPPOB was measured by an ultraviolet-ray electron spectrometer (AC-2) manufactured by RIKENKEIKI Co., Ltd. and found to be beyond 6.8 eV because the threshold was not detected up to the measurement limit of 6.8 eV. The band gap was 3.98 eV. Thus, it was noted that the TDPPOB had a higher ionization potential and a larger band gap than the ionization potential and band gap of bathocuproin which was in general use as an electron-transporting material, as an hole-blocking material and as an exciton-confining material (the ionization potential of bathocuproin: 6.8 eV, the band gap thereof: 3.7 eV). This indicates that TDPPOB has a high capability to block holes and a great effect of confining excitons and is promising as a hole-blocking material and as an exciton-confining material for a phosphorescent element.

(Glass transition temperature)

[0206] The T_g of the TDPPOB obtained was measured by DSC-6200 manufactured by Seiko Instruments & Electronics Ltd. according to differential thermal analysis, and found to be as high as 79.7 °C. The T_g of 79.7 °C is higher than the T_g (63 °C) of TPD which is in general use as a hole-transporting material. This indicates that TDPPOB has excellent heat resistance.

[Manufacture of an organic electroluminescent element using TDPPOB]

[0207] An organic electroluminescent element was manufactured using TDPPOB as an electron-transporting material. The following are details of the constitution of the element
transparent electrode (ITO)/ hole-transporting layer (TPD)/ luminescent layer (Alq_3)/ electron-transporting layer (TDP-POB)/ cathode (MgAg)

[0208] More specifically, the element was manufactured in the same manner as used to obtain the element according to Example 19, except that the TDPPOB was used as the electron-transporting material (thickness 30nm).

[Luminance-voltage characteristic of the organic electroluminescent element]

[0209] A voltage was applied to the organic electroluminescent element according to Example 20, to evaluate its luminance-voltage characteristic. Fig. 14 is a characteristic view showing the luminance-voltage relationship of the element according to Example 20, together with the above-mentioned luminance-voltage relationship of the element according to Comparative Example 4.

[0210] As seen in Fig. 14, the element according to Example 20 emitted light at a lower voltage than the element according to Comparative Example 4. This indicates that TDPPOB has a high capability to transport electrons.

(Example 21)

The characteristics of the TPPO-Trimer prepared in Example 4 were evaluated.

5 [Properties of the TPPO-Trimer]

(Ionization potential and band gap)

10 [0211] The ionization potential of the TPPO-Trimer was measured by an ultraviolet-ray electron spectrometer (AC-2) manufactured by RIKENKEIKI Co., Ltd. and found to be beyond 6.8 eV because the threshold was not detected up to the measurement limit of 6.8 eV. The band gap was 4.02 eV. Thus, it was noted that the TPPO-Trimer had a higher ionization potential and a larger band gap than the ionization potential and band gap of bathocuproin which was in general use as an electron-transporting material, as an hole-blocking material and as an exciton-confining material (the ionization potential of bathocuproin: 6.8 eV, the band gap thereof: 3.7 eV). This indicates that the TPPO-Trimer has a high capability to block holes and a great effect of confining excitons and is promising as a hole-blocking material and as an exciton-confining material for a phosphorescent element

15 (Glass transition temperature)

20 [0212] The Tg of the TPPO-Trimer obtained was measured by DSC-6200 manufactured by Seiko Instruments & Electronics Ltd. according to differential thermal analysis, and found to be as high as 105 °C. The Tg of 105 °C is higher than the Tg (63 °C) of TPD (N,N'-bis(3-methylphenyl)-N,N'-bis(phenyl)-benzidine) which is in general use as a hole-transporting material. This indicates that TPPO-Trimer has excellent heat resistance.

25 [Manufacture of an organic electroluminescent element using TPPO-Trimer]

30 [0213] An organic electroluminescent element was manufactured using TPPO-Trimer as an electron-transporting material. The following are details of the constitution of the element.

35 transparent electrode (ITO)/ hole-transporting layer(TPD)/ luminescent layer(Alq_3)/ electron-transporting layer (TPPO-Dimer) cathode (MgAg)

[0214] More specifically, the element was manufactured in the same manner as used to obtain the element according to Example 19, except that the TPPO-Trimer was used as the electron-transporting material to form the electron-transporting layer (thickness 30 nm).

40 [Luminance-voltage characteristic of the organic electroluminescent element]

[0215] A voltage was applied to the element according to Example 21, to evaluate its luminance-voltage characteristic. Fig. 15 is a characteristic view showing the luminance-voltage relationship of the element according to Example 21, together with the above-mentioned luminance-voltage relationship of the element according to Comparative Example 4.

[0216] As seen in Fig. 15, the element according to Example 21 emitted light at a lower voltage than the element according to Comparative Example 4. This indicates that TPPO-Trimer has a high capability to transport electrons.

(Example 22)

45 [0217] The characteristics of the α -NPPOB prepared in Example 18 were evaluated.

[Characteristics of the α -NPPOB]

(Ionization potential and band gap)

50 [0218] The ionization potential of the α -NPPOB obtained was measured by an ultraviolet-ray electron spectrometer (AC-2) manufactured by RIKENKEIKI Co., Ltd. and found to be beyond 6.8 eV because the threshold was not detected up to the measurement limit of 6.8 eV. The band gap was 3.92 eV. Thus, it was noted that the α -NPPOB had a higher ionization potential and a larger band gap than the ionization potential and band gap of bathocuproin which was in general use as an electron-transporting material, as an hole-blocking material and as an exciton-confining material (the ionization potential of bathocuproin: 6.8 eV, the band gap thereof: 3.7 eV). This indicates that α -NPPOB has a high capability to block holes and a great effect of confining excitons and is promising as a hole-blocking material and as an exciton-confining material for a phosphorescent element.

(Glass transition temperature)

[0219] The Tg of the α -NPPOB obtained was measured by DSC-6200 manufactured by Seiko Instruments & Electronics Ltd. according to differential thermal analysis, and found to be as high as 125 °C. The Tg of 125 °C is higher than the Tg (63 °C) of TPD (N,N'-bis(3-methylphenyl)-N,N'-bis(phenyl)-benzidine) which is in general use as a hole-transporting material. This indicates that α -NPPOB has excellent heat resistance.

[Manufacture of an organic electroluminescent element using α -NPPOB]

[0220] An organic electroluminescent element was manufactured using NPPOB as an electron-transporting material. The following are details of the constitution of the element transparent electrode (ITO)/ hole-transporting layer (TPD)/luminescent layer (Alq_3) / electron-transporting layer (α -NPPOB) / cathode (MgAg)

[0221] More specifically, the element was manufactured in the same manner as used to obtain the element according to Example 19, except that the α -NPPOB was used as the electron-transporting material to form an electron-transporting layer (thickness 30 nm).


[Luminance-voltage characteristic of the organic electroluminescent element]

[0222] A voltage was applied to the element according to Example 22, to evaluate its luminance-voltage characteristic. Fig. 16 is a characteristic view showing the luminance-voltage relationship of the element according to Example 22, together with the above-mentioned luminance-voltage relationship of the element according to Comparative Example 4.

[0223] As seen in Fig. 16, the element according to Example 22 emitted light at a lower voltage than the element according to Comparative Example 4. This indicates that α -NPPOB has a high capability to transport electrons.

Claims

1. An organic electroluminescent element comprising an anode, a cathode and a plurality of organic compound layers sandwiched between the anode and cathode, the organic compound layers including: a hole-transporting layer made of an organic compound insoluble in alcohols; and an electron-transporting layer formed on the hole-transporting layer by a wet method, the electron-transporting layer being made of a phosphorus-containing organic compound soluble in the alcohols, represented by the general formula (1):




wherein Ar¹-Ar³, the same or different from each other, represent an aromatic ring residue optionally containing a substituent, or formula (2):

50

55

5




10

15

wherein Ar¹-Ar⁵, the same or different from each other, represent an aromatic ring residue optionally containing a substituent; and Ar⁷-Ar⁹, the same or different from each other, represent an arylene group optionally containing a substituent, or formula (3):

20

25



30

35

40

wherein R¹ or R², the same or different from each other, represents a hydrogen atom, an alkyl group, a halogen atom, cyano group, nitro group, amino group, an aryl group or a diarylphosphinyl group, and R¹ and R² can form, together with a carbon atom of a benzene ring to which they are linked, a substituted or unsubstituted aromatic ring; and n is 1 or 2.


2. The organic electroluminescent element according to claim 1, wherein the phosphorus-containing organic compound is a nonionic organic compound.
3. The organic electroluminescent element according to claim 1, wherein the phosphorus-containing organic compound has a molecular weight of 300-5000.
4. A manufacturing method of an organic electroluminescent element including an anode, a cathode and a plurality of organic compound layers sandwiched between the anode and cathode, the process comprising the steps of: forming a hole-transporting layer using an organic compound insoluble in alcohols; and forming an electron-transporting layer on the hole-transporting layer by a wet method using as an electron transporting layer material a phosphorus-containing organic compound to be dissolved in an alcohol as defined in claim 1.

50

55

5. The manufacturing method of an organic electroluminescent element according to claim 4, wherein the alcohol is a linear or branched C₁-C₆ aliphatic alcohol.

6. A phosphorus-containing organic compound as a dehydrohalogenation product of a compound represented by the general formula (4):




wherein Ar¹¹, the same or different from each other, represent a phenyl group or naphthyl group optionally substituted with a halogen atom, a methyl, ethyl, n-propyl, iso-propyl, n-butyl, iso-butyl, tert-butyl, methoxy, ethoxy, propoxy, butoxy, or a phenyl group, and either

20 a compound represented by the formula:



25 wherein Ar¹² represents benzene substituted with three halogen atoms, or benzene or biphenyl substituted with two halogen atoms
or
a compound represented by the general formula (5):




40 wherein Ar¹³, the same or different from each other, are a phenyl group or biphenyl group optionally substituted with a halogen atom, at least two of Ar¹³ being a phenyl group or biphenyl group substituted with at least one halogen atom with the exclusion of the compounds:


45

- 4,4'- bis (diphenylphosphine oxide) octafluorobiphenyl;
- 4,4'- bis (diphenylphosphine oxide) biphenyl;
- 4,4'- bis (1-naphthylphenylphosphine oxide) biphenyl;

or a phosphorus-containing organic compound having at least three partial structures represented by a diarylphosphine oxide skeleton, the diarylphosphine oxide skeleton represented by the formula (10) :




wherein $\text{Ar}^{13'}$, the same or different from each other, are a phenyl group or a biphenyl group, or a phenylene group or biphenylene group linked to the formula (9):




wherein Ar^{11} has the same meaning as defined in the general formula (4).

7. The phosphorus-containing organic compound according to claim 6, represented by the subformula (6):



wherein Ar^{11} has the same meaning as defined in the general formula (4); and $\text{Ar}^{12'}$ represents a phenylene group or biphenylene group when $n=2$ and a benzenetriyl group when $n=3$.


8. The phosphorus-containing organic compound according to claim 6, represented by the subformula (7):



wherein Ar^{11} has the same meaning as defined in the general formula (4); and $\text{Ar}^{13'}$, the same or different from each other, represent a phenylene group or a biphenylene group.

9. The phosphorus-containing organic compound according to claim 6, represented by the subformula (8):

5




10

wherein Ar¹¹ has the same meaning as defined in the general formula (4); Ar^{13'}, the same or different from each other, represent a phenylene group or a biphenylene group; and Ar^{13''} represents a phenyl group or a biphenyl group.


15 10. The phosphorus-containing organic compound according to claim 6, selected from compounds of the subformula (6):

20




(A)

25




(B)

30



(C)

35




(D)

40


compounds of the subformula (7):

45









(E)

50





(F)

55



50

55




, and
compounds of the subformula (8):

35

40

45




(P)

Patentansprüche


50

1. Ein organisches elektrolumineszentes Element umfassend eine Anode, eine Kathode und eine Vielzahl von Schichten einer organischen Verbindung angeordnet zwischen der Anode und der Kathode, wobei die Schichten einer organischen Verbindung folgendes einschließen: eine Hohlraum-transportierende Schicht hergestellt aus einer organischen Verbindung, die in Alkoholen unlöslich ist; und eine Elektronen-transportierende Schicht gebildet auf der Hohlraum-transportierenden Schicht durch ein Nassverfahren, wobei die Elektronen-transportierende Schicht hergestellt ist aus einer Phosphor-enthaltenden organischen Verbindung, die in den Alkoholen löslich ist, dargestellt durch die allgemeine Formel (1):

55




worin Ar^1 - Ar^3 , gleich oder verschieden voneinander, einen aromatischen Ring-Rest darstellen, wahlweise enthaltend einen Substituenten, oder Formel (2):



20

worin Ar^1 - Ar^6 , gleich oder verschieden voneinander, einen aromatischen Ring-Rest darstellen, wahlweise enthaltend einen Substituenten; und Ar^7 - Ar^9 , gleich oder verschieden voneinander, stellen eine Arylengruppe dar, wahlweise enthaltend einen Substituenten, oder Formel (3):



40

worin R^1 oder R^2 , gleich oder verschieden voneinander, ein Wasserstoffatom, eine Alkylgruppe, ein Halogenatom, eine Cyanogruppe, eine Nitrogruppe, eine Aminogruppe, eine Arylgruppe oder eine Diarylphosphinylgruppe darstellt, und R^1 und R^2 können, zusammen mit einem Kohlenstoffatom eines Benzenrings, an welchen sie geknüpft sind, einen substituierten oder unsubstituierten aromatischen Ring bilden; und n ist 1 oder 2.

45

2. Das organische elektrolumineszente Element gemäß Anspruch 1, worin die Phosphor-enthaltende organische Verbindung eine nichtionische organische Verbindung ist.
3. Das organische elektrolumineszente Element gemäß Anspruch 1, worin die Phosphor-enthaltende organische Verbindung ein Molekulargewicht von 300-5000 hat.

50


4. Ein Herstellungsverfahren eines organischen elektrolumineszenten Elements einschließlich einer Anode, einer Kathode und einer Vielzahl von organischen Verbindungs-Schichten angeordnet zwischen der Anode und Kathode, wobei das Herfahren die folgenden Schritte umfasst: Bilden einer Hohlraum-transportierenden Schicht unter Verwendung einer organischen Verbindung, die in Alkoholen unlöslich ist; und Bilden einer Elektronen-transportierenden Schicht auf der Hohlraum-transportierenden Schicht durch ein Nassverfahren unter Verwendung einer Phosphor-enthaltenden organischen Verbindung als ein Elektronen-transportierende-Schicht-Material, welche in einem Alkohol aufgelöst werden soll, wie in Anspruch 1 definiert.

55

5. Das Herstellungsverfahren eines organischen elektrolumineszenten Elements gemäß Anspruch 4, worin der Alkohol ein linearer oder verzweigter C_1 - C_6 aliphatischer Alkohol ist.

6. Eine Phosphor-enthaltende organische Verbindung als ein Dehydrohalogenierungsprodukt einer Verbindung dargestellt durch die allgemeine Formel (4):

5



10 worin Ar¹¹, gleich oder verschieden voneinander, eine Phenylgruppe oder Naphthylgruppe wahlweise substituiert mit einem Halogenatom, einer Methyl-, Ethyl-, n-Propyl-, iso-Propyl-, n-Butyl-, iso-Butyl-, tert-Butyl-, Methoxy-, Ethoxy-, Propoxy-, Butoxy- oder einer Phenylgruppe darstellen, und entweder eine Verbindung dargestellt durch die Formel:


15 Ar¹²

worin Ar¹² Benzen substituiert mit drei Halogenatomen, oder Benzen oder Biphenyl substituiert mit zwei Halogenatomen darstellt,

oder

20 eine Verbindung dargestellt durch die allgemeine Formel (5):

25




30 worin Ar¹³, gleich oder verschieden voneinander, eine Phenylgruppe oder Biphenylgruppe sind, wahlweise substituiert mit einem Halogenatom, wobei mindestens zwei von Ar¹³ eine Phenylgruppe oder Biphenylgruppe sind, substituiert mit mindestens einem Halogenatom, unter Ausschluß der folgenden Verbindungen:

- 4,4'-bis(Diphenylphosphinoxid)octafluorobiphenyl;
- 4,4'-bis(Diphenylphosphinoxid)biphenyl;
- 4,4'-bis(1-Naphthylphenylphosphinoxid)biphenyl;


35 oder eine Phosphor-enthaltende organische Verbindung mit mindestens drei Teilstrukturen dargestellt durch ein Diarylphosphinoxidskelett, wobei das Diarylphosphinoxidskelett dargestellt ist durch die Formel (10):

40




45 worin Ar¹³', gleich oder verschieden voneinander, eine Phenylgruppe oder eine Biphenylgruppe sind, oder eine Phenylengruppe oder Biphenylengruppe gebunden an die Formel (9):

50




worin Ar¹¹ dieselbe Bedeutung hat wie in der allgemeinen Formel (4) definiert.

55 7. Die Phosphor-enthaltende organische Verbindung gemäß Anspruch 6, dargestellt durch die Unterformel (6):




worin Ar^{11} dieselbe Bedeutung hat wie in der allgemeinen Formel (4) definiert; und $\text{Ar}^{12'}$ stellt eine Phenylengruppe oder Biphenylengruppe dar, wenn $n=2$, und eine Benzentiarylgruppe, wenn $n=3$.

10 8. Die Phosphor-enthaltende organische Verbindung gemäß Anspruch 6, dargestellt durch die Unterformel (7):




worin Ar^{11} dieselbe Bedeutung hat wie in der allgemeinen Formel (4) definiert; und $\text{Ar}^{13'}$, gleich oder verschieden voneinander, stellen eine Phenylengruppe oder eine Biphenylengruppe dar.


25 9. Die Phosphor-enthaltende organische Verbindung gemäß Anspruch 6, dargestellt durch die Unterformel (8):




worin Ar^{11} dieselbe Bedeutung hat wie in der allgemeinen Formel (4) definiert; $\text{Ar}^{13'}$, gleich oder verschieden voneinander, stellen eine Phenylengruppe oder eine Biphenylengruppe dar; und $\text{Ar}^{13''}$ stellt eine Phenylgruppe oder eine Biphenylgruppe dar.

40 10. Die Phosphor-enthaltende organische Verbindung gemäß Anspruch 6, gewählt aus Verbindungen der Unterformel (6):






(C)




(D)


Verbindungen der Unterformel (7):




(E)




(F)




(G)



(H)




(I)




(J)

5




10




15

20




25



30

35




40

45

und

Verbindungen der Unterformel (8):

50




55

(P)

Revendications

1. Élément électroluminescent organique comprenant une anode, une cathode et une pluralité de couches de composé organique prises en sandwich entre l'anode et la cathode, les couches de composé organique comportant : une couche de transport de trous constituée d'un composé organique insoluble dans les alcools ; et une couche de transport d'électrons formée sur la couche de transport de trous par un procédé humide, la couche de transport d'électrons étant constituée d'un composé organique contenant du phosphore soluble dans les alcools, représenté par la formule générale (1) :

10



15

20 dans laquelle Ar¹-Ar³, identiques ou différents les uns des autres, représentent un résidu de cycle aromatique contenant optionnellement un substituant, ou par la formule (2) :


25

30

35

40


(2)




45

50


55




10



15



20



25 dans laquelle R¹ ou R², identique ou différent l'un de l'autre, représente un atome d'hydrogène, un groupe alkyle, un atome d'halogène, un groupe cyano, un groupe nitro, un groupe amino, un groupe aryle ou un groupe diarylphosphinyle, et R¹ et R² peuvent former, en conjugaison avec un atome de carbone d'un cycle de benzène auquel ils sont liés, un cycle aromatique substitué ou non substitué ; et n vaut 1 ou 2.

30 2. Élément électroluminescent organique selon la revendication 1, dans lequel le composé organique contenant du phosphore est un composé organique non ionique.


35 3. Élément électroluminescent organique selon la revendication 1, dans lequel le composé organique contenant du phosphore a un poids moléculaire de 300 à 5000.

40 4. Procédé de fabrication d'un élément électroluminescent organique comportant une anode, une cathode et une pluralité de couches de composé(s) organique(s) prises en sandwich entre l'anode et la cathode, le procédé comprenant les étapes de formation d'une couche de transport de trous utilisant un composé organique insoluble dans les alcools ; et de formation d'une couche de transport d'électrons sur la couche de transport de trous par un procédé humide utilisant comme matériau de couche de transport d'électrons un composé organique contenant du phosphore devant être dissous dans un alcool comme défini dans la revendication 1.

45 5. Procédé de fabrication d'un élément électroluminescent organique selon la revendication 4, dans lequel l'alcool est un alcool aliphatique en C₁-C₆ linéaire ou ramifié.

6. Composé organique contenant du phosphore en tant que produit de déshydrohalogénéation d'un composé représenté par la formule générale (4) :

50



55


5 dans laquelle Ar^{11} , identiques ou différents l'un de l'autre, représentent un groupe phényle ou un groupe naphthyle éventuellement substitué par un atome d'halogène, un groupe méthyle, éthyle, n-propyle, iso-propyle, n-butyle, iso-butyle, tert-butyle, méthoxy, éthoxy, propoxy, butoxy ou phényle, et l'un ou l'autre d'un composé représenté par la formule :

10 Ar^{12}

15 dans laquelle Ar^{12} représente un benzène substitué par trois atomes d'halogène, ou un benzène ou diphényle substitué par deux atomes d'halogène

20 ou


un composé représenté par la formule générale (5) :




30 dans laquelle Ar^{13} , identiques ou différents les uns des autres, sont un groupe phényle ou un groupe biphenyle éventuellement substitué par un atome d'halogène, au moins deux des Ar^{13} étant un groupe phényle ou un groupe biphenyle substitué par au moins un atome d'halogène à l'exclusion des composés :

- octafluorobiphenyle de 4,4'-bis(oxyde de diphénylphosphine)
- biphenyle de 4,4'-bis(oxyde de diphénylphosphine) ;
- biphenyle de 4,4'-bis(oxyde de 1-naphtylphénylphosphine) ;

35 ou un composé organique contenant du phosphore ayant au moins trois structures partielles représentées par un squelette d'oxyde de diarylphosphine, le squelette d'oxyde de diarylphosphine étant représenté par la formule (10) :




45 dans laquelle $\text{Ar}^{13'}$, identiques ou différents les uns des autres, sont un groupe phényle ou un groupe biphenyle, ou un groupe phénylène ou un groupe biphenylène lié à la formule (9) :




55 dans laquelle Ar^{11} a la même signification que celle définie dans la formule générale (4).

7. Composé organique contenant du phosphore selon la revendication 6, représenté par la sous-formule (6) :




5




10

(A)




(B)

15



20

(C)




(D)

25

les composés de la sous-formule (7)


30



40

(E)

35









(F)

45




50

55




50

55



35 et
les composés de la sous-formule (8) :




50

(P)

55

Fig. 1

[Example 1]

**Fig. 2**

[Comparative Example 1]





**Fig. 3**

Fig. 4**Fig. 5**

[Example 2]

**Fig. 6**

[Comparative Example 2]







Fig. 7**Fig. 8****Fig. 9**




Fig. 10**Fig. 11****Fig. 12**

Fig. 13




Fig. 14




Fig. 15





Fig. 16



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2002063989 A [0010] [0013]
- JP 2004204140 A [0011] [0013]
- JP 2004095221 A [0013]
- US 2001012572 A1 [0014]

Non-patent literature cited in the description

- **C.W.TANG et al.** *Applied Physics Letters*, 1987, vol. 51, 913 [0003] [0013]

专利名称(译)	有机电致发光元件及其制造方法，含磷有机化合物及其制造方法		
公开(公告)号	EP1744598B1	公开(公告)日	2017-05-31
申请号	EP2005734415	申请日	2005-04-20
[标]申请(专利权)人(译)	九州电力株式会社 大电株式会社		
申请(专利权)人(译)	九州电力CO. , INC. 大电CO. , LTD.		
当前申请(专利权)人(译)	九州电力CO. , INC. 大电CO. , LTD.		
[标]发明人	GOTO YASUYUKI C O KYUSHU ELECTRIC POWER CO INC NOTO MITSUHARU C O DAIDEN CO LTD HAYASHIDA TSUYOSHI C O DAIDEN CO LTD ERA MASANAO		
发明人	GOTO, YASUYUKI, C/O KYUSHU ELECTRIC POWER CO., INC. NOTO, MITSUHARU, C/O DAIDEN CO., LTD. HAYASHIDA, TSUYOSHI, C/O DAIDEN CO., LTD. ERA, MASANAO		
IPC分类号	H05B33/22 C07F9/53 C09K11/06 H05B33/10 H05B33/14 H01L51/00 H01L51/50 H01L51/56		
CPC分类号	H01L51/56 C07F9/5329 H01L51/0007 H01L51/0037 H01L51/0039 H01L51/0042 H01L51/005 H01L51/0058 H01L51/0085 H01L51/5012 H01L51/5048		
优先权	2004124712 2004-04-20 JP		
其他公开文献	EP1744598A4 EP1744598A1		
外部链接	Espacenet		

摘要(译)

一种有机电致发光元件，包括阳极，阴极和夹在阳极和阴极之间的多个有机化合物层，所述有机化合物层包括：由不溶于醇的有机化合物制成的空穴传输层；通过湿法在空穴传输层上形成电子传输层，电子传输层由可溶于醇的含磷有机化合物制成。

