



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
23.03.2011 Bulletin 2011/12

(21) Application number: **10011546.8**

(22) Date of filing: **26.12.2001**

(51) Int Cl.:
H05B 33/12 (2006.01) *C07D 213/02 (2006.01)*
C07D 215/00 (2006.01) *C07D 217/00 (2006.01)*
C07D 239/02 (2006.01) *C07F 15/00 (2006.01)*
C07D 213/26 (2006.01) *C07D 213/30 (2006.01)*
C07D 213/61 (2006.01) *C07D 213/68 (2006.01)*
C07D 215/04 (2006.01) *C07D 239/26 (2006.01)*
C09K 11/06 (2006.01) *H01L 51/00 (2006.01)*

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:
01991428.2 / 1 466 506

(27) Previously filed application:
26.12.2001 PCT/US01/49522

(71) Applicant: **E. I. du Pont de Nemours and Company Wilmington, DE 19898 (US)**

(72) Inventors:
• **Petrov, Viacheslav, A. Hockessin, Delaware 19707 (US)**

• **Wang, Ying Wilmington, Delaware 19810 (US)**
• **Grushin, Vladimir Hockessin, Delaware 19707 (US)**

(74) Representative: **Hoffmann, Benjamin Dehns St. Bride's House 10 Salisbury Square London EC4Y 8JD (GB)**

Remarks:
This application was filed on 29-09-2010 as a divisional application to the application mentioned under INID code 62.

(54) **Iridium compounds**

(57) The present invention is generally directed to electroluminescent Ir(III) compounds, and devices made with the Ir(III) compounds.




FIG. 1

DescriptionRELATED APPLICATION

[0001] This application is a continuation-in-part application of U.S. patent application serial no. 09/879,014, filed on June 12, 2001, now pending, which claims the benefit of U.S. provisional application serial no. 60/215,362 filed on June 30, 2000 and claims the benefit of U.S. provisional application serial no. 60/224,273 filed on August 10, 2000.

BACKGROUND OF THE INVENTIONField of the Invention

[0002] This invention relates to electroluminescent complexes of iridium(III) with fluorinated phenylpyridines, phenylpyrimidines, and phenylquinolines. It also relates to electronic devices in which the active layer includes an electroluminescent Ir(III) complex.

Description of the Related Art

[0003] Organic electronic devices that emit light, such as light-emitting diodes that make up displays, are present in many different kinds of electronic equipment. In all such devices, an organic active layer is sandwiched between two electrical contact layers. At least one of the electrical contact layers is light-transmitting so that light can pass through the electrical contact layer. The organic active layer emits light through the light-transmitting electrical contact layer upon application of electricity across the electrical contact layers.

[0004] It is well known to use organic electroluminescent compounds as the active component in light-emitting diodes. Simple organic molecules such as anthracene, thiadiazole derivatives, and coumarin derivatives are known to show electroluminescence. Semiconductive conjugated polymers have also been used as electroluminescent components, as has been disclosed in, for example, Friend et al., U.S. Patent 5,247,190, Heeger et al., U.S. Patent 5,408,109, and Nakano et al., Published European Patent Application 443 861. Complexes of 8-hydroxyquinolate with trivalent metal ions, particularly aluminum, have been extensively used as electroluminescent components, as has been disclosed in, for example, Tang et al., U.S. Patent 5,552,678.

[0005] Burrows and Thompson have reported that fac-tris(2-phenylpyridine) iridium can be used as the active component in organic light-emitting devices. (Appl. Phys. Lett. 1999, 75, 4.) The performance is maximized when the iridium compound is present in a host conductive material. Thompson has further reported devices in which the active layer is poly(N-vinyl carbazole) doped with fac-tris[2-(4',5'-difluorophenyl)pyridine-C²,N]iridium(III). (Polymer Preprints 2000, 41(1), 770.)

[0006] However, there is a continuing need for electroluminescent compounds having improved efficiency.

SUMMARY OF THE INVENTION

[0007] The present invention is directed to an iridium compound (generally referred as "Ir(III) compounds") having at least two 2-phenylpyridine ligands in which there is at least one fluorine or fluorinated group on the ligand. The iridium compound has the following First Formula:



where:

x = 0 or 1, y = 0, 1 or 2, and z = 0 or 1, with the proviso that:


x = 0 or y + z = 0 and
when y = 2 then z = 0;

L' = a bidentate ligand or a monodentate ligand, and is not a phenylpyridine, phenylpyrimidine, or phenylquinoline; with the proviso that:

when L' is a monodentate ligand, y+z = 2, and

when L' is a bidentate ligand, $z = 0$;


L'' = a monodentate ligand, and is not a phenylpyridine, and phenylpyrimidine, or phenylquinoline; and L^a, L^b and L^c are alike or different from each other and each of L^a, L^b and L^c has structure (I) below:




wherein:

adjacent pairs of R₁ through R₄ and R₅ through R₈ can be joined to form a five- or six-membered ring, at least one of R₁ through R₈ is selected from F, C_nF_{2n+1}, OC_nF_{2n+1}, and OCF₂X, where n is an integer from 1 through 6 and X = H, Cl, or Br, and A = C or N, provided that when A = N, there is no R₁.

[0008] In another embodiment, the present invention is directed to substituted 2-phenylpyridine, phenylpyrimidine, and phenylquinoline precursor compounds from which the above Ir(III) compounds are made. The precursor compounds have a structure (II) or (III) below:



where A and R₁ through R₈ are as defined in structure (I) above, and R₉ is H.



where:

at least one of R₁₀ through R₁₉ is selected from F, C_nF_{2n+1}, OC_nF_{2n+1}, and OCF₂X, where n = an integer between 1 and 6 and X is H, Cl, or Br, and R₂₀ is H.

[0009] It is understood that there is free rotation about the phenyl-pyridine, phenyl-pyrimidine and the phenyl-quinoline

bonds. However, for the discussion herein, the compounds will be described in terms of one orientation.

[0010] In another embodiment, the present invention is directed to an organic electronic device having at least one emitting layer comprising the above Ir(III) compound, or combinations of the above Ir(III) compounds.

[0011] As used herein, the term "compound" is intended to mean an electrically uncharged substance made up of molecules that further consist of atoms, wherein the atoms cannot be separated by physical means. The term "ligand" is intended to mean a molecule, ion, or atom that is attached to the coordination sphere of a metallic ion. The term "complex", when used as a noun, is intended to mean a compound having at least one metallic ion and at least one ligand. The term "group" is intended to mean a part of a compound, such a substituent in an organic compound or a ligand in a complex. The term "facial" is intended to mean one isomer of a complex, Ma_3b_3 , having octahedral geometry, in which the three "a" groups are all adjacent, i.e. at the corners of one face of the octahedron. The term "meridional" is intended to mean one isomer of a complex, Ma_3b_3 , having octahedral geometry, in which the three "a" groups occupy three positions such that two are trans to each other. The phrase "adjacent to," when used to refer to layers in a device, does not necessarily mean that one layer is immediately next to another layer. On the other hand, the phrase "adjacent R groups," is used to refer to R groups that are next to each other in a chemical formula (i.e., R groups that are on atoms joined by a bond). The term "photoactive" refers to any material that exhibits electroluminescence and/or photosensitivity. The term "(H+F)" is intended to mean all combinations of hydrogen and fluorine, including completely hydrogenated, partially fluorinated or perfluorinated substituents. By "emission maximum" is meant the wavelength, in nanometers, at which the maximum intensity of electroluminescence is obtained. Electroluminescence is generally measured in a diode structure, in which the material to be tested is sandwiched between two electrical contact layers and a voltage is applied. The light intensity and wavelength can be measured, for example, by a photodiode and a spectrograph, respectively.

DESCRIPTION OF THE DRAWINGS

[0012]

Figure 1 is a schematic diagram of a light-emitting device (LED).

Figure 2 is a schematic diagram of an LED testing apparatus.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0013] The Ir(III) compounds of the invention have the First Formula $\text{Ir}(\text{III})\text{L}^{\text{a}}\text{L}^{\text{b}}\text{L}^{\text{c}}\text{L}'^{\text{y}}\text{L}''^{\text{z}}$ above.

[0014] The above Ir(III) compounds are frequently referred to as cyclometalated complexes: Ir(III) compounds having the following Second Formula is also frequently referred to as a bis-cyclometalated complex.:



where:

y, z, L^{a} , L^{b} , L' , and L'' are as defined in the First Formula above.

Ir(III) compounds having the following Third Formula is also frequently referred to as a tris-cyclometalated complex.:



where:

L^{a} , L^{b} and L^{c} are as defined in the First Formula described above.

[0015] The preferred cyclometalated complexes are neutral and non-ionic, and can be sublimed intact. Thin films of these materials obtained via vacuum deposition exhibit good to excellent electroluminescent properties. Introduction of fluorine substituents into the ligands on the iridium atom increases both the stability and volatility of the complexes. As a result, vacuum deposition can be carried out at lower temperatures and decomposition of the complexes can be avoided. Introduction of fluorine substituents into the ligands can often reduce the non-radiative decay rate and the self-quenching phenomenon in the solid state. These reductions can lead to enhanced luminescence efficiency. Variation

of substituents with electron-donating and electron-withdrawing properties allows for fine-tuning of electroluminescent properties of the compound and hence optimization of the brightness and efficiency in an electroluminescent device.

[0016] While not wishing to be bound by theory, it is believed that the emission from the iridium compounds is ligand-based, resulting from metal-to-ligand charge transfer. Therefore, compounds that can exhibit electroluminescence include those of compounds of the Second Formula $\text{IrL}^a\text{L}^b\text{L}^c$ above, and the Third Formula $\text{IrL}^a\text{L}^b\text{L}^c$ above, where all L^a , L^b , and L^c in the Third Formula are phenylpyridines, phenylpyrimidines, or phenylquinolines. The R_1 through R_8 groups of structures (I) and (II), and the R_{10} through R_{19} groups of structure (III) above may be chosen from conventional substituents for organic compounds, such as alkyl, alkoxy, halogen, nitro, and cyano groups, as well as fluoro, fluorinated alkyl and fluorinated alkoxy groups. The groups can be partially or fully fluorinated (perfluorinated). Preferred iridium compounds have all R_1 through R_8 and R_{10} through R_{19} substituents selected from fluoro, perfluorinated alkyl ($\text{C}_n\text{F}_{2n+1}$) and perfluorinated alkoxy groups ($\text{OC}_n\text{F}_{2n+1}$), where the perfluorinated alkyl and alkoxy groups have from 1 through 6 carbon atoms, or a group of the formula OCF_2X , where X is H, Cl, or Br.

[0017] It has been found that the electroluminescent properties of the cyclometalated iridium complexes are poorer when any one or more of the R_1 through R_8 and R_{10} through R_{19} groups is a nitro group. Therefore, it is preferred that none of the R_1 through R_8 and R_{10} through R_{19} groups is a nitro group.

[0018] It has been found that the luminescence efficiency of the cyclometalated iridium complexes may be improved by using phenylpyridine, phenylpyrimidine, and phenylquinoline ligands in which some or all of the hydrogens have been replaced with deuterium.

[0019] The nitrogen-containing ring can be a pyridine ring, a pyrimidine or a quinoline. It is preferred that at least one fluorinated substituent is on the nitrogen-containing ring; most preferably CF_3 .

[0020] Any conventional ligands known to transition metal coordination chemistry is suitable as the L' and L'' ligands. Examples of bidentate ligands include compounds having two coordinating groups, such as ethylenediamine and acetylacetonate, which may be substituted. Examples of anionic bidentate ligands include beta-enolates, such as acetylacetonate; the anionic form of hydroxyquinolines, such as 8-hydroxyquinoline, which may be substituted, in which the H from the hydroxy group has been extracted; aminocarboxylates; iminocarboxylates, such as pyridine carboxylate; salicylates; salicylaldehydes, such as 2-[(phenylimino)methyl]phenol; and phosphinoalkoxides, such as 3-(diphenylphosphino)-1-propoxide. Examples of monodentate ligands include chloride and nitrate ions; phosphines; isonitriles; carbon monoxide; and mono-amines. It is preferred that the iridium complex be neutral and sublimable. If a single bidentate ligand is used, it should have a net charge of minus one (-1). If two monodentate ligands are used, they should have a combined net charge of minus one (-1). The bis-cyclometalated complexes can be useful in preparing tris-cyclometalated complexes where the ligands are not all the same.

[0021] In a preferred embodiment, the iridium compound has the Third Formula $\text{IrL}^a\text{L}^b\text{L}^c$ as described above.

[0022] In a more preferred embodiment, $\text{L}^a = \text{L}^b = \text{L}^c$. These more preferred compounds frequently exhibit a facial geometry, as determined by single crystal X-ray diffraction, in which the nitrogen atoms coordinated to the iridium are trans with respect to carbon atoms coordinated to the iridium. These more preferred compounds have the following Fourth Formula:



where L^a has structure (I) above.

[0023] The compounds can also exhibit a meridional geometry in which two of the nitrogen atoms coordinated to the iridium are trans to each other. These compounds have the following Fifth Formula:



where L^a has structure (I) above. Examples of compounds of the Fourth Formula and Fifth Formula above are given in Table 1 below:


TABLE 1										
Compound	A	R_1	R_2	R_3	R_4	R_5	R_6	R_7	R_8	Formula
1-a	C	H	H	CF_3	H	H	H	H	H	Fourth
1-b	C	H	H	CF_3	H	H	H	F	H	Fourth




(continued)


TABLE 1

Compound	A	R ₁	R ₂	R ₃	R ₄	R ₅	R ₆	R ₇	R ₈	Formula
1-c	C	H	H	CF ₃	H	F	H	H	H	Fourth
1-d	C	H	H	H	H	F	H	H	H	Fourth
1-e	C	H	H	CF ₃	H	H	CF ₃	H	H	Fourth
1-f	C	H	H	H	H	H	CF ₃	H	H	Fourth
1-g	C	H	H	H	H	H	H	F	H	Fourth
1-h	C	Cl	H	CF ₃	H	H	H	H	H	Fourth
1-i	C	H	H	CF ₃	H	H	H	OCH ₃	H	Fourth
1-j	C	H	H	CF ₃	H	H	F	H	H	Fourth
1-k	C	H	H	NO ₂	H	H	CF ₃	H	H	Fourth
1-l	C	H	H	CF ₃	H	H	H	OCF ₃	H	Fourth
1-m		N -	CF ₃	H	H	H	H	F	H	Fourth
1-q	C	H	H	CF ₃	H	H	OCH ₃	H	H	Fourth
1-r	C	H	OCH ₃	H	H	H	H	CF ₃	H	Fourth
1-s	C	H	H	H	H	F	H	F	H	Fourth and Fifth
1-t	C	H	H	CF ₃	H	H	F	H	F	Fifth
1-u	C	H	H	CF ₃	H	F	H	F	H	Fifth
1-v	C	H	H	CF ₃	H	H	H	F	H	Fifth

[0024] Examples compounds of the Second Formula $\text{IrL}^{\text{a}}\text{L}^{\text{b}}\text{L}'^{\text{y}}\text{L}''^{\text{z}}$ above include compounds 1-n, 1-o, 1-p, 1-w and 1-x, respectively having structure (IV), (V), (VI), (IX) and (X) below:








(X)

[0025] The iridium complexes of the Third Formula $\text{IrL}^{\text{a}}\text{L}^{\text{b}}\text{L}^{\text{c}}$ above are generally prepared from the appropriate substituted 2-phenylpyridine, phenylpyrimidine, or phenylquinoline. The substituted 2-phenylpyridines, phenylpyrimidines, and phenylquinolines, as shown in Structure (II) above, are prepared, in good to excellent yield, using the Suzuki coupling of the substituted 2-chloropyridine, 2-chloropyrimidine or 2-chloroquinoline with arylboronic acid as described in O. Lohse, P.Thevenin, E. Waldvogel *Synlett*, 1999, 45-48. This reaction is illustrated for the pyridine derivative, where X and Y represent substituents, in Equation (1) below:



[0026] Examples of 2-phenylpyridine and 2-phenylpyrimidine compounds, having structure (II) above, are given in Table 2 below:


TABLE 2										
Compound	A	R ₁	R ₂	R ₃	R ₄	R ₅	R ₆	R ₇	R ₈	R ₉
2-a	C	H	H	CF ₃	H	F	H	H	H	H
2-b	C	H	H	CF ₃	H	H	CF ₃	H	H	H
2-c	C	H	H	NO ₂	H	H	CF ₃	H	H	H
2-d	C	H	H	CF ₃	H	H	F	H	H	H
2-e	C	H	H	CF ₃	H	H	H	CH ₃ O	H	H
2-f	C	Cl	H	CF ₃	H	H	H	H	H	H
2-g	C	H	H	H	CH ₃	H	H	F	H	H
2-h	N	-	H	H	H	H	H	F	H	H
2-i	c	H	H	CF ₃	H	H	H	CF ₃ O	H	H
2-j	N	N -	CF ₃	H	H	F	H	H	H	H
2-k	C	H	H	CF ₃	H	H	H	F	H	H

(continued)

TABLE 2										
Compound	A	R ₁	R ₂	R ₃	R ₄	R ₅	R ₆	R ₇	R ₈	R ₉
2-l	C	CF ₃	H	H	H	H	H	H	H	H
2-m	C	Cl	H	CF ₃	H	H	H	F	H	H
2-n	C	CF ₃	H	H	H	H	H	F	H	H
2-o	C	CF ₃	H	H	H	H	H	CH ₃ O	H	H
2-p	C	Cl	H	CF ₃	H	H	H	CH ₃ O	H	H
2-q	N	-	CF ₃	H	H	H	H	F	H	H
2-r	C	Cl	H	CF ₃	H	H	H	H	H	F
2-s	C	H	H	CF ₃	H	H	H	H	H	H
2-t	C	Cl	H	H	H	F	H	H	H	H
2-v	C	H	H	CF ₃	H	H	CH ₃ O	H	H	H
2-w	C	H	CH ₃ O	H	H	H	H	CF ₃	H	H
2-x	C	H	H	H	H	H	F	F	H	H
2-y	C	H	H	CF ₃	H	H	F	H	F	H
2-z	C	H	H	CF ₃	H	F	H	F	H	H
2-aa	C	H	H	Br	H	H	H	Br	H	H


[0027] One example of a substituted 2-phenylquinoline compound, having structure (III) above, is compound 2-u, which has R₁₇ is CF₃ and R₁₀ through R₁₆ and R₁₈ through R₂₀ are H.

[0028] The 2-phenylpyridines, pyrimidines, and quinolines thus prepared are used for the synthesis of the cyclometalated iridium complexes. A convenient one-step method has been developed employing commercially available iridium trichloride hydrate and silver trifluoroacetate. The reactions are generally carried out with an excess of 2-phenylpyridine, pyrimidine, or quinoline, without a solvent, in the presence of 3 equivalents of AgOCOCF₃. This reaction is illustrated for a 2-phenylpyridine in Equation (2) below:



[0029] The tris-cyclometalated iridium complexes were isolated, purified, and fully characterized by elemental analysis, ¹H and ¹⁹F NMR spectral data, and, for compounds 1-b, 1-c, and 1-e, single crystal X-ray diffraction. In some cases, mixtures of isomers are obtained. Often the mixture can be used without isolating the individual isomers.

[0030] The iridium complexes having the Second Formula IrL^aL^bL^c above, may, in some cases, be isolated from the reaction mixture using the same synthetic procedures as preparing those having Third Formula IrL^aL^bL^c above. The complexes can also be prepared by first preparing an intermediate iridium dimer having structure (VII) below:




wherein:

B = H, CH₃, or C₂H₅, and

L^a, L^b, L^c, and L^d can be the same or different from each other and each of L^a, L^b, L^c, and L^d has structure (I) above.


[0031] The iridium dimers can generally be prepared by first reacting iridium trichloride hydrate with the 2-phenylpyridine, phenylpyrimidine or phenylquinoline, and adding NaOB.

[0032] One particularly useful iridium dimer is the hydroxo iridium dimer, having structure (VIII) below:




[0033] This intermediate can be used to prepare compound 1-p by the addition of ethyl acetoacetate.

[0034] Of particular interest, are complexes in which the emission has a maximum in the red region of the visible spectrum, from 570 to 625 nm for red-orange, and from 625 to 700 nm for red. It has been found that the emission maxima of complexes of the Second and Third Formulae are shifted to the red when L has structure (XI) below, derived from a phenyl-quinoline compound having structure (III) above, or when L has structure (XII) below, derived from a phenyl-isoquinoline compound:



where:

at least one of R₁₀ through R₁₉ is selected from F, C_nF_{2n+1}, OC_nF_{2n+1}, and OCF₂X, where n is an integer from 1 through 6 and X is H, Cl, or Br;



15 where:

at least one of R_{21} through R_{30} is selected from F , C_nF_{2n+1} , OC_nF_{2n+1} , and OCF_2X , where n is an integer from 1 through 6 and X is H , Cl , or Br .

20 **[0035]** It has also been found that the ligands of the invention can have perfluoroalkyl and perfluoroalkoxy substituents with up to 12 carbon atoms.

[0036] In the Second Formula, the L' and L'' ligands in the complex can be selected from any of those listed above, and are preferably chosen so that the overall molecule is uncharged. Preferably, z is 0, and L' is a monoanionic bidentate ligand, that is not a phenylpyridine, phenylpyrimidine, or phenylquinoline.

25 **[0037]** Although not preferred, complexes of the Second Formula also have emission maxima that are shifted to the red when L is a phenylpyridine ligand with structure (I) above, and L' is a bidentate hydroxyquinolate ligand.

[0038] Examples of compounds of the Second Formula, where L^a is the same as L^b , L' is a bidentate ligand, y is 1, and z is 0, and compounds of the Third Formula where L^a , L^b , and L^c are the same, are given in Table 8 below. When L has structure (I) above, A is C . In this table, "acac" stands for 2,4-pentanedionate; "8hq" stands for 8-hydroxyquinolate; "Me-8hq" stands for 2-methyl-8-hydroxyquinolate.

30

Table 8.

Compound	Complex Formula	Ligand Structure	R substituents	L'
8-a	Second	I	$R_3 = CF_3$ $R_7 = F$	Me-8hq
8-b	Second	I	$R_3 = CF_3$ $R_7 = F$	8hq
8-c	Second	XI	$R_{18} = CF_3$	acac
8-d	Second	XII	$R_{29} = CF_3$	acac
8-e	Second	XII	$R_{28} = CF_3$	acac
8-f	Second	XII	$R_{29} = F$	acac
8-g	Second	XII	$R_{27} = F$ $R_{29} = F$	acac
8-h	Second	XII	$R_{27} = F$ $R_{29} = F$ $R_{30} = F$	acac
8-i	Second	XII	$R_{28} = F$ $R_{29} = F$ $R_{30} = F$	acac
8-j	Second	XII	$R_{28} = F$ $R_{30} = F$	acac

(continued)

Compound	Complex Formula	Ligand Structure	R substituents	L'
8-k	Second	XII	$R_{29} = C_8F_{17}$	acac
8-l	Third	XII	$R_{29} = CF_3$	-
8-m	Third	XII	$R_{28} = F$ $R_{29} = F$ $R_{30} = F$	-
8-n	Third	XII	$R_{27} = F$ $R_{29} = F$ $R_{30} = F$	-
8-o	Third	XII	$R_{27} = F$ $R_{29} = F$	-
8-p	Third	XII	$R_{28} = CF_3$	-
8-q	Third	XII	$R_{28} = F$ $R_{30} = F$	-
8-r	Second	XII	$R_{27} = F$ $R_{29} = F$	acac
8-s	Second	XII	$R_{29} = OCF_3$	acac

[0039] The complexes in Table 8 have emission maxima in the range of about 590 to 650 nm.

[0040] Also of particular interest, are complexes in which the emission has a maximum in the blue region of the visible spectrum, from about 450 to 500 nm. It has been found that the photoluminescence and electroluminescence of the complexes are shifted to the blue when the complex has the Second Formula where L^a and L^b are phenyl-pyridine ligands with an additional ligand selected from a phosphine, an isonitrile, and carbon monoxide. Suitable complexes have the Sixth Formula below:



(Sixth Formula)

where

L' is selected from a phosphine, an isonitrile, and carbon monoxide;

L'' is selected from F, Cl, Br, and I

L^a and L^b are alike or different and each of L^a and L^b has structure (I) above, wherein:

R_1 through R_8 are independently selected from alkyl, alkoxy, halogen, nitro, cyano, fluoro, fluorinated alkyl and fluorinated alkoxy groups, and at least one of R_1 through R_8 is selected from F, C_nF_{2n+1} , OC_nF_{2n+1} , and OCF_2X , where n is an integer from 1 through 6 and X is H, Cl, or Br, and

A is C.

[0041] The phosphine ligands in the Sixth Formula preferably have the Seventh Formula below



(Seventh Formula)

where Ar is an aromatic group, preferably a phenyl group, which may have alkyl or aryl substituents. Most preferably, the Ar group is a phenyl group having at least one fluorine or fluorinated alkyl substituent. Examples of suitable phosphine ligands include (with the abbreviation provided in brackets):

triphenylphosphine [PPh₃]

tris[3,5-bis(trifluoromethyl)phenyl]phosphine [PtmPh₃]

Some of the phosphine compounds are available commercially, or they can be prepared using any of numerous well-known synthetic procedures, such as alkylation or arylation reactions of PCl_3 or other P-electrophiles with organolithium or organomagnesium compounds.

[0042] The isonitrile ligands in the Sixth Formula, preferably have isonitrile substituents on aromatic groups. Examples of suitable isonitrile ligands include (with the abbreviation provided in brackets):

- 2,6-dimethylphenyl isocyanide [NC-1]
- 3-trifluoromethylphenyl isocyanide [NC-2]
- 4-toluenesulfonylmethyl isocyanide [NC-3]

Some of the isonitrile compounds are available commercially. They also can be prepared using known procedures, such as the Hofmann reaction, in which the dichlorocarbene is generated from chloroform and a base in the presence of a primary amine.

[0043] It is preferred that L" in the Sixth Formula is chloride. It is preferred that L^a is the same as L^b.

[0044] Examples of compounds of the Sixth Formula where L^a is the same as L^b and L" is chloride, are given in Table 9 below, where R₁ through R₈ are as shown in structure (I) above.

Table 9

Comp.	L'	R ₁	R ₂	R ₃	R ₄	R ₅	R ₆	R ₇	R ₈
9-a	NC-1	H	CH ₃	H	H	F	H	F	H
9-b	NC-1	H	H	CH ₃	H	F	H	F	H
9-c	NC-1	H	H	H	H	F	H	F	H
9-d	NC-1	H	H	H	H	H	CF ₃	H	H
9-e	NC-1	H	CH ₃	H	H	H	CF ₃	H	H
9-f	NC-1	H	H	CF ₃	H	H	H	F	H
9-g	NC-1	H	H	CF ₃	H	H	CF ₃	H	H
9-h	NC-2	H	H	H	H	H	CF ₃	H	H
9-i	NC-3	H	H	CF ₃	H	H	H	F	H
9-j	PPh ₃	H	H	CF ₃	H	H	H	F	H
9-k	PtmPh ₃	H	H	CF ₃	H	H	H	F	H
9-l	CO	H	H	CF ₃	H	H	H	F	H
NC-1 is 2,6-(CH ₃) ₂ C ₆ H ₃ NC; NC-2 is 3-CF ₃ C ₆ H ₄ NC; NC-3 is 4-CH ₃ C ₆ H ₄ SO ₂ CH ₂ NC; PPh ₃ is P(C ₆ H ₅) ₃ PtmPh ₃ is (Ar _f) ₃ P, where Ar _f = 3,5-(CF ₃) ₂ C ₆ H ₃ ;									

[0045] The complexes in Table 9 have emission maxima in the range of about 450 to 550 nm.

Electronic Device

[0046] The present invention also relates to an electronic device comprising at least one photoactive layer positioned between two electrical contact layers, wherein the at least one layer of the device includes the iridium complex of the invention. Devices frequently have additional hole transport and electron transport layers. A typical structure is shown in Figure 1. The device 100 has an anode layer 110 and a cathode layer 150. Adjacent to the anode is a layer 120 comprising hole transport material. Adjacent to the cathode is a layer 140 comprising an electron transport material. Between the hole transport layer and the electron transport layer is the photoactive layer 130. Layers 120, 130, and 140 are individually and collectively referred to as the active layers.

[0047] Depending upon the application of the device 100, the photoactive layer 130 can be a light-emitting layer that is activated by an applied voltage (such as in a light-emitting diode or light-emitting electrochemical cell), a layer of material that responds to radiant energy and generates a signal with or without an applied bias voltage (such as in a

photodetector). Examples of photodetectors include photoconductive cells, photoresistors, photoswitches, phototransistors, and phototubes, and photovoltaic cells, as these terms are described in Markus, John, Electronics and Nucleonics Dictionary, 470 and 476 (McGraw-Hill, Inc. 1966).

[0048] The iridium compounds of the invention are particularly useful as the photoactive material in layer 130, or as electron transport material in layer 140. Preferably the iridium complexes of the invention are used as the light-emitting material in diodes. It has been found that in these applications, the fluorinated compounds of the invention do not need to be in a solid matrix diluent in order to be effective. A layer that is greater than 20% by weight iridium compound, based on the total weight of the layer, up to 100% iridium compound, can be used as the emitting layer. This is in contrast to the non-fluorinated iridium compound, tris(2-phenylpyridine) iridium (III), which was found to achieve maximum efficiency when present in an amount of only 6 to 8% by weight in the emitting layer. This was necessary to reduce the self-quenching effect. Additional materials can be present in the emitting layer with the iridium compound. For example, a fluorescent dye may be present to alter the color of emission. A diluent may also be added. The diluent can be a polymeric material, such as poly(N-vinyl carbazole) and polysilane. It can also be a small molecule, such as 4,4'-N,N'-dicarbazole biphenyl or tertiary aromatic amines. When a diluent is used, the iridium compound is generally present in a small amount, usually less than 20% by weight, preferably less than 10% by weight, based on the total weight of the layer.

[0049] In some cases the iridium complexes may be present in more than one isomeric form, or mixtures of different complexes may be present. It will be understood that in the above discussion of OLEDs, the term "the iridium compound" is intended to encompass mixtures of compounds and/or isomers.

[0050] To achieve a high efficiency LED, the HOMO (highest occupied molecular orbital) of the hole transport material should align with the work function of the anode, the LUMO (lowest unoccupied molecular orbital) of the electron transport material should align with the work function of the cathode. Chemical compatibility and sublimation temp of the materials are also important considerations in selecting the electron and hole transport materials.

[0051] The other layers in the OLED can be made of any materials which are known to be useful in such layers. The anode 110, is an electrode that is particularly efficient for injecting positive charge carriers. It can be made of, for example materials containing a metal, mixed metal, alloy, metal oxide or mixed-metal oxide, or it can be a conducting polymer. Suitable metals include the Group 11 metals, the metals in Groups 4, 5, and 6, and the Group 8 through 10 transition metals. If the anode is to be light-transmitting, mixed-metal oxides of Groups 12, 13 and 14 metals, such as indium-tin-oxide, are generally used. The IUPAC numbering system is used throughout, where the groups from the Periodic Table are numbered from left to right as 1 through 18 (CRC Handbook of Chemistry and Physics, 81st Edition, 2000). The anode 110 may also comprise an organic material such as polyaniline as described in "Flexible light-emitting diodes made from soluble conducting polymer," Nature vol. 357, pp 477-479 (11 June 1992). At least one of the anode and cathode should be at least partially transparent to allow the generated light to be observed.

[0052] Examples of hole transport materials for layer 120 have been summarized for example, in Kirk-Othmer Encyclopedia of Chemical Technology, Fourth Edition, Vol. 18, p. 837-860, 1996, by Y. Wang. Both hole transporting molecules and polymers can be used. Commonly used hole transporting molecules are: N,N'-diphenyl-N,N'-bis(3-methylphenyl)-[1,1'-biphenyl]-4,4'-diamine (TPD), 1,1-bis[(di-4-tolylamino) phenyl]cyclohexane (TAPC), N,N'-bis(4-methylphenyl)-N,N'-bis(4-ethylphenyl)-[1,1'-(3,3'-dimethyl)biphenyl]-4,4'-diamine (ETPD), tetrakis-(3-methylphenyl)-N,N,N',N'-2,5-phenylenediamine (PDA), a-phenyl-4-N,N-diphenylaminostyrene (TPS), p-(diethylamino)benzaldehyde diphenylhydrazine (DEH), triphenylamine (TPA), bis[4-(N,N-diethylamino)-2-methylphenyl](4-methylphenyl)methane (MPMP), 1-phenyl-3-[p-(diethylamino)styryl]-5-[p-(diethylamino)phenyl] pyrazoline (PPR or DEASP), 1,2-trans-bis(9H-carbazol-9-yl)cyclobutane (DCZB), N,N,N',N'-tetrakis(4-methylphenyl)-(1,1'-biphenyl)-4,4'-diamine (TTB), and porphyrinic compounds, such as copper phthalocyanine. Commonly used hole transporting polymers are polyvinylcarbazole, (phenylmethyl)polysilane, and polyaniline. It is also possible to obtain hole transporting polymers by doping hole transporting molecules such as those mentioned above into polymers such as polystyrene and polycarbonate.

[0053] Examples of electron transport materials for layer 140 include metal chelated oxinoid compounds, such as tris(8-hydroxyquinolato)aluminum (Alq₃); phenanthroline-based compounds, such as 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (DDPA) or 4,7-diphenyl-1,10-phenanthroline (DPA), and azole compounds such as 2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole (PBD) and 3-(4-biphenyl)-4-phenyl-5-(4-tert-butylphenyl)-1,2,4-triazole (TAZ). Layer 140 can function both to facilitate electron transport, and also serve as a buffer layer or confinement layer to prevent quenching of the exciton at layer interfaces. Preferably, this layer promotes electron mobility and reduces exciton quenching.

[0054] The cathode 150, is an electrode that is particularly efficient for injecting electrons or negative charge carriers. The cathode can be any metal or nonmetal having a lower work function than the anode. Materials for the cathode can be selected from alkali metals of Group 1 (e.g., Li, Cs), the Group 2 (alkaline earth) metals, the Group 12 metals, including the rare earth elements and lanthanides, and the actinides. Materials such as aluminum, indium, calcium, barium, samarium and magnesium, as well as combinations, can be used. Li-containing organometallic compounds can also be deposited between the organic layer and the cathode layer to lower the operating voltage.

[0055] It is known to have other layers in organic electronic devices. For example, there can be a layer (not shown) between the conductive polymer layer 120 and the active layer 130 to facilitate positive charge transport and/or band-

gap matching of the layers, or to function as a protective layer. Similarly, there can be additional layers (not shown) between the active layer 130 and the cathode layer 150 to facilitate negative charge transport and/or band-gap matching between the layers, or to function as a protective layer. Layers that are known in the art can be used. In addition, any of the above-described layers can be made of two or more layers. Alternatively, some or all of inorganic anode layer 110, the conductive polymer layer 120, the active layer 130, and cathode layer 150, may be surface treated to increase charge carrier transport efficiency. The choice of materials for each of the component layers is preferably determined by balancing the goals of providing a device with high device efficiency.

[0056] It is understood that each functional layer may be made up of more than one layer.

[0057] The device can be prepared by sequentially vapor depositing the individual layers on a suitable substrate. Substrates such as glass and polymeric films can be used. Conventional vapor deposition techniques can be used, such as thermal evaporation, chemical vapor deposition, and the like. Alternatively, the organic layers can be coated from solutions or dispersions in suitable solvents, using any conventional coating technique. In general, the different layers will have the following range of thicknesses: anode 110, 500 to 5000 Å, preferably 1000 to 2000 Å; hole transport layer 120, 50 to 1000 Å, preferably 200 to 800 Å; light-emitting layer 130, 10 to 1000 Å, preferably 100 to 800 Å; electron transport layer 140, 50 to 1000 Å, preferably 200 to 800 Å; cathode 150, 200 to 10000 Å, preferably 300 to 5000 Å. The location of the electron-hole recombination zone in the device, and thus the emission spectrum of the device, can be affected by the relative thickness of each layer. Thus the thickness of the electron-transport layer should be chosen so that the electron-hole recombination zone is in the light-emitting layer. The desired ratio of layer thicknesses will depend on the exact nature of the materials used.

[0058] It is understood that the efficiency of devices made with the iridium compounds of the invention, can be further improved by optimizing the other layers in the device. For example, more efficient cathodes such as Ca, Ba or LiF can be used. Shaped substrates and novel hole transport materials that result in a reduction in operating voltage or increase quantum efficiency are also applicable. Additional layers can also be added to tailor the energy levels of the various layers and facilitate electroluminescence.

[0059] The iridium complexes of the invention often are phosphorescent and photoluminescent and may be useful in applications other than OLEDs. For example, organometallic complexes of iridium have been used as oxygen sensitive indicators, as phosphorescent indicators in bioassays, and as catalysts. The bis cyclometalated complexes can be used to synthesize tris cyclometalated complexes where the third ligand is the same or different.

EXAMPLES

[0060] The following examples illustrate certain features and advantages of the present invention. They are intended to be illustrative of the invention, but not limiting. All percentages are by weight, unless otherwise indicated.

EXAMPLE 1

[0061] This example illustrates the preparation of the 2-phenylpyridines and 2-phenylpyrimidines which are used to form the iridium compounds.

[0062] The general procedure used was described in O. Lohse, P. Thevenin, E. Waldvogel Synlett, 1999, 45-48. In a typical experiment, a mixture of 200 mL of degassed water, 20 g of potassium carbonate, 150 mL of 1,2-dimethoxyethane, 0.5 g of Pd(PPh₃)₄, 0.05 mol of a substituted 2-chloropyridine (quinoline or pyrimidine) and 0.05 mol of a substituted phenylboronic acid was refluxed (80-90°C) for 16 to 30 h. The resulting reaction mixture was diluted with 300 mL of water and extracted with CH₂Cl₂ (2 x 100 mL). The combined organic layers were dried over MgSO₄, and the solvent removed by vacuum. The liquid products were purified by fractional vacuum distillation. The solid materials were recrystallized from hexane. The typical purity of isolated materials was 98%. The starting materials, yields, melting and boiling points of the new materials are given in Table 3. NMR data and analytical data are given in Table 4.

TABLE 3
Preparation of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines

Compound	Yield in %	B.p./ mm Hg (m.p.) in °C
2-s	70	---
2-a	72	---
2-b	48	---
2-u	75	(76-78)
2-c	41	(95-96)
2-d	38	(39-40)

EP 2 299 785 A1

(continued)

Preparation of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines

Compound	Yield in %	B.p./ mm Hg (m.p.) in °C
2-e	55	74.5/0.1
2-g	86	71-73/0.07
2-t	65	77-78/0.046
2-k	50	(38-40)
2-m	80	72-73/0.01
2-f	22	52-33/0.12
2-v	63	95-96/13
2-w	72	
2-x	35	61-62/0.095
2-y	62	(68-70)
2-z	42	66-67/0.06 (58-60)
2-aa	60	

TABLE 4

Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines

Compound	¹ H NMR	¹⁹ F NMR	Analysis %, found (calc.) or MS (M ⁺)
2-s	7.48(3H), 7.70(1H), 7.83(1H), 7.90(2H), 8.75(1H)	-62.68	C, 64.50 (64.57) H, 3.49 (3.59) N, 6.07 (6.28)
2-a	7.19(1H), 7.30(1H), 7.43(1H), 7.98(2H), 8.07 (1H) 9.00(1H)	-60.82 (3F, s), -116.96 (1F, m)	C, 59.56 (59.75) H, 3.19 (2.90) N, 5.52 (5.81)
2-b	7.58(1H), 7.66(1H), 7.88(1H), 8.03(1H), 8.23(1H), 8.35 (1H) 8.99(1H)	-62.75 (3F, s), -63.10 (3F, s)	C, 53.68 (53.60) H, 2.61 (2.40) N, 4.53 (4.81)
2-u	7.55(1H), 7.63(1H), 7.75(2H), 7.89(2H), 8.28(2H), 8.38(1H), 8.50 (1H)	-62.89 (s)	C, 69.17 (70.33) H, 3.79 (3.66) N, 4.88 (5.12)

EP 2 299 785 A1

(continued)

Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines

	Compound	¹ H NMR	¹⁹ F NMR	Analysis %, found (calc.) or MS (M ⁺)
5	2-c	7.53(1H), 7.64(1H), 7.90(1H), 8.18(1H), 8.30(1H),	-62.14 (s)	C, 53.83 (53.73) H, 2.89 (2.61) N, 9.99 (10.44)
10		8.53(1H), 9.43(1H)		
	2-d	7.06(1H), 7.48(1H), 7.81(3H), 8.01 (1H), 8.95(1H),	-62.78 (3F, s), -112.61 (1F,m)	C, 59.73 (59.75) H,2.86 (2.90) N, 5.70 (5.81)
15				
20	2-e	3.80(3H), 6.93(2H), 7.68(1H), 7.85(1H), 7.96(2H), 8.82(1H),	-62.63 (s)	C, 61.66 (61.90) H, 3.95 (4.04) N, 5.53 (5.38)
25				
	2-g	2.70(3H), 7.10(3H), 7.48(1H), 7.60(1H), 8.05(2H),	-114.03 (m)	C, 76.56 (77.00) H,5.12 (5.30) N, 5.43 (7.50)
30				
	2-t	7.10(2H), 7.35(2H), 7.96(1H), 8.78(1H),	-62.73 (3F, s) -113.67 (1F, m)	C, 50.51 (52.17) H,1.97 (2.17) N, 5.09 (5.07)
35				
	2-k	7.08(2H), 7.62(1H), 7.90(3H), 8.80(1H),	-62.75 (3F,s) -111.49 (m)	C, 60.39 (59.75), H,3.38 (2.90), N, 5.53 (5.51)
40				
	2-m	7.10(2H), 7.80(2H), 8.00(1H), 8.75(1H),	-62.63 (3F,s) -111.24 (m)	C, 52.13 (52.17) H,2.16 (2.17) N, 4.85 (5.07)
45				
	2-f	7.55(3H), 7.77(2H), 8.06(1H), 8.87(1H)	-62.57(s)	257(M ⁺ , C ₁₂ H ₇ F ₃ CIN ⁺), 222(M-Cl)
50				
	2-v	3.8(3H), 6.95(1H), 7.30(1H), 7.50(1H), 7.58(1H), 7.75(1H), 7.90(1H), 8.87(1H)	-62.70ppm	C, 61.66 (61.37), H, 3.98 (3.67), N,5.53 (5.48)
55				

(continued)

Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines

Compound	¹ H NMR	¹⁹ F NMR	Analysis %, found (calc.) or MS (M ⁺)
2-w	8.54 (1H, d), 8.21 (2H, d), 7.70 (2H, d), 7.24 (1H, s), 6.82 (1H, dd), 3.91 (3H, s)	-63.08 (3F, s)	
2-x	6.9 (2H, m), 7.18 (2H, m), 7.68 (2H, m), 7.95(1H, m), 8.65(1H, m);	-109.70 (1F, m), -113.35(1F, m).	
2-y	6.94(1H), 7.62(2H), 7.82(1H), 8.03(1H), 8.96(1H);	-62.72 (3F, s), -109.11 (2F, m)	
2-z	6.85(1H), 6.93(1H), 7.80, 7.90, 8.05(3H), 8.89(1H);	-62.80 (3F, s), -107.65 (1F, m), -112.45(1F, m).	
2-aa	7.70(3H,m), 7.85(3H, m), 7.80, 7.90, 8.85(1H,m).		

EXAMPLE 2

[0063] This example illustrates the preparation of iridium compounds of the Fourth Formula *fac*-Ir(L^a)₃ above.

[0064] In a typical experiment, a mixture of IrCl₃·nH₂O (53-55% Ir), AgOCOCF₃ (3.1 equivalents per Ir), 2-arylpyridine (excess), and (optionally) a small amount of water was vigorously stirred under N₂ at 180-195°C (oil bath) for 2 to 8 hours. The resulting mixture was thoroughly extracted with CH₂Cl₂ until the extracts were colorless. The extracts were filtered through a silica column to produce a clear yellow solution. Evaporation of this solution gave a residue which was treated with methanol to produce colored crystalline tris-cyclometalated Ir complexes. The complexes were separated by filtration, washed with methanol, dried under vacuum, and (optionally) purified by crystallization, vacuum sublimation, or Soxhlet extraction. Yields: 10-82%. All materials were characterized by NMR spectroscopic data and elemental analysis, and the results are given in Table 5 below. Single-crystal X-ray structures were obtained for three complexes of the series.

Compound 1-b

[0065] A mixture of IrCl₃·nH₂O (54% Ir; 508 mg), 2-(4-fluorophenyl)-5-trifluoromethylpyridine, compound kk (2.20 g), AgOCOCF₃ (1.01 g), and water (1 mL) was vigorously stirred under a flow of N₂ as the temperature was slowly (30 min) brought up to 185°C (oil bath). After 2 hours at 185-190°C the mixture solidified. The mixture was cooled down to room temperature. The solids were extracted with dichloromethane until the extracts decolorized. The combined dichloromethane solutions were filtered through a short silica column and evaporated. After methanol (50 mL) was added to the residue the flask was kept at -10°C overnight. The yellow precipitate of the tris-cyclometalated complex, compound b, was separated, washed with methanol, and dried under vacuum. Yield: 1.07 g (82%). X-Ray quality crystals of the complex were obtained by slowly cooling its warm solution in 1,2-dichloroethane.

Compound 1-e

[0066] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 504 mg), 2-(3-trifluoromethylphenyl)-5-trifluoromethylpyridine, compound bb (1.60 g), and AgOCOCF_3 (1.01 g) was vigorously stirred under a flow of N_2 as the temperature was slowly (15 min) brought up to 192°C (oil bath). After 6 hours at 190-195°C the mixture solidified. The mixture was cooled down to room temperature. The solids were placed on a silica column which was then washed with a large quantity of dichloromethane. The residue after evaporation of the filtrate was treated with methanol to produce yellow solid. The solid was collected and purified by extraction with dichloromethane in a 25-mL micro-Soxhlet extractor. The yellow precipitate of the tris-cyclometalated complex, compound e, was separated, washed with methanol, and dried under vacuum. Yield: 0.59 g (39%). X-Ray quality crystals of the complex were obtained from hot 1,2-dichloroethane.

Compound 1-d

[0067] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 508 mg), 2-(2-fluorophenyl)-5-trifluoromethylpyridine, compound aa (1.53 g), and AgOCOCF_3 (1.01 g) was vigorously stirred under a flow of N_2 at 190-195°C (oil bath) for 6 h 15 min. The mixture was cooled down to room temperature and then extracted with hot 1,2-dichloroethane. The extracts were filtered through a short silica column and evaporated. Treatment of the residue with methanol (20 mL) resulted in precipitation of the desired product, compound d, which was separated by filtration, washed with methanol, and dried under vacuum. Yield: 0.63 g (49%). X-Ray quality crystals of the complex were obtained from dichloromethane / methanol.

Compound 1-i

[0068] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 503 mg), 2-(4-trifluoromethoxyphenyl)-5-trifluoromethylpyridine, compound ee (2.00 g), and AgOCOCF_3 (1.10 g) was vigorously stirred under a flow of N_2 at 190-195°C (oil bath) for 2 h 45 min. The mixture was cooled down to room temperature and then extracted with dichloromethane. The extracts were filtered through a short silica column and evaporated. Treatment of the residue with methanol (20 mL) resulted in precipitation of the desired product, compound i, which was separated by filtration, washed with methanol, and dried under vacuum. The yield was 0.86 g. Additionally, 0.27 g of the complex was obtained by evaporating the mother liquor and adding petroleum ether to the residue. Overall yield: 1.13 g (72%).

Compound 1-g

[0069] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 530 mg), 2-(3-methoxyphenyl)-5-trifluoromethylpyridine (2.50 g), AgOCOCF_3 (1.12 g), and water (1 mL) was vigorously stirred under a flow of N_2 as the temperature was slowly (30 min) brought up to 185°C (oil bath). After 1 hour at 185°C the mixture solidified. The mixture was cooled down to room temperature. The solids were extracted with dichloromethane until the extracts decolorized. The combined dichloromethane solutions were filtered through a short silica column and evaporated. The residue was washed with hexanes and then recrystallized from 1,2-dichloroethane - hexanes (twice). Yield: 0.30 g. ^{19}F NMR (CD_2Cl_2 , 20°C), δ : -63 (s). ^1H NMR (CD_2Cl_2 , 20°C), δ : 8.1 (1H), 7.9 (1H), 7.8 (1H), 7.4 (1H), 6.6 (2H), 4.8 (3H). X-Ray quality crystals of the complex (1,2-dichloroethane, hexane solvate) were obtained from 1,2-dichloroethane - hexanes. This facial complex was orange-photoluminescent.

[0070] Compounds 1-a, 1-c, 1-f through 1-h, 1-j through 1-m, and 1-r were similarly prepared. In the preparation of compound 1-j, a mixture of isomers was obtained with the fluorine in either the R_6 or R_8 position.

TABLE 5

Compound	Analysis (calcd (found))	NMR (CD_2Cl_2 , 25°C)
1-a	C: 50.3 (50.1) H: 2.5 (2.7) N: 4.9 (4.9) Cl: 0.0 (0.2)	^1H : 6.8 (1H), 6.9 (1H), 7.0 (1H), 7.8 (2H), 7.95 (1H), 8.1 (1H) ^{19}F : -63.4
1-b	C: 47.4 (47.3) H: 2.0 (2.1) N: 4.6 (4.4)	^1H : 6.4 (1H), 6.75 (1H), 7.7 (1H), 7.8 (1H), 7.95 (1H), 8.05 (1H) ^{19}F : -63.4 (s); -109.5 (ddd)
1-c	C: 47.4 (47.2) H: 2.0 (2.0)	^1H : 6.6 (1H), 6.7 (1H), 6.9 (1H), 7.8 (1H), 8.0 (1H), 8.6 (1H)

(continued)

TABLE 5		
Compound	Analysis (calcd (found))	NMR (CD ₂ Cl ₂ , 25°C)
	N: 4.6 (4.5)	¹⁹ F: -63.5 (s); -112.8 (ddd)
1-d	C: 55.9 (56.1) H: 3.0 (3.2) N: 5.9 (5.8)	¹ H: 6.6 (2H), 6.8 (1H), 7.0 (1H), 7.6 (1H), 7.7 (1H), 8.4 (1H) ¹⁹ F: -115.0 (ddd)
1-e	C: 44.1 (43.3) H: 1.7 (2.1) N: 3.9 (3.6)	¹ H: 6.9 (1H), 7.1 (1H), 7.8 (1H), 8.0 (2H), 8.2 (1H) ¹⁹ F: -63.0 (1F), -63.4 (1F)
1-f	C: 50.4 (50.5) H: 2.5 (2.7) N: 4.9 (4.9)	¹ H: 6.9 (1H), 7.1 (2H), 7.6 (1H), 7.8 (1H), 7.9 (1H), 8.1 (1H) ¹⁹ F: -62.4
1-g	C: 55.9 (56.3) H: 3.0 (3.2) N: 5.9 (6.0)	¹ H: 6.4 (1H), 6.7 (1H), 7.0 (1H), 7.6 (1H), 7.7 (2H), 7.9 (1H) ¹⁹ F: -112.6 (ddd)
1-h	C: 51.0 (45.2) H: 2.1 (2.3) N: 4.9 (4.2)	¹ H: 6.8 (1H), 6.95 (1H), 7.05 (1H), 7.7 (1H), 8.0 (1H), 8.9 (1H) ¹⁹ F: -63.3
1-i	C: 49.4 (49.3) H: 2.9 (2.8) N: 4.4 (4.4)	¹ H: 3.6 (3H), 6.3 (1H), 6.6 (1H), 7.7 (2H), 7.85 (1H), 7.95 (1H) ¹⁹ F: -63.2
1-j	C: 47.4 (47.4) H: 2.0 (2.3) N: 4.6 (4.7)	¹ H: 6.7 (m), 7.1 (m), 7.5 (m), 7.6 (m), 7.7 (m), 8.0 (m), 8.2 (m) ¹⁹ F: 8 s resonances (-63.0 - -63.6) and 8 ddd resonances (-92.2 - -125.5)
1-k	C: 43.5 (44.0) H: 1.8 (2.1) N: 8.5 (8.4)	¹ H: 6.9 (1H), 7.15 (1H), 8.1 (1H), 8.3 (1H), 8.45 (1H), 8.6 (1H) ¹⁹ F: -62.9
1-l	C: 42.2 (42.1) H: 16. (1.8) N: 3.8 (3.7)	¹ H: 6.5 (1H), 6.7 (1H), 7.75 (1H), 7.85 (1H), 8.0 (1H), 8.1 (1H) ¹⁹ F: -58.1 (1F), -63.4 (1F)

EXAMPLE 3

[0071] This example illustrates the preparation of iridium complexes of the Second Formula $\text{IrL}^{\text{a}}\text{L}^{\text{b}}\text{L}^{\text{c}}\text{L}'^{\text{x}}\text{L}''^{\text{y}}\text{L}'''^{\text{z}}$ above,

Compound 1-n

[0072] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 510 mg), 2-(3-trifluoromethylphenyl)quinoline (1.80 g), and silver trifluoroacetate (1.10 g) was vigorously stirred at 190-195°C for 4 hours. The resulting solid was chromatographed on silica with dichloromethane to produce a mixture of the dicyclometalated complex and the unreacted ligand. The latter was removed from the mixture by extraction with warm hexanes. After the extracts became colorless the hexane-insoluble solid was collected and dried under vacuum. The yield was 0.29 g. ¹⁹F NMR: -63.5 (s, 6F), -76.5 (s, 3F). The structure of this complex was established by a single crystal X ray diffraction study.

Compound 1-o

[0073] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 500 mg), 2-(2-fluorophenyl)-3-chloro-5-trifluoromethylpyridine (2.22 g), water (0.3 mL), and silver trifluoroacetate (1.00 g) was stirred at 190°C for 1.5 hours. The solid product was chromatographed

on silica with dichloromethane to produce 0.33 g of a 2:1 co-crystallized adduct of the dicyclopentametalated aqua trifluoroacetato complex, compound 1-p, and the unreacted ligand. ^{19}F NMR: -63.0 (9F), -76.5 (3F), -87.7 (2F), -114.4 (1F). The co-crystallized phenylpyridine ligand was removed by recrystallization from dichloromethane-hexanes. The structures of both the adduct and the complex were established by a single crystal X-ray diffraction study.

EXAMPLE 4

[0074] This example illustrates the preparation of an hydroxo iridium dimer, having structure (VIII) above.

[0075] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 510 mg), 2-(4-fluorophenyl)-5-trifluoromethylpyridine (725 mg), water (5 mL), and 2-ethoxyethanol (20 mL) was vigorously stirred under reflux for 4.5 hours. After a solution of NaOH (2.3 g) in water (5 mL) was added, followed by 20 mL of water, the mixture was stirred under reflux for 2 hours. The mixture was cooled down to room temperature, diluted with 50 mL of water, and filtered. The solid was vigorously stirred under reflux with 30 mL of 1,2-dichloroethane and aqueous NaOH (2.2 g in 8 mL of water) for 6 hours. The organic solvent was evaporated from the mixture to leave a suspension of an orange solid in the aqueous phase. The orange solid was separated by filtration, thoroughly washed with water, and dried under vacuum to produce 0.94 g (95%) of the iridium hydroxo dimer (spectroscopically pure). ^1H NMR (CD_2Cl_2): -1.0 (s, 1H, IrOH), 5.5 (dd, 2H), 6.6 (dt, 2H), 7.7 (dd, 2H), 7.9 (dd, 2H), 8.0 (d, 2H), 9.1 (d, 2H). ^{19}F NMR (CD_2Cl_2): -62.5 (s, 3F), -109.0 (ddd, 1F).

EXAMPLE 5

[0076] This example illustrates the preparation of bis-cyclopentametalated complexes from an iridium dimer.

Compound 1-p

[0077] A mixture of the iridium hydroxo dimer (100 mg) from Example 4, ethyl acetoacetate (0.075 mL; 4-fold excess), and dichloromethane (4 mL) was stirred at room temperature overnight. The solution was filtered through a short silica plug and evaporated to give an orange-yellow solid which was washed with hexanes and dried. The yield of the complex was 109 mg (94%). ^1H NMR (CD_2Cl_2): 1.1 (t, CH_3), 3.9 (dm, CH_2), 4.8 (s, CH_3COCH), 5.9 (m), 6.7 (m), 7.7 (m), 8.0 (m), 8.8 (d). ^{19}F NMR (CD_2Cl_2): -63.1 (s, 3F), -63.2 (s, 3F), -109.1 (ddd, 1F), -109.5 (ddd). Analysis: Calcd: C, 44.9; H, 2.6; N, 3.5. Found: C, 44.4; H, 2.6; N, 3.3.

Compound 1-w

[0078] A solution of hydroxo iridium dimer from Example 4 (0.20 g) in THF (6 mL) was treated with 50 mg of trifluoroacetic acid, filtered through a short silica plug, evaporated to ca. 0.5 mL, treated with hexanes (8 mL), and left overnight. The yellow crystalline solid was separated, washed with hexanes, and dried under vacuum. Yield (1:1 THF solvate): 0.24 g (96%). ^{19}F NMR (CD_2Cl_2 , 20°C), δ : -63.2 (s, 3F), -76.4 (s, 3F), -107.3 (ddd, 1F). ^1H NMR (CD_2Cl_2 , 20°C), δ : 9.2 (br s, 1H), 8.2 (dd, 1H), 8.1 (d, 1H), 7.7 (m, 1H), 6.7 (m, 1H), 5.8 (dd, 1H), 3.7 (m, 2H, THF), 1.8 (m, 2H, THF).

Compound 1-x

[0079] A mixture of the trifluoroacetate intermediate, compound 1-w (75 mg), and 2-(4-bromophenyl)-5-bromopyridine (130 mg) was stirred under N_2 at 150-155°C for 30 min. The resulting solid was cooled to room temperature and dissolved in CH_2Cl_2 . The resulting solution was filtered through silica gel and evaporated. The residue was washed several times with warm hexanes and dried under vacuum to leave a yellow, yellow-photoluminescent solid. Yield: 74 mg (86%). ^{19}F NMR (CD_2Cl_2 , 20°C), δ : -63.1 (s, 3F), -63.3 (s, 3F), -108.8 (ddd, 1F), -109.1 (ddd, 1F). ^1H NMR (CD_2Cl_2 , 20°C), δ : 8.2 (s), 7.9 (m), 7.7 (m), 7.0 (d), 6.7 (m), 6.2 (dd), 6.0 (dd). The complex was meridional, with the nitrogens of the fluorinated ligands being trans, as confirmed by X-ray analysis.

EXAMPLE 6

[0080] This example illustrates the preparation of iridium compounds of the Fifth Formula $\text{mer-Ir}(\text{L}^a)_3$ above.

Compound 1-s

[0081] This complex was synthesized in a manner similar to compound 1-n. According to the NMR, TLC, and TGA data, the result was an approximately 1:1 mixture of the facial and meridional isomers.

Compound 1-t

[0082] A mixture of $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (54% Ir; 0.40 g), 2-(3,5-difluorophenyl)-5-trifluoromethylpyridine (1.40 g), AgOCOCF_3 (0.81 g), and water (0.5 mL) was vigorously stirred under a flow of N_2 as the temperature was slowly (30-40 min) brought up to 165°C (oil bath). After 40 min at 165°C the mixture solidified. The mixture was cooled down to room temperature. The solids were extracted with dichloromethane until the extracts decolorized. The combined dichloromethane solutions were filtered through a short silica column and evaporated. The residue was thoroughly washed with hexanes and dried under vacuum. Yield: 0.53 g (49%). ^{19}F NMR (CD_2Cl_2 , 20°C), δ : -63.55 (s, 3F), -63.57 (s, 3F), -63.67 (s, 3F), -89.1 (t, 1F), -100.6 (t, 1F), -102.8 (dd, 1F), -118.6 (ddd, 1F), -119.3 (ddd, 1F), -123.3 (ddd, 1F). ^1H NMR (CD_2Cl_2 , 20°C), δ : 8.4 (s), 8.1 (m), 7.9 (m), 7.6 (s), 7.5 (m), 6.6 (m), 6.4 (m). The complex was meridional, as was also confirmed by X-ray analysis.

Compound 1-u

[0083] This complex was prepared and isolated similarly to compound 1-q, then purified by crystallization from 1,2-dichloroethane - hexanes. The yield of the purified product was 53%. The complex is mer, as follows from the NMR data. ^{19}F NMR (CD_2Cl_2 , 20°C), δ : -63.48 (s, 3F), -63.52 (s, 6F), -105.5 (ddd, 1F), -105.9 (ddd, 1F), -106.1 (ddd, 1F), -107.4 (t, 1F), -107.9 (t, 1F), -109.3 (t, 1F). ^1H NMR (CD_2Cl_2 , 20°C), δ : 8.6 (m), 8.3 (s), 8.2 (s), 8.1 (m), 7.9 (m), 7.6 (m), 6.6 (m), 6.4 (m), 6.0 (m), 5.8 (m).

Compound 1-v

[0084] This mer-complex was prepared in a manner similar to compound 1-w, using the trifluoroacetate dicyclometalated intermediate, compound 1-x, and 2-(4-fluorophenyl)-5-trifluoromethylpyridine. ^{19}F NMR (CD_2Cl_2 , 20°C), δ : -63.30 (s, 3F), -63.34 (s, 3F), -63.37 (s, 3F), -108.9 (ddd, 1F), -109.0 (ddd, 1F), -109.7 (ddd, 1F). ^1H NMR (CD_2Cl_2 , 20°C), δ : 8.3-7.6 (m), 6.7 (m), 6.6 (dd), 6.3 (dd), 6.0 (dd). This yellow-luminescent meridional complex isomerised to the green luminescent facial isomer, compound 1-b, upon sublimation at 1 atm.

EXAMPLE 7

[0085] This example illustrates the formation of OLEDs using the iridium complexes of the invention.

[0086] Thin film OLED devices including a hole transport layer (HT layer), electroluminescent layer (EL layer) and at least one electron transport layer (ET layer) were fabricated by the thermal evaporation technique. An Edward Auto 306 evaporator with oil diffusion pump was used. The base vacuum for all of the thin film deposition was in the range of 10^{-6} torr. The deposition chamber was capable of depositing five different films without the need to break up the vacuum.

[0087] An indium tin oxide (ITO) coated glass substrate was used, having an ITO layer of about 1000-2000 Å. The substrate was first patterned by etching away the unwanted ITO area with 1N HCl solution, to form a first electrode pattern. Polyimide tape was used as the mask. The patterned ITO substrates were then cleaned ultrasonically in aqueous detergent solution. The substrates were then rinsed with distilled water, followed by isopropanol, and then degreased in toluene vapor for ~3 hours.

[0088] The cleaned, patterned ITO substrate was then loaded into the vacuum chamber and the chamber was pumped down to 10^{-6} torr. The substrate was then further cleaned using an oxygen plasma for about 5-10 minutes. After cleaning, multiple layers of thin films were then deposited sequentially onto the substrate by thermal evaporation. Finally, patterned metal electrodes of Al were deposited through a mask. The thickness of the film was measured during deposition using a quartz crystal monitor (Sycon STC-200). All film thickness reported in the Examples are nominal, calculated assuming the density of the material deposited to be one. The completed OLED device was then taken out of the vacuum chamber and characterized immediately without encapsulation.

[0089] A summary of the device layers and thicknesses is given in Table 6. In all cases the anode was ITO as discussed above, and the cathode was Al having a thickness in the range of 700-760 Å. In some of the samples, a two-layer electron transport layer was used. The layer indicated first was applied adjacent to the EL layer.

TABLE 6

Alq_3 = tris(8-hydroxyquinolato) aluminum

DDPA = 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline

$\text{Ir}(\text{ppy})_3$ = fac-tris(2-phenylpyridine) iridium

MPMP = bis[4-(N,N-diethylamino)-2-methylphenyl](4-methylphenyl)methane

(continued)

Sample	HT layer (Thickness, Å)	EL layer (Thickness, Å)	ET layer (Thickness, Å)
Comparative	MPMP (528)	Ir(ppy) ₃ (408)	DDPA (106) + Alq ₃ (320)
1	MPMP (520)	Compound <u>1-b</u> (499)	DDPA (125) + Alq ₃ (365)
2	MPMP (541)	Compound <u>1-b</u> (580)	DDPA (407)
3	MPMP (540)	Compound <u>1-e</u> (499)	DDPA (112) + Alq ₃ (340)
4	MPMP (525)	Compound <u>1-k</u> (406)	DDPA (106) Alq ₃ (341)
5	MPMP (570)	Compound <u>1-i</u> (441)	DDPA (107) + Alq ₃ (339)
6	MPMP (545)	Compound <u>1-j</u> (462)	DDPA (111) + Alq ₃ (319)
7	MPMP (643)	Compound <u>1-g</u> (409)	DDPA (112) + Alq ₃ (361)
8	MPMP (539)	Compound <u>1-f</u> (430)	DDPA (109) + Alq ₃ (318)
9	MPMP (547)	Compound <u>1-a</u> (412)	DDPA (105) + Alq ₃ (300)
10	MPMP (532)	Compound <u>1-h</u> (457)	DDPA (108) + Alq ₃ (306)
11	MPMP (603)	Compound <u>1-d</u> (415)	DDPA (111) + Alq ₃ (303)
12	MPMP (551)	Compound <u>1-c</u> (465)	DDPA (106) + Alq ₃ (313)
13	MPMP (520)	Compound <u>1-l</u> (405)	DDPA (410)
14	MPMP (504)	Compound <u>1-b</u> (400)	DDPA (393)
15	MPMP (518)	Compound <u>1-b</u> (153)	DDPA (418)
16	MPMP (556)	Compound <u>1-m</u> (416)	DDPA (430)
17	MPMP (520)	Compound <u>1-n</u> (419)	DDPA (420)
18	MPMP (511)	Compound <u>1-o</u> (412)	DDPA (413)
19	MPMP (527)	Compound <u>1-p</u> (425)	DDPA (412)
20	MPMP (504)	Compound <u>1-q</u> (417)	DPA (407)
21	MPMP (525)	Compound <u>1-t</u> (419)	DPA (416)
22	MPMP (520)	Compound <u>1-u</u> (421)	DPA (405)

[0090] The OLED samples were characterized by measuring their (1) current-voltage (I-V) curves, (2) electroluminescence radiance versus voltage, and (3) electroluminescence spectra versus voltage. The apparatus used, 200, is shown in Figure 2. The I-V curves of an OLED sample, 220, were measured with a Keithley Source-Measurement Unit Model 237, 280. The electroluminescence radiance (in the unit of Cd/m²) vs. voltage was measured with a Minolta LS-110 luminescence meter, 210, while the voltage was scanned using the Keithley SMU. The electroluminescence spectrum was obtained by collecting light using a pair of lenses, 230, through an electronic shutter, 240, dispersed through a spectrograph, 250, and then measured with a diode array detector, 260. All three measurements were performed at the same time and controlled by a computer, 270. The efficiency of the device at certain voltage is determined by dividing the electroluminescence radiance of the LED by the current density needed to run the device. The unit is in Cd/A. The results are given in Table 7 below:

TABLE 7 Electroluminescent Properties of Iridium Compounds				
Sample	Peak Radiance , Cd/m ²	Efficiency at peak radiance, Cd/A	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
Comparative	540 at 22 V	0.39	0.48	522

(continued)

TABLE 7
Electroluminescent Properties of Iridium Compounds

Sample	Peak Radiance , Cd/m ²	Efficiency at peak radiance, Cd/A	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
1	1400 at 21 V	3.4	11	525
2	1900 at 25 V	5.9	13	525
3	830 at 18 V	1.7	13.5	525
4	7.6 at 27 V	0.005	0.13	521
5	175 at 25 V	0.27	1.8	530, 563
6	514 at 20 V	1.5	2.2	560
7	800 at 26 V	0.57	1.9	514
8	1200 at 28 V	0.61	2	517
9	400 at 18 V	1.1	4	545
10	190 at 16 V	2.3	3.3	575
11	1150 at 25 V	1.2	3.8	506, 526
12	340 at 20 V	0.49	2.1	525
13	400 at 21 V	3	5	520
14	1900	5	9	525
15	2500	6	11	525
16	100 at 27 V	0.17	0.2	560
17	3.5 at 28 V	0.005	0.014	575
18	30 at 26 V	0.08	0.16	590
Sample	Peak Radiance Cd/m ²	Efficiency at peak radiance, Cd/A	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
19	2000 at 21 V	6	8	532

(continued)

Sample	Peak Radiance Cd/m ²	Efficiency at peak radiance, Cd/A	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
20	350 at 26 V	0.60	1.6	595
21	1200 at 22 V		5	545
22	80 at 19 V		1	540

[0091] The peak efficiency is the best indication of the value of the electroluminescent compound in a device. It gives a measure of how many electrons have to be input into a device in order to get a certain number of photons out (radiance). It is a fundamentally important number, which reflects the intrinsic efficiency of the light-emitting material. It is also important for practical applications, since higher efficiency means that fewer electrons are needed in order to achieve the same radiance, which in turn means lower power consumption. Higher efficiency devices also tend to have longer lifetimes, since a higher proportion of injected electrons are converted to photons, instead of generating heat or causing an undesirable chemical side reactions. Most of the iridium complexes of the invention have much higher peak efficiencies than the parent factris(2-phenylpyridine) iridium complex. Those complexes with lower efficiencies may also find utility as phosphorescent or photoluminescent materials, or as catalysts, as discussed above.

EXAMPLE 8

[0092] This example illustrates the preparation of the ligand parent compound, 1-(2,4-difluoro-phenyl)-isoquinoline, having Formula XI.

[0093] 2,4-difluorophenylboronic acid (Aldrich Chemical Co., 13.8 g, 87.4 mmol), 1-chloroisoquinoline (Aldrich Chemical Co., 13 g, 79.4 mmol), tetrakis(triphenylphosphine) palladium(0) (Aldrich, 3.00 g, 2.59 mmol), potassium carbonate (EM Science, 24.2 g, 175 mmol), water (300 mL), and dimethoxyethane (Aldrich, 300 mL) were allowed to stir at reflux for 20 h under N₂, after which time the mixture was cooled to room temperature and the organic and aqueous layers were separated. The aqueous layer was extracted with 3 X 150 mL of diethyl ether, and the combined organic fractions were dried with sodium sulfate, filtered, and the filtrate was evaporated to dryness. The crude material was chromatographed on a silica gel column, first by eluting the catalyst byproduct with 4:1 hexanes/CH₂Cl₂, and finally the product was eluted with CH₂Cl₂/MeOH (9.5:0.5, product R_f = 0.7). The pure product fractions were collected and dried *in vacuo*, to afford 17.7 g (92% isolated yield) of a light yellow solid, 95% pure NMR spectroscopy. ¹H NMR (CDCl₃, 296 K, 300 MHz): δ 8.61 (1H, d, *J* = 5.7 Hz), 7.89 (1H, d, *J* = 8.2 Hz), 7.67-7.85 (3H, m), 7.52-7.63 (2H, m), 6.95-7.12 (2H, m) ppm. ¹⁹F NMR (CDCl₃, 296K, 282 MHz) δ -109.01 (1F, brs), -109.87 (1F, d, *J*_{F-F} = 8.5 Hz).

EXAMPLE 9

[0094] This example illustrates the preparation of the bridged dichloro dimer, [IrCl{2-(2,4-difluoro-phenyl)-isoquinoline}Cl]₂.

[0095] 1-(2,4-difluoro-phenyl)-isoquinoline from Example 8 (1.00 g, 4.15 mmol), IrCl₃(H₂O)₃ (Strem Chemicals, 703 mg, 1.98 mmol), and 2-ethoxyethanol (Aldrich Chemical Co., 25 mL) were allowed to stir at reflux for 15 h, after which time the precipitate was isolated by filtration, washed with methanol, and allowed to dry *in vacuo*, to afford 1.04 g (74%) of the product as red-orange solid, 95% pure by NMR spectroscopy. ¹H NMR (CD₂Cl₂, 296 K, 300 MHz): δ 8.85 (2H, d, *J* = 6.4 Hz), 8.38 (2H, dd, *J* = 8.8 and 9.5 Hz), 7.82-7.97 (m, 4H), 7.67-7.78 (2H, m), 6.81 (2H, d, *J* = 6.4 Hz), 6.42 (2H, ddd, *J* = 2.4, 3.3, and 11.4 Hz), 5.25 (2H, dd, *J* = 2.4 and 8.8 Hz) ppm. ¹⁹F NMR (CDCl₃, 296K, 282 MHz) δ -95.7 (2F, d, *J*_{F-F} = 12 Hz), -108.03 (2F, d, *J*_{F-F} = 12 Hz).

EXAMPLE 10

[0096] This example illustrates the preparation of the bis-cyclometallated iridium complex, [Ir(acac){1-(2,4-difluoro-phenyl)-isoquinoline}Cl]₂, complex 8-r in Table 8.

[0097] [IrCl{1-(2,4-difluoro-phenyl)-isoquinoline}Cl]₂ from Example 9 (300 mg, 0.212 mmol), sodium acetylacetonate (Aldrich Chemical Co., 78 mg, 0.636 mmol), and 2-ethoxyethanol (10 mL) were allowed to stir at 120°C for 0.5 h. The volatile components were then removed *in vacuo*. The residue was taken up in dichloromethane, and this solution was

passed through a pad of silica gel with dichloromethane as the eluting solvent. The resulting red-orange filtrate was evaporated to dryness, and then suspended in methanol. The precipitated product was isolated by filtration and dried *in vacuo*. Isolated yield = 230 mg (70%). ¹H NMR (CD₂Cl₂, 296 K, 300 MHz): δ 8.40 (2 H, dd, 1= 8.8 and 9 Hz), 7.97 (2H, d, *J* = 8.1 Hz), 7.78 (2H, ddd, *J* = 0.7, 6.6, and 7.8 Hz), 7.70 (2H, dd, *J* = 1.3 and 8.4 Hz), 7.66 (2H, d, *J* = 6.4 Hz), 6.44 (2H, ddd, *J* = 2.4, 5.9, and 10.8 ppm), 5.68 (2H, dd, *J* = 2.4 and 8.5 Hz), 5.30 (1H, s), 1.78 (6H, s). ¹⁹F NMR (CDCl₃, 296K, 282 MHz) δ -96.15 (2F, d, *J*_{F-F} = 11.3 Hz), -109.13 (2F, d, *J*_{F-F} = 11.3 Hz).

[0098] Compounds 8-a through 8-k, and compound 8-s in Table 8 were prepared using a similar procedure.

[0099] Compounds 8-l through 8-q in Table 8 were prepared using the procedure of Example 2.

EXAMPLE 11

[0100] Thin film OLED devices were fabricated using the procedure according to Example 7. A summary of the device layers and thicknesses is given in Table 10. In all cases the anode was ITO as discussed above, and the cathode was Al having a thickness in the range of 700-760 Å.

TABLE 10			
MPMP = bis[4-(N,N-diethylamino)-2-methylphenyl](4-methylphenyl)-methane			
DPA = 4,7-diphenyl-1,10-phenanthroline			
Sample	HT layer (Thickness, Å)	EL layer (Thickness, Å)	ET layer (Thickness, Å)
11-1	MPMP (572)	Compound 8-a (419)	DPA (400)
11-2	MPMP (512)	Compound 8-b (407)	DPA (394)
11-3	MPMP (548)	Compound 8-c (441)	DPA (408)
19-4	MPMP (508)	Compound 8-d (410)	DPA (408)
11-5	MPMP (560)	Compound 8-e (421)	DPA (407)
11-6	MPMP (526)	Compound 8-f (409)	DPA (405)
11-7	MPMP (890)	Compound 8-g (408)	DPA (402)
11-8	MPMP (514)	Compound 8-h (465)	DPA (403)
11-9	MPMP (564)	Compound 8-i (418)	DPA (413)
11-10	MPMP (564)	Compound 8-j (405)	DPA (407)
11-11	MPMP (522)	Compound 8-k (400)	DPA (408)
11-12	MPMP (529)	Compound 8-l (421)	DPA (408)
11-13	MPMP (530)	Compound 8-m (411)	DPA (411)
11-14	MPMP (537)	Compound 8-o (412)	DPA (409)

EP 2 299 785 A1

(continued)

Sample	HT layer (Thickness, Å)	EL layer (Thickness, Å)	ET layer (Thickness, Å)
11-15	MPMP (509)	Compound 8-p (405)	DPA (405)
11-16	MPMP (512)	Compound 8-q (414)	DPA (402)
11-17	MPMP (529)	Compound 8-r (442)	DPA (412)
11-18 102961-31	MPMP (524)	Compound 8-s (407)	DPA (408)

[0101] The OLED samples were characterized as in Example 7, and the results are given in Table 12 below.

<p>TABLE 11 Electroluminescent Properties of Iridium Compounds</p>			
Sample	Peak Radiance, Cd/m ²	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
11-1	45 at 22 V	0.13	628
11-2	32 at 20 V	0.12	> 600
11-3	340 at 24	2.5	590
11-4	350 at 22 V	1.7	625
11-5	300 at 21 V	1.5	600
11-6	200 at 20 V	1.1	605, 650
11-7	300 at 23 V	5	605
11-8	280 at 21 V	2.9	590
11-9	1000 at 20 V	3.5	592
11-10	380 at 21 V	2.3	610, 650
11-11	8 at 23 V	0.25	624
11-12	800 at 20 V	2.3	610,650
11-13	360 at 22 V	1.5	590
11-14	160 at 24 V	1.2	590
11-15	80 at 21 V	1.1	597

(continued)

TABLE 11
Electroluminescent Properties of Iridium Compounds

Sample	Peak Radiance, Cd/m ²	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
11-16	170 at 21 V	0.8	615
11-17	1300 at 22 V	4	600
11-18	540 at 20 V	1.6	622

EXAMPLE 12

[0102] This example illustrates the preparation of additional phenylpyridine ligands.

[0103] The phenylpyridine compounds 12-a through 12-j, shown in Table 12 below, were prepared as described in Example 1.

TABLE 12

Compound	A	R ₁	R ₂	R ₃	R ₄	R ₅	R ₆	R ₇	R ₈	R ₉
12-a	C	H	CH ₃	H	H	F	H	F	H	H
12-b	C	H	CH ₃	H	H	H	CF ₃	H	CF ₃	H
12-c	C	H	H	CH ₃	H	F	H	F	H	H
12-d	C	H	CH ₃	H	H	H	CF ₃	H	H	H
12-e	C	H	H	CH ₃	H	H	CF ₃	H	CF ₃	H
12-f	C	H	H	H	H	H	CF ₃	H	H	H
12-g	C	H	H	H	H	F	H	F	H	H
12-h	C	H	t-Bu	H	H	H	H	F	H	H
12-i	C	H	t-Bu	H	H	H	CF ₃	H	CF ₃	H
12-j	C	H	CH ₃	H	H	H	H	CF ₃	H	H

[0104] The analytical and NMR data are given in Table 13 below.

Table 13

Compound	Yield (%)	B.p./mm Hg (m.p.) °C	NB No	¹ H NMR	¹⁹ F NMR
12-a	61.5	70-72/0.03	101394-104	2.39(3H), 6.99(2H), 7.02(1H), 7.57(1H), 7.99(1H) 8.56(1H)	-102.96 (1F, m), -113.18 (1F, m)
12-b	39	66-68/0.01	101394-115	2.47(3H), 7.17(1H), 7.63(1H), 7.91(1H), 8.48(2H), 8.60 (1H), 9.00(1H)	-63.23 (s)

(continued)

Compound	Yield (%)	B.p./ mm Hg (m.p.) °C	NB No	¹ H NMR	¹⁹ F NMR
12-c	76	75-76/0.01 (54-56)	101394-121	2.25(3H), 6.90(2H), 7.55(2H), 8.50(1H), 8.85(1H),	-110.37 (1F, m) -113.50 (1F,m)
12-d	76	69-70/0.06 (44-46)	101394-129	2.35(3H), 7.05(1H), 7.55(2H), 8.01(1H), 8.18(1H), 8.50(1H)	-63.03 (s)
12-e	84	(83-85)	102960-48	2.43(3H), 7.66(1H), 7.87(1H), 8.47(2H), 8.59(1H)	-63.18 (s)
12-f	72	64-65/0.026	99344-13	7.20(1H), 7.65(3H), 8.10(1H), 8.17(1H), 8.65(1H), 9.43(1H)	-63.05 (s)
12-g	36	62/0.01	101394-93	6.90(1H), 7.18(2H), 7.68(2H), 7.95(1H), 8.65(1H),	-109.70 (1F, m) -113.35 (1F,m)
12-h	49	99-101/0.26	102960-117	-	-
12-i	58	108-109/0.1	103555-3	1.35(9H) 7.34(1H) 7.72(1H) 7.88(1H) 8.44(2H) 8.61(1H)	-63.19
12-j	46	76-77/01 (52-54)	102960-143	2.46(3H) 7.15(1H) 7.60(1H) 7.73(2H) 8.11(2H) 8.59(1H)	-62.86

[0105] 2-(2',4'-dimethoxyphenyl)-5-trifluoromethylpyridine was prepared via Kumada coupling of 2-chloro-5-trifluoromethylpyridine with 2,4-dimethoxyphenylmagnesium bromide in the presence of [(dppb)PdCl₂] catalyst (dppb = 1,4-bis(diphenylphosphino)butane).

EXAMPLE 13

[0106] This example illustrates the formation of dichloro-bridged dinuclear bis-cyclometallated Ir complexes.

[0107] The Ir complexes were prepared by the reaction between IrCl₃·nH₂O and the corresponding 2-arylpyridine in aqueous 2-ethoxyethanol. The method is similar to the literatures procedure for 2-phenylpyridine (Sprouse, S.; King, K. A.; Spellane, P. J.; Watts, R. J., J. Am. Chem. Soc., 1984, 106, 6647-53; Garces, F. O.; King, K. A.; Watts, R. J., Inorg. Chem., 1988, 27, 3464-71.). A mixture of IrCl₃·nH₂O, a 2-arylpyridine (2.2 - 2.8 equivalents per Ir), 2-ethoxyethanol (ca. 30 mL per 1 g of IrCl₃·nH₂O), and water (ca. 5 mL per 30 mL of 2-ethoxyethanol) was vigorously stirred under reflux

(N₂) for 4-10 hours. After cooling to room temperature, conc. HCl (3 mL per 1 g IrCl₃·nH₂O) was added, and the mixture was stirred for 30 min. The mixture was diluted with water, stirred for 1-2 hours, and filtered. The solid product was washed with water, methanol, and dried under vacuum. The yields ranged from 65 to 99%.

EXAMPLE 14

[0108] This example illustrates the formation of Ir complexes of the invention having the Sixth Formula, where L" is Cl.

Dicyclopentametalated Arylpyridine Iridium (III) Mononuclear Complexes containing monodentate tertiary phosphine, CO, or isonitrile ligands.

[0109] A mixture of a the dichloro-bridged dinuclear bis-cyclopentametalated Ir complex made as in Example 13, a monodentate ligand L', and 1,2-dichloroethane (DCE) or toluene was stirred under reflux (N₂ or CO when L' is CO) until all solids dissolved and then for additional 3 min -1 h. The products were isolated and purified by evaporation and crystallization in air. Detailed procedures for selected complexes are given below. All complexes were characterized by NMR spectroscopic data (³¹P NMR = ³¹P-{¹H} NMR). Satisfactory combustion analyses were not obtained due to insufficient thermal stability of the complexes. Both isomers of compound 9-k, the major isomer with the nitrogens trans and the minor isomer with the nitrogens cis, were characterized by single-crystal X-ray diffraction.

Complex 9-d (Table 9).

[0110] A mixture of the dichloro-bridged dinuclear bis-cyclopentametalated Ir complex made with phenylpyridine compound 12-f from Example 12 (100 mg); ligand NC-1, which is 2,6-(CH₃)₂C₆H₃NC, (26 mg) as ligand L' (purchased from the Fluka line of chemicals, from Sigma-Aldrich); and DCE (1.5 mL) was stirred under reflux for 5 min. Upon cooling to room temperature the strongly bluish-green photoluminescent solution was treated with hexanes (15 mL, portionwise). The yellow crystals were separated, washed with hexanes (3 x 3 mL), and dried under vacuum. Yield: 0.115g(96%). ¹H NMR (CD₂Cl₂, 20°C), δ: 2.2 (s, 6H, CH₃); 6.35 (d, 1H, arom H); 6.65 (d, 1H, arom H); 7.1 (m, 4H, arom H); 7.3 (m, 1H, arom H); 7.5 (m, 1H, arom H); 7.9 (d, 2H, arom H); 8.1 (m, 5H, arom H); 9.4 (d, 1H, arom H); 10.0 (d, 1H, arom H). ¹⁹F NMR (CD₂Cl₂, 20°C), δ: -62.7 (s, 3F, CF₃); -62.8 (s, 3F, CF₃).

Complex 9-g (Table 9):

[0111] A mixture of the dichloro-bridged dinuclear bis-cyclopentametalated Ir complex made with phenylpyridine compound 2-y from Example 1 (120 mg), ligand NC-1, which is 2,6-(CH₃)₂C₆H₃NC, (26 mg) as ligand L' (purchased from the Fluka line of chemicals, from Sigma-Aldrich); and DCE (2 mL) was stirred under reflux for 10 min. Upon cooling to room temperature the strongly bluish-green photoluminescent solution was treated with hexanes (4 mL, portionwise). The yellow crystals were separated, washed with hexanes (3 x 3 mL), and dried under vacuum. Yield: 0.13 g (93%). ¹H NMR (CD₂Cl₂, 20°C), δ: 2.2 (s, 6H, CH₃); 6.35 (d, 1H, arom H); 6.65 (d, 1H, arom H); 7.1 (m, 5H, arom H); 8.0 (d, 2H, arom H); 8.25 (m, 4H, arom H); 9.6 (s, 1H, arom H); 10.4 (s, 1H, arom H). ¹⁹F NMR (CD₂Cl₂, 20°C), δ: -62.8 (s, 6F, CF₃); -62.9 (s, 3F, CF₃); -63.0 (s, 3F, CF₃).

Complex 9-j (Table 9)

[0112] A mixture of the dichloro-bridged dinuclear bis-cyclopentametalated Ir complex made with phenylpyridine compound 2-k from Example 1 (300 mg), triphenylphosphine (120 mg) as ligand L'; and toluene (6 mL) was stirred under reflux for 10 min. Upon cooling to room temperature yellow crystals precipitated from the green photoluminescent solution. After 2 days at room temperature, hexanes (8 mL) was added. After 1 day, the yellow crystals were separated, washed with hexanes (3 x 3 mL), and dried under vacuum. Yield: 0.41 g (97%). ¹H NMR (CD₂Cl₂, 20°C), δ: 5.5 (m, 2H, arom H); 6.7 (m, 2H, arom H); 7.2-7.9 (m, 21H, arom H); 8.05 (s, 2H, arom H); 9.15 (s, 1H, arom H); 9.65 (s, 1H, arom H). ¹⁹F NMR (CD₂Cl₂, 20°C), δ: -62.9 (s, 3F, CF₃); -63.0 (s, 3F, CF₃); -107.9 (m, 1F, arom F); -108.3 (m, 1F, arom F). ³¹P NMR (CD₂Cl₂, 20°C), δ: -3.2 (d, J_{P-F} = 5.9 Hz). The product contains a minor isomer (ca. 10%) with the following NMR parameters: ¹⁹F NMR (CD₂Cl₂, 20°C), δ: -63.5 (s, 3F, CF₃); -63.9 (s, 3F, CF₃); -107.4 (m, 1F, arom F); -108.9 (m, 1F, arom F). ³¹P NMR (CD₂Cl₂, 20°C), δ: -10.8 (d, J_{P-F} = 6.3 Hz).

Complex 9-k (Table 9)

[0113] A mixture of the dichloro-bridged dinuclear bis-cyclopentametalated Ir complex made with phenylpyridine compound 2-k from Example 1 (102 mg); the triarylphosphine compound (Ar_f)₃P, where Ar_f = 3,5-(CF₃)₂C₆H₃ (102 mg) as ligand

L'; and toluene (8 mL) was stirred under reflux for 10 min until all solids dissolved. After cooling to room temperature the mixture was treated with hexanes (10 mL), and kept at ca. +10°C for 3h. The yellow crystalline solid was separated, washed with hexanes, and dried under vacuum. The compound exhibited sky-blue photoluminescence. ¹⁹F NMR analysis of this product indicated ca. 10% of unreacted dichloro bridged complex. After heating the solid in boiling toluene in the presence of L₅ (30 mg) and then cooling at ca. +10°C for 12 hours, complex 9-k was isolated, free of any dichloro bridged complex. It was washed with hexanes, and dried under vacuum. Yield: 0.17 g (86%). ¹H NMR (CD₂Cl₂, 20°C), δ: 5.4 (m, 1H, arom H); 5.9 (m, 1H, arom H); 6.75 (m, 2H, arom H); 7.2 (m, 2H, arom H); 7.75 (m, 2H, arom H); 7.9 (m, 7H; arom H); 8.05 (s, 2H, arom H); 8.15 (s, 2H, arom H); 8.85 (s, 1H, arom H); 9.4 (s, 1H, arom H). ¹⁹F NMR (CD₂Cl₂, 20°C), δ: -63.2 (s, 3F, CF₃); -63.9 (s, 3F, CF₃); -64.0 (s, 18F, L₅ CF₃); -105.4 (m, 1F, arom F); -106.1 (m, 1F, arom F). ³¹P NMR (CD₂Cl₂, 20°C), δ: -2.2 (d, J_{P-F} = 5.9 Hz). This complex has the nitrogen atoms trans to each other (X-ray). In the crop of single crystals submitted for X-ray analysis a few crystals of different shape were also found. One of those few was also analyzed by X-ray diffraction, which established cis-arrangement of the N atoms around Ir for the minor isomer.

Complex 9-l (Table 9)

[0114] Carbon monoxide, as L', was bubbled through a boiling solution of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 2-k from Example 1 (180 mg) in DCE (8 mL). The heater was turned off and the solution was allowed to cool slowly to room temperature with CO bubbling through the mixture. When pale-yellow crystals began to precipitate hexanes (10 mL) was added slowly, in 2-mL portions. After 30 min at room temperature the crystals (whitish-blue photoluminescent) were separated, washed with hexanes, and dried under vacuum for 15 min. Yield: 0.145 g (78%). ¹H NMR (CD₂Cl₂, 20°C), δ: 5.6 (m, 1H, arom H); 6.15 (m, 1H, arom H); 6.8 (m, 2H, arom H); 7.8 (m, 2H, arom H); 8.1 (m, 2H, arom H); 8.25 (m, 2H, arom H); 9.2 (s, 1H, arom H); 10.15 (s, 1H, arom H). ¹⁹F NMR (CD₂Cl₂, 20°C), δ: -62.8 (s, 3F, CF₃); -62.9 (s, 3F, CF₃); -106.5 (m, 1F, arom F); -106.7 (m, 1F, arom F).

[0115] Complexes 9-a, 9-b, 9-c, 9-e, 9-f, 9-h, and 9-i, were made using the same procedure as for complex 9-d, using phenylpyridine compounds 12-a, 12-c, 12-g, 12-d, 2-k, 12-f, and 2-k, respectively.

EXAMPLE 15

[0116] Thin film OLED devices were fabricated using the procedure according to Example 7. A summary of the device layers and thicknesses is given in Table 14. In all cases the anode was ITO as discussed above, and the cathode was Al having a thickness in the range of 700-760 Å.

TABLE 14			
MPMP = bis[4-(N,N-diethylamino)-2-methylphenyl](4-methylphenyl) methane DPA = 4,7-diphenyl-1,10-phenanthroline			
Sample	HT layer (Thickness, Å)	EL layer (Thickness, Å)	ET layer (Thickness, Å)
15-1	MPMP (516)	Compound 9-a (408)	DPA (413)
15-2	MPMP (518)	Compound 9-c (404)	DPA (402)
15-3	MPMP (508)	Compound 9-d (354)	DPA (421)
15-4	MPMP (504)	Compound 9-e (403)	DPA (410)
15-5 102924-5	MPMP (501)	Compound 9-f (407)	DPA (415)
15-6 102924-40	MPMP (518)	Compound 9-g (404)	DPA (405)

[0117] The OLED samples were characterized as in Example 7, and the results are given in Table 15 below.

TABLE 15
Electroluminescent Properties of Iridium Compounds

Sample	Peak Radiance, Cd/m ²	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
15-1	6 at 16 V	0.7	450 + 500
15-2	1 at 21 V	0.25	510
15-3	60 at 22 V	0.8	464 + 493
Sample	Peak Radiance, Cd/m ²	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
15-4	25 at 23 V	1.2	460 + 512
15-5	320 at 22 V	2.4	538
15-6	350 at 23 V	1.5	484 + 509

Claims

1. An organic electronic device comprising an emitting layer having an emission maximum in the range of 570 to 700 nm, wherein at least 20% by weight of the emitting layer comprises at least one compound having either a Second Formula below:



or a Third Formula below:




where:

y is 1;

z is 0;


L' is a bidentate ligand, and is not a phenylpyridine, phenylpyrimidine, or phenylquinoline;

L^a and L^b are alike or different from each other and each of L^a and L^b, has a structure selected from structure (XI) and structure (XII) below:



15 where:

at least one of R_{10} through R_{19} is selected from F , C_nF_{2n+1} , OC_nF_{2n+1} , and OCF_2X , where n is an integer from 1 through 6 and X is H , Cl , or Br ,



35 where:

at least one of R_{21} through R_{30} is selected from F , C_nF_{2n+1} , OC_nF_{2n+1} , and OCF_2X , where n is an integer from 1 through 6 and X is H , Cl , or Br .




FIG. 1




FIG. 2



EUROPEAN SEARCH REPORT

Application Number
EP 10 01 1546

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
E	EP 1 348 711 A (CANON KK [JP]) 1 October 2003 (2003-10-01) * pages 66-76 * * pages 14-51 *	1	INV. H05B33/12 C07D213/02 C07D215/00 C07D217/00 C07D239/02 C07F15/00 C07D213/26 C07D213/30 C07D213/61 C07D213/68 C07D215/04 C07D239/26 C09K11/06 H01L51/00
E	EP 1 295 514 B1 (DU PONT [US]) 2 August 2006 (2006-08-02) * page 7; compound IV * * page 11, paragraph 34 *	1	
E	EP 1 399 002 A (CANON KK [JP]) 17 March 2004 (2004-03-17) * page 10; compound D * * page 17; compound H *	1	
Y	US 2001/019782 A1 (IGARASHI TATSUYA [JP] ET AL) 6 September 2001 (2001-09-06) * page 15 - page 16 *	1	
Y	US 2001/053462 A1 (MISHIMA MASAYUKI [JP]) 20 December 2001 (2001-12-20) * example 2 *	1	
Y	GRUSHIN V V ET AL: "New, efficient electroluminescent materials based on organometallic Ir complexes", CHEMICAL COMMUNICATIONS - CHEMCOM, ROYAL SOCIETY OF CHEMISTRY, GB, 23 July 2001 (2001-07-23), pages 1494-1495, XP002196401, ISSN: 1359-7345 * the whole document *	1	
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 14 February 2011	Examiner Duval, Eric
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

 1
EPO FORM 1503 03.02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 10 01 1546

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

14-02-2011

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1348711	A	01-10-2003	AU 2256602 A	11-06-2002
			CN 1474826 A	11-02-2004
			CN 1781925 A	07-06-2006
			WO 0244189 A1	06-06-2002
			JP 4343528 B2	14-10-2009
			KR 20070087038 A	27-08-2007
			KR 20070087039 A	27-08-2007
			KR 20070087040 A	27-08-2007
			KR 20070087041 A	27-08-2007
			KR 20070087042 A	27-08-2007
			KR 20070087043 A	27-08-2007
			US 2003068526 A1	10-04-2003
			US 2006177694 A1	10-08-2006

EP 1295514	B1	02-08-2006	AT 335386 T	15-08-2006
			AU 7155001 A	14-01-2002
			AU 2001271550 B2	12-05-2005
			CA 2411624 A1	10-01-2002
			CN 1449640 A	15-10-2003
			DE 60121950 T2	15-03-2007
			EP 1295514 A2	26-03-2003
			JP 2004503059 T	29-01-2004
			TW 593623 B	21-06-2004
			WO 0202714 A2	10-01-2002

EP 1399002	A	17-03-2004	CN 1518849 A	04-08-2004
			CN 101916829 A	15-12-2010
			WO 02104080 A1	27-12-2002
			US 2008265761 A1	30-10-2008
			US 2008265762 A1	30-10-2008
			US 2008265763 A1	30-10-2008
			US 2003141809 A1	31-07-2003

US 2001019782	A1	06-09-2001	NONE	

US 2001053462	A1	20-12-2001	JP 4048521 B2	20-02-2008
			JP 2001319780 A	16-11-2001

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 87901401 A [0001]
- US 21536200 P [0001]
- US 22427300 P [0001]
- US 5247190 A, Friend [0004]
- US 5408109 A, Heeger [0004]
- EP 443861 A [0004]
- US 5552678 A, Tang [0004]

Non-patent literature cited in the description

- *Appl. Phys. Lett.*, 1999, vol. 75, 4 [0005]
- *Polymer Preprints*, 2000, vol. 41 (1), 770 [0005]
- **MARKUS ; JOHN.** Electronics and Nucleonics Dictionary. McGraw-Hill, Inc, 1996, 470-476 [0047]
- CRC Handbook of Chemistry and Physics. 2000 [0051]
- Flexible light-emitting diodes made from soluble conducting polymer. *Nature*, 11 June 1992, vol. 357, 477-479 [0051]
- **Y. WANG.** Kirk-Othmer Encyclopedia of Chemical Technology. 1996, vol. 18, 837-860 [0052]
- **O. LOHSE ; P. THEVENIN ; E. WALDVOGEL.** *Synlett*, 1999, 45-48 [0062]
- **SPROUSE, S. ; KING, K. A. ; SPELLANE, P. J. ; WATTS, R. J.** *J. Am. Chem. Soc.*, 1984, vol. 106, 6647-53 [0107]
- **GARCES, F. O. ; KING, K. A. ; WATTS, R. J.** *Inorg. Chem.*, 1988, vol. 27, 3464-71 [0107]

专利名称(译)	铱化合物		
公开(公告)号	EP2299785A1	公开(公告)日	2011-03-23
申请号	EP2010011546	申请日	2001-12-26
[标]申请(专利权)人(译)	纳幕尔杜邦公司		
申请(专利权)人(译)	E·I·杜邦和公司		
当前申请(专利权)人(译)	E·I·杜邦和公司		
[标]发明人	PETROV VIACHESLAV A WANG YING GRUSHIN VLADIMIR		
发明人	PETROV, VIACHESLAV, A. WANG, YING GRUSHIN, VLADIMIR		
IPC分类号	H05B33/12 C07D213/02 C07D215/00 C07D217/00 C07D239/02 C07F15/00 C07D213/26 C07D213/30 C07D213/61 C07D213/68 C07D215/04 C07D239/26 C09K11/06 H01L51/00 H01L51/50 C07D215/12 H01L51/30 H05B H05B33/14 H05B33/22		
CPC分类号	C07D213/30 C07D213/26 C07D213/61 C07D213/68 C07D215/04 C07D239/26 C07F15/0033 C09K11/06 C09K2211/1007 C09K2211/1029 C09K2211/185 H01L51/0059 H01L51/0081 H01L51/0085 H01L51/5016 H05B33/14		
代理机构(译)	霍夫曼BENJAMIN		
优先权	PCT/US2001/049522 2001-12-26 WO		
外部链接	Espacenet		

摘要(译)

本发明一般涉及电致发光Ir(III)化合物，和用Ir(III)化合物制备的器件。




FIG. 1