



(11) **EP 2 927 300 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
16.11.2016 Bulletin 2016/46

(51) Int Cl.:
C09K 11/06 (2006.01) **H01L 51/00** (2006.01)
H01L 51/50 (2006.01) **C07F 15/00** (2006.01)
C07D 401/04 (2006.01) **C07F 5/00** (2006.01)
C07F 5/02 (2006.01)

(21) Application number: **15161743.8**

(22) Date of filing: **30.03.2015**

(54) **PHENYLENEDIAMINE COMPOUNDS FOR PHOSPHORESCENT DIAZABOROLE METAL COMPLEXES**

PHENYLENEDIAMINVERBINDUNGEN FÜR PHOSPHORESZIERENDE
DIAZABOROLMETALLKOMPLEXE

COMPOSÉS DE PHÉNYLÈNEDIAMINE POUR DES COMPLEXES MÉTALLIQUES DE
DIAZABOROLE PHOSPHORESCENTS

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **31.03.2014 AU 2014901154**

(43) Date of publication of application:
07.10.2015 Bulletin 2015/41

(73) Proprietor: **Commonwealth Scientific and
Industrial
Research Organisation
Campbell, Australian Capital Territory 2612 (AU)**

(72) Inventors:
• **Bilyk, Alexander
Mount Waverley, Victoria 3149 (AU)**

- **Bown, Mark
Notting Hill, Victoria 3168 (AU)**
- **Ueno, Kazunori
Glen Waverley, Victoria 3150 (AU)**
- **Groarke, Michelle
4125 Riehen (CH)**

(74) Representative: **Carpmaels & Ransford LLP
One Southampton Row
London WC1B 5HA (GB)**

(56) References cited:
**EP-A1- 0 679 641 WO-A1-2010/099852
WO-A1-2011/134013**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**FIELD**

[0001] The present disclosure generally relates to phenylenediamine compounds, which may be used as precursors in preparing diazaborole compounds and phosphorescent diazaborole metal complexes. The present disclosure also relates to diazaborole compounds, diazaborole metal complexes, and electroluminescent emission materials and electronic devices thereof. The present disclosure further relates to processes for preparing the phenylenediamine compounds and diazaborole metal complexes.

BACKGROUND

[0002] Organic electroluminescent devices (OLEDs) comprising organic semiconductors as functional emission materials are well known. An organic electroluminescent device is generally comprised of a pair of electrodes forming an anode and a cathode, and one layer or multiple layers comprising a hole transporting layer, emission layer (with an emissive material) and electron transporting layer. A voltage differential applied across the cathode and anode inject holes and electrons into the organic layer(s), which results in the formation of excitons within the emission material. The emission material then emits light when the excitons transition to the ground state.

[0003] New and improved phosphorescent materials for this type of application are continually being sought, since the luminous efficiency of OLEDs may potentially be improved by up to a factor of four when phosphorescent emitters are used in place of fluorescent emitters.

[0004] Organometallic complexes are increasingly being used as phosphorescent (triplet) emission materials in OLEDs (M. A. Baldo et al., Appl. Phys. Lett. 1999, 75, 4-6). Organometallic complexes can possess strong intersystem crossing from the singlet to the triplet state and is partly responsible for their success, for application in OLEDs. Metal complexes can also be used in other functions in OLEDs, such as matrix materials, electron-transport materials, hole-blocking materials or as dopants for use in one or more layers of such devices. WO 2010/099852 A1 concerns organic electroluminescent devices comprising metal complexes.


[0005] Improvements are still required in the physical properties of phosphorescent OLEDs, for example in respect of the stability of the metal complexes, efficiency, operating voltage and lifetime for use of triplet emitters in high-quality and long-lived electroluminescent devices. Improvements are sought for red-, green- and blue-phosphorescent metal complexes used in OLEDs, and particularly for blue-phosphorescent metal complexes. In working towards this, the emission wavelength (λ_{em}), lifetimes (T) and quantum yields (Φ_P) are important considerations when searching for suitable phosphorescent materials.

[0006] Consequently, there is a need to identify compounds that can act as ligands for facilitating stability in phosphorescent metal complexes. There is also a need to identify novel metal complexes that can be used in OLEDs as emission materials or other functional materials such as matrix materials, hole-blocking materials and electron-transport materials.

SUMMARY

[0007] The present disclosure provides phenylenediamine compounds, which can be used as precursors in preparing phosphorescent metal complexes. The phenylenediamine compounds can act as chelating ligands in diazaborole metal complexes. The phenylenediamine compounds may facilitate tunability and provide stability in diazaborole metal complexes, or at least provide alternative or improved phosphorescent compounds and emission materials for OLEDs.

[0008] In one aspect, there is provided a compound of Formula 1:



Formula 1

wherein

R¹ is selected from C₁₋₂₀alkyl, C₂₋₂₀alkenyl, C₂₋₂₀alkynyl, and a 5 or 6 membered aryl or heteroaryl, each of which is optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryl and heteroaryl;

R² and R³ are each independently selected from hydrogen and C₁₋₆alkyl;

Each R⁴ is independently selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally two R⁴ substituents from adjacent ring atoms are joined together to form an optionally substituted 5 or 6 membered aryl or heteroaryl ring; wherein R² and R³ are each independently defined as above;

T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from C, N, O, S, Si and B, each of which is optionally substituted with one or more substituents independently selected from hydrogen, halo, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₁₀alkyl, optionally substituted C₂₋₁₀alkenyl, optionally substituted C₂₋₁₀alkynyl and optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally fused with a 3-6 membered carbocycle or heterocycle; and wherein R² and R³ are each independently defined as above,

A is a monocyclic or bicyclic 5 or 6 membered heterocyclic ring containing a donor atom D and a ring atom A¹, and optionally having 1 or 2 additional ring heteroatoms selected from O, S and N, wherein the heterocyclic ring is optionally substituted with 1 to 3 substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, and optionally substituted 5 or 6 membered aryl or heteroaryl; wherein R² and R³ are each independently defined as above;

A¹ is selected from C, N and CR⁷; wherein R⁷ is selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl; R² and R³ are each independently defined as described herein; and

D is a donor atom selected from N, O, S, P, Se and Te.


[0009] In one embodiment, R¹ is selected from optionally substituted C₁₋₂₀alkyl and optionally substituted monocyclic 5 or 6 membered aryl or heteroaryl. In another embodiment, R¹ is selected from optionally substituted C₁₋₁₀alkyl.

[0010] In one embodiment, T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)-, -S(=O)₂-, C₁₋₃alkyl and C₂₋₃alkenyl; wherein the C₁₋₃alkyl and C₂₋₃alkenyl are each optionally interrupted by a group selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)- and S(=O)₂-, and optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², C₁₋₁₀alkyl, C₂₋₁₀alkenyl, C₂₋₁₀alkynyl, C₁₋₁₀alkylhalo, C₂₋₁₀alkenylhalo and C₂₋₁₀alkynylhalo, and optionally fused with a 3-6 membered carbocycle or heterocycle. R⁶ can be selected from hydrogen and C₁₋₁₀alkyl. In another embodiment, T is an optionally substituted, optionally fused C₁₋₃ group, for example an optionally substituted C₁₋₃alkyl or C₂₋₃alkenyl. In another embodiment, the optional substitution on the tether group T may be independently selected from optionally substituted C₁₋₆alkyl, for example optionally substituted methyl, ethyl or propyl.

[0011] In one embodiment, A is an optionally substituted monocyclic or bicyclic 5 or 6 membered heterocyclic ring containing at least one unsaturated bond. In another embodiment, A is an optionally substituted monocyclic or bicyclic

5 or 6 membered heteroaryl ring. In another embodiment, D is selected from N, for example wherein A is an optionally substituted pyridine group. In another embodiment, A¹ is selected from C.

[0012] In another aspect, there is provided a compound of Formula 2:



Formula 2

wherein

R¹ is selected from C₁₋₂₀alkyl, C₂₋₂₀alkenyl, C₂₋₂₀alkynyl, and a 5 or 6 membered aryl or heteroaryl, each of which is optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryl and heteroaryl;

R² and R³ are each independently selected from hydrogen and C₁₋₆alkyl;

Each R⁴ is independently selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally two R⁴ substituents from adjacent ring atoms are joined together to form an optionally substituted 5 or 6 membered aryl or heteroaryl ring; wherein R² and R³ are each independently defined as above;

T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from C, N, O, S, Si and B, each of which is optionally substituted with one or more substituents independently selected from hydrogen, halo, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₁₀alkyl, optionally substituted C₂₋₁₀alkenyl, optionally substituted C₂₋₁₀alkynyl and optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally fused with a 3-6 membered carbocycle or heterocycle; and wherein R² and R³ are each independently defined as above,

A is a monocyclic or bicyclic 5 or 6 membered heterocyclic ring containing a donor atom D and a ring atom A¹, and optionally having 1 or 2 additional ring heteroatoms selected from O, S and N, wherein the heterocyclic ring is optionally substituted with 1 to 3 substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, and optionally substituted 5 or 6 membered aryl or heteroaryl; wherein R² and R³ are each independently defined as above;

A¹ is selected from C, N and CR⁷; wherein R⁷ is selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl; R² and R³ are each independently defined as described herein; and


D is a donor atom selected from N, O, S, P, Se and Te; and

R¹⁰ is selected from hydrogen or halo.

[0013] In one embodiment, R¹⁰ is halo, for example bromine.

[0014] It will be appreciated that the embodiments described herein for R¹, R⁴, T, A, A¹ and D, in relation to compounds of Formula 1, can also provide embodiments for compounds of Formula 2.

[0015] In another aspect, there is provided a metal complex of Formula 3:



Formula 3

wherein

M is a metal atom selected from Ir, Pt, Rh, Pd, Ru and Os;

n is an integer selected from 1, 2 and 3;

m is an integer selected from 0, 1, 2, 3, 4 and 5;

L is a monodentate or bidentate ligand; and

R¹ is selected from C₁₋₂₀alkyl, C₂₋₂₀alkenyl, C₂₋₂₀alkynyl, and a 5 or 6 membered aryl or heteroaryl, each of which is optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryl and heteroaryl;

R² and R³ are each independently selected from hydrogen and C₁₋₆alkyl;

Each R⁴ is independently selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally two R⁴ substituents from adjacent ring atoms are joined together to form an optionally substituted 5 or 6 membered aryl or heteroaryl ring; wherein R² and R³ are each independently defined as above;

T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from C, N, O, S, Si and B, each of which is optionally substituted with one or more substituents independently selected from hydrogen, halo, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₁₀alkyl, optionally substituted C₂₋₁₀alkenyl, optionally substituted C₂₋₁₀alkynyl and optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally fused with a 3-6 membered carbocycle or heterocycle; and wherein R² and R³ are each independently defined as above,

A is a monocyclic or bicyclic 5 or 6 membered heterocyclic ring containing a donor atom D and a ring atom A¹, and optionally having 1 or 2 additional ring heteroatoms selected from O, S and N, wherein the heterocyclic ring is optionally substituted with 1 to 3 substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, and optionally substituted 5 or 6 membered aryl or heteroaryl; wherein R² and R³ are each independently defined as above;

A¹ is selected from C, N and CR⁷; wherein R⁷ is selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl; R² and R³ are each independently defined as described herein; and

D is a donor atom selected from N, O, S, P, Se and Te.

[0016] It will be appreciated that the embodiments described herein for R¹, R², R³, R⁴, T, A, A¹ and D, in relation to compounds of Formula 1, can also provide embodiments for compounds of Formula 3.

[0017] In one embodiment, M is a metal atom selected from Ir and Pt. In a particular embodiment, M is selected from Ir.

[0018] In one embodiment, n is 3, m is 0 and L is absent.

[0019] In another aspect, there is provided an emission material comprising a metal complex of Formula 3, as described herein.

[0020] The emission material may comprise one or more matrix materials. The emission material may comprise one or more functional additives selected from hole-injection materials, hole-transport materials, hole-blocking materials, electron-transport materials, electron-injection materials, electron-blocking materials, exciton-blocking materials, charge-generation materials and/or organic or inorganic p/n junctions.

[0021] In another aspect, there is provided use of a metal complex of Formula 3, as described herein, as an emission material in an electronic device. In one embodiment, the electronic device is an organic electroluminescent device.

[0022] In another aspect, there is provided a matrix material comprising a metal complex of Formula 3 as described herein.

[0023] The matrix material may comprise one or more functional additives selected from emission materials, hole-injection materials, hole-transport materials, hole-blocking materials, electron-transport materials, electron-injection materials, electron-blocking materials, exciton-blocking materials, charge-generation materials and/or organic or inorganic p/n junctions.

[0024] In another aspect, there is provided use of a metal complex of Formula 3, as described herein, as a matrix material in an electronic device. In one embodiment, the electronic device is an organic electroluminescent device.

[0025] In another aspect, there is provided an electronic device comprising a metal complex of Formula 3 as described herein.

[0026] In another aspect, there is provided use of a metal complex of Formula 3 as described herein, in an electronic device.

[0027] In one embodiment, the electronic device is an organic electroluminescent device. The organic electroluminescent device may be an organic light emitting device, a photovoltaic device or a sensor. The organic electroluminescent device may comprise: a pair of electrodes comprising a cathode and an anode; and at least one layer comprising an emission material arranged between the pair of electrodes comprising a metal complex of Formula 3 as described herein. The organic electronic device may comprise further layers, selected from in each case one or more hole-injection layers, hole-transport layers, hole-blocking layers, electron-transport layers, electron-injection layers, electron-blocking layers, exciton-blocking layers, charge-generation layers and/or organic or inorganic p/n junctions.

[0028] In another aspect, there is provided a process for preparing a phenylenediamine compound according to Formula 1, the process comprising the steps:

reacting an optionally substituted benzimidazole compound with an optionally substituted monocyclic or bicyclic 5 or 6 membered heterocyclic ring comprising a donor atom D selected from N, O, S, P, Se and Te, to form an N-substituted benzimidazole compound; and

reacting the N-substituted benzimidazole compound with a reducing agent to form a phenylenediamine compound of Formula 1, as described herein.

[0029] In another aspect, there is provided a process for preparing a metal complex according to Formula 3 comprising the steps:

reacting a phenylenediamine compound of Formula 1 with a boron agent to obtain a diazaborole compound of Formula 2, as described herein;

reacting the diazaborole compound of Formula 2 with a precursor complex of the metal M having substitutable ligands in a ratio suitable to obtain a product being a metal complex of Formula 3 having the desired number n of phenylenediamine compounds of Formula 1, and optionally ligands L, being co-ordinated to the metal M; and

optionally further reacting the product with another ligand L in a ratio suitable to introduce the desired number of ligands L into the metal complex of Formula 3.

[0030] Other features, objects and advantages of the present disclosure and its embodiments will become apparent from the detailed description, examples and claims that follow.

DETAILED DESCRIPTION

[0031] The present invention is described in the following various non-limiting embodiments, which relate to investigations undertaken to identify precursor compounds for preparing alternative or improved phosphorescent metal complexes. The metal complexes of the present disclosure can be used as an active component in electronic devices, such as an emission material in OLEDs.

GENERAL TERMS

[0032] Throughout this specification, unless specifically stated otherwise or the context requires otherwise, reference to a single step, composition of matter, group of steps or group of compositions of matter shall be taken to encompass one and a plurality (i.e. one or more) of those steps, compositions of matter, groups of steps or groups of compositions of matter. Thus, as used herein, the singular forms "a", "an" and "the" include plural aspects unless the context clearly dictates otherwise. For example, reference to "a" includes a single as well as two or more; reference to "an" includes a

single as well as two or more; reference to "the" includes a single as well as two or more and so forth.

[0033] Those skilled in the art will appreciate that the disclosure herein is susceptible to variations and modifications other than those specifically described. It is to be understood that the disclosure includes all such variations and modifications. The disclosure also includes all of the steps, features, compositions and compounds referred to or indicated

[0034] Each example of the present disclosure described herein is to be applied mutatis mutandis to each and every other example unless specifically stated otherwise. The present disclosure is not to be limited in scope by the specific examples described herein, which are intended for the purpose of exemplification only. Functionally-equivalent products, compositions and methods are clearly within the scope of the disclosure as described herein.

[0035] The term "and/or", e.g., "X and/or Y" shall be understood to mean either "X and Y" or "X or Y" and shall be taken to provide explicit support for both meanings or for either meaning.

[0036] Throughout this specification the word "comprise", or variations such as "comprises" or "comprising", will be understood to imply the inclusion of a stated element, integer or step, or group of elements, integers or steps, but not the exclusion of any other element, integer or step, or group of elements, integers or steps.

[0037] It will be clearly understood that, although a number of prior art publications are referred to herein, this reference does not constitute an admission that any of these documents forms part of the common general knowledge in the art, in Australia or in any other country.

[0038] Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. Although methods and materials similar or equivalent to those described herein can be used in the practice or testing of the present invention, suitable methods and materials are described below. In case of conflict, the present specification, including definitions, will control. In addition, the materials, methods, and examples are illustrative only and not intended to be limiting.

SPECIFIC TERMS

[0039] The terms "carbocyclic" and "carbocyclyl" represent a ring system wherein the ring atoms are all carbon atoms, e.g., of about 3 to about 30 carbon atoms, and which may be aromatic, non-aromatic, saturated, or unsaturated, and may be substituted and/or carry fused rings. Examples of such groups include benzene, cyclopentyl, cyclohexyl, or fully or partially hydrogenated phenyl, naphthyl and fluorenyl.

[0040] "Heterocyclyl" or "heterocyclic" whether used alone, or in compound words such as heterocycloxy represents: (i) an optionally substituted cycloalkyl or cycloalkenyl group, e.g., of about 3 to about 30 ring members, which may contain one or more heteroatoms such as nitrogen, oxygen, or sulfur (examples include pyrrolidinyl, morpholino, thiomorpholino, or fully or partially hydrogenated thienyl, furyl, pyrrolyl, thiazolyl, oxazolyl, oxazinyl, thiazinyl, pyridyl and azepinyl); (ii) an optionally substituted partially saturated polycyclic ring system in which an aryl (or heteroaryl) ring and a heterocyclic group are fused together to form a cyclic structure (examples include chromanyl, dihydrobenzofuryl and indolinyl); or (iii) an optionally substituted fully or partially saturated polycyclic fused ring system that has one or more bridges (examples include quinuclidinyl and dihydro-1,4-epoxynaphthyl).

[0041] As will be understood, an "aromatic" group means a cyclic group having $4m+2\pi$ electrons, where m is an integer equal to or greater than 1. As used herein, "aromatic" is used interchangeably with "aryl" to refer to an aromatic group, regardless of the valency of aromatic group.

[0042] "Aryl" whether used alone, or in compound words such as arylalkyl, aryloxy or arylthio, represents: (i) an optionally substituted mono- or polycyclic aromatic carbocyclic moiety, e.g., of about 6 to about 30 carbon atoms, such as phenyl, naphthyl or fluorenyl; or, (ii) an optionally substituted partially saturated polycyclic carbocyclic aromatic ring system in which an aryl and a cycloalkyl or cycloalkenyl group are fused together to form a cyclic structure such as a tetrahydronaphthyl, indenyl, indanyl or fluorene ring.

[0043] A heteroaromatic group is an aromatic group or ring containing one or more heteroatoms, such as N, O, S, Se, Si or P. As used herein, "heteroaromatic" is used interchangeably with "heteroaryl", and a heteroaryl group refers to monovalent aromatic groups, bivalent aromatic groups and higher multivalency aromatic groups containing one or more heteroatoms.

[0044] "Heteroaryl" whether used alone, or in compound words such as heteroaryloxy represents: (i) an optionally substituted mono- or polycyclic aromatic organic moiety, e.g., of about 5 to about 30 ring members in which one or more of the ring members is/are element(s) other than carbon, for example nitrogen, oxygen, sulfur or silicon; the heteroatom(s) interrupting a carbocyclic ring structure and having a sufficient number of delocalized π electrons to provide aromatic character, provided that the rings do not contain adjacent oxygen and/or sulfur atoms. Typical 6-membered heteroaryl groups are pyrazinyl, pyridazinyl, pyrazolyl, pyridyl and pyrimidinyl. All regioisomers are contemplated, e.g., 2-pyridyl, 3-pyridyl and 4-pyridyl. Typical 5-membered heteroaryl rings are furyl, imidazolyl, oxazolyl, isoxazolyl, isothiazolyl, oxadiazolyl, pyrrolyl, 1,3,4-thiadiazolyl, thiazolyl, thienyl, triazolyl, and silole. All regioisomers are contemplated, e.g., 2-thienyl and 3-thienyl. Bicyclic groups typically are benzo-fused ring systems derived from the heteroaryl groups named

above, e.g., benzofuryl, benzimidazolyl, benzthiazolyl, indolyl, indolizynyl, isoquinolyl, quinazolynyl, quinolyl and benzo-thienyl; or, (ii) an optionally substituted partially saturated polycyclic heteroaryl ring system in which a heteroaryl and a cycloalkyl or cycloalkenyl group are fused together to form a cyclic structure such as a tetrahydroquinolyl or pyridinyl ring.

[0045] The term "optionally fused" means that a group is either fused by another ring system or unfused, and "fused" refers to one or more rings that share at least two common ring atoms with one or more other rings. Fusing may be provided by one or more carbocyclic, heterocyclic, aryl or heteroaryl rings, as defined herein, or be provided by substituents of rings being joined together to form a further ring system. The fused ring may be a 5, 6 or 7 membered ring of between 5 and 10 ring atoms in size. The fused ring may be fused to one or more other rings, and may for example contain 1 to 4 rings.

[0046] The term "optionally substituted" means that a functional group is either substituted or unsubstituted, at any available position. Substitution can be with one or more functional groups selected from, e.g., alkyl, alkenyl, alkynyl, cycloalkyl, cycloalkenyl, aryl, heterocyclyl, heteroaryl, formyl, alkanoyl, cycloalkanoyl, aroyl, heteroaroyl, carboxyl, alkoxycarbonyl, cycloalkyloxycarbonyl, aryloxycarbonyl, heterocyclyloxycarbonyl, heteroaryloxycarbonyl, alkylaminocarbonyl, cycloalkylaminocarbonyl, arylaminocarbonyl, heterocyclylaminocarbonyl, heteroarylaminocarbonyl, cyano, alkoxy, cycloalkoxy, aryloxy, heterocyclyloxy, heteroaryloxy, alkanoate, cycloalkanoate, aryloate, heterocyclyloate, heteroaryloate, alkylcarbonylamino, cycloalkylcarbonylamino, arylcarbonylamino, heterocyclylcarbonylamino, heteroarylcarbonylamino, nitro, alkylthio, cycloalkylthio, arylthio, heterocyclylthio, heteroarylthio, alkylsulfonyl, cycloalkylsulfonyl, arylsulfonyl, heterocyclysulfonyl, heteroarylsulfonyl, hydroxyl, halo, haloalkyl, haloaryl, haloheterocyclyl, haloheteroaryl, haloalkoxy, haloalkylsulfonyl, silylalkyl, alkenylsilylalkyl, and alkynylsilylalkyl. It will be appreciated that other groups not specifically described may also be used.

[0047] The term "halo" or "halogen" whether employed alone or in compound words such as haloalkyl, haloalkoxy or haloalkylsulfonyl, represents fluorine, chlorine, bromine or iodine. Further, when used in compound words such as haloalkyl, haloalkoxy or haloalkylsulfonyl, the alkyl may be partially halogenated or fully substituted with halogen atoms which may be independently the same or different. Examples of haloalkyl include, without limitation, $-\text{CH}_2\text{CH}_2\text{F}$, $-\text{CF}_2\text{CF}_3$ and $-\text{CH}_2\text{CHFCl}$. Examples of haloalkoxy include, without limitation, $-\text{OCHF}_2$, $-\text{OCF}_3$, $-\text{OCH}_2\text{CCl}_3$, $-\text{OCH}_2\text{CF}_3$ and $-\text{OCH}_2\text{CH}_2\text{CF}_3$. Examples of haloalkylsulfonyl include, without limitation, $-\text{SO}_2\text{CF}_3$, $-\text{SO}_2\text{CCl}_3$, $-\text{SO}_2\text{CH}_2\text{CF}_3$ and $-\text{SO}_2\text{CF}_2\text{CF}_3$.

[0048] "Alkyl" whether used alone, or in compound words such as alkoxy, alkylthio, alkylamino, dialkylamino or haloalkyl, represents straight or branched chain hydrocarbons ranging in size from one to about 20 carbon atoms, or more. Thus alkyl moieties include, unless explicitly limited to smaller groups, moieties ranging in size, for example, from one to about 6 carbon atoms or greater, such as, methyl, ethyl, n-propyl, iso-propyl and/or butyl, pentyl, hexyl, and higher isomers, including, e.g., those straight or branched chain hydrocarbons ranging in size from about 6 to about 20 carbon atoms, or greater.

[0049] "Alkenyl" whether used alone, or in compound words such as alkenyloxy or haloalkenyl, represents straight or branched chain hydrocarbons containing at least one carbon-carbon double bond, including, unless explicitly limited to smaller groups, moieties ranging in size from two to about 6 carbon atoms or greater, such as, methylene, ethylene, 1-propenyl, 2-propenyl, and/or butenyl, pentenyl, hexenyl, and higher isomers, including, e.g., those straight or branched chain hydrocarbons ranging in size, for example, from about 6 to about 20 carbon atoms, or greater.

[0050] "Alkynyl" whether used alone, or in compound words such as alkynyloxy, represents straight or branched chain hydrocarbons containing at least one carbon-carbon triple bond, including, unless explicitly limited to smaller groups, moieties ranging in size from, e.g., two to about 6 carbon atoms or greater, such as, ethynyl, 1-propynyl, 2-propynyl, and/or butynyl, pentynyl, hexynyl, and higher isomers, including, e.g., those straight or branched chain hydrocarbons ranging in size from, e.g., about 6 to about 20 carbon atoms, or greater.

[0051] "Cycloalkyl" represents a mono- or polycarbocyclic ring system of varying sizes, e.g., from about 3 to about 20 carbon atoms, e.g., cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl or cycloheptyl. The term cycloalkyloxy represents the same groups linked through an oxygen atom such as cyclopentyloxy and cyclohexyloxy. The term cycloalkylthio represents the same groups linked through a sulfur atom such as cyclopentylthio and cyclohexylthio.

[0052] "Cycloalkenyl" represents a non-aromatic mono- or polycarbocyclic ring system, e.g., of about 3 to about 20 carbon atoms containing at least one carbon-carbon double bond, e.g., cyclopentenyl, cyclohexenyl or cycloheptenyl. The term "cycloalkenyloxy" represents the same groups linked through an oxygen atom such as cyclopentenylloxy and cyclohexenylloxy. The term "cycloalkenylthio" represents the same groups linked through a sulfur atom such as cyclopentenylthio and cyclohexenylthio.

[0053] "Cycloalkynyl" represents a non-aromatic mono- or polycarbocyclic ring system, e.g., of about 3 to about 20 carbon atoms containing at least one carbon-carbon double bond, e.g., cyclopentenyl, cyclohexenyl or cycloheptenyl. The term "cycloalkenyloxy" represents the same groups linked through an oxygen atom such as cyclopentenylloxy and cyclohexenylloxy. The term "cycloalkenylthio" represents the same groups linked through a sulfur atom such as cyclopentenylthio and cyclohexenylthio.

[0054] "Formyl" represents a $-\text{CHO}$ moiety.

- [0055]** "Alkanoyl" represents a -C(=O)-alkyl group in which the alkyl group is as defined supra. In a particular embodiment, an alkanoyl ranges in size from about C₂-C₂₀. One example is acyl.
- [0056]** "Aroyl" represents a -C(=O)-aryl group in which the aryl group is as defined supra. In a particular embodiment, an aroyl ranges in size from about C₇-C₂₀. Examples include benzoyl and 1-naphthoyl and 2-naphthoyl.
- 5 **[0057]** "Heterocycloyl" represents a -C(=O)-heterocyclyl group in which the heterocyclic group is as defined supra. In a particular embodiment, an heterocycloyl ranges in size from about C₄-C₂₀.
- [0058]** "Heteroaroyl" represents a -C(=O)-heteroaryl group in which the heteroaryl group is as defined supra.
- [0059]** In a particular embodiment, a heteroaroyl ranges in size from about C₆-C₂₀. An example is pyridylcarbonyl.
- [0060]** "Carboxyl" represents a -CO₂H moiety.
- 10 **[0061]** "Oxycarbonyl" represents a carboxylic acid ester group -CO₂R which is linked to the rest of the molecule through a carbon atom.
- [0062]** "Alkoxycarbonyl" represents an -CO₂-alkyl group in which the alkyl group is as defined supra. In a particular embodiment, an alkoxycarbonyl ranges in size from about C₂-C₂₀. Examples include methoxycarbonyl and ethoxycarbonyl.
- 15 **[0063]** "Aryloxycarbonyl" represents an -CO₂-aryl group in which the aryl group is as defined supra. Examples include phenoxycarbonyl and naphthoxycarbonyl.
- [0064]** "Heterocyclyloxycarbonyl" represents a -CO₂-heterocyclyl group in which the heterocyclic group is as defined supra.
- [0065]** "Heteroaryloxycarbonyl" represents a -CO-heteroaryl group in which the heteroaryl group is as defined supra.
- 20 **[0066]** "Aminocarbonyl" represents a carboxylic acid amide group -C(=O)NHR or -C(=O)NR₂ which is linked to the rest of the molecule through a carbon atom.
- [0067]** "Alkylaminocarbonyl" represents a -C(=O)NHR or -C(=O)NR₂ group in which R is an alkyl group as defined supra.
- "Arylaminocarbonyl" represents a -C(=O)NHR or -C(=O)NR₂ group in which R is an aryl group as defined supra.
- 25 **[0068]** "Heterocyclylaminocarbonyl" represents a -C(=O)NHR or -C(=O)NR₂ group in which R is a heterocyclic group as defined supra. In certain embodiments, NR₂ is a heterocyclic ring, which is optionally substituted.
- [0069]** "Heteroarylaminocarbonyl" represents a -C(=O)NHR or -C(=O)NR₂ group in which R is a heteroaryl group as defined supra. In certain embodiments, NR₂ is a heteroaryl ring, which is optionally substituted.
- [0070]** "Cyano" represents a -CN moiety.
- 30 **[0071]** "Hydroxyl" represents a -OH moiety.
- [0072]** "Alkoxy" represents an -O-alkyl group in which the alkyl group is as defined supra. Examples include methoxy, ethoxy, n-propoxy, iso-propoxy, and the different butoxy, pentoxy, hexyloxy and higher isomers.
- [0073]** "Aryloxy" represents an -O-aryl group in which the aryl group is as defined supra. Examples include, without limitation, phenoxy and naphthoxy.
- 35 **[0074]** "Alkenyloxy" represents an -O-alkenyl group in which the alkenyl group is as defined supra. An example is allyloxy.
- [0075]** "Heterocyclyloxy" represents an -O-heterocyclyl group in which the heterocyclic group is as defined supra.
- [0076]** "Heteroaryloxy" represents an -O-heteroaryl group in which the heteroaryl group is as defined supra. An example is pyridyloxy.
- 40 **[0077]** "Alkanoate" represents an -OC(=O)-R group in which R is an alkyl group as defined supra. "Aryloate" represents a -OC(=O)-R group in which R is an aryl group as defined supra.
- [0078]** "Heterocyclyloate" represents an -OC(=O)-R group in which R is a heterocyclic group as defined supra.
- [0079]** "Heteroaryloate" represents an -OC(=O)-R group in which R is a heteroaryl group as defined supra.
- [0080]** "Amino" represents an -NH₂ moiety.
- 45 **[0081]** "Alkylamino" represents an -NHR or -NR₂ group in which R is an alkyl group as defined supra. Examples include, without limitation, methylamino, ethylamino, n-propylamino, isopropylamino, and the different butylamino, pentylamino, hexylamino and higher isomers.
- [0082]** "Arylamino" represents an -NHR or -NR₂ group in which R is an aryl group as defined supra. An example is phenylamino.
- 50 **[0083]** "Heterocyclylamino" represents an -NHR or -NR₂ group in which R is a heterocyclic group as defined supra. In certain embodiments, NR₂ is a heterocyclic ring, which is optionally substituted.
- [0084]** "Heteroarylaminino" represents a -NHR or -NR₂ group in which R is a heteroaryl group as defined supra. In certain embodiments, NR₂ is a heteroaryl ring, which is optionally substituted.
- [0085]** "Carbonylamino" represents a carboxylic acid amide group -NHC(=O)R that is linked to the rest of the molecule through a nitrogen atom.
- 55 **[0086]** "Alkylcarbonylamino" represents a -NHC(=O)R group in which R is an alkyl group as defined supra.
- [0087]** "Arylcarbonylamino" represents an -NHC(=O)R group in which R is an aryl group as defined supra.
- [0088]** "Heterocyclylcarbonylamino" represents an -NHC(=O)R group in which R is a heterocyclic group as defined

supra.

[0089] "Heteroarylcarbonylamino" represents an -NHC(=O)R group in which R is a heteroaryl group as defined supra.

[0090] "Nitro" represents a -NO_2 moiety.

[0091] "Alkylthio" represents an -S-alkyl group in which the alkyl group is as defined supra. Examples include, without limitation, methylthio, ethylthio, n-propylthio, iso propylthio, and the different butylthio, pentylthio, hexylthio and higher isomers.

[0092] "Arylthio" represents an -S-aryl group in which the aryl group is as defined supra. Examples include phenylthio and naphthylthio.

[0093] "Heterocyclylthio" represents an -S-heterocyclyl group in which the heterocyclic group is as defined supra.

[0094] "Heteroarylthio" represents an -S-heteroaryl group in which the heteroaryl group is as defined supra.

[0095] "Sulfonyl" represents an $\text{-SO}_2\text{R}$ group that is linked to the rest of the molecule through a sulfur atom.

[0096] "Alkylsulfonyl" represents an $\text{-SO}_2\text{-alkyl}$ group in which the alkyl group is as defined supra.

[0097] "Arylsulfonyl" represents an $\text{-SO}_2\text{-aryl}$ group in which the aryl group is as defined supra.

[0098] "Heterocyclylsulfonyl" represents an $\text{-SO}_2\text{-heterocyclyl}$ group in which the heterocyclic group is as defined supra.

[0099] "Heteroarylsulfonyl" presents an $\text{-SO}_2\text{-heteroaryl}$ group in which the heteroaryl group is as defined supra.

[0100] "Aldehyde" represents a -C(=O)H group.

[0101] "Alkanal" represents an alkyl-(C=O)H group in which the alkyl group is as defined supra.

[0102] "Alkylsilyl" presents an alkyl group that is linked to the rest of the molecule through the silicon atom, which may be substituted with up to three independently selected alkyl groups in which each alkyl group is as defined supra.


[0103] "Alkenylsilyl" presents an alkenyl group that is linked to the rest of the molecule through the silicon atom, which may be substituted with up to three independently selected alkenyl groups in which each alkenyl group is as defined supra.

[0104] "Alkynylsilyl" presents an alkynyl group that is linked to the rest of the molecule through the silicon atom, which may be substituted with up to three independently selected alkynyl groups in which each alkenyl group is as defined supra.

DIAMINE COMPOUNDS

[0105] The present disclosure provides phenylenediamine compounds of Formula 1 as described below. The phenylenediamine compounds can be used as precursors in preparing phosphorescent diazaborole metal complexes, which are suitable for use as emission materials or within emission materials and electronic devices, such as OLEDs. Each phenylenediamine compound contains two secondary amine groups attached in an ortho arrangement (i.e. 1,2- attachment at adjacent ring atoms). The two secondary amine groups can provide a chelating group for a phosphorescent boron metal complex. In the phenylenediamine compounds, one of the secondary amine groups is also attached to a further 5 or 6 membered heterocyclic group containing a donor atom D for coordination to a metal atom.

[0106] The phenylenediamine compounds of Formula 1 are described in further detail below, and generally by the following structure:



Formula 1

wherein R^1 , R^4 , T, A, A^1 and D, can be defined as described herein.

R¹ Group

[0107] R^1 can be selected from C_{1-20} alkyl, C_{2-20} alkenyl, C_{2-20} alkynyl, and a 5 or 6 membered aryl or heteroaryl, each of which can be optionally substituted with one or more substituents. The one or more substituents of the above described R^1 groups may be independently selected from halo, CN, NO_2 , C(O)R^2 , OR^2 , $\text{OS(O)}_2\text{R}^2$, NR^2R^3 , SR^2 , aryl and heteroaryl.

R² and R³ can each be independently selected from hydrogen and C₁₋₆alkyl. The 5 or 6 membered aryl or heteroaryl may be monocyclic such as benzene and pyridine, bicyclic such as naphthalene, phenylbenzene and quinoline, or tricyclic such as anthracene, diphenylbenzene and acridine. In one embodiment, R¹ is selected from optionally substituted C₁₋₂₀alkyl and optionally substituted monocyclic 5 or 6 membered aryl or heteroaryl. In another embodiment, R¹ is selected from optionally substituted C₁₋₁₀alkyl.

TETHER GROUP T

[0108] T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from C, N, O, S, Si and B. In one embodiment, the atoms are independently selected from C, N, O and S. Each of the 1 to 3 atoms can be optionally substituted. The optional substitution may be with one or more substituents independently selected from hydrogen, halo, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₁₀alkyl, optionally substituted C₂₋₁₀alkenyl, optionally substituted C₂₋₁₀alkynyl and optionally substituted 5 or 6 membered aryl or heteroaryl. R² and R³ can each be independently defined as herein described. T may be optionally fused with a 3-6 membered carbocycle or heterocycle, for example where T is provided by a linear chain of 2 or 3 atoms then a 3-6 membered ring may be fused to 2 atoms of the linear chain. The optionally fused 3-6 membered carbocycle or heterocycle can be selected from an optionally substituted C₃₋₆cycloalkyl, optionally substituted phenyl, optionally substituted 5 or 6 membered heterocycle, or optionally substituted 5 or 6 membered heteroaryl.

[0109] In another embodiment, T can be a tether group provided by a linear chain of 1 to 3 atoms independently selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)-, -S(=O)₂-, -Si(R⁵)₂-, -B(R⁶)-, C₁₋₃alkyl and C₂₋₃alkenyl, each of which may be optionally substituted and optionally fused. In another embodiment, T can be a tether group provided by a linear chain of 1 to 3 atoms independently selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)-, -S(=O)₂-, C₁₋₃alkyl and C₂₋₃alkenyl, each of which may be optionally substituted and optionally fused. The C₁₋₃alkyl or C₂₋₃alkenyl can be optionally interrupted by a group selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)- and S(=O)₂. The C₁₋₃alkyl or C₂₋₃alkenyl can be optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², C₁₋₁₀alkyl, C₂₋₁₀alkenyl, C₂₋₁₀alkynyl, C₁₋₁₀alkylhalo, C₂₋₁₀alkenylhalo and C₂₋₁₀alkynylhalo. In one embodiment, the C₁₋₃alkyl or C₂₋₃alkenyl is substituted with one or more optionally substituted C₁₋₄alkyl groups, for example where T is -C(CH₃)₂-, -C(CH₃)=C(CH₃)- or -C(CH₂Cl)₂-C(CH₃)₂-. R² and R³ can each be independently defined as described above. The C₁₋₃alkyl or C₂₋₃alkenyl can be optionally fused with a 3-6 membered carbocycle or heterocycle, such as an optionally substituted C₃₋₆cycloalkyl, optionally substituted phenyl, optionally substituted 5 or 6 membered heterocycle, or optionally substituted 5 or 6 membered heteroaryl.





[0110] Each R⁵ group can be independently selected from R⁴ groups according to embodiments as defined herein. In one embodiment, each R⁵ group can be independently selected from hydrogen and C₁₋₁₀alkyl. In another embodiment, each R⁵ can be independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², C₁₋₁₀alkyl, C₂₋₁₀alkenyl, C₂₋₁₀alkynyl, C₁₋₁₀alkylhalo, C₂₋₁₀alkenylhalo and C₂₋₁₀alkynylhalo. In a further embodiment, each R⁵ can be independently selected from optionally substituted C₁₋₄alkyl groups, for example methyl or bromoethyl. R² and R³ can each be independently defined as described herein.


[0111] Each R⁶ can be independently selected from hydrogen, optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, and optionally substituted 5 or 6 membered aryl or heteroaryl. The optional substitution may be with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryl and heteroaryl. R² and R³ can each be independently selected from hydrogen and C₁₋₆alkyl. In one embodiment, each R⁶ is independently selected from hydrogen and C₁₋₁₀alkyl.

[0112] In another embodiment, T is an optionally substituted, optionally fused C₁₋₃ group, for example an optionally substituted, optionally fused C₁₋₃alkyl or C₂₋₃alkenyl. The C₁₋₃alkyl or C₂₋₃alkenyl can be optionally interrupted by a group selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)- and S(=O)₂. The optional substituents and optional fusing may be provided as described above.

[0113] In another embodiment, the optional substitution on the tether group T may be independently selected from optionally substituted C₁₋₁₀alkyl, for example optionally substituted methyl, ethyl or propyl.

[0114] Specific examples of the tether group T for compounds of Formula 1 are provided as follows:





wherein A, A¹, D and R¹, R⁴, R⁵ and R⁶, can each be independently defined according to any embodiments described herein.

RING A


[0115] A is a monocyclic or bicyclic 5 or 6 membered heterocyclic ring containing a donor atom D and a ring atom A¹. The A ring can optionally have 1 or 2 additional ring heteroatoms selected from O, S and N. In one embodiment, A is an optionally substituted monocyclic or bicyclic 5 or 6 membered heterocyclic ring containing at least one unsaturated bond. In another embodiment, A is an optionally substituted monocyclic or bicyclic 5 or 6 membered heteroaryl ring. In a particular embodiment, A is an optionally substituted monocyclic ring.

[0116] The A ring can be optionally substituted with 1 to 3 substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, and optionally substituted 5 or 6 membered aryl or heteroaryl. R² and R³ can be defined as described herein.


[0117] A¹ can be selected from C, N and CR⁷. In an embodiment, A¹ can be selected from C, N, C-H, C-halo, C-C₁₋₁₀alkyl, C-C₁₋₁₀haloalkyl, C-C₁₋₁₀alkoxy and C-C₁₋₁₀alkoxyhalo. In another embodiment, A¹ is selected from C and N. In a further embodiment, A¹ is selected from C. R⁷ can be selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl. R² and R³ can each be independently defined as described herein.

[0118] D is a donor atom that can be selected from N, O, S, P, Se and Te. In one embodiment, D is selected from N, for example wherein A is an optionally substituted pyridine group.

[0119] In another embodiment, compounds of Formula 1 may be provided by compounds according to Formula 1a or Formula 1b:



Formula 1a



Formula 1b

wherein T, D, R¹, R⁴, R⁷ and R⁸, can be defined according to any embodiments as described herein;

A is a 5 or 6 membered heterocyclic ring containing a donor atom D and a ring atom A¹, wherein the dashed circle in ring A indicates one or more optional (unsaturated) double bonds;

A¹ is selected from C, N and CR⁷; and

A², A³ and A⁴, are each independently selected from O, S, N, CR⁷, C(R⁷)₂ and NR⁸.

[0120] Each R^7 can be independently selected from hydrogen, halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , optionally substituted C_{1-20} alkyl, optionally substituted C_{2-20} alkenyl, optionally substituted C_{2-20} alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally two R^7 substituents can be joined together to form an optionally substituted 3 to 7 membered carbocyclic or heterocyclic ring. In an embodiment, each R^7 can be independently selected from hydrogen, halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , C_{1-10} alkyl, C_{2-10} alkenyl, C_{2-10} alkynyl, C_{1-10} alkylhalo, C_{2-10} alkenylhalo and C_{2-10} alkynylhalo. In a further embodiment, each R^7 can be independently selected from optionally substituted C_{1-6} alkyl groups, for example methyl or bromoethyl. R^2 and R^3 can be defined as described herein, including embodiments thereof.


[0121] Each R^8 can be independently selected from hydrogen, C_{1-20} alkyl, C_{2-20} alkenyl, C_{2-20} alkynyl, a 5 or 6 membered aryl or heteroaryl, and optionally two R^8 substituents can be joined together to form an optionally substituted 3 to 7 membered carbocyclic or heterocyclic ring, each of which can be optionally substituted with one or more substituents independently selected from halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , aryl and heteroaryl. In one embodiment, each R^8 can be independently selected from hydrogen, optionally substituted C_{1-20} alkyl and optionally substituted 5 or 6 membered aryl or heteroaryl. In another embodiment, each R^8 can be independently selected from hydrogen and optionally substituted C_{1-10} alkyl. R^2 and R^3 can be defined as described herein, including embodiments thereof.


[0122] In another embodiment, A^2 , A^3 and A^4 , are each independently selected from C, O, S, N, C-H, C-halo, C- C_{1-10} alkyl, C- C_{1-10} haloalkyl, C- C_{1-10} alkoxy and C- C_{1-10} alkoxyhalo, N-H, N- C_{1-10} alkyl, N- C_{1-10} haloalkyl. In another embodiment, A^2 , A^3 and A^4 , are each independently selected from O, S, N, C-H, C-halo, C- C_{1-10} alkyl, C- C_{1-10} haloalkyl, C- C_{1-10} alkoxy, C- C_{1-10} alkoxyhalo. In another embodiment, A^2 , A^3 and A^4 , are C-H.

[0123] In a further embodiment, for compounds of Formula 1a as described above, at least two of A^1 , A^2 , A^3 and A^4 , are each independently selected from C and CR^7 . In another embodiment, at least three of A^1 , A^2 , A^3 and A^4 , are each independently selected from C and CR^7 . In another embodiment, A^1 , A^2 , A^3 and A^4 , are each independently selected from C and CR^7 . R^7 can be defined according to any embodiments described herein.

[0124] In a further embodiment, for compounds of Formula 1b as described above, at least one of A^1 , A^2 and A^3 , is selected from C and CR^7 . In another embodiment, at least two of A^1 , A^2 and A^3 , are each independently selected from C and CR^7 . In another embodiment, A^1 , A^2 and A^3 , are each independently selected from C and CR^7 . R^7 can be defined according to any embodiments described herein.


[0125] Specific examples of the A ring according to compounds of Formula 1a, wherein the donor atom D is N and A^1 is C, are provided as follows:





wherein T, R¹, R⁴, R⁷ and R⁸, can be defined as described herein, including any embodiments thereof as described herein.

[0126] Specific examples of the A ring according to compounds of Formula 1 b, wherein the donor atom D is N and A¹ is C, are provided as follows:



wherein T, R¹, R⁴, R⁷ and R⁸, can be defined as described herein, including any embodiments thereof as described herein.


[0127] R⁷ can be selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl. In an embodiment, each R⁷ can be independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², C₁₋₁₀alkyl, C₂₋₁₀alkenyl, C₂₋₁₀alkynyl, C₁₋₁₀alkylhalo, C₂₋₁₀alkenylhalo and C₂₋₁₀alkynylhalo. In a further embodiment, each R⁷ can be independently selected from optionally substituted C₁₋₄alkyl groups, for example methyl or bromoethyl. R² and R³ can be defined as described herein, including embodiments thereof.

[0128] R⁸ can be selected from hydrogen, C₁₋₂₀alkyl, C₂₋₂₀alkenyl, C₂₋₂₀alkynyl, and a 5 or 6 membered aryl or heteroaryl, each of which can be optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryl and heteroaryl. In one embodiment, each R⁸ can be independently selected from hydrogen and C₁₋₁₀alkyl. R² and R³ can be defined as described herein, including embodiments thereof.

[0129] The compounds described herein may include salts, solvates, hydrates, isomers, tautomers, racemates, stereoisomers, enantiomers or diastereoisomers of those compounds.

DIAZABOROLE COMPOUNDS

[0130] The present disclosure also relates to diazaborole compounds of Formula 2 as described below:



Formula 2


wherein R^1 , R^4 , T, A, A^1 and D, are as described herein and R^{10} is selected from hydrogen or halo.

[0131] The diazaborole compounds may be prepared from the phenylenediamine precursor compounds of Formula 1 as described herein. Reactions may comprise reacting the phenylenediamine precursor compounds with boron agents, such as boron tribromide, in a solvent system, such as ether. It will be appreciated that once the phenylenediamine precursor compounds of Formula 1 are prepared, then methods of preparing boron compounds according to Formula 2 using the precursor compounds would be readily known to a person skilled in the field.

[0132] It will be appreciated that any of the embodiments described herein for groups R^1 , R^4 , T, A, A^1 and D, in relation to Formula 1 may also apply compounds of Formula 3.

DIAZABOROLE METAL COMPLEXES

[0133] The present disclosure also relates to a metal complex of Formula 3 as described below:



Formula 3

wherein

M is a metal atom selected from Ir, Pt, Rh, Pd, Ru and Os;

n is an integer selected from 1, 2 and 3;

m is an integer selected from 0, 1, 2, 3, 4, and 5;

L is a monodentate or bidentate ligand; and

R^1 , R^4 , T, A, A^1 and D, are as described herein.

[0134] It will be appreciated that any of the embodiments described herein for groups R^1 , R^4 , T, A and D, in relation

to Formula 1 may also apply to metal complexes of Formula 3.

[0135] The metal complexes described herein may include salts, solvates, hydrates, isomers, tautomers, racemates, stereoisomers, enantiomers or diastereoisomers of those complexes. The transition metal M may also have different coordination and/or oxidation states. The coordination number of a metal complex refers to the number of ligands (i.e. donor atoms) attached to the metal. A metal may be coordinated to one or more ligands by interactions of the metal's d orbital with the s or p orbitals of the ligand(s). For example, typical oxidation states for Pt are +2 and +4, and Pt is typically coordinated to 4 or 6 ligands depending on the type of ligands. The geometries of metal complexes may also vary, for example Pt is typically square planar when coordinated to 4 ligands and octahedral when coordinated to 6 ligands, although the geometries will depend on the type of metal and coordinated ligands. Common oxidation states for Ir are +3 and +4, and Ir is typically hexacoordinate.

[0136] Integer ranges for "n" and "m" can be selected so that the coordination number on the metal M in total corresponds, depending on the metal, to the usual coordination number for this metal. As mentioned above, it is generally known that metal coordination compounds have different coordination numbers depending on the metal and on the oxidation state of the metal, i.e. bond a different number of ligands. Since the preferred coordination numbers of metals and metal ions in various oxidation states are part of the general knowledge of the person skilled in the art in the area of organometallic chemistry or coordination chemistry, it is straightforward for the person skilled in the art to use a suitable type and number of ligands L, depending on the metal and its oxidation state, and in view of diamine compound of Formula 1 and 2 providing at least a bidentate ligand in itself, and thus to make a suitable choice of n and m.

[0137] For example, it will be appreciated that the phenylenediamine compounds of Formula 1 provide at least one bidentate ligand (two donor atoms as ligands) to the metal M. Consequently, where n is 1 and the coordination number of the metal is 6, then an additional 4 donor atoms to M are required by (L)m, which can be provided by 4 monodentate ligands, or 2 bidentate ligands, or a combination thereof.

[0138] In one embodiment, M is a metal atom selected from Ir and Pt. In a particular embodiment, M is Ir.

[0139] The metal complex may be homoleptic, for example containing the same ligands where m is 0, L is absent and n is an integer selected from 1, 2, and 3. In one embodiment, M is Pt, n is 2, m is 0 and L is absent. In another embodiment, M is Ir, n is 3, m is 0 and L is absent.

[0140] The metal complex may be heteroleptic, for example containing at least one ligand L. In one embodiment, M is Ir, n is 2, and m is an integer selected from 1 and 2, wherein m and L are selected to provide 2 donor atoms as ligands to M. It will be appreciated that the 2 donor atoms from L may be provided by L being 2 monodentate ligands, such as Cl, or by L being a single bidentate ligand, such as ethylenediamine.

Additional Ligands

[0141] The ligand L may be a neutral or monoanionic, monodentate or bidentate ligand.

[0142] A neutral, monodentate ligand L may be independently selected from carbon monoxide, NO, isonitriles, such as, for example, tert-butyl isonitrile, cyclohexyl isonitrile, adamantyl isonitrile, phenyl isonitrile, mesityl isonitrile, 2,6-dimethylphenyl isonitrile, 2,6-diisopropylphenyl isonitrile, 2,6-di-tert-butylphenyl isonitrile, amines, such as, for example, trimethylamine, triethylamine, morpholine, phosphines, such as, for example, trifluorophosphine, trimethylphosphine, tricyclohexylphosphine, tri-tert-butylphosphine, triphenylphosphine, tris(pentafluorophenyl)phosphine, phosphites, such as, for example, trimethyl phosphite, triethyl phosphite, arsines, such as, for example, trifluoroarsine, trimethylarsine, tricyclohexylarsine, tri-tert-butylarsine, triphenylarsine, tris(pentafluorophenyl)arsine, stibines, such as, for example, trifluorostibine, trimethylstibine, tricyclohexylstibine, tri-tert-butylstibine, triphenylstibine, tris(pentafluorophenyl)stibine, and nitrogen-containing heterocycles, such as, for example, pyridine, pyridazine, pyrazine, pyrimidine, triazine.

[0143] A monoanionic, monodentate ligand L may be independently selected from hydride, deuteride, the halides F, Cl, Br and I, alkylacetylides, such as, for example, methyl-C $\equiv$ C-, tert-butyl-C $\equiv$ C-, aryl- and heteroarylacetylides, such as, for example, phenyl-C $\equiv$ C-, cyanide, cyanate, isocyanate, thiocyanate, isothiocyanate, aliphatic or aromatic alcohols, such as, for example, methanolate, ethanolate, propanolate, isopropanolate, tert-butyrate, phenolate, aliphatic or aromatic thioalcohols, such as, for example, methanethiolate, ethanethiolate, propanethiolate, isopropanethiolate, tert-butanethiolate, thiophenolate, amides, such as, for example, dimethylamide, diethylamide, diisopropylamide, morpholide, carboxylates, such as, for example, acetate, trifluoroacetate, propionate, benzoate, and anionic, nitrogen-containing heterocycles, such as pyrrolide, imidazolidine, pyrazolidine. The alkyl groups in these groups may be C₁₋₂₀alkyl groups, C₁₋₁₀alkyl groups, or C₁₋₄alkyl groups. These groups and the aryl and heteroaryl groups are as defined above.

[0144] Di- or trianionic, monodentate ligand L may be independently selected from O₂²⁻, S₂²⁻, nitrenes, which result in coordination in the form R-N=M, where R generally stands for a substituent, or N₃⁻.

[0145] A neutral or mono- or dianionic, bidentate ligand L may be independently selected from diamines, such as, for example, ethylenediamine, N,N,N',N'-tetramethylethylenediamine, propylenediamine, N,N,N',N'-tetramethylpropylenediamine, cis- or trans-diaminocyclohexane, cis- or trans-N,N,N',N'-tetramethyldiaminocyclohexane, imines, such as, for example, 2-[1-(phenylimino)ethyl]pyridine, 2-[1-(2-methylphenylimino)ethyl]pyridine, 2-[1-(2,6-diisopropylphenylimino)

no)ethyl]pyridine, 2-[1-(methylimino)ethyl]-pyridine, 2-[1-(ethylimino)ethyl]pyridine, 2-[1-(isopropylimino)ethyl]pyridine, 2-[1-(tert-butylimino)ethyl]pyridine, diimines, such as, for example, 1,2-bis-(methylimino)ethane, 1,2-bis(ethylimino)ethane, 1,2-bis(isopropylimino)ethane, 1,2-bis(tert-butylimino)ethane, 2,3-bis(methylimino)butane, 2,3-bis-(ethylimino)butane, 2,3-bis(isopropylimino)butane, 2,3-bis(tert-butylimino)butane, 1,2-bis(phenylimino)ethane, 1,2-bis(2-methylphenylimino)ethane, 1,2-bis(2,6-diisopropylphenylimino)ethane, 1,2-bis(2,6-di-tert-butylphenylimino)ethane, 2,3-bis(phenylimino)butane, 2,3-bis(2-methylphenylimino)butane, 2,3-bis(2,6-diisopropylphenylimino)butane, 2,3-bis(2,6-di-tert-butylphenylimino)butane, heterocycles containing two nitrogen atoms, such as, for example, 2,2'-bipyridine, o-phenanthroline, diphosphines, such as, for example, bis(diphenylphosphino)methane, bis(diphenylphosphino)ethane, bis(diphenylphosphino)propane, bis(dimethylphosphino)methane, bis(dimethylphosphino)ethane, bis(dimethylphosphino)propane, bis(diethylphosphino)methane, bis(diethylphosphino)ethane, bis(diethylphosphino)propane, bis(di-tert-butylphosphino)methane, bis(di-tert-butylphosphino)ethane, bis(tert-butylphosphino)propane, 1,3-diketones derived from 1,3-diketones, such as, for example, acetylacetone, benzoylacetone, 1,5-diphenylacetylacetone, dibenzoylmethane, bis(1,1,1-trifluoroacetyl)methane, 3-ketonates derived from 3-ketoesters, such as, for example, ethyl acetoacetate, carboxylates derived from aminocarboxylic acids, such as, for example, pyridine-2-carboxylic acid, quinoline-2-carboxylic acid, glycine, N,N-dimethylglycine, alanine, N,N-dimethylaminoalanine, salicyliminates derived from salicylimines, such as, for example, methylsalicylimine, ethylsalicylimine, phenylsalicylimine, dialcoholates derived from dialcohols, such as, for example, ethylene glycol, 1,3-propylene glycol, and dithiolates derived from dithiols, such as, for example, 1,2-ethylenedithiol, 1,3-propylenedithiol.

[0146] A bidentate monoanionic ligand L may be selected which, with the metal, form a cyclometallated five-membered ring having at least one metal-carbon bond. These are, in particular, ligands as are generally used in the area of phosphorescent metal complexes for organic electroluminescent devices, i.e. ligands of the phenylpyridine, naphthylpyridine, phenylquinoline, phenylisoquinoline, etc., type, each of which may be substituted by one or more radicals.

EMISSION MATERIALS & ELECTRONIC DEVICES

[0147] The metal complexes of Formula 3, as described herein including embodiments thereof as described herein, can be used as an active component in an electronic device.

[0148] Electronic devices may be selected from the group consisting of organic electroluminescent devices (OLEDs), organic field-effect transistors (O-FETs), organic thin-film transistors (O-TFTs), organic light-emitting transistors (O-LETs), organic integrated circuits (O-ICs), organic solar cells (O-SCs), organic field-quench devices (O-FQDs), light-emitting electrochemical cells (LECs), organic photoreceptors and organic laser diodes (O-lasers). In one embodiment, the electronic device is an organic electroluminescent device.

[0149] Active components are generally the organic, organometallic or inorganic materials introduced between the anode and cathode, for example charge-injection, charge-transport or charge-blocking materials, but in particular emission materials and matrix materials. The metal complexes of Formula 3, as described herein including embodiments thereof as described herein, can exhibit particularly good properties for these functions, in particular as an emission material in organic electroluminescent devices, as described in further detail below. Organic electroluminescent devices are therefore a particular embodiment of the invention.

[0150] The organic electroluminescent device can comprise a cathode, an anode and at least one emitting layer (which may also be referred to as an emissive layer). The metal complexes of Formula 3, can be provided as an emitting compound in the emitting layer. The metal complexes of Formula 3, may also be provided as a matrix material for an emitting compound in the emitting layer.

[0151] The organic electronic device may comprise further layers, selected from in each case one or more hole-injection layers, hole-transport layers, hole-blocking layers, electron-transport layers, electron-injection layers, electron-blocking layers, exciton-blocking layers, charge-generation layers and/or organic or inorganic p/n junctions.

[0152] Optional interlayers may be added to provide, for example, an exciton-blocking function, to be introduced between two emitting layers or also between other layers. The OLED may comprise one or more emitting layers, where at least one emitting layer comprises at least one metal complex of Formula 3. If a plurality of emission layers are present, these can have in total a plurality of emission maxima between 380 nm and 750 nm, resulting overall in white emission, i.e. various emitting compounds which are able to fluoresce or phosphoresce are used in the emitting layers. There may be provided a three-layer system, where the three layers exhibit blue, green and orange or red emission, for example in accordance with WO05/011013.

[0153] In one embodiment, the electronic device comprises at least one metal complex of Formula 3, as an emitting compound in an emitting layer. Each of the one or more layers in the device may comprise one or more matrix materials. The mixture of the metal complexes of the Formula 3, and the matrix material may comprise between 1 and 99% by vol., between 2 and 90% by vol., between 3 and 40% by vol., or between 5 and 15% by vol., of the metal complex, based on the mixture as a whole comprising emitter and matrix material. Correspondingly, the mixture may comprise between 99 and 1% by vol., between 98 and 10% by vol., between 97 and 60% by vol., or between 95 and 85% by vol., of the

matrix material, based on the mixture as a whole comprising emitter and matrix material.

[0154] Suitable matrix materials may include ketones, phosphine oxides, sulfoxides and sulfones, for example in accordance with WO04/013080, WO04/093207 or WO06/005627, triaryl amines, carbazole derivatives, for example CBP (N,N-bis(carbazolyl)biphenyl), mCBP or the carbazole derivatives disclosed in WO05/039246, US2005/0069729, JP2004/288381, EP1205527 or WO08/086851, indolocarbazole derivatives, for example in accordance with WO07/063754 or WO08/056746, azacarbazoles, for example in accordance with EP1617710, EP1617711, EP1731584, JP2005/347160, bipolar matrix materials, for example in accordance with WO07/137725, silanes, for example in accordance with WO 05/111172, azaboroles or boronic esters, for example in accordance with WO06/117052, triazine derivatives, for example in accordance with WO07/063754 or WO08/056746, or zinc complexes, for example in accordance with EP652273 or WO09/062578. The metal complexes of Formula 3, may also be suitable as matrix materials. In general, all matrix materials as employed in accordance with the prior art for phosphorescent emitters in organic electroluminescent devices can also be employed for the compounds according to the invention. Mixtures of these matrix materials may also be used.

[0155] The electroluminescent device may comprise a separate hole-transport layer or comprise a metal complex, which is identical or similar to the complex employed in the emitting layer, as hole-transport material in the hole-transport layer.

[0156] The metal complexes of Formula 3, including embodiments as described herein, may be employed as a matrix material for an emitting compound in an emitting layer.

[0157] The electroluminescent device may comprise a matrix material and at least two phosphorescent emitters in the emitting layer, where at least one of the two phosphorescent emitters is a metal complex of Formula 3. The phosphorescent emitter which emits at shorter wavelength serves here as matrix for the phosphorescent emitter which emits at longer wavelength. The metal complex of Formula 3, may be the compound emitting at shorter wavelength or the compound emitting at longer wavelength. Likewise, both phosphorescent compounds can be a metal complex of Formula 3.

[0158] If the metal complexes of Formula 3 are employed as matrix material for an emitting compound in an emitting layer, they can be provided in combination with one or more phosphorescent materials (triplet emitters) or fluorescent materials (singlet emitters). For the purposes of the present disclosure, phosphorescence is taken to mean the luminescence from an excited state of relatively high spin multiplicity, i.e. a spin state >1 , in particular from an excited triplet state or from an MLCT mixed state. For the purposes of the present disclosure, all luminescent transition-metal complexes, in particular all luminescent iridium and platinum complexes, are regarded as phosphorescent materials. The mixture of the metal complexes of Formula 3, as described herein, and the emitting compound can comprise between 99 and 1% by vol., 98 and 10% by vol., between 97 and 60% by vol., or between 95 and 85% by vol., of the metal complex, based on the mixture as a whole comprising emitter and matrix material. Correspondingly, the mixture comprises between 1 and 99% by vol., between 2 and 90% by vol., between 3 and 40% by vol., between 5 and 15% by vol., of the emitter, based on the mixture as a whole comprising emitter and matrix material. A metal complex of Formula 3, may be used in combination with another compound or complex as the matrix material.

[0159] The phosphorescence emitters used may be selected from compounds which contain copper, molybdenum, tungsten, rhenium, ruthenium, osmium, rhodium, iridium, palladium, platinum, silver, gold or europium, in particular compounds which contain iridium or platinum. Examples of the emitters described above are described in WO00/70655, WO01/41512, WO02/02714, WO02/15645, EP1191613, EP1191612, EP1191614, WO05/033244 or WO09/118087.


[0160] The metal complexes of Formula 3, as described herein, may be used as hole-blocking materials in a hole-blocking layer and/or as electron-transport material in an electron-transport layer. The emitting layer may be fluorescent or phosphorescent.

[0161] Each of the one or more layers in the organic electroluminescent device may be prepared by a sublimation process or by organic vapour phase deposition process, such as organic vapour jet printing (see M. S. Arnold et al., Appl. Phys. Lett. 2008, 92, 053301). Each of the one or more layers in the organic electroluminescent device may be produced from solution, such as, for example, by spin coating, or by means of any desired printing process, such as, for example, screen printing, flexographic printing, offset printing, LITI (light induced thermal imaging, thermal transfer printing), ink-jet printing or nozzle printing. Hybrid processes, in which one or more layers are applied from solution and one or more other layers are applied by vapour deposition, are also possible.

[0162] In some embodiments, the metal complexes of Formula 3, as described herein, may be used in combination with one or more of a hole injection material, a hole transporting compound (or material), an electron transporting compound and/or an additional emission compound, examples of which may include the following:


Exemplary hole transporting materials/compounds include:

5




10

15



20


25



30

35







40











45

50


55




Exemplary electron transporting materials/compounds include:




5



10




15



20

25




30

35




40



45

50



55

[0163] The anode is typically selected from a material having a large work function, examples of which may include

metals, such as gold, platinum, nickel, palladium, cobalt, selenium, vanadium and their alloys; metal oxides, such as tin oxide, zinc oxide, indium zinc oxide (IZO) and indium tin oxide (ITO) and electroconductive polymers, such as PE-DOT:PSS, polyaniline, polypyrrole and polythiophene and derivatives thereof. These compounds may be used singly or in combination of two or more species. A substrate for the anode of the organic electroluminescence device may be provided and selected from an opaque substrate made from any suitable material, such as metal or ceramics, or a transparent substrate made from any suitable transparent material such as glass, quartz, plastics.

[0164] The cathode is typically selected from a material having a smaller work function, usually under 4.0 eV, examples of which may include; metals such as sodium, magnesium, calcium, lithium, potassium, aluminium, indium, silver, lead, chromium and their alloys, or oxides.

[0165] A charge blocking layer may be deposited adjacent to either electrode to avoid current leakage. The charge blocking material may be an inorganic compound, examples of which may include aluminium oxide, lithium fluoride, lithium oxide, caesium oxide, magnesium oxide, magnesium fluoride, calcium oxide, calcium fluoride, aluminium nitride, titanium oxide, silicon oxide, silicon nitride, boron nitride, vanadium oxide.

[0166] The one or more organic layers in the electronic device may be constituted by:

a single layer doped with a phosphorescent material of the present application;
multiple layers of which at least one layer may be doped with a phosphorescent material of the present application; or
multiple layers of which at least one layer may be comprised entirely of a phosphorescent material of the present application.

[0167] Further examples of the device structure may be provided as follows:

anode/emissive layer/cathode;
anode/electron transport layer/cathode;
anode/hole transporting layer/emissive layer/electron transporting layer/cathode;
anode/hole injection layer/hole transporting layer/emissive layer/electron transporting layer/cathode;
anode/hole transporting layer/emission layer/electron transporting layer/electron injection layer/cathode;
anode/hole injection layer/emission layer/electron transporting layer/electron injection layer /cathode;
anode/charge blocking layer/hole transporting layer/emission layer/ electron transporting layer/cathode;
anode/hole transporting layer/emission layer/electron transporting layer/ charge blocking layer/cathode;
anode/inorganic semiconductor/ charge blocking layer/hole transporting layer/emission layer/ charge blocking layer/cathode;
anode/ charge blocking layer/hole transporting layer/emission layer/electron transporting layer/ charge blocking layer/cathode;
anode/ charge blocking layer/hole injection layer/hole transporting layer/emission layer/electron transporting layer/electron injection layer/cathode; or
anode/ charge blocking layer/hole injection layer/hole transporting layer/emission layer/electron transporting layer/electron injection layer/ charge blocking layer/cathode.

SYNTHESIS OF COMPOUNDS AND METAL COMPLEXES

[0168] The compounds and complexes of Formula 1-3 can be prepared by various processes, but where the processes described below have proven particularly suitable.

[0169] It will be appreciated that the phenylenediamine compounds of Formula 1 can be precursor compounds for the diazaborole compounds of Formula 2, respectively, and for the metal complexes of Formula 3.

[0170] A general process for preparing the phenylenediamine compounds of Formula 1 may comprise:

reacting an optionally substituted benzimidazole compound with an optionally substituted monocyclic or bicyclic 5 or 6 membered heterocyclic ring comprising a donor atom D selected from N, O, S, P, Se and Te, to form an N-substituted benzimidazole compound; and
reacting the N-substituted benzimidazole compound with a reducing agent to form a phenylenediamine compound of Formula 1, as described herein.

[0171] An example of a suitable reducing agent is a bulky (i.e. sterically hindered) reducing agent such as DIBAL-H. Other suitable reducing agents will be well known to persons skilled in the field, such as LiAlH_4 .

[0172] The metal complexes of Formula 3, as described herein, may be prepared by the following general process:

reacting a phenylenediamine compound of Formula 1 with a boron agent to obtain a diazaborole compound of


Formula 2, as described herein;


reacting the diazaborole compound of Formula 2 with a precursor complex of the metal M having substitutable ligands in a ratio suitable to obtain a product being a metal complex of Formula 3 having the desired number n of phenylenediamine compounds of Formula 1, and optionally ligands L, being co-ordinated to the metal M; and optionally further reacting the product with another ligand L in a ratio suitable to introduce the desired number of ligands L into the metal complex of Formula 3.

[0173] An example of a suitable boron agent is BBr_3 . Other suitable boron agents will be well known to persons skilled in the field.

[0174] An example of a suitable precursor complex metal M is trispyridinoiridium trichloride. Other suitable iridium precursors will be well known to persons skilled in the field.

[0175] An example of a general scheme for preparing a metal complex of Formula 5 via a diamine compound of Formula 1 is provided as follows:





wherein R^1 , R^4 , T, A, A^1 and D can be defined as described herein, wherein T^* is a precursor for T.

[0176] A suitable example of T^* is 2-propene. T^* may be a tertiary alcohol, an acid chloride or any group that can undergo a Friedel-Crafts alkylation.

[0177] It will be appreciated that a process for preparing the phenylenediamine compounds of Formula 1, as described herein, may comprise steps 1 to 3, steps 2 and 3, or step 3 above.

[0178] The process for preparing the diazaborole compounds of Formula 2 may comprise steps 1 to 4, steps 2 to 4, steps 3 and 4, or step 4 above.

[0179] The process for preparing the metal complexes of Formula 3 may comprise steps 1 to 5, steps 2 to 5, steps 3 to 5, steps 4 and 5, or step 5 above.

Step 1 may comprise a substitution reaction of a benzimidazole and a leaving group LG of the A ring. Suitable reagents may include potassium carbonate. A suitable leaving group may include a halogen atom.

Step 2 may comprise a reduction reaction to a diamine compound comprising a reducing agent. Suitable reducing agents may include sterically hindered reducing agents such as diisobutylaluminum hydride (DIBAL-H). Suitable solvents may include tetrahydrofuran (THF) at reflux.

Step 3 may comprise tethering the T group to the benzimidazole for preparing the diamine compounds of Formula 1. Suitable reagents may include phosphoric acid/acetic acid at elevated temperatures (e.g. 120 °C).

Step 4 may comprise a reaction with a boron agent to prepare the diazaborole compounds of Formula 2. A suitable boron agent may include boron tribromide (BBR_3). Suitable solvent include ether at reflux.


Step 5 may comprise a reaction with a metal precursor to form the metal complexes of Formula 3. A suitable metal precursor may be trispyridinoiridium.


[0180] In various embodiments, there are provided processes for preparing compounds and complexes of Formula 1, Formula 2 and Formula 3, which may comprise any one or more of the general steps described in the above general scheme.

EXAMPLES


[0181] The invention is further illustrated by the following examples. The examples are provided for illustrative purposes only. They are not to be construed as limiting the scope or content of the invention in any way.

Scheme 1: Proposed synthesis of metal complex via phenylenediamine compound of Formula 1




Example 1: Synthesis of diamine compound of Formula 1*Synthesis of 2-fluoro-3-(prop-1-en-2-yl)pyridine***[0182]**

[0183] Phosphoric acid (40ml, 85% with water) and acetic acid (3ml) was added to 2-(2-fluoropyridin-3-yl)propan-2-ol (5g, 32mmol) and the mixture heated to 120°C for 12 hours. The mixture was cooled to 0°C in an ice bath and water (100ml) and neutralised with Na_2CO_3 to about pH 7. The aqueous reaction mixture was extracted with dichloromethane, and the organic phase dried (MgSO_4) and the solvent removed. The crude product was chromatographed on silica using dichloromethane to yield the product. $^1\text{H-NMR}$ (CDCl_3 , 400 MHz): 8.04 (m, 1H), 7.67 (m, 1H), 7.10 (m, 1H), 5.28 (m, 1H), 5.25 (m, 1H), 2.09 (m, 3H).

*Synthesis of 1-(3-(prop-1-en-2-yl)pyridin-2-yl)-1H-benzo[d]imidazole***[0184]**

[0185] Benzimidazole (2g, 17mmol), 2-fluoro-3-(prop-1-en-2-yl)pyridine (2.5g, 18mmol) K_3PO_4 (4.2g, 20mmol) and DMF (20ml) was heated under nitrogen at 140°C for 48 hours. The reaction mixture was cooled and water (50ml) added and the mixture allowed to stand overnight. The mixture was filtered and the solid purified on a silica column using dichloromethane with 5% ethyl acetate as eluent to yield the product. $^1\text{H-NMR}$ (CDCl_3 , 400 MHz): 8.53 (d, d, 1H), 8.17 (s, 1H), 7.82 (m, 1H), 7.78 (dd, 1H), 7.61 (m, 1H), 7.33 (dd, 1H), 7.29 (m, 2H), 5.19 (m, 1H), 5.14 (m, 1H), 1.56 (m, 3H).


*Synthesis of N1-methyl-N2-(3-(prop-1-en-2-yl)pyridin-2-yl)benzene-1,2-diamine***[0186]**

[0187] 1M Di-isobobutylaluminium hydride in tetrahydrofuran (87ml, 87mmol) was added to N1-methyl-N2-(3-(prop-1-en-2-yl)pyridin-2-yl)benzene-1,2-diamine (3.4g, 14.4mmol). The mixture was heated at 65°C for 16 hours then cooled in an ice bath. NaF (15.1g) was added portion wise over about 30 minutes then water (4.4ml) added drop wise with continuous cooling and stirring. The reaction mixture was filtered and the solid extracted with copious amounts of dichloromethane with 10% methanol and the filtrate collected and the solvent removed to leave a crude product. This

crude product was purified on silica using dichloromethane with 2% methanol as eluent to yield the product. $^1\text{H-NMR}$ (CDCl_3 , 400 MHz): 8.07 (dd, 1H), 7.32 (dd, 1H), 7.27 (m, 1H), 7.14 (m, 1H), 6.76 (m, 2H), 6.68 (dd, 1H), 6.26 (bs, 1H), 5.40 (m, 1H), 5.24 (m, 1H), 4.13 (bs, 1H), 2.86 (m, 3H), 2.12 (bm, 3H).

Synthesis of N,5,5-trimethyl-5,10-dihydrobenzo[b][1,8]naphthyridin-9-amine


[0188]



[0189] Phosphoric acid (15ml, 85% with water) and acetic acid (1ml) was added to N1-methyl-N2-(3-(prop-1-en-2-yl)pyridin-2-yl)benzene-1,2-diamine (1.2g, 5mmol) and the mixture heated to 120°C for 20 hours. The mixture was cooled to 0°C in an ice bath and water (30ml) added and the aqueous solution neutralised with Na_2CO_3 to about pH 7. The aqueous reaction mixture was extracted with dichloromethane, and the organic phase dried (MgSO_4) and the solvent removed. The resulting crude product was purified on silica using dichloromethane with 0.5% methanol to yield the product. $^1\text{H-NMR}$ (CDCl_3 , 400 MHz): 8.08 (dd, 1H), 7.88 (bs, 1H), 7.72 (dd, 1H), 7.14 (m, 1H), 6.94 (m, 2H), 6.85 (dd, 1H), 6.67 (dd, 1H), 3.36 (bs, 1H), 2.81 (2,3H), 1.59 (s, 6H).

Claims

1. A compound of Formula 1:



Formula 1

wherein

R^1 is selected from C_{1-20} alkyl, C_{2-20} alkenyl, C_{2-20} alkynyl, and a 5 or 6 membered aryl or heteroaryl, each of which is optionally substituted with one or more substituents independently selected from halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , aryl and heteroaryl;

R^2 and R^3 are each independently selected from hydrogen and C_{1-6} alkyl;

Each R^4 is independently selected from hydrogen, halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , optionally substituted C_{1-20} alkyl, optionally substituted C_{2-20} alkenyl, optionally substituted C_{2-20} alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally two R^4 substituents from adjacent ring atoms are joined together to form an optionally substituted 5 or 6 membered aryl or heteroaryl ring; wherein R^2 and R^3 are each independently defined as above;

T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from C, N, O, S, Si and

B, each of which is optionally substituted with one or more substituents independently selected from hydrogen, halo, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₁₀alkyl, optionally substituted C₂₋₁₀alkenyl, optionally substituted C₂₋₁₀alkynyl and optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally fused with a 3-6 membered carbocycle or heterocycle; and wherein R² and R³ are each independently defined as above,

A is a monocyclic or bicyclic heterocyclic ring comprising a 5 or 6 membered ring, containing a donor atom D and a ring atom A¹, and optionally having 1 or 2 additional ring heteroatoms selected from O, S and N, wherein the heterocyclic ring is optionally substituted with 1 to 3 substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, and optionally substituted 5 or 6 membered aryl or heteroaryl; wherein R² and R³ are each independently defined as above;

A¹ is selected from C, N and CR⁷; wherein R⁷ is selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl; R² and R³ are each independently defined as above; and

D is a donor atom selected from N, O, S, P, Se and Te.

2. The compound of claim 1, wherein R¹ is selected from optionally substituted C₁₋₁₀alkyl and optionally substituted monocyclic 5 or 6 membered aryl or heteroaryl.

3. The compound of claim 1 or claim 2, wherein T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)-, -S(=O)₂-, C₁₋₃alkyl and C₂₋₃alkenyl; wherein the C₁₋₃alkyl and C₂₋₃alkenyl are each optionally interrupted by a group selected from -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)- and S(=O)₂, and optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², C₁₋₁₀alkyl, C₂₋₁₀alkenyl, C₂₋₁₀alkynyl, C₁₋₁₀alkylhalo, C₂₋₁₀alkenylhalo and C₂₋₁₀alkynylhalo, and optionally fused with a 3-6 membered carbocycle or heterocycle. R⁶ can be selected from hydrogen and C₁₋₁₀alkyl.


4. The compound of any one of the preceding claims, wherein T is an optionally substituted, optionally fused C₁₋₃alkyl.

5. The compound of any one of the preceding claims, wherein D is selected from N.

6. The compound of any one of the preceding claims, wherein A is an optionally substituted pyridine group.

7. The compound of any one of the preceding claims, wherein each R⁴ is hydrogen.

8. A compound of Formula 2:



Formula 2

wherein

R¹ is selected from C₁₋₂₀alkyl, C₂₋₂₀alkenyl, C₂₋₂₀alkynyl, and a 5 or 6 membered aryl or heteroaryl, each of which is optionally substituted with one or more substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryl and heteroaryl;

R² and R³ are each independently selected from hydrogen and C₁₋₆alkyl;

Each R^4 is independently selected from hydrogen, halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , optionally substituted $\text{C}_{1-20}\text{alkyl}$, optionally substituted $\text{C}_{2-20}\text{alkenyl}$, optionally substituted $\text{C}_{2-20}\text{alkynyl}$, optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally two R^4 substituents from adjacent ring atoms are joined together to form an optionally substituted 5 or 6 membered aryl or heteroaryl ring; wherein R^2 and R^3 are each independently defined as above;

T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from C, N, O, S, Si and B, each of which is optionally substituted with one or more substituents independently selected from hydrogen, halo, CN, NO_2 , $=\text{O}$, $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , optionally substituted $\text{C}_{1-10}\text{alkyl}$, optionally substituted $\text{C}_{2-10}\text{alkenyl}$, optionally substituted $\text{C}_{2-10}\text{alkynyl}$ and optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally fused with a 3-6 membered carbocycle or heterocycle; and wherein R^2 and R^3 are each independently defined as above,


A is a monocyclic or bicyclic heterocyclic ring comprising a 5 or 6 membered ring, containing a donor atom D and a ring atom A^1 , and optionally having 1 or 2 additional ring heteroatoms selected from O, S and N, wherein the heterocyclic ring is optionally substituted with 1 to 3 substituents independently selected from halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , optionally substituted $\text{C}_{1-20}\text{alkyl}$, optionally substituted $\text{C}_{2-20}\text{alkenyl}$, optionally substituted $\text{C}_{2-20}\text{alkynyl}$, and optionally substituted 5 or 6 membered aryl or heteroaryl; wherein R^2 and R^3 are each independently defined as above;

A^1 is selected from C, N and CR^7 ; wherein R^7 is selected from hydrogen, halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , optionally substituted $\text{C}_{1-20}\text{alkyl}$, optionally substituted $\text{C}_{2-20}\text{alkenyl}$, optionally substituted $\text{C}_{2-20}\text{alkynyl}$, optionally substituted 5 or 6 membered aryl or heteroaryl; R^2 and R^3 are each independently defined as above; and

D is a donor atom selected from N, O, S, P, Se and Te; and

R^{10} is selected from hydrogen or halo.

9. A metal complex of Formula 3:



Formula 3

wherein

M is a metal atom selected from Ir, Pt, Rh, Pd, Ru and Os;

n is an integer selected from 1, 2 and 3;

m is an integer selected from 0, 1, 2, 3, 4, and 5;

L is a monodentate or bidentate ligand; and

R^1 is selected from $\text{C}_{1-20}\text{alkyl}$, $\text{C}_{2-20}\text{alkenyl}$, $\text{C}_{2-20}\text{alkynyl}$, and a 5 or 6 membered aryl or heteroaryl, each of which is optionally substituted with one or more substituents independently selected from halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , aryl and heteroaryl;

R^2 and R^3 are each independently selected from hydrogen and $\text{C}_{1-6}\text{alkyl}$;

Each R^4 is independently selected from hydrogen, halo, CN, NO_2 , $\text{C}(\text{O})\text{R}^2$, OR^2 , $\text{OS}(\text{O})_2\text{R}^2$, NR^2R^3 , SR^2 , optionally substituted $\text{C}_{1-20}\text{alkyl}$, optionally substituted $\text{C}_{2-20}\text{alkenyl}$, optionally substituted $\text{C}_{2-20}\text{alkynyl}$, optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally two R^4 substituents from adjacent ring atoms are joined together to form an optionally substituted 5 or 6 membered aryl or heteroaryl ring; wherein R^2 and R^3 are each independently defined as above;

T is a tether group provided by a linear chain of 1 to 3 atoms independently selected from C, N, O, S, Si and B, each of which is optionally substituted with one or more substituents independently selected from hydrogen,

halo, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₁₀alkyl, optionally substituted C₂₋₁₀alkenyl, optionally substituted C₂₋₁₀alkynyl and optionally substituted 5 or 6 membered aryl or heteroaryl, and optionally fused with a 3-6 membered carbocycle or heterocycle; and wherein R² and R³ are each independently defined as above,

A is a monocyclic or bicyclic heterocyclic ring comprising a 5 or 6 membered ring, containing a donor atom D and a ring atom A¹, and optionally having 1 or 2 additional ring heteroatoms selected from O, S and N, wherein the heterocyclic ring is optionally substituted with 1 to 3 substituents independently selected from halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, and optionally substituted 5 or 6 membered aryl or heteroaryl; wherein R² and R³ are each independently defined as above;

A¹ is selected from C, N and CR⁷; wherein R⁷ is selected from hydrogen, halo, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², optionally substituted C₁₋₂₀alkyl, optionally substituted C₂₋₂₀alkenyl, optionally substituted C₂₋₂₀alkynyl, optionally substituted 5 or 6 membered aryl or heteroaryl; R² and R³ are each independently defined as above; and

D is a donor atom selected from N, O, S, P, Se and Te.

10. The compound of claim 9, wherein M is selected from Ir.


11. The compound of claim 9 or claim 10, wherein n is 3, m is 0 and L is absent.

12. An emission material comprising a metal complex of Formula 3 as defined in any one of claims 9 to 11.

13. An organic electroluminescent device comprising at least one pair of electrodes comprising a cathode and an anode; and at least one layer comprising the emission material as defined in claim 12 that is arranged between the at least one pair of electrodes.

Patentansprüche

1. Verbindung der Formel 1:



Formel 1

wobei

R¹ aus C₁₋₂₀-Alkyl, C₂₋₂₀-Alkenyl, C₂₋₂₀-Alkynyl und einem 5- oder 6-gliedrigen Aryl oder Heteroaryl ausgewählt ist, wobei jede dieser Gruppen gegebenenfalls durch einen oder mehrere Substituenten, die unabhängig aus Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², Aryl und Heteroaryl ausgewählt sind, substituiert ist; R² und R³ jeweils unabhängig aus Wasserstoff und C₁₋₆-Alkyl ausgewählt sind;

R⁴ jeweils unabhängig aus Wasserstoff, Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl, gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt ist und gegebenenfalls zwei R⁴-Substituenten von benachbarten Ringatomen miteinander zu einem gegebenenfalls substituierten 5- oder 6-gliedrigen Aryl- oder Heteroarylring verbunden sind; wobei R² und R³ jeweils unabhängig wie

oben definiert sind;

T für eine Ankergruppe steht, die durch eine lineare Kette von 1 bis 3 Atomen, die unabhängig aus C, N, O, S, Si und B ausgewählt sind, bereitgestellt wird, wobei jedes dieser Atome gegebenenfalls durch einen oder mehrere Substituenten, die unabhängig aus Wasserstoff, Halogen, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₁₀-Alkyl, gegebenenfalls substituiertem C₂₋₁₀-Alkenyl, gegebenenfalls substituiertem C₂₋₁₀-Alkynyl und gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt sind, substituiert und gegebenenfalls mit einem 3-6-gliedrigen Carbocyclus oder Heterocyclus anelliert ist und wobei R² und R³ jeweils unabhängig wie oben definiert sind;

A für einen monocyclischen oder bicyclischen 5- oder 6-gliedrigen heterocyclischen Ring steht, der ein Donoratom D und ein Ringatom A¹ enthält und gegebenenfalls 1 oder 2 zusätzliche Ringhetero-atome, die aus O, S und N ausgewählt sind, aufweist, wobei der heterocyclische Ring gegebenenfalls durch 1 bis 3 Substituenten, die unabhängig aus Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl und gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt sind, substituiert ist; wobei R² und R³ jeweils unabhängig wie oben definiert sind;

A¹ aus C, N und CR⁷ ausgewählt ist; wobei R⁷ aus Wasserstoff, Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl, gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt ist; R² und R³ jeweils unabhängig wie oben definiert sind; und

D für ein Donoratom, das aus N, O, S, P, Se und Te ausgewählt ist, steht.

2. Verbindung nach Anspruch 1, wobei R¹ aus gegebenenfalls substituiertem C₁₋₁₀-Alkyl und gegebenenfalls substituiertem monocyclischem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt ist.

3. Verbindung nach Anspruch 1 oder 2, wobei T für eine Ankergruppe steht, die durch eine lineare Kette von 1 bis 3 Atomen bereitgestellt wird, die unabhängig aus -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)-, -S(=O)₂-, C₁₋₃-Alkyl und C₂₋₃-Alkenyl ausgewählt ist; wobei das C₁₋₃-Alkyl und C₂₋₃-Alkenyl jeweils gegebenenfalls durch eine Gruppe, die aus -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)- und S(=O)₂ ausgewählt ist, unterbrochen und gegebenenfalls durch einen oder mehrere Substituenten, die unabhängig aus Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², C₁₋₁₀-Alkyl, C₂₋₁₀-Alkenyl, C₂₋₁₀-Alkynyl, C₁₋₁₀-Alkylhalogen, C₂₋₁₀-Alkenylhalogen und C₂₋₁₀-Alkynylhalogen ausgewählt sind, substituiert und gegebenenfalls mit einem 3-6-gliedrigen Carbocyclus oder Heterocyclus anelliert ist; wobei R⁶ aus Wasserstoff und C₁₋₁₀-Alkyl ausgewählt sein kann.


4. Verbindung nach einem der vorhergehenden Ansprüche, wobei T für ein gegebenenfalls substituiertes, gegebenenfalls anelliertes C₁₋₃-Alkyl steht.

5. Verbindung nach einem der vorhergehenden Ansprüche, wobei D aus N ausgewählt ist.

6. Verbindung nach einem der vorhergehenden Ansprüche, wobei A für eine gegebenenfalls substituierte Pyridingruppe steht.

7. Verbindung nach einem der vorhergehenden Ansprüche, wobei R⁴ jeweils für Wasserstoff steht.

8. Verbindung der Formel 2:



Formel 2

wobei

R¹ aus C₁₋₂₀-Alkyl, C₂₋₂₀-Alkenyl, C₂₋₂₀-Alkynyl und einem 5- oder 6-gliedrigen Aryl oder Heteroaryl ausgewählt ist, wobei jede dieser Gruppen gegebenenfalls durch einen oder mehrere Substituenten, die unabhängig aus Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², Aryl und Heteroaryl ausgewählt sind, substituiert ist; R² und R³ jeweils unabhängig aus Wasserstoff und C₁₋₆-Alkyl ausgewählt sind;

R⁴ jeweils unabhängig aus Wasserstoff, Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl, gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt ist und gegebenenfalls zwei R⁴-Substituenten von benachbarten Ringatomen miteinander zu einem gegebenenfalls substituierten 5- oder 6-gliedrigen Aryl- oder Heteroarylring verbunden sind; wobei R² und R³ jeweils unabhängig wie oben definiert sind;

T für eine Ankergruppe steht, die durch eine lineare Kette von 1 bis 3 Atomen, die unabhängig aus C, N, O, S, Si und B ausgewählt sind, bereitgestellt wird, wobei jedes dieser Atome gegebenenfalls durch einen oder mehrere Substituenten, die unabhängig aus Wasserstoff, Halogen, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₁₀-Alkyl, gegebenenfalls substituiertem C₂₋₁₀-Alkenyl, gegebenenfalls substituiertem C₂₋₁₀-Alkynyl und gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt sind, substituiert und gegebenenfalls mit einem 3-6-gliedrigen Carbocyclus oder Heterocyclus anelliert ist und wobei R² und R³ jeweils unabhängig wie oben definiert sind;


A für einen monocyclischen oder bicyclischen 5 oder 6-gliedrigen heterocyclischen Ring steht, der ein Donoratom D und ein Ringatom A¹ enthält und gegebenenfalls 1 oder 2 zusätzliche Ringhetero-atome, die aus O, S und N ausgewählt sind, aufweist, wobei der heterocyclische Ring gegebenenfalls durch 1 bis 3 Substituenten, die unabhängig aus Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl und gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt sind, substituiert ist; wobei R² und R³ jeweils unabhängig wie oben definiert sind;

A¹ aus C, N und CR⁷ ausgewählt ist; wobei R⁷ aus Wasserstoff, Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl, gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt ist; R² und R³ jeweils unabhängig wie oben definiert sind; und

D für ein Donoratom, das aus N, O, S, P, Se und Te ausgewählt ist, steht; und

R¹⁰ aus Wasserstoff oder Halogen ausgewählt ist.

9. Metallkomplex der Formel 3:



Formel 3

wobei

M für ein Metallatom, das aus Ir, Pt, Rh, Pd, Ru und Os ausgewählt ist, steht;

n für eine ganze Zahl, die aus 1, 2 und 3 ausgewählt ist, steht;

m für eine ganze Zahl, die aus 0, 1, 2, 3, 4 und 5 ausgewählt ist, steht;

L für einen einzähligen oder zweizähligen Liganden steht; und

R¹ aus C₁₋₂₀-Alkyl, C₂₋₂₀-Alkenyl, C₂₋₂₀-Alkynyl und einem 5- oder 6-gliedrigen Aryl oder Heteroaryl ausgewählt ist, wobei jede dieser Gruppen gegebenenfalls durch einen oder mehrere Substituenten, die unabhängig aus Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², Aryl und Heteroaryl ausgewählt sind, substituiert ist; R² und R³ jeweils unabhängig aus Wasserstoff und C₁₋₆-Alkyl ausgewählt sind;

R⁴ jeweils unabhängig aus Wasserstoff, Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl, gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt ist und gegebenenfalls zwei R⁴-Substituenten von benachbarten Ringatomen miteinander zu einem gegebenenfalls substituierten 5- oder 6-gliedrigen Aryl- oder Heteroarylring verbunden sind; wobei R² und R³ jeweils unabhängig wie oben definiert sind;

T für eine Ankergruppe steht, die durch eine lineare Kette von 1 bis 3 Atomen, die unabhängig aus C, N, O, S, Si und B ausgewählt sind, bereitgestellt wird, wobei jedes dieser Atome gegebenenfalls durch einen oder mehrere Substituenten, die unabhängig aus Wasserstoff, Halogen, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₁₀-Alkyl, gegebenenfalls substituiertem C₂₋₁₀-Alkenyl, gegebenenfalls substituiertem C₂₋₁₀-Alkynyl und gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt sind, substituiert und gegebenenfalls mit einem 3-6-gliedrigen Carbocyclus oder Heterocyclus anelliert ist und wobei R² und R³ jeweils unabhängig wie oben definiert sind;

A für einen monocyclischen oder bicyclischen 5- oder 6-gliedrigen heterocyclischen Ring steht, der ein Donoratom D und ein Ringatom A¹ enthält und gegebenenfalls 1 oder 2 zusätzliche Ringhetero-atome, die aus O, S und N ausgewählt sind, aufweist, wobei der heterocyclische Ring gegebenenfalls durch 1 bis 3 Substituenten, die unabhängig aus Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl und gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt sind, substituiert ist; wobei R² und R³ jeweils unabhängig wie oben definiert sind;

A¹ aus C, N und CR⁷ ausgewählt ist; wobei R⁷ aus Wasserstoff, Halogen, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², gegebenenfalls substituiertem C₁₋₂₀-Alkyl, gegebenenfalls substituiertem C₂₋₂₀-Alkenyl, gegebenenfalls substituiertem C₂₋₂₀-Alkynyl, gegebenenfalls substituiertem 5- oder 6-gliedrigem Aryl oder Heteroaryl ausgewählt ist; R² und R³ jeweils unabhängig wie oben definiert sind; und

D für ein Donoratom, das aus N, O, S, P, Se und Te ausgewählt ist, steht.

10. Verbindung nach Anspruch 9, wobei M aus Ir ausgewählt ist.


11. Verbindung nach Anspruch 9 oder Anspruch 10, wobei n für 3 steht, m für 0 steht und L fehlt.

12. Emissionsmaterial, umfassend einen Metallkomplex der Formel 3 gemäß einem der Ansprüche 9 bis 11.

13. Organische Elektrolumineszenzvorrichtung mit mindestens einem Paar von Elektroden, das eine Kathode und eine Anode umfasst; und mindestens einer das Emissionsmaterial gemäß Anspruch 12 umfassenden Schicht, die zwischen dem mindestens einen Paar von Elektroden angeordnet ist.

Revendications

1. Composé de formule 1 :



Formule 1

dans laquelle

R¹ est choisi parmi alkyle en C₁ à C₂₀, alcényle en C₂ à C₂₀, alcynyle en C₂ à C₂₀, et aryle ou hétéroaryle à 5 ou 6 chaînons, chacun étant éventuellement substitué par un ou plusieurs substituants indépendamment choisis parmi halogéno, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryle et hétéroaryle ;

chacun de R² et R³ est indépendamment choisi parmi l'hydrogène et alkyle en C₁ à C₆ ;

chaque R⁴ est indépendamment choisi parmi l'hydrogène, les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué, et éventuellement deux substituants R⁴ d'atomes de cycle adjacents sont joints ensemble pour former un cycle aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;

T est un groupe d'attache constitué d'une chaîne linéaire de 1 à 3 atomes indépendamment choisis parmi C, N, O, S, Si et B, chacun étant éventuellement substitué par un ou plusieurs substituants indépendamment choisis parmi l'hydrogène, les halogènes, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₁₀ éventuellement substitué, alcényle en C₂ à C₁₀ éventuellement substitué, alcynyle en C₂ à C₁₀ éventuellement substitué et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué, et éventuellement condensé à un carbocycle ou hétérocycle à 3 à 6 chaînons ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;


A est un hétérocycle monocyclique ou bicyclique comprenant 5 ou 6 atomes de cycle, contenant un atome donneur D et un atome de cycle A¹, et ayant éventuellement 1 ou 2 hétéroatomes de cycle additionnels choisis parmi O, S et N, l'hétérocycle étant éventuellement substitué par 1 à 3 substituants indépendamment choisis parmi les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;

A¹ est choisi parmi C, N et CR⁷ ; où R⁷ est choisi parmi l'hydrogène, les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ; et

D est un atome donneur choisi parmi N, O, S, P, Se et Te.

2. Composé selon la revendication 1, dans lequel R¹ est choisi parmi alkyle en C₁ à C₁₀ éventuellement substitué et aryle ou hétéroaryle à 5 ou 6 chaînons monocyclique éventuellement substitué.

3. Composé selon la revendication 1 ou la revendication 2, dans lequel T est un groupe d'attache constitué d'une chaîne linéaire de 1 à 3 atomes, indépendamment choisie parmi -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)-, -S(=O)₂-, alkyle en C₁ à C₃ et alcényle en C₂ à C₃; chacun parmi l'alkyle en C₁ à C₃ et l'alcényle en C₂ à C₃ étant éventuellement interrompu par un groupe choisi parmi -N(R⁶)-, -N(R⁶)-C(=O)-, -O-, -O-C(=O)-, -C(=O)-, -S-, -S(=O)- et -S(=O)₂-, et éventuellement substitué par un ou plusieurs substituants indépendamment choisis parmi les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₁₀, alcényle en C₂ à C₁₀, alcynyle en C₂ à C₁₀, halogénoalkyle en C₁ à C₁₀, halogénoalcényle en C₂ à C₁₀ et halogénoalcynyle en C₂ à C₁₀, et éventuellement condensé avec un carbocycle ou hétérocycle à 3 à 6 chaînons, R⁶ pouvant être choisi parmi l'hydrogène et alkyle en C₁ à C₁₀.
4. Composé selon l'une quelconque des revendications précédentes, dans lequel T est un alkyle en C₁ à C₃ éventuellement substitué et éventuellement condensé.
5. Composé selon l'une quelconque des revendications précédentes, dans lequel D est N.
6. Composé selon l'une quelconque des revendications précédentes, dans lequel A est un groupe pyridine éventuellement substitué.
7. Composé selon l'une quelconque des revendications précédentes, dans lequel chaque R⁴ est l'hydrogène.
8. Composé de formule 2 :



Formule 2

dans laquelle

R¹ est choisi parmi alkyle en C₁ à C₂₀, alcényle en C₂ à C₂₀, alcynyle en C₂ à C₂₀, et aryle ou hétéroaryle à 5 ou 6 chaînons, chacun étant éventuellement substitué par un ou plusieurs substituants indépendamment choisis parmi halogéno, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryle et hétéroaryle ;
 chacun de R² et R³ est indépendamment choisi parmi l'hydrogène et alkyle en C₁ à C₆ ;
 chaque R⁴ est indépendamment choisi parmi l'hydrogène, les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué, et éventuellement deux substituants R⁴ d'atomes de cycle adjacents sont joints ensemble pour former un cycle aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;
 T est un groupe d'attache constitué d'une chaîne linéaire de 1 à 3 atomes indépendamment choisis parmi C, N, O, S, Si et B, chacun étant éventuellement substitué par un ou plusieurs substituants indépendamment choisis parmi l'hydrogène, les halogènes, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₁₀ éventuellement substitué, alcényle en C₂ à C₁₀ éventuellement substitué, alcynyle en C₂ à C₁₀ éventuellement substitué et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué, et éventuellement condensé à un carbocycle ou hétérocycle à 3 à 6 chaînons ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;
 A est un hétérocycle monocyclique ou bicyclique comprenant 5 ou 6 atomes de cycle, contenant un atome donneur D et un atome de cycle A¹, et ayant éventuellement 1 ou 2 hétéroatomes de cycle additionnels choisis parmi O, S et N, l'hétérocycle étant éventuellement substitué par 1 à 3 substituants indépendamment choisis


parmi les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;

A¹ est choisi parmi C, N et CR⁷ ; où R⁷ est choisi parmi l'hydrogène, les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ; et

D est un atome donneur choisi parmi N, O, S, P, Se et Te ; et

R¹⁰ est choisi parmi l'hydrogène et les halogènes.

9. Complexe métallique de formule 3 :



Formule 3

dans laquelle

M est un atome de métal choisi parmi Ir, Pt, Rh, Pd, Ru et Os ;

n est un entier choisi parmi 1, 2 et 3 ;

m est un entier choisi parmi 0, 1, 2, 3, 4 et 5 ;

L est un ligand monodenté ou bidenté ; et

R¹ est choisi parmi alkyle en C₁ à C₂₀, alcényle en C₂ à C₂₀, alcynyle en C₂ à C₂₀, et aryle ou hétéroaryle à 5 ou 6 chaînons, chacun étant éventuellement substitué par un ou plusieurs substituants indépendamment choisis parmi halogéno, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², aryle et hétéroaryle ;

chacun de R² et R³ est indépendamment choisi parmi l'hydrogène et alkyle en C₁ à C₆ ;

chaque R⁴ est indépendamment choisi parmi l'hydrogène, les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué, et éventuellement deux substituants R⁴ d'atomes de cycle adjacents sont joints ensemble pour former un cycle aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;

T est un groupe d'attache constitué d'une chaîne linéaire de 1 à 3 atomes indépendamment choisis parmi C, N, O, S, Si et B, chacun étant éventuellement substitué par un ou plusieurs substituants indépendamment choisis parmi l'hydrogène, les halogènes, CN, NO₂, =O, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₁₀ éventuellement substitué, alcényle en C₂ à C₁₀ éventuellement substitué, alcynyle en C₂ à C₁₀ éventuellement substitué et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué, et éventuellement condensé à un carbocycle ou hétérocycle à 3 à 6 chaînons ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;

A est un hétérocycle monocyclique ou bicyclique comprenant 5 ou 6 atomes de cycle, contenant un atome donneur D et un atome de cycle A¹, et ayant éventuellement 1 ou 2 hétéroatomes de cycle additionnels choisis parmi O, S et N, l'hétérocycle étant éventuellement substitué par 1 à 3 substituants indépendamment choisis parmi les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ;

A¹ est choisi parmi C, N et CR⁷ ; où R⁷ est choisi parmi l'hydrogène, les halogènes, CN, NO₂, C(O)R², OR², OS(O)₂R², NR²R³, SR², alkyle en C₁ à C₂₀ éventuellement substitué, alcényle en C₂ à C₂₀ éventuellement substitué, alcynyle en C₂ à C₂₀ éventuellement substitué, et aryle ou hétéroaryle à 5 ou 6 chaînons éventuellement substitué ; chacun de R² et R³ étant indépendamment tel que défini ci-dessus ; et

D est un atome donneur choisi parmi N, O, S, P, Se et Te.

10. Composé selon la revendication 9, dans lequel M est Ir.

11. Composé selon la revendication 9 ou la revendication 10, dans lequel n vaut 3, m vaut 0 et L est absent.

12. Matière émissive comprenant un complexe métallique de formule 3 tel que défini dans l'une quelconque des revendications 9 à 11.

13. Dispositif électroluminescent organique comprenant au moins une paire d'électrodes comprenant une cathode et une anode ; et au moins une couche comprenant la matière émissive telle que définie dans la revendication 12 qui est disposée entre l'au moins une paire d'électrodes.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 2010099852 A1 [0004]
- WO 05011013 A [0152]
- WO 04013080 A [0154]
- WO 04093207 A [0154]
- WO 06005627 A [0154]
- WO 05039246 A [0154]
- US 20050069729 A [0154]
- JP 2004288381 A [0154]
- EP 1205527 A [0154]
- WO 08086851 A [0154]
- WO 07063754 A [0154]
- WO 08056746 A [0154]
- EP 1617710 A [0154]
- EP 1617711 A [0154]
- EP 1731584 A [0154]
- JP 2005347160 A [0154]
- WO 07137725 A [0154]
- WO 05111172 A [0154]
- WO 06117052 A [0154]
- EP 652273 A [0154]
- WO 09062578 A [0154]
- WO 0070655 A [0159]
- WO 0141512 A [0159]
- WO 0202714 A [0159]
- WO 0215645 A [0159]
- EP 1191613 A [0159]
- EP 1191612 A [0159]
- EP 1191614 A [0159]
- WO 05033244 A [0159]
- WO 09118087 A [0159]


Non-patent literature cited in the description

- **M. A. BALDO** et al. *Appl. Phys. Lett.*, 1999, vol. 75, 4-6 [0004]
- **M. S. ARNOLD** et al. *Appl. Phys. Lett.*, 2008, vol. 92, 053301 [0161]

专利名称(译)	苯二胺化合物用于磷光二氮杂硼杂环戊烷金属配合物		
公开(公告)号	EP2927300B1	公开(公告)日	2016-11-16
申请号	EP2015161743	申请日	2015-03-30
[标]申请(专利权)人(译)	联邦科学和工业研究组织		
申请(专利权)人(译)	联邦科学与工业研究组织		
当前申请(专利权)人(译)	联邦科学与工业研究组织		
[标]发明人	BILYK ALEXANDER BOWN MARK UENO KAZUNORI GROARKE MICHELLE		
发明人	BILYK, ALEXANDER BOWN, MARK UENO, KAZUNORI GROARKE, MICHELLE		
IPC分类号	C09K11/06 H01L51/00 H01L51/50 C07F15/00 C07D401/04 C07F5/00 C07F5/02		
CPC分类号	H01L51/0085 C07D471/04 C07F15/004 C09K11/06 H01L51/0072 H01L51/008 H01L51/5012 H01L51/5016		
优先权	2014901154 2014-03-31 AU		
其他公开文献	EP2927300A1		
外部链接	Espacenet		

摘要(译)

本公开一般涉及苯二胺化合物，其可以用作制备二氮杂硼杂环戊二烯化合物和磷光二氮杂硼杂环戊二烯金属络合物的前体。本公开还涉及二氮杂硼杂环戊二烯化合物，二氮杂硼杂环戊二烯金属络合物和电致发光发射材料及其电子器件。本公开进一步涉及制备苯二胺化合物和二氮杂硼杂环戊二烯金属络合物的方法。



Formula 1