



US008803162B2

(12) **United States Patent**  
**Lee et al.**

(10) **Patent No.:** **US 8,803,162 B2**  
(45) **Date of Patent:** **Aug. 12, 2014**

(54) **ORGANIC LIGHT EMITTING DISPLAY OF MOTHER SUBSTRATE UNIT AND METHOD OF FABRICATING THE SAME**

4,610,079 A \* 9/1986 Abe et al. .... 438/462  
(Continued)

FOREIGN PATENT DOCUMENTS

(75) Inventors: **Ho Seok Lee**, Yongin-si (KR); **Won Kyu Kwak**, Seongnam-si (KR)  
(73) Assignee: **Samsung Display Co., Ltd.**, Yongin, Gyeonggi-Do (KR)

JP 09-278483 10/1997  
JP 10-074583 3/1998  
TW 200533234 10/2005

OTHER PUBLICATIONS

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 1535 days.

Taiwanese Office Action dated Jan. 20, 2010 in Taiwanese Patent Application No. 095145106.

(21) Appl. No.: **11/540,066**

*Primary Examiner* — Ori Nadav

(22) Filed: **Sep. 29, 2006**

(74) *Attorney, Agent, or Firm* — Knobbe, Martens, Olson & Bear, LLP

(65) **Prior Publication Data**

US 2007/0176185 A1 Aug. 2, 2007

(57) **ABSTRACT**

(30) **Foreign Application Priority Data**

Jan. 27, 2006 (KR) ..... 10-2006-0008806

A mother substrate unit organic light emitting display in which grooves are formed on the internal surface where a scribing line is formed to scribe a mother substrate on which a plurality of display panels are formed into unit display panels so that a scribing process is easily performed and a method of fabricating the same are disclosed. The mother substrate unit organic light emitting display includes a first substrate including a plurality of display panels and a scribing line defined between the display panels such that each display panel includes a pixel region in which an organic light emitting diode (OLED) including a first electrode, an organic layer, and a second electrode is formed and a non-pixel region, a second substrate that is arranged on the first substrate to overlap the first substrate and on which grooves are formed to correspond to the scribing line, and a plurality of frits provided between the first substrate and the second substrate and formed along the circumference of the pixel regions. The first substrate and the second substrate are attached to each other by the plurality of frits.

(51) **Int. Cl.**

**H01L 27/15** (2006.01)

**H01L 51/52** (2006.01)

(52) **U.S. Cl.**

CPC ..... **H01L 51/5237** (2013.01); **H01L 2251/566** (2013.01)

USPC ..... **257/79**; **257/787**

(58) **Field of Classification Search**

CPC ..... **H01L 51/5237**; **H01L 2251/566**

USPC ..... **257/79**, **787**; **438/115**

See application file for complete search history.


(56) **References Cited**

U.S. PATENT DOCUMENTS

4,238,704 A 12/1980 Bonk et al.  
4,418,284 A \* 11/1983 Ogawa et al. .... 250/208.1

**13 Claims, 8 Drawing Sheets**

100



(56)

**References Cited**

U.S. PATENT DOCUMENTS

6,225,741	B1 *	5/2001	Nakamura et al. ....	313/506	6,734,083	B2 *	5/2004	Kobayashi .....	438/462
6,555,025	B1	4/2003	Krupetsky et al.		7,306,346	B2 *	12/2007	Fukuoka et al. ....	362/84
6,580,094	B1 *	6/2003	Yamazaki et al. ....	257/79	2003/0218422	A1 *	11/2003	Park et al. ....	313/512
					2005/0269926	A1	12/2005	Fukuoka et al.	
					2007/0172971	A1 *	7/2007	Boroson .....	438/26

\* cited by examiner

FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 3E




FIG. 3F




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D





FIG. 5E



# ORGANIC LIGHT EMITTING DISPLAY OF MOTHER SUBSTRATE UNIT AND METHOD OF FABRICATING THE SAME

## CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of Korean Patent Application No. 10-2006-0008806, filed on Jan. 27, 2006, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein by reference.

## BACKGROUND OF THE INVENTION

### 1. Field of the Invention

The present invention relates to organic light emitting display device, and more particularly, to mass production of organic light emitting display devices.

### 2. Description of the Related Technology

Recently, organic light emitting displays are widely used among organic semiconductor devices and have a simple structure. The organic light emitting displays are self-emission displays in which organic layers are used as emission layers and do not require additional back light in order to emit light unlike liquid crystal displays (LCD). The organic light emitting displays are thin and light. Therefore, recently, the organic light emitting displays are actively developed as display panels of portable information terminals such as portable computers, mobile telephones, and portable game devices, and electronic books.

In a typical organic light emitting display, at least one organic layer including an emission layer is interposed between a pair of electrodes, that is, a first electrode and a second electrode. The first electrode is formed on a substrate and functions as an anode that injects holes. An organic layer is formed on the first electrode. A second electrode that functions as a cathode that injects electrons is formed on the organic layer to face the first electrode.

In such an organic light emitting display, when moisture or oxygen permeates from the outside to an organic light emitting diode (OLED), an electrode material is oxidized and separated so that the life span of the OLED is reduced, that emission efficiency deteriorates, and that emission color changes.

Therefore, in fabricating the organic light emitting display, the OLED is sealed from the outside so that moisture cannot penetrate. In order to seal up the OLED, for example, a polymer such as polyethyleneterephthalate (PET) is laminated on the cathode of the OLED. Alternatively, a cover or cap is formed of a metal or glass that includes an absorbent. The cover or cap may be filled with a nitrogen gas, and the circumference of the cover or cap may be sealed up by a sealing material such as epoxy.

However, in such a method, it is difficult to make the substrate and the cap tightly attached to each other and to precisely apply the sealing material and thus the OLED is deteriorated and deformed by heat emitting from the OLED.

In order to solve the above problems, a capsule sealing method of improving attachment between the substrate and the cap using a frit as the sealing material has been proposed. In order to commercialize the organic light emitting display using a frit seal, the organic light emitting display is not fabricated using a unit display panel, but is fabricated using a mother substrate unit display panel. That is, after a plurality of display panels are fabricated simultaneously, they are cut or scribed into individual display panel.

When the mother substrate unit display panel using the frit seal is scribed into unit display panels, tension occurs due to heat during a process of annealing or melting the frit. Thus, a scribing crack is irregularly transmitted during the scribing process and the scribing section is formed irregularly. Therefore, the size of the unit display panel varies.

## SUMMARY OF CERTAIN INVENTIVE ASPECTS

One aspect of the invention provides an organic light emitting device. The device comprises: a first substrate; a second substrate generally opposing the first substrate; two or more arrays of organic light emitting pixels interposed between the first and second substrates; and two or more frit seals interposed between the first and second substrates, a first one of the frit seals surrounding a first one of the arrays, a second one of the frit seals surrounding a second one of the arrays, the first frit seal comprising a first elongated segment, the second frit seal comprising a second elongated segment, wherein the first and second elongated segments extending with a gap therebetween; wherein at least one of the first and second substrates comprises a dividing groove on a surface thereof, the dividing groove being positioned along the gap between the first and second elongated segments.

The second substrate may comprise a substantially transparent material so as to pass visible light emitted from the organic light emitting pixels, and the second substrate may comprise the dividing groove. The second substrate may comprise an outer surface and an inner surface, and the second substrate may comprise the dividing groove on at least one of the outer and inner surfaces. The first substrate may comprise an outer surface and an inner surface, and the first substrate may comprise the dividing groove on one of the outer and inner surfaces. The dividing groove may have a depth of about 30% to about 50% of the thickness of the substrate comprising the dividing groove. The dividing groove may have a width between about 50  $\mu\text{m}$  and about 100  $\mu\text{m}$ .

The first and second elongated segments may extend substantially parallel to each other. The device may further comprise two or more reinforcing members interposed between and bonded to the first and second substrates, the two or more reinforcing members comprising a first reinforcing member and a second reinforcing member, wherein the first reinforcing member extends substantially parallel to the first elongated segment, and wherein the second reinforcing member extends substantially parallel to the second elongated segment.

The first reinforcing member may be positioned between the first elongated segment and the second elongated segment, and the dividing groove may be positioned between the first reinforcing member and the second elongated segment. The second reinforcing member may be positioned between the first reinforcing member and the second elongated segment, and the dividing groove may be positioned between the first reinforcing member and the second reinforcing member. The reinforcing members may comprise one or more selected from the group consisting of cyanoacrylate, acrylate, epoxy, and urethaneacrylate resin. The first elongated segment may be positioned between the first reinforcing member and the second elongated segment, and the dividing groove may be positioned between the first elongated segment and the second elongated segment.

Another aspect of the invention provides an organic light emitting device, comprising: a first substrate; a second substrate generally opposing the first substrate, the second substrate having an outer surface, an inner surface, and a plurality

of sides interconnecting the outer and inner surfaces; an array of organic light emitting pixels interposed between the first and second substrates; and a frit seal interposed between the first and second substrates, the frit seal surrounding the array; wherein at least one of the sides comprises two leveled surfaces, which comprise a first surface and a second surface connected to the first surface with a step or a slanted surface, wherein the first and second surfaces extend substantially parallel to each other.

The first surface may connect to the inner surface of the second substrate, and the second surface may connect to the outer surface of the second substrate. The first surface may have a width extending in a direction interconnecting the outer and inner surfaces of the second substrate in the shortest distance, and the width may be between about 30% to about 50% of the thickness of the second substrate in the direction.

Another aspect of the invention provides a method of making an organic light emitting display. The method comprises: providing a device comprising: a first substrate, a second substrate generally opposing the first substrate, two or more arrays of organic light emitting pixels interposed between the first and second substrates, and two or more frit seals interposed between the first and second substrates, a first one of the frit seals surrounding a first one of the arrays, a second one of the frit seals surrounding a second one of the arrays, the first frit seal comprising a first elongated segment, the second frit seal comprising a second elongated segment, wherein the first and second elongated segments extending with a gap therebetween, wherein at least one of the first and second substrates may comprise a dividing groove on a surface thereof, the dividing groove being positioned along the gap between the first and second elongated segments; and cutting the device into two pieces along the dividing groove.

The method may further comprise further cutting the device along the first frit seal so as to provide a first organic light emitting device comprising: a cut portion of the first substrate; a cut portion of the second substrate; the first frit seal interposed between the cut portions of the first and second substrates; and the first array surrounded by the frit seal.

The second substrate may comprise an outer surface and an inner surface, and the second substrate may comprise the dividing groove on at least one of the outer and inner surfaces. The dividing groove may have a depth of about 30% to about 50% of the thickness of the substrate where the dividing groove is formed. The dividing groove may have a width between about 50  $\mu\text{m}$  and about 100  $\mu\text{m}$ .

In the method, providing the device may comprise: providing the first substrate and the two or more arrays formed over the first substrate; providing the second substrate over the first substrate, the second substrate comprising the dividing groove; and forming the first and second frit seals between the first and second substrates such that the first elongated segment of the first frit seal is positioned on one side of the dividing groove and that the second elongated segment of the second frit seal is positioned on the other side of the dividing groove. Providing the second substrate may comprise forming the dividing groove on the surface of the second substrate.

The device may further comprise two or more reinforcing members interposed between and bonded to the first and second substrates, the two or more reinforcing members comprising a first reinforcing member and a second reinforcing member, wherein the first elongated segment and the first reinforcing member extend substantially parallel, and wherein the second elongated segment and the second reinforcing member extend substantially parallel.

The first reinforcing member and the second reinforcing member may be positioned between the first elongated seg-

ment of the first frit seal and the second elongated segment of the second frit seal, and the dividing groove may be positioned between the first reinforcing member and the second reinforcing member. The reinforcing members may comprise one or more selected from the group consisting of cyanoacrylate, acrylate, epoxy, and urethaneacrylate resin. Providing the device may further comprise curing the reinforcing members.

Another aspect of the invention provides a mother substrate unit organic light emitting display in which grooves are formed on the internal side of a scribing line along which a mother substrate where a plurality of display panels are formed is scribed into unit display panels so that a scribing process is easily performed and a method of fabricating the same.

Another aspect of the invention provides a mother substrate unit organic light emitting display comprising a first substrate including a plurality of display panels and a scribing line defined between the display panels such that each display panel includes a pixel region in which an organic light emitting diode (OLED) including a first electrode, an organic layer, and a second electrode is formed and a non-pixel region, a second substrate that is arranged on the first substrate to overlap the first substrate and on which grooves are formed to correspond to the scribing line, and a plurality of frits provided between the first substrate and the second substrate and formed along the circumference of the pixel regions. The first substrate and the second substrate are attached to each other by the plurality of frits.

The grooves may be formed on the internal surface of the second substrate. The grooves have a depth of 30% to 50% of the thickness of the second substrate. The mother substrate unit organic light emitting display further comprises stiffeners provided between the first substrate and the second substrate and formed on the circumference of the plurality of display panels. The stiffeners are formed of at least one selected from the group consisting of cyanoacrylate, acrylate, epoxy, and urethaneacrylate.

Another aspect of the invention provides a method of fabricating a mother substrate unit organic light emitting display, the method comprising the steps of providing a first substrate including a plurality of display panels and a scribing line defined between the display panels such that each display panel includes a pixel region in which an OLED including a first electrode, an organic layer, and a second electrode is formed and a non-pixel region, positioning a second substrate under the first substrate to overlap the first substrate, forming grooves on the internal surface of the second substrate to correspond to the scribing line, applying frits on the second substrate to correspond to the non-pixel regions and annealing the frits, attaching the second substrate to the first substrate so that the pixel regions are sealed up, and melting the frits to be adhered to the first substrate.

The grooves may be formed by etching or polishing. The frits may be melted by laser or infrared rays. The method further comprises the step of forming stiffeners on the second substrate outside the frits after forming the frits on the second substrate. The stiffeners are hardened by ultraviolet rays or heat. The stiffeners are formed by screen printing or dispensing.

#### BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other objects and advantages of the invention will become apparent and more readily appreciated from the following description of embodiments, taken in conjunction with the accompanying drawings of which:

FIG. 1 is a sectional view illustrating a mother substrate unit light emitting display according to one embodiment;

FIGS. 2A to 2F are sectional views illustrating a method of fabricating the mother substrate unit organic light emitting display according to one embodiment; and

FIGS. 3A to 3F are perspective views illustrating a method of fabricating the mother substrate unit organic light emitting display according to one embodiment.

FIG. 4 is an enlarged partial perspective view of a side of a first (or second) substrate in an organic light emitting device according to one embodiment.

FIG. 5A is a schematic exploded view of a passive matrix type organic light emitting display device in accordance with one embodiment.

FIG. 5B is a schematic exploded view of an active matrix type organic light emitting display device in accordance with one embodiment.

FIG. 5C is a schematic top plan view of an organic light emitting display in accordance with one embodiment.

FIG. 5D is a cross-sectional view of the organic light emitting display of FIG. 5C, taken along the line d-d.

FIG. 5E is a schematic perspective view illustrating mass production of organic light emitting devices in accordance with one embodiment.

#### DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

Hereinafter, certain inventive embodiments will be described with reference to the accompanying drawings.

An organic light emitting display (OLED) is a display device comprising an array of organic light emitting diodes. Organic light emitting diodes are solid state devices which include an organic material and are adapted to generate and emit light when appropriate electrical potentials are applied.

OLEDs can be generally grouped into two basic types dependent on the arrangement with which the stimulating electrical current is provided. FIG. 5A schematically illustrates an exploded view of a simplified structure of a passive matrix type OLED 1000. FIG. 5B schematically illustrates a simplified structure of an active matrix type OLED 1001. In both configurations, the OLED 1000, 1001 includes OLED pixels built over a substrate 1002, and the OLED pixels include an anode 1004, a cathode 1006 and an organic layer 1010. When an appropriate electrical current is applied to the anode 1004, electric current flows through the pixels and visible light is emitted from the organic layer.

Referring to FIG. 5A, the passive matrix OLED (PMOLED) design includes elongate strips of anode 1004 arranged generally perpendicular to elongate strips of cathode 1006 with organic layers interposed therebetween. The intersections of the strips of cathode 1006 and anode 1004 define individual OLED pixels where light is generated and emitted upon appropriate excitation of the corresponding strips of anode 1004 and cathode 1006. PMOLEDs provide the advantage of relatively simple fabrication.

Referring to FIG. 5B, the active matrix OLED (AMOLED) includes local driving circuits 1012 arranged between the substrate 1002 and an array of OLED pixels. An individual pixel of AMOLEDs is defined between the common cathode 1006 and an anode 1004, which is electrically isolated from other anodes. Each driving circuit 1012 is coupled with an anode 1004 of the OLED pixels and further coupled with a data line 1016 and a scan line 1018. In embodiments, the scan lines 1018 supply scan signals that select rows of the driving circuits, and the data lines 1016 supply data signals for particular driving circuits. The data signals and scan signals

stimulate the local driving circuits 1012, which excite the anodes 1004 so as to emit light from their corresponding pixels.

In the illustrated AMOLED, the local driving circuits 1012, the data lines 1016 and scan lines 1018 are buried in a planarization layer 1014, which is interposed between the pixel array and the substrate 1002. The planarization layer 1014 provides a planar top surface on which the organic light emitting pixel array is formed. The planarization layer 1014 may be formed of organic or inorganic materials, and formed of two or more layers although shown as a single layer. The local driving circuits 1012 are typically formed with thin film transistors (TFT) and arranged in a grid or array under the OLED pixel array. The local driving circuits 1012 may be at least partly made of organic materials, including organic TFT. AMOLEDs have the advantage of fast response time improving their desirability for use in displaying data signals. Also, AMOLEDs have the advantages of consuming less power than passive matrix OLEDs.

Referring to common features of the PMOLED and AMOLED designs, the substrate 1002 provides structural support for the OLED pixels and circuits. In various embodiments, the substrate 1002 can comprise rigid or flexible materials as well as opaque or transparent materials, such as plastic, glass, and/or foil. As noted above, each OLED pixel or diode is formed with the anode 1004, cathode 1006 and organic layer 1010 interposed therebetween. When an appropriate electrical current is applied to the anode 1004, the cathode 1006 injects electrons and the anode 1004 injects holes. In certain embodiments, the anode 1004 and cathode 1006 are inverted; i.e., the cathode is formed on the substrate 1002 and the anode is opposingly arranged.

Interposed between the cathode 1006 and anode 1004 are one or more organic layers. More specifically, at least one emissive or light emitting layer is interposed between the cathode 1006 and anode 1004. The light emitting layer may comprise one or more light emitting organic compounds. Typically, the light emitting layer is configured to emit visible light in a single color such as blue, green, red or white. In the illustrated embodiment, one organic layer 1010 is formed between the cathode 1006 and anode 1004 and acts as a light emitting layer. Additional layers, which can be formed between the anode 1004 and cathode 1006, can include a hole transporting layer, a hole injection layer, an electron transporting layer and an electron injection layer.

Hole transporting and/or injection layers can be interposed between the light emitting layer 1010 and the anode 1004. Electron transporting and/or injecting layers can be interposed between the cathode 1006 and the light emitting layer 1010. The electron injection layer facilitates injection of electrons from the cathode 1006 toward the light emitting layer 1010 by reducing the work function for injecting electrons from the cathode 1006. Similarly, the hole injection layer facilitates injection of holes from the anode 1004 toward the light emitting layer 1010. The hole and electron transporting layers facilitate movement of the carriers injected from the respective electrodes toward the light emitting layer.

In some embodiments, a single layer may serve both electron injection and transportation functions or both hole injection and transportation functions. In some embodiments, one or more of these layers are lacking. In some embodiments, one or more organic layers are doped with one or more materials that help injection and/or transportation of the carriers. In embodiments where only one organic layer is formed between the cathode and anode, the organic layer may include

not only an organic light emitting compound but also certain functional materials that help injection or transportation of carriers within that layer.

There are numerous organic materials that have been developed for use in these layers including the light emitting layer. Also, numerous other organic materials for use in these layers are being developed. In some embodiments, these organic materials may be macromolecules including oligomers and polymers. In some embodiments, the organic materials for these layers may be relatively small molecules. The skilled artisan will be able to select appropriate materials for each of these layers in view of the desired functions of the individual layers and the materials for the neighboring layers in particular designs.

In operation, an electrical circuit provides appropriate potential between the cathode **1006** and anode **1004**. This results in an electrical current flowing from the anode **1004** to the cathode **1006** via the interposed organic layer(s). In one embodiment, the cathode **1006** provides electrons to the adjacent organic layer **1010**. The anode **1004** injects holes to the organic layer **1010**. The holes and electrons recombine in the organic layer **1010** and generate energy particles called "excitons." The excitons transfer their energy to the organic light emitting material in the organic layer **1010**, and the energy is used to emit visible light from the organic light emitting material. The spectral characteristics of light generated and emitted by the OLED **1000**, **1001** depend on the nature and composition of organic molecules in the organic layer(s). The composition of the one or more organic layers can be selected to suit the needs of a particular application by one of ordinary skill in the art.

OLED devices can also be categorized based on the direction of the light emission. In one type referred to as "top emission" type, OLED devices emit light and display images through the cathode or top electrode **1006**. In these embodiments, the cathode **1006** is made of a material transparent or at least partially transparent with respect to visible light. In certain embodiments, to avoid losing any light that can pass through the anode or bottom electrode **1004**, the anode may be made of a material substantially reflective of the visible light. A second type of OLED devices emits light through the anode or bottom electrode **1004** and is called "bottom emission" type. In the bottom emission type OLED devices, the anode **1004** is made of a material which is at least partially transparent with respect to visible light. Often, in bottom emission type OLED devices, the cathode **1006** is made of a material substantially reflective of the visible light. A third type of OLED devices emits light in two directions, e.g. through both anode **1004** and cathode **1006**. Depending upon the direction(s) of the light emission, the substrate may be formed of a material which is transparent, opaque or reflective of visible light.

In many embodiments, an OLED pixel array **1021** comprising a plurality of organic light emitting pixels is arranged over a substrate **1002** as shown in FIG. 5C. In embodiments, the pixels in the array **1021** are controlled to be turned on and off by a driving circuit (not shown), and the plurality of the pixels as a whole displays information or image on the array **1021**. In certain embodiments, the OLED pixel array **1021** is arranged with respect to other components, such as drive and control electronics to define a display region and a non-display region. In these embodiments, the display region refers to the area of the substrate **1002** where OLED pixel array **1021** is formed. The non-display region refers to the remaining areas of the substrate **1002**. In embodiments, the non-display region can contain logic and/or power supply circuitry. It will be understood that there will be at least

portions of control/drive circuit elements arranged within the display region. For example, in PMOLEDs, conductive components will extend into the display region to provide appropriate potential to the anode and cathodes. In AMOLEDs, local driving circuits and data/scan lines coupled with the driving circuits will extend into the display region to drive and control the individual pixels of the AMOLEDs.

One design and fabrication consideration in OLED devices is that certain organic material layers of OLED devices can suffer damage or accelerated deterioration from exposure to water, oxygen or other harmful gases. Accordingly, it is generally understood that OLED devices be sealed or encapsulated to inhibit exposure to moisture and oxygen or other harmful gases found in a manufacturing or operational environment. FIG. 5D schematically illustrates a cross-section of an encapsulated OLED device **1011** having a layout of FIG. 5C and taken along the line d-d of FIG. 5C. In this embodiment, a generally planar top plate or substrate **1061** engages with a seal **1071** which further engages with a bottom plate or substrate **1002** to enclose or encapsulate the OLED pixel array **1021**. In other embodiments, one or more layers are formed on the top plate **1061** or bottom plate **1002**, and the seal **1071** is coupled with the bottom or top substrate **1002**, **1061** via such a layer. In the illustrated embodiment, the seal **1071** extends along the periphery of the OLED pixel array **1021** or the bottom or top plate **1002**, **1061**.

In embodiments, the seal **1071** is made of a frit material as will be further discussed below. In various embodiments, the top and bottom plates **1061**, **1002** comprise materials such as plastics, glass and/or metal foils which can provide a barrier to passage of oxygen and/or water to thereby protect the OLED pixel array **1021** from exposure to these substances. In embodiments, at least one of the top plate **1061** and the bottom plate **1002** are formed of a substantially transparent material.

To lengthen the life time of OLED devices **1011**, it is generally desired that seal **1071** and the top and bottom plates **1061**, **1002** provide a substantially non-permeable seal to oxygen and water vapor and provide a substantially hermetically enclosed space **1081**. In certain applications, it is indicated that the seal **1071** of a frit material in combination with the top and bottom plates **1061**, **1002** provide a barrier to oxygen of less than approximately  $10^{-3}$  cc/m<sup>2</sup>-day and to water of less than  $10^{-6}$  g/m<sup>2</sup>-day. Given that some oxygen and moisture can permeate into the enclosed space **1081**, in some embodiments, a material that can take up oxygen and/or moisture is formed within the enclosed space **1081**.

The seal **1071** has a width W, which is its thickness in a direction parallel to a surface of the top or bottom substrate **1061**, **1002** as shown in FIG. 5D. The width varies among embodiments and ranges from about 300  $\mu$ m to about 3000  $\mu$ m, optionally from about 500  $\mu$ m to about 1500  $\mu$ m. Also, the width may vary at different positions of the seal **1071**. In some embodiments, the width of the seal **1071** may be the largest where the seal **1071** contacts one of the bottom and top substrate **1002**, **1061** or a layer formed thereon. The width may be the smallest where the seal **1071** contacts the other. The width variation in a single cross-section of the seal **1071** relates to the cross-sectional shape of the seal **1071** and other design parameters.

The seal **1071** has a height H, which is its thickness in a direction perpendicular to a surface of the top or bottom substrate **1061**, **1002** as shown in FIG. 5D. The height varies among embodiments and ranges from about 2  $\mu$ m to about 30  $\mu$ m, optionally from about 10  $\mu$ m to about 15  $\mu$ m. Generally, the height does not significantly vary at different positions of

the seal **1071**. However, in certain embodiments, the height of the seal **1071** may vary at different positions thereof.

In the illustrated embodiment, the seal **1071** has a generally rectangular cross-section. In other embodiments, however, the seal **1071** can have other various cross-sectional shapes such as a generally square cross-section, a generally trapezoidal cross-section, a cross-section with one or more rounded edges, or other configuration as indicated by the needs of a given application. To improve hermeticity, it is generally desired to increase the interfacial area where the seal **1071** directly contacts the bottom or top substrate **1002**, **1061** or a layer formed thereon. In some embodiments, the shape of the seal can be designed such that the interfacial area can be increased.

The seal **1071** can be arranged immediately adjacent the OLED array **1021**, and in other embodiments, the seal **1071** is spaced some distance from the OLED array **1021**. In certain embodiment, the seal **1071** comprises generally linear segments that are connected together to surround the OLED array **1021**. Such linear segments of the seal **1071** can extend, in certain embodiments, generally parallel to respective boundaries of the OLED array **1021**. In other embodiment, one or more of the linear segments of the seal **1071** are arranged in a non-parallel relationship with respective boundaries of the OLED array **1021**. In yet other embodiments, at least part of the seal **1071** extends between the top plate **1061** and bottom plate **1002** in a curvilinear manner.

As noted above, in certain embodiments, the seal **1071** is formed using a frit material or simply "frit" or glass frit," which includes fine glass particles. The frit particles includes one or more of magnesium oxide (MgO), calcium oxide (CaO), barium oxide (BaO), lithium oxide (Li<sub>2</sub>O), sodium oxide (Na<sub>2</sub>O), potassium oxide (K<sub>2</sub>O), boron oxide (B<sub>2</sub>O<sub>3</sub>), vanadium oxide (V<sub>2</sub>O<sub>5</sub>), zinc oxide (ZnO), tellurium oxide (TeO<sub>2</sub>), aluminum oxide (Al<sub>2</sub>O<sub>3</sub>), silicon dioxide (SiO<sub>2</sub>), lead oxide (PbO), tin oxide (SnO), phosphorous oxide (P<sub>2</sub>O<sub>5</sub>), ruthenium oxide (Ru<sub>2</sub>O), rubidium oxide (Rb<sub>2</sub>O), rhodium oxide (Rh<sub>2</sub>O), ferrite oxide (Fe<sub>2</sub>O<sub>3</sub>), copper oxide (CuO), titanium oxide (TiO<sub>2</sub>), tungsten oxide (WO<sub>3</sub>), bismuth oxide (Bi<sub>2</sub>O<sub>3</sub>), antimony oxide (Sb<sub>2</sub>O<sub>3</sub>), lead-borate glass, tin-phosphate glass, vanadate glass, and borosilicate, etc. In embodiments, these particles range in size from about 2 μm to about 30 μm, optionally about 5 μm to about 10 μm, although not limited only thereto. The particles can be as large as about the distance between the top and bottom substrates **1061**, **1002** or any layers formed on these substrates where the frit seal **1071** contacts.

The frit material used to form the seal **1071** can also include one or more filler or additive materials. The filler or additive materials can be provided to adjust an overall thermal expansion characteristic of the seal **1071** and/or to adjust the absorption characteristics of the seal **1071** for selected frequencies of incident radiant energy. The filler or additive material(s) can also include inversion and/or additive fillers to adjust a coefficient of thermal expansion of the frit. For example, the filler or additive materials can include transition metals, such as chromium (Cr), iron (Fe), manganese (Mn), cobalt (Co), copper (Cu), and/or vanadium. Additional materials for the filler or additives include ZnSiO<sub>4</sub>, PbTiO<sub>3</sub>, ZrO<sub>2</sub>, eucryptite.

In embodiments, a frit material as a dry composition contains glass particles from about 20 to 90 about wt %, and the remaining includes fillers and/or additives. In some embodiments, the frit paste contains about 10-30 wt % organic materials and about 70-90% inorganic materials. In some embodiments, the frit paste contains about 20 wt % organic materials and about 80 wt % inorganic materials. In some embodi-

ments, the organic materials may include about 0-30 wt % binder(s) and about 70-100 wt % solvent(s). In some embodiments, about 10 wt % is binder(s) and about 90 wt % is solvent(s) among the organic materials. In some embodiments, the inorganic materials may include about 0-10 wt % additives, about 20-40 wt % fillers and about 50-80 wt % glass powder. In some embodiments, about 0-5 wt % is additive(s), about 25-30 wt % is filler(s) and about 65-75 wt % is the glass powder among the inorganic materials.

In forming a frit seal, a liquid material is added to the dry frit material to form a frit paste. Any organic or inorganic solvent with or without additives can be used as the liquid material. In embodiments, the solvent includes one or more organic compounds. For example, applicable organic compounds are ethyl cellulose, nitro cellulose, hydroxyl propyl cellulose, butyl carbitol acetate, terpineol, butyl cellusolve, acrylate compounds. Then, the thus formed frit paste can be applied to form a shape of the seal **1071** on the top and/or bottom plate **1061**, **1002**.

In one exemplary embodiment, a shape of the seal **1071** is initially formed from the frit paste and interposed between the top plate **1061** and the bottom plate **1002**. The seal **1071** can in certain embodiments be pre-cured or pre-sintered to one of the top plate and bottom plate **1061**, **1002**. Following assembly of the top plate **1061** and the bottom plate **1002** with the seal **1071** interposed therebetween, portions of the seal **1071** are selectively heated such that the frit material forming the seal **1071** at least partially melts. The seal **1071** is then allowed to resolidify to form a secure joint between the top plate **1061** and the bottom plate **1002** to thereby inhibit exposure of the enclosed OLED pixel array **1021** to oxygen or water.

In embodiments, the selective heating of the frit seal is carried out by irradiation of light, such as a laser or directed infrared lamp. As previously noted, the frit material forming the seal **1071** can be combined with one or more additives or filler such as species selected for improved absorption of the irradiated light to facilitate heating and melting of the frit material to form the seal **1071**.

In some embodiments, OLED devices **1011** are mass produced. In an embodiment illustrated in FIG. 5E, a plurality of separate OLED arrays **1021** is formed on a common bottom substrate **1101**. In the illustrated embodiment, each OLED array **1021** is surrounded by a shaped frit to form the seal **1071**. In embodiments, common top substrate (not shown) is placed over the common bottom substrate **1101** and the structures formed thereon such that the OLED arrays **1021** and the shaped frit paste are interposed between the common bottom substrate **1101** and the common top substrate. The OLED arrays **1021** are encapsulated and sealed, such as via the previously described enclosure process for a single OLED display device. The resulting product includes a plurality of OLED devices kept together by the common bottom and top substrates. Then, the resulting product is cut into a plurality of pieces, each of which constitutes an OLED device **1011** of FIG. 5D. In certain embodiments, the individual OLED devices **1011** then further undergo additional packaging operations to further improve the sealing formed by the frit seal **1071** and the top and bottom substrates **1061**, **1002**.

FIG. 1 is a sectional view illustrating a mother substrate unit organic light emitting display. Referring to FIG. 1, the mother substrate unit organic light emitting display **100** according to one embodiment includes a plurality of display panels **120** and **130** and a scribing line **181** defined between the display panels. The display panels **120** and **130** include a first substrate **110** including pixel regions **120a** and **130a** and non-pixel regions **120b** and **130b**. In the pixel regions **120a**

and **130a**, organic light emitting diodes (OLED) including first electrodes **126a** and **136a**, organic layers **127a** and **137a**, and second electrodes **129a** and **139a** are formed. The non-pixel regions **120b** and **130b** surround the pixel regions **120a** and **130a**. The display panels **120** and **130** also include a second substrate **140** that is arranged over the first substrate **110** to overlap the first substrate **110**. Grooves **150** are formed on the internal surface of the second substrate **140**. The grooves **150** correspond to the scribing line **181**. In addition, a plurality of frits **160** are provided between the first substrate **110** and the second substrate **140** while surrounding the pixel regions **120a** and **130a**. The first substrate **110** and the second substrate **140** are attached to each other by the plurality of frits **160**.

Hereinafter, for convenience sake, specific two display panels that are adjacent to each other among a plurality of display panels are referred to as a first display panel **120** and a second display panel **130**.

The substrate **110** includes at least a first display panel **120** and a second display panel **130** adjacent to the first display panel **120**. A skilled artisan will appreciate that the substrate **110** may include more display panels, for example, in a matrix pattern. The first display panel **120** includes a first pixel region **120a** and a first non-pixel region **120b**. The second display panel **130** includes a second pixel region **130a** and a second non-pixel region **130b**. The pixel regions **120a** and **130a** are regions on which an image is displayed. The non-pixel regions **120b** and **130b** are regions outside the pixel regions of the substrate. Also, since the second display panel **130** has the same configuration as that of the first display panel **120**, description of the second display panel **130** is omitted. In other embodiments, however, the second display panel may have a configuration different from that of the first display panel.

A buffer layer **121a** may be formed on the substrate **110**. The buffer layer **121a** is an optional component and is formed of a nitride layer or an oxide layer. A thin film transistor (TFT) is formed on the buffer layer **121a**. The TFT includes a semiconductor layer **122a**, a gate electrode **123a**, and source and drain electrodes **124a**. The semiconductor layer **122a** is formed on the buffer layer **121a** in a predetermined pattern. A gate insulation layer is formed on the semiconductor layer **122a**. The gate electrode **123a** of a predetermined pattern is formed on one region of the gate insulation layer. An interlayer insulation layer is formed on the gate electrode **123a**. Source and drain electrodes **124a** are formed on a predetermined region of the interlayer insulation layer. A planarization layer **125a** is formed on the source and drain electrodes **124a** and the interlayer insulation layer.

A first electrode **126a** is formed on one region of the planarization layer **125a**. The first electrode **126a** is electrically connected to one of the source and drain electrodes **124a** through a via hole. A pixel definition layer **127a** including an aperture (not shown) that exposes at least one region of the first electrode **126a** is formed on the first electrode **126a**. An emission layer **128a** is formed on the aperture of the pixel definition layer **127a**. A second electrode layer **129a** is formed on the emission layer **128a** and the pixel definition layer **127a**.

The frits **160** are provided between the non-pixel region of the first substrate **110** and the second substrate **140** to attach the first substrate **110** and the second substrate **140** to each other. The term "frit" may refer to glass in the form of powder. In the context of this document, the term "frit" may also refer to a gel-type glass obtained by adding an organic material to a powder-type glass. A frit may also refer to a solidified glass that has been hardened by radiation of laser.

Stiffeners or reinforcing members **170** are formed on the second substrate **140** outside the frits **160** to attach the first substrate **110** and the second substrate **140** to each other. The stiffeners **170** disperse the shock applied to the frits **160** when the first display panel **120** and the second display panel **130** are scribed after radiating laser onto the frits **160**. In one embodiment, the stiffeners **170** include at least one polymeric material selected from the group consisting of an epoxy, acrylate, urethaneacrylate, and cyanoacrylate resin.

The second substrate **140** is attached to the first substrate **110** by the frits **160** and the stiffeners **170**. The second substrate **140** is attached to the first substrate **110** by the frits **160** with organic light emitting pixels interposed therebetween. The frit protects the pixels from outside oxygen and moisture. In one embodiment, the second substrate **140** is formed of a material selected from the group consisting of  $\text{SiO}_2$ ,  $\text{SiNx}$ , and  $\text{SiOxNy}$ .

In the illustrated embodiment, the grooves **150** are formed on the internal surface of the second substrate **140**, that is, on the internal side of the scribing line **181**. The grooves **150** are formed along a boundary between the non-pixel region **120b** of the first display panel **120** and the non-pixel region **130b** of the second display panel **130**. In one embodiment, the groove **150** may have a depth D of about 30% to about 50% of the thickness of the second substrate **140**. The groove **150** may have a width W between about  $50\mu\text{m}$  and about  $100\mu\text{m}$ . The grooves **150** are formed on the internal side of the scribing line **181** for scribing the first display panel **120** and the second display panel **130** into unit display panels. The grooves **150** reduce the transmission length of a crack that may be generated during scribing the display panels. Also, the groove **150** improves the uniformity of the scribing line **181**. Furthermore, the size of each unit display panel may be made uniform, thus improving the quality of a product.

FIGS. 2A to 2F are sectional views illustrating a method of fabricating the mother substrate unit organic light emitting display according to one embodiment. FIGS. 3A to 3F are perspective views illustrating the method of fabricating the mother substrate unit organic light emitting display according to one embodiment.

Referring to FIGS. 2A and 3A, a substrate **110** includes a first display panel **120** including a first pixel region **120a** and a second non-pixel region **120b**. The substrate **110** also includes a second display panel **130** adjacent to the first display panel **120**. The second display panel **130** includes a second pixel region **130a** and a second non-pixel region **130b**. A second substrate **140** for sealing up the first substrate **110** is positioned under the first substrate **110**. On the second substrate **140**, a scribing line **181** is formed on a boundary between the first non-pixel region **120b** of the first display panel **120** and the second non-pixel region **130b** of the second display panel **130**.

Referring to FIGS. 2B and 3B, grooves **150** are formed on the internal surface of the second substrate **140** where the scribing line **181** is formed, that is, on the second substrate **140** corresponding to the boundary between the non-pixel region **120b** of the first display panel **120** and the non-pixel region **130b** of the second display panel **130**. The grooves **150** are patterned by etching or polishing. In one embodiment, the grooves **150** may have a depth D of about 30% to about 50% of the thickness of the second substrate **140**. The grooves **150** may have a width W of about  $50\mu\text{m}$  to about  $100\mu\text{m}$ . The depth and width of the grooves **150** are limited to the extent that the strength of the second substrate **140** is not reduced.

Referring to FIGS. 2C and 3C, the frits **160** are applied on the internal surface of the second substrate **140** corresponding to the non-pixel regions **120b** and **130b** so that the pixel

regions **120a** and **130a** formed on the first substrate **110** are at least sealed up. That is, the frits **160** are formed outside the pixel regions of the plurality of display panels. In one embodiment, the frits **160** include a filler (not shown) for controlling a thermal expansion coefficient and an absorbent (not shown) that absorbs laser or infrared rays. In one embodiment, the frit may be obtained by adding oxide powders to glass powders. The temperature of the glass material is rapidly reduced to form the glass powders so that the frit is obtained. An organic material is added to the frit to create a gel-type paste. Then, when the frits **160** are annealed at a predetermined temperature, the organic material is removed and the gel-type frit paste is hardened so that the glass frits **160** are obtained. In one embodiment, the temperature at which the frits **160** are annealed is in the range of about 300° C. to about 700° C.

Then, the stiffeners **170** are formed on the second substrate **140** outside the frits **160**. The stiffeners **170** are further formed along the inner surface of the second substrate **140** in order to improve adhesion between the first substrate **110** and the second substrate **140**. In one embodiment, the stiffeners **170** are formed by screen printing or dispensing. In the screen printing method, a desired pattern is drawn on a metal sheet having a net or mesh structure. The sheet is selectively masked according to the pattern, using an emulsion solution. The stiffeners **170** are squeezed so that the desired pattern is printed on the second substrate **140**. In the dispensing method, the stiffeners **170** are drawn on the second substrate **140** by an apparatus having a nozzle to have a predetermined pattern and quantity.

Referring to FIGS. 2D and 3D, the first substrate **110** and the second substrate **140** are attached to each other and the stiffeners **170** are hardened by the infrared rays or heat. Then, the frits **160** are irradiated with the laser or infrared rays to be melted. Therefore, the first substrate **110** and the second substrate **140** are adhered to each other.

Referring to FIGS. 2E and 3E, a scribing process is performed using a scribing apparatus **180** so that the first substrate and the second substrate **140** that are attached to each other are divided into unit display panels. The scribing line **181** is formed by along a boundary between the non-pixel region **120b** of the first display panel **120** and the non-pixel region **130b** of the second display panel **130** and the grooves **150** are positioned on the inner side of the scribing line **181**.

Referring to FIGS. 2F and 3F, the plurality of display panels may be fabricated into the unit display panels **120** and **130** according to the above-described method. Then, after each unit display panel is cut off and washed, a driving integrated circuit is mounted on the first substrate **110** and a polarizer is attached to the second substrate **140**.

An organic light emitting device made by a method described above includes a first substrate, a second substrate generally opposing the first substrate, and an array of organic light emitting pixels interposed between the first and second substrates. In addition, a frit seal is interposed between the first and second substrates, surrounding the array. The organic light emitting display device may be a final product or a partially fabricated product.

FIG. 4 is an enlarged partial perspective view of a side of the second substrate **140a** in an organic light emitting device according to one embodiment. The second substrate may have an outer surface **141**, an inner surface **142**, and a plurality of sides **143** interconnecting the outer and inner surfaces **141**, **142**. In other embodiments, a side of the first substrate of the organic light emitting device may have the same structure as that shown in FIG. 4.

The side comprises two leveled surfaces **143a**, **143b**. The surfaces include a first surface **143a** and a second surface

**143b** connected to the first surface **143a** with a step or a slanted surface. Although the step on the side is depicted sharp in FIG. 4, it may be not as sharp as depicted. In addition, the surfaces **143a**, **143b** may not be as plain as shown in FIG. 4. The first and second surfaces **143a**, **143b** extend substantially parallel to each other. The first surface **143a** connects to the inner surface **142** of the second substrate **140a**, whereas the second surface **143b** connects to the outer surface **141** of the second substrate **140a**.

The first surface **143a** has a width **W1** extending in a direction interconnecting the outer and inner surfaces **141**, **142** of the second substrate **140a** in the shortest distance. In one embodiment, the width **W1** is between about 30% to about 50% of the thickness **T** of the second substrate **140a** in the direction. The first and second surfaces **143a**, **143b** may be at different levels by from about 5 μm to about 80 μm. A level difference **L** between the first and second surfaces **143a**, **143b** may be about 5 μm, about 10 μm, about 15 μm, about 20 μm, about 25 μm, about 30 μm, about 35 μm, about 40 μm, about 45 μm, about 50 μm, about 55 μm, about 60 μm, about 65 μm, about 70 μm, about 75 μm, and about 80 μm.

As described above, according to the embodiments, the grooves are formed on the internal side of the scribing line for scribing the mother substrate on which the plurality of display panels are formed into the unit display panels so that it is possible to easily perform the scribing process. That is, the scribing process is performed on the back of the substrate on which the grooves are formed so that it is possible to reduce the transmission length of the scribing crack. Therefore, the scribing section is uniformly scribed and the size of the scribed unit display panel is uniform.

Although a few embodiments have been shown and described, it would be appreciated by those skilled in the art that changes might be made in this embodiment without departing from the principles and spirit of the invention, the scope of which is defined in the claims and their equivalents.

What is claimed is:

1. An organic light emitting device, comprising:

a first substrate, wherein the first substrate comprises an outer surface and an inner surface;

a second substrate generally opposing the first substrate, wherein the second substrate comprises an outer surface and an inner surface;

two or more arrays of organic light emitting pixels interposed between the inner surfaces of the first and second substrates; and

two or more frit seals interposed between the first and second substrates, a first one of the frit seals surrounding a first one of the arrays, a second one of the frit seals surrounding a second one of the arrays, the first frit seal comprising a first elongated segment, the second frit seal comprising a second elongated segment, wherein the first and second elongated segments extend with a gap therebetween;

wherein at least one of the first and second substrates comprises a dividing groove on the inner surface thereof, the dividing groove being positioned along and within the gap between the first and second elongated segments.

2. The device of claim 1, wherein the second substrate comprises a substantially transparent material so as to pass visible light emitted from the organic light emitting pixels, and wherein the second substrate comprises the dividing groove.

3. The device of claim 2, wherein the second substrate comprises the dividing groove.

## 15

4. The device of claim 2, wherein the first substrate comprises the dividing groove.

5. The device of claim 1, wherein the dividing groove has a depth of about 30% to about 50% of the thickness of the substrate comprising the dividing groove.

6. The device of claim 1, wherein the dividing groove has a width between about 50  $\mu\text{m}$  and about 100  $\mu\text{m}$ .

7. The device of claim 1, wherein the first and second elongated segments extend substantially parallel to each other.

8. The device of claim 1, further comprising two or more reinforcing members interposed between and bonded to the first and second substrates, the two or more reinforcing members comprising a first reinforcing member and a second reinforcing member, wherein the first reinforcing member extends substantially parallel to the first elongated segment, and wherein the second reinforcing member extends substantially parallel to the second elongated segment.

9. The device of claim 8, wherein the first reinforcing member is positioned between the first elongated segment and the second elongated segment, and wherein the dividing groove is positioned between the first reinforcing member and the second elongated segment.

10. The device of claim 9, wherein the second reinforcing member is positioned between the first reinforcing member

## 16

and the second elongated segment, wherein the dividing groove is positioned between the first reinforcing member and the second reinforcing member.

11. The device of claim 8, wherein the reinforcing members comprise one or more selected from the group consisting of cyanoacrylate, acrylate, epoxy, and urethaneacrylate resin.

12. The device of claim 8, wherein the first elongated segment is positioned between the first reinforcing member and the second elongated segment, and wherein the dividing groove is positioned between the first elongated segment and the second elongated segment.

13. The device of claim 1, wherein the two or more frit seals comprise one or more materials selected from the group consisting of magnesium oxide ( $\text{MgO}$ ), calcium oxide ( $\text{CaO}$ ), barium oxide ( $\text{BaO}$ ), lithium oxide ( $\text{Li}_2\text{O}$ ), sodium oxide ( $\text{Na}_2\text{O}$ ), potassium oxide ( $\text{K}_2\text{O}$ ), boron oxide ( $\text{B}_2\text{O}_3$ ), vanadium oxide ( $\text{V}_2\text{O}_5$ ), zinc oxide ( $\text{ZnO}$ ), tellurium oxide ( $\text{TeO}_2$ ), aluminum oxide ( $\text{Al}_2\text{O}_3$ ), silicon dioxide ( $\text{SiO}_2$ ), lead oxide ( $\text{PbO}$ ), tin oxide ( $\text{SnO}$ ), phosphorous oxide ( $\text{P}_2\text{O}_5$ ), ruthenium oxide ( $\text{Ru}_2\text{O}$ ), rubidium oxide ( $\text{Rb}_2\text{O}$ ), rhodium oxide ( $\text{Rh}_2\text{O}$ ), ferrite oxide ( $\text{Fe}_2\text{O}_3$ ), copper oxide ( $\text{CuO}$ ), titanium oxide ( $\text{TiO}_2$ ), tungsten oxide ( $\text{WO}_3$ ), bismuth oxide ( $\text{Bi}_2\text{O}_3$ ), antimony oxide ( $\text{Sb}_2\text{O}_3$ ), lead-borate glass, tin-phosphate glass, vanadate glass, and borosilicate.

\* \* \* \* \*

专利名称(译)	母基板单元的有机发光显示器及其制造方法		
公开(公告)号	<a href="#">US8803162</a>	公开(公告)日	2014-08-12
申请号	US11/540066	申请日	2006-09-29
[标]申请(专利权)人(译)	李浩SEOK KWAK WON KYU		
申请(专利权)人(译)	李浩SEOK KWAK WON KYU		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE HO SEOK KWAK WON KYU		
发明人	LEE, HO SEOK KWAK, WON KYU		
IPC分类号	H01L27/15 H01L51/52		
CPC分类号	H01L51/5237 H01L2251/566 H01L51/5246		
优先权	1020060008806 2006-01-27 KR		
其他公开文献	US20070176185A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

一种母基板单元有机发光显示器，其中在形成划线的内表面上形成凹槽，以在其上形成多个显示板的母基板划线成单元显示板，从而容易进行划线处理，并且公开了一种制造它的方法。母基板单元有机发光显示器包括：第一基板，包括多个显示面板；以及划线，限定在显示面板之间，使得每个显示面板包括像素区域，在该像素区域中包括第一电极的有机发光二极管（OLED）形成有机层和第二电极以及非像素区域，第二基板布置在第一基板上以与第一基板重叠并且在其上形成凹槽以对应于划线，并且多个在第一基板和第二基板之间提供的玻璃料沿着像素区域的圆周形成。第一基板和第二基板通过多个玻璃料彼此附接。

