



US 20020149313A1

(19) **United States**

(12) **Patent Application Publication**

Yonekura et al.

(10) **Pub. No.: US 2002/0149313 A1**

(43) **Pub. Date: Oct. 17, 2002**

(54) **ORGANIC EL DISPLAY AND PRODUCTION
DEVICE OF COLOR FILTER**

(52) **U.S. Cl. 313/500**

(76) Inventors: **Seiji Yonekura**, Hitachi (JP);
Yoshinobu Fukano, Tsuchiura (JP);
Mamoru Okano, Hitachi (JP); **Yasuo
Imanishi**, Hitachi (JP); **Sukekazu
Aratani**, Hitachiota (JP); **Yoshiharu
Nagae**, Hitachi (JP)

(57)

ABSTRACT

This invention provides a production device of organic EL display which can form uniform organic light emitting layer for red-, green- and blue-colored light evenly and in a high reliability for every pixel and can make a full color display.

Correspondence Address:
**ANTONELLI TERRY STOUT AND KRAUS
SUITE 1800
1300 NORTH SEVENTEENTH STREET
ARLINGTON, VA 22209**

(21) Appl. No.: **10/105,336**

(22) Filed: **Mar. 26, 2002**

Foreign Application Priority Data

Mar. 29, 2001 (JP) 2001-094556

Publication Classification

(51) Int. Cl.⁷ **H05B 33/00**

The device of this invention has a means 7 for storing a solution 6 in which a light emitting material is dissolved, a means for feeding the solution to a tip 3-1 of a flying electrode, a means for applying a voltage between the tip of the flying electrode and an electrically conductive material of an organic EL substrate and thereby forming an electrostatic field, and a means for relatively shifting the tip of the flying electrode and the organic EL substrate to a perpendicular direction and to a horizontal direction, and is so constructed that the solution is formed into the form of a stringy beam from the tip of the flying electrode to let it fly onto the organic EL substrate, thereby injecting the solution into a concavity formed and surrounded by banks on the organic EL substrate, and forming red, green and blue light emitting layers.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12





FIG. 13



ORGANIC EL DISPLAY AND PRODUCTION DEVICE OF COLOR FILTER

FIELD OF THE INVENTION

[0001] This invention relates to an organic EL (electroluminescence) display forming light-emitting layers capable of making a full color display, and to a device for production of a color filter.

BACKGROUND OF THE INVENTION

[0002] An organic EL element is an element constituted of a thin film containing a fluorescent organic compound, said film being held between a cathode and an anode. When an electron and a hole are injected into the thin film and recombined, an exciton is formed, and upon de-activation of the exciton, a light (fluorescent light or phosphorescent light) is emitted from the element.

[0003] Characteristic feature of the organic EL element consists in that it can emit a surface light having so high luminance as 100 to 100,000 cd/m² at a low voltage of 10 V or less, and it can emit a light ranging from blue color to red color by selecting the kind of fluorescent material.

[0004] In WO 99/48339, there is disclosed a technique of forming a full color display type organic EL display by subjecting an organic EL material which has so far been considered impossible to pattern to an ink jet process (the piezo jet process and the process of discharging the material by the action of thermally caused bubble formation).

[0005] However, the above-mentioned WO 99/48339 makes no mention about the means for letting fly an organic EL material against fine pixels and the method for improving the reliability by giving a flying drop shape necessary for forming a uniform organic light emitting layer and preventing the clogging of ink jet nozzle.

SUMMARY OF THE INVENTION

[0006] For letting an organic EL material fly by the ink jet process, it is necessary to dissolve the organic EL material in a solvent to form a dilute solution so that the drops can fly.

[0007] Further, for vaporizing off the solvent after flying of the solution and thereby forming an organic light-emitting layer, it is also necessary that the solvent used has a high volatility.

[0008] However, in the hitherto adopted piezo driving ink jet process or the discharging process by the thermally caused bubble formation, the nozzle has to have a small diameter at the ink jet head in order to make small the flying quantity of organic EL material solution so as to match with the fineness of pixel. As its result, a solvent of high volatility dries up at the tip of nozzle to cause clogging of the nozzle.

[0009] Further, it has been difficult in the ink jet process (the piezo jet process and the discharging process by thermally caused bubble formation) to form a uniform organic light-emitting layer because, in the ink jet process, the solution of organic EL material flies in the form of fine dots and a pixel is formed as an assembly of the dots.

[0010] This invention aims at solving the problems mentioned above, and the object thereof is to provide a production device of organic EL display capable of making a full

color display by patterning red-, green- and blue-colored uniform organic light emitting layers at every pixel in a high reliability by the action of an electrostatic field. A further object of this invention is to provide an organic EL display which is uniform and free from color mixing, by the use of said production device.

[0011] According to one embodiment of the present invention, the device for producing an organic EL display of this invention has a means for storing a solution in which a light emitting material is dissolved, a means for feeding the solution to a tip of a flying electrode, a means for applying a voltage between the tip of the flying electrode and an electrically conductive material of an organic EL substrate and thereby forming an electrostatic field, and a means for relatively shifting the tip of the flying electrode and the organic EL substrate to a perpendicular direction and to a horizontal direction, and is so constructed that the solution is formed into the form of a stringy beam from the tip of the flying electrode to let it fly onto the organic EL substrate, thereby injecting the solution into a concavity formed and surrounded by banks on the organic EL substrate, and forming red, green and blue light emitting layers.

[0012] Additionally, a thickness of the stringy beam of the solution can be varied by controlling the electrostatic field.

[0013] Meanwhile, the stringy beam referred to herein shows a state that a solution outgone from a tip of 3-1 of the flying electrode, for example at shown at FIG. 1, is reaching the organic EL display 1 at successive state at least at one point, and the stringy beam is different from an ink in the form of dots emitted in the case of the ink jet process for printing characters etc.

[0014] Further, the amount of injection of the solution can be varied by controlling a velocity of relatively shifting the tip of the flying electrode and the organic EL substrate to a perpendicular direction.

[0015] Further, said means for forming an electrostatic field can be formed by applying a voltage obtained by in-series overlapping a pulse voltage on a direct current voltage of bias and said stringy beam can be intermittently cut by controlling the electrostatic field.

[0016] Further, said solution can be injected into a concavity formed and surrounded by the bank and, after vaporizing off the solvent, the injection of the solution can be repeated additionally.

[0017] Further, said device can have a plurality of the flying electrodes.

[0018] According to another embodiment of the present invention, the device for producing a color filter of the present invention has a means for storing a solution in which a light transmitting material is dissolved, a means for feeding said solution to a tip of a flying electrode, a means for applying a voltage between the tip of a flying electrode and an electro-conductive material of a color filter substrate and thereby forming an electrostatic field, and a means for relatively shifting the tip of the flying electrode and the color filter substrate to a perpendicular direction and to a horizontal direction, wherein said solution is formed into the form of a stringy beam to let it fly onto the color filter substrate, thereby injecting the solution into a concavity

formed and surrounded by a black matrix on the color filter substrate, and forming red, green and blue light transmitting layers.

[0019] According to another embodiment of the present invention, the organic EL display of the present invention has a bank for partitioning pixels, wherein the partitioning by the bank exists only between pixels of different colors.

[0020] Further, according to another embodiment of the present invention, the organic EL display of the present invention has on a substrate a display portion composed of a plurality of pixels, wherein an electrode corresponding to each of the pixels is arranged to the plurality of pixels, and wherein, on the electrode corresponding to each of the pixels on the substrate, a light emitting layer of same color is arranged in the same layer over the plurality of pixels.

[0021] Other objects, features and advantages of the invention will become apparent from the following description of the embodiments of the invention taken in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0022] FIG. 1 is a cross-sectional view illustrating the production device of the organic EL display of this invention.

[0023] FIG. 2 is an enlarged view of FIG. 1 in the direction of P.

[0024] FIG. 3 is a diagram illustrating the disposition of the color display part of the organic EL display in FIG. 1.

[0025] FIG. 4 is a view illustrating the a-a' cross section of the organic EL display of FIG. 3 and the b-b' cross section of the organic EL display of FIG. 6.

[0026] FIG. 5 is a view illustrating the c-c' cross section of the organic EL display of FIG. 3.

[0027] FIG. 6 is a view illustrating the disposition of the color display part of the organic EL display according to another example.

[0028] FIG. 7 is a view illustrating the d-d' cross section of the organic EL display of FIG. 6.

[0029] FIG. 8 is a view illustrating the d-d' cross section of the organic EL display of FIG. 6 after the cathode formation.

[0030] FIG. 9 is a schematic view illustrating an image displaying device using the organic EL display of FIG. 8.

[0031] FIG. 10 is a cross-sectional structural view of a color filter.

[0032] FIG. 11 is a cross-sectional view illustrating the production device of an organic EL display according to another example.

[0033] FIG. 12 is a cross-sectional structural views of FIG. 11.

[0034] FIG. 13 is a cross-sectional structural view of FIG. 12.

EXPLANATION OF THE SYMBOLS

[0035] 1—organic EL display, 2—solution flying device, 3—flying electrode, 3-1—tip of flying electrode, 4—elec-

trode holder, 5—voltage applying circuit, 6—solution, 6-1—solution beam, 7—container, 8—solution transporting path, 9—electro-conductive material, 11—bank, 12—insulating layer (SiO_2), 13—electro-conductive layer, 14—transparent electrode, 15—glass substrate, 20—cathode, 31—flying electrode, 31-1—tip of flying electrode, 32—control electrode, 32-1 tip of control electrode, 33—glass substrate, 33-1—tip of glass substrate, 34—resin film, 35—insulating protective film, 36—resin film, 37—solution feeding path, 38—resin film, 39—solution feeding hole, 40—cover, 41—solution recovering member, 42—minute gap, 50—voltage applying circuit, 61—organic EL display, 62 display part, 63—data driving circuit, 64—scanning circuit, 65—electric current supply circuit, 66—substrate, 67—data line, 68—gate line, 69—common electrode, 70—electric current supply line, 100—color filter, 110—black matrix, 130—ITO transparent electrode, 150—glass substrate.

DETAILED DESCRIPTION OF THE INVENTION

[0036] FIG. 1 illustrates one embodiment of the production device of the organic EL display of this invention.

[0037] In FIG. 1, 1 is an organic EL display, 2 is a solution flying device, 3 is a flying electrode, 4 is an electrode holder, 5 is a voltage applying circuit, 6 is a solution in which a light-emitting material is dissolved, 7 is a container, and 8 is a solution transporting path.

[0038] The flying electrode 3 is made of an electro-conductive metal. For example, it is a stainless pipe having an inner diameter of 150-250 μm . The flying electrode tip 3-1 has a sharp pointed shape, and is held so as to keep a narrow gap g from the organic EL display 1.

[0039] To the flying electrode tip 3-1 is fed the solution 6 from container 7 made of glass or the like through a solution transporting path 8 made of Teflon tube or the like.

[0040] A direct current high voltage of about 1.5-3 kV is applied to the voltage applying circuit 5 in the above-mentioned state, whereby a high electrostatic field can be formed between the flying electrode tip 3-1 and the electro-conductive material 9 via the electrode holder 4 made of an electro-conductive metal.

[0041] Herein, the solution 6 is a solution of a light-emitting material such as PPV (polyparaphenylenevinylene) derivative in a high electric resistance solvent such as xylene or the like, and its electric resistance is preferably $10^7 \Omega\cdot\text{cm}$ or more, and its surface tension is preferably 30 mN/m or less.

[0042] Due to formation of the above-mentioned high electrostatic field, the solution 6 flies from the flying electrode tip 3-1 toward the organic EL display 1.

[0043] As a method for feeding the solution 6 to the tip 3-1 of the flying electrode, the present example maintains a state that the solution is usually fed to the tip 3-1 of the flying electrode by arranging the liquid surface of the solution in container 7 at a position above the flying electrode tip 3-1. The flying (outgoing) of solution can be retained by thus feeding the solution 6 to the flying electrode tip 3-1 so far as an application of a high voltage to the voltage applying circuit 5 are continued.

[0044] In the example of **FIG. 1**, the organic EL display **1** is placed perpendicularly, the flying electrode **3** is placed horizontally, and the flying direction of the solution **6** is fixed downward. It is also possible, however, to place the organic EL display **1** upward, the flying electrode **3** downward, and the flying direction of solution **6** downward. Further, it is also possible to make fly the solution **6** in an oblique direction from the viewpoint of overall layout of the device.

[0045] **FIG. 2** is an expanded view from P direction of the neighborhood of flying electrode **3** of **FIG. 1**. The solution **6** supplied to tip **3-1** of the flying electrode forms a stringy solution beam **6-1** stretched in the direction of arrow A from the flying electrode tip **3-1** to the organic EL display **1** due to the electrostatic field between flying electrode tip **3-1** and electro-conductive material **9**, and continuously flies.

[0046] Accordingly, by shifting the organic EL display **1** and the flying electrode tip **3-1** relatively to each other in the direction of arrow B, a straight line of solution **6** can continuously be pictured on the surface of organic EL display **1**, and thereby the solution **6** can be injected into surface of the organic EL display **1**. By varying the velocity of the shifting, the amount of solution **6** injected can be controlled.

[0047] Among the means for forming the electrostatic field of **FIG. 1**, control of the direct current voltage applied to the voltage applying circuit **5** or control of the gap **g** is useful for varying thickness of the stringy solution beam **6-1**.

[0048] It is also possible to control the amount of injected solution **6-1** into the organic EL display **1** by in-series applying a pulse voltage (not shown in the drawing) to the voltage applying circuit **5** of **FIG. 1** in addition to the above-mentioned direct current voltage, and so as to cut the stringy solution beam **6-1** of **FIG. 2** intermittently.

[0049] It is also possible to cut the stringy solution beam **6-1** of **FIG. 2** intermittently by lowering the direct current voltage applied to the voltage applying circuit **5** of **FIG. 1**.

[0050] **FIG. 3** illustrates one example of the color display disposition of the organic EL display **1**, wherein **1-R** is red-colored pixel, **1-G** is green-colored pixel, and **1-B** is blue-colored pixel. A full color display pixel **1-1** is constructed by summarizing the pixels of red, green and blue colors.

[0051] The size of full color display pixel **1-1** varies depending on the display density. For example, the size is $127 \mu\text{m} \times 127 \mu\text{m}$ in the case of 200 PPI (pixel/inch), and $254 \mu\text{m} \times 254 \mu\text{m}$ in the case of 100 PPI. It follows that width **W** of each display element (red, green and blue) is about $30 \mu\text{m}$ in the case of 200 PPI and about $60 \mu\text{m}$ in the case of 100 PPI, and the length **L** is about $120 \mu\text{m}$ in the case of 200 PPI and about $240 \mu\text{m}$ in the case of 100 PPI. The gaps **C1** and **C2** between the red, green and blue pixels are about $10 \mu\text{m}$ in the case of 200 PPI and about $20 \mu\text{m}$ in the case of 100 PPI.

[0052] Solution **6** can be filled into red colored pixels by shifting the flying electrode **3** of **FIG. 1** in the direction of arrow **V** relatively to the organic EL display **1** shown in **FIG. 3**.

[0053] Solution **6** can easily be filled into fine pixels while varying thickness of the stringy solution beam **6-1** of **FIG. 2** in accordance with the width **W**.

[0054] Further, since the display pixels into which the solution **6** is to be filled are as fine as have been mentioned above, the influence of capillary phenomenon can overpass gravity of solution **6**, so that solution **6** can be filled into any of horizontally disposed organic EL display **1** and upward disposed organic EL display **1**.

[0055] At this time, a surplus adhesion of the solution to the gap **C2** part can be prevented by stopping the application of high voltage from the voltage application circuit **5** of **FIG. 1** or by lowering the input voltage to stop the flying of solution **6** only in the areas corresponding to gap **C2**. Needless to say, it is also possible to continue the flying of solution **6** without stopping the flying. After the filling into the flying row **1-R** has been completed, the flying electrode **3** of **FIG. 1** is shifted to the next row of pixel **2-R** for red-colored display, in the direction of arrow **H** relatively to the organic EL display **1** shown in **FIG. 3**.

[0056] Subsequently, the flying electrode **3** of **FIG. 1** is shifted in the direction opposite to the direction of arrow **V**, relatively to the organic EL display **1** shown in **FIG. 3**, and the solution **6** is filled into the red-colored display pixel row **2-R**.

[0057] By repeating the above-mentioned procedures, solution **6** is filled into all the red-colored display pixels on the organic EL display **1**. In the same manner as above, solution **6** can be filled into green-colored pixels **1-G**, **2-G** and blue-colored pixels **1-B**, **2-B**, too.

[0058] Needless to say, it is also possible to achieve a similar filling of solution **6** by shifting the organic EL display **1** while fixing the flying electrode **3**.

[0059] From the viewpoint of improving the productivity, it is desirable to dispose individual solution flying devices **2** for red, green and blue colors of **FIG. 1** in parallel to one another and carry out the flying simultaneously.

[0060] Further, it is desirable from the viewpoint of further improving the productivity to dispose a plurality of flying electrodes **3** in parallel in the solution flying device **2** of **FIG. 1**, and to carry out the flying simultaneously. Especially, productivity can further be improved by making the flying electrodes **3** into a line in accordance with the size of organic EL display **1**.

[0061] **FIG. 4** illustrates the a-a' cross-sectional structure of the organic EL display **1** of **FIG. 3**, wherein **11** is a bank, **12** is an insulating layer made of SiO_2 or the like, **13** is an electro-conductive layer which is a positive pore-injecting layer, **14** is a transparent electrode, **15** is a glass substrate, **1-R** is a red-colored light emitting layer, **1-G** is a green-colored light emitting layer, and **1-B** is a blue-colored light emitting layer. The insulating layer **12** may be omitted. As the transparent electrode **14**, ITO (indium tin oxide), IZO (indium zinc oxide), and the like are used. In a case of using a structure of withdrawing the light from the upper part, it is also possible to use an opaque electrode made of a metal such as Cr, Al or the like.

[0062] The same earthing effect as that brought about by the earthing of electro-conductive material **9** of **FIG. 1** can be obtained by earthing each of the transparent electrodes **14** for each of the display pixels while maintaining the transistors (not shown in the figure) for driving each of the display pixels. Needless to say, it is also possible to dispose an

electro-conductive material **9** for earthing in the organic EL display or under the glass substrate **15**, besides the transparent electrode **14**.

[0063] Bank **11** is constituted of a low dielectric constant material such as polyimide resin or the like, and its thickness **C1** is as depicted by the **C1** of the above-mentioned **FIG. 3**. Its height **h** is 2-10 μm , and its **W** is as shown by the **W** in the above-mentioned **FIG. 3**. Solution **6** is filled into the concavity surrounded by bank **11** by the use of the above-mentioned solution flying device **2**, after which the high-volatility solvent such as xylene or the like is vaporized off to form red-colored light emitting layer **1R**, green-colored light emitting layer **1G** and blue-colored light emitting layer **1B** all having a thickness of 50-100 nm. Needless to say, the solution **6** can be filled in the same manner as above and the same effect as above can be exhibited not only in the above-mentioned case of forming a three-colors light emitting layer but also in the cases of forming two-colors or one-color light emitting layer.

[0064] Herein, it is important to make small the surface roughness of each light emitting layer in order to improve the light-emitting characteristics. Surface roughness of each light-emitting layer can be made small by continuously injecting the solution by the use of the above-mentioned solution flying device **2**.

[0065] After injecting the solution **6** into the concavity surrounded by bank **11** by the use of solution flying device **2** and vaporizing off the high-volatility solvent, the injection of solution **6** is repeated additionally, whereby surface roughness of each light-emitting layer can be made smaller. Since the method of the repeated injection makes it possible to reduce the amount of solution **6** injected at once, such a method is effective for lowering the height **h** of bank **11** shown in **FIG. 4** and lessening the thickness of organic EL substrate.

[0066] **FIG. 5** illustrates the **c-c'** cross-sectional structure of the organic EL display **1** of **FIG. 3**. In the organic EL display **1** of this example, bank **11** exists between the pixels even in the direction **c-c'**. Accordingly, if solution **6** is let fly continuously, the solution collide against the bank **11** present between pixels and is scattered to cause a color mixing and an unevenness in the thickness of light emitting layer between pixels and a thereby caused uneven display.

[0067] **FIG. 6** illustrates another example of the organic EL display. In this example, the red-colored light emitting layer **1-R'**, green-colored light emitting layer **1-G'** and blue-colored light emitting layer **1-B'** in the range of full color pixel **1-1** are continuously extended to the full color display pixel **1-2** without partitioning with bank **11** and further prolonged until they reach the maximum length or the whole dimension of organic EL display **1**. By shifting the flying electrode tip **3-1** of **FIG. 1** in the direction of arrow **V**, injection of solution **6** becomes possible and the above-mentioned effect of continuous flying of solution **6** can be enhanced. By shifting the flying electrode tip **3-1** in the direction of arrow **H**, solution **6** can be injected into the ranges of red-colored light emitting layer **2-R'**, green-colored light emitting layer **2-G'** and blue-colored light emitting layer **2-B'**. Herein, the transparent electrode **14** shown in **FIG. 4** and the driving transistors (not shown in the figure) are disposed for individual colors of display pixel units. That is to say, the cross section **b-b'** of **FIG. 6** is the same as that

in **FIG. 4**. The dimension **W** and **C1** in **FIG. 6** are the same as the dimension **W** and **C1** in **FIG. 3**. **FIG. 7** illustrates the **d-d'** cross-sectional structure of **FIG. 6**. In the organic EL display of this example, no bank exists between pixels in the direction of **d-d'**, and the solution **6**, if made to fly continuously, does not collide with the bank and is not scattered. Thus, no color mixing nor uneven display caused by unevenness in thickness of light emitting layers between pixels occurs in this case, unlike in the preceding example.

[0068] After forming light emitting layers, a cathode **20** is formed and its upper part is sealed by the use of a sealing can to obtain an organic EL display, as seen in the cross-sectional view of **FIG. 8**. In cases where light is to be withdrawn from the upper part, an opaque electrode is formed in place of the transparent electrode **14** of this example, and a charge injecting layer and a transparent layer are formed after formation of the light emitting layer and a transparent sealing can is used, whereby an organic EL display making it possible to take out light from its upper part can be obtained.

[0069] That is, the organic EL display obtained by the above example is an organic EL display having on a substrate a display portion composed of a plurality of pixels, wherein an electrode corresponding to each of the pixels is arranged to the plurality of pixels, and wherein, on the electrode corresponding to each of the pixels on the substrate, a light emitting layer of same color is arranged in the same layer over the plurality of pixels.

[0070] Due to such constitutions, in case light emitting layers of same color are arranged in neighboring pixels, since it is a constitution that no bank is arranged between the neighboring pixels, it can avoid a color mixing due to a collision and scattering of the bank and an uneven display caused by unevenness in thickness of light emitting layers between pixels.

[0071] **FIG. 9** is a schematic view of an image display device using the organic EL display of this example. In the image display device **61**, the nearly central part of substrate **66** functions as a display part **62**. A data driving circuit **63** outputting image signals to the data line **67** is provided over the display part **62**, a scanning circuit **64** outputting the scanning signals to the gate line **68** is provided in the left side, and a current feeding driving circuit **65** is provided in the right side. These driving circuits **63**, **64**, **65** are constituted of a shift resistor circuit constituted of a complementary circuit made from N-channel type and P-channel type of TFT, a level shifter circuit, an analogue switch circuit, etc.

[0072] The use of the above-mentioned solution flying device **2** is not restricted to the production of organic EL display, but it can be applied to other devices, too. One example of said other device is shown in **FIG. 10**, which is a structural cross-sectional view of a color filter produced by the use of the solution flying device **2** shown in **FIG. 1**, in which the organic EL device **1** is replaced by a color filter.

[0073] In **FIG. 10**, **10-R**, **10-G** and **10-B** are a red, green and blue color filter, respectively, **150** is a glass substrate, **130** is a transparent electrode, and **110** is a black matrix made of a resin. A red filter **10-R**, a green filter **10-G** and a blue filter **10-B** are constructed in the concavity partitioned by black matrix **110**. In the solution flying device **2** of **FIG. 1**, solution **6** is a solution prepared by dissolving light-

transmitting pigments or light-transmitting dyes of red, green and blue color in a solvent having a high electric resistance such as isoparaffin, and its electric resistance and surface tension are preferably equal to those used in the organic EL display. A high voltage is applied between the tip 3-1 of flying electrode of **FIG. 1** and the ITO transparent electrode 130 of **FIG. 6** to make fly a stringy solution beam 6-1 and inject the beam into the above-mentioned concavity, whereby a red filter 10-R, a green filter 10-G and a blue filter 10-2 are formed.

[0074] By such a procedure, there is provided a production device of color filter which can form a color filter constituted of a red filter 10-R, a green filter 10-G and a blue filter 10-B in the same dimensions as in **FIG. 3** and **FIG. 6** in high uniformity. Since this device uses no fine nozzles, the color filter thus obtained has a high reliability due to freeness from clogging of fine nozzle.

[0075] **FIG. 11**, **FIG. 12** and **FIG. 13** illustrate the solution flying device 2 of **FIG. 1**. These are outlined structural diagrams according to another example. **FIG. 11** is a top plan cross-sectional view of the solution flying device. **FIG. 12** is an a-a' cross-sectional view of **FIG. 11**. **FIG. 13** is a b-b' cross-sectional view of **FIG. 12**. The flying electrode 31 and control electrode 32 are formed by hot contact-bonding a resin film (for example, a negative type photosensitive resin film) 34 of a low dielectric constant material (specific permittivity 3 or less) on a glass substrate 33, vapor depositing a metallic film thereon, and carrying out a photolithographic wet etching. The tip 31-1 of the flying electrode is protruded from the terminal surface of glass substrate 33. The tip of flying electrode 31-1 has a sharp pointed angle and such tips are disposed in parallel to one another at constant intervals as shown in **FIG. 11**. Further, the flying electrode 31 and control electrode 32 are coated with an insulating protective film 35. On the other hand, the tip 32-1 of control electrode is placed at a position which is retrograde from the tip 31-1 of flying electrode and protruded from the terminal surface of glass substrate 33. The control electrodes 32 are disposed at constant intervals between the flying electrodes 31.

[0076] Since the tip 32-1 of control electrode is covered with a low dielectric constant resin film 34 through inter-mediation of insulating protective film 35 and is protruded, it plays a role of mechanically intercepting the solution meniscus between the adjacent flying electrodes 31 and a role of intercepting an interference of the electric field between the adjacent flying electrodes 31 and, at the same time, it makes it possible to fly the solution evenly with a lessened influence of the adjacent flying electrodes 31 such as bending of flying solution beam and unevenness of thickness. In order to make more efficient the action of mechanically intercepting the solution meniscus between adjacent flying electrodes 31, it is desirable to make the heights of the tip of control electrode equal to or greater than the height h of the solution path.

[0077] The tip of control electrode is made of a dielectric resin and so constructed as to cover the tip of a metallic control electrode and protrude from the terminal surface of glass electrode 33. Needless to say, the same effect as above can be achieved by forming a similar shape only from a metallic control electrode.

[0078] As shown at **FIGS. 12** and **13**, by subjecting a resin film 36 of low dielectric constant material (for

example, negative type photosensitive resin film) which has been hot contact bonded onto insulating protective film 35 to a lithographic wet etching, the solution feeding path 37 in the solution flying device 2 is formed over and along the flying electrode 31.

[0079] Subsequently, a resin film of low dielectric constant material (for example, a negative type photosensitive resin film) 3B is put on the solution feeding path 37, and hot contact bonded onto the above-mentioned dielectric resin film 36 to close the solution feeding path 37 tightly, after which the solution feeding hole 39 is formed by wet etching. Then, cover 40 is bonded onto the low dielectric constant resin film 38. Thus, it becomes possible to supply the solution 6 to the solution feeding path 37.

[0080] As shown in **FIG. 11**, the solution feeding path 37 is formed along the flying electrode 31, to which is supplied the solution 6 in the direction of arrow, and the solution supplied flows toward the tip 31-1 of the flying electrode.

[0081] In **FIGS. 11** and **13**, three flying electrodes 31 and four control electrodes 32 are pictured for convenience. It is needless to say, however, that numbers of flying electrodes 31 and control electrodes 32 can be varied in the range of from several tens to several thousands in accordance with the use of solution flying device 2 by alternately disposing a flying electrode 31 and a control electrode 32, and a multi-channel type solution flying device and a line type solution flying device can be constructed based on the same idea as above.

[0082] In this state, a voltage is input on each of the flying electrodes 31 by means of the voltage applying circuit 50. The content of the solution is the same as has been mentioned above. Thus, by applying a voltage from the voltage applying circuit 50 of **FIG. 11**, an electric field is formed between the earthed electro-conductive material 9 and the organic EL display 1, and solution 6 becomes able to fly in the form of solution beam 6-1.

[0083] It is also possible to provide another voltage applying circuit (not shown in the figure) for applying a voltage lower than an applied voltage of voltage applying circuit 50 to each of the flying electrodes 31 in series with the voltage applying circuit 50 in a state that a voltage from the voltage applying circuit 50 is applied to each of the control electrodes 32, in order to control the flying of solution beam 6-1 from the tip of 31-1 of each flying electrode by on/off change of said another applying circuit.

[0084] Next, the structure for recovering the residual solution after the flying of solution will be explained by referring to **FIG. 12** and **FIG. 13**. A minute gap 42 having a constant dimension g is provided between the tip 33-1 of a glass substrate having a sloped surface in the side closer to the flying electrode and the solution recovering member 41. The above-mentioned residual solution can be recovered into the solution recovering path 43 formed of the solution recovering member 41 and the sloped glass substrate 33, downward the tip 31-1 of flying electrode, at an angle crossing with the direction of the flying electrode tip 31-1, along the terminal surface 33-1 of glass electrode.

[0085] It should be further understood by those skilled in the art that the foregoing description has been made on embodiments of the invention and that various changes and

modifications may be made in the invention without departing from the spirit of the invention and the scope of the appended claims.

EFFECTS OF THE INVENTION

[0086] According to the production device of organic EL display capable of making a full color display of this invention, there can be provided a production device capable of forming a uniform light emitting layer and free from clogging of nozzles, and there can be provided an organic EL display which is uniform and free from color mixing.

What is claimed is:

1. A device for producing an organic EL display having;
 - a means for storing a solution in which a light emitting material is dissolved,
 - a means for feeding said solution to a tip of a flying electrode,
 - a means for applying a voltage between the tip of the flying electrode and an electro-conductive material of an organic EL substrate and thereby forming an electrostatic field, and
 - a means for relatively shifting the tip of the flying electrode and the organic EL substrate to a perpendicular direction and to a horizontal direction, wherein said solution is formed into the form of a stringy beam from the tip of the flying electrode to let it fly onto the organic EL substrate, thereby injecting the solution into a concavity formed and surrounded by banks on the organic EL substrate, and forming red, green and blue light emitting layers.
2. The device for producing an organic EL display according to claim 1, wherein a thickness of the stringy beam of the solution is varied by controlling the electrostatic field.
3. The device for producing an organic EL display according to claim 1, wherein the amount of injection of the solution is varied by controlling a velocity of relatively shifting the tip of the flying electrode and the organic EL substrate to a perpendicular direction.
4. The device for producing an organic EL display according to claim 1, wherein said means for forming an

electrostatic field is formed by applying a voltage obtained by in-series overlapping a pulse voltage on a direct current voltage of bias and said stringy beam is intermittently cut by controlling the electrostatic field.

5. The device for producing an organic EL display according to claim 1, wherein said solution is injected into a concavity formed and surrounded by the bank and, after vaporizing off the solvent, the injection of the solution is repeated additionally.

6. The device for producing an organic EL display according to claim 1, wherein said device has a plurality of the flying electrodes.

7. A device for producing a color filter having:

- a means for storing a solution in which a light transmitting material is dissolved,
- a means for feeding said solution to a tip of a flying electrode,
- a means for applying a voltage between the tip of a flying electrode and an electro-conductive material of a color filter substrate and thereby forming an electrostatic field, and
- a means for relatively shifting the tip of the flying electrode and the color filter substrate to a perpendicular direction and to a horizontal direction,

wherein said solution is formed into the form of a stringy beam to let it fly onto the color filter substrate, thereby injecting the solution into a concavity formed and surrounded by a black matrix on the color filter substrate, and forming red, green and blue light transmitting layers.

8. An organic EL display having a bank for partitioning pixels, wherein the partitioning by the bank exists only between pixels of different colors.

9. An organic EL display having on a substrate a display portion composed of a plurality of pixels, wherein an electrode corresponding to each of the pixels is arranged to the plurality of pixels, and wherein, on the electrode corresponding to each of the pixels on the substrate, a light emitting layer of same color is arranged in the same layer over the plurality of pixels.

* * * * *

专利名称(译)	有机EL显示器和滤色器的生产装置		
公开(公告)号	US20020149313A1	公开(公告)日	2002-10-17
申请号	US10/105336	申请日	2002-03-26
[标]申请(专利权)人(译)	米仓SEIJI 深野庆喜 冈野MAMORU 今西康夫 荒谷SUKEKAZU 永江义治		
申请(专利权)人(译)	米仓SEIJI 深野庆喜 冈野MAMORU 今西康夫 荒谷SUKEKAZU 永江义治		
当前申请(专利权)人(译)	米仓SEIJI 深野庆喜 冈野MAMORU 今西康夫 荒谷SUKEKAZU 永江义治		
[标]发明人	YONEKURA SEIJI FUKANO YOSHINOBU OKANO MAMORU IMANISHI YASUO ARATANI SUKEKAZU NAGAE YOSHIHARU		
发明人	YONEKURA, SEIJI FUKANO, YOSHINOBU OKANO, MAMORU IMANISHI, YASUO ARATANI, SUKEKAZU NAGAE, YOSHIHARU		
IPC分类号	H05B33/10 B05B5/025 H01L27/32 H01L51/00 H01L51/40 H01L51/56 H05B33/00		
CPC分类号	B05B5/0255 H01L27/3211 H01L51/56 H01L51/0005 H01L51/0004		
优先权	2001094556 2001-03-29 JP		
其他公开文献	US6776844		
外部链接	Espacenet USPTO		

摘要(译)

本发明提供一种有机EL显示器的制造装置，其能够均匀且高可靠性地为每个像素形成均匀的红色，绿色和蓝色光的有机发光层，并且可以进行全色显示。本发明的装置具有用于存储其中溶解有发光材料的溶液6的装置7，用于将溶液供给到飞电极的尖端3-1的装置，用于在尖端之间施加电压的装置。飞电极和有机EL基板的导电材料由此形成静电场，以及用于使飞电极和有机EL基板的尖端相对于垂直方向和水平方向相对移动的装置，并且是这样的这种解决方案形成为从飞电极尖端形成的束状光束形式，使其飞到有机

EL基板上，从而将溶液注入由有机EL基板上的堤形成并包围的凹面中，
并形成红色，绿色和蓝色发光层。

