



US008513669B2

(12) **United States Patent**  
**Park et al.**

(10) **Patent No.:** **US 8,513,669 B2**  
(45) **Date of Patent:** **Aug. 20, 2013**

(54) **THIN FILM TRANSISTOR INCLUDING METAL OR METAL SILICIDE STRUCTURE IN CONTACT WITH SEMICONDUCTOR LAYER AND ORGANIC LIGHT EMITTING DIODE DISPLAY DEVICE HAVING THE THIN FILM TRANSISTOR**

6,087,206 A 7/2000 Hamada  
6,191,449 B1 2/2001 Shino  
6,380,007 B1 4/2002 Koyama  
6,399,460 B1 6/2002 Yamaguchi et al.  
6,495,857 B2 \* 12/2002 Yamazaki ..... 257/59  
6,500,704 B1 12/2002 Hirano et al.  
6,506,669 B1 \* 1/2003 Kuramasu et al. .... 438/586

(Continued)

(75) Inventors: **Byoung-Keon Park**, Suwon-si (KR);  
**Jin-Wook Seo**, Suwon-si (KR);  
**Tae-Hoon Yang**, Suwon-si (KR);  
**Kil-Won Lee**, Suwon-si (KR)

**FOREIGN PATENT DOCUMENTS**

CN 1388591 A 1/2003  
CN 1638147 7/2005

(Continued)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin (KR)

**OTHER PUBLICATIONS**

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

Abstract of KR 2000-41547.

(Continued)

(21) Appl. No.: **12/194,739**

*Primary Examiner* — Bilkis Jahan

(22) Filed: **Aug. 20, 2008**

(74) *Attorney, Agent, or Firm* — H.C. Park & Associates, PLC

(65) **Prior Publication Data**

US 2009/0050894 A1 Feb. 26, 2009

(57) **ABSTRACT**

(30) **Foreign Application Priority Data**

Aug. 22, 2007 (KR) ..... 10-2007-0084412

A thin film transistor (TFT) includes a substrate, a semiconductor layer disposed on the substrate and including a channel region and source and drain regions, a gate electrode disposed in a position corresponding to the channel region of the semiconductor layer, a gate insulating layer interposed between the gate electrode and the semiconductor layer to electrically insulate the semiconductor layer from the gate electrode, a metal structure made up of metal layer, a metal silicide layer, or a double layer thereof disposed apart from the gate electrode over or under the semiconductor layer in a position corresponding to a region of the semiconductor layer other than a channel region, the structure being formed of the same material as the gate electrode, and source and drain electrodes electrically connected to the source and drain regions of the semiconductor layer.

(51) **Int. Cl.**  
**H01L 27/15** (2006.01)

(52) **U.S. Cl.**  
USPC ..... **257/72; 257/E21.413**


(58) **Field of Classification Search**  
USPC ..... **257/72, 59, 257, 228, 294, 293, 291, 257/292, E21.413**  
See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

3,465,209 A 9/1969 Denning et al.  
5,637,515 A \* 6/1997 Takemura ..... 438/162

**11 Claims, 12 Drawing Sheets**



(56)

## References Cited

## U.S. PATENT DOCUMENTS

6,531,815	B1 *	3/2003	Okuyama et al. ....	313/506
6,620,661	B2	9/2003	Maekawa et al.	
6,746,905	B1	6/2004	Fukuda	
6,893,503	B1	5/2005	Ohnuma et al.	
7,045,444	B2	5/2006	Yamazaki et al.	
7,098,089	B2	8/2006	Paik	
7,130,002	B2	10/2006	Seo et al.	
7,202,143	B1	4/2007	Naseem et al.	
2001/0025992	A1	10/2001	Nakajima et al.	
2001/0041397	A1	11/2001	Fukushima	
2002/0013114	A1	1/2002	Ohtani et al.	
2002/0016029	A1	2/2002	Kawakita et al.	
2002/0096681	A1	7/2002	Yamazaki et al.	
2002/0182828	A1 *	12/2002	Asami et al. ....	438/485
2003/0013279	A1	1/2003	Jang et al.	
2003/0030108	A1	2/2003	Morosawa	
2003/0148561	A1	8/2003	Nakajima	
2003/0155572	A1	8/2003	Han et al.	
2003/0201442	A1	10/2003	Makita	
2004/0046171	A1 *	3/2004	Lee et al. ....	257/66
2004/0089878	A1 *	5/2004	Takehashi et al. ....	257/200
2004/0135180	A1	7/2004	Makita	
2004/0164300	A1	8/2004	Yamazaki et al.	
2004/0206958	A1 *	10/2004	Yamazaki et al. ....	257/59
2005/0035352	A1 *	2/2005	Onizuka ....	257/72
2005/0105037	A1	5/2005	Kim et al.	
2005/0110022	A1	5/2005	Kim et al.	
2005/0133867	A1	6/2005	Ohtani et al.	
2005/0140841	A1 *	6/2005	Yang et al. ....	349/43
2005/0170573	A1	8/2005	Makita et al.	
2005/0285111	A1	12/2005	Tsuboi	
2006/0033107	A1	2/2006	Lee et al.	
2006/0040438	A1	2/2006	Lu et al.	
2006/0115948	A1	6/2006	Tokunaga	
2006/0263957	A1	11/2006	Wong et al.	
2007/0007529	A1	1/2007	Takemura et al.	
2007/0181890	A1 *	8/2007	Yamazaki et al. ....	257/79
2007/0207577	A1	9/2007	Oyu	
2007/0228420	A1	10/2007	Takano et al.	
2008/0001228	A1	1/2008	Shionoiri et al.	
2008/0217620	A1	9/2008	Park et al.	
2008/0246027	A1	10/2008	Kim	
2009/0008642	A1	1/2009	Kim et al.	

## FOREIGN PATENT DOCUMENTS

EP	0 225 821	6/1987
EP	0 816 903 A1	1/1998
EP	1 052 700	11/2000
EP	1 508 921 A2	2/2005
EP	1 524 702 A2	4/2005
EP	1 858 068	11/2007
EP	2 003 695	12/2008
EP	2 009 680	12/2008
EP	2003695	12/2008
EP	2 028 687	2/2009
EP	2 107 613	10/2009
JP	62-104173	5/1987
JP	05-047791	2/1993
JP	06-151859	5/1994
JP	07-176753	7/1995
JP	07-326764	12/1995
JP	08-255907	10/1996
JP	10-012882	1/1998
JP	10-223533	8/1998
JP	10-242477	9/1998
JP	11-008393	1/1999
JP	11-111992	4/1999
JP	11-261075	9/1999
JP	2000-036598	2/2000
JP	2000-114527	4/2000
JP	2000-252474	9/2000
JP	2001-077364	3/2001
JP	2001-319878	11/2001
JP	2002-093745	3/2002
JP	2003-007719	1/2003

JP	2003-075870	3/2003
JP	2003-100633	4/2003
JP	2003-188098	7/2003
JP	2003-203924	7/2003
JP	2003-298059	10/2003
JP	2003-303831	10/2003
JP	2003-318194	11/2003
JP	2004-022845	1/2004
JP	2005-123565	5/2005
JP	2005-181973	7/2005
JP	2005-197526	7/2005
JP	2006-49823	2/2006
JP	2006-066860	3/2006
JP	2006-345003	12/2006
JP	2007-251149	9/2007
KR	1999-75412	10/1999
KR	1999-88504	12/1999
KR	2000-52006	8/2000
KR	2003-3043	1/2003
KR	2003-57656	7/2003
KR	2003-69779	8/2003
KR	2003-73075	9/2003
KR	2003-73076	9/2003
KR	2003-84738	11/2003
KR	2004-82168	9/2004
KR	10-482462	4/2005
KR	2005-36625	4/2005
KR	10-2005-0049684	5/2005
KR	10-2005-0049692	5/2005
KR	2005-41836	5/2005
KR	10-509529	8/2005
KR	2005-106244	11/2005
KR	2006-99694	9/2006
KR	10-2007-0024016	3/2007
KR	2008-0082827	9/2008

## OTHER PUBLICATIONS

Office Action issued by Korean Intellectual Property Office in Korean Patent Application No. 10-2007-0053314 on Mar. 25, 2008.

Myers, S.M., et al. "Mechanisms of Transition-metal Gettering in Silicon". *Journal of Applied Physics*, V. 88, No. 7 (Oct. 1, 2000), pp. 3795-3819.

Benton, J.L. et al. "Behavior of Molybdenum in Silicon Evaluated for Integrated Circuit Processing", *Journal of Electrochemical Society*, V. 146, No. 5, (1999), pp. 1929-1933.

U.S. Appl. No. 12/405,466, filed Mar. 17, 2009, Byoung-Keon Park et al., Samsung Mobile Display Co., Ltd.

U.S. Appl. No. 12/409,085, filed Mar. 23, 2009, Byoung-Keon Park et al., Samsung Mobile Display Co., Ltd.

U.S. Appl. No. 12/199,232, filed Aug. 27, 2008, Yong-Chan You et al., Samsung SDI Co., Ltd.

Search Report issued by European Patent Office in European Patent Application No. 08157167.1 on Nov. 28, 2008.

Hu, Chen-Ming, et al. "Gettering of Nickel within Ni-Metal Induced Lateral Crystallization Polycrystalline Silicon Film through the Contact Holes". *Japanese Journal of Applied Physics*. No. 46, No. 48. 2007. pp. L1188-L1190.

Ng, K. K. *Complete Guide to Semiconductor Devices*. Second Edition. Wiley. New York. 2002. pp. 694-695.

European Search Report issued on Dec. 11, 2008 in corresponding European Application No. 08162758.0-1528.

Korean Notice of Allowability issued on Dec. 26, 2008 in corresponding Korean Application No. 2007-84934.

Korean Notice of Allowability issued on Dec. 26, 2008 in corresponding Korean Application No. 2007-84412.

Japanese Journal of Applied Physics; vol. 28, No. 7, pp. 1272-1273; 1989; XP009121147.

European Office Action issued on Aug. 11, 2009 in corresponding European Patent Application No. 08 157 16.1.

U.S. Appl. No. 12/502,413, filed Jul. 14, 2009, Byoung-Keon Park et al., Samsung Mobile Display Co., Ltd.

Fariborz Assaderaghi et al.: "Dynamic Threshold-Voltage MOSFET (DTMOS) for Ultra-Low Voltage VLSI" IEEE Transactions on Electron Devices, IEEE Service Center, Piscataway, NJ, US, vol. 44, No. 3, Mar. 1, 1997, XP011016082.

Office Action issued Aug. 28, 2009, in corresponding Chinese Patent Application No. 200810214019.

European Search Report issued Sep. 2, 2009 in corresponding European Application No. 09156279).

European Partial Search Report issued Sep. 4, 2009 in corresponding European Patent Application No. 09157829.

Final Office Action of U.S. Appl. No. 12/194,730 issued on May 4, 2011.

Final Office Action of U.S. Appl. No. 12/130,340 issued on May 12, 2011.

US Office Action dated Nov. 26, 2010, issued in corresponding U.S. Appl. No. 12/130,340.

US Office Action dated Dec. 9, 2010, issued in corresponding U.S. Appl. No. 12/194,730.

Non-Final Office Action dated Jun. 24, 2011 in U.S. Appl. No. 12/409,085.

Jones, et al., "Diffusivity of impurities in polysilicon", Feb. 21, 2007, XP009150765.

Non-Final Office Action issued on Sep. 30, 2011 in co-pending U.S. Appl. No. 12/502,413.

Non-Final Office Action issued on Sep. 21, 2011 in co-pending U.S. Appl. No. 12/405,466.

Non-Final Office Action issued on Oct. 7, 2011 in co-pending U.S. Appl. No. 12/130,340.

Notice of Allowance issued on Oct. 4, 2011 in co-pending U.S. Appl. No. 12/194,730.

Notice of Allowance issued on Oct. 17, 2011 in co-pending U.S. Appl. No. 12/409,085.

Final Office Action of U.S. Appl. No. 12/502,413, dated Feb. 16, 2012.

Notice of Allowance issued for related U.S. Appl. No. 12/194,730 dated Jun. 12, 2012.

Final Office Action of U.S. Appl. No. 12/405,466 dated Apr. 5, 2012.

Final Office Action of U.S. Appl. No. 12/130,340 dated Mar. 8, 2012.

Notice of Allowance issued for related U.S. Appl. No. 12/405,466 dated Aug. 8, 2012.

Notice of Allowance issued for related U.S. Appl. No. 13/333,587 dated Jan. 15, 2013.

Non-Final Office Action issued for related U.S. Appl. No. 13/464,579 dated Mar. 21, 2013.

\* cited by examiner

FIG. 1A




FIG. 1B




FIG. 1C




FIG. 1D




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 4





FIG. 5



**THIN FILM TRANSISTOR INCLUDING  
METAL OR METAL SILICIDE STRUCTURE  
IN CONTACT WITH SEMICONDUCTOR  
LAYER AND ORGANIC LIGHT EMITTING  
DIODE DISPLAY DEVICE HAVING THE THIN  
FILM TRANSISTOR**

CROSS-REFERENCE TO RELATED  
APPLICATION

This application claims the benefit of Korean Application No. 2007-84412, filed Aug. 22, 2007 in the Korean Intellectual Property Office, the disclosure of which is incorporated herein by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

Aspects of the present invention relate to a thin film transistor (TFT), a method of fabricating the TFT, an organic light emitting diode (OLED) display device having the TFT, and a method of fabricating the OLED display device. More particularly, aspects of the present invention relate to a TFT in which an amount of a crystallization-inducing metal remaining in a channel region of a semiconducting layer crystallized using the crystallization-inducing metal is reduced by gettering to improve the electrical properties of the TFT, a method of fabricating the TFT, an OLED display device having the TFT, and a method of fabricating the OLED display device.

2. Description of the Related Art

In general, a polycrystalline silicon (poly-Si) layer is widely used as a semiconductor layer for a thin film transistor (TFT) because the poly-Si has a high field-effect mobility, can be applied to a high-speed operating circuit, and can be used to configure a complementary-metal-oxide-semiconductor (CMOS) circuit. A TFT using a poly-Si layer may be typically used as an active device of an active-matrix liquid crystal display (AMLCD) or a switching device or a driving device of an organic light emitting diode (OLED) display device.

Methods of crystallizing an a-Si layer into a poly-Si layer may include a solid phase crystallization (SPC) method, an excimer laser crystallization (ELC) method, a metal induced crystallization (MIC) method, and a metal induced lateral crystallization (MILC) method. Recently, a vast amount of research has been conducted on methods of crystallizing an a-Si layer using a crystallization-inducing metal, because these methods allow for a-Si layer to be crystallized at a lower temperature for a shorter amount of time than does an SPC method.

Typical methods of crystallizing an a-Si layer using a crystallization-inducing metal are a MIC method and a MILC method. In these methods, however, the device characteristics of a TFT may be degraded due to contamination caused by the crystallization-inducing metal.

In order to prevent the contamination caused by the crystallization-inducing metal, a gettering process may be performed after an a-Si layer is crystallized using the crystallization-inducing metal to remove the remaining crystallization-inducing metal. Conventionally, the gettering process is performed using impurities, such as phosphorus (P) gas or noble gas, or by forming an a-Si layer on a poly-Si layer. However, in the conventional methods, the crystallization-inducing metal may not be effectively removed from the poly-Si layer, so a leakage current may still be problem.

SUMMARY OF THE INVENTION

Aspects of the present invention provide a thin film transistor (TFT) in which an amount of a crystallization-inducing

metal remaining in a channel region after forming a semiconductor layer using a crystallization-inducing metal is reduced by gettering the crystallization-inducing metal existing in the channel region to improve electrical properties of the TFT, a method of fabricating the TFT, an organic light emitting diode (OLED) display device having the TFT, and a method of fabricating the OLED display device.

According to an embodiment of the present invention, a TFT includes: a substrate; a semiconductor layer disposed on the substrate and including a channel region and source and drain regions; a gate electrode disposed in a position corresponding to the channel region of the semiconductor layer; a gate insulating layer interposed between the gate electrode and the semiconductor layer to electrically insulate the semiconductor layer from the gate electrode; a metal structure comprising a metal layer, a metal silicide layer, or a double layer thereof disposed apart from the gate electrode over or under the semiconductor layer in a position corresponding to a region of the semiconductor layer other than a channel region, the structure being formed of the same material as the gate electrode; and source and drain electrodes electrically connected to the source and drain regions of the semiconductor layer.

According to another embodiment of the present invention, a method of fabricating a TFT includes: providing a substrate; forming a crystallized semiconductor layer on the substrate using a crystallization-inducing metal; forming a gate electrode in a position corresponding to a channel region of the semiconductor layer; forming a gate insulating layer between the gate electrode and the semiconductor layer to electrically insulate the semiconductor layer from the gate electrode; forming a structure comprising a metal layer, a metal silicide layer, or a double layer thereof over or under the semiconductor layer in a position corresponding to a region of the semiconductor layer other than a channel region, the metal structure being formed of the same material as the gate electrode; and forming source and drain electrodes to be electrically connected to the source and drain regions of the semiconductor layer. In the method, the substrate on which the metal structure is formed is annealed to getter the crystallization-inducing metal from the channel region of the semiconductor layer into a region of the semiconductor layer corresponding to the metal structure.

According to still another embodiment of the present invention, an OLED display device includes: a substrate; a semiconductor layer disposed on the substrate and including a channel region and source and drain regions; a gate electrode disposed in a position corresponding to the channel region of the semiconductor layer; a gate insulating layer interposed between the gate electrode and the semiconductor layer to electrically insulate the semiconductor layer from the gate electrode; a metal structure comprising a metal layer, a metal silicide layer, or a double layer thereof disposed apart from the gate electrode over or under the semiconductor layer in a position corresponding to a region of the semiconductor layer other than a channel region, the metal structure being formed of the same material as the gate electrode; source and drain electrodes electrically connected to the source and drain regions of the semiconductor layer; a first electrode electrically connected to one of the source and drain electrodes; an organic layer disposed on the first electrode; and a second electrode disposed on the organic layer.

According to yet another embodiment of the present invention, a method of fabricating an OLED display device includes: providing a substrate; forming a crystallized semiconductor layer on the substrate using a crystallization-inducing metal; forming a gate electrode in a position correspond-

ing to a channel region of the semiconductor layer; forming a gate insulating layer between the gate electrode and the semiconductor layer to electrically insulate the semiconductor layer from the gate electrode; forming a metal structure comprising a metal layer, a metal silicide layer, or a double layer thereof over or under the semiconductor layer in a position corresponding to a region of the semiconductor layer other than a channel region, the metal structure being formed of the same material as the gate electrode; and forming source and drain electrodes to be electrically connected to the source and drain regions of the semiconductor layer; forming a first electrode to be electrically connected to one of the source and drain electrodes; forming an organic layer having an emission layer (EML) on the first electrode; and forming a second electrode on the organic layer. In the method, the substrate on which the metal structure is formed is annealed to getter the crystallization-inducing metal from the channel region of the semiconductor layer into a region of the semiconductor layer corresponding to the metal structure.

According to another embodiment of the present invention, there is provided a method of fabricating a top gate thin film transistor, comprising forming a crystallized semiconductor layer on a substrate using a crystallization-inducing metal, the crystallized semiconductor layer comprising a channel region, a source region and a drain region; forming a gate insulating layer on the crystallized semiconductor layer; etching the gate insulating layer to form at least one first contact hole partially exposing a region of the semiconductor layer other than the channel region; depositing a gate electrode material on the gate insulating layer and filling the at least one first contact hole, wherein the gate electrode material comprises a metal, a metal silicide or a double layer or combination thereof; patterning the gate electrode material to form a gate electrode corresponding to the channel region and at least one metal structure separated from the gate electrode and comprising the gate electrode material filling the at least one first contact hole; and annealing the crystallized semiconductor layer having the gate electrode and at least one metal structure formed thereon such that crystallization-inducing metal remaining in the channel region of the crystallized semiconductor layer is getterd to a region of the semiconductor layer contacting the metal structure.

According to another embodiment of the present invention, there is provided a method of fabricating a bottom gate thin film transistor, comprising depositing a gate electrode material on a substrate, wherein the gate electrode material comprises a metal, a metal silicide or a double layer or combination thereof; patterning the gate electrode material to form a gate electrode and at least one metal structure separated from the gate electrode; forming a gate insulating layer on the substrate to cover the gate electrode and the at least one metal structure; etching the gate insulating layer to expose the at least one metal structure; forming an amorphous silicon layer on the gate insulating layer and contacting the at least one metal structure; crystallizing the amorphous silicon layer using a crystallization-inducing metal to form a polycrystalline silicon layer and patterning the polycrystalline silicon layer to form a semiconductor layer comprising a channel region aligned with the gate electrode, a source region and a drain region, wherein the semiconductor layer contacts the metal structure in a region outside the channel region; and annealing the crystallized semiconductor layer such that crystallization-inducing metal remaining in the channel region of the crystallized semiconductor layer is getterd to a region of the semiconductor layer contacting the metal structure.

Additional aspects and/or advantages of the invention will be set forth in part in the description which follows and, in part, will be obvious from the description, or may be learned by practice of the invention.

#### BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects and advantages of the invention will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings of which:

FIGS. 1A through 1D are cross-sectional views illustrating a crystallization process according to an exemplary embodiment of the present invention;

FIGS. 2A through 2F are cross-sectional views illustrating a method of fabricating a top-gate thin film transistor (TFT) according to an exemplary embodiment of the present invention;

FIGS. 3A through 3C are cross-sectional views illustrating a method of fabricating a bottom-gate TFT according to an exemplary embodiment of the present invention;

FIG. 4 is a graph showing a comparison of an off-current per unit width of a semiconductor layer of a TFT according to an exemplary embodiment of the present invention and an off-current per unit width of a semiconductor layer of a conventional TFT fabricated by a gettering process using P doping; and

FIG. 5 is a cross-sectional view of an organic light emitting diode (OLED) display device having a TFT according to an exemplary embodiment of the present invention.

#### DETAILED DESCRIPTION OF THE EMBODIMENTS

Reference will now be made in detail to the present embodiments of the present invention, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to the like elements throughout. The embodiments are described below in order to explain the present invention by referring to the figures. Herein, it is to be understood that where is stated herein that one layer is "formed on" or "disposed on" a second layer, the first layer may be formed or disposed directly on the second layer or there may be intervening layers between the first layer and the second layer. Further, as used herein, the term "formed on" is used with the same meaning as "located on" or "disposed on" and is not meant to be limiting regarding any particular fabrication process.

FIGS. 1A through 1D are cross-sectional views illustrating a crystallization process according to an embodiment of the present invention.

Referring to FIG. 1A, a buffer layer **110** is formed on a substrate **100**, such as a glass substrate or a plastic substrate. The buffer layer **110** may be obtained using a chemical vapor deposition (CVD) technique or a physical vapor deposition (PVD) technique. The buffer layer **110** may be a single or multiple layer formed of one or more insulating materials such as silicon oxide or silicon nitride. In this case, the buffer layer **110** may prevent the diffusion of moisture or impurities generated in the substrate **100** or control the transmission rate of heat during a crystallization process, thereby facilitating the crystallization of an amorphous silicon (a-Si) layer.

Thereafter, an a-Si layer **120** is formed on the buffer layer **110**. The a-Si layer **120** may be obtained using a CVD or PVD technique. Also, a dehydrogenation process may be per-

formed during or after the formation of the a-Si layer **120**, thereby lowering the concentration of hydrogen in the a-Si layer.

The a-Si layer **120** is then crystallized into a poly-Si layer. In the present embodiment, the a-Si layer **120** may be crystallized into the poly-Si layer by a crystallization method that uses a crystallization-inducing metal, such as a metal induced crystallization (MIC) method, a metal induced lateral crystallization (MILC) method, or a super grain silicon (SGS) crystallization method.

In the MIC method, a metal, such as nickel (Ni), palladium (Pd), gold (Au), or aluminum (Al), is brought into contact with or doped into an a-Si layer to induce a phase change of the a-Si layer into a poly-Si layer. In the MILC method, silicide formed by reaction of metal with silicon laterally diffuses so as to sequentially induce crystallization of an a-Si layer.

In the SGS crystallization method, a crystallization-inducing metal that diffuses into the a-Si layer is controlled to a low concentration such that the size of crystal grains ranges from several to several hundred  $\mu\text{m}$ . For example, the SGS crystallization method may include forming a capping layer to control diffusion of a crystallization-inducing metal on the a-Si layer, forming a crystallization-inducing metal layer on the capping layer, and annealing the crystallization-inducing metal layer to diffuse a crystallization-inducing metal into the a-Si layer, thereby crystallizing the a-Si layer into a poly-Si layer. Alternatively, the concentration of a crystallization-inducing metal that diffuses into an a-Si layer may be lowered by forming a crystallization-inducing metal layer at a low concentration without forming a capping layer.

According to the SGS crystallization method using a capping layer, the concentration of a crystallization-inducing metal that diffuses into an a-Si layer is controlled more effectively than in the MIC or MILC method. Thus, the SGS crystallization method will now be described.

FIG. 1B is a cross-sectional view illustrating a process of forming a capping layer and a crystallization-inducing metal layer on the a-Si layer. Referring to FIG. 1B, a capping layer **130** is formed on the a-Si layer **120**. The capping layer **130** may be a silicon nitride layer into which a crystallization-inducing metal may diffuse during a subsequent annealing process or a double layer of a silicon nitride layer and a silicon oxide layer. The capping layer **130** may be formed using a deposition method such as CVD or PVD. The capping layer **130** may be formed to a thickness of about 1 to 2000  $\text{\AA}$ . When the capping layer **130** is formed to a thickness of less than 1  $\text{\AA}$ , the capping layer **130** may not properly function to control the amount of crystallization-inducing metal that diffuses into the a-Si layer **120**. When the capping layer **130** is formed to a thickness of more than 2000  $\text{\AA}$ , only a small amount of crystallization-inducing metal diffuses into the a-Si layer **120**, thereby resulting in incomplete crystallization of the a-Si layer **120**.

Thereafter, a crystallization-inducing metal is deposited on the capping layer **130**, thereby forming a crystallization-inducing metal layer **140**. The crystallization-inducing metal may be one selected from the group consisting of Ni, Pd, Ag, Au, Al, Sn, Sb, Cu, Tr, and Cd. For example, the crystallization-inducing metal may be Ni. In this case, the crystallization-inducing metal layer **140** may be formed to an areal density of about  $10^{11}$  to  $10^{15}$  atoms/cm<sup>2</sup> on the capping layer **130**. When the crystallization-inducing metal layer **140** is formed to an areal density lower than about  $10^{11}$  atoms/cm<sup>2</sup>, only a small number of seeds are formed, thereby precluding crystallization of the a-Si layer **120** into a poly-Si layer. When the crystallization-inducing metal layer **140** is formed to an

areal density of more than about  $10^{15}$  atoms/cm<sup>2</sup>, the amount of crystallization-inducing metal diffusing into the a-Si layer **120** is increased, thereby reducing the size of crystal grains of the poly-Si layer. Also, the amount of the remaining crystallization-inducing metal is increased so that the characteristics of a semiconductor layer formed by patterning the poly-Si layer may be degraded.

When the capping layer **130** is formed as in the present embodiment, it is not necessary to precisely control the thickness of the crystallization-inducing metal layer **140** since the capping layer **130** controls the diffusion of the crystallization-inducing metal such that only a very small amount of crystallization-inducing metal diffuses into the a-Si layer **120** to enable the crystallization of the a-Si layer **120**.

FIG. 1C is a cross-sectional view illustrating a process of annealing the substrate to diffuse the crystallization-inducing metal through the capping layer into the a-Si layer. Referring to FIG. 1C, the substrate **100** having the buffer layer **110**, the a-Si layer **120**, the capping layer **130**, and the crystallization-inducing metal layer **140** is annealed so that some of the crystallization-inducing metal of the crystallization-inducing metal layer **140** diffuses to the surface of the a-Si layer **120**. Specifically, only a small amount of the crystallization-inducing metal **140b** out of crystallization-inducing metals **140a** and **140b** diffusing through the capping layer **130** diffuses all the way onto the surface of the a-Si layer **120**, while a large amount of crystallization-inducing metal **140a** neither reaches the a-Si layer **120** nor passes through the capping layer **130**.

Thus, the amount of crystallization-inducing metal that diffuses to the surface of the a-Si layer **120** may depend on the diffusion barrier capability of the capping layer **130**, which is closely related to the thickness of the capping layer **130**. In other words, as the thickness of the capping layer **130** increases, the diffused amount of crystallization-inducing metal decreases and the size of crystal grains increases. Conversely, as the thickness of the capping layer **130** decreases, the diffused amount of crystallization-inducing metal increases and the size of the crystal grains decreases.

In this case, the annealing process to diffuse the crystallization-inducing metal may be performed at a temperature of about 200 to 900° C. for several seconds to several hours. When the annealing process is performed under the above-described time and temperature conditions, deformation of the substrate **100** due to overheating may be prevented, and desired results may be obtained in terms of fabrication cost and yield. The annealing process may be performed using any one of a furnace process, a rapid thermal annealing (RTA) process, an ultraviolet (UV) process, and a laser process.

FIG. 1D is a cross-sectional view illustrating a process of crystallizing the a-Si layer into a poly-Si layer using the diffused crystallization-inducing metal. Referring to FIG. 1D, the a-Si layer **120** is crystallized into a poly-Si layer **150** as catalyzed by the crystallization-inducing metal **140b** that passes through the capping layer **130** and diffuses into the surface of the a-Si layer **120**. That is, the diffused crystallization-inducing metal **140b** combines with Si of the a-Si layer **120** to form a metal silicide. The metal silicide forms crystal nuclei (i.e., seeds), thereby crystallizing the a-Si layer **120** into the poly-Si layer **150**.

Accordingly, the number of seeds formed by the metal silicide, that is, the amount of diffused crystallization-inducing metal **140b** that contributes toward crystallizing the a-Si layer **120**, is controlled such that the size of crystal grains of the poly-Si layer **150** may range from several to several hundred  $\mu\text{m}$ . Also, since only a very small amount of crystallization-inducing metal remains in the poly-Si layer **150** due to

the diffusion inhibiting effects of the capping layer **130**, the poly-Si layer **150** exhibits better characteristics than layers formed by other crystallization methods.

Although it is illustrated in FIG. 1D that the annealing process is performed on the resultant structure having the capping layer **130** and the crystallization-inducing metal layer **140**, after the crystallization-inducing metal is diffused into the surface of the a-Si layer **120** to form the metal silicide, the capping layer **130** and the crystallization-inducing metal layer **140** may be removed before the annealing process for forming the poly-Si layer **150** is performed.

FIGS. 2A through 2F are cross-sectional views illustrating a process of fabricating a top-gate TFT according to an exemplary embodiment of the present invention.

Referring to FIG. 2A, a poly-Si layer **150**, which is formed using the SGS crystallization method described with reference to FIGS. 1A through 1D, is patterned, thereby forming a semiconductor layer **160** on the substrate **100** (refer to FIG. 1A) having the buffer layer **110** (refer to FIG. 1A). As an alternative, the poly-Si layer **150** may be patterned during a subsequent process.

Referring to FIG. 2B, a gate insulating layer **170** is formed on the substrate **100** having the semiconductor layer **160**. The gate insulating layer **170** may be a silicon oxide layer, a silicon nitride layer, or a double layer thereof.

A photoresist pattern **180** is formed on the gate insulating layer **170** to correspond to a region where a channel region of the semiconductor layer **160** will be defined. Thereafter, conductive impurity ions **190** may be doped using the photoresist pattern **180** as a mask, thereby forming a source region **161**, a drain region **163**, and a channel region **162**. In this case, the impurity ions **190** may be p-type impurity ions or n-type impurity ions. The p-type ions may be ions of one selected from the group consisting of boron (B), aluminum (Al), gallium (Ga), and indium (In), and the n-type ions may be ions of one selected from the group consisting of phosphorus (P), arsenic (As), and antimony (Sb).

Referring to FIG. 2C, the photoresist pattern **180** is removed, and the gate insulating layer **170** is etched, thereby forming first holes **200** to partially expose regions of the semiconductor layer **160** other than the channel region **162**.

Thereafter, a gate electrode material is deposited on the entire surface of the substrate **100** and patterned, thereby forming a gate electrode **210** and at least one metal structure **211** comprising a metal, a metal silicide or a combination or double layer of a metal and metal silicide at the same time. Herein, the term "metal structure" refers to a structure that includes a metal, a metal silicide or a combination or double layer of a metal and metal silicide. Each metal structure **211** contacts the exposed region of the semiconductor layer through one of the first holes **200** and is spaced apart from the gate electrode **210**. Each metal structure **211** is disposed in one of the first holes **200** and may or may not protrude from the surface of the gate insulating layer **170**. It is to be understood that the number of holes **200** and metal structures **211** may be fewer than or greater than what is shown in FIG. 2C.

The metal structure **211** is formed of a metal having a lower diffusion coefficient than the crystallization-inducing metal in the semiconductor layer **160** or an alloy thereof or a metal silicide layer formed of a silicide of the metal. The metal or metal silicide used to form the metal structure **211** may be a gettering metal or metal silicide.

More specifically, the metal or metal silicide used for forming the metal structure **211** may have a diffusion coefficient in the semiconductor layer **160** that is 1/100 or less than the diffusion coefficient of the crystallization-inducing metal. When the metal or metal silicide has a diffusion coefficient

that is 1/100 or less than that of the crystallization-inducing metal, the metal or metal silicide may be prevented from departing from the adjoining region **160a** of the semiconductor layer **160** that corresponds to metal structure, and from diffusing into the other region of the semiconductor layer **160**.

Nickel (Ni) is widely used as the crystallization-inducing metal for the crystallization of the semiconductor layer **160**. Since Ni has a diffusion coefficient of about  $10^{-5}$  cm<sup>2</sup>/s or less in the semiconductor layer **160**, when Ni is used as the crystallization-inducing metal, the metal structure **211** used in the gettering process may be formed of a metal or metal silicide having a diffusion coefficient that is 1/100 or less than the diffusion coefficient of Ni in the semiconductor layer **160**, that is, a metal or metal silicide having a diffusion coefficient of about 0 to  $10^{-7}$  cm<sup>2</sup>/s. More specifically, the metal structure **211** may be formed of a metal or metal silicide having a diffusion coefficient of about 0 to  $10^{-7}$  cm<sup>2</sup>/s at a temperature of about 500 to 993° C. When the metal structure **211** is formed of a metal or metal silicide having a diffusion coefficient of about 0 to  $10^{-7}$  cm<sup>2</sup>/s, the metal or metal silicide may be prevented from diffusing into the channel region **162** of the semiconductor layer **160**.

The gate electrode **210** and the metal structure **211** may be formed of one selected from the group consisting of Sc, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Re, Ru, Os, Co, Rh, Ir, Pt, Y, Ta, La, Ce, Pr, Nd, Dy, Ho, TiN, TaN, an alloy thereof, and a silicide of the metal.

The gate electrode **210** and the metal structure **211** may be formed as a single layer or a multiple layer. The single layer may be formed of one selected from the group consisting of Sc, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Re, Ru, Os, Co, Rh, Ir, Pt, Y, Ta, La, Ce, Pr, Nd, Dy, Ho, TiN, TaN, an alloy thereof, and a silicide of the metal. The multiple layer may include lower layers **210a** and **211a**, which are formed by depositing the material described above for the single layer, and upper layers **210b** and **211b**, which are formed of Al or an Al—Nd alloy. When the upper layers **210b** and **211b** formed of Al or an Al—Nd alloy are formed, the gate electrode **210** may have a low resistance, since Al or the Al—Nd alloy has a low resistance.

The metal structure **211** may be formed in a region that is spaced 50 μm or less from the channel region **162** of the semiconductor layer **160**. When the metal structure **211** is formed in a region that is spaced more than 50 μm from the channel region **162** of the semiconductor layer **160**, the distance from the channel region **162** to the adjoining region **160a** of the semiconductor layer **162** that corresponds to metal structure **211** becomes so great that an annealing time taken to getter the crystallization-inducing metal from the channel region **162** to the adjoining region **160a** of the semiconductor layer **162** that corresponds to metal structure **211** may be increased, which may cause the deformation of the substrate **100** or to prevent the crystallization-inducing metal from reaching the adjoining region **160a**.

The metal structure **211** may be formed to a thickness of about 30 to 10000 Å. When the metal structure **211** is formed to a thickness of less than 30 Å, the crystallization-inducing metal may not be effectively gettering into the region **160a** of the semiconductor layer **160** corresponding to the metal layer, the metal silicide layer, or the double layer thereof **211**. When the metal layer, the metal silicide layer, or the double layer thereof **211** is formed to a thickness of more than 10000 Å, the metal structure **211** may peel due to stress.

Referring to FIG. 2D, an interlayer insulating layer **220** is formed on the entire surface of the substrate **100** to protect and electrically insulate the underlying structure. The inter-

layer insulating layer **220** may be a silicon oxide layer, a silicon nitride layer, or a double layer thereof.

Subsequently, in order to remove the crystallization-inducing metal from the semiconductor layer **160**, or more specifically, from the channel region **162** of the semiconductor layer **160**, an annealing process is performed. As a result, the metal of the metal structure **211** combines with silicon of the semiconductor layer **160** to form a metal silicide in the surface of the semiconductor layer **160** that contacts the metal structure **211**, or the metal silicide of the metal structure diffuses into the surface of the semiconductor layer **160**. Thus, a metal silicide made up of a metal different from the crystallization-inducing metal is formed to a predetermined depth from the surface of the semiconductor layer **160** in the adjoining region **160a** of the semiconductor layer **160** that contacts the metal structure **211**. A portion of the metal structure **211** that contacts the semiconductor layer **160** may turn into a metal silicide layer.

When the crystallization-inducing metal (e.g., Ni) remaining in the channel region **162** of the semiconductor layer **160** is diffused into the adjoining region **160a** of the semiconductor layer **160** corresponding to metal structure **211** due to the annealing process, the crystallization-inducing metal is precipitated in the region **160a** and is not diffused any more. This is because the crystallization-inducing metal (e.g., Ni) for crystallization is thermodynamically more stable in the adjoining region **160a** containing the metal silicide than in the rest of the semiconductor layer **160**. On the above-described principle, the crystallization-inducing metal for crystallization may be removed from the channel region **162** of the semiconductor layer **160**.

The annealing process may be performed at a temperature of about 500 to 993° C. for 10 seconds to 10 hours. When the annealing process is performed at a temperature lower than 500° C., the crystallization-inducing metal (e.g., Ni) is not diffused in the semiconductor layer **160** so that the crystallization-inducing metal may not move to the adjoining region **160a** of the semiconductor layer **160**. When the annealing process is performed at a temperature higher than 993° C., Ni for the crystallization-inducing metal may be in a solid phase because the eutectic point of Ni for the crystallization-inducing metal is 993° C., and the substrate **100** may be deformed due to a high temperature.

When the annealing process is performed for a shorter time than 10 seconds, it may be difficult to sufficiently remove the crystallization-inducing metal (e.g., Ni) from the channel region **162** of the semiconductor layer **160**. When the annealing process is performed for a longer time than 10 hours, the substrate **100** may be deformed due to a long-duration annealing process, problems may be caused in terms of fabrication cost and yield. When the annealing process is performed at a relatively high temperature, it is possible to remove the crystallization-inducing metal in a relatively short amount of time.

As an alternative, the annealing process may be performed any other time after the metal structure **211** is formed. For example, when the annealing process is performed after an insulating layer is formed on the gate electrode **210**, the gate electrode **210** may prevent thermal damage caused by the annealing process. Also, the annealing process may be performed in an inert atmosphere in order to protect the gate electrode **210**.

Referring to FIG. 2E, the gate insulating layer **170** and the interlayer insulating layer **220** may be etched, thereby forming contact holes **230** to expose the source and drain regions **161** and **163** of the semiconductor layer **160**.

Thereafter, a source/drain electrode material is deposited on the entire surface of the substrate **100** and patterned, thereby forming source and drain electrodes **240a** and **240b**. The source and drain electrodes **240a** and **240b** are electrically connected to the source and drain regions **161** and **163** of the semiconductor layer **160** through the contact holes **230**, respectively. The source and drain electrodes **240a** and **240b** may be formed of one selected from the group consisting of molybdenum (Mo), chrome (Cr), tungsten (W), molybdenum-tungsten (MoW), aluminum (Al), aluminum-neodymium (Al—Nd), titanium (Ti), titanium nitride (TiN), copper (Cu), an Mo alloy, an Al alloy, and a Cu alloy.

Alternatively, referring to FIG. 2F, the interlayer insulating layer **220** may be etched to form contact holes **230a** that expose the metal structure **211**. In this case, there may be two metal structures **211** electrically connected to the source and drain region **161** and **163**, respectively, of the semiconductor layer **160** through the first holes **200**, and the source and drain electrodes **240a** and **240b** may be electrically connected to the metal structures **211** through the contact holes **230a**, so that the source and drain electrodes **240a** and **240b** may be electrically connected to the source and drain regions **161** and **163** of the semiconductor layer **160**.

As a consequence, the fabrication of the top-gate TFT according to the embodiment of FIG. 2F is completed.

FIGS. 3A through 3C are cross-sectional views illustrating a method of fabricating a bottom-gate TFT according to another embodiment of the present invention. The method of fabricating the bottom-gate TFT will now be described with reference to the method shown in FIGS. 2A through 2F except for particulars mentioned below.

Referring to FIG. 3A, a buffer layer **310** is formed on a substrate **300**. A gate electrode material is deposited on the buffer layer **310** and patterned, thereby forming a gate electrode **320** and at least one metal structure **321** at the same time. Here also, the term “metal structure” refers to a structure that includes a metal, a metal silicide or a combination or double layer of a metal and metal silicide. The metal structure **321** may be formed apart from the gate electrode **320** under the semiconductor layer **340** (refer to FIG. 3B) in a position corresponding to a region of a semiconductor layer **340** other than a channel region. Although two metal structures **321** are shown in FIG. 3A, it is to be understood that the number of metal structures can be greater than or less than what is shown.

The metal structure **321** may comprise a metal having a lower diffusion coefficient than a crystallization-inducing metal in the semiconductor layer **340** or an alloy thereof or a metal silicide layer formed of a silicide of the metal. The metal or metal silicide used to form the metal structure **321** may be a gettering metal or metal silicide.

The metal structure **321** may be formed of one selected from the group consisting of Sc, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Re, Ru, Os, Co, Rh, Ir, Pt, Y, Ta, La, Ce, Pr, Nd, Dy, Ho, TiN, TaN, an alloy thereof, and a silicide of the metal.

The gate electrode **320** and metal structure **321** may be formed as a single layer or as a multiple layer. The single layer may be formed of one selected from the group consisting of Sc, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Re, Ru, Os, Co, Rh, Ir, Pt, Y, Ta, La, Ce, Pr, Nd, Dy, Ho, TiN, TaN, an alloy thereof, and a silicide of the metal. The multiple layer may include lower layers **320a** and **321a**, which are formed by depositing the material described above for the single layer, and upper layers **320b** and **321b**, which are formed of Al or an Al—Nd alloy. When the upper layers **320b** and **321b** formed of Al or

an Al—Nd alloy are formed, the gate electrode **320** may have a low resistance, since Al or an Al—Nd alloy has a low resistance.

The metal structure **321** may be formed in a region that is spaced 50  $\mu\text{m}$  or less from a channel region of the semiconductor layer **340**. When the metal structure **321** is formed in a region that is spaced more than 50  $\mu\text{m}$  from the channel region of the semiconductor layer **340**, the distance from the channel region to the adjoining region **340a** of the semiconductor layer **162** that corresponds to the metal structure **321** becomes so great that an annealing time taken to getter the crystallization-inducing metal from the channel region to the adjoining region **340a** of the semiconductor layer **162** that corresponds to the metal structure **321** may be increased, thereby causing the deformation of the substrate **300** or the crystallization-inducing metal may not reach the adjoining region **340a**.

The metal structure **321** may be formed to a thickness of about 30 to 10000  $\text{\AA}$ . When the metal structure **321** is formed to a thickness of less than 30  $\text{\AA}$ , the crystallization-inducing metal may not be effectively gettered into the adjoining region **340a** of the semiconductor layer **340** corresponding to the metal structure **321**. When the metal structure **321** is formed to a thickness of more than 10000  $\text{\AA}$ , the metal structure **321** may peel due to stress.

Referring to FIG. 3B, a gate insulating layer **330** is formed on the substrate **300** having the gate electrode **320** and metal structure **321**. During the formation of the gate insulating layer **330**, a gate insulating layer material is removed from a top surface of the metal structure **321** in order to allow the metal structure **321** to directly contact a poly-Si layer that will be formed later.

Thereafter, an a-Si layer is formed on the gate insulating layer **330** and crystallized into a poly-Si layer using the same SGS crystallization method as described with reference to FIGS. 1A through 1D. The poly-Si layer is patterned to form the semiconductor layer **340**. As an alternative, the poly-Si layer may be patterned in a subsequent process. Meanwhile, during an annealing process for crystallizing the a-Si layer, a crystallization-inducing metal may be gettered into the adjoining region **340a** of the semiconductor layer **340** corresponding to the metal structure **321**.

Thereafter, an annealing process may be performed on the substrate **300** having the buffer layer **310**, the gate electrode **320**, metal structure **321**, the gate insulating layer **330**, and the semiconductor layer **340**. The annealing process may be performed in order to getter the crystallization-inducing metal from the semiconductor layer **340**, particularly, a channel region **341** of the semiconductor layer **340**, into the adjoining region **340a** of the semiconductor layer **340** corresponding to the metal structure **321**. Alternatively, the annealing process may be performed any other time after the metal structure **321** is formed.

Referring to FIG. 3C, an ohmic contact material layer and a source/drain conductive layer are sequentially formed on the semiconductor layer **340** and sequentially patterned, thereby forming an ohmic contact layer **350** and source and drain electrodes **360a** and **360b**. The ohmic contact layer **350** may be a doped a-Si layer.

In order to reduce the number of mask processes, the source/drain conductive layer and the ohmic contact material layer may be patterned using a single mask. As a result, the ohmic contact layer **350** may be disposed under the entire source and drain electrodes **360a** and **360b**. The ohmic contact layer **350** may be interposed between the semiconductor layer **340** and the source and drain electrodes **360a** and **360b** so that the source and drain electrodes **360a** and **360b** may be in ohmic contact with the semiconductor layer **340**. Alternatively,

the formation of the ohmic contact layer **350** may be omitted. In this case, before the source/drain conductive layer is stacked, a conductive region may be formed on the semiconductor layer **340** so that the source and drain electrodes **360a** and **360b** may be in ohmic contact with the semiconductor layer **340**. As a consequence, the fabrication of the bottom-gate TFT having the gate electrode **320**, the semiconductor layer **340**, and the source and drain electrodes **360a** and **360b** is completed.

FIG. 4 is a graph showing a comparison of off-current values per unit width of a semiconductor layer of a TFT according to embodiments of the present invention and off-current values per unit width of a semiconductor layer of a conventional TFT fabricated by a gettering process using phosphorus (P) doping.

In the abscissa of the graph, a region A refers to a conventional TFT fabricated by a gettering process using P doping, and regions B and C refer to TFTs according to embodiments of the present invention. Specifically, the region B is a TFT fabricated using titanium (Ti) as the metal structure, and the region C is a TFT fabricated using molybdenum (Mo) as the metal structure. The ordinate of the graph denotes off-current ( $\text{A}/\mu\text{m}$ ) values per unit width of a semiconductor layer of each of the TFTs.

In forming the conventional TFT, the gettering process included doping P ions into a region of a crystallized semiconductor layer other than a channel region at a dose of about  $2 \times 10^{14}/\text{cm}^2$  and annealing a substrate having the doped semiconductor layer at a temperature of about 550° C. for 1 hour. In forming the TFTs according to the embodiments of the present invention, either a Ti layer or a Mo layer was deposited to a thickness of about 100  $\text{\AA}$  over the region of the semiconductor layer other than a channel region to be spaced apart from a gate electrode. A gettering process was performed by annealing under the same conditions as the above-described gettering process using P doping. After the annealing process, an off-current of each of the TFTs was measured.

When the Ti layer or the Mo layer was deposited and the annealing process was performed to provide gettering according to aspects of the present invention, Ti or Mo reacted with Si of the semiconductor layer to form a Ti silicide or a Mo silicide. The Ti silicide or Mo silicide was formed in a lower region of the semiconductor layer that contacts the Ti layer or Mo layer, and a crystallization-inducing metal was gettered into the region where the Ti silicide or Mo silicide was formed.

Referring to the region A of FIG. 4, in the TFT formed by a process including a gettering process using P doping, the off-current per unit width of the semiconductor layer of the TFT was about  $4.5\text{E-}12$  to  $7.0\text{E-}12$   $\text{A}/\mu\text{m}$ . However, referring to the regions B and C of FIG. 4, the off-current per unit width of the semiconductor layer of the TFT formed by a process including gettering using the Ti layer (region B) was about  $5.0\text{E-}13$   $\text{A}/\mu\text{m}$  or less, and the off-current per unit width of the semiconductor layer of the TFT formed by a process including gettering using the Mo layer (region C) was about  $6.0\text{E-}13$   $\text{A}/\mu\text{m}$  or less. Therefore, it can be observed that the off-current per unit width of the semiconductor of the TFT according to the embodiments of the present invention was far smaller than that of the conventional TFT.

Based on the above-described results, it can be concluded that the amount of a crystallization-inducing metal remaining in the channel region of the semiconductor layer was greatly reduced in the TFTs preparing according to embodiments of the present invention. Therefore, according to the embodiments of the present invention, a TFT having reduced leakage current and good electrical properties can be fabricated.

Hereinafter, an organic light emitting display (OLED) display device having a TFT according to another embodiment of the present invention will be described with reference to FIG. 5.

Referring to FIG. 5, an insulating layer 250 is formed on the entire surface of the substrate 100 having the TFT shown in FIG. 2F. The insulating layer 250 may be an inorganic layer or an organic layer. The inorganic layer may be a silicon oxide layer, a silicon nitride layer, or a silicon on glass (SOG) layer. The organic layer may be formed of one selected from the group consisting of polyimide, benzocyclobutene series resin, and acrylate. Alternatively, the insulating layer 250 may be a stack structure of the inorganic layer and the organic layer.

The insulating layer 250 may be etched, thereby forming a via hole exposing one of the source and drain electrodes 240a and 240b. A first electrode 260 is formed to be connected to one of the source and drain electrodes 240a and 240b through the via hole. The first electrode 260 may be an anode or a cathode. When the first electrode 260 is an anode, the anode may be formed of a transparent conductive material selected from the group consisting of indium tin oxide (ITO), indium zinc oxide (IZO), and indium tin zinc oxide (ITZO). When the first electrode 260 is a cathode, the cathode may be formed of one selected from the group consisting of Mg, Ca, Al, Ag, Ba, and an alloy thereof.

Thereafter, a pixel defining layer 270 is formed on the first electrode 260 having an opening partially exposing the surface of the first electrode 260, and an organic layer 280 having an emission layer (EML) is formed on the exposed surface of the first electrode 260. The organic layer 280 may further include at least one selected from the group consisting of a hole injection layer (HIL), a hole transport layer (HTL), a hole blocking layer (HBL), an electron blocking layer (EBL), an electron injection layer (EIL), and an electron transport layer (ETL). Subsequently, a second electrode 290 is formed on the organic layer 280. Thus, the fabrication of the OLED display device according to the present embodiment is completed.

As described above, a metal structure is formed over or under a semiconductor layer, which is crystallized using a crystallization-inducing metal, in a predetermined region corresponding to a region of the semiconductor layer other than a channel region. The metal structure is formed of a metal having a lower diffusion coefficient than the crystallization-inducing metal in the semiconductor layer, an alloy thereof, or a silicide of the metal. Thereafter, a substrate having the metal structure is annealed, thereby removing the remaining crystallization-inducing metal from the channel region of the semiconductor layer. As a result, the off-current of the TFT can be markedly reduced.

Furthermore, the metal structure can be formed of the same material as the gate electrode, thereby simplifying the fabrication process.

According to aspects of the present invention, the remaining crystallization-inducing metal is removed from a channel region of a semiconductor layer so that a TFT having excellent electrical properties and an OLED display device having the TFT can be fabricated.

Although a few embodiments of the present invention have been shown and described, it would be appreciated by those skilled in the art that changes may be made in this embodiment without departing from the principles and spirit of the invention, the scope of which is defined in the claims and their equivalents.

What is claimed is:

1. A thin film transistor (TFT) comprising:

a substrate;

a semiconductor layer disposed on the substrate and including a channel region and source and drain regions; a gate electrode disposed in a position corresponding to the channel region of the semiconductor layer;

a gate insulating layer interposed between the gate electrode and the semiconductor layer to electrically insulate the semiconductor layer from the gate electrode;

a metal structure comprising a double layer disposed apart from the gate electrode, over the semiconductor layer, and contacting a surface of a region of the semiconductor layer other than the channel region through a hole in the gate insulating layer, the metal structure consisting of a same material as the gate electrode; and

source and drain electrodes electrically connected to the source and drain regions, respectively, of the semiconductor layer,

wherein an insulating layer is disposed between the metal structure and the source and drain electrodes, and wherein the metal structure is not directly connected to the source and drain electrodes.

2. The TFT according to claim 1, wherein the metal structure is disposed at a distance of 50  $\mu\text{m}$  or less from the channel region of the semiconductor layer.

3. The TFT according to claim 1, wherein the metal structure has a thickness of about 30 to 10000  $\text{\AA}$ .

4. The TFT according to claim 1, wherein the metal structure and the gate electrode include a multiple layer formed by stacking an Al layer or an Al—Nd alloy layer and a layer formed of one selected from the group consisting of Sc, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Re, Ru, Os, Co, Rh, Ir, Pt, Y, La, Ce, Pr, Nd, Dy, Ho, TiN, TaN, an alloy thereof, and a silicide thereof.

5. The TFT according to claim 1, wherein the insulating layer is disposed on the gate insulating layer.

6. The TFT according to claim 1, wherein the metal structure and the gate electrode include a metal layer formed of a metal or an alloy thereof or a metal silicide layer formed of a silicide of the metal having a lower diffusion coefficient than a crystallization-inducing metal in the semiconductor layer.

7. The TFT according to claim 6, wherein the metal layer or the metal silicide layer has a diffusion coefficient that is 1/100 or lower of the diffusion coefficient of the crystallization-inducing metal.

8. The TFT according to claim 7, wherein the crystallization-inducing metal is nickel (Ni), and the metal layer or the metal silicide layer has a diffusion coefficient of about 0 to  $10^{-7}$   $\text{cm}^2/\text{s}$ .

9. The TFT according to claim 7, wherein the metal layer or the metal silicide layer is formed of one selected from the group consisting of Sc, Zr, Hf, V, Nb, Ta, Co, Mn, Re, Os, Ir, Y, La, Ce, Pr, Nd, Dy, Ho, an alloy thereof, and a silicide of the metal.

10. An organic light emitting diode (OLED) display device comprising:

a substrate;

a semiconductor layer disposed on the substrate and including a channel region and source and drain regions; a gate electrode disposed in a position corresponding to the channel region of the semiconductor layer;

a gate insulating layer interposed between the gate electrode and the semiconductor layer to electrically insulate the semiconductor layer from the gate electrode;

a metal structure comprising a double layer disposed apart from the gate electrode and over the semiconductor layer

in a position corresponding to a region of the semiconductor layer other than the channel region, the metal structure consisting of a same material as the gate electrode;

source and drain electrodes electrically connected to the source and drain regions, respectively, of the semiconductor layer;

a first electrode electrically connected to one of the source and drain electrodes;

an organic layer disposed on the first electrode; and

a second electrode disposed on the organic layer, wherein the metal structure contacts a surface of the semiconductor layer in the region of the semiconductor layer other than the channel region through a hole in the gate insulating layer,

wherein an insulating layer is disposed between the metal structure and the source and drain electrodes, and wherein the metal structure is directly connected to the source and drain electrodes.

**11.** The OLED display device according to claim **10**, wherein the insulating layer is disposed on the gate insulating layer.

\* \* \* \* \*

专利名称(译)	包括与半导体层接触的金属或金属硅化物结构的薄膜晶体管和具有薄膜晶体管的有机发光二极管显示装置		
公开(公告)号	<a href="#">US8513669</a>	公开(公告)日	2013-08-20
申请号	US12/194739	申请日	2008-08-20
申请(专利权)人(译)	三星SDI CO., LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO., LTD.		
[标]发明人	PARK BYOUNG KEON SEO JIN WOOK YANG TAE HOON LEE KIL WON		
发明人	PARK, BYOUNG-KEON SEO, JIN-WOOK YANG, TAE-HOON LEE, KIL-WON		
IPC分类号	H01L27/15		
CPC分类号	H01L29/458 H01L27/1277 H01L29/66757 H01L29/66765 H01L29/4908 H01L21/02532 H01L21/02672		
优先权	1020070084412 2007-08-22 KR		
其他公开文献	US20090050894A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

薄膜晶体管 ( TFT ) 包括基板, 设置在基板上并包括沟道区和源区和漏区的半导体层, 设置在与半导体层的沟道区对应的位置的栅电极, 栅绝缘层插入在栅电极和半导体层之间以使半导体层与栅电极电绝缘, 由金属层, 金属硅化物层或其双层构成的金属结构在半导体上方或下方与栅电极分开设置在沟道区域以外的半导体层的区域对应的位置处的层, 该结构由与栅电极相同的材料形成, 并且源电极和漏电极电连接到半导体层的源区和漏区。

