



US 20080129194A1

(19) **United States**

(12) **Patent Application Publication**

Abe et al.

(10) **Pub. No.: US 2008/0129194 A1**

(43) **Pub. Date: Jun. 5, 2008**

(54) **ORGANIC EL DISPLAY AND
MANUFACTURING METHOD THEREOF**

(75) Inventors: **Shinichi Abe, Higashiomi (JP);
Motohiko Asano, Yasu (JP);
Hiromitsu Ogawa, Yasu (JP)**

Correspondence Address:
**BIRCH STEWART KOLASCH & BIRCH
PO BOX 747
FALLS CHURCH, VA 22040-0747**

(73) Assignee: **KYOCERA CORPORATION,
Kyoto (JP)**

(21) Appl. No.: **11/976,612**

(22) Filed: **Oct. 25, 2007**

(30) **Foreign Application Priority Data**

Oct. 26, 2006 (JP) 2006-291550

Publication Classification

(51) **Int. Cl.**
H01L 51/54 (2006.01)
C09K 11/02 (2006.01)

(52) **U.S. Cl.** **313/504; 427/66**

(57) **ABSTRACT**

An organic EL display comprises an element substrate, an organic EL element formed on the element substrate, comprising an organic layer including a light emitting layer and a pair of electrode layers disposed on both sides of the organic layer. The organic layer comprises a first organic material. The organic EL display further comprises a capping layer comprising a second organic material having a glass transition point lower than one of the first organic material and a protective layer on the capping layer.




FIG. 1




FIG. 2A




FIG. 2B




FIG. 3




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9





FIG. 10



ORGANIC EL DISPLAY AND MANUFACTURING METHOD THEREOF

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] The present application claims priority of Japanese Patent Application No. 2006-291550, filed on Oct. 26, 2006." The contents of this application are incorporated herein by reference in their entirety.

FIELD OF THE INVENTION

[0002] 1. Technical Field

[0003] The invention relates to an organic EL (electroluminescent) display and a manufacturing method thereof.

[0004] 2. Description of the Related Art

[0005] Generally, an organic EL display has a structure including an organic EL element capable of emitting light disposed on an element substrate, and a protective layer for sealing the organic EL element disposed on the organic EL element. A structure has also been proposed which further includes a capping layer disposed between the organic EL element and the protective layer so that light emitted from the organic EL element is efficiently extracted to the outside (refer to Japanese Unexamined Patent Application Publication No. 2006-173092).

[0006] A manufacturing method of such an organic EL display will be briefly described below. For example, first, an element substrate is prepared. An organic EL element and a capping layer are deposited by vapor deposition on the element substrate, and then a protective layer is formed by CVD on the capping layer.

[0007] However, in the process of manufacturing the organic EL display, foreign matter, such as particles, may be present between the organic EL element and the capping layer. The protective layer does not easily adhere around such foreign matter, and there may be a case where pinholes are formed in the protective layer. In such a case, moisture and oxygen in air infiltrate into the organic EL element through the pinholes of the protective layer, thus degrading the organic EL element, resulting in a decrease in the yield.

SUMMARY OF THE INVENTION

[0008] According to one aspect of the invention, a manufacturing method of an organic EL display comprising preparing an organic EL element comprising an organic layer including a light emitting layer, and a pair of electrode layers disposed on both upper and lower sides of the organic layer. The organic layer comprises first organic material. The manufacturing method also comprising depositing an organic material layer comprising second organic material having a glass transition point lower than one of the first organic material, on the organic EL element.

[0009] According to another aspect of the invention, a first organic EL display comprises an organic EL element comprising an organic layer including a light emitting layer, and a pair of electrode layers formed on both upper and lower sides of the organic layer, the organic layer comprising a first organic material. The first organic EL display also comprises a capping layer formed on the organic EL element. The capping layer comprises a second organic material having a glass transition point lower than that of the first organic material. The first organic EL display further comprises a protective layer formed on the capping layer. The capping layer covers at

least a lower part of a foreign matter between the organic EL element and the protective layer while an upper part of the foreign matter is exposed from the capping layer.

[0010] According to another aspect of the invention, a second organic EL display comprises an organic EL element comprising an organic layer including a light emitting layer, and a pair of electrode layers disposed on both upper and lower sides of the organic layer, the organic layer comprising first organic material. The second organic EL display also comprises a capping layer formed on the organic EL element, comprising second organic material having a glass transition point lower than that of the first organic material. The second organic EL display further comprises a protective layer formed on the capping layer and a partition wall disposed around the organic EL element. The capping layer covers at least a lower part of the partition wall with the upper part of the partition wall exposed from the capping layer.

[0011] According to the invention, since at least a lower part of a foreign matter or a partition wall can be satisfactorily covered with the capping layer, the protective layer can be satisfactorily deposited. Consequently, the sealing properties of the organic EL element can be improved.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] FIG. 1 is a perspective plan view of an organic EL display according to a first embodiment of the invention;

[0013] FIG. 2A is a cross-sectional view of a display area of the organic EL display according to the first embodiment, and FIG. 2B is an enlarged partial cross-sectional view of the organic EL display according to the first embodiment;

[0014] FIG. 3 is a cross-sectional view of a non-display area of the organic EL display according to the first embodiment;

[0015] FIGS. 4A, 4B, and 4C illustrate a process of forming an organic material layer of the organic EL display illustrated in FIG. 1 and illustrate, respectively, the organic material layer before fluidization, the organic material layer after fluidization, and the organic material layer after solidification;

[0016] FIG. 5 is a cross-sectional view of a display area of an organic EL display according to a second embodiment of the invention;

[0017] FIG. 6 is a cross-sectional view of a display area of an organic EL display according to a third embodiment of the invention;

[0018] FIG. 7 is a cross-sectional view of the display area of the organic EL display according to the third embodiment and illustrates an organic material layer before fluidization;

[0019] FIG. 8 is a cross-sectional view of the display area of the organic EL display according to the third embodiment and shows an example of the organic material layer after solidification;

[0020] FIG. 9 is a cross-sectional view of the display area of the organic EL display according to the third embodiment and shows another example of the organic material layer after solidification; and

[0021] FIG. 10 is an enlarged partial cross-sectional view of an organic EL display according to a fourth embodiment of the invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT

[0022] Embodiments of the organic EL display according to the invention will now be described in detail with reference to the drawings.

First Embodiment Organic EL Display

[0023] An organic EL display according to a first embodiment is used in an electric household appliance, such as a

television, or an electronic apparatus, such as a mobile phone or a computer device, and includes a planar element substrate 1 and organic EL elements 2 disposed on the element substrate 1, as illustrated in FIG. 1. A capping layer 3 and a protective layer 4 are disposed on the organic EL elements 2.

[0024] The element substrate 1 is composed of glass or plastic. A plurality of organic EL elements 2 are arranged in a matrix on a display region located in the center of the element substrate 1. A driver IC 5 configured to control light emission of the organic EL elements 2 is mounted on a non-display region located at an end of the element substrate 1.

[0025] A cover substrate 6 is disposed on the element substrate 1 so as to be opposed to the element substrate 1. The cover substrate 6 is a transparent substrate and can be composed of, for example, glass or plastic. Furthermore, a sealing material 7 is disposed along the periphery of the display region of the element substrate 1. The plurality of organic EL elements 2 are sealed by the element substrate 1, the cover substrate 6, and the sealing material 7. As the sealing material 7, for example, a photo-curable or thermosetting acrylic resin, epoxy resin, urethane resin, or silicone resin can be used.

[0026] The individual layers disposed between the element substrate 1 and the cover substrate 6 will now be described with reference to FIGS. 2A, 2B, and 3. A circuit layer 8 provided with TFTs and electric circuit is disposed on the element substrate 1. An insulating layer 9 composed of SiNx ($0 < x \leq 1.2$) or the like is disposed on the circuit layer 8 so that the circuit layer 8 is electrically isolated from outside. A planarizing layer 10 composed of a resin is disposed on the insulating layer 9, the planarizing layer 10 reducing irregularities on the circuit layer 8 and the insulating layer 9. As the planarizing layer 10, an organic material having an insulating property, such as a novolac resin, an acrylic resin, an epoxy resin, or a silicone resin, can be used. The planarizing layer 10 is formed in a tapered shape.

[0027] Furthermore, through-holes that pass through the planarizing layer 10 and the insulating layer 9 are formed. A contact layer 11 composed of a metal material, such as copper or aluminum, is disposed on the interior surface of each of the through-holes and so as to extend from the interior surface toward the upper surface of the planarizing layer 10. Such a contact layer 11 is electrically connected to the circuit layer 8.

[0028] The organic EL elements 2 are disposed on the planarizing layer 10, and each of the organic EL elements 2 includes a lower electrode layer 12, an organic layer 13, and an upper electrode layer 14.

[0029] The lower electrode layer 12 is disposed on the upper surface of the planarizing layer 10 and spaced from the contact layer 11. The lower electrode layer 12 is composed of a metal, such as aluminum, silver, copper, gold, or rhodium, an alloy of these metals, or the like. An interlayer insulation film 15 is interposed between the lower electrode layer 12 and the contact layer 11. A part of the interlayer insulation film 15 is interposed between the upper electrode layer 14 and the lower electrode layer 12, thus preventing short-circuiting therebetween.

[0030] The organic layer 13 is disposed on the lower electrode layer 12. The organic layer 13 includes, for example, a hole injection layer for injecting holes, a hole transporting layer for transporting holes, a luminescent layer that emits EL light, an electron transporting layer for transporting electrons, and an electron injection layer for injecting electrons stacked in that order from the element substrate 1 side. Note that the structure of the organic layer 13 is not limited to the five-

layered structure described above. As long as the luminescent layer is included, any of various layer structures, such as one-layered to four-layered structures, may be employed for the organic layer 13.

[0031] Materials for the individual layers constituting the organic layer 13 will be described below. The hole injection layer is composed of, for example, NiOx ($0 < x \leq 1.2$), CuPc, TiOx ($0 < x \leq 1.2$), CFx ($0 < x \leq 1.2$), or the like. The hole transporting layer is composed of, for example, α -NPD, TPD, or the like. The luminescent layer is composed of, for example, CBP, Alq₃, SDPVBi, or the like, to which an additive, such as DCJTB, coumarin, quinacridone, styrylamine, or perylene, may be added. The electron transporting layer is composed of, for example, Alq₃, oxadiazole, silole, benzothiazole, or the like. The electron injection layer is composed of, for example, LiF, MgF₂, CaF₂, CsF, BaF₂, or the like. Note that the refractive index of the organic layer 13 is in a range of 1.2 to 2.7.

[0032] When a voltage is applied between the lower electrode layer 12 and the upper electrode layer 14, a current flows through the organic layer 13, thereby causing electroluminescence.

[0033] The upper electrode layer 14 is disposed on the organic layer 13 and is composed of a light-transmitting electrically conductive material. The upper electrode layer 14 extends from the organic layer 13 through the interlayer insulation film 15 onto the contact layer 11 and is electrically connected to the contact layer 11. The upper electrode layer 14 is composed of, for example, a transparent electrically conductive material, such as ITO or IZO, an alkali metal, such as Li, an alkaline-earth metal, such as Mg, Ca, Sr, or Ba, or an alloy of these metals. When a metal, such as an alkali metal or an alkaline-earth metal, is used for the upper electrode layer 14, by decreasing the thickness of the upper electrode layer 14, light can be transmitted through the upper electrode layer 14.

[0034] The capping layer 3 is allowed to have a function of efficiently extracting light emitted by the organic layer 13 to the outside by appropriately setting the thickness and the refractive index thereof so that the wavelength of the forward wave traveling from the capping layer 3 toward the protective layer 4 and the wavelength of the reflected wave reflected by the upper electrode layer 14 and traveling toward the protective layer 4 are combined to efficiently resonate light. In view of efficient resonance of light, the difference in the refractive index between the protective layer 4 and the capping layer 3 is preferably 0.7 or less, and more preferably 0.3 or less.

[0035] The capping layer 3 is formed so as to cover the organic EL element 2 disposed on the element substrate 1 side. Specifically, in the display region, the capping layer 3 is formed so as to cover the upper electrode layer 14, and in the non-display region, the capping layer 3 is formed from on the planarizing layer 10 onto the insulating layer 9 through the side surface of the planarizing layer 10. The end of the capping layer 3 is located between the sealing material 7 and the planarizing layer 10. The thickness of the capping layer 3 is in a range of 50 to 200 nm.

[0036] The capping layer 3 is composed of an organic material, such as α -NPD, TPD, or m-MTDA, having a glass transition point lower than that of the organic material constituting the organic layer 13 of the organic EL element 2. The capping layer 3 includes a crystalline portion where molecules are densely packed and an amorphous portion where molecules are sparsely packed. Here, the glass transition

point is defined as the temperature at which the amorphous portion starts to fluidize when the capping layer **3** is heated. [0037] Specifically, when α -NPD with a glass transition point of 95°C. is used for a part of the layers constituting the organic EL element **2**, the organic material used for the capping layer **3** is composed of m-MTADATA with a glass transition point of 75°C. or TPD with a glass transition point of 60°C. Note that the melting point of α -NPD is 280°C. to 285°C., which is higher than the glass transition point. When any of the materials described above is used for the capping layer **3**, the refractive index of the capping layer **3** is in a range of 1.6 to 2.7.

[0038] The capping layer **3** is composed of a low-molecular-weight organic material that can be deposited by vapor deposition, unlike polymers, and thus the production process can be simplified.

[0039] As illustrated in FIG. 2B, foreign matter P, such as a particle, often adheres onto a part of the organic EL element **2**. In this embodiment, the capping layer **3** is in close contact with the lower side surface of the foreign matter P so that the capping layer **3** is not easily separated from the foreign matter P by a gap. As illustrated in FIG. 2B, the thickness of the capping layer **3** is smaller than the height of the foreign matter P. In this case, although the upper part of the foreign matter P is not covered with the capping layer **3**, the capping layer **3** can keep close contact with the foreign matter without having a gap therebetween. A portion **3a** of the capping layer **3** covering the side surface of the foreign matter P covers the periphery of the foreign matter P so as to swell from the element substrate **1** side toward the cover substrate **6** side, and thus the difference in level between the planer portion of the capping layer **3** and the top of the foreign matter P is decreased.

[0040] The protective layer **4** extends from on the capping layer **3** onto the element substrate **1** so as to cover the capping layer **3**. The protective layer **4** covers the organic EL elements **2** and the capping layer **3** and can protect them from moisture and external air. The protective layer **4** has a light-transmitting property and is composed of an inorganic material, such as SiNx (0 < x ≤ 1.2), SiOx (0 < x ≤ 1.2), or SiON. The thickness of the protective layer **4** is in a range of 500 nm to 5 μm. When the protective layer **4** is composed of SiNx (0 < x ≤ 1.2), SiOx (0 < x ≤ 1.2), or the like, the refractive index thereof is 1.5 to 2.0.

[0041] When the foreign matter P adheres onto the organic EL element **2**, the protective layer **4** is formed so as to cover the foreign matter P. The protective layer **4** is continuously formed on the upper surface of the capping layer, the portion **3a** and a part of the foreign matter P.

[0042] In such a manner, by covering the entire surface of the capping layer **3** comprising an organic material through which moisture and oxygen easily pass compared with the inorganic material, it is possible to reduce moisture and oxygen infiltrating into the capping layer **3**. Furthermore, since the capping layer **3** is in close contact with the foreign matter P, it is possible to reduce peeling of the protective layer **4** due to the presence of a gap.

[0043] <Manufacturing Method of Organic EL Display>

[0044] A manufacturing method of the organic EL display according to the first embodiment described above will now be described. First, a circuit layer **8** can be formed in a pre-determined pattern on an element substrate **1** using a thin-film forming technique, such as known CVD, sputtering, or spin-coating, and a thin-film processing technique, such as etching

or photolithography. Then, an insulating layer **9**, a planarizing layer **10**, a contact layer **11**, a lower electrode layer **12**, and an interlayer insulation film **15** are formed in that order on the circuit layer **8** using the thin-film forming technique and the thin-film processing technique.

[0045] Subsequently, an organic layer **13** is formed on the lower electrode layer **12** and the interlayer insulation film **15** by vapor deposition using a vapor deposition mask. Specifically, in a vacuum chamber provided with a vapor deposition source capable of heating and vaporizing a vapor deposition material on the lower part thereof, the element substrates on which the individual layers described above are formed and a vapor deposition mask having many openings are prepared. Then, the element substrate **1** is arranged on the upper part in the vacuum chamber with the side provided with the individual layers being directed downward.

[0046] The vapor deposition mask is disposed between the element substrate **1** and the vapor deposition source, and at the same time, the vapor deposition mask is aligned with the element substrate **1** so as to expose portions of the element substrate **1** on which the organic layer **13** is formed. A high vacuum is produced in the vacuum chamber, and an organic material is heated and vaporized from the vapor deposition source to form the organic layer **13** on the element substrate **1** through the openings of the vapor deposition mask.

[0047] Subsequently, with the vacuum being maintained, an upper electrode layer **14** is deposited by vapor deposition to form each of organic EL elements **2**. Then, with the vacuum being maintained, an organic material constituting a capping layer **3** is vaporized by vapor deposition to deposit an organic material layer **3'** on the upper electrode layer **14**.

[0048] Subsequently, by applying heat to the organic EL element **2** and the organic material layer **3'**, the organic material layer **3'** is fluidized. Since heat is not easily transmitted in a vacuum, the temperature of the vapor deposition source located on the lower part of the vacuum chamber is greatly different from the temperature of the element substrate **1** located on the upper part. Consequently, heat is directly applied to the element substrate **1** by a heater or the like.

[0049] The temperature applied to the organic EL element **2** and the organic material layer **3'** is higher than the glass transition point of the organic material layer **3'** and lower than the glass transition point of the organic layer **13** constituting the organic EL element **2**. Preferably, the temperature applied to the organic EL element **2** and the organic material layer **31** is lower than the glass transition point of the organic layer **13** by 10°C. or more. When the temperature is increased to the glass transition of the organic material constituting the organic material layer **3'**, the amorphous portion of the organic material layer **3'** starts to be fluidized, and when the organic EL element **2** and the organic material layer **3'** are heated up to the melting point of the organic material constituting the organic material layer **3'**, a non-amorphous portion of the organic material layer **31** starts to be fluidized. Consequently, the heating temperature for the organic EL element **2** and the organic material layer **3'** is lower than the glass transition point of the organic layer **13** constituting the organic EL element **2**. Most of the portion fluidized in the organic material layer **3'** may correspond to the amorphous portion of the organic material layer **3'**.

[0050] As a result, the amorphous portion of the organic material layer **3'** can be fluidized without fluidizing the organic layer **13** constituting the organic EL element **2**. Then, the temperature of the organic material layer **3'** is set lower

than the glass transition point of the organic material layer **3** to solidify the fluidized organic material layer **3'**, and thus a capping layer **3** is formed.

[0051] The method for forming the capping layer **3** will be described below in detail with reference to FIGS. 4A to 4C. FIGS. 4A to 4C are cross-sectional views schematically illustrating the state of the organic EL element **2** and the capping layer **3**.

[0052] As illustrated in FIG. 4A, when foreign matter **P**, such as a particle, adheres on the organic EL element **2** and the organic material layer **3'**, there may be a case where a part of the organic material layer **3'** is formed on the foreign matter **P** and a gap **G** is present between the organic EL element **2** and the foreign matter **P**. As illustrated in FIG. 4B, when the organic material layer **3'** is fluidized, the part of the organic material layer **3'** on the foreign matter **P** moves to the element substrate **1** side through the side surface of the foreign matter **P**. The fluidized organic material layer **3'** enters and fills the gap **G**. Then, the organic material layer **3'** is solidified to form the capping layer **3**.

[0053] Subsequently, the element substrate **1** is transferred to a CVD apparatus, and as illustrated in FIG. 4C, the protective layer **4** is formed by CVD on the solidified capping layer **3**. When CVD is employed, a reactive gas constituting the protective layer **4** is easily adsorbed onto a planar surface. However, when a gap **G** is present, the reactive gas does not easily infiltrate into the gap **G**, and thus pinholes may be formed in the protective layer **4**. On the other hand, according to this embodiment, the gap **G** can be filled with the capping layer **3**, and the protective layer **4** can be continuously formed on the capping layer **3**.

[0054] Finally, the organic EL elements **2** of the element substrate **1** and one surface of a cover substrate **6** are placed so as to oppose each other, and a sealing material **7** is provided in the periphery of each of the element substrate **1** and the cover substrate **6** to seal the organic EL elements **2**. A driver IC **5**, etc. is connected to the element substrate **1**, and thereby, an organic EL display is completed.

[0055] As described above, when there is a gap between the capping layer **3** and the foreign matter **P**, the gap can be filled by fluidizing the organic material layer **3'**. Such a capping layer **3** is formed on the planarizing layer **10** so as to cover the side surface of the planarizing layer **10**, as illustrated in FIG. 3. Consequently, when there is a space between the end of the planarizing layer **10** and the insulating layer **9**, the space can be filled. As a result, the step coverage of the protective layer **4** formed on the capping layer **3** can be improved. Furthermore, since the planarizing layer **10** is composed of an organic material, moisture and oxygen easily pass through the planarizing layer **10**. However, by fluidizing the organic material layer **3'**, irregularities on the planarizing layer **10** can be reduced, and the protective layer **4** can be continuously formed on the planarizing layer **10** through the capping layer **3**. As a result, it is possible to reduce moisture and oxygen passing through the planarizing layer **10** and infiltrating into the organic EL element **2**.

[0056] In the manufacturing method described above, after the organic material constituting the capping layer **3** is vaporized by vapor deposition, the organic material layer **3'** is fluidized. A method may be used in which the upper electrode layer **14** is previously heated when vapor deposition is performed so that the organic material deposited on the upper electrode layer **14** is fluidized with the heat held in the upper

electrode layer. In such a case, it is possible to shorten the period of time for manufacturing the organic EL display.

[0057] In the manufacturing method described above, after the vapor deposition material for the capping layer **3** is vaporized by vapor deposition, the organic material layer **3'** is heated without turning the element substrate **1** upside down. Specifically, the organic material layer **3'** keeps facing downward during fluidizing and vaporizing the organic material layer **3'**. However, when the viscosity of the organic material constituting the capping layer **3** is relatively low, in order to prevent the fluidized organic material layer **3'**, which has been fluidized by heating, from dripping from the surface of the upper electrode layer **14** toward the vapor deposition source located below, preferably, after the element substrate **1** is reversed such that the organic material layer **3'** is arranged above the element substrate **1**, the organic material layer **3'** is heated.

Second Embodiment

[0058] An organic EL display according to a second embodiment will be described below with reference to FIG. 5. The parts different from the first embodiment will be mainly described.

[0059] In the organic EL display according to the second embodiment, a first protective layer **16**, a capping layer **3**, and a second protective layer **17** are formed in that order on an upper electrode layer **14**. Each of the first protective layer **16** and the second protective layer **17** is composed of, for example, an inorganic material, such as SiNx ($0 < x \leq 1.2$), SiOx ($0 < x \leq 1.2$), or SiON, and the thickness thereof is in a range of 500 nm to 5 μ m, as in the protective layer **4** described above. Each of the first protective layer **16** and the second protective layer **17** is formed by known CVD. The first protective layer **16** and the second protective layer **17** protect the organic EL element **2** from moisture and external air as in the protective layer **4**.

[0060] By forming the capping layer **3** on the first protective layer **16**, even when the first protective layer **16** has a gap such as a pinhole, the gap can be covered with the capping layer **3**. Furthermore, by fluidizing the organic material layer **3'** by heating, the organic material layer **3'** is allowed to even enter the gap, and the step coverage on the first protective layer **16** can be improved. Consequently, the second protective layer **17** can be continuously formed on the capping layer **3**.

[0061] Furthermore, by doubly covering the organic EL element **2** with the first protective layer **16** and the second protective layer **17**, it is possible to reduce moisture and oxygen infiltrating into the organic EL element **2**. By forming the first protective layer **16** using SiON that can easily reduce irregularities on the substrate, the capping layer **3** can be easily formed on the first protective layer **16**, and thus the step coverage on the first protective layer **16** can be improved. Furthermore, by forming the second protective layer **17** using SiNx ($0 < x \leq 1.2$) that can more effectively prevent the infiltration of moisture and oxygen than SiON, it is possible to satisfactorily reduce degradation of the organic EL element.

Third Embodiment

[0062] An organic EL display according to a third embodiment will be described below with reference to FIG. 6. The parts different from the first embodiment will be mainly described.

[0063] In the organic EL display according to the third embodiment, a partition wall **18** having a reversed-tapered shape in which the bottom is narrower than the top is formed on an interlayer insulation film **15**, and an organic material layer **3** is formed on the side surface of the partition wall **18**.

[0064] When an organic EL element **2** is formed by known vapor deposition, the upper surface of the partition wall **18** functions as an eaves or a mask so that an organic layer **13** and an upper electrode **14** are not continuously formed at the inclined side surface of the partition wall **18**. Consequently, the upper electrode layer **14** can be divided into the individual pixels.

[0065] After an organic material layer **3'** is formed on the partition wall **18** and the organic EL element **2** by vapor deposition, a capping layer **3** is formed by heating at a temperature equal to or higher than the glass transition point of the organic material layer **3'** and equal to or lower than the glass transition point of the organic layer **13**.

[0066] As illustrated in FIG. 7, since the partition wall **18** has a reversed-tapered shape, the organic material layer **3'** before heating does not adhere to the lower side surface of the partition wall **18**, and the organic material layer **3'** is formed separately on the organic EL element **2** and on the partition wall **18**. At this stage, there may be a case where a gap **G** is formed between the organic material layer **3'** deposited on the partition wall **18** and the lower side surface of the partition wall **18**. If a protective layer **4** is formed on the organic material layer **3'** with such a gap **G** being present, the protective layer **4** does not easily adhere to the periphery of the gap **G**, and there is a possibility that pinholes may be formed in the protective layer **4**.

[0067] Consequently, in this embodiment, as described above, the organic material layer **3'** is heated at the temperature described above. Therefore, when the organic material layer **3'** is heated, as illustrated in FIG. 8 or 9, the organic material layer **3'** on the partition wall **18** is fluidized by heating and fills the gap **G**. Depending on the relationship between the material for the partition wall **18** and the material for the organic material layer **3'**, in the case where the organic material layer **3'** is not easily fluidized, a state as illustrated in FIG. 8 is obtained, and in the case where the organic material layer **3'** is easily fluidized, a state as illustrated in FIG. 9 is obtained.

[0068] As a result, as shown in FIG. 6, it is possible to enhance the quality of the protective layer **4**. Furthermore, by covering the side surface of the reversed-tapered partition wall with a part of the capping layer **3**, the step coverage of the protective layer **4** formed on the partition wall **18** can be improved, and the protective layer **4** can be formed continuously.

Fourth Embodiment

[0069] An organic EL display according to a fourth embodiment will be described below with reference to FIG. 10. The parts different from the first embodiment will be mainly described.

[0070] Foreign matter **P**, such as a particle, often adheres onto a planarizing layer **10**. In such a case, as in the embodiment described above, a pinhole may be formed due to the foreign matter **P** in a protective layer **4**.

[0071] Consequently, as in the embodiment described above, an organic material layer **3'** formed on the planarizing layer **10** is fluidized by heating so that a gap between the foreign matter **P** and the organic material layer **3'** is filled, and

thus a capping layer **3** is formed. The thickness of the capping layer **3** is smaller than the height of the foreign matter **P**. Even at such a thickness, it is possible to fill the gap caused by the foreign matter **P**. In such a case, as illustrated in FIG. 10, a part of the capping layer **3** is in contact with the lower side surface of the foreign matter **P** with an upper portion of the foreign matter **P** being exposed.

[0072] Since the part of the surface of the lower portion of the foreign matter **P** is satisfactorily covered with the capping layer **3**, it is possible to reduce pinholes which may be formed in the protective layer **3** disposed thereon.

[0073] In each of the embodiments described above, the sealing material **7** is disposed along the periphery of the element substrate **1**. However, the sealing material **7** may be formed so as to cover the entire display region between the element substrate **1** and the cover substrate **6**.

[0074] In each of the embodiments described above, a top emission structure has been explained in which light emitted from the organic EL element **2** is extracted from the cover substrate **6** side. A bottom emission structure in which light is extracted from the element substrate **1** side may be possible.

[0075] It is to be understood that the invention is not limited to the embodiments described above, and various modifications, improvements, etc. will be possible within the scope of the invention.

What is claimed is:

1. A manufacturing method of an organic EL display comprising:

preparing an organic EL element comprising an organic layer including a light emitting layer, and a pair of electrode layers disposed on both upper and lower sides of the organic layer, the organic layer comprising a first organic material;

depositing an organic material layer comprising a second organic material having a glass transition point lower than that of the first organic material, on the organic EL element;

heating the organic material layer at a temperature which is lower than the glass transition point of the first organic material and higher than that of the second organic material, to fluidize at least a part of the organic material layer;

cooling the organic material layer to a temperature which is lower than the glass transition point of the second organic material, to change the fluidized organic material layer into a capping layer by solidifying the fluidized organic material layer; and

forming a protective layer on the capping layer.

2. A manufacturing method of an organic EL display according to claim 1,

wherein, when a foreign matter is adhered to the organic EL element, a first gap is formed between the foreign matter and the organic material layer on the organic EL element before fluidizing the organic material layer.

3. A manufacturing method of an organic EL display according to claim 2,

wherein the fluidized organic material layer enters the first gap.

4. A manufacturing method of an organic EL display according to claim 2,

wherein the organic material layer comprises a first portion on the organic EL element and a second portion disposed on the foreign matter and separated from the first portion before fluidizing the organic material layer, and

wherein the second portion enters the first gap while fluidizing the organic material layer.

5. A manufacturing method of an organic EL display according to claim 1, further comprising:

forming a partition wall around the organic EL element before depositing the organic material layer, wherein a second gap is formed between the partition wall and the organic material layer before fluidizing the organic material layer.

6. A manufacturing method of an organic EL display according to claim 5, wherein the fluidized organic material layer enters the second gap.

7. A manufacturing method of an organic EL display according to claim 5, wherein the organic material layer comprises a first portion on the organic EL element and a second portion disposed on the partition wall and separated from the first portion before fluidizing the organic material layer, and wherein the second portion enters the second gap while fluidizing the organic material layer.

8. An organic EL display comprising:
an organic EL element comprising an organic layer including a light emitting layer, and a pair of electrode layers on both upper and lower sides of the organic layer, the organic layer comprising a first organic material;
a capping layer on the organic EL element, comprising a second organic material having a glass transition point lower than that of the first organic material; and
a protective layer on the capping layer;

wherein the capping layer covers at least a lower part of a first foreign matter between the organic EL element and the protective layer while an upper part of the first foreign matter is exposed from the capping layer.

9. An organic EL display comprising:

an organic EL element comprising an organic layer including a light emitting layer, and a pair of electrode layers on both upper and lower sides of the organic layer, the organic layer comprising first organic material;
a capping layer on the organic EL element, comprising second organic material having a glass transition point lower than that of the first organic material;
a protective layer on the capping layer; and
a partition wall around the organic EL element;

wherein the capping layer covers at least a lower part of the partition wall while an upper part of the partition wall is exposed from the capping layer.

10. An organic EL display according to claim 8, wherein a difference in refractive indexes between the capping layer and the protective layer is within 0.7.

11. An organic EL display according to claim 8, further comprising:

a circuit layer configured to control light emission of the organic EL element; and
a planarizing layer covering the circuit layer;
wherein the organic EL element is formed on the planarizing layer and a part of the protective layer is formed on the planarizing layer; and
wherein the capping layer has an extended portion on the planarizing layer, the extended portion covering at least a lower part a second foreign matter between the part of the protective layer and the planarizing layer while an upper part of the second foreign matter is exposed from the extended portion.

12. An organic EL display according to claim 9, further comprising:

a circuit layer configured to control light emission of the organic EL element; and
a planarizing layer covering the circuit layer;
wherein the organic EL element is formed on the planarizing layer and a part of the protective layer is formed on the planarizing layer; and
wherein the capping layer has an extended portion on the planarizing layer, the extended portion covering at least a lower part of a second foreign matter between the protective layer and the planarizing layer while an upper part of the second foreign matter is exposed from the extended portion.

13. An organic EL display according to claim 12, further comprising:

an element substrate comprising the circuit layer;
a cover substrate disposed on the element substrate to be opposite to the element substrate; and
a sealing material disposed between the element substrate and cover substrate, surrounding the organic EL element;

wherein the capping layer is formed inside a region surrounded by the sealing material.

14. An organic EL display according to claim 13, further comprising:

an element substrate comprising the circuit layer;
a cover substrate disposed on the element substrate to be opposite to the element substrate; and
a sealing material disposed between the element substrate and cover substrate, surrounding the organic EL element;

wherein the capping layer is formed inside a region surrounded by the sealing material.

15. An organic EL display according to claim 12, further comprising:

an element substrate comprising the circuit layer;
a cover substrate disposed on the element substrate to be opposite to the element substrate; and
a sealing material disposed between the element substrate and cover substrate, contacting the protective layer on the organic EL element.

16. An organic EL display according to claim 13, further comprising:

an element substrate comprising the circuit layer;
a cover substrate disposed on the element substrate to be opposite to the element substrate; and
a sealing material disposed between the element substrate and cover substrate, contacting the protective layer on the organic EL element.

17. An organic EL display according to claim 8, wherein the lower part of the first foreign matter is the lower side surface thereof.

18. An organic EL display according to claim 9, wherein the lower part of the partition wall is the lower side surface thereof.

19. An organic EL display according to claim 11, wherein the lower part of the second foreign matter is the lower side surface thereof.

20. An organic EL display according to claim 12, wherein the lower part of the second foreign matter is the lower side surface thereof.

专利名称(译)	有机EL显示器及其制造方法		
公开(公告)号	US20080129194A1	公开(公告)日	2008-06-05
申请号	US11/976612	申请日	2007-10-25
[标]申请(专利权)人(译)	京瓷株式会社		
申请(专利权)人(译)	京瓷株式会社		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	ABE SHINICHI ASANO MOTOHIKO OGAWA HIROMITSU		
发明人	ABE, SHINICHI ASANO, MOTOHIKO OGAWA, HIROMITSU		
IPC分类号	H01L51/54 C09K11/02		
CPC分类号	H01L51/5237 H01L51/5253 H01L51/524		
优先权	2006291550 2006-10-26 JP		
其他公开文献	US8053983		
外部链接	Espacenet USPTO		

摘要(译)

有机EL显示器包括元件基板，形成在元件基板上的有机EL元件，包括有机层和有机层，有机层包括发光层和设置在有机层两侧的一对电极层。有机层包含第一有机材料。有机EL显示器还包括覆盖层，该覆盖层包括第二有机材料，该第二有机材料具有低于第一有机材料之一的玻璃化转变点和覆盖层上的保护层。

