



US007255938B2

(12) **United States Patent**
Hamada et al.

(10) **Patent No.:** **US 7,255,938 B2**
(45) **Date of Patent:** **Aug. 14, 2007**

(54) **ORGANIC ELECTROLUMINESCENT DEVICE AND ORGANIC COMPOUND FOR USE IN ORGANIC ELECTROLUMINESCENT DEVICE**

(75) Inventors: **Yuji Hamada**, Nara (JP); **Nobuo Saito**, Gifu (JP); **Kazuki Nishimura**, Hirakata (JP); **Hiroshi Kanno**, Osaka (JP)

(73) Assignee: **Sanyo Electric Co., Ltd.**, Osaka (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 142 days.

(21) Appl. No.: **10/950,669**

(22) Filed: **Sep. 28, 2004**

(65) **Prior Publication Data**

US 2005/0118456 A1 Jun. 2, 2005

(30) **Foreign Application Priority Data**

Sep. 30, 2003 (JP) 2003-342592

(51) **Int. Cl.**
H01L 51/50 (2006.01)

(52) **U.S. Cl.** **428/690; 428/917; 313/504;**
..... **313/506**

(58) **Field of Classification Search** **428/690;**
..... **428/917; 313/504, 506**

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,281,489 A * 1/1994 Mori et al. 428/690
2002/0086180 A1 * 7/2002 Seo et al. 428/690
2003/0215667 A1 * 11/2003 Xie 428/690

FOREIGN PATENT DOCUMENTS

JP	4-334894 A	11/1992
JP	9-63770 A	3/1997
JP	10-36832 A	2/1998
JP	10-294179 A	11/1998
JP	2000-164362 A	6/2000
JP	2001-338761 A	12/2001
JP	2003-51388 A	2/2003
JP	2004-146221 A	5/2004

* cited by examiner

Primary Examiner—Dawn L. Garrett

(74) *Attorney, Agent, or Firm*—Kubovcik & Kubovcik

(57) **ABSTRACT**

An organic electroluminescent device includes a hole-injecting electrode, an electron-injecting electrode and a blue light-emitting layer which is provided between the electrodes and contains a host material, a luminescent dopant and an assist dopant for complementing carrier transport of the host material. When the host material is an electron-transporting material, the assist dopant has a smaller absolute HOMO (Highest Occupied Molecular Orbital) energy level than the host material and a higher hole mobility than the host material.

9 Claims, 1 Drawing Sheet





FIG. 1



**ORGANIC ELECTROLUMINESCENT
DEVICE AND ORGANIC COMPOUND FOR
USE IN ORGANIC ELECTROLUMINESCENT
DEVICE**

BACKGROUND OF THE INVENTION

1. Field of the Invention

The invention relates to an organic electroluminescent device and an organic compound for use in such an organic electroluminescent device and particularly to an organic electroluminescent device having a blue light-emitting layer and an organic compound which can be used as a blue light-emitting material for an organic electroluminescent device.

2. Description of the Related Art

Organic electroluminescent devices are a light-emitting device in which holes injected from a hole-injecting electrode and electrons injected from an electron-injecting electrode are recombined at an interface between a light-emitting layer and a carrier-transporting layer or recombined in a light-emitting layer to produce light emission. Such organic electroluminescent devices can be driven by relatively low voltage as compared with inorganic electroluminescent devices, and thus their application to flat panel displays particularly has received attention in recent years.

Luminescent materials can be selected so as to form an organic electroluminescent device capable of emitting light of the desired color. Thus, organic electroluminescent devices are expected to be a multicolor or full-color display device.

Organic electroluminescent devices have been required to have high brightness, high luminous efficiency, and high reliability. Japanese Patent Application Laid-Open (JP-A) No. 2000-164362 discloses an organic electroluminescent device comprising a red light-emitting layer or a green light-emitting layer and a carrier-transporting layer, wherein the carrier-transporting layer and/or the light-emitting layer is doped with a dopant for transporting carriers or for transferring excitation energy so that emission properties and lifetime can be improved.

However, such improvements are not specifically investigated for organic electroluminescent devices having a blue light-emitting layer. Thus, there has been a demand for an organic electroluminescent device with a blue light-emitting layer, which can have improved luminous efficiency and improved reliability.

SUMMARY OF THE INVENTION

It is an object of the invention to provide an organic electroluminescent device comprising a blue light-emitting layer which can have high luminous efficiency and high reliability and to provide an organic compound which can be used as a blue light-emitting material for such an organic electroluminescent device.

The invention is directed to an organic electroluminescent device, comprising: a hole-injecting electrode; an electron-injecting electrode; and a light-emitting layer provided between the hole-injecting electrode and the electron-injecting electrode, wherein the light-emitting layer is a blue light-emitting layer which contains a host material, a luminescent dopant and an assist dopant for complementing carrier transport of the host material.

According to the invention, the blue light-emitting layer contains a host material, a luminescent dopant and an assist dopant. The assist dopant complements carrier transport of the host material. Thus, the carrier transport is accelerated by the assist dopant in the light-emitting layer so that the probability of carrier recombination can be increased and that the luminous efficiency is increased. Thus, the reliability can also be increased.

In the light-emitting layer, the content of the host material is generally higher than that of any other component. The host material serves to facilitate the film formation of the light-emitting layer and to support the light-emitting layer film. Thus, the host material should be stable and should be resistant to crystallization after the film production and resistant to chemical change. When an electric current is applied between the electrodes, carriers are generally recombined in the host molecule. Thus, the host material plays a role in transferring the excitation energy to the luminescent dopant and allowing the luminescent dopant to emit light.

The luminescent dopant is a fluorescent or phosphorescent compound, which receives excitation energy from the host molecule and is excited and quenched to emit light.

The assist dopant plays a role in complementing the carrier transport properties of the host material and accelerating the injection and transfer of the carriers into the light-emitting layer.

If the host material is an electron-transporting material, namely, a material that dominantly causes electron transfer rather than hole transfer, the assist dopant should be a hole-transporting material, which is a material that dominantly causes hole transfer rather than electron transfer. If the host material is a hole-transporting material, on the other hand, the assist dopant should be an electron-transporting material. If the light-emitting layer contains both the hole-transporting material and the electron-transporting material, which have opposite properties, in a mixed manner, namely, if the light-emitting layer itself is bipolar or capable of transporting both types of carriers, it can have an increased probability of recombination in the light-emitting layer and thus have improved luminous efficiency.


The hole-transporting material serving as the assist dopant preferably has a smaller absolute HOMO (Highest Occupied Molecular Orbital) energy level than the host material and a higher hole mobility than the host material. The electron-transporting material serving as the assist dopant preferably has a larger absolute LUMO (Lowest Unoccupied Molecular Orbital) energy level than the host material and a higher electron mobility than the host material.

The electron-transporting host material may be an anthracene derivative. In this case, the hole-transporting material is used as the assist dopant as stated above. Such a hole-transporting assist dopant may be a phenylamine derivative. In this case, examples of the luminescent dopant include a perylene derivative, an oxadiazole derivative or an anthracene derivative etc.

In the invention, the assist dopant may be contained only in a partial region of the blue light-emitting layer along its thickness direction. Namely, the blue light-emitting layer comprises the host material, the luminescent dopant and the assist dopant, wherein the assist dopant may be contained only in a partial region along the thickness direction of the blue light-emitting layer. In this case, the other region only contains the host material and the luminescent dopant. If the assist dopant-containing region is restricted in such a manner, the carriers would be efficiently transferred to the light-emitting region so that the probability of recombination can be increased and the luminous efficiency can be improved.

In a preferred mode of the invention, the blue light-emitting layer has a luminescence peak wavelength of from 450 nm to 520 nm, and the color of the emitted light is blue to blue-green.

The invention is also directed to an organic compound for use in an organic electroluminescent device, comprising an anthracene derivative represented by Structural Formula (1) below (hereinafter also referred to as DBzA).



15

The above organic compound may be used as a luminescent material for an organic electroluminescent device, specifically as the luminescent dopant according to the invention.

The above organic compound may be used as a blue light-emitting material.

According to the invention, the organic electroluminescent device comprising the blue light-emitting layer can have high luminous efficiency and high reliability.

20

25

BRIEF DESCRIPTION OF THE DRAWING

30

FIG. 1 is a schematic cross-sectional view showing an organic electroluminescent device prepared in Examples according to the invention.

35

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The invention is described in more detail by means of the examples below, which are not intended to limit the scope of the invention. It will be understood that various modifications can be made thereto without departing from the gist of the invention.


40

45

Host Material

The anthracene derivative represented by Structural Formula (2) below (hereinafter referred to as DNA) is used as the host material in the examples and the comparative examples.

(1)



(2)


DNA

Examples of any other anthracene derivative to be used as host material include analogues of the Formula (2) compound which have any other substituent in place of the substituent C(CH₃)₃ and other analogues of the Formula (2) compound which have the substituent C(CH₃)₃ or any other substituent at any other position.


Luminescent Dopant

DBzA, the perylene derivative represented by Structural Formula (3) below and the oxadiazole derivative represented by Structural Formula (4) below are used as the luminescent dopants in the examples and the comparative examples.

(3)



-continued



Examples of the anthracene derivative to be used as luminescent dopant include DBzA analogues having any other substituent in place of the substituent CH₃ and other analogues which have the substituent CH₃ or any other substituent at any other position.

Examples of any other perylene derivative to be used as luminescent dopant include analogues of the Formula (3) compound which have any other substituent in place of the substituent C(CH₃)₃ and other analogues of the Formula (3) compound which have the substituent C(CH₃)₃ or any other substituent at any other position.


Examples of any other oxadiazole derivative to be used as luminescent dopant include analogues of the Formula (4) compound which have any other substituent in place of the substituent N(CH₃)₂ and other analogues of the Formula (4) compound which have the substituent N(CH₃)₂ or any other substituent at any other position.

Synthesis of DBzA


DBzA (9,10-bis(4-(6-methylbenzothiazole-2-yl)phenyl)anthracene may be synthesized by a series of reactions as shown in the formula below. Compound A (1-iodo-(4-(6-methylbenzothiazole-2-yl)phenyl) is used as a starting material. The iodine of Compound A is replaced with lithium. The lithium-substituted product is allowed to react with anthraquinone to form Compound B, which is then converted into DBzA by dehydration reaction.

(4)

-continued




Compound B




Compound A


40




45



55



60



DBzA



Example of DBzA Synthesis Method

Compound A (10 g, 0.0284 mol) is placed in an argon-filled glass vessel, and 100 ml of dry toluene is added thereto and stirred. A hexane solution of 1.1 equivalents of n-BuLi is added per one equivalent of Compound A and stirred. Anthraquinone (2.9 g, 0.0139 mol) is placed in an argon-filled glass vessel, and 100 ml of dry toluene is added thereto and stirred. The product of replacing iodine with Li in Compound A is slowly added dropwise to the resulting anthraquinone solution. After the addition is completed, the mixture is stirred at room temperature for 24 hours. The reaction solution is transferred to a separating funnel and washed with dilute hydrochloric acid and water. The organic layer is dried by addition of magnesium sulfate. After the drying agent is separated, the solvent is removed under reduced pressure. The resulting Compound B is purified using a silica gel column. The purified Compound B is dissolved in 300 ml of THF, and then a solution of tin chloride in hydrochloric acid is added thereto and stirred at room temperature for 12 hours. The reaction solution is transferred to a separating funnel, mixed with toluene, then washed with dilute hydrochloric acid and water, and dried by addition of magnesium sulfate. After the drying agent is separated, the solvent is removed under reduced pressure, and then the resulting DBzA is purified using a silica gel column.


The molecular weight of the resulting DBzA is measured by mass spectroscopy (MALDI-TOFMS) and found to be 624.214. The result of elemental analysis is as follows: C: 80.8% by weight, H: 4.99% by weight, N: 5.03% by weight (Calculation: C: 80.74% by weight, H: 4.52% by weight, N: 4.48% by weight).

Assist Dopant

In the examples, the phenylamine derivatives (NBP, mTPD and pTPD) each represented by the formula below are used as the assist dopants.




-continued



20 Examples of any other phenylamine derivative to be used as assist dopant include NPB derivatives having the skeleton represented by the structural formula of NPB.

Hole-Injecting Layer

25 The copper phthalocyanine represented by the structural formula below (hereinafter referred to as CuPc) is used in the examples and the comparative examples.




Hole-Transporting Layer

45 In the examples and the comparative examples, NBP is used to form the hole-transporting layer.

Electron-Transporting Layer

50 In the examples and the comparative examples, tris(8-quinolinolato)aluminum represented by the structural formula below (hereinafter referred to as Alq) is used to form the electron-transporting layer.



65 Table 1 shows the HOMO (Highest Occupied Molecular Orbital) energy level and the hole mobility of each of the host material and the assist dopants.

TABLE 1

		HOMO Energy (eV)	Hole Mobility (cm ² /Vs)
Host Material	DNA	5.6	10 ⁻⁷
Assist Dopant	NPB	5.4	10 ⁻⁴
	mTPD	5.3	10 ⁻³
	pTPD	5.25	10 ⁻³

The host material DNA is an electron-transporting material, while the assist dopants NPB, mTPD and pTPD are

5

The half life (the period for which the initial brightness (500 cd/m²) is reduced to half) was measured in a constant-current continuous-emission mode. The result of the measurement is shown as lifetime in Table 2.

COMPARATIVE EXAMPLE 1

An organic electroluminescent device was prepared using the process of Example 1 except that the blue light-emitting layer was free of the assist dopant NPB. Evaluation was performed as in Example 1. The results of the evaluation are shown in Table 3.

TABLE 2

	Anode	Hole-Injecting Layer	Hole-Transporting Layer	Blue Light-Emitting Layer				Electron-Transporting Layer		Cathode	
				Thickness: (nm)	Thickness: (nm)	Host (nm)	Luminous Material Dopant	Assist Dopant	Thickness: (nm)		
Ex. 1	ITO	CuPc(10)	NPB(75)	40	DNA	Formula (1) DBzA (2.5% by Weight)	NPB (7% by Weight)	Alq(10)	LiF(1)/ Al(200)		
Comp. Ex. 1	ITO	CuPc(10)	NPB(75)	40	DNA	Formula (1) DBzA (2.5% by Weight)	Absent	Alq(10)	LiF(1)/ Al(200)		

each a hole-transporting material. As appeared in Table 1, the assist dopant materials each have a smaller absolute HOMO energy level than the host material DNA and a 35 higher hole mobility than the host material DNA.

EXAMPLE 1

As shown in FIG. 1, a transparent hole-injecting electrode (anode) 2 made of an indium-tin compound (hereinafter referred to as ITO) was formed on a glass substrate 1, and a hole-injecting layer 3 made of CuPc (10 nm in thickness) was formed on the hole-injecting electrode 2. A hole-transporting layer 4 made of NPB (75 nm in thickness) was formed on the hole-injecting layer 3.

40

A blue light-emitting layer 5 was formed on the hole-transporting layer 4. The blue light-emitting layer 5 was made of a composition comprising a host material of DNA which contained 2.5% by weight of the luminescent dopant DBzA and 7% by weight of the assist dopant NPB.

45

An electron-transporting layer 6 (10 nm in thickness) made of Alq was formed on the blue light-emitting layer 5. An electron-injecting electrode (cathode) 7 composed of LiF (1 nm in thickness) and Al (200 nm in thickness) was formed on the electron-transporting layer 6.

55

Each layer was formed in a vacuum of 5×10^{-5} Pa by a resistance-heating vacuum deposition method.

60

The organic electroluminescent device prepared as described above was evaluated for light-emitting properties. The luminous efficiency, the voltage and the chromaticity were measured when the brightness of the emitted light was 500 cd/m². The results of the measurement are shown in Table 2.

TABLE 3

	Luminous Efficiency (cd/A)	Voltage (V)	Chromaticity		Lifetime (Hours)
			x	y	
Ex. 1	3.5	7.9	0.150	0.135	750
Comp. Ex. 1	2.6	8.3	0.151	0.134	400

45

50

55

60

65

70

75

80

85

90

95

100

105

110

115

120

125

130

135

140

145

150

155

160

165

170

175

180

185

190

195

200

205

210

215

220

225

230

235

240

245

250

255

260

265

270

275

280

285

290

295

300

305

310

315

320

325

330

335

340

345

350

355

360

365

370

375

380

385

390

395

400

405

410

415

420

425

430

435

440

445

450

455

460

465

470

475

480

485

490

495

500

505

510

515

520

525

530

535

540

545

550

555

560

565

570

575

580

585

590

595

600

605

610

615

620

625

630

635

640

645

650

655

660

665

670

675

680

685

690

695

700

705

710

715

720

725

730

735

740

745

750

755

760

765

770

775

780

785

790

795

800

805

810

815

820

825

830

835

840

845

850

855

860

865

870

875

880

885

890

895

900

905

910

915

920

925

930

935

940

945

950

955

960

965

970

975

980

985

990

995

1000

1005

1010

1015

1020

1025

1030

1035

1040

1045

1050

1055

1060

1065

1070

1075

1080

1085

1090

1095

1100

1105

1110

1115

1120

1125

1130

1135

1140

1145

1150

1155

1160

1165

1170

1175

1180

1185

1190

1195

1200

1205

1210

1215

1220

1225

1230</

TABLE 4

Anode	Hole-Injecting	Hole-Transporting	First Blue Light-Emitting Layer				Second Blue Light-Emitting Layer				Electron-Transporting	Cathode
	Layer (Thickness: nm)	Layer (Thickness: nm)	Thickness (nm)	Host Material	Luminous Dopant	Assist Dopant	Thickness (nm)	Host Material	Luminous Dopant	Assist Dopant	Layer (Thickness: nm)	(Thickness: nm)
Ex. 2 ITO	CuPc(10)	NPB(75)	10	DNA	Formula (1) DBzA (2.5% by Weight)	NPB (7% by weight)	30	DNA	Formula (1) DBzA (2.5% by Weight)	Absent	Alq(10)	LiF(1)/Al(200)

The blue organic electroluminescent device of this example was evaluated for light-emitting properties as in Example 1. The result of the evaluation is shown in Table 5.

TABLE 5

Ex. 2	Luminous Efficiency (cd/A)	Voltage (V)	Chromaticity		Lifetime (Hours)
	x	y			
Ex. 2	5.1	7.1	0.150	0.136	1100

A comparison with the results of Example 1 shown in Table 3 indicates that the light-emitting properties and the reliability can be improved if the assist dopant is contained only in a partial region of the blue light-emitting layer along its thickness direction as in the Example. This is probably because the assist dopant contained restrictively in a specific region of the light-emitting layer can efficiently transfer carriers to the light-emitting region so that the recombination probability can be increased.

EXAMPLES 3 TO 6 AND COMPARATIVE EXAMPLES 2 AND 3

Blue organic electroluminescent devices were prepared using DNA as the host material for the light emitting layer

15 and using the process of Example 1, except that each light-emitting layer was formed using the specific content of each of the luminescent dopant and the assist dopant as shown in Table 6.

20 In Example 3, the blue light-emitting layer contains 2% by weight of the perylene derivative of Structural Formula (3) as a luminescent dopant and 7% by weight of NPB as an assist dopant. In Example 4, the blue light-emitting layer 25 contains 2% by weight of the oxadiazole derivative of Structural Formula (4) as a luminescent dopant and 7% by weight of NPB as an assist dopant. In Example 5, the blue light-emitting layer contains 2% by weight of DBzA as a luminescent dopant and 7% by weight of mTPD as an assist dopant. In Example 6, the blue light-emitting layer contains 30 2% by weight of DBzA as a luminescent dopant and 7% by weight of pTPD as an assist dopant.

35 In Comparative Example 2, the blue light-emitting layer contains 2% by weight of the perylene derivative of Structural Formula (3) as a luminescent dopant and no assist dopant. In Comparative Example 3, the blue light-emitting layer contains 2% by weight of the oxadiazole derivative of 40 Structural Formula (4) as a luminescent dopant and no assist dopant.

TABLE 6

Anode	Hole-Injecting Layer (Thickness: nm)	Hole-Transporting Layer (Thickness: nm)	Blue Light-Emitting Layer				Electron-Transporting Layer	Cathode
			Thickness (nm)	Host Material	Luminous Dopant	Assist Dopant	(Thickness: nm)	(Thickness: nm)
Ex. 3 ITO	CuPc(10)	NPB(75)	40	DNA	Formula (3) (2% by Weight)	NPB (7% by weight)	Alq(10)	LiF(1)/Al(200)
Ex. 4 ITO	CuPc(10)	NPB(75)	40	DNA	Formula (4) (2% by Weight)	NPB (7% by weight)	Alq(10)	LiF(1)/Al(200)
Ex. 5 ITO	CuPc(10)	NPB(75)	40	DNA	Formula (1) DBzA (2% by Weight)	mTPD (7% by Weight)	Alq(10)	LiF(1)/Al(200)
Ex. 6 ITO	CuPc(10)	NPB(75)	40	DNA	Formula (1) DBzA (2% by Weight)	pTPD (7% by Weight)	Alq(10)	LiF(1)/Al(200)

TABLE 6-continued

Anode	Hole-Injecting Layer	Hole-Transporting Layer	Blue Light-Emitting Layer				Electron-Transporting Layer	Cathode
	(Thickness: nm)	(Thickness: nm)	Thickness (nm)	Host Material	Luminescent Dopant	Assist Dopant	(Thickness: nm)	(Thickness: nm)
Comp. Ex. 2	ITO	CuPc(10)	NPB(75)	40	DNA Formula (3) (2% by Weight)	Absent	Alq(10)	LiF(1)/Al(200)
Comp. Ex. 3	ITO	CuPc(10)	NPB(75)	40	DNA Formula (4) (2% by Weight)	Absent	Alq(10)	LiF(1)/Al(200)

Each of the organic electroluminescent devices was evaluated for light-emitting properties and lifetime as in Example 1. The results of the evaluation are shown in Table 7.

TABLE 7

	Luminous Efficiency	Voltage	Chromaticity		Lifetime	25
	(cd/A)	(V)	x	y	(Hours)	
Ex. 3	2.4	8.5	0.151	0.161	300	
Ex. 4	2.1	8.8	0.151	0.18	240	
Ex. 5	4.2	7.6	0.15	0.135	900	30
Ex. 6	4.4	7.5	0.15	0.135	980	
Comp. Ex. 2	1.8	8.9	0.151	0.16	150	
Comp. Ex. 3	1.6	9.3	0.15	0.181	100	



The results shown in Table 7 indicate that each of Examples 3 to 6, in which the blue light-emitting layer contains the assist dopant according to the present invention, exhibits higher light-emitting properties and reliability as compared with Comparative Examples 2 and 3.

What is claimed is:

1. An organic electroluminescent device, comprising: a hole-injecting electrode; an electron-injecting electrode; and a light-emitting layer provided between the hole-injecting electrode and the electron-injecting electrode,

wherein the light-emitting layer is a blue light-emitting layer which contains a host material, a luminescent dopant and an assist dopant for complementing carrier transport of the host material, and

further wherein the luminescent dopant is an organic compound comprising an anthracene derivative represented by Structural Formula (1):



2. The organic electroluminescent device of claim 1, wherein a hole transporting material is used as the assist dopant when the host material is an electrontransporting material; or an electron-transporting material is used as the assist dopant when the host material is a hole-transporting material.

3. The organic electroluminescent device of claim 2, wherein the hole-transporting material used as the assist dopant has a smaller absolute value of HOMO (Highest Occupied Molecular Orbital) energy level than that of the host material and has a higher hole mobility than that of the host material.

4. The organic electroluminescent device of claim 2, wherein the electron-transporting material used as the assist dopant has a larger absolute value of LUMO (Lowest Unoccupied Molecular Orbital) energy level than that of the host material and has a higher electron mobility than that of the host material.

5. The organic electroluminescent device of claim 1, wherein the host material is an anthracene derivative.

6. The organic electroluminescent device of claim 1, wherein the assist dopant is a phenylamine derivative.

7. The organic electroluminescent device of claim 1, wherein the assist dopant is contained only in a partial region of the blue light-emitting layer along its thickness direction.

8. The organic electroluminescent device of claim 1, wherein the blue light-emitting layer has a luminescence peak wavelength of from 450 nm to 520 nm.


9. An organic electroluminescent device, comprising a luminescent material that is an anthracene derivative represented by Structural Formula (1):

US 7,255,938 B2

15

16

(1)



* * * * *

专利名称(译)	有机电致发光器件和用于有机电致发光器件的有机化合物		
公开(公告)号	US7255938	公开(公告)日	2007-08-14
申请号	US10/950669	申请日	2004-09-28
[标]申请(专利权)人(译)	滨田YUJI 斎藤信雄 西村KAZUKI 菅野HIROSHI		
申请(专利权)人(译)	滨田YUJI 斎藤信雄 西村KAZUKI 菅野HIROSHI		
当前申请(专利权)人(译)	SANYO ELECTRIC CO. , LTD.		
[标]发明人	HAMADA YUJI SAITO NOBUO NISHIMURA KAZUKI KANNO HIROSHI		
发明人	HAMADA, YUJI SAITO, NOBUO NISHIMURA, KAZUKI KANNO, HIROSHI		
IPC分类号	H01L51/50 B32B9/00 C09K11/06 H01L51/00 H05B33/14 H05B33/22		
CPC分类号	H01L51/0052 H01L51/0058 H01L51/5012 H01L51/002 H01L51/0059 H01L51/007 H01L51/0071 H01L51/0078 H01L51/0081 H01L2251/308 Y10S428/917		
优先权	2003342592 2003-09-30 JP		
其他公开文献	US20050118456A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机电致发光器件，包括空穴注入电极，电子注入电极和蓝色发光层，蓝色发光层设置在电极之间并含有主体材料，发光掺杂剂和辅助掺杂剂，用于补充主体材料的载流子传输。当主体材料是电子传输材料时，辅助掺杂剂具有比主体材料更小的绝对HOMO (最高占据分子轨道)能级和比主体材料更高的空穴迁移率。

