



US007476900B2

(12) **United States Patent**
Yamauchi et al.

(10) **Patent No.:** US 7,476,900 B2
(45) **Date of Patent:** Jan. 13, 2009

(54) **THIN FILM TRANSISTOR, ORGANIC ELECTROLUMINESCENCE DISPLAY DEVICE AND MANUFACTURING METHOD OF THE SAME**

(75) Inventors: **Yukio Yamauchi**, Atsugi (JP); **Michio Arai**, Chuo (JP)

(73) Assignees: **Semiconductor Energy Laboratory Co., Ltd.**, Kanagawa-ken (JP); **TDK Corporation**, Tokyo (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 119 days.

(21) Appl. No.: **11/296,436**

(22) Filed: **Dec. 8, 2005**

(65) **Prior Publication Data**

US 2006/0087222 A1 Apr. 27, 2006

Related U.S. Application Data

(62) Division of application No. 11/041,702, filed on Jan. 25, 2005, now Pat. No. 6,992,435, which is a division of application No. 09/266,012, filed on Mar. 11, 1999, now Pat. No. 6,853,083, which is a division of application No. 08/855,391, filed on May 13, 1997, now Pat. No. 5,897,328, which is a division of application No. 08/617,121, filed on Mar. 18, 1996, now Pat. No. 5,640,067.

(30) **Foreign Application Priority Data**

Mar. 24, 1995 (JP) 7-065943

(51) **Int. Cl.**

H01L 27/14 (2006.01)
H01L 29/04 (2006.01)
H01L 29/15 (2006.01)
H01L 31/036 (2006.01)

(52) **U.S. Cl.** 257/72; 257/59

(58) **Field of Classification Search** 257/40, 257/59, 72
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,885,196 A 5/1975 Fischer

(Continued)

FOREIGN PATENT DOCUMENTS

JP 62-259469 11/1987

(Continued)

OTHER PUBLICATIONS

Specification, claims, abstract and drawings, U.S. Appl. No. 08/205,300, as filed Mar. 3, 1994.

Primary Examiner—Jerome Jackson, Jr.


Assistant Examiner—Anthony Ho

(74) *Attorney, Agent, or Firm*—Eric J. Robinson; Robinson Intellectual Property Law Office, P.C.

(57) **ABSTRACT**

An organic EL display device has a substrate, a plurality of organic EL elements formed on the substrate and a plurality of thin film transistors formed on the substrate. The transistors are connected to the respective EL elements for controlling current applied to the respective elements. Each of the transistors includes an active layer of semiconductor material, formed on the substrate, a source region and a drain region being formed in the active layer, a source electrode of aluminum material electrically coupled to the source region formed in the active layer, a drain electrode of aluminum material electrically coupled to the drain region formed in the active layer, an insulation layer formed on the active layer, a gate electrode formed on the insulation layer, a first barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or titanium, inserted between the source electrode and the source region of the active layer, and a second barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or titanium, inserted between the drain electrode and the drain region of the active layer.

18 Claims, 3 Drawing Sheets



US 7,476,900 B2

Page 2

U.S. PATENT DOCUMENTS

4,042,854 A	8/1977	Luo et al.	5,808,315 A	9/1998	Murakami et al.
4,266,223 A	5/1981	Frame	5,828,429 A	10/1998	Takemura
4,368,467 A	1/1983	Unotoro et al.	5,986,632 A	11/1999	Takayama et al.
4,511,756 A	4/1985	Moeller et al.	6,023,308 A	2/2000	Takemura
4,523,189 A	6/1985	Takahara et al.	6,031,290 A	2/2000	Miyazaki et al.
4,528,480 A	7/1985	Unagami et al.	6,147,451 A	11/2000	Shibata et al.
4,602,192 A	7/1986	Nomura et al.	6,166,414 A	12/2000	Miyazaki et al.
4,837,566 A	6/1989	Channing et al.	6,448,612 B1	9/2002	Miyazaki et al.
4,887,146 A	12/1989	Hinode	2002/0179969 A1	12/2002	Miyazaki et al.
5,095,248 A	3/1992	Sato	2004/0023445 A1	2/2004	Miyazaki et al.
5,250,931 A	10/1993	Misawa et al.	2004/0051102 A1	3/2004	Miyazaki et al.
5,276,380 A	1/1994	Tang			
5,294,869 A	3/1994	Tang et al.			
5,294,870 A	3/1994	Tang et al.			
5,302,966 A	4/1994	Stewart	JP	62-280890	12/1987
5,384,267 A	1/1995	Hutchins et al.	JP	03-108767	5/1991
5,384,517 A	1/1995	Uno	JP	03-216996	9/1991
5,396,084 A *	3/1995	Matsumoto	JP	4-125683	4/1992
5,508,715 A	4/1996	Kuroki	JP	04-328791	11/1992
5,526,013 A	6/1996	Ono et al.	JP	6-064229	3/1994
5,550,066 A	8/1996	Tang et al.	JP	06-088973	3/1994
5,578,166 A	11/1996	Hirota	JP	06-232129	8/1994
5,621,427 A	4/1997	Kanbe et al.	JP	06-260500	9/1994
5,623,157 A	4/1997	Miyazaki et al.	JP	06-260650	9/1994
5,642,129 A	6/1997	Zavracky et al.	JP	06-090954	11/1994
5,670,792 A	9/1997	Utsugi et al.	JP	06-314698	11/1994
5,677,240 A	10/1997	Murakami et al.	JP	06-314784	11/1994
5,684,365 A	11/1997	Tang et al.	JP	06-314786	11/1994
5,714,968 A	2/1998	Ikeda	JP	06-325869	11/1994
5,804,878 A	9/1998	Miyazaki et al.			

FOREIGN PATENT DOCUMENTS

JP	62-280890	12/1987
JP	03-108767	5/1991
JP	03-216996	9/1991
JP	4-125683	4/1992
JP	04-328791	11/1992
JP	6-064229	3/1994
JP	06-088973	3/1994
JP	06-232129	8/1994
JP	06-260500	9/1994
JP	06-260650	9/1994
JP	06-090954	11/1994
JP	06-314698	11/1994
JP	06-314784	11/1994
JP	06-314786	11/1994
JP	06-325869	11/1994

* cited by examiner



Fig. 1*Fig. 2*






Fig. 3a*Fig. 3b**Fig. 3c**Fig. 3d*

Fig. 4
Y-DIRECTION PERIPHERAL DRIVE CIRCUIT



THIN FILM TRANSISTOR, ORGANIC ELECTROLUMINESCENCE DISPLAY DEVICE AND MANUFACTURING METHOD OF THE SAME

FIELD OF THE INVENTION

The present invention relates to a thin film transistor used in an organic electroluminescence (EL) display device, the organic EL display device and a method of manufacturing the organic EL display device.

DESCRIPTION OF THE RELATED ART

In an organic EL display device, many of organic EL elements are arranged in matrix on a substrate. Each of the EL elements, namely a pixel (picture element), consists of a transparent electrode layer, an organic EL layer and an upper electrode layer. At least one thin film transistor for controlling current applied to the EL element is electrically connected to this EL element.

In general, each of the thin film transistors has a silicon active layer with a source region and a drain region, and source and drain electrodes of aluminum material to be electrically connected to the source and drain regions, respectively. In the conventional thin film transistor, barrier metal layers made of chrome material are inserted between the silicon active layer and the source and drain electrodes so as to prevent silicon atoms in the silicon active layer from being diffused and disappeared into the source and drain electrodes of aluminum material.

However, according to the conventional organic EL display device, chrome used for material of the barrier metal layers of the thin film transistors often elutes into the upper electrode layers and the transparent electrode layers of the EL elements causing the thin film transistors to short-circuit with the upper electrode layers or the transparent electrode layers. Subsequently to this, all the chrome of the barrier metal layers may elute so that hollow spaces will be formed between the source and drain regions of the silicon active layers and the aluminum source and drain electrodes. This results disconnection of the source and drain regions and the respective electrodes. These short-circuit and disconnection will stop operations of the thin film transistors causing reliability of the organic EL display device to extremely lower.

SUMMARY OF THE INVENTION

It is therefore an object of the present invention to provide a thin film transistor used in an organic EL display device, the organic EL display device and a method of manufacturing the organic EL display device, whereby short-circuit and disconnection in the organic EL display device due to elusion of the barrier metal material of the thin film transistors can be prevented from occurring to keep high reliability of the organic EL display device.

According to careful study by the inventors of this application, it has come out that the aforementioned short-circuit and disconnection are caused by movement of ionized chrome to the organic EL elements. The ionization of the chrome and the movement of the ionized chrome will be occurred due to moisture provided from the organic EL layer made of high hydroscopic material and due to relatively high DC current (bias current) continuously flowing through the current control thin film transistors connected to the EL elements and through switching thin film transistors connected to and for driving the respective current control transistors.

Thus, according to the present invention, a thin film transistor which is formed in an organic EL display device having a substrate and a plurality of organic EL elements formed on the substrate is provided. This transistor used to drive one of the EL elements includes an active layer of semiconductor material, formed on the substrate, a source region and a drain region being formed in the active layer, a source electrode of aluminum material electrically coupled to the source region formed in the active layer, a drain electrode of aluminum material electrically coupled to the drain region formed in the active layer, an insulation layer formed on the active layer, a gate electrode formed on the insulation layer, a first barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the source electrode and the source region of the active layer, and a second barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the drain electrode and the drain region of the active layer.

According to the present invention, also, an organic EL display device having a substrate, a plurality of organic EL elements formed on the substrate and a plurality of thin film transistors formed on the substrate is provided. The transistors are connected to the respective EL elements for controlling current applied to the respective elements. Each of the transistors includes an active layer of semiconductor material, formed on the substrate, a source region and a drain region being formed in the active layer, a source electrode of aluminum material electrically coupled to the source region formed in the active layer, a drain electrode of aluminum material electrically coupled to the drain region formed in the active layer, an insulation layer formed on the active layer, a gate electrode formed on the insulation layer, a first barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the source electrode and the source region of the active layer, and a second barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the drain electrode and the drain region of the active layer.

Since the barrier metal layers in the current control thin film transistors arranged nearest to the respective organic EL elements are made of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, no elusion of the barrier metal layers occurs resulting no short-circuit nor disconnection in the organic EL display device to keep high reliability of the organic EL display device.

It is preferred that each of the organic EL elements includes a transparent electrode layer formed on the substrate, an organic EL layer formed on the transparent electrode layer and an upper electrode layer formed on the organic EL layer, the transparent electrode being electrically coupled to a conductive lead of aluminum material, and that each of the organic EL elements further includes a contact metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the transparent electrode layer and the conductive lead. The above-mentioned conductive lead may be connected to the drain electrode.

Since both the barrier metal layers in the current control thin film transistors and the contact metal layer in the organic EL elements are simultaneously manufactured in the same process, manufacturing cost can be decreased. Of course, the contact metal layers made of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium

will result tight and stable contact between the respective conductive leads of aluminum and the respective transparent electrode layers.

According to the present invention, furthermore, an organic EL display device of active matrix type having a substrate, a plurality of organic EL elements formed on the substrate and a plurality of first and second thin film transistors formed on the substrate is provided. The first transistors are connected to the respective EL elements for controlling current applied to the respective elements, and the second transistors are connected to the respective first transistors for switching the respective first transistors. Each of the first and second transistors includes an active layer of semiconductor material, formed on the substrate, a source region and a drain region being formed in the active layer, a source electrode of aluminum material electrically coupled to the source region formed in the active layer, a drain electrode of aluminum material electrically coupled to the drain region formed in the active layer, an insulation layer formed on the active layer, a gate electrode formed on the insulation layer, a first barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the source electrode and the source region of the active layer, and a second barrier metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the drain electrode and the drain region of the active layer.

It is preferred that each of the organic EL elements includes a transparent electrode layer formed on the substrate, an organic EL layer formed on the transparent electrode layer and an upper electrode layer formed on the organic EL layer, the transparent electrode being electrically coupled to a conductive lead of aluminum material, and that each of the organic EL elements further includes a contact metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, inserted between the transparent electrode layer and the conductive lead. The above-mentioned conductive lead may be connected to the drain electrode.

According to the present invention, also, a method for manufacturing an organic EL display device having a plurality of organic EL elements and a plurality of thin film transistors formed on a substrate is provided. Each of the organic EL elements and the thin film transistors is manufactured by the steps of depositing an active layer of semiconductor material on the substrate, forming a source region and a drain region in the active layer, forming a gate insulation layer on the active layer, forming a gate electrode on the gate insulation layer, depositing an insulation interlayer on the active layer and the substrate, removing part of the insulation interlayer to form contact holes on the source and drain regions of the active layer and organic EL element forming region, forming a transparent electrode layer in the organic EL element forming region on the substrate, simultaneously forming first and second barrier metal layers and a contact metal layer of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium, the first and second barrier metal layers being formed in the contact holes on the source and drain regions of the active layer, the contact metal layer being formed on the transparent electrode layer, forming source and drain electrode and a conductive lead of aluminum material on the first and second barrier metal layers and the contact metal layer, respectively, forming an organic EL layer on the transparent electrode layer, and forming an upper electrode layer on the EL layer.

Further objects and advantages of the present invention will be apparent from the following description of the preferred embodiments of the invention as illustrated in the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows a sectional view of a part of a preferred embodiment of an organic EL display device according to the present invention;

FIG. 2 shows a sectional view of a part of the embodiment shown in FIG. 1;

FIGS. 3a to 3d show sectional views of a part of manufacturing steps of the EL display device according to the embodiment shown in FIG. 1; and

FIG. 4 shows a circuit diagram of the EL display device shown in FIG. 1.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

FIG. 1 shows an organic electroluminescence (EL) element and a current control thin film transistor for controlling current applied to the EL element in a preferred embodiment of an organic EL display device according to the present invention.

In FIG. 1, a reference numeral 101 denotes a transparent substrate such as a quartz substrate. On the substrate 101, many of the organic EL elements and their peripheral circuit elements such as current control thin film transistors, switching thin film transistors for switching the respective current control transistors, another thin film transistors which constitute peripheral driving circuits and capacitors are formed.

Each of the current control thin film transistors is substantially constituted by an active silicon layer 102 formed on the substrate 101, a gate oxide layer of SiO_2 103 formed on a central region of the active silicon layer 102, a gate electrode of phosphorous doped Polysilicon 104 laminated on the gate oxide layer 103, a source electrode and conductive lead of aluminum material 113 and a drain electrode and conductive lead of aluminum material 114. The gate electrode 104 can be made of aluminum material instead of the phosphorous doped polysilicon. In the active silicon layer 102, a source region 105, a channel region 106 and a drain region 107 are formed. To the source region 105 of the active silicon layer 102, the source electrode and conductive lead 113 is electrically coupled via a barrier metal layer of titanium nitride which contains 10 atm % of nitrogen 110. Also, to the drain region 107 of the active silicon layer 102, the drain electrode and conductive lead 114 is electrically coupled via a barrier metal layer of titanium nitride which contains 10 atm % of nitrogen 111. An insulation interlayer of SiO_2 108 is formed between the active silicon layer 102 and the conductive leads 113 and 114 and between the gate electrode 104 and the barrier metal layers 110 and 111.

Each of the organic EL elements is substantially constituted by a transparent electrode layer of ITO (Indium Tin Oxide) 109 formed on the substrate 101, an organic EL layer 115 formed on the transparent electrode layer 109, an upper electrode layer of a magnesium film including silver material 116 formed on the EL layer 115 and a common electrode of aluminum material 118 formed on the upper electrode layer 116. The transparent electrode layer 109 is electrically coupled to the drain conductive lead 114 via a contact metal layer of titanium nitride which contains 10 atm % of nitrogen 112. A protection layer of SiO_2 117 is formed between the common electrode 118 and the conductive leads 113 and 114.

FIG. 2 shows the switching thin film transistor in the preferred embodiment of the organic EL display device according to the present invention.

Each of the switching thin film transistors is substantially constituted by an active silicon layer 202 formed on the substrate 101, a gate oxide layer of SiO_2 203 formed on a central region of the active silicon layer 202, a gate electrode of phosphorous doped polysilicon 204 laminated on the gate oxide layer 203, a source electrode and conductive lead of aluminum material 213 and a drain electrode and conductive lead of aluminum material 214. The gate electrode 204 can be made of aluminum material instead of the phosphorous doped polysilicon. In the active silicon layer 202, a source region 205, a channel region 206 and a drain region 207 are formed. To the source region 205 of the active silicon layer 202, the source electrode and conductive lead 213 is electrically coupled via a barrier metal layer of titanium nitride which contains 10 atm % of nitrogen 210. Also, to the drain region 207 of the active silicon layer 202, the drain electrode and conductive lead 214 is electrically coupled via a barrier metal layer of titanium nitride which contains 10 atm % of nitrogen 211. An insulation interlayer of SiO_2 208 is formed between the active silicon layer 202 and the conductive leads 213 and 214 and between the gate electrode 204 and the barrier metal layers 210 and 211.

Referring to FIGS. 3a to 3d, manufacturing processes of the current control thin film transistor and the organic EL element of this embodiment will be described in detail. It should be noted that manufacturing processes of the switching thin film transistor and another thin film transistors which constitute peripheral driving circuits of the EL element will be the same as following processes of the current control thin film transistor.

As shown in FIG. 3a, on a transparent substrate 101 such as a quartz substrate, a glass substrate or a ceramic substrate, an active silicon layer 102 with an island shape is formed by depositing an amorphous silicon layer by a CVD (Chemical Vapor Deposition) method, annealing the deposited amorphous silicon layer to form a polysilicon layer (solid-phase growth), and then performing patterning process of the polysilicon layer.

Then, on the active silicon layer 102, a gate oxide layer of SiO_2 103 and a gate electrode of phosphorous doped polysilicon 104 are formed in lamination. The gate electrode 104 can be made of aluminum material instead of the phosphorous doped polysilicon. Thereafter, a source region 105, a channel region 106 and a drain region 107 are formed in the active silicon layer 102 by an Ion doping method. In this embodiment, dopant is for example P and the gate electrode 104 is used as a mask for the doping process. Then, to cover all of these layers, an insulation interlayer of SiO_2 108 is deposited.

Then, contact holes are formed by etching the insulation interlayer 108 at the source region 105 and at the drain region 107. Also, by this etching process, the insulation interlayer 108 in a region for forming the EL element is removed.

Then, an transparent conductive film of ITO, ZnO or SnO is sputtered to form an transparent electrode layer 109 in the EL element forming region on the substrate 101. Without removing the insulation interlayer 108 from the EL element forming region, the transparent electrode layer may be formed on this insulation interlayer 108 not directly on the substrate 101. Thereafter, a titanium nitride film consisting nitrogen of 10 atm % with a thickness of 100 to 1000 Angstrom preferably 500 Angstrom is deposited on all of the these layers. Then, this deposited titanium nitride film is etched to simultaneously form a barrier metal layer of titanium nitride 10 on the source region 105, a barrier metal layer of titanium

nitride 111 on the drain region 107 and a contact metal layer of titanium nitride 112 on the transparent electrode layer 109, respectively.

It will be apparent that barrier metal layers of titanium nitride in the switching thin film transistor and in the another thin film transistors which constitute peripheral driving circuits of the EL element can be simultaneously formed in this process.

Then, as shown in FIG. 3c, an aluminum film with a thickness of 6000 Angstrom is deposited by for example sputtering to cover all of these layers and the deposited aluminum film is etched so as to form a source electrode and conductive lead 113 and a drain electrode and conductive lead 114. Thus, the source electrode and conductive lead of aluminum 113 is electrically coupled to the source region 105 of the active silicon layer 102 via the barrier metal layer of titanium nitride 110, and also, the drain electrode and conductive lead of aluminum 114 is electrically coupled to the drain region 107 of the active silicon layer 102 via the barrier metal layer of titanium nitride 111 and to the transparent electrode layer 109 via the contact metal layer of titanium nitride 112.

Then, as shown in FIG. 3d, an organic EL layer 115 and an upper electrode layer of a magnesium film including silver material 116 are formed in the EL element forming region on the transparent electrode layer 109 by vapor deposition methods using a metal mask. Thereafter, on these layers, a protection layer of SiO_2 117 is deposited and a contact hole is etched on the upper electrode layer 116. Finally, a common electrode of aluminum material 118 is deposited on all of the matrix portion of the organic EL display device.

In the aforementioned embodiment, it is described that the barrier metal layers 110 and 111 and the contact metal layer 112 are made of titanium nitride containing 10 atm % of nitrogen. Higher containing amount of nitrogen in the titanium nitride material will increase degree of contact and stability but decrease electrical conductivity. Thus, according to the present invention, this containing amount of nitrogen in the titanium nitride material is selected to a value equal to or less than 50 atm % preferably 5 to 15 atm % for obtaining both good stability and electrical conductivity.

According to the present invention, since the barrier metal layers in the current control thin film transistors arranged nearest to the respective organic EL elements are made of titanium nitride containing equal to or less than 50 atm % of nitrogen, no elusion of the barrier metal layers occurs resulting no short-circuit nor disconnection in the organic EL display device to keep high reliability of the organic EL display device. Furthermore, since both the barrier metal layers in the current control thin film transistors and the contact metal layer in the organic EL elements are simultaneously manufactured in the same process, manufacturing cost can be decreased. Of course, the contact metal layers of titanium nitride containing equal to or less than 50 atm % of nitrogen will result tight and stable contact between the respective conductive leads of aluminum and the respective transparent electrode layers.

According to the present invention, also, the barrier metal layers in the current control thin film transistors and the contact metal layers in the respective organic EL elements can be made of titanium. Thus, no elusion of the barrier metal layers occurs resulting no short-circuit nor disconnection in the organic EL display device to keep high reliability of the organic EL display device. Furthermore, if both the barrier metal layers in the current control thin film transistors and the contact metal layer in the organic EL elements can be simultaneously manufactured in the same process, manufacturing cost can be decreased. Of course, the contact metal layers of

titanium will also result tight and stable contact between the respective conductive leads of aluminum and the respective transparent electrode layers.

As shown in FIG. 4, the organic EL display device according to the embodiment shown in FIG. 1 is constituted by X-direction signal lines 401₁, 401₂, . . . , Y-direction signal lines 402₁, 402₂, . . . , power supply lines (Vdd) 403₁, 403₂, . . . , switching thin film transistors 404₁, 404₂, 404₃, 404₄, . . . , current control thin film transistors 405₁, 405₂, 405₃, 405₄, . . . , organic EL elements 406₁, 406₂, 406₃, 406₄, . . . , capacitors 407₁, 407₂, 407₃, 407₄, . . . , a X-direction peripheral drive circuit 408 and a Y-direction peripheral drive circuit 409.

Each of the pixels of the EL display device is specified by one of the X-direction signal lines 401₁, 401₂, . . . and one of the Y-direction signal lines 402₁, 402₂, If a signal corresponding to picture data is applied to the X-direction signal line 401₂ and Y-direction scanning signal is applied to the Y-direction signal line 402₁, the switching transistor 404₂ in the specified pixel turns on. Thus, the current control transistor 405₂ controls current flowing from the power supply line 403₂ into the organic EL element 406₂ in accordance with the picture data causing corresponding light emission from this EL element 406₂.

According to the present invention, at least the barrier metal layers in the current control thin film transistors and preferably the barrier metal layers in the switching thin film transistors are made of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium. In manufacturing the EL display device, it is desired that the contact metal layers in the organic EL elements are simultaneously formed in the same process of the barrier metal layers with the same material, namely titanium nitride containing equal to or less than 50 atm % of nitrogen or titanium. Furthermore, according to the present invention, the barrier metal layers in the thin film transistors in the peripheral drive circuits are preferably made of titanium nitride containing equal to or less than 50 atm % of nitrogen or made of titanium.

Many widely different embodiments of the present invention may be constructed without departing from the spirit and scope of the present invention. It should be understood that the present invention is not limited to the specific embodiments described in the specification, except as defined in the appended claims.

What is claimed is:

1. An electroluminescence display device comprising:
a substrate having an insulating surface;
a first signal line extending in a first direction over the substrate;
a second signal line extending in a second direction over the substrate wherein a pixel is defined at an intersection between the first signal line and the second signal line;
a first thin film transistor formed in said pixel over said substrate, said thin film transistor comprising an active layer comprising crystalline silicon formed over said substrate and a gate electrode adjacent to the active layer;
an insulating film formed over the first thin film transistor;
a first electrode formed over the substrate in a region where the insulating film is removed;
a conductive layer formed over the insulating film wherein the first electrode is electrically connected to the thin film transistor through the conductive layer;
an electroluminescence layer comprising an organic material formed over said first electrode;
a second electrode formed over said electroluminescence layer; and

a peripheral driving circuit comprising a second thin film transistor formed over said substrate, said peripheral driving circuit electrically connected to said first signal line wherein said second thin film transistor comprises an active layer comprising crystalline silicon formed over said substrate and a gate electrode adjacent to the active layer.

2. The electroluminescence display device according to claim 1 wherein said first electrode is transparent.

3. The electroluminescence display device according to claim 1 wherein said gate electrode is formed over said active layer.

4. The electroluminescence display device according to claim 1 wherein the first electrode and the active layer of the first thin film transistor are formed on a same insulating surface over the substrate.

5. The electroluminescence display device according to claim 1 wherein the active layer of the first thin film transistor and the first electrode are formed on a same insulating surface.

6. The electroluminescence display device according to claim 1 wherein the conductive layer comprises an aluminum layer and a barrier metal layer including titanium and nitrogen.

7. An electroluminescence display device comprising:
a substrate having an insulating surface;
a first signal line extending in a first direction over the substrate;
a second signal line extending in a second direction over the substrate wherein a pixel is defined at an intersection between the first signal line and the second signal line;
at least one switching thin film transistor and one current control thin film transistor provided in said pixel over the substrate wherein the first signal line is electrically connected to a gate electrode of the switching thin film transistor;
an insulating film formed over the current control thin film transistor;

a first electrode formed over the substrate in a region where the insulating film is removed;

a conductive layer formed over the insulating film wherein the first electrode is electrically connected to the current control thin film transistor through the conductive layer;
an electroluminescence layer comprising an organic material over said first electrode;

a second electrode formed over said electroluminescence layer;
a peripheral driving circuit comprising at least a third thin film transistor formed over said substrate, said peripheral driving circuit being electrically connected to said first signal line,

wherein each of the switching thin film transistor, the current control thin film transistor and the third thin film transistor comprises a semiconductor layer comprising crystalline silicon and including source, drain and channel regions, a gate insulating film adjacent to the semiconductor layer and a gate electrode adjacent the gate insulating film.

8. The display device according to claim 7 wherein said gate electrode is located over the channel region with the gate insulating film interposed therebetween in each of the switching thin film transistor, the current control thin film transistor and the third thin film transistor.

9. The electroluminescence display device according to claim 7 wherein said first electrode is transparent.

10. The electroluminescence display device according to claim 7 wherein the first electrode and the semiconductor

layers of the switching thin film transistor, the current control thin film transistor and the third thin film transistor are formed on a same insulating surface over the substrate.

11. The electroluminescence display device according to claim 7 wherein the semiconductor layer of the current control thin film transistor and the first electrode are formed on a same insulating surface.

12. The electroluminescence display device according to claim 7 wherein the conductive layer comprises an aluminum layer and a barrier metal layer including titanium and nitrogen.

13. An electroluminescence display device comprising:
a substrate having an insulating surface;
at least one X-direction signal line over said substrate;
at least one Y-direction signal line crossing said X-direction signal line;
at least one pixel defined at an intersection between the X-direction signal line and the Y-direction signal line;
at least one switching thin film transistor and one current control thin film transistor provided over the substrate in said pixel wherein a gate electrode of the switching thin film transistor is electrically connected to said X-direction signal line, one of source and drain regions of the switching thin film transistor is electrically connected to said Y-direction signal line, the other one of the source and drain regions of the switching thin film transistor is electrically connected to a gate electrode of the current control thin film transistor;
an insulating film formed over the current control thin film transistor;
a first electrode electrically connected to said current control thin film transistor formed over the substrate in a region where the insulating film is removed;
a conductive layer formed over the insulating film wherein the first electrode is electrically connected to the current control thin film transistor through the conductive layer;

an electroluminescence layer comprising an organic material over said first electrode;
a second electrode formed over said electroluminescence layer;

5 a peripheral driving circuit comprising at least a third thin film transistor formed over said substrate for supplying a signal to at least one of said X-direction signal line and said Y-direction signal line,

wherein each of the switching thin film transistor, the current control thin film transistor and the third thin film transistor comprises a semiconductor layer comprising crystalline silicon and including source, drain and channel regions, a gate insulating film adjacent to the semiconductor layer and a gate electrode adjacent the gate insulating film.

14. The electroluminescence display device according to claim 13 wherein said gate electrode is located over the channel region with the gate insulating film interposed therebetween in each of the switching thin film transistor, the current control thin film transistor and the third thin film transistor.

15. The electroluminescence display device according to claim 13 wherein said first electrode is transparent.

16. The electroluminescence display device according to claim 13 wherein the first electrode and the semiconductor layers of the switching thin film transistor, the current control thin film transistor and the third thin film transistor are formed on a same insulating surface over the substrate.

17. The electroluminescence display device according to claim 13 wherein the semiconductor layer of the current control thin film transistor and the first electrode are formed on a same insulating surface.

18. The electroluminescence display device according to claim 13 wherein the conductive layer comprises an aluminum layer and a barrier metal layer including titanium and nitrogen.

* * * * *

专利名称(译)	薄膜晶体管，有机电致发光显示装置及其制造方法		
公开(公告)号	US7476900	公开(公告)日	2009-01-13
申请号	US11/296436	申请日	2005-12-08
[标]申请(专利权)人(译)	株式会社半导体能源研究所		
申请(专利权)人(译)	半导体能源研究所有限公司. TDK株式会社		
当前申请(专利权)人(译)	半导体能源研究所有限公司. TDK株式会社		
[标]发明人	YAMAUCHI YUKIO ARAI MICHIO		
发明人	YAMAUCHI, YUKIO ARAI, MICHIO		
IPC分类号	H01L27/14 H01L29/04 H01L29/15 H01L31/036 G09G3/32 H01L27/32 H05B33/06 H05B33/12		
CPC分类号	G09G3/3233 H01L27/12 H01L27/3248 H05B33/06 H05B33/12 G09G2300/0842 H01L27/124		
助理审查员(译)	HO , ANTHONY		
优先权	1995065943 1995-03-24 JP		
其他公开文献	US20060087222A1		
外部链接	Espacenet USPTO		

摘要(译)

有机EL显示装置具有基板，形成在基板上的多个有机EL元件和形成在基板上的多个薄膜晶体管。晶体管连接到相应的EL元件，用于控制施加到各个元件的电流。每个晶体管包括形成在基板上的半导体材料的有源层，形成在有源层中的源区和漏区，电耦合到形成在有源层中的源区的铝材料的源电极，铝电极的漏电极电耦合到形成在有源层中的漏区，形成在有源层上的绝缘层，形成在绝缘层上的栅电极，含有等于或小于50的氮化钛的第一阻挡金属层插入在有源层的源电极和源区之间的氮或钛的atm%，和插入在漏电极和漏区之间的氮或钛的等于或小于50atm%的氮化钛的第二阻挡金属层。有源层的漏极区域。

