



US007456037B2

(12) **United States Patent**
Yamazaki

(10) **Patent No.:** **US 7,456,037 B2**
(45) **Date of Patent:** **Nov. 25, 2008**

(54) **EL DISPLAY DEVICE AND A METHOD OF MANUFACTURING THE SAME**

(75) Inventor: **Shunpei Yamazaki**, Tokyo (JP)

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd.** (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 1111 days.

(21) Appl. No.: **10/747,864**

(22) Filed: **Dec. 29, 2003**

(65) **Prior Publication Data**

US 2004/0229392 A1 Nov. 18, 2004

Related U.S. Application Data

(60) Continuation of application No. 10/186,956, filed on Jul. 1, 2002, now Pat. No. 6,673,643, which is a division of application No. 09/615,264, filed on Jul. 13, 2000, now Pat. No. 6,432,561.

(30) **Foreign Application Priority Data**

Jul. 23, 1999 (JP) 11-209227

(51) **Int. Cl.**

H01L 51/40 (2006.01)

H01L 21/00 (2006.01)

(52) **U.S. Cl.** **438/30; 438/99; 257/E21.352**

(58) **Field of Classification Search** **438/30, 438/99; 257/E21.352, E21.053, E21.358**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,356,429 A 10/1982 Tang 313/503
4,539,507 A 9/1985 VanSlyke et al. 313/504
4,720,432 A 1/1988 VanSlyke et al. 428/457
4,769,292 A 9/1988 Tang et al. 428/690

4,885,211 A 12/1989 Tang et al. 428/457

5,047,687 A 9/1991 VanSlyke 313/503

5,093,698 A 3/1992 Egusa 357/17

5,328,854 A 7/1994 Vakhshoori et al.

(Continued)

FOREIGN PATENT DOCUMENTS

EP 0 498 979 A1 8/1992

(Continued)

OTHER PUBLICATIONS

Kofuji, T., "Development of Organic EL Element to Single Layer Type," Electronic Journal 6th FPD Seminar, pp. 83-88, Jun. 29, 1999.

(Continued)

Primary Examiner—Scott B. Geyer


Assistant Examiner—Seahvosh J Nikmanesh

(74) *Attorney, Agent, or Firm*—Cook Alex Ltd.

(57) **ABSTRACT**

To decrease the number of layers while keeping or improving the performance of an EL element, so that the production cost is reduced. Cathodes (106, 107), a light emitting layer (108), an anode (109), and a passivation film (110) are formed on pixel electrodes (104, 105). Thereafter, the vicinity of the interface between the light emitting layer (108) and the anode (109) are doped with a halogen element through the passivation film (110) and the anode (109). This leads to formation of a hole conveying region (111) that functions as a hole conveying layer, thereby enhancing the light emission efficiency.

15 Claims, 8 Drawing Sheets



U.S. PATENT DOCUMENTS

5,429,884 A	7/1995	Namiki et al.	428/690
5,518,825 A *	5/1996	Murayama et al.	428/690
5,558,904 A *	9/1996	Hsieh et al.	427/66
5,641,991 A	6/1997	Sakoh	257/755
5,677,572 A	10/1997	Hung et al.	257/750
5,684,365 A	11/1997	Tang et al.	315/169.3
5,751,108 A	5/1998	Kanemura et al.	
5,776,623 A	7/1998	Hung et al.	428/690
5,882,761 A	3/1999	Kawami et al.	428/69
6,013,384 A	1/2000	Kido et al.	428/690
6,064,151 A	5/2000	Choong et al.	313/504
6,099,980 A	8/2000	Schoo et al.	428/690
6,114,088 A	9/2000	Wolk et al.	430/273.1
6,137,223 A	10/2000	Hung et al.	313/506
6,137,459 A	10/2000	Eida et al.	345/76
6,169,359 B1	1/2001	Sun et al.	313/503
6,188,134 B1	2/2001	Stumborg et al.	257/751
6,221,701 B1	4/2001	Yamazaki	438/166
6,259,138 B1	7/2001	Ohtani et al.	257/351
6,278,236 B1	8/2001	Madathil et al.	313/504
6,326,091 B1	12/2001	Schoo et al.	428/690
6,406,949 B1	6/2002	Kim	438/159
6,407,780 B1	6/2002	Sung	349/43
6,465,808 B2	10/2002	Lin	257/81
6,483,236 B1	11/2002	Hung	313/506
6,489,176 B2	12/2002	Ninomiya	438/30
6,521,359 B1	2/2003	Noguchi et al.	428/690
6,551,725 B2	4/2003	Raychaudhuri et al.	428/690
6,555,820 B1	4/2003	Tacke et al.	250/339.01
6,555,840 B1	4/2003	Hudson et al.	257/40
6,620,528 B1	9/2003	Yamazaki et al.	428/690
6,861,799 B1	3/2005	Friend et al.	313/504

7,285,904 B2 *	10/2007	Lee	313/503
2001/0033944 A1 *	10/2001	Onikubo et al.	428/690

FOREIGN PATENT DOCUMENTS





EP	0 618 625 A2	10/1994
EP	0 717 445 A2	6/1996
EP	0 776 147 A1	5/1997
EP	0 855 848 A2	7/1998
EP	1 071 145 A2	1/2001
JP	05-275174	10/1993
JP	8-078519	3/1996
JP	08-124679	5/1996
JP	8-241048	9/1996
JP	09-078059	3/1997
JP	9-148066	6/1997
JP	10-050480	2/1998
JP	10-189252	7/1998
JP	10-255982	9/1998
JP	10-261487	9/1998
WO	WO 97/040648	10/1997
WO	WO 98/003042	1/1998
WO	WO 98/059529 A1	12/1998







OTHER PUBLICATIONS

U.S. Appl. No. 09/619,485 to Yamazaki et al filed Jul. 19, 2000, including specification, claims, abstract, drawings and PTO filing receipt.

Huang, F. et al, "An Iodine-Doped Polymer Light-Emitting Diode," Applied Physics Letters, vol. 71, pp. 2415-2417, Oct. 27, (1997).
European Search Report re application No. EP 00115471.5, dated Mar. 14, 2006.

* cited by examiner








FIG. 4









FIG. 5






FIG. 8A




FIG. 8B




FIG. 9




FIG. 10




FIG. 11




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 12D




FIG. 12E




FIG. 12F

EL DISPLAY DEVICE AND A METHOD OF MANUFACTURING THE SAME

This application is a continuation of U.S. application Ser. No. 10/186,956, filed on Jul. 1, 2002 now U.S. Pat. No. 6,673,643 which is a divisional of U.S. application Ser. No. 09/615,264, filed on Jul. 13, 2000, now U.S. Pat. No. 6,432,561.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an electro-optical device represented by an EL (electroluminescence) display device comprising a semiconductor element (an element using a semiconductor thin film, typically, a thin film transistor) that is formed on a substrate, and to an electronic device (electronic equipment) having the electro-optical device as a display. Specifically, the invention relates to a method of manufacturing these devices.

2. Description of the Related Art

In recent years, remarkable progress has been made in a technique for forming a thin film transistor (hereinafter referred to as a TFT) on a substrate, and developing the application of TFTs to active matrix type display devices is proceeding. TFTs using a polysilicon film, in particular, have a higher electric field mobility than that of conventional TFTs using an amorphous silicon film, and hence are capable of high speed operation. Accordingly, control of pixels, which in the past has been made by driver circuits outside the substrate, now can be made by driver circuits formed on the same substrate on which the pixels are formed.

The attention is kept drawn to such active matrix type display devices in expectation of various advantages, such as lowering of production cost, downsizing of display devices, and an increase in yield and throughput, as a result of putting all the various kinds of circuits and elements onto the same single substrate.

In active matrix type EL display devices, every pixel is provided with a switching element formed of a TFT, and an EL layer emits light when a drive element that controls current is operated by this switching element. The mainstream at present of the structure of the EL layer is the layered structure with three or four layers, proposed by Tang, et al. from Eastman Kodak Company.

Lately, however, many are concerned that multi-layering of the element structure will invite complication of the manufacture process and increase of the production cost. Attempts have been made in this connection to reduce the number of layers by doping a light emitting layer with a specific impurity element and using it as an electron conveying layer or an electron injection layer.

For instance, Idemitsu Kosan, Co. Ltd. proposes doping the light emitting layer (distyrylene derivative) near its surface with cesium (Cs) that has a small work function to use the doped region as the electron conveying layer. (Preliminaries for the Sixth FPD Seminar, sponsored by Electronic Journal, pp. 83-88)

SUMMARY OF THE INVENTION

The present invention has been made in view of the problem in multi-layering of the EL element, mentioned above, and an object of the present invention is therefore to provide a technique for reducing the number of the layers while keeping, or improving the performance of the EL element. More specifically, the present invention aims at providing a novel

method of manufacturing an EL display device of the type that emits light from one side of a substrate where the element is formed.

Another object of the present invention is to reduce production cost so that an inexpensive EL display device is provided. Still another object of the present invention is to reduce product cost of an electronic device (electronic equipment) having the inexpensive EL display device as its display.

According to the present invention, a light emitting layer is doped with a specific impurity element to make the doped region function as a carrier conveying layer (or a carrier injection layer), thereby reducing the number of the layers in the light emitting layer of the EL element.

Specifically, the light emitting layer in the vicinity of an anode is doped with a halogen element in order to encourage the conveyance of holes. On the other hand, the light emitting layer in the vicinity of a cathode is doped with an alkali metal element or an alkaline earth metal element in order to encourage the conveyance of electrons. Ion doping that involves mass separation, or ion implantation that does not, may be used at the doping step of the impurity element.

The present invention is characterized in that doping of the above specific impurity element is carried out under a state in which no factors are found that might possibly invite degradation of the light emitting layer. To elaborate, the light emitting layer is doped with the specific impurity element while avoiding exposure to the open air (especially, oxygen). The conveyance of the holes or the electrons are thus improved without causing degradation of the light emitting layer.

As a typical example, an EL element consisting of a cathode, a light emitting layer and an anode layered in order from the bottom is doped with an impurity element through a passivation film formed on the anode. In this case, it is desirable that the process of from forming the cathode to forming the passivation film is completed without exposing the element to the open air not even once. An appropriate apparatus to achieve this is a thin film forming apparatus of multi-chamber system (also called cluster tool system) where various kinds of processing chambers are integrated, or a thin film forming apparatus of in-line system.

BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings:

FIGS. 1A to 1D are diagrams showing a process of manufacturing an EL display device;

FIGS. 2A to 2D are diagrams showing a process of manufacturing an EL display device;

FIGS. 3A and 3B are diagrams showing a process of manufacturing an EL display device;

FIG. 4 is a diagram showing a process of manufacturing an EL display device;

FIG. 5 is a diagram showing a process of manufacturing an EL display device;

FIGS. 6A to 6D are diagrams showing a process of manufacturing an EL display device;

FIG. 7 is a diagram showing a process of manufacturing an EL display device;

FIGS. 8A and 8B are diagrams showing the state of an EL display device before and after emitting light.

FIG. 9 is a diagram showing the structure of a thin film forming apparatus;

FIG. 10 is a diagram showing the structure of an EL display device;

FIG. 11 is a diagram showing in section the structure of an EL display device; and

FIGS. 12A to 12F are diagrams showing examples of an electronic device.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Embodiment 1

An embodiment of the present invention will be described with reference to FIGS. 1A to 1D. First, TFTs **102**, **103** are formed on a substrate **101** using a known method. Though any substrate may be employed as the substrate **101**, a glass substrate, a ceramic substrate, a plastic substrate, and a stainless steel substrate are preferred. (FIG. 1A)

The TFTs **102**, **103** may take any structure. However, since they are TFTs that control current flowing into pixel electrodes **104**, **105**, a structure that can lessen degradation by heat generation and by hot carrier effect is desirable. On the other hand, too much current generates heat to degrade the EL layer, and therefore, in some cases, channel length is extended or a resistor is placed in order to suppress an excessive current.

Note that, though FIGS. 1A to 1D illustrate the TFT as if only one TFT is formed in one pixel, actually, two TFTs, one is a switching TFT and the other is a current controlling TFT (this one is the TFT shown in FIGS. 1A to 1D) are provided. The arrangement of the respective TFTs may follow the illustration of FIG. 1 (where the TFTs are denoted by T1 and T2) disclosed in Japanese Patent Application Laid-open No. Hei 8-241048.

The pixel electrodes **104**, **105** are formed of a material having high reflectivity. Specifically, a material containing aluminum as a main ingredient (containing 50 wt % or more aluminum) is preferable. Of light beams emitted from the EL element, one that travels toward the substrate **101** side is almost entirely reflected at the pixel electrodes **104**, **105** and exits therefrom.

Next, the EL element will be formed using a thin film forming apparatus shown in FIG. 9. In FIG. 9, reference symbol **901** denotes a loading chamber for loading and unloading the substrate which is also called a load lock chamber. A carrier **902** in which the substrate shown in FIG. 1A is set is arranged in this chamber. The loading chamber **901** may be divided into a substrate loading chamber and a substrate unloading chamber.

Reference symbol **903** denotes a common chamber including a mechanism **904** for transferring the substrate (hereinafter referred to as a transferring mechanism). The common chamber **903** communicates with a plurality of processing chambers (denoted by **906** to **910**) through gates **905a** to **905f**, respectively.

The respective processing chambers are completely closed off to the common chamber **903** by the gates **905a** to **905f**, providing air-tight spaces. Accordingly, the processing can be made in vacuum if an exhaust pump is provided in each processing chamber. Usable exhaust pumps may be a hydraulic rotary pump, a mechanical booster pump, a turbomolecular pump, and a cryopump, of which the cryopump is preferred because it is effective in discharging moisture.

The substrate is transferred first to the common chamber **903** by the transferring mechanism **904**, and then to a first vapor phase film formation processing chamber **906**. In the first vapor phase film formation processing chamber **906**, cathodes **106**, **107** are formed from a metal film containing an alkali metal element, or an alkaline earth metal element. Either evaporation or sputtering may be employed to form the

film. In this embodiment, an MgAg alloy obtained by joint evaporation of magnesium and silver at a ratio of 10:1 is used.

Being formed on the pixel electrodes **104**, **105** that are connected to the TFTs, the cathodes **106**, **107** can receive current output from the TFTs **102**, **103**. In short, the cathodes **106**, **107** can establish electrical connection with the TFTs **102**, **103**.

The substrate is then transferred from the first vapor phase film formation processing chamber **906** to a solution application processing chamber **907**. In the solution application processing chamber **907**, a solution containing an EL material is applied by spin coating to form a polymer precursor that contains a polymer-based EL material. In this embodiment, a solution in which polyvinyl carbazole is dissolved in chloroform is used as the solution containing an EL material. It is of course possible to use other polymer-based EL material (typically, polyphenylene vinylene, polycarbonate, etc.) and other organic solvent (typically, dichloromethane, tetrahydrofuran, etc.) in combination.

Subsequently, the substrate is transferred from solution application processing chamber **907** to a calcination processing chamber **908**. In the calcination processing chamber **908**, the EL material is polymerized by calcination processing (heat treatment). In this embodiment, a stage is heated by a heater so that the heat treatment is performed on the entire substrate at a temperature of 50 to 150° C. (preferably, 110 to 120° C.). Excess chloroform is thus volatilized, forming a polymer-based light emitting layer **108** made of polyvinyl carbazole. (FIG. 1B)

Next, the substrate is transferred from the calcination processing chamber **908** to a second vapor phase film formation processing chamber **909**. An anode **109** is formed therein from a transparent conductive film by sputtering or evaporation on the polymer-based light emitting layer **108**. For the anode **109**, a transparent conductive film made of, for example, a compound of indium oxide and tin oxide (ITO) or a compound of indium oxide and zinc oxide may be used. A compound obtained by mixing 10 to 15% zinc oxide with indium oxide is used in this embodiment.

The substrate is then transferred from the second vapor phase film formation processing chamber **909** to a third vapor phase film formation processing chamber **910**. A passivation film **110** is formed in there from an insulating film or, preferably, an insulating film containing silicon by sputtering or evaporation. The passivation film **110** is provided to protect the light emitting layer **108** from moisture and oxygen. Accordingly, a silicon nitride film or a silicon nitride oxide film which contains almost no oxygen is preferred for the passivation film.

As the passivation film **110**, an insulating film may be used which contains Si (silicon), Al (aluminum), N (nitrogen), O (oxygen), and M (M is at least one member of the rare earth elements, preferably, at least one element selected from Ce (cerium), Yb (ytterbium), Sm (samarium), Er (erbium), Y (yttrium), La (lanthanum), Gd (gadolinium), Dy (dysprosium), and Nd (neodymium)).

In this way, the state shown in FIG. 1C is obtained. After that the substrate is transferred from the third vapor phase film formation processing chamber **910** to the carrier **902** placed in the loading chamber **901**. A series of processing using the thin film forming apparatus shown in FIG. 9 is thus completed.

An advantage of using the thin film forming apparatus shown in FIG. 9 is that the process of from forming the cathode **106** to forming the passivation film **110** can be carried out continuously without exposing the substrate to the air (moisture, especially) not even once. In other words, all the

processes are carried out in vacuum or in an inert gas atmosphere, so that degradation of the light emitting layer is not caused.

In addition, the thin film forming apparatus is also provided with a processing chamber for spin coating, which makes it possible to form an EL element using a polymer-based EL material. It is also possible to form the light emitting layer **108** by evaporation or sputtering, of course.

After thus obtaining the state shown in FIG. **1C**, doping of an impurity element is then performed through the passivation film **110** and the anode **109**. In this embodiment, a halogen element (typically, fluorine, chlorine, bromine, or iodine) is the dopant. At this point, the doping is made such that the concentration of halogen element is the highest in the vicinity of the interface between the anode **109** and the light emitting layer **108**. The vicinity of the interface between the anode and the light emitting layer refers to the extent 100 nm (typically 50 nm) down the depth of the light emitting layer from the interface between the anode and the light emitting layer. It causes no trouble if the halogen element is contained in the anode. (FIG. **1D**)

The thus formed region **111** doped with the halogen element serves as a region for facilitating movement of carriers (holes, in this case) from the anode **109** to the light emitting layer **108**, enhancing the light emission efficiency. That is, the region **111** functions substantially as a hole conveying layer (or a hole injection layer). Regions as such are therefore referred to as hole conveying regions in this specification.

Accordingly, the need for separately forming a hole conveying layer on the light emitting layer **108** is eliminated, simplifying the manufacture process of the EL display device. Also, the present invention has an advantage in that there is no fear of degrading the light emitting layer **108** because the impurity element doping step is not carried out until formation of films up through the passivation film is finished.

Embodiment 2

This embodiment will be described with reference to FIGS. **2A** to **2D**. First, an auxiliary electrode **202** and a cathode **203** are formed on a substrate **201**. The electrode and the cathode are selectively and continuously layered by evaporation or sputtering while using a mask. Though not shown in FIG. **2A**, there are formed a plurality of electrodes which extend in the depth direction of the space defined in the drawing, forming stripes.

The auxiliary electrode **202** is an electrode formed of a material mainly containing aluminum, copper or silver, and having a very low resistivity. In this embodiment, an MgAg alloy is used as the cathode **203** with a low resistance electrode layered thereon as an auxiliary to enhance the conductivity, thereby reducing the film thickness. This low resistance electrode is therefore referred to as the auxiliary electrode.

Then a light emitting layer **204** is formed so as to cover the auxiliary electrode **202** and the cathode **203**. In this embodiment, Alq₃ (tris-8-chinolino-aluminum), which is a monomer-based EL material, is selectively formed by evaporation using a mask. (FIG. **2B**)

Subsequently, an anode **205** is formed from a transparent conductive film into stripe form so as to be perpendicular to the cathode **203**. Evaporation or sputtering using a mask is appropriate for this film formation. A compound obtained by mixing tin oxide or zinc oxide with indium oxide is used as the anode **205** in this embodiment.

A passivation film **206** is formed next to cover the anode **205**. In this embodiment, a silicon nitride film is formed as the

passivation film **206** onto the entire surface. Other insulating films, as mentioned in Embodiment 1, may of course be used instead. The sectional view of the device in the state of FIG. **2C**, taken along the line A-A', is shown in FIG. **3A**.

After the state shown in FIG. **2C** is obtained, the device is doped with a halogen element through the passivation film **206** and the anode **205**. At this point, similar to Embodiment 1, the doping is made such that the concentration of the halogen element is the highest in the vicinity of the interface between the anode **205** and the light emitting layer **204**. As a result, a hole conveying region **207** is formed in the vicinity of the interface between the anode **205** and the light emitting layer **204** to enhance the light emission efficiency. (FIG. **2D**)

The sectional view of the device in the state of FIG. **2D**, taken along the line B-B', is shown in FIG. **3B**. However, a region denoted by **208** is doped with the halogen element at a deeper level as compared with the area right beneath the anode **205**, for the region **208** is in between the anode **205** and the adjacent anode **205**.

As described above, according to this embodiment, the need for separately forming a hole conveying layer on the light emitting layer **204** is eliminated, simplifying the manufacture process of the EL display device. Also, the present invention has an advantage in that there is no fear of degrading the light emitting layer **204** because the impurity element doping step is not carried out until formation of films up through the passivation film is finished.

Embodiment 3

This embodiment gives a description of the case where the impurity element used for doping in Embodiment 1 is changed to other elements. The symbols used in Embodiment 1 will be referred when necessary.

First, following the steps of Embodiment 1, the state shown in FIG. **1C** is obtained. A doping step of an impurity element is then carried out as shown in FIG. **4**. In this embodiment, the vicinity of the interface between the cathode **107** and the light emitting layer **108** is doped with an alkali metal element, typical examples of which include Li (lithium), Na (sodium), K (potassium), and Cs (cesium), or an alkaline earth metal element, typical examples of which include Be (beryllium), Mg (magnesium), Ca (calcium), and Ba (barium). The vicinity of the interface between the cathode and the light emitting layer here refers to an extent 100 nm (typically, 50 nm) up in the depth direction of the light emitting layer from the interface between the cathode and the light emitting layer. It causes no trouble if the alkali metal element or the alkaline earth metal element is contained in the cathode.

The thus formed region **401** doped with the alkali metal element or the alkaline earth metal element serves as a region for promoting movement of carriers (electrons, in this case) from the cathode **107** to the light emitting layer **108**. That is, the region **401** functions substantially as an electron conveying layer (or an electron injection layer). Regions as such are therefore referred to as electron conveying regions in this specification.

As described above, the need for separately forming an electron conveying layer below the light emitting layer **108** is eliminated, simplifying the manufacture process of the EL display device. Also, the present invention has an advantage in that there is no fear of degrading the light emitting layer **108** because the impurity element doping step is not carried out until formation of films up through the passivation film is finished.

This embodiment may be combined with Embodiment 1. To elaborate, if the two embodiments are combined, the vicin-

ity of the interface between the light emitting layer **108** and the anode **109** is doped with the halogen element to form the hole conveying region while the vicinity of the interface between the light emitting layer **108** and the cathode **107** is doped with the alkali metal element or the alkaline earth metal element to form the electron conveying region.

Embodiment 4

This embodiment gives a description of the case where the impurity element used for doping in Embodiment 2 is changed to other elements. The symbols used in Embodiment 2 will be referred when necessary.

First, following the steps of Embodiment 2, the state shown in FIG. **2C** is obtained. A doping step of an impurity element is then carried out as shown in FIG. **5**. In this embodiment, the vicinity of the interface between the cathode **203** and the light emitting layer **204** is doped with an alkali metal element, typical examples of which include Li (lithium), Na (sodium), K (potassium), and Cs (cesium), or an alkaline earth metal element, typical examples of which include Be (beryllium), Mg (magnesium), Ca (calcium), and Ba (barium). That the vicinity of the interface between the cathode **203** and the light emitting layer **204** is doped is the same as Embodiment 2. As a result, an electron conveying region **501** is formed.

As described above, the need for separately forming an electron conveying layer below the light emitting layer **204** is eliminated, simplifying the manufacture process of the EL display device. Also, the present invention has an advantage in that there is no fear of degrading the light emitting layer **204** because the impurity element doping step is not carried out until formation of films up through the passivation film is finished.

This embodiment may be combined with Embodiment 2. To elaborate, if the two embodiments are combined, the vicinity of the interface between the light emitting layer **204** and the anode **205** is doped with the halogen element to form the hole conveying region while the vicinity of the interface between the light emitting layer **204** and the cathode **203** is doped with the alkali metal element or the alkaline earth metal element to form the electron conveying region.

Embodiment 5

An example of an EL display device is shown in this embodiment in which a light emitting region is distinguished from a non-light emitting region by using the present invention to control positions for forming a hole conveying region and an electron conveying region.

First, a substrate **601** is put into a carrier **902** of a thin film forming apparatus shown in FIG. **9**, and the carrier **902** carrying the substrate is set in a loading chamber **901**. The substrate **601** is then transferred to a first vapor phase film formation processing chamber **906** to form a cathode **602** by evaporation from an Al—LiF alloy. The Al—LiF alloy is obtained by joint evaporation of aluminum (Al) and lithium fluoride (LiF). (FIG. **6A**)

The substrate is then transferred to a solution application processing chamber **907**. There, a solution in which polyphenylene vinylene is dissolved in dichloromethane is applied to the substrate by spin coating to form a polymer precursor. The substrate is further transferred to a calcination processing chamber **908**. There, heat treatment is performed for polymerization, to thereby form a light emitting layer **603** of polyphenylene vinylene. (FIG. **6B**)

Next, the substrate is transferred to a second vapor phase film formation processing chamber **909**. An anode **604** is

formed in there from a compound of indium oxide and zinc oxide. The substrate is further transferred to a third vapor phase film formation processing chamber **910**. A passivation film **605** is formed in there from a silicon nitride film. (FIG. **6C**)

After the state shown in FIG. **6C** is obtained, the substrate is returned to the loading chamber **901** and taken out from the thin film forming apparatus. The process of from forming the cathode **602** to forming the passivation film **605** is continuously carried out without exposing the device to the air not even once. All of the thin films are formed on the entire surface of the substrate without using a mask or the like.

A resist **606** is then formed on the passivation film **606**, and a doping step of an impurity element is carried out in this state. A halogen element is used in this embodiment as the impurity element to dope the vicinity of the interface between the light emitting layer **603** and the anode **604**. A hole conveying region **607** is thus selectively formed in the light emitting layer **603**. (FIG. **6D**)

In this embodiment, the hole conveying region **607** is selectively formed in the vicinity of the light emitting layer **603** and the anode **604**. When the voltage is applied to the light emitting layer **603**, only a portion where the hole conveying region **607** is formed emits light. In other words, a driving voltage of an EL element in this embodiment is adjusted so that the light emitting layer **603** emit no light by itself, or emit light with extremely low brightness. Further adjustment is made so that the portion where the hole conveying region **607** is formed emits light with a sufficient brightness by the same driving voltage. The contrast ratio of the brightness of the emitted light is adjusted such that the brightness of the region where the hole conveying region **607** is formed is 10^3 or more (preferably 10^4 or more) times the brightness of the region where the hole conveying region **607** is not formed.

FIGS. **8A** and **8B** illustrate an outline of the light emission in this display device. FIG. **8A** shows the state before the voltage is applied to the light emitting layer. In the drawing, the inside of a figure drawn by the dotted line is a region doped with an impurity element (a halogen element, in this embodiment) while the periphery of the figure is a region that is not doped with the impurity element.

The state after the voltage is applied to the light emitting layer is shown in FIG. **8B**. The region doped with the impurity element in FIG. **8A** emits light, so that the region can be visually recognized as a light emitting region. On the other hand, the region that is not doped with the impurity element in FIG. **8A** does not emit light regardless of the application of voltage.

As described above, according to this embodiment, selective light emission only from the hole conveying region can be obtained by doping of the halogen element. That is, distinguishing a light emitting region from a non-light emitting region by photolithography technique is made possible. Also, this embodiment requires patterning only once during the process. In other words, there is no need for patterning the anode or the cathode. The manufacture process is therefore very simple, providing an advantage of low production cost.

Embodiment 6

This embodiment gives a description of the case where the impurity element used for doping in Embodiment 5 is changed to other elements. The symbols used in Embodiment 5 will be referred when necessary.

First, following the steps of Embodiment 5, the state shown in FIG. **6C** is obtained. A doping step of an impurity element is then carried out as shown in FIG. **7**. In this embodiment, the

vicinity of the interface between the cathode **602** and the light emitting layer **603** is doped with an alkali metal element or an alkaline earth metal element. The vicinity of the interface between the cathode **602** and the light emitting layer **603** is doped with the impurity element. As a result, an electron conveying region **701** is formed.

The selective light emission control as in Embodiment 5 can be attained also by this embodiment. That is, the selective light emission only by the portion where the electron conveying region **701** is possible according to this embodiment.

This embodiment may be combined with Embodiment 5. To elaborate, if the two embodiments are combined, the vicinity of the interface between the light emitting layer **603** and the anode **604** is doped with the halogen element to form the hole conveying region while the vicinity of the interface between the light emitting layer **603** and the cathode **602** is doped with the alkali metal element or the alkaline earth metal element to form the electron conveying region.

Embodiment 7

This embodiment shows an example in which Embodiment 1 or 3 is applied to manufacture of an active matrix type EL display device where a pixel portion and its driver circuits are integrally formed on the same substrate. Reference is made to FIGS. **10** and **11** for explanation.

In FIG. **10**, reference symbol **10** denotes a substrate, **11**, a pixel portion, **12**, a source side driver circuit, and **13**, a gate side driver circuit. Wirings from the respective driver circuits are connected to external equipment through input/output wirings **14** to **16** and through an FPC **17**. The wiring **14** is a wiring for sending a video signal, a clock signal, etc., to the source side driver circuit **12**. The wiring **15** is a wiring for sending a clock signal or the like to the gate side driver circuit **13**. The wiring **16** is a wiring for supplying the pixel portion **11** with the current to be fed to an EL element.

A sealing member (also called as a housing member) **18** is provided so as to cover at least the pixel portion, preferably, the driver circuits and the pixel portion. The sealing member **18** has a shape with a concave portion whose inner size (depth) is larger than the outer size (height) of the pixel portion **11**, or is in a sheet form. An adhesive (also called as a sealant) **19** fixes the sealing member **18** to the substrate **10** so that the sealing member **18** and the substrate **10** together form an airtight space. At this point, the EL element reaches a state in which it is completely sealed in the airtight space, and access to the open air is completely cut off. The housing member **18** may be provided in plural numbers.

A preferred material for the sealing member **18** is an insulative substance such as glass or polymer. However, in a top view of FIG. **10**, EL light is emitted toward the front of the drawing and, therefore, to use a light transmitting material is required. For example, amorphous glass (borosilicate glass, quartz, etc.), crystallized glass, ceramic glass, organic resins (acrylic resins, styrene-based resins, polycarbonate-based resins, epoxy-based resins, etc.), silicone-based resins can be named.

Epoxy-based resins, acrylate-based resins or the like may be used as the adhesive **19**. Thermally curable resins or optically curable resins may also be used for the adhesive. However, to transmit as little amount of oxygen and moisture as possible is required for the material used as the adhesive **19**.

A gap (a region denoted by **20** in FIG. **11**) between the sealing member **18** and the substrate **10** is preferably filled with an inert gas (argon, helium, nitrogen, etc.). The filler is not necessarily limited to gas but may be an inert liquid (liquid fluoro carbon represented by perfluoroalkane, or the

like) may also be used. Other appropriate inert liquid is disclosed in Japanese Patent Application Laid-open No. Hei 8-78519.

To put a drying agent in the gap **20** is also effective. As the drying agent, materials disclosed in Japanese Patent Application Laid-open No. Hei 9-148066 may be used. Barium oxide is typically used.

As shown in FIG. **11**, a plurality of pixels each having an isolated EL element are formed in the pixel portion. After forming a pixel electrode **21**, a light emitting layer **22** is formed by evaporation using a mask, and an anode **23** is formed thereon using another mask to fabricate the EL element having the sectional structure as shown in FIG. **11**. In this embodiment, the pixel electrode (also serving as a cathode) **21**, the light emitting layer **22**, the anode **23**, and a passivation film **24** are formed continuously using a thin film forming apparatus of multi-chamber type as shown in FIG. **9**.

The anode **23** is connected to the input/output wiring **26** in a region denoted by reference symbol **25**. The input/output wiring **26** is a power supply line for providing the anode **23** with a given voltage, and is connected to the FPC **17** through a conductive paste material **27**.

The input/output wiring **26** is formed at the same time as source wirings and drain wirings of TFTs are formed. If the input/output wiring **26** is formed of a material mainly containing aluminum and an ITO film is used to form the anode **23**, corrosion of aluminum may take place at a portion where the wiring comes into contact with the anode, which is unpreferable. In this case, the trouble of corrosion can be averted by using as the anode **23** a compound obtained by mixing indium oxide with zinc oxide.

The input/output wiring **26** passes through the gap (which is not hollow but filled with the adhesive **19**; the adhesive therefore has to be poured to a thickness enough to flatten the level difference that is made by the input/output wiring) between the sealing member **18** and the substrate **10**, and is connected to the FPC **17**. Although description here takes the input/output wiring **26**, the other input/output wirings **14** to **16** are similarly connected to the FPC **17** passing under the sealing member **18**.

Embodiment 8

A structure in which a source side driver circuit and a gate side driver circuit are formed in the periphery of a pixel portion is described in Embodiment 7. It is also possible to form the driver circuits in the pixel portion, which will be explained in this embodiment. In that case, all of light emitted from a light emitting layer exit from the opposite side of a substrate, creating deadspace, where no light can pass, between the substrate and a pixel electrode.

Therefore, any element or circuit may be formed in this deadspace without affecting display of images. To form the driver circuits in the deadspace thus makes it possible to reduce the size of the substrate even further.

Details of the basic concept of this embodiment is described in Japanese Patent Application No. Hei 11-182590, filed by the present applicant. The filed specification makes a complete reference for Embodiment 8 of the present invention.

Embodiment 9

EL display devices fabricated by implementing Embodiments 1 to 4 are of self-light emitting type, and hence are superior in visibility in a bright place to liquid crystal display

devices. This is the reason why the devices of the present invention can be used as a direct-view type EL display.

Wide view angle may be named as one of advantages the EL displays hold over the liquid crystal displays. Accordingly, it is recommendable to employ an EL display that applies the present invention to a display (display monitor) of 30 inches or more in diagonal (typically, 40 inches or more), when watching a television broadcast on a large screen.

The present invention can be utilized not only as an EL display (a monitor for a personal computer, a monitor for receiving television broadcasting, a monitor for advertisement display, etc.) but also as a display for various kinds of electronic devices.

The electronic devices as such may include video cameras, digital cameras, goggle type displays (head mount displays), navigation systems for automobiles, personal computers, video game machines integrated with displays, portable information terminals (mobile computers, cellular phones, electronic books, etc.), and image reproducing devices provided with recording media (specifically, devices that are provided with a display capable of reproducing recording media such as compact discs (CDs), laser discs (LDs), and digital video discs (DVDs) and displaying images recorded therein). Examples of these electronic devices are shown in FIGS. 12A to 12F.

FIG. 12A shows a personal computer that is comprised of a main body **2001**, a housing **2002**, a display monitor **2003**, and a keyboard **2004**. The present invention can be used for the display monitor **2003**.

FIG. 12B shows a video camera that is comprised of a main body **2101**, a display monitor **2102**, an audio input unit **2103**, operation switches **2104**, a battery **2105**, and an image receiving unit **2106**. The present invention can be used for the display monitor **2102**.

FIG. 12C shows a part (right hand piece) of a head mount type EL display that is comprised of a main body **2201**, signal cables **2202**, a fixating band **2203**, a display monitor **2204**, an optical system **2205**, and a display device **2206**. The present invention can be used for the display device **2206**.

FIG. 12D shows an image reproducing device provided with a recording medium (specifically, a DVD player) which is comprised of a main body **2301**, a recording medium (CD, LD, DVD, or the like) **2302**, operation switches **2303**, a display monitor (a) **2304**, and a display monitor (b) **2305**. The display monitor (a) mainly displays image information while the display monitor (b) mainly displays character information. The present invention can be used for both the display monitors (a) and (b). Other image reproducing device provided with a recording medium, to which the present invention is applicable, includes a CD player, a game machine and the like.

FIG. 12E shows a portable (mobile) computer that is comprised of a main body **2401**, a camera unit **2402**, an image receiving unit **2403**, an operation switch **2404**, and a display monitor **2405**. The present invention can be used for the display monitor **2405**.

FIG. 12F shows an EL display that is comprised of a housing **2501**, a support stand **2502**, and a display monitor **2503**. The present invention can be used for the display monitor **2503**. Having wide view angles, the EL display is advantageous over a liquid crystal display in a large screen display, especially in a display whose diagonal line extends 10 inches or longer (more particularly, 30 inches or longer).

If the brightness of emitted light of EL materials is improved in future, it will become possible to use the present invention for a front type or a rear type projector by enlarging

and projecting, with the use of a lense or the like, light including image information that is output.

According to the present invention, the number of layers can be reduced while the performance of the EL element is kept or improved. The production cost of the EL display device can thus be reduced. In addition, An electronic device (electronic equipment) having such an inexpensive EL display device as a display may accordingly be decreased in product cost.

What is claimed is:

1. A method of manufacturing an EL display device comprising the steps of:

forming a cathode;

forming an organic layer comprising a light emitting material over the cathode;

forming an anode over the organic layer; and

introducing a halogen element into a portion of the organic layer through at least the anode so that the portion of the organic layer functions as a hole transport layer,

wherein the portion of the organic layer is in contact with the anode.

2. The method according to claim 1 further comprising a step of forming a passivation film on the anode wherein the halogen element is introduced through the passivation film.

3. The method according to claim 2 wherein the passivation film comprises an insulating film which contains silicon.

4. The method according to claim 1, wherein the halogen element is introduced in such a manner that a concentration of the halogen element is highest in a vicinity of an interface between the anode and the organic layer.

5. A method of manufacturing an EL display device comprising the steps of:

forming a cathode;

forming an organic layer comprising a light emitting material over the cathode;

forming an anode over the organic layer;

forming an insulating film over the anode;

introducing a halogen element into a portion of the organic layer through at least the insulating film so that the portion of the organic layer functions as a hole transport layer,

wherein the portion of the organic layer is in contact with the anode.

6. The method according to claim 5, wherein the halogen element is introduced in such a manner that a concentration of the halogen element is highest in a vicinity of an interface between the anode and the organic layer.

7. The method according to claim 5 wherein the insulating film comprises silicon.

8. A method of manufacturing an EL display device comprising the steps of:

forming a cathode;

forming an organic layer comprising a light emitting material over the cathode;

forming an anode over the organic layer;

introducing an alkali metal element into a portion of the organic layer through at least the anode so that the portion of the organic layer functions as an electron transport layer,

wherein the portion of the organic layer is in contact with the cathode.

9. The method according to claim 8 further comprising a step of forming a passivation film on the anode wherein the alkali metal element is introduced through the passivation film.

10. The method according to claim 9 wherein the passivation film comprises an insulating film which contains silicon.

13

11. The method according to claim 8, wherein the alkali metal element is introduced in such a manner that a concentration of the alkali metal element is highest in a vicinity of an interface between the cathode and the organic layer.

12. A method of manufacturing an EL display device comprising the steps of:

forming a cathode;

forming an organic layer comprising a light emitting material over the cathode;

forming an anode over the organic layer;

introducing an alkaline earth metal element into a portion of the organic layer through at least the anode so that the portion of the organic layer functions as an electron transport layer,

14

wherein the portion of the organic layer is in contact with the cathode.

13. The method according to claim 12 further comprising a step of forming a passivation film on the anode wherein the alkaline earth metal element is introduced through the passivation film.

14. The method according to claim 13 wherein the passivation film comprises an insulating film which contains silicon.

15. The method according to claim 12, wherein the alkaline earth metal element is introduced in such a manner that a concentration of the alkaline earth metal element is highest in a vicinity of an interface between the cathode and the organic layer.

* * * * *

专利名称(译)	EL显示装置及其制造方法		
公开(公告)号	US7456037	公开(公告)日	2008-11-25
申请号	US10/747864	申请日	2003-12-29
[标]申请(专利权)人(译)	株式会社半导体能源研究所		
申请(专利权)人(译)	半导体能源研究所有限公司.		
当前申请(专利权)人(译)	半导体能源研究所有限公司.		
[标]发明人	YAMAZAKI SHUNPEI		
发明人	YAMAZAKI, SHUNPEI		
IPC分类号	H01L51/40 H01L21/00 H05B33/10 H01L27/32 H01L31/12 H01L51/50 H01L51/52 H05B33/12 H05B33/14 H05B33/22		
CPC分类号	H01L51/5056 H01L51/5072 H01L51/5088 H01L51/5092 H01L27/3244 H01L51/5253 Y10S428/917		
优先权	1999209227 1999-07-23 JP		
其他公开文献	US20040229392A1		
外部链接	Espacenet USPTO		

摘要(译)

在保持或改善EL元件性能的同时减少层数，从而降低生产成本。在像素电极（104,105）上形成阴极（106,107），发光层（108），阳极（109）和钝化膜（110）。此后，发光层（108）和阳极（109）之间的界面附近通过钝化膜（110）和阳极（109）掺杂有卤素元素。这导致形成用作空穴传输层的空穴传输区域（111），从而提高发光效率。

