



US008808875B2

(12) **United States Patent**
Kamatani et al.

(10) **Patent No.:** **US 8,808,875 B2**
(45) **Date of Patent:** **Aug. 19, 2014**

(54) **COMPOUND AND ORGANIC EL DEVICE**

(52) **U.S. CL.**

(75) Inventors: **Jun Kamatani**, Tokyo (JP); **Shinjiro Okada**, Kamakura (JP); **Takao Takiguchi**, Chofu (JP); **Akihito Saitoh**, Yokohama (JP); **Keiji Okinaka**, Kawasaki (JP); **Satoshi Igawa**, Fujisawa (JP); **Naoki Yamada**, Inagi (JP); **Masashi Hashimoto**, Tokyo (JP)

CPC **H01L 51/0054** (2013.01); **C09K 2211/1007** (2013.01); **H05B 33/14** (2013.01); **C09K 2211/1011** (2013.01); **C09K 11/06** (2013.01); **H01L 51/5012** (2013.01); **C07C 2103/40** (2013.01); **C07C 13/66** (2013.01); **Y10S 428/917** (2013.01)
USPC **428/690**; 428/917; 428/411.1; 428/336; 570/129

(73) Assignee: **Canon Kabushiki Kaisha**, Tokyo (JP)

(58) **Field of Classification Search**

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 987 days.

USPC 428/690
See application file for complete search history.

(21) Appl. No.: **12/298,300**

(56) **References Cited**

(22) PCT Filed: **Apr. 19, 2007**

U.S. PATENT DOCUMENTS

(86) PCT No.: **PCT/JP2007/059000**

§ 371 (c)(1),
(2), (4) Date: **Oct. 23, 2008**

2002/0022151 A1 2/2002 Ishikawa et al. 428/690
2004/0232409 A1* 11/2004 Igarashi et al. 257/40
2005/0236974 A1 10/2005 Suzuki et al. 313/504
2007/0063189 A1* 3/2007 Schwalm et al. 257/40
2007/0104977 A1* 5/2007 Arakane et al. 428/690
2007/0252141 A1 11/2007 Negishi et al. 257/40
2008/0124577 A1 5/2008 Saitoh et al. 428/704
2008/0272692 A1 11/2008 Hashimoto et al. 313/504

(87) PCT Pub. No.: **WO2007/125976**

PCT Pub. Date: **Nov. 8, 2007**

FOREIGN PATENT DOCUMENTS

(65) **Prior Publication Data**

US 2009/0096368 A1 Apr. 16, 2009

JP 10-189247 7/1998
JP 10-189248 7/1998
JP 10189248 A * 7/1998 H05B 33/14
JP 2000-007587 1/2000
JP 2000-007594 1/2000
JP 2002-043058 2/2002
JP 2004-107326 4/2004
JP 2005-068087 3/2005
JP 2005-235787 9/2005
WO WO 2004-020371 A1 3/2004
WO WO 2005/026088 * 3/2005 C08C 13/00

(30) **Foreign Application Priority Data**


Apr. 25, 2006 (JP) 2006-120806

OTHER PUBLICATIONS

Machine English translation of JP 10-189248 A. Apr. 13, 2012.*
International Preliminary Report on Patentability dated Oct. 28, 2008 for PCT/JP2007/059000.

(51) **Int. Cl.**

H01J 1/63 (2006.01)
C07C 25/13 (2006.01)
C07C 43/205 (2006.01)
H05B 33/14 (2006.01)
H01L 51/00 (2006.01)
C09K 11/06 (2006.01)
C07C 13/66 (2006.01)
H01L 51/50 (2006.01)




Chinese Office Action issued in corresponding application
No. 200780014786.0 dated Sep. 30, 2011—9 pages.

* cited by examiner

Primary Examiner — J. L. Yang

(74) Attorney, Agent, or Firm — Fitzpatrick, Cella, Harper &
Scinto



(57)

ABSTRACT

The present invention provides a high-performance organic EL device and a novel compound used for the device. The novel compound of the present invention is a fluorenone compound having the following general formula (2):

The organic EL device of the present invention is an organic EL device comprising: an anode; a cathode; and an organic compound layer interposed between the anode and the cathode, wherein the organic compound layer has the fluorenone compound.

10 Claims, 3 Drawing Sheets

FIG. 1A




FIG. 1B




FIG. 1C




FIG. 2





FIG. 3



1

COMPOUND AND ORGANIC EL DEVICE

TECHNICAL FIELD

The present invention relates to a novel organic compound and a light-emitting device having the compound.

BACKGROUND ART

An organic light-emitting device has a constitution in which a thin film containing a fluorescent organic compound or a phosphorescent organic compound is interposed between an anode and a cathode. Electrons and holes are injected from the respective electrodes so that excitons of the fluorescent compound or of the phosphorescent compound are generated. The organic light-emitting device utilizes light to be radiated upon return of the excitons to a ground state.


A benzofluoranthene compound has been researched (Japanese Patent Application Laid-Open Nos. H10-189247, 2005-235787, 2000-7587, 2000-7594, and 2005-68087).

DISCLOSURE OF THE INVENTION

However, at present, an optical output with additionally high luminance or additionally high conversion efficiency has been needed. In addition, the organic light-emitting device still involves a large number of problems in terms of durability such as a change with elapse of time due to long-term use and deterioration due to an atmospheric gas containing oxygen, moisture or the like. Further, when the application of the device to a full-color display or the like is taken into consideration, the emission of blue, green, or red light with a good color purity is needed. However, a problem concerning the emission has not been sufficiently solved yet.

An object of the present invention is to provide a novel compound and an organic electroluminescence (EL) device having the compound and having an optical output with high efficiency and high luminance. Another object of the present invention is to provide a highly durable organic EL device. Another object of the present invention is to provide an organic EL device that can be easily produced at a relatively low cost.

According to the present invention, there is provided a compound represented by the following general formula (1):



Wherein R_1 and R_2 are each independently selected from a halogen atom, a linear or branched alkyl group having 1 to 5 carbon atoms, a diallylamino group which may have a substituent, a silyl group which may have a substituent, an aryl group which may have a substituent, and a heterocyclic group which may have a substituent;

R_3 to R_6 are each independently selected from a hydrogen atom, a halogen atom, a linear or branched alkyl group having 1 to 5 carbon atoms, a diallylamino group which may have a substituent, a silyl group which may have a substituent, an aryl group which may have a substituent, and a heterocyclic group which may have a substituent; and

the substituents are each independently selected from a halogen atom, a linear or branched alkyl group having 1 to 20

2

carbon atoms (in the alkyl group, one methylene group, or two or more methylene groups not adjacent to each other may be replaced by $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{CO}-\text{O}-$, $-\text{O}-\text{CO}-$, $-\text{CH}=\text{CH}-$, or $-\text{C}=\text{C}-$, and one methylene group, or two or more methylene groups may be replaced by an arylene group or a divalent heterocyclic group; and a hydrogen atom of the alkyl group may be substituted with a fluorine atom), a diphenylamino group, a triphenylsilyl group, an aryl group, and a heterocyclic group.

The compound of the present invention can be suitably utilized in a light-emitting device. In addition, the light-emitting device of the present invention using such compound in its light-emitting layer is an excellent device capable of not only emitting light with high efficiency but also maintaining high luminance for a long time period. In addition, the device shows a larger current value than that of a conventional device at the same voltage value, so the driving of the device at a low voltage can be expected.

BRIEF DESCRIPTION OF THE DRAWINGS


FIGS. 1A, 1B and 1C are schematic views each showing an example of a light-emitting device of the present invention.

FIG. 2 is a graph showing the light-emitting characteristics of Exemplified Compound No. F-28 in toluene.

FIG. 3 is a graph showing the light-emitting characteristics of Exemplified Compound No. F-11 in toluene.

DESCRIPTION OF THE EMBODIMENTS

The present invention relates to a compound represented by the following general formula (1):



wherein R_1 and R_2 are each independently selected from a halogen atom, a linear or branched alkyl group having 1 to 5 carbon atoms, an amino group which may have a substituent, a silyl group which may have a substituent, an aryl group which may have a substituent, and a heterocyclic group which may have a substituent;


R_3 to R_6 are each independently selected from a hydrogen atom, a halogen atom, a linear or branched alkyl group having 1 to 5 carbon atoms, an amino group which may have a substituent, a silyl group which may have a substituent, an aryl group which may have a substituent, and a heterocyclic group which may have a substituent; and

the substituents shown here are each independently selected from a halogen atom, a linear or branched alkyl group having 1 to 20 carbon atoms (in the alkyl group, one methylene group, or two or more methylene groups not adjacent to each other may be replaced by $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{CO}-\text{O}-$, $-\text{O}-\text{CO}-$, $-\text{CH}=\text{CH}-$, or $-\text{C}=\text{C}-$, and one methylene group, or two or more methylene groups may be replaced by an arylene group or a divalent heterocyclic group; and a hydrogen atom of the alkyl group may be substituted with a fluorine atom), a diphenylamino group, a triphenylsilyl group, an aryl group, and a heterocyclic group.

Alternatively, the compound according to the present invention is a compound, among the compounds represented

3

by the above general formula (1), which is represented by the following general formula (2):




wherein R_1 , R_2 , R_7 and R_8 are each independently selected from a halogen atom, a linear or branched alkyl group having 1 to 5 carbon atoms, an amino group which may have a substituent, a silyl group which may have a substituent, an aryl group which may have a substituent, and a heterocyclic group which may have a substituent;

R_3 to R_6 and R_9 to R_{11} are each independently selected from a hydrogen atom, a halogen atom, a linear or branched alkyl group having 1 to 20 carbon atoms, an amino group which may have a substituent, a silyl group which may have a substituent, an aryl group which may have a substituent, and a heterocyclic group which may have a substituent; and


the substituents shown here are each independently selected from a halogen atom, a linear or branched alkyl group having 1 to 20 carbon atoms (in the alkyl group, one methylene group, or two or more methylene groups not adjacent to each other may be replaced by $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{CO}-\text{O}-$, $-\text{O}-\text{CO}-$, $-\text{CH}=\text{CH}-$, or $-\text{C}=\text{C}-$, and one methylene group, or two or more methylene groups may be replaced by an arylene group or a divalent heterocyclic group; and a hydrogen atom of the alkyl group may be substituted with a fluorine atom), a diphenylamino group, a triphenylsilyl group, an aryl group, and a heterocyclic group.

Alternatively, the compound according to the present invention is a compound, among the compounds represented by the above general formula (1), which is represented by the following general formula (3):



Alternatively, the compound according to the present invention is a compound, among the compounds represented by the above general formula (2), which is represented by the following general formula (4):

4



In addition, the organic EL device according to the present invention is an organic electroluminescent device (organic EL device) including at least one layer containing an organic compound between a pair of electrodes.

In addition, the organic EL device according to the present invention is an organic EL device in which the layer containing the organic compound is a light-emitting layer.

In addition, the organic EL device according to the present invention is an organic electroluminescent device in which the layer containing the organic compound is a light-emitting layer, the light-emitting layer is composed of at least a compound as a host and a compound as a guest, and at least one of the host and the guest is the above organic compound.

In addition, the organic EL device according to the present invention is an organic EL device in which light emission from the guest is fluorescent emission.

Further description is given below.

When a light emitting layer is formed of a carrier transportable host material and a guest, a main process for light emission includes the following several steps of:

1. transporting an electron or a hole in the light emitting layer;
2. generating an exciton of the host material;
3. transferring excitation energy between host material molecules; and
4. moving of the excitation energy from the host material to the guest.

Desired energy movement in each step and light emission occur in competition with various deactivation steps.

Needless to say, the emission quantum yield of a light emission central material itself must be large in order that the emission efficiency of an EL device may be improved. However, the efficiency with which energy movement between host molecules or between host and guest molecules can be performed is also of a great concern. In addition, the deterioration of light emission due to supply of current is assumed to be related to a change in environment surrounding a light emitting material due to at least the light emission central material itself or a molecule around the light emission central material, though no causes for the deterioration have been revealed at present.

In view of the foregoing, the inventors of the present invention have made various studies. As a result, the inventors have found that an organic EL device using a compound represented by the general formula (1) as an electron transport layer or a light-emitting layer, preferably a host or guest for the light-emitting layer, emits light with high efficiency, keeps high luminance for a long time period, and shows small deterioration of light emission due to supply of current.

One possible cause for the deterioration of light emission due to supply of current is the generation of an excimer between guest molecules due to the migration of a guest in a light-emitting layer. When the molecules of a light-emitting material has a shape in which the overlapping extent of the

conjugate planes of the molecules is large as in the case of fluoranthene, the probability that an excimer is generated between the molecules is high, so the insufficiency of light-emitting sites due to the fact that the guest is not used at a high concentration, or quenching between light-emitting molecules due to the migration is apt to occur.

Accordingly, such design that fluoranthene is used as a luminous core, and the core portion is covered without any expansion of a conjugate plane can provide a light-emitting device having high efficiency and showing a small color change even at a high concentration. Specifically, the realization of such light-emitting device was attained by introducing a phenyl group as a substituent into fluoranthene and by substituting two hydrogen atoms at ortho-positions of the phenyl group with skeletons each having an atomic radius larger than that of a hydrogen atom to obtain the compound of the present invention.

In addition, when a phenyl group having substituents other than a hydrogen atom at its ortho-positions is introduced into fluoranthene, fluoranthene and the phenyl group change their structures in the direction of losing planarity between fluoranthene and the phenyl group as compared to that in the case where the phenyl group has no substituents at its ortho-positions. The structural change progresses in the direction of breaking conjugation between fluoranthene and the phenyl group, so the case where the phenyl group has substituents at its ortho-positions can exert an effect of shortening the luminous wavelength as compared to that in the case where the phenyl group has no substituents at its ortho-positions.

As described above, the use of the compound of the present invention in a light-emitting layer is effective. The use of the compound in an electron transport layer, a hole transport layer, an electron blocking layer, a hole blocking layer, an electron injection layer, or a hole injection layer is also effective.

An organic layer containing the compound of the present invention can be produced by, for example, a vacuum vapor deposition method, a cast method, an application method, a spin coating method, or an ink-jet method.

In addition, among the substituents, the dialkylamino group includes a diphenylamino group, a naphthylphenylamino group, and a dinaphthylamino group.

FIGS. 1A, 1B and 1C each show the basic device constitution of the present invention.

As shown in FIGS. 1A, 1B and 1C, an organic EL device generally has a constitution that a transparent electrode **14** having a thickness of 50 nm or more to 200 nm or less, a plurality of organic layers, and a metal electrode **11** are

formed on a transparent substrate **15** so as to interpose the organic layers between the electrodes.

FIG. 1A shows an example in which the organic layers are composed of a light-emitting layer **12** and a hole transport layer **13**. For example, ITO having a large work function is used in the transparent electrode **14** so that the injection of a hole from the transparent electrode **14** into the hole transport layer **13** is facilitated. A metal material having a small work function such as aluminum, magnesium, or an alloy thereof is used in the metal electrode **11** so that the injection of an electron into the organic layers is facilitated.

The compound of the present invention is used in the light-emitting layer **12**. A material having electron-donating property such as a triphenylamine derivative typified by α -NPD can be appropriately used in the hole transport layer **13**.

A device having the above-mentioned constitution exhibits electrical rectifying property. When an electric field is applied so that the metal electrode **11** serves as a cathode and the transparent electrode **14** serves as an anode, an electron is injected from the metal electrode **11** into the light-emitting layer **12**, and a hole is injected from the transparent electrode **14** into the light-emitting layer **12**.


The injected hole and electron recombine in the light-emitting layer **12** to generate an exciton, whereby light is emitted. In this case, the hole transport layer **13** serves as an electron blocking layer. As a result, the efficiency of recombining a hole and an electron at an interface between the light-emitting layer **12** and the hole transport layer **13** improves, and hence the emission efficiency of the device improves.

Further, in FIG. 1B, an electron transport layer **16** is provided between the metal electrode **11** and the light-emitting layer **12** as shown in FIG. 1A. A light-emitting function, and electron- and hole-transporting functions are separated from one another so that the constitution of a device is more effective in blocking a carrier. As a result, the emission efficiency of the device improves. For example, an oxadiazole derivative can be used in the electron transport layer **16**.

In addition, four-layered constitution as shown in FIG. 1C is also desirable, in which four layers, that is, the hole transport layer **13**, the light-emitting layer **12**, an exciton diffusion prevention layer **17**, and the electron transport layer **16**, and the metal electrode **11** are provided in the stated order from the side of the transparent electrode **14** as an anode.


Specific structural formulae of organic compounds to be used in the present invention are shown below.

These formulae are merely representative examples, and the present invention is not limited to them.



F-1






F-3



F-2

F-4


7



8


-continued

F-5




F-6

F-7




F-8

F-9




F-10

F-11



F-12

F-13






F-14

9

10



-continued
F-15

F-16





F-17

F-18





F-19

F-20




F-21

F-22



F-23


F-24




11

12


-continued




F-25




F-26




F-27




F-28




F-29




F-30




F-31




F-32




F-33



F-34



F-35



F-36



13

14

-continued



F-37

F-38





F-39

F-40





F-41

F-42





F-43

F-44



F-45

F-46





15

16

-continued



F-47

F-48




F-49


F-50




F-51




F-52



17

-continued
F-53

18




F-54

Hereinafter, the present invention will be specifically described with referring to the following examples, but the present invention is not limited to them.

Example 1

Synthesis of Exemplified Compound No. F-28



360 mg (1 mmole) of Compound 1-1, 450 mg (3 mmole) of Compound 1-2 (manufactured by SIGMA-ALDRICH), 0.1 g of Pd(PPh₃)₄, 10 ml of toluene, 5 ml of ethanol, and 10 ml of a 2M aqueous solution of sodium carbonate were charged into a 100-ml egg plant flask, and the mixture was stirred in a stream of nitrogen at 80° C. for 8 hours. After the completion of the reaction, the crystal was separated by filtration, and was washed with water and ethanol. After having been subjected to hot filtration with toluene, the resultant crystal was recrystallized with toluene/heptane and dried in a vacuum at 120° C., whereby 356 mg of Exemplified Compound No. F-28 were obtained (yield: 87%).

FIG. 2 shows the graph of the light-emitting characteristics of the compound in toluene.

Example 2

In this example, a device having such device constitution including three organic layers as shown in FIG. 1B was used.

ITO was patterned onto a glass substrate to form a pattern having a thickness of 100 nm. The following organic layers and electrode layers were continuously formed on the resultant ITO substrate by vacuum vapor deposition using resistance heating in a vacuum chamber at a pressure of 10⁻⁵ Pa so that an opposing electrode area was 3 mm².

Device A:



Hole transport layer (20 nm): Compound A

Light-emitting layer (25 nm): Exemplified Compound No. F-28 (weight ratio 5%):Compound B

Electron transport layer (40 nm): Bphen

Metal electrode layer 1 (1 nm): KF

Metal electrode layer 2 (100 nm): Al




The current-voltage characteristics of the EL device were measured with a microammeter 4140B manufactured by Hewlett-Packard Company, and the emission luminance of the device was measured with a BM7 manufactured by TOP-

CON CORPORATION. As a result, the observation of light emission derived from Exemplified Compound No. F-28 was attained.

Example 3

Synthesis of Exemplified Compound No. F-



984 mg (4 mmole) of Compound 3-1, 1,420 mg (4 mmole) of Compound 3-2, 0.1 g of Pd(PPh₃)₄, 20 ml of toluene, 10 ml of ethanol, and 20 ml of a 2-M aqueous solution of sodium carbonate were charged into a 200-ml egg plant flask, and the mixture was stirred in a stream of nitrogen at 80° C. for 8 hours. After the completion of the reaction, the crystal was separated by filtration, and was washed with water and ethanol. After having been subjected to hot filtration with toluene, the resultant crystal was recrystallized with toluene/heptane and dried in a vacuum at 120° C., whereby 900 mg of Exemplified Compound No. F-11 were obtained (yield: 72%).

FIG. 3 shows the graph of the light-emitting characteristic of the compound in toluene.

Matrix-assisted laser desorption/ionization time-of-flight mass spectrometry (MALDI-TOF MS) confirmed that the compound had an M⁺ of 430.1.


A device was produced in the same manner as in Example 2 except that Exemplified Compound No. F-11 was used

instead of Exemplified Compound No. F-28 of Example 2. As a result, the observation of light emission was attained.

This application claims the benefit of Japanese Patent Application No. 2006-120806, filed Apr. 25, 2006, which is hereby incorporated by reference herein in its entirety.

The invention claimed is:

1. A compound represented by the following general formula (2):



wherein R₁ and R₂ are the same and selected from a halogen atom and a linear or branched alkyl group having 3 to 5 carbon atoms;
 wherein R₃ to R₅ are each a hydrogen atom;
 wherein R₇ and R₈ are the same and are a linear or branched alkyl group having 3 to 5 carbon atoms; and
 wherein R₉ to R₁₁ are each a hydrogen atom.

2. An organic EL device comprising:
 an anode;
 a cathode; and
 an organic compound layer interposed between the anode and the cathode,

wherein the organic compound layer has the compound of general formula (2) according to claim 1.

3. The organic EL device according to claim 2, wherein the organic compound layer is a light-emitting layer.

4. The organic EL device according to claim 3, wherein the light-emitting layer has a host and a guest, and the host is the compound of general formula (2).

5. The organic EL device according to claim 3, wherein the light-emitting layer has a host and a guest, and the guest is the compound of general formula (2).

6. The organic EL device according to claim 3, wherein the light-emitting layer has a host and a guest, and the host and the guest each are independently selected from the compound of general formula (2).

7. A full-color display comprising the organic EL device according to claim 3, wherein the display emits blue, green, or red light.

8. A full-color display comprising the organic EL device according to claim 4, wherein the display emits blue, green, or red light.

9. A full-color display comprising the organic EL device according to claim 5, wherein the display emits blue, green, or red light.

10. A full-color display comprising the organic EL device according to claim 6, wherein the display emits blue, green, or red light.

* * * * *

专利名称(译)	复合和有机EL器件		
公开(公告)号	US8808875	公开(公告)日	2014-08-19
申请号	US12/298300	申请日	2007-04-19
[标]申请(专利权)人(译)	佳能株式会社		
申请(专利权)人(译)	佳能株式会社		
当前申请(专利权)人(译)	佳能株式会社		
[标]发明人	KAMATANI JUN OKADA SHINJIRO TAKIGUCHI TAKAO SAITOH AKIHITO OKINAKA KEIJI IGAWA SATOSHI YAMADA NAOKI HASHIMOTO MASASHI		
发明人	KAMATANI, JUN OKADA, SHINJIRO TAKIGUCHI, TAKAO SAITOH, AKIHITO OKINAKA, KEIJI IGAWA, SATOSHI YAMADA, NAOKI HASHIMOTO, MASASHI		
IPC分类号	H05B33/14 C09K11/06 C07C25/13 C07C13/66 C07C43/205 H01L51/50 H01L51/00 H01J1/63		
CPC分类号	H01L51/0054 H05B33/14 C09K11/06 C07C13/66 C09K2211/1007 C09K2211/1011 H01L51/5012 C07C2103/40 Y10S428/917 Y10T428/265 Y10T428/31504 C07C2603/40		
优先权	2006120806 2006-04-25 JP		
其他公开文献	US20090096368A1		
外部链接	Espacenet USPTO		

摘要(译)

本发明提供高性能有机EL器件和用于该器件的新型化合物。本发明的新化合物是具有下列通式(2)的荧蒽化合物：本发明的有机EL器件是有机EL器件，包括：阳极；阴极；和介于阳极和阴极之间的有机化合物层，其中有机化合物层具有荧蒽化合物。

