



US009266851B2

(12) **United States Patent**
Yoshida et al.

(10) **Patent No.:** **US 9,266,851 B2**
(45) **Date of Patent:** **Feb. 23, 2016**

(54) **FLUORENE-CONTAINING AROMATIC COMPOUND, MATERIAL FOR ORGANIC ELECTROLUMINESCENT ELEMENT, AND ORGANIC ELECTROLUMINESCENT ELEMENT USING SAME**

C07D 401/14 (2006.01)
C07D 403/10 (2006.01)
C07D 403/14 (2006.01)
C07D 405/14 (2006.01)
C07D 409/12 (2006.01)
C07D 409/14 (2006.01)
C07D 471/04 (2006.01)
H01L 51/00 (2006.01)
C09B 57/00 (2006.01)
C09B 57/10 (2006.01)
C09B 69/00 (2006.01)

(75) Inventors: **Kei Yoshida**, Sodegaura (JP); **Kazuki Nishimura**, Sodegaura (JP); **Mitsunori Ito**, Sodegaura (JP); **Yuichiro Kawamura**, Sodegaura (JP); **Toshinari Ogiwara**, Sodegaura (JP); **Toshihiro Iwakuma**, Sodegaura (JP)

(52) **U.S. Cl.**
CPC **C07D 307/91** (2013.01); **C07D 209/86** (2013.01); **C07D 401/10** (2013.01); **C07D 401/14** (2013.01); **C07D 403/10** (2013.01); **C07D 403/14** (2013.01); **C07D 405/14** (2013.01); **C07D 409/12** (2013.01); **C07D 409/14** (2013.01); **C07D 471/04** (2013.01); **C09B 57/00** (2013.01); **C09B 57/08** (2013.01); **C09B 57/10** (2013.01); **C09B 69/008** (2013.01); **H01L 51/0071** (2013.01); **H01L 51/5016** (2013.01); **H01L 51/5072** (2013.01)

(73) Assignee: **IDEIMITSU KOSAN CO., LTD.**, Tokyo (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 1071 days.

(21) Appl. No.: **13/386,240**

(22) PCT Filed: **Oct. 14, 2010**

(86) PCT No.: **PCT/JP2010/068079**

§ 371 (c)(1),
(2), (4) Date: **Jan. 20, 2012**

(87) PCT Pub. No.: **WO2011/046182**

PCT Pub. Date: **Apr. 21, 2011**

(65) **Prior Publication Data**

US 2012/0126217 A1 May 24, 2012

(30) **Foreign Application Priority Data**

Oct. 16, 2009 (JP) 2009-239786

(51) **Int. Cl.**

H01L 51/50 (2006.01)
C07D 307/91 (2006.01)
C07D 209/86 (2006.01)
C07D 401/10 (2006.01)


(58) **Field of Classification Search**

None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,550,594 B2	6/2009	Okajima et al.
7,632,578 B2	12/2009	Lee et al.
2004/0086745 A1	5/2004	Iwakuma et al.
2004/0115476 A1	6/2004	Oshiyama et al.
2004/0157084 A1	8/2004	Lee et al.
2005/0127823 A1	6/2005	Iwakuma et al.
2005/0164032 A1	7/2005	Ise et al.
2005/0249976 A1	11/2005	Iwakuma et al.
2006/0041126 A1	2/2006	Schäfer et al.
2006/0051616 A1	3/2006	Suzuki et al.
2006/0097227 A1	5/2006	Okajima et al.
2006/0134460 A1	6/2006	Kondakova et al.
2006/0141284 A1	6/2006	Tomita et al.
2006/0154105 A1*	7/2006	Yamamoto et al. 428/690
2006/0180806 A1	8/2006	Arakane et al.
2006/0251918 A1	11/2006	Iwakuma



2006/0257684 A1	11/2006	Arakane et al.	JP	2003-277743 A	10/2003
2007/0051944 A1	3/2007	Vestweber et al.	JP	2004-2297 A	1/2004
2007/0052346 A1	3/2007	Iwakuma et al.	JP	2004-31004 A	1/2004
2007/0069638 A1	3/2007	Matsuura et al.	JP	2004-171808 A	6/2004
2007/0090753 A1	4/2007	Arakane	JP	2004-214050 A	7/2004
2007/0141387 A1	6/2007	Nakano et al.	JP	2005-255561 A	9/2005
2007/0159083 A1	7/2007	Matsuura et al.	JP	2005 289914	10/2005
2007/0172698 A1	7/2007	Iwakuma et al.	JP	2007-220721 A	8/2007
2007/0188083 A1	8/2007	Iwakuma et al.	JP	2007 261969	10/2007
2007/0190355 A1	8/2007	Ikeda et al.	JP	2008-147424 A	6/2008
2007/0194701 A1	8/2007	Ito et al.	JP	2008-205488 A	9/2008
2007/0224448 A1	9/2007	Ikeda et al.	JP	2009-16693 A	1/2009
2007/0257600 A1	11/2007	Matsuura et al.	JP	2009-21336 A	1/2009
2007/0296328 A1	12/2007	Matsuura et al.	JP	2009-76511 A	4/2009
2008/0145699 A1	6/2008	Yabe et al.	JP	2009-152528 A	7/2009
2008/0206597 A1	8/2008	Iwakuma	JP	2009-152529 A	7/2009
2009/0072732 A1	3/2009	Arakane et al.	JP	2009-158848 A	7/2009
2009/0091240 A1*	4/2009	Ikeda et al. 313/504	JP	2009-218547 A	9/2009
2009/0102363 A1	4/2009	Haga et al.	JP	2010-185047 A	8/2010
2009/0218940 A1	9/2009	Okajima et al.	JP	2010-202599 A	9/2010
2009/0224658 A1	9/2009	Iwakuma et al.	KR	10-2009-0131958 A	12/2009
2009/0243473 A1	10/2009	Iwakuma et al.	KR	10-2010-0121238 A	11/2010
2009/0284138 A1	11/2009	Yasukawa et al.	KR	10-2010-0131745	12/2010
2009/0302743 A1	12/2009	Kato et al.	TW	306890 B	3/2009
2009/0309488 A1	12/2009	Kato et al.	WO	03 080760	10/2003
2010/0039026 A1	2/2010	Yang et al.	WO	2004 026870	4/2004
2010/0044689 A1	2/2010	Nishimura et al.	WO	2005 085387	9/2005
2010/0051106 A1	3/2010	Kim et al.	WO	2006 049013	5/2006
2010/0084971 A1	4/2010	Nakano et al.	WO	WO 2006/049013 A1	5/2006
2010/0163857 A1	7/2010	Kim et al.	WO	WO 2008/072539 A1	6/2008
2010/0194270 A1	8/2010	Kawamura et al.	WO	WO 2008-147110 *	12/2008 C09K 11/06
2010/0200848 A1	8/2010	Arakane et al.	WO	WO 2009/008205 A1	1/2009
2010/0207110 A1	8/2010	Nishimura et al.	WO	WO 2009/035296 A2	3/2009
2010/0219404 A1	9/2010	Endo et al.	WO	WO 2009/104733 *	8/2009 C09K 11/06
2010/0240892 A1	9/2010	Schäfer et al.	WO	WO 2010/044342 A1	4/2010
2010/0270539 A1	10/2010	Nishimura et al.	WO	WO 2010/084729 A1	7/2010
2010/0314644 A1	12/2010	Nishimura et al.	WO	WO 2010/114264 A2	10/2010
2011/0042654 A1	2/2011	Jung et al.	WO	WO 2011/037429 A2	3/2011
2011/0121277 A1	5/2011	Matsuura et al.			
2011/0248257 A1	10/2011	Kim et al.			
2011/0253995 A1	10/2011	Kato et al.			
2011/0272679 A1	11/2011	Yokoyama et al.			
2011/0309338 A1	12/2011	Iwakuma et al.			
2012/0080670 A1	4/2012	Park et al.			
2012/0085995 A1	4/2012	Kato et al.			
2012/0104940 A1	5/2012	Shin et al.			
2012/0126221 A1	5/2012	Kitamura et al.			
2012/0126690 A1	5/2012	Ise et al.			
2012/0126691 A1	5/2012	Ise et al.			
2012/0126692 A1	5/2012	Ise et al.			
2012/0153267 A1	6/2012	Matsuura et al.			
2012/0235129 A1	9/2012	Iwakuma et al.			
2012/0298975 A1	11/2012	Iwakuma et al.			
2012/0319099 A1	12/2012	Iwakuma et al.			
2012/0326601 A1	12/2012	Yasukawa et al.			
2013/0126849 A1	5/2013	Arakane et al.			
2013/0240858 A1	9/2013	Nishimura et al.			
2014/0001460 A1	1/2014	Iwakuma et al.			

FOREIGN PATENT DOCUMENTS

CN	101052636 A	10/2007
CN	102292327 A	12/2011
EP	1 724 323 A1	11/2006
EP	1 808 433 A1	7/2007
EP	1 962 354 A1	8/2008
EP	2 256 176 A1	1/2010
EP	2 166 585 A1	3/2010
EP	2 166 586 A1	3/2010
EP	2 182 040 A2	5/2010
EP	2 380 888 A1	10/2011
EP	2 461 390 A1	6/2012
JP	2000 068059	3/2000
JP	2000 169448	6/2000
JP	2001 192653	7/2001
JP	2001 247858	9/2001
JP	2003-45662 A	2/2003


* cited by examiner

Primary Examiner — Gregory Clark


(74) Attorney, Agent, or Firm — Oblon, McClelland, Maier & Neustadt, L.L.P.

(57) ABSTRACT


A fluorene-containing aromatic compound represented by a formula (1) below.



In the formula (1): Nr_1 represents a substituted or unsubstituted monocyclic nitrogen-containing aromatic ring having 2 to 5 ring carbon atoms, or a bicyclic nitrogen-containing aromatic ring having 2 to 9 ring carbon atoms; Ar represents an aromatic ring and the like; Fl_1 and Fl_2 represent a fluorenyl group; and Cz_1 and Cz_2 represent a carbazolyl group. A compound represented by a formula (2) below is omitted from the fluorene-containing aromatic compound represented by the formula (1).



28 Claims, 1 Drawing Sheet



FLUORENE-CONTAINING AROMATIC COMPOUND, MATERIAL FOR ORGANIC ELECTROLUMINESCENT ELEMENT, AND ORGANIC ELECTROLUMINESCENT ELEMENT USING SAME

TECHNICAL FIELD

The present invention relates to a fluorene-containing aromatic compound, a material for an organic electroluminescence device, and an organic electroluminescence device using the material.

BACKGROUND ART

An organic electroluminescence device (hereinafter, electroluminescence is occasionally abbreviated as EL) is a self-emitting device based on the principle that, when an electrical field is applied, a fluorescent material emits light using energy generated by a recombination of holes injected from an anode with electrons injected from a cathode. Studies on an organic EL device formed of an organic material have been vigorously carried out since a layered organic EL device driven at low voltage was reported (for instance, Patent Literatures 1 to 8). In the layered device, tris(8-quinolinolato)aluminum is used as an emitting layer and a triphenylamine derivative is used as a hole transporting layer. Advantages of such a layered structure are to improve efficiency of injecting holes into the emitting layer, to improve efficiency of generating excitons by recombination due to blockage of electrons injected from the cathode, to trap the excitons generated in the emitting layer, and the like. As a device structure of such an organic EL device, a two-layered structure, a three-layered structure or the like has been well known. The two-layered structure includes a hole transporting (injecting) layer and an electron transporting/emitting layer. The three-layered structure includes a hole transporting (injecting) layer, an emitting layer and an electron transporting (injecting) layer. In such a layered device, a device structure and a preparation method have been contrived in order to improve efficiency of recombining the injected holes and electrons.

Luminescent materials of an organic EL device such as a chelate complex (e.g. a tris(8-quinolinol)aluminum complex), a coumarin complex, a tetraphenyl butadiene derivative, a distyrylarylene derivative and an oxadiazole derivative have been known. These materials, which have been reported to emit light of blue to red in visible region, are expected to be applied to a color-display device.

Moreover, in addition to a fluorescent material, application of a phosphorescent material has been recently proposed for the emitting layer of the organic EL device. Thus, in the emitting layer of the organic EL device, a singlet state and a triplet state of excited states of an organic phosphorescent material are used to achieve a high luminous efficiency. When electrons and holes are recombined in the organic EL device, it is presumed that a singlet exciton and a triplet exciton are produced at a rate of 1:3 due to difference in spin multiplicity. Accordingly, luminous efficiency of the device using a phosphorescent material can reach three to four times as much as that of the device only using a fluorescent material.

In forming the emitting layer, a doping method, according to which the above luminescent material (dopant) is doped to a host material, has been known.

The emitting layer formed by the doping method can efficiently generate excitons from electric charges injected into

the host material. With the exciton energy generated by the excitons being transferred to the dopant, the dopant can emit light with high efficiency.

Recently, in order to upgrade an organic EL device, a further study on the doping method has been made to seek favorable host materials.

Such a host material is disclosed in, for instance, Patent Literatures 1 to 6. Patent Literature 1 discloses a compound containing a carbazole skeleton and a benzimidazole ring in the same molecule, and data of the compound as a blue fluorescent material host. Patent Literature 2 discloses a compound containing a carbazole skeleton and a 1,2,4-triazole ring in the same molecule, and data of the compound as a blue to blue-green fluorescent material host. Patent Literature 3 discloses a compound containing a carbazole skeleton and an imidazopyridine ring in the same molecule, and data of the compound as a blue fluorescent material host. Patent Literature 4 discloses a compound containing a carbazole skeleton, a fluorene skeleton and an imidazopyridine ring (a nitrogen-containing aromatic ring) in the same molecule, and data of the compound as a blue fluorescent material host. Patent Literature 5 discloses a compound containing a carbazole skeleton and a nitrogen-containing aromatic ring in the same molecule, and data of the compound as a host material used together with a blue to blue-green phosphorescent material. Patent Literature 6 discloses a compound containing a carbazole skeleton, a fluorene skeleton and a phenanthroline ring (a nitrogen-containing aromatic ring) in the same molecule, and data of the compound as a green phosphorescent material host.

Patent Literatures 7 and 8 disclose compounds having the same skeletons as those of the compounds Patent Literatures 1 to 6. Patent Literature 7 discloses a compound containing a carbazole skeleton and a pyridine ring in the same molecule, and data of the compound serving as a hole transporting material. Patent Literature 8 discloses a compound containing a fluorene skeleton and a pyridine ring (a nitrogen-containing aromatic ring) in the same molecule, and application of the compound to the emitting layer.

CITATION LIST

Patent Literatures

- Patent Literature 1 JP-A-2001-247858
- Patent Literature 2 JP-A-2000-68059
- Patent Literature 3 JP-A-2001-192653
- Patent Literature 4 US2004-157084
- Patent Literature 5 WO2003/080760
- Patent Literature 6 WO2004/026870
- Patent Literature 7 JP-A-2000-169448
- Patent Literature 8 JP-A-2007-261969

SUMMARY OF THE INVENTION

Problems to be Solved by the Invention

Although Patent Literatures 1 to 4 disclose data on when the compounds therein serve as a fluorescent material host, Patent Literatures 1 to 4 fail to disclose whether or not the compounds serve as a green phosphorescent material host. In Patent Literature 5 and 6, in which the compounds serving as a phosphorescent material host are disclosed, organic EL devices using the compounds do not exhibit a sufficient luminous efficiency and driving voltage for the organic EL devices

is not satisfactory. Patent Literatures 7 and 8 do not disclose whether or not the compounds therein serve as a phosphorescent material host.

Typically, a phosphorescent organic EL device emits light using excited triplet energy. As compared with a typical fluorescent organic EL device, a difference in electron affinity between the emitting layer and the electron transporting layer and a difference in ionization potential between the hole transporting layer and the emitting layer become large, so that carrier injection is blocked to often require high voltage.


An object of the invention is to provide a long-life organic EL device that exhibits a high luminous efficiency and is capable of being driven at low voltage required for power consumption saving and to provide a fluorene-containing aromatic compound usable for an organic-EL-device material providing such an organic EL device.

Means for Solving the Problems

After conducting concentrated studies in order to achieve such an object, the inventors have found that a difference in electron affinity between the electron transporting layer and the emitting layer can be reduced by using a material in which a carbazole skeleton and a nitrogen-containing hetero aromatic ring are combined, and that introduction of a fluorene skeleton in the same molecule improves transporting performance of carrier (particularly, electrons) and significantly lowers voltage applied to a phosphorescent organic EL device. In other words, an aromatic compound having a carbazole skeleton represented by a formula (1) below, a nitrogen-containing hetero aromatic ring and a fluorene skeleton in the same molecule can be provided. Also, an organic EL device that can be driven at low voltage required for power consumption saving can be provided by using the aromatic compound as an organic-EL-device material.

Specifically, a fluorene-containing aromatic compound represented by the formula (1) according to an aspect of the invention includes a carbazole skeleton, a nitrogen-containing hetero aromatic ring and a fluorene skeleton in the same molecule.

[Chemical Formula 1]




In the formula: Nr_1 represents a substituted or unsubstituted monocyclic nitrogen-containing aromatic ring having 2 to 5 carbon atoms for forming the aromatic ring (hereinafter referred to as ring carbon atoms), or a bicyclic nitrogen-containing aromatic ring having 2 to 9 ring carbon atoms; Ar represents a single bond, a substituted or unsubstituted aromatic ring having 5 to 40 ring carbon atoms; Fl_1 and Fl_2 each independently represent a substituted or unsubstituted fluorenyl group; p is an integer of 0 to 3 representing the number of a substituent(s) of $-(\text{L}_4-\text{Fl}_1)$ directly bonding to Nr_1 ; when p is 2 or more, L_4 may be the same or different and Fl_1 may be the same or different; q is an integer of 0 to 3 representing the number of a substituent of $-(\text{L}_7-\text{Fl}_2)$ directly bonding to Ar ; when q is 2 or more, L_7 may be the same or different and Fl_2

may be the same or different; $p+q=1$ or more; Cz_1 and Cz_2 each independently represent a substituted or unsubstituted carbazolyl group; m is an integer of 0 to 3 representing the number of a substituent of $-(L_2-Cz_1)$ directly bonding to Nr_1 ;

5 when m is 2 or more, L_2 may be the same or different and Cz_1 may be the same or different; n is an integer of 0 to 3 representing the number of a substituent of $-(L_5-Cz_2)$ directly bonding to Ar ; when n is 2 or more, L_5 may be the same or different and Cz_2 may be the same or different; $m+n=1$ or more; Y^1 and Y^2 each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, a iodine atom, a cyano group, a substituted or unsubstituted and linear, branched or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; x is an integer of 1 to 3 representing the number of a substituent of $-(L_3-Y_1)$ directly bonding to Nr_1 ; when x is 2 or more, L_3 may be the same or different and Y_1 may be the same or different; y is an integer of 1 to 3 representing the number of a substituent of $-(L_6-Y_2)$ directly bonding to Ar ; when y is 2 or more, L_6 may be the same or different and Y_2 may be the same or different; $m+p+x$ is less than or equal to a numeral represented by (the number of the possible substituent(s) for selected Nr_1 minus 1);

30 $n+q+y$ is less than or equal to a numeral represented by (the number of the possible substituent(s) for selected Ar minus 1); and L_1 to L_7 each independently represent a single bond, a substituted or unsubstituted aromatic ring having 6 to 30 ring carbon atoms, or a substituted or unsubstituted aromatic heterocyclic ring having 2 to 30 ring carbon atoms; and k represents an integer of 1 to 3, in which a compound represented by a formula (2) below is omitted from the fluorene-containing aromatic compound represented by the formula (1).

[Chemical Formula 2]




In the fluorene-containing aromatic compound according to the above aspect of the invention, in the formula (1), Nr_1 is preferably a nitrogen-containing aromatic ring selected from a substituted or unsubstituted pyrrole ring, pyrazole ring, imidazole ring, triazole ring, pyridine ring, pyrimidine ring, pyridazine ring, pyrazine ring, triazine ring, indole ring, inda-

sole ring, benzimidazole ring, quinoline ring, isoquinoline ring, cinnoline ring, quinoxaline ring and imidazopyridine ring.


Moreover, according to the above aspect of the invention, it is preferable that each of Cz_1 and Cz_2 in the formula (1) is independently represented by the following formula (3) or (4).

[Chemical Formula 3]



In the formula (3), Ra and Rb each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, a iodine atom, a cyano group, a substituted or unsubstituted and linear, branched or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; and f and g each independently represent an integer of 1 to 4.

[Chemical Formula 4]



In the formula (4), Ra', Rb' and Rc' each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, a iodine atom, a cyano group, a substituted or unsubstituted and linear, branched or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30

ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; f is an integer of 1 to 4; g¹ is an integer of 1 to 3; and h¹ is an integer of 1 to 5.

According to the above aspect of the invention, in the formula (1), it is preferable that k is 1 and $m+n+p+q$ is less than or equal to 6.

Moreover, it is preferable that each of Y_1 and Y_2 is independently represented by a hydrogen atom or a phenyl group.


According to the above aspect of the invention, it is preferable that k is 1; L_1 , L_2 , L_3 , L_5 and L_6 each independently represent a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, a substituted or unsubstituted terphenylene group, or a substituted or unsubstituted fluorenylene group; and L_4 and L_7 each independently represent a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, or a substituted or unsubstituted terphenylene group. When a hydrogen atom is bonded to the above groups, the hydrogen atom may be a deuterium atom.

It is preferable that $m+n=1$ or 2 and $p+q=1$ for 2.

Ar is preferably a monocyclic aromatic ring selected from a substituted or unsubstituted benzene ring, pyrazole ring, imidazole ring, triazole ring, pyridine ring, pyrimidine ring, pyridazine ring, pyrazine ring, triazine ring or thiophene ring, particularly preferably a benzene ring.

According to the above aspect of the invention, it is preferable that each of Fl_1 and Fl_2 in the formula (1) is independently represented by a formula (5) below.

[Chemical Formula 5]




In the formula (5): Y_3 and Y_4 each independently represent: a hydrogen atom; a deuterium atom; a linear, branched or cyclic alkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms; a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms; a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; and Y_5 , Y_6 , Y_7 , Y_8 , Y_9 , Y_{10} and Y_{11} each independently represent: a hydrogen atom; a deuterium atom; a fluorine atom; a chlorine atom; a bromine atom; an iodine atom; a cyano group; a linear, branched or cyclic alkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic alkoxy group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkoxy group having 1 to 10 carbon atoms; a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms; a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms; a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms.

According to the above aspect of the invention, each of Y_3 and Y_4 is independently a linear alkyl group having 1 to 10 carbon atoms or a phenyl group in the formula (5).


It is more preferable that both of Y_3 and Y_4 are a methyl group.

According to the above aspect of the invention, it is preferable that each of Cz_1 and Cz_2 in the formula (1) is independently represented by a formula (3) or a formula (4).

[Chemical Formula 6]



[Chemical Formula 7]



According to the aspect of the invention, it is more preferable that Nr_1 is a pyrimidine ring in the formula (1).

It is preferable that the fluorene-containing aromatic compound is used as an organic-electroluminescence-device material.

An organic electroluminescence device according to another aspect of the invention includes: a cathode; an anode; and an organic thin-film layer provided between the cathode and the anode, the organic thin-film layer formed out of one or more layers including an emitting layer, in which at least one layer of the organic thin-film layer contains the fluorene-containing aromatic compound.

In the organic electroluminescence device according to the above aspect of the invention, the emitting layer preferably contains the as a host material.

It is preferable that the organic electroluminescence device further contains a phosphorescent material.

It is more preferable that the emitting layer includes a host material and a phosphorescent material, in which the phosphorescent material is an ortho metalation of a complex of a metal atom selected from iridium (Ir), osmium (Os) and platinum (Pt).

In the organic electroluminescence device according to the above aspect of the invention, it is preferable that the organic thin-film layer includes an electron injecting layer provided between the cathode and the emitting layer, the electron injecting layer containing a nitrogen-containing cyclic derivative.

Moreover, it is preferable that the organic thin-film layer includes an electron transporting layer provided between the cathode and the emitting layer, the electron transporting layer containing the fluorene-containing aromatic compound.

In the organic EL device according to the above aspect of the invention, a reduction-causing dopant is preferably added in an interfacial region between the cathode and the organic thin-film layer.

Effects of the Invention

According to the aspect(s) of the invention, a fluorene-containing compound represented by the formula (1) is used as an organic-EL-device material to provide an organic EL device with a high luminous efficiency, a long lifetime and low voltage drivability. Moreover, the organic-EL-device material is effective as an organic-electron-device material for an organic solar cell, an organic semiconductor laser, a sensor using an organic substance and an organic TFT.

BRIEF DESCRIPTION OF DRAWING

FIG. 1 schematically shows an exemplary structure of an organic electroluminescence device according to an exemplary embodiment of the invention.

DESCRIPTION OF EMBODIMENT

20 Description will be made below on an exemplary embodiment(s) of the invention. A fluorene-containing aromatic compound according to this exemplary embodiment of the invention is suitably used especially as an organic-EL-device material. The fluorene-containing aromatic compound is 25 used in an organic EL device according to this exemplary embodiment of the invention.

Structure of Organic EL Device

Firstly, structure(s) of an organic EL device will be described below.

30 The following are representative structure examples of an organic EL device:

- (1) anode/emitting layer/cathode;
- (2) anode/hole injecting layer/emitting layer/cathode;
- (3) anode/emitting layer/electron injecting•transporting 35 layer/cathode;
- (4) anode/hole injecting layer/emitting layer/electron injecting•transporting layer/cathode;
- (5) anode/organic semiconductor layer/emitting layer/cathode;

40 (6) anode/organic semiconductor layer/electron blocking layer/emitting layer/cathode;

- (7) anode/organic semiconductor layer/emitting layer/adhesion improving layer/cathode;
- (8) anode/hole injecting•transporting layer/emitting layer/ 45 electron injecting•transporting layer/cathode;

(9) anode/insulating layer/emitting layer/insulating layer/cathode;

- (10) anode/inorganic semiconductor layer/insulating layer/ 50 emitting layer/insulating layer/cathode;

(11) anode/organic semiconductor layer/insulating layer/ 55 emitting layer/insulating layer/cathode;

- (12) anode/insulating layer/hole injecting•transporting layer/ 60 emitting layer/insulating layer/cathode; and

(13) anode/insulating layer/hole injecting•transporting layer/ 65 emitting layer/electron injecting•transporting layer/cathode.

The structure (8) is suitably used among the above, but the structure of the invention is not limited to the above structures.

60 FIG. 1 schematically shows an exemplary structure of an organic EL device according to an exemplary embodiment of the invention.

The organic EL device 1 includes a transparent substrate 2, an anode 3, a cathode 4 and an organic thin-film layer 10 positioned between the anode 3 and the cathode 4.

65 The organic thin-film layer 10 includes a phosphorescent-emitting layer 5 containing a phosphorescent host as a host

material and a phosphorescent dopant as a phosphorescent material. A layer such as a hole injecting/transporting layer 6 may be provided between the phosphorescent-emitting layer 5 and the anode 3 while a layer such as an electron injecting/transporting layer 7 may be provided between the phosphorescent-emitting layer 5 and the cathode 4.

In addition, an electron blocking layer may be provided to the phosphorescent-emitting layer 5 adjacent to the anode 3 while a hole blocking layer may be provided to the phosphorescent-emitting layer 5 adjacent to the cathode 4.

With this structure, electrons and holes can be trapped in the phosphorescent-emitting layer 5, thereby enhancing probability of exciton generation in the phosphorescent-emitting layer 5.

It should be noted that a “fluorescent host” and a “phosphorescent host” herein respectively mean a fluorescent host combined with a fluorescent dopant and a phosphorescent host combined with a phosphorescent dopant, and that a distinction between the fluorescent host and phosphorescent host is not unambiguously derived only from a molecular structure of the host in a limited manner.

In other words, the fluorescent host herein means a material for forming a fluorescent-emitting layer containing a fluorescent dopant, and does not mean a host that is only usable as a host of a fluorescent material.

Likewise, the phosphorescent host herein means a material for forming a phosphorescent-emitting layer containing a phosphorescent dopant, and does not mean a host that is only usable as a host of a phosphorescent material.

It should be noted that the “hole injecting/transporting layer” herein means “at least either one of a hole injecting layer and a hole transporting layer” while the “electron injecting/transporting layer” herein means “at least either one of an electron injecting layer and an electron transporting layer.”

Transparent Substrate

The organic EL device according to this exemplary embodiment of the invention is formed on a light-transmissive substrate. The light-transmissive plate, which supports the organic EL device, is preferably a smooth substrate that transmits 50% or more of light in a visible region of 400 nm to 700 nm.

The light-transmissive plate is exemplarily a glass plate, a polymer plate or the like.

For the glass plate, materials such as soda-lime glass, barium/strontium-containing glass, lead glass, aluminosilicate glass, borosilicate glass, barium borosilicate glass and quartz can be used.

For the polymer plate, materials such as polycarbonate, acryl, polyethylene terephthalate, polyether sulfide and polysulfone can be used.

Anode and Cathode

The anode of the organic EL device is used for injecting holes into the hole injecting layer, the hole transporting layer or the emitting layer. It is effective that the anode has a work function of 4.5 eV or more.

Exemplary materials for the anode are alloys of indium-tin oxide (ITO), tin oxide (NESA), indium zinc oxide, gold, silver, platinum and copper.

The anode may be made by forming a thin film from the above electrode materials through methods such as vapor deposition and sputtering.

When light from the emitting layer is to be emitted through the anode as in this embodiment, the anode preferably transmits more than 10% of the light in the visible region. Sheet resistance of the anode is preferably several hundreds Ω/square or lower. Although depending on the material of the

anode, the thickness of the anode is typically in a range of 10 nm to 1 μm , and preferably in a range of 10 nm to 200 nm.

The cathode is preferably formed of a material with smaller work function in order to inject electrons into the electron injecting layer, the electron transporting layer and the emitting layer.

Although a material for the cathode is subject to no specific limitation, examples of the material are indium, aluminum, magnesium, alloy of magnesium and indium, alloy of magnesium and aluminum, alloy of aluminum and lithium, alloy of aluminum, scandium and lithium, and alloy of magnesium and silver.

Like the anode, the cathode may be made by forming a thin film from the above materials through a method such as vapor deposition or sputtering. In addition, the light may be emitted through the cathode.

Emitting Layer

The emitting layer of the organic EL device has functions as follows.

Specifically:

- (1) injecting function: a function for accepting, when an electrical field is applied, the holes injected by the anode or the hole injecting layer, or the electrons injected by the cathode or the electron injecting layer;
- (2) transporting function: a function for transporting injected electric charges (the electrons and the holes) by the force of the electrical field; and
- (3) emitting function: a function for providing a condition for recombination of the electrons and the holes to emit light.

Injectability of the holes may differ from that of the electrons and transporting capabilities of the hole and the electrons (represented by mobilities of the holes and the electrons) may differ from each other.

As a method of forming the emitting layer, known methods such as vapor deposition, spin coating and an LB method may be employed.

The emitting layer is preferably a molecular deposit film.

The molecular deposit film means a thin film formed by depositing a material compound in gas phase or a film formed by solidifying a material compound in a solution state or in liquid phase. The molecular deposit film is typically distinguished from a thin film formed by the LB method (molecular accumulation film) by differences in aggregation structures, higher order structures and functional differences arising therefrom.

As disclosed in JP-A-57-51781, the emitting layer can be formed from a thin film formed by spin coating or the like, the thin film being formed from a solution prepared by dissolving a binder (e.g. a resin) and a material compound in a solvent.


The thickness of the emitting layer is preferably in a range of 5 nm to 50 nm, more preferably in a range of 7 nm to 50 nm and most preferably in a range of 10 nm to 50 nm. The thickness less than 5 nm may cause difficulty in forming the emitting layer and in controlling chromaticity, while the thickness more than 50 nm may increase driving voltage.

The organic EL device according to this exemplary embodiment includes: a cathode; an anode; and a single or a plurality of organic thin-film layers provided between the cathode and the anode, in which the organic thin-film layer(s) includes at least one emitting layer, and the organic thin-film layer(s) includes at least one phosphorescent material and at least one organic-EL-device material according to another aspect of the invention (later described). In addition, at least one of the emitting layer(s) preferably contains the organic-EL-device material of the exemplary embodiment and at least one phosphorescent material.

Organic-EL-Device Material

The organic-EL-device material according to this exemplary embodiment is represented by a formula (1) below.

[Chemical Formula 8]




In the formula (1): Nr₁ represents a substituted or unsubstituted monocyclic nitrogen-containing aromatic ring having 2 to 5 ring carbon atoms, or a bicyclic nitrogen-containing aromatic ring having 2 to 9 ring carbon atoms; Ar represents a single bond, a substituted or unsubstituted aromatic ring having 5 to 40 ring carbon atoms; Fl₁ and Fl₂ each independently represent a substituted or unsubstituted fluorenyl group; p is an integer of 0 to 3 representing the number of a substituent of -(L₄-Fl₁) directly bonding to Nr₁; when p is 2 or more, L₄ may be the same or different and Fl₁ may be the same or different; q is an integer of 0 to 3 representing the number of a substituent of -(L₇-Fl₂) directly bonding to Ar; when q is 2 or more, L₇ may be the same or different and Fl₂ may be the same or different; p+q=1 or more; Cz₁ and Cz₂ each independently represent a substituted or unsubstituted carbazolyl group; m is an integer of 0 to 3 representing the number of a substituent of -(L₂-Cz₁) directly bonding to Nr₁; when m is 2 or more, L₂ may be the same or different and Cz₁ may be the same or different; n is an integer of 0 to 3 representing the number of a substituent of -(L₅-Cz₂) directly bonding to Ar; when n is 2 or more, L₅ may be the same or different and Cz₂ may be the same or different; m+n=1 or more; Y¹ and Y² each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, a iodine atom, a cyano group, a substituted or unsubstituted and linear, branched or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; x is an integer of 1 to 3 representing the number of a substituent of -(L₃-Y₁) directly bonding to Nr₁; when x is 2 or more, L₃ may be the same or different and Y₁ may be the same or different; y is an integer of 1 to 3 representing the number of a substituent of -(L₆-Y₂) directly bonding to Ar; when y is 2 or more, L₆ may be the same or different and Y₂ may be the same or different; m+p+x is less than or equal to a numeral represented by (the number of the possible substituent(s) for selected Nr₁ minus 1); n+q+y is less than or equal to a numeral represented by (the number of the possible substituent(s) for selected Ar minus 1); and L₁ to L₇ each independently represent a single bond, a substituted or unsubstituted aromatic ring having 6 to 30 ring carbon atoms, or a substituted or

unsubstituted aromatic heterocyclic ring having 2 to 30 ring carbon atoms; and k represents an integer of 1 to 3, in which a compound represented by the following formula (2) is omitted from the organic-EL-device material represented by the formula (1).

5

[Chemical Formula 9]



In the formula (1), Nr₁ is preferably a nitrogen-containing aromatic ring selected from a substituted or unsubstituted pyrrole ring, pyrazole ring, imidazole ring, triazole ring, pyridine ring, pyrimidine ring, pyridazine ring, pyrazine ring, triazine ring, indole ring, indazole ring, benzimidazole ring, quinoline ring, isoquinoline ring, cinnoline ring, quinoxaline ring and imidazopyridine ring. When a hydrogen atom is bonded to the nitrogen-containing aromatic ring, the hydrogen atom may be a deuterium atom.

25 Nr₁ is more preferably a substituted or unsubstituted pyridine ring, pyrimidine ring, or triazine ring, particularly preferably a substituted or unsubstituted pyrimidine ring. In the formula (1), when Nr₁ is an imidazopyridine ring, a case where both of Y₃ and Y₄ in Fl₂ are a phenyl group may be omitted.


30 Moreover, in the formula (1), when Nr₁ is an imidazopyridine ring, a case where L₇ is a single bond may be omitted.

35 In the formula (1), Ar is preferably a monocyclic aromatic ring such as a substituted or unsubstituted benzene ring having 2 to 6 ring carbon atoms, pyrazole ring, imidazole ring, triazole ring, pyridine ring, pyrimidine ring, pyridazine ring, pyrazine ring, triazine ring or thiophene ring, particularly preferably a benzene ring. When a hydrogen atom is bonded to the monocyclic aromatic ring, the hydrogen atom may be a deuterium atom.

40 In addition, preferably, each of Cz₁ and Cz₂ in the formula (1) is independently represented by the following formula (3) or (4).

45

[Chemical Formula 10]



In the formula, Ra and Rb each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, a iodine atom, a cyano group, a substituted or unsubstituted and linear, branched or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms.

55


60

65

13

tuted and linear, branched or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; and f and g each independently represent an integer of 1 to 4.


[Chemical Formula 11]



In the formula, Ra', Rb' and Rc' each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, a iodine atom, a cyano group, a substituted or unsubstituted and linear, branched or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted and linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; f' is an integer of 1 to 4; g' is an integer of 1 to 3; and h' is an inter of 1 to 5.

In addition, preferably, each of Cz₁ and Cz₂ is independently represented by the following formula (3a) or (4a).


[Chemical Formula 12]



[Chemical Formula 13]

14
-continued

(4a)



In the formula (1), it is preferable that k is 1 and m+n+p+q is less than or equal to 6. More preferably, m+n=1 or 2 and p+q=1 or 2. m represents the number of a substituent(s) of -(L₂-Cz₁) directly bonding to Nr₁. Likewise, n, p and q represent the number of a substituent(s).


In the formula (1), preferably, Y₁ and Y₂ each independently represent a hydrogen atom, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms, particularly preferably a hydrogen atom or a phenyl group.

In the formula (1), it is preferable that L₁, L₂, L₃, L₅ and L₆ each independently represent a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, a substituted or unsubstituted terphenylene group, or a substituted or unsubstituted fluorenylene group; and L₄ and L₇ each independently represent a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, or a substituted or unsubstituted terphenylene group. When a hydrogen atom is bonded to the above groups, the hydrogen atom may be a deuterium atom.

In the formula (1), preferably, each of Fl₁ and Fl₂ is independently represented by the following formula (5).

[Chemical Formula 14]

(5)



In the formula (5): Y₃ and Y₄ each independently represent: a hydrogen atom; a deuterium atom; a linear, branched or cyclic alkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms; a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms; a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; and Y₅, Y₆, Y₇, Y₈, Y₉, Y₁₀ and Y₁₁ each independently represent: a hydrogen atom; a deuterium atom; a fluorine atom; a chlorine atom; a bromine atom; an iodine atom; a cyano group; a linear, branched or cyclic alkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic alkoxy group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkoxy group having 1 to 10 carbon atoms; a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms; a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms; a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms.

In the formula (5): Y₃ and Y₄ each independently represent: a hydrogen atom; a deuterium atom; a linear, branched or cyclic alkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms; a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms; a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; and Y₅, Y₆, Y₇, Y₈, Y₉, Y₁₀ and Y₁₁ each independently represent: a hydrogen atom; a deuterium atom; a fluorine atom; a chlorine atom; a bromine atom; an iodine atom; a cyano group; a linear, branched or cyclic alkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic alkoxy group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkyl group having 1 to 10 carbon atoms; a linear, branched or cyclic haloalkoxy group having 1 to 10 carbon atoms; a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms; a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms; a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms.

15

carbon atoms; a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms; a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms; a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms.

Further, in the formula (5), Y_3 and Y_4 each independently represent a linear, branched or cyclic alkyl group having 1 to 10 carbon atoms, a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms or a phenyl group. Y_5 , Y_6 , Y_7 , Y_8 , Y_9 , Y_{10} and Y_{11} are preferably a hydrogen atom. More preferably, Y_3 and Y_4 each are independently a linear alkyl group having 1 to 10 carbon atoms or a phenyl group. Among the above, particularly preferably, Y_3 and Y_4 each are represented by a methyl group.

When Nr_1 , Ar , Y_1 , Y_2 , Fl_1 , Fl_2 , Cz_1 , Cz_2 , and L_1 to L_7 in the formulae (1) and (3) to (5) each have one substituent or a plurality of substituents, the substituent(s) is preferably a linear, branched or cyclic alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms, a cyano group, a halogen atom, or an aryl group having 6 to 22 ring carbon atoms.

Examples of the linear, branched or cyclic alkyl group having 1 to 20 carbon atoms are a methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, neo-pentyl group, 1-methylpentyl group, 2-methylpentyl group, 1-pentylhexyl group, 1-butylpentyl group, 1-heptyloctyl group, 3-methylpentyl group, cyclopentyl group, cyclohexyl group, cyclooctyl group and 3,5-dimethylcyclohexyl group.

Examples of the linear, branched or cyclic alkylsilyl group having 1 to 10 carbon atoms are a trimethylsilyl group, triethylsilyl group, tributylsilyl group, dimethylethylsilyl group, dimethylisopropylsilyl group, dimethylpropylsilyl group, dimethylbutylsilyl group, dimethyl-tertiary-butylsilyl group and diethylisopropylsilyl group.

Examples of the arylsilyl group having 6 to 30 carbon atoms are a phenyldimethylsilyl group, diphenylmethylsilyl group, diphenyl-tertiary-butylsilyl group and triphenylsilyl group.

Examples of the halogen atom are a fluorine atom, a chlorine atom, a bromine atom and an iodine atom.

Examples of the aryl group having 6 to 30 ring carbon atoms are a phenyl group, biphenyl group, terphenyl group, naphthyl group, fluoranthenyl group, triphenylenyl group and phenanthrenyl group.

Examples of the heteroaryl group having 2 to 10 ring carbon atoms are a pyrrolyl group, pyrazinyl group, pyridinyl group, indolyl group, isoindolyl group, furyl group, benzofuranyl group, isobenzofuranyl group, dibenzofuranyl group, dibenzothiophenyl group, quinolyl group, isoquinolyl group, quinoxalinyl group, carbazolyl group, phenanthridinyl group, acridinyl group, phenanthrolinyl group and thiényl group.


16

Examples of the aromatic ring having 6 to 30 ring carbon atoms are a benzene ring, naphthalene ring, phenanthrene ring, biphenyl ring, terphenyl ring and quarter-phenyl ring.

Examples of the aromatic heterocyclic group having 2 to 30 ring carbon atoms are a pyridine ring, pyrazine ring, pyrimidine ring, pyridazine ring, triazine ring, indole ring, quinoline ring, acridine ring, pyrrolidine ring, dioxane ring, piperidine ring, morpholine ring, piperazine ring, carbazole ring, furan ring, thiophene ring, oxazole ring, oxadiazole ring, benzoxazole ring, thiazole ring, thiadiazole ring, benzothiazole ring, triazole ring, imidazole ring, benzimidazole ring, pyrane ring and dibenzofuran ring.


Examples of the fluorene-containing aromatic compound according to this exemplary embodiment represented by the formula (1) are as follows.

[Chemical Formula 15]



17

-continued



5





10

15

20


18

-continued




19


-continued




5




30




55




5




10



35




60



65


21

-continued

**22**


-continued

[Chemical Formula 16]




23

-continued


**24**

-continued



25


-continued



5

10


15



20


25

30




35

40



45

50




55

60

65

26


-continued



5


10

15




20

30




35

40



45

50




55

60

65

27

-continued




5

10

15

20

25



30




35

40

45

28


-continued






[Chemical Formula 17]

29

-continued


**30**

-continued



31

-continued




5

10

15

20

25




30


35

40

45

**32**

-continued




5

50

55


60

65



33


-continued



34


-continued

[Chemical Formula 18]




35


-continued



5



25



30

35

40

45

50


55

60

65

36

-continued



10

20

25

30

35

40

50


55

60




65

37

-continued

**38**

-continued



5

10

15

20

25

30

35

40

45

50


55

60

65

39

-continued




5

10

15

20




25

30

35

40

45



50



55

60


65

40

-continued




[Chemical Formula 19]






41

-continued


**42**

-continued




43


-continued




5




25




50





60



65




**44**

-continued





45


-continued

**46**

-continued




[Chemical Formula 20]




47

-continued




48

-continued



49

-continued




5

10

15

20



25


30

35


40

45

50

**50**

-continued



5

10

15

20

25

30

35

40




45

50

55


60

65




51


-continued




5



10




15




20


[Chemical Formula 21]

**52**

-continued



25



30

35

40

45

50




55

60


65

53

-continued


**54**

-continued




55

-continued


**56**

-continued



57


-continued

**58**

-continued

[Chemical Formula 22]

5



25

30

35

40


45

50

55


60

65



59

-continued




5

10


15

25




40

45

**60**

-continued



30



35

40

50


60

65








61

-continued


**62**

-continued



63


-continued



5


10
15

25

30
35

40

45


50
55

60

65

64

-continued



5

10
15

25

30
35

40


45

50
55

60


65

[Chemical Formula 23]




65

-continued




**66**

-continued






67

-continued


**68**

-continued






69

-continued

**70**




-continued



71




-continued

[Chemical Formula 24]




72

-continued



73

-continued



5

10

15

20

30

40








50

60

65


74

-continued



75

-continued



5

10

15


20

25


30

76

-continued



35



40


45

50

55

60




65



77

-continued


[Chemical Formula 25]




78

-continued

5



10



15

20

25

30

35

40


45

50

55




60

65











79

-continued





80

-continued



50




65

81**82**

-continued


-continued



83

-continued

[Chemical Formula 26]



5

10

15

20

25

30

35

40

45

50



55

60

65

84

-continued





30

35


40

45








85

-continued


**86**

-continued



87

-continued



88

In the organic EL device according to this exemplary embodiment, the emitting layer preferably contains the fluorene-containing aromatic compound as a host material. In addition, the emitting layer is preferably formed of a host material and a phosphorescent material while the host material is the fluorene-containing aromatic compound.

The fluorene-containing aromatic compound may be a host material used with a phosphorescent material, or may be an electron transporting material used with a phosphorescent material. The fluorene-containing aromatic compound preferably has an excited triplet energy of 2.2 eV to 3.2 eV, more preferably 2.4 eV to 3.2 eV.

15 The organic EL device according to this exemplary embodiment may preferably include an electron transporting layer that contains the organic-EL-device material according to this exemplary embodiment.

The organic EL device according to this exemplary embodiment may preferably include at least one of the electron transporting layer and the hole blocking layer that contains the organic-EL-device material according to this exemplary embodiment.

25 The organic EL device according to this exemplary embodiment may preferably include the hole transporting layer (hole injecting layer) that contains the organic-EL-device material according to this exemplary embodiment.


Phosphorescent Material

30 According to this exemplary embodiment, the phosphorescent material preferably contains a metal complex, and the metal complex preferably has a metal atom selected from Ir, Pt, Os, Au, Cu, Re and Ru, and a ligand. Particularly, the ligand preferably has an ortho-metal bond.

35 The phosphorescent material is preferably a compound containing a metal selected from iridium (Ir), osmium (Os) and platinum (Pt) because such a compound, which exhibits high phosphorescence quantum yield, can further enhance 40 external quantum efficiency of the emitting device. The phosphorescent material is more preferably a metal complex such as an iridium complex, osmium complex or platinum complex, among which an iridium complex and platinum complex are more preferable and ortho metalation of an iridium 45 complex is the most preferable.







Examples of such a preferable metal complex are shown below.

50 [Chemical Formula 27]








89

-continued


**90**

-continued

60
65

91


-continued



[Chemical Formula 28]






92

-continued




93

-continued









[Chemical Formula 29]








94

-continued



Ir (ppy)₃

95

-continued








[Chemical Formula 30]




96

-continued

5
1015
2025
30
3540
45
5055
60
65

97



According to this exemplary embodiment, at least one of the phosphorescent material contained in the emitting layer preferably emits light with the maximum wavelength of 450 nm to 720 nm.

By doping the phosphorescent material (phosphorescent dopant) having such an emission wavelength to the specific host material used in this exemplary embodiment to form the emitting layer, the organic EL device can exhibit high efficiency.

Reduction-Causing Dopant

In the organic EL device according to this exemplary embodiment, a reductive dopant may be preferably contained in an interfacial region between the cathode and the organic thin-film layer.

With this structure, the organic EL device can emit light with enhanced luminance intensity and have a longer lifetime.

The reduction-causing dopant may be at least one compound selected from a group of an alkali metal, alkali metal complex, alkali metal compound, alkali earth metal, alkali earth metal complex, alkali earth metal complex compound, rare-earth metal, rare-earth metal complex, a rare-earth metal compound and the like.

Examples of the alkali metal are Na (work function: 2.36 eV), K (work function: 2.28 eV), Rb (work function: 2.16 eV), and Cs (work function: 1.95 eV), among which the alkali metal having a work function of 2.9 eV or less is particularly

98

preferable. Among the above, the reduction-causing dopant is preferably K, Rb or Cs, more preferably Rb or Cs, the most preferably Cs.

Examples of the alkali earth metal are Ca (work function: 9 eV), Sr (work function: 2.0 eV to 2.5 eV), and Ba (work function: 2.52 eV), among which the alkali earth metal having a work function of 2.0 eV or less is particularly preferable.

Examples of the rare-earth metal are Sc, Y, Ce, Tb, and Yb, among which the rare-earth metal having a work function of 2.9 eV or less is particularly preferable.

Since the above preferred metals have particularly high reducibility, addition of a relatively small amount of the metals to an electron injecting zone can enhance luminance intensity and lifetime of the organic EL device.

15 Examples of the alkali metal compound are an alkali oxide such as Li_2O , Cs_2O or K_2O , and an alkali halogen compound such as LiF , NaF , CsF or KF , among which LiF , Li_2O and NaF are preferable.

Examples of the alkali earth metal compound are BaO, SrO, CaO, and a mixture thereof such as $Ba_xSr_{1-x}O$ ($0 < x < 1$) or $Ba_xCa_{1-x}O$ ($0 < x < 1$), among which BaO, SrO and CaO are preferable.

Examples of the rare-earth metal compound are YbF_3 , ScF_3 , Sc_2O_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , TbF_3 and the like, among which YbF_3 , ScF_3 and TbF_3 are preferable.

The alkali metal complex, alkali earth metal complex and rare-earth metal complex are subject to no limitation as long as they contain at least one metal ion of an alkali metal ion, an alkali earth metal ion and a rare-earth metal ion. The ligand is preferably quinolinol, benzoquinolinol, acridinol, phenanthridinol, hydroxyphenyl oxazole, hydroxyphenyl thiazole, hydroxydiaryl oxadiazole, hydroxydiaryl thiadiazole, hydroxyphenyl pyridine, hydroxyphenyl benzoimidazole, hydroxybenzo triazole, hydroxy fluborane, bipyridyl, phenanthroline, phthalocyanine, porphyrin, cyclopentadiene, β -diketones, azomethines, or a derivative thereof, but the ligand is not limited thereto.

The reduction-causing dopant is added to preferably form a layer or an island pattern in the interfacial region. The layer 40 of the reduction-causing dopant or the island pattern of the reduction-causing dopant is preferably formed by depositing the reduction-causing dopant by resistance heating deposition while an emitting material for forming the interfacial region or an organic substance as an electron-injecting material are simultaneously deposited, so that the reduction-causing dopant is dispersed in the organic substance. Dispersion concentration at which the reduction-causing dopant is dispersed in the organic substance is a mole ratio (organic substance to reduction-causing dopant) of 100:1 to 1:100, preferably 45 5:1 to 1:5.

When the reduction-causing dopant forms the layer, the emitting material or the electron injecting material for forming the organic layer of the interfacial region is initially layered, and the reduction-causing dopant is subsequently deposited singularly thereon by resistance heating deposition to form a preferably 0.1 nm- to 15 nm-thick layer.

When the reduction-causing dopant forms the island pattern, the emitting material or the electron injecting material for forming the organic layer of the interfacial region is initially formed in an island shape, and the reduction-causing dopant is subsequently deposited singularly thereon by resistance heating deposition to form a preferably 0.05 nm- to 1 nm-thick island shape.

65 A ratio of the main component to the reduction-causing dopant in the organic EL device according to this exemplary embodiment is preferably a mole ratio (main component to reductive dopant) of 5:1 to 1:5, more preferably 2:1 to 1:2.

Electron Injecting Layer and Electron Transporting Layer

The electron injecting layer or the electron transporting layer, which aids injection of the electrons into the emitting layer, has a large electron mobility. The electron injecting layer is provided for adjusting energy level, by which, for instance, sudden changes in the energy level can be reduced.


The organic EL device according to this exemplary embodiment preferably includes the electron injecting layer between the emitting layer and the cathode, and the electron injecting layer preferably contains a nitrogen-containing cyclic derivative as a main component. The electron injecting layer may serve as an electron transporting layer.

It should be noted that "as a main component" means that the nitrogen-containing cyclic derivative is contained in the electron injecting layer at a content of 50 mass % or more.

A preferable example of an electron transporting material for forming the electron injecting layer is an aromatic heterocyclic compound having at least one heteroatom in a molecule. Particularly, a nitrogen-containing cyclic derivative is preferable. The nitrogen-containing cyclic derivative is preferably an aromatic ring having a nitrogen-containing six-membered or five-membered ring skeleton, or a fused aromatic cyclic compound having a nitrogen-containing six-membered or five-membered ring skeleton.

The nitrogen-containing cyclic derivative is preferably exemplified by a nitrogen-containing cyclic metal chelate complex represented by the following formula (A).

[Chemical Formula 31]



R² to R⁷ in the formula (A) each independently represent a hydrogen atom, halogen atom, oxy group, amino group, hydrocarbon group having 1 to 40 carbon atoms, alkoxy group, aryloxy group, alkoxy carbonyl group, or heterocyclic group. These groups may be substituted or unsubstituted.

Examples of the halogen atom include fluorine, chlorine, bromine, and iodine. In addition, examples of the substituted or unsubstituted amino group include an alkylamino group, an arylamino group, and an aralkylamino group.


The alkoxy carbonyl group is represented by —COOY'. Examples of Y' are the same as the examples of the alkyl group. The alkylamino group and the aralkylamino group are represented by —NQ¹Q². Examples for each of Q¹ and Q² are the same as the examples described in relation to the alkyl group and the aralkyl group, and preferred examples for each of Q¹ and Q² are also the same as those described in relation to the alkyl group and the aralkyl group. Either one of Q¹ and Q² may be a hydrogen atom.

The arylamino group is represented by —NAr¹Ar². Examples for each of Ar¹ and Ar² are the same as the examples described in relation to the non-fused aryl group and the fused aryl group. Either one of Ar¹ and Ar² may be a hydrogen atom.

M represents aluminum (Al), gallium (Ga) or indium (In), among which In is preferable.

L in the formula (A) represents a group represented by a formula (A') or (A'') below.

[Chemical Formula 32]



(A)

In the formula (A'), R⁸ to R¹² each independently represent a hydrogen atom or a substituted or unsubstituted hydrocarbon group having 1 to 40 carbon atoms. Adjacent groups may form a cyclic structure. In the formula (A''), R¹³ to R²⁷ each independently represent a hydrogen atom or a substituted or unsubstituted hydrocarbon group having 1 to 40 carbon atoms. Adjacent groups may form a cyclic structure.


Examples of the hydrocarbon group having 1 to 40 carbon atoms represented by each of R⁸ to R¹² and R¹³ to R²⁷ in the formulae (A') and (A'') are the same as those of R² to R⁷.

Examples of a divalent group formed when an adjacent set of R⁸ to R¹² and R¹³ to R²⁷ forms a cyclic structure are a tetramethylene group, a pentamethylene group, a hexamethylene group, a diphenylmethane-2,2'-diyl group, a diphenylethane-3,3'-diyl group, and a diphenylpropane-4,4'-diyl group.

In the exemplary embodiment of the invention, the aromatic compound represented by the formulae (1) and (3) to (5) is preferably contained as the electron transporting layer.

As an electron transporting compound for the electron injecting layer or the electron transporting layer, 8-hydroxyquinoline or a metal complex of its derivative, an oxadiazole derivative, and a nitrogen-containing heterocyclic derivative are preferable. A specific example of the 8-hydroxyquinoline or the metal complex of its derivative is a metal chelate oxinoid compound containing a chelate of oxine (typically 8-quinolinol or 8-hydroxyquinoline). For instance, tris(8-quinolinol)aluminum can be used. Examples of the oxadiazole derivative are as follows.

[Chemical Formula 33]




In the formula, Ar^{17} , Ar^{18} , Ar^{19} , Ar^{21} , Ar^{22} and Ar^{25} each represent a substituted or unsubstituted aryl group. Ar^{17} , Ar^{19} and Ar^{22} may be the same as or different from Ar^{18} , Ar^{21} and Ar^{25} respectively. Ar^{20} , Ar^{23} and Ar^{24} each represent a substituted or unsubstituted arylene group. Ar^{23} and Ar^{24} may be mutually the same or different.

Examples of the arylene group are a phenylene group, naphthylene group, biphenylene group, anthranylene group, perylenylene group and pyrenylene group. Examples of the substituent therefor are an alkyl group having 1 to 10 carbon atoms, alkoxy group having 1 to 10 carbon atoms and cyano group.

Such an electron transporting compound is preferably an electron transporting compound that can be favorably formed into a thin film(s). Examples of the electron transporting compound are as follows.

5

[Chemical Formula 35]




(A)

(B)

In the formula (B), X represents a carbon atom or a nitrogen atom. Z_1 and Z_2 each independently represent an atom group from which a nitrogen-containing heterocycle can be formed.

Preferably, the nitrogen-containing heterocyclic derivative is an organic compound having a nitrogen-containing aromatic polycyclic group having a five-membered ring or six-membered ring. Further, when the nitrogen-containing heterocyclic derivative is such a nitrogen-containing aromatic polycyclic group that contains plural nitrogen atoms, the nitrogen-containing heterocyclic derivative is preferably a nitrogen-containing aromatic polycyclic organic compound having a skeleton formed by a combination of the skeletons respectively represented by the formulae (A) and (B), or by a combination of the skeletons respectively represented by the formulae (A) and (C).

[Chemical Formula 34]



An example of the nitrogen-containing heterocyclic derivative as the electron transporting compound is a nitrogen-containing compound that is not a metal complex, the derivative being formed of an organic compound represented by one of the following general formulae. Examples of the nitrogen-containing heterocyclic derivative are a five-membered ring or six-membered ring derivative having a skeleton represented by the following formula (A) and a derivative having a structure represented by the following formula (B).

[Chemical Formula 36]




(C)

A nitrogen-containing group of the nitrogen-containing aromatic polycyclic organic compound is selected from nitro-

103

gen-containing heterocyclic groups respectively represented by the following general formulae.

[Chemical Formula 37]



the formulae: R represents an aryl group having 6 to 40 carbon atoms, heteroaryl group having 3 to 40 carbon atoms, alkyl group having 1 to 20 carbon atoms or alkoxy group having 1 to 20 carbon atoms; and n represents an integer in a range of 0 to 5. When n is an integer of 2 or more, plural R may be mutually the same or different.

A preferable specific compound is a nitrogen-containing heterocyclic derivative represented by the following formula.




In the formula: HAr represents a substituted or unsubstituted nitrogen-containing heterocycle having 3 to 40 carbon atoms; L^1 represents a single bond, substituted or unsubstituted arylene group having 6 to 40 carbon atoms, or substituted or unsubstituted heteroarylene group having 3 to 40

104

carbon atoms; Ar^1 represents a substituted or unsubstituted divalent aromatic hydrocarbon group having 6 to 40 carbon atoms; and Ar^2 represents a substituted or unsubstituted aryl group having 6 to 40 carbon atoms, or substituted or unsubstituted heteroaryl group having 3 to 40 carbon atoms.









HAr is exemplarily selected from the following group.

[Chemical Formula 38]









105


-continued

**106**


-continued

30 L^1 is exemplarily selected from the following group.

[Chemical Formula 39]

40 Ar^1 is exemplarily selected from the following arylanthra-nil group.

[Chemical Formula 40]



60

In the formula: R^1 to R^{14} each independently represent a hydrogen atom, halogen atom, alkyl group having 1 to 20 carbon atoms, alkoxy group having 1 to 20 carbon atoms, aryloxy group having 6 to 40 carbon atoms, substituted or unsubstituted aryl group having 6 to 40 carbon atoms, or heteroaryl group having 3 to 40 carbon atoms; and Ar^3 rep-






107

resents a substituted or unsubstituted aryl group having 6 to 40 carbon atoms, or a heteroaryl group having 3 to 40 carbon atoms.


All of R¹ to R⁸ of a nitrogen-containing heterocyclic derivative may be hydrogen atoms. 5

Ar² is exemplarily selected from the following group.


[Chemical Formula 41]

**108**

-continued



10




15

20

Other than the above, the following compound (see JP-A-9-3448) can be favorably used for the nitrogen-containing aromatic polycyclic organic compound as the electron transporting compound. 25

[Chemical Formula 42]



30

35


40

45

In the formula: R₁ to R₄ each independently represent a hydrogen atom, substituted or unsubstituted aliphatic group, substituted or unsubstituted alicyclic group, substituted or unsubstituted carbocyclic aromatic cyclic group, or substituted or unsubstituted heterocyclic group; and X₁ and X₂ each independently represent an oxygen atom, sulfur atom or dicyanomethylene group.

The following compound (see JP-A-2000-173774) can also be favorably used for the electron transporting compound.


[Chemical Formula 43]



109

In the formula, R¹, R², R³ and R⁴, which may be mutually the same or different, each represent an aryl group represented by the following formula.

[Chemical Formula 44]




In the formula, R⁵, R⁶, R⁷, R⁸ and R⁹, which may be mutually the same or different, each represent a hydrogen atom, saturated or unsaturated alkoxy group, alkyl group, amino group or alkylamino group. At least one of R⁵, R⁶, R⁷, R⁸ and R⁹ represents a saturated or unsaturated alkoxy group, alkyl group, amino group or alkylamino group.


A polymer compound containing the nitrogen-containing heterocyclic group or a nitrogen-containing heterocyclic derivative may be used for the electron transporting compound.

The electron transporting layer preferably contains at least one of nitrogen-containing heterocycle derivatives respectively represented by the following formulae (201) to (203).


[Chemical Formula 45]



(201)



(202)



(203)

In the formulae (201) to (203), R represents a hydrogen atom, substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms. n represents an integer of 0 to 4. R¹ represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, or alkoxy group having 1 to 20 carbon atoms. R² and R³ each independently represent a hydrogen atom, substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group hav-

110

ing 1 to 20 carbon atoms, or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms. L represents a substituted or unsubstituted arylene group having 6 to 60 carbon atoms, substituted or unsubstituted pyridinylene group, substituted or unsubstituted quinolinylene group, or substituted or unsubstituted fluorenylene group. Ar¹ represents a substituted or unsubstituted arylene group having 6 to 60 carbon atoms, substituted or unsubstituted pyridinylene group, or substituted or unsubstituted quinolinylene group. Ar² represents substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms.

Ar³ represents a substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms or a group represented by —Ar¹—Ar² (Ar¹ and Ar² may be the same as the above).

In the formulae (201) to (203), R represents a hydrogen atom, substituted or unsubstituted aryl group having 6 to 60 carbon atoms, substituted or unsubstituted pyridyl group, substituted or unsubstituted quinolyl group, substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, or substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms.

Although a thickness of the electron injecting layer or the electron transporting layer is subject to no limitation, the thickness is preferably 1 nm to 100 nm.

The electron injecting layer preferably contains an inorganic compound such as an insulator or a semiconductor in addition to the nitrogen-containing cyclic derivative. Such an insulator or a semiconductor, when contained in the electron injecting layer, can effectively prevent a current leak, thereby enhancing electron injectability.

As the insulator, it is preferable to use at least one metal compound selected from the group consisting of an alkali metal chalcogenide, an alkali earth metal chalcogenide, a halogenide of alkali metal and a halogenide of alkali earth metal. When the electron injecting layer is formed from the alkali metal chalcogenide or the like, the electron injectability can preferably be further enhanced. Specifically, preferred examples of the alkali metal chalcogenide are Li₂O, K₂O, Na₂S, Na₂Se and Na₂O, while preferable example of the alkali earth metal chalcogenide are CaO, BaO, SrO, BeO, BaS and CaSe. Preferred examples of the halogenide of the alkali metal are LiF, NaF, KF, LiCl, KCl and NaCl. Preferred examples of the halogenide of the alkali earth metal are fluorides such as CaF₂, BaF₂, SrF₂, MgF₂ and BeF₂, and halogenides other than the fluoride.

Examples of the semiconductor are one of or a combination of two or more of an oxide, a nitride or an oxidized nitride containing at least one element selected from Ba, Ca, Sr, Yb, Al, Ga, In, Li, Na, Cd, Mg, Si, Ta, Sb and Zn. An inorganic compound for forming the electron injecting layer is preferably a microcrystalline or amorphous insulative film. When the electron injecting layer is formed of such insulative film, more uniform thin film can be formed, thereby reducing pixel defects such as a dark spot. Examples of such an inorganic compound are the alkali metal chalcogenide, alkali earth metal chalcogenide, halogenide of the alkali metal and halogenide of the alkali earth metal.

When the electron injecting layer contains such an insulator or semiconductor, a thickness thereof is preferably in a


111

range of approximately 0.1 nm to 15 nm. The electron injecting layer according to this exemplary embodiment may preferably contain the above-described reduction-causing dopant.

Hole Injecting Layer and Hole Transporting Layer

The hole injecting layer or the hole transporting layer (including the hole injecting/transporting layer) may contain an aromatic amine compound such as an aromatic amine derivative represented by the following formula (I).



[Chemical Formula 46]




In the formula (I), Ar^1 to Ar^4 each represent a substituted or unsubstituted aryl group having 6 to 50 ring carbon atoms, substituted or unsubstituted heteroaryl group having 5 to 50 atoms for forming a ring, or a group formed by bonding the aryl group to the heteroaryl group.

Examples of the compound represented by the formula (I) are shown below. However, the compound represented by the formula (I) is not limited thereto.

[Chemical Formula 47]


**112**

-continued



113

-continued




5

10

15

20

25




30

35

40

45



50


55

60

65

114

-continued




5

10

15

20

25




30

35

40

45



50



55

60



65

115



-continued



25




45

**116**


-continued

117

-continued

**118**

-continued



5

10

15

20

25

30

35

40



45

50

55


60

65




119

-continued

**120**


-continued



121


Aromatic amine represented by the following (II) can also be preferably used for forming the hole injecting layer or the hole transporting layer.

[Chemical Formula 48]




In the above (II), Ar^1 to Ar^3 each represent the same as Ar^1 to Ar^4 of the above formula (I). Examples of the compound represented by the general formula (II) are shown below. However, the compound represented by the formula (II) is not limited thereto.

[Chemical Formula 49]


**122**

-continued

5
10
(II)




20
25
30
35
40
45
50
55
60
65




123

-continued


**124**

-continued



125

-continued



It should be noted that the invention is not limited to the above description but may include any modification as long as such modification stays within a scope and a spirit of the present invention.

For instance, the following is a preferable example of such modification made to the invention.

According to this exemplary embodiment, the emitting layer may also preferably contain an assistance substance for assisting injection of charges.

When the emitting layer is formed of a host material having a wide energy gap, a difference in ionization potential (I_p) between the host material and the hole injecting/transporting layer etc. becomes so large that injection of the holes into the emitting layer becomes difficult, which may cause a rise in a driving voltage required for providing sufficient luminance.

In the above instance, introducing a hole-injectable or hole-transportable assistance substance for assisting injection of charges in the emitting layer can contribute to facilitation of the injection of the holes into the emitting layer and to reduction of the driving voltage.

As the assistance substance for assisting the injection of charges, for instance, a general hole injecting material, a general hole transporting material or the like can be used.

Examples of the assistance substance are a triazole derivative (see, for instance, the specification of U.S. Pat. No. 3,112,197), an oxadiazole derivative (see, for instance, the specification of U.S. Pat. No. 3,189,447), an imidazole derivative (see, for instance, JP-B-37-16096), a polyarylalkane derivative (see, for instance, the specifications of U.S. Pat. No. 3,615,402, U.S. Pat. No. 3,820,989, and U.S. Pat. No. 3,542,544, JP-B-45-555, JP-B-51-10983, JP-A-51-93224, JP-A-55-17105, JP-A-56-4148, JP-A-55-108667, JP-A-55-156953 and JP-A-56-36656), a pyrazoline derivative and a pyrazolone derivative (see, for instance, the specifications of U.S. Pat. No. 3,180,729 and U.S. Pat. No. 4,278,746, JP-A-55-88064, JP-A-55-88065, JP-49-105537, JP-A-55-51086, JP-A-56-80051, JP-A-56-88141, JP-A-57-45545, JP-A-54-112637 and JP-A-55-74546), a phenylenediamine derivative (see, for instance, the specification of U.S. Pat. No. 3,615,404, JP-B-51-10105, JP-B-46-3712, JP-B-47-25336, JP-A-54-53435, JP-A-54-110536 and JP-A-54-119925), an arylamine derivative (see, for instance, the specifications of U.S. Pat. No. 3,567,450, U.S. Pat. No. 3,180,703, U.S. Pat. No.

126

3,240,597, U.S. Pat. No. 3,658,520, U.S. Pat. No. 4,232,103, U.S. Pat. No. 4,175,961 and U.S. Pat. No. 4,012,376, JP-B-49-35702, JP-B-39-27577, JP-A-55-144250, JP-A-56-119132 and JP-A-56-22437 and the specification of West Germany Patent No. 1,110,518), an amino-substituted chalcone derivative (see, for instance, the specification of U.S. Pat. No. 3,526,501), an oxazole derivative (disclosed in, for instance, the specification of U.S. Pat. No. 3,257,203), a styrylanthracene derivative (see, for instance, JP-A-56-46234), a fluorenone derivative (see, for instance, JP-A-54-110837), a hydrazone derivative (see, for instance, the specification of U.S. Pat. No. 3,717,462 and JP-A-54-59143, JP-A-55-52063, JP-A-55-52064, JP-A-55-46760, JP-A-55-85495, JP-A-57-11350, JP-A-57-148749 and JP-A-02-311591), a stilbene derivative (see, for instance, JP-A-61-210363, JP-A-61-228451, JP-A-61-14642, JP-A-61-72255, JP-A-62-47646, JP-A-62-36674, JP-A-62-10652, JP-A-62-30255, JP-A-60-93455, JP-A-60-94462, JP-A-60-174749 and JP-A-60-175052), a silazane derivative (see the specification of U.S. Pat. No. 4,950,950), a polysilane type (see JP-A-02-204996), an aniline-based copolymer (see JP-A-02-282263), and a conductive polymer oligomer (particularly, thiophene oligomer) disclosed in JP-A-01-211399.

25 The hole-injectable material, examples of which are as listed above, is preferably a porphyrin compound (disclosed in JP-A-63-295695 etc.), an aromatic tertiary amine compound or a styrylamine compound (see, for instance, the specification of U.S. Pat. No. 4,127,412, JP-A-53-27033, JP-A-54-58445, JP-A-54-149634, JP-A-54-64299, JP-A-55-79450, JP-A-55-144250, JP-A-56-119132, JP-A-61-295558, JP-A-61-98353 or JP-A-63-295695), particularly preferably an aromatic tertiary amine compound.

30 35 In addition, 4,4'-bis(N-(1-naphthyl)-N-phenylamino)biphenyl (hereinafter, abbreviated as NPD) having two fused aromatic rings in the molecule as disclosed in U.S. Pat. No. 5,061,569, or 4,4',4''tris(N-(3-methylphenyl)-N-phenylamino)triphenylamine (hereinafter, abbreviated as 40 MTDATA) in which three triphenylamine units are bonded in a starburst form as disclosed in JP-A-04-308688 and the like may also be used.

40 45 Further, a hexaazatriphenylene derivative disclosed in Japanese Patent No. 3614405 and No. 3571977 and U.S. Pat. No. 4,780,536 may also preferably be used as the hole-injectable material.

50 Alternatively, inorganic compounds such as p-type Si and p-type SiC can also be used as the hole-injecting material.

55 A method of forming each of the layers in the organic EL device according to the aspect of the invention is not particularly limited. A conventionally-known method such as vacuum deposition or spin coating may be employed for forming the layers. The organic thin-film layer containing the compound represented by the formula (1), which is used in the organic EL device according to the exemplary embodiment of the invention, may be formed by a conventional coating method such as vacuum deposition, molecular beam epitaxy (MBE method) and coating methods using a solution such as a dipping, spin coating, casting, bar coating, and roll coating.

60 65 Although the thickness of each organic layer of the organic EL device is not particularly limited, the thickness is generally preferably in a range of several nanometers to 1 μm because an excessively-thinned film likely entails defects

such as a pin hole while an excessively-thickened film requires high voltage to be applied and deteriorates efficiency.

EXAMPLES

5

Next, the invention will be described in further detail by exemplifying Example(s) and Comparative(s). However, the invention is not limited by the description of Example(s).


10

Synthesis Example 1

Synthesis of Compound No. 1

15

[Chemical Formula 50]



20

Under an Ar gas atmosphere, 2,4,6-trichloropyrimidine (18.3 g, 100 mmol), phenylboronic acid (24.4 g, 200 mmol), palladium acetate (0.56 g, 2.5 mmol), triphenylphosphine (1.31 g, 5.0 mmol), DME (930 ml) and an aqueous solution of 2M sodium carbonate (310 ml) were stirred for 15 hours at a reflux temperature. The solvent was distilled away under reduced pressure. The obtained residue was extracted by dichloromethane. The residue obtained by concentrating the organic phase was refined by silica-gel column chromatography (a developing solvent: hexane-ethyl acetate) to provide an intermediate body X_1 as a white solid. A yield of the intermediate body X_1 was 18.7 g and a yield rate thereof was 70%. (reference document: J. Org. Chem. 66 7125-7128 (2001))


40

45

50


55

[Chemical Formula 51]



60

65



-continued

The intermediate body X_2 (5.14 g, 10 mmol) was added in dehydrated THF (100 ml), and was stirred at -70 degrees C.

129

under an Ar gas atmosphere. Next, n-BuLi (1.6M in hexane) (6.3 ml) was dropped thereto. After stirring for two hours at -70 degrees C., 5.64 g (30 mmol) of triisopropylborate was dropped thereto. After stirring for one hour at -70 degrees C., the reactant mixture was stirred at the room temperature for five hours. Subsequently, 1N-hydrochloric acid (30 ml) was added thereto and stirred for one hour at the room temperature. THF was distilled away under reduced pressure and was extracted by dichloromethane to provide an organic phase. The organic phase was dried by anhydrous magnesium sulfate. The residue obtained by concentrating the solvent was washed with toluene to provide an intermediate body X_3 as a white solid. A yield of the intermediate body X_3 was 3.1 g and a yield rate thereof was 65%.

130


phase was refined by silica-gel column chromatography (a developing solvent: hexane-toluene) and was recrystallized by toluene twice to provide a target object (a compound No. 1) as a white solid. A yield of the compound No. 1 was 3.0 g and a yield rate thereof was 45%.

FD mass analysis consequently showed that m/e was equal to 665 while a calculated molecular weight was 654.



10 Synthesis Example 2

Synthesis of Compound No. 2

[Chemical Formula 53]



[Chemical Formula 54]


Intermediate body X_4 

Compound No. 1

Under an Ar gas atmosphere, the intermediate body X_3 (4.8 g, 10 mmol), the intermediate body X_1 (2.66 g, 10 mmol), an aqueous solution of 2M sodium carbonate (12 ml), toluene (20 ml), DME (20 ml) and Pd(PPh₃)₄ (0.35 g) were stirred for 16 hours at a reflux temperature. After the reactant solution was cooled down to the room temperature, toluene (200 ml) and water (100 ml) were added thereto to separate an organic phase. The residue obtained by concentrating the organic


Under an Ar gas atmosphere, 2,4,6-trichloropyrimidine (25.0 g, 136.3 mmol), phenylboronic acid (16.6 g, 136.3 mmol), palladium acetate (1.53 g, 6.82 mmol), triphenylphosphine (3.58 g, 13.6 mmol), DME (1250 ml) and an aqueous solution of 2M sodium carbonate (211 ml) were stirred for 16 hours at a reflux temperature. The solvent was distilled away under reduced pressure. The obtained residue was extracted by dichloromethane. The residue obtained by concentrating the organic phase was refined by silica-gel column chromatography (a developing solvent: hexane-ethyl acetate) to provide an intermediate body X_4 as a white solid. A yield of the intermediate body X_4 was 22.1 g and a yield rate thereof was 72%. (reference document: J. Org. Chem. 66 7125-7128 (2001))

[Chemical Formula 55]




131

-continued



132

-continued



Under an Ar gas atmosphere, 2,4-dichloro-6-phenylpyrimidine (the intermediate body X₄) (6.0 g, 26.6 mmol), 9,9-dimethylfluorene-2-boronic acid (6.34 g, 26.6 mmol), palladium acetate (0.30 g, 1.33 mmol), triphenylphosphine (0.70 g, 2.66 mmol), DME (250 ml) and an aqueous solution of 2M sodium carbonate (42 ml) were stirred for 8 hours at a reflux temperature. The solvent was distilled away under reduced pressure. The obtained residue was extracted by toluene. The residue obtained by concentrating the organic phase was refined by silica-gel column chromatography (a developing solvent: hexane-toluene) to provide an intermediate body X₅ as a white solid. A yield of the intermediate body X₅ was 7.2 g and a yield rate thereof was 70%.

[Chemical Formula 56]

25 Under an Ar gas atmosphere, 3,5-bis-carbazolylphenyl boronic acid (4.52 g, 10 mmol), the intermediate body X₅ (3.83 g, 10 mmol), an aqueous solution of 2M sodium carbonate (12 ml), toluene (20 ml) and Pd(PPh₃)₄ (0.35 g) were stirred for 16 hours at a reflux temperature. After the reactant solution was cooled down to the room temperature, toluene (200 ml) and water (100 ml) were added thereto to separate an organic phase. The residue obtained by concentrating the organic phase was refined by silica-gel column chromatography (a developing solvent: hexane-toluene) and was recrystallized by toluene twice to provide a target object (a compound No. 2) as a white solid. A yield of the compound No. 2 was 3.0 g and a yield rate thereof was 40%.

30

35

FD mass analysis consequently showed that m/e was equal to 754 while a calculated molecular weight was 754.


40

Synthesis Example 3

Synthesis of Compound No. 3


45

[Chemical Formula 57]



133

-continued




Intermediate body X₆

3-bromobenzaldehyde (18.5 g, 100 mmol), acetophenone (12.0 g, 100 mmol), 1N-sodium methoxide/methanol solution (10 ml) and ethanol (200 ml) were stirred for five hours at the room temperature under an Ar gas atmosphere. Subsequently, the reactant mixture was heated and stirred for another four hours at a reflux temperature. Next, benzamidine hydrochloride (9.4 g, 60 mmol) and sodium hydroxide (8.0 g, 200 mmol) were added thereto and stirred for five hours at 70 degrees C. After the reaction, the reactant mixture was filtered to separate an extract. The extract was refined by silica-gel column chromatography (a developing solvent: dichloromethane) to provide an intermediate body X_6 as a white solid. A yield of the intermediate body X_6 was 10.1 g and a yield rate thereof was 26%.

[Chemical Formula 58]

134

-continued



Compound No. 3




25 Under an Ar gas atmosphere, the intermediate body X₃ (4.8 g, 10 mmol), the intermediate body X₆ (3.9 g, 10 mmol), an aqueous solution of 2M sodium carbonate (12 ml), toluene (20 ml), DME (20 ml) and Pd(PPh₃)₄ (0.35 g) were stirred for 16 hours at a reflux temperature. After the reactant solution
 30 was cooled down to the room temperature, toluene (200 ml) and water (100 ml) were added thereto to separate an organic phase. The residue obtained by concentrating the organic phase was refined by silica-gel column chromatography (a developing solvent: hexane-toluene) and was recrystallized by toluene twice to provide a target object (a compound No. 3) as a white solid. A yield of the compound No. 3 was 3.2 g and a yield rate thereof was 43%.

FD mass analysis consequently showed that m/e was equal to 741 while a calculated molecular weight was 741.

Synthesis Example 4


Synthesis of Compound No. 4

50 [Chemical Formula 59]




135

-continued

Intermediate body X₇

136

-continued



Compound No. 4

4-bromobenzaldehyde (18.5 g, 100 mmol), acetophenone (12.0 g, 100 mmol), 1N-sodium methoxide/methanol solution (10 ml) and ethanol (200 ml) were stirred at room temperature for 5 hours at the room temperature under an Ar gas atmosphere. Subsequently, the reactant mixture was heated and stirred for another four hours at a reflux temperature. Next, benzamidine hydrochloride (9.4 g, 60 mmol) and sodium hydroxide (8.0 g, 200 mmol) were added thereto and stirred for five hours at 70 degrees C. After the reaction, the reactant mixture was filtered to separate an extract. The extract was refined by silica-gel column chromatography (a developing solvent: dichloromethane) to provide an intermediate body X₇ as a white solid. A yield of the intermediate body X₇ was 11.6 g and a yield rate thereof was 30%.

[Chemical Formula 60]

20

Under an Ar gas atmosphere, the intermediate body X₃ (4.8 g, 10 mmol), the intermediate body X₇ (3.9 g, 10 mmol), an aqueous solution of 2M sodium carbonate (12 ml), toluene (20 ml), DME (20 ml) and Pd(PPh₃)₄ (0.35 g) were stirred for 16 hours at a reflux temperature. After the reactant solution was cooled down to the room temperature, toluene (200 ml) and water (100 ml) were added thereto to separate an organic phase. The residue obtained by concentrating the organic phase was refined by silica-gel column chromatography (a developing solvent: hexane-toluene) and was recrystallized by toluene twice to provide a target object (a compound No. 4) as a white solid. A yield of the compound No. 4 was 2.6 g and a yield rate thereof was 35%.


35 FD mass analysis consequently showed that m/e was equal to 741 while a calculated molecular weight was 741.

Synthesis Example 5


40

Synthesis of Compound No. 5


45 [Chemical Formula 61]



55




65



137



-continued



138

[Chemical Formula 62]

Compound A



Under an Ar gas atmosphere, the intermediate body X_5 (3.8 g, 10 mmol), 4-carbazolylphenyl boronic acid (2.9 g, 10 mmol), an aqueous solution of 2M sodium carbonate (12 ml), toluene (20 ml), DME (20 ml) and $Pd(PPh_3)_4$ (0.35 g) were stirred for 20 hours at a reflux temperature. After the reactant solution was cooled down to the room temperature, toluene (200 ml) and water (100 ml) were added thereto to separate an organic phase. The residue obtained by concentrating the organic phase was refined by silica-gel column chromatography (a developing solvent: hexane-toluene) and was recrystallized by toluene twice to provide a target object (a compound No. 5) as a white solid. A yield of the compound No. 5 was 2.8 g and a yield rate thereof was 47%.

FD mass analysis consequently showed that m/e was equal to 589 while a calculated molecular weight was 589.

Example 1



Manufacture of Organic EL Device 1

A glass substrate (size: 25 mm×75 mm×1.1 mm) having an ITO transparent electrode (manufactured by Geomatec Co., Ltd.) was ultrasonic-cleaned in isopropyl alcohol for five minutes, and then UV (Ultraviolet)/ozone-cleaned for 30 minutes.

After the glass substrate having the transparent electrode was cleaned, the glass substrate was mounted on a substrate holder of a vacuum deposition apparatus, and a hole injecting layer was initially formed by depositing a compound A onto the substrate to be 40 nm thick to cover a surface of the glass substrate where a transparent electrode line was provided. Next, a compound B was deposited onto the hole injecting layer to be 20 nm thick to provide a hole transporting layer.


On the hole transporting layer, the compound No. 1 as a phosphorescent host and $Ir(Ph-ppy)_3$ as a phosphorescent dopant were co-evaporated (thickness: 40 nm), thereby providing a phosphorescent-emitting layer. The concentration of $Ir(Ph-ppy)_3$ was 20 mass %.

On the phosphorescent-emitting layer, a 30-nm thick film of a compound C, a 1-nm thick film of LiF, an 80-nm thick film of a metal Al were laminated in sequence, thereby providing a cathode. LiF, which is an electron injectable electrode, was formed at a speed of 1 Å/min.



139

-continued

Ir(Ph-ppy)₃ (facial body)

Evaluation on Luminescent Performance of Organic EL Device

The organic EL devices each manufactured as described above were driven by direct-current electricity to emit light, so that luminance intensity and current density were measured to obtain voltage and luminous efficiency at a current density of 1 mA/cm². Further, time elapsed until the initial luminance intensity of 20,000 cd/m² was reduced to the half (i.e., time until half-life) was obtained. The results are shown in Table 1.


Examples 2 to 5

The organic EL devices according respectively to Examples 2 to 5 were formed and evaluated in the same manner as in Example 1 except that the host compound No. 1 was replaced by host materials described in Table 1. The results of the evaluation are shown in Table 1.


140

-continued


Compound No. 3




Compound No. 4



Compound No. 5



Comparative 1



An organic EL device according to Comparative 1 was formed and evaluated in the same manner as in Example 1 except that the host compound No. 1 was replaced by a compound D (a host material described in WO2003/08076). The results of the evaluation are shown in Table 1.

[Chemical Formula 64]




TABLE 1

	Host compound	Voltage (V) @ 1 mA/cm ²	Luminous efficiency (cd/A) @ 1 mA/cm ²	Time until half-life (hrs) 20000 cd/m ²
Example 1	No. 1	3.2	86.7	350
Example 2	No. 2	3.0	87.9	450
Example 3	No. 3	3.6	88.3	500
Example 4	No. 4	3.5	81.3	500
Example 5	No. 5	3.1	74.4	300
Comparative 1	Compound D	4.7	51.1	300

As seen from Table 1, the organic EL devices of Examples were emittable at low voltage and exhibited a high luminous efficiency as compared with the organic EL device of Comparative 1.

Example 6

A glass substrate (size: 25 mm×75 mm×1.1 mm) having an ITO transparent electrode (manufactured by Geomatec Co., Ltd.) was ultrasonic-cleaned in isopropyl alcohol for five minutes, and then UV (Ultraviolet)/ozone-cleaned for 30 minutes.

After the glass substrate having the transparent electrode was cleaned, the glass substrate was mounted on a substrate holder of a vacuum deposition apparatus, and a hole injecting layer was initially formed by depositing a compound A onto the substrate to be 40 nm thick to cover a surface of the glass substrate where a transparent electrode line was provided. Next, a compound B was deposited onto the hole injecting layer to be 20 nm thick to provide a hole transporting layer.

On the hole transporting layer, the compound D as a phosphorescent host and Ir(Ph-ppy)₃ as a phosphorescent dopant were co-evaporated (thickness: 40 nm), thereby providing a phosphorescent-emitting layer. The concentration of Ir(Ph-ppy)₃ was 20 mass %.

On the phosphorescent-emitting layer, a 5-nm thick film of the compound No. 2, a 25-nm thick film of the compound C, a 1-nm thick film of LiF, an 80-nm thick film of a metal Al were laminated in sequence, thereby providing a cathode. LiF, which is an electron injectable electrode, was formed at a speed of 1 Å/min.

The results of the evaluation of the organic EL device are shown in Table 2. The comparative 1 shown in Table 2 as a comparative is the same as the comparative 1 above.

TABLE 2


	Host compound	Electron transporting compound	Voltage (V) @ 1 mA/cm ²	Luminous efficiency (cd/A) @ 1 mA/cm ²	Time until half-life (hrs) 20000 cd/m ²
Example 6	Compound D	No. 2	4.7	52.5	400
Comparative 1	Compound D	none	4.7	51.1	300

As seen from Table 2, the compound of the invention was usable as an electron transporting compound and the organic EL devices of Examples had a longer lifetime than the organic EL device of the comparative.

As described in detail, when the compounds of the invention are used as an organic-EL-device material, an organic EL device having a high luminous efficiency and being emittable at low voltage is obtainable. Accordingly, the organic EL device of the invention is significantly usable as a light source of various electronic devices and the like. Moreover, the compound of the invention is effectively usable as an organic-electron-device material for an organic solar cell, an organic semiconductor laser, a sensor using an organic substance and an organic TFT.

The invention claimed is:

1. A fluorene-containing aromatic compound represented by formula (1):



wherein:

Nr₁ represents a substituted or unsubstituted pyridine ring, a substituted or unsubstituted pyrimidine ring, or a substituted or unsubstituted triazine ring;

Ar represents a single bond or a substituted or unsubstituted aromatic ring having 5 to 40 ring carbon atoms;

Fl₁ and Fl₂ each independently represent a substituted or unsubstituted fluorenyl group, and when Fl₁ or Fl₂ comprises one or more substituents, each substituent is independently a linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a cyano group, a halogen atom, or an aryl group having 6 to 22 ring carbon atoms;

p represents an integer of 0 to 3, such that when p is 2 or more, the L₄s are the same or different, and the Fl₁s are the same or different;

q represents an integer of 0 to 3, such that when q is 2 or more, the L₇s are the same or different, and the Fl₂s are the same or different;

p+q=1 or more;

Cz₁ and Cz₂ each independently represent a substituted or unsubstituted carbazolyl group;

m represents an integer of 0 to 3, such that when m is 2 or more, the L₂s are the same or different, and the Cz₁s are the same or different;

143

n represents an integer of 0 to 3, such that when n is 2 or more, the L₅s are the same or different, and the C₂₂s are the same or different;

m+n=1 or more;

Y¹ and Y² each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, an iodine atom, a cyano group, a substituted or unsubstituted linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms;

x represents an integer of 1 to 3, such that when x is 2 or more, the L₃s are the same or different, and the Y₁s are the same or different;

y represents an integer of 1 to 3, such that when y is 2 or more, the L₆s are the same or different, and the Y₂s are the same or different;

m+p+x is less than or equal to the number of substituents of N_{r1} minus 1;

n+q+y is less than or equal to the number of substituents of Ar minus 1;

L₁ represents a single bond or a substituted or unsubstituted aromatic ring having 6 to 30 ring carbon atoms;


L₂ to L₇ each independently represent a single bond, a substituted or unsubstituted aromatic ring having 6 to 30 ring carbon atoms, or a substituted or unsubstituted aromatic heterocyclic ring having 2 to 30 ring carbon atoms;

k represents an integer of 1 to 3;

when p is 1 or greater, Fl₁ is joined to L₄ via the 2-position of Fl₁;

when q is 1 or greater, Fl₂ is joined to L₇ via the 2-position of Fl₂; and


the fluorene-containing aromatic compound represented by formula (1) is not a compound represented by formula (2):



2. The compound of claim 1, wherein:

Cz₁ and Cz₂ are each independently represented by formula (3) or formula (4):


144



wherein:

Ra and Rb each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, an iodine atom, a cyano group, a substituted or unsubstituted linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms;

f and g each independently represent an integer of 1 to 4,



wherein:

Ra', Rb' and Rc' each independently represent a hydrogen atom, a deuterium atom, a fluorine atom, a chlorine atom, a bromine atom, an iodine atom, a cyano group, a substituted or unsubstituted linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic haloalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic haloalkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms, a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms, or a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms;

f represents an integer of 1 to 4;

g' represents an integer of 1 to 3; and

h' represents an integer of 1 to 5.

145

3. The compound of claim 1, wherein:

k is 1; and

m+n+p+q is less than or equal to 6.

4. The compound of claim 1, wherein Y₁ and Y₂ each independently represent a hydrogen atom or a phenyl group. 5

5. The compound of claim 1, wherein:

k is 1;

L₁, L₂, L₃, L₅, and L₆ each independently represent a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, a substituted or unsubstituted terphenylene group, or a substituted or unsubstituted fluorenylene group; and

10

L₄ and L₇ each independently represent a single bond, a substituted or unsubstituted phenylene group, a substituted or unsubstituted biphenylene group, or a substituted or unsubstituted terphenylene group.

15

6. The compound of claim 1, wherein:

m+n=1 or 2; and


p+q=1 or 2.

7. The compound of claim 1, wherein Ar represents a monocyclic aromatic ring selected from the group consisting of a substituted or unsubstituted benzene ring, a substituted or unsubstituted pyrazole ring, a substituted or unsubstituted imidazole ring, a substituted or unsubstituted triazole ring, a substituted or unsubstituted pyridine ring, a substituted or unsubstituted pyrimidine ring, a substituted or unsubstituted pyridazine ring, a substituted or unsubstituted pyrazine ring, a substituted or unsubstituted triazine ring, and a substituted or unsubstituted thiophene ring.

8. The compound of claim 1, wherein Ar is a benzene ring.

9. The compound of claim 1, wherein:

Fl₁ and Fl₂ are each independently represented by formula (5):



30

(5)

35

Y₃ and Y₄ each independently represent:

a hydrogen atom;

a deuterium atom;

a linear, branched, or cyclic alkyl group having 1 to 10 carbon atoms;

a linear, branched, or cyclic haloalkyl group having 1 to 10 carbon atoms;

a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms;

a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms;

a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or

a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms; and

50

Y₅, Y₆, Y₇, Y₈, Y₉, Y₁₀, and Y₁₁ each independently represent:

a hydrogen atom;

a deuterium atom;

a fluorine atom;

a chlorine atom;

a bromine atom;

60

65

146

an iodine atom;

a cyano group;

a linear, branched, or cyclic alkyl group having 1 to 10 carbon atoms;

a linear, branched, or cyclic alkoxy group having 1 to 10 carbon atoms;

a linear, branched, or cyclic haloalkyl group having 1 to 10 carbon atoms;

a linear, branched, or cyclic haloalkoxy group having 1 to 10 carbon atoms;

a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms;

a substituted or unsubstituted arylsilyl group having 6 to 30 carbon atoms;

a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms; or


a substituted or unsubstituted heteroaryl group having 2 to 10 ring carbon atoms.

10. The compound of claim 9, wherein Y₃ and Y₄ each independently represent a linear alkyl group having 1 to 10 carbon atoms or a phenyl group.


11. The compound of claim 10, wherein Y₃ and Y₄ each represent a methyl group.

12. The compound of claim 1, wherein Cz₁ and Cz₂ are each independently represented by formula (3a) or formula (4a):

(3a)



(4a)



13. The compound of claim 1, wherein Nr₁ is a pyrimidine ring.

14. An organic electroluminescence device material, comprising the compound of claim 1.

15. An organic electroluminescence device, comprising:

a cathode;

an anode; and

an organic thin-film layer between the cathode and the anode;

wherein:

the organic thin-film layer comprises one or more layers; at least one layer of the organic thin-film layer is an emitting layer; and

at least one layer of the organic thin-film layer comprises the fluorene-containing aromatic compound of claim 1.

16. The device of claim 15, wherein the emitting layer comprises the fluorene-containing aromatic compound as a host material.

17. The device of claim 16, wherein the emitting layer further comprises a phosphorescent material.

147

18. The device of claim 17, wherein the phosphorescent material is an ortho metalation of a complex of a metal atom selected from the group consisting of iridium (Ir), osmium (Os), and platinum (Pt).

19. The device of claim 16, wherein:
the organic thin-film layer comprises an electron injecting layer situated between the cathode and the emitting layer; and
the electron injecting layer comprises a nitrogen-containing cyclic derivative.

20. The device of claim 15, wherein:
the organic thin-film layer comprises an electron transporting layer situated between the cathode and the emitting layer; and
the electron transporting layer comprises the fluorene-containing aromatic compound.

21. The device of claim 15, wherein a reduction-causing dopant is added in an interfacial region between the cathode and the organic thin-film layer.

22. The compound of claim 1, wherein Nr_1 is a pyridine ring.

23. The compound of claim 1, wherein Nr_1 is a triazine ring.

24. The compound of claim 1, wherein, when Nr_1 comprises one or more substituents, each substituent is independently a linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a cyano group, a halogen atom, or an aryl group having 6 to 22 ring carbon atoms.

148

25. The compound of claim 1, wherein, when Ar comprises one or more substituents, each substituent is independently a linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a cyano group, a halogen atom, or an aryl group having 6 to 22 ring carbon atoms.

26. The compound of claim 1, wherein, when Y_1 or Y_2 comprises one or more substituents, each substituent is independently a linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a cyano group, a halogen atom, or an aryl group having 6 to 22 ring carbon atoms.

27. The compound of claim 1, wherein, when Cz_1 or Cz_2 comprises one or more substituents, each substituent is independently a linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a cyano group, a halogen atom, or an aryl group having 6 to 22 ring carbon atoms.

28. The compound of claim 1, wherein, when any of L_1 to L_7 comprises one or more substituents, each substituent is independently a linear, branched, or cyclic alkyl group having 1 to 20 carbon atoms, a haloalkyl group having 1 to 20 carbon atoms, a linear, branched, or cyclic alkylsilyl group having 1 to 10 carbon atoms, a cyano group, a halogen atom, or an aryl group having 6 to 22 ring carbon atoms.

* * * * *

专利名称(译)	含芴芳族化合物，用于有机电致发光元件的材料和使用其的有机电致发光元件		
公开(公告)号	US9266851	公开(公告)日	2016-02-23
申请号	US13/386240	申请日	2010-10-14
申请(专利权)人(译)	出光兴产CO.LTD.		
当前申请(专利权)人(译)	出光兴产股份有限公司.		
[标]发明人	YOSHIDA KEI NISHIMURA KAZUKI ITO MITSUNORI KAWAMURA YUICHIRO OGIWARA TOSHINARI IWAKUMA TOSHIHIRO		
发明人	YOSHIDA, KEI NISHIMURA, KAZUKI ITO, MITSUNORI KAWAMURA, YUICHIRO OGIWARA, TOSHINARI IWAKUMA, TOSHIHIRO		
IPC分类号	H01L51/50 C07D209/86 C07D307/91 C07D403/14 C07D401/10 C07D401/14 C07D403/10 C09B69/00 C07D405/14 C07D409/12 C07D409/14 C07D471/04 H01L51/00 C09B57/00 C09B57/10		
CPC分类号	C07D307/91 C07D209/86 C07D401/10 C07D401/14 C07D403/10 C07D403/14 C07D405/14 C07D409/12 C07D409/14 C07D471/04 C09B57/00 C09B57/008 C09B57/10 C09B69/008 H01L51/0071 H01L51/5016 H01L51/5072		
审查员(译)	CLARK , GREGORY		
优先权	2009239786 2009-10-16 JP		
其他公开文献	US20120126217A1		
外部链接	Espacenet USPTO		

摘要(译)

由下式(1)表示的含芳族化合物。在式(1)中:Nr₁表示具有2至5个环碳原子的取代或未取代的单环含氮芳环,或具有2至9个环碳原子的双环含氮芳环;Ar表示芳香环等;F₁<>1</>和F₁<>2</>代表芳基;和C_z<>1</>和C_z<>2</>代表咔唑基。由式(1)表示的含芳族化合物中省略由下式(2)表示的化合物。

