



US009379170B2

(12) **United States Patent**  
**Cho et al.**

(10) **Patent No.:** **US 9,379,170 B2**  
(45) **Date of Patent:** **Jun. 28, 2016**

(54) **ORGANIC LIGHT EMITTING DIODE DISPLAY DEVICE AND METHOD OF FABRICATING THE SAME**

USPC ..... 438/158, 29, 160, 159; 257/40, 82, 84, 257/88, 184, 257  
See application file for complete search history.

(71) Applicant: **LG DISPLAY CO., LTD.**, Seoul (KR)

(56) **References Cited**

(72) Inventors: **KiSul Cho**, Gumi (KR); **JinChae Jeon**, Daegu (KR)

U.S. PATENT DOCUMENTS

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

7,557,382 B2\* 7/2009 Koh ..... G09G 3/3225  
257/184  
8,860,303 B2\* 10/2014 Kim ..... H01L 27/3246  
313/504

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(Continued)

FOREIGN PATENT DOCUMENTS

(21) Appl. No.: **14/920,642**

CN 1551690 A 12/2004  
CN 1610110 A 4/2005

(22) Filed: **Oct. 22, 2015**

(Continued)

(65) **Prior Publication Data**

US 2016/0043160 A1 Feb. 11, 2016

**Related U.S. Application Data**

*Primary Examiner* — Bradley K Smith

*Assistant Examiner* — David Goodwin

(62) Division of application No. 13/720,651, filed on Dec. 19, 2012.

(74) *Attorney, Agent, or Firm* — Birch, Stewart, Kolasch & Birch, LLP

(30) **Foreign Application Priority Data**

Aug. 10, 2012 (KR) ..... 10-2012-0087980

(57) **ABSTRACT**


(51) **Int. Cl.**  
**H01L 27/15** (2006.01)  
**H01J 1/62** (2006.01)  
(Continued)

An organic light emitting diode (OLED) display device can include a gate line including a gate electrode; an active layer over the gate line with a gate insulating layer interposed therebetween and including an amorphous zinc oxide semiconductor; a first protective layer over color filters on an insulating layer over first source and drain electrodes; second source and drain electrodes on the first protective layer and connected to the first source and drain electrodes; a second protective layer having a third contact hole; a pixel electrode on the second protective layer and connected to the second drain electrode through the third contact hole; a partition partitioning the pixel region; and an organic light emitting layer over the partition. Also, the gate electrode is located to cover a lower portion of the active layer and the second source electrode is extended to cover the channel region of the active layer.

(52) **U.S. Cl.**  
CPC ..... **H01L 27/3272** (2013.01); **H01L 27/1288** (2013.01); **H01L 27/322** (2013.01); **H01L 27/3244** (2013.01); **H01L 51/0001** (2013.01)

**11 Claims, 13 Drawing Sheets**

(58) **Field of Classification Search**  
CPC ..... H01L 29/4908; H01L 2924/12044; H01L 27/1214; H01L 27/322; H01L 27/3244; H01L 51/5253; H01L 2227/323; H01L 27/3272; H01L 27/1259; H01L 27/3225



---

(51)	<b>Int. Cl.</b>			2011/0049523 A1	3/2011	Choi et al.	
	<b>H01L 27/32</b>	(2006.01)		2013/0168648 A1*	7/2013	Jeong .....	H01L 27/3225 257/40
	<b>H01L 51/00</b>	(2006.01)					
	<b>H01L 27/12</b>	(2006.01)		2013/0313530 A1*	11/2013	Seo .....	H01L 29/66969 257/40

(56) **References Cited**

FOREIGN PATENT DOCUMENTS

U.S. PATENT DOCUMENTS

2006/0050192 A1*	3/2006	Cho .....	G02F 1/136286 349/42
2007/0249122 A1	10/2007	Seo et al.	
2009/0302750 A1*	12/2009	Jun .....	H01L 51/5265 313/504

CN	101470295 A	7/2009
CN	102468232 A	5/2012
JP	2007-149693 A	6/2007
KR	10-2011-002159 A	3/2011
KR	10-2012-0072949 A	7/2012

\* cited by examiner

FIG. 1  
RELATED ART




FIG. 2  
RELATED ART




FIG. 3  
RELATED ART




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E




FIG. 5F




FIG. 5G




FIG. 5H




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 6E




FIG. 6F




FIG. 7




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D




FIG. 8E




FIG. 8F




FIG. 8G




FIG. 9




FIG. 10A




FIG. 10B




FIG. 10C




FIG. 10D




FIG. 10E




FIG. 10F





FIG. 10G



# ORGANIC LIGHT EMITTING DIODE DISPLAY DEVICE AND METHOD OF FABRICATING THE SAME

This application is a Divisional of co-pending U.S. application Ser. No. 13/720,651, filed on Dec. 19, 2012, which claims priority to Korean Application No. 10-2012-0087980, filed on Aug. 10, 2012. The entire contents of all these applications are expressly incorporated by reference herein.

## BACKGROUND OF THE INVENTION

### 1. Field of the Invention

The present invention relates to organic light emitting diode (OLED) display device and a method of fabricating the same and, more particularly, to an OLED display device in which OLED pixels are patterned through a photolithography process, and a method of fabricating the same.

### 2. Description of the Related Art

Recently, as interest in information displays has been on the rise and demand for the use of portable information media has been increased, lightweight flat panel displays (FPDs) substituting cathode ray tubes (CRTs) as existing display devices have been actively researched and commercialized.

In the FPD fields, a liquid crystal display (LCD) device, which is lighter and consumes less power, has been spotlighted; however, since an LCD device is a light receiving device, rather than a light emitting device, having shortcomings of brightness, contrast ratio, and a viewing angle, and the like, so a development of a new display device that may overcome such drawbacks has been actively made.

An LED display device, one of new display devices, is a self-luminous type device, which thus is excellent in a viewing angle and contrast ratio, is lighter and thinner because it does not need a backlight, and is advantageous in terms of power consumption, relative to an LCD device. In addition, an OLED display device can be driven by a DC and at a low voltage, has a fast response speed, and is especially advantageous in terms of fabrication costs.

Unlike an LCD device or a plasma display panel (PDP), deposition and encapsulation are the whole of a fabrication process of an OLED display device, so the fabrication process is very simple. Also, when the OLED display device is driven according to an active matrix scheme in which each pixel has a thin film transistor (TFT) as a switching element, the same luminance can be obtained although a low current is applied, so, advantageously, the OLED display device consumes low power, has a high pitch (or high definition or high resolution), and can be increased in size.

Hereinafter, a basic structure and operational characteristics of an OLED display device will be described in detail with reference to the accompanying drawings.

FIG. 1 is a diagram illustrating a light emission principle of a related art OLED display device.

As shown in FIG. 1, a related art OLED display device includes an OLED. The OLED includes organic compound layers 301, 30b, 30c, 30d, and 30e formed between an anode 18 as a pixel electrode and a cathode 28 as a common electrode.

Here, the organic compound layers 30a, 30b, 30c, 30d, and 30e include a hole injection layer 30a, a hole transport layer 30b, an emission layer 30c, an electron transport layer 30d, and an electron injection layer 30e.

When a driving voltage is applied to the anode 18 and the cathode 28, holes which have passed through the hole transport layer 30b and electrons which have passed through the

electron transport layer 30e move to the light emission layer 30c to form excitons, and as a result, the light emission layer 30c emits visible light.

In the OLED display device, the pixels each having the OLED having the foregoing structure are arranged in a matrix form and selectively controlled by a data voltage and a scan voltage to display an image.

The OLED display device is divided into a passive matrix type OLED display device and an active matrix type display device using TFTs as switching elements. Among them, in the active matrix type OLED display device, TFTs as active elements are selectively turned on to select pixels and emitting of pixels is maintained by a voltage maintained in a storage capacitor.

FIG. 2 is an equivalent circuit diagram of a pixel in a related art OLED display device. Namely, FIG. 2 illustrates an example of an equivalent circuit diagram of a pixel having a related art 2T1C (including two transistors and one capacitor) in an active matrix type OLED display device.

Referring to FIG. 2, a pixel of an active matrix type OLED display device includes an OLED, a data line DL and a gate line GL crossing each other, a switching TFT SW, a driving TFT DR, and a storage capacitor Cst.

Here, the switching TFT SW is turned on in response to a scan pulse from the gate line GL to conduct a current path between a source electrode and a drain electrode thereof. During an ON-time period of the switching TFT SW, a data voltage from the data line DL is applied to a gate electrode of the driving TFT DR and the storage capacitor Cst by way of the source electrode and drain electrode of the switching TFT SW.

Here, the driving TFT DR controls a current flowing in the OLED according to the data voltage applied to the gate electrode thereof. The storage capacitor Cst stores a voltage between the data voltage and a low potential power source voltage VSS and uniformly maintains it during one frame period.

Recently, interest in a middle and large display market, beyond a small display panel for portable devices, has increased and a white organic light emitting diode (W-OLED) has come to prominence as a technique satisfying such market demand. A W-OLED uses color filters to implement red, green, and blue colors. Also, in order to achieve a large OLED display device, the development of a transistor which stably operates and has durability by securing constant current characteristics, as a driving thin film transistor (TFT) has been requested.

Thus, an oxide TFT in which an active layer is formed of an oxide semiconductor has been developed. Hereinafter, a structure of a related art W-OLED display device employing an oxide TFT will be described in detail.

FIG. 3 is a cross-sectional view schematically illustrating a structure of a related art W-OLED display device. The related art W-OLED display device illustrated in FIG. 3 has a color filter on TFT (COT) structure in which a color filter is formed on a lower array substrate.

Referring to FIG. 3, the W-OLED display device having the COT structure implement red, green, and blue colors by using a color filter 17 formed on an array substrate 10. In detail, the array substrate includes a plurality of gate lines (not shown) and data lines (not shown) defining a plurality of pixel regions, TFTs formed at crossings of the gate lines and the data lines, the color filter 17 and a pixel electrode 18 formed in each of the pixel regions.

The TFT includes a gate electrode 21 connected to the gate line, a source electrode 22 connected to the data line, and a drain electrode 23 connected to the pixel electrode 18. Also,

the TFT includes a gate insulating layer **15a** for insulating the gate electrode **21** and the source and drain electrodes **22** and **23**, and an active layer **24** made of an oxide semiconductor and forming a conductive channel between the source electrode **22** and the drain electrode **23** by a gate voltage supplied to the gate electrode **21**.

An oxide semiconductor used in the oxide TFT has a weak bonding structure. Thus, in order to prevent damage to a back channel region, an etch stopper **25** is required to be additionally formed on the active layer **24**, having shortcomings in that a corresponding process is additionally performed. In this case, the etch stopper **25** is applied to secure stability of the back channel in a bottom gate structure.

A protective film **15b** is formed at an upper portion of the TFT configured as described above, and the red, green, and blue color filter **17** is formed on the protective film **15b** of the pixel region. An overcoat layer **15c** is formed on a front surface of the array substrate **10** on which the color filter **17** is formed, in order to compensate for a step between the color filter **17** and the TFT.

The pixel electrode **18** is formed on the overcoat layer **15c**. In this case, the pixel electrode **18** is electrically connected to the drain electrode **23** through a contact hole.

Here, although not shown, a partition is formed on the array substrate **10** on which the pixel electrode **18** is formed, and a white organic light emitting layer is formed on the array substrate **10** on which the partition is formed. A common electrode as a cathode is formed on the organic light emitting layer.

In the related art W-OLED display device having the etch stopper configured as described above, in order to form up to the pixel electrode, at least 11 masks such as a gate wiring (i.e., the gate electrode and the gate line), the active layer, the etch stopper, a gate contact, a data wiring (i.e., the source electrode, the drain electrode, and the data line), the protective layer, the red, green, and blue color filter, the overcoat layer, the pixel electrode, and the like, are required, and parasitic capacitance is large due to interlayer superposition.

Also, as mentioned above, the etch stopper is applied in order to secure stability of the back channel, but it is difficult to secure reliability characteristics due to light introduced from upper and lower portions of the active layer, and although a high temperature thermal treatment is required to improve reliability, it is difficult to apply copper (Cu) as a gate wiring.

For reference, in the related art OLED display device, two or more TFTs including a driving TFT and a switching TFT are present in a single pixel region, and the foregoing gate contact is required in order to connect the gate electrode of the driving TFT and the drain electrode of the switching TFT.

#### SUMMARY OF THE INVENTION

An aspect of the present invention provides an organic light emitting diode (OLED) display device in which light introduced from upper and lower sides of an active layer is blocked to improve reliability of an oxide thin film transistor (TFT) and a fabrication process is simplified, and a fabrication method thereof.

According to an aspect of the present invention, there is provided an organic light emitting diode (OLED) display device including: a gate line formed on an array substrate and including a gate electrode; an active layer formed on the gate line with a gate insulating layer interposed therebetween and formed of an amorphous zinc oxide semiconductor; a first source electrode and a drain electrode formed on a source region and a drain region of the active layer, respectively; an

interlayer insulating layer formed on the array substrate with the first source electrode and drain electrode formed thereon; red, green, and blue color filters formed on the array substrate with the interlayer insulating layer formed thereon and covering a pixel region in which an image is displayed; a first protective layer formed on the array substrate with the color filters formed thereon and including a first contact hole and a second contact hole exposing the first source electrode and the drain electrode, respectively; a second source electrode and a second drain electrode formed on the first protective layer and electrically connected to the first source electrode and the first drain electrode through the first contact hole and the second contact hole, respectively; a second protective layer formed on the array substrate with the second source electrode and the drain electrode formed thereon and having a third contact hole exposing the second drain electrode; a pixel electrode formed on the second protective layer and electrically connected to the second drain electrode through the third contact hole; a partition formed on the array substrate with the pixel electrode formed thereon and partitioning the pixel region; a white organic light emitting layer formed on the array substrate with the partition formed thereon; and a common electrode formed on the organic light emitting layer, wherein the gate electrode is formed to cover a lower portion of the active layer and the source electrode is formed to extend to cover the channel region of the active layer from above.

The color filter may be formed to cover a TFT region as well as the pixel region.

The OLED display device may further include: an overcoat layer formed to cover the pixel region in which the color filters are formed and the TFT region.

According to another aspect of the present invention, there is provided a method for fabricating an organic light emitting diode (OLED) display device, including: forming a first conductive layer, a gate insulating layer, and an active layer on an array substrate; forming a first source electrode and a drain electrode formed of a second conductive layer on a source region and a drain region of the active layer, and forming a gate line including a gate electrode formed of the first conductive layer under the active layer; forming an interlayer insulating layer on the array substrate with the first source electrode, the drain electrode, the gate electrode, and the gate line formed thereon; forming red, green, and blue color filters to cover a pixel region in which an image is displayed; forming a first protective layer on the array substrate with the color filters formed thereon, the protective layer having a first contact hole and a second contact hole exposing the first source electrode and the drain electrode, respectively; forming a second source electrode and a second drain electrode electrically connected to the first source electrode and the first drain electrode through the first contact hole and the second contact hole, respectively, the second source electrode and the second drain electrode being formed of a third conductive layer on the first protective layer; forming a second protective layer on the array substrate with the second source electrode and the drain electrode formed thereon, the second protective layer including a third contact hole exposing the second drain electrode; forming a pixel electrode electrically connected to the second drain electrode through the third contact hole, the pixel electrode being formed of a fourth conductive layer on the second protective layer; forming a partition partitioning the pixel region on the array substrate with the pixel electrode formed thereon; forming a white organic light emitting layer on the array substrate with the partition formed thereon; and forming a common electrode on the organic light emitting layer.

The first conductive layer may be made of an opaque low resistance conductive material such as molybdenum, a molybdenum alloy such as molybdenum-titanium, chromium, tantalum, or titanium.

The active layer may be made of an amorphous zinc oxide semiconductor.

The second conductive layer may be formed to have a tri-layer structure by applying molybdenum-titanium, or the like, as a barrier layer to upper and lower portions of a low resistance conductive material such as copper, or the like, as a main wiring.

The first source electrode, the drain electrode, the gate electrode, and the gate line may be formed through the same masking process.

When the gate electrode and the gate line are formed, a first data pad line and a first gate pad line formed of the first conductive layer may be formed in a pad part of the array substrate.

When the first source electrode and the drain electrode are formed, a second data pad line and a second gate pad line may be formed of the second conductive layer on the first data pad line and the first gate pad line.

When the second protective layer is formed, the second protective layer, the first protective layer, and the interlayer insulating layer may be selectively patterned to form a fourth contact hole and a fifth contact hole, exposing the second data pad line and the second gate pad line, respectively, in the pad part of the array substrate.

When the pixel electrode is formed, a data pad electrode and a gate pad electrode electrically connected to the second data pad line and the second gate pad line through the fourth contact hole and the fifth contact hole may be formed in the pad part of the array substrate.

When the gate electrode and the gate line are formed, a first gate pad line formed of the first conductive layer may be formed in the pad part of the array substrate.

When the first source electrode and the drain electrode are formed, a second gate pad line formed of the second conductive layer may be formed on the first gate pad line.

When the second source electrode and the drain electrode are formed, a data pad line formed of the third conductive layer may be formed in the pad part of the array substrate.

When the second protective layer is formed, the second protective layer, the first protective layer, and the interlayer insulating layer may be selectively patterned to form a fourth contact hole and a fifth contact hole, exposing the data pad line and the second gate pad line, respectively, in the pad part of the array substrate.

When the pixel electrode is formed, a data pad electrode and a gate pad electrode electrically connected to the data pad line and the second gate pad line through the fourth contact hole and the fifth contact hole, respectively, may be formed in the pad part of the array substrate.

The color filters may be formed to cover the TFT region as well as the pixel region.

The method may further include: forming an overcoat layer to cover the pixel region in which the color filters are formed and the TFT region, after the color filters are formed.

The gate electrode may be formed to cover a lower portion of the active layer, and the second source electrode may be formed to extend to cover a channel region of the active layer from above.

The third conductive layer may be formed to have a dual-layer structure including a low resistance conductive material such as copper, or the like, as a main wiring and a molybdenum-titanium as an underlying barrier layer.

As described, in the case of the OLED display device in which an oxide-based semiconductor is used as an active layer of a TFT and the fabrication method thereof according to embodiments of the present invention, since the active layer is formed at an upper portion of the gate electrode and the source electrode is patterned to completely cover the channel region of the active layer, light introduced from upper and lower portions of the active layer can be blocked. As a result, reliability of the oxide TFT can be improved.

Also, in the case of the OLED display device and the fabrication method thereof according to embodiments of the present invention, since an etch stopper is eliminated, the process is simplified and, since a gap is formed by forming the color filters or the overcoat layer in the interlayer superposed portion, parasitic capacitance can be minimized.

In this case, a high temperature thermal treatment is performed in advance during a first masking process to improve reliability of the oxide semiconductor, and by applying copper to form the gate wiring during a second masking process, the present invention can be applied to a large ultra definition (UD) display device, or the like.

The foregoing and other objects, features, aspects and advantages of the present invention will become more apparent from the following detailed description of the present invention when taken in conjunction with the accompanying drawings.

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a diagram illustrating a light emission principle of a related art organic light emitting diode (OLED) display device.

FIG. 2 is an equivalent circuit diagram of a pixel in a related art OLED display device.

FIG. 3 is a cross-sectional view schematically illustrating a structure of a related art white (W)-OLED display device.

FIG. 4 is a cross-sectional view schematically illustrating a structure of an OLED display device according to the first embodiment of the present invention.

FIGS. 5A to 5H are cross-sectional views sequentially illustrating a method for fabricating the OLED display device according to the first embodiment of the present invention illustrated in FIG. 4.

FIGS. 6A to 6F are cross-sectional views specifically illustrating a first masking process according to the first embodiment of the present invention illustrated in FIG. 5A.

FIG. 7 is a cross-sectional view schematically illustrating a structure of an OLED display device according to a second embodiment of the present invention.

FIGS. 8A to 8G are cross-sectional views sequentially illustrating a method for fabricating the OLED display device according to the second embodiment of the present invention illustrated in FIG. 7.

FIG. 9 is a cross-sectional view schematically illustrating a structure of an OLED display device according to a third embodiment of the present invention.

FIGS. 10A to 10G are cross-sectional views sequentially illustrating a method for fabricating the OLED display device according to the third embodiment of the present invention illustrated in FIG. 9.

#### DETAILED DESCRIPTION OF THE INVENTION

Hereinafter, an organic light emitting diode (OLED) display device and a method for fabricating the same according to embodiments of the present invention will be described in detail with reference to the accompanying drawings such that

they can be easily implemented by a person skilled in the art to which the present invention pertains. The present invention may be implemented in various forms without being limited to the embodiments described herein.

FIG. 4 is a cross-sectional view schematically illustrating a structure of an OLED display device according to the first embodiment of the present invention, in which a white organic light emitting diode (W-OLED) display device having a color filter on TFT (COT) structure in which color filters are formed on a lower array substrate is illustrated as an example.

Here, a single pixel including a pixel part, a data pad part, and a gate pad part is illustrated in the drawing, and N number of gate lines and M number of data lines cross to form M×N number of pixels in an actual OLED device, but for the description purpose, a single pixel is illustrated in the drawings.

As illustrated, in the W-OLED display device according to the first embodiment of the present invention, a gate line 116 including a gate electrode 121, a first data pad line 117p', and a first gate pad line 116p' are formed on an array substrate 110 made of an insulating material such as transparent glass, plastic, or the like.

The gate line 116 extends in a horizontal direction and transfers a gate signal. Here, the gate line 116 is connected to the first gate pad line 116p' for a connection to a different layer or an external driving circuit (not shown), and the gate electrode 121 may form a portion of the gate line 116. When a gate driving circuit generating a gate signal is integrated on the array substrate 110, the gate line 116 may extend to be directly connected to the gate driving circuit.

A gate insulating layer 115a formed of a silicon nitride layer SiNx, a silicon oxide layer SiO<sub>2</sub>, or the like, is formed on the gate line 116 including the gate electrode 121 and the predetermined first gate pad line 116p'.

An active layer 124 formed of an oxide semiconductor is formed on the gate insulating layer 115a, and in this case, the active layer 124 is positioned on the gate electrode 121 such that a lower portion thereof is completely covered by the gate electrode 121.

Here, in the first embodiment of the present invention, for example, the active layer 124 is formed of the oxide semiconductor, but the present invention is not limited thereto and the active layer 124 may be formed of hydrogenated amorphous silicon or polycrystalline silicon.

The oxide TFT employing the oxide semiconductor as the active layer 124 has high mobility and can be fabricated at a low temperature, thus advantageously being used in a transparent electronic circuit.

Also, unlike the existing amorphous silicon TFT, the oxide TFT is fabricated to have a structure without an n+ layer, advantageously simplifying the process.

For example, in the oxide TFT according to the first embodiment of the present invention, since the active layer 124 is formed by using an amorphous zinc oxide (ZnO) semiconductor, high mobility and constant current test conditions are satisfied and uniform characteristics are secured to be applicable to a large display.

Namely, the zinc oxide is a material capable of implementing three types of qualities such as conductivity, semiconductor characteristics, and resistivity according to the content of oxygen, and an oxide TFT employing an amorphous zinc oxide semiconductor material as the active layer 124 may be applied to a large display.

Also, recently, a huge interest and activities are concentrated on transparent electronic circuits, and here, since the oxide TFT employing the amorphous zinc oxide semiconduc-

tor material as the active layer 124 has high mobility and is fabricated at a low temperature, it is advantageously used in the transparent electronic circuits.

In particular, in the oxide TFT according to the first embodiment of the present invention, the active layer is formed of an a-IGZO containing heavy metal such as indium (In) and gallium (Ga) in the ZnO.

The a-IGZO semiconductor is so transparent as to allow a visible light to pass therethrough, and also, since the oxide TFT formed of the a-IGZO semiconductor has mobility of 1~100 cm<sup>2</sup>/Vs, exhibiting high mobility characteristics in comparison to an amorphous silicon TFT. Also, the a-IGZO semiconductor can be processed at a low temperature, it can produce a light, flexible product.

In addition, the oxide TFT formed of the a-IGZO semiconductor has characteristics similar to that of the amorphous silicon TFT, and thus, it has a component structure as simple as that of the amorphous silicon TFT and can be applied to a large flat panel display device.

A first source electrode 122' and a first drain electrode 123' are formed on a source region and a drain region of the active layer 124, respectively, and a second data pad line 117p and a second gate pad line 116p are formed on the first data pad line 117p' and the first gate pad line 116p', respectively.

Here, the first source electrode 122', the first drain electrode 123', the second data pad line 117p, and the second gate pad line 116p may use a low-resistance conductive material such as copper (Cu), or the like, as a main wiring, and in this case, they may be formed to have a tri-layer structure employing a molybdenum-titanium (MoTi), or the like, as a barrier layer to upper and lower portions thereof. However, the present invention is not limited thereto.

An interlayer insulating layer 115b formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the first source electrode 122', the first drain electrode 123', the second data pad line 117p, and the second gate pad line 116p.

Here, in the W-OLED display device according to the first embodiment of the present invention, red, green, and blue color filters 117 are formed on the interlayer insulating layer 115b of the pixel region in which an image is displayed.

An overcoat layer 115c made of photoacryl, or the like, is formed to cover the pixel region in which the color filters 117 are formed and the TFT region.

A first protective layer 115d formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the entire surface of the array substrate 110 with the overcoat layer 115 formed thereon.

In this case, certain regions of the first protective layer 115d are removed to form a first contact hole and a second contact hole exposing portions of the first source electrode 122' and the first drain electrode 123'.

A data line (not shown) is formed on the first protective layer 115d, and a second source electrode 122 and a second drain electrode 123 electrically connected to the first source electrode 122' and the first drain electrode 123' through the first contact hole and the second contact hole, respectively, are formed on the first protective layer 115d.

Here, the second source electrode 122 is formed to extend to completely cover a channel region of the active layer 124 from above, blocking light introduced from upper and lower portions of the active layer 124 together with the lower gate electrode 121, to improve reliability of the oxide TFT.

The data line transfers a data signal and extends in a vertical direction to cross the gate line 116. Here, the data line includes an end portion (not shown) having a large area for a connection between the second source electrode 122 extending toward the gate electrode 121 and a different layer or an

external driving circuit (not shown). When a data driving circuit generating a data signal is integrated on the array substrate **110**, the data line may extend to be directly connected to the data driving circuit.

Here, the data line, the second source electrode **122**, and the second drain electrode **123** may use a low-resistance conductive material such as copper (Cu), or the like, as a main wiring, and in this case, the data line, the second source electrode **122**, and the second drain electrode **123** may be formed to have a dual-layer structure employing MoTi, or the like, as a barrier layer thereunder. However, the present invention is not limited thereto.

A certain second protective layer **115e** is formed on the array substrate **110** with the data line, the second source electrode **122**, and the second drain electrode **123** formed thereon.

Here, a third contact hole exposing a portion of the second drain electrode **123** is formed in the second protective layer **115e** of the pixel part, and a fourth contact hole and a fifth contact hole exposing portions of the second data pad line **117p** and the second gate pad line **116p**, respectively, may be formed in the second protective layer **115e**, the first protective layer **115d**, and the interlayer insulating layer **115b** of the pad part.

A pixel electrode **118**, a data pad electrode **127p**, and a gate pad electrode **126p** are formed on the second protective layer **115e**. The pixel electrode **118**, the data pad electrode **127p**, and the gate pad electrode **126p** may be made of a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), or the like, or a reflective conductive material such as aluminum, silver, or an alloy thereof, or the like.

Here, the pixel electrode **118** as a positive electrode is electrically connected to the second drain electrode **123** through the third contact hole, and the data pad electrode **127p** and the gate pad electrode **126p** are electrically connected to the second data pad line **117p** and the second gate pad line **116p** through the fourth contact hole and the fifth contact hole, respectively.

Although not shown, a partition is formed on the array substrate with the pixel electrode **118** formed thereon. Here, the partition may surround the edges of the pixel electrode **118**, like a bank, to define an opening, and is made of an organic insulating material or an inorganic insulating material. The partition may be made of a photosensitizer including black pigment, and in this case, the partition serves as a light blocking member.

A white organic light emitting layer is formed on the array substrate **110** with the partition formed thereon.

Here, the organic light emitting layer may have a multi-layer structure including an auxiliary layer for enhancing luminous efficiency of the light emitting layer, in addition to the light emitting layer that emits light. The auxiliary layer includes an electron transport layer and a hole transport layer for balancing electrons and holes and an electron injection layer and a hole injection layer for strengthening injection of electrons and holes, and the like.

A common electrode as a negative electrode is formed on the inorganic light emitting layer. Here, the common electrode receives a common voltage and may be made of a reflective conductive material including calcium (Ca), barium (Ba), magnesium (Mg), aluminum (Al), silver (Ag), and the like, or a transparent conductive material such as ITO, IZO, or the like.

In the W-OLED display device according to the first embodiment of the present invention configured as described above, the second source electrode **122** and the second drain electrode **123** connected to the gate electrode **121** connected

to the gate line **116** and the data line form a switching TFT together with the active layer **124**. Although not shown, a driving gate electrode connected to the second electrode **123**, the driving source electrode connected to a driving voltage line, and the driving drain electrode connected to the pixel electrode **118** constitute a driving TFT together with the driving active layer.

Also, the pixel electrode **118**, the organic light emitting layer, and the common electrode may form an organic light emitting diode, and a storage electrode and the driving voltage line that overlap with each other constitute a storage capacitor.

As described above, in the W-OLED display device according to the first embodiment of the present invention, the active layer **124** is formed above the gate electrode **121** and the second source electrode **122** is formed to completely cover the channel region of the active layer **124**, thereby blocking light introduced from upper and lower sides of the active layer **124**. As a result, reliability of the oxide TFT can be improved.

Also, in the W-OLED display device according to the first embodiment of the present invention, since an etch stopper is deleted while forming the active layer **124** by using an oxide semiconductor, the process is simplified, and since the overcoat layer **115c** is formed in the interlayer superposition portion to form a gap, parasitic capacitance can be minimized.

In this case, a high temperature heat treatment is performed in advance during a first masking process to improve reliability of the oxide semiconductor, and copper is applied as a gate wiring during a second masking process to obtain an effect of being applied to a large ultra definition (UD) display device, or the like.

Also, since the etch stopper is deleted and there is no need to additionally apply a mask for a gate contact for connecting the gate electrode of the driving TFT and the second drain electrode **123** of the switching TFT, the process is simplified. This will be described in detail through a method for fabricating a W-OLED display device according to the first embodiment of the present invention.

FIGS. **5A** to **5H** are cross-sectional views sequentially illustrating a method for fabricating the OLED display device according to the first embodiment of the present invention illustrated in FIG. **4**, in which a method for fabricating an array substrate with respect to a single pixel including a pixel part, a data pad part, and a gate pad part is illustrated for the description purpose.

As illustrated in FIG. **5A**, the first conductive layer **130**, the gate insulating layer **115a**, and the active layer **124** are formed on the array substrate **110** made of an insulating material such as transparent glass, plastic, or the like.

Here, an oxide semiconductor is applied to the TFT according to an embodiment of the present invention is available for a low temperature deposition (or low temperature evaporation), so a substrate applicable to a low temperature process, such as a plastic substrate, soda lime glass, or the like, can be used. Also, since the oxide semiconductor exhibits amorphous characteristics, a substrate for a large display may be used.

The first conductive layer **130**, the gate insulating layer **115a**, and the active layer **124** are formed by depositing the first conductive layer **130**, an insulating layer, and an oxide semiconductor on the entire surface of the array substrate **110** and selectively patterning them through a photolithography process (a first masking process).

In this case, the first masking process may be performed by using a half-tone mask or a slit mask (mentioning of the

half-tone mask will also include the slit mask, hereinafter), and this will be described in detail with reference to the accompanying drawings.

FIGS. 6A to 6F are cross-sectional views specifically illustrating a first masking process according to the first embodiment of the present invention illustrated in FIG. 5A.

As illustrated in FIG. 6A, the first conductive layer **130**, the insulating layer **115**, and the semiconductor thin film **120** are deposited sequentially on the array substrate **110** made of an insulating material such as transparent glass, plastic, or the like.

Here, the first conductive layer **130** may be made of a low-resistance opaque conductive material such as molybdenum (Mo), a molybdenum alloy such as molybdenum-titanium (MoTi), chromium (Cr), tantalum (Ta), or titanium (Ti). However, the first conductive layer **130** may have a multi-layer structure including two conductive layers having different physical qualities.

Here, the insulating layer **115** may be formed as an inorganic insulating layer such as a silicon nitride layer or a silicon oxide layer, or a high dielectric oxide layer such as hafnium (Hf) oxide or aluminum oxide and may be formed by using chemical vapor deposition (CVD), plasma enhanced chemical vapor deposition (PECVD), or the like.

An oxide semiconductor including amorphous zinc oxide semiconductor may be used as the semiconductor thin film **120**.

Here, the amorphous zinc oxide semiconductor, in particular, a-IGZO semiconductor may be formed according to a sputtering method by using a composite target of a gallium oxide ( $\text{Ga}_2\text{O}_3$ ), an indium oxide ( $\text{In}_2\text{O}_3$ ), and a zinc oxide (ZnO), and besides, a chemical deposition method such as CVD or atomic layer deposition (ALD), or the like, may also be used.

As described above, the oxide TFT employing the oxide semiconductor as an active layer has high mobility and can be fabricated at a low temperature, so it may be used in a transparent electronic circuit.

Also, unlike the existing amorphous silicon TFT, the oxide TFT is fabricated to have a structure without an n+ layer, simplifying the process.

In the oxide TFT according to the first embodiment of the present invention, for example, since the active layer is formed by using an amorphous zinc oxide semiconductor, high mobility and constant current test conditions are satisfied, and since uniform characteristics are secured, the oxide TFT can be applied to a large display. In particular, in the oxide TFT according to the first embodiment of the present invention, the active layer may be formed with a-IGZO semiconductor containing heavy metal such as indium and gallium in ZnO.

After the semiconductor thin film **120** formed of a-IGZO semiconductor is deposited, a heat treatment is performed thereon at a temperature of 400° C. or higher in order to improve reliability of the oxide semiconductor.

Next, as illustrated in FIG. 6B, a photosensitive layer **160** made of a photosensitive material such as photoresist is formed on the entire surface of the array substrate **110** with the semiconductor thin film **120** deposited thereon, light is selectively irradiated to the photosensitive layer **160** through a half-tone mask **170** according to the first embodiment of the present invention.

Here, the half-tone mask **170** includes a first transmission region I allowing irradiated light to be entirely transmitted therethrough, a second transmission region II allowing only a portion of light to be transmitted therethrough and blocking a portion thereof, and a blocking region III blocking entire

irradiated light, and here, only light which has transmitted through the half-tone mask **170** may be irradiated to the photosensitive film **160**.

Subsequently, when the photosensitive film **160** which has been exposed through the half-tone mask **180** is developed, as shown in FIG. 6C, first and second photosensitive film patterns **160a** and **160b** having a certain thickness remain at regions where light was entirely blocked or partially blocked through the blocking region (III) and the second transmission region (II), and the photosensitive film at the transmission region (I) through which light was entirely transmitted has been completely removed to expose the surface of the third conductive film **130**.

At this time, the first photosensitive film pattern **160a** formed at the blocking region III is thicker than the second photosensitive film pattern **160b** formed through the second transmission region II. In addition, the photosensitive film at the region in which the light had entirely transmitted through the first transmission region I was completely removed. This is because positive photoresist was used, but without being limited thereto, negative photoresist may also be used in an embodiment of the present invention.

Subsequently, as shown in FIG. 6D, portions of the underlying insulating layer and the semiconductor thin film are selectively removed by using the first and second photosensitive film patterns **160a** and **160b** as masks to form a semiconductor thin film pattern **120'** formed of the oxide semiconductor in a state in which the gate insulating layer **115a** is interposed on the first conductive layer **130**. At this time, the gate insulating layer **115a** formed of the insulating layer is patterned to have the substantially same shape as that of the semiconductor thin film pattern **120'**.

Thereafter, an ashing process is performed to remove portions of the first to fourth and second photosensitive film patterns **160a** and **160b**. Then, as shown in FIG. 6E, the second photosensitive film pattern at the second transmission region II is completely removed.

In this case, the first photosensitive film pattern remains as a third photosensitive film pattern **160a'** with a thickness obtained by removing the thickness of the second photosensitive film pattern only on the region corresponding to the blocking region (III).

Thereafter, as illustrated in FIG. 6F, when a portion of the underlying semiconductor thin film is selectively removed by using the third photosensitive film pattern **160a'** as a mask, the active layer **124** formed of the semiconductor thin film is formed on the gate insulating layer **115a**.

Next, as illustrated in FIG. 5B, after a second conductive layer is deposited on the entire surface of the array substrate **110** with the active layer **124** formed thereon and selectively patterned through a photolithography process (a second masking process) to form the first source and drain electrodes **122'** and **123'** formed of the second conductive layer on certain regions, i.e., the source and drain regions, of the active layer **124**.

Also, the second conductive layer is selectively patterned through the second masking process to form the second data pad line **117p** and the second gate pad line **116p** formed of the second conductive layer in the pad part of the array substrate **110**.

As described above, the second conductive layer may have a tri-layer structure in which MoTi, or the like, is applied as upper and lower barrier layers of a low-resistance conductive material such as copper (Cu), or the like, as a main wiring. However, the present invention is not limited thereto.

Here, the first conductive layer is also selectively patterned through the second masking process, and accordingly, the

gate line **116** including the gate electrode **121** formed of the first conductive layer is formed in the pixel part of the array substrate **110** and the first data pad line **117p'** and the first gate pad line **116p'** formed of the first conductive layer are formed in the pad part of the array substrate **110**.

The gate line **116** transfers a gate signal and extends in a horizontal direction. In this case, for a connection with a different layer or an external driving circuit (not shown), the gate line **116** is connected to the first gate pad line **116p'**, and the gate electrode **121** forms a portion of the gate line **116**. When a gate driving circuit generating a gate signal is integrated on the array substrate **110**, the gate line **116** may extend to be directly connected to the gate driving circuit.

Here, the active layer **124** is positioned on the gate electrode **121** such that a lower portion thereof is completely covered by the gate electrode **121**. The second data pad line **117p** and the second gate pad line **116p** are positioned on the first data pad line **117p'** and the first gate pad line **116p'**, respectively.

In this manner, in an embodiment of the present invention, a high temperature thermal treatment is performed on the active layer **124** in advance during the first masking process to improve reliability of the oxide TFT, and since the gate wiring (i.e., the second data pad line **117p** and the second gate pad line **116p**) is made of copper during the second masking process, the oxide TFT can be applied to a large ultra-definition display device, or the like.

Next, as illustrated in FIG. 5C, the interlayer insulating layer **115b** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the first source electrode **122'**, the first drain electrode **123'**, the second data pad line **117p**, and the second gate pad line **116p**.

Also, red, green, and blue color filters **117** are formed on the interlayer insulating layer **115b** of the pixel region in which an image is displayed through a photolithography process three times (third masking process to fifth masking process).

Thereafter, as illustrated in FIG. 5D, the overcoat layer **115c** made of photoacryl, or the like, is formed to cover the pixel region in which the color filters **117** are formed and the TFT region through a photolithography process (a sixth masking process).

And then, as illustrated in FIG. 5E, the first protective layer **115d** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the entire surface of the array substrate **110** with the overcoat layer **115c** formed thereon.

Thereafter, the first protective layer **115d** is selectively patterned through a photolithography process (a seventh masking process) to form the first contact hole **140a** and the second contact hole **140b** exposing the first source electrode **122'** and the first drain electrode **123'**, respectively.

Thereafter, as illustrated in FIG. 5F, a third conductive layer is deposited on the first protective layer **115d** and selectively patterned through a photolithography process (an eighth masking process) to form a data line (not shown) formed of the third conductive layer in the pixel part of the array substrate **110** and form the second source electrode **122** and the second drain electrode **123** electrically connected to the first source electrode **122'** and the first drain electrode **123'** through the first contact hole **140a** and the second contact hole **140b**, respectively.

Here, since the second source electrode **122** is formed to extend to completely cover the channel region of the active layer **124** from above, it blocks light introduced from upper and lower sides of the active layer **124** together with the lower gate electrode **121**, thereby improving reliability of the oxide TFT.

As described above, the data line transfers a data signal and extends in the vertical direction to cross the gate line **116**. Here, the data line includes an end portion (not shown) having a large area for a connection between the second source electrode **122** extending toward the gate electrode **121** and a different layer or an external driving circuit (not shown). When a data driving circuit generating a data signal is integrated on the array substrate **110**, the data line may extend to be directly connected with the data driving circuit.

At this time, the third conductive layer may be formed to have a dual-layer structure in which MoTi, or the like, is applied as a lower barrier layer of a low-resistance conductive material such as copper (Cu), or the like, as a main wiring. However, the present invention is not limited thereto.

Next, as illustrated in FIG. 5G, a certain second protective layer **115e** is formed on the array substrate **110** with the data line, the second source electrode **122**, and the second drain electrode **123** formed thereon.

Thereafter, the second protective layer **115e** is selectively patterned through a photolithography process (a ninth masking process) to form a third contact hole **140c** exposing a portion of the second drain electrode **123** in the pixel part, and the second protective layer **115e**, the first protective layer **115d**, and the interlayer insulating layer **115b** are selectively patterned to form the fourth contact hole **140d** and the fifth contact hole **140e** exposing portions of the second data pad line **117p** and the second gate pad line **116p** in the pad part of the array substrate **110**.

Next, as illustrated in FIG. 5H, a fourth conductive layer is deposited on the entire surface of the array substrate with the second protective layer **115e** formed thereon, and selectively patterned through a photolithography process (a tenth masking process) to form the pixel electrode **118** formed of the fourth conductive layer.

At this time, the fourth conductive layer may be made of a transparent conductive material such as ITO, IZO, or the like, or a reflective conductive material such as aluminum, silver, or an alloy thereof, or the like.

Here, the pixel electrode **118** as an anode is electrically connected to the second drain electrode **123** through the third contact hole **140c**, and the data pad electrode **127p** and the gate pad electrode **126p** are electrically connected to the second data pad line **117p** and the second gate pad line **116p** through the fourth contact hole **140d** and the fifth contact hole **140e**, respectively.

Also, although not shown, a partition is formed on the array substrate **110** with the pixel electrode **118** formed thereon. Here, the partition surrounds the edges of the pixel electrode **118** to define an opening, and is made of an organic insulating material or an inorganic insulating material. Also, the partition may be made of a photosensitizer including black pigment, and in this case, the partition serves as a light blocking member.

A white organic light emitting layer is formed on the array substrate **110** with the partition formed thereon.

Here, the organic light emitting layer may have a multi-layer structure including an auxiliary layer for improving luminous efficiency of the light emitting layer, in addition to the light emitting layer. The auxiliary layer includes an electron transport layer and a hole transport layer for balancing electrons and holes and an electron injection layer and a hole injection layer for strengthening injection of electrons and holes, and the like.

A common electrode as a negative electrode is formed on the inorganic light emitting layer. Here, the common electrode receives a common voltage and may be made of a reflective conductive material including calcium (Ca),

barium (Ba), magnesium (Mg), aluminum (Al), silver (Ag), and the like, or a transparent conductive material such as ITO, IZO, or the like.

In the case of the present invention, since the second source electrode **122** is formed to extend to completely cover the channel region of the active layer **124** from above, it can block light introduced from upper and lower sides of the active layer **124** together with the lower gate electrode **121**, thus improving reliability of the oxide TFT. Also, the second source electrode **122** serves to prevent moisture (H<sub>2</sub>O) or hydrogen (H<sub>2</sub>) from being introduced into the active layer **124** from the outside.

Meanwhile, the data pad line may be formed of the third conductive layer constituting the data wiring (i.e., the second source electrode, the second drain electrode, and the data line).

Also, since the color filters are formed to extend to the TFT region, an overcoat layer may be eliminated, and this will be described in detail through a second embodiment of the present invention.

FIG. 7 is a cross-sectional view schematically illustrating a structure of an OLED display device according to a second embodiment of the present invention, in which a white organic light emitting diode (W-OLED) display device having a color filter on TFT (COT) structure in which color filters are formed on a lower array substrate is illustrated as an example.

Here, a single pixel including a pixel part, a data pad part, and a gate pad part is illustrated in the drawing, and N number of gate lines and M number of data lines cross to form M×N number of pixels in an actual OLED device, but for the description purpose, a single pixel is illustrated in the drawings.

As illustrated, in the W-OLED display device according to the second embodiment of the present invention, a gate line **216** including a gate electrode **221**, a first data pad line **217p'**, and a first gate pad line **216p'** are formed on an array substrate **210** made of an insulating material such as transparent glass, plastic, or the like.

As described above, the gate line **216** extends in a horizontal direction and transfers a gate signal. Here, the gate line **216** is connected to the first gate pad line **216p'** for a connection to a different layer or an external driving circuit (not shown), and the gate electrode **221** may form a portion of the gate line **216**. When a gate driving circuit generating a gate signal is integrated on the array substrate **210**, the gate line **216** may extend to be directly connected to the gate driving circuit.

A gate insulating layer **215a** formed of a silicon nitride layer SiNx, a silicon oxide layer SiO<sub>2</sub>, or the like, is formed on the gate line **216** including the gate electrode **221** and the predetermined first gate pad line **216p'**.

An active layer **224** formed of an oxide semiconductor is formed on the gate insulating layer **215a**, and in this case, the active layer **224** is positioned on the gate electrode **221** such that a lower portion thereof is completely covered by the gate electrode **221**.

Here, like the first embodiment of the present invention as described above, in the second embodiment of the present invention, for example, the active layer **224** is formed of the oxide semiconductor, but the present invention is not limited thereto and the active layer **224** may be formed of hydrogenated amorphous silicon or polycrystalline silicon.

Also, the oxide TFT employing the oxide semiconductor as the active layer **224** has high mobility and can be fabricated at a low temperature, thus advantageously being used in a transparent electronic circuit.

Also, unlike the existing amorphous silicon TFT, the oxide TFT is fabricated to have a structure without an n+ layer, advantageously simplifying the process.

For example, in the oxide TFT according to the second embodiment of the present invention, since the active layer **224** is formed by using a ZnO semiconductor, high mobility and constant current test conditions are satisfied and uniform characteristics are secured to be applicable to a large display.

In particular, in the oxide TFT according to the second embodiment of the present invention, the active layer is formed of an a-IGZO containing heavy metal such as indium (In) and gallium (Ga) in the ZnO.

A first source electrode **222'** and a first drain electrode **223'** are formed on a source region and a drain region of the active layer **224**, respectively, and a second data pad line **217p** and a second gate pad line **216p** are formed on the first data pad line **217p'** and the first gate pad line **216p'**, respectively.

Here, the first source electrode **222'**, the first drain electrode **223'**, the second data pad line **217p**, and the second gate pad line **216p** may use a low-resistance conductive material such as copper (Cu), or the like, as a main wiring, and in this case, they may be formed to have a tri-layer structure employing a molybdenum-titanium (MoTi), or the like, as a barrier layer to upper and lower portions thereof. However, the present invention is not limited thereto.

An interlayer insulating layer **215b** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the first source electrode **222'**, the first drain electrode **223'**, the second data pad line **217p**, and the second gate pad line **216p**.

Here, unlike the first embodiment of the present invention, in the W-OLED display device according to the second embodiment of the present invention, red, green, and blue color filters **217** are formed to cover the TFT region as well as the pixel region in which an image is displayed.

A first protective layer **215c** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the entire surface of the array substrate **210** on which the color filter **217** is formed.

In this case, certain regions of the first protective layer **215c** are removed to form a first contact hole and a second contact hole exposing portions of the first source electrode **222'** and the first drain electrode **223'**.

A data line (not shown) is formed on the first protective layer **215c**, and a second source electrode **222** and a second drain electrode **223** electrically connected to the first source electrode **222'** and the first drain electrode **223'** through the first contact hole and the second contact hole, respectively, are formed on the first protective layer **215c**.

Here, the second source electrode **222** is formed to extend to completely cover a channel region of the active layer **224** from above, blocking light introduced from upper and lower portions of the active layer **224** together with the lower gate electrode **221**, to improve reliability of the oxide TFT.

The data line transfers a data signal and extends in a vertical direction to cross the gate line **216**. Here, the data line includes an end portion (not shown) having a large area for a connection between the second source electrode **222** extending toward the gate electrode **221** and a different layer or an external driving circuit (not shown). When a data driving circuit generating a data signal is integrated on the array substrate **210**, the data line may extend to be directly connected to the data driving circuit.

Here, the data line, the second source electrode **222**, and the second drain electrode **223** may use a low-resistance conductive material such as copper (Cu), or the like, as a main wiring, and in this case, the data line, the second source electrode **222**, and the second drain electrode **223** may be

formed to have a dual-layer structure employing MoTi, or the like, as a barrier layer thereunder. However, the present invention is not limited thereto.

A certain second protective layer **215d** is formed on the array substrate **210** with the data line, the second source electrode **222**, and the second drain electrode **223** formed thereon.

Here, a third contact hole exposing a portion of the second drain electrode **223** is formed in the second protective layer **215d** of the pixel part, and a fourth contact hole and a fifth contact hole exposing portions of the second data pad line **217p** and the second gate pad line **216p**, respectively, may be formed in the second protective layer **215d**, the first protective layer **215c**, and the interlayer insulating layer **215b** of the pad part.

A pixel electrode **218**, a data pad electrode **227p**, and a gate pad electrode **226p** are formed on the second protective layer **215e**. The pixel electrode **218**, the data pad electrode **227p**, and the gate pad electrode **226p** may be made of a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), or the like, or a reflective conductive material such as aluminum, silver, or an alloy thereof, or the like.

Here, the pixel electrode **218** as a positive electrode is electrically connected to the second drain electrode **223** through the third contact hole, and the data pad electrode **227p** and the gate pad electrode **226p** are electrically connected to the second data pad line **217p** and the second gate pad line **216p** through the fourth contact hole and the fifth contact hole, respectively.

Although not shown, a partition is formed on the array substrate with the pixel electrode **218** formed thereon.

A white organic light emitting layer is formed on the array substrate **210** with the partition formed thereon.

A common electrode as a negative electrode is formed on the inorganic light emitting layer. Here, the common electrode receives a common voltage and may be made of a reflective conductive material including calcium (Ca), barium (Ba), magnesium (Mg), aluminum (Al), silver (Ag), and the like, or a transparent conductive material such as ITO, IZO, or the like.

In the W-OLED display device according to the second embodiment of the present invention configured as described above, the second source electrode **222** and the second drain electrode **223** connected to the gate electrode **221** connected to the gate line **216** and the data line form a switching TFT together with the active layer **224**. Although not shown, a driving gate electrode connected to the second electrode **223**, the driving source electrode connected to a driving voltage line, and the driving drain electrode connected to the pixel electrode **218** constitute a driving TFT together with the driving active layer.

Also, the pixel electrode **218**, the organic light emitting layer, and the common electrode may form an organic light emitting diode, and a storage electrode and the driving voltage line that overlap with each other constitute a storage capacitor.

As described above, in the W-OLED display device according to the second embodiment of the present invention, the active layer **224** is formed above the gate electrode **221** and the second source electrode **222** is formed to completely cover the channel region of the active layer **224**, thereby blocking light introduced from upper and lower sides of the active layer **224**. As a result, reliability of the oxide TFT can be improved.

Also, in the W-OLED display device according to the second embodiment of the present invention, since an etch stopper is deleted while forming the active layer **224** by using an

oxide semiconductor, the process is simplified, and since the overcoat layer, i.e., the first protective layer **215c** is formed in the interlayer superposition portion to form a gap, parasitic capacitance can be minimized.

In this case, a high temperature heat treatment is performed in advance during a first masking process to improve reliability of the oxide semiconductor, and copper is applied as a gate wiring during a second masking process to obtain an effect of being applied to a large ultra definition (UD) display device, or the like.

Also, since the etch stopper is deleted and there is no need to additionally apply a mask for a gate contact for connecting the gate electrode of the driving TFT and the second drain electrode **223** of the switching TFT, the process is simplified by omitting an overcoat layer. This will be described in detail through a method for fabricating a W-OLED display device according to the second embodiment of the present invention.

FIGS. **8A** to **8G** are cross-sectional views sequentially illustrating a method for fabricating the OLED display device according to the second embodiment of the present invention illustrated in FIG. **7**, in which a method for fabricating an array substrate with respect to a single pixel including a pixel part, a data pad part, and a gate pad part is illustrated for the description purpose.

As illustrated in FIG. **8A**, the first conductive layer **230**, the gate insulating layer **215a**, and the active layer **224** are formed on the array substrate **210** made of an insulating material such as transparent glass, plastic, or the like.

Here, an oxide semiconductor is applied to the TFT according to an embodiment of the present invention is available for a low temperature deposition (or low temperature evaporation), so a substrate applicable to a low temperature process, such as a plastic substrate, soda lime glass, or the like, can be used. Also, since the oxide semiconductor exhibits amorphous characteristics, a substrate for a large display may be used.

The first conductive layer **230**, the gate insulating layer **215a**, and the active layer **224** are formed by depositing the first conductive layer **230**, an insulating layer, and an oxide semiconductor on the entire surface of the array substrate **210** and selectively patterning them through a photolithography process (a first masking process).

In this case, the first masking process may be performed by using a half-tone mask in the same manner as that of the first embodiment described above.

Here, the first conductive layer **230** may be made of a low-resistance opaque conductive material such as molybdenum (Mo), a molybdenum alloy such as molybdenum-titanium (MoTi), chromium (Cr), tantalum (Ta), or titanium (Ti). However, the first conductive layer **230** may have a multi-layer structure including two conductive layers having different physical qualities.

Here, the insulating layer **215** may be formed as an inorganic insulating layer such as a silicon nitride layer or a silicon oxide layer, or a high dielectric oxide layer such as hafnium (Hf) oxide or aluminum oxide.

An oxide semiconductor including ZnO semiconductor may be used as the semiconductor thin film **220**.

In the oxide TFT according to the second embodiment of the present invention, for example, since the active layer is formed by using ZnO semiconductor, high mobility and constant current test conditions are satisfied, and since uniform characteristics are secured, the oxide TFT can be applied to a large display. In particular, in the oxide TFT according to the second embodiment of the present invention, the active layer may be formed with a-IGZO semiconductor containing heavy metal such as indium and gallium in ZnO.

After the semiconductor thin film **220** formed of a-IGZO semiconductor is deposited, a heat treatment is performed thereon at a temperature of 400° C. or higher in order to improve reliability of the oxide semiconductor.

Next, as illustrated in FIG. 8B, after a second conductive layer is deposited on the entire surface of the array substrate **210** with the active layer **224** formed thereon and selectively patterned through a photolithography process (a second masking process) to form the first source and drain electrodes **222'** and **223'** formed of the second conductive layer on certain regions, i.e., the source and drain regions, of the active layer **224**.

Also, the second conductive layer is selectively patterned through the second masking process to form the second data pad line **217p** and the second gate pad line **216p** formed of the second conductive layer in the pad part of the array substrate **210**.

As described above, the second conductive layer may have a tri-layer structure in which MoTi, or the like, is applied as upper and lower barrier layers of a low-resistance conductive material such as copper (Cu), or the like, as a main wiring. However, the present invention is not limited thereto.

Here, the first conductive layer is also selectively patterned through the second masking process, and accordingly, the gate line **216** including the gate electrode **221** formed of the first conductive layer is formed in the pixel part of the array substrate **210** and the first data pad line **217p'** and the first gate pad line **216p'** formed of the first conductive layer are formed in the pad part of the array substrate **210**.

As described above, the gate line **216** transfers a gate signal and extends in a horizontal direction. In this case, for a connection with a different layer or an external driving circuit (not shown), the gate line **216** is connected to the first gate pad line **216p'**, and the gate electrode **221** forms a portion of the gate line **216**. When a gate driving circuit generating a gate signal is integrated on the array substrate **210**, the gate line **216** may extend to be directly connected to the gate driving circuit.

Here, the active layer **224** is positioned on the gate electrode **221** such that a lower portion thereof is completely covered by the gate electrode **221**. The second data pad line **217p** and the second gate pad line **216p** are positioned on the first data pad line **217p'** and the first gate pad line **216p'**, respectively.

In this manner, in an embodiment of the present invention, a high temperature thermal treatment is performed on the active layer **224** in advance during the first masking process to improve reliability of the oxide TFT, and since the gate wiring (i.e., the second data pad line **217p** and the second gate pad line **216p**) is made of copper during the second masking process, the oxide TFT can be applied to a large ultra-definition display device, or the like.

Next, as illustrated in FIG. 8C, the interlayer insulating layer **215b** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the first source electrode **222'**, the first drain electrode **223'**, the second data pad line **217p**, and the second gate pad line **216p**.

Also, red, green, and blue color filters **217** are formed on the interlayer insulating layer **215b** of the pixel region in which an image is displayed through a photolithography process three times (third masking process to fifth masking process).

As illustrated in FIG. 8D, the first protective layer **215c** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the entire surface of the array substrate **210** with the color filters **217** formed thereon.

Thereafter, the first protective layer **215c** is selectively patterned through a photolithography process (a sixth masking process) to form the first contact hole **240a** and the second contact hole **240b** exposing the first source electrode **222'** and the first drain electrode **223'**, respectively.

Thereafter, as illustrated in FIG. 8E, a third conductive layer is deposited on the first protective layer **215c** and selectively patterned through a photolithography process (a seventh masking process) to form a data line (not shown) formed of the third conductive layer in the pixel part of the array substrate **210** and form the second source electrode **222** and the second drain electrode **223** electrically connected to the first source electrode **222'** and the first drain electrode **223'** through the first contact hole **240a** and the second contact hole **240b**, respectively.

Here, since the second source electrode **222** is formed to extend to completely cover the channel region of the active layer **224** from above, it blocks light introduced from upper and lower sides of the active layer **224** together with the lower gate electrode **221**, thereby improving reliability of the oxide TFT.

As described above, the data line transfers a data signal and extends in the vertical direction to cross the gate line **216**. Here, the data line includes an end portion (not shown) having a large area for a connection between the second source electrode **222** extending toward the gate electrode **221** and a different layer or an external driving circuit (not shown). When a data driving circuit generating a data signal is integrated on the array substrate **210**, the data line may extend to be directly connected with the data driving circuit.

At this time, the third conductive layer may be formed to have a dual-layer structure in which MoTi, or the like, is applied as a lower barrier layer of a low-resistance conductive material such as copper (Cu), or the like, as a main wiring. However, the present invention is not limited thereto.

Next, as illustrated in FIG. 8F, a certain second protective layer **215e** is formed on the array substrate **210** with the data line, the second source electrode **222**, and the second drain electrode **223** formed thereon.

Thereafter, the second protective layer **215d** is selectively patterned through a photolithography process (a ninth masking process) to form a third contact hole **240c** exposing a portion of the second drain electrode **223** in the pixel part, and the second protective layer **215d**, the first protective layer **215c**, and the interlayer insulating layer **215b** are selectively patterned to form the fourth contact hole **240d** and the fifth contact hole **240e** exposing portions of the second data pad line **217p** and the second gate pad line **216p** in the pad part of the array substrate **210**.

Next, as illustrated in FIG. 8G, a fourth conductive layer is deposited on the entire surface of the array substrate with the second protective layer **215d** formed thereon, and selectively patterned through a photolithography process (a tenth masking process) to form the pixel electrode **218** formed of the fourth conductive layer.

At this time, the fourth conductive layer may be made of a transparent conductive material such as ITO, IZO, or the like, or a reflective conductive material such as aluminum, silver, or an alloy thereof, or the like.

Here, the pixel electrode **218** as an anode is electrically connected to the second drain electrode **223** through the third contact hole **240c**, and the data pad electrode **227p** and the gate pad electrode **226p** are electrically connected to the second data pad line **217p** and the second gate pad line **216p** through the fourth contact hole **240d** and the fifth contact hole **240e**, respectively.

Also, although not shown, a partition is formed on the array substrate **210** with the pixel electrode **218** formed thereon.

A white organic light emitting layer is formed on the array substrate **210** with the partition formed thereon.

A common electrode as a negative electrode is formed on the inorganic light emitting layer. Here, the common electrode receives a common voltage and may be made of a reflective conductive material including calcium (Ca), barium (Ba), magnesium (Mg), aluminum (Al), silver (Ag), and the like, or a transparent conductive material such as ITO, IZO, or the like.

In the case of the present invention, since the second source electrode **222** is formed to extend to completely cover the channel region of the active layer **224** from above, it can block light introduced from upper and lower sides of the active layer **224** together with the lower gate electrode **221**, thus improving reliability of the oxide TFT. Also, the second source electrode **222** serves to prevent moisture (H<sub>2</sub>O) or hydrogen (H<sub>2</sub>) from being introduced into the active layer **224** from the outside.

Meanwhile, as mentioned above, the data pad line may be formed of the third conductive layer constituting the data wiring (i.e., the second source electrode, the second drain electrode, and the data line), and this will be described in detail through a third embodiment of the present invention.

FIG. 9 is a cross-sectional view schematically illustrating a structure of an OLED display device according to a third embodiment of the present invention, in which a white organic light emitting diode (W-OLED) display device having a color filter on TFT (COT) structure in which color filters are formed on a lower array substrate is illustrated as an example.

Here, a single pixel including a pixel part, a data pad part, and a gate pad part is illustrated in the drawing, and N number of gate lines and M number of data lines cross to form M×N number of pixels in an actual OLED device, but for the description purpose, a single pixel is illustrated in the drawings.

As illustrated, in the W-OLED display device according to the third embodiment of the present invention, a gate line **316** including a gate electrode **321**, and a first gate pad line **316p'** are formed on an array substrate **310** made of an insulating material such as transparent glass, plastic, or the like.

A gate insulating layer **315a** formed of a silicon nitride layer SiN<sub>x</sub>, a silicon oxide layer SiO<sub>2</sub>, or the like, is formed on the gate line **316** including the gate electrode **321** and the predetermined first gate pad line **316p'**.

An active layer **324** formed of an oxide semiconductor is formed on the gate insulating layer **315a**, and in this case, the active layer **324** is positioned on the gate electrode **321** such that a lower portion thereof is completely covered by the gate electrode **321**.

Here, like the first and second embodiments of the present invention as described above, in the third embodiment of the present invention, for example, the active layer **324** is formed of the oxide semiconductor, but the present invention is not limited thereto and the active layer **324** may be formed of hydrogenated amorphous silicon or polycrystalline silicon.

For example, in the oxide TFT according to the third embodiment of the present invention, since the active layer **324** is formed by using an (ZnO) semiconductor, high mobility and constant current test conditions are satisfied and uniform characteristics are secured to be applicable to a large display.

In particular, in the oxide TFT according to the third embodiment of the present invention, the active layer is

formed of an a-IGZO containing heavy metal such as indium (In) and gallium (Ga) in the ZnO.

A first source electrode **322'** and a first drain electrode **323'** are formed on a source region and a drain region of the active layer **324**, respectively, and a second gate pad line **316p** is formed on the first gate pad line **316p'**.

Here, the first source electrode **322'**, the first drain electrode **323'**, and the second gate pad line **316p** may use a low-resistance conductive material such as copper (Cu), or the like, as a main wiring, and in this case, they may be formed to have a tri-layer structure employing a molybdenum-titanium (MoTi), or the like, as a barrier layer to upper and lower portions thereof. However, the present invention is not limited thereto.

An interlayer insulating layer **315b** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the first source electrode **322'**, the first drain electrode **323'**, and the second gate pad line **316p**.

Here, unlike the first embodiment of the present invention, in the W-OLED display device according to the third embodiment of the present invention, red, green, and blue color filters **317** are formed to cover the TFT region as well as the pixel region in which an image is displayed.

A first protective layer **315c** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the entire surface of the array substrate **310** on which the color filter **317** is formed.

In this case, certain regions of the first protective layer **315c** are removed to form a first contact hole and a second contact hole exposing portions of the first source electrode **322'** and the first drain electrode **323'**.

A data line (not shown) is formed on the first protective layer **315c**, and a second source electrode **322** and a second drain electrode **323** electrically connected to the first source electrode **322'** and the first drain electrode **323'** through the first contact hole and the second contact hole, respectively, are formed on the first protective layer **315c**. Here, in the case of the third embodiment of the present invention, unlike the first and second embodiments of the present invention, the data pad line **317p** formed of the drain wiring (i.e., the data line, the second source electrode **322**, and the second drain electrode **323**) is formed in the data pad part.

Here, the second source electrode **322** is formed to extend to completely cover a channel region of the active layer **324** from above, blocking light introduced from upper and lower portions of the active layer **324** together with the lower gate electrode **321**, to improve reliability of the oxide TFT.

Here, the data line, the second source and drain electrodes **322** and **323**, and the data pad line **317p** may use a low-resistance conductive material such as copper (Cu), or the like, as a main wiring, and in this case, the data line, the second source electrode **322**, and the second drain electrode **323** may be formed to have a dual-layer structure employing MoTi, or the like, as a barrier layer thereunder. However, the present invention is not limited thereto.

A certain second protective layer **315d** is formed on the array substrate **310** with the data line, the second source and drain electrodes **322** and **323**, and the data pad line **317p** formed thereon.

Here, a third contact hole exposing a portion of the second drain electrode **323** is formed in the second protective layer **315d** of the pixel part, and a fourth contact hole and a fifth contact hole exposing portions of the second data pad line **317p** and the second gate pad line **316p**, respectively, may be formed in the second protective layer **315d**, the first protective layer **315c**, and the interlayer insulating layer **315b** of the pad part.

A pixel electrode **318**, a data pad electrode **327p**, and a gate pad electrode **326p** are formed on the second protective layer **315e**. The pixel electrode **318**, the data pad electrode **327p**, and the gate pad electrode **326p** may be made of a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), or the like, or a reflective conductive material such as aluminum, silver, or an alloy thereof, or the like.

Here, the pixel electrode **318** as a positive electrode is electrically connected to the second drain electrode **323** through the third contact hole, and the data pad electrode **327p** and the gate pad electrode **326p** are electrically connected to the second data pad line **317p** and the second gate pad line **316p** through the fourth contact hole and the fifth contact hole, respectively.

Although not shown, a partition is formed on the array substrate **310** with the pixel electrode **318** formed thereon.

A white organic light emitting layer is formed on the array substrate **310** with the partition formed thereon.

A common electrode as a negative electrode is formed on the inorganic light emitting layer. Here, the common electrode receives a common voltage and may be made of a reflective conductive material including calcium (Ca), barium (Ba), magnesium (Mg), aluminum (Al), silver (Ag), and the like, or a transparent conductive material such as ITO, IZO, or the like.

A method for fabricating a W-OLED display device according to the third embodiment of the present invention will be described in detail with reference to the accompanying drawings.

FIGS. **10A** to **10G** are cross-sectional views sequentially illustrating a method for fabricating the OLED display device according to the third embodiment of the present invention illustrated in FIG. **9**, in which a method for fabricating an array substrate with respect to a single pixel including a pixel part, a data pad part, and a gate pad part is illustrated for the description purpose.

As illustrated in FIG. **10A**, the first conductive layer **330**, the gate insulating layer **315a**, and the active layer **324** are formed on the array substrate **310** made of an insulating material such as transparent glass, plastic, or the like.

Here, an oxide semiconductor is applied to the TFT according to an embodiment of the present invention is available for a low temperature deposition (or low temperature evaporation), so a substrate applicable to a low temperature process, such as a plastic substrate, soda lime glass, or the like, can be used. Also, since the oxide semiconductor exhibits amorphous characteristics, a substrate for a large display may be used.

The first conductive layer **330**, the gate insulating layer **315a**, and the active layer **324** are formed by depositing the first conductive layer **330**, an insulating layer, and an oxide semiconductor on the entire surface of the array substrate **310** and selectively patterning them through a photolithography process (a first masking process).

In this case, the first masking process may be performed by using a half-tone mask in the same manner as that of the first embodiment described above.

Here, the first conductive layer **330** may be made of a low-resistance opaque conductive material such as molybdenum (Mo), a molybdenum alloy such as molybdenum-titanium (MoTi), chromium (Cr), tantalum (Ta), or titanium (Ti). However, the first conductive layer **330** may have a multi-layer structure including two conductive layers having different physical qualities.

Here, the insulating layer **315** may be formed as an inorganic insulating layer such as a silicon nitride layer or a

silicon oxide layer, or a high dielectric oxide layer such as hafnium (Hf) oxide or aluminum oxide.

An oxide semiconductor including ZnO semiconductor may be used as the semiconductor thin film **320**.

In the oxide TFT according to the third embodiment of the present invention, for example, since the active layer is formed by using ZnO semiconductor, high mobility and constant current test conditions are satisfied, and since uniform characteristics are secured, the oxide TFT can be applied to a large display. In particular, in the oxide TFT according to the third embodiment of the present invention, the active layer may be formed with a-IGZO semiconductor containing heavy metal such as indium and gallium in ZnO.

After the semiconductor thin film **320** formed of a-IGZO semiconductor is deposited, a heat treatment is performed thereon at a temperature of 400° C. or higher in order to improve reliability of the oxide semiconductor.

Next, as illustrated in FIG. **10B**, after a second conductive layer is deposited on the entire surface of the array substrate **310** with the active layer **324** formed thereon and selectively patterned through a photolithography process (a second masking process) to form the first source and drain electrodes **322'** and **323'** formed of the second conductive layer on certain regions, i.e., the source and drain regions, of the active layer **324**.

Also, the second conductive layer is selectively patterned through the second masking process to form the second gate pad line **316p** formed of the second conductive layer in the gate pad part of the array substrate **310**.

As described above, the second conductive layer may have a tri-layer structure in which MoTi, or the like, is applied as upper and lower barrier layers of a low-resistance conductive material such as copper (Cu), or the like, as a main wiring. However, the present invention is not limited thereto.

Here, the first conductive layer is also selectively patterned through the second masking process, and accordingly, the gate line **316** including the gate electrode **321** formed of the first conductive layer is formed in the pixel part of the array substrate **310** and the first gate pad line **316p'** formed of the first conductive layer is formed in the gate pad part of the array substrate **310**.

Here, the active layer **324** is positioned on the gate electrode **321** such that a lower portion thereof is completely covered by the gate electrode **321**. The second gate pad line **316p** is positioned on the first gate pad line **316p'**.

In this manner, in an embodiment of the present invention, a high temperature thermal treatment is performed on the active layer **324** in advance during the first masking process to improve reliability of the oxide TFT, and since the gate wiring (i.e., the second gate pad line **316p**) is made of copper during the second masking process, the oxide TFT can be applied to a large ultra-definition display device, or the like.

Next, as illustrated in FIG. **10C**, the interlayer insulating layer **315b** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the first source electrode **322'**, the first drain electrode **323'**, and the second gate pad line **316p**.

Also, red, green, and blue color filters **317** are formed on the interlayer insulating layer **315b** of the pixel region in which an image is displayed through a photolithography process three times (third masking process to fifth masking process).

And then, as illustrated in FIG. **10D**, the first protective layer **315c** formed of a silicon nitride layer, a silicon oxide layer, or the like, is formed on the entire surface of the array substrate **310** with the color filters **317** formed thereon.

Thereafter, the first protective layer **315c** is selectively patterned through a photolithography process (a sixth masking process) to form the first contact hole **340a** and the second contact hole **340b** exposing the first source electrode **322'** and the first drain electrode **323'**, respectively.

Thereafter, as illustrated in FIG. 10E, a third conductive layer is deposited on the first protective layer **315c** and selectively patterned through a photolithography process (a seventh masking process) to form a data line (not shown) formed of the third conductive layer in the pixel part of the array substrate **310** and form the second source electrode **322** and the second drain electrode **323** electrically connected to the first source electrode **322'** and the first drain electrode **323'** through the first contact hole **340a** and the second contact hole **340b**, respectively.

Here, in the case of the third embodiment of the present invention, unlike the first and second embodiments of the present invention, the data pad line **317p** formed of the drain wiring (i.e., the data line, the second source electrode **322**, and the second drain electrode **323**) is formed in the data pad part through the seventh masking process.

Here, since the second source electrode **322** is formed to extend to completely cover the channel region of the active layer **324** from above, it blocks light introduced from upper and lower sides of the active layer **324** together with the lower gate electrode **321**, thereby improving reliability of the oxide TFT.

At this time, the third conductive layer may be formed to have a dual-layer structure in which MoTi, or the like, is applied as a lower barrier layer of a low-resistance conductive material such as copper (Cu), or the like, as a main wiring. However, the present invention is not limited thereto.

Next, as illustrated in FIG. 10F, a certain second protective layer **315e** is formed on the array substrate **310** with the data line, the second source and drain electrodes **322** and **323**, and the data pad line **317p** formed thereon.

Thereafter, the second protective layer **315d** is selectively patterned through a photolithography process (a ninth masking process) to form a third contact hole **340c** exposing a portion of the second drain electrode **323** in the pixel part, and the second protective layer **315d**, the first protective layer **315c**, and the interlayer insulating layer **315b** are selectively patterned to form the fourth contact hole **340d** and the fifth contact hole **340e** exposing portions of the second data pad line **317p** and the second gate pad line **316p** in the pad part of the array substrate **310**.

Next, as illustrated in FIG. 10G, a fourth conductive layer is deposited on the entire surface of the array substrate with the second protective layer **315d** formed thereon, and selectively patterned through a photolithography process (a tenth masking process) to form the pixel electrode **318** formed of the fourth conductive layer.

At this time, the fourth conductive layer may be made of a transparent conductive material such as ITO, IZO, or the like, or a reflective conductive material such as aluminum, silver, or an alloy thereof, or the like.

Here, the pixel electrode **318** as an anode is electrically connected to the second drain electrode **323** through the third contact hole **340c**, and the data pad electrode **327p** and the gate pad electrode **326p** are electrically connected to the second data pad line **317p** and the second gate pad line **316p** through the fourth contact hole **340d** and the fifth contact hole **340e**, respectively.

Also, although not shown, a partition is formed on the array substrate **310** with the pixel electrode **318** formed thereon.

A white organic light emitting layer is formed on the array substrate **310** with the partition formed thereon.

A common electrode as a negative electrode is formed on the inorganic light emitting layer. Here, the common electrode receives a common voltage and may be made of a reflective conductive material including calcium (Ca), barium (Ba), magnesium (Mg), aluminum (Al), silver (Ag), and the like, or a transparent conductive material such as ITO, IZO, or the like.

What is claimed is:

1. An organic light emitting diode (OLED) display device comprising:

a gate line including a gate electrode on an array substrate and comprised of a first conductive layer;

an active layer over the gate line with a gate insulating layer interposed therebetween and comprised of an amorphous zinc oxide semiconductor;

a first source electrode and a first drain electrode on a source region and a drain region of the active layer, respectively, and comprised of a second conductive layer;

an interlayer insulating layer over the array substrate with the first source electrode and the first drain electrode;

red, green, and blue color filters on the interlayer insulating layer and covering a pixel region in which an image is displayed;

a first protective layer over the array substrate with the color filters and including a first contact hole and a second contact hole exposing the first source electrode and the first drain electrode, respectively;

a second source electrode and a second drain electrode comprised of a third conductive layer on the first protective layer and electrically connected to the first source electrode and the first drain electrode through the first contact hole and the second contact hole, respectively;

a second protective layer over the array substrate with the second source electrode and the second drain electrode and having a third contact hole exposing the second drain electrode;

a pixel electrode comprised of a fourth conductive layer on the second protective layer and electrically connected to the second drain electrode through the third contact hole;

a partition over the array substrate with the pixel electrode and partitioning the pixel region;

an organic light emitting layer over the array substrate with the partition; and

a common electrode on the organic light emitting layer, wherein the gate electrode is located to cover a lower portion of the active layer and the second source electrode is extended to cover the channel region of the active layer.

2. The display device of claim 1, wherein the color filters are located to cover a TFT region as well as the pixel region.

3. The display device of claim 2, further comprising an overcoat layer covering the pixel region in which the color filters are located and the TFT region.

4. The display device of claim 3, wherein the first contact hole and the second contact hole penetrate the interlayer insulating layer, the color filters and the overcoat layer exposing the first source electrode and the first drain electrode, respectively.

5. The display device of claim 1, wherein the first conductive layer is an opaque low resistance conductive material selected from molybdenum, a molybdenum alloy, chromium, tantalum, or titanium.

6. The display device of claim 1, wherein the second conductive layer has a tri-layer structure comprised of molybde-

num-titanium as a barrier layer on upper and lower portions of a low resistance conductive material as a main wiring.

7. The display device of claim 1, further comprising:  
a first data pad line and a first gate pad line in a pad part of the array substrate and comprised of the first conductive layer. 5

8. The display device of claim 7, further comprising:  
a second data pad line and a second gate pad line on the first data pad line and the first gate pad line, respectively, and comprised of the second conductive layer. 10

9. The display device of claim 8, further comprising:  
a data pad electrode and a gate pad electrode electrically connected to the second data pad line and the second gate pad line, respectively, and comprised of the fourth conductive layer. 15

10. The display device of claim 1, further comprising:  
a first gate pad line and a second gate pad line in a pad part of the array substrate and comprised of the first conductive layer and the second conductive layer, respectively; and 20

a data pad line in a pad part of the array substrate and comprised of the third conductive layer.

11. The display device of claim 10, further comprising:  
a data pad electrode and a gate pad electrode electrically connected to the data pad line and the second gate pad line, respectively, and comprised of the fourth conductive layer. 25

\* \* \* \* \*

专利名称(译)	有机发光二极管显示装置及其制造方法		
公开(公告)号	<a href="#">US9379170</a>	公开(公告)日	2016-06-28
申请号	US14/920642	申请日	2015-10-22
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	CHO KISUL JEON JINCHAE		
发明人	CHO, KISUL JEON, JINCHAE		
IPC分类号	H01L27/15 H01J1/62 H01L27/32 H01L27/12 H01L51/00		
CPC分类号	H01L27/3272 H01L27/1288 H01L27/322 H01L27/3244 H01L51/0001		
代理机构(译)	桦木, STEWART, KOLASCH与桦木, LLP		
助理审查员(译)	古德温DAVID		
优先权	1020120087980 2012-08-10 KR		
其他公开文献	US20160043160A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

有机发光二极管 ( OLED ) 显示装置可包括包括栅电极的栅极线;栅极线上方的有源层, 栅极绝缘层插入其间并包括非晶氧化锌半导体;在第一源极和漏极上的绝缘层上的滤色器上方的第一保护层;第一保护层上的第二源极和漏极连接到第一源极和漏极;第二保护层, 具有第三接触孔;第二保护层上的像素电极, 通过第三接触孔连接到第二漏电极;划分像素区域的分区;和隔板上方的有机发光层。而且, 栅电极位于覆盖有源层的下部, 第二源电极延伸以覆盖有源层的沟道区。

