



US 20110240970A1

(19) United States

(12) Patent Application Publication  
PARK et al.

(10) Pub. No.: US 2011/0240970 A1  
(43) Pub. Date: Oct. 6, 2011

(54) ORGANIC LIGHT-EMITTING DISPLAY APPARATUS

(75) Inventors: Jin-Woo PARK, Yongin-city (KR); Myung-Jong JUNG, Yongin-city (KR); Tae- Min KANG, Yongin-city (KR); Sang-Woo PYO, Yongin-city (KR); Beom-Joon KIM, Yongin-city (KR); Hyo-Yeon KIM, Yongin-city (KR)

(73) Assignee: SAMSUNG MOBILE DISPLAY CO., LTD., Yongin-city (KR)

(21) Appl. No.: 13/069,039

(22) Filed: Mar. 22, 2011

(30) Foreign Application Priority Data

Mar. 31, 2010 (KR) ..... 10-2010-0029344


Publication Classification



(51) Int. Cl.  
*H01L 51/54* (2006.01)  
*H01L 51/52* (2006.01)  
*B82Y 99/00* (2011.01)



(52) U.S. Cl. ..... 257/40; 257/89; 257/E51.041;  
257/E51.022; 977/735

(57) ABSTRACT

An organic light-emitting display apparatus is disclosed. The organic light-emitting display apparatus includes a first sub-pixel, a second sub-pixel, and a third sub-pixel, where each of said first, second and third sub-pixels displays a different color, a substrate, a first electrode disposed on the substrate, a second electrode disposed on the first electrode, facing the first electrode, an organic emission layer disposed between the first electrode and the second electrode, including a first organic emission layer, a second organic emission layer, and a third organic emission layer, and an electron acceptor layer disposed between the first electrode and the second electrode configured to contact the organic emission layer, where the first organic emission layer is disposed in the first sub-pixel, the second organic emission layer is disposed in the second sub-pixel, and the third organic emission layer is commonly disposed over the first sub-pixel, the second sub-pixel, and the third sub-pixel, and where the electron acceptor layer is disposed between the first organic emission layer and the third organic emission layer in the first sub-pixel and between the second organic emission layer and the third organic emission layer in the second sub-pixel.



**FIG. 1****FIG. 2**

**FIG. 3****FIG. 4**

## ORGANIC LIGHT-EMITTING DISPLAY APPARATUS

### CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of Korean Patent Application No. 10-2010-0029344, filed on Mar. 31, 2010, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

### BACKGROUND

#### [0002] 1. Field

[0003] The present disclosure relates to an organic light-emitting display apparatus that improves image quality and life.

#### [0004] 2. Description of the Related Technology

[0005] Recently, display apparatuses have been replaced by portable thin flat panel display apparatuses. An organic or inorganic light-emitting display apparatus, a type of thin flat panel display apparatus, is a self-emission display apparatus. An organic or inorganic light-emitting display apparatus generally has a wide view angle, excellent contrast, and quick response speeds. Also, an organic light emitting display apparatus, in which a light emitting layer is formed of an organic material, generally has excellent luminance, driving voltage, and response speed, as compared to an inorganic light emitting display apparatus, and displays multi-colors.

[0006] In an organic light-emitting display apparatus, an organic emission layer is typically interposed between a cathode and an anode, and, when a voltage is applied to the cathode and the anode, the organic emission layer connected to the cathode and the anode emits visible light.

[0007] The organic emission layer typically includes an organic emission layer emitting different colors of visible light such as red, green, or blue. In the organic emission layer, holes and electrons are recombined, thereby emitting visible light. Surplus electrons that do not participate in the recombination typically move toward a hole injection layer (HIL), a hole transport layer (HTL) or a first electrode, thereby resulting in deterioration of light efficiency and life of an organic light-emitting display apparatus.

[0008] In a structure in which a blue organic emission layer is commonly used in all sub-pixels, the surplus electrons generate visible light in an undesirable organic emission layer, and thus color mixture occurs, thereby resulting in deterioration of image quality. Therefore, it is generally difficult to improve the image quality.

### SUMMARY OF CERTAIN INVENTIVE ASPECTS

[0009] One aspect is an organic light-emitting display apparatus including: a first sub-pixel, a second sub-pixel, and a third sub-pixel, where each of said first, second and third sub-pixels displays a different color, a substrate, a first electrode disposed on the substrate, a second electrode disposed on the first electrode, facing the first electrode, an organic emission layer disposed between the first electrode and the second electrode, including a first organic emission layer, a second organic emission layer, and a third organic emission layer, and an electron acceptor layer disposed between the first electrode and the second electrode configured to contact the organic emission layer, where the first organic emission layer is disposed in the first sub-pixel, the second organic emission layer is disposed in the second sub-pixel, and the

third organic emission layer is commonly disposed over the first sub-pixel, the second sub-pixel, and the third sub-pixel, and where the electron acceptor layer is disposed between the first organic emission layer and the third organic emission layer in the first sub-pixel and between the second organic emission layer and the third organic emission layer in the second sub-pixel.

[0010] Another aspect is an organic light-emitting display apparatus including: a first sub-pixel, a second sub-pixel, and a third sub-pixel, where each of said first, second and third sub-pixels displays a different color, a first electrode, a second electrode disposed on the first electrode, facing the first electrode, an organic emission layer disposed between the first electrode and the second electrode, including a first organic emission sublayer, a second organic emission sublayer, and a third organic emission sublayer, an electron acceptor layer disposed between the first electrode and the second electrode configured to contact the organic emission layer, where the first organic emission sublayer is disposed in the first sub-pixel, the second organic emission sublayer is disposed in the second sub-pixel, and the third organic emission sublayer is commonly disposed over the first sub-pixel, the second sub-pixel, and the third sub-pixel, and where the electron acceptor layer is disposed between the first organic emission sublayer and the third organic emission sublayer in the first sub-pixel and between the second organic emission sublayer and the third organic emission sublayer in the second sub-pixel, and a buffer layer between the electron acceptor layer and the first organic emission sublayer, and between the electron acceptor layer and the second organic emission sublayer.

[0011] Another aspect is an organic light-emitting display apparatus, including: a first sub-pixel, which includes a first electrode, a third organic emission layer, an electron acceptor layer, a first organic emission layer, and a second electrode, a second sub-pixel, which includes another first electrode, said third organic emission layer, another electron acceptor layer, a second organic emission layer, and said second electrode, and a third sub-pixel, which includes yet another first electrode, said third organic emission layer, and said second electrode, where each of said first, second and third sub-pixels displays a different color.

### BRIEF DESCRIPTION OF THE DRAWINGS

[0012] The above and other features and advantages will become more apparent by describing in detail exemplary embodiments with reference to the attached drawings in which:

[0013] FIG. 1 is a schematic cross-sectional view of an embodiment of an organic light-emitting display apparatus;

[0014] FIG. 2 is a schematic cross-sectional view of another embodiment of an organic light-emitting display apparatus;

[0015] FIG. 3 is a schematic cross-sectional view of another embodiment of an organic light-emitting display apparatus; and

[0016] FIG. 4 is a graph illustrating the life of an embodiment of an organic light-emitting display apparatus.

### DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

[0017] FIG. 1 is a schematic cross-sectional view of an embodiment of an organic light-emitting display apparatus 100.

[0018] The organic light-emitting display apparatus **100** includes a first sub-pixel **SP1**, a second sub-pixel **SP2**, and a third sub-pixel **SP3**. The sub-pixels **SP1**, **SP2**, and **SP3** may be different in color. In one embodiment, the first sub-pixel **SP1** may be a red sub-pixel, the second sub-pixel **SP2** may be a green sub-pixel, and the third sub-pixel **SP3** may be a blue sub-pixel.

[0019] In the embodiment of FIG. 1, one first sub-pixel **SP1**, one second sub-pixel **SP2**, and one third sub-pixel **SP3** are illustrated. In other embodiments, the organic light-emitting display apparatus **100** may include a plurality of first sub-pixels **SP1**, a plurality of second sub-pixels **SP2**, and a plurality of third sub-pixels **SP3**.

[0020] The first sub-pixel **SP1** includes a first electrode **110**, a third organic emission layer **133**, an electron acceptor layer **125**, a first organic emission layer **131**, and a second electrode **150**. The second sub-pixel **SP2** includes a first electrode **110**, the third organic emission layer **133**, an electron acceptor layer **125**, a second organic emission layer **132**, and the second electrode **150**. The third sub-pixel **SP3** includes a first electrode **110**, the third organic emission layer **133**, and the second electrode **150**.

[0021] In some embodiments, a substrate **101** may be formed of a transparent glass consisting SiO<sub>2</sub> as a main component. In other embodiments, the substrate **101** may be formed of a transparent plastic material. The transparent plastic material may be an organic material selected from the insulating organic material group consisting of polyethersulfone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylenen napthalate (PEN), polyethyleneterephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide, polycarbonate (PC), cellulose triacetate (TAC), cellulose acetate propionate (CAP) and the like.

[0022] In yet other embodiments, the substrate **101** may be formed of a metal. In such embodiments, the substrate **101** may include at least one selected from the group consisting of carbon (C), steel (Fe), chrome (Cr), manganese (Mn), nickel (Ni), titanium (Ti), molybdenum (Mo), stainless steel (SUS), an invar alloy, an inconel alloy, a kovar alloy and the like. In other embodiments, the substrate **101** may be formed of metal foil.

[0023] A passivation layer (not shown) may be formed on the substrate **101** so as to prevent impurities from entering the substrate **101**. The passivation layer may be formed of SiO<sub>2</sub> and/or SiNx.

[0024] The first electrode **110** may be formed in a predetermined pattern by photolithography. In various embodiments, the first electrode **110** may be a reflective electrode or a transmissive electrode. In embodiments where the first electrode **110** is a reflective electrode, a reflective layer may be formed of one material selected from the group consisting of silver (Ag), magnesium (Mg), aluminum (Al), platinum (Pt), palladium (Pd), gold (Au), Ni, neodymium (Nd), iridium (Ir), Cr, lithium (Li), calcium (Ca), and the like, or a combination thereof. A material selected from ITO, IZO, ZnO or In<sub>2</sub>O<sub>3</sub> having a high work function may be disposed on the reflective layer, thereby forming the first electrode **110**.

[0025] In one embodiment, the first electrode **110** and the second electrode **150** are an anode and a cathode, respectively. In another embodiment, polarities thereof may be reversed.

[0026] Still referring to FIG. 1, a hole injection layer **121** and a hole transport layer **122** are formed on the first electrode

**110**. In other embodiments, the hole injection layer **121** and the hole transport layer **122** may not be formed, or only one of them may be formed.

[0027] An organic emission layer **130** is formed on the hole transport layer **122**. The organic emission layer **130** includes a first organic emission layer **131**, a second organic emission layer **132**, and a third organic emission layer **133**.

[0028] In the embodiment shown in FIG. 1, the third organic emission layer **133** is formed on the hole transport layer **122** across all of the first sub-pixel **SP1**, the second sub-pixel **SP2**, and the third sub-pixel **SP3**.

[0029] In the embodiment shown, the third organic emission layer **133** emits blue visible light and may include oxadiazole dimer dyes (Bis-DAPDXP), spiro compounds (Spiro-DPVBi, Spiro-6P), triarylamine compounds, bis(styryl) amine (DPVBi, DSA), 4,4'-bis(9-ethyl-3-vinylene)-1,1'-biphenyl (BCzVBi), perylene, 2,5,8,11-tetra-tert-butylperylene (TPBe), 9H-carbazole-3,3'-1,4-phenylene-di-2,1-ethene-diyl)bis[9-ethyl-(9C)] (BCzVB), 4,4-bis[4-(di-p-tolylamino)styryl]biphenyl (DPAVBi), 4-(di-p-tolylamino)-4'-(di-p-tolylamino)styryl]stilbene (DPAVB), 4,4'-bis[4-(diphenylamino)styryl]biphenyl (BDAVBi), b is 3,5-difluoro-2-(2-pyridyl)phenyl-(2-carboxypyridyl)iridium III (FIrPic) that is a blue light-emitting material, or the like, and may also include a polymer light-emitting material such as a polyfluorene-based polymer a polyvinyl-based polymer, or the like.

[0030] Still referring to FIG. 1, in the first sub-pixel **SP1** and the second sub-pixel **SP2**, the electron acceptor layer **125** is disposed on the third organic emission layer **133**. The electron acceptor layer **125** may include any one selected from the group consisting of hexaazatriphenylene hexacarbonitrile (HAT-CN), MoO<sub>3</sub> and fullerene (C60). In one embodiment, the electron acceptor layer **125** may include 1,4,5,8,9,11-HAT-CN.

[0031] The electron acceptor layer **125** may trap surplus electrons remaining after electrons and holes are recombined.

[0032] In the first sub-pixel **SP1**, the first organic emission layer **131** is formed on the electron acceptor layer **125**. The first organic emission layer **131** may emit red visible light and may include tetraphenylnaphthalocene (rubrene), tris(1-phenylisoquinoline)iridium(III) (Ir(piq)<sub>3</sub>), bis(2-benz[b]thiophene-2-yl-pyridine)(acetylacetone)iridium(III) (Ir(btp)<sub>2</sub>(acac)), tris(dibenzoylmethan)phenanthroline europium(III) (Eu(dbm)<sub>3</sub>(phen)), tris[4,4'-di-tert-butyl-(2,2'-bipyridine)ruthenium(III) complex (Ru(dt-bpy)<sub>3</sub>\*2 (PF<sub>6</sub>)), DCM1, DCM2, Eu (thenoyltrifluoroacetone)3 (Eu (TTA)3), butyl-6-(1,1,7,7-tetramethyl julolidyl-9-enyl)-4H-pyran) (DCJTB), or the like, and may also include a polymer light-emitting material such as polyfluorene-based polymer, polyvinyl-based polymer or the like.

[0033] In the second sub-pixel **SP2**, the second organic emission layer **132** is formed on the electron acceptor layer **125**. The second organic emission layer **132** may include 3-(2-benzothiazolyl)-7-(diethylamino)coumarin (Coumarin 6 2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H,5H,11H-10-(2-benzothiazolyl)quinolizino-[9,9a,1gh]coumarin (C545T), N,N'-dimethyl-quinacridone (DMQA), or tris(2-phenylpyridine)iridium(III) (Ir(ppy)<sub>3</sub>) or the like, that is a green light-emitting material, and may also include a polymer light-emitting material such as polyfluorene-based polymer, polyvinyl-based polymer or the like.

[0034] In the embodiment of FIG. 1, an electron transport layer **141** and an electron injection layer **142** are disposed on

the organic emission layer 130 across all of the sub-pixels. In other embodiments, the electron transport layer 141 and the electron injection layer 142 may not be disposed, or one of them may be disposed.

[0035] The second electrode 150 is disposed on the electron injection layer 142. In various embodiments, the second electrode 150 may be a transmissive electrode or a reflective electrode. In embodiments where the second electrode 150 is a transmissive electrode, a metal having a small work function, such as Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca, and the like, or a combination thereof, is deposited on the electron injection layer 142, and an auxiliary electrode layer or a bus electrode line, which is formed of a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), ZnO, In<sub>2</sub>O<sub>3</sub>, or the like, may be formed on the metal.

[0036] In embodiments where the second electrode 150 is a reflective electrode, the second electrode 150 may be formed of a metal having a small work function such as Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca, or the like.

[0037] A sealing member (not shown) may be disposed on the second electrode 150 so as to face the substrate 101. The sealing member may be formed to protect the organic emission layer from external moisture and oxygen. The sealing member may be formed of a transparent material. In some embodiments, the sealing member may be formed of glass, plastic, or a stack structure including a plurality of layers formed of organic or inorganic materials.

[0038] In the embodiment of the organic light-emitting display apparatus 100 in FIG. 1, the electron acceptor layer 125 is disposed between the third organic emission layer 133 and the first organic emission layer 131 of the first sub-pixel SP1, and between the third organic emission layer 133 and the second organic emission layer 132 of the second sub-pixel SP2.

[0039] The electron acceptor layer 125 may prevent electrons injected through the second electrode 150 from passing through the first organic emission layer 131, the second organic emission layer 132, and the third organic emission layer 133 and from entering the hole transport layer 122 and the hole injection layer 121.

[0040] Electrons injected through the second electrode 150 in the first sub-pixel SP1 are recombined with holes in the first organic emission layer 131, and surplus electrons are trapped in the electron acceptor layer 125. The electron acceptor layer 125 prevents the surplus electrons from moving toward the third organic emission layer 133 and/or the hole transport layer 122. Electrons are recombined with holes in the second organic emission layer 132 of the second sub-pixel SP2, and surplus electrons are trapped in the electron acceptor layer 125. The electron acceptor layer 125 prevents the surplus electrons from moving toward the third organic emission layer 133 and/or the hole transport layer 122.

[0041] By trapping the surplus electrons in the electron acceptor layer 125, the surplus electrons are prevented from entering an undesired organic layer, for example, the third organic emission layer 133, the hole injection layer 121, or the hole transport layer 122, and the life of the organic light-emitting display apparatus 100 may thus be extended. Since the first organic emission layer 131 and the second organic emission layer 132 are closer to the second electrode 150 than the third organic emission layer 133, the life of the organic light-emitting display apparatus 100 may be reduced due to the surplus electrons, and thus the electron acceptor layer 125

may effectively prevent reduction of the life of the organic light-emitting display apparatus 100.

[0042] Electrons injected through the second electrode 150 in the first sub-pixel SP1 are recombined with holes in the first organic emission layer 131, and surplus electrons enter the third organic emission layer 133 and are recombined with holes in the third organic emission layer 133, thereby emitting blue visible light. Thus, visible light including blue visible light and red visible light may be emitted in the first sub-pixel SP1. Similarly, in the second sub-pixel SP2, surplus electrons are recombined with holes in the third organic emission layer 133, and thus mixed visible light, not a desirable green visible light, may be emitted in the second sub-pixel SP2.

[0043] The color mixture of the visible light may remarkably deteriorate image quality of the organic light-emitting display apparatus 100. However, the electron acceptor layer 125 is disposed between the first organic emission layer 131 and the third organic emission layer 133 and between the second organic emission layer 132 and the third organic emission layer 133, so as to trap surplus electrons, thereby preventing the color mixture of the visible light, and consequently the image quality of the organic light-emitting display apparatus 100 may be improved.

[0044] In addition, a distance between the first electrode 110 and the second electrode 150 is different in each sub-pixel, so that an optical path length of visible light generated from the organic emission layer 130 may be different in each sub-pixel, and thus a microcavity effect may be realized.

[0045] FIG. 2 is a schematic cross-sectional view of another embodiment of an organic light-emitting display apparatus 200.

[0046] The organic light-emitting display apparatus 200 includes a first sub-pixel SP1, a second sub-pixel SP2, and a third sub-pixel SP3. The first, second, and third sub-pixels SP1, SP2 and SP3 may be sub-pixels of different colors, and in one embodiment, the first sub-pixel SP1 may be red, the second sub-pixel SP2 may be green, and the third sub-pixel SP3 may be blue.

[0047] In the embodiment of FIG. 2, one first sub-pixel SP1, one second sub-pixel SP2, and one third sub-pixel SP3 are illustrated. In other embodiments, the organic light-emitting display apparatus 200 may include a plurality of first sub-pixels SP1, a plurality of second sub-pixels SP2, and a plurality of third sub-pixels SP3.

[0048] The first sub-pixel SP1 includes a first electrode 210, a third organic emission layer 233, an electron acceptor layer 225, a buffer layer 226, a first organic emission layer 231, and a second electrode 250. The second sub-pixel SP2 includes a first electrode 210, the third organic emission layer 233, an electron acceptor layer 225, a buffer layer 226, a second organic emission layer 232, and the second electrode 250. The third sub-pixel SP3 includes a first electrode 210, the third organic emission layer 233, and the second electrode 250.

[0049] The first electrode 210 is formed on a substrate 201. Components of the substrate 201 and the first electrode 210 may be the same as those of the above-described embodiment.

[0050] In some embodiments, a hole injection layer 221 and a hole transport layer 222 are formed on the first electrode 210. In other embodiments, the hole injection layer 221 and the hole transport layer 222 may not be formed, or one of them may be formed.

[0051] An organic emission layer 230 is formed on the hole transport layer 222. The organic emission layer 230 includes the first organic emission layer 231, the second organic emission layer 232 and the third organic emission layer 233.

[0052] The third organic emission layer 233 is formed on the hole transport layer 222 across all of the first sub-pixel SP1, the second sub-pixel SP2, and the third sub-pixel SP3.

[0053] The third organic emission layer 233 emits blue visible light and its components are the same as those of the above-described embodiment.

[0054] In the first sub-pixel SP1 and the second sub-pixel SP2, the buffer layer 226 and the electron acceptor layer 225 are disposed on the third organic emission layer 233. The buffer layer 226 is disposed between the first organic emission layer 231 and the electron acceptor layer 225.

[0055] The electron acceptor layer 225 may include any one selected from the group consisting of HAT-CN, MoO<sub>3</sub>, and C60. In one embodiment, the electron acceptor layer 225 may include 1,4,5,8,9,11-HAT-CN.

[0056] The buffer layer 226 includes a hole transport material or a hole injection material. The buffer layer 226 controls the amount of electrons trapped in the electron acceptor layer 225.

[0057] The first organic emission layer 231 is formed on the buffer layer 226 in the first sub-pixel SP1. The first organic emission layer 231 emits red visible light, and its components are the same as those of the above-described embodiment.

[0058] The second organic emission layer 232 is formed on the buffer layer 226 in the second sub-pixel SP2. The second organic emission layer 232 emits green visible light and its components are the same as those of the above-described embodiment.

[0059] In some embodiments, an electron transport layer 241 and an electron injection layer 242 are disposed on the organic emission layer 230 across all the sub-pixels. In other embodiments, the electron transport layer 241 and the electron injection layer 242 may not be disposed, or one of them may be disposed.

[0060] The second electrode 250 is disposed on the electron injection layer 242. A sealing member (not shown) may be disposed on the second electrode 250. The second electrode 250 and the sealing member are the same as those of the above-described embodiment, and thus a detailed description thereof will be omitted here.

[0061] In the embodiment of the organic light-emitting display apparatus 200 of FIG. 2, the electron acceptor layer 225 is disposed between the third organic emission layer 233 and the first organic emission layer 231 of the first sub-pixel SP1, and between the third organic emission layer 233 and the second organic emission layer 232 of the second sub-pixel SP2. Surplus electrons are trapped in the electron acceptor layer 225, and consequently, the life of the organic light-emitting display apparatus 200 is extended. Also, in the first sub-pixel SP1 and the second sub-pixel SP2, the electron acceptor layer 225 prevents surplus electrons from recombining with holes in the third organic emission layer 233 and thus prevents light from being emitted so as to prevent color mixture, and consequently, the image quality of the organic light-emitting display apparatus 200 may be improved.

[0062] Such an effect may be improved because of the buffer layer 226. Electrons injected through the second electrode 250 in the first sub-pixel SP1 are recombined with holes in the first organic emission layer 231, and thus, emit red

visible light. Electrons that contribute to the recombination in the first organic emission layer 231 may be reduced due to the electron acceptor layer 225.

[0063] The buffer layer 226 may be disposed between the first organic emission layer 231 and the electron acceptor layer 225 so as to control electrons to move from the first organic emission layer 231 to the electron acceptor layer 225. Thus, an efficiency of recombination between the electrons and the holes in the first organic emission layer 231 may be improved.

[0064] As a result, an increase in image quality and life of the organic light-emitting display apparatus 200 may be expected.

[0065] In addition, a distance between the first electrode 210 and the second electrode 250 is different in each sub-pixel, so that an optical path length of visible light generated from the organic emission layer 230 may be different in each sub-pixel, and thus a microcavity effect may be realized.

[0066] FIG. 3 is a schematic cross-sectional view of another embodiment of an organic light-emitting display apparatus 300.

[0067] The organic light-emitting display apparatus 300 includes a first sub-pixel SP1, a second sub-pixel SP2, and a third sub-pixel SP3. The first, second, and third sub-pixels SP1, SP2 and SP3 may be sub-pixels of different colors. In one embodiment, the first sub-pixel SP1 may be red, the second sub-pixel SP2 may be green, and the third sub-pixel SP3 may be blue.

[0068] In the embodiment of FIG. 3, one first sub-pixel SP1, one second sub-pixel SP2, and one third sub-pixel SP3 are illustrated. In other embodiments, the organic light-emitting display apparatus 300 may include a plurality of first sub-pixels SP1, a plurality of second sub-pixels SP2, and a plurality of third sub-pixels SP3.

[0069] The first sub-pixel SP1 includes a first electrode 310, an intermediate layer 323, a third organic emission layer 333, an electron acceptor layer 325, a buffer layer 326, a first organic emission layer 331, and a second electrode 350. The second sub-pixel SP2 includes a first electrode 310, an intermediate layer 323, the third organic emission layer 333, an electron acceptor layer 325, a buffer layer 326, a second organic emission layer 332, and the second electrode 350. The third sub-pixel SP3 includes the intermediate layer 323, a first electrode 310, the third organic emission layer 333, and the second electrode 350.

[0070] The first electrode 310 is formed on a substrate 301. Components of the substrate 301 and the first electrode 310 are the same as those of the above-described embodiment.

[0071] A hole injection layer 321 and a hole transport layer 322 are formed on the first electrode 310. The intermediate layer 323 is disposed between the hole injection layer 321 and the hole transport layer 322. The intermediate layer 323 may include any one selected from the group consisting of HAT-CN, MoO<sub>3</sub>, and C60. In one embodiment, the intermediate layer 323 may include 1,4,5,8,9,11-HAT-CN.

[0072] The HAT-CN, MoO<sub>3</sub>, and C60 may trap electrons and may also have an excellent hole transport capability. Therefore, the intermediate layer 323 is disposed between the hole injection layer 321 and the hole transport layer 322, so that holes injected through the first electrode 310 may easily move toward the organic emission layer 330.

[0073] In some embodiments, an auxiliary layer 324 including a hole transport material or a hole injection material may be disposed between the intermediate layer 323 and the hole transport layer 322.

[0074] The organic emission layer 330 is formed on the hole transport layer 322. The organic emission layer 330 includes the first organic emission layer 331, the second organic emission layer 332, and the third organic emission layer 333.

[0075] The third organic emission layer 333 is formed on the hole transport layer 322 across all of the first sub-pixel SP1, the second sub-pixel SP2, and the third sub-pixel SP3.

[0076] The third organic emission layer 333 emits blue visible light and its components are the same as those of the above-described embodiments.

[0077] In the first sub-pixel SP1 and the second sub-pixel SP2, the buffer layer 326 and the electron acceptor layer 325 are disposed on the third organic emission layer 333.

[0078] The electron acceptor layer 325 may include any one selected from the group consisting of HAT-CN, MoO<sub>3</sub>, and C60. In one embodiment, the electron acceptor layer 325 may include 1,4,5,8,9,11-HAT-CN.

[0079] The buffer layer 326 may include a hole transport material or a hole injection material.

[0080] The first organic emission layer 331 is formed on the buffer layer 326 in the first sub-pixel SP1. The first organic emission layer 331 emits red visible light, and its components are the same as those of the above-described embodiments.

[0081] The second organic emission layer 332 is formed on the buffer layer 326 in the second sub-pixel SP2. The second organic emission layer 332 emits green visible light and its components are the same as those of the above-described embodiments.

[0082] An electron transport layer 341 and an electron injection layer 342 are disposed on the organic emission layer 330 across all the sub-pixels. In some embodiments, the electron transport layer 341 and the electron injection layer 342 may not be disposed, or one of them may be disposed.

[0083] The second electrode 350 is disposed on the electron injection layer 342. A sealing member (not shown) may be disposed on the second electrode 350. The second electrode 350 and the sealing member are the same as those of the above-described embodiments.

[0084] In the embodiment of the organic light-emitting display apparatus 300 of FIG. 3, the electron acceptor layer 325 is disposed between the third organic emission layer 333 and the first organic emission layer 331 of the first sub-pixel SP1 and between the third organic emission layer 333 and the second organic emission layer 332 of the second sub-pixel SP2. Thus, surplus electrons are trapped in the electron acceptor layer 325, thereby extending the life of the organic light-emitting display apparatus 300, preventing color mixture, and improving the image quality of the organic light-emitting display apparatus 300. An increase in image quality and life of the organic light-emitting display apparatus 300 may be improved because of the buffer layer 326.

[0085] In addition, in the organic light-emitting display apparatus 300, the intermediate layer 323 formed of the same material as the electron acceptor layer 325 is formed between the hole injection layer 321 and the hole transport layer 322, and thus hole transport efficiency may be improved because of the intermediate layer 323. Thus, the efficiency of recombination between the electrons and the holes in the organic

emission layer 330 may be improved, and consequently light efficiency of the organic light-emitting display apparatus 300 may be improved.

[0086] In addition, an optical path length of visible light is different in each sub-pixel, and thus a microcavity effect may be realized.

[0087] FIG. 4 is a graph illustrating life of an embodiment of the organic light-emitting display apparatus. FIG. 4 illustrates a relative luminance of the organic light-emitting display apparatus over time. The relative luminance is an indicator representing life of the organic light-emitting display apparatus, and is the ratio of luminance at a given time compared to a luminance at the initial time. In FIG. 4, curve (a) is an example of the relative luminance of an embodiment of the organic light-emitting display apparatus, and curve (b) is an example of the relative luminance of a conventional organic light-emitting display apparatus, which does not include an electron acceptor layer.

[0088] Referring to curve (a) of FIG. 4, if the organic light-emitting display apparatus is continuously used for 1000 hours, the relative luminance is about 95%. That is, if 1000 hours has elapsed, the relative luminance is decreased by about 5%, compared to the initial luminance. Referring to curve (b) of FIG. 4, when the organic light-emitting display apparatus is continuously used for 1000 hours, the relative luminance is about 80%. That is, when 1000 hours has elapsed, the relative luminance is decreased by about 20%, compared to the initial luminance.

[0089] As illustrated in FIG. 4, the life of embodiments of the organic light-emitting display apparatus is remarkably extended because luminance is reduced less over time.

[0090] Embodiments of the organic light emitting display apparatus improve the image quality and life of the apparatus.

[0091] While the present invention has been particularly shown and described with reference to certain exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope.

What is claimed is:

1. An organic light-emitting display apparatus comprising:
  - a first sub-pixel, a second sub-pixel, and a third sub-pixel, wherein each of said first, second and third sub-pixels displays a different color;
  - a substrate;
  - a first electrode disposed on the substrate;
  - a second electrode disposed on the first electrode, facing the first electrode;
  - an organic emission layer disposed between the first electrode and the second electrode, comprising a first organic emission layer, a second organic emission layer, and a third organic emission layer; and
  - an electron acceptor layer disposed between the first electrode and the second electrode configured to contact the organic emission layer,
  - wherein the first organic emission layer is disposed in the first sub-pixel, the second organic emission layer is disposed in the second sub-pixel, and the third organic emission layer is commonly disposed over the first sub-pixel, the second sub-pixel, and the third sub-pixel; and
  - wherein the electron acceptor layer is disposed between the first organic emission layer and the third organic emission layer in the first sub-pixel and between the

second organic emission layer and the third organic emission layer in the second sub-pixel.

**2.** The organic light-emitting display apparatus of claim 1, wherein the first organic emission layer emits red visible light, the second organic emission layer emits green visible light, and the third organic emission layer emits blue visible light.

**3.** The organic light-emitting display apparatus of claim 1, wherein the electron acceptor layer comprises one of hexaazatriphenylene hexacarbonitrile (HAT-CN), MoO<sub>3</sub>, and fullerene (C60).

**4.** The organic light-emitting display apparatus of claim 1, wherein the third organic emission layer is disposed between the first electrode and the first organic emission layer, and further disposed between the first electrode and the second organic emission layer.

**5.** The organic light-emitting display apparatus of claim 1, further comprising a buffer layer between the electron acceptor layer and the first organic emission layer, and between the electron acceptor layer and the second organic emission layer.

**6.** The organic light-emitting display apparatus of claim 5, wherein the buffer layer comprises one of a hole injection material and a hole transport material.

**7.** The organic light-emitting display apparatus of claim 1, wherein a hole transport layer and a hole injection layer are disposed between the substrate and the third organic emission layer.

**8.** The organic light-emitting display apparatus of claim 7, further comprising an intermediate layer between the hole injection layer and the hole transport layer.

**9.** The organic light-emitting display apparatus of claim 8, wherein the intermediate layer comprises one of HAT-CN, MoO<sub>3</sub>, and C60.

**10.** An organic light-emitting display apparatus comprising:

a first sub-pixel, a second sub-pixel, and a third sub-pixel, wherein each of said first, second and third sub-pixels displays a different color;

a first electrode;

a second electrode disposed on the first electrode, facing the first electrode;

an organic emission layer disposed between the first electrode and the second electrode, comprising a first organic emission sublayer, a second organic emission sublayer, and a third organic emission sublayer;

an electron acceptor layer disposed between the first electrode and the second electrode configured to contact the organic emission layer,

wherein the first organic emission sublayer is disposed in the first sub-pixel, the second organic emission sublayer is disposed in the second sub-pixel, and the third organic emission sublayer is commonly disposed over the first sub-pixel, the second sub-pixel, and the third sub-pixel; and

wherein the electron acceptor layer is disposed between the first organic emission sublayer and the third

organic emission sublayer in the first sub-pixel and between the second organic emission sublayer and the third organic emission sublayer in the second sub-pixel; and

a buffer layer between the electron acceptor layer and the first organic emission sublayer, and between the electron acceptor layer and the second organic emission sublayer.

**11.** The organic light-emitting display apparatus of claim 10, wherein the first organic emission sublayer emits red visible light, the second organic emission sublayer emits green visible light, and the third organic emission sublayer emits blue visible light.

**12.** The organic light-emitting display apparatus of claim 10, wherein the electron acceptor layer comprises one of hexaazatriphenylene hexacarbonitrile (HAT-CN), MoO<sub>3</sub>, and fullerene (C60).

**13.** The organic light-emitting display apparatus of claim 10, wherein the third organic emission sublayer is disposed between the first electrode and the first organic emission sublayer, and further disposed between the first electrode and the second organic emission sublayer.

**14.** The organic light-emitting display apparatus of claim 10, wherein the buffer layer comprises one of a hole injection material and a hole transport material.

**15.** The organic light-emitting display apparatus of claim 10, further comprising a hole transport layer and a hole injection layer.

**16.** The organic light-emitting display apparatus of claim 15, further comprising an intermediate layer between the hole injection layer and the hole transport layer.

**17.** The organic light-emitting display apparatus of claim 16, wherein the intermediate layer comprises one of HAT-CN, MoO<sub>3</sub>, and C60.

**18.** An organic light-emitting display apparatus, comprising:

a first sub-pixel, which comprises a first electrode, a third organic emission layer, an electron acceptor layer, a first organic emission layer, and a second electrode;

a second sub-pixel, which comprises another first electrode, said third organic emission layer, another electron acceptor layer, a second organic emission layer, and said second electrode; and

a third sub-pixel, which comprises yet another first electrode, said third organic emission layer, and said second electrode.

wherein each of said first, second and third sub-pixels displays a different color.

**19.** The organic light-emitting display apparatus of claim 18, wherein the apparatus comprises a plurality of first subpixels, a plurality of second sub-pixels, and a plurality of third sub-pixels.

**20.** The organic light-emitting display apparatus of claim 18, wherein the first sub-pixel displays red color, the second sub-pixel displays green color, and the third sub-pixel displays blue color.

\* \* \* \* \*

专利名称(译)	有机发光显示装置		
公开(公告)号	<a href="#">US20110240970A1</a>	公开(公告)日	2011-10-06
申请号	US13/069039	申请日	2011-03-22
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星移动显示器有限公司.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	PARK JIN WOO JUNG MYUNG JONG KANG TAE MIN PYO SANG WOO KIM BEOM JOON KIM HYO YEON		
发明人	PARK, JIN-WOO JUNG, MYUNG-JONG KANG, TAE- MIN PYO, SANG-WOO KIM, BEOM-JOON KIM, HYO-YEON		
IPC分类号	H01L51/54 H01L51/52 B82Y99/00		
CPC分类号	H01L27/3211 H01L51/5096 H01L51/5036		
优先权	1020100029344 2010-03-31 KR		
其他公开文献	US8581270		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

### 摘要(译)

公开了一种有机发光显示装置。有机发光显示装置包括第一子像素，第二子像素和第三子像素，其中所述第一，第二和第三子像素中的每一个显示不同的颜色，基板，第一电极设置在基板上的第二电极，面对第一电极的第二电极，设置在第一电极和第二电极之间的有机发光层，包括第一有机发光层，第二有机发光层和第三有机发光层发光层，设置在第一电极和第二电极之间的电子受体层，用于接触有机发光层，其中第一有机发光层设置在第一子像素中，第二有机发光层设置在第二子像素中所述子像素，所述第三有机发光层共同设置在所述第一子像素，所述第二子像素和所述第三子像素上方，所述电子受体层为dis在第一子像素中的第一有机发光层和第三有机发光层之间以及第二子像素中的第二有机发光层和第三有机发光层之间。

