



US010586949B2

(12) **United States Patent**  
**Kwak**

(10) **Patent No.:** **US 10,586,949 B2**  
(45) **Date of Patent:** **Mar. 10, 2020**

(54) **ORGANIC LIGHT-EMITTING DISPLAY APPARATUS AND METHOD OF MANUFACTURING THE SAME**

(58) **Field of Classification Search**  
CPC ... H01L 27/32-326; H01L 51/50-5012; H01L 51/525-5287;

(Continued)

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin, Gyeonggi-Do (KR)

(56) **References Cited**

U.S. PATENT DOCUMENTS

(72) Inventor: **Won-Kyu Kwak**, Yongin (KR)

7,671,532 B2 3/2010 Kim  
2003/0168966 A1 9/2003 Kobayashi ..... H01L 27/3246 313/495

(73) Assignee: **SAMSUNG DISPLAY CO., LTD.**, Gyeonggi-Do (KR)

(Continued)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

FOREIGN PATENT DOCUMENTS

(21) Appl. No.: **15/871,196**

KR 1020050081541 A 8/2005  
KR 1020060035147 A 4/2006

(Continued)

(22) Filed: **Jan. 15, 2018**

OTHER PUBLICATIONS

(65) **Prior Publication Data**

US 2018/0138452 A1 May 17, 2018

Korean Office Action for Korean Patent Application No. 1020130102658 dated Nov. 26, 20219.

*Primary Examiner* — Cuong B Nguyen

(74) *Attorney, Agent, or Firm* — Cantor Colburn LLP

**Related U.S. Application Data**

(60) Continuation of application No. 15/096,534, filed on Apr. 12, 2016, now Pat. No. 9,905,803, which is a (Continued)

(57) **ABSTRACT**

An organic light-emitting display apparatus including a substrate; a display unit which defines an active area of the substrate and includes a thin film transistor; concave-convex portions protruded from the substrate in an area outside the active area; and an encapsulation layer which encapsulates the display unit. The thin film transistor includes an active layer, a gate insulating layer on the active layer, a gate electrode, a source electrode, a drain electrode, and an interlayer insulating layer between the gate electrode and the source electrode, and between the gate electrode and the drain electrode. The concave-convex portions include portions of the gate insulating layer and the interlayer insulating layer, and the encapsulation layer covers the concave-convex portions.

(30) **Foreign Application Priority Data**

Aug. 28, 2013 (KR) ..... 10-2013-0102658

**20 Claims, 6 Drawing Sheets**

(51) **Int. Cl.**


**H01L 51/52** (2006.01)

**H01L 27/32** (2006.01)

**H01L 51/05** (2006.01)

(52) **U.S. Cl.**

CPC ..... **H01L 51/5256** (2013.01); **H01L 27/3258** (2013.01); **H01L 27/3262** (2013.01); **H01L 51/0525** (2013.01); **H01L 51/5253** (2013.01)



**Related U.S. Application Data**

division of application No. 14/262,757, filed on Apr. 27, 2014, now Pat. No. 9,343,699.

(58) **Field of Classification Search**

CPC . H01L 2227/32-326; H01L 2251/5323-5361;  
H01L 2924/12044; H01L 51/5256; H01L  
27/3262; H01L 51/0525; H01L 51/5253;  
H01L 27/3258

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2004/0125314	A1	7/2004	Choi	
2005/0184927	A1*	8/2005	Kwak	..... H01L 27/3276 345/45
2007/0159043	A1	7/2007	Kubota et al.	
2008/0224599	A1	9/2008	Kim	
2010/0200846	A1*	8/2010	Kwack	..... H01L 51/5253 257/40
2012/0139000	A1*	6/2012	Lee	..... H01L 27/1255 257/99
2013/0316475	A1*	11/2013	Yu	..... H01L 51/56 438/26

FOREIGN PATENT DOCUMENTS

KR	1020100005525	A	1/2010
KR	1020110035444	A	4/2011
KR	1020120075145	A	7/2012
KR	1020130015033	A	2/2013

\* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5





FIG. 6







**ORGANIC LIGHT-EMITTING DISPLAY  
APPARATUS AND METHOD OF  
MANUFACTURING THE SAME**

This application is a continuation application of U.S. patent application Ser. No. 15/096,534 filed on Apr. 12, 2016, which is divisional application of U.S. patent application Ser. No. 14/262,757 filed on Apr. 27, 2014 and issued as U.S. Pat. No. 9,343,699 on May 17, 2016, which claims priority to Korean Patent Application No. 10-2013-0102658, filed on Aug. 28, 2013, and all the benefits accruing therefrom under 35 U.S.C. § 119, the disclosure of which is incorporated herein in its entirety by reference.

**BACKGROUND**

1. Field

One or more exemplary embodiment of the invention relate to an organic light-emitting display apparatus and a method of manufacturing the same, and more particularly, to an organic light-emitting display apparatus including a thin film encapsulation layer having an improved encapsulation characteristic and a method of manufacturing the organic light-emitting display apparatus.

2. Description of the Related Art

An organic light-emitting display apparatus is a self-emissive display apparatus having an organic light-emitting device. The organic light-emitting device includes a hole injection electrode and an electron injection electrode, and an organic emission layer (organic EML) therebetween. A hole injected from the hole injection electrode and an electron injected from the electron injection electrode are combined in the organic EML so that an exciton is generated from the combination and emits light when the exciton transitions from an excited state to a ground state.

The organic light-emitting display apparatus that is a self-emissive display apparatus does not require a separate light source, is capable of operating with a relatively low voltage, is capable of having a relatively light weight and slimness, and is expected to become a next generation display apparatus due to high display quality characteristics such as a wide viewing angle, high contrast and a fast response time.

**SUMMARY**

One or more exemplary embodiment of the invention include an organic light-emitting display apparatus including a thin film encapsulation layer having an improved encapsulation characteristic and a method of manufacturing the organic light-emitting display apparatus.

Additional features will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the exemplary embodiments described herein.

According to one or more exemplary embodiment of the invention, an organic light-emitting display apparatus includes a substrate; a display unit which defines an active area of the substrate and includes a thin film transistor; concave-convex portions protruded from the substrate in an area outside the active area; and an encapsulation layer which encapsulates the display unit. The thin film transistor includes an active layer, a gate insulating layer on the active layer, a gate electrode, a source electrode, a drain electrode,

and an interlayer insulating layer between the gate electrode and the source electrode, and between the gate electrode and the drain electrode. The concave-convex portions include portions of the gate insulating layer and the interlayer insulating layer, and the encapsulation layer covers the concave-convex portions.

Each of the concave-convex portions may have a double-layer structure including the portions of the gate insulating layer and the interlayer insulating layer.

The encapsulation layer may include an inorganic layer, and the inorganic layer may contact the concave-convex portions.

The inorganic layer and the interlayer insulating layer may include a same material.

The inorganic layer and the gate insulating layer may include a same material.

The encapsulation layer may include a stacked structure including an organic layer and an inorganic layer, and the inorganic layer may contact the concave-convex portions.

The stacked structure may include more than one of the organic layer or the inorganic layer.

The inorganic layer and the interlayer insulating layer may include a same material.

The inorganic layer and the gate insulating layer may include a same material.

The organic light-emitting display apparatus may further include a protective layer between the encapsulation layer and the display unit.

According to one or more exemplary embodiment of the invention, an organic light-emitting display apparatus includes a substrate; a display unit which defines an active area of the substrate and includes a thin film transistor and an organic light-emitting device electrically connected to each other; and an encapsulation layer which encapsulates the display unit. The thin film transistor includes a gate insulating layer extending to an area outside the active area, and an interlayer insulating layer on the gate insulating layer and extending to the area outside the active area. Protruding portions are between the gate insulating layer and the interlayer insulating layer in the area outside the active area. The concave-convex portions are defined by the interlayer insulating layer in the area outside the active area, and the encapsulation layer covers the concave-convex portions.

Each of the stepped portions may include a metal layer.

The thin film transistor may further include an active layer, a gate electrode, a source electrode and a drain electrode. The interlayer insulating layer may be between the gate electrode and the source electrode, and between the gate electrode and the drain electrode. The display unit may further include an organic light-emitting device including a pixel electrode connected to the source electrode or the drain electrode; an intermediate layer on the pixel electrode and including an organic emission layer; and an opposite electrode on the intermediate layer. The protruding portions may include a same material as that of the gate electrode, the source electrode, the drain electrode or the pixel electrode.

The encapsulation layer may include an inorganic layer, and the inorganic layer may contact the concave-convex portions.

The inorganic layer and the interlayer insulating layer may include a same material.

The encapsulation layer may have a stacked structure including an organic layer and an inorganic layer, and the inorganic layer may contact the concave-convex portions.

The stacked structure may include more than one of the organic layer or the inorganic layer.

The inorganic layer and the interlayer insulating layer may include a same material.

The inorganic layer and the interlayer insulating layer may each include silicon nitride (SiNx).

The organic light-emitting display apparatus may further include a protective layer between the encapsulation layer and the display unit.

#### BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other features will become apparent and more readily appreciated from the following description of the exemplary embodiments, taken in conjunction with the accompanying drawings of which:

FIG. 1 is a plane view illustrating an exemplary embodiment of an organic light-emitting display apparatus according to the invention;

FIG. 2 is a cross-sectional view of the organic light-emitting display apparatus of FIG. 1, taken along line II-II';

FIG. 3 is a cross-sectional view of the organic light-emitting display apparatus of FIG. 1, taken along line III-III';

FIG. 4 is a magnified cross-sectional view illustrating portion P1 of FIG. 3;

FIG. 5 is a plane view illustrating another exemplary embodiment of an organic light-emitting display apparatus according to the invention;

FIG. 6 is a cross-sectional view of the organic light-emitting display apparatus of FIG. 5, taken along line VI-VI';

FIG. 7 is a cross-sectional view of the organic light-emitting display apparatus of FIG. 5, taken along line VII-VII'; and

FIG. 8 is a magnified cross-sectional view illustrating portion P2 of FIG. 7.

#### DETAILED DESCRIPTION

Reference will now be made in detail to exemplary embodiments, examples of which are illustrated in the accompanying drawings. In this regard, the exemplary embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the exemplary embodiments are merely described below, by referring to the figures, to explain features of the invention. In the drawings, the size and relative sizes of layers and regions may be exaggerated for clarity.

It will be understood that when an element or layer is referred to as being "on" or "connected to" another element or layer, the element or layer can be directly on or connected to another element or layer or intervening elements or layers. In contrast, when an element is referred to as being "directly on" or "directly connected to" another element or layer, there are no intervening elements or layers present. As used herein, connected may refer to elements being physically and/or electrically connected to each other. Like numbers refer to like elements throughout. As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items.

It will be understood that, although the terms first, second, third, etc., may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section dis-

cussed below could be termed a second element, component, region, layer or section without departing from the teachings of the invention.

Spatially relative terms, such as "below," "above," and the like, may be used herein for ease of description to describe the relationship of one element or feature to another element (s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation, in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as "below" relative to other elements or features would then be oriented "above" relative to the other elements or features. Thus, the exemplary term "below" can encompass both an orientation of above and below. The device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. As used herein, the singular forms "a," "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms "comprises," "comprising," "includes" and/or "including," when used in this specification, specify the presence of stated features, integers, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof. Expressions such as "at least one of," when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

Embodiments of the invention are described herein with reference to cross-section illustrations that are schematic illustrations of idealized embodiments (and intermediate structures) of the invention. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments of the invention should not be construed as limited to the particular shapes of regions illustrated herein but are to include deviations in shapes that result, for example, from manufacturing.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

Since an organic light-emitting display apparatus may deteriorate due to external moisture or oxygen, the organic light-emitting device is encapsulated to be protected from external moisture or oxygen.

In order to obtain slimness and/or flexibility of the organic light-emitting display apparatus, a thin film encapsulation ("TFE") such as including a plurality of inorganic layers or a plurality of layers including an organic layer and an inorganic layer, is used to encapsulate the organic light-emitting device.

The inorganic layer of the TFE may reduce or effectively prevent penetration of external moisture or oxygen, as a thickness of the inorganic layer is increased. However, when the thickness of the inorganic layer is increased, a stress of the inorganic layer is increased such that the inorganic layer

may be delaminated from other layers in the organic light-emitting display apparatus. When the delamination of the inorganic layer occurs, external moisture or oxygen may penetrate into the organic light-emitting device such that a lifetime of the organic light-emitting display apparatus may be decreased. Therefore, there remains a need for an improved organic light-emitting display apparatus and organic light-emitting device in which delamination of the TFE is reduced and penetration of external moisture or oxygen is reduced or effectively prevented.

Hereinafter, the invention will be described in detail with reference to the accompanying drawings.

FIG. 1 is a plane view illustrating an exemplary embodiment of an organic light-emitting display apparatus 10 according to the invention. FIG. 2 is a cross-sectional view of the organic light-emitting display apparatus 10 of FIG. 1, taken along line II-II'. FIG. 3 is a cross-sectional view of the organic light-emitting display apparatus 10 of FIG. 1, taken along line III-III'. FIG. 4 is a magnified cross-sectional view illustrating portion P1 of FIG. 3.

Referring to FIGS. 1 through 4, the organic light-emitting display apparatus 10 includes a substrate 101, a display unit 200 which defines an active area AA of the substrate 101 and/or the organic light-emitting display apparatus 10, and an encapsulation layer 300 which encapsulates the display unit 200. The active area AA may be a display area while an area outside the active area AA may be a peripheral or non-display area.

The substrate 101 may be a flexible substrate including a plastic material such as polyimide, polyethylene terephthalate ("PET"), polycarbonate, polyethylene naphthalate, polyarylate ("PAR"), polyetherimide ("PEI") or the like that have excellent heat-resistance and durability. However, the invention is not limited thereto, and the substrate 101 may include various materials such as including metal, glass or the like.

The display unit 200 defines the active area AA of the substrate 101 or the organic light-emitting display apparatus 10 and includes a thin film transistor TFT and an organic light-emitting device OLED that are electrically connected to each other. A plurality of pad units 1 is disposed around the active area AA, thereby transmitting an electric signal from a power supply device (not shown) or a signal generation device (not shown) to the active area AA.

Hereinafter, the display unit 200 is described in detail with reference to FIG. 3.

A buffer layer 201 may be disposed on the substrate 101. The buffer layer 201 may be on an entire top surface of the substrate 101, e.g., the buffer layer 201 may be disposed in the active area AA and an area outside of the active area AA. The buffer layer 201 may function to reduce or effectively prevent penetration of foreign substances via the substrate 101 and to provide a flat surface on the substrate 101. The buffer layer 201 may include various materials capable of performing the above-described functions.

In one exemplary embodiment, for example, the buffer layer 201 may be a composite layer of two or more layers such as an inorganic material layer including silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, titanium oxide, titanium nitride, or the like, and an organic material layer including polyimide, polyester, acryl or the like.

The thin film transistor TFT may be disposed on the buffer layer 201. The thin film transistor TFT may include an active layer 202, a gate electrode 204, a source electrode 206 and a drain electrode 207.

The active layer 202 may include an inorganic semiconductor such as amorphous silicon or polysilicon, an organic semiconductor, or an oxide semiconductor. The active layer 202 may include a source region, a drain region, and a channel region respectively corresponding to the source, drain and gate electrodes 206, 207 and 204.

A gate insulating layer 203 is disposed on the active layer 202. The gate insulating layer 203 may correspond to the entire top surface of the substrate 101. That is, the gate insulating layer 203 may correspond to the active area AA and the area outside of the active area AA. The gate insulating layer 203 may insulate the active layer 202 from the gate electrode 204. The gate insulating layer 203 may include an organic material, or an inorganic material including SiNx, SiO<sub>2</sub>, or the like.

The gate electrode 204 is disposed on the gate insulating layer 203. The gate electrode 204 may include Au, Ag, Cu, Ni, Pt, Pd, Al, Mo, or an alloy of Al:Nd or Mo:W. However, the invention is not limited thereto, and the gate electrode 204 may include various materials in consideration of a design condition of the organic light-emitting display apparatus 10.

An interlayer insulating layer 205 is disposed on the gate electrode 204. The interlayer insulating layer 205 may correspond to the entire top surface of the substrate 101. That is, the interlayer insulating layer 205 may correspond to the active area AA and the outer area of the active area AA.

The interlayer insulating layer 205 is disposed between the gate electrode 204 and the source electrode 206, and between the gate electrode 204 and the drain electrode 207 so as to respectively obtain insulation therebetween. The interlayer insulating layer 205 may include an inorganic material including SiNx, SiO<sub>2</sub>, or the like.

Concave-convex portions 209 may be disposed in the area outside of the active area AA. The concave-convex portions 209 may be disposed on the buffer layer 201.

Each of the concave-convex portions 209 may have a double-layer structure including the gate insulating layer 203 and the interlayer insulating layer 205. In an exemplary embodiment of manufacturing the organic light-emitting display apparatus 10, the concave-convex portions 209 may be formed by patterning the gate insulating layer 203 and the interlayer insulating layer 205. A region of the organic light-emitting display apparatus 10 in which the concave-convex portions 209 are formed may be considered to have an embossed shape. The concave-convex portions 209 are covered by the encapsulation layer 300. Due to the repeating protruding and recessed shape defined by the concave-convex portions 209, a contact area between the encapsulation layer 300 and each of the gate and interlayer insulating layers 203 and 205 is increased. Thus, adhesion between the encapsulation layer 300 and each of the gate and interlayer insulating layers 203 and 205 is improved, so that delamination of the encapsulation layer 300 may be reduced or effectively prevented, and by doing so, penetration of external moisture or oxygen to organic light-emitting device OLED may be efficiently reduced or effectively prevented. Also, because portions of the gate insulating layer 203 and the interlayer insulating layer 205 are absent between and around the concave-convex portions 209, a strain in and below the encapsulation layer 300 due to occurrence of a stress may be decreased.

The source electrode 206 and the drain electrode 207 are disposed on the interlayer insulating layer 205. In more detail, the interlayer insulating layer 205 and the gate insulating layer 203 expose the source region and the drain

region of the active layer **202**, and the source electrode **206** and the drain electrode **207** respectively contact the exposed source and drain regions of the active layer **202**. In an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10**, the concave-convex portions **209** may be formed by a process in which the interlayer insulating layer **205** and the gate insulating layer **203** are formed to expose the source region and the drain region of the active layer **202**, such that an additional process to form the concave-convex portions **209** is omitted.

While FIG. 3 illustrates a top gate type thin film transistor TFT that sequentially includes the active layer **202**, the gate electrode **204**, the source electrode **206** and the drain electrode **207**, the invention is not limited thereto, and the gate electrode **204** may be disposed below the active layer **202** in a bottom gate type thin film transistor TFT.

The thin film transistor TFT is electrically connected to the organic light-emitting device OLED and drives the organic light-emitting device OLED. The thin film transistor TFT is covered by a passivation layer **208**.

The passivation layer **208** may include an inorganic insulating layer and/or an organic insulating layer. The inorganic insulating layer may include SiO<sub>2</sub>, silicon nitride (SiN<sub>x</sub>), silicon oxynitride (SiON), Al<sub>2</sub>O<sub>3</sub>, TiO<sub>2</sub>, Ta<sub>2</sub>O<sub>5</sub>, HfO<sub>2</sub>, ZrO<sub>2</sub>, barium strontium titanate ("BST"), lead zirconate titanate ("PZT") or the like, and the organic insulating layer may include polymer derivatives having a commercial polymer such as poly(methyl methacrylate) ("PMMA") and polystyrene ("PS") and a phenol group, an acryl-based polymer, an imide-based polymer, an allyl ether-based polymer, an amide-based polymer, a fluorine-based polymer, a p-xylene-based polymer, a vinylalcohol-based polymer or a combination thereof. The passivation layer **208** may have a multi-layer structure including the inorganic insulating layer and the organic insulating layer.

The organic light-emitting device OLED may be disposed on the passivation layer **208**, and may include a pixel electrode **211**, an intermediate layer **214** and an opposite electrode **215**.

The pixel electrode **211** is disposed on the passivation layer **208**. In more detail, the passivation layer **208** may expose a predetermined region of the drain electrode **207** without covering an entire portion of the drain electrode **207**, and the pixel electrode **211** may be connected to the exposed portion of the drain electrode **207**.

In the illustrated exemplary embodiment, the pixel electrode **211** may be a reflective electrode. The pixel electrode **211** may include a reflective material layer including Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr or a combination thereof, and a transparent or translucent electrode layer disposed on the reflective layer. The transparent or translucent electrode layer may include indium tin oxide ("ITO"), indium zinc oxide ("IZO"), zinc oxide ("ZnO"), indium oxide (In<sub>2</sub>O<sub>3</sub>), indium gallium oxide ("IGO") aluminum zinc oxide ("AZO") or a combination thereof.

The opposite electrode **215** disposed to face the pixel electrode **211** may be a transparent or translucent electrode. The opposite electrode **215** may include a metal thin layer having a low work function and including Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg or a combination thereof. Also, opposite electrode **215** may include an auxiliary electrode layer or a bus electrode, which includes a transparent electrode forming material such as ITO, IZO, ZnO, In<sub>2</sub>O<sub>3</sub> or a combination thereof may be further disposed on the metal thin layer.

Thus, the opposite electrode **215** may transmit light emitted from an organic emission layer (organic EML) included in the intermediate layer **214**. That is, the light

emitted from the organic EML may be directly emitted toward the opposite electrode **215**, or may be reflected from the pixel electrode **211** as a reflective electrode and then emitted toward the opposite electrode **215**.

The organic light-emitting display apparatus **10** according to the invention is not limited to a top-emission type organic light-emitting display apparatus and alternatively may be a bottom-emission type organic light-emitting display apparatus in which light from the organic EML is emitted toward the substrate **101**. In an exemplary embodiment of the bottom-emission type organic light-emitting display apparatus, the pixel electrode **211** may be a transparent or translucent electrode, and the opposite electrode **215** may be a reflective electrode. Also, in another alternative exemplary embodiment, the organic light-emitting display apparatus **10** according to the illustrated exemplary embodiment may be a dual-emission type organic light-emitting display apparatus in which light is emitted toward both top and bottom surfaces.

A pixel defining layer **213** including an insulating material is disposed on the pixel electrode **211**. An opening defined in the pixel defining layer **213** exposes a predetermined region of the pixel electrode **211**, and the intermediate layer **214** including the organic EML is disposed on the exposed region of the pixel electrode **211** and in the opening defined in the pixel defining layer **213**.

The organic EML may be a relatively small-molecule organic layer or a polymer organic layer. In addition to the organic EML, the intermediate layer **214** may selectively further include a functional layer such as a hole transport layer ("HTL"), a hole injection layer ("HIL"), an electron transport layer ("ETL"), an electron injection layer ("EIL"), or the like.

The encapsulation layer **300** is disposed on the opposite electrode **215**. The encapsulation layer **300** may include a first inorganic layer **301**, a first organic layer **302** and a second inorganic layer **303**. Also, a protective layer **220** may be further disposed between the encapsulation layer **300** and the display unit **200**.

The protective layer **220** includes a capping layer **222** covering the opposite electrode **215**, and a blocking layer **224** on the capping layer **222**.

The capping layer **222** may include an organic material such as N,N'-diphenyl-N,N'-bis(1-naphthyl)-1,1'-biphenyl-4,4"-diamine ("a-NPD"), N,N'-di(naphthalene-1-yl)-N,N'-diphthalbenzidine ("NPB"), N,N'-diphenyl-N,N'-bis(3-methylphenyl)-(1,1'-biphenyl)-4,4'-diamine ("TPD"), 4,4',4"-Tris(N-3-methylphenyl-N-phenylamino)triphenylamine ("m-MTDATA"), tris(8-quinolinolato)aluminum ("Alq<sub>3</sub>") copper phthalocyanine ("CuPc"), or the like. The capping layer **222** may function to protect the organic light-emitting device OLED and to help light, which is generated in the organic light-emitting device OLED, to be efficiently emitted from the organic light-emitting device OLED.

The blocking layer **224** may include an inorganic material such as lithium fluoride (LiF), magnesium fluoride (MgF<sub>2</sub>), calcium fluoride (CaF<sub>2</sub>) or the like. In an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10**, the blocking layer **224** may function to block plasma, which is used in forming the first inorganic layer **301**, from penetrating into the organic light-emitting device OLED and then damaging elements thereof such as the intermediate layer **214**, the opposite electrode **215** or the like. In the illustrated exemplary embodiment, the blocking layer **224** may include LiF having a pin-hole structure.

The first inorganic layer **301** is disposed on the protective layer **220**. In one exemplary embodiment, for example, the

first inorganic layer **301** may include an aluminum oxide (AlOx). The first inorganic layer **301** may have a preset cross-sectional thickness, formed in an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10** such as by a sputtering method.

The first organic layer **302** is disposed on the first inorganic layer **301** and may have a preset cross-sectional thickness so as to planarize a step difference due to the pixel defining layer **213**. The first organic layer **302** may include epoxy, acrylate, urethane-acrylate or a combination thereof. A planar area of the first organic layer **302** may be less than that of the first inorganic layer **301**.

The second inorganic layer **303** may surround the first inorganic layer **301** and the first organic layer **302**. That is, the first organic layer **302** is completely surrounded by the first inorganic layer **301** and the second inorganic layer **303**, so that penetration of external moisture or oxygen may be efficiently reduced or effectively prevented.

The second inorganic layer **303** may include SiNx and may have a preset cross-sectional thickness formed in an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10** such as by chemical vapor deposition ("CVD").

A planar area of the second inorganic layer **303** may be greater than that of the first inorganic layer **301** and may directly cover the concave-convex portions **209** in the area outside of the active area AA.

Also, the second inorganic layer **303** may include a same material as the interlayer insulating layer **205** and/or be in same layer as the interlayer insulating layer **2205**. That is, in an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10**, when the second inorganic layer **303** is formed of SiNx and the interlayer insulating layer **205** is also formed of SiNx, adhesion between the second inorganic layer **303** and the interlayer insulating layer **205** may be improved, so that adhesion between the second inorganic layer **303** and the concave-convex portions **209** may be improved. In this manner, the second inorganic layer **303** has a cross-sectional thickness sufficient to cover particles, so that, although a layer stress is increased, delamination of the second inorganic layer **303** may be reduced or effectively prevented, and by doing so, penetration of external moisture or oxygen to the organic light-emitting device OLED may be efficiently reduced or effectively prevented.

Also, the second inorganic layer **303** may include a same material as the gate insulating layer **203**. That is, in an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10**, when the second inorganic layer **303** is formed of SiNx and the gate insulating layer **203** is also formed of SiNx, adhesion between the second inorganic layer **303** and the concave-convex portions **209** including portions of the gate insulating layer **203** may be improved. In this manner, the second inorganic layer **303** has a cross-sectional thickness sufficient to cover particles, so that, although a layer stress is increased, delamination of the second inorganic layer **303** may be reduced or effectively prevented, and by doing so, penetration of external moisture or oxygen to the organic light-emitting device OLED may be efficiently reduced or effectively prevented.

A second organic layer **304** and a third inorganic layer **305** may be disposed on the second inorganic layer **303**. Although not illustrated, a fourth inorganic layer (not shown) including AlOx may be disposed on an exterior surface of the encapsulation layer **300**.

The second organic layer **304** may include epoxy, acrylate, urethane-acrylate or a combination thereof, and may have a preset cross-sectional thickness. The second organic layer **304** may lessen a layer stress occurred in the first inorganic layer **301** and may evenly cover the particles or the like.

The third inorganic layer **305** covers the second organic layer **304**. The third inorganic layer **305** contacts a top surface of the second inorganic layer **303** in the area outside the active area AA.

The third inorganic layer **305** may include a same material as the second inorganic layer **303**. In one exemplary embodiment, for example, the third inorganic layer **305** may include SiNx. Thus, adhesion between the third inorganic layer **305** and the second inorganic layer **303** is improved, so that penetration of external moisture or oxygen to the organic light-emitting device OLED may be efficiently reduced and effectively prevented.

The encapsulation layer **300** may further include additional inorganic layers and organic layers that alternate with each other, and the number of times of stacking the inorganic and organic layers is not limited.

A protection film (not shown) is attached on a top surface of the encapsulation layer **300**. In an exemplary embodiment where the protection film has strong adhesion, when the protection film is removed, the encapsulation layer **300** may be delaminated. In this regard, by further disposing the outermost fourth inorganic layer including AlOx and having weak adhesion with respect to the protection film, the delamination problem may be reduced or effectively prevented.

FIG. **5** is a plane view illustrating another exemplary embodiment of an organic light-emitting display apparatus **20** according to the invention. FIG. **6** is a cross-sectional view of the organic light-emitting display apparatus **20** of FIG. **5**, taken along line VI-VI'. FIG. **7** is a cross-sectional view of the organic light-emitting display apparatus **20** of FIG. **5**, taken along line VII-VII'. FIG. **8** is a magnified cross-sectional view illustrating portion P2 of FIG. **7**.

Hereinafter, the exemplary embodiment of FIGS. **5** through **8** will now be described with reference to differences with respect to the previous exemplary embodiment shown in FIGS. **1** through **4**. Here, like reference numerals in FIGS. **5** through **8** refer to the like elements in FIGS. **1** through **4**.

Referring to FIGS. **5** through **8**, the organic light-emitting display apparatus **20** includes a substrate **101**, a display unit **2200** which defines an active area AA of the substrate **101** and/or the organic light-emitting display apparatus **20**, and an encapsulation layer **300** which encapsulates the display unit **2200**.

Hereinafter, the display unit **2200** is described in detail with reference to FIG. **7**.

A buffer layer **201** may be disposed on the substrate **101**. A thin film transistor TFT may be disposed on the buffer layer **201**. The thin film transistor TFT may include an active layer **202**, a gate electrode **204**, a source electrode **206** and a drain electrode **207**.

A gate insulating layer **203** is disposed on the active layer **202**. The gate insulating layer **203** may correspond to an entire top surface of the substrate **101**. That is, the gate insulating layer **203** may correspond to the active area AA and an area outside of the active area AA.

The gate electrode **204** is disposed on the gate insulating layer **203**.

An interlayer insulating layer **2205** is disposed on the gate electrode **204**. The interlayer insulating layer **2205** may

correspond to the entire top surface of the substrate **101**. That is, the interlayer insulating layer **2205** may correspond to the active area **AA** and the area outside of the active area **AA**.

The interlayer insulating layer **2205** is disposed between the gate electrode **204** and the source electrode **206**, and between the gate electrode **204** and the drain electrode **207** so as to respectively obtain insulation therebetween. The interlayer insulating layer **2205** may include an inorganic material including SiNx, SiO<sub>2</sub>, or the like.

Stepped portions **2210** may be disposed in the area outside of the active area **AA** and spaced apart from each other. The stepped portions **2210** may be disposed between the gate insulating layer **203** and the interlayer insulating layer **2205** in a cross-sectional thickness direction. Each of the stepped portions **2210** may include a metal layer. Each of the stepped portions **2210** may include a same material as that of the gate electrode **204**, the source electrode **206** and/or a pixel electrode **211**. Thus, in an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10**, the stepped portions **2210** may be formed by using the same method of forming the aforementioned electrodes so as to be in a same layer as the respective electrode.

Concave-convex portions **2209** may be disposed in the area outside of the active area **AA**. Since the interlayer insulating layer **2205** is disposed on the stepped portions **2210**, the concave-convex portions **2209** may be formed by portions of the interlayer insulating layer **2205** due to a step difference between the stepped portions **2210** and the gate insulating layer **303**.

A region in which the concave-convex portions **2209** are disposed may be considered to have an embossed shape. The concave-convex portions **2209** are covered by the encapsulation layer **300**. Due to the repeating protruding and recessed shape defined by the concave-convex portions **2209**, a contact area between the encapsulation layer **300** and the interlayer insulating layer **2205** is increased. Thus, adhesion between the encapsulation layer **300** and the interlayer insulating layer **2205** is improved, so that delamination of the encapsulation layer **300** may be reduced or effectively prevented, and by doing so, penetration of external moisture or oxygen to organic light-emitting device **OLED** may be efficiently reduced or effectively prevented.

The source electrode **206** and the drain electrode **207** are disposed on the interlayer insulating layer **2205**.

The thin film transistor **TFT** is electrically connected to an organic light-emitting device **OLED** and drives the organic light-emitting device **OLED**, and is covered by a passivation layer **208**.

The passivation layer **208** may include an inorganic insulating layer and/or an organic insulating layer.

The organic light-emitting device **OLED** may be disposed on the passivation layer **208**, and may include a pixel electrode **211**, an intermediate layer **214** and an opposite electrode **215**.

A pixel defining layer **213** including an insulating material is disposed on the pixel electrode **211**. An opening defined in the pixel defining layer **213** exposes a predetermined region of the pixel electrode **211**, and the intermediate layer **214** including an organic **EML** is disposed on the exposed region of the pixel electrode **211** and in the opening defined in the pixel defining layer **213**.

The encapsulation layer **300** is disposed on the opposite electrode **215**. The encapsulation layer **300** may include a first inorganic layer **301**, a first organic layer **302** and a

second inorganic layer **303**. Also, a protective layer **220** may be further disposed between the encapsulation layer **300** and the display unit **2200**.

The protective layer **220** includes a capping layer **222** covering the opposite electrode **215**, and a blocking layer **224** on the capping layer **222**.

The first inorganic layer **301** is disposed on the protective layer **220**. In one exemplary embodiment, for example, the first inorganic layer **301** may include AlOx.

The first organic layer **302** is disposed on the first inorganic layer **301** and may have a preset cross-sectional thickness so as to planarize a step difference due to the pixel defining layer **213**. A planar area of the first organic layer **302** may be less than that of the first inorganic layer **301**.

The second inorganic layer **303** may surround the first inorganic layer **301** and the first organic layer **302**. That is, the first organic layer **302** is completely surrounded by the first inorganic layer **301** and the second inorganic layer **303**, so that penetration of external moisture or oxygen may be efficiently reduced or effectively prevented.

The second inorganic layer **303** may include SiNx and may have a preset cross-sectional thickness formed in an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10** such as by **CVD**.

A planar area of the second inorganic layer **303** may be greater than that of the first inorganic layer **301** and may directly cover the concave-convex portions **2209** in the area outside of the active area **AA**.

Also, the second inorganic layer **303** may include a same material as the interlayer insulating layer **2205** and/or be in same layer as the interlayer insulating layer **2205**. That is, in an exemplary embodiment of manufacturing the organic light-emitting display apparatus **10**, when the second inorganic layer **303** is formed of SiNx and the interlayer insulating layer **2205** is also formed of SiNx, adhesion between the second inorganic layer **303** and the interlayer insulating layer **2205** may be improved, so that adhesion between the second inorganic layer **303** and the concave-convex portions **2209** may be improved. In this manner, the second inorganic layer **303** has a cross-sectional thickness sufficient to cover particles, so that, although a layer stress is increased, delamination of the second inorganic layer **303** may be reduced or effectively prevented, and by doing so, penetration of external moisture or oxygen to the organic light-emitting device **OLED** may be efficiently reduced or effectively prevented.

A second organic layer **304** and a third inorganic layer **305** may be disposed on the second inorganic layer **303**, and although not illustrated, a fourth inorganic layer (not shown) including of AlOx may be disposed on an exterior surface of the encapsulation layer **300**.

The second organic layer **304** may lessen a layer stress occurring in the first inorganic layer **301** and may evenly cover the particles or the like.

The third inorganic layer **305** covers the second organic layer **304**. The third inorganic layer **305** contacts a top surface of the second inorganic layer **303** in the area outside of the active area **AA**.

The third inorganic layer **305** may include a same material as the second inorganic layer **303**. In one exemplary embodiment, for example, the third inorganic layer **305** may include SiNx. Thus, adhesion between the third inorganic layer **305** and the second inorganic layer **303** is improved, so that penetration of external moisture or oxygen to the organic light-emitting device **OLED** may be efficiently reduced or effectively prevented.

The encapsulation layer **300** may further include additional inorganic layers and organic layers that alternate with

each other, and the number of times of stacking the inorganic and organic layers is not limited.

As described above, according to one or more of the above-described exemplary embodiments of the invention, delamination of an encapsulation layer may be reduced or effectively prevented so that penetration of external moisture or oxygen to the organic light-emitting device OLED may be efficiently reduced or effectively prevented.

It should be understood that the exemplary embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features within each exemplary embodiment should typically be considered as available for other similar features in other exemplary embodiments.

While one or more exemplary embodiments of the invention have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the invention as defined by the following claims.

What is claimed is:

1. An organic light-emitting display apparatus comprising:

a substrate;

a display unit which defines an active area of the substrate, and comprises a thin film transistor and an organic light-emitting device which are connected to each other;

an encapsulation layer which is in the active area and encapsulates the display unit, the encapsulation layer in the active area disposing each of the thin film transistor and the organic light-emitting device between the substrate and the encapsulation layer; and

concave-convex portions protruded from the substrate in an area outside the active area and spaced apart from each other,

wherein

the thin film transistor in the active area comprises an insulating material layer which extends to the area outside of the active area,

the concave-convex portions comprise portions of the insulating material layer,

the concave-convex portions include two convex portions spaced apart from each other and one concave portion therebetween, and

a vertical distance between a top surface of the substrate and a top surface of the encapsulation layer in the region corresponding to the concave-convex portions is smaller than a vertical distance between the top surface of substrate and the top surface of the encapsulation layer in the region corresponding to the active area.

2. The organic light-emitting display apparatus of claim 1, wherein

the insulating material layer within the thin film transistor comprises:

a gate insulating layer extending to the area outside the active area, and

an interlayer insulating layer on the gate insulating layer and extending to the area outside the active area, and

the concave-convex portions comprise portions of the gate insulating layer or portions of the interlayer insulating layer.

3. The organic light-emitting display apparatus of claim 2, wherein each of the concave-convex portions has a double-layer structure comprising the portions of the gate insulating layer and the portions of the interlayer insulating layer.

4. The organic light-emitting display apparatus of claim 1, wherein the concave-convex portions are covered with an insulating layer.

5. The organic light-emitting display apparatus of claim 4, wherein the insulating layer contacts the concave-convex portions.

6. The organic light-emitting display apparatus of claim 4, wherein the insulating layer comprises an inorganic layer.

7. The organic light-emitting display apparatus of claim 4, wherein the insulating layer comprises an organic layer.

8. The organic light-emitting display apparatus of claim 4, wherein the insulating layer comprises a stacked structure comprising more than one of an organic layer or an inorganic layer.

9. The organic light-emitting display apparatus of claim 1, wherein the encapsulation layer has a stacked structure comprising an organic layer and an inorganic layer.

10. The organic light-emitting display apparatus of claim 1, further comprising a protective layer between the encapsulation layer and the display unit.

11. An organic light-emitting display apparatus comprising:

a substrate;

a display unit which defines an active area of the substrate, and comprises a thin film transistor and an organic light-emitting device which are connected to each other;

an encapsulation layer which in the active area and encapsulates the display unit, the encapsulation layer in the active area disposing each of the thin film transistor and the organic light-emitting device between the substrate and the encapsulation layer; and

concave-convex portions protruded from the substrate in an area outside the active area and spaced apart from each other,

wherein

the thin film transistor in the active area comprises at least two insulating material layers which extend to the area outside of the active area, the two insulating material layers being between the substrate, and a source electrode or a drain electrode of the thin film transistor, the concave-convex portions comprise portions of the two insulating material layers, and

a vertical distance between a top surface of the substrate and a top surface of the encapsulation layer in the region corresponding to the concave-convex portions is smaller than a vertical distance between the top surface of substrate and the top surface of the encapsulation layer in the region corresponding to the active area.

12. The organic light-emitting display apparatus of claim 11, wherein the two insulating material layers within the thin film transistor comprise:

a gate insulating layer extending to the area outside the active area, and

an interlayer insulating layer on the gate insulating layer and extending to the area outside the active area.

13. The organic light-emitting display apparatus of claim 12, wherein each of the concave-convex portions has a double-layer structure comprising the portions of the gate insulating layer and the portions of the interlayer insulating layer.

14. The organic light-emitting display apparatus of claim 11, wherein the concave-convex portions are covered with an insulating layer.

15. The organic light-emitting display apparatus of claim 14, wherein the insulating layer contacts the concave-convex portions.

16. The organic light-emitting display apparatus of claim 14, wherein the insulating layer comprises an inorganic layer.

17. The organic light-emitting display apparatus of claim 14, wherein the insulating layer comprises an organic layer. 5

18. The organic light-emitting display apparatus of claim 14, wherein the insulating layer comprises a stacked structure comprising more than one of an organic layer or an inorganic layer.

19. The organic light-emitting display apparatus of claim 10 10  
11, wherein the encapsulation layer has a stacked structure comprising an organic layer and an inorganic layer.

20. The organic light-emitting display apparatus of claim 11, further comprising a protective layer between the encapsulation layer and the display unit. 15

\* \* \* \* \*

专利名称(译)	有机发光显示装置及其制造方法		
公开(公告)号	<a href="#">US10586949</a>	公开(公告)日	2020-03-10
申请号	US15/871196	申请日	2018-01-15
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO., LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO., LTD.		
[标]发明人	KWAK WON KYU		
发明人	KWAK, WON-KYU		
IPC分类号	H01L51/52 H01L27/32 H01L51/05		
CPC分类号	H01L27/3262 H01L51/5253 H01L27/3258 H01L51/0525 H01L51/5256 H01L27/1237 H01L27/1248		
代理机构(译)	康托科尔伯恩LLP		
优先权	1020130102658 2013-08-28 KR		
其他公开文献	US20180138452A1		
外部链接	<a href="#">Espacenet</a>		

摘要(译)

一种有机发光显示设备，包括基板；显示单元，其限定基板的有源区域并且包括薄膜晶体管；封装层封装显示单元。薄膜晶体管包括有源层，有源层上的栅绝缘层，栅电极，源电极，漏电极以及在栅电极和源电极之间以及在栅电极和源电极之间的层间绝缘层。漏电极。凹凸部分包括栅极绝缘层和层间绝缘层的一部分，并且包封层覆盖凹凸部分。

