

US009490450B2

(12) **United States Patent**
Kang et al.

(10) **Patent No.:** **US 9,490,450 B2**
(45) **Date of Patent:** **Nov. 8, 2016**

(54) **ORGANIC LIGHT EMITTING DISPLAY APPARATUS AND METHOD OF MANUFACTURING ORGANIC LIGHT EMITTING DISPLAY APPARATUS**
(75) Inventors: **Tae-Wook Kang**, Yongin (KR); **Dong-Won Han**, Yongin (KR); **Young-Seo Choi**, Yongin (KR); **Jin-Ho Kwack**, Yongin (KR)
(73) Assignee: **Samsung Display Co., Ltd.**, Samsung-ro, Giheung-Qu, Yongin-si, Gyeonggi-Do (KR)

(56) **References Cited**
U.S. PATENT DOCUMENTS
7,510,913 B2 3/2009 Moro et al.
7,648,925 B2 1/2010 Moro et al.
2002/0125822 A1 9/2002 Graff et al.
2003/0203210 A1 10/2003 Graff et al.
2007/0049155 A1 3/2007 Moro et al.
2007/0132381 A1* 6/2007 Hayashi et al. 313/512
2007/0145895 A1* 6/2007 Yamamoto et al. 313/512
2009/0208754 A1 8/2009 Chu et al.
2009/0278277 A1 11/2009 Gong et al.
2010/0244057 A1 9/2010 Ryu et al.
2011/0062603 A1 3/2011 Hawker et al.

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 597 days.

FOREIGN PATENT DOCUMENTS
KR 10-0730220 6/2007
KR 10-2010-0106796 10/2010

(21) Appl. No.: **13/593,255**

* cited by examiner

(22) Filed: **Aug. 23, 2012**

Primary Examiner — Anh Mai
Assistant Examiner — Zachary J Snyder

(65) **Prior Publication Data**
US 2013/0181602 A1 Jul. 18, 2013

(74) *Attorney, Agent, or Firm* — Robert E. Bushnell, Esq.

(30) **Foreign Application Priority Data**
Jan. 16, 2012 (KR) 10-2012-0004914

(57) **ABSTRACT**
An organic light emitting display apparatus includes a substrate, an organic light emitting portion comprising a plurality of organic light emitting devices formed on the substrate, and an encapsulation portion for encapsulating the organic light emitting portion. The encapsulation portion includes a porous layer formed on the organic light emitting portion, a planarization layer formed on the porous layer, and a barrier layer formed on the planarization layer. The porous layer prevents impurities from being concentrated at a part of the porous layer.

(51) **Int. Cl.**
H01L 51/52 (2006.01)
(52) **U.S. Cl.**
CPC **H01L 51/5256** (2013.01)
(58) **Field of Classification Search**
USPC 313/498-512
See application file for complete search history.

33 Claims, 3 Drawing Sheets




FIG. 1




FIG. 2




FIG. 3





FIG. 4



**ORGANIC LIGHT EMITTING DISPLAY
APPARATUS AND METHOD OF
MANUFACTURING ORGANIC LIGHT
EMITTING DISPLAY APPARATUS**

CLAIM OF PRIORITY

This application makes reference to, incorporates the same herein, and claims all benefits accruing under 35 U.S.C. §119 from an application earlier filed in the Korean Intellectual Property Office on the 16 Jan. 2012 and there duly assigned Serial No. 10-2012-0004914.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an organic light emitting display apparatus, and more particularly, to a method of manufacturing an organic light emitting display apparatus.

2. Description of the Related Art

Organic light emitting display apparatuses using an organic light emitting device are widely accepted as a next generation display apparatus due to their fast response speed that enables smooth display of a motion picture and their self-light emitting characteristic that provides a wide view angle and a high brightness, compared to liquid crystal display (LCD) devices that are currently widely used.

An organic light emitting device includes a pixel electrode and an opposed electrode, which are arranged to face each other, and a light emitting layer including an organic material provided between the pixel electrode and the opposed electrode. The organic light emitting device is very sensitive to moisture, oxygen, light, etc. Thus, when contacted by these elements, the organic light emitting device may be easily degraded. Also, when moisture, oxygen, etc. intrude and diffuse into an organic layer, an electrochemical charge transfer reaction occurs at a boundary surface between an electrode and the organic layer so that an oxide is generated. The oxide separates the organic layer and the pixel electrode or the opposed electrode, causing a phenomenon such as a dark spot so that the life of the organic light emitting device may be reduced. The organic light emitting device exhibits a weak resistance to heat, and thus, the life of the organic light emitting device is reduced by about 20 times when the temperature rises to 30° C. to 60° C. Thus, encapsulation technology to prevent external moisture, oxygen, light, etc. from intruding into the organic light emitting device is commonly used in the organic light emitting device.

SUMMARY OF THE INVENTION

The present invention provides an organic light emitting display apparatus capable of delaying revelation of progressive dark spots so as to extend the life of the organic light emitting display apparatus, and a method of manufacturing the organic light emitting display apparatus.

According to an aspect of the present invention, an organic light emitting display apparatus includes a substrate, an organic light emitting portion comprising a plurality of organic light emitting devices formed on the substrate, and an encapsulation portion for encapsulating the organic light emitting portion. The encapsulation portion includes a porous layer formed on the organic light emitting portion, a planarization layer formed on the porous layer, and a barrier

layer formed on the planarization layer. The porous layer prevents impurities from being concentrated at a part of the porous layer.

The porous layer may prevent impurities, intruding into the porous layer, from being concentrated at a part of the porous layer by diffusing the impurities into the porous layer.

The porous layer may have a path through which the impurities move so as to be evenly diffused into the porous layer without being concentrated at a part of the porous layer.

The impurities may be generated from the planarization layer or may intrude from the outside of the organic light emitting apparatus, and may degrade the organic light emitting device.

The impurities may be oxygen or moisture generated from the planarization layer or the outside of the organic light emitting apparatus.

The planarization layer may be formed of an organic material.

The barrier layer may be formed of an inorganic material. The barrier layer may be formed of AlO_x , Al_2O_3 , SiN_x , Si_3N_4 , ZnO, ZrO, or Al-doped zinc oxide (AZO).

The barrier layer may be formed as two or more layers.

The porous layer may be formed as a single layer.

The porous layer may be formed of LiF.

The porous layer may include a first porous layer and a second porous layer that are stacked above the organic light emitting portion.

The first porous layer may be formed of LiF.

The second porous layer may be formed of AlO_x .

At least one planarization layer and at least one barrier layer are alternately stacked above the porous layer.

The organic light emitting device may include a first electrode formed on the substrate, an intermediate layer formed on the first electrode and emitting light, and a second electrode formed so as to cover the intermediate layer.

According to another aspect of the present invention, a method of manufacturing an organic light emitting display apparatus includes forming an organic light emitting device on a substrate, forming a porous layer on the organic light emitting device, forming a planarization layer on the porous layer, and forming a barrier layer on the planarization layer.

The porous layer may prevent impurities intruding into the porous layer from being concentrated at a part of the porous layer by diffusing the impurities into the porous layer.

The porous layer may have a path through which the impurities move so as to be evenly diffused into the porous layer without being concentrated at a part of the porous layer.

The impurities may be oxygen or moisture generated from the planarization layer or intruding from the outside of the organic light emitting apparatus.

The impurities may degrade the organic light emitting device.

The planarization layer may be formed of an organic material.

The barrier layer may be formed of an inorganic material. The barrier layer may be formed of AlO_x , Al_2O_3 , SiN_x , Si_3N_4 , ZnO, ZrO, or Al-doped zinc oxide (AZO).

The barrier layer may be formed as two or more layers.

The porous layer may be formed as a single layer.

The porous layer may be formed of LiF.

The porous layer may include a first porous layer and a second porous layer that are stacked above the organic light emitting portion.

The first porous layer may be formed of LiF.

The second porous layer may be formed of AlO_x .

The forming of the organic light emitting device may include forming a first electrode on the substrate, forming an intermediate layer for emitting light on the first electrode, and forming a second electrode covering the intermediate layer.

BRIEF DESCRIPTION OF THE DRAWINGS

A more complete appreciation of the invention, and many of the attendant advantages thereof, will be readily apparent as the same becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings, in which like reference symbols indicate the same or similar components, wherein:

FIG. 1 is a cross-sectional view schematically illustrating an organic light emitting display apparatus according to an embodiment of the present invention;

FIG. 2 is an enlarged cross-sectional view of a portion A of FIG. 1;

FIG. 3 is an image of an organic light emitting display apparatus in which progressive dark spots are revealed; and

FIG. 4 is a cross-sectional view schematically illustrating an organic light emitting display apparatus according to another embodiment of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

The attached drawings for illustrating exemplary embodiments of the present invention are referred to in order to gain a sufficient understanding of the present invention, the merits thereof, and the objectives accomplished by the implementation of the present invention. Hereinafter, the present invention will be described in detail by explaining exemplary embodiments of the invention with reference to the attached drawings. Like reference numerals in the drawings denote like elements.

As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items. Expressions such as "at least one of," when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

FIG. 1 is a cross-sectional view schematically illustrating an organic light emitting display apparatus according to an embodiment of the present invention; and FIG. 2 is an enlarged cross-sectional view of a portion A of FIG. 1.

Referring to FIG. 1, the organic light emitting display apparatus **100** according to the present embodiment includes a substrate **101**, an organic light emitting portion **110**, and an encapsulation portion **120**. The organic light emitting portion **110** is formed as an organic light emitting device and is provided on the substrate **101**. The substrate **101** may be formed not only of a glass member but also of various plastic members such as acryl, or further a metal plate. Also, the substrate **101** may be a low-temperature polycrystalline silicon (LTPS) substrate. A buffer layer (not shown) may be further provided on the substrate **101**, if necessary.

As shown in FIG. 2, the organic light emitting portion **110** may include a plurality of organic light emitting devices EL. Each organic light emitting device EL includes a first electrode **111**, an intermediate layer **112**, and a second electrode **113**.

The first and second electrodes **111** and **113**, respectively, may be used as an anode electrode and a cathode electrode,

respectively. The first and second electrodes **111** and **113**, respectively, may be used as the cathode electrode and the anode electrode, respectively.

When the organic light emitting display apparatus **100** is of a bottom emission type in which an image is presented in a direction toward the substrate **101**, the first electrode **111** and the second electrode **113** are a transparent electrode and a reflective electrode, respectively. In another embodiment, when the organic light emitting display apparatus **100** is of a top emission type in which an image is presented in a direction toward the encapsulation portion **120**, the first electrode **111** and the second electrode **113** are a reflective electrode and a transparent electrode, respectively.

The transparent electrode may contain at least one selected from a group consisting of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In_2O_3), indium gallium oxide (IGO), and aluminum zinc oxide (AZO).

The reflective electrode may be formed by thinly depositing metal having a low work function, for example, Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca, LiF/Ca, LiF/Al, or a compound thereof.

One surface of the first electrode **111** may be exposed by a pixel define layer. The pixel define layer may be formed, by a method such as spin coating, of at least one organic insulation material selected from a group consisting of polyimide, polyamide, acryl resin, benzocyclobutene, and phenol resin. The pixel define layer may be formed of not only the above-described organic insulation material, but also an inorganic insulation material selected from a group consisting of SiO_2 , SiN_x , Al_2O_3 , CuO_x , Tb_4O_7 , Y_2O_3 , Nb_2O_5 , and Pr_2O_3 . Also, the pixel define layer may be formed in a multilayer structure in which the organic insulation material and the inorganic insulation material are alternately arranged.

The intermediate layer **112** is provided between the first and second electrodes **111** and **113**, respectively. The intermediate layer **112** may be formed by stacking at least one functional layer of an emissive layer (EML), a hole transport layer (HTL), a hole injection layer (HIL), an electron transport layer (ETL), and an electron injection layer (EIL) in a single or composite structure.

The EML may be formed of a low molecular or polymer organic material. When the EML is formed of a low molecular organic material, in the intermediate layer **112**, an HTL and an HIL are stacked in a direction toward the first electrode **111** and an ETL and an EIL are stacked in a direction toward the second electrode **113**, with respect to the EML. A variety of layers may be additionally stacked if necessary. A variety of organic materials, such as copper phthalocyanine (CuPc), N,N'-Di(naphthalene-1-yl)-N,N'-diphenyl-benzidine (NPB), tris-8-hydroxyquinoline aluminum (Alq_3), etc., may be used therefor.

When the EML is formed of a polymer organic material, in the intermediate layer **112**, only an HTL is included in a direction toward the first electrode **111** with respect to the EML. The HTL may be formed above the first electrode **111** by a method of inkjet printing or spin coating using poly(3,4-ethylenedioxythiophene) (PEDOT), polyaniline (PANI), etc. A polymer organic material, such as a polyphenylene vinylene (PPV) based material and a polyfluorene based material, may be used as the organic material. A color pattern may be formed by a typical method such as inkjet printing, spin coating, or a thermal transfer method using laser.

The encapsulation portion **120** of FIG. 1 encapsulates the organic light emitting portion **110**. As shown in FIG. 2, the

encapsulation portion **120** is formed by stacking porous layers **115** and **116**, a planarization layer **1211**, and a barrier layer **1212**.

The porous layers **115** and **116** are formed above the second electrode **113**. The porous layers **115** and **116** may be formed in a double layer as illustrated in FIG. 2. That is, the porous layers **115** and **116** may be formed of the first porous layer **115** and the second porous layer **116** stacked on the second electrode **113**.

The porous layers **115** and **116** may be formed of an inorganic material. For example, the first porous layer **115** may be formed of LiF and the second porous layer **116** may be formed of AlO_x , Al_2O_3 , SiN_x , Si_3N_4 , ZnO, ZrO, or Al-doped zinc oxide (AZO). The second porous layer **116** may be formed by sputtering, atomic layer deposition (ALD), chemical vapor deposition (CVD), etc. The first porous layer **115** may protect the intermediate layer **112** from plasma damage or ultraviolet damage by a process for forming the second porous layer **116**. In a modified example of the present invention, when the porous layers **115** and **116** are formed as a single layer, the porous layers **115** and **116** may be formed of LiF.

The porous layers **115** and **116** have a structure having a plurality of tiny holes therein. The porous layers **115** and **116** may delay generation of dark spots which are generated as impurities, such as moisture, oxygen, etc. generated from the planarization layer **1211** or intruding from the outside of the organic light emitting display apparatus **100**, are concentrated at a part of the inside of the porous layers **115** and **116**.

The planarization layer **1211** may be formed of an organic material, for example, acrylate, silicon, silicon acrylate, epoxy, epoxy acrylate, etc. The planarization layer **1211** formed of acrylate may be formed by a thermal deposition method. The planarization layer **1211** may be formed so as to be thicker than the barrier layer **1212**.

The barrier layer **1212** may be formed of an inorganic material, for example, AlO_x , Al_2O_3 , SiN_x , Si_3N_4 , ZnO, ZrO, or Al-doped zinc oxide (AZO). The barrier layer **1212** may be formed of the above materials in two or more layers. The barrier layer **1212** may be formed by a method such as thermal evaporation, E-beam evaporation, RF sputtering, reactive sputtering, atomic layer deposition (ALD), etc.

FIG. 3 is an image of an organic light emitting display apparatus in which progressive dark spots are revealed.

FIG. 3 shows a dark spot **11** that is generated in a conventional organic light emitting display apparatus **10** having a multilayer thin film encapsulation layer in which an organic layer and an inorganic layer are stacked on a buffer layer without the porous layers **115** and **116** of FIG. 2. As illustrated in FIG. 3, in the conventional organic light emitting display apparatus **10**, impurities such as moisture or oxygen in an organic layer are concentrated at a scratch or a gap formed in an inorganic layer arranged under the organic layer. As the impurities gather in the scratch or gap, the dark spot **11** gradually increases and becomes a progressive dark spot. As the progressive dark spot is revealed, the life of the organic light emitting display apparatus **10** may be shortened.

According to the present invention, the porous layers **115** and **116** of FIG. 2 may prevent the concentration of impurities generated from the planarization layer **1211** or intruding from the outside at a part of the porous layers **115** and **116** by diffusing the impurities into the porous layers **115** and **116** through the tiny holes formed therein. Accordingly, the revelation of progressive dark spots due to the impurities is delayed so that the life of the organic light emitting display apparatus **100** may be extended.

FIG. 4 is a cross-sectional view schematically illustrating an organic light emitting display apparatus according to another embodiment of the present invention.

Referring to FIG. 4, the organic light emitting display apparatus **200** is different from the organic light emitting display apparatus **100** of FIG. 2 in that the organic light emitting display apparatus **200** includes an encapsulation portion **220** of a multilayer structure. That is, the organic light emitting display apparatus **200** of FIG. 4 includes the encapsulation portion **220** in which a first planarization layer **2211** and a first barrier layer **2212** are deposited above the porous layers **115** and **116**, a second planarization layer **2221** and a second barrier layer **2222** are deposited above the first barrier layer **2212**, and a third planarization layer **2231** and a third barrier layer **2232** are deposited above the second barrier layer **2222**. The present invention is not limited to the above structure and the encapsulation portion **220** may have a structure in which at least one pair of a planarization layer and a barrier layer is stacked.

The porous layers **115** and **116** prevent impurities generated from the first to third planarization layers **2211**, **2221**, and **2231**, respectively, from intruding into the organic light emitting devices EL, and diffuse the impurities into the porous layers **115** and **116**. Thus, the revelation of progressive dark spots generated as the impurities are concentrated at a part of the porous layers **115** and **116** is delayed as much as possible so that the life of the organic light emitting display apparatus **200** may be extended.

As described above, according to the present invention, the revelation of progressive dark spots that may be generated at the encapsulation portion is delayed so that the life of the organic light emitting display apparatus may be extended.

While this invention has been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those skilled in the art that various changes in form and detail may be made therein without departing from the spirit and scope of the invention as defined by the appended claims.

What is claimed is:

1. An organic light emitting display apparatus, comprising:

a substrate;

an organic light emitting portion including a plurality of organic light emitting devices formed on the substrate; and

an encapsulation portion for encapsulating the organic light emitting portion;

wherein the encapsulation portion comprises:

a porous layer formed on the organic light emitting portion;

a planarization layer formed on the porous layer; and

a barrier layer formed on the planarization layer; wherein the porous layer prevents impurities from being concentrated at a part of the porous layer.

2. The organic light emitting apparatus of claim 1, wherein the porous layer is interposed between the planarization layer and the substrate.

3. The organic light emitting apparatus of claim 1, wherein the porous layer is interposed between the planarization layer and each of the substrate and the organic light emitting portion.

4. The organic light emitting apparatus of claim 1, wherein the porous layer includes a structure having a plurality of tiny holes therein, wherein the planarization layer being essentially non-porous.

5. The organic light emitting apparatus of claim 1, wherein porous layer includes a structure having a plurality of tiny holes therein to delay a generation of dark spots within the organic light emitting portion by dissipating any impurities generated from either an outside or the planarization layer.

6. The organic light emitting apparatus of claim 1, wherein the planarization layer is comprised of an organic material selected from a group consisting of acrylate, silicon acrylate, epoxy and epoxy acrylate.

7. The organic light emitting apparatus of claim 1, wherein the porous layer is characterized by having a plurality of pores therein, wherein the barrier layer is formed of one of AlO_x , Al_2O_3 , SiN_x , Si_3N_4 , ZnO , ZrO , and Al-doped zinc oxide (AZO).

8. The organic light emitting apparatus of claim 1, wherein the porous layer is formed as a single layer, wherein the porous layer is formed of LiF.

9. The organic light emitting apparatus of claim 1, wherein the encapsulation portion comprises a plurality of planarization layers and a plurality of barrier layers that are alternately stacked above the porous layer.

10. The organic light emitting apparatus of claim 1, wherein the organic light emitting device comprises:

- a first electrode formed on the substrate;
- an intermediate layer formed on the first electrode and emitting light; and
- a second electrode formed so as to cover the intermediate layer.

11. The organic light emitting apparatus of claim 1, wherein the planarization layer is comprised of a different material than that of the porous layer, and the barrier layer being comprised of a different material than any of the planarization layer and the porous layer.

12. The organic light emitting apparatus of claim 1, wherein each of the planarization layer, the porous layer and the barrier layer being distinguished from one another.

13. The organic light emitting apparatus of claim 1, wherein the porous layer includes a plurality of tiny pores.

14. The organic light emitting apparatus of claim 13, wherein each of the barrier layer and the planarization layer being essentially absent of any pores.

15. The organic light emitting apparatus of claim 1, wherein the porous layer comprises a first porous layer and a second porous layer that are stacked above the organic light emitting portion.

16. The organic light emitting apparatus of claim 15, wherein the second porous layer is formed of AlO_x .

17. The organic light emitting apparatus of claim 15, wherein the first porous layer is formed of LiF.

18. The organic light emitting apparatus of claim 17, wherein the second porous layer is comprised of a material selected from a group consisting of AlO_x , Al_2O_3 , SiN_x , Si_3N_4 , ZnO , ZrO , and Al-doped zinc oxide (AZO).

19. The organic light emitting apparatus of claim 17, wherein the second porous layer is comprised of AlO_x .

20. A method of manufacturing an organic light emitting display apparatus, the method comprising the steps of:
forming an organic light emitting device on a substrate;
forming a porous layer on the organic light emitting device;

forming a planarization layer on the porous layer; and
forming a barrier layer on the planarization layer.

21. The method of claim 20, wherein the porous layer includes a structure having a plurality of tiny holes to delay a generation of dark spots within the organic light emitting portion by dissipating any impurities generated from either an outside or the planarization layer.

22. The method of claim 20, wherein the step of forming the organic light emitting device comprises:

- forming a first electrode on the substrate;
- forming an intermediate layer for emitting light on the first electrode; and
- forming a second electrode covering the intermediate layer.

23. The method of claim 20, wherein the forming of the planarization layer occurs after the forming of the porous layer has completed, and the forming of the barrier layer occurs after the forming of the planarization layer has completed.

24. The method of claim 20, wherein the porous layer is interposed between the planarization layer and the substrate, and the planarization layer is interposed between the barrier layer and the porous layer, each of the planarization layer, the porous layer and the barrier layer being distinguished from one another.

25. The method of claim 20, wherein the porous layer prevents impurities, intruding into the porous layer, from being concentrated at a part of the porous layer by diffusing the impurities into the porous layer.

26. The method of claim 25, wherein the porous layer is characterized by including a plurality of tiny holes to produce a path through which the impurities move so as to be evenly diffused into the porous layer without being concentrated at a part of the porous layer.

27. The method of claim 25, wherein the impurities are at least one of oxygen and moisture intruding from outside the organic light emitting apparatus.

28. The method of claim 25, wherein the impurities degrade the organic light emitting device.

29. The method of claim 20, wherein the porous layer is formed as a single layer.

30. The method of claim 29, wherein the porous layer is formed of LiF.

31. The method of claim 20, wherein the porous layer comprises a first porous layer and a second porous layer that are stacked above the organic light emitting portion.

32. The method of claim 31, wherein the first porous layer is formed of LiF.

33. The method of claim 31, wherein the second porous layer is formed of AlO_x .

* * * * *

专利名称(译)	有机发光显示装置和制造有机发光显示装置的方法		
公开(公告)号	US9490450	公开(公告)日	2016-11-08
申请号	US13/593255	申请日	2012-08-23
[标]申请(专利权)人(译)	姜泰旭 韩东WON 崔英SEO KWACK何家劲		
申请(专利权)人(译)	康, 泰旭 韩, 东元 CHOI, YOUNG-SEO KWACK, JIN-HO		
当前申请(专利权)人(译)	三星DISPLAY CO., LTD.		
[标]发明人	KANG TAE WOOK HAN DONG WON CHOI YOUNG SEO KWACK JIN HO		
发明人	KANG, TAE-WOOK HAN, DONG-WON CHOI, YOUNG-SEO KWACK, JIN-HO		
IPC分类号	H01L51/52		
CPC分类号	H01L51/5256 A41D1/02 A41D3/00 A41D27/20 A41D2300/322 A44B1/00 H01L51/56 H01L2251/301 H01L2251/303		
审查员(译)	MAI, ANH		
优先权	1020120004914 2012-01-16 KR		
其他公开文献	US20130181602A1		
外部链接	Espacenet USPTO		

摘要(译)

有机发光显示装置包括基板，包括形成在基板上的多个有机发光器件的有机发光部分和用于封装有机发光部分的封装部分。封装部分包括形成在有机发光部分上的多孔层，形成在多孔层上的平坦化层以及形成在平坦化层上的阻挡层。多孔层防止杂质集中在多孔层的一部分。

