



US009362533B2

(12) **United States Patent**  
**Choi et al.**

(10) **Patent No.:** **US 9,362,533 B2**  
(45) **Date of Patent:** **Jun. 7, 2016**

(54) **ORGANIC LIGHT EMITTING DISPLAY DEVICE AND METHOD FOR MANUFACTURING THE SAME**

(71) Applicant: **LG DISPLAY CO., LTD.**, Seoul (KR)

(72) Inventors: **Hee Dong Choi**, Seosan-si (KR); **Seung Joon Jeon**, Paju-si (KR)

(73) Assignee: **LG DISPLAY CO., LTD.**, Seoul (KR)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/732,264**

(22) Filed: **Jun. 5, 2015**

(65) **Prior Publication Data**

US 2015/0270513 A1 Sep. 24, 2015

**Related U.S. Application Data**

(62) Division of application No. 13/339,925, filed on Dec. 29, 2011, now Pat. No. 9,076,745.

(30) **Foreign Application Priority Data**

Aug. 30, 2011 (KR) ..... 10-2011-0087327

(51) **Int. Cl.**

**H01L 27/32** (2006.01)  
**H01L 51/56** (2006.01)  
**H01L 51/52** (2006.01)

(52) **U.S. Cl.**

CPC ..... **H01L 51/56** (2013.01); **H01L 27/3244** (2013.01); **H01L 27/3276** (2013.01); **H01L 51/5203** (2013.01); **H01L 51/5246** (2013.01); **H01L 27/3246** (2013.01)

(58) **Field of Classification Search**

CPC . H01L 51/65; H01L 51/5203; H01L 27/3244; H01L 27/3276

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,026,511 B2 9/2011 Choi et al.  
2006/0061268 A1 3/2006 Nakanishi

(Continued)

FOREIGN PATENT DOCUMENTS

CN 101009310 A 8/2007  
JP 2011-044417 3/2011

(Continued)

OTHER PUBLICATIONS

Office Action issued in corresponding Korean Patent Application No. 10-2011-0087327, mailed Mar. 27, 2014, 7 pages.

(Continued)

*Primary Examiner* — Matthew Reames


(74) *Attorney, Agent, or Firm* — Brinks Gilson & Lione

(57)

**ABSTRACT**

An OLED device is disclosed. The OLED device includes: a substrate defined into an active area in which a plurality of pixels are formed in a matrix shape, a GIP (gate-in-panel) area in which drive elements are formed, a ground contact area, and a seal line area; a thin film transistor formed in each pixel region within the active area; an organic light emission diode formed on a protective film and configured to include a first electrode, an organic light emission layer and a second electrode; a bank layer formed to divide the organic light emission diode into pixel units; a signal wiring formed in the ground contact area and the seal line area; and an extended portion formed from the same material as the first electrode of the organic light emission diode and configured to cover the signal wiring, wherein a seal line within in the seal line area is formed on an edge of the signal wiring, which is covered with the extended portion, and an interlayer insulation film adjacent to the edge of the signal wiring. Such an OLED device can prevent a stained fault generation in the seal line region by largely forming a connection electrode, which makes contact with signal wirings formed along edges of an active area, and covering the signal wirings with a metal pattern.

**8 Claims, 9 Drawing Sheets**



(56)

**References Cited**

U.S. PATENT DOCUMENTS

2009/0261712 A1 10/2009 Choi et al.  
2011/0043495 A1 2/2011 Bang et al.

FOREIGN PATENT DOCUMENTS

KR 20080062899 A 7/2008

KR 20100013879 A 2/2010  
KR 1020110071646 A 6/2011

OTHER PUBLICATIONS

Notice of Allowance issued in Korean Patent Application No. 10-2011-0087327, mailed Sep. 22, 2014, 6 pages.  
Notice of Allowance issued in Chinese Patent Application No. 201110456846.2, mailed Nov. 15, 2014, 6 pages.

FIG.1




FIG.2




FIG.3

100




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C







FIG. 6





## ORGANIC LIGHT EMITTING DISPLAY DEVICE AND METHOD FOR MANUFACTURING THE SAME

The present patent document is a divisional of U.S. patent application Ser. No. 13/339,925, filed on Dec. 29, 2011, which claims the priority and the benefit under 35 U.S.C. §119(a) on Korean Patent Application No. 10-2011-0087327 filed on Aug. 30, 2011, the entire contents of which are hereby incorporated by reference.

### BACKGROUND

#### 1. Field of the Invention

This disclosure relates to an organic light emitting display (OLED) device and a method of manufacturing the same.

#### 2. Discussion of the Related Art

Image display devices used for displaying a variety of information on a screen are one of the core technologies of the information and communication era. Such image display devices have been being developed to be thinner, lighter, and more portable, and furthermore to have a high performance. Actually, flat panel display devices are spotlighted in the display field due to their reduced weight and volume, well known disadvantages of cathode ray tubes (CRTs). The flat panel display devices include OLED devices, which display images by controlling the light emitting quantity of an organic light emission layer.

The OLED devices are self-illuminating display devices employing a thin light emission layer between electrodes. As such, the OLED devices can become thinner like a paper. Such OLED devices display images by emitting light through an encapsulated substrate. The encapsulated substrate includes a plurality of pixels arranged in a matrix shape and each configured with 3 colored (i.e., red, green and blue) sub-pixels, a cell driver array, and an organic light emission array.

In order to realize a variety of colors, the OLED device employs organic light emission layers, which are configured to emit red, green and blue lights, respectively. The organic light emission layer is interposed between two electrodes and used to form an organic light emission diode.

FIG. 1 is a cross-sectional view showing a seal region of the OLED device according to the related art.

As shown in FIG. 1, the OLED device is defined into an active area on which a plurality of pixels each including an organic light emission diode are arranged, and a pad area in which drive elements or power supply wirings are formed along the outline of the active area. A seal line area occupying edges of the pad area is included. In the seal line area, a sealant used for combining an array substrate provided with the organic light emission diodes with an upper substrate **18** is disposed.

The array substrate of the OLED device includes a buffer layer **11**, a gate insulation layer **12** and an interlayer insulation film **13** stacked on a lower substrate **10**. The array substrate further includes signal wirings **15** formed on the interlayer insulation film **13**. The signal wirings **15** may be used for forming either the power supply wirings with a ground wiring or the drive elements. A reference number "**20**", which is inserted in the drawing but not explained, indicates a bank layer. The bank layer **20** is used for not only defining the pixel regions within the active area but also forming the organic light emission diodes.

When the elements such as thin film transistors and the organic light emission diodes are formed on the lower substrate **10** as described above, a seal line **19** is formed along

edges of the lower substrate in such a manner as to be across the signal wirings **15** (or the power wirings). Then, the upper and lower substrates **20** and **10** are combined with each other.

As shown in the drawing, a protective film, which had been formed on the signal wiring **15** is removed in order to reduce a number of processes. In other words, the protective film formation process is removed from the recent manufacturing process of an OLED device. However, due to this, a stained fault is generated in an area in which the seal line **19** and the signal wiring **15** are disposed.

FIG. 2 is a photographic view showing a stained fault, which is generated in the seal line area of the OLED device according to the related art. Referring to FIG. 2, it is seen that a stained fault is generated in an area A, which includes the seal line **19** formed on the signal wiring **15**.

In other words, the stained fault which had been not generated in the case that the related art protective film is formed on the thin film transistor region of the active area and the signal wiring region of the pad area, is caused by removing the protective film formation process.

However, it is necessary to reduce a number of manufacturing processes by removing the protective film formation process, in order to provide high productivity and the cost reduction for the OLED device. Therefore, a new technology adapted to reduce a number of processes and prevent the stained fault must be developed.

### BRIEF SUMMARY

According to one general aspect of the present embodiment, an OLED device includes: a substrate defined into an active area in which a plurality of pixels are formed in a matrix shape, a GIP (gate-in-panel) area in which drive elements are formed, a ground contact area, and a seal line area; a thin film transistor formed in each pixel region within the active area; an organic light emission diode formed on a protective film and configured to include a first electrode, an organic light emission layer and a second electrode; a bank layer formed to divide the organic light emission diode into pixel units; a signal wiring formed in the ground contact area and the seal line area; and an extended portion formed from the same material as the first electrode of the organic light emission diode and configured to cover the signal wiring, wherein a seal line within in the seal line area is formed on an edge of the signal wiring, which is covered with the extended portion, and an interlayer insulation film adjacent to the edge of the signal wiring.

An OLED device manufacturing method according to another general aspect of the present embodiment includes: preparing a substrate defined into an active area in which a plurality of pixels will be formed in a matrix shape, a GIP (gate-in-panel) area in which drive elements will be formed, a ground contact area, and a seal line area; forming a thin film transistor, which is configured with a channel layer, a gate insulation film, a gate electrode, and source and drain electrodes, in each pixel region within the active area as well as a signal wiring on an interlayer insulation film corresponding to the seal line area and the ground contact area; forming a protective film on the substrate provided with the thin film transistor, and exposing a part of the drain electrode of the thin film transistor and the signal wiring through a contact hole formation process; and forming an organic light emission diode, which is configured with a first electrode, an organic light emission layer and a second electrode, on the substrate provided with the protective film, wherein an extended portion is formed to cover the signal wiring at the formation of the first electrode.

An OLED device according to still another general aspect of the present embodiment includes: a substrate defined into an active area in which a plurality of pixels will be formed in a matrix shape, a GIP (gate-in-panel) area in which drive elements will be formed, a ground contact area, and a seal line area; a thin film transistor formed in each pixel region within the active area; an organic light emission diode configured to include a first electrode, an organic light emission layer and a second electrode and formed on a protective film which is provided to cover the thin film transistor; a bank layer formed to divide the organic light emission diode into pixel units; a signal wiring formed in the ground contact area and the seal line area; and a seal line formed in the seal line area, wherein the signal wiring is formed in the same layer as a gate electrode of the thin film transistor between a gate insulation film and an interlayer insulation film, and the seal line opposite to the signal wiring is formed on the interlayer insulation film which is formed to cover the signal wiring.

An OLED device manufacturing method according to further still another general aspect of the present embodiment includes: preparing a substrate defined into an active area in which a plurality of pixels will be formed in a matrix shape, a GIP (gate-in-panel) area in which drive elements will be formed, a ground contact area, and a seal line area; forming a thin film transistor, which is configured with a channel layer, a gate electrode, and source and drain electrodes, in each pixel region within the active area as well as a signal wiring on a gate insulation film corresponding to the seal line area and the ground contact area at the formation of the gate electrode; forming a protective film on the substrate provided with the thin film transistor, and exposing a part of the drain electrode of the thin film transistor; forming an organic light emission diode, which is configured with a first electrode, an organic light emission layer and a second electrode, on the substrate provided with the protective film; and forming a seal line on an interlayer insulation film, which is formed to cover the signal wiring, within the seal line area and in direct contact with the interlayer insulation film.

Other systems, methods, features and advantages will be, or will become, apparent to one with skill in the art upon examination of the following figures and detailed description. It is intended that all such additional systems, methods, features and advantages be included within this description, be within the scope of the invention, and be protected by the following claims. Nothing in this section should be taken as a limitation on those claims. Further aspects and advantages are discussed below in conjunction with the embodiments. It is to be understood that both the foregoing general description and the following detailed description of the present disclosure are exemplary and explanatory and are intended to provide further explanation of the disclosure as claimed.

#### BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the embodiments and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the invention and together with the description serve to explain the disclosure. In the drawings:

FIG. 1 is a cross-sectional view showing a seal region of the OLED device according to the related art;

FIG. 2 is a photographic view showing a stained fault which is generated in a seal line area of the OLED device according to the related art;

FIG. 3 is a planar view showing the structure of an OLED device according to an embodiment of the present disclosure;

FIG. 4 is a cross-sectional view showing the OLED device taken along a line I-I' in FIG. 3;

FIGS. 5A to 5D are cross-sectional views illustrating a method of manufacturing an OLED device according to an embodiment of the present disclosure; and

FIGS. 6 and 7 are cross-sectional views showing OLED devices according to other embodiments of the present disclosure.

#### DETAILED DESCRIPTION OF THE DRAWINGS AND THE PRESENTLY PREFERRED EMBODIMENTS

Reference will now be made in detail to the embodiments of the present disclosure, examples of which are illustrated in the accompanying drawings. These embodiments introduced hereinafter are provided as examples in order to convey their spirits to the ordinary skilled person in the art. Therefore, these embodiments might be embodied in a different shape, so are not limited to these embodiments described here. In the drawings, the size, thickness and so on of a device can be exaggerated for convenience of explanation. Wherever possible, the same reference numbers will be used throughout this disclosure including the drawings to refer to the same or like parts.

FIG. 3 is a planar view showing the structure of an OLED device according to an embodiment of the present disclosure. FIG. 4 is a cross-sectional view showing the OLED device taken along a line I-I' in FIG. 3.

Referring to FIGS. 3 and 4, the OLED device 100 can be defined into an active area (an X area), a seal line area (a Z area) and a GIP (Gate-In-Panel) area (a Y area). The active area (X area) can be defined into a plurality of pixel regions arranged in a matrix shape. An organic light emission diode 230 and a thin film transistor TFT are formed in each of the pixel regions. The seal line area (Z area) occupying edges of the OLED device 100 is used for combining a lower substrate 200 with an upper substrate 300. The GIP area (Y area) is positioned between the active area (X area) and the seal line area (Z area). Gate drive circuit elements are formed in the GIP area (Y area).

A pad area 130 and a data driver area 140 can be provided in an edge of the OLED device 100. The pad area 130 is used for electrical connections with external signal connectors (not shown).

As shown in the drawings, a ground contact area positioned between the GIP area (Y area) and the seal line area (Z area) can be further included in the OLED device 100. Signal wirings 275 for ground connections are formed on the ground contact area. The signal wirings 275 are in electrical contact with the elements within the GIP area (Y area).

In the detailed structure of the OLED device according to an embodiment of the present disclosure, the thin film transistor TFT is formed in the active area (X area) of the lower substrate 200. The thin film transistor TFT is configured with a channel layer 214 formed on a buffer layer 201 which is formed on the lower substrate 200, a gate electrode 211 formed on a gate insulation film 202 which is formed to cover the channel layer 214, and source and drain electrodes 217a and 217b configured to contact source and drain regions of the channel layer 214 through contact holes which are formed with having the gate electrode 211 therebetween.

Also, the organic light emission diode 230 is formed over the thin film transistor TFT. The organic light emission diode 230 is configured with a first electrode (an anode) 220, an organic light emission layer 221 and a second electrode (a cathode) 223 sequentially formed opposite the thin film tran-

sistor TFT with having a protective film 209 therebetween. The protective film 209 is formed from an organic material.

The organic light emission diode 230 is divided into pixel units by a bank layer 240. The bank layer 240 is used for defining the plurality of pixel regions.

In order to reduce a number of mask processes, an embodiment of the present disclosure forces the bank layer 240 and a spacer 250 to be formed in a single body using a single mask such as a half-tone mask or a diffractive mask.

Similarly to the active area (X area), the buffer layer 201 and the gate insulation film 202 are also formed on the lower substrate 200 corresponding to the GIP area (Y area), the ground contact area and the seal line area (Z area). Moreover, a plurality of drive elements (not shown) and a power supply wiring 247 is formed on the gate insulation film 202 corresponding to the GIP area (Y area).

Also, the protective film 209 is formed on the lower substrate where the plurality of drive elements are formed. A first connection electrode 270 positioned at the same layer as the first electrode 220 and a second connection electrode 260 extended from the second electrode 223 are sequentially formed on the protective film 209. The first and second connection electrodes 270 and 260 are used for grounding the second electrode 223 of the organic light emission diode 230 within the active area (X area).

The first and second connection electrodes 270 and 260 are in electrical contact with each other through a contact hole, which is formed in the bank layer 240. An extended portion 270a is formed to extend from the first connection electrode 270 to the seal line area (Z area) and electrically contact a signal wiring 275. The signal wiring 275 can become a ground wiring. The extended portion 270a configured to extend from the first electrode 270 completely covers the signal wiring 275 which is formed on the interlayer insulation film 212 corresponding to the ground contact area and the seal line area (Z area).

A seal line 400 is formed on the signal wiring 275 covered with the extended portion 270a.

In this manner, the OLED device according to an embodiment of the present disclosure enables the signal wiring 275 formed in the seal line area (Z area) and the ground contact area to be covered with the extended portion 270a, which is formed to extend from the first connection electrode 270 at the formation of the first electrode 220 of the organic light emission diode 230, instead of the protective film. As such, the seal line 400 directly contacts the extended portion 270a. In other words, the seal line 400 contacts the extended portion 270a with a superior adhesive property. In accordance therewith, the combining characteristic of the lower and upper substrates 200 and 300 can be enhanced.

Also, the OLED device according to an embodiment of the present disclosure forces the signal wiring 275 to be positioned in an inner direction from the center of the seal line 400 toward the center of the lower substrate 200. As such, the seal line 400 contacts the interlayer insulation film 212, adjacent to the signal wiring 275, and the extended portion 270a covering the signal wiring 275. In accordance therewith, the deterioration fault of the organic light emission diode 230 due to the intrusion of moisture can be prevented.

FIGS. 5A to 5D are cross-sectional views illustrating a method of manufacturing an OLED device according to an embodiment of the present disclosure.

Referring to FIGS. 5A through 5D, a buffer layer 201 is formed on a lower substrate 200 which is defined into an active area (X area), a GIP area (Y area), a ground contact area, and a seal line area (Z area).

As an example of the lower substrate 200, an insulated glass, plastic, or conductive substrate can be used. The buffer layer 201 can be formed from either an organic insulation material such as polyimide, photoacrylic and so on, or an inorganic insulation material such as SiN<sub>x</sub> and SiO<sub>2</sub>.

A thin film transistor TFT of the top-gate type is formed in the active area (X area). In order to form the thin film transistor TFT, a channel layer 214 is formed on the buffer layer 201. The channel layer 214 includes a channel region and source/drain regions doped with impurities. An gate insulation film 202 is formed on the entire surface of the lower substrate 200 provided with the channel layer 214.

The channel layer 214 can be prepared by forming an amorphous silicon layer on the buffer layer 201 and crystallizing the amorphous silicon into a crystalline silicon layer through a heat treatment process. The gate insulation film 202 can be formed from an inorganic insulation material such as silicon nitride SiN<sub>x</sub>, silicon oxide SiO<sub>x</sub>, and so on. Also, the gate insulation film 202 can include either a single layer formed from one of the inorganic insulation materials, or multiple layers formed from different inorganic insulation materials.

After the above-mentioned gate insulation film 202 is formed on the lower substrate 200, a gate electrode 211 is formed on the gate insulation film 202 opposite to the channel layer 214. The gate electrode 211 can be prepared by forming a metal film on the entire area of the lower substrate 200 and patterning the metal film through a mask process.

At the same time, a power supply wiring 247 and other gate electrodes of transistors included in a plurality of drive elements, which are not shown in the drawings, are formed on the GIP area (Y area) of the lower substrate 200 (more specifically, on the gate insulation film 202 corresponding to the GIP area (Y area)).

Meanwhile, the buffer layer 201 and the gate insulation film 202 are stacked on the lower substrate 200 corresponding to the seal line area (Z area) and the ground contact area.

As shown in FIG. 5C, an interlayer insulation film 212 is formed on the entire surface of the lower substrate 200 and contact holes are formed in the interlayer insulation film 212 opposite to the source/drain regions of the channel layer 214 through a contact hole formation process, after the formation of the above-mentioned gate electrode 211 and so on.

Thereafter, the thin film transistor is completed by forming source/drain electrodes 217a and 217b which are being in electrical contact with the source/drain regions of the channel layer 214, respectively. The source/drain electrodes 217a and 217b are formed by depositing a source/drain metal film on the entire surface of the lower substrate 200 and patterning the source/drain metal film through another mask process.

The source/drain metal film can be formed in either a single layer or a structure of multiple layers, formed from copper Cu, aluminum Al, aluminum alloy AlNd, molybdenum Mo, chrome Cr, titanium Ti, tantalum Ta, molybdenum-tungsten MoW, alloys thereof, and so on.

At the same time, signal wirings 275 are formed on the interlayer insulation film 212 corresponding to the seal line area (Z area) and the ground contact area. Data lines and source/drain electrodes of transistors, which are not shown in the drawings, are also formed in the interlayer insulation film 212 corresponding to the GIP area (Y area).

After the above-mentioned thin film transistor TFT is completed, a protective film 209 is formed on the entire surface of the lower substrate 200. Still another mask process is performed for the protective film 209 so that a contact hole is formed in the protective film 209 opposite to the drain elec-

trode **217b** and the signal wirings formed in the seal line area (Z area) and the ground contact area are externally exposed.

The protective film **209** can be formed from either an inorganic insulation material or an organic insulation material such as BCB (benzocyclobutene), an acrylic-based resin, PFCB, or others. Also, the protective film **209** can be formed by applying one of the above-mentioned materials through a spin coating method and so on.

Afterward, a first electrode **220** for an organic light emission diode **230** is formed on the protective film **209** in such a manner as to electrically contact the drain electrode **217b** of the thin film transistor TFT. The first electrode **220** of the organic light emission diode **230** is prepared by forming a metal film on the entire surface of the above-mentioned lower substrate **200** and patterning the metal film through further still another mask process.

The first electrode **220** can be formed from a transparent conductive material such as ITO (indium tin oxide), TO (tin oxide), IZO (indium zinc oxide), ITZO (indium tin zinc oxide), or others. Alternatively, the first electrode **220** can be formed with a structure of double or triple layers including a metal film such as a silver film.

When the first electrode **220** is formed, a first connection electrode **270** and an extended portion **270a** configured to extend from the first electrode to the seal line area (Z area) are simultaneously formed in the GIP area (Y area), the ground contact area and the seal line area (Z area). The first connection electrode **270** and the extended portion **270a** are formed in a single body united with each other and from the same material.

According to the manufacturing method of the present embodiment, the extended portion **270a** is formed to completely cover the signal wirings **275** which is externally exposed by removing the protective film **209**. As such, the signal wirings **275** can be screened from the exterior by the extended portion **270a**.

After the above-mentioned first electrode **220** is formed, a bank layer **240** for defining a formation area of the organic light emission diode **230** into pixel units and a spacer **250** are formed in a single body united with each other. The bank layer **240** and the spacer **250** can be prepared by forming an organic film on the entire surface of the above-mentioned lower substrate **200** and patterning the organic film using either a half-tone mask or a diffractive mask.

More specifically, the organic film is formed to have a thickness corresponding to the height of the spacer **250**. Also, the organic film is patterned by allowing a semi-transmission region of the half-tone mask or a diffractive pattern of the diffractive mask to be opposite the bank layer **240**, a non-transmission region of the half-tone mask or diffractive mask to be opposite the spacer **250**, and a transmission region of the half-tone mask or the diffractive mask to be opposite a region of the first electrode **220** which will be exposed.

Thereafter, an organic light emission layer **221** and a second electrode **223** are sequentially formed on the exposed portion of the first electrode **220**. In accordance therewith, the organic light emission diode **230** is completed.

In other words, the bank layer **240** defines the active area (X area) of the OLED device **100** into pixel units. Red, green, blue, or white organic light emission layer **221** can be formed in each of the pixel regions.

A reference number “**260**”, which is inserted in the drawings but not explained, indicates a second connection electrode. The second connection electrode **260** is formed in a single body united with the second electrode **223**. Also, the second connection electrode **260** comes in electrical contact

with the first connection electrode **270**, which is formed under the bank layer in the GIP area (Y area).

After the above-mentioned organic light emission diode **230** is formed on the lower substrate **200**, a seal line **400** is formed on the lower substrate **200** corresponding to the seal line area (Z area), and then an upper substrate **300** is combined with the lower substrate **200**. In accordance therewith, the OLED device is completed.

Particularly, the OLED device manufacturing method of the present embodiment forces the seal line **400** to be formed on edges of the signal wiring **275** and the extended portion **270a** as well as the interlayer insulation film **212** adjacent to the signal wiring **275**. As such, the signal wiring **275** is not exposed to the exterior unlike that of the related art.

Moreover, the seal line **400** directly contacts the extended portion **270a** covering the signal line **275** without being in direct contact with the signal wiring **275**. As such, the contacting property of the seal line **400** can be enhanced compared to when it is in contact with the signal wiring **275**.

In this way, the OLED device manufacturing method of the present embodiment forces the signal wirings formed along outlines of the active area to be covered with the extended portion, which is formed from a metal material. As such, the OLED device can prevent external moisture intrusion.

Also, the OLED device manufacturing method of the present embodiment forces edges of the signal wiring **275** and the extended portion **270a** to be positioned in an inner direction of the OLED device **100** tending from the center of the seal line **400** within the seal line area (Z area) toward the active area (X area). In accordance therewith, a deterioration phenomenon of the organic light emission diode **230**, which can be caused by moisture intrusion, can be prevented.

FIGS. **6** and **7** are cross-sectional views showing OLED devices according to other embodiments of the present disclosure. Reference numbers of FIGS. **6** and **7** being the same as those of FIG. **4** correspond to the same components. Therefore, the OLED devices of FIGS. **6** and **7** will be explained in regards to the components, which are distinguished from those of FIG. **4**.

Referring to FIG. **6**, the OLED device according to another embodiment of the present disclosure can be defined into an active area (X area), a seal line area (Z area), a GIP area (Y area) and a ground contact area. The active area (X area) can be defined into a plurality of pixel regions arranged in a matrix shape. An organic light emission diode **230** and a thin film transistor TFT are formed in each of the pixel regions. The seal line area (Z area) occupying edges of the OLED device **100** is used for combining a lower substrate **200** with an upper substrate **300**. The GIP area (Y area) is positioned between the active area (X area) and the seal line area (Z area). Gate drive circuit elements are formed in the GIP area (Y area).

According to another embodiment of the present disclosure, a buffer layer **201**, a channel layer **214** and a gate insulation film **202** are sequentially formed on the lower substrate **200**, and then a gate electrode **211** is formed on the gate insulation film **202** opposite to the channel layer **214**. The gate electrode **211** can be prepared by forming a metal film on the entire surface of the lower substrate **200** with the gate insulation film **202** and patterning the metal film through a mask process.

At the formation of the gate electrode **211**, a power supply wiring **247** in the GIP area (Y area) and signal wirings **375** in the seal line area (Z area) and the ground contact area are simultaneously formed.

After the formation of the above-mentioned gate electrode **211** and signal wirings **375**, an interlayer insulation film **212** is formed on the entire surface of the lower substrate **200**.

When, the above-mentioned interlayer insulation film **212** is formed on the lower substrate **200**, contact holes are formed in regions of the interlayer insulation film opposite to source/drain regions of the channel layer **214** through a contact hole formation process. At the same time, still another contact hole can be formed in still another region of the interlayer insulation film **212** opposite to the signal wirings **375**. Although it is not shown in the drawing, still another contact hole will be used for bringing a first connection electrode **370** into electrical contact with one of the signal wirings **375** later.

Subsequently, source/drain electrodes **217a** and **217b** being in electrical contact with the source/drain regions of the channel layer **214** are formed, so that a thin film transistor is completed. The source/drain electrodes **217a** and **217b** can be prepared by forming a source/drain metal film on the entire surface of the lower substrate **200** with the contact holes and patterning the source/drain metal film through another mask process.

The source/drain metal film can be formed in a single layer or a multi-layer structure. The single layer and the multi-layers can be formed from copper Cu, aluminum Al, aluminum alloy AlNd, molybdenum Mo, chrome Cr, titanium Ti, tantalum Ta, molybdenum-tungsten MoW, alloys thereof, and so on.

After the above-mentioned thin film transistor is completed, a protective film **209** is formed on the entire surface of the lower substrate **200**. Still another mask process is performed for the protective film **209** so that a contact hole is formed in the protective film **209** opposite to the drain electrode **217b**. Also, another contact hole exposing one of the signal wirings **375** which are formed in the seal line area (Z area) and the ground contact area can be formed through still another mask process.

In other words, the contact hole used for electrically connecting the signal wiring **375** with the first connection electrode **370** is formed when forming another contact hole in the protective film **209**, not when forming still another contact holes in the interlayer insulation film **212**. When another contact hole is formed in the protective film **209**, the contact hole for connecting the signal wiring **375** with the first connection electrode **370** can be formed by sequentially removing regions of the protective film **209** and the interlayer insulation film **212** which are opposite the signal wiring **375**.

More specifically, the protective film **209** within the seal line area (Z area) and the ground contact area is removed to expose the interlayer insulation film **212** when another contact hole is formed in the protective film **202**. Then, the above-mentioned contact hole exposing a part of the signal wirings **375** can be formed in the interlayer insulation film **212**.

The protective film **209** can be formed from either an inorganic insulation material or an organic insulation material such as BCB (benzocyclobutene), an acrylic-based resin, PFCB, or others. Also, the protective film **209** can be formed by applying one of the above-mentioned materials through a spin coating method and so on.

Afterward, a first electrode **220** for an organic light emission diode **230** is formed on the protective film **209** in such a manner as to electrically contact the drain electrode **217b** of the thin film transistor TFT. The first electrode **220** of the organic light emission diode **230** is prepared by forming a metal film on the entire surface of the above-mentioned lower substrate **200** and patterning the metal film through further still another mask process.

The first electrode **220** can be formed from a transparent conductive material such as ITO (indium tin oxide), TO (tin oxide), IZO (indium zinc oxide), ITZO (indium tin zinc

oxide), or others. Alternatively, the first electrode **220** can be formed with a structure of double or triple layers including a metal film such as a silver film.

When the first electrode **220** is formed, the first connection electrode **370** can be simultaneously formed in the GIP area (Y area), the ground contact area and the seal line area (Z area). The first connection electrode **370** is formed from the same material. Such a first connection electrode **370** is formed on the protective film **209** and comes in electrical contact with a second connection electrode **260** which will be formed later.

Thereafter, an organic light emission diode **230**, the second connection electrode **260** and a seal line **400** are formed through the same processes as those described in FIG. 4. As such, the detailed description regarding the formation of the organic light emission diode **230**, the second connection electrode **260** and the seal line **400** will be omitted to avoid overlapping.

In this manner, another embodiment of the present disclosure forces the signal wirings **375** overlapped with the seal line **400** to be not only formed on the gate insulation film **202** but also completely covered with the interlayer insulation film **212** which is formed later. As such, the seal line **400** comes into direct contact with the upper substrate **300** and the interlayer insulation film **212** of the lower substrate **200**. Therefore, the adhesive property of the seal line **400** for the interlayer insulation film **212** can be largely enhanced compared to that for the metal pattern.

Also, another embodiment of the present disclosure makes the signal wirings disposed under the seal line to be formed between the gate insulation film and the interlayer insulation film. In accordance therewith, a deterioration phenomenon of the organic light emission diode, which can be caused by moisture intrusion can be prevented.

Furthermore, another embodiment of the present disclosure allows the signal wirings to be formed under an insulation film (more specifically, under the interlayer insulation film) so that the signal wirings are not exposed to the outside of the seal line area. Therefore, moisture intrusion into the signal wiring area in which the seal line is formed can be prevented.

As shown in FIGS. 3 and 4, the signal wirings **275** can be formed in the seal line area (Z area) and the ground contact area in such a manner as to be positioned in a inner direction from the seal line **400** toward an active area (X area). In this case, the resistance of the signal wiring **275** must increase because of its narrowed width.

To address this matter, still another embodiment of the present disclosure forces an auxiliary signal wiring **475** to be formed on the gate insulation film **202** at the formation of the gate electrode, as shown in FIG. 7. Subsequently, a through hole H is formed in the interlayer insulation film **212** opposite to the auxiliary signal wiring **475** when the contact holes for the source/drain electrodes **217a** and **217b** are formed in the interlayer insulation film **212**. Thereafter, the auxiliary signal wiring **475** comes into electrical contact with a signal wiring **275** via the through hole H when the signal wiring **275** is formed on the interlayer insulation film **212**. In accordance therewith, the resistance increment of the signal wiring **275** can be prevented or alleviated.

Also, still another embodiment of the present disclosure covers the signal wiring **275** within the seal line area (Z area) and the ground contact area with an extended portion **270a**, which is formed to extend from the a first electrode at the formation of the signal wiring **275**, instead of the protective film **209**. As such, a seal line **400** comes into direct contact with the extended portion **270a**. In other words, the seal line

400 contacts the extended portion 270a with a superior adhesive property. In accordance therewith, the combining characteristic of the lower and upper substrates 200 and 300 can be enhanced.

Moreover, the OLED device according to an embodiment of the present disclosure forces the signal wiring 275 to be positioned in an inner direction from the center of the seal line 400 toward the center of the lower substrate 200. As such, the seal line 400 contacts the interlayer insulation film 212, adjacent to the signal wiring 275, and the extended portion 270a covering the signal wiring 275. In accordance therewith, the deterioration fault of the organic light emission diode 230 due to the intrusion of moisture can be prevented.

Particularly, still another embodiment of the present disclosure can solve the resistance increment of the signal wiring 275 caused by the narrowed width. To this end, the auxiliary signal wiring 475 is formed on the gate insulation film 202 opposite to the signal wiring 275 in such a manner as to be electrically connected to the signal wiring 275.

Although the present disclosure has been limitedly explained regarding only the embodiments described above, it should be understood by the ordinary skilled person in the art that the present disclosure is not limited to these embodiments, but rather that various changes or modifications thereof are possible without departing from the spirit of the present disclosure. Accordingly, the scope of the present disclosure shall be determined only by the appended claims and their equivalents.

The invention claimed is:

1. A method of manufacturing an organic light emitting display device, the method comprising:
  - preparing a substrate defined into an active area in which a plurality of pixels will be formed in a matrix shape, a GIP (gate-in-panel) area in which drive elements will be formed, a ground contact area, and a seal line area;
  - forming a thin film transistor, which is configured with a channel layer, a gate insulation film, a gate electrode, and source and drain electrodes, in each pixel region within the active area as well as a signal wiring on an interlayer insulation film corresponding to the seal line area and the ground contact area;
  - forming a protective film on the substrate provided with the thin film transistor, and exposing a part of the drain electrode of the thin film transistor and the signal wiring through a contact hole formation process;
  - forming an extend portion on the signal wiring; and
  - forming an organic light emission diode, which is configured with a first electrode, an organic light emission layer and a second electrode, on the protective film, wherein the extended portion is formed on the signal wiring simultaneously with formation of the first electrode.
2. The method claimed as claim 1, wherein the formation of the organic light emission diode further includes:
  - forming a material layer on the protective film, the material layer including a first portion defining a bank layer and a second portion defining a spacer, wherein the bank

layer is configured to divide the active area into pixel regions, and the second portion extends upwardly from the first portion, the first and second portions being a single body.

3. The method claimed as claim 1, further comprises forming a seal line configured to directly contact an edge of the signal wiring and the interlayer insulation film adjacent to the edge of the signal wiring.

4. The method claimed as claim 1, wherein a first connection electrode is formed on the protective film and electrically connected to a second connection electrode, wherein the second connection electrode is simultaneously with formation of the second electrode of the organic light emission diode, the second connection electrode and the second electrode are formed as a single body.

5. The method claimed as claim 1, wherein the protective film is formed from one of an inorganic insulation material and organic insulation materials including BCB (benzocyclobutene), an acryl-based resin and PFCB.

6. The method claimed as claim 1, further comprising forming an auxiliary signal wiring on the gate insulation film simultaneously with formation of the gate electrode, the auxiliary signal wiring being disposed opposite to the signal wiring with the interlayer insulation film disposed therebetween.

7. The method claimed as claim 6, wherein the auxiliary signal wiring is electrically connected to the signal wiring via a through hole formed in the interlayer insulation film.

8. A method of manufacturing an organic light emitting display device, the method comprising:

- preparing a substrate defined into an active area in which a plurality of pixels will be formed in a matrix shape, a GIP (gate-in-panel) area in which drive elements will be formed, a ground contact area, and a seal line area;
- forming a thin film transistor, which is configured with a channel layer, a gate electrode, and source and drain electrodes, on a gate insulation film in each pixel region within the active area;
- forming a signal wiring on the gate insulation film corresponding to the seal line area and the ground contact area simultaneously with formation of the gate electrode;
- forming a protective film on the substrate provided with the thin film transistor, and exposing a part of the drain electrode of the thin film transistor;
- forming an organic light emission diode, which is configured with a first electrode, an organic light emission layer and a second electrode, on the substrate provided with the protective film; and
- forming a seal line on an interlayer insulation film, which is formed to cover the signal wiring, within the seal line area and in direct contact with the interlayer insulation film.

\* \* \* \* \*

专利名称(译)	有机发光显示装置及其制造方法		
公开(公告)号	<a href="#">US9362533</a>	公开(公告)日	2016-06-07
申请号	US14/732264	申请日	2015-06-05
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	CHOI HEE DONG JEON SEUNG JOON		
发明人	CHOI, HEE DONG JEON, SEUNG JOON		
IPC分类号	H01L27/32 H01L51/56 H01L51/52		
CPC分类号	H01L51/56 H01L27/3244 H01L27/3276 H01L51/5203 H01L51/5246 H01L27/3246 H01L27/3279 H01L23/26 H05B33/04		
优先权	1020110087327 2011-08-30 KR		
其他公开文献	US20150270513A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

公开了一种OLED器件。OLED器件包括：限定在有源区中的基板，其中多个像素以矩阵形状形成，GIP（面板中栅）区域，其中形成驱动元件，接地区域和密封线区；在有源区域内的每个像素区域中形成薄膜晶体管；有机发光二极管，形成在保护膜上，并包括第一电极，有机发光层和第二电极；形成的堤层用于将有机发光二极管分成像素单元；信号布线形成在接地区域和密封线区域中；延伸部分由与有机发光二极管的第一电极相同的材料形成，并构成覆盖信号布线，其中密封线区域内的密封线形成在信号布线的边缘上，其被覆盖具有延伸部分，以及与信号布线的边缘相邻的层间绝缘膜。这样的OLED装置可以通过大量形成连接电极来防止在密封线区域中产生污染的故障，该连接电极与沿着有源区域的边缘形成的信号布线接触，并且用金属图案覆盖信号布线。

