



US009130181B2

(12) **United States Patent**
Choi et al.

(10) **Patent No.:** **US 9,130,181 B2**
(45) **Date of Patent:** **Sep. 8, 2015**

(54) **ORGANIC LIGHT EMITTING DISPLAY AND METHOD FOR MANUFACTURING THE SAME**

(71) Applicant: **LG DISPLAY CO., LTD.**, Seoul (KR)

(72) Inventors: **Ho-Won Choi**, Daegu (KR); **Jae-Do Lee**, Gumi-si (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/718,391**

(22) Filed: **Dec. 18, 2012**

(65) **Prior Publication Data**

US 2014/0061597 A1 Mar. 6, 2014

(30) **Foreign Application Priority Data**

Aug. 31, 2012 (KR) 10-2012-0096740

(51) **Int. Cl.**

H01L 51/44 (2006.01)

H01L 27/32 (2006.01)

H01L 51/00 (2006.01)

H01L 51/52 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/447** (2013.01); **H01L 27/323** (2013.01); **H01L 51/0001** (2013.01); **H01L 51/5284** (2013.01)

(58) **Field of Classification Search**

CPC H01L 51/447; H01L 51/0001

USPC 257/40, 91, E21.001; 438/29, 23

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,068,261	B2 *	6/2006	Kubo et al.	345/173
2005/0059179	A1	3/2005	Erchak et al.	
2008/0211394	A1 *	9/2008	Koshihara et al.	313/504
2010/0033443	A1 *	2/2010	Hashimoto	345/173
2010/0066683	A1	3/2010	Chang et al.	
2010/0110041	A1	5/2010	Jang	
2010/0265206	A1 *	10/2010	Chen	345/174
2011/0109622	A1 *	5/2011	Son et al.	345/419
2011/0273397	A1 *	11/2011	Hanari	345/174

FOREIGN PATENT DOCUMENTS

EP	1426813	A2	6/2004
JP	2010-243930	A	10/2010

(Continued)

OTHER PUBLICATIONS

Extended European Search Report issued in corresponding European Patent Application No. 12196447.2, mailed Jan. 2, 2014, 10 pages.

(Continued)

Primary Examiner — Sheng Zhu


(74) Attorney, Agent, or Firm — Brinks Gilson & Lione

(57)

ABSTRACT

Disclosed are an organic light emitting display that has a configuration excluding a polarizing plate and exhibits improved flexibility and visibility, and a method for manufacturing the same, the organic light emitting display includes a touch electrode array facing the organic light emitting diode on the second buffer layer, the touch electrode array including first and second touch electrodes intersecting each other and an exterior light shielding layer including at least a color filter layer, an adhesive layer formed between the organic light emitting diode and the touch electrode array.

19 Claims, 10 Drawing Sheets



(56)

References Cited

FOREIGN PATENT DOCUMENTS

KR	10-2008-0080912 A	9/2008
KR	10-2011-0052241 A	5/2011
TW	1361496 B	4/2012

OTHER PUBLICATIONS

Office Action issued in Taiwanese Patent Application No. 101149192, mailed Feb. 3, 2015, 24 pages.

Office Action issued in Korean Patent Application No. 10-2012-0096740, mailed Feb. 26, 2015, 4 pages.

* cited by examiner

FIG. 1
RELATED ART





FIG. 2

FIG. 3




FIG. 4






FIG. 5**FIG. 6**

FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D






FIG. 7E



[illegible]

FIG. 9



ORGANIC LIGHT EMITTING DISPLAY AND METHOD FOR MANUFACTURING THE SAME

This application claims the benefit of Korean Patent Application No. 10-2012-0096740, filed on Aug. 31, 2012, which is hereby incorporated by reference as if fully set forth herein.

BACKGROUND

1. Field of the Disclosure

The present disclosure relates to an organic light emitting display, and more particularly, to an organic light emitting display that has a configuration excluding a polarizing plate and exhibits improved flexibility and visibility, and a method for manufacturing the same.

2. Discussion of the Related Art

Examples of flat panel displays include liquid crystal displays (LCDs), organic light emitting displays (OLEDs), plasma display panels (PDPs), quantum dot panels (PDPs), field emission displays (FEDs), electrophoretic displays (EPDs) and the like. These displays include a flat display panel realizing an image in common as an essential component. In such a flat display panel, a pair of transparent insulating substrates are joined together such that they face each other via a layer containing an inherently luminescent or polarizing material or other optical material interposed therebetween.

In accordance with the recent trend toward large-size displays, demand has gradually increased for flat panel displays that occupy a smaller space. Of these flat panel displays, organic light emitting display technologies are being rapidly developed.

Organic light emitting displays do not require any separate light source and include an organic light emitting diode that spontaneously emits light in each pixel, to realize display. The organic light emitting displays attract much attention as next-generation displays since they advantageously do not require light sources as well as structures for assembling the light sources with a display panel, thus having advantages of decrease in thickness and weight.

When electric charges are injected into an organic film formed between an electron injection electrode (cathode) and a hole injection electrode (anode), electrons pair with holes and the pairs then decay. At this time, an organic light emitting diode emits light.

There is an increasing demand for an organic light emitting display of a touchscreen in which a site touched by the hand or separate input element is sensed and information is transferred in response thereto. Such a touchscreen is typically applied by adhesion to the outer surface of the display.

Depending on touch sense method, a touchscreen is divided into resistive, capacitive and infrared sensing types. In consideration of ease of manufacture, sensing force and the like, capacitive type touchscreens attract much attention in small models.

Hereinafter, a touchscreen-integrated organic light emitting display of related art will be described with reference to the annexed drawings.

FIG. 1 is a sectional view illustrating a touchscreen-integrated organic light emitting display of related art.

As shown in FIG. 1, the touchscreen-integrated organic light emitting display of related art includes an organic light emitting display panel 1, a touchscreen 2 and a cover window 3 laminated in this order from the bottom and includes first and second adhesive layers 15 and 25 disposed between the respect layers.

Here, the organic light emitting display panel 1 includes a substrate, a thin film transistor array having a matrix form disposed on the substrate, and an organic light emitting diode connected to each thin film transistor of the thin film transistor array, and includes a protective film and a polarizing layer that cover the top of the organic light emitting diode. In this case, the first adhesive layer 15 corresponds to the polarizing layer of the organic light emitting display panel 1. Also, the second adhesive layer 25 is formed between the touchscreen 2 and the cover window 3 to adhere the touchscreen 2 to the cover window 3.

The touchscreen-integrated organic light emitting display has the following disadvantages.

First, in a case in which an organic light emitting display panel and a touchscreen are independently formed and the touchscreen is then attached to the organic light emitting display panel, the organic light emitting display panel and the touchscreen require separate glasses, thus causing increase in hardness and thickness, which makes realization of thin and flexible organic light emitting displays impossible.

Second, the organic light emitting display panel and the touchscreen have different panel shapes, thus making processes for forming these components complicated and thus decreasing yield and price competitiveness.

Third, a polarizing plate is provided in order to prevent recognition of exterior light of the organic light emitting display panel. The polarizing plate has a thickness of about 150 μm or more, is expensive and causes a deterioration in transmittance. Accordingly, since the polarizing plate deteriorates flexibility when used for displays and is expensive, other alternative capable of preventing deterioration in visibility is required.

SUMMARY

An organic light emitting display includes: a first buffer layer and a second buffer layer facing each other; a thin film transistor array including a thin film transistor in each of a plurality of pixels defined in a matrix on the first buffer layer; an organic light emitting diode connected to a thin film transistor of each pixel; a touch electrode array facing the organic light emitting diode on the second buffer layer, the touch electrode array including first and second touch electrodes intersecting each other, and an exterior light shielding layer including at least a color filter layer; an adhesive layer between the organic light emitting diode and the touch electrode array; a cover glass on a rear surface of the second buffer layer; and a film substrate on a rear surface of the first buffer layer.

In accordance with another aspect of the present invention, provided is a method for fabricating an organic light emitting display including: forming a first etch stopper film and a first buffer layer on a first substrate, and forming a thin film transistor array including a thin film transistor in each of a plurality of pixels defined in a matrix form and an organic light emitting diode connected to a thin film transistor of each pixel in an active region of the first buffer layer; forming a second etch stopper film and a second buffer layer on a second substrate; forming a touch electrode array facing the organic light emitting diode on the second buffer layer, wherein the touch electrode array includes first and second touch electrodes intersecting each other, and an exterior light shielding layer including at least a color filter layer; joining the first and second substrates via an adhesive layer between the organic light emitting diode and the touch electrode array; removing the first substrate and the second substrate; and adhering a

3

film substrate to the exposed first etch stopper film and covering the exposed second etch stopper film with a cover glass.

It is to be understood that both the foregoing general description and the following detailed description of the present invention are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the invention and simultaneously with the description serve to explain the principle of the invention. In the drawings:

FIG. 1 is a sectional view illustrating a touchscreen-integrated organic light emitting display of related art;

FIG. 2 is a plan view illustrating an organic light emitting display according to an embodiment of the present invention;

FIG. 3 is a sectional view taken along the line I-I' of FIG. 2;

FIG. 4 is an enlarged plan view of a region "A" of FIG. 2;

FIG. 5 is a sectional view taken along the line II-II' of FIG. 4 according to a first embodiment of the present invention;

FIG. 6 is a view illustrating a process of forming a touch electrode array of an organic light emitting display according to the present invention;

FIGS. 7A to 7E illustrate a touch electrode array according to an organic light emitting display according to another embodiment;

FIG. 8 is a sectional view illustrating an organic light emitting display according to a modified embodiment of the present invention; and

FIG. 9 is a reference embodiment of the present invention compared with the organic light emitting display in terms of visibility.

DETAILED DESCRIPTION OF THE EXEMPLARY EMBODIMENTS

Reference will now be made in detail to the preferred embodiments of the present invention, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers will be used throughout the drawings to refer to the same or like parts.

Hereinafter, an organic light emitting display and a method for manufacturing the same will be described in detail with reference to the annexed drawings.

In recent years, there has been an increasing demand for touch sensing as well as thinness and flexibleness of organic light emitting displays. In response to this, a method in which a thin film transistor and an organic light emitting array are formed on a first substrate, a touch electrode array is formed on a second substrate, these substrates are joined together, and the hard and thick first and second substrates are removed by laser irradiation or etching in order to realize thin film and flexibility is suggested. In this case, a pad portion of the touch electrode array faces a pad portion of the organic light emitting array, and these pad portions are connected to each other via a conductive ball, thus enabling transfer of signals to the touch electrode array and detection of signals from the touch electrode array.

Hereinafter, an in-cell organic light emitting display in which a touch electrode array is provided inside a cover glass will be described.

4

FIG. 2 is a plan view illustrating an organic light emitting display according to the present invention. FIG. 3 is a sectional view taken along the line I-I' of FIG. 2.

As shown in FIG. 2 and FIG. 3, the organic light emitting display according to the present invention has a configuration in which an organic light emitting array 150 and a touch electrode array 230, that are formed at an inside of a film substrate 1000 and at an inside of a cover glass 3000, respectively, and have different sizes, are joined to each other via an adhesive layer 400.

Also, the organic light emitting display according to the present invention excludes a polarizing plate under a cover glass, and further includes an exterior light shielding layer 2400 including a black matrix layer (represented by "242" in FIG. 5) and a color filter layer (represented by "241" in FIG. 5) in the touch electrode array that performs a function of preventing recognition of exterior light, instead of the polarizing plate. The black matrix layer and the color filter layer prevent emission of incident light in order to prevent exterior light incident upon the organic light emitting display from being reflected and be seen by a viewer. A detailed description of the touch electrode array having this configuration will be provided with reference to FIG. 5.

These arrays are not directly formed on the film substrate 1000 or the cover glass 3000 and are obtained by separately preparing first and second substrates (both, not shown), each being made of glass, joining the substrates via an adhesive layer disposed between the organic light emitting array 150 and the touch electrode array 230 (that is, this joining process is performed while keeping the first and second substrates), and removing the first and second substrates by laser irradiation or etching for realization of thin film and flexibility. In this case, as shown in FIG. 2, the first and second substrates formed of glass materials are removed and the film substrate 1000 and the cover glass 3000 are adhered to the bottom of the exposed arrays, respectively, in order to protect these arrays.

A film adhesive layer 1100, a first etch stopper layer 120, a first buffer layer 130 and a thin film transistor array 140 and an organic light emitting array 150 are formed on the film substrate 1000 in this order and a protective layer 160 is formed to cover the organic light emitting array 150. A second etch stopper layer 210, a second buffer layer 220 and a touch electrode array 230 are disposed on the cover glass 3000. The touch electrode array 230 is disposed to face the organic light emitting array 150. In this case, the protective layer 160 directly contacts the bottom of the adhesive layer 400 and the touch electrode array 230 directly contacts the top thereof.

An active region and a dead region are defined in the first buffer layer 130 and the second buffer layer 220, respectively, and the touch electrode array 230, the organic light emitting array 150 and thin film transistors present in the thin film transistor array 140 excluding a pad portion are formed in the active region. Also, the touch electrode pad portion 2350 and the pad portion of the thin film transistor array are defined in part regions of the dead region.

The first etch stopper layer 120 and the second etch stopper layer 210 function to prevent damage to an internal array, in addition to the glass materials of first and second substrates during laser irradiation or etching. If desired, the first and second buffer layers 130 and 220 disposed thereunder are not damaged during removal of the first and second substrates, the first and/or second etch stopper layers 120 and 210 may be omitted.

Also, the first buffer layer 130 and the second buffer layer 220 may be formed by sequentially laminating the same type of inorganic film such as an oxide film (SiO_2) or nitride film (SiN_x), or alternatively laminating different types of inor-

ganic films. The first and second buffer layers **130** and **220** serve as barriers that prevent permeation of moisture or exterior air into the organic light emitting array **150** after the second substrate is joined to the first substrate.

Also, both the touch pad portion **2350** and the touch electrode array **230** are formed on the same surface of the second buffer layer **220**.

The touch pad portion **2350** is connected to the pad portion of the thin film transistor array **140** via a sealant **450** including a conductive ball **455**, when the upper and lower substrates are joined to each other via the adhesive layer **400**. The adhesive layer **400** functions to prevent permeation of moisture and directly contacts the protective layer **160** that covers the organic light emitting array **150**, thus preventing permeation of exterior air into the organic light emitting array **150** and more certainly prevents permeation of moisture, in addition to the functions of the protective layer **160**.

The thin film transistor array **140** including the pad portion has a side that protrudes from the touch electrode array **230**. This configuration aims at providing, at the protrusion, an IC **500** that transfers a signal to simultaneously drive the touch electrode array and the thin film transistor array, and the organic light emitting array. Although not shown, the IC **500** is connected through lines (not shown) formed on the IC **500** and the first buffer layer **130** to driving pads and dummy pads of the thin film transistor array. Also, the IC **500** is bonded and connected to a flexible printed circuit board (FPCB, not shown) and may be controlled by a controller (not shown) provided in the FPCB. The dummy pad is formed in the same layer as a metal constituting a gate or data line in a region corresponding to the touch pad portion among the dead region disposed out of the active region.

The touch pad portion **2350** is formed on the second buffer layer **220** and is formed at both edges of the side adjacent to a portion where the first buffer layer **130** protrudes more than the second buffer layer **220**. Also, the touch pad portion **2350** formed at one edge is divided into a plurality of pad electrodes to enable voltage application or detection of first electrodes arrayed in an X-axis direction in the touch electrode array, and the touch pad portion **2350** formed at the other edge is divided into a plurality of pad electrodes to enable voltage application or detection of second electrodes arrayed in an Y-axis direction.

The conductive ball **455** connected to the touch pad portion **2350** is electrically connected to a dummy electrode (not shown) formed out of the thin film transistor array **140**.

During an actual process, the adhesive layer **160** and the sealant **450** are separately formed by application to different regions.

Meanwhile, as shown in FIG. 3, the organic light emitting display according to the present invention includes a film substrate **1000**, a first etch stopper film **120** and a first buffer layer **130** formed in this order on the film substrate **1000**, a thin film transistor array **140** having a thin film transistor in each pixel defined in a matrix form on the first buffer layer **130**, an organic light emitting array **150** connected to the thin film transistor of each pixel, a protective layer **160** that covers the thin film transistor array **140** excluding the pad portion and the organic light emitting array **150**, a touch electrode array **230** adhered to the protective layer via an adhesive layer **400** interposed between the protective layer **160** and the touch electrode array **230**, and a second buffer layer **220** and a second etch stopper film **210** formed in this order on the touch electrode array **230**, and includes a cover glass **3000** disposed on the second etch stopper film **210**.

The cover glass **3000** may be adhered to the second etch stopper film **210** via an adhesive layer interposed between the

second etch stopper film **210** and the cover glass **3000**, or may be disposed on the second etch stopper film **210** by a mechanical method or another method. The cover glass **3000** prevents damage to internal array from direct touch of a user and protects the internal array therefrom.

The organic light emitting display according to the present invention can be reduced in thickness by omitting a glass substrate having a thickness of about 0.7 mm, which is the thickest of components in the display, and can realize a bendable or flexible display using the film substrate **1000** as a plastic insulating film that functions to support the thin film transistor array **140**, the organic light emitting array **150** and the touch electrode array **230**.

In addition, in the process of forming arrays such as the thin film transistor array **140**, the organic light emitting array **150** and the touch electrode array **230** on the film substrate, the film substrate is thermally expanded by heat applied to apparatuses for depositing or patterning the arrays, thus making normal processing impossible. In order to prevent this phenomenon, substantially, formation of arrays is carried out by forming etch stopper films **120** and **210** and buffer layers **130** and **220** under the thin film transistor array **140** and the touch electrode array **230**, respectively, on the glass substrate, before formation of the thin film transistor array **140** and formation of the touch electrode array **230**, and then loading the glass substrate in an apparatus for deposition or patterning.

Meanwhile, the thin film transistor array **140** includes a plurality of gate lines and a plurality of data lines that intersect each other to define pixels, and thin film transistors formed at the respective intersections between the gate lines and the data lines. A pad portion of the thin film transistor array **140** is obtained by forming a pad portion metal in the process of forming the gate and data lines.

Also, the organic light emitting array **150** includes a first electrode formed at least in the pixel, a second electrode formed in an upper layer spaced from the first electrode, and an organic light emitting layer formed between the first and second electrodes. The first electrode may be connected to a drain electrode of the thin film transistor.

In addition, the first etch stopper film **120** and the second etch stopper film **210** may be for example formed of polyimide or photo-acryl.

The first and second etch stopper films **120** and **210** have a thickness of about 1 μm to about 20 μm .

Also, the first buffer layer **130** and the second buffer layer **220** function to prevent permeation of oxygen or moisture into organic films provided in the organic light emitting array and serve as barriers that prevent permeation of exterior air or moisture injected from a lower part.

The first buffer layer **130** and the second buffer layer **220** include a plurality of inorganic films. For example, the inorganic films may be formed by continuously or alternatively laminating SiNx or SiO₂. It can be seen from experimentation that, when two or more layers are laminated to a thickness of about 5,000 Å to 6,500 Å as the first and second buffer layers **130** and **220**, permeation of exterior air or moisture can be prevented. A total thickness of the first and second buffer layers **130** and **220** is 1 μm or less, which does not increase the thickness of the touchscreen-integrated display device.

Hereinafter, a configuration of the touch electrode array according to the present invention will be described in detail.

FIG. 4 is an enlarged plan view of a part "A" of FIG. 2. FIG. 5 is a sectional view taken along the line II-II' of FIG. 4 according to a first embodiment of the present invention.

As shown in FIGS. 4 and 5, the touch electrode array **230** according to the first embodiment of the present invention

includes a first touch electrode and a second touch electrode intersecting each other, and a touch pad **2351b** (provided in a touch pad portion **2350**) transferring a signal to the first and second touch electrodes. The touch pad **2351b** may be connected to a dummy pad (not shown) formed in the dead region of the thin film transistor array. FIG. 3 illustrates a thin film transistor array **140** including the dummy pad, and a touch electrode layer as one layer including the touch pad, and first and second touch electrodes **2331** and **2332**. These layers are patterned according to individual electrodes.

The first touch electrode is disposed in a first direction and includes a first electrode pattern **2331** disposed in an island form and a metal bridge **231** to electrically connect the first electrode pattern **2331** to another first electrode pattern **2331** adjacent to a layer different from the first electrode pattern, and the second touch electrode is disposed in a direction intersecting the first direction and includes a second electrode pattern **2332** having the same shape as the first electrode pattern **2331** and a connection pattern **2332c** to connect adjacent second electrode patterns **2332** in an integrated form with the second electrode pattern.

The first electrode pattern **2331**, the second electrode pattern **2332** and the connection pattern **2332c** are formed as the same transparent electrode in a first layer, the metal bridge **231** is formed in a second layer on a first interlayer insulating film **232** interposed between the first layer and the second layer, and the first interlayer insulating film may include a contact hole **232a** in a region where the metal bridge **231** overlaps the second electrode patterns **2332**.

In the drawing of FIG. 5, the first layer corresponds to the surface of the first interlayer insulating film **232** and the second layer corresponds to the second buffer layer **220**. This shows an example in which the metal bridge **231** is formed on the second buffer layer **220**, a first interlayer insulating film **232** including a contact hole **232a** is then formed, the first electrode pattern **2331**, and the second electrode pattern **2332** and the connection pattern **2332c** are then formed, although the present invention is not necessarily limited thereto. If desired, formation order of the metal bridge **231** and the first and second electrode patterns **2331** and **2332** and connection pattern **2332c** may be changed.

Also, an exterior light shielding layer **2400** including a black matrix layer **242** and a color filter layer **241** is formed on the first interlayer insulating film **232** including the first and second electrode patterns **2331** and **2332** and the connection pattern **2332c**.

The black matrix layer **242** absorbs light and blocks transmission of light, and is formed on the edge of respective pixels of the thin film transistor array and the organic light emitting diode that face the touch electrode array **230**.

Also, a red pigment layer (R), a green pigment layer (G) and a blue pigment layer (B) constituting the color filter layer **241** correspond to pigment layers that transmit light having the same color as light emitted from the light emitting layer of the organic light emitting diode in respective pixels. For example, in a pixel in which the light emitting layer of the organic light emitting diode is a red light emitting layer, the red pigment layer (R) corresponds to the red light emitting layer, in a pixel in which the light emitting layer is a green light emitting layer, the green pigment layer (G) corresponds to the green light emitting layer, and in a pixel in which the light emitting layer is a blue light emitting layer, the blue pigment layer (B) corresponds to the blue light emitting layer.

Meanwhile, as shown in FIG. 4, the first interlayer insulating film **232** is exposed on a neighboring portion of touch pads **2351b** in the touch pad portion **2350**. This means that the neighboring portion has a step lower than the touch pad **2351b**

including electrodes, transparent electrodes and the like which are laminated. This step makes the level of the touch pad **2351b** higher, makes the conductive ball **455** compressed during bonding and thereby facilitates contact between the touch pad **2351b** and the conductive ball **455**.

FIG. 6 is a view illustrating a process of forming a touch electrode array of an organic light emitting display according to the present invention.

As shown in FIG. 6, formation of the touch electrode array **230** of the organic light emitting display is carried out on a second buffer layer **220** after sequentially forming a second etch stopper film **210** and the second buffer layer **220** on a second substrate **200**.

As described above, the second buffer layer **220** is a laminate having a thickness of 1 μm including a plurality of inorganic films. In order to prevent damage from heat, etching solution or the like applied during formation of the array, an array formation process is not directly performed on the second buffer layer **220** and an array formation process is performed on the second substrate **200** made of a glass component.

After the touch electrode array **230** is joined to the organic light emitting array **150** such that these arrays face each other, the first substrate (not shown) and the second substrate **200** made of glass components are removed by etching using an etching solution or through laser irradiation. At this time, the second etch stopper film **210** prevents damage to the first and second buffer layers **130** and **220** and arrays disposed thereon. As described above, the first and second etch stopper films **120** and **210** may be organic film components resistant to etching solution or laser irradiation. However, the first and second etch stopper films **120** and **210** have a thickness of 20 μm or less and thus neither increase the thickness of the device nor deteriorate flexibility.

Meanwhile, the exterior light shielding layer **2400** including the black matrix layer **242** and the color filter layer **241** may have other shapes.

Hereinafter, another embodiment of the touch electrode array including another form of exterior light shielding layer will be described.

FIGS. 7A to 7E illustrate a touch electrode array according to an organic light emitting display according to another embodiment.

FIG. 7A illustrates a touch electrode array of an organic light emitting display according to the second embodiment of the present invention. Comparing the second embodiment with the first embodiment, the second embodiment further comprises common transparent electrode patterns **235a** and **235b** that cover the second interlayer insulating film **234** and the first electrode pattern **2331**, the second electrode pattern **2332** and the connection pattern **2332c** on the first interlayer insulating film **232** including the first electrode pattern **2331**, the second electrode pattern **2332** and the connection pattern **2332c**.

The first electrode pattern **2331** is covered with the first common transparent electrode pattern **235a** and the second electrode pattern **2332** and the connection pattern **2332c** which are integrated with each other are covered with the second common transparent electrode pattern **235b**.

Also, the exterior light shielding layer **3400** including the black matrix layer **342** and the color filter layer **341** is formed on the second interlayer insulating film **234** including the common transparent electrode pattern **235a**.

As shown in FIG. 2, the common transparent electrode pattern **235a** blocks effects of a signal transferred from the organic light emitting array **150** or the thin film transistor array **140** disposed in a lower part on driving of the touch

electrode array **230**, when the touch electrode array **230** contacts the protective film **160** covering the organic light emitting array **150** via an adhesive layer **400**. The common transparent electrode pattern **235a** has a floating state, which stabilizes driving of the first touch electrode and the second touch electrode disposed therein without application of exterior voltage.

FIG. 7B illustrates a touch electrode array of an organic light emitting display according to a third embodiment of the present invention. In comparison with the second embodiment, the third embodiment includes a shielding layer **2400** including the black matrix layer **242** and the color filter layer **241**, instead of the second interlayer insulating film **234**. In this case, the second interlayer insulating film **234** may be omitted, and the process of the first embodiment is simplified, as compared to the second embodiment.

FIG. 7C illustrates a touch electrode array of an organic light emitting display according to a fourth embodiment of the present invention. In comparison with the second embodiment, the third embodiment includes a shielding layer **2400** including the black matrix layer **442** and the color filter layer **441**, instead of the first interlayer insulating film **232**. In this case, the first interlayer insulating film **232** may be omitted, and the process of the first embodiment can be simplified, as compared to the second embodiment.

FIG. 7D illustrates a touch electrode array of an organic light emitting display according to a fifth embodiment of the present invention. In comparison with the second embodiment, the fifth embodiment includes a color filter layer **541** including a red pigment (R), a green pigment (G) and a blue pigment (B), instead of the first interlayer insulating film **232**.

In the fifth embodiment, a contact hole **232a** is formed in the color filter layer **541**, the first electrode pattern **2331** connected to the metal bridge **231** through the contact hole **232a**, the second electrode pattern **2332** which is spaced from the first electrode pattern **2331** and is disposed in a direction intersecting the disposition direction of the first electrode pattern **2331**, and a connection pattern **2332c** integrated therewith are formed on the color filter layer **541**. Also, at the edge of a pixel where the organic light emitting array faces the thin film transistor array during joining, the black matrix layer **542** is formed on transparent electrode layers of the first electrode pattern **2331**, the second electrode pattern **2332** and the connection pattern **2332c** including the color filter layer **541**. In the fifth embodiment, as compared to the second embodiment, the first interlayer insulating film may be omitted.

Also, the black matrix layer **542** and the color filter layer **541** formed in different layers serve as exterior light shielding layer **5400**.

FIG. 7E illustrates a touch electrode array of an organic light emitting display according to a sixth embodiment of the present invention. Compared with the second embodiment, the sixth embodiment comprises an exterior light shielding layer **6400** including a black matrix layer **642** and a color filter layer **641** under the metal bridge **231**.

Meanwhile, according to the organic light emitting display of the present invention, the reason for forming the exterior light shielding layer using the black matrix layer and the color filter layer during formation of the touch electrode array is as follows.

Through the array formation process, the black matrix layer is formed to have a small thickness of 1 μm to 3 μm and is readily formed in a predetermined region through a printing process only, without using any mask. Accordingly, the black matrix layer is easily formed, absorbs certain colors of light according to individual wavelength bands and thus prevents

reflection and recognition of exterior light incident upon the organic light emitting display by the electrode of the organic light emitting diode. Also, a combination of a circular or linear polarizing plate and a phase-retarder layer which is required for organic light emitting displays and has a large thickness can be omitted and flexibility and thinness of organic light emitting displays can thus be easily realized. Generally polarizing plates have a thickness of about 150 μm or more. This thickness can be reduced and great effects of improvement in transmittance and reduction in thickness can thus be obtained.

Also, in a case in which the circular polarizing plate or the like is provided, an organic film requiring light-isotropy is used as the etch stopper layer in order to compensate a viewing angle. The present invention does not require this organic film, thus enabling use of a general organic film incapable of performing optical compensation. Accordingly, an expensive optical film can be omitted and costs can thus be reduced.

Also, the black matrix layer and the color filter layer used for the exterior light shielding layer can alternate interlayer insulating films, thus enabling formation of a touch electrode array without increase in thickness and addition of separate processes.

Meanwhile, the afore-mentioned embodiment as well as a modified embodiment as shown in FIG. 8 may be used.

FIG. 8 is a sectional view illustrating an organic light emitting display according to a modified embodiment of the present invention.

In comparison with the fifth embodiment, in the modified embodiment shown in FIG. 8, the black matrix layer **701** is formed, instead of a bank to isolate respective pixels, on the organic light emitting array **150** formed on the first buffer layer **130** and thin film transistor array **140** which face the black matrix layer **701**.

In this case, the black matrix layer is not further provided in order to prevent recognition of exterior light and the black matrix layer **701** is disposed instead of the bank, thus having an advantage of process simplification.

In this case, in order to prevent recognition of exterior light, the black matrix layer **701** is formed on the thin film transistor array **140** and the color filter layer **541** is formed in the touch electrode array **230**.

Non-described reference numeral "703" represents a second electrode of the organic light emitting array **150** and **702** (**702a**, **702b** and **702c**) represents a light emitting layer provided in each pixel.

In this case, the remaining first electrode of the organic light emitting diode may be formed on the thin film transistor array **140**.

FIG. 9 is a reference embodiment of the present invention compared with the organic light emitting display in terms of visibility.

In comparison with the embodiment shown in FIG. 3, the reference embodiment of FIG. 9 further includes a polarizing plate **2000** inside the cover glass **3000** and excludes an exterior light shielding layer in the touch electrode array **230**. The remaining components having the same reference numeral as in FIG. 3 have the same configurations and a detailed description thereof will be omitted.

Reflectivity and transmittance values obtained by simulating the configurations shown in FIGS. 3 and 9, actual transmittance under conditions of exterior light at 320,000 cd and transmittance of organic light emitting diode of 500 nit are shown in Table 1 below.

TABLE 1

		Reference embodiment	Present invention
Simulation	Reflectivity	0%	3.3%
	Transmittance	40%	90%
Actually measured	Reflectivity (under 320,000 cd)	Measured data: 20777 cd	Measured data: 26755 cd
		6.5%	8.4%
	Transmittance (under 500 nit)	Measured data: 190 nit	Measured data: 440 nit
		38%	88%

As can be seen from Table 1 above, in this simulation, when an aperture ratio is 10%, in the reference embodiment, reflectivity and transmittance are determined as 0% and 40%, respectively, regardless of aperture ratio, depending on polarizing plate properties. Also, reflectivity of the present invention is determined by reflectivity of a region corresponding to the color filter layer, which corresponds to about 3.3% obtained by the equation of $10\% \times 1/3$. Also, in the simulation of the present invention, transmittance is about 90% when the color filter layer corresponds to the light emitting layer having the same color.

The values obtained by the simulation are ideal values which are slightly different from measured values.

That is, under exterior light of 320,000 cd, reference embodiment reflects light of 20,777 cd which is 6.5% greater than the simulation value, 0%, and the present invention reflects light of 26,755 cd, which corresponds to 8.4% which is slightly larger than a simulated value, 3.3%. This difference in values is caused by reflection to other layers, in addition to the touch electrode array. These values are 10% or less, such that a viewer does not see exterior light. From the actually measured values of the reference embodiment and the present invention, recognition of exterior light is prevented.

Also, actually measured transmittance of the reference embodiment and the present invention is obtained by testing at an organic light emitting diode brightness of 500 nit. That is, when brightness of the organic light emitting diode disposed under the touch electrode array is 500 nit, the reference embodiment has a measured value of 190 nit and has a transmittance efficiency of about 38% due to presence of the polarizing plate having a strong light-absorbing property, while the present invention has a measured data of 440 nit and has a transmittance efficiency of 88% due to use of the color filter layer having superior transmittance.

That is, as can be seen from the simulation and actual measurement, the present invention and the reference embodiment have similar reflectivity, but the present invention has considerably higher transmittance.

Hereinafter, a method for fabricating an organic light emitting display according to the present invention will be described with reference to FIGS. 2 to 6.

First, a first etch stopper film 120, a first buffer layer 130, a thin film transistor array 140 including a thin film transistor formed in each of a plurality of pixels defined in a matrix form in an active region of the first buffer layer 130, and an organic light emitting array 150 including an organic light emitting diode connected to the thin film transistor of each pixel are formed on a first substrate (not shown).

Also, a protective film 160 is formed such that it covers the organic light emitting array 150. This protective film 160 may be omitted, if desired.

Also, a second etch stopper film 210 and a second buffer layer 220 are formed on the second substrate 200.

Then, first and second touch electrodes intersecting each other, and a touch electrode array 230 including a black matrix layer 242 and a color filter layer 241 are formed on the second buffer layer 220. During formation of the touch electrode array 230, a touch pad portion 2350 including a plurality of touch pads 2351b is formed in a part of the dead region. A detailed description and various embodiments associated with formation of the touch electrode array 230 can be seen from FIGS. 5, 7a to 7e and 8.

Then, an adhesive layer 400 is interposed between the protective film 160 that covers the organic light emitting array 150 and the touch electrode array 230 and a joining process is performed. In this process, a sealant 450 including a conductive ball 455 is applied to the touch pad portion 2350 and the conductive ball 455 bonds the touch pad portion 2350 disposed on the second buffer layer 220 to a dummy pad of the thin film transistor array 140 disposed on the first buffer layer 130.

Then, the first substrate and the second substrate 200 are removed via laser irradiation or using an etching solution.

Then, a film substrate 1000 is adhered to the exposed first etch stopper film 120 via an adhesive layer 110 and the exposed second etch stopper film 210 is covered with a cover glass 3000. Here, an adhesive layer may also be interposed between the second etch stopper film 210 and the cover glass 3000.

For realization of flexibility and thinness of displays, as recent trends, the organic light emitting display of the present invention is characterized in that a layer having the same function of preventing recognition of exterior light as the polarizing plate is formed during the touch electrode array formation process, instead of the polarizing plate. As a result, realization of ultra-slim organic light emitting displays is possible.

The organic light emitting display and the method for fabricating the same according to the present invention have the following effects.

First, the black matrix layer is readily formed to have a small thickness of 1 μm to 3 μm through an array formation process. Also, a combination of a circular polarizing plate or a linear polarizing plate and a phase-retarder layer requires a large thickness for organic light emitting displays of related art. However, in the present invention, the polarizer for preventing exterior light can be omitted. Also, flexibility and thinness of organic light emitting displays can thus be easily realized. Generally polarizing plates have a thickness of about 150 μm or more, but this thickness can be reduced and great effects of improvement in transmittance and reduction in thickness can thus be obtained.

Second, the black matrix layer and the color filter layer can be readily formed through a printing process only, without using any mask.

Third, the black matrix layer can be easily formed, further can absorb colors of light according to individual wavelength bands and thus prevents reflection and recognition of exterior light incident upon the organic light emitting display by existing the electrode in the organic light emitting diode. As compared to a structure using a polarizing plate, the structure according to the present invention has similar reflectivity and improved transmittance of a device and thus improved optical efficiency.

Fourth, in a case in which the circular polarizing plate or the like is provided, an organic film requiring light-isotropy is used as the etch stopper layer in order to compensate a viewing angle. The present invention does not require this organic film, thus enabling use of a general organic film incapable of

performing optical compensation. Accordingly, an expensive optical film can be omitted and the cost can thus be reduced.

Fifth, the black matrix layer and the color filter layer used for the exterior light shielding layer can alternate interlayer insulating films, thus enabling formation of a touch electrode array without increase in thickness and addition of separate processes.

Sixth, the organic light emitting display of the present invention is of an in-cell type in which the touch electrode array is included in the cover glass, thus requiring no separate process for attaching a touchscreen thereto and thus enabling realization of slim displays fabricated through a simple process.

It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the spirit or scope of the inventions. Thus, it is intended that the present invention covers the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An organic light emitting display comprising:
a film substrate;
a first buffer layer on the film substrate;
a thin film transistor in each of a plurality of pixels on the first buffer layer;
an organic light emitting diode connected to a thin film transistor of each pixel;
a protective layer on the organic light emitting diode and the thin film transistor;
an adhesive layer on the protective layer;
first and second touch electrodes and an exterior light shielding layer on the adhesive layer;
a second buffer layer on the touch electrodes and the exterior light shielding layer; and
a cover glass on the second buffer layer, wherein at least one of the first and second touch electrodes, and the exterior light shielding layer is in direct contact with the adhesive layer and adhered to the protective layer via the adhesive layer.
2. The organic light emitting display according to claim 1, wherein the exterior light shielding layer further comprises at least of a color filter layer and a black matrix layer.
3. The organic light emitting display according to claim 1, wherein the exterior light shielding layer is disposed on the first touch electrode.
4. The organic light emitting display according to claim 1, wherein the first and second touch electrodes are disposed on the exterior light shielding layer.
5. The organic light emitting display according to claim 2, wherein the black matrix layer and the color filter layer are disposed in the same layer.
6. The organic light emitting display according to claim 2, wherein the black matrix layer and the color filter layer are disposed in different layers.
7. The organic light emitting display according to claim 1, wherein the first buffer layer and the second buffer layer have a laminate structure comprising a plurality of inorganic films.
8. The organic light emitting display according to claim 1, further comprising a first etch stopper film between the rear surface of the first buffer layer and the film substrate and, a

second etch stopper film between the rear surface of the second buffer layer and the cover glass.

9. The organic light emitting display according to claim 8, wherein the first etch stopper film and the second etch stopper film comprise one of polyimide or photoacryl.

10. The organic light emitting display according to claim 1, wherein the organic light emitting diode comprises a bank comprising a black matrix corresponding to the edge of each pixel.

11. The organic light emitting display according to claim 2, wherein the first touch electrode is disposed in a first direction and comprises a plurality of first electrode patterns, each having an island shape and a metal bridge to electrically connect adjacent first electrode patterns, and

the second touch electrode is disposed in a direction intersecting the first direction, and comprises a plurality of second electrode patterns, each having the same shape as each of the first electrode patterns and a connection pattern to connect adjacent second electrode patterns, integrated with the second electrode patterns.

12. The organic light emitting display according to claim 11, wherein the plurality of first electrode patterns, the plurality of second electrode patterns and the connection patterns are formed as the same transparent electrode in a first layer,

the metal bridge is formed in a second layer on a first interlayer insulating film interposed between the first layer and the second layer, and

the first interlayer insulating film comprises a contact hole formed in a region where the metal bridge overlaps the adjacent first electrode patterns.

13. The organic light emitting display according to claim 12, further comprising: a second interlayer insulating film on the first interlayer insulating film including the plurality of first and second electrode pattern, and a common transparent electrode pattern covering the second interlayer insulating film, the plurality of first and second electrode patterns and the connection pattern.

14. The organic light emitting display according to claim 12, wherein both of the black matrix layer and the color filter layer comprise the first interlayer insulating films or the second interlayer insulating films.

15. The organic light emitting display according to claim 12, wherein one of the black matrix layer and the color filter layer is comprised in the first interlayer insulating film and the other is comprised in the second interlayer insulating film.

16. The organic light emitting display according to claim 12, wherein the black matrix layer and the color filter layer are disposed under the metal bridge.

17. The organic light emitting display according to claim 13, wherein the black matrix layer and the color filter layer are on the common transparent electrode pattern.

18. The organic light emitting display according to claim 1, wherein the organic light emitting diode comprises:
first and second electrodes facing each other; and

a light emitting layer between layers of the first and second electrodes.

19. The organic light emitting display according to claim 18, wherein the color filter layer of each pixel comprises a color filter that transmits light having the same color as light emitted from the light emitting layer in each pixel.

专利名称(译)	有机发光显示器及其制造方法		
公开(公告)号	US9130181	公开(公告)日	2015-09-08
申请号	US13/718391	申请日	2012-12-18
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	CHOI HO WON LEE JAE DO		
发明人	CHOI, HO-WON LEE, JAE-DO		
IPC分类号	H01L51/44 H01L51/00 H01L27/32 H01L51/52		
CPC分类号	H01L51/447 H01L27/323 H01L51/0001 H01L51/5284 G06F3/0412 G06F3/044 G06F2203/04103 G06F2203/04111 H01L27/322 H01L51/003 H01L51/5203 H01L51/56 H01L2227/323 H01L2227/326 B32B2457/206		
审查员(译)	朱盛		
优先权	1020120096740 2012-08-31 KR		
其他公开文献	US20140061597A1		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种有机发光显示器，其具有不包括偏振片的构造并且显示出改善的柔性和可视性，以及制造该有机发光显示器的方法，所述有机发光显示器包括在所述第二缓冲器上面对所述有机发光二极管的触摸电极阵列层，包括彼此交叉的第一和第二触摸电极的触摸电极阵列和至少包括滤色器层的外部光屏蔽层，形成在有机发光二极管和触摸电极阵列之间的粘合层。

