



US009614191B2

(12) **United States Patent**
Madigan

(10) **Patent No.:** **US 9,614,191 B2**
(45) **Date of Patent:** **Apr. 4, 2017**

(54) **HIGH RESOLUTION ORGANIC
LIGHT-EMITTING DIODE DEVICES,
DISPLAYS, AND RELATED METHODS**

(71) Applicant: **Kateeva, Inc.**, Menlo Park, CA (US)

(72) Inventor: **Conor Francis Madigan**, San
Francisco, CA (US)

(73) Assignee: **Kateeva, Inc.**, Newark, CA (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/030,776**

(22) Filed: **Sep. 18, 2013**

(65) **Prior Publication Data**

US 2014/0197385 A1 Jul. 17, 2014

Related U.S. Application Data

(60) Provisional application No. 61/753,692, filed on Jan.
17, 2013.

(51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 51/05 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 51/56** (2013.01); **H01L 27/3218**
(2013.01); **H01L 27/3246** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 51/0545; H01L 51/0036; H01L
51/0541; H01L 51/5012; H01L 27/1214;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,541,479 A * 7/1996 Nagakubo H01J 11/12
313/113

6,294,398 B1 9/2001 Kim et al.
(Continued)

FOREIGN PATENT DOCUMENTS

CN 1770938 5/2006
EP 1708294 10/2006
(Continued)

OTHER PUBLICATIONS

Reid Chesterfield et al. "Solution-Coating Technology for
AMOLED Displays", Frontline Technology, Information Display
1/11, pp. 24-29.

(Continued)


Primary Examiner — Allen Parker

Assistant Examiner — Didarul Mazumder

(57) **ABSTRACT**

A method of manufacturing an organic-light emitting diode (OLED) display can include providing on a substrate a first electrode associated with a first sub-pixel and a second electrode associated with a second sub-pixel, wherein a gap is formed between the first electrode and the second electrode and wherein the first electrode and the second electrode are positioned in a well having boundaries defined by a confinement structure on the substrate. The method can also include depositing in the well with the electrodes positioned therein, active OLED material to form a substantially continuous layer of active OLED material that spans the boundaries of the well such that a surface of the layer of active OLED material that faces away from the substrate has a non-planar topography. The depositing can be via inkjet printing.

43 Claims, 17 Drawing Sheets



- (51) **Int. Cl.**
H01L 51/50 (2006.01)
H01L 51/52 (2006.01)
H01L 51/56 (2006.01)
B82Y 10/00 (2011.01)
B82Y 30/00 (2011.01)
H01L 27/12 (2006.01)
H01L 27/32 (2006.01)
- (52) **U.S. Cl.**
CPC **H01L 51/0005** (2013.01); **H01L 27/326**
(2013.01); **H01L 51/5203** (2013.01)
- (58) **Field of Classification Search**
CPC H01L 51/56; B82Y 10/00; B82Y 30/00;
Y02E 10/50
USPC 257/40; 438/82, 99
See application file for complete search history.
- (56) **References Cited**

U.S. PATENT DOCUMENTS

- 6,992,326 B1 1/2006 MacPherson et al.
7,132,788 B2 11/2006 Gupta et al.
7,443,093 B2 10/2008 Jianpu et al.
8,110,825 B2 2/2012 Obata et al.
8,115,216 B2 2/2012 Smith et al.
8,124,172 B2 2/2012 Lang et al.
8,309,376 B2 11/2012 Lang et al.
8,330,352 B2 12/2012 Sung et al.
9,444,050 B2 9/2016 Madigan
2004/0144975 A1 7/2004 Seki et al.
2005/0100657 A1 5/2005 MacPherson et al.
2005/0112341 A1 5/2005 Ito et al.
2005/0218807 A1* 10/2005 Min H01J 9/242
313/582
2006/0164010 A1* 7/2006 Hwang H01J 11/12
313/582
2006/0170354 A1* 8/2006 Hwang H01J 11/12
313/582
2008/0024402 A1* 1/2008 Nishikawa et al. 345/82
2008/0111474 A1 5/2008 Sung et al.
2009/0195144 A1* 8/2009 Kitabayashi H01L 27/3246
313/503
2009/0243483 A1 10/2009 Yang
2010/0194269 A1 8/2010 Sonoda et al.
2011/0127502 A1 6/2011 Kim
2011/0183268 A1 7/2011 Lang et al.
2011/0229994 A1* 9/2011 Jung H01L 27/3211
438/29
2011/0248247 A1* 10/2011 Matsumoto C09K 11/06
257/40
2011/0309389 A1* 12/2011 Yu H01L 27/322
257/89

- 2012/0049178 A1 3/2012 Sugimoto et al.
2012/0091482 A1 4/2012 Uchida et al.
2012/0187389 A1* 7/2012 Shoda H01L 27/3246
257/40
2012/0228602 A1 9/2012 Nakatani et al.
2012/0319089 A1 12/2012 Shin et al.
2012/0326136 A1 12/2012 Chen
2012/0326600 A1 12/2012 Heeks et al.
2013/0109117 A1 5/2013 Lee et al.
2014/0070175 A1* 3/2014 Kang 257/40
2014/0078126 A1* 3/2014 Hack et al. 345/211

FOREIGN PATENT DOCUMENTS

- EP 1 601 032 B1 6/2012
GB 2437110 10/2007
JP 2001-143868 5/2001
JP 2005203351 7/2005
JP 2010-021138 1/2010
JP 2010-34143 1/2010
JP 2010186582 8/2010
JP 201113982 6/2011
JP 2012028180 2/2012
JP 2010141059 6/2016
TW 201244222 1/2012
WO WO 2009/097377 8/2009
WO WO 2010092795 8/2010
WO WO 2012/087977 6/2012

OTHER PUBLICATIONS

- International Search Report and Written Opinion issued on Feb. 24, 2014, to PCT Application PCT/US13/60687.
International Search Report and Written Opinion issued on May 13, 2014 to PCT Application No. PCT/US2014/11723.
Non-Final Office Action issued on Jan. 4, 2016, to U.S. Appl. No. 14/156,188.
Applicant Initiated Interview Summary issued on Apr. 29, 2016, to U.S. Appl. No. 14/156,188.
Notice of Allowance issued Jul. 14, 2016 for U.S. Appl. No. 14/156,188.
Extended European Search Report issued Oct. 19, 2016 for EP Application No. 13872170.9.
Extended European Search Report issued Nov. 2, 2016 for EP 14740323.2.
First Office Action issued Sep. 1, 2016 for CN 201480016484.7.
Examination Report issued on Nov. 11, 2016, to TW Patent Application No. 103101751.
Examination Report issued on Dec. 19, 2016 to TW Patent Application No. 102140259.
JP Office action issued on Jan. 26, 2017, to JP Patent Application No. 2015-553715.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3A




FIG. 3B




FIG. 4




FIG. 5A




FIG. 5B




FIG. 6




FIG. 7




FIG. 8




FIG. 9

FIG. 11





FIG. 12






FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21

HIGH RESOLUTION ORGANIC LIGHT-EMITTING DIODE DEVICES, DISPLAYS, AND RELATED METHODS

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims priority to U.S. Provisional Patent Application No. 61/753,692, filed Jan. 17, 2013, which is incorporated by reference herein in its entirety.

TECHNICAL FIELD

Aspects of the present disclosure generally relate to electronic displays and methods for making electronic displays. More particularly, aspects of the present disclosure relate to depositing organic light-emissive layers on a substrate so as to fabricate high resolution displays.

INTRODUCTION

The section headings used herein are for organizational purposes only and are not to be construed as limiting the subject matter described in any way.

Electronic displays are present in many differing kinds of electronic equipment such as, for example, television screens, computer monitors, cell phones, smart phones, tablets, handheld game consoles, etc. One type of electronic display relies on organic light emitting diode (OLED) technology. OLED technology utilizes an organic light-emissive layer sandwiched between two electrodes disposed on a substrate. A voltage can be applied across the electrodes causing charge carriers to be excited and injected into the organic light-emissive layer. Light emission can occur through photoemission as the charge carriers relax back to normal energy states. OLED technology can provide displays with a relatively high contrast ratio because each pixel can be individually addressed to produce light emission only within the addressed pixel. OLED displays also can offer a wide viewing angle due to the emissive nature of the pixels. Power efficiency of an OLED display can be improved over other display technologies because an OLED pixel only consumes power when directly driven. Additionally, the panels that are produced can be much thinner than in other display technologies due to the light-generating nature of the technology eliminating the need for light sources within the display itself and the thin device structure. OLED displays also can be fabricated to be flexible and bendable due to the compliant nature of the active OLED layers.

Inkjet printing is a technique that can be utilized in OLED manufacturing, and may reduce manufacturing cost. Inkjet printing uses droplets of ink containing OLED layer material and one or more carrier liquids ejected from a nozzle at a high speed to produce one or more active OLED layers including, for example a hole injection layer, a hole transport layer, an electron blocking layer, an organic light emissive layer, an electron transport layer, an electron injecting layer, and a hole blocking layer.

To form sub-pixels and prevent OLED ink from spreading between defined sub-pixels, confinement structures such as banks are provided on the substrate to define confinement wells. Inkjet printing methods can require substantial precision. In particular, as pixel density increases, the confinement areas of the confinement wells are reduced and small errors in droplet placement can cause the droplet to be deposited outside the intended well. Moreover, droplet volumes can be too large with respect to the confinement well

and droplets can undesirably spill over into adjacent sub-pixels. In addition, non-uniformities can form at the edges of the confinement wells due to film drying imperfections. As the confinement well area is reduced, the non-uniformities can encroach on the active emission area of the pixel creating undesirable visual artifacts in the light emission from the pixel caused by the non-uniformities. In addition, the ratio of the active area to the total area, both the active and non-active areas, of each pixel (referred to as the "fill factor") is reduced due to the confinement structures which in turn can reduce the lifetime of the display because each pixel has to be driven using more current to achieve equivalent display brightness levels and using more current to drive each pixel is known to reduce the pixel lifetime.

Although traditional inkjet methods address some of the challenges associated with OLED manufacturing, there exists a continued need for improvement. For example, there exists a continued need to reduce the sensitivity of the OLED manufacturing process to the droplet placement precision, in particular for OLED displays having a high resolution (i.e., high pixel density). Moreover, there exists a need to reduce undesirable visual artifacts created by the deposition of the organic light-emissive layer in high resolution displays. There also exists a need to improve the device lifetime by improving the fill factor of each pixel such that the area associated with active elements is increased. Further, there exists a need for improvement in using and manufacturing OLED displays in high resolution display applications, including but not limited to, for example, high resolution mobile phones and tablet computers, which present challenges in achieving acceptable resolution, power efficiency, display lifetime, and manufacturing cost.

SUMMARY

The present disclosure may solve one or more of the above-mentioned problems and/or achieve one or more of the above-mentioned desirable features. Other features and/or advantages may become apparent from the description which follows.

In accordance with an exemplary embodiment of the present disclosure, a method of manufacturing an organic-light emitting diode (OLED) display can include providing on a substrate a first electrode associated with a first sub-pixel and a second electrode associated with a second sub-pixel, wherein a gap is formed between the first electrode and the second electrode and wherein the first electrode and the second electrode are positioned in a well having boundaries defined by a confinement structure on the substrate. The method can also include depositing in the well with the electrodes positioned therein, active OLED material to form a substantially continuous layer of active OLED material that spans the boundaries of the well such that a surface of the layer of active OLED material that faces away from the substrate has a non-planar topography. The depositing can be via inkjet printing. The present disclosure also contemplates an organic light emitting diode (OLED) display made according to the above method.

In accordance with an additional exemplary embodiment of the present disclosure, an organic light-emitting diode (OLED) display can include a first electrode disposed on a substrate, wherein the first electrode is associated with a first sub-pixel; and a second electrode disposed on the substrate and spaced from the first electrode to provide a gap between the first and second electrodes, wherein the second electrode is associated with a second sub-pixel. The display can

further include a confinement structure positioned on the substrate to define boundaries of a well containing the first electrode and the second electrode; and a substantially continuous active OLED material layer that spans the boundaries of the well and is disposed over the first electrode and second electrodes, wherein a surface of the active OLED material layer that faces away from the substrate has a non-planar topography.

Additional objects and advantages will be set forth in part in the description which follows, and in part will be obvious from the description, or may be learned by practice of the present teachings. At least some of the objects and advantages of the present disclosure may be realized and attained by means of the elements and combinations particularly pointed out in the appended claims.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are not restrictive of the invention, as claimed. It should be understood that the invention, in its broadest sense, could be practiced without having one or more features of these exemplary aspects and embodiments.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are incorporated in and constitute a part of this specification, illustrate some exemplary embodiments of the present disclosure together with the description, serve to explain certain principles. In the drawings,

FIG. 1 is a partial plan view of a conventional pixel arrangement.

FIG. 2 is a partial plan view of an exemplary pixel arrangement in accordance with the present disclosure;

FIG. 3A is a cross-sectional view of a confinement well along line 3A-3A in FIG. 1 of an exemplary embodiment in accordance with the present disclosure;

FIG. 3B is a cross-sectional view of a plurality of confinement wells along line 3B-3B in FIG. 1 of an exemplary embodiment in accordance with the present disclosure;

FIG. 4 is a cross-sectional view similar to the view of FIG. 3A of another exemplary embodiment of a confinement well in accordance with the present disclosure;

FIG. 5A is a cross-sectional view similar to the view of FIG. 3A of another exemplary embodiment of a confinement well in accordance with the present disclosure;

FIG. 5B is a cross-sectional view similar to the view of FIG. 3B of another embodiment of a confinement well in accordance with the present disclosure;

FIG. 6 is a cross-sectional view of yet another exemplary embodiment of a confinement well in accordance with the present disclosure;

FIG. 7 is a cross-sectional view of yet another exemplary embodiment of a confinement well in accordance with the present disclosure;

FIGS. 8-11 are cross-sectional views of another exemplary embodiment of a confinement well and exemplary steps for creating an OLED display in accordance with the present disclosure;

FIGS. 12-19 are partial plan views of various exemplary pixel arrangements in accordance with the present disclosure;

FIG. 20 is a front view of an exemplary apparatus including an electronic display in accordance with the present disclosure; and

FIG. 21 is a front view of another exemplary apparatus including an electronic display in accordance with the present disclosure.

DESCRIPTION OF EXEMPLARY EMBODIMENTS

Reference will now be made in detail to various exemplary embodiments of the present disclosure, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers will be used throughout the drawings to refer to the same or like parts.

For the purposes of this specification and appended claims, unless otherwise indicated, all numbers expressing quantities, percentages, or proportions, and other numerical values used in the specification and claims, are to be understood as being modified in all instances by the term “about,” to the extent they are not already so modified. Accordingly, unless indicated to the contrary, the numerical parameters set forth in the following specification and attached claims are approximations that may vary depending upon the desired properties sought to be obtained. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques.

It is noted that, as used in this specification and the appended claims, the singular forms “a,” “an,” and “the,” and any singular use of any word, include plural referents unless expressly and unequivocally limited to one referent. As used herein, the term “include” and its grammatical variants are intended to be non-limiting, such that recitation of items in a list is not to the exclusion of other like items that can be substituted or added to the listed items.

Further, this description’s terminology is not intended to limit the invention. For example, spatially relative terms—such as “beneath,” “below,” “lower,” “top,” “bottom,” “above,” “upper,” “horizontal,” “vertical,” and the like—may be used to describe one element’s or feature’s relationship to another element or feature as illustrated in the figures. These spatially relative terms are intended to encompass differing positions (i.e., locations) and orientations (i.e., rotational placements) of a device in use or operation in addition to the position and orientation shown in the figures. For example, if a device in the figures is turned over, elements described as “below” or “beneath” other elements or features would then be “above” or “over” the other elements or features. Thus, the exemplary term “below” can encompass both positions and orientations of above and below depending on the overall orientation of the device. A device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

As used herein, “pixel” is intended to mean the smallest functionally complete and repeating unit of a light emitting pixel array. The term “sub-pixel” is intended to mean a portion of a pixel that makes up a discrete light emitting part of the pixel, but not necessarily all of the light emitting parts. For example, in a full color display, a pixel can include three primary color sub-pixels such as red, green, and blue. In a monochrome display, the terms sub-pixel and pixel are equivalent, and may be used interchangeably.

The term “coupled” when used to refer to electronic components is intended to mean a connection, linking, or association of two or more electronic components, circuits, systems, or any combination of: (1) at least one electronic

component, (2) at least one circuit, or (3) at least one system in such a way that a signal (e.g. current, voltage, or optical signal) can be transferred from one to another. The connection, linking, or association of two or more electronic components, circuits, or systems can be direct; alternatively intermediary connections, linkings, or associations may be present, and thus coupling does not necessarily require a physical connection.

One of ordinary skill in the art would generally accept the term "high resolution" to mean a resolution greater than 100 pixels per inch (ppi) where 300 ppi can sometimes be referred to as very high resolution. One of ordinary skill in the art would also recognize that pixel density does not directly correlate to the size of the display. Various exemplary embodiments disclosed herein can be used to achieve high resolution in small and large display sizes. For example, displays having a size of about 3 inches to about 11 inches can be implemented as high resolution displays. Moreover, displays having larger sizes, such as television displays up to 55" and beyond, can also be used with various exemplary embodiments described herein to achieve high resolution displays.

As used herein, a layer or structure being "on" a surface includes both the case where the layer is directly adjacent to and in direct contact with the surface over which it is formed and the case where there are intervening layers or structures between the layer or structure being formed over the surface.

Various factors can influence deposition precision of organic light-emissive layers in OLED display manufacturing techniques such factors include for example, display resolution, droplet size, target droplet area, droplet placement error, fluid properties (e.g., surface tension, viscosity, boiling point) associated with the OLED layer material (e.g., active OLED materials) inks, which are comprised of a combination of OLED layer material and one or more carrier fluids, and the velocity at which the droplets are deposited. As display resolutions increase, for example greater than 100 ppi, or for example greater than 300 ppi, various issues arise in using inkjet printing techniques for OLED display manufacturing. High precision inkjet heads used in the conventional printing techniques can produce droplet sizes ranging from about 1 picoliter (pL) to about 50 picoliters (pL), with about 10 pL being a relatively common size for high precision inkjet printing applications. Droplet placement accuracy of a conventional inkjet printing system is approximately $\pm 10 \mu\text{m}$. In various exemplary embodiments, confinement wells can be provided on the substrate to compensate for droplet placement errors. A confinement well can be a structure that prevents OLED material from migrating beyond a desired sub-pixel area. To ensure that a droplet accurately lands at a desired location on a substrate, such as entirely within a confinement well, various exemplary embodiments configure the confinement well to be as wide as the droplet diameter plus twice the droplet placement error of the system. For example, the diameter of a 10 pL droplet is about $25 \mu\text{m}$ and thus the preceding parameters would indicate the use of a confinement well of at least $45 \mu\text{m}$ ($25 \mu\text{m} + (2 \times 10 \mu\text{m})$) in its smallest dimension. Even for a 1 pL droplet, the droplet diameter is $12 \mu\text{m}$, which indicates a confinement well of at least $32 \mu\text{m}$ in its smallest dimension.

Various pixel layouts that rely on a confinement well of at least $45 \mu\text{m}$ in its smallest dimension can be used in OLED displays having a resolution up to 100 ppi. However, in high resolution displays of greater than 100 ppi, for example, 10 pL droplets are too large and droplet placement accuracies too poor to reliably provide for consistent loading of drop-

lets into confinement wells around each sub-pixel. In addition, as noted above, for high resolution displays, covering an increased amount of display area with structures used to define confinement wells can negatively impact the fill factor of each pixel, where fill factor is defined as the ratio of the light emitting area of the pixel relative to the total pixel area. As fill factor decreases, each pixel must be driven harder to achieve the same overall display brightness thereby decreasing longevity and performance of each pixel of the display.

To further illustrate some of the above mentioned challenges of working with very high resolution displays, FIG. 1 illustrates one conventional pixel layout 1700. Pixel 1750 can comprise sub-pixels 1720, 1730, 1740 arranged in a side-by-side configuration, sub-pixel 1720 being associated with light emission in the red spectrum range, sub-pixel 1730 being associated with light emission in the green spectrum range, and sub-pixel 1740 being associated with light emission in the blue spectrum range. Each sub-pixel can be surrounded by confinement structures 1704 forming confinement wells directly corresponding to the sub-pixels 1720, 1730, 1740. One sub-pixel electrode can be associated with each confinement well such that electrode 1726 corresponds to sub-pixel 1720, electrode 1736 corresponds to sub-pixel 1730, and electrode 1746 corresponds to sub-pixel 1740. Sub-pixel 1720 can have a width D, sub-pixel 1730 can have a width C, and sub-pixel 1740 can have a width B, which may be the same or differ from each other. As shown, all sub-pixels can have a length A. In addition, dimensions E, F, and G can indicate the spacing between confinement well openings. Values assigned to dimensions E, F, G can be very large in some instances, e.g., greater than $100 \mu\text{m}$, particularly in lower resolution displays. However, for higher resolution displays, it is desirable to minimize these dimensions in order to maximize the active pixel area and thus maximize the fill factor. As illustrated in FIG. 1, the active pixel area, indicated by the shaded regions, is the entire area within each of the sub-pixel confinement wells.

Various factors can influence dimensions E, F, G, such as, for example, the minimum value for these dimensions can be restricted by the processing method. For example, in various illustrative embodiments described herein $E=F=G=12 \mu\text{m}$ as a minimum dimension. For example, in a display having a 326 ppi resolution, the pixel pitch can be equal to $78 \mu\text{m}$ and $E=F=G=12 \mu\text{m}$. The confinement wells associated with each of the sub-pixels 1720, 1730, 1740 can have a target droplet area of $14 \mu\text{m} \times 66 \mu\text{m}$ (i.e. dimensions $B \times A$, $C \times A$, and $D \times A$) where $14 \mu\text{m}$ is significantly less than the $45 \mu\text{m}$ smallest dimension discussed above regarding using inkjet droplets having a volume of 10 pL. It is also less than the $32 \mu\text{m}$ dimension discussed above for 1 pL droplets. In addition, the fill factor of the pixel, defined as the ratio of the active pixel area (i.e. the area associated with light emission), and the total pixel area is 46%. In other words, 54% of the pixel area corresponds to confinement structures 1704. Along the same lines, in a display having a 440 ppi resolution, the pixel pitch, P, can be equal to $58 \mu\text{m}$ and $E=F=G=12 \mu\text{m}$. Confinement wells associated with each of the emitting sub-pixels 1720, 1730, 1740 can have a target droplet area of, for example, $7 \mu\text{m} \times 46 \mu\text{m}$ where a dimension of $7 \mu\text{m}$ is significantly less than the minimum dimensions discussed above for accurate droplet placement of both 10 pL and 1 pL inkjet droplets. In this instance, the fill factor for a display having 440 ppi is around 30%.

Deposition techniques in accordance with various exemplary embodiments described herein can provide improved reliability in loading of confinement wells and deposition of

active OLED layers for electronic displays, such as, for example, high resolution displays. Active OLED layers can include, for example, one or more of the following layers: a hole injection layer, a hole transport layer, an electron blocking layer, an organic light emissive layer, an electron transport layer, an electron injecting layer, and a hole blocking layer. Implementation of some of the above-identified active OLED layers is preferred and implementation of some active OLED layers is optional for electronic displays. For example, at least one hole conducting layer such as a hole injection layer or a hole transport layer must be present as well as an organic light emissive layer. All other above-identified layers may be included as desired to alter (e.g., improve) light emission and power efficiency of an electronic display such as an OLED display.

Various exemplary embodiments of confinement well configurations described herein can increase the size of the confinement well while maintaining high pixel resolution. For instance, various exemplary embodiments use relatively large confinement wells that span a plurality of sub-pixels, thereby enabling the use of relatively attainable droplet sizes and conventional printing system accuracies in the deposition of the active OLED layers, while also achieving relatively high pixel densities. Accordingly, inkjet nozzles that deposit droplet volumes in the range from 1 pL to 50 pL can be used, rather than requiring specially configured or reconfigured printheads with smaller droplet volumes and new printing systems, which may or may not be available. Moreover, by using such larger confinement wells, small manufacturing errors will not have a significant negative effect on deposition precision and the deposited active OLED layers can remain contained within the confinement well.

In accordance with various exemplary embodiments, inkjet printing techniques can provide sufficiently uniform deposition of active OLED layers. For example, various components typically used in OLED displays result in topographies of varying heights on the top surface layer of a confinement well, for example, heights differing by about 100 nanometers (nm) or more. For instance, components such as electrodes may be deposited on a substrate such that a gap is formed between neighboring electrodes in order to form separately addressable electrodes each associated with a differing sub-pixel. Regardless of which active OLED layers are deposited over the electrodes disposed on the substrate of the display, height differentials between the plane of the top surfaces of the electrodes and the top surface of the substrate of the display in regions between neighboring electrodes can contribute to the topography of the subsequently deposited OLED layers. Exemplary inkjet printing techniques and resulting displays in accordance with the present disclosure allow the active OLED layers to be deposited such that the thickness of the active OLED layers are sufficiently uniform, for example over the active electrode region, where active electrode regions can be regions of the electrode associated with the active sub-pixel area from which light is emitted. In an exemplary embodiment, a thickness of the OLED layer, at least over the active electrode region, can be less than the thickness of the sub-pixel electrodes. Sufficiently uniform thicknesses of the OLED layers over the active electrode area can reduce undesirable visual artifacts. For example, OLED ink formulations and printing processes can be implemented to minimize non-uniformity in the deposited film thickness within a given deposition area, even when that area includes both electrode and non-electrode regions. In other words, portions within the deposition area not covered by an electrode

structure can contribute to the OLED layer topography such that the OLED layer can sufficiently conform to the underlying structures over which it is deposited within the deposition area. Minimizing non-uniformities in the deposited film thickness can provide for substantially uniform light emission when a particular sub-pixel electrode is addressed and activated.

In accordance with yet other exemplary embodiments, pixel layout configurations contemplated by the present disclosure can increase active region areas. For example, confinement structures can define confinement wells having a contiguous area that spans a plurality of sub-pixels such that non-active portions (e.g., substrate areas associated with confinement structures) of the display are reduced. For instance, rather than a confinement structure surrounding each sub-pixel electrode as in various conventional OLED displays, a plurality of individually addressed sub-pixel electrodes can be surrounded by a confinement structure where each sub-pixel electrode can be associated with a differing pixel. By reducing the area taken up by the confinement structures, the fill factor can be maximized because the ratio of the non-active region to the active region of each pixel is increased. Achieving such increases in fill factor can enable high resolution in smaller size displays, as well as improve the lifetime of the display.

In accordance with yet other exemplary embodiments, the present disclosure contemplates an organic light-emissive display that includes a confinement structure disposed on a substrate, wherein the confinement structure defines a plurality of wells in an array configuration. The display further includes a plurality of electrodes disposed within each well and spaced apart from one another. The display further can include first, second, and third organic light emissive layers in at least one of the plurality of wells, each layer having first, second, and third light emissive wavelength ranges, respectively. A number of electrodes disposed within the well associated with the first and second organic light-emissive layer differs from a number of electrodes disposed within the well associated with the third organic light emissive layer.

In accordance with yet other exemplary embodiments, the present disclosure contemplates an organic light-emissive display that includes a confinement structure disposed on a substrate, wherein the confinement structure defines a plurality of wells in an array configuration, including a first well, a second well, and a third well. The display further can include a first plurality of electrodes disposed within the first well and associated with a differing pixel, a second plurality of electrodes disposed within the second well and associated with a differing pixel, and at least one third electrode disposed within the third well, wherein a number of electrodes disposed within each of the first and second wells differs from a number of electrodes disposed within the third well. The display can further include a first organic light emissive layer having a first light-emissive wavelength range disposed in the first well, a second organic light emissive layer having a second light-emissive wavelength range disposed in the second well, and third organic light emissive layer having a third light-emissive wavelength range disposed in the third well.

In accordance with various other exemplary embodiments, pixel layout configurations can be arranged to extend the lifetime of the device. For example, sub-pixel electrode size can be based on the corresponding organic light-emission layer wavelength range. For instance, a sub-pixel electrode associated with light emission in the blue wavelength range can be larger than a sub-pixel electrode asso-

ciated with light emission in the red or green wavelength ranges, respectively. Organic layers associated with blue light emission in OLED devices typically have shortened lifetimes relative to organic layers associated with red or green light emission. In addition, operating OLED devices to achieve a reduced brightness level increases the lifetime of the devices. By increasing the emission area of the blue sub-pixel relative to the red and green sub-pixels, respectively, in addition to driving the blue sub-pixel to achieve a relative brightness less than a brightness of the red and green sub-pixels (e.g., by adjusting the current supplied when addressing the sub-pixel as those of ordinary skill in the art are familiar with), the blue sub-pixel can serve to better balance the lifetimes of the differing colored sub-pixels while still providing for the proper overall color balance of the display. This improved balancing of lifetimes can increase the overall lifetime of the display by extending the lifetime of the blue sub-pixels.

FIG. 2 illustrates a partial, plan view of one exemplary pixel arrangement of an organic light-emitting diode (OLED) display 100 according to an exemplary embodiment of the present disclosure. FIG. 3A illustrates a cross-sectional view along section 3A-3A identified in FIG. 2 of one exemplary embodiment of a substrate, depicting various structures for forming an OLED display. FIG. 3B illustrates a cross-sectional view along section 3B-3B identified in FIG. 2 of one exemplary embodiment of a substrate, depicting various structures for forming an OLED display.

The OLED display 100 generally includes a plurality of pixels, e.g., such as defined by dotted line boundaries 150, 151, 152, that when selectively driven emit light that can create an image to be displayed to a user. In a full color display, a pixel 150, 151, 152 can include a plurality of sub-pixels of differing colors. For example, as illustrated in FIG. 2, pixel 150 can include a red sub-pixel R, a green sub-pixel G, and a blue sub-pixel B. As can be seen in the exemplary embodiment of FIG. 2, sub-pixels need not be the same size, although in an exemplary embodiment they could be. Pixels 150, 151, 152 can be defined by driving circuitry that cause light emission such that no additional structure is necessary to define a pixel. Alternatively, exemplary embodiments of the present disclosure contemplate various new arrangements of pixel definition structures that can be included within display 100 to delineate the plurality of pixels 150, 151, 152. Those having ordinary skill in the art are familiar with materials and arrangements of conventional pixel definition structures used to provide crisper delineation between pixels and sub-pixels.

With reference to FIGS. 3A and 3B in addition to FIG. 2, OLED display 100 can include a substrate 102. Substrate 102 can be any rigid or flexible structure that can include one or more layers of one or more materials. Substrate 102 can include, for example, glass, polymer, metal, ceramic, or combinations thereof. While not illustrated for simplicity, substrate 102 can include additional electronic components, circuits, or conductive members, with which those having ordinary skill in the art have familiarity. For instance, thin-film transistors (TFTs) (not shown) can be formed on the substrate before depositing any of the other structures that are discussed in further detail below. TFTs can include, for example, at least one of a thin film of an active semiconductor layer, a dielectric layer, and a metallic contact where those of ordinary skill in the art would be familiar with materials used in the manufacture of such TFTs. Any of the active OLED layers can be deposited to conform to any topography created by TFTs or other structures formed on substrate 102, as discussed below.

Confinement structures 104 can be disposed on the substrate 102 such that the confinement structures 104 define a plurality of confinement wells. For instance, the confinement structures 104 can be a bank structure. A plurality of sub-pixels can be associated with each confinement well and the organic light-emissive material deposited within each confinement well allows all sub-pixels associated with the confinement well to have the same light emission color. For example, in the arrangement of FIG. 2, confinement well 120 can receive droplets of OLED ink associated with sub-pixels that emit red light denoted by R, confinement well 130 can receive droplets of OLED ink associated with sub-pixels that emit green light denoted by G, and confinement well 140 can receive droplets of OLED ink associated with sub-pixels that emit blue light denoted by B. Those having ordinary skill in the art would appreciate, as will be further explained below, that the confinement wells can also receive various other active OLED layers, including but not limited to, for example, additional organic light-emissive material and a hole conducting layer.

The confinement structures 104 can define confinement wells 120, 130, 140 to confine material associated with a plurality of sub-pixels. In addition, confinement structures 104 can prevent spreading of OLED ink into adjacent wells, and/or can assist (through appropriate geometry and surface chemistry) in the loading and drying process such that the deposited film is continuous within the region bounded by confinement structures 104. For example, edges of the deposited films can contact the confinement structures 104 that surround the confinement wells 120, 130, 140. The confinement structures 104 can be a single structure or can be composed of a plurality of separate structures that form the confinement structures 104.

The confinement structures 104 can be formed of various materials such as, for example, photoresist materials such as photoimageable polymers or photosensitive silicone dielectrics. The confinement structures 104 can comprise one or more organic components that are, after processing, substantially inert to the corrosive action of OLED inks, have low outgassing, have a shallow (e.g. <25 degrees) sidewall slope at the confinement well edge, and/or have high phobicity towards one or more of the OLED inks to be deposited into the confinement well, and may be chosen based on the desired application. Examples of suitable materials include, but are not limited to PMMA (poly-methylmethacrylate), PMGI (poly-methylglutarimide), DNQ-Novolacs (combinations of the chemical diazonaphthoquinone with different phenol formaldehyde resins), SU-8 resists (a line of widely used, proprietary epoxy based resists manufactured by MicroChem Corp.), fluorinated variations of conventional photoresists and/or any of the aforementioned materials listed herein, and organo-silicone resists, each of which can be further combined with each other or with one or more additives to further tune the desired characteristics of the confinement structures 104.

Confinement structures 104 can define confinement wells that have any shape, configuration, or arrangement. For example, the confinement wells 120, 130, 140 can have any shape such as rectangular, square, circular, hexagonal, etc. Confinement wells in a single display substrate can have the same shape and/or size or differing shapes and/or sizes. Confinement wells associated with differing light emission colors can have differing or the same shapes and/or sizes. Moreover, adjacent confinement wells can be associated with alternating light emission colors or adjacent confinement wells can be associated with the same light emission colors. In addition, confinement wells can be arranged in

columns and/or rows where the columns and/or rows can have uniform or non-uniform alignment.

The confinement wells can be formed using any of a variety of manufacturing methods, such as, for example, inkjet printing, nozzle printing, slit coating, spin coating, spray coating, screen printing, vacuum thermal evaporation, sputtering (or other physical vapor deposition method), chemical vapor deposition, etc. and any additional patterning not otherwise achieved during the deposition technique can be achieved by using shadow masking, one or more photolithography steps (e.g. photoresist coating, exposure, development, and stripping), wet etching, dry etching, lift-off, etc.

As illustrated in FIG. 2, confinement wells **120**, **130**, **140** according to various exemplary embodiments, can be defined by the confinement structures **104** such that they span a plurality of pixels **150**, **151**, **152**. For example, pixel **150** includes a red sub-pixel R, a green sub-pixel G, and a blue sub-pixel B that are each part of a differing confinement well **120**, **130**, **140**. Each confinement well **120**, **130**, **140** can include a plurality of electrodes, such as **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144**, wherein the electrodes within the confinement wells **120**, **130**, **140** can be spaced apart from each other such that a gap S is formed between adjacent electrodes within a confinement well. In exemplary embodiments, the gap S can be of sufficient size to electrically isolate an electrode from any adjacent electrode, and in particular, the active electrode regions of adjacent electrodes can be isolated from one another. The gap or space S can reduce current leakage and improve sub-pixel definition and overall pixel definition.

While omitted for clarity and ease of illustration, drive circuitry can be disposed on the substrate **102**, and such circuitry can be disposed either beneath the active pixel areas (i.e., the light emitting regions) or within the non-active pixel areas (i.e., the non-light emitting regions). In addition, while not illustrated, circuitry can also be disposed under confinement structures **104**. The drive circuitry can be coupled to each electrode such that each electrode can be selectively addressed independently of the other electrodes within the confinement well. The region of non-uniform topography that results due to the gap S between electrodes is described in further detail below.

Each electrode **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144** within a confinement well **120**, **130**, **140** can be associated with a differing sub-pixel. For example, as illustrated in FIG. 2, confinement well **120** can be associated with red light emission. Electrodes **106**, **107**, **108**, **109** can be positioned within the confinement well **120** where each electrode is operable to address a sub-pixel of a differing pixel (e.g., pixels **151** and **152** being illustrated). At least two electrodes can be positioned within each confinement well **120**, **130**, **140**. The number of electrodes positioned within each confinement well **120**, **130**, **140** can be the same or differing from other confinement wells. For example, as illustrated in FIG. 2, confinement well **140** can include two sub-pixel electrodes **142**, **144** associated with blue light emission and confinement well **130** can include four sub-pixel electrodes **136**, **137**, **138**, **139** associated with green light emission.

In an exemplary embodiment, the confinement structures **104** can be disposed on a portion of the electrodes **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144**. As illustrated in FIGS. 3A and 3B, the confinement well **120** can be defined by the confinement structures **104** where the confinement structures **104** are disposed partially over a portion of electrodes **106**, **108** and partially directly over substrate **102**

without being over an electrode. Alternatively, the confinement structures **104** can be disposed over the substrate **102** between electrodes of adjacent confinement wells. For example, the confinement structures **104** can be disposed on substrate **102** in a space formed between electrodes associated with a differing sub-pixel emission color such that the confinement structures **104** are directly disposed on substrate **102** and are not disposed over any portion of an electrode. In such a configuration (not illustrated), the electrodes corresponding to sub-pixels can be disposed either directly adjacent to (in abutment with) the confinement structures **104** or the electrodes can be spaced apart from the confinement structures **104** such that sub-pixel definition can be achieved.

When a voltage is selectively applied to an electrode **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144**, light emission can be generated within a sub-pixel of a pixel, such as, pixels **150**, **151**, **152**. Electrodes **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144**, can be transparent or reflective and can be formed of a conductive material such as a metal, a mixed metal, an alloy, a metal oxide, a mixed oxide, or a combination thereof. For example, in various exemplary embodiments, the electrodes may be made of indium-tin-oxide, magnesium silver, or aluminum. Electrodes **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144**, can have any shape, arrangement, or configuration. For example, referring to FIG. 3A, electrodes **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144**, can have a profile such that the top surface **106a**, **108a** can be substantially planar and parallel to the surface of the substrate **102** while the side edges **106b**, **108b** of the electrodes can be substantially perpendicular to or can be angled and/or rounded with respect to the surface of the substrate.

It is further noted that the active portion of the electrode, i.e. the portion associated with light emission, are those portions of the electrode which are disposed directly underneath the deposited OLED layers without any intervening insulating substrate structures between the electrode surface and the OLED layers. By way of example, again with reference to FIG. 3A, the portions of electrodes **106** and **108** that are disposed beneath confinement structures **104** are excluded from the active portion of the electrode area, whereas the remainder of the regions of electrodes **106** and **108** are included in the active portion of the electrode area.

The electrodes may be deposited in various ways, such as, by a thermal evaporation, chemical vapor deposition, or sputtering method. The patterning of the electrodes may be achieved, for example, using shadow masking or photolithography. As mentioned above, electrodes **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144** can have a thickness and be spaced apart such that a topography is formed on the substrate **102**, shown best in the various cross-sectional views, such as in FIG. 3A. In an exemplary embodiment, electrodes **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144** can have a thickness ranging from 60 nm to 120 nm, though this range is nonlimiting and larger or smaller thicknesses are possible as well.

One or more active OLED layers can be provided within each confinement well **120**, **130**, **140** such as hole conducting layer **110** and organic light emissive layer **112** shown in FIGS. 3A and 3B. The active OLED layers can be deposited such that they can sufficiently conform to the topographies that result from thickness of and spacing between the electrodes **106**, **107**, **108**, **109**, **136**, **137**, **138**, **139**, **142**, **144** within a confinement well **120**, **130**, **140**, as well as the thickness of the respective active OLED layers. For example, the active OLED layers can be continuous within

a well and have a thickness so as to sufficiently conform and follow the resultant topography of the underlying electrode structures disposed within each confinement well.

The deposited OLED layers may therefore result in a surface topography that does not lie in a single plane parallel to the substrate and across the entire confinement well. For example, one or both of OLED layers 110, 112 can be non-planar and discontinuous in a single plane of the display (wherein the plane of the display is intended as a plane parallel to substrate 102) due to the relative depression or protrusion associated with any surface feature including electrodes disposed on substrate 102. As shown, the OLED layers 110, 112 can sufficiently conform to underlying surface feature topographies such that a top surface of the OLED layer can have a resulting topography that follows the topography of the underlying surface features. In other words, each deposited OLED layer sufficiently conforms to all underlying layers and/or surface features disposed on the substrate 102 such that those underlying layers contribute to the resulting non-planar top surface topography of the OLED layers after they are deposited. In this way, in a plane across the confinement well that is parallel to a plane of the display, a discontinuity in layer 110 or 112, or both, can arise as the layer(s) rise and/or fall, relative to the plane, with the existing surface features provided from electrodes, circuitry, pixel definition layers, etc., in the confinement well. While the active OLED layers 110 and/or 112 need not perfectly conform to the underlying surface topography (for example, as explained below there may be local non-uniformities in thickness around edge regions and the like), a sufficiently conformal coating in which there are no significant build-ups or depletions of material can promote a more even, uniform, and repeatable coating.

As shown in FIG. 3A, each layer 110, 112 can be substantially continuous within the entire confinement well 120 such that each layer is disposed over substantially all surface features within the confinement well 120 (e.g. sub-pixel electrodes, circuitry, pixel definition layers, etc.) where the edges of each layer contact the confinement structures 104 surrounding the confinement well 120. In various exemplary embodiments, active OLED layer material can be deposited to form a discrete continuous layer entirely within a confinement well to substantially prevent any discontinuities in the layer within the well (in other words a region within the well where the active OLED layer material is missing). Such discontinuities can cause undesirable visual artifacts within the emission region of a sub-pixel. It is worth noting that though each layer 110, 112 is substantially continuous within the confinement well, it can nonetheless be discontinuous in a single plane, as noted above, due to the rising/falling of the layer as it sufficiently conforms to existing topographies of features disposed in the confinement well over which the layers are deposited. For example, in exemplary embodiments, if such a rise and/or fall is by an amount, e.g., 100 nm, greater than the thickness of the thinnest part of the deposited layer within the well, e.g., 50 nm, the OLED material layer will not be continuous in a plane parallel to the display within the well.

The layers 110, 112 can have a substantially uniform thickness within each confinement well which may provide for more uniform light emission. For the purpose of this application, substantially uniform thickness can refer to an average thickness of the OLED layer over planar surface regions, such as over active electrode regions, but also can encompass minute variations or local non-uniformities in thickness as described below. Over the planar surface regions, e.g. 106a, 108a, and bottom surface of gaps in FIG.

3A, it is anticipated that for a substantially uniform OLED coating the variation in thickness from an average thickness of the OLED layer can be less than $\pm 20\%$, such as less than $\pm 10\%$ or less than $\pm 5\%$.

As noted above, however it is contemplated that local non-uniformities in thickness may arise in portions of the layers 110, 112 surrounding changes in surface topography and/or surface chemistry, and in such regions, the film thickness can locally deviate substantially from the $\pm 20\%$, $\pm 10\%$, or $\pm 5\%$ parameters specified above. For example, local non-uniformities in the thickness of a continuous layer can occur due to the topography associated with surface features disposed on substrate 102 and/or a change in surface chemistry between the surface features disposed on the substrate 102 such as at the edge of the confinement well structures 104, at the edge of a pixel definition layer (discussed below), on the electrode edge sidewalls (e.g. along 106b, 108b), or where the electrode meets the substrate surface. Local non-uniformities can lead to deviations in film thickness. For example, the local non-uniformities can deviate from the thickness of the layers 110, 112 provided over the active electrode regions (e.g. along 106a, 108a) of electrodes 106, 108. The non-uniformities can create generally localized "edge effect" deviations within a range of approximately 5 μm -10 μm around such surface features disposed on substrate 102 in the confinement well, such as at edges of electrodes, circuitry, pixel definition layers, etc. For the purposes of this application, such "edge effect" deviations are intended to be encompassed when describing the OLED film coating as having a "substantially uniform thickness" within the well.

In an exemplary embodiment, the thickness of each layer 110, 112 can be equal to or less than the thickness of the electrodes such that the upper surface of each layer does not lie in a single plane parallel to the plane of the display (i.e., a plane parallel to the substrate) due to the dip in the film formed as the layer traverses the gap between the active regions of the electrodes. This is illustrated, for example, in FIG. 3A, wherein a dashed line is provided to illustrate a plane P that is parallel to the plane of the substrate 102. As shown, layers 110, 112 can each have an average thickness that is substantially uniform within the region of layers 110, 112 over with the active electrode regions of electrodes 106, 108. However, layers 110, 112 can also include small and localized non-uniform thickness in areas associated with topography changes caused by the surface features such as around edges of those surface features (e.g. edges of electrodes 106, 108 adjacent to the gap).

The layers 110, 112 can be deposited using any manufacturing method. In an exemplary embodiment, the hole conducting layer 110 and the organic light-emission layer 112 can be deposited using inkjet printing techniques. For example, the material of hole conducting layer 110 can be mixed with a carrier fluid to form an inkjet ink that is formulated to provide reliable and uniform loading into the confinement wells. The ink for depositing hole conducting layer 110 can be delivered to the substrate at high speeds from an inkjet head nozzle into each confinement well. In various exemplary embodiments, the same hole conducting material can be delivered to all of the confinement wells 120, 130, 140 so as to provide for depositing of the same hole conducting layer 110 within all of the confinement wells 120, 130, 140. After material is loaded into the confinement wells to form hole conducting layer 110, the display 100 can be dried to allow any carrier fluid to evaporate, a process which can include exposing the display to heat, to vacuum, or ambient condition for a set period of time. Following

drying, the display may be baked at an elevated temperature so as to treat the deposited film material, for example, to induce a chemical reaction or change in film morphology that is beneficial for the quality of the deposited film or for the overall process. The material associated with each organic light-emissive layer **112** can be similarly mixed with a carrier fluid such as an organic solvent or a mixture of solvents to form inkjet inks that are formulated to provide reliable and uniform loading into the confinement wells. These inks can then be inkjet deposited using an inkjet process within the appropriate confinement wells **120**, **130**, **140** associated with each emission color. For example, the ink associated with the red organic light-emissive layer, the ink associated with the green organic light-emissive layer, and the ink associated with the blue organic light-emissive layer are separately deposited into the corresponding confinement wells **120**, **130**, **140**. The differing organic light-emissive layers **112** can be deposited simultaneously or sequentially. After loading with one or more of the inks associated with the organic light emissive layers, the display can be similarly dried and baked as described above for the hole conducting layer.

While not illustrated, additional active OLED layers of material can be disposed within the confinement well. For example, OLED display **100** can further include a hole injection layer, a hole transport layer, an electron blocking layer, a hole blocking layer, an electron transport layer, an electron injection layer, a moisture protection layer, an encapsulation layer, etc., all of which those having ordinary skill in the art are familiar with but are not discussed in detail here.

The hole conducting layer **110** can include one or more layers of material that facilitates injection of holes into the organic light-emissive layer **112**. For example, hole conducting layer **110** can include a single layer of hole conducting material such as, for example, a hole injection layer. Alternatively, hole conducting layer **110** can include a plurality of layers such as at least one of a hole injection layer, such as Poly(3,4-ethylenedioxythiophene:poly(styrenesulfonate) (PEDOT:PSS), and a hole transport layer, such as N,N'-Di-((1-naphthyl)-N,N'-diphenyl)-1,1'-biphenyl)-4,4'-diamine (NPB).

The organic light-emissive layer **112** can be deposited over the hole conducting layer **110** such that organic light-emissive layer **112** sufficiently conforms to the topography created by the electrodes, the space between the electrodes, and the topography of the hole conducting layer. The organic light-emissive layer **112** can include material to facilitate light emission such as an organic electroluminescence material.

In an exemplary embodiment, the thickness of the OLED stack (e.g. all active OLED layers deposited over the electrodes within a confinement well) can range from 10 nm to 250 nm. For example, a hole transport layer can have a thickness ranging from 10 nm to 40 nm; a hole injection layer can have a thickness ranging from 60 nm to 150 nm; an organic light-emissive layer can have a thickness ranging from 30 nm-150 nm, and optionally a hole blocking layer, electron transport layer, and electron injection layer having combined thickness ranging from 10 nm to 60 nm.

In an exemplary embodiment, it is contemplated that droplets having a volume of about 10 pL or less may be used to produce each of layers **110**, **112**. In various exemplary embodiments, droplet volumes of 5 pL or less, 3 pL or less, or 2 pL or less may be used. The OLED layers **110**, **112** can be formed using from 1 to 20 droplets having the above described volumes.

In one exemplary and nonlimiting embodiment, the present disclosure contemplates confinement wells arranged such that the areas of the wells associated with red, green, or blue light emissions **120**, **130**, **140** can be $66\text{ }\mu\text{m}\times 66\text{ }\mu\text{m}$ for displays having a resolution of 326 ppi (e.g., Pitch=78 μm) where the width between neighboring wells in this embodiment can be 12 μm . The area associated with red or green sub-pixel light emission of such an arrangement can be $31.5\text{ }\mu\text{m}\times 31.5\text{ }\mu\text{m}$, and the area associated with blue sub-pixel light emission can be $66\text{ }\mu\text{m}\times 30\text{ }\mu\text{m}$, leading to an overall pixel fill factor of 65%, as compared to the fill factor of 46% for the conventional RGB side-by-side layout described with reference to FIG. 1. For another exemplary and nonlimiting embodiment, a display having a resolution of 440 ppi (e.g., Pitch=58 μm), it is contemplated to arrange confinement wells such that areas of the wells associated with red, green, or blue light emissions **120**, **130**, **140** can be $46\text{ }\mu\text{m}\times 46\text{ }\mu\text{m}$, where again the width between neighboring wells in this embodiment is 12 μm . An area associated with red or green sub-pixel light emission of such a display structure can be $20.3\text{ }\mu\text{m}\times 20.3\text{ }\mu\text{m}$, while an area associated with blue sub-pixel light emission can be $76\text{ }\mu\text{m}\times 49.1\text{ }\mu\text{m}$, thereby producing a fill factor of approximately 46%, as compared to the fill factor of 30% for the conventional RGB side-by-side layout described with reference to FIG. 1. In these embodiments the width between adjacent wells can be 12 μm , but as discussed above, this width can take on different values, and while a smaller value may be desirable (to provide for a greater proportion of the substrate area assigned to the active electrode areas), processing constraints on the formation of the well structure and circuit layout constraints may effectively set a lower bound on this dimension. The value of 12 μm is selected as representative for these examples, but one having ordinary skill in the art would appreciate that other dimensions could be used, for example, larger dimensions like 20 μm , or smaller dimensions, like 8 μm , 6 μm , or even 1 μm without departing from the scope of the present disclosure and claims. One having ordinary skill in the art can further appreciate that while in the above examples, the red, green, and blue confinement wells each have identical dimensions, other arrangements are possible. For example, two confinement wells associated with differing emission colors can have the same dimensions and one confinement well associated with yet another differing emission color can have a differing dimension or the confinement wells associated with each emission color can have differing dimensions.

These exemplary, non-limiting arrangements in accordance with the present disclosure provide for confinement wells having minimum well dimensions of greater than 45 μm even for the very high resolution case of 440 ppi, and therefore can permit droplet volumes, for example, of around 10 pL, to be used, thereby simplifying manufacturing by allowing for the use of droplet volumes that are available from existing inkjet printing. In addition, the above exemplary, non-limiting arrangements increase pixel fill factor as compared to a conventional RGB side-by-side layout by about 43% and 84% for the 326 ppi and 440 ppi cases respectively. More generally, the various exemplary embodiments in accordance with the present disclosure provide enhancements in the fill factor of high resolution displays manufactured using inkjet, such as very high resolution displays, for which enhancements of 40% or more are possible.

As those of ordinary skill in the art are familiar with, a common electrode (not shown) can be disposed over the organic light-emissive layer **112** following deposition. After

the common electrode is deposited, the resulting topography of the common electrode can sufficiently conform to topography of organic light-emissive layer **112**. The common electrode can be deposited using any manufacturing technique, for example, by vacuum thermal evaporation, sputtering, chemical vapor deposition, spray coating, inkjet printing, or other techniques. The common electrode can be transparent or reflective and can be formed of a conductive material such as a metal, a mixed metal, an alloy, a metal oxide, a mixed oxide, or a combination thereof. For example, indium tin oxide or a thin layer of magnesium silver. The thickness of the common electrode can range from approximately 30 nm to 500 nm.

In addition, the common electrode can have any shape, arrangement, or configuration. For example, the common electrode can be disposed as a discrete layer associated with single sub-pixel, or a single pixel. Alternatively, the common electrode can be disposed over multiple sub-pixels or pixels, for example, over the entire pixel arrangement of the display **100**. For instance, the common electrode can be blanket deposited within the confinement wells **120**, **130**, **140** as well as over the confinement structures **104**. Additional active OLED layers (not shown for simplicity) can be deposited onto the organic light emissive layer **112** before deposition of a common electrode, such as electron transport layers, electronic injection layers, and/or hole blocking layers. Such additional OLED layers can be deposited by inkjet printing, by vacuum thermal evaporation, or by another method.

In accordance with exemplary embodiments, the OLED device **100** can have a top emissive configuration or a bottom emissive configuration. For example, as illustrated in FIG. 3A, in a top emissive configuration, electrodes **106**, **108** can be reflective electrodes and the common electrode that is disposed over the organic light-emissive layer can be a transparent electrode. Alternatively, in a bottom emissive configuration, electrodes **106**, **108** can be transparent and the common electrode can be reflective.

In another exemplary embodiment, the OLED display **100** can be an active-matrix OLED (AMOLED). An AMOLED display, as compared to a passive-matrix OLED (PMOLED) display, can enhance display performance, but relies on active drive circuitry, including thin film transistors (TFTs), on the substrate and such circuitry is not transparent. While PMOLED displays have some elements, such as conductive bus lines that are not transparent, AMOLED displays have substantially more elements that are non-transparent. As a result, for a bottom emission AMOLED display, the fill factor may be reduced compared to a PMOLED because light can only be emitted through the bottom of the substrate between the non-transparent circuit elements. For this reason, it may be desirable to use a top emission configuration for AMOLED displays since using such a configuration may permit the OLED device to be constructed on top of such non-transparent active circuit elements. Thus, light can be emitted through the top of the OLED device without concern for the opacity of the underlying elements. In general, using a top emission structure can increase the fill factor of each pixel **150** of display **100** because light emission is not blocked by additional non-transparent elements (e.g. TFTs, driving circuitry components, etc.) deposited on the substrate **102**.

In addition, non-active areas of each pixel can be limited to the confinement structures, surface features, and/or pixel definition layers (examples of which are described in further detail below) formed on the substrate **102**. A conductive grid also can be disposed on substrate **102** to prevent an unde-

sirable voltage drop across the display **100**, which can arise because the transparent top electrodes used in top emission OLED structures typically have low conductivities. When the common electrode is blanket deposited within the confinement wells **120**, **130**, **140** and over the confinement structures **104**, the conductive grid can be disposed on non-active portions of the substrate **102** and coupled to the common electrode through via holes formed in selected confinement structures **104**. However, the present disclosure is not limited to a top emission active-matrix OLED configuration. The techniques and arrangements discussed herein can be used with any other type of displays such as bottom emission and/or passive displays as well as those one of ordinary skill in the art would understand how to make using appropriate modifications.

In an exemplary embodiment, as illustrated in FIG. 3A, each confinement well can include a plurality of active sub-pixel regions that span W1 and W2, respectively, and are separated by gap S, and are confined within a well having width CW. The dimensions, W1, W2, and CW are primarily related to pixel pitch, which correlates to the resolution (e.g. 326 ppi, 440 ppi) of the display. The dimension of the gap S is related to restrictions associated with fabrication techniques and processes, and layout. In general, it may be desirable to minimize the dimension associated with the gap S. For example, 3 μm may be a minimum dimension; however, one of ordinary skill in the art would appreciate that dimensions from as small as 1 μm to greater than 10 μm are possible. The height H of confinement structures **104** is also related to processing restrictions rather than a particular display layout or resolution. While an exemplary value of the height H of confinement structures **104** may be 1.5 μm , the height H, can range from 0.5 μm to 5 μm in various exemplary embodiments. Referring to FIG. 3B, BW is the width of the confinement structures **104** between adjacent wells (e.g., wells **120** and **130** in FIG. 3B). As described above, it may be desirable to minimize this dimension and an exemplary value is 12 μm . However, one of ordinary skill would understand that this value can be arbitrarily large (e.g. hundreds of microns) in some instances, and can also be as small as 1 μm , depending on fabrication techniques and processes that may permit such a small value for BW.

Referring now to FIG. 4, a cross-sectional view of an exemplary embodiment of a confinement well **220** of a display **200** is illustrated. The arrangement of FIG. 4 is similar to that described above with reference to FIG. 3A, with like numbers used to represent like elements except using the 200 series as opposed to the 100 series. As illustrated, however, the OLED display **200** also includes an additional surface feature **216** disposed in the gap S between electrodes **206**, **208**.

Surface feature **216** can be any structure that does not directly provide electrical current into the OLED films disposed over it, thereby comprising a non-active region of the pixel area between the active regions associated with the electrodes **206** and **208**. For example, the surface feature **216** can further comprise an opaque material. As depicted in FIG. 4, a hole conducting layer **210** and organic light-emissive layer **212** can be deposited over a portion of such circuitry elements, as represented topographically by surface feature **216**. In the case that surface feature **216** contains electrical elements, such elements may be further coated with an electrically insulating material so as to electrically isolate those elements from the OLED films deposited onto surface feature **216**.

In an exemplary embodiment, surface feature **216** can include driving circuitry, including but not limited to, for

example, an interconnect, bus lines, transistors, and other circuitry with which those having ordinary skill in the art are familiar. In some displays, driving circuitry is disposed proximal to the active region of the pixel driven by such circuitry to minimize complicated interconnections and to reduce the voltage drop. In some cases, the confinement well would surround an individual sub-pixel, and such circuitry can be outside the confinement well region such that the circuitry would not be coated with active OLED layers. However, in the exemplary embodiment of FIG. 4, as well as others described herein, because the confinement well 220 can contain a plurality of sub-pixels that are associated with differing pixels, such driving circuitry elements can be provided within the confinement wells, which may optimize the electrical performance of the drive electronics, optimize drive electronics layout, and/or optimize the fill factor.

The hole conducting layer 210 and organic light emissive layer 212 can be deposited (as previously discussed, for example, with reference to FIGS. 3A and 3B) into the region defined by confinement well structures 204 and over the surface feature 216 such that layers 210, 212 sufficiently conform to underlying surface feature topographies and have a substantially uniform thickness in the confinement well, leading to layers 210 and 212 having non-planar top surfaces. In the configuration wherein surface feature 216 extends above the plane of the top surface of the electrode a distance greater than the thickness of one or both of the layers 210 and 212, then one or both of those layers will also be discontinuous in a plane parallel to the plane of the display within the well 220. Thus, one or both layers 210, 212 will be non-planar and discontinuous in a plane parallel to the plane of the display due to the protrusion associated with the surface feature 216. As above, this is illustrated, for example, by the dashed line illustrating a plane P that is coplanar with the surface of 212 that is disposed over the electrodes 206, 208. As shown, the layer 212 is not planar across the entire confinement well and instead sufficiently conforms to the underlying topographies such that the layer 212 has an overall non-planar top surface due to the gap region S and protrusion 216. In other words, one or both of the layers 210, 212 will rise and fall across the confinement well to sufficiently conform to the existing topography of the well prior to the deposition of the layers 210, 212.

While the surface feature 216 is illustrated in FIG. 4 as having a thickness greater than the electrodes, the surface feature 216 can alternatively have a thickness less than or equal to the electrodes. Moreover, while surface feature 216 is illustrated in FIG. 4 as being disposed on substrate 202, surface feature 216 can be further disposed over one or both of electrodes 206, 208. Surface feature 216 can differ for each confinement well in the array and not all confinement wells have to include a surface feature. Surface feature 216 can further function as a pixel definition layer where the non-transparent properties of surface feature 216 can be used to define portions of sub-pixels or overall pixel arrangements.

Referring now to FIGS. 5A and 5B, partial cross-sectional views of another exemplary embodiment of a display confinement well in accordance with the present disclosure is illustrated. The arrangement of FIGS. 5A and 5B is similar to that described above with reference to FIGS. 3A and 3B, with like numbers used to represent like elements except using the 300 series as opposed to the 100 series. As illustrated in FIGS. 5A and 5B, however, the OLED display 300 also includes a definition layer 314. Definition layer 314 can be deposited on substrate 302 where confinement structures 304 can be disposed over the definition layer 314. In

addition, definition layer 314 can be disposed over a non-active portion of electrodes 306, 308. Definition layer 314 can be any physical structure having electrically insulating properties used to define portions of OLED display 300. In an embodiment, definition layer 314 can be a pixel definition layer that can be any physical structure used to delineate pixels within the pixel array. Definition layer 314 can also delineate sub-pixels.

As illustrated, in an exemplary embodiment, the definition layer 314 can extend beyond the confinement structures 304 to over a portion of electrodes 306, 308. Definition layer 314 can be made of an electrically resistant material such that the definition layer 314 prevents current flow and thus can reduce unwanted visual artifacts by substantially preventing light emission through the edges of the sub-pixel. Definition layer 314 can also be provided to have a structure and chemistry to mitigate or prevent the formation of non-uniformities where the OLED films coat over the edge of the definition layer. In this way, definition layer 314 can assist in masking film non-uniformities formed around surface features that would otherwise be included in the active regions of the pixel area and then contribute to pixel non-uniformity; such non-uniformities could occur, for example, at the exterior edges of each sub-pixel where the OLED films contact the confinement well, or at the interior edges of the each sub-pixel where the OLED films contact the substrate surface.

The hole conducting layer 310 and the organic light-emissive layer 312 can each be deposited within the region defined by the confinement structure 304 and over the pixel definition layers so as to form a continuous layer within the confinement well 320. As described above with respect to FIGS. 3A and 3B, the layers 310, 312 can sufficiently conform to the overall topography of the confinement well, and thus may have non-planar surfaces and/or be discontinuous in a plane of the display, as illustrated for example by plane P in FIG. 5A. As explained above with reference to exemplary embodiment of FIG. 3A, the thickness of the hole conducting layer 310 and the organic light-emissive layer 312 can be substantially uniform, as described above.

In an exemplary embodiment, as illustrated in FIG. 5A, each confinement well can include a plurality of active sub-pixel regions including W1 and W2 separated by gap S and contained within a confinement well having width CW, with W1, W2, and CW being primarily related to the pixel pitch, as discussed above with reference to FIG. 3A. Similarly, the dimension of the gap S is related to fabrication and processing techniques, and layout, wherein S may range in exemplary embodiments from 1 μm to greater than 10 μm , with 3 μm being an exemplary dimension for S. The height H of confinement structures 304 may be as described above with reference to FIG. 3A. Referring to FIG. 5B, BW is, as described above, the width of the confinement structures 304 between adjacent wells and can be selected as described above with reference to FIG. 3B.

The dimension T associated with the thickness of the definition layer can be variable based on fabrication techniques and processing conditions, and the type of definition layer material that is used. In various exemplary embodiments, the dimension T associated with the thickness of the definition layer can range from 25 nm to 2.5 μm , but from 100 nm to 500 nm can be considered the most typical range. The dimensions labeled B1, B2 in FIG. 5A and B1, B1' in FIG. 5B, associated with the extension of the definition layer beyond the edge of the confinement structure 104 within the confinement wells, can be selected as desired. However, a larger dimension may contribute to a reduction in fill factor

by reducing the amount of available active pixel electrode area. Therefore, it may be desirable to select the minimum dimension that will serve the desired function, which is generally to exclude edge non-uniformities from the active electrode area. In various exemplary embodiments, this dimension can range from 1 μm to 20 μm , and may, for example, range from 2 μm to 5 μm .

With reference now to FIG. 6, a cross-sectional view of an exemplary embodiment of a confinement well 420 of a display 400 is illustrated. The arrangement of FIG. 6 is similar to that described above with reference to FIGS. 5A and 5B, with like numbers used to represent like elements except using the 400 series as opposed to the 300 series. As shown, however, the OLED display 400 also includes an additional definition layer 416 disposed in the gap S between electrodes 406, 408. As shown in FIG. 6, the definition layer 416 can be a surface feature that has a somewhat differing structure than the surface feature of FIG. 4 in that a portion of the additional definition layer 416 extends throughout the gap S on the substrate 402 and over portions of electrodes 406, 408 adjacent the gaps. The additional definition layer 416 can have any topography, with the one illustrated in FIG. 6 being exemplary only. As illustrated in FIG. 6, a notch 417 can be present in the surface of the additional definition layer 416 that faces away from the substrate 102. The notch 417 can be formed using various methods. For example, notch 417 may result from the manufacturing process such that during deposition of the additional definition layer 416, the layer 416 can generally conform to any topography present within the confinement well such as electrodes 406, 408 where notch 417 is formed by the differing thickness between a substantially uniform thickness over the electrodes 406, 408 and a substantially non-uniform thickness with surfaces not associated with the top surface of electrodes 406, 407. Alternatively, notch 417 can be omitted and the top surface of additional definition layer 416 can have a substantially planar topography, for instance, in the case that the additional definition layer 416 is deposited using a non-conformal deposition method such that the underlying surface topography is smoothed out.

In either configuration, the hole conducting layer 410 and/or the organic light-emissive layer 412 can be deposited (as previously discussed, for example, with reference to FIGS. 3A and 3B) such that layers 410, 412 sufficiently conform to the topography of the additional definition layer 416 and have a substantially uniform thickness, as has been described above.

The distance between the top surface (i.e., the surface facing away from the substrate) of the additional definition layer 416 and the substrate 402 can be greater than or less than the distance between the top surface of the electrodes 406, 408 and the substrate 402. Alternatively, the distance between the top surface of the additional definition layer 416 and the substrate 402 can be substantially equal to the distance between the top surface of the electrodes 406, 408 and the substrate 402. In other words, the thickness of the additional definition layer 416 can be such that it ranges from being positioned between the top surface of the substrate and the top surfaces of the surrounding confinement structures 404, or such that it substantially lies in the same plane as the top surfaces of the confinement structures 404. Alternatively, the additional definition layer 416 can be substantially the same height as the electrodes 406, 408 such that the additional definition layer 416 does not overlap a portion of the electrodes 406, 408, but rather fills in the gap S between them.

Hole conducting layer 410 and organic light-emissive layer 412 can be disposed over the portions of definition layer 414 that extend beyond the confinement structure 404 and into the well 420, and the layers 410, 412 can extend over the additional definition layer 416 within the confinement well 420 defined by confinement structure 404. The additional definition layer 416 can be made of an electrically resistant material such that the additional definition layer 416 can prevent current flow and thus may reduce undesirable visual artifacts by preventing light emission through the edges of the sub-pixel. The definition layer 414 and the additional definition layer 416 can be made of the same or differing materials.

In an exemplary embodiment, as illustrated in FIG. 6, each confinement well can include a plurality of active sub-pixel regions including W1 and W2 separated by gap S and contained within a confinement well having width CW, with W1, W2, CW, and S being primarily related to the pixel pitch, as discussed above. As above, 3 μm may be a minimum dimension for S, but one of ordinary skill in the art would appreciate that dimensions from as small as 1 μm to even greater than 10 μm are possible. The height H of confinement structures 404 can be chosen and with the ranges as described above with reference to FIGS. 3A and 3B, for example.

The dimension T1 associated with the thickness of the definition layer and the dimension T2 associated with the thickness of the additional definition layer can be variable based on fabrication techniques, processing conditions and the type of definition layer material that is used. As a result, the dimension T1 associated with the thickness of the definition layer and the dimension T2 associated with the thickness of the additional definition layer can range from 50 nm to 2.5 μm , for example, from 100 nm to 500 nm. The dimensions SB1, SB2, and B2 associated with the extension of the definition layer inside the edge of the confinement well can be selected as desired. However, a larger dimension will contribute to a reduction in fill factor by reducing the amount of available active pixel electrode area. Therefore, it may be desirable to select the minimum dimension that will serve the desired function, which is generally to exclude edge non-uniformities from the active electrode area. In various exemplary embodiments, this dimension can range from 1 μm to 20 μm , and may for example range from 2 μm to 5 μm .

As those having ordinary skill in the art would appreciate based on the present disclosure, any of the disclosed definition layer configurations can be used in any combination of differing ways to achieve a desirable pixel definition configuration. For example, definition layer 414 and/or additional definition layer 416 can be configured to define any pixel and/or a sub-pixel region or any partial pixel and/or sub-pixel region where definition layer 414 can be associated a definition layer deposited under any confinement structures 404 and additional definition layer 416 can be associated with any definition layer deposited within a confinement well between electrodes such as in confinement well 420. An artisan of ordinary skill would recognize that the cross-sections shown within the present disclosure are merely illustrative cross-sections and therefore the present disclosure is not to be limited to the specific cross-sections illustrated. For instance, while FIGS. 3A and 3B are illustrated along line 3A-3A and 3B-3B respectively, a different cross-sectional view, taken along a different line, for example including in directions orthogonal to 3A-3A and 3B-3B, may reflect differing definition layer configurations. In an exemplary embodiment, definition layers can be used

in combination to outline a pixel, such as pixels **150**, **151**, **152** illustrated in FIG. 2. Alternatively, definition layers can be configured to define a sub-pixel such that the definition layers completely or partially surround a sub-pixel electrode within a confinement well.

Referring now to FIG. 7, a cross-sectional view of yet another exemplary embodiment is illustrated. OLED display **500** can include surface feature **516** and a definition layer **514**. The arrangement of FIG. 7 is similar to that described above with reference to FIG. 4, with like numbers used to represent like elements except using the 500 series as opposed to the 200 series. As illustrated in FIG. 7, however, OLED display **500** further includes a definition layer **514** disposed under confinement structures **504**. The definition layer **514** can be any physical structure used to define portions of OLED display **500**. In an embodiment, definition layer **514** can be a definition layer that can be any physical structure used to delineate pixels within the pixel array and/or sub-pixels with a pixel. As illustrated, in an exemplary embodiment, the definition layer **514** can extend beyond the confinement structure **504** and over a portion of electrodes **506**, **508**. Definition layer **514** can be made of an electrically resistant material such that the definition layer **514** prevents current flow and thus can reduce unwanted visual artifacts by preventing light emission through the edges of the sub-pixel. In this way, definition layer **514** can assist in masking film layer non-uniformities formed at the edge of each sub-pixel that may occur due to edge drying effects. The hole conducting layer **510** and the organic light-emissive layer **512** can be deposited (as previously discussed, for example, with reference to FIGS. 3A and 3B) such that layers **510**, **512** sufficiently conform to underlying surface feature topographies and have a substantially uniform thickness, as has been described above.

Those having ordinary skill in the art would appreciate that the various arrangements and structures, e.g. surface features, definition layers, etc., are exemplary only and that various other combinations and arrangements may be envisioned and fall within the scope of the present disclosure.

Referring now to FIGS. 8-11, partial cross-sectional views of the substrate exhibiting various exemplary steps during an exemplary method of manufacturing an OLED display **600** are illustrated. While the method of manufacturing will be discussed below with reference to display **600**, any and/or all of the steps described can be used in manufacturing other OLED displays, for example OLED displays **100**, **200**, **300**, **400**, and **500** described above. As illustrated in FIG. 8, electrodes **606**, **608** and surface features **616** can be provided over substrate **602**. The electrodes **606**, **608** and surface features **616** can be formed using any manufacturing method such as inkjet printing, nozzle printing, slit coating, spin coating, vacuum thermal evaporation, sputtering (or other physical vapor deposition method), chemical vapor deposition, etc., and any additional patterning not otherwise included in the deposition technique can be achieved by using shadow masking, photolithography (photoresist coating, exposure, development, and stripping), wet etching, dry etching, lift-off, etc. The electrodes **606**, **608** can be formed simultaneously with surface features **616** or sequentially with either the electrodes or the surface features being formed first.

Definition layer **614** and additional definition layer **618** can then be deposited over the surface features **616** and electrodes **606**, **608**, as illustrated in FIG. 9. Layers **614** and **618** can be formed using any manufacturing method, such as inkjet printing, nozzle printing, slit coating, spin coating, vacuum thermal evaporation, sputtering (or other physical

vapor deposition method), chemical vapor deposition, etc., and any needed additional patterning not otherwise included in the deposition technique can be achieved by using shadow masking, photolithography (photoresist coating, exposure, development, and stripping), wet etching, dry etching, lift-off, etc. Definition layer **614** can be formed simultaneously with additional definition layer **618** or the layers **614**, **618** can be formed sequentially with either layer **614** or **618** being formed first.

Confinement structures **604** are provided over definition layers **614**. The confinement structures **604** can be formed to define confinement wells **620** that surround a plurality of sub-pixel electrodes **606**, **608** while spanning a plurality of pixels. The confinement structures **604** can be formed using any manufacturing method, such as inkjet printing, nozzle printing, slit coating, spin coating, vacuum thermal evaporation, sputtering (or other physical vapor deposition method), chemical vapor deposition, etc., and any additional patterning not otherwise included in the deposition technique can be achieved by using shadow masking, photolithography (photoresist coating, exposure, development, and stripping), wet etching, dry etching, lift-off, etc. In one exemplary technique, as illustrated in FIG. 10, confinement structure material can be deposited over substrate **602** in a continuous layer **604'** and the layer can then be patterned using a mask **607** such that a portion **605** of layer **604'** can be removed to expose the sub-pixel electrodes **606**, **608**. The confinement structures **604** are formed by the material of layer **604'** remaining after portions **605** are removed. Alternatively, confinement structures **604** can be formed by actively depositing material to form only the confinement structure such that the deposited confinement structure **604** can define boundaries and the confinement wells are formed within the boundaries of the deposited confinement structures **604**.

In an exemplary embodiment, as illustrated in FIG. 10, each confinement well can include a plurality of active sub-pixel regions including W1 and W2 separated by gap S. As above, the dimensions, W1, W2, and CW are primarily related to the pixel pitch. And the dimension of the gap S is related to restrictions associated with fabrication techniques and processing, and layout, and may range from 1 μm to even greater than 10 μm , with 3 μm being an exemplary minimum dimension. The dimensions SB1 and SB2 associated with the extension of the definition layer inside the edge of the confinement well can be selected as desired. However, a larger dimension will contribute to a reduction in fill factor by reducing the amount of available active pixel electrode area. Therefore, it may be desirable to select the minimum dimension that will serve the desired function, which is generally to exclude edge non-uniformities from the active electrode area. In various exemplary embodiments, this dimension can range from 1 μm to 20 μm , and may for example range from 2 μm to 5 μm .

As illustrated in FIG. 11, a hole conducting layer **610** can then be deposited using inkjet printing within the confinement well **620**. For example, inkjet nozzle **650** can direct droplet(s) **651** of hole conducting material within a target area defined within the confinement well **620**. The hole conducting layer **610** may further comprise two discrete layers, for example, a hole injection layer and a hole transporting layer, and these layers can be sequentially deposited by an inkjet method as described herein. In addition, organic light-emissive layer **612** can be deposited using inkjet printing within the confinement well **620** over the hole conducting layer **610**. Inkjet nozzle **650** can direct droplet(s) **651** of organic light-emissive material within a

target area over the hole conducting layer **610**. One of ordinary skill in the art would appreciate that while a single nozzle is discussed with reference to FIG. **11**, multiple nozzles can be implemented to provide droplets containing hole conducting material or organic light-emissive material within a plurality of confinement wells. As those of ordinary skill in the art are familiar with, in some embodiments, the same or differing colors of organic light-emissive material can be deposited from multiple inkjet nozzle heads simultaneously. In addition, droplet ejection and placement on the target substrate surface can be performed using technology known to those of ordinary skill in the art.

In an exemplary embodiment, a single organic light-emissive layer **612** can be deposited within confinement well **620** such as a red, green, or blue layer. In an alternative exemplary embodiment, a plurality of organic light emissive layers can be deposited within confinement well **620**, one over the other. Such an arrangement can work, for example, when the light emissive layers have differing light emissive wavelengths ranges such that when one light emissive layer is activated to emit light, the other light emissive layer does not emit light or interfere with the light emission of the first organic light-emissive layer. For example, a red organic light-emissive layer or a green organic light-emissive layer can be deposited within confinement well **620** and then a blue organic light-emissive layer can be deposited over the red or green organic light-emissive layer. In this way, while a confinement well can include two different light-emissive layers, only one light emissive-layer is configured to emit light within the confinement well.

Layers **610** and **612** can be deposited so as to sufficiently conform to the topography of definition layer **614**, surface structure **616**, additional definition layer **618**, and electrodes **606**, **608**, as has been described above, and can have a substantially uniform thickness as described above.

The various aspects described above with reference to FIGS. **3A-11** can be used for a variety of pixel and sub-pixel layouts in accordance with the present disclosure, with FIG. **2** being one exemplary and nonlimiting such layout. Various additional exemplary layouts contemplated by the present disclosure are depicted in FIGS. **12-18**. The various exemplary layouts illustrate that there are many ways to implement the exemplary embodiments described herein; in many cases, the selection of any particular layout is driven by various factors, such as, for example, the underlying layout of the electrical circuitry, a desired pixel shape (which are depicted as rectangular and hexagonal shape in the illustrated embodiments, but can be other shapes as well, such as chevrons, circles, hexagons, triangles, and the like), and factors related to visual appearance of the display (such as visual artifacts that can be observed for differing configurations and for differing types of display content, such as text, graphics, or moving video). Those having ordinary skill in the art would appreciate that a number of other layouts fall within the scope of the present disclosure and can be obtained through modification and based on the principles described herein. Further, those having ordinary skill in the art would understand that although for simplicity only the confinement structures that define the confinement wells are described below in the descriptions of FIGS. **12-18**, any of the features, including surface features, circuitry, pixel definition layers, and other layers, described above with reference to FIGS. **3A-11** can be used in combination with any of the pixel layouts herein.

FIG. **12** depicts a partial plan view of an exemplary embodiment of pixel and sub-pixel layout for an OLED display **700**, and is similar to the layout of FIG. **2** with

further aspects of the layout being described below. A confinement structure **704**, for example, a bank structure, as discussed above can be provided on a substrate to define a plurality of confinement wells **720**, **730**, **740** in an arrayed configuration. Each confinement well **720**, **730**, **740** can include a substantially continuous layer of OLED material (indicated by the shaded regions) such that the organic layer extends through the confinement well **720**, **730**, **740** to the confinement structure **704** surrounding the confinement well, for example, edges of the layer of OLED material in each well **720**, **730**, **740** may contact the confinement structure **704**. OLED layers can include, for example, one or more of hole injecting materials, hole transporting materials, electron transporting materials, electron injecting materials, hole blocking materials, and organic light emissive materials providing for emission of differing light-emissive wavelength ranges. For example, confinement well **720** can include an organic light-emissive layer associated with light emission within the red wavelength range and is indicated by R, confinement well **730** can include an organic light-emissive layer associated with light emission within the green wavelength range indicated by G, and confinement well **740** can include an organic light-emissive layer associated with light emission within the blue wavelength range indicated by B. The wells **720**, **730**, **740** can have a variety of arrangements and configurations, including with respect to each other (e.g., layouts). For example, as illustrated in FIG. **12**, confinement wells **720** and confinement wells **730** that respectively contain red organic light-emissive layer R and green organic light-emissive layer G are disposed in rows R_1 , R_3 in an alternating arrangement. Alternating with the rows R_1 and R_3 are rows R_2 , R_4 of the confinement wells **740** that contain blue organic-light emissive layer B. Confinement wells **720**, **730** also can be alternatively arranged within the rows R_1 , R_3 .

A plurality of electrodes **706**, **707**, **708**, **709**; **736**, **737**, **738**, **739**; and **742**, **744** can be disposed in each confinement well **720**, **730**, **740**, respectively, wherein each electrode can be associated with a sub-pixel associated with a particular light emission color such as red, green, or blue light emission. A pixel **750**, **751**, **752**, **753**, identified in FIG. **12** by dashed lines, can be defined to include one sub-pixel having red light emission, one sub-pixel having green light emission, and one sub-pixel having blue light emission. For example, each confinement well **720**, **730**, **740** can respectively include a plurality of electrodes **706**, **707**, **708**, **709**; **736**, **737**, **738**, **739**; and **742**, **744** configured such that their associated electrode active regions correspond to the electrode outlines shown in FIG. **12**, are spaced apart from each other. Confinement wells **720**, **730**, **740** can have a differing number and/or arrangement of electrodes within the confinement well. Alternatively, additional arrangements are possible, such as arrangements with other sets of colors than red, green, and blue, including combinations of colors involving more than three sub-pixel colors. Other arrangements are also possible in which more than one sub-pixel of a single color is associated with a particular pixel, for example, each pixel can have associated with it one red, one green, and two blue sub-pixels, or other combinations of numbers of sub-pixels of a particular color and other combinations of colors. Moreover, if multiple layers of differing light-emissive material are positioned over each other, it is contemplated that differing color sub-pixels may overlap each other. As illustrated in FIG. **12**, sub-pixel electrodes can be spaced apart from structures that define the confinement wells. In an alternative embodiment, the sub-pixel electrodes can be deposited such that they are directly adjacent to the

confinement well structures such that no gap occurs between the electrode and the confinement structure. In addition, the confinement well structures can be disposed over a portion of the sub-pixel electrodes.

In addition, adjacent confinement wells can have differing sub-pixel arrangements. For example, as illustrated in FIG. 12, confinement wells 720 and 730 include a 2x2 active electrode region arrangement, and confinement well 740 includes a 1x2 active electrode region arrangement, with the active electrode regions in the 2x2 arrangements being squares of the same size and the active electrode regions in the 1x2 arrangement being rectangles of the same size. As noted above, electrodes within differing confinement wells can have differing surface areas of active regions.

In one exemplary arrangement, the active regions associated with the electrodes used to address sub-pixels of light-emission within the blue wavelength range B can have a greater surface area than the active regions associated with the electrodes used to address light-emission within the red and/or green wavelength range R, G. It may be desirable for the active regions of the electrodes associated with the sub-pixels having light-emission in the blue wavelength range B to have a greater surface area than the active regions associated with a sub-pixel electrode associated with a red or green light emission because sub-pixels associated with blue light emission often have substantially shorter lifetimes than sub-pixels associated with having red or green light emission when operating at the same area brightness levels. Increasing the relative active area of the sub-pixels associated with blue light emission enables operation at relatively lower area brightness levels while still maintaining the same overall display brightness, thereby increasing the lifetime of the sub-pixels associated with blue light emission and the overall lifetime of the display. It is noted that sub-pixels associated with red and green light emission may be correspondingly reduced in relation to the sub-pixel associated with blue light emission. This can lead to the sub-pixels associated with red and green light-emission to be driven at a higher brightness level in relation to a sub-pixel associated with blue light-emission which can reduce the red and green OLED device lifetime. However, the lifetimes of the sub-pixels associated with red and green light emission can be significantly longer than the lifetime associated with the sub-pixel associated with the blue sub-pixel that the sub-pixel associated with the blue light emission remains the limiting sub-pixel with respect to the overall display lifetime. While the active regions of the electrodes within confinement well 740 are illustrated as being arranged with their elongate direction extending horizontally in FIG. 12, the electrodes could alternatively be arranged such that their elongate direction extends vertically in FIG. 12.

Intervals between adjacent confinement wells can be equal throughout the pixel layout or can vary. For example, with reference to FIG. 12, an interval b' between confinement wells 720, 730 can be greater than or equal to the interval f' between confinement wells 720 or 730 and 740. In other words, the horizontal interval between adjacent confinement wells in a row may differ from the vertical interval between adjacent confinement wells in adjacent rows, in the orientation of FIG. 12. Moreover, the horizontal interval b' in rows R₁, R₃ may be equal to or differ from the horizontal interval a' in R₂, R₄.

Spacing (gaps) between the active regions of the electrodes within each of the differing confinement wells 720, 730, 740 also can be the same or differ and may vary depending on the direction of spacing (e.g., horizontal or vertical). In one exemplary embodiment, the gaps d and e

between the active regions of the electrodes within the confinement wells 720, 730 can be the same and can differ from the gap between active regions of the electrodes within the confinement well 740. Further, in various exemplary embodiments, the gaps between adjacent active electrode regions within a confinement well are less than the gaps between adjacent active electrode regions in neighboring confinement wells, either in the same or differing rows. For example, c, d, and e may each be less than either a, b, or f in FIG. 12.

In FIG. 12 there is shown a gap between the interior edges of each confinement well, e.g. 720, and the exterior edges of each of the active electrode regions associated within that confinement well, e.g. 706, 707, 708, 709. However, as illustrated in FIG. 2, according to various exemplary embodiments, such a gap may not be present and the exterior edge of each of active electrode regions may be the same as the interior edge of the confinement well. This configuration can be achieved, for example, using a structure like the one illustrated in FIG. 3A, where the configuration show in FIG. 12, in which such a gap is present, can be achieved, for example, using a structure like the one illustrated in FIG. 5A. However, other structures may also be able to achieve the same configurations illustrated in FIGS. 2 and 12.

Pixels 750, 751, 752, 753 can be defined based on the confinement well arrangement and corresponding sub-pixel layout. The overall spacing, or pitch, of pixels 750, 751, 752, 753 can be based on the resolution of the display. For example, the higher the display resolution, the smaller the pitch. In addition, adjacent pixels can have differing sub-pixel arrangements. For example, as illustrated in FIG. 12, pixel 750 includes a red sub-pixel R in the top left portion, a green sub-pixel G in the top right portion, and a blue sub-pixel B in spanning the majority of the bottom portion of the pixel. The sub-pixel layout of pixel 751 is similar to that of pixel 750 except the relative positions of the green sub-pixel G and the red sub-pixel R being switched, with the green sub-pixel G in the top left portion, a red sub-pixel R in the top right portion. Pixels 752 and 753, which are adjacent and underneath pixels 751, 750 respectively, are mirror images of pixels 751 and 750, respectively. Thus, pixel 752 includes a blue sub-pixel B in the top portion, a green sub-pixel G in the bottom left portion, and a red sub-pixel R in the bottom right portion. And pixel 753 includes a blue sub-pixel in the top portion, a green sub-pixel in the bottom left portion, and a red sub-pixel in the bottom right portion.

In an exemplary embodiment for a high resolution display according to FIG. 12 and having 326 pixels per inch (ppi), a pixel including a red sub-pixel, a green sub-pixel, and a blue sub-pixel can have overall dimensions of approximately 78 μm x 78 μm , corresponding to the overall pitch of the display needed to achieve 326 ppi. Assuming for this embodiment that a'=b'=f'=12 μm , reflecting, as previously discussed, the state of the art minimum spacing between confinement regions, further assuming that a=b=f=12 μm +6 μm =18 μm , reflecting a case in which a definition layer is utilized that extends 3 μm inside the confinement well edge, and finally assuming c=d=e=3 μm as a typical gap between electrode active regions within a confinement well, the areas associated with each of the red and green sub-pixels can be 28.5 μm x 28.5 μm and the area associated with the blue sub-pixels can be 60 μm x 27 μm . The surface area of the blue sub-pixels can be greater than each of the red and green sub-pixels to increase overall display lifetime as described above. Such a layout can have confinement wells associated with groupings of 2x2 red and green sub-pixels having

dimensions of $66\text{ }\mu\text{m}\times 66\text{ }\mu\text{m}$, and confinement wells associated with groupings of 1×2 blue sub-pixels having dimensions of $66\text{ }\mu\text{m}\times 66\text{ }\mu\text{m}$. Such dimensions provide for straightforward loading of active OLED material with conventional inkjet print heads and printing systems while also providing for a high resolution display with high fill factor of greater than 50%, such as 53%. Such dimensions also provide for such features in a structure having a definition layer that can provide for enhanced film uniformity within the active electrode region by blocking current flow through the film region immediately adjacent to the confinement well wall.

In a corresponding exemplary embodiment for a high resolution display having 440 pixels per inch (ppi) a pixel including a red sub-pixel, a green sub-pixel, and a blue sub-pixel can have an overall dimension of approximately $58\text{ }\mu\text{m}\times 58\text{ }\mu\text{m}$ where assuming the same value for the dimensions a, b, c, d, e, f, a', b', and f' as in the immediately previous example, the area associated with each of the red and green sub-pixels can be $18.5\text{ }\mu\text{m}\times 18.5\text{ }\mu\text{m}$ and the area associated with the blue sub-pixels can be $40\text{ }\mu\text{m}\times 17\text{ }\mu\text{m}$. The surface area of the blue sub-pixels can be greater than each of the red and green sub-pixels to increase overall display lifetime as described above. Such a layout can have confinement wells associated with groupings of 2×2 red and green sub-pixels having dimensions of $46\text{ }\mu\text{m}\times 46\text{ }\mu\text{m}$, and confinement wells associated with groupings of 1×2 blue sub-pixels having dimensions of $46\text{ }\mu\text{m}\times 46\text{ }\mu\text{m}$. Such dimensions provide for relatively straightforward loading of active OLED material with conventional inkjet print heads and printing systems while also providing for a high resolution display with high fill factor of 40%.

In each of the above exemplary embodiments, various values for the dimensions a, b, c, d, e, f, a', b', f' can be implemented. However, one of ordinary skill in the art would recognize that these dimensions vary. For example, the spacing between confinement walls (a', b', f') can be varied, as previously discussed from as little as $1\text{ }\mu\text{m}$ to as large as hundreds of microns for large ppi. The gap between active electrode regions within a confinement well (c, d, e) can vary, as discussed above, from as little as $1\text{ }\mu\text{m}$ to as large as tens of microns. The gap between the active electrode regions and the edge of the confinement walls (effectively half the difference between a' and a, b' and b' and f' and f, respectively) can also vary, as discussed above, from as little as $1\text{ }\mu\text{m}$ to as large as $10\text{ }\mu\text{m}$. Furthermore, as these dimensions are varied, they apply constraints, along with the ppi (that determines the overall pitch of the display), that limit the range of values allowed for the confinement well dimensions and the active electrode regions contained therein. In the above exemplary embodiments, for simplicity, square confinement wells of the same dimension are used for all three colors. However, the confinement wells need not be square, and need not all be the same size. In addition, the dimensions provided for in FIG. 12 indicate various common dimensions, for example, the gap between active electrode regions within the red confinement wells and the green confinement wells, but in some exemplary embodiments, those gaps are not common dimensions but differ from each other.

FIG. 13 depicts a partial plan view of another exemplary pixel/sub-pixel layout of an OLED display 800. Features common to previously discussed exemplary embodiments are not described. For simplicity, differences will be discussed.

Display 800 can have a greater separation between the active regions associated with sub-pixel electrodes within a

confinement well than for example, sub-pixel electrodes of display 700 as illustrated in FIG. 12. Spacing between adjacent active regions associated with electrodes 806, 807, 808, 809; 836, 837, 838, 839; and 842, 844 within respective confinement wells 820, 830, 840 can be greater than an interval between adjacent active electrode regions in adjacent confinement wells. For example, the active regions associated with electrode 836 can be spaced apart from one another a predetermined distance g, and similarly for the active regions associated with electrode 838. The interval k between adjacent active electrode regions in neighboring confinement wells 820, 830 can be less than the interval g between the active regions associated with electrodes 836, 838, and the interval m between the active regions associated with electrode 842 (and similarly for electrode 844) can be greater than the interval n between the adjacent active electrode regions in neighboring confinement well 840 and confinement wells 820, 830. Such spacing can provide for greater spacing between sub-pixel electrodes disposed within a confinement well and associated with the same light emission color while providing for a closer arrangement of sub-pixel electrodes associated with a single defined pixel. This spacing can reduce undesirable visual artifacts such that the display appears to be an array of closely arranged RGB triplets and not an array of closely arranged RRRR quadruplets, GGGG quadruplets, and BB pairs.

Another exemplary pixel/sub-pixel layout for a display in accordance with the present disclosure is depicted in FIG. 14. A confinement structure 904 can be provided on a substrate to define a plurality of confinement wells 920, 930, 940 in an arrayed configuration. Each confinement well 920, 930, 940 can include a substantially continuous layer of OLED material (indicated by the shaded regions) such that edges of the organic layer extends throughout the confinement well 920, 930, 940 to the confinement structure 904 surrounding the confinement well, for example, edges of the layer of OLED material in each well 920, 930, 940 may contact the confinement structure 904. Active OLED layers can include, for example, without limitation, one or more of hole injecting materials, hole transporting materials, electron transporting materials, electron injecting materials, hole blocking materials, and organic light emissive materials providing for emission of differing light-emissive wavelength ranges. For example, confinement well 920 can include an organic light-emissive layer associated with light-emission within the red wavelength ranges range R, confinement well 930 can include an organic light-emissive layer associated with light-emission within the green wavelength range G, and confinement well 940 can include an organic light-emissive layer associated with light-emission within the blue wavelength range B. The organic light-emissive layers can be disposed within the wells in any arrangement and/or configuration. For example, the organic light-emissive layers disposed in confinement wells 920, 930, 940 are arranged having an alternating arrangement within each row. Adjacent rows can have the same arrangement or differing arrangement. In addition, while the adjacent rows of confinement wells 920, 930, 940 are illustrated as having a uniform alignment, adjacent rows of confinement wells 920, 930, 940 can alternatively have a non-uniform alignment such as an offset arrangement. Moreover, confinement wells 920 and 930 can be reversed in the alternative pattern.

The configuration of each well 920, 930, 940 can have a rectangular shape such that each well is elongated in a vertical direction. Wells 920, 930, 940 can have approximately the same dimensions in the elongated vertical direc-

tion. In addition, wells **920**, **930**, **940** can have approximately the same width. However, the entire well **940** associated with a blue organic light-emissive layer can correlate to a single sub-pixel and thus pixel, while wells **920**, **930** associated with the red and green organic light-emissive layer can correlate to a plurality of sub-pixels and thus a plurality of pixels. For example, confinement wells **920**, **930** can include a plurality of electrodes such that each electrode is associated with a differing sub-pixel of a differing pixel. As illustrated in FIG. **14**, well **920** includes two electrodes **926**, **928** and is associated with two differing pixels **950**, **951**.

A differing number of electrodes **926**, **928**, **936**, **938**, **946** can be disposed within differing confinement wells. For example, some confinement wells **920**, **930** can include a plurality of electrodes **926**, **928**; and **936**, **938** so as to selectively address electrodes disposed in the same confinement well but produce light emission for differing sub-pixels in differing pixels, while other confinement wells **940** only include one electrode **946** to address an electrode disposed in one confinement well associated with one pixel. Alternatively, the number of electrodes disposed in confinement well **940** can be half of the number of electrodes disposed in other confinement wells **920**, **930**. In addition, electrodes within differing confinement wells can have differing surface areas. For example, electrodes associated with light-emission within the blue wavelength range can have a greater surface area than electrodes associated with light-emission within the red and/or green wavelength range to improve the life of display **900** and reduce power consumption.

Pixels **950**, **951** can be defined based on the confinement well arrangement and corresponding sub-pixel layout. The overall spacing, or pitch, of pixels **950**, **951** can be based on the resolution of the display. For example, the higher the display resolution, the smaller the pitch. In addition, adjacent pixels can have differing pixel arrangements. For example, as illustrated in FIG. **14**, pixel **950** can include a green sub-pixel G on the left, a blue sub-pixel B in the middle, and a red sub-pixel R on the right. Pixel **951** can include a red sub-pixel R on the left, a blue sub-pixel B in the middle and a green sub-pixel G on the right.

FIG. **15** depicts a partial plan view of an exemplary embodiment of a pixel and sub-pixel layout for an OLED display **1000**. Features common to embodiments discussed above are not described (though similar labels can be found with a **1000** series in FIG. **15**). For simplicity, differences will be discussed. Confinement structure **1004** can be configured to define a plurality of wells **1020**, **1030**, **1040**. Wells **1020**, **1030**, **1040** can be arranged such that wells **1020**, **1030**, **1040** are aligned in uniform rows where wells associated with red light emission and green light emission (for example **1020**, **1030**) alternate within a single row and wells associated with blue light emission (for example **1040**) are within a single row. In addition, wells **1020**, **1030**, **1040** can be configured such that the wells **1020**, **1030**, **1040** are aligned within a uniform column such that columns of wells **1020**, **1040** alternate with columns of wells **1030**, **1040**. Confinement wells **1020** and **1030** can be alternatively arranged such that confinement wells **1030** begin the alternating pattern.

Each confinement well **1020**, **1030**, **1040** can be approximately the same size. However, the number of electrodes associated with each well **1020**, **1030**, **1040** can differ. For example, as illustrated in FIG. **15**, the well associated with red light emission **1020** can include electrodes **1026**, **1027**, **1028**, **1029**, the well associated with green light emission

1030 can include electrodes **1036**, **1037**, **1038**, **1039**, and the well associated with blue light emission **1040** can include electrodes **1046**, **1048**. While electrodes within confinement well **1040** are illustrated as being arranged horizontally spaced, the electrodes could alternatively be arranged so as to be vertically spaced.

While electrodes **1026**, **1027**, **1028**, **1029**, **1036**, **1037**, **1038**, **1039** are illustrated in FIG. **15** as having a square shape and electrodes **1046**, **1048** are illustrated as having a rectangular shape, electrodes having any shape are contemplated as within the scope of the present disclosure such as, for example, circular, chevrons, hexagonal, asymmetrical, irregular curvature, etc. A plurality of differing shapes of electrodes could be implemented within a single confinement well. In addition, differing confinement wells can have differing shaped electrodes. The size and shape of the electrode can influence the distance between the electrodes and thus the overall layout of the display. For example, when the shapes are complementary, electrodes can be spaced closer together while still maintaining electrical isolation between adjacent electrodes. In addition, the shape and spacing of the electrodes can influence the degree of visual artifacts created. Electrode shapes can be selected to reduce undesired visual artifacts and enhance image blending to produce a continuous image.

Pixels **1050**, **1051**, shown in dashed lines, can be defined based on the confinement well arrangement and corresponding sub-pixel layout. The overall spacing, or pitch, of pixels **1050**, **1051** can be based on the resolution of the display. For example, the higher the display resolution, the smaller the pitch. In addition, pixels can be defined as having an asymmetrical shape. For example, as illustrated in FIG. **15**, pixel **1050**, **1051** can have an "L" shape.

FIG. **16** depicts a partial plan view of an exemplary embodiment of a pixel and sub-pixel layout for an OLED display **1100**. Features common to exemplary embodiments discussed above will not be described (though similar labels with an **1100** series can be found in FIG. **16**). Confinement structure **1104** can be configured to define a plurality of confinement wells **1120**, **1130**, **1140** in a plurality of columns C_1 , C_2 , C_3 , C_4 . Columns C_1 , C_2 , C_3 , C_4 can be arranged to produce a staggered arrangement. For example, the confinement wells in columns C_1 , and C_3 can be offset from columns C_2 and C_4 , producing a staggered row arrangement while maintaining a uniform column arrangement. Pixels **1150**, **1151** can be defined based on the pitch of the confinement well arrangement. The pitch of the confinement well arrangement can be based on the resolution of the display. For example, the smaller the pitch the higher the display resolution. In addition, pixels can be defined as having an asymmetrical shape. For example, as illustrated in FIG. **16** by the dashed lines, pixel **1150**, **1151** can have a non-uniform shape.

FIG. **17** depicts a partial plan view of an exemplary embodiment of a pixel and sub-pixel layout for an OLED display **1200**. Features common to embodiments discussed above are not described (though similar labels with a **1200** series can be found in FIG. **17**). As illustrated in FIG. **17**, confinement structure **1204** can be configured to define a plurality of confinement wells **1220**, **1230**, **1240**. Each confinement well **1220**, **1230**, **1240** can have a differing area. For example, the well **1220** associated with red light emission R can have an area greater than the well **1230** associated with the green light emission G. In addition, confinement wells **1220**, **1230**, **1240** can be associated with a differing number of pixels. For example, confinement well **1220** can be associated with pixels **1251**, **1252**, **1254**, **1256**

and confinement wells **1230**, **1240** can be associated with pixels **1251**, **1252**. Wells **1220**, **1230**, **1240** can be configured in uniform rows R_1 , R_2 , R_3 , R_4 , R_5 . Rows R_2 , R_3 , and R_5 can be associated with blue light emission wells **1240** and rows R_1 and R_4 can be associated with alternating red light emission wells **1220** and green light emission wells **1230**. The confinement structure **1204** can have a variety of dimensions D_1 , D_2 , D_3 , D_4 . For example, D_1 can be greater than D_2 , D_3 , or D_4 . D_2 can be less than D_1 , D_3 , or D_4 , and D_3 can be approximately equal to D_4 .

FIG. **18** depicts a partial plan view of an exemplary embodiment of a pixel and sub-pixel layout for an OLED display **1300**. Features common to embodiments discussed above, for example FIG. **17**, are not described (though similar labels with a **1300** series can be found in FIG. **18**). Confinement structure **1304** can be configured to define a plurality of confinement wells **1320**, **1330**, **1340**. Wells **1320**, **1330**, **1340** can be arranged such that wells associated with red light emission **1320** and green light emission **1330** can be alternated within a row with wells associated with blue light emission **1340**.

While various pixel and sub-pixel layouts are described above, the exemplary embodiments in no way limit the shape, arrangement, and/or configuration of confinement wells that span a plurality of pixels as described. Instead, confinement wells associated with the present disclosure in combination with inkjet printing manufacturing methods allow for flexible pixel layout arrangements to be selected.

Various pixel layouts are contemplated that can enable a high resolution OLED display using inkjet printing. For example, as illustrated in FIG. **19**, confinement structures **1404** can create a hexagonal pattern such that a pixel **1450** can comprise a confinement well **1420** associated with red emission R , a confinement well **1430** associated with green emission G , and a confinement well **1440** associated with blue emission B . Due to the pitch, the shape of the confinement wells, and the ability to pack the confinement wells closer together, an OLED display having high resolution can be created using inkjet printing.

Embodiments disclosed herein can be used to achieve high resolution in any OLED display. Accordingly, it can be applied to various electronic display apparatuses. Some non-limiting examples of such electronic display apparatuses include television displays, video cameras, digital cameras, head mounted displays, car navigation systems, audio systems including a display, laptop personal computers, digital game equipment, portable information terminals (such as a tablet, a mobile computer, a mobile telephone, mobile game equipment or an electronic book), image playback devices provided with recording medium. Exemplary embodiments of two types of electronic display apparatuses are illustrated in FIGS. **20** and **21**.

FIG. **20** illustrates a television monitor and/or a monitor of a desktop personal computer that incorporates any of the OLED displays according to the present disclosure. Monitor **1500** can include a frame **1502**, a support **1504**, and a display portion **1506**. The OLED display embodiments disclosed herein can be used as the display portion **1506**. Monitor **1500** can be any size display, for example up to 55" and beyond.

FIG. **21** illustrates an exemplary embodiment of a mobile device **1600** (such as a cellular phone, tablet, personal data assistant, etc.) that incorporates any of the OLED displays according to the present disclosure. Mobile device **1600** can include a main body **1062**, a display portion **1604**, and operation switches **1606**. The OLED display embodiments disclosed herein can be used as the display portion **1604**.

Using various aspects in accordance with exemplary embodiments of the present disclosure, some exemplary dimensions and parameters could be useful in attaining high resolution OLED displays with an increased fill factor.

Tables 1-3 include conventional dimensions and parameters as well as prophetic, non-limiting examples in accordance with exemplary embodiments of the present disclosure associated with an OLED display having a resolution of 326 ppi where Table 1 describes a sub-pixel associated with red light-emission, Table 2 describes a sub-pixel associated with green light-emission, and Table 3 describes a sub-pixel associated with blue light-emission. Tables 4-6 include conventional dimensions and parameters as well as prophetic, non-limiting examples in accordance with exemplary embodiments of the present disclosure associated with a display having a resolution of 440 ppi where Table 4 describes a sub-pixel associated with red light-emission, Table 5 describes a sub-pixel associated with green light-emission, and Table 6 describes a sub-pixel associated with blue light emission.

TABLE 1

For a sub-pixel associated with red emission in display having resolution of 326 ppi	Length of Sub-pixel (μm)	Width of Sub-pixel (μm)	Area of Confinement Well (μm^2)
Conventional sub-pixel	65.9	10.5	690.7
Sub-pixel associated with Confinement Structure as illustrated in FIGS. 3A, 3B	31.5	31.5	989.5
Conventional sub-pixel with Pixel Definition Layer	59.9	9.0	537.9
Sub-pixel associated with Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	28.5	28.5	809.8

TABLE 2

For a sub-pixel associated with green emission in display having resolution of 326 ppi	Length of Sub-pixel (μm)	Width of Sub-pixel (μm)	Area of Confinement Well (μm^2)
Conventional sub-pixel	65.9	10.5	690.7
Sub-pixel associated with Confinement Structure as illustrated in FIGS. 3A, 3B	31.5	31.5	989.5
Conventional sub-pixel with Pixel Definition Layer	59.9	9.0	537.9
Sub-pixel associated with Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	28.5	28.5	809.8

TABLE 3

For a sub-pixel associated with blue emission in display having resolution of 326 ppi	Length of Sub-pixel (μm)	Width of Sub-pixel (μm)	Area of Confinement Well (μm^2)
Conventional sub-pixel	65.9	21.0	1381.4
Sub-pixel associated with Confinement Structure as illustrated in FIGS. 3A, 3B	30.0	65.9	1979.1
Conventional sub-pixel with Pixel Definition Layer	59.9	18.0	1075.9
Sub-pixel associated with Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	27.0	59.9	1619.6

35

TABLE 4

For a sub-pixel associated with red emission of a display having resolution of 440 ppi	Length of Sub-pixel (μm)	Width of Sub-pixel (μm)	Area of Confinement Well (μm ²)
Conventional sub-pixel	45.7	5.4	248.4
Sub-pixel associated with Confinement Structure as illustrated in FIGS. 3A, 3B	21.4	21.4	456.4
Conventional sub-pixel with Pixel Definition Layer	39.7	3.9	159.2
Sub-pixel associated with Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	18.4	18.4	337.2

TABLE 5

For a sub-pixel associated with green emission of a display having resolution of 440 ppi	Length of Sub-pixel (μm)	Width of Sub-pixel (μm)	Area of Confinement Well (μm ²)
Conventional sub-pixel	45.7	5.4	248.4
Sub-pixel associated with Confinement Structure as illustrated in FIGS. 3A, 3B	21.4	21.4	456.4
Conventional sub-pixel with Pixel Definition Layer	39.7	3.9	156.2
Sub-pixel associated with Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	18.4	18.4	337.2

TABLE 6

For a sub-pixel associated with blue emission of a display having resolution of 440 ppi	Length of Sub-pixel (μm)	Width of Sub-pixel (μm)	Area of Confinement Well (μm ²)
Conventional sub-pixel	45.7	10.9	496.8
Sub-pixel associated with Confinement Structure as illustrated in FIGS. 3A, 3B	20.0	45.7	912.8
Conventional sub-pixel with Pixel Definition Layer	39.7	7.9	312.4
Sub-pixel associated with Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	17.0	39.7	674.4

Table 7 includes conventional dimensions and parameters as well as prophetic, non-limiting examples in accordance with exemplary embodiments of the present disclosure associated with a pixel within a display having a resolution of 326 ppi where the pixel includes a red sub-pixel, a green sub-pixel, and a green sub-pixel.

TABLE 7

For a display having resolution of 326 ppi	Active Area of Pixel (μm ²)	Total Area of Pixel (μm)	Fill Factor*
Conventional Confinement Structure	2762.7	6070.6	46%
Confinement Structure as illustrated in FIGS. 3A, 3B	3958.2	6070.6	65%
Conventional Confinement Structure with Pixel Definition Layer	2151.8	6070.6	35%
Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	3239.2	6070.6	53%

*(Active Area/Total Area) rounded up to the nearest percentage point

36

As illustrated in Table 7 above, it is contemplated that various exemplary embodiments in accordance with the present disclosure can achieve a fill factor improvement over conventional confinement structures. For example, a fill factor for a display that contemplates a confinement structure illustrated in FIGS. 3A and 3B can increase the fill factor by about 43% over a conventional structure, thereby achieving a total fill factor of 65%. In another embodiment, a fill factor for a display that contemplates a confinement structure as illustrated in FIGS. 5A and 5B can improve the fill factor by about 51% over a conventional structure thereby achieving a total fill factor of 53%.

Table 8 includes conventional dimensions and parameters as well as prophetic, non-limiting examples in accordance with exemplary embodiments of the present disclosure associated with a pixel within a display having a resolution of 440 ppi where the pixel includes a red sub-pixel, a green sub-pixel, and a green sub-pixel.

TABLE 8

For a display having resolution of 440 ppi	Active Area of Pixel (μm ²)	Total Area of Pixel (μm)	Fill Factor*
Conventional Confinement Structure	993.5	3332.4	30%
Confinement Structure as illustrated in FIGS. 3A, 3B	1825.6	3332.4	55%
Conventional Confinement Structure with Pixel Definition Layer	624.8	3332.4	19%
Confinement Structure with definition layer as illustrated in FIGS. 5A, 5B	1348.9	3332.4	40%

*(Active Area/Total Area) rounded up to the nearest percentage point

As illustrated in Table 8 above, it is contemplated that various exemplary embodiments in accordance with the present disclosure can achieve a fill factor improvement over conventional confinement structures. For example, a fill factor for a display that contemplates a confinement structure illustrated in FIGS. 3A and 3B can improve the fill factor by about 84% over conventional structure thereby achieving a total fill factor of 55%. In another embodiment, a fill factor for a display that contemplates a confinement structure as illustrated in FIGS. 5A and 5B can improve the fill factor by about 116% over a conventional structure thereby achieving a total fill factor of 40%.

Various exemplary embodiments described above and pursuant to the present disclosure can permit inkjet printing of OLED displays having relatively high pixel density and increased fill factors by increasing the size of the confinement wells into which the OLED material droplets are loaded and thereby enable the use of attainable droplet sizes and attainable inkjet system droplet placement accuracies, according to the present disclosure. Due to the larger confinement well areas, high resolution OLED displays can be manufactured using sufficiently large inkjet droplet volumes and attainable droplet placement accuracies, without needing to utilize too small of droplet volumes or excessively high droplet placement accuracies that could pose prohibitive challenges in inkjet equipment design and printing techniques. Without implementing a confinement well that spans a plurality of sub-pixels according to the present disclosure, droplet size and system droplet placement errors could significantly increase issues in any high resolution display manufactured using existing inkjet heads, as the droplets would have too large volumes and would overflow each sub-pixel well and the conventional droplet placement

accuracies would lead to misplacement of droplets either entirely or partially outside of the target confinement well, both of which would lead to undesired errors in film deposition and corresponding visual defects in the final display appearance. The ability to achieve high pixel density with existing droplet volumes and droplet placement accuracies enables the techniques described herein to be utilized in the manufacture of displays of relatively high resolutions for many applications, from small size displays, such as, for example, are found in smart phones and/or tablets, and large size displays, such as, for example, ultra high resolution televisions. Moreover, achieving OLED material layer(s) of substantially uniform thickness that sufficiently conform to underlying topography, in accordance with exemplary embodiments, can promote overall OLED display performance and quality, and in particular can permit desirable performance and quality to be achieved in high resolution OLED displays. One or more of the above described embodiments can achieve a reduced fill factor. In conventional pixel arrangements, a fill factor for a display having a resolution in the range of 300-440 ppi has a fill factor of less than 40%, and frequently less than 30%. In contrast, exemplary embodiments of the present disclosure may achieve a fill factor of greater than 40%, and in some instances as high as 60%, for displays having a resolution in the range of 300-440 ppi. The exemplary embodiments can be used for any pixel size and arrangement, including pixel arrangements within high resolution displays.

The exemplary embodiments can be used with any size display and more particularly with small displays having a high resolution. For example, exemplary embodiments of the present disclosure can be used with displays having a diagonal size in the range of 3-70 inches and having a resolution greater than 100 ppi, for example, greater than 300 ppi.

Although various exemplary embodiments described contemplate utilizing inkjet printing techniques, the various pixel and sub-pixel layouts described herein and the way of producing those layouts for an OLED display can also be manufactured using other manufacturing techniques such as thermal evaporation, organic vapor phase deposition, organic vapor jet printing. In exemplary embodiments, alternative organic layer patterning can also be performed. For example, patterning methods can include shadow masking (in conjunction with thermal evaporation) and organic vapor jet printing. In particular, though the pixel layouts described herein, in which multiple sub-pixels of the same color are grouped together and in which the deposited OLED film layers span substantial topographies within the grouped sub-pixel regions, have been conceived for inkjet printing applications, such layouts can also have beneficial alternative application to vacuum thermal evaporation techniques for OLED film layer deposition, in which the patterning step is achieved using shadow masking. Such layouts as described herein provide for larger shadow mask holes and increased distances between such holes, thereby potentially improving the overall mechanical stability and general practicality of such shadow masks. While vacuum thermal evaporation techniques with shadow masks may be not as low cost as inkjet techniques, the use of the pixel layouts in accordance with the present disclosure and the use of OLED film layer coatings spanning substantial topographies within the grouped sub-pixels associated with the same color, also represent a potentially important application of the present disclosure described herein.

Although only a few exemplary embodiments have been described in detail above, those skilled in the art will readily

appreciate that many modifications are possible in the example embodiments without materially departing from this disclosure. Accordingly, all such modifications are intended to be included within the scope of this disclosure as defined in the following claims.

It is to be understood that the various embodiments shown and described herein are to be taken as exemplary. Elements and materials, and arrangement of those elements and materials, may be substituted for those illustrated and described herein, and portions may be reversed, all as would be apparent to one skilled in the art after having the benefit of the description herein. Changes may be made in the elements described herein without departing from the spirit and scope of the present disclosure and following claims, including their equivalents.

Those having ordinary skill in the art will recognize that various modifications may be made to the configuration and methodology of the exemplary embodiments disclosed herein without departing from the scope of the present teachings.

Those having ordinary skill in the art also will appreciate that various features disclosed with respect to one exemplary embodiment herein may be used in combination with other exemplary embodiments with appropriate modifications, even if such combinations are not explicitly disclosed herein.

It will be apparent to those skilled in the art that various modifications and variations can be made to the devices, methods, and systems of the present disclosure without departing from the scope of the present disclosure and appended claims. Other embodiments of the disclosure will be apparent to those skilled in the art from consideration of the specification and practice of the disclosure disclosed herein. It is intended that the specification and examples be considered as exemplary only.

What is claimed is:

1. A method of manufacturing an organic light-emitting diode (OLED) display comprising:

providing on a substrate a first electrode associated with a first sub-pixel and a second electrode associated with a second sub-pixel, wherein a gap is formed between the first electrode and the second electrode and wherein the first electrode and the second electrode are positioned in a well having boundaries defined by a confinement structure on the substrate; and

depositing in the well with the electrodes positioned therein, active OLED material to form a substantially continuous layer of active OLED material that spans and is contained within the boundaries of the well such that a surface of the layer of active OLED material that faces away from the substrate has a non-planar topography, wherein the depositing is via inkjet printing.

2. The method of claim 1, wherein the layer of active OLED material has a substantially uniform thickness.

3. The method of claim 2, wherein the layer of active OLED material includes local non-uniformities in thickness.

4. The method of claim 3, wherein the local non-uniformities in thickness are within 5 μm -10 μm of edges of surface features in the well.

5. The method of claim 1, the layer of active OLED material has a thickness less than a thickness of the first electrode and the second electrode.

6. The method of claim 1, wherein the active OLED material comprises light-emissive material.

7. The method of claim 6, wherein the light-emissive material has a light-emissive wavelength range that is the same for the first sub-pixel and the second sub-pixel.

39

8. The method of claim 1, wherein the layer of active OLED material comprises two layers of active OLED materials including a light-emissive material and a hole conducting material.

9. The method of claim 8, wherein the hole conducting material is at least one of a hole injecting material and a hole transporting material.

10. The method of claim 1, wherein the first and second sub-pixels correspond to differing pixels.

11. The method of claim 1, further comprising providing a structure on the substrate within the gap between the first electrode and the second electrode.

12. The method of claim 11, wherein the structure comprises an electrically resistive material.

13. The method of claim 1, further comprising depositing a definition layer on the substrate and a portion of the first electrode and the second electrode and then depositing the confinement structure over the definition layer.

14. The method of claim 13, wherein the definition layer comprises an electrically resistive material.

15. The method of claim 13, further comprising depositing a structure on the substrate in the gap between the first electrode and the second electrode.

16. The method of claim 15, further comprising depositing a second definition layer on the structure.

17. The method of claim 1, wherein the organic light-emissive display is a top emission display.

18. The method of claim 1, wherein the display has a fill factor greater than 40%.

19. The method of claim 1, wherein the display has a fill factor greater than 60%.

20. The method of claim 1, wherein the display has a resolution of at least 100 ppi.

21. The method of claim 1, wherein the display has a resolution of at least 300 ppi.

22. An organic light-emitting diode (OLED) display, comprising:

a first electrode disposed on a substrate, wherein the first electrode is associated with a first sub-pixel;

a second electrode disposed on the substrate and spaced from the first electrode to provide a gap between the first and second electrodes, wherein the second electrode is associated with a second sub-pixel;

a confinement structure positioned on the substrate to define boundaries of a well containing the first electrode and the second electrode; and

a substantially continuous active OLED material layer that spans and is contained within the boundaries of the well and is disposed over the first electrode and second electrode, wherein a surface of the active OLED material layer that faces away from the substrate has a non-planar topography.

40

23. The display of claim 22, wherein the active OLED material layer has a substantially uniform thickness.

24. The display of claim 23, wherein the active OLED material layer includes local non-uniformities.

25. The display of claim 24, wherein the local non-uniformities in thickness are within 5 μm to 10 μm of edges of surface features in the well.

26. The display of claim 22, wherein the active OLED material layer has a thickness less than a thickness of the first electrode and the second electrode.

27. The display of claim 22, wherein the active OLED material layer comprises a light-emissive material.

28. The display of claim 27, wherein the light-emissive material has a light-emissive wavelength range that is the same for the first sub-pixel and the second sub-pixel.

29. The display of claim 22, wherein the active OLED material layer comprises two active OLED material layers including a light-emissive material layer and a hole conducting material layer.

30. The display of claim 29, wherein the hole conducting material is chosen from at least one of a hole injecting material and a hole transporting material.

31. The display of claim 22, wherein the first and second sub-pixels correspond to differing pixels.

32. The display of claim 22, further comprising a structure disposed on the substrate within the gap between the first electrode and the second electrode.

33. The display of claim 32, wherein the structure comprises an electrically resistive material.

34. The display of claim 22, further comprising a definition layer disposed on the substrate over a portion of the first electrode and the second electrode, wherein the confinement structure is disposed over the definition layer.

35. The display of claim 34, wherein the definition layer comprises an electrically resistive material.

36. The display of claim 34, further comprising a structure disposed on the substrate in the gap between the first electrode and the second electrode.

37. The display of claim 36, further comprising a second definition layer disposed over the structure.

38. The display of claim 22, wherein the display is a top emission display.

39. The display of claim 22, wherein the display is an active matrix device.

40. The display of claim 22, wherein the display has a fill factor greater than 40%.

41. The display of claim 22, wherein the display has a fill factor greater than 60%.

42. The display of claim 22, wherein the display has a resolution of at least 100 ppi.

43. The display of claim 22, wherein the display has a resolution of at least 300 ppi.

* * * * *

专利名称(译)	高分辨率有机发光二极管器件，显示器和相关方法		
公开(公告)号	US9614191	公开(公告)日	2017-04-04
申请号	US14/030776	申请日	2013-09-18
[标]申请(专利权)人(译)	科迪华公司		
申请(专利权)人(译)	KATEEVA INC.		
当前申请(专利权)人(译)	KATEEVA INC.		
[标]发明人	MADIGAN CONOR FRANCIS		
发明人	MADIGAN, CONOR FRANCIS		
IPC分类号	H01L51/00 H01L27/12 H01L27/32 B82Y30/00 B82Y10/00 H01L51/56 H01L51/05 H01L51/50 H01L51/52		
CPC分类号	H01L51/56 H01L27/3218 H01L27/3246 H01L51/0005 H01L27/326 H01L51/5203 H01L27/3209 H01L27/3211 H01L51/5012 H01L51/502 H01L51/5056 H01L2227/32 H01L51/5088 H01L51/5206 H01L51/5221 H01L2251/301 H01L2251/308 H01L2251/558		
审查员(译)	PARKER , ALLEN		
优先权	61/753692 2013-01-17 US		
其他公开文献	US20140197385A1		
外部链接	Espacenet USPTO		

摘要(译)

一种制造有机发光二极管 (OLED) 显示器的方法可以包括在衬底上提供与第一子像素相关联的第一电极和与第二子像素相关联的第二电极，其中在第一子像素之间形成间隙电极和第二电极，并且其中第一电极和第二电极位于具有由衬底上的约束结构限定的边界的阱中。该方法还可以包括在阱中沉积有位于其中的电极的有源OLED材料，以形成跨越阱的边界的基本上连续的有源OLED材料层，使得活性OLED材料层的表面远离衬底具有非平面形貌。沉积可以通过喷墨印刷。

