



US009431634B2

(12) **United States Patent**
Song

(10) **Patent No.:** **US 9,431,634 B2**
(45) **Date of Patent:** **Aug. 30, 2016**

(54) **ORGANIC LIGHT EMITTING DISPLAY DEVICE HAVING IMPROVED LIGHT EMITTING EFFICIENCY**

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**
Yongin-si, Gyeonggi-do (KR)

(72) Inventor: **Seung-Yong Song**, Suwon-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**,
Samsung-ro, Giheung-Gu, Yongin-si,
Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/832,742**

(22) Filed: **Mar. 15, 2013**

(65) **Prior Publication Data**
US 2014/0138636 A1 May 22, 2014

(30) **Foreign Application Priority Data**
Nov. 20, 2012 (KR) 10-2012-0131598

(51) **Int. Cl.**
H01L 51/56 (2006.01)
B82Y 10/00 (2011.01)
H01L 51/52 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/56** (2013.01); **H01L 51/5253**
(2013.01); **H01L 51/5262** (2013.01)

(58) **Field of Classification Search**
CPC H01L 51/0545; H01L 51/5012; H01L 51/0036; H01L 51/0541; B82Y 10/00
USPC 257/40
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,389,983 B2*	3/2013	Seo et al.	257/40
2002/0070663 A1*	6/2002	Ogura	H01L 51/5237 313/506
2008/0006819 A1*	1/2008	McCormick et al.	257/40
2008/0142789 A1*	6/2008	Suganuma	H01L 27/3244 257/40
2009/0267487 A1	10/2009	Kwack et al.	
2010/0001301 A1*	1/2010	Karg et al.	257/98
2010/0084677 A1*	4/2010	Michellys	257/98
2010/0181903 A1	7/2010	Kim et al.	
2011/0073897 A1*	3/2011	Kang et al.	257/98

(Continued)

FOREIGN PATENT DOCUMENTS

JP	2011521423 A	7/2011
JP	2012017448 *	1/2012

(Continued)

OTHER PUBLICATIONS

Awazu et al. (A Plasmonic Photocatalyst Consisting of Silver Nanoparticles Embedded in Titanium Dioxide, University of Tokyo, Japan, 2008).*


(Continued)

Primary Examiner — John C Ingham
Assistant Examiner — Didarul Mazumder
(74) *Attorney, Agent, or Firm* — Robert E. Bushnell, Esq.

(57) **ABSTRACT**

In an organic light emitting display device according to an embodiment of the present disclosure, a light extraction reduction preventing layer is disposed between a display unit disposed on a substrate and an encapsulation layer for protecting the display unit, and as a result, light emission efficiency may be improved by reducing an amount of light dissipating while light generated from an emission layer of the display unit is extracted to the outside.

18 Claims, 3 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

2011/0163330	A1 *	7/2011	Kim et al.	257/88
2012/0133275	A1	5/2012	Lee et al.	
2012/0138918	A1 *	6/2012	Naraoka et al.	257/40
2012/0146492	A1 *	6/2012	Ryu et al.	313/512
2012/0228601	A1 *	9/2012	Hiyama G02B	5/0231 257/40
2012/0228668	A1 *	9/2012	Thoumazet et al.	257/100
2012/0248422	A1 *	10/2012	Mine et al.	257/40
2012/0256218	A1 *	10/2012	Kwack et al.	257/98
2012/0261701	A1	10/2012	Yoo et al.	
2013/0056717	A1 *	3/2013	Ishihara et al.	257/40
2013/0103123	A1 *	4/2013	Khan et al.	607/90
2013/0168644	A1 *	7/2013	Park	257/40
2013/0193419	A1 *	8/2013	Mizuno	257/40

FOREIGN PATENT DOCUMENTS

KR	1020090112387	A	10/2009
KR	10-2009-0132025	A	12/2009
KR	10-2011-0135045	A	6/2010
KR	10-2010-0085347	A	7/2010
KR	10-2011-0080050	A	7/2011
KR	10-2012-0057286	A	6/2012
KR	20120118306	A	10/2012
KR	1020140033867	A	3/2014

OTHER PUBLICATIONS

Korean Office Action issued by Korean Patent Office on Dec. 16, 2013 in connection with Korean Patent Application No. 10-2012-013598 and Request for Entry attached herewith.

* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5





FIG. 6



**ORGANIC LIGHT EMITTING DISPLAY
DEVICE HAVING IMPROVED LIGHT
EMITTING EFFICIENCY**

CLAIM OF PRIORITY

This application makes reference to, incorporates the same herein, and claims all benefits accruing under 35 U.S.C. §119 from an application for ORGANIC LIGHT EMITTING DISPLAY DEVICE HAVING IMPROVED LIGHT EMITTING EFFICIENCY, earlier filed in the Korean Intellectual Property Office on 20 Nov. 2012 and there duly assigned Serial No. 10-2012-0131598.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present disclosure relates to an organic light emitting display device, and, more particularly, to an organic light emitting display device improving light emitting efficiency by reducing an amount of light that dissipates while the light generated from an emission layer is discharged to the outside environment.

2. Description of the Related Art

An organic light emitting display device is a self-emission display device which has an organic light emitting diode that emits light to display an image. Since the organic light emitting display device has characteristics such as low power consumption, high luminance, and a high response speed, the organic light emitting display device currently receives attention as a display device.

In general, in the organic light emitting display device, a portion of the device generating light is called a display unit, and the display unit includes a hole injection electrode, an emission layer, and an electron injection electrode. In the organic light emitting display device, holes supplied from the hole injection electrode and electrons supplied from the electron injection electrode are coupled with each other in the emission layer to generate light. Generally, the hole injection electrode is an anode, and the electron injection electrode is a cathode.

However, the display unit can be easily damaged by an external gas such as oxygen or moisture, and the display unit may deteriorate due to contact with oxygen or moisture. Accordingly, in order to prevent oxygen or moisture from penetrating from the outside, an encapsulation structure for sealing and protecting the display unit is required.

As an example of such an encapsulation structure, an encapsulation layer, specifically a thin film encapsulation layer, in which inorganic layers and organic layers are alternately laminated is adopted. That is, the encapsulation layer, in which inorganic layers and organic layers are alternately laminated, is formed on the display unit, which is formed on a substrate to seal the display unit and thus protect the display unit. Here, the organic layer mainly functions to give flexibility to a flat panel display, and the inorganic layer mainly serves to prevent oxygen or moisture from penetrating into the device.

However, when the light generated from the emission layer is discharged to the outside environment, a large amount of light dissipates while passing through a laminated structure such as the encapsulation layer disposed on the emission layer. The light efficiency of the organic light emitting display device is not good because the light dissi-

pates. Accordingly, in order to increase the light efficiency in the organic light emitting display device, dissipation of the light needs to be minimized.

SUMMARY OF THE INVENTION

The present disclosure has been made in an effort to provide an organic light emitting display device having improved light extraction efficiency by properly controlling a refractive index difference between a display unit and an encapsulation layer to properly establish a resonance condition.

Further, the present disclosure has been made in an effort to provide an organic light emitting display device including a light efficiency reduction preventing layer between the display unit and the encapsulation layer.

An embodiment of the present disclosure provides an organic light emitting display device, including: a substrate; a display unit disposed on the substrate; a light extraction reduction preventing layer disposed on the display unit; and an encapsulation layer disposed on the light extraction reduction preventing layer.

The encapsulation layer may have a structure in which a plurality of inorganic layers and a plurality of organic layers are alternately laminated.

A thickness of the organic layers may be larger than a thickness of the inorganic layers.

A refractive index of the encapsulation layer may be in the range of from about 1.5 to about 2.0.

A capping layer may be disposed between the display unit and the light extraction reduction preventing layer.

A thickness of the capping layer may be in the range of from about 20 nm to about 200 nm.

The capping layer may comprise at least one selected from a group consisting of tris(8-hydroxyquinolino) aluminum (Alq3), ZnSe, 2,5-bis(6'-(2',2''-bipyridyl))-1,1-dimethyl-3,4-diphenylsilole, 4,4'-bis[N-(1-naphthyl)-N-phenyl-amino]biphenyl (α -NPD), N,N'-diphenyl-N,N'-bis(3-methylphenyl)-1,1'-biphenyl-4,4'-diamine (TPD), and 1,1-bis[di-(4-tolylamino)phenyl]cyclohexane (TAPC).

A refractive index of the capping layer may be in the range of from about 1.6 to about 3.0.

A refractive index of the light extraction reduction preventing layer may be in the range of from about 1.1 to less than about 1.5.

The light extraction reduction preventing layer may comprise at least one selected from CaF₂, NaF, Na₃AlF₆, SiO_x, AlF₃, LiF, MgF₂, and IF₃.

A thickness of the light extraction reduction preventing layer may be in the range of from about 20 nm to about 200 nm.

The display unit may include a first electrode formed on the substrate; an emission layer formed on the first electrode; and a second electrode formed on the emission layer.

Another embodiment of the present disclosure provides a manufacturing method of an organic light emitting display device, including: forming a display unit on a substrate; forming a light extraction reduction preventing layer on the display unit; and forming an encapsulation layer on the light extraction reduction preventing layer.

The manufacturing method of an organic light emitting display device may further include forming a capping layer before the forming of the light extraction reduction preventing layer and after the forming of the display unit.

In the forming of the encapsulation layer, laminating inorganic layers and laminating organic layers may be alternately performed one or more times.

A refractive index of the capping layer may be in the range of from about 1.6 to about 3.0.

A refractive index of the light extraction reduction preventing layer may be in the range of from about 1.1 or more to less than about 1.5.

Yet another embodiment of the present disclosure provides an organic light emitting display device, including: a substrate; a first electrode disposed on the substrate; an emission layer disposed on the first electrode; a second electrode formed on the emission layer; a capping layer disposed on the second electrode; a light extraction reduction preventing layer disposed on the capping layer; and an encapsulation layer disposed on the light extraction reduction preventing layer, in which a refractive index of the light extraction reduction preventing layer is lower than a refractive index of the capping layer and lower than a refractive index of the encapsulation layer.

According to an embodiment of the present disclosure, a light extraction reduction preventing layer is disposed between a display unit and an encapsulation layer, and thus while light generated from an emission layer is discharged to the outside environment, resonance efficiently occurs reducing light dissipation, thereby improving light emission efficiency of the organic light emitting display device. Particularly, in the case where a capping layer having a high refractive index is disposed on the display unit, the light extraction reduction preventing layer is disposed between the capping layer and the encapsulation layer and thus a difference in a refractive index between the capping layer and the encapsulation layer occurs, and as a result, a resonance condition can be efficiently established during a light extraction process. As a result, it is possible to improve light emission efficiency by improving light extraction efficiency.

The foregoing summary is illustrative only and is not intended to be in any way limiting. In addition to the illustrative aspects, embodiments, and features described above, further aspects, embodiments, and features will become apparent by reference to the drawings and the following detailed description.

BRIEF DESCRIPTION OF THE DRAWINGS

A more complete appreciation of the invention, and many of the attendant advantages thereof, will be readily apparent as the same becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings in which like reference symbols indicate the same or similar components, wherein:

FIG. 1 is a schematic diagram of an example of an organic light emitting display device.

FIG. 2 is a schematic diagram of an example of a laminated structure in the organic light emitting display device.

FIG. 3 is a diagram for describing a structure of an organic light emitting display device according to an embodiment of the present disclosure.

FIG. 4 is a diagram for describing a structure of an organic light emitting display device according to another embodiment of the present disclosure.

FIG. 5 is a diagram for describing a structure of an organic light emitting display device according to yet another embodiment of the present disclosure.

FIG. 6 is a cross-sectional view illustrating the structure of the organic light emitting display device in more detail according to an embodiment of the present disclosure.

DETAILED DESCRIPTION OF THE INVENTION

Hereinafter, embodiments of the present disclosure will be described in more detail with reference to the accompanying drawings. However, the scope of the present disclosure is not limited to the following Examples and drawings. Embodiments to be described below and illustrated in the drawings may include various equivalents and modifications.

The terminology used in this specification is used in order to express the embodiments of the present disclosure and may depend on the intention of users or operators or the custom in the art to which the present disclosure belongs. Accordingly, the terminology needs to be defined base on the details provided throughout this specification.

For reference, respective components and shapes thereof are schematically drawn or exaggeratedly drawn in the accompanying drawings for easy understanding. Like reference numerals designate like elements throughout the drawings.

Further, it will be understood that when a layer or an element is described as being "on" another layer or element, it may be directly disposed on another layer or element, or an intervening layer or element may also be present therebetween.

FIG. 1 illustrates an example of a structure of an organic light emitting display device. The organic light emitting display device illustrated in FIG. 1 includes a substrate **100**, a display unit **200** disposed on the substrate **100**, and an encapsulation layer **300** disposed on the display unit **200**. In a thin organic light emitting display device or a flexible organic light emitting display device, the display unit **200** is protected by using the encapsulation layer **300**.

FIG. 2 illustrates a structure of the organic light emitting display device of one embodiment of the invention in more detail.

In the organic light emitting display device, a portion generating light is called the display unit **200**, and the display unit **200** includes a first electrode **210**, an emission layer **220**, and a second electrode **230**.

The first electrode **210** may be a hole injection electrode, and the second electrode **230** may be an electron injection electrode. Holes supplied from the first electrode and electrons supplied from the second electrode are coupled with each other in the emission layer **220** to generate light.

Alternatively, the first electrode **210** may be an electron injection electrode, and the second electrode **230** may be a hole injection electrode. Electrons supplied from the first electrode and holes supplied from the second electrode are coupled with each other in the emission layer **220** to generate light.

However, the display unit **200** is very vulnerable to intrusion of external gas such as oxygen or moisture. Accordingly, in order to prevent oxygen or moisture from penetrating from the outside, the encapsulation layer **300** may be disposed as a seal around the display unit **200**. Further, in order to protect the display unit **200** before forming the encapsulation layer **300** and prevent the display unit from being damaged while forming the encapsulation layer **300**, a capping layer **400** may be disposed on the display unit before the encapsulation layer **300** is put in place.

In FIG. 2, as the encapsulation layer 300, a thin film encapsulation layer in which inorganic layers 310 and organic layers 320 are alternately laminated is illustrated. The inorganic layers 310 and organic layers 320, which are alternately laminated, form the encapsulation layer 300. That is, a plurality of inorganic layers 311, 312, and 313 and a plurality of organic layers 321 and 322 are alternately laminated on the display unit 200 to seal the display unit 200. Here, the organic layer 320 may mainly function to give flexibility to a flat panel display, and the inorganic layer may mainly serve to prevent oxygen or moisture from penetrating.

In FIG. 2, three inorganic layers 311, 312, and 313 and two organic layers 321 and 322 are shown alternately laminated each other to cover the emission layer 200 on the substrate 100.

The inorganic layer 310 may be made of metal oxide or metal nitride by a method such as, for example, one of sputtering, chemical vapor deposition (CVD), ion beam assisted deposition (IBAD), and the like.

Further, the organic layer 320 may be formed, for example, by depositing a liquefied or evaporated monomer and then irradiating the monomer coating with ultraviolet light to cure the deposited material. Acceptable methods of forming the organic layer 320 are not limited to the exemplary methods specifically described herein.

A capping layer 400 may be disposed between the encapsulation layer 300 and the display unit 200.

As an example of the capping layer 400, an ultraviolet blocking layer capable of blocking ultraviolet light that can have a bad influence on the display unit 200 may be formed. For example, ultraviolet light may be irradiated onto an organic precursor or monomer coating in order to form the organic layer 320 while the encapsulation layer 300 is formed. In this case, in order to prevent the display unit 200 from being damaged by the ultraviolet light, a capping layer 400 having an ultraviolet blocking characteristic may be formed on the display unit 200. The capping layer 400 may be formed by a single layer or may be formed by a multilayer with two or more layers. The capping layer 400 may have a moisture or oxygen blocking characteristic.

FIG. 3 illustrates a structure of an organic light emitting display device according to an embodiment of the present disclosure.

The organic light emitting display device illustrated in FIG. 3 includes a substrate 100, a display unit 200 disposed on the substrate 100, a light extraction reduction preventing layer 500 disposed on the display unit 200, and an encapsulation layer 300 disposed on the light extraction reduction preventing layer 500. Further, in the organic light emitting display device illustrated in FIG. 3, a capping layer 400 is disposed between the display unit 200 and the light extraction reduction preventing layer 500.

In detail, the display unit 200 may be formed on the substrate 100, and the display unit may include a first electrode 210 formed on the substrate 100, an emission layer 220 formed on the first electrode 210, and a second electrode 230 formed on the emission layer 220.

Although not illustrated in FIG. 3, at least one of a hole injection layer and a hole transport layer may be disposed between the first electrode 210 and the emission layer 220. Similarly, although not illustrated in FIG. 3, at least one of an electron transport layer and an electron injection layer may be disposed between the emission layer 220 and the second electrode 230.

The encapsulation layer 300 is disposed to cover display unit 200 in order to protect the display unit 200. In order to

form the encapsulation layer 300, the inorganic layers 310 and the organic layers 320 are alternately laminated.

In detail, first, the first inorganic layer 311 is coated to cover the display unit 200, a first organic layer 321 is coated thereon, a second inorganic layer 312 and a second organic layer 322 are coated thereon, and then an inorganic layer 313 is finally coated on the top organic layer to form the encapsulation layer 300.

In the illustration of FIG. 3, three inorganic layers and two organic layers are formed, but the inorganic layers and the organic layers may be alternately coated two additional times or more. If necessary, the inorganic layers and the organic layers may be alternately coated thirty times, or more than thirty times. A thickness of the encapsulation layer may depend on the laminated number of inorganic layers and organic layers. The thickness of the encapsulation layer may be properly controlled if necessary.

In the encapsulation layer 300 in FIG. 3, it is exemplified that both the first layer disposed to be closest to the display unit 200 while covering the display unit 200 and the last layer disposed at the outermost side of the encapsulation layer 300 while being farthest away from the display unit 200 are formed as the inorganic layers. In the other cases, the first layer disposed to be closest to the display unit 200 and the outermost layer disposed to be farthest away from the display unit 200 may not be formed as inorganic layers.

The inorganic layer 310 may be made of metal oxide or metal nitride by, for example, a method such as one of sputtering, CVD, ion beam assisted deposition (IBAD), and the like. The inorganic layer may be formed by using a material selected from, for example, calcium oxide, alumina, silica, titania, indium oxide, tin oxide, silicon oxide, silicon nitride, and aluminum nitride, and the material is not necessarily limited to the examples presented herein.

The organic layers 320 may be formed by depositing a liquefied or evaporated monomer and then irradiating ultraviolet light to cure the deposited material. The organic layer material may include, for example, any one selected from acrylic, metacrylic, polyester, poly(ethylene terephthalate) (PET), polyethylene, and polypropylene or a mixture thereof, and is not necessarily limited to the examples.

A refractive index of the encapsulation layer 300 including the inorganic layers and the organic layers which are formed as described above may have a value in the range of from about 1.5 to about 2.0. Even though the encapsulation layer in different embodiments of the invention may be formed by using the same material, the value of the refractive index may vary depending on a method of forming the encapsulation layer. In the case where the encapsulation layer is formed by using the above materials using a method which is generally used in the art, the refractive index of the encapsulation layer 300 may be in the range of from about 1.5 to about 2.0.

In the embodiment illustrated in FIG. 3, the encapsulation layer 300 is formed in different thicknesses of the inorganic layer 310 and the organic layer 320. Considering the inorganic layer 310 and the organic layer 320, a thickness of the organic layer is set to be larger than a thickness of the inorganic layer. For example, the thickness of each organic layer may be about 2 to 5 times larger than the thickness of each inorganic layer. Further, as illustrated in FIG. 3, respective ends of the inorganic layer and the organic layer may have a structure directly contacting the substrate.

Here, the thickness of the inorganic layers 311, 312, and 313 may be set in the range of from about 10 nm to about 50 nm respectively, and the thickness of the organic layers 321 and 322 may be set in the range of from about 20 nm

to about 200 nm respectively. In another embodiment of the present disclosure, the thickness of each layer of the inorganic layers is set to about 100 nm and the thickness of each layer of the organic layers is set to about 500 nm to form the encapsulation layer 300.

Further, in order to prevent the display unit 200 from being damaged while forming the encapsulation layer 300, a capping layer 400 may be disposed on the display unit 200 before the encapsulation layer is disposed on the capping layer.

That is, as illustrated in FIG. 3, the capping layer 400 may be formed between the encapsulation layer 300 and the display unit 200.

As an example of the capping layer 400, the capping layer 400 may be formed as an ultraviolet blocking layer capable of blocking ultraviolet light that can negatively influence the display unit 200. That is, in some cases, in order to form the organic layer 320 while forming the encapsulation layer 300, the ultraviolet light is irradiated. In this case, in order to prevent the display unit 200 from being damaged by the ultraviolet light, the capping layer 400 having an ultraviolet blocking characteristic may be formed on the display unit 200. The capping layer 400 may be formed in a single layer or may be formed as a multilayer with two or more layers.

To this end, the capping layer 400 may be made of a transparent material having an ultraviolet blocking characteristic. As the material, a material reflecting or absorbing ultraviolet light is included. As the capping layer 400, a material having a characteristic of blocking moisture, air, or oxygen may be used.

The thickness of the capping layer 400 may be controlled to satisfy the following Formula.

$$n \cdot d = \lambda / 4$$

Here, n is a refractive index, d is a thickness, and λ is a center value of an emission wavelength band. Here, the emission wavelength is a visible light emission wavelength, and a wavelength λ may depend on a use thereof, in the case of being applied as a use for emitting specific color light.

In the case of considering an ultraviolet blocking characteristic, the thickness of the capping layer 400 may be set in the range of from about 20 to about 200 nm. When the thickness of the capping layer 400 is less than about 20 nm, the ultraviolet light is not easily blocked, and thus display unit 200 may be damaged due to exposure to the ultraviolet light, and when the thickness is more than about 200 nm, a light extraction ratio or a color purity characteristic of the organic light emitting display device may deteriorate.

According to an embodiment of the present disclosure, the capping layer may comprise at least one material selected from tris(8-hydroxyquinolino) aluminum (Alq3), ZnSe, 2,5-bis(6'-(2',2''-bipyridyl))-1,1-dimethyl-3,4-diphenylsilole, 4,4'-bis[N-(1-naphthyl)-N-phenyl-amino]biphenyl (α -NPD), N,N'-diphenyl-N,N'-bis(3-methylphenyl)-1,1'-biphenyl-4,4'-diamine (TPD), 1,1'-bis[di-(4-tolylamino)phenyl]cyclohexane (TAPC).

When the capping layer is formed by using one of these materials, the refractive index of the capping layer may be in the range of about 1.6 or more.

As the refractive index of the capping layer is increased, the capping layer can be made thinner. That is, in the Formula, in a relationship of $n \cdot d = \lambda / 4$, as a refractive index n is increased, a thickness d may be decreased, and as a result, as the n is increased, it is advantageous to slim the device. However, it is not easy to increase the refractive index of the capping layer 400 without limit because it must be matched with other desirable characteristics of the cap-

ping layer material. Accordingly, considering the refractive index of the display unit 200 and the refractive index of the encapsulation layer 300, the refractive index of the capping layer may desirably be in the range of from about 1.6 to about 3.0.

When considering thicknesses of other constituent elements of the organic light emitting display device in addition to that of the encapsulation layer 300, an efficiency characteristic of the organic light emitting display device and the refractive index of the capping layer material, a condition of $n \cdot d = \lambda / 4$ may be satisfied if the thickness of the capping layer 400 is in the range from about 50 to about 150 nm.

Since the organic light emitting display device is formed in a multilayer laminated structure, light generated from the emission layer must pass through the laminated structure disposed above the emission layer before being discharged to the outside. However, as the light generated from the emission layer passes through the laminated structure disposed above the emission layer, a large amount of light may dissipate. Light extraction efficiency of the organic light emitting display device is not good because the light dissipates.

An important factor among factors in explaining the dissipation of light as it passes through the multilayered structure is total reflection. In order to prevent the light from dissipating due to total reflection while light is being discharged to the outside, a structure that can induce a proper reflection on the interface of the multilayered laminated structure, thereby preventing a total reflection on the interface, may be adopted. Such a structure, designed to make proper reflection on the interface between the layers in order to increase light extraction efficiency as light generated from the emission layer is discharged to the outside, is called a resonance structure. In this embodiment of the invention, in order to reduce the amount of light dissipating while light generated from the emission layer is discharged to the outside, the resonance structure is constructed.

In order to improve extraction of light using a resonance structure, the proper reflection needs to be arranged. However, in the case where the refractive index difference between the display unit 200 and the encapsulation layer 300 is not large enough, minimal reflection occurs on the interface, and the resonance condition is not optimally established.

Further, when the capping layer 400 is disposed on the display unit 200, in the case where a difference in a refractive index between the capping layer 400 and the encapsulation layer 300 is not large, the reflection on the interface does not easily occur, and the resonance condition is not optimally established. For slimness of the device, it is advantageous that the capping layer be made of a high refractive index material. Regarding the encapsulation layer, in order to prevent primary penetration of moisture, the first component layer of the encapsulation layer, the one adjacent to the capping layer, may be formed as an inorganic layer having a high refractive index. In this case, since the refractive index of the inorganic layer is high, the difference in a refractive index between the capping layer and the inorganic layer is not large and thus the resonance condition may not be established well.

Considering this, in an embodiment of the present disclosure, the light extraction reduction preventing layer 500, having a low refractive index, is disposed between the display unit 200 and the encapsulation layer 300 in order to improve light extraction efficiency. In detail, since the light extraction reduction preventing layer 500 is disposed between the display unit 200 and the encapsulation layer

300, a low refractive index layer is disposed between the display unit 200 and the encapsulation layer 300 and thus a difference in a refractive index between the layers occurs and may facilitate the establishment of a desired resonance condition.

Further, when the capping layer 400 is disposed on the display unit 200, the light extraction reduction preventing layer 500, having a low refractive index, is disposed between the capping layer 400 and the encapsulation layer 300, and, as a result, the difference in refractive index between the layers occurs and improves light extraction efficiency.

More generally, in an organic light emitting display device, the light extraction reduction preventing layer may be interposed between a first adjacent layer and a second adjacent layer and may have a refractive index that is lower than a refractive index of the first adjacent layer and lower than a refractive index of the second adjacent layer. This configuration may improve light extraction efficiency in the organic light emitting display device.

In FIG. 3, the capping layer 400 is disposed on the display unit 200, the light extraction reduction preventing layer 500 is disposed on the capping layer 400, and the encapsulation layer 300 is disposed on the light extraction reduction preventing layer 500. A portion of encapsulation layer 300 contacting the light extraction reduction preventing layer 500 is formed by the inorganic layer 311.

The light extraction reduction preventing layer 500 may be made of a light transmitting material, and it is advantageous if the refractive index of the light extraction reduction preventing layer 500 is very different from the refractive indexes of the capping layer 400 and the encapsulation layer 300. In general, when considering that a refractive index of a transparent solid material is 1.1 or more and the refractive indexes of the capping layer 400 and the encapsulation layer 300 are 1.5 or more, the refractive index of the light extraction reduction preventing layer 500 may advantageously be controlled to 1.1 or more to less than 1.5.

Considering that readily available options exist for selecting a low refractive index transparent solid material and the difference in refractive index between that low refractive index material and adjacent layers including the capping layer 400 and the encapsulation layer 300, the refractive index of the light extraction reduction preventing layer 500 may advantageously be controlled to be in a range of from about 1.2 to about 1.4.

When considering the difference in the refractive index of the light extraction reduction preventing layer 500 compared to those of the capping layer 400 and the encapsulation layer 300 and considering the need for transparency of the material, the light extraction reduction preventing layer 500 may comprise at least one of CaF_2 , NaF , Na_3AlF_6 , SiO_x , AlF_3 , LiF , MgF_2 , and IF_3 .

Meanwhile, in order to form the resonance structure, the light extraction reduction preventing layer 500 may also be formed to satisfy the condition of the Formula, that is, $n \cdot d = \lambda/4$. When considering the details, the thickness of the light extraction reduction preventing layer 500 may be set in the range of from about 20 nm to about 200 nm.

FIG. 4 illustrates a structure of an organic light emitting display device according to another embodiment of the present disclosure. In the organic light emitting display device illustrated in FIG. 4, an inorganic layer 410 is formed after forming the display unit 200, the light extraction reduction preventing layer 500 is disposed on the inorganic layer 410, and the encapsulation layer 300 is disposed thereon. Here, the inorganic layer 410 may correspond to the

capping layer 400 of FIG. 3. The inorganic layer 410 may be formed with the same material used in the inorganic layer 310 of the encapsulation layer 300 by the same method applied in the formation of the inorganic layer 310. That is, the inorganic layer 410 may also correspond to the inorganic layer 310 of the encapsulation layer 300.

FIG. 5 illustrates a structure of an organic light emitting display device according to yet another embodiment of the present disclosure. Here, as illustrated in FIG. 3, the encapsulation layer 300 is formed after the capping layer 400 and the light extraction reduction preventing layer 500 are formed on the display unit 200, and the organic layer 320 is first formed when the encapsulation layer 300 is formed.

Further, another embodiment of the present disclosure provides a manufacturing method of an organic light emitting display device.

The manufacturing method of an organic light emitting display device may include forming a display unit on a substrate, forming a light extraction reduction preventing layer on the display unit, and forming an encapsulation layer on the light extraction reduction preventing layer.

Here, the manufacturing method of an organic light emitting display device may further include forming a capping layer before the step of forming of the light extraction reduction preventing layer and after the forming of the display unit.

The forming of the encapsulation layer may further comprise laminating at least one inorganic layer and laminating at least one organic layer, one of the sequence of laminating an inorganic layer and then laminating an organic layer and the sequence of laminating an organic layer and then laminating an inorganic layer being repeated one or more times.

Hereinafter, the structure of the organic light emitting display device according to an embodiment of the present disclosure and a manufacturing method thereof will be described in more detail with reference to FIG. 6.

In the organic light emitting display device illustrated in FIG. 6, the substrate 100 may be made of glass or polymer plastic which is generally used in organic light emitting display devices. The substrate 100 may be transparent or may not be transparent.

The first electrode 210 is disposed on the substrate 100.

As illustrated in FIG. 6, a plurality of thin film transistors 120 may be formed on the substrate 100 before forming the first electrode 210. The thin film transistor 120 includes a gate electrode 121, a drain electrode 122, a source electrode 123, and a semiconductor layer 124, which are formed on the substrate 100. Further, a gate insulating layer 113 and an interlayer insulating layer 115 are provided on the thin film transistor 120. The structure of the thin film transistor 120 is not limited to the form illustrated in FIG. 6 and may be configured by another form. A buffer layer 111 made of silicon oxide or silicon nitride may be further included between the thin film transistor 120 and the substrate 100, if necessary.

A first electrode 210, an emission layer 220, and a second electrode 230 are sequentially formed above the thin film transistors 120. The first electrode 210, the emission layer 220, and the second electrode 230 form the display unit 200. Here, the first electrode 210 is an anode as a pixel electrode which is electrically connected to the thin film transistor 120, and the second electrode 230 is a cathode.

The first electrode 210 is electrically connected with a lower thin film transistor 120. In this case, when a planarization layer 117 covering the thin film transistor 120 is provided, the first electrode 210 is disposed on the planarization layer 117, and the first electrode 210 is electrically

connected to the thin film transistor **120** through a contact hole provided in the planarization layer **117**.

The first electrode **210** may be provided as a transparent electrode or a reflective electrode. In the case where the first electrode **210** is provided as the transparent electrode, the first electrode **210** may be made of indium tin oxide (ITO), indium zinc oxide (IZO), ZnO or In₂O₃, and in the case where the first electrode **210** is provided as the reflective electrode, the first electrode **210** may include a reflective layer made of one of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, and a compound thereof and a layer made of ITO, IZO, ZnO or In₂O₃ thereon. In the case where the first electrode **210** is the anode, as a material of the first electrode **210**, ITO may be a preferred choice.

In FIG. 6, it is exemplified that the first electrode **210** serves as an anode and the second electrode **230** serves as a cathode, but polarities of the first electrode **210** and the second electrode **230** may be reversed.

A pixel defining layer (PDL) **240** may be provided between the first electrodes **210**. The pixel defining layer **240** may be made of a material having an insulation property and may partition the first electrodes **210**, electrically isolating the first electrode **210** of each pixel from those of other pixels. In detail, the pixel defining layer **240** may be disposed at an edge of the first electrode **210** to partition the first electrodes by forming pixel units and defining pixel areas.

The emission layer **220** may be provided between the first electrode **210** and the second electrode **230**. That is, the emission layer **220** may be disposed in an opening on the first electrode **210**, which may be partitioned from other pixels by the pixel defining layer **210**. The emission layer **220** may include a red emission layer **221**, a green emission layer **222**, and a blue emission layer **223**.

The emission layer **220** may be formed by various methods, and, for example, may be formed by a one of a deposition method and a transfer method using a transfer donor film.

At least one of a hole injection layer, a hole transport layer, an electron transport layer and an electron injection layer in addition to the emission layer **220** may be further provided between the first electrode **210** and the second electrode **230**. The emission layer **220**, together with any of or any combination of the hole injection layer, the hole transport layer, the electron transport layer, and the electron injection layer, are referred to collectively as an organic layer. The organic layer may be made of a low-molecular weight organic material or a high-molecular weight organic material.

Low molecular weight organic materials may be used for each of the hole injection layer, the hole transport layer, the emission layer, the electron transport layer, and the electron injection layer. The low-molecular organic materials may be laminated in a single or complex structure, and the applicable organic material includes copper phthalocyanine (CuPc), N,N'-Di(naphthalene-1-yl)-N,N'-diphenylbenzidine (NPB), tris(8-hydroxyquinolino)aluminum (Alq₃), and the like. A vacuum deposition and the like is performed by using a mask, and any of the light emission layer **220**, the hole injection layer, the hole transport layer, the electron transport layer, and the electron injection layer may be formed by using the low-molecular weight organic material.

The high-molecular weight organic material may be used for each of a hole transport layer (HTL) and an emission layer (EML). In this case, the hole transport layer may be made of poly(3,4-ethylenedioxythiophene) (PEDOT), and

the emission layer may be made of poly-phenylenevinylene (PPV)-based and polyfluorene-based high-molecular weight organic materials.

The second electrode **230** may be disposed on the emission layer **220** and the pixel defining layer **240**. The second electrode **230** may be made of a material which is generally used in the art. The second electrode **230** may also be provided as a transparent electrode or a reflective electrode. When the second electrode **230** is provided as the transparent electrode, the second electrode **230** may include a layer made of one of Li, Ca, LiF/Ca, LiF/Al, Al, Mg and a compound thereof and a layer made of a material for forming a transparent electrode such as ITO, IZO, ZnO, or In₂O₃ thereon. When the second electrode **230** is provided as the reflective electrode, the second electrode **230** may be provided by depositing one of Li, Ca, LiF/Ca, LiF/Al, Al, Mg and a compound thereof. In the embodiment illustrated in FIG. 6, when a top emission type organic light emitting display device is described, the second electrode **230** may be manufactured as the transparent electrode. For example, the second electrode **230** may be formed by using LiF/Al.

The capping layer **400** may be formed on the second electrode **230**. The capping layer may be made of a transparent material having an ultraviolet blocking characteristic to protect the display unit **200** including the first electrode **210**, the emission layer **220**, and the second electrode **230**.

The light extraction reduction preventing layer **500** may be formed on the capping layer **400**. The light extraction reduction preventing layer **500** is made of a low refractive index material, and while the light generated from the emission layer **220** is discharged to the outside, the light is suppressed from dissipating, thereby improving light emission efficiency.

The encapsulation layer **300** may be formed on the light extraction reduction preventing layer **500**.

The capping layer **400**, the light extraction reduction preventing layer **500**, and the encapsulation layer **300** are described above in detail.

As described above, the present disclosure provides an organic light emitting display device that includes a substrate, a first electrode disposed on the substrate, an emission layer disposed on the first electrode, a second electrode disposed on the emission layer, a capping layer disposed on the second electrode, a light extraction reduction preventing layer disposed on the capping layer, and an encapsulation layer disposed on the light extraction reduction preventing layer, in which a refractive index of the light extraction reduction preventing layer is lower than a refractive index of the capping layer and lower than a refractive index of the encapsulation layer.

From the foregoing, it will be appreciated that various embodiments of the present disclosure have been described herein for purposes of illustration, and that various modifications may be made without departing from the scope and spirit of the present disclosure. Accordingly, the various embodiments disclosed herein are not intended to be limiting, with the true scope and spirit being indicated by the following claims.

What is claimed is:

1. An organic light emitting display device, comprising:
 - a substrate;
 - a display unit disposed on the substrate;
 - a light extraction reduction preventing layer disposed on the display unit;
 - an encapsulation layer disposed on the light extraction reduction preventing layer, and

a capping layer disposed between the display unit and the light extraction reduction preventing layer,

the light extraction reduction preventing layer being interposed between a first adjacent layer and a second adjacent layer and having a refractive index that is lower than a refractive index of the first adjacent layer and lower than a refractive index of the second adjacent layer, the first adjacent layer being entirely covered by the second adjacent layer, and

in a cross-sectional view, the light extraction reduction preventing layer is entirely covered and contacted by the encapsulation layer and the capping layer.

2. The organic light emitting display device of claim 1, the encapsulation layer having a structure in which a plurality of inorganic layers and a plurality of organic layers are alternately laminated.

3. The organic light emitting display device of claim 2, a thickness of the organic layers being larger than a thickness of the inorganic layers.

4. The organic light emitting display device of claim 1, a refractive index of the encapsulation layer being in the range of from about 1.5 to about 2.0.

5. The organic light emitting display device of claim 1, a thickness of the capping layer being from about 20 nm to about 200 nm.

6. The organic light emitting display device of claim 1, the capping layer comprising at least one of tris(8-hydroxyquinolinato) aluminum (Alq3), ZnSe, 2,5-bis(6'-(2',2''-bipyridyl))-1,1-dimethyl-3,4-diphenylsilole, 4,4'-bis[N-(1-naphthyl)-N-phenyl-amino]biphenyl (α -NPD), N,N'-diphenyl-N,N'-bis(3-methylphenyl)-1,1'-biphenyl-4,4'-diamine (TPD), and 1,1'-bis[di-(4-tolylamino)phenyl]cyclohexane (TAPC).

7. The organic light emitting display device of claim 1, a refractive index of the capping layer being in the range of from about 1.6 to about 3.0.

8. The organic light emitting display device of claim 1, a refractive index of the light extraction reduction preventing layer being in the range of 1.1 or more to less than 1.5.

9. The organic light emitting display device of claim 1, the light extraction reduction preventing layer comprising at least one of CaF₂, NaF, Na₃AlF₆, SiO_x, AlF₃, LiF, MgF₂, and IF₃.

10. The organic light emitting display device of claim 1, a thickness of the light extraction reduction preventing layer being from about 20 nm to about 200 nm.

11. The organic light emitting display device of claim 1, the display unit comprising:

a first electrode formed on the substrate;
an emission layer formed on the first electrode; and
a second electrode formed on the emission layer.

12. A manufacturing method of an organic light emitting display device, comprising:

forming a display unit on a substrate;
forming a light extraction reduction preventing layer on the display unit;
forming an encapsulation layer on the light extraction reduction preventing layer, the light extraction reduc-

tion preventing layer being interposed between a first adjacent layer and a second adjacent layer and having a refractive index that is lower than a refractive index of the first adjacent layer and lower than a refractive index of the second adjacent layer, the first adjacent layer being entirely covered by the second adjacent layer; and

forming a capping layer before the step of forming the light extraction reduction preventing layer and after the step of forming the display unit, the capping layer disposed between the display unit and the light extraction reduction preventing layer,

in a cross-sectional view, the light extraction reduction preventing layer is entirely covered and contacted by the encapsulation layer and the capping layer.

13. The manufacturing method of an organic light emitting display device of claim 12, the step of forming the encapsulation layer further comprising laminating at least one inorganic layer and laminating at least one organic layer, one of the sequence of laminating an inorganic layer and then laminating an organic layer and the sequence of laminating an organic layer and then laminating an inorganic layer being repeated one or more times.

14. The manufacturing method of an organic light emitting display device of claim 12, a refractive index of the capping layer being in the range of from about 1.6 to about 3.0.

15. The manufacturing method of an organic light emitting display device of claim 12, a refractive index of the light extraction reduction preventing layer being in the range of 1.1 or more to less than 1.5.

16. An organic light emitting display device, comprising:

a substrate;
a first electrode disposed on the substrate;
an emission layer disposed on the first electrode;
a second electrode formed on the emission layer;
a capping layer disposed on the second electrode;
a light extraction reduction preventing layer disposed on the capping layer; and

an encapsulation layer disposed on the light extraction reduction preventing layer,

a refractive index of the light extraction reduction preventing layer being lower than a refractive index of the capping layer and lower than a refractive index of the encapsulation layer, the capping layer being entirely covered by the encapsulation layer,

in a cross-sectional view, the light extraction reduction preventing layer is entirely covered and contacted by the encapsulation layer and the capping layer.

17. The organic light emitting display device of claim 16, a refractive index of the light extraction reduction preventing layer being in a range from about 1.1 to about 1.5, a refractive index of the capping layer being in a range from about 1.6 to about 3.0, and a refractive index of the encapsulation layer being in a range from about 1.5 to about 2.0.

18. The organic light emitting display device of claim 16, the capping layer being capable of blocking ultraviolet light.

* * * * *

专利名称(译)	有机发光显示装置具有改善的发光效率		
公开(公告)号	US9431634	公开(公告)日	2016-08-30
申请号	US13/832742	申请日	2013-03-15
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SONG SEUNG YONG		
发明人	SONG, SEUNG-YONG		
IPC分类号	H01L51/56 B82Y10/00 H01L51/52		
CPC分类号	H01L51/5262 H01L51/56 H01L51/5253 H01L51/5275 H01L51/5246		
优先权	1020120131598 2012-11-20 KR		
其他公开文献	US20140138636A1		
外部链接	Espacenet USPTO		

摘要(译)

在根据本公开实施例的有机发光显示装置中，光提取减少防止层设置在设置在基板上的显示单元和用于保护显示单元的封装层之间，结果，发光效率可以通过减少从显示单元的发光层产生的光被提取到外部时消散的光量来改善。

