



US009673396B2

(12) **United States Patent**
Kwon

(10) **Patent No.:** **US 9,673,396 B2**
(45) **Date of Patent:** **Jun. 6, 2017**

(54) **METHOD OF MANUFACTURING
SUBSTRATE OF ORGANIC
LIGHT-EMITTING DISPLAY DEVICE**

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin
(KR)

(72) Inventor: **Young Gil Kwon**, Suwon-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-si
(KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/082,726**

(22) Filed: **Mar. 28, 2016**

(65) **Prior Publication Data**

US 2016/0211451 A1 Jul. 21, 2016

Related U.S. Application Data

(62) Division of application No. 14/668,351, filed on Mar.
25, 2015.

(30) **Foreign Application Priority Data**

Oct. 20, 2014 (KR) 10-2014-0141764

(51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 27/32 (2006.01)

(Continued)

(52) **U.S. Cl.**
CPC **H01L 51/0013** (2013.01); **H01L 27/3246**
(2013.01); **H01L 27/3283** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 51/0013; H01L 51/0018; H01L
51/5012; H01L 51/0039; G03F 7/0046;
B41M 5/46

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,093,612 B2* 1/2012 Tanaka H01L 51/0013
257/40
8,153,201 B2* 4/2012 Aoyama H01L 51/0013
427/407.1

(Continued)

FOREIGN PATENT DOCUMENTS

KR 10-2005-0082953 8/2005
KR 10-2006-0089838 8/2006

(Continued)

OTHER PUBLICATIONS

Alexander A. Zakhidov et al., Orthogonal processing: A new
strategy for organic electronics, Chemical Science, 2011, vol. 2,
1178-1182 (2011).

(Continued)

Primary Examiner — Jaehwan Oh


(74) *Attorney, Agent, or Firm* — H.C. Park & Associates,
PLC

(57) **ABSTRACT**

A method of manufacturing a substrate of an organic light-
emitting display device, the method including: forming, on
a first surface of a transparent substrate, a photothermal
conversion layer configured to covert incident light into
thermal energy; forming partition walls on the first surface
in a first region of the photothermal conversion layer, the
partition walls including a photosensitive compound includ-
ing a resorcinarene, the resorcinarene including a perfluo-
rocarbon group; forming an organic material layer on the
first surface in a second region of the photothermal conver-
sion layer, the second region being defined by the partition
walls; removing the partition walls; placing a target sub-
strate over the organic material layer; and applying light to
a second surface of the transparent substrate, the second
surface being opposite the first surface of the transparent
substrate.

9 Claims, 22 Drawing Sheets

S14



- (51) **Int. Cl.**
H01L 51/56 (2006.01)
H01L 51/50 (2006.01)
- (52) **U.S. Cl.**
CPC **H01L 51/56** (2013.01); **H01L 51/5012**
(2013.01); **H01L 51/5056** (2013.01); **H01L**
51/5072 (2013.01); **H01L 51/5088** (2013.01);
H01L 51/5092 (2013.01); **H01L 2227/323**
(2013.01)
- (56) **References Cited**
- U.S. PATENT DOCUMENTS
- 9,217,926 B2 * 12/2015 Ferro G03F 7/2022
2006/0043881 A1 * 3/2006 Chin H01L 51/0013
313/503
2008/0233827 A1 * 9/2008 Kagami H01L 51/0013
445/24
2009/0104835 A1 * 4/2009 Aoyama H01L 51/0013
445/58
2009/0117403 A1 * 5/2009 Sutcliffe B22F 3/1055
428/650
2010/0289019 A1 * 11/2010 Katz G03F 7/0035
257/40
2011/0129779 A1 * 6/2011 Lee B41M 5/38214
430/312
2011/0159252 A1 * 6/2011 Ober G03F 7/0046
428/195.1
- 2013/0337649 A1 * 12/2013 Tachibana G03F 7/094
438/694
2014/0057379 A1 * 2/2014 Park G03F 7/094
438/46
2014/0335445 A1 * 11/2014 Kang G03F 1/68
430/5
2015/0092136 A1 * 4/2015 Kim G02F 1/136227
349/46
2015/0140729 A1 * 5/2015 Ferro G03F 7/2022
438/99
2015/0188063 A1 * 7/2015 Takeya H01L 51/0554
257/40
2016/0035561 A1 * 2/2016 Aibara H01L 21/67028
134/4
2016/0035564 A1 * 2/2016 Aibara H01L 21/02057
134/4
- FOREIGN PATENT DOCUMENTS
- KR 10-2014-0065147 5/2014
WO 2009/126916 10/2009
WO 2009/143357 11/2009
- OTHER PUBLICATIONS
- Notice of Allowance issued on Feb. 12, 2016, 2016 in U.S. Appl.
No. 14/668,351.
- * cited by examiner

FIG.1

S1




FIG.2




FIG.3




FIG.4

S4




FIG.5




FIG.6

S6




FIG.7

S11




FIG.8




FIG.9




FIG.10




FIG.11

S15




FIG.12

S1




FIG.13




FIG.14

S'3




FIG.15

S'4




FIG.16




FIG.17

S'6




FIG.18

S'11




FIG. 19




FIG.20




FIG.21

S'14





FIG.22

S'15



1

METHOD OF MANUFACTURING SUBSTRATE OF ORGANIC LIGHT-EMITTING DISPLAY DEVICE

CROSS-REFERENCE TO RELATED APPLICATION

This application is a divisional of U.S. patent application Ser. No. 14/668,351, filed on Mar. 25, 2015, which claims priority from and the benefit of Korean Patent Application No. 10-2014-0141764, filed on Oct. 20, 2014, both of which are hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND

Field

Exemplary embodiments relate to a method of manufacturing a substrate of an organic light-emitting display device.

Discussion of the Background

An organic light-emitting display device includes an anode electrode, a cathode electrode, and organic layers disposed between the anode electrode and the cathode electrode. The organic layers may include a hole injection layer (HIL), a hole transport layer (HTL), an electron transport layer (ETL), an electron injection layer (EIL), and an emission layer (EML). The organic electroluminescence (EL) device may be classified as a high molecular organic EL device or a low molecular organic EL device according to the type of material that form the organic layers, and particularly, the EML.

In case of a low-molecular organic light-emitting display device, the organic layers may be patterned via a method using a fine metal mask (FMM). In case of a high-molecular organic light-emitting display device, the organic layers may be patterned via an inkjet printing method or a laser induced thermal imaging (LITI) method. The patterning of a high molecular organic layer via the LITI method may require a light source, a target substrate on which an organic EL device is to be formed, and a donor film. The donor film typically includes a base substrate and a transfer layer including, for instance, a photothermal conversion layer and an organic film. The organic film may be formed on an entire surface of the photothermal conversion layer. According to the LITI method, the organic film can be transferred onto the target substrate by selectively applying laser light to a particular region on the donor film to enable the photothermal conversion layer to generate heat in the particular region.

The above information disclosed in this Background section is only for enhancement of understanding of the background of the inventive concept, and, therefore, it may contain information that does not form the prior art that is already known in this country to a person of ordinary skill in the art.

SUMMARY

Exemplary embodiments provide a method of manufacturing a substrate of an organic light-emitting display device with improved processability.

Additional aspects will be set forth in the detailed description which follows, and, in part, will be apparent from the disclosure, or may be learned by practice of the inventive concept.

According to one or more exemplary embodiments, a method of manufacturing a substrate of an organic light-

2

emitting display device, the method including: forming, on a first surface of a transparent substrate, a photothermal conversion layer configured to convert incident light into thermal energy; forming partition walls on the first surface in a first region of the photothermal conversion layer, the partition walls including a photosensitive compound including a resorcinarene, the resorcinarene including a perfluorocarbon group; forming an organic material layer on the first surface in a second region of the photothermal conversion layer, the second region being defined by the partition walls; removing the partition walls; placing a target substrate over the organic material layer; and applying light to a second surface of the transparent substrate, the second surface being opposite the first surface of the transparent substrate.

According to one or more exemplary embodiments, a method of manufacturing a substrate of an organic light-emitting display device, the method including: forming, on a first surface of a transport substrate, a photothermal conversion layer configured to convert incident light into thermal energy; forming a fluorine-based resin layer on the photothermal conversion layer, the fluorine-based resin layer including a fluorine-based resin; forming first partition walls on the first surface in a first region of the photothermal conversion layer, the first partition walls including a photosensitive polymer compound; forming second partition walls using the first partition walls as a mask, the second partition walls including the fluorine-based resin; forming an organic material layer on the first surface of a second region of the photothermal conversion layer, the second region being defined by the first partition walls and the second partition walls; removing the first partition walls and the second partition walls; placing a target substrate over the organic material layer; and applying light to a second surface of the transparent substrate, the second surface being opposite the first surface of the transparent substrate.

The foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the claimed subject matter.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the inventive concept, and together with the description serve to explain the principles of the inventive concept.

FIGS. 1, 2, 3, and 4 are cross-sectional views illustrating processes of manufacturing a transfer substrate, according to one or more exemplary embodiments.

FIGS. 5 and 6 are cross-sectional views of a substrate of an organic light-emitting display device at various stages of manufacture, according to one or more exemplary embodiments.

FIGS. 7, 8, 9, 10, and 11 are cross-sectional views of a transfer substrate at various stages of manufacture, according to one or more exemplary embodiments.

FIGS. 12, 13, 14, and 15 are cross-sectional views of a transfer substrate at various stages of manufacture, according to one or more exemplary embodiments.

FIGS. 16 and 17 are cross-sectional views of a substrate of an organic light-emitting display device at various stages of manufacture, according to one or more exemplary embodiments.

FIGS. 18, 19, 20, 21, and 22 are cross-sectional views of a transfer substrate at various stages of manufacture, according to one or more exemplary embodiments.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

In the following description, for the purposes of explanation, numerous specific details are set forth in order to provide a thorough understanding of various exemplary embodiments. It is apparent, however, that various exemplary embodiments may be practiced without these specific details or with one or more equivalent arrangements. In other instances, well-known structures and devices are shown in block diagram form in order to avoid unnecessarily obscuring various exemplary embodiments.

In the accompanying figures, the size and relative sizes of layers, films, panels, regions, etc., may be exaggerated for clarity and descriptive purposes. Also, like reference numerals denote like elements.

When an element or layer is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it may be directly on, connected to, or coupled to the other element or layer or intervening elements or layers may be present. When, however, an element or layer is referred to as being “directly on,” “directly connected to,” or “directly coupled to” another element or layer, there are no intervening elements or layers present. For the purposes of this disclosure, “at least one of X, Y, and Z” and “at least one selected from the group consisting of X, Y, and Z” may be construed as X only, Y only, Z only, or any combination of two or more of X, Y, and Z, such as, for instance, XYZ, XYY, YZ, and ZZ. Like numbers refer to like elements throughout. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

Although the terms first, second, etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer, and/or section from another element, component, region, layer, and/or section. Thus, a first element, component, region, layer, and/or section discussed below could be termed a second element, component, region, layer, and/or section without departing from the teachings of the present disclosure.

Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper,” and the like, may be used herein for descriptive purposes, and, thereby, to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the drawings. Spatially relative terms are intended to encompass different orientations of an apparatus in use, operation, and/or manufacture in addition to the orientation depicted in the drawings. For example, if the apparatus in the drawings is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. Furthermore, the apparatus may be otherwise oriented (e.g., rotated 90 degrees or at other orientations), and, as such, the spatially relative descriptors used herein interpreted accordingly.

The terminology used herein is for the purpose of describing particular embodiments and is not intended to be limiting. As used herein, the singular forms, “a,” “an,” and “the” are intended to include the plural forms as well, unless the

context clearly indicates otherwise. Moreover, the terms “comprises,” “comprising,” “includes,” and/or “including,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

Various exemplary embodiments are described herein with reference to sectional illustrations that are schematic illustrations of idealized exemplary embodiments and/or intermediate structures. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, exemplary embodiments disclosed herein should not be construed as limited to the particular illustrated shapes of regions, but are to include deviations in shapes that result from, for instance, manufacturing. For example, an implanted region illustrated as a rectangle will, typically, have rounded or curved features and/or a gradient of implant concentration at its edges rather than a binary change from implanted to non-implanted region. Likewise, a buried region formed by implantation may result in some implantation in the region between the buried region and the surface through which the implantation takes place. Thus, the regions illustrated in the drawings are schematic in nature and their shapes are not intended to illustrate the actual shape of a region of a device and are not intended to be limiting.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure is a part. Terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense, unless expressly so defined herein.

FIGS. 1, 2, 3, and 4 are cross-sectional views illustrating processes S1, S2, S3, and S4, respectively, of manufacturing a transfer substrate, according to one or more exemplary embodiments.

Referring to FIG. 1, a photothermal conversion layer 120 is formed on an entire first surface of a transparent substrate 110, and a photosensitive compound layer 130, which includes a resorcinarene containing a perfluorocarbon group, is formed on an entire first surface of the photothermal conversion layer 120.

The transparent substrate 110 may be transparent (or at least translucent) to transmit light emitted from a light source (not illustrated) therethrough. For example, the transparent substrate may be at least one of, but is not limited to, a glass substrate, a quartz substrate, and a synthetic resin substrate formed of a transparent polymer material with high optical transmissivity, such as polyester, polyacryl, polyepoxy, polyethylene, polystyrene, and/or polyethylene terephthalate.

The light source may be at least one of a flash lamp, a tungsten halogen lamp and a laser beam. The light source is disposed below a second surface of the transparent substrate 110, as illustrated in FIG. 5 as light source L. A laser beam may be applied to scan the entire second surface of the transparent substrate 110, or may be selectively applied to an organic material layer formed in a particular region.

The photothermal conversion layer 120 is formed on the entire first surface of the transparent substrate 110. The photothermal conversion layer 120 may absorb light within


5

an infrared-visible light range of the light transmitted thereto through the transparent substrate **110**, and may convert the absorbed light into thermal energy. For example, the photothermal conversion layer **120** may be formed of at least one of a metal material with relatively high light absorptivity, such as molybdenum (Mo), chromium (Cr), titanium (Ti), tin (Sn), tungsten (W), and an alloy thereof, or any other suitable material.


The photothermal conversion layer **120** may be formed by various methods, for example, but not limited to, sputtering, electron beam deposition and vacuum deposition. The photosensitive compound layer **130**, which includes a resorcinarene containing a perfluorocarbon group, may be formed on

6


the entire first surface of the photothermal conversion layer **120**. The resorcinarene containing a perfluorocarbon group may be material immiscible with an organic material. For example, the resorcinarene containing a perfluorocarbon group may include, but is not limited to, a resorcinarene of Formula (1) and a resorcinarene of Formula (2), wherein R^1 is



and R^2 is a tert-butoxycarbonyl (t-butoxycarbonyl) group:



Formula (1)



Formula (2)

The photosensitive compound layer **130**, which includes the resorcinarene containing a perfluorocarbon group, may include at least one of the resorcinarene of Formula (1), the resorcinarene of Formula (2), and a mixture thereof.

The photosensitive compound layer **130**, which includes the resorcinarene containing a perfluorocarbon group, may also include a photo-acid generator. For example, the photo-acid generator may be, but is not limited to, N-nonafluorobutane-sulfonyloxy-1,8-naphthalimide, N-nonafluoropropane-sulfonyloxy-1,8-naphthalimide, N-nonafluoroethane-sulfonyloxy-1,8-naphthalimide, N-nonafluoromethane-sulfonyloxy-1,8-naphthalimide, triphenylsulfonium perfluorooctanesulfonate, triphenylsulfonium perfluorobutanesulfonate, triphenylsulfonium trifluoromethanesulfonate, triphenylsulfonium hexafluorophosphate, triphenylsulfonium hexafluoroantimonate, diphenyliodonium perfluorooctanesulfonate, diphenyliodonium perfluorobutanesulfonate, diphenyliodonium trifluoromethanesulfonate, diphenyliodonium hexafluorophosphate, diphenyliodonium hexafluoroantimonate, n-hydroxynaphthalimide perfluorobutanesulfonate, n-hydroxynaphthalimide trifluoromethanesulfonate and/or a mixture thereof.

FIG. 2 illustrates a process of performing photolithography on the photosensitive compound layer **130**, which includes the resorcinarene containing a perfluorocarbon group.

The process of performing photolithography on the photosensitive compound layer **130**, which includes the resorcinarene containing a perfluorocarbon group, removes part of the photosensitive compound layer **130** overlapping a second region of the photothermal conversion layer **120** while leaving the remaining part of the photosensitive compound layer **130** overlapping a first region of the photothermal conversion layer **120**. The first region is a region where an organic material layer **140B**, which will be described in FIG. 3, is not formed, and the second region is a region where the organic material layer **140B** is formed. The second region corresponds to a pixel region of a target substrate to be transferred (i.e., the substrate of an organic light-emitting display device), which is defined by a pixel-defining layer.

Portions of the photosensitive compound layer **130** remaining in the first region of the photothermal conversion layer **120** may serve as partition walls for defining the second region of the photothermal conversion layer **120**. The portions of the photosensitive compound layer **130** remaining in the first region of the photothermal conversion layer **120** will hereinafter be referred to as first partition wall patterns **130P**, and a region between the first partition wall patterns **130P** will hereinafter be referred to as a first incision pattern **130R**. The second region of the photothermal conversion layer **120** is exposed through the first incision pattern **130R**.

The first partition wall patterns **130P** may be formed by placing a mask (not illustrated) over the photosensitive compound layer **130** to protect the part of the photosensitive compound layer **130** overlapping the first region of the photothermal conversion layer **120**, and selectively exposing it to light and developing the part of the photosensitive compound layer **130** overlapping the second region of the photothermal conversion layer **120** to remove the photosensitive compound layer **130** from the second region of the photothermal conversion layer **120**. The first incision pattern **130R** is formed where the photosensitive compound layer **130** is removed, and corresponds to the second region of the photothermal conversion layer **120**.

FIG. 3 illustrates a process of forming an organic material layer **140U** on the first partition wall patterns **130P** and the organic material layer **140B** on the surface of the second region of the photothermal conversion layer **120**, which is exposed through the first incision pattern **130R**.

The organic material layers **140U** and **140B** may include organic materials for forming organic layers of an organic light-emitting display device. More specifically, the organic material layers **140U** and **140B** may include an organic material for forming an emission layer (EML), an organic material for forming a hole injection layer (HIL), an organic material for forming a hole transport layer (HTL), an organic material for forming an electron injection layer (EIL), and an organic material for forming an electron transport layer (ETL).

The first partition wall patterns **130P** may include a fluorine-based material that is immiscible with an organic material, and, as such, the first partition wall patterns **130P** may not deteriorate the physical properties of the organic material layers **140U** and **140B**.

Conventionally, however, a photosensitive resin composition often causes a reaction with an organic material, and, thus, may cause the deterioration of the physical properties of an organic material layer. As a result, it is not easy to directly pattern an organic material layer when using a photosensitive resin composition. On the other hand, in the method of manufacturing a transfer substrate according to the exemplary embodiments, an organic material layer may be directly patterned using a fluorine-based material that is immiscible with an organic material without deteriorating the physical properties of the organic material layer.

FIG. 4 illustrates a process of removing the first partition wall patterns **130P** by using a lift-off method.

The first partition wall patterns **130P** may be lifted off using a fluorine-based solvent. The fluorine-based solvent may be, but is not limited to, hydrofluoroether (HFE). Since the fluorine-based solvent does not affect the organic material layer **140B**, the fluorine-based solvent, unlike a typical organic solvent, does not deteriorate the physical properties of the organic material layer **140B**. Examples of the HFE may include, but are not limited to, methyl nonafluorobutyl ether, methyl nonafluoroisobutyl ether, an isomeric mixture of methyl nonafluorobutyl ether and methyl nonafluoroisobutyl ether, ethyl nonafluorobutyl ether, ethyl nonafluoroisobutyl ether, an isomeric mixture of ethyl nonafluorobutyl ether and ethyl nonafluoroisobutyl ether, 3-ethoxy-1,1,1,2,3,4,4,5,5,6,6,6-dodecafluoro-2-trifluoromethyl-hexane, 1,1,1,2,2,3,4,5,5,5-decafluoro-3-methoxy-4-trifluoromethyl-pentane, and/or a mixture thereof.

Since the first partition wall patterns **130P** may be removed using the fluorine-based solvent, the organic material layer **140B** may be formed only in the second region of the photothermal conversion layer **120**.

According to one or more exemplary embodiments, a transfer substrate **100** can be formed to have a simple structure in which the transparent substrate **110** and the photothermal conversion layer **120** are stacked. As such, the structure may be free of reflective layer patterns, and, as a result, the time, effort, and cost of manufacturing a transfer substrate may be reduced.

FIGS. 5 and 6 are cross-sectional views of a substrate of an organic light-emitting display at various stages of manufacture, according to one or more exemplary embodiments.

FIG. 5 illustrates a process of applying light **L** to the transfer substrate **100** of FIG. 4 from below the transfer substrate **100** after placing the transfer substrate the transfer substrate **100** to face the target substrate **200**.

Referring to FIG. 5, the target substrate **200** may include a transparent substrate **210** and a pixel-defining layer **220**, which is formed on a bottom surface of the transparent substrate **210**. The target substrate **200** is a target substrate to which the organic material layer **140B** on the transfer substrate **100** is to be transferred. A region between parts of the pixel-defining layer **220** is a pixel region **220H**.

More specifically, the transfer substrate **100** is aligned with the target substrate **200** such that the second region of the photothermal conversion layer **120** can correspond to the pixel region **220H** of the target substrate **200**. Thereafter, the light **L** is applied to the transfer substrate **100** from below the transfer substrate **100**.

The light **L**, which is applied to the transfer substrate **100** from below the transfer substrate **100**, is incident upon the photothermal conversion layer **120** through the transparent substrate **110**, and the photothermal conversion layer **120** converts the light incident thereupon into heat. The heat generated by the photothermal conversion layer **120** is transmitted to the organic material layer **140B**.

FIG. 6 illustrates a process of transferring the organic material layer **140B** onto the pixel region **220H** of the target substrate **200**.

Referring to FIG. 6, the organic material layer **140B** is evaporated by the heat generated by the photothermal conversion layer **120** and is thus transferred onto a target substrate to be transferred, i.e., the target substrate **200**. The organic material layer **140B** is transferred to completely cover the pixel region **220H** of the target substrate **200**. The organic material layer **140B** may also be transferred onto the pixel-defining layer **220**.

The transfer substrate **100** from which the organic material layer **140B** is transferred onto the target substrate **200** has a structure in which the photothermal conversion layer **120** is formed on one surface of the transparent substrate **110**, and can be reused regardless of the type of organic material used or the size of a pixel region of a substrate of an organic light-emitting display device.

FIGS. 7, 8, 9, 10, and 11 are cross-sectional views of a transfer substrate at various stages of manufacture, according to one of more exemplary embodiments.

The process **S11** of FIG. 7 is identical to the process **S1** of FIG. 1 in that a photothermal conversion layer **120** is formed on an entire first surface of a transparent substrate **110**. However, the process **S11** of FIG. 7 differs from the process **S1** of FIG. 1 in that a fluorine-based resin layer **150** is formed on an entire first surface of the photothermal conversion layer **120** and a photosensitive resin composition layer **160** is formed on an entire first surface of the fluorine-based resin layer **150**.

The fluorine-based resin layer **150** is formed of a fluorine-based resin. For example, the fluorine-based resin may be, but not limited to, polytetrafluoroethylene (PTFE), poly(perfluoroalkyl acrylate (PFA), polychlorotrifluoroethylene (PCTFE), fluorinated ethylenepropylene resin (FEP), polychloro-trifluoroethylene (PCFE), polyvinylidene fluoride (PVDF), and/or a copolymer thereof.

The photosensitive resin composition layer **160** may be formed of a photosensitive resin composition. For example, the photosensitive resin composition may encompass any kind of photosensitive resin compositions that may be commonly use in photolithography.

FIG. 8 illustrates a process of performing photolithography on the photosensitive resin composition layer **160**. Referring to FIG. 8, photosensitive resin composition layer patterns may be formed by placing a mask (not illustrated) over the photosensitive resin composition layer **160** to

protect part of the photosensitive resin composition layer **160** overlapping a first region of the photothermal conversion layer **120**, and selectively exposing to light and developing the remaining part of the photosensitive resin composition layer **160** overlapping a second region of the photothermal conversion layer **120**.

The photosensitive resin composition layer patterns may include second partition wall patterns **160P** and a second incision pattern **160R**, and the second incision pattern **160R** may be disposed between the second partition wall patterns **160P**.

The process **S12** of FIG. 8 differs from the process **S2** of FIG. 2 in that photosensitive resin composition layer patterns, instead of photosensitive compound layer patterns containing a resorcinarene containing a perfluorocarbon group, are formed by photolithography.

FIG. 9 illustrates a process of performing photolithography on the fluorine-based resin layer **150**. Referring to FIG. 9, the fluorine-based resin layer **150** may be patterned by using the second partition wall patterns **160P** as a mask, thereby obtaining fluorine-based resin layer patterns. The fluorine-based resin layer patterns may include third partition wall patterns **150P** and a third incision pattern **150R**, and the third incision pattern **150R** may be disposed between the third partition wall patterns **150P**.

The process **S13** of FIG. 9 differs from the process **S2** of FIG. 2 in that the surface of the second region of the photothermal conversion layer **120** is exposed through both the second incision pattern **160R** and the third incision pattern **150R**, instead of through the first incision pattern **130R** only.

The process **S14** of FIG. 10 is identical to the process **S3** of FIG. 3 in that the organic material layer **140B** is formed on the entire first surface of the photothermal conversion layer **120**. However, the process **S14** of FIG. 10 differs from the process **S3** of FIG. 3 in that an organic material layer **140U** is formed on the second partition wall patterns **160P**.

The process **S15** of FIG. 11 differs from the process **S4** of FIG. 4 in that the transfer substrate **100** is formed by lifting off both the second partition wall patterns **160P** and the third partition wall patterns **150**, instead of lifting off only the first partition wall patterns **130P**, with the use of a fluorine-based solvent.

FIGS. 12, 13, 14, and 15 are cross-sectional views of a transfer substrate at various stages of manufacture, according to one or more exemplary embodiments.

The process **S'1** of FIG. 12 is identical to the process **S1** of FIG. 1 in that a photothermal conversion layer **120** is formed on an entire first surface of a transparent substrate **110** and a photosensitive compound layer **130**, which includes a resorcinarene containing a perfluorocarbon group, is formed on an entire first surface of the photothermal conversion layer **120**.

The processes **S'2** and **S'3** of FIGS. 13 and 14 differ from the process **S2** of FIG. 2 in that first partition wall patterns **130P** are formed overlapping the surface of a third region of the photothermal conversion layer **120**, which is provided inside a second region of the photothermal conversion layer **120**, whereas in the process **S2** of FIG. 2, only the incision pattern **130R** is formed in the second region of the photothermal conversion layer **120**.

First incision patterns **130R**, which are isolated from each other, are arranged between the first partition wall patterns **130P** formed in the second region of the photothermal conversion layer **120**, and an organic material layer **140B** is formed on parts of the photothermal conversion layer **120** exposed between the first incision patterns **130R**.

11

The process S'4 of FIG. 15 is identical to the process S4 of FIG. 4 in that the first partition wall patterns 130P are lifted off by using a fluorine-based solvent. However, the process S'4 of FIG. 15 differs from the process S4 of FIG. 4 in that a plurality of organic material layers 140B are formed in the second region of the photothermal conversion layer isolated from one another, whereas in the process S4 of FIG. 4, a single continuous organic material layer 140B is formed.

FIGS. 16 and 17 are cross-sectional views of a substrate of an organic light-emitting display device at various stages of manufacture, according to one or more exemplary embodiments.

The process S'5 of FIG. 16 is identical to the process S5 of FIG. 5 in that the transfer substrate 100 is aligned with a target substrate to be transferred, i.e., a target substrate 200 of an organic light-emitting display device, such that the second region of the photothermal conversion layer 120 can correspond to a pixel region 220H of the target substrate 200 and light L is applied to the transfer substrate 100 from below the transfer substrate 100.

Referring to FIG. 16, the organic material layers 140B are formed in the second region of the photothermal conversion layer 120 isolated from one another. Since the organic material layers 140B are isolated from another, the amount by which the organic material layers 140B is evaporated onto a target substrate may be adjusted. Accordingly, the pattern profile of an organic layer formed on the target substrate may have a surface with improved flatness.

FIG. 17 illustrates a process of evaporating the organic material layers 140B with the use of heat generated by the photothermal conversion layer 120 to deposit an organic material layer 140B in the pixel region 220H of the target substrate 200.

Referring to FIG. 17, the organic material layer 140B may cover the entire pixel region 220H of the target substrate 200. The organic material layers 140B of FIG. 16, which are isolated from one another, are evaporated and diffused into a single organic material layer 140B that covers the entire pixel region 220H, as illustrated in FIG. 17. The target substrate 200 of FIG. 17 differs from the target substrate 200 of FIG. 6 in that the organic material layer 140B may have a pattern profile with improved flatness, as mentioned above.

FIGS. 18, 19, 20, 21, and 22 are cross-sectional views of a transfer substrate at various stages of manufacture, according to one or more exemplary embodiments.

The processes S'11, S'12, S'13, S'14, and S'15 of FIGS. 18, 19, 20, 21, and 22 differ from the processes S'1, S'2, S'3, S'4, and S'5 of FIGS. 12, 13, 14, and 15 in that a plurality of second partition wall patterns 160P and a plurality of third partition wall patterns 150P are formed in a second region of a photothermal conversion layer 120, and a plurality of organic material layers 140B are formed to be isolated from one another.

Although certain exemplary embodiments and implementations have been described herein, other embodiments and modifications will be apparent from this description. Accordingly, the inventive concept is not limited to such embodiments, but rather to the broader scope of the presented claims and various obvious modifications and equivalent arrangements.

What is claimed is:

1. A method of manufacturing a substrate of an organic light-emitting display device, the method comprising:

forming, on a first surface of a transparent substrate, a photothermal conversion layer configured to convert incident light into thermal energy;

12

forming a fluorine-based resin layer on the photothermal conversion layer, the fluorine-based resin layer comprising a fluorine-based resin;

forming first partition walls on the first surface in a first region of the photothermal conversion layer, the first partition walls comprising a photosensitive polymer compound;

forming second partition walls using the first partition walls as a mask, the second partition walls comprising the fluorine-based resin;

forming an organic material layer on the first surface of a second region of the photothermal conversion layer, the second region being defined by the first partition walls and the second partition walls, wherein the organic material layer is in contact with the second partition walls and the photothermal conversion layer;

removing the first partition walls and the second partition walls;

placing a target substrate over the organic material layer; and

applying light to a second surface of the transparent substrate, the second surface being opposite the first surface of the transparent substrate.

2. The method of claim 1, further comprising:

forming first partition walls on the first surface in a third region of the photothermal conversion layer, the first partition walls comprising the photosensitive polymer compound, the third region being inside the second region.

3. The method of claim 2, further comprising:

forming second partition walls in the third region utilizing the first partition walls in the third region as a mask, the second partition walls in the third region comprising the fluorine-based resin.

4. The method of claim 1, wherein the fluorine-based resin is at least one selected from the group consisting of polytetrafluoroethylene (PTFE), poly(perfluoroalkyl acrylate) (PEA), polychlorotrifluoroethylene (PCTFE), fluorinated ethylenepropylene resin (FEP), polychlorotrifluoroethylene (PCFE), polyvinylidene fluoride (PVDF), and a copolymer thereof.

5. The method of claim 1, wherein a fluorine-based solvent is utilized to remove the first partition walls and the second partition walls.

6. The method of claim 5, wherein the fluorine-based solvent comprises at least one hydrofluoroether (HFE) selected from the group consisting of methyl nonafluorobutyl ether, methyl nonafluoroisobutyl ether, an isomeric mixture of methyl nonafluorobutyl ether and methyl nonafluoroisobutyl ether, ethyl nonafluorobutyl ether, ethyl nonafluoroisobutyl ether, an isomeric mixture of ethyl nonafluorobutyl ether and ethyl nonafluoroisobutyl ether, 3-ethoxy-1,1,1,2,3,4,4,5,5,6,6,6-dodecafluoro-2-trifluoromethyl-hexane, and 1,1,1,2,2,3,3,4,5,5,5-decafluoro-3-methoxy-4-trifluoromethyl-pentane.

7. The method of claim 1, wherein the photothermal conversion layer is formed on an entire surface of the transparent substrate.

8. The method of claim 1, wherein the fluorine-based resin layer is formed on an entire surface of the photothermal conversion layer.

9. The method of claim 1, wherein the first and second partition walls are removed utilizing a lift-off method.

专利名称(译)	制造有机发光显示装置的基板的方法		
公开(公告)号	US9673396	公开(公告)日	2017-06-06
申请号	US15/082726	申请日	2016-03-28
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KWON YOUNG GIL		
发明人	KWON, YOUNG GIL		
IPC分类号	H01L51/00 H01L27/32 H01L51/56 H01L51/50		
CPC分类号	H01L51/0013 H01L27/3246 H01L27/3283 H01L51/56 H01L51/5012 H01L51/5056 H01L51/5072 H01L51/5088 H01L51/5092 H01L2227/323 G03F7/0045 G03F7/0046 G03F7/16 G03F7/2002 G03F7/26 H01L51/0016		
审查员(译)	OH , JAEHWAN		
优先权	1020140141764 2014-10-20 KR		
其他公开文献	US20160211451A1		
外部链接	Espacenet USPTO		

摘要(译)

一种制造有机发光显示装置的基板的方法，该方法包括：在透明基板的第一表面上形成光热转换层，该光热转换层构造成为将入射光转换成热能；在光热转换层的第一区域中的第一表面上形成分隔壁，分隔壁包括含有间苯二酚的光敏化合物，含有全氟化碳基团的间苯二酚；在光热转换层的第二区域中的第一表面上形成有机材料层，第二区域由分隔壁限定；拆除隔墙；将目标基板放置在有机材料层上；并且，将光照射到透明基板的第二表面，第二表面与透明基板的第一表面相对。

