



US 20140117338A1

(19) **United States**

(12) **Patent Application Publication**

**Cho et al.**

(10) **Pub. No.: US 2014/0117338 A1**

(43) **Pub. Date: May 1, 2014**

(54) **ORGANIC LIGHT EMITTING DISPLAY DEVICE**

**Publication Classification**

(71) Applicant: **LG DISPLAY CO., LTD.**, Seoul (KR)

(51) **Int. Cl.**  
**H01L 51/52** (2006.01)

(72) Inventors: **Gwi-Jeong Cho**, Daegu (KR); **Jae-Man Lee**, Seoul (KR); **Jeong-Haeng Heo**, Paju-si (KR); **So-Yeon Ahn**, Seoul (KR); **Tae-Shick Kim**, Yongin-si (KR); **Hee-Dong Choi**, Uiwang-si (KR)

(52) **U.S. Cl.**  
CPC ..... **H01L 51/52** (2013.01)  
USPC ..... **257/40; 257/88**

(73) Assignee: **LG DISPLAY CO., LTD.**, Seoul (KR)

(57) **ABSTRACT**


(21) Appl. No.: **14/062,128**

An organic light emitting display device with improved lifespan is disclosed. The organic light emitting display device includes first and second electrodes facing each other on a substrate, at least two light emitting units formed between the first and second electrodes, an N-type charge generation layer and a P-type charge generation layer sequentially stacked between the light emitting units, and at least one auxiliary charge generation layer formed between at least any one of the P-type charge generation layer and the N-type charge generation layer and an emitting layer of the light emitting unit disposed on an upper or lower portion of the at least any one thereof and generating electrons and holes supplied to the emitting layer of the light emitting unit.


(22) Filed: **Oct. 24, 2013**

(30) **Foreign Application Priority Data**


Oct. 31, 2012 (KR) ..... 10-2012-0122577  
Jul. 31, 2013 (KR) ..... 10-2013-0091181




**FIG.1**




**FIG.2**




**FIG.3A**




**FIG.3B**




**FIG.3C**




**FIG.3D**




### FIG.4




### FIG.5



### FIG.6A



### FIG.6B



**FIG.7**




FIG.8







FIG.9




**FIG.10**



**FIG.11A**



**FIG.11B**



**FIG.12**




FIG.13





FIG.14



## ORGANIC LIGHT EMITTING DISPLAY DEVICE

[0001] This application claims the benefit of priority of Korean Patent Applications No. 10-2012-0122577, filed on Oct. 31, 2012 and No. 10-2013-0091181, filed on Jul. 31, 2013, which is hereby incorporated by reference as if fully set forth herein.

### BACKGROUND

[0002] 1. Field of the Disclosure

[0003] The present disclosure relates to an organic light emitting display device with improved lifespan.

[0004] 2. Discussion of the Related Art

[0005] In line with recent information era, display field technology, which visually displays electrical information signals, has rapidly developed. To meet such development, various flat panel display devices with excellent performance, such as ultra-thin in thickness, lightweight, and low power consumption, have been developed.

[0006] Examples of flat panel display devices include a liquid crystal display (LCD) device, a plasma display panel (PDP) device, a field emission display (FED) device, an organic light emitting device (OLED), etc.

[0007] In particular, OLEDs, which are self-emissive devices, have faster response time, higher luminous efficiency, higher luminance and wider viewing angles than other flat panel display devices.

[0008] However, OLEDs have shorter lifespan than other flat panel display devices. Therefore, there is a need to improve OLED lifespan.

### SUMMARY

[0009] An organic light emitting display device includes first and second electrodes facing each other on a substrate, at least two light emitting units formed between the first and second electrodes, an N-type charge generation layer and a P-type charge generation layer sequentially stacked between the light emitting units, and at least one auxiliary charge generation layer formed between at least any one of the P-type charge generation layer and the N-type charge generation layer and an emitting layer of the light emitting unit disposed on an upper or lower portion of the at least any one thereof and generating electrons and holes supplied to the emitting layer of the light emitting unit.

[0010] It is to be understood that both the foregoing general description and the following detailed description of the present invention are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

### BRIEF DESCRIPTION OF THE DRAWINGS

[0011] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the invention and together with the description serve to explain the principle of the invention. In the drawings:

[0012] FIG. 1 is a sectional view of an organic light emitting display device according to a first embodiment of the present invention;

[0013] FIG. 2 is a band diagram illustrating the organic light emitting display device illustrated in FIG. 1;

[0014] FIGS. 3A to 3D are sectional views illustrating other examples of an auxiliary charge generation layer of the organic light emitting display device according to the first embodiment of the present invention;

[0015] FIG. 4 is a graph for explaining lifespan of a conventional organic light emitting display device and lifespan of the organic light emitting display device according to the first embodiment of the present invention;

[0016] FIG. 5 is a graph for explaining time-voltage variation of each of the conventional organic light emitting display device and the organic light emitting display device according to the first embodiment of the present invention;

[0017] FIGS. 6A and 6B are graphs for explaining voltage-current density of each of the conventional organic light emitting display device and the organic light emitting display device according to the first embodiment of the present invention;

[0018] FIG. 7 is a sectional view of an organic light emitting display device according to a second embodiment of the present invention;

[0019] FIG. 8 is a band diagram illustrating the organic light emitting display device illustrated in FIG. 7;

[0020] FIG. 9 is a graph for explaining lifespan of the conventional organic light emitting display device and lifespan of the organic light emitting display device according to the second embodiment of the present invention;

[0021] FIG. 10 is a graph for explaining time-voltage variation of the conventional organic light emitting display device and the organic light emitting display device according to the second embodiment of the present invention;

[0022] FIGS. 11A and 11B are graphs for explaining voltage-current density-luminance characteristics of the conventional organic light emitting display device and the organic light emitting display device according to the second embodiment of the present invention;

[0023] FIG. 12 is a sectional view of an organic light emitting display device according to a third embodiment of the present invention;

[0024] FIG. 13 is a band diagram illustrating the organic light emitting display device illustrated in FIG. 12; and

[0025] FIG. 14 is a sectional view of the organic light emitting display device according to one of the first, second and third embodiments of the present invention having color filters.

### DETAILED DESCRIPTION OF THE EXEMPLARY EMBODIMENTS

[0026] Reference will now be made in detail to the preferred embodiments of the present invention, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers will be used throughout the drawings to refer to the same or like parts.

[0027] Hereinafter, embodiments of the present invention will be described in detail with reference to the accompanying drawings.

[0028] FIG. 1 is a sectional view illustrating an organic light emitting display device according to a first embodiment of the present invention.

[0029] Referring to FIG. 1, the organic light emitting display device includes first and second electrodes 102 and 104 facing each other, first and second light emitting units 110 and 120 that are disposed between the first and second electrodes 102 and 104, and a charge generation layer 130 disposed between the first and second light emitting units 110 and 120.

In the present embodiment, two light emitting units are described by way of example, although three or more light emitting units may be formed.

[0030] Any one of the first and second electrodes **102** and **104** is formed as a transparent electrode. When the second electrode **104** is an opaque electrode, the organic light emitting display device is embodied as a bottom emission type that emits light in a bottom direction. When the second electrode **104** is a transparent electrode and the first electrode **102** is an opaque electrode, the organic light emitting display device is embodied as a top emission type that emits light in a top direction. When both the first and second electrodes **102** and **104** are transparent electrodes, the organic light emitting display device is embodied as a dual emission type that emits light in top and bottom directions.

[0031] The transparent electrode may be formed of indium tin oxide (ITO), indium zinc oxide (IZO), or the like and the opaque electrode may be formed of aluminum (Al), gold (Au), molybdenum (Mo), chromium (Cr), copper (Cu), LiF, or the like, or a multi-layer structure using these materials may be formed.

[0032] In the first embodiment of the present invention, a case in which the first electrode **102** as an anode is formed as a transparent electrode and the second electrode **104** as a cathode is formed as an opaque electrode will be described by way of example.

[0033] The first light emitting unit **110** is formed between the first electrode **102** and an N-type charge generation layer **132**. The first light emitting unit **110** includes a hole injection layer **112**, at least one first hole transport layer **114**, a first emitting layer **116**, and a first electron transport layer **118** that are sequentially formed on the first electrode **102**. The first hole transport layer **114** supplies holes from the first electrode **102** to the first emitting layer **116**, the first electron transport layer **118** supplies electrons from the N-type charge generation layer **132** to the first emitting layer **116**, and the holes supplied via the first hole transport layer **114** and the electrons supplied via the first electron transport layer **118** are recombined in the first emitting layer **116** and thus light is generated.

[0034] The second light emitting unit **120** is formed between the second electrode **104** and a P-type charge generation layer **134**. The second light emitting unit **120** includes a second hole transport layer **124a**, an auxiliary charge generation layer **122**, a third hole transport layer **124b**, a second emitting layer **126**, and a second electron transport layer **128** that are sequentially formed on the P-type charge generation layer **134**.

[0035] The second and third hole transport layers **124a** and **124b** supply holes from the P-type charge generation layer **134** to the second emitting layer **126**, the second electron transport layer **128** supplies electrons from the second electrode **104** to the second emitting layer **126**, and the holes supplied via the second and third hole transport layers **124a** and **124b** and the electrons supplied via the second electron transport layer **128** are recombined in the second emitting layer **126** and thus light is generated.

[0036] In this regard, the first emitting layer **116** includes a fluorescent blue dopant and host to emit blue light and the second emitting layer **126** includes a phosphorescent yellow-green dopant and host to emit orange light, which enables emission of white light. In addition, white light may be generated using other fluorescent dopants and phosphorescent dopants.

[0037] The charge generation layer **130** includes the N-type charge generation layer **132** and the P-type charge generation layer **134** that are sequentially stacked.

[0038] The N-type charge generation layer **132** is disposed closer to the first electrode **102** than the P-type charge generation layer **134**. The N-type charge generation layer **132** attracts n-type charges (i.e., electrons) separated from an interface between the P-type charge generation layer **134** and the second hole transport layer **124a** and an interface between the auxiliary charge generation layer **122** and the third hole transport layer **124a**. The N-type charge generation layer **132** is formed by doping alkali metal particles with an organic material.

[0039] The P-type charge generation layer **134** is disposed closer to the second electrode **104** than the N-type charge generation layer **132**. As illustrated in FIG. 2, n-type charges, i.e., electrons, and p-type charges, i.e., holes, are generated and separated at an interface between the P-type charge generation layer **134** and the second hole transport layer **124a** and an interface between the auxiliary charge generation layer **122** and the third hole transport layer **124a**.

[0040] The separated electrons move to the first light emitting unit **110** via the N-type charge generation layer **132** and combine with holes moved from the first electrode **102** in the first emitting layer **116** of the first light emitting unit **110** to form excitons, thereby releasing energy and emitting visible light.

[0041] The separated holes move to the second light emitting unit **120** and combine with electrons moved from the second electrode **104** in the second emitting layer **126** to form excitons, thereby releasing energy and emitting visible light.


[0042] The auxiliary charge generation layer **122** is formed between the second and third hole transport layers **124a** and **124b**. The auxiliary charge generation layer **122** generates holes and electrons at an interface between the auxiliary charge generation layer **122** and the third hole transport layer **124b** of the second light emitting unit **120**. In this regard, the auxiliary charge generation layer **122** is formed farther from the N-type charge generation layer **132** than the P-type charge generation layer **134**. Accordingly, the auxiliary charge generation layer **122** may more reduce impact due to cations dissociated from alkali metal particles constituting the N-type charge generation layer **132** than the P-type charge generation layer **134**.

[0043] In particular, when the alkali metal particles constituting the N-type charge generation layer **132** are dissociated into cations and diffuse into the P-type charge generation layer **134** and the second hole transport layer **124a** of the second light emitting unit **120**, the P-type charge generation layer **134** and the second hole transport layer **124a** are damaged and thus are unable to do function appropriately. In this case, the auxiliary charge generation layer **122** generates holes and electrons at an interface between the auxiliary charge generation layer **122** and the third hole transport layer **124b** of the second light emitting unit **120** and supplies the holes to the second emitting layer **126** of the second light emitting unit **120**. Accordingly, transfer of holes to the second emitting layer **126** smoothly occurs and thus the ratio of electrons to holes is uniform, which results in sufficient utilization of lifespan of the second emitting layer **126**.


[0044] The auxiliary charge generation layer **122** is formed of the same material as or a different material from that of the P-type charge generation layer **134**.

[0045] For example, the auxiliary charge generation layer 122 is formed of an organic material such as 1,4,5,8,9,11-hexaazatriphenylenehexacarbonitrile (HAT-CN). In this regard, HAT-CN has a lower deposition temperature and higher transmissivity than MoO<sub>3</sub>.


[0046] In addition, the auxiliary charge generation layer 122 is formed using a host capable of transporting holes and 1 to 99 wt % of a P-type dopant in combination. In this regard, the amount of the P-type dopant may be in a range of 1 wt % to 30 wt %. The host of the auxiliary charge generation layer 122 is formed of a material that is the same as or different from that of at least one of the second and third hole transport layers 124a and 124b. For example, the host of the auxiliary charge generation layer 122 is formed of at least one of NPB, CBP, NPD, TPD, TBA, and TTA, and the P-type dopant thereof is formed of a material having a lowest unoccupied molecular orbital (LUMO) energy level of -5 eV or less and a molecular weight of 76 or greater. In particular, the P-type dopant is formed of a TNAP derivative (e.g., F4TNAP derivative) represented by Formula 1 below or an organic compound represented by any one of Formulas 2 to 6 below. In Formula 1, R1 to R6 may be substituted or may not be substituted with fluorine or a cyano group.




&lt;Formula 1&gt;




&lt;Formula 2&gt;




&lt;Formula 3&gt;



&lt;Formula 4&gt;



&lt;Formula 5&gt;



&lt;Formula 6&gt;

[0047] In this regard, when the auxiliary charge generation layer 122 and the P-type charge generation layer 134 are formed of a host capable of transporting holes and a P-type dopant, the P-type dopant doped in the P-type charge generation layer 134 fills pores of the N-type charge generation layer 132 having a plate structure, whereby surface uniformity may be improved.

[0048] Although FIG. 1 illustrates the auxiliary charge generation layer 122 as having a single-layer structure, two or more auxiliary charge generation layers may be formed. For example, as illustrated in FIGS. 3A to 3D, first and second auxiliary charge generation layers 122a and 122b may be formed between the second emitting layer 126 of the second light emitting unit 120 and the P-type charge generation layer 134.

[0049] In particular, the first auxiliary charge generation layer 122a generates holes and electrons at an interface between the first auxiliary charge generation layer 122a and the third hole transport layer 124b of the second light emitting

unit **120**, and the second auxiliary charge generation layer **122b** generates holes and electrons at an interface between the second auxiliary charge generation layer **122b** and a fourth hole transport layer **124c**. In this regard, the first and second auxiliary charge generation layers **122a** and **122b** are formed farther from the N-type charge generation layer **132** than the P-type charge generation layer **134**. Accordingly, the first and second auxiliary charge generation layers **122a** and **122b** may more reduce impact due to cations dissociated from the alkali metal particles constituting the N-type charge generation layer **132** than the P-type charge generation layer **134**.

[0050] The first and second auxiliary charge generation layers **122a** and **122b** may be formed of the same material or different materials.

[0051] When the first and second auxiliary charge generation layers **122a** and **122b** are formed of the same material, each of the first and second auxiliary charge generation layers **122a** and **122b** may be independently formed of HAT-CN as illustrated in FIG. 3A or may be independently formed using a host capable of transporting holes and a P-type dopant of any one of Formulas 1 to 6 in combination as illustrated in FIG. 3B.

[0052] In particular, in a structure illustrated in FIG. 3B, host materials of the first and second auxiliary charge generation layers **122a** and **122b** may be the same or different from those of the second, third and fourth hole transport layers **122a**, **122b** and **122c**, and host materials of the first and second auxiliary charge generation layers **122a** and **122b** may be the same or different from each other. In addition, the first and second auxiliary charge generation layers **122a** and **122b** may be doped with the P-type dopant at the same or different doping concentration.

[0053] When the first and second auxiliary charge generation layers **122a** and **122b** are formed of different materials, as illustrated in FIG. 3C, the first auxiliary charge generation layer **122a** is formed of HAT-CN and the second auxiliary charge generation layer **122b** is formed of a host capable of transporting holes and a P-type dopant of any one of Formulas 1 to 6. In another embodiment, as illustrated in FIG. 3D, the first auxiliary charge generation layer **122a** is formed of a host capable of transporting holes and a P-type dopant of any one of Formulas 1 to 6 and the second auxiliary charge generation layer **122b** is formed of HAT-CN.

[0054] The first and second auxiliary charge generation layers **122a** and **122b** have a smaller thickness than that of the P-type charge generation layer **134**. In particular, a sum of the thicknesses of the first and second auxiliary charge generation layers **122a** and **122b** is smaller than the thickness of the P-type charge generation layer **134** and thus an overall thickness of the organic light emitting display device is not increased. The sum of the thicknesses of the first and second auxiliary charge generation layers **122a** and **122b** is the same as the thickness of the auxiliary charge generation layer **122** illustrated in FIG. 1.

[0055] Meanwhile, when four or more auxiliary charge generation layers are formed, the overall thickness of the organic light emitting display device increases, which makes it difficult to fabricate an ultra-thin organic light emitting display device. When the auxiliary charge generation layer **122** having a four-layered structure and the hole transport layer **124** having a four-layered structure are formed to a small thickness so as not to cause change in the overall thickness of the organic light emitting display device, working efficiencies of the auxiliary charge generation layer **122** and

the hole transport layer **124** are reduced. Thus, the auxiliary charge generation layer **122** may be formed as three or fewer layers in the organic light emitting display device.

[0056] Table 1 shows characteristics of a conventional white organic light emitting device (OLED) and a white OLED according to the first embodiment of the present invention.

TABLE 1

Conditions	T95 (hour)	Volt (V)	10 mA/cm <sup>2</sup>			
			Cd/A	CIE <sub>x</sub>	CIE <sub>y</sub>	QE (%)
Conventional	3,426	7.3	80.3	0.319	0.331	33.2
Structure of FIG. 1	4,645 to 7,000	7.3	79.3	0.315	0.317	32.6
Structures of FIGS. 3A to 3D	4,526 to 7,000	7.0	78.3	0.315	0.316	32.7

[0057] In Table 1, the conventional structure does not include an auxiliary charge generation layer, the structure according to the first embodiment of the present invention includes the P-type charge generation layer **134** having a thickness of about 100 Å, the second hole transport layer **124a** having a thickness of about 190 Å, the auxiliary charge generation layer **122** having a thickness of about 50 Å, and the third hole transport layer **124b** having a thickness of about 150 Å, and the structures including other examples of auxiliary charge generation layers according to the present invention include the P-type charge generation layer **134** having a thickness of about 100 Å, the second hole transport layer **124a** having a thickness of about 190 Å, the first auxiliary charge generation layer **122a** having a thickness of about 50 Å, the third hole transport layer **124b** having a thickness of about 75 Å, the second auxiliary charge generation layer **122b** having a thickness of about 50 Å, and the fourth hole transport layer **124c** having a thickness of about 75 Å.

[0058] In Table 1, T95 denotes the time required for the white OLED to reach 95% of total lifespan. As shown in Table 1 and FIG. 4, a conventional white OLED has a T95 of 3,426 hours, while the white OLED according to the present invention has a T95 between 4,526 and 7,000 hours. In addition, as illustrated in FIG. 5, the organic light emitting display device according to the present invention has lower voltage variation over time than a conventional organic light emitting display device and thus may stably supply current. That is, it can be confirmed that the white OLED according to the present invention has longer lifespan than a conventional white OLED.

[0059] As illustrated in FIGS. 6A and 6B, it can be confirmed that the organic light emitting display device according to the present invention has higher current density according to voltage than a conventional organic light emitting display device and thus driving voltage for the same current density is low. In particular, from the results shown in Table 1, it can be confirmed that a driving voltage of the structure including the first and second auxiliary charge generation layers **122a** and **122b** is lower than that of the structure including the auxiliary charge generation layer **122**.

[0060] That is, as shown in Table 1 and FIGS. 4 to 6B, it can be confirmed that the organic light emitting display device according to the present invention has higher driving voltage (V), higher efficiency (cd/A), improved color coordinates

( $CIE_x$ ,  $CIE_y$ ), and higher quantum efficiency (QE), when compared to a conventional white organic light emitting display device.

[0061] FIG. 7 is a sectional view of an organic light emitting display device according to a second embodiment of the present invention.

[0062] The organic light emitting display device illustrated in FIG. 7 includes the same elements as those of the organic light emitting display device illustrated in FIG. 1, except that an auxiliary charge generation layer 222 is formed between electron transport layers 118a and 118b. Thus, a detailed description of the same elements will be omitted.

[0063] As illustrated in FIG. 8, the auxiliary charge generation layer 222 generates and separates n-type charges, i.e., electrons, and p-type charges, i.e., holes, at an interface between the auxiliary charge generation layer 222 and the electron transport layer 118a and an interface between the auxiliary charge generation layer 222 and the electron transport layer 118b. Accordingly, the auxiliary charge generation layer 222 may prevent ionization of an alkali metal constituting the N-type charge generation layer 132.

[0064] In particular, when the alkali metal constituting the N-type charge generation layer 132 is ionized over time, the N-type charge generation layer 132 cannot serve function appropriately. In this case, the auxiliary charge generation layer 222 generates holes and electrons at interfaces between each of the electron transport layers 118a and 118b and the auxiliary charge generation layer 222 and supplies the electrons to the first emitting layer 116 of the first light emitting unit 110. When the electrons are smoothly transferred to the first emitting layer 116, the amounts of holes and electrons become uniform and thus increase in voltage while the organic light emitting display device operates may be suppressed, and resistance thereof is reduced, which results in improved lifespan.

[0065] The auxiliary charge generation layer 222 is formed of a material that is the same or different from that of the N-type charge generation layer 132. For example, each of the auxiliary charge generation layer 222 and the N-type charge generation layer 132 is formed of a metal and an organic compound.

[0066] In this regard, the organic compound has a fused aromatic ring with 15 to 40 carbon atoms, a substituent of which has at least one selected from among N, S, and O. In particular, the organic compound has a LUMO energy level of  $-2.0$  eV or less and a bandgap of  $2.5$  eV or more. Preferably, the organic compound has a LUMO energy level between  $-3.0$  and  $-2.0$  eV and a bandgap between  $2.5$  and  $3.5$  eV. For example, the organic compound is formed of tris(8-hydroxyquinoline)aluminum ( $Alq_3$ ), 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), 2,2'-[1,1'-biphenyl]-4,4'-diylbis[4,6-(p-tolyl)-1,3,5-triazine] (TRAZ), or a combination thereof.

[0067] As the metal, an alkali metal or an alkali earth metal is used. For example, Ca, Li, Mg, Cs, or the like may be used as the metal.

[0068] In this regard, a doping amount of the alkali metal or the alkali earth metal is 1% to 10% based on the volume of the N-type charge generation layer 132.

[0069] In addition, the auxiliary charge generation layer 222 has the same thickness as that of the N-type charge generation layer 132 or has a smaller thickness than that of the N-type charge generation layer 132. When the auxiliary charge generation layer 222 has a greater thickness than that

of the N-type charge generation layer 132, the amount of the metal included in the auxiliary charge generation layer 222 increases and thus ion diffusion of the metal increases, which results in damage to the emitting layer 116. When the auxiliary charge generation layer 222 is formed to a very small thickness so as not to cause change in the overall thickness of the organic light emitting display device, working efficiency of the auxiliary charge generation layer 222 is reduced, which results in decreased lifespan thereof.

[0070] Table 2 shows characteristics of a conventional white organic light emitting display device and a white OLED according to the second embodiment of the present invention.

TABLE 2

Conditions	T80 (hrs) @50 mA/Cm <sup>2</sup>	$\Delta V$ @T95
Conventional	330	0.2
Structure including a single auxiliary charge generation layer	390	0.1
Structure including two auxiliary charge generation layers	420	0.1

[0071] In Table 2, T80 denotes the time required for the white OLED to reach approximately 80% of total lifespan, and T95 denotes the time required for the white OLED to reach approximately 95% of total lifespan. As shown in Table 2 and FIG. 9, the conventional white OLED has a T80 of about 330 hours, while the white OLED according to the second embodiment including a single auxiliary charge generation layer has a T80 of about 390 hours and the white OLED according to the second embodiment including two auxiliary charge generation layers has a T80 of about 420 hours. In addition, as shown in Table 2 and FIG. 10, the white organic light emitting display device according to the second embodiment of the present invention has lower voltage variation over time than the conventional organic light emitting display device and thus may stably supply current, which results in improved lifespan.

[0072] In addition, as illustrated in FIG. 11A, the organic light emitting display device according to the present invention has similar current efficiency vs. luminance to that of the conventional organic light emitting display device, while, as illustrated in FIG. 11B, the organic light emitting display device according to the second embodiment of the present invention has higher current density according to voltage than the conventional organic light emitting display device and thus driving voltage for the same current density of the organic light emitting display device according to the second embodiment of the present invention is lower than that of the conventional organic light emitting display device.

[0073] FIG. 12 is a sectional view of an organic light emitting display device according to a third embodiment of the present invention.

[0074] The organic light emitting display device illustrated in FIG. 12 includes the same elements as those of the organic light emitting display device illustrated in FIG. 1, except that auxiliary charge generation layers 322 and 324 are formed between first and second electron transport layers 118a and 118b and between second and third hole transport layers 124a and 124b, respectively. Thus, a detailed description of the same elements will be omitted.

[0075] Auxiliary charge generation layers illustrated in FIG. 12 consist of a first auxiliary charge generation layer 322 formed between the first and second electron transport layers 118a and 118b and a second auxiliary charge generation layer 324 formed between the second and third hole transport layers 124a and 124b.

[0076] As illustrated in FIG. 13, the first auxiliary charge generation layer 322 generates holes and electrons at interfaces between the first auxiliary charge generation layer 322 and each of the first and second electron transport layers 118a and 118b and supplies the electrons to the first emitting layer 116 of the first light emitting unit 110. When the electrons are smoothly transferred to the first emitting layer 116, the amounts of holes and electrons become uniform and thus increase in voltage while the organic light emitting display device operates may be suppressed, and resistance thereof is reduced, which results in improved lifespan.

[0077] The first auxiliary charge generation layer 322 is formed of the same or different material from that of the N-type charge generation layer 132. For example, the first auxiliary charge generation layer 322 is formed of the same material as that of the auxiliary charge generation layer 222 illustrated in the second embodiment of the present invention. In addition, the first auxiliary charge generation layer 322 has the same thickness as that of the N-type charge generation layer 132 or has a smaller thickness than that of the N-type charge generation layer 132 so that the overall thickness of the organic light emitting display device does not increase.

[0078] The second auxiliary charge generation layer 324 is formed between the second and third hole transport layers 124a and 124b. As illustrated in FIG. 13, the second auxiliary charge generation layer 324 generates holes and electrons at an interface between the second auxiliary charge generation layer 324 and the third hole transport layer 124b of the second light emitting unit 120 and supplies the holes to the second emitting layer 126 of the second light emitting unit 120. Accordingly, the holes are smoothly transferred to the second emitting layer 126 and thus the ratio of the electrons to the holes is uniform, which enables lifespan of the second emitting layer 126 to be fully utilized.

[0079] The second auxiliary charge generation layer 324 is formed of the same or different material from that of the P-type charge generation layer 134. For example, the second auxiliary charge generation layer 324 is formed of the same material as that of the auxiliary charge generation layer 122 illustrated in the first embodiment of the present invention. In addition, the second auxiliary charge generation layer 324 has the same thickness as that of the P-type charge generation layer 134 or has a smaller thickness than that of the P-type charge generation layer 134.

[0080] The organic light emitting display devices according to the first, second and third embodiments of the present invention may also be applied to a structure including red, green and blue color filters 150R, 150G and 150B as illustrated in FIG. 14. That is, white light generated via the first and second light emitting units is emitted as red light while passing through a sub-pixel region provided with the red color filter 150R, is emitted as green light while passing through a sub-pixel region provided with the green color filter 150G, is emitted as blue light while passing through a sub-pixel region provided with the blue color filter 150B, and is emitted unchanged while passing through a sub-pixel region not provided with a color filter.

[0081] As is apparent from the foregoing description, an organic light emitting display device according to the present invention includes at least any one of a P-type charge generation layer and an N-type charge generation layer and at least one auxiliary charge generation layer disposed between emitting layers of corresponding light emitting units and generating holes and electrons. Accordingly, holes and electrons generated via the auxiliary charge generation layer may be stably supplied to the emitting layers, whereby lifespan of the organic light emitting display device may be increased by approximately 35% when compared to lifespan of a conventional organic light emitting display device.

[0082] It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the spirit or scope of the inventions. Thus, it is intended that the present invention covers the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An organic light emitting display device comprising:
  - first and second electrodes facing each other on a substrate;
  - at least two light emitting units formed between the first and second electrodes;
  - an N-type charge generation layer and a P-type charge generation layer sequentially stacked between the light emitting units; and
  - at least one auxiliary charge generation layer formed between at least one of the P-type charge generation layer and the N-type charge generation layer and an emitting layer of the light emitting unit disposed on an upper or lower portion of the at least one of the P-type charge generation layer and the N-type charge generation layer to generate electrons and holes supplied to the emitting layer of the light emitting unit.
2. The organic light emitting display device according to claim 1, wherein the at least two light emitting units comprises:
  - a first light emitting unit comprising a hole injection layer, a first hole transport layer, a first emitting layer, and a first electron transport layer, the layers being stacked between the first electrode and the N-type charge generation layer; and
  - a second light emitting unit comprising a second hole transport layer, the auxiliary charge generation layer, a third hole transport layer, a second emitting layer, and a second electron transport layer, the layers being stacked between the P-type charge generation layer and the second electrode.
3. The organic light emitting display device according to claim 2, wherein:
  - the P-type charge generation layer comprises a host capable of transporting holes and 1 to 99 wt % of a p-type dopant in combination or comprises HAT-CN, and
  - the host comprises a material that is the same or different from that of at least any one of the second and third hole transport layers.
4. The organic light emitting display device according to claim 1, wherein the auxiliary charge generation layer comprises a first auxiliary charge generation layer and a second auxiliary charge generation layer, and

the at least two light emitting units comprise:

a first light emitting unit comprising a hole injection layer, a first hole transport layer, a first emitting layer, and a first electron transport layer, the layers being stacked between the first electrode and the N-type charge generation layer; and

a second light emitting unit comprising a second hole transport layer, the first auxiliary charge generation layer, a third hole transport layer, the second auxiliary charge generation layer, a fourth hole transport layer, a second emitting layer, and a second electron transport layer, the layers being stacked between the P-type charge generation layer and the second electrode.


5. The organic light emitting display device according to claim 4, wherein:

each of the first auxiliary charge generation layer and the second auxiliary charge generation layer comprises a material that is the same or different from that of the P-type charge generation layer, and


the P-type charge generation layer comprises a host capable of transporting holes and 1 to 99 wt % of a p-type dopant in combination or comprises HAT-CN.

6. The organic light emitting display device according to claim 5, wherein, when the first auxiliary charge generation layer and the second auxiliary charge generation layer comprise the host capable of transporting holes and the p-type dopant in combination, the host comprises the same material as that of at least any one of the second, third and fourth hole transport layer.

7. The organic light emitting display device according to claim 3, wherein the p-type dopant comprises an organic compound represented by any one of Formulas 1 to 6 below where R1 to R6 are substituted or unsubstituted with fluorine or cyano group:




<Formula 1>



<Formula 2>


1,4-TCAQ

-continued




<Formula 3>

6,3-TCPQ




<Formula 4>

TCAQ



<Formula 5>

TCNTHPQ



<Formula 6>

TCNPQ

8. The organic light emitting display device according to claim 3, wherein the P-type charge generation layer comprises the host capable of transporting holes and 1 to 30 wt % of the p-type dopant.

9. The organic light emitting display device according to claim 1, wherein the at least two light emitting units comprise:

a first light emitting unit comprising a hole injection layer, a first hole transport layer, a first emitting layer, a first

electron transport layer, the auxiliary charge generation layer, and a second electron transport layer, the layers being stacked between the first electrode and the N-type charge generation layer; and

a second light emitting unit comprising a second hole transport layer, a second emitting layer, and a third electron transport layer, the layers being stacked between the P-type charge generation layer and the second electrode.

**10.** The organic light emitting display device according to claim **9**, wherein the auxiliary charge generation layer comprises a material that is the same or different from that of the N-type charge generation layer and has a thickness that is the same as or smaller than that of the N-type charge generation layer.

**11.** The organic light emitting display device according to claim **1**, wherein the auxiliary charge generation layer comprises a first auxiliary charge generation layer and a second auxiliary charge generation layer, and

wherein the at least two light emitting units comprise:

a first light emitting unit comprising a hole injection layer, a first hole transport layer, a first emitting layer, a first

electron transport layer, the first auxiliary charge generation layer and a second electron transport layer, the layers being stacked between the first electrode and the N-type charge generation layer; and

a second light emitting unit comprising a second hole transport layer, the second auxiliary charge generation layer, a third hole transport layer, a second emitting layer, and a third electron transport layer, the layers being stacked between the P-type charge generation layer and the second electrode.

**12.** The organic light emitting display device according to claim **9**, wherein the first auxiliary charge generation layer comprises a material that is the same or different from that of the N-type charge generation layer and has a thickness that is the same as or smaller than that of the N-type charge generation layer, and the second auxiliary charge generation layer comprises a material that is the same or different from that of the P-type charge generation layer and has a thickness that is the same as or smaller than that of the P-type charge generation layer.

\* \* \* \* \*

专利名称(译)	有机发光显示装置		
公开(公告)号	<a href="#">US20140117338A1</a>	公开(公告)日	2014-05-01
申请号	US14/062128	申请日	2013-10-24
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	CHO GWI JEONG LEE JAE MAN HEO JEONG HAENG AHN SO YEON KIM TAE SHICK CHOI HEE DONG		
发明人	CHO, GWI-JEONG LEE, JAE-MAN HEO, JEONG-HAENG AHN, SO-YEON KIM, TAE-SHICK CHOI, HEE-DONG		
IPC分类号	H01L51/52		
CPC分类号	H01L51/52 H01L51/5044 H01L51/0054 H01L51/50 H01L51/506 H01L51/5278		
优先权	1020120122577 2012-10-31 KR 1020130091181 2013-07-31 KR		
其他公开文献	US9048447		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

公开了一种具有改善的寿命的有机发光显示装置。有机发光显示装置包括在基板上彼此面对的第一和第二电极，在第一和第二电极之间形成的至少两个发光单元，在它们之间顺序堆叠的N型电荷产生层和P型电荷产生层。发光单元，以及形成在P型电荷产生层和N型电荷产生层中的至少任一个之间的至少一个辅助电荷产生层和设置在上部或下部的发光单元的发光层其中至少任何一个的一部分产生电子和空穴，提供给发光单元的发光层。

