



US 20190131535A1

(19) **United States**(12) **Patent Application Publication**
Lee et al.(10) **Pub. No.: US 2019/0131535 A1**(43) **Pub. Date: May 2, 2019**(54) **HETEROCYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME****C07F 9/6521** (2006.01)**C07F 9/6568** (2006.01)(52) **U.S. CL.**CPC **H01L 51/0067** (2013.01); **H01L 51/56**
(2013.01); **C07F 9/65216** (2013.01); **C07F**
9/65212 (2013.01); **H01L 51/0052** (2013.01);
H01L 51/0058 (2013.01); **C07F 9/65685**
(2013.01); **H01L 51/0073** (2013.01); **H01L**
51/0071 (2013.01); **H01L 51/5072** (2013.01);
H01L 51/5012 (2013.01); **H01L 51/5004**
(2013.01); **H01L 2251/552** (2013.01); **H01L**
51/506 (2013.01); **H01L 51/5016** (2013.01);
H01L 51/001 (2013.01); **H01L 2251/558**
(2013.01); **H01L 51/504** (2013.01)(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si
(KR)(72) Inventors: **Hyoyoung Lee**, Yongin-si (KR); **Junha**
Park, Yongin-si (KR); **Munki Sim**,
Yongin-si (KR); **Youngkook Kim**,
Yongin-si (KR); **Seokhwan Hwang**,
Yongin-si (KR)(21) Appl. No.: **15/969,232**(22) Filed: **May 2, 2018**(30) **Foreign Application Priority Data**

Oct. 31, 2017 (KR) 10-2017-0144221

Publication Classification(51) **Int. Cl.****H01L 51/00** (2006.01)**H01L 51/50** (2006.01)(57) **ABSTRACT**

A heterocyclic compound and an organic light-emitting device including the same are provided. The organic light-emitting device includes: a first electrode; a second electrode facing the first electrode; and an organic layer disposed between the first electrode and the second electrode, where the organic layer may include an emission layer and at least one of the heterocyclic compound described above.

40**220****190****150****110****210**

FIG. 1

10

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3

30

220
190
150
110

FIG. 4

40

220
190
150
110
210

HETEROCYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2017-0144221, filed on Oct. 31, 2017, in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

1. Field

[0002] One or more embodiments relate to a heterocyclic compound and an organic light-emitting device including the same.

2. Description of the Related Art

[0003] Organic light-emitting devices (OLEDs) are self-emission devices that, as compared with other devices, have wide viewing angles, high contrast ratios, short response times, and excellent brightness, driving voltage, and response speed characteristics, and produce full-color images.


[0004] OLEDs may include a first electrode disposed on a substrate, and may include a hole transport region, an emission layer, an electron transport region, and a second electrode sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region. Electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, may recombine in the emission layer to produce excitons. These excitons transit (or relax) from an excited state to a ground state to thereby generate light.

SUMMARY

[0005] One or more embodiments include a heterocyclic compound and an organic light-emitting device including the same.

[0006] Additional aspects of embodiments will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0007] According to one or more embodiments, a heterocyclic compound may be represented by Formula 1:



[0008] wherein, in Formula 1,

[0009] X_{11} may be selected from N and C-[(L_{11}) $_{a11}$ -(R_{11}) $_{b11}$], X_{12} may be selected from N and C-[(L_{12}) $_{a12}$ -(R_{12}) $_{b12}$], X_{13} may be selected from N and C-[(L_{13}) $_{a13}$ -(R_{13}) $_{b13}$], X_{14}

may be selected from N and C-[(L_{14}) $_{a14}$ -(R_{14}) $_{b14}$], X_{15} may be selected from N and C-[(L_{15}) $_{a15}$ -(R_{15}) $_{b15}$],

[0010] at least one selected from X_{11} to X_{15} may be N, provided that at least one selected from X_{11} to X_{15} is not N,

[0011] n_1 may be selected from 0, 1, and 2, n_2 may be selected from 1, 2, and 3, a sum of n_1+n_2 may be 3,

[0012] L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} may each independently be selected from a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group and a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

[0013] a_1 , a_2 , and a_{11} to a_{15} may each independently be an integer from 0 to 5,

[0014] when a_1 is 0, $-(\text{L}_1)_{a1}-^*$ may be a single bond; when a_2 is 0, $-(\text{L}_2)_{a2}-^*$ may be a single bond; when a_{11} is 0, $-(\text{L}_{11})_{a11}-^*$ may be a single bond; when a_{12} is 0, $-(\text{L}_{12})_{a12}-^*$ may be a single bond; when a_{13} is 0, $-(\text{L}_{13})_{a13}-^*$ may be a single bond; when a_{14} is 0, $-(\text{L}_{14})_{a14}-^*$ may be a single bond; when a_{15} is 0, $-(\text{L}_{15})_{a15}-^*$ may be a single bond,

[0015] when a_1 is 2 or greater, at least two L_1 groups may be identical to or different from each other; when a_2 is 2 or greater, at least two L_2 groups may be identical to or different from each other; when a_{11} is 2 or greater, at least two L_{11} groups may be identical to or different from each other; when a_{12} is 2 or greater, at least two L_{12} groups may be identical to or different from each other; when a_{13} is 2 or greater, at least two L_{13} groups may be identical to or different from each other; when a_{14} is 2 or greater, at least two L_{14} groups may be identical to or different from each other; when a_{15} is 2 or greater, at least two L_{15} groups may be identical to or different from each other,

[0016] b_1 and b_{11} to b_{15} may each independently be an integer from 1 to 10,

[0017] when b_1 is 2 or greater, at least two R_1 groups may be identical to or different from each other; when b_{11} is 2 or greater, at least two R_{11} groups may be identical to or different from each other; when b_{12} is 2 or greater, at least two R_{12} groups may be identical to or different from each other; when b_{13} is 2 or greater, at least two R_{13} groups may be identical to or different from each other; when b_{14} is 2 or greater, at least two R_{14} groups may be identical to or different from each other; when b_{15} is 2 or greater, at least two R_{15} groups may be identical to or different from each other,

[0018] two adjacent groups selected from L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} may optionally be bound to form a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

[0019] the heterocyclic compound represented by Formula 1 may include at least one —F, and

[0020] at least one substituent of the substituted $\text{C}_5\text{-C}_{60}$ carbocyclic group and the substituted $\text{C}_1\text{-C}_{60}$ heterocyclic group may be selected from:

[0021] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, and a $\text{C}_1\text{-C}_{60}$ alkoxy group;

[0022] a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, and a $\text{C}_1\text{-C}_{60}$ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl

group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

[0023] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

[0024] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and

[0025] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂).

[0026] wherein Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

[0027] * indicates a binding site to an adjacent atom.

[0028] According to one or more embodiments, an organic light-emitting device may include: a first electrode; a second electrode facing the first electrode; and an organic layer disposed between the first electrode and the second electrode, wherein the organic layer may include an emission layer and at least one of the heterocyclic compound described above.

BRIEF DESCRIPTION OF THE DRAWINGS

[0029] These and/or other aspects of embodiments will become apparent and more readily appreciated from the

following description of the embodiments, taken in conjunction with the accompanying drawings in which:

[0030] FIG. 1 is schematic view of an organic light-emitting device according to an embodiment;

[0031] FIG. 2 is schematic view of an organic light-emitting device according to an embodiment;

[0032] FIG. 3 is schematic view of an organic light-emitting device according to an embodiment; and

[0033] FIG. 4 is schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0034] Reference will now be made in more detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the figures, to explain aspects of embodiments of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of”, when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0035] As the present disclosure allows for various modifications and include various embodiments, example embodiments will be illustrated in the drawings and described in detail in the written description. Effects, features, and a method of achieving the subject matter of the present disclosure will become apparent by reference to the example embodiments of the present disclosure, together with the accompanying drawings. The subject matter of the present disclosure may, however, be embodied in many different forms and should not be construed as being limited to the example embodiments set forth herein.

[0036] Hereinafter, the subject matter of the present disclosure will be described in more detail by explaining example embodiments of the present disclosure with reference to the attached drawings. Like reference numerals in the drawings denote like elements, and thus their description will not be repeated unnecessarily.


[0037] In the embodiments described in the present specification, an expression used in the singular encompasses the expression of the plural, unless it has a clearly different meaning in the context.

[0038] In the present specification, it is to be understood that the terms such as “including,” “having,” and “comprising” are intended to indicate the existence of the features or components disclosed in the specification, and are not intended to preclude the possibility that one or more other features or components may exist or may be added.

[0039] It will be understood that when a layer, region, or component is referred to as being “on” or “onto” another layer, region, or component, it may be directly or indirectly formed over the other layer, region, or component. For example, intervening layers, regions, or components may be present.

[0040] Sizes of components in the drawings may be exaggerated for convenience of explanation. In other words, since sizes and thicknesses of components in the drawings may be arbitrarily illustrated for convenience of explanation, the following embodiments are not limited thereto.

[0041] A heterocyclic compound may be represented by Formula 1:



[0042] wherein, in Formula 1, X_{11} may be selected from N and C- $[(L_{11})_{a11}-(R_{11})_{b11}]$, X_{12} may be selected from N and C- $[(L_{12})_{a12}-(R_{12})_{b12}]$, X_{13} may be selected from N and C- $[(L_{13})_{a13}-(R_{13})_{b13}]$, X_{14} may be selected from N and C- $[(L_{14})_{a14}-(R_{14})_{b14}]$, X_{15} may be selected from N and C- $[(L_{15})_{a15}-(R_{15})_{b15}]$, and at least one selected from X_{11} to X_{15} may be N, provided that at least one selected from X_{11} to X_{15} may not be N.

[0043] In some embodiments, X_{11} , X_{12} , X_{13} , X_{14} , or X_{15} may be N; X_{11} and X_{13} may each be N; X_{12} and X_{14} may each be N; X_{11} and X_{15} may each be N; or X_{11} , X_{13} , and X_{15} may each be N, but embodiments are not limited thereto.

[0044] In some embodiments, X_{11} , X_{13} , and X_{15} may each be N, X_{12} may be C- $[(L_{12})_{a12}-(R_{12})_{b12}]$, and X_{14} may be C- $[(L_{14})_{a14}-(R_{14})_{b14}]$, but embodiments are not limited thereto.

[0045] In Formula 1, n_1 may be selected from 0, 1, and 2, and n_2 may be selected from 1, 2, and 3, wherein a sum of n_1+n_2 may be 3.

[0046] In some embodiments, n_1 may be 0, and n_2 may be 3; n_1 may be 1, and n_2 may be 2; or n_1 may be 2, and n_2 may be 1.

[0047] In some embodiments, n_1 may be 2, and n_2 may be 1, but embodiments are not limited thereto.

[0048] n_1 represents the number of substituent(s) represented by $^*-(L_1)_{a1}-(R_1)_{b1}$; when n_1 is 2 or greater, at least two substituents represented by $^*-(L_1)_{a1}-(R_1)_{b1}$ may identical to or different from each other. Descriptions for n_2 may be understood by referring to the descriptions for n_1 provided herein.

[0049] In Formula 1, L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} may each independently be selected from a substituted or unsubstituted C_5 - C_{60} carbocyclic group and a substituted or unsubstituted C_1 - C_{60} heterocyclic group.

[0050] In some embodiments, L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} may each independently be selected from:

[0051] a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzoxazole group, a


benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothiophene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothiophene group, a benzo-carbazole group, and a dibenzocarbazole group; and

[0052] a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzoxazole group, a benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothiophene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothiophene group, a benzo-carbazole group, and a dibenzocarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, a C_2 - C_{20} heteroaryl group, and —Si(Q_{31})(Q_{32})(Q_{33}),


[0053] Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group,

[0054] but embodiments are not limited thereto.


[0055] In some embodiments, L_1 , L_2 , and L_{11} to L_{15} may each independently be selected from groups represented by Formulae 3-1 to 3-47, but embodiments are not limited thereto:












-continued



-continued




-continued




-continued

3-21




3-22

3-23



3-24


3-25




3-26

3-27

3-28



3-29



3-30

3-31






3-32

3-33

3-34


3-35

-continued




-continued

3-36




3-41

3-37




3-42

3-38




3-43

3-39




3-44

3-40




3-45



3-46

-continued

3-47



[0056] wherein, in Formulae 3-1 to 3-47,

[0057] Y_1 may be selected from O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, and $Si(Z_6)(Z_7)$,

[0058] Z_1 to Z_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$,

[0059] d_2 may be an integer from 0 to 2; when d_2 is 2 or greater, at least two Z_1 groups may be identical to or different from each other,

[0060] d_3 may be an integer from 0 to 3; when d_3 is 2 or greater, at least two Z_1 groups may be identical to or different from each other, and at least two Z_2 groups may be identical to or different from each other,

[0061] d_4 may be an integer from 0 to 4; when d_4 is 2 or greater, at least two Z_1 groups may be identical to or different from each other, and at least two Z_2 groups may be identical to or different from each other,


[0062] d_5 may be an integer from 0 to 5; when d_5 is 2 or greater, at least two Z_1 groups may be identical to or different from each other, and at least two Z_2 groups may be identical to or different from each other,

[0063] d_6 may be an integer from 0 to 6; when d_6 is 2 or greater, at least two Z_1 groups may be identical to or different from each other, and at least two Z_2 groups may be identical to or different from each other,


[0064] d_8 may be an integer from 0 to 8; when d_8 is 2 or greater, at least two Z_1 groups may be identical to or different from each other, and

[0065] * and * 1 each indicate a binding site to an adjacent atom.


[0066] In some embodiments, L_1 , L_2 , and L_{11} to L_{15} may each independently be selected from groups represented by Formulae 4-1 to 4-24, but embodiments are not limited thereto:




4-1




4-2




4-3




4-4




4-5




4-6



4-7




4-8




4-9

-continued



-continued



[0067] wherein, in Formulae 4-1 to 4-24,

[0068] Y_{21} may be selected from O, S, $C(Z_{23})(Z_{24})$, $N(Z_{25})$, and $Si(Z_{26})(Z_{27})$,[0069] Z_{21} to Z_{27} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, and a naphthyl group,[0070] d_2 may be an integer from 0 to 2; when d_2 is 2 or greater, at least two Z_{21} groups may be identical to or different from each other,[0071] d_3 may be an integer from 0 to 3; when d_3 is 2 or greater, at least two Z_{21} groups may be identical to or different from each other, and at least two Z_{22} groups may be identical to or different from each other,[0072] d_4 may be an integer from 0 to 4; when d_4 is 2 or greater, at least two Z_{21} groups may be identical to or different from each other, and at least two Z_{22} groups may be identical to or different from each other,

[0073] d_6 may be an integer from 0 to 6; when d_6 is 2 or greater, at least two Z_{21} groups may be identical to or different from each other,

[0074] d_8 may be an integer from 0 to 8; when d_8 is 2 or greater, at least two Z_{21} groups may be identical to or different from each other, and

[0075] * and *' each indicate a binding site to an adjacent atom.

[0076] In Formula 1, a_1 , a_2 , and a_{11} to a_{15} may each independently be an integer from 0 to 5, but embodiments are not limited thereto.

[0077] a_1 indicates the number of L_1 groups; when a_1 is 2 or greater, at least two L_1 groups may be identical to or different from each other. Descriptions for a_2 and a_{11} to a_{15} may each be understood by referring to the descriptions for a_1 provided herein.

[0078] When a_1 is 0, $*(L_1)_{a1}-*$ may be a single bond; when a_2 is 0, $*(L_2)_{a2}-*$ may be a single bond; when a_{11} is 0, $*(L_{11})_{a11}-*$ may be a single bond; when a_{12} is 0, $*(L_{12})_{a12}-*$ may be a single bond; when a_{13} is 0, $*(L_{13})_{a13}-*$ may be a single bond; when a_{14} is 0, $*(L_{14})_{a14}-*$ may be a single bond; and when a_{15} is 0, $*(L_{15})_{a15}-*$ may be a single bond.


[0079] In some embodiments, a_1 may be 0, but embodiments are not limited thereto.

[0080] In some embodiments, a_2 may be 0, 1, 2, 3, or 4, but embodiments are not limited thereto.


[0081] In some embodiments, a_{11} to a_{15} may each independently be 0, 1, or 2, but embodiments are not limited thereto.

[0082] In some embodiments, a_1 may be 0, a_2 may be 0, 1, 2, 3, or 4, and a_{11} to a_{15} may each independently be 0, 1, or 2, but embodiments are not limited thereto.


[0083] In some embodiments, R_1 and R_{11} to R_{15} may each independently be selected from groups represented by Formulae 5-1 to 5-79, but embodiments are not limited thereto:




5-1



5-2




5-3




5-4

-continued


5-5




5-6




5-7




5-8




5-9











5-10



5-11




-continued



-continued


5-12

5-20




5-13

5-14




5-21

5-15




5-22

5-16




5-23

5-17




5-24

5-18




5-25


5-19




5-26



5-27



5-28













5-29











-continued




-continued




-continued




-continued




5-74




5-75




5-76



5-77



5-78



5-79

[0084] wherein, in Formulae 5-1 to 5-79,

[0085] Y_{31} may be selected from O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, and $Si(Z_{36})(Z_{37})$,

[0086] Z_{31} to Z_{37} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a

phenanthrolinyl group, a phenazinyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$,

[0087] e_2 may be an integer from 0 to 2; when e_2 is 2 or greater, at least two Z_{31} groups may be identical to or different from each other, and at least two Z_{32} groups may be identical to or different from each other,

[0088] e_3 may be an integer from 0 to 3; when e_3 is 2 or greater, at least two Z_{31} groups may be identical to or different from each other, and at least two Z_{32} groups may be identical to or different from each other,

[0089] e_4 may be an integer from 0 to 4; when e_4 is 2 or greater, at least two Z_{31} groups may be identical to or different from each other, and at least two Z_{32} groups may be identical to or different from each other,

[0090] e_5 may be an integer from 0 to 5; when e_5 is 2 or greater, at least two Z_{31} groups may be identical to or different from each other, and at least two Z_{32} groups may be identical to or different from each other,

[0091] e_6 may be an integer from 0 to 6; when e_6 is 2 or greater, at least two Z_{31} groups may be identical to or different from each other, and at least two Z_{32} groups may be identical to or different from each other,

[0092] e_7 may be an integer from 0 to 7; when e_7 is 2 or greater, at least two Z_{31} groups may be identical to or different from each other,

[0093] e_9 may be an integer from 0 to 9; when e_9 is 2 or greater, at least two Z_{31} groups may be identical to or different from each other, and

[0094] * indicates a binding site to an adjacent atom.

[0095] In some embodiments, R_1 may be selected from a benzene group and a naphthalene group; and

[0096] a benzene group and a naphthalene group, each substituted with at least one selected from $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, and a naphthyl group, but embodiments are not limited thereto.


[0097] b_1 and b_{11} to b_{15} may each independently be an integer from 1 to 10.

[0098] b_1 indicates the number of R_1 groups; when b_1 is 2 or greater, at least two R_1 groups may be identical to or different from each other. Descriptions for b_1 to b_{15} may each be understood by referring to the descriptions for b_1 provided herein.

[0099] In Formula 1, two adjacent groups selected from L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} may optionally be bound to form a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group.


[0100] In some embodiments, the heterocyclic compound may be represented by Formula 1-2 or 1-3:

Formula 1-2



-continued

Formula 1-3



[0101] wherein, in Formulae 1-2 and 1-3,

[0102] A_1 and A_2 may each independently be selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group,

[0103] X_{21} may be selected from a single bond, $C(R_{21})$ (R_{22}), $N(R_{21})$, O , S , and $Si(R_{21})(R_{22})$,

[0104] descriptions for L_3 may be understood by referring to the descriptions for L_1 in Formula 1,

[0105] descriptions for a_3 may be understood by referring to the descriptions for a_1 in Formula 1,

[0106] R_{21} , R_{22} , Z_1 , Z_{31} , and Z_{32} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$,

[0107] e_{51} , e_{52} , and d_{51} may each independently be an integer from 1 to 10, and

[0108] X_{11} to X_{15} , L_1 , L_2 , a_1 , a_2 , R_1 , and b_1 may respectively be defined the same as those of Formula 1.

[0109] The heterocyclic compound represented by Formula 1 may include at least one $-F$.

[0110] In other words, at least one of L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} may include a substituted or unsubstituted fluorine-containing C_5 - C_{60} carbocyclic group and a substituted or unsubstituted fluorine-containing C_1 - C_{60} heterocyclic group.

[0111] The number of $-F(s)$ included in the heterocyclic compound represented by Formula 1 may be an integer from 1 to 20, but embodiments are not limited thereto.

[0112] In some embodiments, the number of $-F(s)$ included in the heterocyclic compound may be 1, 2, 3, 4, or 6, but embodiments are not limited thereto.

[0113] In some embodiments, at least one of R_{11} and R_{15} may be selected from a substituted or unsubstituted fluorine-containing C_5 - C_{60} carbocyclic group and a substituted or unsubstituted fluorine-containing C_1 - C_{60} heterocyclic group.

[0114] In some embodiments, at least one of R_{11} and R_{15} may be a substituted or unsubstituted fluorine-containing C_5 - C_{60} carbocyclic group.

[0115] In some embodiments, R_{11} to R_{15} may each independently be selected from

[0116] a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene



















group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzoxazole group, a benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothiophene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothiophene group, a benzo-carbazole group, and a dibenzocarbazole group; and

[0117] a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzoxazole group, a benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothiophene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothiophene group, a benzo-carbazole group, and a dibenzocarbazole group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, a C_2 - C_{20} heteroaryl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$,










[0118] wherein at least one of $R_{11}(s)$ in the number of b_{11} , $R_{12}(s)$ in the number of b_{12} , $R_{13}(s)$ in the number of b_{13} , $R_{14}(s)$ in the number of b_{14} , and $R_{15}(s)$ in the number of b_{15} may be substituted with at least one $-F$, but embodiments are not limited thereto.

[0119] In some embodiments, at least one of $R_{11}(s)$ in the number of b_{11} , $R_{12}(s)$ in the number of b_{12} , $R_{13}(s)$ in the number of b_{13} , $R_{14}(s)$ in the number of b_{14} , and $R_{15}(s)$ in the number of b_{15} may be selected from groups represented by Formulae 7-1 to 7-77, but embodiments are not limited thereto:

-continued




-continued




-continued

7-19



7-28


7-20



7-29


7-21

7-22




7-30

7-23




7-31

7-24




7-32

7-25




7-33

7-26




7-34

7-27




7-35


-continued




7-36




7-37




7-38




7-39




7-40



7-41




7-42




7-43


-continued




7-44




7-45




7-46




7-47




7-48



7-49



7-50












7-51




7-52

-continued




-continued

7-53




7-62

7-54




7-63

7-55




7-64

7-56




7-65

7-57




7-66

7-58




7-67

7-59




7-68

7-60




7-69

7-61




7-70


-continued




7-71




7-72




7-73




7-74



7-75



7-76



7-77

[0120] wherein, in Formulae 7-1 to 7-77,

[0121] Z_{41} may be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl

group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$,

[0122] f_2 may be an integer selected from 1 and 2; when f_2 is 2 or greater, at least two Z_{41} groups may be identical to or different from each other,

[0123] f_3 may be an integer from 1 to 3; when f_3 is 2 or greater, at least two Z_{41} groups may be identical to or different from each other,

[0124] f_4 may be an integer from 1 to 4; when f_4 is 2 or greater, at least two Z_{41} groups may be identical to or different from each other,

[0125] f_5 may be an integer from 1 to 5; when f_5 is 2 or greater, at least two Z_{41} groups may be identical to or different from each other,

[0126] f_6 may be an integer from 1 to 6; when f_6 is 2 or greater, at least two Z_{41} groups may be identical to or different from each other, and

[0127] * indicates a binding site to an adjacent atom.

[0128] In some embodiments, R_1 may be selected from a benzene group and a naphthalene group; and

[0129] a benzene group and a naphthalene group, each substituted with at least one selected from —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, and a naphthyl group, and

[0130] at least one of $R_{11}(s)$ in the number of b11, $R_{12}(s)$ in the number of b12, $R_{13}(s)$ in the number of b13, $R_{14}(s)$ in the number of b14, and $R_{15}(s)$ in the number of b15 may be selected from groups represented by Formulae 7-1 to 7-77, but embodiments are not limited thereto:


[0131] In some embodiments, X_{11} , X_{13} , and X_{15} may each be N, X_{12} may be $\text{C}-[(\text{L}_{12})_{a12}-(\text{R}_{12})_{b12}]$, and X_{14} may be $\text{C}-[(\text{L}_{14})_{a14}-(\text{R}_{14})_{b14}]$,

[0132] wherein at least one of $R_{12}(s)$ in the number of b12 and $R_{14}(s)$ in the number of b14 may be selected from a substituted or unsubstituted fluorine-containing C_5 - C_{60} carbocyclic group and a substituted or unsubstituted fluorine-containing C_1 - C_{60} heterocyclic group, but embodiments are not limited thereto.


[0133] In some embodiments, X_{11} , X_{13} , and X_{15} may each be N, X_{12} may be $\text{C}-[(\text{L}_{12})_{a12}-(\text{R}_{12})_{b12}]$, and X_{14} may be $\text{C}-[(\text{L}_{14})_{a14}-(\text{R}_{14})_{b14}]$,

[0134] at least one of $R_{12}(s)$ in the number of b12 and $R_{14}(s)$ in the number of b14 may be selected from groups represented by Formulae 7-1 to 7-77, but embodiments are not limited thereto:


[0135] In some embodiments, the heterocyclic compound represented by Formula 1 may be selected from Compounds 1 to 132, but embodiments are not limited thereto:




1




2




3




4




5



6




7




8

-continued


9




10




11




12




13











14



-continued




-continued




-continued


29




30




31




32




33




34



35




36




-continued


37




38



39




40




-continued


41




42



43




44




-continued


45




46




47




48




-continued




49




50




51



52




53




54

-continued


55




56




57




58




59




60




-continued
61




62




63




64











65



66




-continued




-continued


75




76




77




78




79




80




81




82




-continued
83




84




85




86



87




88




-continued


89




90



91




92




-continued


93




94



95




96




-continued


97




98




99




100




101



102




-continued




-continued


111




112



113




114




-continued


115




116




117









118




119




-continued




-continued
126




127




128




129



130




131



-continued

132



[0136] The heterocyclic compound represented by Formula 1 may include at least one fluorine substituent. As fluorine has high electronegativity and electron affinity, a dipole moment of a molecule may be increased, thereby improving electron injection ability and electron transport ability of a compound. Therefore, as the heterocyclic compound represented by Formula 1 includes at least one fluorine substituent, the heterocyclic compound may have improved electron injection ability and electron transport ability of a compound.

[0137] In addition, the heterocyclic compound represented by Formula 1 may include a phosphine oxide structure. As the phosphine oxide compound has a tetrahedral structure, an amorphous film may be formed due to its steric molecular structure. Also, as the phosphine oxide compound is capable of forming a negative hyper conjugation (back donation) and a hydrogen bond and has high electronegativity, a molecule may be stabilized; a dipole may be formed in a molecule, thereby improving electron transport ability.

[0138] In addition, an electronic device, e.g., an organic light-emitting device, employing the heterocyclic compound may have a low driving voltage, high current density, and high efficiency.

[10139] The heterocyclic compound represented by Formula 1 may be synthesized by using any suitable organic synthetic method available in the art. A method of synthesizing the heterocyclic compound may be understood by one of ordinary skill in the art by referring to Examples described herein.

[0140] At least one heterocyclic compound represented by Formula 1 may be included between a pair of electrodes in an organic light-emitting device. In some embodiments, the heterocyclic compound may be included in at least one selected from a hole transport region, an electron transport region, and an emission layer. In some embodiments, the heterocyclic compound represented by Formula 1 may be used as a material for forming a capping layer, which is disposed on outer sides of a pair of electrodes in an organic light-emitting device.

[0141] Accordingly, there is provided an organic light-emitting device including a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, wherein the organic layer includes an emission layer and at least one heterocyclic compound represented by Formula 1.

[0142] As used herein, the statement “(for example, the organic layer) including at least one heterocyclic compound” means that “(the organic layer) including a hetero-

cyclic compound of Formula 1, or at least two different heterocyclic compounds of Formula 1”.

[0143] For example, the organic layer may include Compound 1 only as the heterocyclic compound. In this embodiment, Compound 1 may be included in the emission layer of the organic light-emitting device. In some embodiments, the organic layer may include Compounds 1 and 2 as the heterocyclic compounds. In this embodiment, Compounds 1 and 2 may be present in the same layer (for example, Compounds 1 and 2 may be both present in an emission layer), or in different layers (for example, Compound 1 may be present in an emission layer, and Compound 2 may be present in an electron transport layer).

[0144] The term “organic layer,” as used herein, refers to a single and/or a plurality of layers disposed between the first electrode and the second electrode in an organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0145] In some embodiments, the first electrode may be an anode, the second electrode may be a cathode, and the organic layer may further include a hole transport region disposed between the first electrode and the emission layer and an electron transport region disposed between the emission layer and the second electrode, wherein the hole transport region may include a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or a combination thereof, and the electron transport region may include a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or a combination thereof.

[0146] In some embodiments, the electron transport region may include the heterocyclic compound, but embodiments are not limited thereto.

[0147] In some embodiments, the electron transport region may include the electron transport layer, and the electron transport layer may include the heterocyclic compound.

[0148] In some embodiments, the emission layer may include the heterocyclic compound, but embodiments are not limited thereto.

[0149] In some embodiments, the hole transport region may include a p-dopant, wherein the p-dopant may have the lowest unoccupied molecular orbital (LUMO) level of -3.5 electron Volts (eV) or less.

[0150] The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments are not limited thereto. For example, the p-dopant may include a cyano group-containing compound, but embodiments are not limited thereto.

[0151] The organic light-emitting device may further include i) at least one second emission layer for emitting second color light or ii) at least one second emission layer for emitting second color light and at least one third emission layer for emitting third color light, between the first electrode and the second electrode, a maximum emission wavelength of the first color light, a maximum emission wavelength of the second color light, and a maximum emission wavelength of the third color light may be identical to or different from each other, and the first color light and the second color light are emitted in the form of mixed light, or the first color light, the second color light, and the third color light are emitted in the form of mixed light.

[0152] Description of FIG. 1

[0153] FIG. 1 illustrates a schematic cross-sectional view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

[0154] Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIG. 1.

[0155] First electrode 110

[0156] Referring to FIG. 1, a substrate may be additionally disposed under the first electrode 110 or over the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0157] The first electrode 110 may be formed by depositing or sputtering, onto the substrate, a material for forming the first electrode 110. When the first electrode 110 is an anode, the material for forming the first electrode 110 may be selected from materials with a high work function that facilitate hole injection.

[0158] The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming the first electrode 110 may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO_2), zinc oxide (ZnO), and any combinations thereof, but embodiments are not limited thereto. In some embodiments, when the first electrode 110 is a semi-transmissive electrode or a reflective electrode, as a material for forming the first electrode 110, at least one of magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), and any combination thereof may be used, but embodiments are not limited thereto.

[0159] The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. In some embodiments, the first electrode 110 may have a triple-layered structure of ITO/Ag/ITO, but embodiments are not limited thereto.

[0160] Organic Layer 150

[0161] The organic layer 150 may be on the first electrode 110. The organic layer 150 may include an emission layer.

[0162] The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer and an electron transport region between the emission layer and the second electrode 190.


[0163] Hole Transport Region in Organic Layer 150

[0164] The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.


[0165] The hole transport region may include at least one selected from a hole injection layer, an emission auxiliary layer, and an electron blocking layer.

[0166] For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials or a multi-layered structure, e.g., a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein layers of each structure are sequentially stacked on the first electrode 110 in each stated order, but embodiments are not limited thereto.

[0167] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPB), β -NPB, TPD, a spiro-TPD, a spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




-continued




2-TNATA


-continued




Spiro-TPD





Spiro-NPB




NPB




methylated NPB

 β -NPB

TAPC



TPD



HMTPD



[0181] In one or more embodiments, R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl

group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

[0182] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q_{31})(Q_{32})(Q_{33}), and —N(Q_{31})(Q_{32}),

[0183] wherein descriptions for Q_{31} to Q_{33} may each independently be understood by referring to those provided herein.

[0184] In one or more embodiments, in Formula 201, at least one of R_{201} to R_{203} may each independently be selected from:

[0185] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0186] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, but embodiments are not limited thereto.

[0187] In one or more embodiments, in Formula 202, i) R_{201} may be linked to R_{202} via a single bond, and/or ii) R_{203} may be linked to R_{204} via a single bond.


[0188] In one or more embodiments, in Formula 202, at least one of R_{201} to R_{204} may be selected from:

[0189] a carbazolyl group; and

[0190] a carbazolyl group substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, but embodiments are not limited thereto.


[0191] The compound represented by Formula 201 may be represented by Formula 201A:

Formula 201A




[0192] In some embodiments, the compound represented by Formula 201 may be represented by Formula 201A(1), but embodiments are not limited thereto:

Formula 201A(1)




[0193] In some embodiments, the compound represented by Formula 201 may be represented by Formula 201A-1, but embodiments are not limited thereto:

Formula 201A-1




[0194] In some embodiments, the compound represented by Formula 202 may be represented by Formula 202A:

Formula 202A



[0195] In some embodiments, the compound represented by Formula 202 may be represented by Formula 202A-1:

Formula 202A-1



[0196] In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,

[0197] descriptions for L_{201} to L_{203} , $xa1$ to $xa3$, $xa5$, and R_{202} to R_{204} may each be understood by referring to those provided herein,


[0198] descriptions for R_{211} and R_{212} may each be understood by referring to those for R_{203} provided herein, and

[0199] R_{213} to R_{217} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-F$, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl


group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0200] The hole transport region may include at least one compound selected from Compounds HT1 to HT39, but embodiments are not limited thereto:

HT1




HT2




-continued


HT3




HT4



HT5




HT6




-continued


HT7




HT8



HT9




HT10




-continued


HT11




HT12




HT13




HT14



HT15




HT16




-continued


HT17




HT18



HT19




HT20




-continued


HT21



HT22




HT23




-continued


HT24




HT25




HT26




HT27



HT28




HT29




-continued


HT30




HT31




HT32




HT33




HT34




HT35




-continued
HT36


HT38



HT37



HT39



[0201] The thickness of the hole transport region may be in a range of about 100 (Angstroms) Å to about 10,000 Å, and in some embodiments, about 100 Å to about 1,000 Å. When the hole transport region includes at least one selected from a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, and in some embodiments, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and in some embodiments, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within any of these ranges, excellent hole transport characteristics may be obtained without a substantial increase in driving voltage.

[0202] The emission auxiliary layer may increase light emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer. The electron blocking layer may reduce or eliminate the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the aforementioned materials.

[0203] p-Dopant

[0204] The hole transport region may include a charge generating material as well as the aforementioned materials,

to improve conductive properties of the hole transport region. The charge generating material may be substantially homogeneously or non-homogeneously dispersed in the hole transport region.

[0205] The charge generating material may include, for example, a p-dopant.

[0206] In some embodiments, the LUMO of the p-dopant may be about -3.5 eV or less.

[0207] The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments are not limited thereto.




[0208] In some embodiments, the p-dopant may include at least one selected from

[0209] a quinone derivative, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

[0210] a metal oxide, such as tungsten oxide or molybdenum oxide;

[0211] 1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and

[0212] a compound represented by Formula 221, but embodiments are not limited thereto:



Formula 221

[0213] wherein, in Formula 221,

[0214] R₂₂₁ to R₂₂₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, provided that at least one selected from R₂₂₁ to R₂₂₃ may include at least one substituent selected from a cyano group, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group substituted with —F, a C₁-C₂₀ alkyl group substituted with —Cl, a C₁-C₂₀ alkyl group substituted with —Br, and a C₁-C₂₀ alkyl group substituted with —I.

[0215] Emission Layer in Organic Layer 150

[0216] When the organic light-emitting device 10 is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer may have a stacked structure. The stacked structure may include two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer. The two or more layers may be in direct contact with each other. In some embodiments, the two or more layers may be separated from each other. In one or more embodiments, the emission layer

may include two or more materials. The two or more materials may include a red light-emitting material, a green light-emitting material, or a blue light-emitting material. The two or more materials may be mixed with each other in a single layer. The two or more materials mixed with each other in the single layer may emit white light.


[0217] The emission layer may include a host and a dopant. The dopant may include at least one of a fluorescent dopant and a phosphorescent dopant.

[0218] The amount of the dopant in the emission layer may be, in general, in a range of about 0.01 parts to about 15 parts by weight based on 100 parts by weight of the host, but embodiments are not limited thereto.

[0219] The thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, and in some embodiments, about 200 Å to about 600 Å. When the thickness of the emission layer is within any of these ranges, improved luminescence characteristics may be obtained without a substantial increase in driving voltage.

[0220] Host in Emission Layer

[0221] The host may include a compound represented by Formula 301:



Formula 301

[0222] wherein, in Formula 301,

[0223] Ar₃₀₁ may be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

[0224] xb11 may be 1, 2, or 3,

[0225] L₃₀₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0226] xb1 may be an integer from 0 to 5,

[0227] R₃₀₁ may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃), —N(Q₃₀₁)(Q₃₀₂), —B(Q₃₀₁)(Q₃₀₂), —C(=O)(Q₃₀₁), —S(=O)₂(Q₃₀₁), and —P(=O)(Q₃₀₁)(Q₃₀₂), and

[0228] xb21 may be an integer from 1 to 5,

[0229] wherein Q₃₀₁ to Q₃₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group,

a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0230] In some embodiments, Ar_{301} in Formula 301 may be selected from:


[0231] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group; and

[0232] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$,


[0233] wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0234] When $xb11$ in Formula 301 is 2 or greater, at least two Ar_{301} groups may be linked via a single bond.

[0235] In one or more embodiments, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:



Formula 301-1



Formula 301-2

[0236] wherein, in Formulae 301-1 to 301-2,

[0237] A_{301} to A_{304} may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine group, an indene group, a fluorene group, a spiro-bifluorene

group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran group, a dinaphthofuran group, a thiophene group, a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, and a dinaphthothiophene group,

[0238] X_{301} may be O, S, or $N-[(L_{304})_{xb4}-R_{304}]$,

[0239] R_{311} to R_{314} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$,

[0240] $xb22$ and $xb23$ may each independently be 0, 1, or 2,

[0241] descriptions for L_{301} , $xb1$, R_{301} , and Q_{31} to Q_{33} may each independently be understood by referring to those provided herein,

[0242] descriptions for L_{302} to may each independently be understood by referring to those for L_{301} provided herein,

[0243] descriptions for $xb2$ to $xb4$ may each independently be understood by referring to those for $xb1$ provided herein, and

[0244] descriptions for R_{302} to R_{304} may each independently be understood by referring to those for R_{301} provided herein.

[0245] In some embodiments, in Formulae 301, 301-1, and 301-2, L_{301} to L_{304} may each independently be selected from:

[0246] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthre-

nylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a ben-

zofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group; and

[0247] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolylenylene group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group,

a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

[0248] wherein descriptions for Q_{31} to Q_{33} may each independently be understood by referring to those provided herein.

[0249] In some embodiments, in Formulae 301, 301-1, and 301-2, R_{301} to R_{304} may each independently be selected from:

[0250] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolylenylene group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

[0251] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolylenylene group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinyl group, an acridinyl group, a


phenanthrolyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuran group, a benzothiophenyl group, a dibenzofuran group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}).

[0252] wherein descriptions for Q_{31} to Q_{33} may each independently be understood by referring to those provided herein.


[0253] In some embodiments, the host may include an alkaline earth metal complex. For example, the host may include a beryllium (Be) complex, e.g., Compound H55, a magnesium (Mg) complex, or a zinc (Zn) complex.

[0254] The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55, but embodiments are not limited thereto:


-continued




H2




H3




H4




H5



H6




H7




H1

-continued


H8




H9




H10




H11



H12




H13




-continued


H14




H15




H16







H17






H18




-continued



-continued




-continued




H26

-continued




H29


H27




H30



H28



H31




H32


-continued

-continued


H33




H34




H35




H36




H37




H38



H39




-continued




H40


-continued




H43




H41



H44




H42



H45


-continued

H46




-continued

H52




H53




H54


H47




H48




H49



H50




H51




[0255] Phosphorescent Dopant Included in Emission Layer of Organic Layer **150**

[0256] The phosphorescent dopant may include an organometallic complex represented by Formula 401:



Formula 401

Formula 402



[0257] wherein, in Formulae 401 and 402,

[0258] M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

[0259] L_{401} may be selected from ligands represented by Formula 402, xc1 may be an integer from 1, 2, and 3; when xc1 is two or greater, at least two L_{401} groups may be identical to or different from each other,

[0260] L_{402} may be an organic ligand, xc2 may be an integer from 0 to 4; when xc2 is 2 or greater, at least two L_{402} groups may be identical to or different from each other,

[0261] X_{401} to X_{404} may each independently be nitrogen (N) or carbon (C),

[0262] X_{401} and X_{403} may be linked via a single bond or a double bond, X_{402} and X_{404} may be linked via a single bond or a double bond,

[0263] A_{401} and A_{402} may each independently be a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

[0264] X_{405} may be a single bond, $^*O^*$, $^*S^*$, $^*C(=O)^*$, $^*N(Q_{411})^*$, $^*C(Q_{411})(Q_{412})^*$, $^*C(Q_{411})=C(Q_{412})^*$, $^*C(Q_{411})=^*$, or $^*=C(Q_{411})^*$, wherein Q_{411} and Q_{412} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

[0265] X_{406} may be a single bond, O, or S,

[0266] R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$, wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group,

[0267] xc11 and xc12 may each independently be an integer from 0 to 10, and

[0268] $*$ and * in Formula 402 each indicate a binding site to M in Formula 401.

[0269] In some embodiments, in Formula 402, A_{401} and A_{402} may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

[0270] In one or more embodiments, in Formula 402, i) X_{401} may be nitrogen, and X_{402} may be carbon, or ii) X_{401} and X_{402} may each be nitrogen.

[0271] In one or more embodiments, in Formula 402, R_{401} and R_{402} may each independently be selected from:

[0272] hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0273] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, and a norbornenyl group;

[0274] a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0275] a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and


[0276] $-\text{Si}(\text{Q}_{401})(\text{Q}_{402})(\text{Q}_{403})$, $-\text{N}(\text{Q}_{401})(\text{Q}_{402})$, $-\text{B}(\text{Q}_{401})(\text{Q}_{402})$, $-\text{C}(=\text{O})(\text{Q}_{401})$, $-\text{S}(=\text{O})_2(\text{Q}_{401})$, and $-\text{P}(=\text{O})(\text{Q}_{401})(\text{Q}_{402})$,

[0277] wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group, but embodiments are not limited thereto.


[0278] In one or more embodiments, when xc1 in Formula 401 is 2 or greater, two A_{401} groups of at least two L_{401} groups may optionally be linked to each other via X_{407} as a linking group; or two A_{402} groups may optionally be linked to each other via X_{408} as a linking group (see Compounds PD1 to PD4 and PD7). X_{407} and X_{408} may each independently be selected from a single bond, $^*\text{O}^*$, $^*\text{S}^*$, $^*\text{C}(=\text{O})^*$, $^*\text{N}(\text{Q}_{413})^*$, $^*\text{C}(\text{Q}_{413})(\text{Q}_{414})^*$, and $^*\text{C}(\text{Q}_{413})=\text{C}(\text{Q}_{414})^*$, wherein Q_{413} and Q_{414} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, but embodiments are not limited thereto.

[0279] L_{402} in Formula 401 may be any suitable monovalent, divalent, or trivalent organic ligand. For example, L_{402} may be selected from halogen, diketone (e.g., acetylacetonate), a carboxylic acid (e.g., picolinate), $-\text{C}(=\text{O})$, isonitrile, $-\text{CN}$, and phosphorus (e.g., phosphine or phosphite), but embodiments are not limited thereto.

[0280] In some embodiments, the phosphorescent dopant may include, for example, at least one selected from Compounds PD1 to PD25, but embodiments are not limited thereto:




PD1




PD2


-continued




PD3




PD4




PD5



PD6




PD7




PD8

-continued




PD9


-continued




PD14




PD10




PD15




PD11




PD16




PD12



PD17




PD13



PD18


-continued



PD19



-continued

PD23




PD20


PD24




PD25




PD21

**[0281]** Fluorescent Dopant in Emission Layer**[0282]** The fluorescent dopant may include an arylamine compound or a styrylamine compound.**[0283]** In some embodiments, the fluorescent dopant may include a compound represented by Formula 501:

PD22



Formula 501

**[0284]** wherein, in Formula 501,**[0285]** Ar_{501} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,**[0286]** L_{501} to L_{503} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocyc-

cycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0287] $xd1$ to $xd3$ may each independently be an integer from 0 to 3,

[0288] R_{501} and R_{502} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

[0289] $xd4$ may be an integer from 1 to 6.

[0290] In some embodiments, Ar_{501} in Formula 501 may be selected from

[0291] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

[0292] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0293] In one or more embodiments, in Formula 501, L_{501} to L_{503} may each independently be selected from

[0294] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

[0295] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group,

nylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0296] In one or more embodiments, in Formula 501, R_{501} and R_{502} may each independently be selected from

[0297] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and


[0298] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group,

a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$,


[0299] wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0300] In one or more embodiments, xd4 in Formula 501 may be 2, but embodiments are not limited thereto.


[0301] In some embodiments, the fluorescent dopant may be selected from Compounds FD1 to FD22:




FD1



FD2



FD3




FD4


-continued

-continued


FD5



FD6




FD7




-continued


FD8




FD9




FD10



-continued




-continued

FD12Cc1ccc(cc1N(c2ccc3c(c2)sc4ccccc34))c5ccc6ccccc6c5FD16Cc1ccc(cc1N(c2ccc3c(c2)sc4ccccc34))c5ccc6ccccc6c5FD13CC(C)c1ccc(cc1N(c2ccc3c(c2)oc4ccccc34))c5ccc6ccccc6c5FD17Cc1ccc(cc1N(c2ccc3c(c2)sc4ccccc34))c5ccc6ccccc6c5FD14c1ccc(cc1N(c2ccc3c(c2)sc4ccccc34))c5ccc6ccccc6c5FD18CC(C)c1ccc(cc1N(c2ccc3c(c2)sc4ccccc34))c5ccc6ccccc6c5


-continued

FD19





-continued

FD21




FD22


FD20




[0302] In some embodiments, the fluorescent dopant may be selected from the following compounds, but embodiments are not limited thereto:



DPVBi



DPAVBi



[0303] Electron transport region in organic layer 150

[0304] The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure each having a plurality of layers, each having a plurality of different materials.

[0305] The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer, but embodiments are not limited thereto.

[0306] In some embodiments, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein layers of each structure are sequentially stacked on the emission layer in each stated order, but embodiments are not limited thereto.

[0307] The electron transport region may include the heterocyclic compound represented by Formula 1.

[0308] Further, the electron transport region, e.g., a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region, may include a metal-free compound as well as the heterocyclic compound represented by Formula 1. The metal-free compound may include at least one π electron-depleted nitrogen-containing ring.

[0309] The term “ π electron-depleted nitrogen-containing ring,” as used herein, refers to a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

[0310] For example, the “ π electron-depleted nitrogen-containing ring” may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed, or iii) a heteropolycyclic group in which at least one 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety is condensed with at least one C_5 - C_{60} carbocyclic group.

[0311] Examples of the π electron-depleted nitrogen-containing ring may include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an iso-benzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, a thiadiazole, an imidazopyridine, an imidazopyrimidine, and an azacarbazole, but embodiments are not limited thereto.

[0312] In some embodiments, the electron transport region may include a compound represented by Formula 601:



[0313] wherein, in Formula 601,

[0314] Ar_{601} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0315] $xe11$ may be 1, 2, or 3,

[0316] L_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a sub-

stituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0317] xe1 may be an integer from 0 to 5,

[0318] R₆₀₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₆₀₁)(Q₆₀₂)(Q₆₀₃), —C(=O)(Q₆₀₁), —S(=O)₂(Q₆₀₁), and —P(=O)(Q₆₀₁)(Q₆₀₂),

[0319] wherein Q₆₀₁ to Q₆₀₃ may each independently be a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and

[0320] xe21 may be an integer from 1 to 5.

[0321] In one embodiment, at least one of Ar₆₀₁ groups in the number of xe11 and R₆₀₁ groups in the number of xe21 may include the π electron-depleted nitrogen-containing ring.

[0322] In some embodiments, Ar₆₀₁ in Formula 601 may be selected from

[0323] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

[0324] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a

quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),


[0325] wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0326] When xe11 in Formula 601 is 2 or greater, at least two Ar₆₀₁ groups may be linked via a single bond.

[0327] In one or more embodiments, Ar₆₀₁ in Formula 601 may be an anthracene group.

[0328] In some embodiments, the compound represented by Formula 601 may be represented by Formula 601-1:

Formula 601-1



[0329] wherein, in Formula 601-1,

[0330] X₆₁₄ may be N or C(R₆₁₄), X₆₁₅ may be N or C(R₆₁₅), X₆₁₆ may be N or C(R₆₁₆), and at least one selected from X₆₁₄ to X₆₁₆ may be N,

[0331] descriptions for L₆₁₁ to L₆₁₃ may each independently be the same as those for L₆₀₁ as provided herein,

[0332] descriptions for xe611 to xe613 may each independently be the same as those for xe1 as provided herein,

[0333] descriptions for R₆₁₁ to R₆₁₃ may each independently be the same as those for R₆₀₁ as provided herein, and

[0334] R₆₁₄ to R₆₁₆ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0335] In one embodiment, in Formulae 601 and 601-1, L₆₀₁ and L₆₁₁ to L₆₁₃ may each independently be selected from

[0336] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene

group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group; and

[0337] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolylenylene group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, but embodiments are not limited thereto.

[0338] In one or more embodiments, in Formulae 601 and 601-1, x_{e1} and x_{e611} to x_{e613}, may each independently be 0, 1, or 2.

[0339] In one or more embodiments, in Formulae 601 and 601-1, R₆₀₁ and R₆₁₁ to R₆₁₃ may each independently be selected from

[0340] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolylenylene group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

[0341] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolylenylene group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

phenanthrolyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


[0342] $-S(=O)_2(Q_{601})$ and $-P(=O)(Q_{601})(Q_{602})$,

[0343] wherein descriptions for Q_{601} and Q_{602} may each independently be understood by referring to those provided herein.


[0344] The electron transport region may include at least one compound selected from Compounds ET1 to ET36, but embodiments are not limited thereto:

-continued


ET2




ET3




ET1







ET4



-continued




-continued




-continued

ET10





-continued

ET13





ET11

ET14




ET12

ET15




-continued




ET16

-continued





ET18

ET19




ET17

ET20




-continued




ET21


-continued




ET24




ET22



ET25




ET23



ET26


-continued

ET27




-continued


ET30




ET28




ET29




ET31



ET32




-continued





-continued

ET36








[0345] In one or more embodiments, the electron transport region may include at least one selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAlq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ:

ET34



ET35





[0346] The thicknesses of the buffer layer, the hole blocking layer, or the electron control layer may each independently be in a range of about 20 Å to about 1,000 Å, and in some embodiments, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer or the electron control layer are within any of these ranges, excellent hole blocking characteristics or excellent electron controlling characteristics may be obtained without a substantial increase in driving voltage.

[0347] The thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, and in some embodiments, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within any of these ranges, excellent electron transport characteristics may be obtained without a substantial increase in driving voltage.

[0348] The electron transport region (e.g., the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a material including metal.

[0349] The material including metal may include at least one selected from an alkali metal complex and an alkaline earth metal complex. The alkali metal complex may include a metal ion selected from a lithium (Li) ion, a sodium (Na) ion, a potassium (K) ion, a rubidium (Rb) ion, and a cesium (Cs) ion. The alkaline earth metal complex may include a metal ion selected from a beryllium (Be) ion, a magnesium (Mg) ion, a calcium (Ca) ion, a strontium (Sr) ion, and a barium (Ba) ion. Each ligand coordinated with the metal ion of the alkali metal complex and the alkaline earth metal complex may independently be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyloxazole, a hydroxyphenylthiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenyl thiadiazole, a hydroxyphenyl pyridine, a hydroxyphenyl benzimidazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments are not limited thereto.

[0350] For example, the material including metal may include a Li complex. The Li complex may include, e.g., Compound ET-D1 (lithium quinolate, LiQ) or Compound ET-D2:

[0351] The electron transport region may include an electron injection layer that facilitates injection of electrons from the second electrode 190. The electron injection layer may be in direct contact with the second electrode 190.

[0352] The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers, each including a plurality of different materials.

[0353] The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth metal complex, a rare earth metal complex, or a combination thereof.

[0354] The alkali metal may be selected from Li, Na, K, Rb, and Cs. In one embodiment, the alkali metal may be Li, Na, or Cs. In one or more embodiments, the alkali metal may be Li or Cs, but embodiments are not limited thereto.

[0355] The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

[0356] The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

[0357] The alkali metal compound, the alkaline earth metal compound, and the rare earth metal compound may each independently be selected from oxides and halides (e.g., fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth metal, and the rare earth metal, respectively.

[0358] The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, KI, or RbI. In one embodiment, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, and KI, but embodiments are not limited thereto.

[0359] The alkaline earth metal compound may be selected from alkaline earth metal compounds such as BaO, SrO, CaO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ (where $0 < x < 1$), and $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ (where $0 < x < 1$). In one embodiment, the alkaline earth metal compound may be selected from BaO, SrO, and CaO, but embodiments are not limited thereto.

[0360] The rare earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one embodiment, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 , but embodiments are not limited thereto.

[0361] The alkali metal complex, the alkaline earth metal complex, and the rare earth metal complex may each include ions of the above-described alkali metal, alkaline earth

metal, and rare earth metal. Each ligand coordinated with the metal ion of the alkali metal complex, the alkaline earth metal complex, and the rare earth metal complex may independently be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyl oxazole, a hydroxyphenyl thiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenyl thiadiazole, a hydroxyphenyl pyridine, a hydroxyphenyl benzimidazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments are not limited thereto.

[0362] The electron injection layer may consist of an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth metal complex, a rare earth metal complex, or a combination thereof, as described above. In some embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, the alkali metal, the alkaline earth metal, the rare earth metal, the alkali metal compound, the alkaline earth metal compound, the rare earth metal compound, the alkali metal complex, the alkaline earth metal complex, the rare earth metal complex, or a combination thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

[0363] The thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, and in some embodiments, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within any of these ranges, excellent electron injection characteristics may be obtained without a substantial increase in driving voltage.

[0364] Second Electrode 190

[0365] The second electrode 190 may be disposed on the organic layer 150. In an embodiment, the second electrode 190 may be a cathode that is an electron injection electrode. In this embodiment, a material for forming the second electrode 190 may be a material having a low work function, for example, a metal, an alloy, an electrically conductive compound, or a combination thereof.

[0366] The second electrode 190 may include at least one selected from lithium (Li), silver (Ag), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO, but embodiments are not limited thereto. The second electrode 190 may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

[0367] The second electrode 190 may have a single-layered structure, or a multi-layered structure including two or more layers.

[0368] Description of FIGS. 2 to 4

[0369] Referring to FIG. 2, an organic light-emitting device 20 has a first capping layer 210, the first electrode 110, the organic layer 150, and the second electrode 190 structure, wherein the layers are sequentially stacked in this stated order. Referring to FIG. 3, an organic light-emitting device 30 has the first electrode 110, the organic layer 150, the second electrode 190, and a second capping layer 220 structure, wherein the layers are sequentially stacked in this stated order. Referring to FIG. 4, an organic light-emitting device 40 has the first capping layer 210, the first electrode 110, the organic layer 150, the second electrode 190, and the second capping layer 220 structure, wherein the layers are stacked in this stated order.

[0370] The first electrode 110, the organic layer 150, and the second electrode 190 illustrated in FIGS. 2 to 4 may be substantially the same as those illustrated in FIG. 1.

[0371] In the organic light-emitting devices 20 and 40, light emitted from the emission layer in the organic layer 150 may pass through the first electrode 110 (which may be a semi-transmissive electrode or a transmissive electrode) and through the first capping layer 210 to the outside. In the organic light-emitting devices 30 and 40, light emitted from the emission layer in the organic layer 150 may pass through the second electrode 190 (which may be a semi-transmissive electrode or a transmissive electrode) and through the second capping layer 220 to the outside.


[0372] The first capping layer 210 and the second capping layer 220 may improve the external luminescence efficiency based on the principle of constructive interference.


[0373] The first capping layer 210 and the second capping layer 220 may each independently be a capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

[0374] At least one of the first capping layer 210 and the second capping layer 220 may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine derivatives, naphthalocyanine derivatives, alkali metal complexes, and alkaline earth metal complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may optionally be substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one embodiment, at least one of the first capping layer 210 and the second capping layer 220 may each independently include an amine-based compound.

[0375] In one or more embodiments, at least one of the first capping layer 210 and the second capping layer 220 may each independently include a compound represented by Formula 201 or a compound represented by 202.

[0376] In one or more embodiments, at least one of the first capping layer 210 and the second capping layer 220 may each independently include a compound selected from Compounds HT28 to HT33 and Compound CP1 to CP5, but embodiments are not limited thereto:





[0377] Hereinbefore, the organic light-emitting device has been described with reference to FIGS. 1 to 4, but embodiments are not limited thereto.

[0378] The layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region may be formed in a set or specific region by using one or more suitable methods such as vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser printing, and laser-induced thermal imaging.

[0379] When the layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region are each formed by vacuum deposition, the vacuum deposition may be performed at a deposition temperature in a range of about 100° C. to about 500° C. at a vacuum degree in a range of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition rate in a range of about 0.01

Angstroms per second (Å/sec) to about 100 Å/sec, depending on the material to be included in each layer and the structure of each layer to be formed.

[0380] When the layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region are each formed by spin coating, the spin coating may be performed at a coating rate of about 2,000 revolutions per minute (rpm) to about 5,000 rpm and at a heat treatment temperature of about 80° C. to about 200° C., depending on the material to be included in each layer and the structure of each layer to be formed.

[0381] General definitions of some of the substituents

[0382] The term “C₁-C₆₀ alkyl group,” as used herein, refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Examples thereof include a methyl group, an ethyl group, a propyl group, an iso-butyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term “C₁-C₆₀ alkenylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₁-C₆₀ alkyl group.

[0383] The term “C₂-C₆₀ alkenyl group,” as used herein, refers to a hydrocarbon group having at least one carbon-carbon double bond at a main chain (e.g., in the middle) or at the terminus of the C₂-C₆₀ alkyl group. Examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkenyl group.

[0384] The term “C₂-C₆₀ alkynyl group,” as used herein, refers to a hydrocarbon group having at least one carbon-carbon triple bond at a main chain (e.g., in the middle) or at the terminus of the C₂-C₆₀ alkyl group. Examples thereof include an ethynyl group and a propynyl group. The term “C₂-C₆₀ alkynylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkynyl group.

[0385] The term “C₁-C₆₀ alkoxy group,” as used herein, refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is a C₁-C₆₀ alkyl group). Examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

[0386] The term “C₃-C₁₀ cycloalkyl group,” as used herein, refers to a monovalent monocyclic saturated hydrocarbon group including 3 to 10 carbon atoms. Examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkyl group.

[0387] The term “C₁-C₁₀ heterocycloalkyl group,” as used herein, refers to a monovalent monocyclic group including at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms. Examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuran group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkyl group.

[0388] The term “C₃-C₁₀ cycloalkenyl group,” as used herein, refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in its ring, and is not aromatic. Examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl

group. The term “C₃-C₁₀ cycloalkenylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkenyl group.

[0389] The term “C₁-C₁₀ heterocycloalkenyl group,” as used herein, refers to a monovalent monocyclic group including at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Examples of the C₁-C₁₀ heterocycloalkenyl group include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranlyl group, and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0390] The term “C₆-C₆₀ aryl group,” as used herein, refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. The term “C₆-C₆₀ arylene group,” as used herein, refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each independently include two or more rings, the respective rings may be fused (e.g., combined together).

[0391] The term “C₁-C₆₀ heteroaryl group,” as used herein, refers to a monovalent group having a heterocyclic aromatic system having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group,” as used herein, refers to a divalent group having a heterocyclic aromatic system having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 60 carbon atoms. Examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each independently include two or more rings, the respective rings may be fused (e.g., combined together).

[0392] The term “C₆-C₆₀ aryloxy group,” as used herein, refers to a group represented by —OA₁₀₂ (where A₁₀₂ is a C₆-C₆₀ aryl group). The term “C₆-C₆₀ arylthio group,” as used herein, refers to a group represented by —SA₁₀₃ (where A₁₀₃ is a C₆-C₆₀ aryl group).

[0393] The term “monovalent non-aromatic condensed polycyclic group,” as used herein, refers to a monovalent group that has two or more rings condensed and only carbon atoms as ring forming atoms (e.g., 8 to 60 carbon atoms), wherein the entire molecular structure is non-aromatic. An example of the monovalent non-aromatic condensed polycyclic group may be a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group,” as used herein, refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed polycyclic group.

[0394] The term “monovalent non-aromatic condensed heteropolycyclic group,” as used herein, refers to a monovalent group that has two or more condensed rings and at least one heteroatom selected from N, O, Si, P, and S, in addition to carbon atoms (e.g., 1 to 60 carbon atoms), as a ring-forming atom, wherein the entire molecular structure is non-aromatic. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group.

The term “divalent non-aromatic condensed heteropolycyclic group,” as used herein, refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0395] The term “C₅-C₆₀ carbocyclic group,” as used herein, refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms only as ring-forming atoms. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The term “C₅-C₆₀ carbocyclic group,” as used herein, refers to a ring (e.g., a benzene group), a monovalent group (e.g., a phenyl group), or a divalent group (e.g., a phenylene group). In one or more embodiments, depending on the number of substituents coupled or connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

[0396] The term “C₁-C₆₀ heterocyclic group,” as used herein, refers to a group having substantially the same structure as the C₅-C₆₀ carbocyclic group, except that at least one heteroatom selected from N, O, Si, P, and S is used as a ring-forming atom, in addition to carbon atoms (e.g., 1 to 60 carbon atoms).

[0397] The term “fluorine-containing C₅-C₆₀ carbocyclic group,” as used herein, refers to the C₅-C₆₀ carbocyclic group having at least one substituent of —F. The term “substituted fluorine-containing C₅-C₆₀ carbocyclic group,” as used herein, refers to the fluorine-containing C₅-C₆₀ carbocyclic group further substituted with at least one substituent defined herein. The term “unsubstituted fluorine-containing C₅-C₆₀ carbocyclic group,” as used herein, refers to the fluorine-containing C₅-C₆₀ carbocyclic group having hydrogen only as a substituent, other than —F.

[0398] The term “fluorine-containing C₁-C₆₀ heterocyclic group,” as used herein, refers to the C₁-C₆₀ heterocyclic group having at least one substituent of —F. The term “substituted fluorine-containing C₁-C₆₀ heterocyclic group,” as used herein, refers to the fluorine-containing C₁-C₆₀ heterocyclic group further substituted with at least one substituent defined herein. The term “unsubstituted fluorine-containing C₁-C₆₀ heterocyclic group,” as used herein, refers to the fluorine-containing C₁-C₆₀ heterocyclic group having hydrogen only as a substituent, other than —F.

[0399] In the present specification, at least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0400] deuterium (-D), —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0401] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

[0402] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0403] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and

[0404] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

[0405] wherein Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0406] The term “Ph,” as used herein, represents a phenyl group. The term “Me,” as used herein, represents a methyl

group. The term “Et,” as used herein, represents an ethyl group. The term “ter-Bu” or “Bu^t,” as used herein, represents a tert-butyl group. The term “OMe,” as used herein, represents a methoxy group.

[0407] The term “biphenyl group,” as used herein, refers to a phenyl group substituted with a phenyl group. In other words, the “biphenyl group” may be a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

[0408] The term “terphenyl group,” as used herein, refers to a phenyl group substituted with a biphenyl group. In other words, the “terphenyl group” may be a substituted phenyl group having a C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group as a substituent.



[0409] The symbols * and *, as used herein, unless defined otherwise, refer to a binding site to an adjacent atom in a corresponding formula.

[0410] Hereinafter, compounds and an organic light-emitting device according to one or more embodiments will be described in more detail with reference to Synthesis Examples and Examples. The wording “B was used instead of A” used in describing Synthesis Examples refers to that an identical (or substantially identical) number of molar equivalents of B was used in place of A.


SYNTHESIS EXAMPLES

Synthesis Example 1: Synthesis of Compound 2

[0411]



-continued



Synthesis of Intermediate I-1

[0412] 1.84 g (10 mmol) of cyanuric chloride, 1.22 g (10 mmol) of phenylboronic acid, 1.15 g (1 mmol) of $\text{Pd}(\text{PPh}_3)_4$, and 4.14 g (30 mmol) of potassium carbonate were dissolved in 100 mL of a mixture solution of tetrahydrofuran (THF) and H_2O (at a ratio of 2:1). Subsequently, the mixture was stirred at a temperature of about 80°C . for about 24 hours. Distilled water was added to the resulting mixture, and an organic layer was extracted therefrom three times using 60 mL of ethyl acetate. The obtained organic layer was dried using magnesium sulfate (MgSO_4), and a solvent was removed therefrom by evaporation to obtain a residue. The residue was separated and purified through silica gel chromatography to thereby obtain 1.92 g of Intermediate I-1 (yield: 85%). The obtained compound was identified by liquid chromatography-mass spectrometry (LC-MS).

[0413] $\text{C}_9\text{H}_5\text{Cl}_2\text{N}_3$; M^+ 225.03

Synthesis of Intermediate I-2

[0414] 2.26 g (10 mmol) of Intermediate I-1 was dissolved in 100 mL of THF. Subsequently, 10 mL (10 mmol) of 4-fluorophenyl magnesiumbromide was added dropwise to the mixture solution at a temperature of 0°C . Next, the resulting mixture was stirred for 12 hours at a temperature of 0°C ., which was then allowed to raise to room temperature. Distilled water was added to the resulting mixture, and an organic layer was extracted therefrom three times using 60 mL of ethyl acetate. The obtained organic layer was dried using MgSO_4 , and a solvent was removed therefrom by evaporation to obtain a residue. The residue was separated and purified through silica gel chromatography to thereby obtain 2.14 g of Intermediate I-2 (yield: 75%). The obtained compound was identified by LC-MS.

[0415] $\text{C}_{15}\text{H}_9\text{ClFN}_3$; M^+ 285.13

Synthesis of Compound 2

[0416] 2.85 g (10 mmol) of Intermediate I-2, 4.44 g (11 mmol) of diphenyl(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide, 1.14 g (10 mol %) of $\text{Pd}(\text{PPh}_3)_4$, and 4.15 g (30 mmol) of K_2CO_3 were dissolved in 100 mL of a mixture solution of THF and H_2O (at a ratio of 2:1). Subsequently, the mixture was stirred at a temperature of about 80°C . for about 24 hours. The resulting mixture was cooled to room temperature, and an organic layer was extracted therefrom three times using 60 mL of

ethyl acetate. The obtained organic layer was dried using MgSO_4 , and a solvent was removed therefrom by evaporation to obtain a residue. The residue was separated and purified through silica gel chromatography to thereby obtain 4.06 g of Compound 2 (yield: 77%). The obtained compound was identified by LC-MS.

[0417] $\text{C}_{33}\text{H}_{23}\text{FN}_3\text{OP}$; M^+ 527.17

Synthesis Example 2: Synthesis of Compound 3

[0418] 3.97 g of Compound 3 was obtained in substantially the same manner as in Synthesis of Compound 2, except that 1.84 g (10 mmol) of cyanuric chloride was used as a start material, and 20 mL (20 mmol) of 4-fluorophenyl magnesiumbromide was added dropwise instead of phenylboronic acid in Synthesis of Intermediate I-1 (yield: 73%). The obtained compound was identified by mass spectrometry/fast atom bombardment (MS/FAB) and ^1H nuclear magnetic resonance (NMR).

[0419] $\text{C}_{33}\text{H}_{22}\text{F}_2\text{N}_3\text{OP}$; M^+ 545.14

Synthesis Example 3: Synthesis of Compound 6

[0420] 3.60 g of Compound 6 was obtained in substantially the same manner as in Synthesis of Compound 3, except that 10 mmol of 4-bromo-1,2-difluorobenzene was used instead of 4-fluorophenyl magnesium bromide (yield: 62%). The obtained compound was identified by MS/FAB and ^1H NMR.

[0421] $\text{C}_{33}\text{H}_{20}\text{F}_4\text{N}_3\text{OP}$; M^+ 581.15

Synthesis Example 4: Synthesis of Compound 17

[0422] 4.71 g of Compound 17 was obtained in substantially the same manner as in Synthesis of Compound 2, except that (4-cyanophenyl)boronic acid was used instead of phenylboronic acid, and diphenyl(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide was used instead of diphenyl(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide (yield: 75%). The obtained compound was identified by MS/FAB and ^1H NMR.

[0423] $\text{C}_{40}\text{H}_{26}\text{FN}_4\text{OP}$; M^+ 628.17

Synthesis Example 5: Synthesis of Compound 30

[0424] 4.78 g of Compound 30 was obtained in substantially the same manner as in Synthesis of Compound 3, except that diphenyl(4-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)phenyl)phosphine oxide was used instead of diphenyl(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide (yield: 64%). The obtained compound was identified by MS/FAB and ^1H NMR.

[0425] $\text{C}_{49}\text{H}_{32}\text{F}_2\text{N}_3\text{OP}$; M^+ 747.25

Synthesis Example 6: Synthesis of Compound 78

[0426] 4.49 g of Compound 78 was obtained in substantially the same manner as in Synthesis of Compound 3, except that diphenyl(3-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)phenyl)phosphine oxide was used instead of diphenyl(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide (yield: 60%). The obtained compound was identified by MS/FAB and ^1H NMR.

[0427] $\text{C}_{49}\text{H}_{32}\text{F}_2\text{N}_3\text{OP}$; M^+ 747.24

Synthesis Example 7: Synthesis of Compound 98

[0428] 4.13 g of Compound 98 was obtained in substantially the same manner as in Synthesis of Compound 3, except that diphenyl(3-(2-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)dibenzo[b,d]furan-4-yl)phenyl)phosphine oxide was used instead of diphenyl(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide (yield: 58%). The obtained compound was identified by MS/FAB and ^1H NMR.

[0429] $\text{C}_{45}\text{H}_{28}\text{F}_2\text{N}_3\text{O}_2\text{P}$: M^+ 711.20

Synthesis Example 8: Synthesis of Compound 116

[0430] 3.40 g of Compound 116 was obtained in substantially the same manner as in Synthesis of Compound 3, except that 5-phenyl-3-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)benzo[b]phosphindole 5-oxide was used instead of diphenyl(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide (yield: 55%). The obtained compound was identified by MS/FAB and ^1H NMR.

[0431] $\text{C}_{39}\text{H}_{24}\text{F}_2\text{N}_3\text{OP}$: M^+ 619.18

to a size of 50 millimeters (mm) $\times$ 50 mm $\times$ 0.7 mm, sonicated in isopropyl alcohol and pure water for 5 minutes in each solvent, and cleaned by exposure to ultraviolet rays and ozone for 30 minutes so as to use the ITO glass substrate as a substrate and an anode. Then, the glass substrate was mounted on a vacuum-deposition device.

[0433] 2-TNATA was vacuum-deposited on the ITO anode formed on the glass substrate to form a hole injection layer having a thickness of about 600 Å. 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (hereinafter, referred to as "NPB") was then vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of about 300 Å.

[0434] On the hole transport layer, 9,10-di-naphthalene-2-yl-anthracene (hereinafter referred to as "ADN") as a host and 4,4'-bis[2-(4-(N,N-diphenylamino)phenyl)vinyl]biphenyl (hereinafter referred to as "DPAVBI") as a dopant were co-deposited to a weight ratio of about 98:2 to form an emission layer having a thickness of about 300 Å.

[0435] Compound 2 was deposited on the emission layer to form an electron transport layer having a thickness of 300

TABLE 1


Compound	^1H NMR (CDCl_3 , 500 MHz)	HR-EIMS	
		found	calc.
2	δ = 8.80-8.79 (m, 2H), 8.47-8.45 (m, 2H), 8.34-8.31 (m, 2H), 8.07-8.02 (m, 2H), 7.70-7.68 (m, 4H), 7.63-7.59 (m, 2H), 7.49-7.47 (m, 2H), 7.44-7.39 (m, 5H), 7.29-7.25 (m, 2H)	527.17	527.16
3	δ = 8.47-8.45 (m, 2H), 8.34-8.31 (m, 4H), 8.07-8.02 (m, 2H), 7.70-7.66 (m, 4H), 7.52-7.48 (m, 2H), 7.44-7.42 (m, 4H), 7.29-7.25 (m, 4H)	545.14	545.15
6	δ = 8.47-8.42 (m, 4H), 7.19-7.16 (m, 2H), 8.07-8.02 (m, 2H), 7.70-7.66 (m, 4H), 7.52-7.48 (m, 2H), 7.44-7.41 (m, 4H), 7.31-7.25 (m, 2H)	581.15	581.13
17	δ = 8.58-8.56 (m, 2H), 8.41-8.38 (m, 2H), 8.34-8.31 (m, 2H), 8.00-7.97 (m, 1H), 7.89-7.84 (m, 4H), 7.70-7.63 (m, 5H), 7.57-7.48 (m, 4H), 7.43-7.41 (m, 4H), 7.29-7.25 (m, 2H)	628.17	628.18
30	δ = 8.53-8.50 (m, 2H), 8.34-8.31 (m, 4H), 8.07-8.05 (m, 2H), 7.73-7.66 (m, 7H), 7.62-7.57 (m, 4H), 7.52-7.42 (m, 7H), 7.29-7.25 (m, 4H), 7.01-6.98 (m, 2H)	747.25	747.23
78	δ = 8.53-8.50 (m, 2H), 8.34-8.31 (m, 4H), 8.07-8.01 (m, 3H), 7.83-7.81 (m, 1H), 7.70-7.63 (m, 5H), 7.57-7.53 (m, 2H), 7.51-7.46 (m, 4H), 7.43-7.41 (m, 4H), 7.29-7.25 (m, 4H), 7.00-7.69 (m, 2H)	747.24	747.23
98	δ = 9.08-9.06 (m, 1H), 8.73-8.71 (m, 1H), 8.34-8.31 (m, 4H), 8.26-8.23 (m, 1H), 7.96-7.94 (m, 1H), 7.87-7.85 (m, 1H), 7.68-7.62 (m, 6H), 7.54-7.47 (m, 4H), 7.43-7.41 (m, 4H), 7.33-7.25 (m, 5H)	711.20	711.19
116	δ = 8.43-8.41 (m, 2H), 8.34-8.31 (m, 4H), 8.00-7.96 (m, 2H), 7.87-7.77 (m, 6H), 7.57-7.52 (m, 2H), 7.49-7.45 (m, 1H), 7.41-7.37 (m, 2H), 7.35-7.33 (m, 1H), 7.29-7.25 (m, 4H)	619.18	619.16

EXAMPLES


Example 1

[0432] A 15 Ohms per square centimeter (Ω/cm^2) (1,200 Å) ITO glass substrate (available from Corning Inc.) was cut


to a size of 50 millimeters (mm) $\times$ 50 mm $\times$ 0.7 mm, sonicated in isopropyl alcohol and pure water for 5 minutes in each solvent, and cleaned by exposure to ultraviolet rays and ozone for 30 minutes so as to use the ITO glass substrate as a substrate and an anode. Then, the glass substrate was mounted on a vacuum-deposition device.




2-TNATA



NPB



ADN



DPAVB

Examples 2 to 8 and Comparative Examples 1 to 3

[0436] Organic light-emitting devices were manufactured in substantially the same manner as in Example 1, except that the compounds shown in Table 2 were used instead of Compound 2 in forming each electron transport layer.

[0437] The device performances (driving voltage, luminance, and efficiency) of the organic light-emitting device


manufactured in Examples 1 to 8 and Comparative Examples 1 to 3 at a current density of 50 mA/cm² were measured, and the half lifespans of the devices were measured at a current density of 100 mA/cm². The results thereof are shown in Table 2.

[0438] The efficiency and luminescence were measured using a luminance meter PR650 powered by a current voltmeter (Keithley SMU 236).

TABLE 2

	Material	Driving voltage (V)	Current density (mA/cm ²)	Luminescence (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr @ 100 mA/cm ²)
Example 1	Compound 2	4.85	50	3,375	6.75	blue	371 hrs
Example 2	Compound 3	4.51	50	3,595	7.19	blue	398 hrs
Example 3	Compound 6	4.57	50	3,520	7.04	blue	382 hrs
Example 4	Compound 17	4.64	50	3,425	6.85	blue	377 hrs
Example 5	Compound 30	4.60	50	3,690	7.38	blue	422 hrs
Example 6	Compound 78	4.68	50	3,635	7.27	blue	403 hrs
Example 7	Compound 98	4.89	50	3,275	6.55	blue	375 hrs
Example 8	Compound 116	4.84	50	3,320	6.64	blue	384 hrs
Comparative Example 1	Compound 200	5.06	50	3,010	6.02	blue	325 hrs
Comparative Example 2	Compound A	5.17	50	3,185	6.37	blue	379 hrs
Comparative Example 3	Compound B	5.31	50	3,150	6.30	blue	297 hrs

Compound 200



Compound A





TABLE 2-continued

Material	Driving voltage (V)	Current density (mA/cm ²)	Luminescence (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr @ 100 mA/cm ²)
----------	---------------------	---------------------------------------	-----------------------------------	-------------------	----------------	--

Compound B



[0439] Referring to the results of Table 1, it was found that the organic light-emitting devices of Examples 1 to 8 have improved driving voltage, excellent I-V-L characteristics with improved efficiency, and for example, significantly improved lifespan, as compared with the organic light-emitting devices of Comparative Examples 1 to 3.

[0440] In other words, when the compound according to one or more embodiments are used as an electron transport material in a device, the device may have excellent effects in driving voltage, luminescence, efficiency, and lifespan.

[0441] As apparent from the foregoing description, an organic light-emitting device including the heterocyclic compound may have a low driving voltage, high efficiency, long lifespan, and high maximum quantum efficiency.

[0442] It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

[0443] It will be understood that, although the terms “first,” “second,” “third,” etc., may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section described below could be termed a second element, component, region, layer or section, without departing from the spirit and scope of the present disclosure.

[0444] Spatially relative terms, such as “beneath,” “below,” “lower,” “under,” “above,” “upper,” and the like, may be used herein for ease of explanation to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or in operation, in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as “below” or “beneath” or “under” other elements or features would then be oriented “above” the other elements or features. Thus, the example terms “below” and “under” can encompass both an orientation of above and below. The device may be otherwise oriented (e.g., rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein should be interpreted accordingly.

[0445] As used herein, the terms “substantially,” “about,” and similar terms are used as terms of approximation and not


as terms of degree, and are intended to account for the inherent deviations in measured or calculated values that would be recognized by those of ordinary skill in the art. Further, the use of “may” when describing embodiments of the present disclosure refers to “one or more embodiments of the present disclosure.” As used herein, the terms “use,” “using,” and “used” may be considered synonymous with the terms “utilize,” “utilizing,” and “utilized,” respectively. Also, the term “exemplary” is intended to refer to an example or illustration.

[0446] Also, any numerical range recited herein is intended to include all subranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein, and any minimum numerical limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein.

[0447] While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims, and equivalents thereof.

What is claimed is:

1. A heterocyclic compound represented by Formula 1:



wherein, in Formula 1,

X_{11} is selected from N and C- $[(L_{11})_{a1}] - (R_{11})_{b1}$, X_{12} is selected from N and C- $[(L_{12})_{a12}] - (R_{12})_{b12}$, X_{13} is selected from N and C- $[(L_{13})_{a13}] - (R_{13})_{b13}$, X_{14} is selected from N and C- $[(L_{14})_{a14}] - (R_{14})_{b14}$, X_{15} is selected from N and C- $[(L_{15})_{a15}] - (R_{15})_{b15}$,

at least one selected from X_{11} to X_{15} is N, provided that at least one selected from X_{11} to X_{15} is not N, n_1 is selected from 0, 1, and 2, n_2 is selected from 1, 2, and 3, a sum of n_1+n_2 is 3,

L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} are each independently selected from a substituted or unsubstituted C_5 - C_{60} carbocyclic group and a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

a_1 , a_2 , and a_{11} to a_{15} are each independently an integer from 0 to 5,

when a_1 is 0, $*(L_1)_{a_1}-*$ is a single bond; when a_2 is 0, $*(L_2)_{a_2}-*$ is a single bond; when a_{11} is 0, $*(L_{11})_{a_{11}}-*$ is a single bond; when a_{12} is 0, $*(L_{12})_{a_{12}}-*$ is a single bond; when a_{13} is 0, $*(L_{13})_{a_{13}}-*$ is a single bond; when a_{14} is 0, $*(L_{14})_{a_{14}}-*$ is a single bond; when a_{15} is 0, $*(L_{15})_{a_{15}}-*$ is a single bond,

when a_1 is 2 or greater, at least two L_1 groups are identical to or different from each other; when a_2 is 2 or greater, at least two L_2 groups are identical to or different from each other; when a_{11} is 2 or greater, at least two L_{11} groups are identical to or different from each other; when a_{12} is 2 or greater, at least two L_{12} groups are identical to or different from each other; when a_{13} is 2 or greater, at least two L_{13} groups are identical to or different from each other; when a_{14} is 2 or greater, at least two L_{14} groups are identical to or different from each other; when a_{15} is 2 or greater, at least two L_{15} groups are identical to or different from each other, b_1 and b_{11} to b_{15} are each independently an integer from 1 to 10,

when b_1 is 2 or greater, at least two R_1 groups are identical to or different from each other; when b_{11} is 2 or greater, at least two R_{11} groups are identical to or different from each other; when b_{12} is 2 or greater, at least two R_{12} groups are identical to or different from each other; when b_{13} is 2 or greater, at least two R_{13} groups are identical to or different from each other; when b_{14} is 2 or greater, at least two R_{14} groups are identical to or different from each other; when b_{15} is 2 or greater, at least two R_{15} groups are identical to or different from each other,

two adjacent groups selected from L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} are optionally bound to form a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group, the heterocyclic compound represented by Formula 1 comprises at least one —F, and

at least one substituent of the substituted C_5 - C_{60} carbocyclic group and the substituted C_1 - C_{60} heterocyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a

C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{11})(Q_{12})(Q_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), and —P(=O)(Q_{11})(Q_{12});

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q_{21})(Q_{22})(Q_{23}), —N(Q_{21})(Q_{22}), —B(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), and —P(=O)(Q_{21})(Q_{22}); and

—Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

* indicates a binding site to an adjacent atom.

2. The heterocyclic compound of claim 1, wherein X_{11} , X_{13} , and X_{15} are each N, X_{12} is C-[$(L_{12})_{a_{12}}-(R_{12})_{b_{12}}$], and X_{14} is C-[$(L_{14})_{a_{14}}-(R_{14})_{b_{14}}$].

3. The heterocyclic compound of claim 1, wherein L_1 , L_2 , L_{11} to L_{15} , R_1 , and R_{11} to R_{15} are each independently selected from:

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene


group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzoxazole group, a benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothiophene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, and a dibenzocarbazole group; and

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzoxazole group, a benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothiophene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, and a dibenzocarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₆-C₂₀ aryl group, a C₂-C₂₀ heteroaryl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃)













wherein Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a mon-

ovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.











4. The heterocyclic compound of claim 1, wherein L₁, L₂, and L₁₁ to L₁₅ are each independently selected from groups represented by Formulae 3-1 to 3-47:









-continued








-continued




-continued




-continued




-continued




3-42




3-43




3-44



3-45



3-46



3-47

wherein, in Formulae 3-1 to 3-47,

Y_1 is selected from O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, and $Si(Z_6)(Z_7)$,

Z_1 to Z_7 are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyridinyl group, a

pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$,

d_2 is an integer from 0 to 2; when d_2 is 2 or greater, at least two Z_1 groups are identical to or different from each other,

d_3 is an integer from 0 to 3; when d_3 is 2 or greater, at least two Z_1 groups are identical to or different from each other, and at least two Z_2 groups are identical to or different from each other,

d_4 is an integer from 0 to 4; when d_4 is 2 or greater, at least two Z_1 groups are identical to or different from each other, and at least two Z_2 groups are identical to or different from each other,

d_5 is an integer from 0 to 5; when d_5 is 2 or greater, at least two Z_1 groups are identical to or different from each other, and at least two Z_2 groups are identical to or different from each other,


d_6 is an integer from 0 to 6; when d_6 is 2 or greater, at least two Z_1 groups are identical to or different from each other, and at least two Z_2 groups are identical to or different from each other,

d_8 is an integer from 0 to 8; when d_8 is 2 or greater, at least two Z_1 groups are identical to or different from each other,


Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{60} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

* and * each indicate a binding site to an adjacent atom.

5. The heterocyclic compound of claim 1, wherein R_1 and R_{11} to R_{15} are each independently selected from groups represented by Formulae 5-1 to 5-79:




5-1




5-2


-continued




-continued



-continued



-continued



5-29

5-30

5-31

5-32

5-33

5-34

5-35

5-36

5-37











5-38

5-39

-continued




-continued




-continued

5-64




5-74

5-65




5-75

5-66




5-76

5-67




5-77

5-68



5-78

5-69



5-79

5-70

wherein, in Formulae 5-1 to 5-79,

Y₃₁ is selected from O, S, C(Z₃₃)(Z₃₄), N(Z₃₅), and Si(Z₃₆)(Z₃₇),

5-71

Z₃₁ to Z₃₇ are each independently selected from hydrogen,

5-72

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a

5-73

triazinyl group, a dibenzofuranyl group, a dibenzothio-phenyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$,
 e2 is an integer from 0 to 2; when e2 is 2 or greater, at least two Z_{31} groups are identical to or different from each other, and at least two Z_{32} groups are identical to or different from each other,
 e3 is an integer from 0 to 3; when e3 is 2 or greater, at least two Z_{31} groups are identical to or different from each other, at least two Z_{32} groups are identical to or different from each other,
 e4 is an integer from 0 to 4; when e4 is 2 or greater, at least two Z_{31} groups are identical to or different from each other, at least two Z_{32} groups are identical to or different from each other,
 e5 is an integer from 0 to 5; when e5 is 2 or greater, at least two Z_{31} groups are identical to or different from each other, at least two Z_{32} groups are identical to or different from each other,
 e6 is an integer from 0 to 6; when e6 is 2 or greater, at least two Z_{31} groups are identical to or different from each other, at least two Z_{32} groups are identical to or different from each other,
 e7 is an integer from 0 to 7; when e7 is 2 or greater, at least two Z_{31} groups are identical to or different from each other,
 e9 is an integer from 0 to 9; when e9 is 2 or greater, at least two Z_{31} groups are identical to or different from each other,
 Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryl group substituted with a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and
 * indicates a binding site to an adjacent atom.

6. The heterocyclic compound of claim 1, wherein n1 is 2, and n2 is 1.

7. The heterocyclic compound of claim 1, wherein at least one selected from R_{11} to R_{15} is selected from:

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzox-

azole group, a benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothio-phenylene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothio-phenylene group, a benzocarbazole group, and a dibenzocarbazole group; and

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphenylene group, a hexacene group, a pyrrole group, an imidazole group, a pyrazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzoxazole group, a benzimidazole group, a furan group, a benzofuran group, a thiophene group, a benzothio-phenylene group, a thiazole group, an isothiazole group, a benzothiazole group, an isoxazole group, an oxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a benzoxazole group, a dibenzofuran group, a dibenzothio-phenylene group, a benzocarbazole group, and a dibenzocarbazole group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a $\text{C}_6\text{-C}_{20}$ aryl group, a $\text{C}_2\text{-C}_{20}$ heteroaryl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$,


wherein Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{101}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryl group substituted with a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, wherein at least one selected from R_{11} to R_{15} is substituted with $-\text{F}$.

8. The heterocyclic compound of claim 1, wherein X_{11} , X_{13} , and X_{15} are each N, X_{12} is $\text{C}-[(\text{L}_{12})_{a12}-(\text{R}_{12})_{b12}]$, and X_{14} is $\text{C}-[(\text{L}_{14})_{a14}-(\text{R}_{14})_{b14}]$, wherein at least one of $\text{R}_{12}(\text{s})$ in the number of a12 and $\text{R}_{14}(\text{s})$ in the number of a14 is selected from a substituted or unsubstituted fluorine-containing $\text{C}_5\text{-C}_{60}$ carbocyclic group and a substituted or unsubstituted fluorine-containing $\text{C}_1\text{-C}_{60}$ heterocyclic group.


9. The heterocyclic compound of claim 1, wherein X_{11} , X_{13} , and X_{15} are each N, X_{12} is $\text{C}-[(\text{L}_{12})_{a12}-(\text{R}_{12})_{b12}]$, and

X_{14} is $C-[(L_{14})_{a14}-(R_{14})_{b14}]$, wherein at least one of $R_{12}(S)$ in the number of a12 and $R_{14}(s)$ in the number of a14 is selected from groups represented by Formulae 7-1 to 7-77:


-continued




7-1




7-10




7-2




7-11




7-3




7-12




7-4




7-13




7-5




7-14




7-6




7-15




7-7




7-16



7-8











7-17












7-9









-continued











-continued




-continued




-continued




-continued




7-51




7-52




7-53




7-54




7-55




7-56




7-57



7-58




7-59




7-60


-continued




7-61




7-62




7-63




7-64




7-65




7-66



7-67




7-68




7-69


-continued




7-70




7-71




7-72




7-73




7-74



7-75



7-76



7-77

wherein, in Formulae 7-1 to 7-77,

Z_{41} is selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a

fluoranthrenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a triazinyl group, a dibenzofuran group, a dibenzothiophenyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$.

f_2 is an integer selected from 1 and 2; when f_2 is 2 or greater, at least two Z_{41} groups are identical to or different from each other,

f_3 is an integer from 1 to 3; when f_3 is 2 or greater, at least two Z_{41} groups are identical to or different from each other,

f_4 is an integer from 1 to 4; when f_4 is 2 or greater, at least two Z_{41} groups are identical to or different from each other,

f_5 is an integer from 1 to 5; when f_5 is 2 or greater, at least two Z_{41} groups are identical to or different from each other,

f_6 is an integer from 1 to 6; when f_6 is 2 or greater, at least two Z_{41} groups are identical to or different from each other,


Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

* indicates a binding site to an adjacent atom.


10. The heterocyclic compound of claim 1, wherein a number of $-F(s)$ comprised in the heterocyclic compound is an integer from 1 to 20.

11. The heterocyclic compound of claim 1, being represented by one selected from Formulae 1-2 and 1-3:

Formula 1-2



Formula 1-3



wherein, in Formulae 1-2 and 1-3,

A_1 and A_2 are each independently selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group,

X₂₁ is selected from a single bond, C(R₂₁)(R₂₂), N(R₂₁), O, S, and Si(R₂₁)(R₂₂),

L₃ is defined the same as L₁ of Formula 1,

a₃ is defined the same as a₁ of Formula 1,


R₂₁, R₂₂, Z₁, Z₃₁, and Z₃₂ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

e₅₁, e₅₂, and d₅₁ are each independently an integer from 1 to 10,


X₁₁ to X₁₅, L₁, L₂, a₁, a₂, R₁, and b₁ are respectively defined the same as those of Formula 1, and

Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.


12. The heterocyclic compound of claim 1, being selected from Compounds 1 to 132:




1




2




3



4









5









6









-continued



-continued




-continued




-continued


27




28




29




30




31



32




33




-continued


34




35



36




37




-continued


38




39



40




41




-continued


42




43



44




45




-continued


46




47




48




49




50




-continued




51




52




53



54




55




56

-continued


57




58




59




60



61




62




-continued


63




64




65




66



67




68




-continued

69




70

71





72

73




74

75




-continued




-continued


84




85




86



87




88




-continued


89




90



91




92




-continued


93




94



95




96




-continued


97



98





99




100

101




102





-continued

103





104

105





106

107




108

109




-continued


110




111




112



113




114




-continued

115




116


117




118





119







120



121




-continued




-continued


126




127




128




129



130




131



-continued

132



13. An organic light-emitting device comprising:
a first electrode;
a second electrode facing the first electrode; and
an organic layer between the first electrode and the second electrode and comprising an emission layer and at least one of the heterocyclic compound of claim 1.

14. The organic light-emitting device claim 13, wherein:
the first electrode is an anode,
the second electrode is a cathode,
the organic layer further comprises a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,
the hole transport region comprises a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or a combination thereof, and
the electron transport region comprises a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or a combination thereof.

15. The organic light-emitting device of claim 14, wherein the electron transport region comprises the heterocyclic compound.

16. The organic light-emitting device of claim 14, wherein the electron transport region comprises the electron transport layer, and the electron transport layer comprises the heterocyclic compound.

17. The organic light-emitting device claim 13, wherein the emission layer comprises the heterocyclic compound.

18. The organic light-emitting device of claim 14, wherein the hole transport region comprises a p-dopant having a lowest unoccupied molecular orbital (LUMO) energy level of -3.5 eV or less.

19. The organic light-emitting device of claim 18, wherein the p-dopant comprises a cyano-group-containing compound.

20. The organic light-emitting device claim 13, wherein:
the emission layer is a first emission layer for emitting first color light,

the organic light-emitting device further comprises i) at least one second emission layer for emitting second color light or ii) at least one second emission layer for emitting second color light and at least one third emission layer for emitting third color light, between the first electrode and the second electrode,

a maximum emission wavelength of the first color light, a maximum emission wavelength of the second color light, and a maximum emission wavelength of the third color light are identical to or different from each other, and

the first color light and the second color light are emitted in the form of mixed light, or the first color light, the second color light, and the third color light are emitted in the form of mixed light.

* * * * *

专利名称(译)	杂环化合物和包括其的有机发光装置		
公开(公告)号	US20190131535A1	公开(公告)日	2019-05-02
申请号	US15/969232	申请日	2018-05-02
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE HYOYOUNG PARK JUNHA SIM MUNKI KIM YOUNGKOOK HWANG SEOKHWAN		
发明人	LEE, HYOYOUNG PARK, JUNHA SIM, MUNKI KIM, YOUNGKOOK HWANG, SEOKHWAN		
IPC分类号	H01L51/00 H01L51/50 C07F9/6521 C07F9/6568		
CPC分类号	C07F9/6521 H01L51/504 H01L51/56 H01L51/0052 H01L51/0058 C07F9/65685 H01L51/0073 H01L51/0071 H01L51/5072 H01L51/5012 H01L51/5004 H01L2251/552 H01L51/506 H01L51/5016 H01L51/001 H01L2251/558 H01L51/0067 C07F9/65583 C07F9/65586 H01L51/0069		
优先权	1020170144221 2017-10-31 KR		
外部链接	Espacenet USPTO		

摘要(译)

提供杂环化合物和包含其的有机发光装置。有机发光装置包括：第一电极;面向第一电极的第二电极;和设置在第一电极和第二电极之间的有机层，其中有机层可以包括发光层和至少一种上述杂环化合物。

40

220
190
150
110
210