



(19) **United States**

(12) **Patent Application Publication**

Kim et al.

(10) **Pub. No.: US 2017/0077422 A1**

(43) **Pub. Date: Mar. 16, 2017**

(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) Applicants: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si (KR);
INDUSTRY-ACADEMIC COOPERATION FOUNDATION GYEONGSANG NATIONAL UNIVERSITY, Jinju-si (KR)

(72) Inventors: **Mikyung Kim**, Yongin-si (KR); **Yunhi Kim**, Jinju-si (KR); **Soonki Kwon**, Jinju-si (KR); **Heeyeon Kim**, Yongin-si (KR); **Yunjee Park**, Yongin-si (KR); **Hyein Jeong**, Yongin-si (KR); **Jaeyoung Hwang**, Jinju-si (KR)

(21) Appl. No.: **15/263,136**

(22) Filed: **Sep. 12, 2016**

(30) **Foreign Application Priority Data**

Sep. 14, 2015 (KR) 10-2015-0129782

Publication Classification


(51) **Int. Cl.**
H01L 51/00 (2006.01)
C09K 11/06 (2006.01)
C07D 487/04 (2006.01)
C09K 11/02 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/0072** (2013.01); **C09K 11/025** (2013.01); **C09K 11/06** (2013.01); **H01L 51/0085** (2013.01); **C07D 487/04** (2013.01); **H01L 51/0067** (2013.01); **H01L 51/5056** (2013.01)

(57) **ABSTRACT**

An organic light-emitting device includes: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer includes at least one condensed cyclic compound of Formula 1:

Formula 1



An organic light-emitting device including the condensed cyclic compound according to embodiments of the present disclosure may have low driving voltage, high efficiency, high luminance, and long lifespan.

10

190
150
110

10

190
150
110

**CONDENSED CYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME**

CROSS-REFERENCE TO RELATED
APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2015-0129782, filed on Sep. 14, 2015, in the Korean Intellectual Property Office, the entire disclosure of which is incorporated herein by reference.

BACKGROUND

[0002] 1. Field

[0003] One or more aspects of embodiments of the present disclosure relate to a condensed cyclic compound and an organic light-emitting device including the same.

[0004] 2. Description of the Related Art

[0005] Organic light emitting devices are self-emission devices that have wide viewing angles, high contrast ratios, short response times, and excellent brightness, driving voltage, and response speed characteristics, and can produce full-color images.

[0006] An organic light-emitting device may include a first electrode disposed (e.g., positioned) on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, can then recombine in the emission layer to produce excitons. These excitons transition from an excited state to a ground state, thereby generating light.


SUMMARY

[0007] One or more aspects of example embodiments are directed toward a novel condensed cyclic compound and an organic light-emitting device including the same.

[0008] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0009] According to one or more example embodiments, a condensed cyclic compound is represented by Formula 1:

<Formula 1>



[0010] In Formula 1,

[0011] Ring A₁ and ring A₂ may each independently be a C₆-C₂₀ aromatic ring that does not include a heteroatom as a ring-forming atom, provided that ring A₁ and ring A₂ are not both benzene at the same time;

[0012] L₁ to L₄ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

[0013] a₁ to a₄ may each independently be an integer selected from 0 to 3, and when a₁ is two or more, 2 or more L₁(s) may be identical to or different from each other; when a₂ is two or more, 2 or more L₂(s) may be identical to or different from each other; when a₃ is two or more, 2 or more L₃(s) may be identical to or different from each other, and when a₄ is two or more, 2 or more L₄(s) may be identical to or different from each other;

[0014] Ar₁, Ar₂, R₁, and R₂ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), and —B(Q₆)(Q₇);

[0015] b₁ and b₂ may each independently be an integer selected from 0 to 3, and when b₁ is 2 or more, 2 or more Ar₁(s) may be identical to or different from each other, and when b₂ is 2 or more, 2 or more Ar₂(s) may be identical to or different from each other;

[0016] c₁ and c₂ may each independently be an integer selected from 0 to 3;

[0017] n₁ and n₂ may each independently be an integer selected from 0 to 10; and

[0018] at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, a substituted divalent non-aromatic condensed polycyclic group, a substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl

group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0019] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0020] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

[0021] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

[0022] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

[0023] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄)(Q₃₅) and —B(Q₃₆)(Q₃₇),

[0024] wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ may be each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

BRIEF DESCRIPTION OF THE DRAWING


[0025] These and/or other aspects will become apparent and more readily appreciated from the following description of the example embodiments, taken in conjunction with the drawing, which is a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0026] Reference will now be made in more detail to example embodiments, examples of which are illustrated in the accompanying drawing, wherein like reference numerals refer to like elements throughout. In this regard, the present example embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the example embodiments are merely described below, by referring to the drawing, to explain aspects of the present invention. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed. Expressions such as “at least one of,” “one of,” “at least one selected from,” and “one selected from,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. Further, the use of “may” when describing embodiments of the present invention refers to “one or more embodiments of the present invention.”

[0027] A condensed cyclic compound according to embodiments may be represented by Formula 1:

<Formula 1>



[0028] In Formula 1,

[0029] Ring A₁ and ring A₂ may each independently be a C₆-C₂₀ aromatic ring that does not include a heteroatom as a ring-forming atom, provided that ring A₁ and ring A₂ are not both benzene at the same time (or concurrently).

[0030] Ring A_1 and ring A_2 in Formula 1 are each a ring that is condensed (e.g., fused) with an adjacent 5-membered ring while sharing at least one carbon with the adjacent 5-membered ring.

[0031] For example, ring A_1 and ring A_2 in Formula 1 may each independently be selected from a benzene, a naphthalene, an anthracene, a phenanthrene, a chrysene, and a pyrene.

[0032] In an embodiment, ring A_1 and ring A_2 in Formula 1 may each independently be selected from a benzene, a naphthalene, and a phenanthrene, but are not limited thereto.

[0033] In some embodiments, ring A_1 and ring A_2 in Formula 1 may be identical to or different from each other.

[0034] For example, ring A_1 and ring A_2 in Formula 1 may be identical to each other.

[0035] L_1 to L_4 in Formula 1 may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

[0036] For example, L_1 to L_4 in Formula 1 may each independently be selected from:



[0037] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

[0038] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphth-











ylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenyl group, a pentacenylenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group,

a benzocarbazolyl group, a dibenzocarbazolyl group, a thia-diazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.

[0039] In an embodiment, L_1 to L_4 in Formula 1 may each independently be selected from groups represented by Formulae 3-1 to 3-33:




-continued




-continued


3-21



3-22



3-23



3-24

3-25

3-31

3-32

3-33

[0040] In Formulae 3-1 to 3-33,

[0041] Y₁ may be selected from O, S, C(Z₃)(Z₄), N(Z₅), and Si(Z₆)(Z₇);

3-26

[0042] Z₁ to Z₇ may be each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, and

3-27


3-28

3-29

[0043] d₁ may be an integer selected from 1 to 4, d₂ may be an integer selected from 1 to 3, d₃ may be an integer selected from 1 to 6, d₄ may be an integer selected from 1 to 8, d₅ may be an integer selected from 1 and 2, d₆ may be an integer selected from 1 to 5, and each of * and *' indicates a binding site to a neighboring atom.










3-30

[0044] In some embodiments, L₁ to L₄ in Formula 1 may each independently be selected from groups represented by Formulae 4-1 to 4-28, but they are not limited thereto:




4-1

-continued




-continued

4-2




4-3


4-4



4-5




4-6




4-7



4-8



4-9



4-10



4-11

4-12

4-13

4-14


4-15

4-16


4-17

4-18


-continued




4-19




4-20




4-21




4-22




4-23




4-24



4-25




4-26



4-27

-continued

4-28



[0045] * and *' in Formulae 4-1 and 4-28 may each be a binding site to a neighboring atom, and "D" may refer to deuterium.

[0046] a₁ in Formula 1 indicates the number of L₁(s), and may be an integer selected from 0 to 3. For example, a₁ in Formula 1 may be 0 or 1, and is not limited thereto. When a₁ is 0, *(L₁)_{a1}-*' indicates a single bond. When a₁ is two or more, 2 or more L₁(s) may be identical to or different from each other. a₂, a₃, and a₄ in Formula 1 may be understood by referring to the description of a₁ and the structure of Formula 1.

[0047] a₁ to a₄ in Formula 1 may each independently be 0 or 1.

[0048] Ar₁, Ar₂, R₁, and R₂ in Formula 1 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), and —B(Q₆)(Q₇). Q₁ to Q₇ may be the same as described herein.

[0049] For example, Ar₁ and Ar₂ in Formula 1 may each independently be selected from:

[0050] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spirofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl

group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, and

[0051] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indaceny group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthaceny group, a picenyl group, a perylenyl group, a pentapheny group, a hexaceny group, a pentaceny group, a rubiceny group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indaceny group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthaceny group, a picenyl group, a perylenyl group, a pentapheny group, a hexaceny group, a pentaceny group, a rubiceny group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an

oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃),

[0052] wherein Q₃₁ to Q₃₃ may be each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.

[0053] In an embodiment, Ar₁ and Ar₂ in Formula 1 may each independently be selected from:

[0054] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a benzoimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

[0055] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an

isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}),

[0056] wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, and a naphthyl group.

[0057] R_1 and R_2 in Formula 1 may each independently be selected from:

[0058] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0059] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

[0060] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl


group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}); and

[0061] —Si(Q_1)(Q_2)(Q_3),


[0062] wherein Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0063] In an embodiment, Ar_1 and Ar_2 in Formula 1 may each independently be a group represented by any of Formulae 5-1 to 5-55;


[0064] R_1 and R_2 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, and a group represented by any of Formulae 5-1 to 5-55:




-continued




5-2




5-3




5-4




5-5




5-6




5-7



5-8




5-9




5-10


-continued




5-11




5-12




5-13




5-14




5-15




5-16



5-17













5-18




5-19

-continued




-continued


5-20




5-21




5-22




5-23




5-24




5-25




5-26







5-27



5-28



5-29



5-30

5-31

5-32

5-33

5-34

5-35

5-36

5-37

5-38














5-39

5-40

5-41

5-42


-continued



-continued

5-55

5-43



5-44

[0065] In Formulae 5-1 to Formula 5-55,

[0066] Y_{31} may be selected from O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, and $Si(Z_{36})(Z_{37})$;

[0067] Z_{31} to Z_{37} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group,

[0068] e_2 may be 1 or 2, e_3 may be an integer selected from 1 to 3, e_4 may be an integer selected from 1 to 4, e_5 may be an integer selected from 1 to 5, e_6 may be an integer selected from 1 to 6, e_7 may be an integer selected from 1 to 7, e_9 may be an integer selected from 1 to 9, and * indicates a binding site to a neighboring atom.

[0069] In some embodiments, Ar_1 and Ar_2 in Formula 1 may each independently be a group represented by any of Formulas 6-1 to 6-76; and

[0070] R_1 and R_2 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, and a group represented by any of Formulae 6-1 to 6-76, but they are not limited thereto:


5-49

5-50

5-51


5-52

6-1




5-53

6-2




5-54


6-3









-continued



-continued




-continued




-continued

6-20




6-26

6-21




6-27

6-22




6-28

6-23




6-29

6-24




6-30


6-25



6-31














6-32




6-33

-continued




-continued

6-34




6-45

6-35




6-46

6-36




6-47

6-37




6-48

6-38




6-49

6-39




6-50

6-40




6-51

6-41




6-52

6-42




6-53

6-43

















6-54

6-44




6-55

-continued




-continued

6-56




6-69

6-57




6-70

6-58




6-71

6-59




6-72

6-60




6-73

6-61




6-74

6-62



6-75


6-63



6-76

6-64

6-65



6-66

6-67

[0071] * in Formulae 6-1 to Formula 6-76 indicates a binding site to a neighboring atom.

[0072] For example, Ar₁ and Ar₂ in Formula 1 may be identical to or different from each other. In an embodiment, Ar₁ and Ar₂ in Formula 1 may be identical to each other.

6-68

[0073] b₁ in Formula 1 indicates the number of Ar₁(s), and may be an integer selected from 0 to 3. For example, b₁ may be 1 or 2. When b₁ is 2 or more, 2 or more Ar₁(s) may be identical to or different from each other. b₂ may be understood by referring to the description of b₁ and the structure of Formula 1.


[0074] c_1 in Formula 1 indicates the number of $R_1(s)$, and may be an integer selected from 0 to 3. For example, c_1 may be 0, 1, or 2. When c_1 is 2 or more, 2 or more $R_1(s)$ may be identical to or different from each other. c_2 may be understood by referring to the description of c_1 and the structure of Formula 1.

[0075] n_1 in Formula 1 indicates the number of $^*-(L_3)_{a3}-(R_1)_{c1}$, and may be an integer selected from 0 to 10. For example, n_1 may be an integer selected from 1 to 8. When n_1 is 2 or more, 2 or more $^*-(L_3)_{a3}-(R_1)_{c1}$ may be identical to or different from each other. n_2 may be understood by referring to the description of n_1 and the structure of Formula 1.


[0076] In an embodiment, the condensed cyclic compound may be represented by one of Formulae 1A to 1L:

-continued


<Formula 1D>




<Formula 1A>




<Formula 1E>




<Formula 1B>




<Formula 1F>



<Formula 1C>




<Formula 1G>




-continued


<Formula 1H>




<Formula 1I>



<Formula 1J>




<Formula 1K>



-continued

<Formula 1L>



[0077] In Formulae 1A to 1L, L_1 , L_2 , a_1 , a_2 , Ar_1 , Ar_2 , b_1 , and b_2 are the same as described above, R_{1a} to R_{1h} may each independently be the same as described in connection with R_1 , and R_{2a} to R_{2h} may each independently be the same as described in connection with R_2 .

[0078] For example, in Formulae 1A to 1L,

[0079] L_1 and L_2 may each independently be selected from groups represented by Formulae 3-1 to 3-33;

[0080] a_1 and a_2 may each independently be 0 or 1;

[0081] Ar_1 and Ar_2 may each independently be selected from groups represented by Formulae 5-1 to 5-55;

[0082] b_1 and b_2 may each independently be an integer selected from 1 to 3;

[0083] R_{1a} to R_{1h} and R_{2a} to R_{2h} may each independently be selected from:

[0084] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0085] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

[0086] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a

pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, and a triazinyl group.

[0087] In some embodiments, in Formulae 1A to 1L,

[0088] L_1 and L_2 may each independently be selected from groups represented by Formulae 4-1 to 4-28;

[0089] a_1 and a_2 may each independently be 0 or 1;

[0090] Ar_1 and Ar_2 may each independently be selected from groups represented by Formulae 6-1 to 6-76;

[0091] b_1 and b_2 may each independently be an integer selected from 1 to 3;

[0092] R_{1a} to R_{1h} and R_{2a} to R_{2h} may each independently be selected from:

[0093] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0094] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

[0095] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an



isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, and a triazinyl group.

[0096] In some embodiments, in Formulae 1A to 1L, a_1 and a_2 may each independently be 0 or 1, and b_1 and b_2 may each be 1.

[0097] In some embodiments, in Formulae 1A to 1L,

[0098] R_{1a} to R_{1h} and R_{2a} to R_{2h} may each be hydrogen.


[0099] In some embodiments, the condensed cyclic compound may be selected from Compounds 1 to 12, but is not limited thereto:



1


2

-continued




3

-continued




6


4




7






5



8




-continued



9

-continued

12



10

[0100] In the condensed cyclic compound represented by Formula 1, ring A_1 and ring A_2 may not both be benzene at the same time (or concurrently). When ring A_1 and ring A_2 are both benzene at the same time, the condensed cyclic compound may have low electric stability, and accordingly, the organic light-emitting device manufactured using the condensed cyclic compound may have a short lifespan.

[0101] The condensed cyclic compound represented by Formula 1 may be synthesized by using one or more suitable organic synthesis methods. A synthesis method of the condensed cyclic compound should be apparent to those of ordinary skill in the art in view of the following embodiments.

[0102] At least one condensed cyclic compound of Formula 1 may be used (e.g., included) between a pair of electrodes of an organic light-emitting device. For example, the condensed cyclic compound may be included in an emission layer. Accordingly, an organic light-emitting device according to an embodiment may include: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer includes at least one condensed cyclic compound represented by Formula 1 as described above.

11

[0103] The expression “(an organic layer) includes at least one condensed cyclic compound” used herein may refer to a case in which (an organic layer) includes one or more identical condensed cyclic compounds represented by Formula 1 and/or a case in which (an organic layer) includes two or more different condensed cyclic compounds represented by Formula 1.

[0104] For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. In this regard, Compound 1 may be included in an emission layer of the organic light-emitting device. In some embodiments, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may both be included in the same layer (e.g., Compound 1 and Compound 2 may both be in an emission layer), or may be included in different layers (e.g., Compound 1 may be in an emission layer and Compound 2 may be in an electron transport layer).

[0105] The organic layer may include i) a hole transport region between the first electrode (e.g., anode) and the emission layer, the hole transport region including at least

one selected from a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer, and ii) an electron transport region between the emission layer and the second electrode (e.g., cathode), the electron transport region including at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer. The emission layer may include the condensed cyclic compound represented by Formula 1.

[0106] The term “organic layer” used herein may refer to a single layer and/or a plurality of layers positioned between the first electrode and the second electrode of an organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0107] The drawing is a schematic view of an organic light-emitting device **10** according to an embodiment. The organic light-emitting device **10** includes a first electrode **110**, an organic layer **150**, and a second electrode **190**.

[0108] Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with the drawing.

[0109] In the drawing, a substrate may be additionally disposed (e.g., positioned) under the first electrode **110** or above the second electrode **190**. The substrate may be a glass substrate or a transparent plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and/or water-resistance.

[0110] The first electrode **110** may be formed by depositing or sputtering a material for forming the first electrode **110** on the substrate. When the first electrode **110** is an anode, the material for forming the first electrode **110** may be selected from materials with a high work function, to facilitate hole injection. The first electrode **110** may be a reflective electrode or a transmissive electrode. The material for the first electrode **110** may be a transparent and highly conductive material, and non-limiting examples of such material include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), and zinc oxide (ZnO). When the first electrode **110** is a semi-transmissive electrode or a reflective electrode, as a material for forming the first electrode **110**, at least one selected from magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag) may be used.

[0111] The first electrode **110** may have a single-layer structure, or a multi-layer structure including two or more layers. For example, the first electrode **110** may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode **110** is not limited thereto.

[0112] An organic layer **150** may be disposed on the first electrode **110**. The organic layer **150** may include an emission layer.

[0113] The organic layer **150** may further include a hole transport region positioned between the first electrode and the emission layer, and an electron transport region positioned between the emission layer and the second electrode.

[0114] The hole transport region may include at least one selected from a hole injection layer (HIL), a hole transport

layer (HTL), a buffer layer, and an electron blocking layer (EBL); and the electron transport region may include at least one selected from a hole blocking layer (HBL), an electron transport layer (ETL), and an electron injection layer (EIL), but they are not limited thereto.

[0115] The hole transport region may have a single-layered structure formed of a single material, a single-layered structure formed of a plurality of different materials, or a multi-layered structure having a plurality of layers formed of a plurality of different materials.

[0116] For example, the hole transport region may have a single-layered structure formed of a plurality of different materials; or a structure of hole injection layer/hole transport layer, a structure of hole injection layer/hole transport layer/buffer layer, a structure of hole injection layer/buffer layer, a structure of hole transport layer/buffer layer, or a structure of hole injection layer/hole transport layer/electron blocking layer, wherein the layers of each structure are sequentially stacked from the first electrode **110** in this stated order, but the structure of the hole transport region is not limited thereto.

[0117] When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode **110** by using one or more methods selected from vacuum deposition, spin coating, casting, a Langmuir-Blodgett (LB) method, ink-jet printing, laser-printing, and laser-induced thermal imaging.






[0118] When the hole injection layer is formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of about 100 to about 500° C., at a vacuum degree of about 10⁻⁸ to about 10⁻³ torr, and at a deposition rate of about 0.01 to about 100 Å/sec, by taking into account a compound for forming the hole injection layer to be deposited, and the structure of the hole injection layer to be formed.


[0119] When the hole injection layer is formed by spin coating, the spin coating may be performed at a coating rate of about 2,000 rpm to about 5,000 rpm, and at a temperature of about 80° C. to 200° C., by taking into account a compound for forming the hole injection layer to be deposited, and the structure of the hole injection layer to be formed.

[0120] When the hole transport region includes a hole transport layer, the hole transport layer may be formed on the first electrode **110** or the hole injection layer by using one or more methods selected from vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, and laser-induced thermal imaging. When the hole transport layer is formed by vacuum deposition and/or spin coating, deposition and coating conditions for the hole transport layer may be determined by referring to the deposition and coating conditions for the hole injection layer.


[0121] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, p-NPB, TPD, Spiro-TPD, Spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid

(PANI/CSA), (polyaniline)/poly(4-styrenesulfonate) (Pani/PSS), HT 21, a compound represented by Formula 201 below, and a compound represented by Formula 202 below:







Spiro-TPD




Spiro-NPB




methylated NPB





TAPC



HMTDP



HT 21



[0122] In Formulae 201 and 202,

[0123] L_{201} to L_{205} may be each independently the same as described in connection with L_1 ;

[0124] $\text{xa}1$ to $\text{xa}4$ may be each independently selected from 0, 1, 2, and 3;

[0125] $\text{xa}5$ may be selected from 1, 2, 3, 4, and 5; and

[0126] R_{201} to R_{204} may be each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0127] In some embodiments, in Formulae 201 and 202,

[0128] L_{201} to L_{205} may be each independently selected from:

[0129] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a pyrenylene group, a chrysenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylene group, a quinazolinylene group, a carbazolylene group, and a triazinylene group; and

[0130] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a pyrenylene group,

a chrysenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylene group, a quinazolinylenylene group, a carbazolylene group, and a triazinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group;

[0131] xa1 to xa4 may be each independently 0, 1, or 2;


[0132] xa5 may be 1, 2, or 3;

[0133] R₂₀₁ to R₂₀₄ may be each independently selected from:


[0134] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group; and

[0135] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, an azulenyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group, but they are not limited thereto.


[0136] The compound represented by Formula 201 may be represented by Formula 201A:



[0137] For example, the compound represented by Formula 201 may be represented by Formula 201A-1 below, but is not limited thereto:



[0138] For example, the compound represented by Formula 202 may be represented by Formula 202A below, but is not limited thereto:



[0139] L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ in Formulae 201A, 201A-1, and 202A are already described above, R₂₁₁ may be the same as defined in connection with R₂₀₃, and R₂₁₃ to R₂₁₆ may be each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀

aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0140] For example, in Formulae 201A, 201A-1, and 202A,

[0141] L₂₀₁ to L₂₀₃ may be each independently selected from:

[0142] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a pyrenylene group, a chrysenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylene group, a quinazolinylene group, a carbazolylene group, and a triazinylene group; and

[0143] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a pyrenylene group, a chrysenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylene group, a quinazolinylene group, a carbazolylene group, and a triazinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinylnyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0144] xa1 to xa3 may be each independently 0 or 1;

[0145] R₂₀₃, R₂₁₁, and R₂₁₂ may be each independently selected from:

[0146] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinylnyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0147] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinylnyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F,

—Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinylnyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0148] R₂₁₃ and R₂₁₄ may be each independently selected from:

[0149] a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group;

[0150] a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinylnyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0151] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinylnyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0152] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinylnyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group,

an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group; and

[0153] R_{215} and R_{216} may be each independently selected from:

[0154] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0155] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group;

[0156] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, and a triazinyl group; and


[0157] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group; and

[0158] x_5 may be 1 or 2.


[0159] In some embodiments, R_{213} and R_{214} in Formulae 201A, and 201A-1 may be linked to each other to form a saturated or unsaturated ring.

[0160] The compound represented by Formula 201, and the compound represented by Formula 202 may each independently include compounds HT1 to HT20 illustrated below, but are not limited thereto.

HT1




HT2




-continued

HT3




-continued


HT5



HT4




HT6




-continued

HT7





-continued

HT9




HT10

HT8




-continued

HT11




-continued


HT14




HT15




HT12




HT16




HT13



HT17



-continued




[0161] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer and the hole transport layer are within any of these ranges, satisfactory (or suitable) hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0162] The hole transport region may further include, in addition to the materials described above, a charge-generation material for the improvement of conductive properties.


The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0163] The charge-generation material may be, for example, a p-dopant. The p-dopant may be one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments are not limited thereto. Non-limiting examples of the p-dopant include quinone derivatives (such as tetracyanoquinonodimethane (TCNQ) and/or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ)); metal oxides (such as tungsten oxide and/or molybdenum oxide), and Compound HT-D1 illustrated below, but are not limited thereto.

<Compound HT-D1>



<F4-TCNQ>



[0164] The hole transport region may further include, in addition to the hole injection layer and the hole transport layer, at least one selected from a buffer layer and an electron blocking layer. Since the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, light-emission efficiency of the formed organic light-emitting device may be improved. For use as a material included in the buffer layer, any of the materials that are included in the hole transport region may be used. The electron blocking layer may prevent or reduce the injection of electrons from the electron transport region.

[0165] An emission layer may be formed on the first electrode 110 or the hole transport region by using one or more methods selected from vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, and laser-induced thermal imaging. When the emission layer is formed by vacuum deposition and/or spin coating, deposition and coating conditions for the emission layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0166] When the organic light-emitting device 10 is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and/or a blue emission layer, according to a sub pixel. In some embodiments, the emission layer may have a stacked structure of a red emission layer, a green emission layer, and a blue emission layer, or may include a red-light emission material, a green-light emission material, and a


blue-light emission material, which are mixed with each other in a single layer, to emit white light.

[0167] The emission layer may include the condensed cyclic compound represented by Formula 1.

[0168] The emission layer may include a host and a dopant. The host may include the condensed cyclic compound represented by Formula 1.

[0169] The dopant may include at least one selected from a fluorescent dopant and a phosphorescent dopant.

[0170] The phosphorescent dopant may include an organometallic complex represented by Formula 401 below:



[0171] In Formula 401,

[0172] M may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm);

[0173] X₄₀₁ to X₄₀₄ may be each independently nitrogen or carbon;

[0174] A₄₀₁ and A₄₀₂ rings may be each independently selected from a substituted or unsubstituted benzene, a substituted or unsubstituted naphthalene, a substituted or unsubstituted fluorene, a substituted or unsubstituted spirofluorene, a substituted or unsubstituted indene, a substituted or unsubstituted pyrrole, a substituted or unsubstituted thiophene, a substituted or unsubstituted furan, a substituted or unsubstituted imidazole, a substituted or unsubstituted pyrazole, a substituted or unsubstituted thiazole, a substituted or unsubstituted isothiazole, a substituted or unsubstituted oxazole, a substituted or unsubstituted isoxazole, a substituted or unsubstituted pyridine, a substituted or unsubstituted pyrazine, a substituted or unsubstituted pyrimidine, a substituted or unsubstituted pyridazine, a substituted or unsubstituted quinoline, a substituted or unsubstituted isoquinoline, a substituted or unsubstituted benzoquinoline, a substituted or unsubstituted quinoxaline, a substituted or unsubstituted quinazoline, a substituted or unsubstituted carbazole, a substituted or unsubstituted benzoimidazole, a substituted or unsubstituted benzofuran, a substituted or unsubstituted benzothiophene, a substituted or unsubstituted isobenzothiophene, a substituted or unsubstituted benzoxazole, a substituted or unsubstituted isobenzoxazole, a substituted or unsubstituted triazole, a substituted or unsubstituted oxadiazole, a substituted or unsubstituted triazine, a substituted or unsubstituted dibenzofuran, and a substituted or unsubstituted dibenzothiophene; and

[0175] at least one substituent of the substituted benzene, substituted naphthalene, substituted fluorene, substituted spirofluorene, substituted indene, substituted pyrrole, substituted thiophene, substituted furan, substituted imidazole, substituted pyrazole, substituted thiazole, substituted isothiazole, substituted oxazole, substituted isoxazole, substituted pyridine, substituted pyrazine, substituted pyrimidine, sub-

stituted pyridazine, substituted quinoline, substituted isoquinoline, substituted benzoquinoline, substituted quinoxaline, substituted quinazoline, substituted carbazole, substituted benzoimidazole, substituted benzofuran, substituted benzothiophene, substituted isobenzothiophene, substituted benzoxazole, substituted isobenzoxazole, substituted triazole, substituted oxadiazole, substituted triazine, substituted dibenzofuran, and substituted dibenzothiophene may be selected from:

[0176] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0177] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —N(Q₄₀₁)(Q₄₀₂), —Si(Q₄₀₃)(Q₄₀₄)(Q₄₀₅), and —B(Q₄₀₆)(Q₄₀₇);

[0178] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic heterocondensed polycyclic group, a biphenyl group, and a terphenyl group;

[0179] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic heterocondensed polycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic heterocondensed polycyclic group, a biphenyl group, a terphenyl group, —N(Q₄₁₁)(Q₄₁₂), —Si(Q₄₁₃)(Q₄₁₄)(Q₄₁₅), and —B(Q₄₁₆)(Q₄₁₇); and

[0180] —N(Q₄₂₁)(Q₄₂₂), —Si(Q₄₂₃)(Q₄₂₄)(Q₄₂₅), and —B(Q₄₂₆)(Q₄₂₇);

[0181] L₄₀₁ may be an organic ligand;

[0182] xc1 may be 1, 2, or 3; and

[0183] xc2 may be 0, 1, 2, or 3,


[0184] wherein Q_{401} to Q_{407} , Q_{411} to Q_{417} , and Q_{421} to Q_{427} may be each independently selected from hydrogen, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_6 - C_{60} aryl group, and a C_1 - C_{60} heteroaryl group.

[0185] In Formula 401, L_{401} may be a monovalent, divalent, or trivalent organic ligand. For example, L_{401} may be selected from a halogen ligand (e.g., Cl and/or F), a diketone ligand (e.g., acetylacetonate, 1,3-diphenyl-1,3-propanedionate, 2,2,6,6-tetramethyl-3,5-heptanedionate, and/or hexafluoroacetonate), a carboxylic acid ligand (e.g., picolinate, dimethyl-3-pyrazolecarboxylate, and/or benzoate), a carbon monoxide ligand, an isonitrile ligand, a cyano ligand, and a phosphorous ligand (e.g., phosphine and/or phosphite), but is not limited thereto.

[0186] When A_{401} in Formula 401 has two or more substituents, the substituents of A_{402} may be linked to each other to form a saturated or unsaturated ring.


[0187] When A_{402} in Formula 401 has two or more substituents, the substituents of A_{402} may be linked to each other to form a saturated or unsaturated ring.

[0188] When xc1 in Formula 401 is two or more, a plurality of ligands




in Formula 401 may be identical to or different from each other. When xc1 in Formula 401 is two or more, A_{401} and A_{402} of one ligand may be each independently connected to A_{401} and A_{402} of other neighboring ligands, respectively, either directly (e.g., via a bond such as a single bond) or with a linker or a linking group (e.g., a C_1 - C_5 alkylene group, $-N(R')$ — (wherein R' may be a C_1 - C_{10} alkyl group or a C_6 - C_{20} aryl group) and/or $-C(=O)-$) therebetween.

[0189] The phosphorescent dopant may include at least one of Compounds PD1 to PD74 below, but is not limited thereto:




PD1


-continued




PD2




PD3



PD4








PD5




PD6

-continued




-continued

PD7




PD12

PD8




PD13

PD9




PD14

PD10







PD15

PD11




PD16

-continued




-continued

PD17




PD21

PD18




PD22

PD19




PD23

PD20








PD24

PD25




-continued




-continued

PD26




PD31

PD27




PD32

PD28




PD33

PD29








PD34

PD30




PD35

-continued




-continued

PD36




PD41

PD37




PD42

PD38




PD43

PD39









PD44

PD40




PD45

-continued




-continued

PD46




PD52

PD47




PD53

PD48




PD54

PD49



PD55


PD50



PD56


PD51

-continued




PD57

-continued




PD62


PD58




PD63




PD59




PD64




PD60




PD65








PD61



PD66




-continued




-continued

PD67




PD72

PD68



PD73

PD69




PD74

PD70

[0190] In some embodiments, the phosphorescent dopant may include PtOEP and/or Compound PD75 illustrated below:


PtOEP

PD71




-continued

PD75




[0191] The fluorescent dopant may include at least one selected from DPVBi, DPAVBi, TBPe, DCM, DCJTb, Coumarin 6, and C545T.

DPVBi




DPVBi

DPAVBi






DPAVBi

TBPe




DCM



-continued
DCJTB

Coumarin 6



C545T

C545T

[0192] An amount of the dopant in the emission layer may be, for example, in a range of about 0.01 to about 15 parts by weight based on 100 parts by weight of the host, but is not limited thereto.

[0193] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within any of these ranges, excellent (or suitable) light-emission characteristics may be obtained without a substantial increase in driving voltage.

[0194] An electron transport region may be disposed on the emission layer.

[0195] The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer (ETL), and an electron injection layer, but is not limited thereto.

[0196] For example, the electron transport region may have a structure of electron transport layer/electron injection layer or a structure of hole blocking layer/electron transport layer/electron injection layer, wherein the layers of each structure are sequentially stacked in a direction from the emission layer in the stated order, but the structure of the electron transport region is not limited thereto.


[0197] According to an embodiment, the organic layer 150 of the organic light-emitting device includes an electron transport region positioned between the emission layer and the second electrode 190, wherein the electron transport region includes the condensed cyclic compound represented by Formula 1.

[0198] The electron transport region may include a hole blocking layer. When the emission layer includes a phosphorescent dopant, the hole blocking layer may be formed to prevent or reduce the diffusion of excitons or holes into an electron transport layer.


[0199] When the electron transport region includes a hole blocking layer, the hole blocking layer may be formed on the emission layer by using one or more methods selected from

vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, and laser-induced thermal imaging. When the hole blocking layer is formed by vacuum deposition and/or spin coating, deposition and coating conditions for the hole blocking layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0200] The hole blocking layer may include, for example, at least one of BCP and Bphen, but is not limited thereto.



BCP





Bphen

[0201] A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within any of these ranges, the hole blocking layer may have improved hole blocking ability without a substantial increase in driving voltage.


[0202] The electron transport region may include an electron transport layer. The electron transport layer may be formed on the emission layer or the hole blocking layer by using one or more methods selected from vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, and laser-induced thermal imaging. When an electron transport layer is formed by vacuum deposition and/or spin coating, deposition and coating conditions for the electron transport layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0203] According to an embodiment, the organic layer 150 of the organic light-emitting device may include an electron transport region positioned between the emission layer and the second electrode 190. The electron transport region may include at least one selected from an electron transport layer and an electron injection layer.


[0204] The electron transport layer may include at least one selected from BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ.

Alq₃

Balq




TAZ



NTAZ

[0205] In some embodiments, the electron transport layer may include at least one compound selected from a compound represented by Formula 601 and a compound represented by Formula 602 illustrated below:



<Formula 601>

[0206] In Formula 601,

[0207] Ar₆₀₁ may be selected from:

[0208] a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthalene group, a picene group, a perylene group, a pentaphene group, and an indenoanthracene group; and

[0209] a naphthalene group, a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthalene group, a picene group, a perylene group, a pentaphene group, and an indenoanthracene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, and —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃) (wherein Q₃₀₁ to Q₃₀₃ may be each independently selected from hydrogen, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₁-C₆₀ aryl group, and a C₁-C₆₀ heteroaryl group);

[0210] L₆₀₁ may be the same as explained in connection with L₃₀₁;

[0211] E₆₀₁ may be selected from:

[0212] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl

group, carbazolyl, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, benzoimidazolyl, a benzofuranlyl group, a benzothiophenyl group, isobenzothiazolyl, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and


[0213] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl

group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

[0214] xe1 may be selected from 0, 1, 2, and 3; and

[0215] xe2 may be selected from 1, 2, 3, and 4.

<Formula 602>



[0216] In Formula 602,

[0217] X₆₁₁ may be N or C-(L₆₁₁)_{xe611}-R₆₁₁, X₆₁₂ may be N or C-(L₆₁₂)_{xe612}-R₆₁₂, X₆₁₃ may be N or C-(L₆₁₃)_{xe613}-R₆₁₃, and at least one of X₆₁₁ to X₆₁₃ may be N;

[0218] L₆₁₁ to L₆₁₆ may be each independently the same as explained in connection with L₃₀₁;

[0219] R₆₁₁ to R₆₁₆ may be each independently selected from:

[0220] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and


[0221] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0222] xe611 to xe616 may be each independently selected from 0, 1, 2, and 3.


[0223] The compound represented by Formula 601 and the compound represented by Formula 602 may be each independently selected from Compounds ET1 to ET15 illustrated below:

-continued


ET1




ET4




ET2




ET5



ET3




ET6




-continued

ET11





-continued

ET14




ET15

ET12




ET13



[0224] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within any of the ranges described above, the electron transport layer may have satisfactory (or suitable) electron transport characteristics without a substantial increase in driving voltage.


[0225] The electron transport layer may further include, in addition to the materials described above, a metal-containing material.

[0226] The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) and/or Compound ET-D2:



ET-D1

-continued



ET-D2

[0227] The electron transport region may include an electron injection layer that facilitates the injection of electrons from the second electrode **190**.

[0228] The electron injection layer may be formed on the electron transport layer by using one or more methods selected from vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, and laser-induced thermal imaging. When an electron injection layer is formed by vacuum deposition and/or spin coating, deposition and coating conditions for the electron injection layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0229] The electron injection layer may include at least one selected from LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

[0230] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within any of the ranges described above, the electron injection layer may have satisfactory (or suitable) electron injection characteristics without a substantial increase in driving voltage.

[0231] The second electrode **190** may be disposed (e.g., positioned) on the organic layer **150** having the structure according to embodiments of the present disclosure. The second electrode **190** may be a cathode that is an electron injection electrode, and in this regard, a material for forming the second electrode **190** may be a material having a low work function, for example, a metal, an alloy, an electrically conductive compound, or a mixture thereof. Non-limiting examples of the material for forming the second electrode **190** include lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag). In some embodiments, the material for forming the second electrode **190** may be ITO and/or IZO. The second electrode **190** may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode.

[0232] Hereinbefore, the organic light-emitting device has been described with reference to the drawing, but embodiments of the present disclosure are not limited thereto.

[0233] A C₁-C₆₀ alkyl group used herein may refer to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and non-limiting examples thereof are a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkylene group used herein may refer to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

[0234] A C₁-C₆₀ alkoxy group used herein may refer to a monovalent group represented by—OA₁₀₁ (wherein A₁₀₁ is

the C₁-C₆₀ alkyl group), and non-limiting examples thereof are a methoxy group, an ethoxy group, and an isopropoxy group.

[0235] A C₂-C₆₀ alkenyl group used herein may refer to a hydrocarbon group having at least one carbon double bond at one or more positions along the hydrocarbon chain of the C₂-C₆₀ alkyl group (e.g., in the middle or at either terminal end of the C₂-C₆₀ alkyl group), and non-limiting examples thereof are an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkenylene group used herein may refer to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0236] A C₂-C₆₀ alkynyl group used herein may refer to a hydrocarbon group having at least one carbon triple bond at one or more positions along the hydrocarbon chain of the C₂-C₆₀ alkyl group (e.g., in the middle or at either terminal end of the C₂-C₆₀ alkyl group), and non-limiting examples thereof are an ethynyl group and a propynyl group. A C₂-C₆₀ alkynylene group used herein may refer to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0237] A C₃-C₁₀ cycloalkyl group used herein may refer to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms, and non-limiting examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C₃-C₁₀ cycloalkylene group used herein may refer to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

[0238] A C₁-C₁₀ heterocycloalkyl group used herein may refer to a monovalent monocyclic group having at least one heteroatom selected from N, O, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and non-limiting examples thereof are a tetrahydrofuranyl group and a tetrahydrothiophenyl group. A C₁-C₁₀ heterocycloalkylene group used herein may refer to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

[0239] A C₃-C₁₀ cycloalkenyl group used herein may refer to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof and does not have aromaticity, and non-limiting examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C₃-C₁₀ cycloalkenylene group used herein may refer to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0240] A C₁-C₁₀ heterocycloalkenyl group used herein may refer to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group are a 2,3-hydrofuranyl group and a 2,3-hydrothiophenyl group. A C₁-C₁₀ heterocycloalkenylene group used herein may refer to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0241] A C₆-C₆₀ aryl group used herein may refer to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein may refer to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group

each independently include two or more rings, the respective rings may be fused to each other.

[0242] A C_1 - C_{60} heteroaryl group used herein may refer to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. A C_1 - C_{60} heteroarylene group used herein may refer to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. Non-limiting examples of the C_1 - C_{60} heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C_1 - C_{60} heteroaryl group and the C_1 - C_{60} heteroarylene group each independently include two or more rings, the respective rings may be fused to each other.

[0243] A C_6 - C_{60} aryloxy group used herein may refer to a monovalent group represented by $-OA_{102}$ (wherein A_{102} is the C_6 - C_{60} aryl group), and a C_6 - C_{60} arylthio group used herein may refer to a monovalent group represented by $-SA_{103}$ (wherein A_{103} is the C_6 - C_{60} aryl group).

[0244] A monovalent non-aromatic condensed polycyclic group used herein may refer to a monovalent group that has two or more rings condensed (e.g., fused) to each other, only carbon atoms as ring-forming atoms (e.g., 8 to 60 carbon atoms), and non-aromaticity in the entire molecular structure (e.g., does not have overall aromaticity). A non-limiting example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. A divalent non-aromatic condensed polycyclic group used herein may refer to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0245] A monovalent non-aromatic condensed heteropolycyclic group used herein may refer to a monovalent group that has two or more rings condensed (e.g., fused) to each other, has at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms (e.g., 1 to 60 carbon atoms), as ring-forming atoms, and has non-aromaticity in the entire molecular structure (e.g., does not have overall aromaticity). An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. A divalent non-aromatic condensed heteropolycyclic group used herein may refer to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0246] At least one substituent of the substituted C_3 - C_{10} cycloalkylene group, substituted C_1 - C_{10} heterocycloalkylene group, substituted C_3 - C_{10} cycloalkenylene group, substituted C_1 - C_{10} heterocycloalkenylene group, substituted C_6 - C_{60} arylene group, substituted C_1 - C_{60} heteroarylene group, substituted divalent non-aromatic condensed polycyclic group, substituted divalent non-aromatic condensed heteropolycyclic group, substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0247] deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

[0248] a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, $-Si(Q_{11})(Q_{12})(Q_{13})$, $-N(Q_{14})(Q_{15})$ and $-B(Q_{16})(Q_{17})$;

[0249] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

[0250] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, $-Si(Q_{21})(Q_{22})(Q_{23})$, $-N(Q_{24})(Q_{25})$, and $-B(Q_{26})(Q_{27})$; and

[0251] $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{34})(Q_{35})$, and $-B(Q_{36})(Q_{37})$;

[0252] wherein Q_{11} to Q_{17} , Q_{21} to Q_{27} , and Q_{31} to Q_{37} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

cloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0253] The term “Ph”, as used herein may refer to a phenyl group; the term “Me”, as used herein may refer to a methyl group; the term “Et”, as used herein may refer to an ethyl group; and the terms “ter-Bu” or “Bu”, as used herein may refer to a tert-butyl group.

[0254] Hereinafter, an organic light-emitting device according to one or more embodiments of the present disclosure will be described in more detail with reference to Synthesis Examples and Examples. The expression “B was used instead of A” used in describing Synthesis Examples may refer to an identical number of molar equivalents of A being used in place of molar equivalents of B.



[0255] The term “a biphenyl group”, as used herein, may refer to a monovalent group in which two benzene rings are linked to each other via a single bond, and the term “a terphenyl group”, as used herein, may refer to a monovalent group in which three benzene rings are respectively linked via two single bonds.

EXAMPLES

Synthesis Example 1

Synthesis of Compound 2

[0256]



Synthesis of Intermediate (B)

[0257] To Intermediate (A), 120 mL of anhydrous methanol (MeOH) was added, the temperature was maintained at 0° C., and 60 mL of c-H₂SO₄ was slowly added dropwise thereto. The obtained reaction mixture was refluxed at a temperature of about 90° C. for about 14 hours, and then cooled to room temperature. After reduced-pressure distillation, the resulting reaction mixture was slowly added to ice water, and then neutralized using NaHCO₃. Here, the formed solid product was subjected to filtration and washed using distilled water. The formed solid product was dissolved in CH₂Cl₂, and an organic layer was extracted therefrom. The organic layer was washed with water, treated with magnesium sulfate (MgSO₄), distilled under reduced pressure, thereby obtaining 7.58 g of yellow Intermediate (B) (yield: 60%). ¹H NMR (300 MHz, DMSO-d₆): 7.69-7.57 (m, 6H), 7.42 (t, 2H), 3.10 (t, 3H).

Synthesis of Intermediate (C)

[0258] 15 g (74.5 mmol) of Intermediate (B) was added to 200 mL of tetrahydrofuran (THF). Then, while slowly stirring the resulting mixture, 5.72 g (149 mmol) of NaH (60% dispersion in mineral oil) was added dropwise thereto. The obtained reaction mixture was refluxed at a temperature of about 60° C. for about 72 hours, cooled to room temperature, and 250 mL of distilled water was added thereto to complete the reaction. 500 mL of 2N HCl was slowly added to the resulting reaction mixture, followed by stirred for about 60 minutes. The formed solid product was subjected

to filtration and washed using distilled water. The formed solid product was vacuum-dried, thereby obtaining 8.07 g of Intermediate (C) (yield: 64%). $^1\text{H NMR}$ (300 MHz, DMSO-d_6): 10.5 (s, 2H), 7.92 (m, 4H), 7.88 (m, 4H), 7.64 (s, 2H), 7.46 (s, 2H).

Synthesis of Intermediate (D)

[0259] 8.1 g (24 mmol) of Intermediate (C) was added to 100 mL of anhydrous CHCl_3 , and then stirred for about 30 minutes under a nitrogen atmosphere. 11 g (52.8 mmol) of PCl_5 was slowly added to the resulting reaction mixture, and then refluxed at a temperature of about 100°C . for about 6 hours. The resulting reaction mixture was cooled to room temperature, distilled under a reduced pressure, and washed with 50 mL of acetone three times. The formed solid product was vacuum-dried, thereby obtaining 4.70 g of Intermediate (D) (yield: 53%). $^1\text{H NMR}$ (300 MHz, DMSO-d_6): 8.29 (d, 2H), 8.20 (d, 2H), 7.85-7.72 (m, 8H); $^{13}\text{C NMR}$ (300 MHz, DMSO-d_6): 133.50, 130.02, 128.00, 127.95, 125.80.

Synthesis of Intermediate (E)

[0260] 5.1 g (13.7 mmol) of Intermediate (D) was added to 400 mL of anhydrous THF contained in a reaction vessel, and then stirred for about 20 minutes under a nitrogen atmosphere. 12.5 g (191.8 mmol) of zinc (Zn) was added to the reaction vessel, and then intensely stirred for about 30 minutes. 23.5 mL (315.1 mmol) of trifluoroacetic acid (TFA) was slowly added dropwise to the resulting reaction mixture, and then stirred at room temperature for about 8 hours. 100 mL of a supersaturated NH_4Cl aqueous solution was added thereto to thereby complete the reaction. The obtained reaction mixture was subject to filtration, and the filtrate was extracted using ethylacetate (EtOAc), and then washed with distilled water. An organic solvent obtained therefrom was distilled under reduced pressure to obtain a resulting compound. The compound was purified by column chromatography using n-hexane and THF (at a volume ratio of 1:3), thereby obtaining 1.64 g of Intermediate (E) (yield: 39%). $^1\text{H NMR}$ (300 MHz, DMSO-d_6): 11.28 (s, 2H), 8.30 (s, 2H), 8.05 (d, 2H), 8.00 (m, 4H), 7.36 (m, 4H); $^{13}\text{C NMR}$ (300 MHz, DMSO-d_6): 136.8, 136.5, 127.6, 127.4, 126.9, 121.5, 120.1, 113.5; Electron ionization mass spectrometry (EI^+ (mass)): $m/z=306$.

Synthesis of Compound 2


[0261] 1.0 g (3.26 mmol) of Intermediate (E) was dissolved in 100 mL of toluene. Then, 2.54 g (8.15 mmol) of 3,3'-(5-bromo-1,3-phenylene)dipyridine, 0.17 g (0.19 mmol) of $\text{Pd}_2(\text{dba})_3$, 0.39 mL (0.39 mmol) of $\text{P}(\text{t-Bu})_3$ (1 molar (M) in toluene), and 1.87 g (19.5 mmol) of NaO^tBu were added thereto and stirred at a temperature of about 100°C . for about 48 hours. The resulting reaction was checked by thin layer chromatography (TLC). Once the reaction was complete, after checking the reaction by TLC, an organic layer was extracted therefrom using ethylacetate, washed with distilled water, and dried using MgSO_4 . After reduced pressure-distillation, the obtained compound was subjected to column chromatography using n-hexane and THF (at a volume ratio of about 1:1), thereby obtaining 1.47 g of Compound 2 (yield: 59%). $^1\text{H NMR}$ (300 MHz, DMSO-d_6): 9.58 (s, 2H), 8.44 (d, 2H), 8.07 (m, 6H), 7.91-7.83 (m, 12H), 7.60-7.67 (m, 6H), 7.51 (m, 3H), 7.40 (m, 3H); $^{13}\text{C NMR}$ (300 MHz, DMSO-d_6): 149.9, 148.2, 144.6, 143.5, 138.5, 136.6, 134.0, 133.2, 133.0, 128.5, 125.1, 124.0, 123.4, 122.5, 120.5, 119.5, 115.4; EI^+ (mass): $m/z=766$.

[0262] Methods of synthesizing compounds other than Compound 2 should be apparent to those of skilled in the art by referring to the synthesis pathways and raw materials described above.


Example 1

[0263] A top substrate having the structure of ITO/Ag/ITO was sonicated in isopropyl alcohol and pure water for 5 minutes in each solvent, cleaned with ultraviolet rays for 10 minutes, and then ozone, and was mounted on a vacuum deposition apparatus. HT-D1 was deposited on the ITO glass substrate (here, anode) to form a hole injection layer having a thickness of about 100 Å. HT3 was deposited on the hole injection layer to form a hole transport layer having a thickness of about 1,100 Å. HT21 was deposited on the hole transport layer to form a buffer layer having a thickness of about 700 Å.

[0264] Compound 2 (as a host) and Compound PD75 (as a dopant) were co-deposited on the buffer layer at a weight ratio of about 97:3 to form an emission layer having a thickness of 400 Å. Thereafter, ET1 and ET-D1 were co-deposited on the emission layer to form an electron transport layer having a thickness of 360 Å. ET-D1 was then deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å. Mg and Ag were next co-deposited on the electron injection layer to form a cathode having a thickness of 110 Å, thereby completing the manufacture of a top-emission type organic light-emitting device (top-emission organic light-emitting device).




HT-D1



HT3



-continued

HT21



-continued

ET1



PD75


Example 2

[0265] An organic light-emitting device was manufactured in the same (or substantially the same) manner as in Example 1, except that Compound 5 was used instead of Compound 2 as a host in the formation of the emission layer.

Example 3

[0266] An organic light-emitting device was manufactured in the same (or substantially the same) manner as in Example 1, except that Compound 6 was used instead of Compound 2 as a host in the formation of the emission layer.

Compound 2




Comparative Example 1

[0267] An organic light-emitting device was manufactured in the same (or substantially the same) manner as in Example 1, except that Compound A was used instead of Compound 2 as a host in the formation of the emission layer.

<Compound A>

ET-D1




Comparative Example 2

[0268] An organic light-emitting device was manufactured in the same (or substantially the same) manner as in Example 1, except that CBP was used instead of Compound 2 as a host in the formation of the emission layer.

Examples 1 to 3 were measured by using a Keithley 236 source-measure unit (SMU) and a PR650 luminance meter. The results thereof are shown in Table 1. The lifespan refers to a time that has elapsed for the luminance of the organic light-emitting device to be reduced by 3% of the initial luminance thereof.


TABLE 1

	Emission layer host	Driving voltage (V)	Luminance (cd/m ²)	Efficiency (cd/A)	3% reduced luminance lifespan (hr @10 mA/cm ²)
Example 1	Compound 2	5.0	3,700	43	250
Example 2	Compound 5	4.8	3,700	42	200
Example 3	Compound 6	4.0	3,700	46	300
Comparative Example 1	Compound A	4.4	3,700	40	10
Comparative Example 2	CBP	6.0	3,700	25	10
Comparative Example 3	Compound B	6.4	3,700	21	5



Comparative Example 3

[0269] An organic light-emitting device was manufactured in the same (or substantially the same) manner as in Example 1, except that Compound B was used instead of Compound 2 as a host in the formation of the emission layer.



Evaluation Example 1

[0270] The driving voltage, current density, luminance, efficiency, and lifespan of each of the organic light-emitting devices manufactured in Examples 1 to 3 and Comparative

[0271] Referring to the results shown in Table 1, it can be seen that the organic light-emitting devices manufactured in Examples 1 to 3 exhibited excellent efficiency and lifespan, as compared with the organic light-emitting devices manufactured in Comparative Examples 1 to 3, while maintaining the same luminance and substantially the same driving voltage.

[0272] An organic light-emitting device including the condensed cyclic compound according to embodiments of the present disclosure may have low driving voltage, high efficiency, high luminance, and long lifespan.

[0273] As used herein, the terms “use,” “using,” and “used” may be considered synonymous with the terms “utilize,” “utilizing,” and “utilized,” respectively.

[0274] In addition, the terms “substantially,” “about,” and similar terms are used as terms of approximation and not as terms of degree, and are intended to account for the inherent deviations in measured or calculated values that would be recognized by those of ordinary skill in the art.

[0275] Also, any numerical range recited herein is intended to include all sub-ranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein and any minimum numerical limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein.


[0276] It should be understood that example embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each example embodiment should typically be considered as available for other similar features or aspects in other example embodiments.

[0277] While one or more example embodiments have been described with reference to the drawing, it will be

understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure as defined by the following claims and equivalents thereof.

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:



wherein, in Formula 1,

ring A₁ and ring A₂ are each independently a C₆-C₂₀ aromatic ring that does not include a heteroatom as a ring-forming atom, provided that ring A₁ and ring A₂ are not both benzene at the same time,

L₁ to L₄ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a₁ to a₄ are each independently an integer selected from 0 to 3, wherein when a₁ is two or more, two or more L₁(s) are identical to or different from each other, when a₂ is two or more, two or more L₂(s) are identical to or different from each other, when a₃ is two or more, two or more L₃(s) are identical to or different from each other, and when a₄ is two or more, two or more L₄(s) are identical to or different from each other,

Ar₁, Ar₂, R₁, and R₂ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsub-

stituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), and —B(Q₆)(Q₇),

b₁ and b₂ are each independently an integer selected from 0 to 3, wherein when b₁ is two or more, two or more Ar₁(s) are identical to or different from each other, and when b₂ is two or more, two or more Ar₂(s) are identical to or different from each other,

c₁ and c₂ are each independently an integer selected from 0 to 3,

n₁ and n₂ are each independently an integer selected from 0 to 10, and

at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, a substituted divalent non-aromatic condensed polycyclic group, a substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ het-

eroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkenyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇),

wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkenyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

2. The condensed cyclic compound of claim 1, wherein ring A₁ and ring A₂ in Formula 1 are each independently selected from a benzene, a naphthalene, an anthracene, a phenanthrene, a chrysene, and a pyrene.

3. The condensed cyclic compound of claim 1, wherein ring A₁ and ring A₂ in Formula 1 are each independently selected from a benzene, a naphthalene, and a phenanthrene.

4. The condensed cyclic compound of claim 1, wherein ring A₁ and ring A₂ in Formula 1 are identical to each other.

5. The condensed cyclic compound of claim 1, wherein L₁ to L₄ in Formula 1 are each independently selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluo-


renylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene


group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a thiadiazolylylene group, an imidazopyridinylylene group, and an imidazopyrimidinylylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, a pyrazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinylyl group, an isoquinolinylyl group, a benzoquinolinylyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.

6. The condensed cyclic compound of claim 1, wherein L₁ to L₄ in Formula 1 are each independently selected from groups represented by Formulae 3-1 to 3-33:


-continued




3-3




3-4




3-5




3-6




3-7




3-8




3-9




3-10



3-11














3-1













3-2


-continued




-continued



-continued



3-32



3-33

wherein, in Formulae 3-1 to 3-33,


Y_1 is selected from O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, and $Si(Z_6)(Z_7)$;

Z_1 to Z_7 are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group,


d_1 is an integer selected from 1 to 4, d_2 is an integer selected from 1 to 3, d_3 is an integer selected from 1 to 6, d_4 is an integer selected from 1 to 8, d_5 is an integer selected from 1 and 2, d_6 is an integer selected from 1 to 5, and each of * and *' indicates a binding site to a neighboring atom.

7. The condensed cyclic compound of claim 1, wherein

L_1 to L_4 in Formula 1 are each independently selected from groups represented by Formulae 4-1 to 4-28:




4-1




4-2


-continued




4-3




4-4




4-5




4-6




4-7




4-8



4-9




4-10




4-11


-continued




4-12




4-13




4-14




4-15




4-16



4-17




4-18




4-19


-continued




4-20




4-21




4-22




4-23




4-24



4-25




4-26



4-27

-continued

4-28



wherein * and *' in Formulae 4-1 and 4-28 each indicate a binding site to a neighboring atom.

8. The condensed cyclic compound of claim 1, wherein a1 to a4 in Formula 1 are each independently 0 or 1.

9. The condensed cyclic compound of claim 1, wherein Ar₁ and Ar₂ in Formula 1 are each independently selected from:

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyly group, a pentacenyly group, a rubicenyly group, a coronenyly group, an ovalenyly group, a pyrrolyly group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyly group, a pentacenyly group, a rubicenyly group, a coronenyly group, an ovalenyly group, a pyrrolyly group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridi-

nyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyly group, a pentacenyly group, a rubicenyly group, a coronenyly group, an ovalenyly group, a pyrrolyly group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃),

wherein Q₃₁ to Q₃₃ are each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a

pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.

10. The condensed cyclic compound of claim 1, wherein Ar_1 and Ar_2 in Formula 1 are each independently selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a

biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}),

wherein Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

11. The condensed cyclic compound of claim 1, wherein R_1 and R_2 in Formula 1 are each independently selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a benzoimidazolyl group, a

benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a phenalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃); and


—Si(Q₁)(Q₂)(Q₃),

wherein Q₁ to Q₃ and Q₃₁ to Q₃₃ are each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


12. The condensed cyclic compound of claim 1, wherein Ar₁ and Ar₂ in Formula 1 are each independently selected from groups represented by Formulae 5-1 to 5-55; and

R₁ and R₂ are each independently selected from:


hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, and a group represented by any of Formulae 5-1 to 5-55:




5-1




5-2




5-3




5-4




5-5




5-6




5-7



5-8












5-9



5-10


-continued

-continued




-continued

5-11




5-20

5-12




5-21

5-13




5-22

5-14




5-23

5-15




5-24

5-16




5-25

5-17




5-26

5-18




5-27

5-19




5-28




5-29


-continued




5-52



5-53



5-54



5-55

wherein, in Formulae 5-1 to 5-55,

Y_{31} is selected from O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, and $Si(Z_{36})(Z_{37})$;


Z_{31} to Z_{37} are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, and

e_2 is 1 or 2, e_3 is an integer selected from 1 to 3, e_4 is an integer selected from 1 to 4, e_5 is an integer selected from 1 to 5, e_6 is an integer selected from 1 to 6, e_7 is an integer selected from 1 to 7, e_9 is an integer selected from 1 to 9, and * indicates a binding site to a neighboring atom.


13. The condensed cyclic compound of claim 1, wherein Ar_1 and Ar_2 in Formula 1 are each independently selected from groups represented by Formulae 6-1 to 6-76; and R_1 and R_2 are each independently selected from:

hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt


thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, and a group represented by any of Formulae 6-1 to 6-76:




6-1




6-2




6-3




6-4



6-5











6-6




6-7

-continued




-continued

6-8




6-9

6-10




6-11




6-12


6-13



6-14



6-15



6-16

6-17


6-18

6-19


6-20

6-21


-continued




6-22




6-23




6-24



6-25




6-26




6-27


-continued




6-28




6-29




6-30




6-31




6-32



6-33















6-34




6-35

-continued




-continued

6-36




6-47

6-37




6-48

6-38




6-49

6-39



6-50


6-40



6-51


6-41

6-42




6-52

6-43




6-53

6-44




6-54

6-45




6-55

6-46




6-56


-continued




6-57




6-58




6-59




6-60




6-61




6-62




6-63




6-64




6-65



6-66




6-67




6-68


-continued



6-69




6-70




6-71




6-72




6-73




6-62




6-63




6-64




6-65



6-66







6-67



6-68


wherein* in Formulae 6-1 to 6-76 indicates a binding site to neighboring atom.

14. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one of Formulae 1A to 1L:




-continued


Formula 1E




Formula 1F



Formula 1G




Formula 1H




-continued


Formula 1I




Formula 1J



Formula 1K



Formula 1L



descriptions of R_{1a} to R_{1h} are each independently the same as described in connection with R_1 in Formula 1, and


descriptions of R_{2a} to R_{2h} are each independently the same as described in connection with R_2 in Formula 1.

15. The condensed cyclic compound of claim 14, wherein, in Formulae 1A to 1L,


a_1 and a_2 are each independently 0 or 1, and

b_1 and b_2 are each 1.

16. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is selected from Compounds 1 to 12:




1



2


wherein in Formulae 1A to 1L, descriptions of L_1 , L_2 , a_1 , a_2 , Ar_1 , Ar_2 , b_1 , and b_2 are the same as described in Formula 1,

-continued




3


-continued




6




4



7






5



8


-continued



9

-continued

12



10

17. An organic light-emitting device comprising:
a first electrode;
a second electrode facing the first electrode; and
an organic layer between the first electrode and the second electrode, the organic layer comprising an emission layer,
wherein the organic layer comprises the condensed cyclic compound of claim 1.

18. The organic light-emitting device of claim 17, wherein the first electrode is an anode, the second electrode is a cathode, and the organic layer further comprises:


- i) a hole transport region between the first electrode and the emission layer, the hole transport region comprising at least one selected from a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer, and
- ii) an electron transport region between the emission layer and the second electrode, the electron transport region comprising at least one selected from a hole blocking layer, electron transport layer, and an electron injection layer.

11

19. The organic light-emitting device of claim 17, wherein the emission layer comprises the condensed cyclic compound represented by Formula 1.

20. The organic light-emitting device of claim 19, wherein the emission layer further comprises a phosphorescent dopant, and the phosphorescent dopant comprises an organometallic complex represented by Formula 401:

<Formula 401>



wherein, in Formula 401,

M is selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm),

X₄₀₁ to X₄₀₄ are each independently nitrogen or carbon,

ring A₄₀₁ and ring A₄₀₂ are each independently selected from a substituted or an unsubstituted benzene, a substituted or an unsubstituted naphthalene, a substituted or an unsubstituted fluorene, a substituted or an unsubstituted spiro-fluorene, a substituted or an unsubstituted indene, a substituted or an unsubstituted pyrrole, a substituted or an unsubstituted thiophene, a substituted or an unsubstituted furan, a substituted or an unsubstituted imidazole, a substituted or an unsubstituted pyrazole, a substituted or an unsubstituted thiazole, a substituted or an unsubstituted isothiazole, a substituted or an unsubstituted oxazole, a substituted or an unsubstituted isoxazole, a substituted or an unsubstituted pyridine, a substituted or an unsubstituted pyrazine, a substituted or an unsubstituted pyrimidine, a substituted or an unsubstituted pyridazine, a substituted or an unsubstituted quinoline, a substituted or an unsubstituted isoquinoline, a substituted or an unsubstituted benzoquinoline, a substituted or an unsubstituted quinoxaline, a substituted or an unsubstituted quinazoline, a substituted or an unsubstituted carbazole, a substituted or an unsubstituted benzimidazole, a substituted or an unsubstituted benzofuran, a substituted or an unsubstituted benzothiophene, a substituted or an unsubstituted isobenzothiophene, a substituted or an unsubstituted benzoxazole, a substituted or an unsubstituted isobenzoxazole, a substituted or an unsubstituted triazole, a substituted or an unsubstituted oxadiazole, a substituted or an unsubstituted triazine, a substituted or an unsubstituted dibenzofuran, and a substituted or an unsubstituted dibenzothiophene,

at least one substituent of the substituted benzene, substituted naphthalene, substituted fluorene, substituted spiro-fluorene, substituted indene, substituted pyrrole, substituted thiophene, substituted furan, substituted imidazole, substituted pyrazole, substituted thiazole, substituted isothiazole, substituted oxazole, substituted isoxazole, substituted pyridine, substituted pyrazine, substituted pyrimidine, substituted pyridazine, substituted quinoline, substituted isoquinoline, substituted benzoquinoline, substituted quinoxaline, substituted quinazoline, substituted carbazole, substituted benzimidazole, substituted benzofuran, substituted benzothiophene, substituted isobenzothiophene, substituted benzoxazole, substituted isobenzoxazole, substituted triazole, substituted oxadiazole, substituted triazine, substituted dibenzofuran, and substituted dibenzothiophene is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —N(Q₄₀₁)(Q₄₀₂), —Si(Q₄₀₃)(Q₄₀₄)(Q₄₀₅), and —B(Q₄₀₆)(Q₄₀₇);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —N(Q₄₁₁)(Q₄₁₂), —Si(Q₄₁₃)(Q₄₁₄)(Q₄₁₅), and —B(Q₄₁₆)(Q₄₁₇); and —N(Q₄₂₁)(Q₄₂₂), —Si(Q₄₂₃)(Q₄₂₄)(Q₄₂₅), and —B(Q₄₂₆)(Q₄₂₇),

wherein Q₄₀₁ to Q₄₀₇, Q₄₁₁ to Q₄₁₇ and Q₄₂₁ to Q₄₂₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycy-

elic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group,

L₄₀₁ is an organic ligand,

xc1 is selected from 1, 2, and 3, and

xc2 is selected from 0, 1, 2, and 3.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US20170077422A1	公开(公告)日	2017-03-16
申请号	US15/263136	申请日	2016-09-12
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO., LTD. 产学合作基础庆尚大学		
当前申请(专利权)人(译)	三星DISPLAY CO., LTD. 产学合作基础庆尚大学		
[标]发明人	KIM MIKYUNG KIM YUNHI KWON SOONKI KIM HEEYEON PARK YUNJEE JEONG HYEIN HWANG JAEYOUNG		
发明人	KIM, MIKYUNG KIM, YUNHI KWON, SOONKI KIM, HEEYEON PARK, YUNJEE JEONG, HYEIN HWANG, JAEYOUNG		
IPC分类号	H01L51/00 C09K11/06 C07D487/04 C09K11/02		
CPC分类号	H01L51/0072 C09K2211/185 C09K11/06 H01L51/0085 C07D487/04 H01L51/0067 H01L51/5056 H01L51/5088 H01L51/5096 H01L51/5072 H01L51/5092 H01L51/5024 H01L51/5016 C09K2211/1007 C09K2211/1029 C09K11/025 C09K2211/1033 C09K2211/1037 C09K2211/1044 C09K2211/1092 H01L51/0052 H01L51/0065		
优先权	1020150129782 2015-09-14 KR		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光装置，包括：第一电极；面向第一电极的第二电极；第一电极和第二电极之间的有机层，所述有机层包括发光层，其中所述有机层包含至少一种式1的稠环化合物：包含根据本公开实施方案的稠环化合物的有机发光装置可具有低驱动电压，高效率，高亮度和长寿命。

