



(19) **United States**

(12) **Patent Application Publication**
KIM et al.

(10) **Pub. No.: US 2018/0226579 A1**
(43) **Pub. Date: Aug. 9, 2018**

(54) **AMINE-BASED COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

C07C 211/56 (2006.01)
C07C 211/59 (2006.01)
C07D 213/74 (2006.01)
C07D 405/12 (2006.01)
C07D 209/88 (2006.01)
C09K 11/02 (2006.01)
C09K 11/06 (2006.01)

(71) Applicant: **Samsung Display Co., Ltd., Yongin-si (KR)**

(72) Inventors: **Jongwoo KIM, Yongin-si (KR); Sanghyun HAN, Yongin-si (KR); Youngkook KIM, Yongin-si (KR); Seokhwan HWANG, Yongin-si (KR)**

(52) **U.S. Cl.**
CPC *H01L 51/006* (2013.01); *H01L 51/5206* (2013.01); *C07C 211/61* (2013.01); *C07D 307/91* (2013.01); *H01L 51/0061* (2013.01); *C07C 211/58* (2013.01); *C07C 211/56* (2013.01); *C07C 211/59* (2013.01); *C07D 213/74* (2013.01); *C07D 405/12* (2013.01); *C07D 209/88* (2013.01); *C09K 11/025* (2013.01); *C09K 11/06* (2013.01); *H01L 51/0058* (2013.01); *H01L 51/0059* (2013.01); *C07C 211/54* (2013.01)

(21) Appl. No.: **15/869,988**

(22) Filed: **Jan. 12, 2018**

(30) **Foreign Application Priority Data**

Feb. 3, 2017 (KR) 10-2017-0015690

Publication Classification

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07C 211/54 (2006.01)
C07C 211/61 (2006.01)
C07D 307/91 (2006.01)
C07C 211/58 (2006.01)

(57) **ABSTRACT**
An amine-based compound and an organic light-emitting device including the same are provided. The organic light-emitting device may include: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer and at least one of the amine-based compound.

10

190
150
110

10

190
150
110

**AMINE-BASED COMPOUND AND ORGANIC
LIGHT-EMITTING DEVICE INCLUDING
THE SAME**

CROSS-REFERENCE TO RELATED
APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2017-0015690, filed on Feb. 3, 2017, in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

1. Field

[0002] One or more embodiments relate to an amine-based compound and an organic light-emitting device including the same.

2. Description of the Related Art

[0003] Organic light-emitting devices are self-emission devices that produce full-color images, and also have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of brightness, driving voltage, and response speed, as compared to other devices in the art.

[0004] The organic light-emitting device may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transit (or transition) from an excited state to a ground state, thereby generating light.

SUMMARY

[0005] One or more embodiments include an amine-based compound and an organic light-emitting device including the same.

[0006] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0007] According to one or more embodiments, an amine-based compound is represented by Formula 1:

[0008] In Formula 1,

[0009] L_1 to L_3 may each independently be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0010] R_1 to R_{13} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, $-Si(Q_{31})(Q_{32})(Q_{33})$, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

[0011] R_{11} and R_{12} may optionally be linked to form a substituted or unsubstituted ring,

[0012] a_1 may be an integer from 1 to 10,

[0013] a_2 and a_3 may each independently be an integer from 0 to 10,


[0014] at least one substituent of the substituted C_5 - C_{60} carbocyclic group, the substituted C_1 - C_{60} heterocyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0015] deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

[0016] a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0017] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic

Formula 1



group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

[0018] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group; and

[0019] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

[0020] Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

[0021] The amine-based compound may have a molecular amount of 970 or less.

[0022] According to one or more embodiments, an organic light-emitting device includes: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer and at least one of the amine-based compound.

BRIEF DESCRIPTION OF THE DRAWING

[0023] These and/or other aspects will become apparent and more readily appreciated from the following description of embodiments, taken in conjunction with the accompanying drawing which is a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0024] In one embodiment, an amine-based compound represented by Formula 1 is provided.

[0025] In one embodiment, the amine-based compound may have a molecular weight of 1,000 or less, for example, 970 or less. For example, the amine-based compound may have a molecular weight of 1,000 Dalton or less, 970 Dalton or less, or any range of molecular weight subsumed therein.


[0026] In one embodiment, L₁ to L₃ may each independently be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group.

[0027] In one embodiment, L₁ to L₃ may each independently be selected from:


[0028] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a naphthofluorene group, a pyridine group, a pyrimidine group, a pyridazine group, a triazine group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, an oxazole group, an isoxazole group, a thiazole group, an isoxazole group, a triazole group, a carbazole group, a dibenzofuran group, a benzonaphthofuran group, a dibenzothiophene group, a dibenzosilole group, a benzocarbazole group, and a dibenzocarbazole group; and

[0029] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a naphthofluorene group, a pyridine group, a pyrimidine group, a pyridazine group, a triazine group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, an oxazole group, an isoxazole group, a thiazole group, an isoxazole group, a triazole group, a carbazole group, a dibenzofuran group, a benzonaphthofuran group, a dibenzothiophene group, a dibenzosilole group, a benzocarbazole group, and a dibenzocarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuran group, a benzonaphthofuran group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group.


[0030] In one embodiment, L₁ to L₃ may each independently be selected from groups represented by Formulae 3-1 to 3-72.



3-1










3-2




3-3

-continued




-continued

3-4




3-11

3-5




3-12

3-6




3-13

3-7




3-14

3-8




3-15

3-9




3-16


3-10




3-17



3-18












3-19




3-20

-continued



-continued


3-21



3-30

3-22


3-23



3-31


3-24

3-25




3-32

3-26




3-33

3-27




3-34

3-28










3-35

3-29




3-36

-continued




-continued

3-37




3-44

3-38




3-45

3-39




3-46

3-40




3-47

3-41




3-48

3-42




3-49

3-43




3-50




3-51


-continued




3-52




3-53




3-54




3-55




3-56



3-57




3-58




3-59


-continued




3-60




3-61




3-62




3-63



3-64




3-65




3-66

-continued




3-67




3-68




3-69



3-70



3-71



3-72

[0031] In Formulae 3-1 to 3-72,
 [0032] Y_1 may be O, S, $C(Z_4)(Z_5)$, or $Si(Z_6)(Z_7)$,
 [0033] Z_1 to Z_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chry-

senyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a triazinyl group, a benzimidazolyl group, a phenanthrolinyl group, and $-Si(Q_{33})(Q_{34})(Q_{35})$,
 [0034] Q_{33} to Q_{35} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

[0035] d_2 may be an integer from 0 to 2,
 [0036] d_3 may be an integer from 0 to 3,
 [0037] d_4 may be an integer from 0 to 4,
 [0038] d_5 may be an integer from 0 to 5,
 [0039] d_6 may be an integer from 0 to 6,
 [0040] d_8 may be an integer from 0 to 8, and

[0041] * and *' each indicate a binding site to a neighboring atom.


[0042] In one embodiment, a_1 may be an integer from 1 to 10.

[0043] In one embodiment, a_2 and a_3 may each independently be an integer from 0 to 10.


[0044] In one embodiment, a_1 may be 1 or 2, and a_2 and a_3 may each independently be selected from 0, 1, and 2.

[0045] In one embodiment, a_1 may be 1 or 2.


[0046] In one embodiment, L_1 may be selected from groups represented by Formulae 4-1 to 4-30:




4-1




4-2




4-3



4-4












4-5




4-6

-continued




-continued

4-7




4-16

4-8




4-17

4-9




4-18

4-10




4-19

4-11




4-20

4-12




4-21

4-13




4-22

4-14




4-23


4-15




-continued




4-24




4-25




4-26




4-27



4-28



4-29



4-30

[0047] In Formulae 4-1 to 4-30,


[0048] Y₂ may be O or S, and

[0049] * and *' each indicate a binding site to a neighboring atom.


[0050] In one embodiment, R₁ to R₁₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, —Si(Q₃₁)(Q₃₂)(Q₃₃), a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a

substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.


[0051] In one embodiment, R₁ to R₁₃ may each independently be selected from hydrogen, alkyl, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, —Si(Q₃₁)(Q₃₂)(Q₃₃), a substituted or unsubstituted C₁-C₆₀ alkyl group, and groups represented by Formulae 5-1 to 5-81:




5-1




5-2




5-3




5-4



5-5










5-6




5-7

-continued




-continued

5-8




5-15

5-9




5-16

5-10




5-17

5-11




5-18

5-12




5-19

5-13




5-20

5-14














5-21

5-15




5-22

-continued




-continued


5-23




5-24




5-25




5-26




5-27




5-28




5-29




5-30





5-31



5-32



5-33



5-34

5-35

5-36

5-37

5-38

5-39

5-40

5-41


5-42

5-43


5-44

5-45


-continued




5-46




5-47




5-48




5-49




5-50




5-51




5-52




5-53




5-54




5-55



5-56




5-57




5-58


-continued




5-59




5-60




5-61




5-62




5-63




5-64




5-65



5-66













5-67




5-68

-continued




-continued

5-69




5-70

5-71



5-72



5-79

5-80

5-81

[0052] In Formulae 5-1 to 5-81,

[0053] Y_{31} may be O, S, C(Z_{34})(Z_{35}), or Si(Z_{36})(Z_{37}),

[0054] Z_{31} to Z_{37} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a phenyl group substituted with —F, a phenyl group substituted with —Si(CH_3)₃, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, an anthracenyl group, a phenanthrenyl group, an imidazolyl group, a pyrazole group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, any isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group,

[0055] e_2 may be an integer from 0 to 2,

[0056] e_3 may be an integer from 0 to 3,

[0057] e_4 may be an integer from 0 to 4,

[0058] e_5 may be an integer from 0 to 5,

[0059] e_6 may be an integer from 0 to 6,

[0060] e_7 may be an integer from 0 to 7,

[0061] e_9 may be an integer from 0 to 9, and

[0062] * and *1 each indicate a binding site to a neighboring atom.

[0063] In one embodiment, R_9 may be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a substituted or unsubstituted phenyl group,

a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted spiro-bifluorenyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted benzocarbazolyl group, and a dibenzocarbazolyl group.

[0064] In one embodiment, R_9 may be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a cyano group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a phenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.

[0065] In one embodiment, R_1 to R_8 and R_{10} to R_{13} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, and a hexyl group.


[0066] In one embodiment, R_{11} and R_{12} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a substituted or unsubstituted phenyl group, and a substituted or unsubstituted naphthyl group.

[0067] In one embodiment, R_{11} and R_{12} may each independently be hydrogen, a substituted or unsubstituted methyl group, or a substituted or unsubstituted phenyl group.

[0068] In one embodiment, R_{11} and R_{12} may optionally be linked (e.g., chemically bonded to each other) to form a substituted or unsubstituted ring.

[0069] When R_{11} and R_{12} are optionally linked (e.g., chemically bonded to each other) to form a substituted or unsubstituted ring, the ring may be fluorene.


[0070] In one embodiment, the amine-based compound may be selected from the following structures:




1

-continued


2




3



4











5











-continued

-continued




-continued

-continued




-continued


22




23



24




25




-continued


26




27



28











29




-continued

-continued




-continued


38




39



40




41




-continued


42




43



44




45




-continued


46




47



48




49




-continued


50




51



52




53




-continued


54




55



56




57




-continued


58




59



60



61





-continued



-continued

66

62





63





67

64



68


65




69

-continued


70




71



72




73




-continued


74




75



76




77




-continued


78




79



80




81




-continued


82




83



84



85





-continued

-continued



86

90





87

91





88

92




89

93




94




-continued


95




96




97



98




99




-continued


100




101




102



103




104




-continued


105




106




107



108




109




-continued


110




111



112




113




-continued


114



115




116




-continued


117



118




119




-continued

120




-continued


124




121




125




122




126




123



127




128




-continued


129




130




131



132




133




-continued


134




135




136



137




138




-continued


139




140



141




142




-continued


143



144




145




-continued

146




-continued


149




147




150



148




151




-continued

152




-continued


155




153




156




157



154




158




-continued


159




160



161




162




-continued


163



164



165





-continued

-continued



166

169





170

167



171



168





-continued

-continued



175



176



177



[0071] The amine-based compound has a structure in which benzene is further condensed at a set (e.g., specific) position of the fluorene and an amine group is not directly linked (e.g., directly chemically bonded) to a benzofluorene core. Due to the inclusion of a linker, a highest occupied molecular orbital (HOMO) energy level is reduced. Thus, when the amine-based compound is used as a hole transport material, an energy level barrier for an emission layer or an additional hole transport layer is reduced, thereby obtaining an effect of a long lifespan.

[0072] Therefore, an electronic device (for example, an organic light-emitting device) including the amine-based compound may have a low driving voltage, high current density, and high efficiency.

[0073] In one embodiment, at least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0074] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0075] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0076] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

[0077] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group; and

[0078] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂).

[0079] In one embodiment, Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

[0080] * indicates a binding site to a neighboring atom.

[0081] In one embodiment, an organic light-emitting device may include: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer may include at least one of the amine-based compounds described above.

[0082] In one embodiment, the first electrode may be an anode.

[0083] In one embodiment, the second electrode may be a cathode.

[0084] In one embodiment, the first electrode may be an anode and the second electrode may be a cathode.

[0085] In one embodiment, the organic layer may further include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode.

[0086] The hole transport region may include at least one layer selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer.

[0087] The electron transport region may include at least one layer selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

[0088] In one embodiment, the hole transport region may include the amine-based compound.

[0089] In one embodiment, the hole transport layer may include the amine-based compound.

[0090] In one embodiment, the emission layer may include the amine-based compound.

[0091] In one embodiment, the emission layer may emit fluorescence.

[0092] In one embodiment, a host of the emission layer may include the amine-based compound.

[0093] In one embodiment, the emission layer may include a host and a dopant, and the dopant may include a styryl-based compound.

[0094] In one embodiment, the hole injection layer may include an arylamine-based compound.

[0095] In one embodiment, the hole injection layer may include the amine-based compound.

[0096] In one embodiment, at least one of the electron transport layer and the electron injection layer may include an alkali metal, an alkaline earth metal, a rare-earth metal, an alkali metal compound, an alkaline earth metal compound, a rare-earth metal compound, an alkali metal complex, an alkaline earth metal complex, a rare-earth metal complex, or any combination thereof. As used herein, the terms “combination thereof” and “combinations thereof”

may refer to a chemical combination (e.g., an alloy or chemical compound), a mixture, or a laminated structure of components.

[0097] Since the organic light-emitting device includes the amine-based compound, the organic light-emitting device may have a low driving voltage, high current density, and high efficiency. 4

[0098] Suitable, or more specific, conditions of synthesis methods of the amine-based compound and methods of manufacturing the organic light-emitting device may be recognizable by those of ordinary skill in the art by referring to Examples provided below, but embodiments of the present disclosure are not limited thereto.

[0099] In addition to the compounds described above, any other suitable compounds available in the art may be used between a pair of electrodes of the organic light-emitting device. For example, other compounds may be included in at least one of the hole transport region and the emission layer. In one embodiment, other compounds may be used as a material for forming a capping layer disposed outside the pair of electrodes of the organic light-emitting device.

[0100] Accordingly, an organic light-emitting device according to an embodiment may include: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer may include at least one of the amine-based compound represented by Formula 1.

[0101] The expression “(an organic layer) includes at least one of first compounds of Formula 1,” as used herein, may include a case in which “(an organic layer) includes identical amine-based compounds represented by Formula 1” and a case in which “(an organic layer) includes two or more different amine-based compounds represented by Formula 1.”

[0102] For example, the organic layer may include, as the amine-based compound, only Compound 1. In this regard, Compound 1 may exist in an emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the amine-based compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may exist in an identical layer (for example, Compound 1 and Compound 2 may all exist in an emission layer), or different layers (for example, Compound 1 may exist in an emission layer and Compound 2 may exist in an electron transport layer).

[0103] The term “organic layer,” as used herein, refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of an organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0104] The accompanying drawing is a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 includes a first electrode 110, an organic layer 150, and a second electrode 190.

[0105] Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing the organic light-emitting device 10 will be described in connection with the accompanying drawing.

[0106] Referring to the accompanying drawing, a substrate may be additionally disposed under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent

mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0107] The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material for forming the first electrode 110 may be selected from materials with a high work function to facilitate hole injection.

[0108] The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming a first electrode may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), and any combinations thereof, but embodiments of the present disclosure are not limited thereto. When the first electrode 110 is a semi-transmissive electrode or a reflective electrode, as a material for forming the first electrode 110, magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or any combination thereof may be used. However, the material for forming the first electrode 110 is not limited thereto.

[0109] The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 110 is not limited thereto.

[0110] The organic layer 150 is disposed on the first electrode 110. The organic layer 150 may include a first organic layer.

[0111] In one embodiment, the organic layer 150 may include an emission layer. In one embodiment, the first organic layer includes an emission layer.

[0112] In one embodiment, the organic layer 150 includes an electron transport region. The organic layer 150 includes a second organic layer between the first organic layer and the second electrode 190. In more detail, the second organic layer includes an electron transport region.

[0113] The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer. In one embodiment, the organic layer 150 may include a hole transport region between the first electrode 110 and the emission layer and an electron transport region between the emission layer and the second electrode 190.


[0114] The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0115] The hole transport region may include at least one layer selected from a hole injection layer (HIL), a hole transport layer (HTL), an emission auxiliary layer, and an electron blocking layer (EBL).


[0116] For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure having a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/

electron blocking layer structure, wherein for each structure, constituting layers are sequentially stacked from the first electrode **110** in this stated order, but the structure of the hole transport region is not limited thereto.


[0117] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPD), β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), PEDOT/PSS (poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate)), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




m-MTDATA





TDATA



2-TNATA




NPB


 β -NPB

TPD


-continued




Spiro-TPD



Spiro-NPB




methylated NPB




TAPC

-continued




HMTPD

Formula 201



Formula 202



[0118] In Formulae 201 and 202,

[0119] L₂₀₁ to L₂₀₄ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0120] L₂₀₅ may be selected from *-O-*, *-S-*, *-N(Q₂₀₁)-*, a substituted or unsubstituted C₁-C₂₀ alkenylene group, a substituted or unsubstituted C₂-C₂₀ alkenylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0121] xa1 to xa4 may each independently be an integer from 0 to 3,

[0122] xa5 may be an integer from 1 to 10,

[0123] R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent

non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0124] For example, in Formula 202, R₂₀₁ and R₂₀₂ may optionally be linked (e.g., chemically bonded to each other) via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, R₂₀₃ and R₂₀₄ may optionally be linked (e.g., chemically bonded to each other) via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group.

[0125] In one or more embodiments, regarding Formulae 201 and 202,

[0126] L₂₀₁ to L₂₀₅ may each independently be selected from:

[0127] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group;

[0128] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl

group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂); and

[0129] Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0130] In one or more embodiments, xa1 to xa4 may each independently be 0, 1, or 2.

[0131] In one or more embodiments, xa5 may be 1, 2, 3, or 4.

[0132] In one or more embodiments, R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group;

[0133] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl

group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$; and

[0134] Q_{31} to Q_{33} may be the same as described above.

[0135] In one or more embodiments, R_{201} to R_{203} in Formula 201 may each independently be selected from:

[0136] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0137] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-\text{F}$, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0138] but embodiments of the present disclosure are not limited thereto.

[0139] In one or more embodiments, in Formula 202, i) R_{201} and R_{202} may be linked via a single bond, and/or ii) R_{203} and R_{204} may be linked (e.g., chemically bonded to each other) via a single bond.

[0140] In one or more embodiments, at least one selected from R_{201} to R_{204} in Formula 202 may be selected from:


[0141] a carbazolyl group; and

[0142] a carbazolyl group, substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-\text{F}$, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0143] but embodiments of the present disclosure are not limited thereto.


[0144] The compound represented by Formula 201 may be represented by Formula 201A:

Formula 201A




[0145] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A(1) below, but embodiments of the present disclosure are not limited thereto:

Formula 201A(1)




[0146] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A-1 below, but embodiments of the present disclosure are not limited thereto:

Formula 201A-1




[0147] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A:

Formula 202A



[0148] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A-1:

Formula 202A-1



[0149] In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,





[0150] L_{201} to L_{203} , $xa1$ to $xa3$, $xa5$, and R_{202} to R_{204} are the same as described above,

[0151] R_{211} and R_{212} may be understood by referring to the description provided herein in connection with R_{203} .

[0152] R_{213} to R_{217} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-F$, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaph-

thyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.



[0153] The hole transport region may include at least one compound selected from Compounds HT1 to HT39, but embodiments of the present disclosure are not limited thereto:



-continued



HT5

HT6





HT7

HT8




HT9

HT10




-continued


HT11




HT12




HT13




HT14



HT15




HT16




-continued


HT17




HT18




HT19




HT20



HT21




HT22





-continued

HT23





HT24

HT25




HT26

HT27




-continued


HT28



HT29




HT30




-continued


HT31




HT32




HT33




-continued
HT34


HT35




HT36




HT37



HT38



HT39



[0154] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, the thickness of the hole injection layer

may be in a range of about 100 Å to about 9,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region,

the hole injection layer and the hole transport layer are within these ranges, suitable or satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0155] The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer, and the electron blocking layer may block the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the materials as described above.

[0156] The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0157] The charge-generation material may be, for example, a p-dopant.

[0158] In one embodiment, a lowest unoccupied molecular orbital (LUMO) energy level of the p-dopant may be -3.5 eV or less.

[0159] The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments of the present disclosure are not limited thereto.

[0160] For example, the p-dopant may include at least one selected from:


[0161] a quinone derivative, such as tetracyanoquinodimethane (TCNQ) and 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

[0162] a metal oxide, such as tungsten oxide or molybdenum oxide;

[0163] 1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and


[0164] a compound represented by Formula 221 below:

[0165] but embodiments of the present disclosure are not limited thereto:



-continued

Formula 221



[0166] In Formula 221,

[0167] R_{221} to R_{223} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, provided that at least one selected from R_{221} to R_{223} has at least one substituent selected from a cyano group, $-F$, $-Cl$, $-Br$, $-I$, a C_1 - C_{20} alkyl group substituted with $-F$, a C_1 - C_{20} alkyl group substituted with $-Cl$, a C_1 - C_{20} alkyl group substituted with $-Br$, and a C_1 - C_{20} alkyl group substituted with $-I$.


[0168] When the organic light-emitting device **10** is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers contact each other or are separated from each other. In one or more embodiments, the emission layer may include two or more materials selected from a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials are mixed with each other in a single layer to emit white light.

[0169] The emission layer may include a host and a dopant. The dopant may include at least one selected from a phosphorescent dopant and a fluorescent dopant. In one or more embodiments, the dopant may include a second compound represented by Formula 2. In one embodiment, the dopant may include the second compound represented by Formula 2 as a fluorescent dopant.

[0170] An amount of the dopant in the emission layer may be, in general, in a range of about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

[0171] A thickness of the emission layer may be in a range of about 100 \AA to about $1,000 \text{ \AA}$, for example, about 200 \AA to about 600 \AA . When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

[0172] In one or more embodiments, the host may include a compound represented by Formula 301 below.



Formula 301

[0173] In Formula 301,

[0174] Ar_{301} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0175] $xb11$ may be 1, 2, or 3,

[0176] L_{301} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0177] $xb1$ may be an integer from 0 to 5,

[0178] R_{301} may be selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{301})(Q_{302})(Q_{303})$, $-N(Q_{301})(Q_{302})$, $-B(Q_{301})(Q_{302})$, $-C(=O)(Q_{301})$, $-S(=O)_2(Q_{301})$, and $-P(=O)(Q_{301})(Q_{302})$,

[0179] $xb21$ may be an integer from 1 to 5, and

[0181] In one embodiment, Ar_{301} in Formula 301 may be selected from:


[0182] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group;

[0183] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$; and


[0184] Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group. However, embodiments of the present disclosure are not limited thereto.

[0185] When $xb11$ in Formula 301 is two or more, two or more $Ar_{301}(s)$ may be linked (e.g., chemically bonded to each other) via a single bond.

[0186] In one or more embodiments, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:



Formula 301-1



Formula 301-2

[0180] Q_{301} to Q_{303} may each independently be selected from a C_1 - C_{60} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.

[0187] In Formulae 301-1 and 301-2,

[0188] A_{301} to A_{304} may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine

group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole, benzocarbazole, dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran, dinaphthofuran group, a thiophene group, a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, and a dinaphthothiophene group,

[0189] X_{301} may be O, S, or N- $[(L_{304})_{xb4}-R_{304}]$,

[0190] R_{311} to R_{314} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

[0191] $xb22$ and $xb23$ may each independently be 0, 1, or 2,

[0192] L_{301} , $xb1$, R_{301} and Q_{31} to Q_{33} may be the same as described above,

[0193] L_{302} to L_{304} may each independently be the same as described in connection with L_{301} ,

[0194] $xb2$ to $xb4$ may each independently be the same as described in connection with $xb1$, and

[0195] R_{302} to R_{304} may each independently be the same as described in connection with R_{301} .

[0196] For example, L_{301} to L_{304} in Formulae 301, 301-1 and 301-2 may each independently be selected from:

[0197] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a benzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazolylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylylene group, an isoxazolylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, a triazinylylene group, a quinolinylylene group, an isoquinolinylylene group, a benzoquinolinylylene group, a phthalazinylylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylylene group, a cinnolinylylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a phenazinylylene group, a benzimidazolylylene group, an isobenzothiazolylylene group, a benzoxazolylylene group, a tetrazolylylene group, an imidazopyridinylylene group, an imidazopyrimidinylylene group, and an azacarbazolylylene group; and

[0198] a phenylene group, a naphthylene group, a fluorenylylene group, a spiro-bifluorenylylene group, a benzofluorenylylene group, a dibenzofluorenylylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene

group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a benzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazolylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylylene group, an isoxazolylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, a triazinylylene group, a quinolinylylene group, an isoquinolinylylene group, a benzoquinolinylylene group, a phthalazinylylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylylene group, a cinnolinylylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a phenazinylylene group, a benzimidazolylylene group, an isobenzothiazolylylene group, a benzoxazolylylene group, an isobenzoxazolylylene group, a triazolylylene group, a tetrazolylylene group, an imidazopyridinylylene group, an imidazopyrimidinylylene group, and an azacarbazolylylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinylyl group, an isoquinolinylyl group, a benzoquinolinylyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylyl group, a quinazolinylyl group, a cinnolinylyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}); and

[0199] Q_{31} to Q_{33} may be the same as described above.

[0200] In one embodiment, R_{301} to R_{304} in Formulae 301, 301-1, and 301-2 may each independently be selected from:

[0201] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl

group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;


[0202] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexaceny group, a pentaceny group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexaceny group, a pentaceny group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl

group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂); and


[0203] Q₃₁ and Q₃₃ may be the same as described above.

[0204] In one or more embodiments, the host may include an alkaline earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.


[0205] The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and at least one selected from Compounds H1 to H55, but embodiments of the present disclosure are not limited thereto:




H1



H2




H3




H4


-continued




H5




H6




H7



H8




H9




H10


-continued




H11




H12



H13




H14




H15


-continued




H16




H17



H18




H19




H20


-continued




H21



H22




H23




H24

-continued





-continued



H27


H25

H28




H26


H29




-continued




H30



H31




H32




H33


-continued




H34



H35




H36




H37

-continued


-continued




H38




H41




H39



H42




H40




H43


-continued




H44




H45



H46




H47




H48


-continued




H49




H50



H51




H52




H53

-continued




H54




H55

[0206] The phosphorescent dopant may include an organometallic complex represented by Formula 401 below:



Formula 401



Formula 402

[0207] In Formulae 401 and 402,

[0208] M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

[0209] L_{401} may be selected from ligands represented by Formula 402, and $xc1$ may be 1, 2, or 3, wherein, when $xc1$ is two or more, two or more $L_{401}(s)$ may be identical to or different from each other,

[0210] L_{402} may be an organic ligand, and $xc2$ may be an integer from 0 to 4, wherein, when $xc2$ is two or more, two or more $L_{402}(s)$ may be identical to or different from each other,

[0211] X_{401} to X_{404} may each independently be nitrogen or carbon,

[0212] X_{401} and X_{403} may be linked (e.g., chemically bonded to each other) via a single bond or a double bond, and X_{402} and X_{404} may be linked via (e.g., chemically bonded to each other) a single bond or a double bond,

[0213] A_{401} and A_{402} may each independently be selected from a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

[0214] X_{405} may be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{411})-*$, $*-C(Q_{411})(Q_{412})-*$, $*-C(Q_{411})=C(Q_{412})-*$, $*-C(Q_{411})=*$, or $*=C(Q_{411})=*$, wherein Q_{411} and Q_{412} may be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

[0215] X_{406} may be a single bond, O, or S,

[0216] R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$, and Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group,

[0217] $xc11$ and $xc12$ may each independently be an integer from 0 to 10, and

[0218] $*$ and $*'$ in Formula 402 each indicate a binding site to M in Formula 401.

[0219] In one embodiment, A_{401} and A_{402} in Formula 402 may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

[0220] In one or more embodiments, in Formula 402, i) X_{401} may be nitrogen, and X_{402} may be carbon, or ii) X_{401} and X_{402} may each be nitrogen at the same time.

[0221] In one or more embodiments, R_{401} and R_{402} in Formula 402 may each independently be selected from:

[0222] hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino

group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

[0223] a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

[0224] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0225] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0226] —Si(Q₄₀₁)(Q₄₀₂)(Q₄₀₃), —N(Q₄₀₁)(Q₄₀₂), —B(Q₄₀₁)(Q₄₀₂), —C(=O)(Q₄₀₁), S(=O)₂(Q₄₀₁), and —P(=O)(Q₄₀₁)(Q₄₀₂); and

[0227] Q₄₀₁ to Q₄₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.


[0228] In one or more embodiments, when xc1 in Formula 401 is two or more, two A₄₀₁(s) in two or more L₄₀₁(s) may optionally be linked (e.g., chemically bonded to each other) via X₄₀₇, which is a linking group, or two A₄₀₂(S) in two or more L₄₀₁(s) may optionally be linked (e.g., chemically bonded to each other) via X₄₀₈, which is a linking group (see Compounds PD1 to PD4 and PD7). X₄₀₇ and X₄₀₈ may each independently be a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q₄₁₃)*, *—C(Q₄₁₃)(Q₄₁₄)*, or *—C(Q₄₁₃)=C(Q₄₁₄)* (wherein Q₄₁₃ and Q₄₁₄ may each independently be hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group), but embodiments of the present disclosure are not limited thereto.

[0229] L₄₀₂ in Formula 401 may be a monovalent, divalent, or trivalent organic ligand. For example, L₄₀₂ may be


selected from halogen, diketone (for example, acetylacetonate), carboxylic acid (for example, picolinate), —C(=O), isonitrile, —CN, and phosphorus (for example, phosphine, or phosphite), but embodiments of the present disclosure are not limited thereto.

[0230] In one or more embodiments, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25, but embodiments of the present disclosure are not limited thereto:


PD1




PD2









PD3



PD4




-continued




-continued

PD5




PD11

PD6



PD12


PD7



PD13


PD8

PD9








PD14

PD10




PD15

-continued




-continued

PD16




PD21

PD17




PD22

PD18




PD23

PD19




PD24

PD20



[0231] The fluorescent dopant may include an arylamine compound or a styrylamine compound.

[0232] The fluorescent dopant may include a compound represented by Formula 501 below.



[0233] In Formula 501,

[0234] Ar_{501} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0235] L_{501} to L_{503} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0236] $xd1$ to $xd3$ may each independently be an integer of 0 to 3;

[0237] R_{501} and R_{502} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

[0238] $xd4$ may be an integer of 1 to 6.

[0239] In one embodiment, Ar_{501} in Formula 501 may be selected from:

[0240] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

[0241] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0242] In one or more embodiments, L_{501} to L_{503} in Formula 501 may each independently be selected from:

[0243] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, and a pyridinylylene group; and

[0244] a phenylene group, a naphthylene group, a fluorenylylene group, a spiro-bifluorenylylene group, a benzofluorenylylene group, a dibenzofluorenylylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, and a pyridinylylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenan-

threnyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0245] In one or more embodiments, R_{501} and R_{501} in Formula 502 may each independently be selected from:

[0246] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group;


[0247] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}); and

[0248] Q_{31} to Q_{33} may each be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


[0249] In one or more embodiments, xd4 in Formula 501 may be 2, but embodiments of the present disclosure are not limited thereto.

[0250] For example, the fluorescent dopant may include at least one selected from Compounds FD1 to FD22:


FD1




FD2



FD3




-continued




FD4

-continued




FD6


FD7



FD5




FD8




-continued

FD9




-continued


FD13




FD14



FD15




FD16




FD17



FD10




FD11



FD12




-continued




FD18

-continued





FD20




FD21

FD19




FD22

[0251] In one or more embodiments, the fluorescent dopant may include at least one selected from the following compounds, but embodiments of the present disclosure are not limited thereto.



DPVBi

-continued



[0252] The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0253] The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer, but embodiments of the present disclosure are not limited thereto.

[0254] For example, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein for each structure, constituting layers are sequentially stacked from an emission layer. However, embodiments of the structure of the electron transport region are not limited thereto.

[0255] The electron transport region (for example, a buffer layer, a hole blocking layer, an electron control layer, or an

electron transport layer in the electron transport region) may include a metal-free compound containing at least one π electron-depleted nitrogen-containing ring.

[0256] The “ π electron-depleted nitrogen-containing ring” indicates a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

[0257] For example, the “ π electron-depleted nitrogen-containing ring” may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed with each other, or iii) a heteropolycyclic group in which at least one of 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*$ moiety, is condensed with at least one C_5 - C_{60} carbocyclic group.

[0258] Examples of the π electron-depleted nitrogen-containing ring include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine,

a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, thiadiazol, an imidazopyridine, an imidazopyrimidine, and an azacarbazole, but embodiments of the present disclosure are not limited thereto.

[0259] For example, the electron transport region may include a compound represented by Formula 601:



[0260] In Formula 601,

[0261] Ar_{601} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

[0262] $\text{xe}11$ may be 1, 2, or 3,

[0263] L_{601} may be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0264] $\text{xe}1$ may be an integer from 0 to 5,

[0265] R_{601} may be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $\text{---Si}(\text{Q}_{601})(\text{Q}_{602})(\text{Q}_{603})$, $\text{---C}(\text{=O})(\text{Q}_{601})$, $\text{---S}(\text{=O})_2(\text{Q}_{601})$, and $\text{---P}(\text{=O})(\text{Q}_{601})(\text{Q}_{602})$,

[0266] Q_{601} to Q_{603} may each independently be a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and

[0267] $\text{xe}21$ may be an integer from 1 to 5.

[0268] In one embodiment, at least one of $\text{Ar}_{601}(\text{s})$ in the number of $\text{xe}11$ and/or at least one of $\text{R}_{601}(\text{s})$ in the number of $\text{xe}21$ may include the π electron-depleted nitrogen-containing ring.

[0269] In one embodiment, ring Ar_{601} in Formula 601 may be selected from:

[0270] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline

group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group;

[0271] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, ---F , ---Cl , ---Br , ---I , a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $\text{---Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $\text{---S}(\text{=O})_2(\text{Q}_{31})$, and $\text{---P}(\text{=O})(\text{Q}_{31})(\text{Q}_{32})$; and


[0272] Q_{31} to Q_{33} may each independently be selected from a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0273] When $\text{xe}1$ in Formula 601 is two or more, two or more $\text{Ar}_{601}(\text{s})$ may be linked (e.g., chemically bonded to each other) via a single bond.

[0274] In one or more embodiments, Ar_{601} in Formula 601 may be an anthracene group.

[0275] In one or more embodiments, a compound represented by Formula 601 may be represented by Formula 601-1:

Formula 601-1



[0276] In Formula 601-1,

[0277] X_{614} may be N or C(R_{614}), X_{615} may be N or C(R_{615}), X_{616} may be N or C(R_{616}), and at least one selected from X_{614} to X_{616} may be N,

[0278] L_{611} to L_{613} may each independently be the same as described in connection with L_{601} ,

[0279] xe611 to xe613 may each independently be the same as described in connection with xe1,

[0280] R₆₁₁ to R₆₁₃ may each independently be the same as described in connection with R₆₀₁,

[0281] R₆₁₄ to R₆₁₆ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0282] In one embodiment, L₆₀₁ and L₆₁₁ to L₆₁₃ in Formulae 601 and 601-1 may each independently be selected from:

[0283] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a benzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group;

[0284] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a benzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group,

a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, but embodiments of the present disclosure are not limited thereto.

[0285] In one or more embodiments, xe1 and xe613 in Formulae 601 and 601-1 may each independently be 0, 1, or 2.

[0286] In one or more embodiments, R₆₀₁ and R₆₁₁ to R₆₁₃ in Formula 601 and 601-1 may each independently be selected from:

[0287] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetra-

zoyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;


[0288] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

[0289] —S(=O)₂(Q₆₀₁), and —P(=O)(Q₆₀₁)(Q₆₀₂); and


[0290] Q₆₀₁ and Q₆₀₂ may be the same as described above.

[0291] The electron transport region may include at least one compound selected from Compounds ET1 to ET36, but embodiments of the present disclosure are not limited thereto:


ET1






ET2






ET3



-continued




-continued




-continued

ET10




-continued


ET13




ET11




ET14




ET12



ET15




-continued




ET16


-continued




ET19




ET17



ET20




ET18



ET21


-continued

ET22




-continued


ET25




ET23




ET26



ET24




ET27




-continued


ET28



ET29




ET30




-continued


ET31






ET32




ET33





-continued




ET34



ET35



TAZ



ET36

NTAZ

[0292] In one or more embodiments, the electron transport region may include at least one selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAlq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ.


[0293] The thickness of the buffer layer, the hole blocking layer, or the electron controlling layer may each independently be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å, to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have excellent electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.

[0294] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have suitable or satisfactory electron transport characteristics without a substantial increase in driving voltage.


[0295] The electron transport region (for example, the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a metal-containing material.

[0296] The metal-containing material may include at least one selected from alkali metal complex and alkaline earth-metal complex. The alkali metal complex may include a metal ion selected from a Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth-metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenylan oxazole, a hydroxy phenylthiazole, a hydroxy diphenylan oxadiazole, a hydroxy diphenylthiadiazol, a hydroxy phenylpyridine, a hydroxy phenylbenzimidazole, a hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

[0297] For example, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.



ET-D1



ET-D2

[0298] The electron transport region may include an electron injection layer that facilitates injection of electrons from the second electrode **190**. The electron injection layer may directly contact the second electrode **190**.

[0299] The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0300] The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof.

[0301] The alkali metal may be selected from Li, Na, K, Rb, and Cs. In one embodiment, the alkali metal may be Li,

Na, or Cs. In one or more embodiments, the alkali metal may be Li or Cs, but embodiments of the present disclosure are not limited thereto.

[0302] The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

[0303] The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

[0304] The alkali metal compound, the alkaline earth-metal compound, and the rare earth metal compound may be selected from oxides and halides (for example, fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, and the rare earth metal.

[0305] The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, KI, or RbI. In one embodiment, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, and KI, but embodiments of the present disclosure are not limited thereto.

[0306] The alkaline earth-metal compound may be selected from alkaline earth-metal oxides, such as BaO, SrO, CaO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), or $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$). In one embodiment, the alkaline earth-metal compound may be selected from BaO, SrO, and CaO, but embodiments of the present disclosure are not limited thereto.

[0307] The rare earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one embodiment, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 , but embodiments of the present disclosure are not limited thereto.

[0308] The alkali metal complex, the alkaline earth-metal complex, and the rare earth metal complex may include an ion of alkali metal, alkaline earth-metal, and rare earth metal as described above, and a ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare earth metal complex may be selected from hydroxy quinoline, hydroxy isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenylan oxazole, hydroxy phenylthiazole, hydroxy diphenylan oxadiazole, hydroxy diphenylthiadiazol, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, and cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

[0309] The electron injection layer may consist of an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof, as described above. In one or more embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

[0310] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron

injection layer is within the range described above, the electron injection layer may have suitable or satisfactory electron injection characteristics without a substantial increase in driving voltage.

[0311] The second electrode **190** is disposed on the organic layer **150** having such a structure. The second electrode **190** may be a cathode that is an electron injection electrode, and in this regard, a material for forming the second electrode **190** may be a material having a low work function, and such a material may be metal, alloy, an electrically conductive compound, or any combination thereof.

[0312] The second electrode **190** may include at least one selected from lithium (Li), silver (Si), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO, but embodiments of the present disclosure are not limited thereto. The second electrode **190** may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

[0313] The first electrode **190** may have a single-layered structure, or a multi-layered structure including two or more layers.

[0314] Hereinbefore, the organic light-emitting device has been described with reference to the accompanying drawing, but embodiments of the present disclosure are not limited thereto.

[0315] Layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region may be formed in a certain region by using one or more suitable methods selected from vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, and laser-induced thermal imaging.

[0316] In one embodiment, the first organic layer is formed by performing a solution process, and the second organic layer is formed by deposition.

[0317] When the respective layers of the hole transport region, the emission layer, and the respective layers of the electron transport region are formed by deposition, the deposition may be performed at a deposition temperature of about 100° C. to about 500° C., at a vacuum degree of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition rate of about 0.01 Å/sec to about 100 Å/sec by taking into account a material for forming a layer to be deposited, and the structure of a layer to be formed.

[0318] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of about 80° C. to about 200° C., depending on a material to be included in a layer and the structure of each layer to be formed.

[0319] The term “C₁-C₆₀ alkyl group,” as used herein, refers to a linear or branched saturated aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and non-limiting examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₁-C₆₀ alkyl group, except that the C₁-C₆₀ alkylene group is divalent instead of monovalent.

[0320] The term “C₂-C₆₀ alkenyl group,” as used herein, refers to a hydrocarbon group formed by substituting at least one carbon-carbon double bond at a main chain (e.g., in the middle) or at the terminus of the C₂-C₆₀ alkyl group, and non-limiting examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkenyl group, except that the C₂-C₆₀ alkenylene group is divalent instead of monovalent.

[0321] The term “C₂-C₆₀ alkynyl group,” as used herein, refers to a hydrocarbon group formed by substituting at least one carbon-carbon triple bond at a main chain (e.g., in the middle) or at the terminus of the C₂-C₆₀ alkyl group, and non-limiting examples thereof include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkynyl group, except that the C₂-C₆₀ alkynylene group is divalent instead of monovalent.

[0322] The term “C₁-C₆₀ alkoxy group,” as used herein, refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and non-limiting examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

[0323] The term “C₃-C₁₀ cycloalkyl group,” as used herein, refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and non-limiting examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkyl group, except that the C₃-C₁₀ cycloalkylene group is divalent instead of monovalent.

[0324] The term “C₁₀-C₁₀ heterocycloalkyl group,” as used herein, refers to a monovalent saturated monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and non-limiting examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuranyl group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group,” as used herein refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkyl group, except that the C₁-C₁₀ heterocycloalkylene group is divalent instead of monovalent.

[0325] The term “C₃-C₁₀ cycloalkenyl group,” as used herein, refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and no aromaticity (e.g., the ring is not aromatic, or the entire monovalent monocyclic group is not aromatic), and non-limiting examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group,” as used herein refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkenyl group, except that the C₃-C₁₀ cycloalkenylene group is divalent instead of monovalent.

[0326] The term “C₁-C₁₀ heterocycloalkenyl group,” as used herein, refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group include a

4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuran-yl group, and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group,” as used herein refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkenyl group, except that the C₁-C₁₀ heterocycloalkenylene group is divalent instead of monovalent.

[0327] The term “C₆-C₆₀ aryl group,” as used herein, refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group,” as used herein, refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other (e.g., combined together).

[0328] The term “C₆-C₆₀ heteroaryl group,” as used herein, refers to a monovalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group,” as used herein, refers to a divalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other (e.g., combined together).

[0329] The term “C₆-C₆₀ aryloxy group,” as used herein, refers to —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and the term “C₆-C₆₀ arylthio group,” as used herein, indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

[0330] The term “monovalent non-aromatic condensed polycyclic group,” as used herein, refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed with each other (e.g., combined together), only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure (e.g., the entire monovalent non-aromatic condensed polycyclic group is not aromatic). A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group,” as used herein, refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed polycyclic group, except that the divalent non-aromatic condensed polycyclic group is divalent instead of monovalent.

[0331] The term “monovalent non-aromatic condensed heteropolycyclic group,” as used herein, refers to a monovalent group (for example, having 1 to 60 carbon atoms) having two or more rings condensed to each other (e.g., combined together), at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure (e.g., the entire monovalent non-aromatic condensed heteropolycyclic group is not aromatic). An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group,” as used herein,

refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed heteropolycyclic group, except that the divalent non-aromatic condensed heteropolycyclic group is divalent instead of monovalent.

[0332] The term “C₅-C₆₀ carbocyclic group,” as used herein, refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom is a carbon atom only (e.g., the atoms of the ring structure only include carbon, though the substituents of the ring may include atoms other than carbon). The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring, such as benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. In one or more embodiments, depending on the number of substituents coupled or connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

[0333] The term “C₁-C₆₀ heterocyclic group,” as used herein, refers to a group having substantially the same structure as the C₁-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon (the number of carbon atoms may be in a range of 1 to 60).

[0334] At least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0335] deuterium (-D), —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0336] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic

group, $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$, $-\text{N}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{B}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{C}(=\text{O})(\text{Q}_{11})$, $-\text{S}(=\text{O})_2(\text{Q}_{11})$, and $-\text{P}(=\text{O})(\text{Q}_{11})(\text{Q}_{12})$;

[0337] a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0338] a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{21})(\text{Q}_{22})(\text{Q}_{23})$, $-\text{N}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{B}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{C}(=\text{O})(\text{Q}_{21})$, $-\text{S}(=\text{O})_2(\text{Q}_{21})$, and $-\text{P}(=\text{O})(\text{Q}_{21})(\text{Q}_{22})$; and

[0339] $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$.

[0340] In one embodiment, at least one substituent of the substituted $\text{C}_5\text{-C}_{60}$ carbocyclic group, the substituted $\text{C}_1\text{-C}_{60}$ heterocyclic group, the substituted $\text{C}_1\text{-C}_{60}$ alkyl group, the substituted $\text{C}_2\text{-C}_{60}$ alkenyl group, the substituted $\text{C}_2\text{-C}_{60}$ alkynyl group, the substituted $\text{C}_1\text{-C}_{60}$ alkoxy group, the substituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, the substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, the substituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, the substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, the substituted $\text{C}_6\text{-C}_{60}$ aryl group, the substituted $\text{C}_6\text{-C}_{60}$ aryloxy group, the substituted $\text{C}_6\text{-C}_{60}$ arylthio group, the substituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0341] deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0342] Q_{11} to Q_{13} , Q_{21} to Q_{23} and Q_{31} to Q_{33} used herein may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a

$\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0343] In one embodiment, Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryl group substituted with a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0344] In one embodiment, Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryl group substituted with a $\text{C}_1\text{-C}_{60}$ alkyl group, and a $\text{C}_1\text{-C}_{60}$ heteroaryl group.

[0345] The term “Ph”, as used herein, may refer to a phenyl group; the term “Me”, as used herein, may refer to a methyl group; the term “Et”, as used herein, may refer to an ethyl group; the terms “ter-Bu” or “Bu”, as used herein, may refer to a tert-butyl group; the term “OMe,” as used herein, may refer to a methoxy group; and the term “TMS,” as used herein, may refer to a trimethylsilyl group.

[0346] The term “biphenyl group,” as used herein, refers to “a phenyl group substituted with a phenyl group.” In other words, the “biphenyl group” is a substituted phenyl group having a $\text{C}_6\text{-C}_{60}$ aryl group as a substituent.

[0347] The term “terphenyl group,” as used herein, refers to “a phenyl group substituted with a biphenyl group.” In other words, the “terphenyl group” is a phenyl group having, as a substituent, a $\text{C}_6\text{-C}_{60}$ aryl group substituted with a $\text{C}_6\text{-C}_{60}$ aryl group.


[0348] * and *, as used herein, unless defined otherwise, each refer to a binding site to a neighboring atom in a corresponding formula.


[0349] Hereinafter, a compound according to embodiments and an organic light-emitting device according to embodiments will be described in more detail with reference to Synthesis Examples and Examples. The wording “B was used instead of A” used in describing Synthesis Examples refers to that an identical (or substantially identical) molar equivalent of B was used in place of A.

SYNTHESIS EXAMPLE

Synthesis of Compound 3

[0350]





[0351] (1) Synthesis of Intermediate 3-3

[0352] 10 g of methyl 5-bromo-2-iodobenzoate (3-1) and 5 g of a naphthalene-1-boronic acid (3-2) were diluted with

100 mL of tetrahydrofuran (THF) and 25 mL of water, and 1 g of $\text{Pd}(\text{PPh}_3)_4$ and 12 g of K_2CO_3 were added thereto dropwise. The reaction vessel was stirred under reflux at a temperature of 65°C . for 6 hours. The reaction vessel was cooled to room temperature and THF was removed therefrom under reduced pressure. Then, an extraction process was performed thereon three times by using ethyl acetate. The resultant was dried by using magnesium sulfate and filtered under reduced pressure. The residue obtained therefrom was purified in substantially the same manner as used to synthesize Intermediate 3-6 to be described below to obtain 8.3 g (83%) of Intermediate 3-3. The obtained compound was identified by LC-MS. $\text{C}_{18}\text{H}_{13}\text{BrO}_2$: $\text{M}+$ 342.2

[0353] (2) Synthesis of Intermediate 3-4

[0354] 8.3 g of Intermediate 3-3 was diluted with 120 mL of THF, and 60 mL of 1M MeMgBr was slowly added thereto dropwise at a temperature of 0°C . The resultant mixture was slowly heated to room temperature and stirred for 16 hours. The reaction was terminated at a temperature of 0°C . by a saturated aqueous ammonium chloride solution. Then, an extraction process was performed thereon three times by using ethyl acetate. The resultant was dried by using magnesium sulfate and filtered under reduced pressure. The residue obtained therefrom was purified in substantially the same manner as used to synthesize Intermediate 3-6 to be described below to obtain 7.7 g (93%) of Intermediate 3-4. The obtained compound was identified by LC-MS. $\text{C}_{19}\text{H}_{17}\text{BrO}$: $\text{M}+$ 342.3

[0355] (3) Synthesis of Intermediate 3-5

[0356] 7.7 g of Intermediate 3-4 was diluted with 80 mL of dichloromethane, and 0.5 mL of a methanesulfonic acid was added thereto and stirred for 3 hours. The reaction was terminated by 1 mL of triethylamine. Then, the resultant was filtered under reduced pressure. The residue obtained therefrom was purified in substantially the same manner as used to synthesize Intermediate 3-6 to be described below to obtain 7.7 g (93%) of Intermediate 3-5. The obtained compound was identified by LC-MS. $\text{C}_{19}\text{H}_{15}\text{Br}$: $\text{M}+$ 324.2

[0357] (4) Synthesis of Intermediate 3-6

[0358] 7.7 g of Intermediate 3-5 was dissolved in 130 mL of THF, and 10.5 mL of $n\text{-BuLi}$ (2.5M in hexane) was slowly added thereto dropwise at a temperature of -78°C . After the resultant mixture was stirred at the same temperature for 1 hour, 4.65 mL (25.0 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane was slowly added thereto dropwise. Then, the reaction solution was stirred at a temperature of -78°C . for 1 hour and additionally stirred at room temperature for 24 hours. After the reaction was terminated, 30 mL of 10% HCl (aq) and 30 mL of H_2O were added thereto and an extraction process was performed thereon three times by using 50 mL of diethylether. An organic layer collected therefrom was dried by using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was purified by silica gel column chromatography to obtain 6.4 g (73%) of Intermediate 3-6. The obtained compound was identified by LC-MS. $\text{C}_{25}\text{H}_{27}\text{BO}_2$: 371.3

[0359] (5) Synthesis of Intermediate 3-7


[0360] 5.8 g (81%) of Intermediate 3-7 was synthesized in substantially the same manner as in Intermediate 3-3, except that 6.6 g of Intermediate 3-6 and 6.6 g of 1-bromo-4-iodobenzene were used. The obtained compound was identified by LC-MS. $\text{C}_{25}\text{H}_{19}\text{Br}$: 400.3

[0361] (6) Synthesis of Compound 3


[0362] 4 g of Intermediate 3-7, 4 g of di([1,1'-biphenyl]-4-yl)amine, 0.34 g of $\text{Pd}_2(\text{dba})_3$, 0.1 mL of PtBu_3 , and 3.6 g of KOtBu were dissolved in 60 mL of toluene, and the

reaction solution was stirred at a temperature of 85° C. for 2 hours. The reaction solution was then cooled to room temperature, and the reaction was terminated using water. Then, an extraction process was performed thereon three times by using ethyl acetate. An organic layer collected therefrom was dried by using anhydrous magnesium sulfate and distilled under reduced pressure. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 5.5 g (yield: 86%) of Compound 3.

[0363] Synthesis of Compound 20



-continued



20

[0364] (1) Synthesis of Intermediate 20-1

[0365] 6.8 g of Intermediate 3-3 was diluted with 120 mL of THF, and 27 mL of 3M MeMgBr was added thereto dropwise at a temperature of 0° C. The resultant mixture was slowly heated to a temperature of 60° C. and stirred for 4 hours. The reaction was terminated at a temperature of 0° C. by a saturated aqueous ammonium chloride solution. Then, an extraction process was performed thereon three times by using ethyl acetate. The resultant was dried by using anhydrous magnesium sulfate and filtered under reduced pressure. The residue obtained therefrom was purified by column chromatography to obtain 6.7 g (72%) of Intermediate 20-1. The obtained compound was identified by LC-MS. $C_{29}H_{21}BrO$: M+ 466.4

[0366] (2) Synthesis of Intermediate 20-2

[0367] 5.7 g (86%) of Intermediate 20-2 was synthesized in substantially the same manner as in Intermediate 3-5, except that Intermediate 20-1 was used. The obtained compound was identified by LC-MS. $C_{29}H_{19}Br$: M+ 447.4

[0368] (3) Synthesis of Intermediate 20-3

[0369] 5.1 g (81%) of Intermediate 20-3 was synthesized in substantially the same manner as in Intermediate 3-6, except that 5.7 g of Intermediate 20-2 was used. The obtained compound was identified by LC-MS. $C_{35}H_{31}BO_2$: M+ 495.4


[0370] (4) Synthesis of Intermediate 20-4

[0371] 4.2 g (78%) of Intermediate 20-4 was synthesized in substantially the same manner as in Intermediate 3-7, except that 5.1 g of Intermediate 20-3 was used. The obtained compound was identified by LC-MS. $C_{35}H_{23}Br$: M+ 524.5


[0372] (5) Synthesis of Compound 20

[0373] 5.2 g (76%) of Compound 20 was synthesized in substantially the same manner as in Compound 3, except that 5.2 g of Intermediate 20-3 was used instead of Intermediate 3-7, and 2.7 g of N-phenyl-[1,1'-biphenyl]-4-amine was used instead of di([1,1'-biphenyl]-4-yl)amine.

[0374] Synthesis of Compound 22




20-4



22

[0375] 4.9 g (68%) of Compound 22 was synthesized in substantially the same manner as in Compound 3, except that 3 g of 9,9-dimethyl-N-phenyl-9H-fluorene-2-amine was used instead of di([1,1'-biphenyl]-4-yl)amine.

[0376] Synthesis of Compound 27




20-4


27

[0377] 6 g (81%) of Compound 27 was synthesized in substantially the same manner as in Compound 3, except that 3.2 g of N-([1,1'-biphenyl]-4-yl)naphthalene-1-amine was used instead of di([1,1'-biphenyl]-4-yl)amine.

[0378] Synthesis of Compound 30




30-1



30

[0379] 3.3 g (77%) of Compound 30 was synthesized in substantially the same manner as in Compound 3, except that 3 g of Intermediate 30-1 was used instead of Intermediate 3-7.

[0380] Synthesis of Compound 32




30-1


32

[0381] 3.2 g (84%) of Compound 32 was synthesized in substantially the same manner as in Compound 3, except that 3 g of Intermediate 30-1 was used instead of Intermediate 3-7, and 2.8 g of N-phenyldibenzo[b,d]furan-3-amine was used instead of di([1,1'-biphenyl]-4-yl)amine.

[0382] Synthesis of Compound 37




37-1



[0383] 3.8 g (75%) of Compound 37 was synthesized in substantially the same manner as in Compound 3, except that 4.2 g of Intermediate 37-1 was used instead of Intermediate 3-7, and 1.8 g of diphenylamine was used instead of di([1,1'-biphenyl]-4-yl)amine.

[0384] Synthesis of Compound 66




[0385] (1) Synthesis of Intermediate 66-1

[0386] 5 g (88%) of Intermediate 66-1 was synthesized instead of Intermediate 3-3, except that 5 g of Intermediate 20-3 and 3.1 g of 1,4-dibromonaphthalene were used. The obtained compound was identified by LC-MS. $C_{39}H_{25}Br$: M^+ : 574.5

[0387] (2) Synthesis of Compound 66

[0388] 5.3 g (74%) of Compound 66 was synthesized in substantially the same manner as in Compound 3, except that 5 g of Intermediate 66-1 was used instead of Intermediate 3-7.

[0389] Synthesis of Compound 84




[0390] (1) Synthesis of Intermediate 84-1

[0391] 4.5 g (43%) of Intermediate 84-1 was synthesized in substantially the same manner as in Intermediate 3-3, except that 9.8 g of Intermediate 20-3 and 4.1 g of 5-bromo-2-chloropyridine were used. The obtained compound was identified by LC-MS. $C_{34}H_{22}BrN$: M^+ : 525.5

[0392] (2) Synthesis of Compound 84


[0393] 4.5 g (68%) of Compound 84 was synthesized in substantially the same manner as in Compound 3, except that 5 g of Intermediate 84-1 was used instead of Intermediate 3-7.

[0394] Synthesis of Compound 169



[0395] 3.2 g (80%) of Compound 169 was synthesized in substantially the same manner as in Compound 3, except that 2.6 g of Intermediate 20-4 was used instead of Intermediate 3-7, and 1.8 g of N,9-diphenyl-9H-carbazole-3-amine was used instead of di([1,1'-biphenyl]-4-yl)amine.

[0396] Synthesis of Compound 180



[0397] 3.7 g (85%) of Compound 180 was synthesized in substantially the same manner as in Compound 3, except that 2.6 g of Intermediate 20-4 was used instead of Intermediate 3-7, and 2.2 g of N,9,9-triphenyl-9H-fluorene-2-amine was used instead of di([1,1'-biphenyl]-4-yl)amine.

[0398] The LC/MS values measured in the Synthesis Example and the ¹H NMR measurement results are shown in Table 1.

TABLE 1

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	LC/MS	
		found	calc.
3	7.87-7.83 (m, 2H), 7.78-7.75 (m, 2H), 7.63-7.60 (m, 5H), 7.53-7.30 (m, 13H), 7.19 (dd, 1H), 7.15 (td, 1H), 6.84-6.76 (m, 6H), 1.55 (s, 6H)	640.8	639.8
20	7.88 (d, 1H), 7.72-7.66 (m, 3H), 7.63-7.60 (m, 3H), 7.54-7.35 (m, 11H), 7.32-7.23 (m, 5H), 7.21 (d, 1H), 7.16-6.99 (m, 9H), 6.86-6.76 (m, 4H), 6.65 (td, 1H), 6.23-6.16 (m, 2H)	688.9	687.9
22	7.88 (dd, 1H), 7.72-7.60 (m, 5H), 7.56 (d, 1 H), 7.43-7.7.24 (m, 9H), 7.22 (d, 1H), 7.16-7.00 (m, 11H), 6.69 (dd, 1H), 6.63 (td, 1H), 6.45-6.38 (m, 3H), 6.24-6.18 (m, 2H), 1.61 (s, 6H)	729.0	728.0
27	7.88 (dd, 1H), 7.79-7.60 (m, 8H), 7.57-7.37 (m, 12H), 7.32-7.18 (m, 6H), 7.14-6.98 (m, 7H), 6.92 (dd, 1H), 6.60-6.50 (m, 4H)	738.9	737.9
30	7.98-7.94 (m, 2H), 7.86 (dd, 1H), 7.70-7.68 (m, 1H), 7.64-7.57 (m, 5H), 7.53-7.34 (m, 16H), 7.32-7.22 (m, 5H), 7.17 (dd, 1H), 7.13-7.08 (m, 6H), 7.00 (dd, 1H), 6.92 (dd, 1H), 6.89-6.74 (m, 6H)	841.1	840.1

TABLE 1-continued

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	LC/MS	
		found	calc.
32		779.0	778.0
37		506.6	505.6
66		815.0	814.0
84		766.0	765.0
169		778.0	777.0
180		853.1	852.1

Example


Comparative Example 1

[0399] As an anode, a Corning 15 Ω/cm² (1,200 Å) ITO glass substrate was cut to a size of 50 mm×50 mm×0.7 mm, sonicated with isopropyl alcohol and pure water each for 5 minutes, and then cleaned by irradiation of ultraviolet rays and ozone for 30 minutes. Then, the resultant glass substrate was provided to a vacuum deposition apparatus.


[0400] 2-TNATA was vacuum-deposited on the ITO glass substrate to form a hole injection layer having a thickness of

600 Å, and 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB), a hole transport compound, was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of 300 Å.



[0401] 9,10-di(naphthalene-2-yl)anthracene (DNA), a blue fluorescent host, and 4,4'-bis[2-(4-(N,N-diphenylamino)phenyl)vinyl]biphenyl (DPAVBi), a blue fluorescent dopant, were co-deposited on the hole transport layer at a weight ratio of 98:2 to form an emission layer having a thickness of 300 Å.



2-TNATA






NPB



[0402] Then, Alq₃ was deposited on the emission layer to form an electron transport layer having a thickness of 300 Å. Then, LiF, which is an alkali metal halide, was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was vacuum-deposited on the electron injection layer to form a cathode electrode having a thickness of 3,000 Å, thereby forming a LiF/Al electrode. In this manner, an organic light-emitting device was manufactured.

Examples 1 to 11 and Comparative Examples 2 to
4

[0403] Organic light-emitting devices of Examples 1 to 11 and Comparative Examples 2 to 4 were manufactured in substantially the same manner as in Comparative Example 1, except that Compounds shown in Table 2 were each used as a material for forming a hole transport layer.



Evaluation Example

[0404] The driving voltage, efficiency, and color purity of the organic light-emitting devices manufactured according

to Examples 1 to 11 and Comparative Examples 1 to 3 were measured by using the following methods. Results thereof are shown in Table 2:

[0405] Color coordinates: a current-voltage meter (Keithley SMU 236) supplied power and a luminance meter PR650 was used to measure color coordinates.

[0406] Luminance: A current-voltage meter (Keithley SMU 236) supplied power and a luminance meter PR650 was used to measure luminance.

[0407] Efficiency: A current-voltage meter (Keithley SMU 236) supplied power and a luminance meter PR650 was used to measure efficiency.

[0408] Half lifespan indicates an amount of time (hr) that had elapsed when luminance was 50% of initial luminance (100%) at 10 mA/cm².

[0412] It will be understood that, although the terms “first,” “second,” “third,” etc., may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section described below could be termed a second element, component, region, layer or section, without departing from the spirit and scope of the present disclosure.

[0413] Spatially relative terms, such as “beneath,” “below,” “lower,” “under,” “above,” “upper,” and the like,

TABLE 2

	Hole transport material	Driving voltage (V)	Current density (mA/cm ²)	Luminance (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr @100 mA/cm ²)
Comparative Example 1	NPB	7.01	50	2645	5.29	Blue	258
Comparative Example 2	Compound A	6.01	50	2875	5.75	Blue	283
Comparative Example 3	Compound B	5.51	50	3105	6.21	Blue	310
Comparative Example 4	Compound C	6.89	50	3205	6.41	Blue	230
Example 1	Compound 3	4.32	50	3670	7.34	Blue	362
Example 2	Compound 20	4.21	50	3715	7.43	Blue	353
Example 3	Compound 22	4.22	50	3665	7.33	Blue	372
Example 4	Compound 27	4.26	50	3730	7.46	Blue	374
Example 5	Compound 30	4.25	50	3630	7.26	Blue	384
Example 6	Compound 32	4.41	50	3725	7.45	Blue	343
Example 7	Compound 37	4.26	50	3630	7.26	Blue	366
Example 8	Compound 66	4.32	50	3670	7.34	Blue	378
Example 9	Compound 84	4.45	50	3440	6.88	Blue	325
Example 10	Compound 169	4.60	50	3490	6.98	Blue	330
Example 11	Compound 180	4.34	50	3615	7.23	Blue	356

[0409] Referring to Table 2, it was confirmed that the organic light-emitting devices in which Compounds 3, 20, 22, 27, 30, 32, 37, 66, 84, 169, and 180 according to one or more embodiments were used as a hole transport material of a blue emission layer had improved driving voltage and efficiency characteristics, as compared with those of the organic light-emitting device of Comparative Example 1 in which NPB was used. For example, it was confirmed that lifespan improvement effects were remarkable, and thus, lifespans were substantially prolonged. Also, it was confirmed that the organic light-emitting devices according to one or more embodiments had a significantly low driving voltage and excellent efficiency and half lifespan, as compared with those of the organic light-emitting devices of Comparative Examples 2 to 4 in which Compounds A to C were each used.

[0410] According to one or more embodiments, an organic light-emitting device including the amine-based compound may have a low driving voltage, high efficiency, high luminance, and a long lifespan.

[0411] It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

may be used herein for ease of explanation to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or in operation, in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as “below” or “beneath” or “under” other elements or features would then be oriented “above” the other elements or features. Thus, the example terms “below” and “under” can encompass both an orientation of above and below. The device may be otherwise oriented (e.g., rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein should be interpreted accordingly.

[0414] It will be understood that when an element or layer is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it can be directly on, connected to, or coupled to the other element or layer, or one or more intervening elements or layers may be present. In addition, it will also be understood that when an element or layer is referred to as being “between” two elements or layers, it can be the only element or layer between the two elements or layers, or one or more intervening elements or layers may also be present.

[0415] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the present disclosure. As used herein, the

singular forms “a” and “an” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises,” “comprising,” “includes,” and “including,” when used in this specification, specify the presence of the stated features, integers, acts, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, acts, operations, elements, components, and/or groups thereof. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0416] As used herein, the terms “substantially,” “about,” and similar terms are used as terms of approximation and not as terms of degree, and are intended to account for the inherent deviations in measured or calculated values that would be recognized by those of ordinary skill in the art. Further, the use of “may” when describing embodiments of the present disclosure refers to “one or more embodiments of the present disclosure.” As used herein, the terms “use,” “using,” and “used” may be considered synonymous with the terms “utilize,” “utilizing,” and “utilized,” respectively. Also, the term “exemplary” is intended to refer to an example or illustration.


[0417] Also, any numerical range recited herein is intended to include all sub-ranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein, and any minimum numerical limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein.

[0418] While one or more embodiments have been described with reference to the accompanying drawing, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims, and equivalents thereof.

What is claimed is:

1. An amine-based compound represented by Formula 1:

Formula 1



wherein, in Formula 1,

L_1 to L_3 are each independently a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

R_1 to R_{13} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, —Si(Q_{31})(Q_{32})(Q_{33}), a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

R_{11} and R_{12} are optionally linked to form a substituted or unsubstituted ring,

a_1 is an integer from 1 to 10,

a_2 and a_3 are each independently an integer from 0 to 10,

at least one substituent of the substituted C_5 - C_{60} carbocyclic group, the substituted C_1 - C_{60} heterocyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed

polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

- a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group; and

—Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂).

Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₆₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

2. The amine-based compound of claim 1, wherein:

the amine-based compound has a molecular weight of 970 or less.

3. The amine-based compound of claim 1, wherein:

L₁ to L₃ are each independently selected from:


a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a naphthofluorene group, a pyridine group, a pyrimidine group, a pyridazine group, a triazine group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, an oxazole group, an isoxazole group, a thiazole group, an isoxazole group, a triazole group, a carbazole group, a dibenzofuran group, a benzonaphthofuran group, a dibenzothiophene group, a dibenzosilole group, a benzocarbazole group, and a dibenzocarbazole group; and

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a naphthofluorene group, a pyridine group, a pyrimidine group, a pyridazine group, a triazine group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, an oxazole group, an isoxazole group, a thiazole group, an isoxazole group, a triazole group, a carbazole group, a dibenzofuran


group, a benzonaphthofuran group, a dibenzothiophene group, a dibenzosilole group, a benzocarbazole group, and a dibenzocarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a benzonaphthofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group.

4. The amine-based compound of claim 1, wherein:


L₁ to L₃ are each independently selected from groups represented by Formulae 3-1 to 3-72:




3-1




3-2




3-3




3-4




3-5




3-6




-continued




-continued




-continued




3-24




3-25




3-26




3-27



3-28




3-29




3-30


-continued




3-31




3-32




3-33




3-34



3-35




3-36




3-37


-continued




3-38




3-39




3-40



3-41




3-42




3-43


-continued




3-44




3-45




3-46



3-47










3-48




3-49

-continued




-continued

3-50




3-57

3-51




3-58

3-52




3-59

3-53




3-60

3-54




3-61

3-55




3-62

3-56




3-63


-continued




3-64




3-65




3-66



3-67




3-68




3-69


-continued



3-70



3-71



3-72

wherein, in Formulae 3-1 to 3-72,

Y₁ is O, S, C(Z₄)(Z₅), or Si(Z₆)(Z₇),

Z₁ to Z₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a triazinyl group, a benzimidazolyl group, a phenanthrolinyl group, and —Si(Q₃₃)(Q₃₄)(Q₃₅).

Q₃₃ to Q₃₅ are each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

d₂ is an integer from 0 to 2,d₃ is an integer from 0 to 3,d₄ is an integer from 0 to 4,d₅ is an integer from 0 to 5,d₆ is an integer from 0 to 6,d₈ is an integer from 0 to 8, andand *₁ each indicate a binding site to a neighboring atom.

5. The amine-based compound of claim 1, wherein:


a₁ is 1 or 2, anda₂ and a₃ are each independently selected from 0, 1, and

2.


6. The amine-based compound of claim 1, wherein:

L₁ is selected from groups represented by Formulae 4-1 to 4-30:


-continued




4-1




4-9




4-2




4-10




4-3




4-11




4-4




4-13




4-5




4-14




4-6




4-15




4-7



4-16




4-8




4-17


-continued




4-18




4-19




4-20




4-21



4-22




4-23




4-24


-continued




4-25




4-26




4-27



4-28



4-29



4-30

wherein, in Formulae 4-1 to 4-30,

Y_2 is O or S, and

and *¹ each indicate a binding site to a neighboring atom.


7. The amine-based compound of claim 1, wherein:

R_1 to R_{13} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, —Si(Q₃₁)(Q₃₂)(Q₃₃), a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₅-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.


8. The amine-based compound of claim 1, wherein:

R_1 to R_{13} are each independently selected from hydrogen, alkyl, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, —Si(Q₃₁)(Q₃₂)


(Q₃₃), a substituted or unsubstituted C₁-C₆₀ alkyl group, and groups represented by Formulae 5-1 to 5-81:




5-1




5-2




5-3




5-4




5-5



5-6




5-7




5-8


-continued




5-9




5-10




5-11




5-12



5-13




5-14




5-15


-continued




5-16




5-24




5-17




5-25




5-18




5-26




5-19




5-27




5-20




5-28




5-21




5-29




5-22




5-30




5-23



5-31













5-32



5-33


-continued

-continued




-continued

5-34




5-44

5-35




5-45

5-36




5-46

5-37




5-47

5-38




5-48

5-39




5-49

5-40




5-50

5-41




5-51

5-42




5-52


5-43



5-53












5-54




5-55

-continued




-continued


5-56




5-57




5-58




5-59




5-60




5-61




5-62



5-63



5-64



5-65

5-66

5-67

5-68

5-69


5-70

5-71


5-72

5-73


-continued




5-74




5-75




5-76




5-77




5-78



5-79



5-80



5-81

wherein, in Formulae 5-1 to 5-81,

Y₃₁ is O, S, C(Z₃₄)(Z₃₅), or Si(Z₃₆)(Z₃₇),

Z₃₁ to Z₃₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a phenyl

group substituted with —F, a phenyl group substituted with —Si(CH₃)₃, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, an anthracenyl group, a phenanthrenyl group, an imidazolyl group, a pyrazole group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group,

e2 is an integer from 0 to 2,

e3 is an integer from 0 to 3,

e4 is an integer from 0 to 4,

e5 is an integer from 0 to 5,

e6 is an integer from 0 to 6,

e7 is an integer from 0 to 7,

e9 is an integer from 0 to 9, and

and * each indicate a binding site to a neighboring atom.

9. The amine-based compound of claim 1, wherein:

R₉ is selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted spiro-bifluorenyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted benzocarbazolyl group, and a dibenzocarbazolyl group.

10. The amine-based compound of claim 1, wherein:

R₁ to R₈ and R₁₀ to R₁₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, and a hexyl group.

11. The amine-based compound of claim 1, wherein:

R₁₁ and R₁₂ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a substituted or unsubstituted phenyl group, and a substituted or unsubstituted naphthyl group.

12. The amine-based compound of claim 1, wherein:
R₁₁ and R₁₂ are each independently hydrogen, a substituted or unsubstituted methyl group, or a substituted or unsubstituted phenyl group.
13. An organic light-emitting device comprising:
a first electrode;
a second electrode facing the first electrode; and
an organic layer between the first electrode and the second electrode, the organic layer comprising an emission layer and at least one of the amine-based compound of claim 1.
14. The organic light-emitting device of claim 13, wherein:
the first electrode is an anode,
the second electrode is a cathode,
the organic layer further comprises a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,
the hole transport region comprises at least one layer selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer, and
the electron transport region comprises at least one layer selected from a buffer layer, a hole blocking layer, an electron transport layer, and an electron injection layer.
15. The organic light-emitting device of claim 14, wherein:
the hole transport region comprises the amine-based compound.
16. The organic light-emitting device of claim 14, wherein:
the hole transport layer comprises the amine-based compound.
17. The organic light-emitting device of claim 14, wherein:
the emission layer comprises the amine-based compound.
18. The organic light-emitting device of claim 13, wherein:
the emission layer comprises a host and a dopant, and the host comprises the amine-based compound.
19. The organic light-emitting device of claim 13, wherein:
the emission layer comprises a host and a dopant, and the dopant comprises a styryl-based compound.
20. The organic light-emitting device of claim 14, wherein:
the hole injection layer comprises an arylamine-based compound.

* * * * *

专利名称(译)	胺类化合物和包括其的有机发光装置		
公开(公告)号	US20180226579A1	公开(公告)日	2018-08-09
申请号	US15/869988	申请日	2018-01-12
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM JONGWOO HAN SANGHYUN KIM YOUNGKOOK HWANG SEOKHWAN		
发明人	KIM, JONGWOO HAN, SANGHYUN KIM, YOUNGKOOK HWANG, SEOKHWAN		
IPC分类号	H01L51/00 C07C211/54 C07C211/61 C07D307/91 C07C211/58 C07C211/56 C07C211/59 C07D213/74 C07D405/12 C07D209/88 C09K11/02 C09K11/06		
CPC分类号	H01L51/006 C07C211/54 C07C211/61 C07D307/91 H01L51/0061 C07C211/58 C07C211/56 C07C211/59 C07D213/74 C07D405/12 C07D209/88 C09K11/025 C09K11/06 H01L51/0058 H01L51/0059 H01L51/5206 H01L51/5221 H01L51/5012 H01L51/5088 H01L51/5056 H01L51/5096 H01L51/5072 H01L51/5092 C07C2603/40 H01L51/0054 H01L51/0073 C07C2603/18 H01L51/0067 H01L51/0072 C09K2211/1007 C09K2211/1014 H01L51/0085 H01L51/0087		
优先权	1020170015690 2017-02-03 KR		
外部链接	Espacenet USPTO		

摘要(译)

Formula 1

提供胺类化合物和包含其的有机发光装置。有机发光装置可包括：第一电极;面向第一电极的第二电极;第一电极和第二电极之间的有机层，有机层包括发光层和至少一种胺类化合物。

