



US010461262B2

(12) **United States Patent**
Sim et al.

(10) **Patent No.:** US 10,461,262 B2
(45) **Date of Patent:** Oct. 29, 2019

(54) **CONDENSED CYCLIC COMPOUND AND AN ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) **Applicant:** **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si, Gyeonggi-do (KR)

(72) **Inventors:** **Munki Sim**, Yongin-si (KR); **Jeonga Oh**, Yongin-si (KR); **Hyejin Jung**, Yongin-si (KR); **Sanghyun Han**, Yongin-si (KR); **Sooyon Kim**, Yongin-si (KR); **Youngkook Kim**, Yongin-si (KR); **Taekyung Kim**, Yongin-si (KR); **Seokhwan Hwang**, Yongin-si (KR)

(73) **Assignee:** **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si, Gyeonggi-Do (KR)

(*) **Notice:** Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 9 days.

(21) **Appl. No.:** 15/386,877

(22) **Filed:** **Dec. 21, 2016**

(65) **Prior Publication Data**

US 2017/0179408 A1 Jun. 22, 2017

(30) **Foreign Application Priority Data**

Dec. 22, 2015 (KR) 10-2015-0184065
Aug. 4, 2016 (KR) 10-2016-0099627

(51) **Int. Cl.**

H01L 51/00 (2006.01)
C07D 403/10 (2006.01)
H01L 51/50 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/0072** (2013.01); **C07D 403/10** (2013.01); **H01L 51/0052** (2013.01); **H01L 51/0067** (2013.01); **H01L 51/5064** (2013.01)

(58) **Field of Classification Search**

None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,645,948 A 7/1997 Shi et al.
6,878,469 B2 4/2005 Yoon et al.
(Continued)

FOREIGN PATENT DOCUMENTS

JP 10-017860 1/1998
JP 11-087067 3/1999
(Continued)

OTHER PUBLICATIONS

Tang et al., "Organic electroluminescent diodes", Appl. Phys. Lett. 51 (12), Sep. 21, 1987, pp. 913-915.
Adachi et al., "Confinement of charge carriers and molecular excitons within 5nmthick emitter layer in organic electroluminescent devices with a double heterostructure", Appl. Phys. Lett. 57 (6), Aug. 6, 1990, pp. 531-533.


(Continued)

Primary Examiner — Jay Yang

(74) **Attorney, Agent, or Firm:** F. Chau & Associates, LLC

(57) **ABSTRACT**

A condensed cyclic compound represented by Formula 1 and an organic light-emitting device including the same.



18 Claims, 1 Drawing Sheet

10

190
150
110

(56)

References Cited

U.S. PATENT DOCUMENTS		
8,951,647 B2	2/2015	Parham et al.
2014/0061548 A1	3/2014	Montenegro et al.
2015/0144924 A1	5/2015	Shin et al.
2016/0276600 A1 *	9/2016	Park C07F 9/65128

FOREIGN PATENT DOCUMENTS		
KR 10-0691543	3/2007	
KR 10-2010-0073954	7/2010	
KR 10-2011-0052540	5/2011	
KR 10-2013-0135178	12/2013	
KR 10-2014-0026552	3/2014	
KR 10-2015-0024811	3/2015	
KR 10-2015-0061976	6/2015	
WO 2014002871	1/2014	
WO WO-2014/123392 A1 *	8/2014	

OTHER PUBLICATIONS

Sakamoto et al., "Synthesis, Characterization, and Electron-Transport Property of Perfluorinated Phenylene Dendrimers", *J. Am. Chem. Soc.* 2000, 122, pp. 1832-1833.

Johansson et al., "Solid-State Amplified Spontaneous Emission in Some Spiro-Type Molecules: a New Concept for the Design of Solid-State Lasing Molecules", *Adv. Mater.*, 10, No. 14, 1998, pp. 1136-1141.

Tao et al., "Sharp green electroluminescence from 1H-pyrazolo[3,4-b]quinoline-based light-emitting diodes", *Applied Physics Letters*, vol. 77, No. 11, Sep. 11, 2000, pp. 1575-1577.

Yamaguchi et al., "Diphenylamino-Substituted 2,5-Diarylsiloles for Single-Layer Organic Electroluminescent Devices", *Chemistry Letters*, The Chemical Society of Japan, 2001, pp. 98-99.

* cited by examiner

FIG. 1

10

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3

30

220
190
150
110

FIG. 4

40

220
190
150
110
210

**CONDENSED CYCLIC COMPOUND AND AN
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME**

**CROSS-REFERENCE TO RELATED
APPLICATIONS**

This application claims the benefit of Korean Patent Application Nos. 10-2015-0184065 filed on Dec. 22, 2015, and 10-2016-0099627 filed on Aug. 4, 2016, in the Korean Intellectual Property Office, the disclosures of which are incorporated by reference herein in their entireties.

TECHNICAL FIELD

Exemplary embodiments of the present invention relate to a condensed cyclic compound, and more particularly to an organic light-emitting device including the same.

DISCUSSION OF RELATED ART


Organic light-emitting devices may be self-emission devices. Organic light-emitting devices may produce full-color images. Organic light-emitting devices may have relatively wide viewing angles, relatively high contrast ratios, and relatively short response times, and increased brightness, driving voltage, and response speed characteristics.

Organic light-emitting devices may include a first electrode disposed on a substrate. Organic light-emitting devices may include a hole transport region, an emission layer, an electron transport region, and a second electrode sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region. Electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, may recombine in the emission layer to produce excitons. The excitons may transition from an excited state to a ground state, thus generating light.

SUMMARY

One or more exemplary embodiments of the present invention may include a condensed cyclic compound and an organic light-emitting device including the same.

According an exemplary embodiment of the present invention, a condensed cyclic compound is represented by Formula 1:



<Formula 1>

<Formula 2>

2

In Formulae 1 and 2:
 X_1 is N or $C(R_{11})$, X_2 is N or $C(R_{12})$, and X_3 is N or $C(R_{13})$, in which at least one selected from X_1 to X_3 is N;
 L_1 to L_3 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;
 a_1 to a_3 are each independently an integer selected from 0 to 3, in which, when a_1 is 2 or greater, at least two L_1 (s) are the same as or different from each other, when a_2 is 2 or greater, at least two L_2 (s) may be the same as or different from each other, and when a_3 is 2 or greater, at least two L_3 (s) are the same as or different from each other;
 Ar_1 and Ar_2 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group;
 R_1 to R_8 and R_{11} to R_{13} are each independently selected from a group represented by Formula 2 above, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2);
 R_7 and R_8 are linked to form a saturated or unsaturated ring;
at least one of R_1 to R_6 is a group represented by Formula 2; and
* indicates a binding site to a neighboring atom.
At least one substituent of the substituted C_3 - C_{10} cycloalkylene group, substituted C_1 - C_{10} heterocycloalkylene group, substituted C_3 - C_{10} cycloalkenylene group, substituted C_1 - C_{10} heterocycloalkenylene group, substituted C_6 - C_{60} arylene group, substituted C_1 - C_{60} heteroarylene group, a substituted divalent non-aromatic condensed polycyclic group, a substituted divalent non-aromatic condensed heteropolycyclic group, substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl

group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, or substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, or a terphenyl group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); or

—Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), or —P(=O)(Q₃₁)(Q₃₂),

Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group substituted with a C_6 - C_{60} aryl group, a terphenyl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group substituted with a

C_6 - C_{60} aryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

According to an exemplary embodiment of the present invention, an organic light-emitting device includes a first electrode; a second electrode facing the first electrode; and an organic layer disposed between the first electrode and the second electrode. The organic layer includes an emission layer. The organic layer includes at least one of the condensed cyclic compounds represented by Formula 1.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features of the present invention will become more apparent by describing in detail exemplary embodiments thereof, with reference to the accompanying drawings, in which:

FIG. 1 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention;

FIG. 2 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention;

FIG. 3 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention; and

FIG. 4 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS


Exemplary embodiments of the present invention will be described below in more detail with reference to the accompanying drawings. “and/or” includes any exemplary embodiments may have different forms and should not be construed as being limited to the exemplary embodiments of the present invention described herein.

Like reference numerals may refer to like elements throughout the specification and drawings.

Sizes of elements in the drawings may be exaggerated for clarity of description.

It will be understood that when a component, such as a layer, a film, a region, or a plate, is referred to as being “on” another component, the component can be directly on the other component or intervening components may be present.

A condensed cyclic compound according to an exemplary embodiment of the present invention may be represented by Formula 1:



In Formula 1, R₁ to R₈ may each independently be selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a substituted or unsubstituted C_1 - C_{60}

5

alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(Q_1)(Q_2)(Q_3)$, $-\text{N}(Q_1)(Q_2)$, $-\text{B}(Q_1)(Q_2)$, $-\text{C}(=\text{O})(Q_1)$, $-\text{S}(=\text{O})_2(Q_1)$, or $-\text{P}(=\text{O})(Q_1)(Q_2)$.

R_7 and R_8 in Formula 1 may be linked to form a saturated or unsaturated ring.

Q_1 to Q_3 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group substituted with a C_6 - C_{60} aryl group, a terphenyl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group substituted with a C_6 - C_{60} aryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

At least one of R_1 to R_6 in Formula 1 may be a group represented by Formula 2:


6

cycloalkenylenes group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylenes group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted 5 divalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

For example, L_1 to L_3 in Formula 2 may each independently be selected from:

10 a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylenne group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chryselenylene group, a naphthacenylenne group, a picenylene group, a perphenylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, a ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, or an imidazopyrimidinylene group; or

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylene group, a pyrenylene group, a chrysene group, a naphthacenylene group, a picenylene group, a perylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an iso-thiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a



In Formula 2, X_1 may be nitrogen (N) or C(R_{11}), X_2 may be nitrogen (N) or C(R_{12}), and X_3 may be nitrogen (N) or C(R_{13}). At least one of X_1 to X_3 in Formula 2 may be nitrogen (N).

According to an exemplary embodiment of the present invention, in Formula 2, one of X_1 to X_3 may be nitrogen (N), two of X_1 to X_3 may be nitrogen (N), or three of X_1 to X_3 may be nitrogen (N). According to one or more exemplary embodiments of the present invention, in Formula 2, X_1 may be nitrogen (N), X_2 may be $C(R_{12})$, and X_3 may be $C(R_{13})$. According to one or more exemplary embodiments of the present invention, in Formula 2, X_1 and X_2 may each be nitrogen (N), X_2 may be nitrogen (N), and X_3 may be $C(R_{13})$. According to one or more exemplary embodiments of the present invention, X_1 , X_2 , and X_3 may each be nitrogen (N). However, exemplary embodiments of the present invention are not limited thereto.


¹ L_1 to L_3 in Formula 2 may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_2 - C_{10}

triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group and —Si(Q₃₁)(Q₃₂)(Q₃₃).


Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, or a naphthyl group.

According to one or more exemplary embodiments of the present invention, L₁ to L₃ in Formula 2 may each independently be a group represented by any one of Formula 3-1 to Formula 3-41:


Formula 3-1



Formula 3-2



Formula 3-3




60

65

-continued

Formula 3-4



5

10

15

20

25

30

35

40

45



50

55


60

65


Formula 3-5




Formula 3-6




Formula 3-7




Formula 3-8




Formula 3-9



Formula 3-10



Formula 3-11
















Formula 3-12

US 10,461,262 B2

9


-continued




10

-continued


Formula 3-13




Formula 3-14




Formula 3-15




Formula 3-16




Formula 3-17




Formula 3-18




Formula 3-19




Formula 3-20




Formula 3-21




Formula 3-22



Formula 3-23



Formula 3-24



Formula 3-25

Formula 3-26

Formula 3-27

Formula 3-28

Formula 3-29

Formula 3-30







Formula 3-31

Formula 3-32

Formula 3-33

11

-continued




12

-continued

Formula 3-34

5




Formula 3-35 10

15

(Z2)d4

Formula 3-36

20



Formula 3-37 35

40

In Formulae 3-1 to 3-41: Y_1 may be selected from oxygen (O), sulfur (S), $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$.

Z_1 to Z_7 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, or — $Si(Q_{31})(Q_{32})(Q_{33})$.

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group,

d_2 may be an integer selected from 1 or 2.

d_3 may be an integer selected from 1 to 3.

d_4 may be an integer selected from 1 to 4.

d_5 may be an integer selected from 1 to 5.

d_6 may be an integer selected from 1 to 6.

d_8 may be an integer selected from 1 to 8.












* and *' in Formulae 3-1 to 3-41 may each indicate a binding site to a neighboring atom.

a_1 to a_3 in Formula 2 may each independently be selected from an integer from 0 to 3. When a_1 is 2 or greater, at least two $L_1(s)$ may be the same as or different from each other. For example, when a_1 is 0, $-(L_1)_{a_1}-*$ may be a single bond. a_2 and a_3 may be the same as a_1 , as described herein.

According to an exemplary embodiment of the present invention, a_1 may be an integer selected from 1 or 2, and a_2 and a_3 may each independently be an integer selected from 0 or 1.

According to an exemplary embodiment of the present invention, $-(L_1)_{a_1}-*$, $-(L_2)_{a_2}-*$, and $-(L_3)_{a_3}-*$ in Formula 2 may each independently be a single bond. Alternatively, $-(L_1)_{a_1}-*$, $-(L_2)_{a_2}-*$, and $-(L_3)_{a_3}-*$ in Formula 2

may each independently be a group represented by one of Formulae 4-1 to Formula 4-44:



Formula 4-1 5

Formula 4-2 10

Formula 4-3 15

Formula 4-4 20

Formula 4-5 25

Formula 4-6 30

Formula 4-7 35

40

Formula 4-8

45

Formula 4-9 50

55









Formula 4-10

60

65

-continued

Formula 4-11



Formula 4-12

Formula 4-13

Formula 4-14

Formula 4-15










Formula 4-16

Formula 4-17

Formula 4-18


15

-continued

**16**
-continued


Formula 4-19

5




Formula 4-20

10




Formula 4-21

15




Formula 4-22

20




Formula 4-23

25




Formula 4-24

30




Formula 4-25

35




Formula 4-26

40




Formula 4-27

45




Formula 4-28

50




Formula 4-29

55




Formula 4-30

60




Formula 4-31

65




Formula 4-32

70




Formula 4-33

75




Formula 4-34

80




Formula 4-35

85




Formula 4-36

90




Formula 4-37

95




Formula 4-38

100




Formula 4-39

105




Formula 4-40

110




Formula 4-41

115




Formula 4-42

120




Formula 4-43

125




Formula 4-44

130




Formula 4-45

135




Formula 4-46

140




Formula 4-47

145




Formula 4-48

150




Formula 4-49

155




Formula 4-50

160




Formula 4-51

165




Formula 4-52

170




Formula 4-53

175




Formula 4-54

180




Formula 4-55

185




Formula 4-56

190




Formula 4-57

195




Formula 4-58

200




Formula 4-59

205




Formula 4-60

210




Formula 4-61

215




Formula 4-62

220




Formula 4-63

225




Formula 4-64

230




Formula 4-65

235




Formula 4-66

240




Formula 4-67

245




Formula 4-68

250




Formula 4-69


255



-continued



-continued



Formula 4-44


* and *' in Formulae 4-1 to 4-44 may each indicate a binding site to a neighboring atom.

19


a phenanthridinyl group, an acridinyl group, a phenanthroli-
nyl group, a phenazinyl group, a benzimidazolyl group, a
benzofuranyl group, a benzothiophenyl group, a benzothi-
azolyl group, an isobenzothiazolyl group, a benzoazolyl
group, an isobenzoxazolyl group, a triazolyl group, a tetra-
azolyl group, an oxadiazolyl group, a triazinyl group, a
benzocarbazolyl group, a dibenzocarbazolyl group, a thia-
diazolyl group, an imidazopyridinyl group, and an imida-
zopyrimidinyl group, each substituted with at least one
selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl
group, a cyano group, a nitro group, an amidino group, a
hydrazino group, a hydrazone group, a C₁-C₂₀ alkyl group,
a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl
group, a cycloheptyl group, a cyclopentenyl group, a cyclo-
hexenyl group, a phenyl group, a pentenyl group, an
indenyl group, a naphthyl group, an azulenyl group, a
heptalenyl group, an indacenyl group, an acenaphthyl group,
a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl
group, a dibenzofluorenyl group, a phenalenyl group, a
phenanthrenyl group, an anthracenyl group, a fluoranthenyl
group, a triphenylenyl group, a pyrenyl group, a chrysene-
nyl group, a naphthacenyl group, a picenyl group, a perylenyl
group, a pentaphenyl group, a hexacenyl group, a pentacenyl
group, a rubicenyl group, a coronenyl group, an ovalenyl
group, a pyrrol group, a thiophenyl group, a furanyl group,
an imidazolyl group, a pyrazolyl group, a thiazolyl group, an
isothiazolyl group, an oxazolyl group, an isoxazolyl group,
a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a
pyridazinyl group, an isoindolyl group, an indolyl group, an
indazolyl group, a purinyl group, a quinolinyl group, an
isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl
group, a naphthyridinyl group, a quinoxalinyl group, a
quinazolinyl group, a cinnolinyl group, a carbazolyl group,
a phenanthridinyl group, an acridinyl group, a phenanthroli-
nyl group, a phenazinyl group, a benzimidazolyl group, a
benzofuranyl group, a benzothiophenyl group, an isobenzothia-
zolyl group, a benzoazolyl group, an isobenzoxazolyl
group, a triazolyl group, a tetraazolyl group, an oxadiazolyl
group, a triazinyl group, a benzocarbazolyl group, a dibenzocar-
bazolyl group, a thiadiazolyl group, an imidazopyridinyl
group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)
(Q₃₃); or
—Si(Q₁)(Q₂)(Q₃).

Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, or a naphthyl group.


According to an exemplary embodiment of the present invention, Ar₁ and Ar₂ in Formula 2 may each independently be a group represented by one of Formula 5-1 to Formula 5-79:



Formula 5-1




Formula 5-2




Formula 5-3

20


-continued




Formula 5-4




Formula 5-5




Formula 5-6




Formula 5-7




Formula 5-8




Formula 5-9




Formula 5-10




Formula 5-11



Formula 5-12



Formula 5-13
















Formula 5-14

US 10,461,262 B2

21


-continued

**22****22**

-continued


Formula 5-15

5




Formula 5-16

10




Formula 5-17

15




Formula 5-18

20




Formula 5-19

25




Formula 5-20

30




Formula 5-21

35




Formula 5-22

40




Formula 5-23

45




Formula 5-24

50




Formula 5-25

55




Formula 5-26

60



Formula 5-27

65



Formula 5-28

Formula 5-29

Formula 5-30

Formula 5-31

Formula 5-32

Formula 5-33

Formula 5-34

Formula 5-35

Formula 5-36

Formula 5-37











Formula 5-38

Formula 5-39

US 10,461,262 B2

23

-continued



Formula 5-40

5

Formula 5-41

10

Formula 5-42

15

Formula 5-43

20

Formula 5-44

25

Formula 5-45

30

Formula 5-46

35

Formula 5-47

40

Formula 5-48

45

Formula 5-49

50

Formula 5-50

55

Formula 5-51













60

Formula 5-52

65

24

-continued



Formula 5-50

Formula 5-51

Formula 5-52

Formula 5-53

Formula 5-54

Formula 5-55

Formula 5-56

Formula 5-57

Formula 5-58

Formula 5-59









Formula 5-60

Formula 5-61

US 10,461,262 B2

25

-continued




26

-continued


Formula 5-62

5




Formula 5-63

10




Formula 5-64

15
20




Formula 5-65

25




Formula 5-66

30




Formula 5-67

35




Formula 5-68

45




Formula 5-69

60



65



Formula 5-70

Formula 5-71

Formula 5-72

Formula 5-73

Formula 5-74


Formula 5-75

Formula 5-76

Formula 5-77


27

-continued




Formula 5-78

5



Formula 5-79


10




28

-continued


Formula 6-3




Formula 6-4




Formula 6-5




Formula 6-6




Formula 6-7




Formula 6-8




Formula 6-9




Formula 6-10




Formula 6-11



Formula 6-12



Formula 6-13



Formula 6-14

In Formulae 5-1 to 5-79:

Y_{11} may be selected from O, S, C(Z_{13})(Z_{14}), N(Z_{15}), or Si(Z_{16})(Z_{17}).

Z_{11} to Z_{17} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenol group, a spiro-fluorenol group, a benzofluorenol group, a dibenzofluorenol group, a phenanthrenol group, an anthracenol group, a pyrenol group, a chrysenol group, a pyridinol group, a pyrazinol group, a pyrimidinol group, a pyridazinol group, a quinolinol group, an isoquinolinol group, a quinoxalinol group, a quinazolinol group, a carbazolyl group, a triazinyl group, a biphenyl group, a terphenyl group, or —Si(Q_{31})(Q_{32})(Q_{33}).

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group.

$e2$ may be an integer selected from 1 or 2.

$e3$ may be an integer selected from 1 to 3.

$e4$ may be an integer selected from 1 to 4.

$e5$ may be an integer selected from 1 to 5.


$e6$ may be an integer selected from 1 to 6.

$e7$ may be an integer selected from 1 to 7.

$e9$ may be an integer selected from 1 to 9.


* in Formulae 5-1 to 5-79 may indicate a binding site to a neighboring atom.

According to one or more exemplary embodiments of the present invention, Ar_1 and Ar_2 in Formula 2 may each independently be a group represented by one of Formula 6-1 to Formula 6-158:



Formula 6-1

60










Formula 6-2

65

US 10,461,262 B2

29


-continued

**30**

-continued


Formula 6-15

5




Formula 6-16 10

15




Formula 6-17

20



Formula 6-18


25



30

Formula 6-19


40



45

Formula 6-20


50



55

Formula 6-21

60



65

Formula 6-22

Formula 6-23

Formula 6-24

Formula 6-25


Formula 6-26

Formula 6-27

US 10,461,262 B2

31


-continued




Formula 6-28

32

-continued




Formula 6-34




Formula 6-29

15




Formula 6-35




Formula 6-30

25




Formula 6-36




Formula 6-31 35

30




Formula 6-37




Formula 6-32 45

40




Formula 6-38



Formula 6-33









50



Formula 6-39

33


-continued

**34**


-continued

Formula 6-40

5




10



Formula 6-41


15



20

Formula 6-42


25



30


Formula 6-43

35




Formula 6-44

40



45


Formula 6-45



50


Formula 6-46

55



Formula 6-47 60

65



Formula 6-48

Formula 6-49

Formula 6-50

Formula 6-51

Formula 6-52

Formula 6-53

Formula 6-54










Formula 6-55

Formula 6-56

US 10,461,262 B2

35


-continued

**36**

-continued


Formula 6-57

5




Formula 6-58 10

15




Formula 6-59

20




Formula 6-60

25




Formula 6-61

30




Formula 6-62

35




Formula 6-63 45

50




Formula 6-64

55



Formula 6-65 60

65



Formula 6-66

Formula 6-67

Formula 6-68

Formula 6-69

Formula 6-70

Formula 6-71








Formula 6-72

Formula 6-73

Formula 6-74

37

-continued

**38**

-continued

Formula 6-75

5




Formula 6-76

10

Formula 6-77


15



20

Formula 6-78


25



30

Formula 6-79


35



40


Formula 6-80

35



Formula 6-81


45



50

Formula 6-82

55



Formula 6-83

60

65

Formula 6-84

Formula 6-85

Formula 6-86


Formula 6-87

Formula 6-88

Formula 6-89

41


-continued




Formula 6-100

42


-continued




Formula 6-105




Formula 6-101




Formula 6-106




Formula 6-102




Formula 6-108




Formula 6-103



Formula 6-110



Formula 6-104











Formula 6-111

US 10,461,262 B2


43

-continued

**44**


-continued

Formula 6-112




5

Formula 6-113




10

Formula 6-114




20

Formula 6-115




30

Formula 6-116




40

Formula 6-117




50

Formula 6-118



60

Formula 6-119



65

Formula 6-120

Formula 6-121

Formula 6-122

Formula 6-123

Formula 6-124

Formula 6-125









Formula 6-126

Formula 6-127

Formula 6-128

45


-continued

**46**

-continued

Formula 6-129


5



10

Formula 6-130


15



20

Formula 6-131


25



30


Formula 6-132

35




Formula 6-133

40




45

Formula 6-134




Formula 6-135

50



Formula 6-136

55



Formula 6-137

Formula 6-138

Formula 6-139

Formula 6-140

Formula 6-141

Formula 6-142


Formula 6-143

Formula 6-144

Formula 6-145


47

-continued



48

-continued



³⁰ * in Formulae 6-1 to 6-158 may indicate a binding site to a neighboring atom.

R₁ to R₈ and R₁₁ to R₁₃ in Formulae 1 and 2 may each independently be selected from a group represented by Formula 2 above, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazone group, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substituted or unsubstituted C₁-C₂₀ alkoxy group, a substituted or unsubstituted C₆-C₂₀ aryl group, a substituted or unsubstituted C₁-C₂₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, or —Si(Q₁)₄₅(O₂)(O₂).

According to one or more exemplary embodiments of the present invention, R_1 to R_8 and R_{11} to R_{13} in Formulae 1 and 2 may each independently be selected from:

1 may each independently be selected from:
2 a group represented by Formula 2, hydrogen, deuterium,
50 —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a
nitro group, an amino group, an amidino group, a hydrazino
group, a hydrazone group, a C₁-C₂₀ alkyl group or a C₁-C₂₀
alkoxy group;

55 a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, and a hydrazone group;

Formula 6-155 a phenyl group, a biphenyl group, a terphenyl group, a pentenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a

hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, an indenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or a triazinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group;

According to an exemplary embodiment of the present invention, R_1 to R_8 and R_{11} to R_{13} in Formulae 1 and 2 may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group.

According to an exemplary embodiment of the present invention, one of R_1 and R_2 in Formula 1 may be a group represented by Formula 2.

According to one or more exemplary embodiments of the present invention, R_1 in Formula 1 may be a group represented by Formula 2.

According to an exemplary embodiment of the present invention, R_3 to R_8 and R_{11} to R_{13} in Formulae 1 and 2 may each be hydrogen.

* in Formula 2 may indicate a binding site to a neighboring atom.

According to an exemplary embodiment of the present invention, the condensed cyclic compound may be represented by one of Formulae 1A to 1F:

group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a quinoliny group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}); or

—Si(Q_1)(Q_2)(Q_3).

Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group.

According to an exemplary embodiment of the present invention, R_1 to R_8 and R_{11} to R_{13} in Formulae 1 and 2 may each independently be selected from:

a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or a triazinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}); or

—Si(Q_1)(Q_2)(Q_3).

Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group.


According to an exemplary embodiment of the present invention, one of R_1 and R_2 in Formula 1 may be a group represented by Formula 2.

According to one or more exemplary embodiments of the present invention, R_1 in Formula 1 may be a group represented by Formula 2.

According to an exemplary embodiment of the present invention, R_3 to R_8 and R_{11} to R_{13} in Formulae 1 and 2 may each be hydrogen.


* in Formula 2 may indicate a binding site to a neighboring atom.

According to an exemplary embodiment of the present invention, the condensed cyclic compound may be represented by one of Formulae 1A to 1F:




5

<Formula 1A>



10

<Formula 1B>



15

<Formula 1C>


20

In Formulae 1A to 1F, X_1 to X_3 , L_1 to L_3 , $a1$ to $a3$, Ar_1 , Ar_2 , and R_1 to R_8 may be the same as described above.


According to one or more exemplary embodiments of the present invention, the condensed cyclic compound may be represented by one of Formulae 1A-1 to 1A-3 and 1B-1 to 1B-3:

25


<Formula 1A-1>




<Formula 1A-2>



<Formula 1A-3>




<Formula 1B-1>




50

<Formula 1D>




55

<Formula 1E>



<Formula 1F>



-continued



<Formula 1F>

53

-continued



L_1 , a_1 , Ar_1 , Ar_2 , R_7 , and R_8 in Formulae 1A-1 to 1A-3 and 1B-1 to 1B-3 may be the same as described above.

For example, in Formulae 1A-1 to 1A-3 and 1B-1 to 1B-3:

L_1 may be a group represented by one of Formulae 3-1 to 3-41;

a_1 may be an integer selected from 1 or 2;

Ar_1 and Ar_2 may each independently be a group represented by one of Formula 5-1 to Formula 5-79.

R_7 and R_8 in Formulae 1A-1 to 1A-3 and 1B-1 to 1B-3, may each independently be selected from:

54

<Formula 1B-2>

5 hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{10} alkyl group, or a C_1 - C_{10} alkoxy group;

10 a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or a triazinyl group;

15 10 a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and — $Si(Q_{31})(Q_{32})(Q_{33})$; or

— $Si(Q_1)(Q_2)(Q_3)$.

20 Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, 25 a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group.

According to an exemplary embodiment of the present invention, in Formulae 1A-1 to 1A-3 and 1B-1 to 1B-3:

30 *— $(L_1)a_1$ * may be a group represented by one of Formula 4-1 to Formula 4-44;


Ar_1 and Ar_2 may each independently be a group represented by one of Formula 6-1 to Formula 6-158;

35 35 R_7 and R_8 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group; and


40 R_7 and R_8 may optionally be linked to form a saturated or unsaturated ring.

45 45 The condensed cyclic compound according to an exemplary embodiment of the present invention may be represented by one of Compounds 1 to 79; however, exemplary embodiments of the present invention are not limited thereto:

1



2





55

56


-continued

3


4




5




6




7




8




9




10













11



12



-continued





59

60

-continued



23

24





25

26





27

28





29


30



31


32



61**62**


-continued

33




34


35




36




37




38




39




40



41



42





63

64

-continued



43

44





45

46





47

48





49

50



51


52




65**66**

-continued

53





54





55

56





57

58




59


60



67




68



-continued


61

62





63

64





65

66





67

68



69

70




69

70

-continued


71

72




73

74




75

76




77

78




79

79



The condensed cyclic compound according to an exemplary embodiment of the present invention may have a condensed cyclic core in which, as illustrated in Formula 1', for example, a fluorene structure having bipolarity may include two nitrogen atoms. Since the condensed cyclic core may have such a structure, the condensed cyclic compound may have electron-deficient characteristics and increased electron transport characteristics. In the condensed cyclic core of the condensed cyclic compound, a nitrogen atom may be present in first and third carbon positions in the fluorene structure. Additionally, a substituted triazine, pyrimidine, or pyridine, may be linked to the condensed cyclic core. Thus, the overall molecular structure of the condensed cyclic compound may have planarity. Thus, intermolecular packing may be increased. An increase in intermolecular packing may increase electron mobility. Since the molecular structure of the condensed cyclic compound may be rod-shaped, a hopping rate may be increased. An organic light-emitting device including the condensed cyclic compound represented by Formula 1 according to an exemplary embodiment of the present invention may have a relatively low driving voltage, relatively high efficiency, relatively high brightness, and a relatively long lifespan.

<Formula 1'>



The condensed cyclic compound represented by Formula 1 may be synthesized by using known organic synthesis method. A synthesis method of the condensed cyclic compound represented by Formula 1 may be recognizable by one of ordinary skill in the art in view of the following Examples.

At least one of the condensed cyclic compounds represented by Formula 1 may be disposed between a pair of electrodes of an organic light-emitting device. According to one or more exemplary embodiments of the present invention, the condensed cyclic compound represented by Formula 1 may be included in an electron transport region, for example, an electron transport layer.

Thus, an organic light-emitting device according to an exemplary embodiment of the present invention may include: a first electrode; a second electrode disposed opposite the first electrode; and an organic layer disposed between the first electrode and the second electrode. The organic layer may include an emission layer. The organic layer may include at least one of the condensed cyclic compounds represented by Formula 1.

The expression "(an organic layer) includes at least one of the condensed cyclic compounds" used herein may include a case in which "(an organic layer) includes identical condensed cyclic compounds represented by Formula 1" and a case in which "(an organic layer) includes two or more different condensed cyclic compounds represented by Formula 1."

For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. Thus, Compound 1 might be only in the emission layer of the organic

light-emitting device. According to one or more exemplary embodiments of the present invention, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. According to one or more exemplary embodiments of the present invention, Compound 1 and Compound 2 may both be in a same layer. For example, Compound 1 and Compound 2 may both be in a hole transport layer. Alternatively, Compound 1 and Compound 2 may both be in different layers. For example, Compound 1 may be in a hole transport layer and Compound 2 may be in an emission auxiliary layer.

The organic layer may include a hole transport region and an electron transport region. The hole transport region may be disposed between the first electrode and the emission layer. The first electrode may be an anode. The hole transport region may include at least one of a hole injection layer, a hole transport layer, a buffer layer, or an electron blocking layer. The electron transport region may be disposed between the emission layer and the second electrode. The second electrode may be a cathode. The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, or an electron injection layer. At least one of the hole transport region and the emission layer may include at least one of the condensed cyclic compounds represented by Formula 1. For example, the electron transport region of the organic light-emitting device may include at least one of the organometallic compounds represented by Formula 1.

The term "an organic layer" as used herein may refer to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of an organic light-emitting device. A material included in the "organic layer" is not limited to an organic material.

FIG. 1 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention. An organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

A structure of an organic light-emitting device according to an exemplary embodiment of the present invention and a method of manufacturing the organic light-emitting device 10 according to an exemplary embodiment of the present invention will be described in more detail below with reference to FIG. 1.

Referring to FIG. 1, a substrate may be disposed below the first electrode 110. Alternatively, the substrate may be disposed above the second electrode 190. The substrate may include a glass substrate or a plastic substrate. The glass substrate and the plastic substrate may have a relatively high mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

The first electrode 110 may be formed by depositing or sputtering a material included in the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material included in the first electrode 110 may include at least one material with a relatively high work function, which may facilitate hole injection.

The first electrode 110 may be a reflective electrode, a semi-reflective electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material included in a first electrode may include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO_2), zinc oxide (ZnO), or any combination thereof; however, exemplary embodiments of the present invention are not limited thereto. When the first electrode 110 is a semi-transmissive electrode or a reflective electrode, a material included in the first electrode 100 may include magnesium (Mg), silver

(Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or any combination thereof; however, exemplary embodiments of the present invention are not limited thereto.

The first electrode 110 may have a single-layered structure. Alternatively, the first electrode may have a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO; however, the structure of the first electrode 110 is not limited thereto.

The organic layer 150 may be disposed on the first electrode 110. The organic layer 150 may include an emission layer.


The organic layer 150 may include a hole transport region and an electron transport region. The hole transport region may be disposed between the first electrode 110 and the emission layer. The electron transport region may be disposed between the emission layer and the second electrode 190.

The hole transport region may have a single-layered structure including a single layer including a single material. The hole transport region may have a single-layered structure including a single layer including different materials. The hole transport region may have a multi-layered structure having layers including different materials.


The hole transport region may include at least one layer selected from a hole injection layer (HIL), a hole transport layer (HTL), an emission auxiliary layer, and an electron blocking layer (EBL).

For example, the hole transport region may have a single-layered structure. The single layered structure may include a single layer including different materials. Alternatively, the hole transport region may have a multi-layered structure. The multi-layered structure may include a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure. For each structure, the layers may be sequentially stacked on the first electrode 110; however, the structure of the hole transport region is not limited thereto.


The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPD), β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




75




NPB




β -NPB



TPD




Spiro-TPD




Spiro-NPB

76


-continued




methylated NPB




▼ TAPC



HMTPD



<Formula 202>



<Formula 202>

50 In Formulae 201 and 202:

L₂₀₁ to L₂₀₄ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalk-
55 enylene group, a substituted or unsubstituted C₁-C₁₀ hetero-
cycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent
60 non-aromatic condensed polycyclic group, or a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

L_{205} may be selected from $-\text{O}-$, $-\text{S}-$, $-\text{N}$ (Q₂₀₁)-, a substituted or unsubstituted C₁-C₂₀ alkylene group, a substituted or unsubstituted C₂-C₂₀ alkenylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀

cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

xa1 to xa4 may each independently be an integer selected from 0 to 3.

xa5 may be an integer selected from 1 to 10.

R_{201} to R_{204} and Q_{201} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

For example, in Formula 202, R_{201} and R_{202} may be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R_{203} and R_{204} may be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group. However, exemplary embodiments of the present invention are not limited thereto.

According to an exemplary embodiment of the present invention, in Formulae 201 and 202,

L_{201} to L_{205} may each independently be selected from: a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylene group, a pyrenylene group, a chrysene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, or a pyridinylene group; or

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylene group, a pyrenylene group, a chrysene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group, each substituted with at least one

selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysene group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q_{31})(Q_{32})(Q_{33}), and —N(Q_{31})(Q_{32}).

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group.

According to one or more exemplary embodiments of the present invention, xa1 to xa4 in Formulae 201 and 202 may each independently be an integer selected from 0, 1, or 2.

According to one or more exemplary embodiments of the present invention, xa5 in Formula 202 may be an integer selected from 1, 2, 3, or 4.

According to one or more exemplary embodiments of the present invention, R_{201} to R_{204} and Q_{201} in Formulae 201 and 202 may each independently be selected from a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysene group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, or a pyridinyl group; or

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysene group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, or a pyridinyl group; or

dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂).

Q₃₁ to Q₃₃ may be the same as described above.

According to one or more exemplary embodiments of the present invention, at least one of R₂₀₁ to R₂₀₃ in Formula 201 may each independently be selected from:

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, or a dibenzothiophenyl group; or

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; however, exemplary embodiments of the present invention are not limited thereto.

According to one or more exemplary embodiments of the present invention, in Formula 202, R₂₀₁ and R₂₀₂ may be linked via a single bond, and/or R₂₀₃ and R₂₀₄ may be linked via a single bond.


According to one or more exemplary embodiments of the present invention, at least one of R₂₀₁ to R₂₀₄ in Formula 202 may be selected from:

a carbazolyl group; or


a carbazolyl group, substituted with at least one selected

from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; however, exemplary embodiments of the present invention are not limited thereto.


The compound represented by Formula 201 may be represented by Formula 201A:




The compound represented by Formula 201 may be represented by Formula 201A(1); however, exemplary embodiments of the present invention are not limited thereto:




The compound represented by Formula 201 may be represented by Formula 201A-1; however, exemplary embodiments of the present invention are not limited thereto:




The compound represented by Formula 202 may be represented by Formula 202A:



According to one or more exemplary embodiments of the present invention, the compound represented by Formula 202 may be represented by Formula 202A-1:



HT1



HT2

In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1, L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ may be the same as described above.

15 In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1, R₂₁₁ and R₂₁₂ may be the same as described with reference to R₂₀₃.

In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1, R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perphenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, or a pyridinyl group.

40 The hole transport region may include at least one compound selected from Compounds HT1 to HT39; however, exemplary embodiments of the present invention are not limited thereto:

US 10,461,262 B2



83

84

-continued



HT3

HT4



HT5

HT6





85

86



-continued
HT7

HT8





HT9

HT10



HT11



HT12



-continued



HT13

HT14





HT15

HT16




HT17

HT18



89




90

-continued



HT19

HT20




HT21

HT22



TH23





91

92



-continued
HT24

HT25





HT26


HT27



HT28

HT29




-continued
HT30

HT31


HT32





HT33



HT34

HT35





A thickness of the hole transport region may be in a range of from about 100 Å to about 10,000 Å, for example, from about 100 Å to about 3,000 Å. When the hole transport region includes at least one selected from a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of from about 100 Å to about 9,000 Å, for example, from about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of from about 50 Å to about 2,000 Å, for example from about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer. The electron blocking layer may decrease or prevent the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include materials described herein.

The hole transport region may include a charge-generation material, which may increase conductive properties of the hole transport region. The charge-generation material may be substantially homogeneously or non-homogeneously dispersed in the hole transport region.

The charge-generation material may be, for example, a p-dopant.

45 According to an exemplary embodiment of the present invention, a lowest unoccupied molecular orbital (LUMO) of the p-dopant may be -3.5 eV or less.

The p-dopant may include at least one of a quinone derivative, a metal oxide, or a compound including a cyano group; however, exemplary embodiments of the present invention are not limited thereto.


50 According to an exemplary embodiment of the present invention, the p-dopant may include at least one selected from:

55 a quinone derivative, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

60 a metal oxide, such as tungsten oxide or molybdenum oxide;

65 1,4,5,8,9,11-hexaaazatriphenylene-hexacarbonitrile (HAT-CN); and

a compound represented by Formula 221; however, exemplary embodiments of the present invention are not limited thereto:



In Formula 221:

R_{221} to R_{223} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and at least one selected from R_{221} to R_{223} may have at least one substituent selected from a cyano group, —F, —Cl, —Br, —I, a C_1 - C_{20} alkyl group substituted with —F, a C_1 - C_{20} alkyl group substituted with —Cl, a C_1 - C_{20} alkyl group substituted with —Br, and a C_1 - C_{20} alkyl group substituted with —I.

When the organic light-emitting device 10 is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. According to one or more exemplary embodiments of the present invention, the emission layer may have a stacked structure. The stacked structure may include two or more layers selected from a red emission layer, a green emission layer, or a blue emission layer. The two or more layers may be in direct contact with each other. Alternatively, the two or more layers may be separated from each other. According to one or more exemplary embodiments of the present invention, the emission layer may include two or more materials. The two or more materials may include a red-light emission material, a green-light emission material, or a blue-light emission material. The two or more materials may be mixed

with each other in a single layer. The two or more materials mixed with each other in the single layer may emit white light.

The emission layer may include a host and a dopant. The 5 dopant may include at least one of a phosphorescent dopant or a fluorescent dopant.

An amount of the dopant in the emission layer may be in a range of from about 0.01 parts by weight to about 15 parts by weight based on about 100 parts by weight of the host; 10 however, exemplary embodiments of the present invention are not limited thereto.

A thickness of the emission layer may be in a range of from about 100 Å to about 1,000 Å, for example, from about 200 Å to about 600 Å. When the thickness of the emission 15 layer is within this range, increased emission characteristics may be obtained without a substantial increase in driving voltage.

The host may include a compound represented by Formula 301:

20 $[Ar_{301}]_{xb11}^x[(L_{301})_{xb1}^xR_{301}]_{xb21}^x$ <Formula 301>

In Formula 301:

Ar_{301} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group;

25 $xb11$ may be an integer selected from 1, 2, or 3;

L_{301} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

30 $xb1$ may be an integer selected from 0 to 5;

35 R_{301} may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{301})(Q_{302})(Q_{303}), —N(Q_{301}) (Q_{302}) , —B(Q_{301})(Q_{302}), —C(=O)(Q_{301}), —S(=O) $_2$ (Q_{301}), or —P(=O)(Q_{301})(Q_{302});

40 $xb21$ may be an integer selected from 1 to 5; and

45 Q_{301} to Q_{303} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group; however, exemplary embodiments of the present invention are not limited thereto.

50 According to an exemplary embodiment of the present invention, Ar_{301} in Formula 301 may be selected from:

55 a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a

phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, or a dibenzothiophene group; or

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), or —P(=O)(Q₃₁)(Q₃₂).

Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group; however, exemplary embodiments of the present invention are not limited thereto.

When xb11 in Formula 301 is 2 or greater, at least two Ar₃₀₁(s) may be linked via a single bond.

According to one or more exemplary embodiments of the present invention, the compound represented by Formula 301 may be represented by Formula 301-1 or Formula 301-2:

X₃₀₁ may be oxygen (O), sulfur (S), or N-[(L₃₀₄)_{xb4}-R₃₀₄];

R₃₁₁ to R₃₁₄ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), or —P(=O)(Q₃₁)(Q₃₂),

xb22 and xb23 may each independently be an integer selected from 0, 1, or 2;

L₃₀₁, xb1, R₃₀₁ and Q₃₁ to Q₃₃ may be the same as described above;

L₃₀₂ to L₃₀₄ may be the same as described with reference to L₃₀₁, as described herein;


xb2 to xb4 may be the same as described with reference to xb1, as described herein; and

R₃₀₂ to R₃₀₄ may be the same as described with reference to L₃₀₁, as described herein.


For example, L₃₀₁ to L₃₀₄ in Formulae 301, 301-1, and 301-2 may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofura-

<Formula 301-1>



<Formula 301-2>



In Formulae 301-1 and 301-2:

A₃₀₁ to A₃₀₄ may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran group, a dinaphthofuran group, a thiophene group, a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, or a dinaphthothiophene group;

ylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group,

a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, or an azacarbazolylene group; or

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{20} alkyl group, a C_1-C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysene group, a perylenyl group, a pentaphenylene group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an aza carbazolyl group, —Si(Q_{31}) (Q_{32}) (Q_{33}) , —N(Q_{31}) (Q_{32}) , —B(Q_{31}) (Q_{32}) , —C(=O)(Q_{31}), —S(=O) $_2$ (Q_{31}), and —P(=O)(Q_{31}) (Q_{32}) .

Q_{31} to Q_{33} may be the same as described above.

According to one or more exemplary embodiments of the present invention, R_{301} to R_{304} in Formulae 301, 301-1, and 301-2 may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group,
5 a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylene group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenz-
10 furanyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadi-
15 azolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group,
20 an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or an
25 azacarbazolyl group; or

103

a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzooquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an aza carbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$.

Q_{31} to Q_{33} may be the same as described above.

According to one or more exemplary embodiments of the present invention, the host may include an alkali-earth metal complex. For example, the host may be selected from a (Be complex (for example, Compound H55), a Mg complex, or a Zn complex.


The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55; however, exemplary embodiments of the present invention are not limited thereto:

5
10
15


104

-continued


H5




H6




H7




H8



H9




H10



US 10,461,262 B2

105


-continued



H11

5

10




H12

15

20

25



H13


30

35

H14


40

45



55

H15




60


65

106


-continued




H16




H17



H18




H19



H20

107

-continued




5

10

15


H22 20



25

30


H23 35



40

45

H24




55

60

65

108

-continued






H25

H26

109


-continued

**110**

-continued

H27


5



10

15

H20




H28

30

H31

35




45

H32

H29


55



H33

60


65



H30

111

-continued




5

10

15

H36

20



25

30

35

H37

45

50

55

H38



60

65


112

-continued




H39



H40







H41




113

-continued

**114**

-continued

H42

10
15

H43 20

25
30

H44

40

45

H45

55

60

65

H46


H47

H48

H49


H50

H51



115

-continued




H52


116

M(L₄₀₁)_{xc1}(L₄₀₂)_{xc2}

<Formula 401>



<Formula 402>



H53

In Formulae 401 and 402,

20 M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), or thulium (Tm).

25 In Formulae 401 and 402, L₄₀₁ may be selected from ligands represented by Formula 402. xc1 may be an integer selected from 1, 2, or 3. When xc1 is 2 or greater, at least two L₄₀₁(s) may be the same as or different from each other.

In Formulae 401 and 402, L₄₀₂ may be an organic ligand. xc2 may be an integer selected from 0 to 4. When xc2 is 2 or greater, at least two L₄₀₂(s) may be the same as or different from each other.

30 In Formulae 401 and 402, X₄₀₁ to X₄₀₄ may each independently be selected from nitrogen (N) or carbon (C).


35 In Formulae 401 and 402, X₄₀₁ and X₄₀₃ may be linked via a single bond or a double bond. X₄₀₂ and X₄₀₄ may be linked via a single bond or a double bond.

40 In Formulae 401 and 402, A₄₀₁ and A₄₀₂ may each independently be selected from a C₅-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group.


45 In Formulae 401 and 402, X₄₀₅ may be selected from a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q₄₁₁)—*, *—C(Q₄₁₁)(Q₄₁₂)—*, *—C(Q₄₁₁)=C(Q₄₁₂)—*, *—C(Q₄₁₁)=*, or *—C(Q₄₁₁)=*. Q₄₁₁ and Q₄₁₂ may be selected from hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group.

50 In Formulae 401 and 402, X₄₀₆ may be selected from a single bond, oxygen (O), or sulfur (S).


55 In Formulae 401 and 402, R₄₀₁ and R₄₀₂ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substituted or unsubstituted C₁-C₂₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₄₀₁)(Q₄₀₂)(Q₄₀₃), —N(Q₄₀₁)(Q₄₀₂), —B(Q₄₀₁)(Q₄₀₂), —C(=O)(Q₄₀₁), —S(=O)₂(Q₄₀₁), and —P(=O)(Q₄₀₁)(Q₄₀₂), wherein Q₄₀₁ to Q₄₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a C₆-C₂₀ aryl group, or a C₁-C₂₀ heteroaryl group.



H54



H55



The phosphorescent dopant may include an organometallic complex represented by Formula 401:

117

In Formulae 401 and 402, x_{c1} and x_{c2} may each independently be an integer selected from 0 to 10.

In Formula 402, * and *' may each indicate a binding site to M in Formula 401.

According to an exemplary embodiment of the present invention, A_{401} and A_{402} in Formula 402 may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, or a dibenzothiophene group.

In Formula 402, X_{401} may be nitrogen (N), and X_{402} may be carbon, (C). Alternatively, X_{401} and X_{402} may each be nitrogen (N).

According to one or more exemplary embodiments of the present invention, R_{401} and R_{402} in Formula 402 may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, or a dibenzothiophenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; or

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; or

118



—Si(Q_{401})(Q_{402})(Q_{403}), —N(Q_{401})(Q_{402}), —B(Q_{401})(Q_{402}), —C(=O)(Q_{401}), —S(=O)₂(Q_{401}), or —P(=O)(Q_{401})(Q_{402}).

Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, or a naphthyl group; however, exemplary embodiments of the present invention are not limited thereto.

According to one or more exemplary embodiments of the present invention, when x_{c1} in Formula 401 is 2 or greater, two A_{401} (s) in at least two L_{401} (s) may be linked to each other via X_{407} , which is a linking group. Alternatively, two A_{402} (s) in at least two L_{401} (s) may be linked to each other via X_{408} , which is a linking group (see, e.g., Compounds PD1 to PD4 and PD7). X_{407} and X_{408} may each independently be selected from a single bond, —O—', —S—', —C(=O)—', —N(Q_{413})-', —C(Q_{413})(Q_{414})-', or *—C(Q_{413})=C(Q_{414})-*', in which Q_{413} and Q_{414} may each independently be selected from hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group; however, exemplary embodiments of the present invention are not limited thereto.







L_{402} in Formula 401 may be selected from a monovalent, divalent, or trivalent organic ligand. For example, L_{402} may be selected from a halogen, a diketone (e.g., acetylacetone), a carboxylic acid (e.g., picolinate), —C(=O), an isonitrile, —CN, or phosphorus (e.g., phosphine, or phosphite); however, exemplary embodiments of the present invention are not limited thereto.

According to one or more exemplary embodiments of the present invention, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25; however, exemplary embodiments of the present invention are not limited thereto:




119

-continued


**120**

-continued


PD9




PD4




PD5



PD6



PD7



PD10


PD11

PD12

PD13


121

-continued

**122**


-continued

PD14




PD19

PD15 15




PD20

20




PD21

30



PD17

35




PD22

55

PD18


60




65

123


-continued



PD23



PD24



PD25

According to one or more exemplary embodiments of the present invention, the fluorescent dopant may include an arylamine compound or a styrylamine compound.

The fluorescent dopant may include a compound represented by Formula 501:

45

According to one or more exemplary embodiments of the present invention, L_{501} to L_{503} in Formula 501 may each independently be selected from:

independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chryslenylene group, a perylbenzene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, or a pyridinylene group; or

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chryslenylene group, a pervlenylene group, a pentaphenylene group, a

In Formula 501,

Ar₅₀₁ may be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group.

In Formula 501, L_{501} to L_{503} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or

zolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, or a pyridinylene group; or a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chryseneylene group, a pervlenylene group, a pentaphenylene group, a

125

hexacenylenes group, a pentacenylenes group, a thiophenylenes group, a furanylenes group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylenes group, a benzothiophenylenes group, a dibenzofuranylenes group, a dibenzothiophenylenes group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

According to one or more exemplary embodiments of the present invention, R_{501} and R_{502} in Formula 501 may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, or a pyridinyl group; or

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a



126

hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}).

Q_{31} to Q_{33} may be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group.


According to one or more exemplary embodiments of the present invention, xd_4 in Formula 501 may be 2; however, exemplary embodiments of the present invention are not limited thereto.

As an example, the fluorescent dopant may be selected from Compounds FD1 to FD2:



127


-continued



FD3

128

-continued



5

10

15

20

25

FD5

FD6

30

35

40

FD4

45


50

FD7

55


60

65



129


-continued




FD8

130


-continued




FD12




FD9




FD13




35




FD14




FD10



FD15






FD11



FD16


131

-continued


**132**

-continued


FD17




FD18



FD19



FD22




DPVBi

According to one or more exemplary embodiments of the present invention, the fluorescent dopant may be selected from the following compounds; however, exemplary embodiments of the present invention are not limited thereto.


133

134

-continued




DPAVBi



TBP ϵ

DCM

POINT



Coumarin 6

85/15

The electron transport region may have a single-layered structure including a single layer including a single material. The electron transport region may have a single-layered structure including a single layer including different materials. The electron transport region may have a multi-layered structure having a plurality of layers each including different materials.


The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer; however, exemplary embodiments of the present invention are not limited thereto.

For example, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer

50 layer/electron transport layer/electron injection layer structure. For each structure, the layers may be sequentially stacked on an emission layer. However, exemplary embodiments of the structure of the electron transport region are not limited thereto.

55 According to an exemplary embodiment of the present invention, the electron transport region may include the condensed cyclic compound represented by Formula 1. According to one or more exemplary embodiments of the present invention, the electron transport region may include 60 an electron transport layer, which may include the condensed cyclic compound represented by Formula 1.

According to one or more exemplary embodiments of the present invention, the electron transport region may include at least one selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-dphenyl-1,10-phenanthroline (Bphen), Alq₃, BAIq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ.



Thicknesses of the buffer layer, the hole blocking layer, and the electron control layer may each be in a range of from about 20 Å to about 1,000 Å, for example, from about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have increased electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.


A thickness of the electron transport layer may be in a range of from about 100 Å to about 1,000 Å, for example, from about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

The electron transport region, for example, the electron transport layer in the electron transport region, may include, in addition to the condensed cyclic compound represented by Formula 1, a material including metal.

The material including metal may include at least one of an alkali metal complex or an alkaline earth-metal complex. The alkali metal complex may include a metal ion selected from a lithium (Li) ion, a sodium (Na) ion, a potassium (K) ion, a rubidium (Rb) ion, or a caesium (Cs) ion. The alkaline earth-metal complex may include a metal ion selected from a beryllium (Be) ion, a magnesium (Mg) ion, a calcium (Ca) ion, a strontium (Sr) ion, or a barium (Ba) ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenylan oxazole, a hydroxy phenylthiazole, a hydroxy diphenylan oxadiazole, a hydroxy diphenylthiadiazol, a hydroxy phenylpyridine, a hydroxy phenylbenzimidazole, a hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, or a cyclopentadiene; however, exemplary embodiments of the present invention are not limited thereto.

For example, the material including metal may include a lithium (Li) complex. The lithium (Li) complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.

25



45

The electron transport region may include an electron injection layer. The electron injection layer may facilitate injection of electrons from the second electrode 190. The electron injection layer may be in direct contact with the second electrode 190.

The electron injection layer may have a single-layered structure including a single layer including a single material. The electron injection layer may have a single-layered structure including a single layer including different materials. The electron injection layer may have a multi-layered structure having a plurality of layers including different materials.

The electron injection layer may include an alkali metal, an alkaline earth metal, a rare-earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare-earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare-earth metal complex, or any combination thereof.

The alkali metal may be selected from Li, Na, K, Rb, or Cs. According to an exemplary embodiment of the present invention, the alkali metal may be Li, Na, or Cs. According to an exemplary embodiment of the present invention, the

alkali metal may be Li or Cs; however, exemplary embodiments of the present invention are not limited thereto.

The alkaline earth metal may be selected from Mg, Ca, Sr, or Ba.

The rare-earth metal may be selected from Sc, Y, Ce, Yb, Gd, or Tb.

The alkali metal compound, the alkaline earth-metal compound, and the rare-earth metal compound may be selected from oxides or halides (e.g., fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, or the rare-earth metal.

The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , or alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, KI, or RbI. According to an exemplary embodiment of the present invention, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, or KI; however, exemplary embodiments of the present invention are not limited thereto.

The alkaline earth-metal compound may be selected from alkaline earth-metal compounds, such as BaO, SrO, CaO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), or $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$). According to an exemplary embodiment of the present invention, the alkaline earth-metal compound may be selected from BaO, SrO, or CaO; however, exemplary embodiments of the present invention are not limited thereto.

The rare-earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , or TbF_3 . According to an exemplary embodiment of the present invention, the rare-earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , or TbI_3 ; however, exemplary embodiments of the present invention are not limited thereto.

The alkali metal complex, the alkaline earth-metal complex, and the rare-earth metal complex may include an ion of an alkali metal, an alkaline earth-metal, or a rare-earth metal as described above. A ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare-earth metal complex may each independently be selected from hydroxy quinoline, hydroxy isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenylan oxazole, hydroxy phenylthiazole, hydroxy diphenylan oxadiazole, hydroxy diphenylthiadiazol, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, or cyclopentadiene; however, exemplary embodiments of the present invention are not limited thereto.

The electron injection layer may include an alkali metal, an alkaline earth metal, a rare-earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare-earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare-earth metal complex, or any combination thereof. According to one or more exemplary embodiments of the present invention, the electron injection layer may include an organic material. When the electron injection layer includes an organic material, an alkali metal, an alkaline earth metal, a rare-earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare-earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare-earth metal complex, or any combination thereof may be substantially homogeneously or non-homogeneously dispersed in a matrix including the organic material.

A thickness of the electron injection layer may be in a range of from about 1 to about 100, for example, from about 3 to about 90. When the thickness of the electron injection

layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

The second electrode 190 may be disposed on the organic layer 150. The organic layer 150 may have a structure as described above. The second electrode 190 may be a cathode. The cathode may be an electron injection electrode. Thus, the second electrode 190 may include a metal, an alloy, an electrically conductive compound, or any combination thereof, which may have a relatively low work function.

The second electrode 190 may include at least one of lithium (Li), silver (Ag), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), indium tin oxide (ITO), or indium zinc oxide (IZO); however, exemplary embodiments of the present invention are not limited thereto. The second electrode 190 may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

The second electrode 190 may have a single-layered structure. Alternatively, the second electrode 190 may have a multi-layered structure including two or more layers.

FIG. 2 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention. Referring to FIG. 2, an organic light-emitting device 20 may include a first capping layer 210, the first electrode 110, the organic layer 150, and the second electrode 190. The first capping layer 210, the first electrode 110, the organic layer 150, and the second electrode 190 may be sequentially stacked.

FIG. 3 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention. Referring to FIG. 3, an organic light-emitting device 30 may include the first electrode 110, the organic layer 150, the second electrode 190, and a second capping layer 220. The first electrode 110, the organic layer 150, the second electrode 190, and the second capping layer 220 may be sequentially stacked.

FIG. 4 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention. Referring to FIG. 4, an organic light-emitting device 40 may include the first capping layer 210, the first electrode 110, the organic layer 150, the second electrode 190, and the second capping layer 220. The first capping layer 210, the first electrode 110, the organic layer 150, the second electrode 190, and the second capping layer 220 may be sequentially stacked.

In the organic layer 150 of each of the organic light-emitting devices 20 and 40, light generated in an emission layer may pass through the first electrode 110 and the first capping layer 210 toward the outside. The first electrode 110 may be a semi-transmissive or a transmissive electrode. In the organic layer 150 of each of the organic light-emitting devices 30 and 40, light generated in an emission layer may pass through the second electrode 190 and the second capping layer 220 toward the outside. The second electrode 190 may be a semi-transmissive or a transmissive electrode.

The first capping layer 210 and the second capping layer 220 may increase external luminescent efficiency according to the principle of constructive interference.

The first capping layer 210 and the second capping layer 220 may each independently be an organic capping layer including an organic material, an inorganic capping layer




139

including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

At least one of the first capping layer 210 and the second capping layer 220 may include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine derivatives, naphthalocyanine derivatives, alkali metal complexes, and alkaline earth-based complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be substituted with a substituent including at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. According to one or more exemplary embodiments of the present invention, at least one of the first capping layer 210 and the second capping layer 220 may include an amine-based compound.

According to an exemplary embodiment of the present invention, each of at least one of the first capping layer 210 and the second capping layer 220 may independently include the condensed cyclic compound represented by Formula 201 or Formula 202.



According to one or more exemplary embodiments of the present invention, at least one of the first capping layer 210 and the second capping layer 220 may include a compound selected from Compounds HT28 to HT33 and Compounds CP1 to CP5; however, exemplary embodiments of the present invention are not limited thereto.



140

-continued

CP4



The organic light-emitting device according to some exemplary embodiments of the present invention has been described with reference to FIGS. 1-4. However, exemplary embodiments of the present invention are not limited thereto.

Layers included in the hole transport region, the emission layer, and the electron transport region may be formed by, for example, using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, or laser-induced thermal imaging (LITI).

When layers included in the hole transport region, the emission layer, and the electron transport region are formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of from about 100 Å to about 500 Å, at a vacuum degree of from about 10^{-8} torr to about 10^{-3} torr, and at a deposition rate of from about 0.01 Å/sec to about 100 Å/sec by taking into account a compound to be included in a layer to be formed, and the structure of a layer to be formed.

When layers included in the hole transport region, the emission layer, and the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of from about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of from about 80 to 200 by taking into account a compound to be included in a layer to be formed, and the structure of a layer to be formed.

The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched aliphatic saturated hydrocarbon monovalent group having 1 to 60 carbon atoms, and non-limiting examples thereof may include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, or a hexyl group. The term “C₁-C₆₀ alkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon

double bond in the middle or at the terminus of the C_2 - C_{60} alkyl group, and non-limiting examples thereof may include an ethenyl group, a propenyl group, or a butenyl group. The term “ C_2 - C_{60} alkenylene group” as used herein refers to a divalent group having the same structure as the C_2 - C_{60} alkenyl group.

The term “ C_2 - C_{60} alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the middle or at the terminus of the C_2 - C_{60} alkyl group, and non-limiting examples thereof may include an ethynyl group or a propynyl group. The term “ C_2 - C_{60} alkynylene group” as used herein refers to a divalent group having the same structure as the C_2 - C_{60} alkynyl group.

The term “ C_1 - C_{60} alkoxy group” as used herein refers to a monovalent group represented by $-OA_{101}$, in which A_{101} is the C_1 - C_{60} alkyl group, and non-limiting examples thereof may include a methoxy group, an ethoxy group, or an isopropoxy group.

The term “ C_3 - C_{10} cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and non-limiting examples thereof may include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, or a cycloheptyl group. The term “ C_3 - C_{10} cycloalkylene group” as used herein refers to a divalent group having the same structure as the C_3 - C_{10} cycloalkyl group.

The term “ C_1 - C_{10} heterocycloalkyl group” as used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and non-limiting examples thereof may include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuranyl group, or a tetrahydrothiophenyl group. The term “ C_1 - C_{10} heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C_1 - C_{10} heterocycloalkyl group.

The term “ C_3 - C_{10} cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and does not have aromaticity, and non-limiting examples thereof may include a cyclopentenyl group, a cyclohexenyl group, or a cycloheptenyl group. The term “ C_3 - C_{10} cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C_3 - C_{10} cycloalkenyl group.

The term “ C_1 - C_{10} heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Non-limiting examples thereof may include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranyl group, or a 2,3-dihydrothiophenyl group. The term “ C_1 - C_{10} heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C_1 - C_{10} heterocycloalkenyl group.

The term “ C_6 - C_{60} aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. The term “ C_6 - C_{60} arylene group” as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C_6 - C_{60} aryl group may include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, or a chrysenyl group. When the C_6 - C_{60} aryl group and the C_6 - C_{60} arylene group each include two or more rings, the rings may be chemically bonded to each other.

The term “ C_1 - C_{60} heteroaryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system

that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “ C_1 - C_{60} heteroarylene group” as used herein refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Non-limiting examples of the C_1 - C_{60} heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group. When the C_1 - C_{60} heteroaryl group and the C_1 - C_{60} heteroarylene group each include two or more rings, the rings may be chemically bonded to each other.

The term “ C_6 - C_{60} aryloxy group” as used herein refers to $-OA_{102}$, in which A_{102} is the C_6 - C_{60} aryl group. The term “ C_6 - C_{60} arylthio group” as used herein refers to a monovalent group represented by $-SA_{103}$, in which A_{103} is the C_6 - C_{60} aryl group.

The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group, for example, having 8 to 60 carbon atoms. The monovalent group has two or more rings condensed with each other. Additionally, only carbon atoms are used as a ring-forming atom. The entire molecular structure has non-aromaticity. An example of the monovalent non-aromatic condensed polycyclic group may include a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group, for example, having 1 to 60 carbon atoms. The monovalent group has two or more rings condensed with each other. The monovalent group has at least one heteroatom selected from N, O, Si, P, and S. Additionally, atoms other than carbon atoms are used as a ring-forming atom. The entire molecular structure has non-aromaticity. A non-limiting example of the monovalent non-aromatic condensed heteropolycyclic group may include a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

The term “ C_5 - C_{60} carbocyclic group” as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom is a carbon atom only. The C_5 - C_{60} carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The term “ C_5 - C_{60} carbocyclic group” as used herein refers to a ring, such as benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. According to one or more exemplary embodiments of the present invention, depending on the number of substituents connected to the C_5 - C_{60} carbocyclic group, the C_5 - C_{60} carbocyclic group may be a trivalent group or a quadrivalent group.

The term “ C_1 - C_{60} heterocyclic group” as used herein refers to a group having the same structure as the C_1 - C_{60} carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon. The number of carbon atoms may be in a range of 1 to 60.

At least one substituent of the substituted C_5 - C_{60} carbocyclic group, substituted C_1 - C_{60} heterocyclic group, substituted C_3 - C_{10} cycloalkylene group, substituted C_1 - C_{10} heterocycloalkylene group, substituted C_3 - C_{10}

cycloalkenylene group, substituted C_1 - C_{10} heterocycloalkenylene group, substituted C_6 - C_{60} arylene group, substituted C_1 - C_{60} heteroarylene group, substituted divalent non-aromatic condensed polycyclic group, substituted divalent non-aromatic condensed heteropolyyclic group, substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, or substituted monovalent non-aromatic condensed heteropolyyclic group may be selected from:

deuterium (-D), —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, or a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br,

—I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolyyclic group, —Si(Q_{11})(Q_{12})(Q_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), and —P(=O)(Q_{11})(Q_{12});

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolyyclic group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolyyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolyyclic group, —Si(Q_{21})(Q_{22})(Q_{23}), —N(Q_{21})(Q_{22}), —B(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), and —P(=O)(Q_{21})(Q_{22});

—Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), or —P(=O)(Q_{31})(Q_{32}).

Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a

C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolyyclic group, a biphenyl group, or a terphenyl group.

The term “Ph” as used herein refers to a phenyl group; the term “Me” as used herein refers to a methyl group; the term “Et” as used herein refers to an ethyl group; the term “ter-Bu” or “Bu” as used herein refers to a tert-butyl group; and the term “OMe” as used herein refers to a methoxy group.

The term “biphenyl group” as used herein refers to “a phenyl group substituted with a phenyl group.” As an example, a “biphenyl group” is a substituted phenyl group having a C_6 - C_{60} aryl group as a substituent.

The term “terphenyl group” as used herein refers to “a phenyl group substituted with a biphenyl group.” As an example, the “terphenyl group” is a substituted phenyl group having, as a substituent, a C_6 - C_{60} aryl group substituted with a C_6 - C_{60} aryl group.


The symbols * and * as used herein, unless defined otherwise, each refer to a binding site to a neighboring atom in a corresponding formula.


A compound according to one or more exemplary embodiments of the present invention and an organic light-emitting device according to one or more exemplary embodiments of the present invention will be described in more detail below with reference to Synthesis Examples and Examples. However, exemplary embodiments of the present invention are not limited thereto. The wording “B was used instead of A” as used in describing Synthesis Examples refers to an example in which a molar equivalent of B was used in place of A.

EXAMPLES

Synthesis Example 1

Synthesis of Compound 1



145**146**

Synthesis of Intermediate 1-2

2.4 g (10 mmol) of Intermediate 1-1, 2.88 g (11 mmol) of methyl 2-iodobenzoate, 0.58 g (0.5 mol) of $\text{Pd}(\text{PPh}_3)_4$, 4.15 g (30 mmol) of K_2CO_3 , 80 mL of distilled water, 160 mL of toluene, and 50 mL of ethanol were mixed while refluxing. After about 12 hours, the resulting mixture was cooled at room temperature, and then subjected to an extraction process using MC, and then washed using distilled water. Then, the resultant was dried using MgSO_4 , distilled under reduced pressure, and then the residue was separated by silica gel column chromatography, thus preparing 1.86 g (75%) of Intermediate 1-2.

Synthesis of Intermediate 1-3

2.48 g (10 mmol) of Intermediate 1-2 was dissolved in 200 mL of ethylether, and, at a temperature of -78° C. , 9.38 mL (15 mmol, 1.6M in diethyl ether) of MeLi was added thereto, and after about 30 minutes, the resultant was stirred at room temperature. After about 12 hours, distilled water was added thereto, and an extraction process was performed thereon by using EA. The resultant was dried by using MgSO_4 , distilled under reduced pressure to obtain a residue, which was then separated by silica gel column chromatography, thus preparing 1.88 g (80%) of Intermediate 1-3.

Synthesis of Intermediate 1-4

2.35 g (10 mmol) of Intermediate 1-3, 100 mL of an acetic acid, and 80 mL of H_3PO_4 were mixed at room temperature for about 2 hours. Distilled water was added thereto, and the resulting mixture was then neutralized by using a NaOH aqueous solution, subjected to an extraction process using MC, and then separated by silica gel column chromatography, thus preparing 0.92 g (40%) of Intermediate 1-4.

Synthesis of Compound 1

2.3 g (10 mmol) of Intermediate 1-4, 4.35 g (10 mmol) of 2,4-diphenyl-6-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-1,3,5-triazine, 0.58 g (0.5 mol) of $\text{Pd}(\text{PPh}_3)_4$, 4.15 g (30 mmol) of K_2CO_3 , 80 mL of distilled water, 160 mL of toluene, and 50 mL of ethanol were stirred while refluxing. After about 12 hours, the resultant was cooled to room temperature, subjected to an extraction process using MC, and then washed using distilled water. A residue was obtained after drying using MgSO_4 , distilling under reduced pressure, and then separating by silica gel column chromatography, thus preparing 3.02 g (Yield: 60%) of Compound 1.


Synthesis Example 2

Synthesis of Compound 5

Compound 1



Synthesis of Intermediate 1-1

1.93 g (10 mmol) of 5-bromo-2-chloropyrimidine was dissolved in 200 mL of THF, and then, at a temperature of -78° C. , 4 mL (2.5M in hexane) of normal butyllithium was added thereto. At the same temperature about one hour thereafter, 2.0 mL (10 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane was added thereto. At room temperature, the result was stirred for about 5 hours, and then, water was added thereto and a washing process was performed three times thereon using diethylether (100 mL). A washed diethylether layer was dried by using MgSO_4 , and then, dried under reduced pressure, thereby obtaining a product. The product was separation-purified by silica gel column chromatography, thus preparing 1.56 g (Yield 65%) of Intermediate 1-1.



147

148



Synthesis of Intermediate 5-1

2.48 g (10 mmol) of Intermediate 1-2 was dissolved in 200 mL of anhydrous THF, and then, at room temperature, 72.4 mL of phenyl magnesium bromide dissolved in THF (2 mol/L) was added dropwise thereto. After the dropwise-adding was completed, the resultant was stirred overnight while heating at a temperature of 50° C. A reaction solution was cooled to room temperature, and 100 mL of 10% ammonium chloride aqueous solution was added thereto to quench the reaction. An organic layer was washed three times with 50 mL of distilled water, and then dried by using MgSO₄. A compound obtained by filtering and concentrating the organic layer was stirred at room temperature overnight after 40 mL of acetic acid was added thereto. An organic layer was extracted therefrom and neutralized, and

then dried by using MgSO₄. A solid was obtained after the concentration was washed by using methanol, and then, filtered to complete the preparation of 1.28 g (Yield: 35%) of Intermediate 5-1.



Synthesis of Compound 5

4.1 g (Yield: 60%) of Compound 5 was synthesized in substantially the same manner as used to synthesize Compound 1 in Synthesis Example 1, except that Intermediate 5-1 was used instead of Intermediate 1-4, and 2,4-diphenyl-6-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-1,1'-bi-phenyl)-4-yl-1,3,5-triazine was used instead of 2,4-diphenyl-6-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-1,3,5-triazine.

149

Synthesis Example 3

Synthesis of Compound 22



Compound 22


Synthesis of Compound 22

4.1 g (Yield: 60%) of Compound 22 was synthesized in substantially the same manner as used to synthesize Compound 1 in Synthesis Example 1, except that 2,4-diphenyl-6-(4-(10-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)anthracen-9-yl)phenyl)-1,3,5-triazine was used instead of 2,4-

⁴⁵ diphenyl-6-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-1,3,5-triazine.


Synthesis Example 4

Synthesis of Compound 35



151

152




Compound 35

Synthesis of Compound 35

3.86 g (Yield: 55%) of Compound 35 was synthesized in substantially the same manner as used to synthesize Compound 5 in Synthesis Example 2, except that 4,6-diphenyl-2-(4'-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-[1,1'-biphenyl]-3-yl)pyrimidine was used instead of 2,4-diphenyl-6-(4'-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-[1,1'-biphenyl]-4-yl)-1,3,5-triazine.

Synthesis Example 5

Synthesis of Compound 75




Compound 75

30

Synthesis of Compound 75


3.6 g (Yield: 65%) of Compound 75 was synthesized in substantially the same manner as used to synthesize Compound 1 in Synthesis Example 1, except that 2,4-diphenyl-6-(7-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)naphthalen-2-yl)-1,3,5-triazine was used instead of 2,4-diphenyl-6-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-1,3,5-triazine.

Synthesis Example 6




Intermediate 1-4

Synthesis of Compound 76



Intermediate 5-1

153



Compound 76

154

Synthesis of Compound 76

3.39 g (Yield: 60%) of Compound 76 was synthesized in substantially the same manner as used to synthesize Compound 5 in Synthesis Example 2, except that 2,4-diphenyl-6-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)naphthalen-2-yl-1,3,5-triazine was used instead of 2,4-diphenyl-6-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-[1,1'-biphenyl]-4-yl)-1,3,5-triazine.

The compounds synthesized according to Synthesis Examples 1 to 6 were confirmed by ¹H NMR and MS/FAB. Results thereof are shown in Table 1 below.

TABLE 1

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	MS/FAB	
		found	calc.
1	9.12-9.10 (s, 1H), 8.83-8.77 (m, 4H), 8.64-8.58 (m, 2H), 8.55-8.51 (m, 2H), 8.02-7.98 (m, 1H), 7.64-7.58 (m, 4H), 7.47-7.35 (m, 4H), 7.31-7.26 (m, 1H), 2.36-2.31 (m, 6H),	503.62	503.61
5	9.29-9.25 (s, 1H), 8.82-8.77 (m, 4H), 8.56-8.43 (m, 3H), 7.98-7.86 (m, 5H), 7.65-7.58 (m, 4H), 7.50-7.33 (m, 4H), 7.29-7.13 (m, 10H), 7.05-7.00 (m, 1H)	703.84	703.85
22	9.38-9.35 (s, 1H), 8.82-8.77 (m, 4H), 8.63-8.58 (m, 2H), 8.28-8.21 (m, 2H), 8.01-7.98 (m, 1H), 7.93-7.87 (m, 2H), 7.75-7.71 (m, 2H), 7.66-7.58 (m, 4H), 7.48-7.35 (m, 8H), 7.31-7.25 (m, 1H), 2.40-2.36 (m, 6H)	679.82	679.83
35	9.28-9.23 (s, 1H), 8.61-8.49 (m, 4H), 8.31-8.25 (m, 4H), 8.08-8.04 (m, 2H), 8.00-7.98 (s, 1H), 7.98-7.94 (m, 1H), 7.86-7.83 (m, 2H), 7.54-7.44 (m, 6H), 7.37-7.33 (m, 1H), 7.31-7.22 (m, 6H), 7.21-7.13 (m, 6H), 7.04-7.00 (m, 1H)	702.84	702.86
75	9.25-9.22 (s, 1H), 9.07-8.97 (m, 2H), 8.81-8.77 (m, 4H), 8.71-8.58 (m, 2H), 8.32-8.23 (m, 2H), 8.01-7.98 (m, 1H), 7.63-7.58 (m, 4H), 7.47-7.35 (m, 4H), 7.31-7.25 (m, 1H), 2.35-2.32 (m, 6H)	553.65	553.67
76	9.05-9.02 (m, 1H), 9.01-9.00 (s, 1H), 8.89-8.74 (m, 7H), 8.41-8.39 (m, 1H), 7.97-7.92 (m, 2H), 7.63-7.59 (m, 4H), 7.49-7.34 (m, 4H), 7.28-7.14 (m, 10H), 7.04-7.00 (m, 1H)	677.80	677.81

Example 1

A substrate with ITO/Ag/ITO (thickness=70/1,000/70 Å) deposited thereon as an anode was cut to a size of 50 mm×50 mm×0.5 mm, sonicated by using isopropyl alcohol and pure water each for about 5 minutes, cleaned by exposure to ultraviolet rays for about 30 minutes and then exposure to ozone, and then the ITO glass substrate was mounted onto a vacuum deposition apparatus.

N-([1,1'-biphenyl]-4-yl)-9,9-dimethyl-N-(4-(9-phenyl-9H-carbazol-3-yl)phenyl)-9H-fluoren-2-amine (Compound HT3) and F4-TCNQ were co-deposited at a weight ratio of 98:2 on the substrate to form a hole injection layer having a thickness of about 100 Å. Compound 301 was vacuum


deposited on the hole transport layer to form a first hole transport layer having a thickness of about 1,200 Å. N,N-di([1,1'-biphenyl]-4-yl)-4'-(9H-carbazol-9-yl)-[1,1-biphenyl]-4-amine (Compound HT18) was vacuum deposited on the first hole transport layer to form a second hole transport layer having a thickness of about 100 Å.

9,10-di-naphthalene-2-yl-anthracene (ADN), which is a blue fluorescent host, and N,N,N',N'-tetraphenyl-pyrene-1,6-diamine (TPD), which is a blue fluorescent dopant, were


co-deposited on the second hole transport layer at a weight ratio of 98:2 to form an emission layer having a thickness of about 300 Å.

Then, Compound 1 and LiQ were co-deposited on the emission layer at a ratio of 5:5 to form an electron transport layer having a thickness of about 300 Å. LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of about 10 Å. Mg and Ag were vacuum deposited on the electron injection layer at a weight ratio of 90:10 to form a cathode having a thickness of about 120 Å. Thus, an organic light-emitting device was formed.

155



HT3



F4-TCNQ

5

10

15


20

25


30

35

40




ADN



FD1

Examples 2 to 6 and Comparative Examples 1 and
3

Organic light-emitting devices were manufactured in substantially the same manner as in Example 1, except that, in forming the electron transport layer, compounds shown in Table 2 were used instead of Compound 1.



HT18

55

60

65

Evaluation Example

The driving voltage, luminance, efficiency, and half lifespan of the organic light-emitting devices manufactured according to Examples 1 to 6 and Comparative Examples 1 to 3 were measured at a current density of 10 mA/cm² by using a Kethley SMU 236 and a luminance meter PR650. Results thereof are shown in Table 2. The half lifespan refers to an amount of time that has lapsed when luminance reaches 97% of the initial luminance at the current density of 10 mA/cm².

156

-continued


TABLE 2

	Electron transport layer	Driving voltage (V)	Current density (mA/cm ²)	luminance (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr @ 10 mA/cm ²) (T97)
Example1	Compound1	3.9	10	650	6.50	Blue	152 hr
Example2	Compound5	4.2	10	587	5.87	Blue	175 hr
Example3	Compound22	3.95	10	642	6.42	Blue	132 hr
Example4	Compound35	4.3	10	594	5.94	Blue	181 hr
Example5	Compound75	3.84	10	648	6.48	Blue	154 hr
Example6	Compound76	4.02	10	612	6.12	Blue	179 hr
Comparative	Compound A	6.1	10	510	5.10	Blue	53 hr
Example 1							
Comparative	Compound B	4.4	10	526	5.26	Blue	95 hr
Example 2							
Comparative	Compound C	4.5	10	465	4.65	Blue	70 hr
Example 3							

-continued


1 20

75



159

-continued



Compound B

5

10

15

20

Compound C

25

30

35


40

45

50

55

60



Referring to Table 2, the organic light-emitting devices of Examples 1 to 6 had relatively low driving voltage, and a relatively high luminance, efficiency, and half lifespan characteristics than Comparative Examples 1 to 3.

An organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have a low driving voltage, high efficiency, high luminance, and a long lifespan.


It should be understood that exemplary embodiments of the present invention described herein should be considered in a descriptive sense and not for purposes of limitation. Descriptions of features or aspects within each example embodiment should typically be considered as available for other similar features or aspects in other example embodiments.

While one or more example embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention.


160

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:



<Formula 1>



<Formula 2>

wherein, in Formulae 1 and 2,
 X_1 is N or $C(R_{11})$, X_2 is N or $C(R_{12})$, and X_3 is N or $C(R_{13})$, and at least one of X_1 to X_3 is N;

L_1 to L_3 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene, a substituted or unsubstituted C_6 - C_{60} arylene, a substituted or unsubstituted C_1 - C_{60} heteroarylene, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

a_1 to a_3 are each independently an integer selected from 0 to 3, wherein, when a_1 is 2 or greater, at least 2 or L_1 (s) are the same as or different from each other, when a_2 is 2 or greater, at least 2 L_2 (s) are the same as or different from each other, and when a_3 is 2 or greater, at least 2 L_3 (s) are the same as or different from each other;

Ar_1 and Ar_2 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_1 cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group;

one of R_1 and R_2 is a group represented by Formula 2 and the other of R_1 and R_2 is hydrogen;

R_3 , R_4 , R_5 and R_6 are each hydrogen;

R_7 , R_8 and R_{11} to R_{13} are each independently selected from a group represented by Formula 2, hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or

161

unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $—Si(Q_1)(Q_2)(Q_3)$, $—N(Q_1)(Q_2)$, $—B(Q_1)(Q_2)$, $—C(=O)(Q_1)$, $—S(=O)_2(Q_1)$, or $—P(=O)(Q_1)(Q_2)$;

R_7 and R_8 are optionally linked to form a saturated or unsaturated ring; at least one of R_1 or R_2 is a group represented by Formula 2;

* indicates a binding site to a neighboring atom; and at least one substituent of the substituted C_3 - C_{10} cycloalkylene group, substituted C_1 - C_{10} heterocycloalkylene group, substituted C_3 - C_{10} cycloalkenylene group, substituted C_1 - C_{10} heterocycloalkenylene group, substituted C_6 - C_{60} arylene group, substituted C_1 - C_{60} heteroarylene group, a substituted divalent non-aromatic condensed polycyclic group, a substituted divalent non-aromatic condensed heteropolycyclic group, substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, or substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $—Si(Q_{11})(Q_{12})(Q_{13})$, $—N(Q_{11})(Q_{12})$, $—B(Q_{11})(Q_{12})$, $—C(=O)(Q_{11})$, $—S(=O)_2(Q_{11})$, and $—P(=O)(Q_{11})(Q_{12})$;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, or a terphenyl group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} hetero-

162

cycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, 13 $Si(Q_{21})(Q_{22})(Q_{23})$, $—N(Q_{21})(Q_{22})$, $—B(Q_{21})(Q_{22})$, $—C(=O)(Q_{21})$, $—S(=O)_2(Q_{21})$, and $—P(=O)(Q_{21})(Q_{22})$; or $—Si(Q_{31})(Q_{32})(Q_{33})$, $—N(Q_{31})(Q_{32})$, $—B(Q_{31})(Q_{32})$, $—C(=O)(Q_{31})$, $—S(=O)_2(Q_{31})$, or $—P(=O)(Q_{31})(Q_{32})$,

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{60} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group substituted with a C_6 - C_{60} aryl group, a terphenyl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group substituted with a C_6 - C_{60} aryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

2. The condensed cyclic compound of claim 1, wherein X_1 is N , X_2 is $C(R_{12})$, and X_3 is $C(R_{13})$ or X_1 and X_2 are each N , X_2 is N , and X_3 is $C(R_{13})$, or X_1 , X_2 , and X_3 are each N .

3. The condensed cyclic compound of claim 1, wherein L_1 to L_3 are each independently selected from: a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chryseneylene group, a naphthaceneylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolin-

163

nylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, or an imidazopyrimidinylene group; or


a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an arnidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysene group, a naphthacenyl group, a picenyl group, a perylenyl group, a naphthacenyl group, a picenyl group, a perylenyl group;

164


group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃),

wherein Q₃₁ to Q₃₃ are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group.


4. The condensed cyclic compound of claim 1, wherein L₁ to L₃ are each independently selected from groups represented by Formula 3-1 to Formula 3-41:




Formula 3-1




Formula 3-2



Formula 3-3













Formula 3-4



Formula 3-5

165


-continued

**166**

-continued


Formula 3-6

5




Formula 3-7

10




Formula 3-8

20




Formula 3-9

30




Formula 3-10

35




Formula 3-11

40




Formula 3-12

45




Formula 3-13

50






Formula 3-14

55



Formula 3-15

60



Formula 3-16

Formula 3-17

Formula 3-18

Formula 3-19

Formula 3-20

Formula 3-21

Formula 3-22

Formula 3-23

Formula 3-24









Formula 3-25

Formula 3-26

Formula 3-27

167


-continued

**168**

-continued


Formula 3-28

5




Formula 3-29 10

15




Formula 3-30

20




Formula 3-31 25

30




Formula 3-32 35

35




Formula 3-33

45




Formula 3-34 50

55



Formula 3-35

60



65

Formula 3-36

Formula 3-37


Formula 3-38

Formula 3-39

Formula 3-40

169

-continued



wherein, in Formulae 3-1 to 3-41,
 Y_1 is selected from O, S, C(Z_3)(Z_4), N(Z_5), or Si(Z_6)(Z_7);
 Z_1 to Z_7 are each independently selected from hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a diheuzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}), wherein Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group,
 d_2 is an integer selected from 1 or 2,
 d_3 is an integer selected from 1 to 3,
 d_4 is an integer selected from 1 to 4,
 d_5 is an integer selected from 1 to 5,
 d_6 is an integer selected from 1 to 6,
 d_8 is an integer selected from 1 to 8, and

* and *' each indicate binding sites to a neighboring atom.

5. The condensed cyclic compound of claim 1, wherein
 a_1 is an integer selected from 1 or 2, and
 a_2 and a_3 are each independently an integer selected from 0 or 1.


6. The condensed cyclic compound of claim 1, wherein
 $*(L_1)_{a_1}-*'$, $*(L_2)_{a_2}-*'$, and $*(L_3)_{a_3}-*'$ are each independently a single bond; or are selected from groups represented by Formula 4-4 to Formula 4-44:

Formula 3-41


170

-continued


Formula 4-4




5




10




15




20




25



30



35



40

Formula 4-10

Formula 4-11

Formula 4-1


55

Formula 4-2

60

Formula 4-3









65



Formula 4-12


171

-continued

**172**
-continued

Formula 4-13


5



10

Formula 4-14


15



20


Formula 4-15

25



Formula 4-16


30



35


Formula 4-17

40



Formula 4-18


45



50


Formula 4-19

55



Formula 4-20

60



65

Formula 4-21

Formula 4-22

Formula 4-23

Formula 4-24

Formula 4-25

Formula 4-26








Formula 4-27

Formula 4-28

Formula 4-29

173

-continued




174


-continued

Formula 4-30

5




10




Formula 4-31

15



Formula 4-32


20



25

Formula 4-33


30



35

Formula 4-34


40



45


Formula 4-35

50



Formula 4-36

65



55 wherein, in Formulae 4-1 to 4-44,
 * and */ each indicate a binding site to a neighboring atom.

7. The condensed cyclic compound of claim 1, wherein
 Ar₁ and Ar₂ are each independently selected from:

a phenyl group, a biphenyl group, a terphenyl group, a
 pentalenyl group, an indenyl group, a naphthyl group,
 an azulenyl group, a heptalenyl group, an indacenyl
 group, an acenaphthyl group, a phenalenyl group, a
 phenanthrenyl group, an anthracenyl group, a fluoranthenyl
 group, a triphenylenyl group, a pyrenyl group, a chrysene group, a
 naphthacenyl group, a picenyl group, a perylenyl group, a
 pentaphenyl group,

175

a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, an isobenzothiazolyl group, a benzoazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group; or

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysanyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, an isobenzothiazolyl group, a benzoazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$; or

$-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$,


wherein Q_1 to Q_3 and Q_{31} to Q_{33} are each independently selected from a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, or a naphthyl group.

176


a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$;

8. The condensed cyclic compound of claim 1, wherein


Ar_1 and Ar_2 are each independently selected from groups represented by one of the following Formulae 5-1 to 5-79:




Formula 5-1




Formula 5-2




Formula 5-3



Formula 5-4




Formula 5-5



Formula 5-6


177

-continued



178












-continued



US 10,461,262 B2

179

-continued




180

-continued


Formula 5-32

5




Formula 5-33

10




Formula 5-34

15




Formula 5-35

20




Formula 5-36

25




Formula 5-37

30




Formula 5-38

35




Formula 5-39

40




Formula 5-40

45




Formula 5-41

50




Formula 5-42

55



Formula 5-43

60



Formula 5-43

Formula 5-44

Formula 5-45

Formula 5-46

Formula 5-47

Formula 5-48

Formula 5-49

Formula 5-50












Formula 5-51

Formula 5-52

US 10,461,262 B2

181


-continued

**182**

-continued


Formula 5-53

5




Formula 5-54

10




Formula 5-55

15




Formula 5-56

20




Formula 5-57

25




Formula 5-58

30




Formula 5-59

35




Formula 5-60

40




Formula 5-61

45




Formula 5-62

50



Formula 5-63

55



Formula 5-64

Formula 5-65

Formula 5-66

Formula 5-67


Formula 5-68

Formula 5-69

Formula 5-70

183

-continued




184

-continued

Formula 5-71

5



Formula 5-72

10

Formula 5-73

15

wherein, in Formulae 5-1 to 5-79,
 Y_{11} is selected from O, S, C(Z_{13})(Z_{14}), N(Z_{15}) or Si(Z_{16})(Z_{17}),

Z_{11} to Z_{17} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenol group, a Spiro-fluorenol group, a benzofluorenol group, a dibenzofluorenol group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysene group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, and —Si(Q_{33})(Q_{34})(Q_{35}), wherein Q_{33} to Q_{35} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

Formula 5-74

20

Formula 5-75

25

Formula 5-76

30

Formula 5-77

35

Formula 5-78

40

Formula 5-79

45

e_2 is an integer selected from 1 or 2,

e_3 is an integer selected from 1 to 3,

e_4 is an integer selected from 1 to 4,

e_5 is an integer selected from 1 to 5,

e_6 is an integer selected from 1 to 6,


e_7 is an integer selected from 1 to 7,

e_9 is an integer selected from 1 to 9, and


* indicates a binding site to a neighboring atom.

9. The condensed cyclic compound of claim 1, wherein Ar_1 and Ar_2 are each independently selected from groups represented by Formulae 6-1 to 6-158:


Formula 6-1




Formula 6-2



Formula 6-3




Formula 6-4




185

-continued

**186**

-continued


Formula 6-5



Formula 6-6

5

Formula 6-7



10

Formula 6-8

15

Formula 6-9

20

Formula 6-10

25

Formula 6-11

30

Formula 6-12

35

Formula 6-13

40

Formula 6-14






45

Formula 6-15

50

Formula 6-16

60



65

Formula 6-17

Formula 6-18

Formula 6-19

Formula 6-20

Formula 6-21


Formula 6-22

Formula 6-23

US 10,461,262 B2


187

-continued



Formula 6-24


5



188


-continued

Formula 6-30




Formula 6-25

15




Formula 6-31




Formula 6-26

20




Formula 6-32




Formula 6-27

25




Formula 6-33




Formula 6-28

30




Formula 6-34



Formula 6-29








35



Formula 6-35










189

-continued

**190**

-continued

Formula 6-36



Formula 6-43

Formula 6-44

Formula 6-45

Formula 6-46

Formula 6-47

Formula 6-48







Formula 6-49

Formula 6-50

Formula 6-51

191


-continued

**192**

-continued


Formula 6-52

5



Formula 6-53 10

15




Formula 6-54

20




Formula 6-55 25

30




Formula 6-56

35




Formula 6-57 40

40




Formula 6-58 45

45




Formula 6-59 50

50




Formula 6-60 55

55



Formula 6-61 60

60



Formula 6-61

Formula 6-62

Formula 6-63

Formula 6-64

Formula 6-65

Formula 6-66








Formula 6-67

Formula 6-68

Formula 6-69

193

-continued




194

-continued


Formula 6-70




Formula 6-71




Formula 6-72




Formula 6-73




Formula 6-74




Formula 6-75




Formula 6-76



Formula 6-77



Formula 6-78



Formula 6-79

Formula 6-80

Formula 6-81

Formula 6-82

Formula 6-83


Formula 6-84

Formula 6-85


Formula 6-86

195

-continued




Formula 6-87


**196**

-continued


Formula 6-92




Formula 6-88




Formula 6-93




Formula 6-89




Formula 6-94




Formula 6-90



Formula 6-95




Formula 6-91



Formula 6-96

197


-continued




Formula 6-97

198


-continued




Formula 6-102




Formula 6-98




Formula 6-103




Formula 6-99




Formula 6-104




Formula 6-100



Formula 6-105











Formula 6-101



Formula 6-107


199

-continued


**200**

-continued


Formula 6-108




Formula 6-109




Formula 6-110




Formula 6-111




Formula 6-112




Formula 6-113




Formula 6-114




Formula 6-115




Formula 6-116




Formula 6-117




Formula 6-118




Formula 6-119




Formula 6-120




Formula 6-121



Formula 6-122



Formula 6-123











Formula 6-124



Formula 6-125

201


-continued

**202**

-continued


Formula 6-126

5




Formula 6-127

10




Formula 6-128

15




20




Formula 6-129

25




30




Formula 6-130

35




40




Formula 6-131

45



Formula 6-132


50



55

Formula 6-133

60



65

Formula 6-134

Formula 6-135

Formula 6-136

Formula 6-137

Formula 6-138

Formula 6-139










Formula 6-140

Formula 6-141

Formula 6-142

203


-continued



204


-continued

Formula 6-152




Formula 6-143

5




Formula 6-144

10




Formula 6-145

15




Formula 6-146

20




Formula 6-147

25



Formula 6-148

30



Formula 6-149

35

Formula 6-150

40

45

Formula 6-151

50

55

wherein, in Formulae 6-1 to 6-158,

* indicates a binding site to a neighboring atom.

10. The condensed cyclic compound of claim 1, wherein one of R₁ and R₂ is a group represented by Formula 2, and the other of R₁ and R₂ is hydrogen;R₃, R₄, R₅ and R₆ are each hydrogen;R₇, R₈, and R₁₁ to R₁₃ are each independently selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazone group, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substi-

Formula 6-153

Formula 6-154

Formula 6-155

Formula 6-156

Formula 6-157

Formula 6-158

205

tuted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_1 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, or $-\text{Si}(Q_1)(Q_2)(Q_3)$.

11. The condensed cyclic compound of claim 1, wherein one of R_1 and R_2 is a group represented by Formula 2, and the other of R_1 and R_2 is hydrogen;

R_3 , R_4 , R_5 and R_6 are each hydrogen;

R_7 , R_8 and R_{11} to R_{13} are each independently selected from:

a group represented by Formula 2, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxaliny group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(Q_1)(Q_2)(Q_3)$; or

$-\text{Si}(Q_1)(Q_2)(Q_3)$,

wherein Q_1 to Q_3 and Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group.

12. The condensed cyclic compound of claim 1, wherein one of R_1 and R_2 is a group represented by Formula 2, and the other of R_1 and R_2 is hydrogen;

R_3 , R_4 , R_5 and R_6 are each hydrogen;

R_7 , R_8 and R_{11} to R_{13} are each independently selected from:

a group represented by Formula 2, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or a triazinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluo-

206

ranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(Q_{31})(Q_{32})(Q_{33})$; or

$-\text{Si}(Q_1)(Q_2)(Q_3)$,

wherein Q_1 to Q_3 and Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, or a naphthyl group.

13. A condensed cyclic compound represented by one of Formulae 1A-1 to 1A-3 and 1B-1 to 1B-3:


a group represented by Formula 2, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or a triazinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and $-\text{Si}(Q_{31})(Q_{32})(Q_{33})$; or


$-\text{Si}(Q_1)(Q_2)(Q_3)$,

wherein Q_1 to Q_3 and Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group.




<Formula 1A-1>

5




<Formula 1A-2>

10




<Formula 1A-3>

15




<Formula 1B-1>

30





<Formula 1B-2>

55



-continued

<Formula 1B-3>



<Formula 2>

wherein, in Formulae 1A-1 to 1A-3 and 1B-1 to 1B-3, X_1 is N or $C(R_{11})$, X_2 is N or $C(R_{12})$, and X_3 is N or $C(R_{13})$, and at least one of X_1 to X_3 is N; L_1 to L_3 is selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene, a substituted or unsubstituted C_6 - C_{60} arylene, a substituted or unsubstituted C_1 - C_{60} heteroarylene, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

a1 to a3 is an integer selected from 0 to 3, wherein, when a1 is 2 or greater, at least 2 L_1 (s) are the same as or different from each other; when a2 is 2 or greater, at least 2 L_2 (s) are the same as or different from each other, and when a3 is 2 or greater, at least 2 L_3 (s) are the same as or different from each other;

Ar_1 and Ar_2 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group;

R_7 , R_8 and R_{11} to R_{13} are each independently selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or

209

unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $—Si(Q_1)(Q_2)(Q_3)$, $—N(Q_1)(Q_2)$, $—B(Q_1)(Q_2)$, $—C(=O)(Q_1)$, $—S(=O)_2(Q_1)$, or $—P(=O)(Q_1)(Q_2)$;

R_7 and R_8 are optionally linked to form a saturated or unsaturated ring;

* indicates a binding site to a neighboring atom; and at least one substituent of the substituted C_3 - C_{10} cycloalkylene group, substituted C_1 - C_{10} heterocycloalkylene group, substituted C_3 - C_{10} cycloalkenylene group, substituted C_1 - C_{10} heterocycloalkenylene group, substituted C_6 - C_{60} arylene group, substituted C_1 - C_{60} heteroarylene group, a substituted divalent non-aromatic condensed polycyclic group, a substituted divalent non-aromatic condensed heteropolycyclic group, substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, or substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $—Si(Q_{11})(Q_{12})(Q_{13})$, $—N(Q_{11})(Q_{12})$, $—B(Q_{11})(Q_{12})$, $—C(=O)(Q_{11})—S(=O)_2(Q_{11})$, and $—P(=O)(Q_{11})(Q_{12})$;

C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, or a terphenyl group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, or a terphenyl group;


210

eroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazone group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $—Si(Q_{21})(Q_{22})(Q_{23})$, $—N(Q_{21})(Q_{22})$, $—B(Q_{21})(Q_{22})$, $—C(=O)(Q_{21})$, $—S(=O)_2(Q_{21})$, and $—P(=O)(Q_{21})(Q_{22})$; or $—Si(Q_{31})(Q_{32})(Q_{33})$, $—N(Q_{31})(Q_{32})$, $—B(Q_{31})(Q_{32})$, $—C(=O)(Q_{31})$, $—S(=O)_2(Q_{31})$, or **13** $P(=O)(Q_{31})(Q_{32})$,

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $—F$, $—Cl$, $—Br$, $—I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group substituted with a C_6 - C_{60} aryl group, a terphenyl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group substituted with a C_6 - C_{60} aryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.


14. The condensed cyclic compound of claim **1**, wherein the condensed cyclic compound is one of the following Compounds 1 to 79:

1




211


-continued




2



15




40




55

212


-continued




5




20



30



50



60

6

7


8

9


10

213


-continued



11




12




13

25

14



15



55


60

65


214

-continued

16



17



20

25

30

35

40

45

50

55

60

65

17


18

19

20

215


-continued




21

216


-continued




25




22 20




26




23



27




24



28


217

-continued



**218**

-continued




29 33





30 34



30 35




32 37



219


-continued




38

220


-continued




42




39




43




40



44




41




45

221


-continued




46




5



20



40




55


222

-continued


50




10




15




25




30




40



50



60




65

53


223

-continued



**224**

-continued


58



59




57



225

-continued

63




5

10

15


64




20

25

30



35




45

50

67

55




60

65

226

-continued

68



5

10

15

64

20

25

30

40

45

50

67

55


60

65

69

70


71



227


-continued

72




5

73 15




20

74 30




35

75



55




60

65


228

-continued


77



78



79



15. An organic light-emitting device comprising:
a first electrode;
a second electrode facing the first electrode; and
an organic layer disposed between the first electrode and
the second electrode, the organic layer including an
emission layer,

wherein the organic layer includes at least one condensed
cyclic compound represented by Formula 1 of claim 1.

16. The organic light-emitting device of claim 15, wherein
the first electrode is an anode,
the second electrode is a cathode, and

the organic layer includes a hole transport region disposed
between the first electrode and the emission layer, and
an electron transport region disposed between the emis-
sion layer and the second electrode.

17. The organic light-emitting device of claim 16, wherein
the electron transport region includes the at least one
condensed cyclic compound represented by Formula 1
of claim 1.

229

18. The organic light-emitting device of claim 16, wherein the electron transport region includes an electron transport layer, and the electron transport layer includes the at least one condensed cyclic compound represented by Formula 1 of claim 1. 5

* * * * *

230

专利名称(译)	稠合环状化合物和包括该稠合环状化合物的有机发光装置		
公开(公告)号	US10461262	公开(公告)日	2019-10-29
申请号	US15/386877	申请日	2016-12-21
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SIM MUNKI OH JEONGA JUNG HYEJIN HAN SANGHYUN KIM SOOYON KIM YOUNGKOOK KIM TAEKYUNG HWANG SEOKHWAN		
发明人	SIM, MUNKI OH, JEONGA JUNG, HYEJIN HAN, SANGHYUN KIM, SOOYON KIM, YOUNGKOOK KIM, TAEKYUNG HWANG, SEOKHWAN		
IPC分类号	H01L51/00 C07D403/10 H01L51/50		
CPC分类号	H01L51/0052 H01L51/0067 C07D403/10 H01L51/0072 H01L51/5064		
审查员(译)	杨 , JAY		
优先权	1020150184065 2015-12-22 KR 1020160099627 2016-08-04 KR		
其他公开文献	US20170179408A1		
外部链接	Espacenet		

摘要(译)

由式1表示的稠合环状化合物和包括该稠合环状化合物的有机发光装置。

10

190
150
110