



US009548341B2

(12) **United States Patent**
So et al.

(10) **Patent No.:** **US 9,548,341 B2**
(45) **Date of Patent:** **Jan. 17, 2017**

(54) **ORGANIC LIGHT EMITTING DIODE
DISPLAY**

USPC 257/40, 483, E21.158, E51.022; 313/504,
313/505, 506, 509; 345/204, 600, 76, 82,
85

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin, Gyeonggi-do (KR)

See application file for complete search history.

(72) Inventors: **Dong-Yoon So**, Yongin (KR); **Ji-Eun
Kim**, Yongin (KR); **Han-Soo Kim**,
Yongin (KR); **Young-Jun Chung**,
Yongin (KR)

(56) **References Cited**

U.S. PATENT DOCUMENTS

2009/0146929 A1* 6/2009 Kim H01L 51/5278
345/77
2011/0043096 A1* 2/2011 Asaki H01L 27/3211
313/483

(73) Assignee: **SAMSUNG DISPLAY CO., LTD.**,
Yongin, Gyeonggi-Do (KR)

FOREIGN PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

KR 1020040025449 3/2004
KR 1020110058407 6/2011
KR 1020120015675 2/2012

* cited by examiner

(21) Appl. No.: **14/257,359**

Primary Examiner — David Vu

(22) Filed: **Apr. 21, 2014**

Assistant Examiner — Mouloucoulaye Inoussa

(65) **Prior Publication Data**

US 2015/0048322 A1 Feb. 19, 2015

(74) *Attorney, Agent, or Firm* — F. Chau & Associates,
LLC

(30) **Foreign Application Priority Data**

Aug. 14, 2013 (KR) 10-2013-0096837

(57) **ABSTRACT**

OLED display that includes: a substrate; a plurality of thin film transistors formed on the substrate; a plurality of first electrodes respectively connected to the thin film transistors; a pixel definition layer formed on the substrate and having a first opening, a second opening, and a third opening respectively exposing first, second, and third first electrodes of the plurality of first electrodes; an emission layer formed at the first opening, the second opening, and the third opening; and a second electrode formed on the emission layer, wherein the first opening has a first pair of boundary lines facing each other and a second pair of boundary lines facing each other, and the first pair of boundary lines overlap boundary lines of a pair of boundary lines of the first first electrode or are positioned outside the boundary lines of the pair of boundary lines of the first first electrode.

(51) **Int. Cl.**

H01L 27/32 (2006.01)
H01L 51/52 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 27/3246** (2013.01); **H01L 27/3276**
(2013.01); **H01L 27/326** (2013.01); **H01L**
27/3216 (2013.01); **H01L 27/3218** (2013.01);
H01L 51/5203 (2013.01); **H01L 2227/323**
(2013.01)

(58) **Field of Classification Search**

CPC H01L 27/3246; H01L 27/3218; H01L
51/5203

17 Claims, 11 Drawing Sheets





FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10





FIG. 11



1

**ORGANIC LIGHT EMITTING DIODE
DISPLAY****CROSS-REFERENCE TO RELATED
APPLICATION**

This application claims priority under 35 U.S.C. §119 to Korean Patent Application No. 10-2013-0096837 filed in the Korean Intellectual Property Office on Aug. 14, 2013, the disclosure of which is incorporated by reference herein in its entirety.

TECHNICAL FIELD

The present invention relates to an organic light emitting diode (OLED) display.

DISCUSSION OF RELATED ART

An OLED display includes two electrodes and an organic emission layer interposed therebetween. One electrode may be a cathode and the other may be an anode. Electrons injected from the cathode and holes injected from the anode are bonded to each other in the organic emission layer to form excitons, and while the excitons discharge energy, light is emitted.

The OLED display includes a plurality of pixels each including an OLED that is formed of a cathode, an anode, and an organic emission layer. A plurality of transistors and capacitors for driving the OLED are formed in each pixel. The plurality of transistors include a switching transistor and a driving transistor.

Among the transistors, the organic emission layer may be deposited and formed by using a fine metal mask (FMM), and in this case, an open region of the mask and a region where the organic emission layer is to be formed are aligned with each other. However, a misalignment may occur while the mask is moved.

If the misalignment occurs, the region corresponding to the organic emission layer is reduced or a wrong color is deposited such that color mixing occurs, for example.

SUMMARY

An organic light emitting diode (OLED) display according to an exemplary embodiment of the present invention includes: a substrate; a plurality of thin film transistors formed on the substrate; a plurality of first electrodes respectively connected to the thin film transistors; a pixel definition layer formed on the substrate and having a first opening, a second opening, and a third opening respectively exposing first, second, and third first electrodes of the plurality of first electrodes; an emission layer formed at the first opening, the second opening, and the third opening; and a second electrode formed on the emission layer, wherein the first opening has a first pair of boundary lines facing each other and a second pair of boundary lines facing each other, and the first pair of boundary lines overlap boundary lines of a pair of boundary lines of the first first electrode or are positioned outside the boundary lines of the pair of boundary lines of the first first electrode.

The second pair of boundary lines of the first opening may be positioned apart from another pair of boundary lines of the first first electrode by at least 4 μm .

Boundary lines of the second and third openings may be respectively positioned within boundary lines of the second and third first electrodes.

2

The boundary lines of the second and third openings may be positioned apart from the boundary lines of the second and third first electrodes by at least 4 μm .

The emission layer may include a first emission layer, a second emission layer, and a third emission layer respectively positioned on the first, second, and third electrodes, and the first emission layer, the second emission layer, and the third emission layer are respectively positioned in the first, second, and third openings.

The first emission layer, the second emission layer, and the third emission layer may emit light of different colors.

The first emission layer, the second emission layer, and the third emission layer may be a blue emission layer, a red emission layer, and a green emission layer, respectively.

A plurality of the first, second and third emission layers may form columns and rows, and the columns may include a first column formed of the first emission layers and a second column formed of the second emission layers and the third emission layers.

The first column and the second column may be alternately repeated, and the second emission layer and the third emission layer may be alternately positioned in the second column.

An OLED display according to an exemplary embodiment of the present invention includes: a substrate; a plurality of thin film transistors formed on the substrate; a plurality of first electrodes respectively connected to the thin film transistors; a pixel definition layer formed on the substrate and having a first opening, a second opening, and a third opening respectively exposing first, second, and third first electrodes of the plurality of first electrodes; an emission layer formed in the first opening, the second opening, and the third opening; and a second electrode formed on the emission layer, wherein the first opening exposes at least one side of the first first electrode, and the second and third openings respectively have a boundary entirely positioned within the boundary of the second and third first electrodes.

The emission layer may include a first emission layer, a second emission layer, and a third emission layer for emitting different colors, wherein the first emission layer, the second emission layer, and the third emission layer may be respectively positioned in the first, second, and third openings.

The first emission layer, the second emission layer, and the third emission layer may be a blue emission layer, a red emission layer, and a green emission layer, respectively.

A plurality of the first, second and third emission layers may form columns and rows, and the columns may include a first column formed of the first emission layers, and a second column formed of the second emission layers and the third emission layers.

The first column and the second column may be alternately repeated, and the second emission layer and the third emission layer may be alternately positioned in the second column.

An OLED display according to an exemplary embodiment of the present invention includes: a substrate; a plurality of pixel electrodes formed on the substrate; and a pixel definition layer having a plurality of openings exposing the pixel electrodes, wherein a first opening of the pixel definition layer exposes at least one side of a first pixel electrode of the pixel electrodes or overlaps at least one side of the first pixel electrode.

A second opening of the pixel definition layer may be surrounded by a second pixel electrode of the pixel elec-

trodes and a third opening of the pixel definition layer may be surrounded by a third pixel electrode of the pixel electrodes.

The first opening may expose at least one side of a fourth pixel electrode of the pixel electrodes.

The first and fourth pixel electrodes may be disposed in the same column.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a layout view of a pixel of an organic light emitting diode (OLED) display according to an exemplary embodiment of the present invention.

FIG. 2 is a pixel layout view of an OLED display according to an exemplary embodiment of the present invention.

FIG. 3 to FIG. 8 are top plan views of intermediate steps of manufacturing an OLED display according to an exemplary embodiment of the present invention.

FIG. 9 is an equivalent circuit of one pixel of an OLED display according to an exemplary embodiment of the present invention.

FIG. 10 is a cross-sectional view of one pixel of the OLED display of FIG. 9.

FIG. 11 is an equivalent circuit of one pixel of an OLED display according to an exemplary embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Exemplary embodiments of the present invention will be described more fully hereinafter with reference to the accompanying drawings. However, the described embodiments may be modified in various different ways and should not be construed as limited to the embodiments disclosed herein.

Like reference numerals may designate like elements throughout the specification.

In the drawings, the thickness of layers, films, panels, regions, etc., may be exaggerated for clarity. It will be understood that when an element such as a layer, film, region, or substrate is referred to as being "on" another element, it can be directly on the other element or intervening elements may also be present.

Now, an organic light emitting diode (OLED) display according to an exemplary embodiment of the present invention will be described with reference to accompanying drawings.

FIG. 1 is a layout view of a pixel of an OLED display according to an exemplary embodiment of the present invention.

As shown in FIG. 1, an OLED display according to an exemplary embodiment of the present invention includes a plurality of pixels. Each pixel includes a thin film transistor (not shown) and an organic light emitting element (not shown) connected to the thin film transistor.

The organic light emitting elements of each pixel include first, second, and third first electrodes 71, 73, and 75 as anodes, an organic emission layer, and a second electrode as a cathode. A pixel definition layer having openings 91, 93, and 95 exposing the first, second, and third first electrodes 71, 73, and 75 may be formed around the first electrodes, and the organic emission layer is formed in the openings 91, 93, and 95.

Each pixel may be one among red, green, and blue pixels, and the red pixel includes a red organic emission layer while

the green pixel includes a green organic emission layer. The blue pixel includes a blue organic emission layer, and the blue organic emission layer is formed on the entirety of a substrate such that it may also be formed in the red pixel and the green pixel.

If the openings formed in each of the blue, red, and green pixels are respectively referred to as first openings 91, second openings 93, and third openings 95, the second openings 93 and the third openings 95 are alternately disposed in a y-axis direction to form a second pixel column, and the first openings 91 are continuously disposed in the y-axis direction with a predetermined interval therebetween to form a first pixel column. The second pixel column formed by the second openings 93 and the third openings 95 and the first pixel column formed by the first openings 91 are alternately disposed in the x-axis direction.

Each of the second openings 93 and the third openings 95 may be formed with an approximate quadrangle plane shape while having the same or about the same area, and the first openings 91 may be formed with a greater area than the second openings 93 and the third openings 95. The second opening 93 and the third opening 95 are quadrangular with longer sides extending in the x-axis direction, and the first opening 91 is quadrangular with longer sides extending in the y-axis direction.

All boundary lines of the second opening 93 and the third opening 95 are respectively positioned within the boundary lines of the second and third first electrodes 73 and 75 at a predetermined distance from the boundary lines of the second and third first electrodes 73 and 75. The boundary lines of the second opening 93 and the third opening 95 are respectively positioned apart from the boundary lines of the second and third first electrodes 73 and 75 by a distance of at least 4 μm .

The boundary lines of the first opening 91 include two pairs of boundary lines respectively facing each other, and the longer boundary lines among them are positioned within longer boundary lines of the first first electrode 71 at a predetermined distance from the longer boundary lines of the first first electrode 71. The longer boundary lines of the first opening 91 are positioned apart from the longer boundary lines of the first first electrode 71 by a distance of at least 4 μm .

The shorter boundary lines among the boundary lines of the first opening 91 overlap the shorter boundary lines of the first first electrode 71. In addition, the shorter boundary lines of the first opening 91 may be positioned outside the shorter boundary lines of the first first electrode 71 such that the shorter boundary lines of the first first electrode 71 may be exposed by the first opening 91.

FIG. 2 is a pixel layout view of an OLED display according to an exemplary embodiment of the present invention.

Most of FIG. 2 is the same as that of FIG. 1 such that differences may only be described.

All boundary lines of the second opening 93 and the third opening 95 of FIG. 2 are positioned apart from boundary lines of the second and third first electrodes 73 and 75 by a predetermined distance, and all boundary lines of the second opening 93 and the third opening 95 are positioned within the boundary lines of the second and third first electrodes 73 and 75.

The first opening 91 exposes the first first electrode 71 positioned in the column of the first opening 91. A boundary line of the first first electrode 71 is exposed by the first opening 91.

In the exemplary embodiment of FIG. 2, the first opening 91 is formed across two first first electrodes 71; however, more first first electrodes 71 may be exposed by the first opening 91 (not shown). Further, all first first electrodes 71 positioned in the same column may be exposed through one first opening 91.

According to an exemplary embodiment of the present invention, when forming the openings (e.g., 91, 93 and/or 95), a misalignment margin of a mask used to form an organic emission layer is increased such that a defect due to the misalignment may be minimized.

Next, this will be described with reference to FIG. 3 to FIG. 8.

FIG. 3 to FIG. 8 are top plan views of intermediate steps of manufacturing an OLED display according to an exemplary embodiment of the present invention.

FIG. 3 to FIG. 8 are top plan views showing a first electrode of an organic light emitting element, an opening, and a fine film mask.

As shown in FIG. 3, a metal layer is formed on a substrate 100 and is patterned to respectively form the first, second, and third first electrodes 71, 73, and 75, respectively, at the first pixel, the second pixel, and the third pixel. The first pixel may be the blue pixel, the second pixel may be the red pixel, and the third pixel may be the green pixel.

A thin film transistor (not shown) connected to the first, second, and third first electrodes 71, 73, and 75 of each pixel is formed on the substrate 100.

The first, second, and third first electrodes 71, 73, and 75 of each pixel may have a protruding portion of various shapes depending on a connection to be made with the thin film transistor.

Next, as shown in FIG. 4, a pixel definition layer having the first opening 91, the second opening 93, and the third opening 95 exposing the first electrodes of each pixel is formed on the first, second, and third first electrodes 71, 73, and 75.

Next, as shown in FIG. 5, a mask M exposing the first opening 91 is disposed on the substrate 100 and an organic emission layer is deposited to form a blue organic emission layer at the first opening 91. For the second opening 93 and the third opening 95, the organic emission layer is deposited through the mask M by the same method described for the first opening 91 to form a red organic emission layer and a green organic emission layer, respectively.

However, when forming the organic emission layer by using the mask M, a misalignment may occur. First, an example of forming the blue organic emission layer will be described.

The mask M to form the blue organic emission layer includes a light blocking part (a gray color region, M1) covering the second pixel column and an exposure part M2 exposing the first pixel column.

After disposing the mask M on the substrate 100 while moving it in the x-axis and the y-axis directions, the mask M is aligned to correspond the second pixel column to the light blocking part M1 and the first pixel column to the exposure part M2. At this time, the first pixel column and the exposure part M2 are aligned at the proper position, however the mask M may be moved in the x-axis or the y-axis direction to be misaligned.

As shown in FIG. 6, if the mask M is moved in the +x-axis direction such that a misalign of a distance L1 occurs, the light blocking part M1 of the mask M may overlap the first opening 91 of the first pixel column by a distance L2 as well as the second opening 93 and the third opening 95 of the second pixel column.

When the first opening 91 is covered by the light blocking part M1, the area (a hatched region) of the exposed first opening 91 is reduced such that the area of the blue emission layer may be reduced.

Accordingly, in an exemplary embodiment of the present invention, the boundary line of the first opening 91 is positioned apart from the boundary line of the first first electrode 71 by a predetermined distance, for example, at least 4 μm , which is a greater distance than a range that the mask M may be moved when it is misaligned. In other words, if the mask M is moved like that shown in FIG. 6 and overlaps the first first electrode 71, the first opening 91 is positioned far enough away from the boundary line of the first first electrode 71 such that the light blocking part M1 of the mask M does not cover the first opening 91.

On the other hand, as shown in FIG. 7, when the mask M is moved in the y-axis direction by a distance L3, the exposure part M2 of the mask M still exposes a plurality of first openings 91 that are positioned in the first pixel column and the light blocking part M1 of the mask M does not overlap the first pixel column such that the first openings 91 are not covered by the light blocking part M1 even though the misalignment occurs in the y-axis direction.

In this way, although the misalignment takes place, the first openings 91 are not covered by the light blocking part M1 of the mask M such that the boundary lines of the first openings 91 are positioned at the same position as the boundary lines of the first first electrodes 71 like in FIG. 1, or the first openings 91 expose the boundary lines of the first first electrodes 71 as shown in FIG. 2, thereby increasing the area of the blue organic emission layer.

Since the method of forming the red organic emission layer and the green organic emission layer of the second pixel and the third pixel is substantially the same, only an example of forming the red organic emission layer of the second pixel is described.

The mask M to form the green organic emission layer of the third pixel has a light blocking part M1 blocking the first opening 91 and the second opening 93 and an exposure part M2 exposing the third opening 95 such that the mask M is moved and aligned in the x-axis and the y-axis directions for the exposure part M2 of the mask M to correspond to the third opening 95.

At this time, the exposure part M2 of the mask M is aligned at the proper position with the third opening 95, however movement of the mask M may result in it being misaligned.

As shown in FIG. 8, if the mask M is moved in the y-axis direction and a misalignment of a distance L4 occurs, the exposure part M2 of the mask M may expose a portion (a hatched region) of the second opening 93 as well as the third opening 95.

In this way, when the second opening 93 is not covered by the light blocking part M1 of the mask M and is overlapped by the exposure part M2 of the mask M, the green organic emission layer of the third pixel is also formed at the exposed second opening 93 in addition to the third opening 95 such that the colors may mix with the light emitting color of the organic emission layer formed at the second opening 93. For example, the color green may mix with the color red.

Accordingly, in an exemplary embodiment of the present invention, the boundary line of the second opening 93 is positioned apart from the boundary line of the second electrode 73 by a predetermined distance, for example, at least 4 μm , which is a greater distance than a range that the mask M may be moved when it is misaligned. In other words, if the mask M is moved like that shown in FIG. 8, the

second opening **93** is positioned far enough away from the boundary line of the second first electrode **73** such that the opening **93** is not exposed by the exposure part M2 of the mask M.

One pixel of the organic light emitting diode (OLED) display will be described in detail with reference to FIG. **9** and FIG. **10**.

FIG. **9** is an equivalent circuit of one pixel of an OLED display according to an exemplary embodiment of the present invention.

An OLED display according to the present exemplary embodiment includes a plurality of signal lines **121**, **171**, and **172**, and a pixel PX connected thereto.

The signal lines include a plurality of gate lines **121** for transmitting gate signals (or scanning signals), a plurality of data lines **171** for transmitting data signals, and a plurality of driving voltage lines **172** for transmitting a driving voltage ELVDD. The gate lines **121** extend substantially in a row direction and substantially parallel to each other, and the data lines **171** extend substantially in a column direction and substantially parallel to each other. The driving voltage lines **172** extend substantially in a column direction and substantially parallel to each other, however they may extend in the row direction or the column direction, and may form a mesh shape with the data lines **171** and the gate lines **121**.

One pixel PX includes a switching transistor T2, a driving transistor T1, a capacitor Cst, and an organic light emitting element LD.

The switching transistor T2 has a control terminal connected to one of the gate lines **121**, an input terminal connected to one of the data lines **171**, and an output terminal connected to the driving transistor T1. The switching transistor T2 transmits data signals applied to the data line **171** to the driving transistor T1 in response to a gate signal applied to the gate line **121**.

The driving transistor T1 has a control terminal connected to the switching transistor T2, an input terminal connected to the driving voltage line **172**, and an output terminal connected to the organic light emitting element LD. The driving transistor T1 drives an output current ILD having a magnitude depending on the voltage between its control terminal and output terminal.

The capacitor Cst is connected between the control terminal and the input terminal of the driving transistor T1. The capacitor Cst stores a data signal applied to the control terminal of the driving transistor T1 and maintains the data signal after the switching transistor T2 turns off.

The organic light emitting element LD, which may be an OLED, has an anode connected to the output terminal of the driving transistor T1 and a cathode connected to a common voltage ELVSS. The organic light emitting element LD emits light having an intensity depending on the output current ILD of the driving transistor T1, thereby displaying images. The organic light emitting element LD may include an organic material uniquely emitting at least one of three primary colors of red, green, and blue, and the OLED display displays desired images by a spatial sum thereof.

FIG. **10** is a cross-sectional view of one pixel of the OLED display of FIG. **9**.

FIG. **10** illustrates the pixel according to a layer lamination order focusing on the driving transistor T1 and the organic light emitting element LD of FIG. **9**. Hereafter, the driving transistor T1 is referred to as a thin film transistor.

As shown in FIG. **10**, the OLED display includes a substrate **110**, and a buffer layer **120** is formed on the substrate **110**.

The substrate **110** may be a transparent insulating substrate made of glass, quartz, ceramic, or plastic, or a metal substrate made of stainless steel.

The buffer layer **120** may be formed of a single SiNx layer or a double layer of SiNx and SiO₂. The buffer layer **120** prevents unnecessary components such as impurities or moisture from infiltrating into the substrate **110**, and planarizes the surface of the substrate **110**.

A semiconductor layer **135** is formed of polysilicon on the buffer layer **120**.

The semiconductor layer **135** may be formed of a polysilicon or an oxide semiconductor. The oxide semiconductor may include any one of oxides having titanium (Ti), hafnium (Hf), zirconium (Zr), aluminum (Al), tantalum (Ta), germanium (Ge), zinc (Zn), gallium (Ga), tin (Sn), or indium (In) as a base, and complex oxides thereof, such as zinc oxide (ZnO), indium-gallium-zinc oxide (InGaZnO₄), indium-zinc oxide (Zn—In—O), zinc-tin oxide (Zn—Sn—O), indium-gallium oxide (In—Ga—O), indium-tin oxide (In—Sn—O), indium-zirconium oxide (In—Zr—O), indium-zirconium-zinc oxide (In—Zr—Zn—O), indium-zirconium-tin oxide (In—Zr—Sn—O), indium-zirconium-gallium oxide (In—Zr—Ga—O), indium-aluminum oxide (In—Al—O), indium-zinc-aluminum oxide (In—Zn—Al—O), indium-tin-aluminum oxide (In—Sn—Al—O), indium-aluminum-gallium oxide (In—Al—Ga—O), indium-tantalum oxide (In—Ta—O), indium-tantalum-zinc oxide (In—Ta—Zn—O), indium-tantalum-tin oxide (In—Ta—Sn—O), indium-tantalum-gallium oxide (In—Ta—Ga—O), indium-germanium oxide (In—Ge—O), indium-germanium-zinc oxide (In—Ge—Zn—O), indium-germanium-tin oxide (In—Ge—Sn—O), indium-germanium-gallium oxide (In—Ge—Ga—O), titanium-indium-zinc oxide (Ti—In—Zn—O), and hafnium-indium-zinc oxide (Hf—In—Zn—O). In the case where the semiconductor layer **135** is formed of the oxide semiconductor, a separate protective layer may be added to protect the oxide semiconductor that is weak with regard to an external environment such as high temperatures.

The semiconductor layer **135** is divided into a channel region **1355**, and a source region **1356** and a drain region **1357** formed on respective sides of the channel region **1355**. The channel region **1355** of the semiconductor layer **135** is made of undoped polysilicon, in other words, an intrinsic semiconductor. The source region **1356** and the drain region **1357** are made of polysilicon doped with a conductive impurity, in other words, an impurity semiconductor. The impurity doped into the source region **1356** and the drain region **1357** may be a p-type impurity or an n-type impurity.

A gate insulating layer **140** is formed on the semiconductor layer **135**. The gate insulating layer **140** may be a single layer or a multi-layer including at least one of tetraethyl orthosilicate (TEOS), silicon nitride, and a silicon oxide.

A gate electrode **155** is formed on the semiconductor layer **135** and overlaps the channel region **1355**.

The gate electrode **155** may be formed of a single layer or multiple layers of a low resistance material or a highly corrosion-resistant material such as Al, Ti, Mo, Cu, Ni, and alloys thereof.

A first interlayer insulating layer **160** is formed on the gate electrode **155**. The first interlayer insulating layer **160** may be formed of a single layer or multiple layers including at least one of TEOS, silicon nitride, and a silicon oxide, like the gate insulating layer **140**.

The first interlayer insulating layer **160** and the gate insulating layer **140** have a source contact hole **66** and a drain contact hole **67** which respectively expose the source region **1356** and the drain region **1357**.

A source electrode **176** and a drain electrode **177** are formed on the first interlayer insulating layer **160**. The source electrode **176** is connected to the source region **1356** through the source contact hole **66**, and the drain electrode **177** is connected to the drain region **1357** through the drain contact hole **67**.

The source electrode **176** and the drain electrode **177** may be made of single or multiple layers of a low resistance material or a highly corrosion-resistant material such as Al, Ti, Mo, Cu, Ni, and alloys thereof. For example, the source electrode **176** and drain electrode **177** can be formed of three-level layers of Ti/Cu/Ti, Ti/Ag/Ti, or Mo/Al/Mo.

The gate electrode **155**, the source electrode **176**, and the drain electrode **177** respectively correspond to the control terminal, the input terminal, and the output terminal shown in FIG. 9, and form the thin film transistor along with the semiconductor layer **135**. A channel of the thin film transistor is formed in a portion of the semiconductor layer **135**, which is disposed between the source electrode **176** and the drain electrode **177**.

A second interlayer insulating layer **180** is formed on the source electrode **176** and the drain electrode **177**. The second interlayer insulating layer **180** includes a contact hole **85** exposing the drain electrode **177**.

The second interlayer insulating layer **180** may be formed of a single layer or multiple layers of at least one of TEOS, silicon nitride, and a silicon oxide, or may be formed of a low dielectric constant organic material, like the first interlayer insulating layer **160**.

A first electrode **710** is formed on the second interlayer insulating layer **180**. The first electrode **710** is electrically connected to the drain electrode **177** through the contact hole **85** and may be the anode of the organic light emitting element LD of FIG. 9.

While the second interlayer insulating layer **180** is formed between the first electrode **710** and the drain electrode **177** in the present exemplary embodiment, the first electrode **710** can be formed at the same level as the drain electrode **177** and may be integrated with the drain electrode **177**.

The first electrode **710** may be formed to have a protruding portion of various shapes to be connected to the drain electrode **177**, as shown by the protruding parts in FIG. 1 and FIG. 2.

A pixel definition layer **190** is formed on the first electrode **710**.

The pixel definition layer **190** has an opening **195** exposing the first electrode **710**. The pixel definition layer **190** may be formed of a resin such as a polyacrylate or a polyimide resin, or of an inorganic material such as silica.

The opening **195** may be formed with various shapes according to each pixel, and the boundary line of the opening **195** may be positioned apart from the boundary line of the first electrode **710** by at least 4 μm . When one column of the pixels forming the column emit light of the same color, as shown in FIG. 1 and FIG. 2, the boundary line of the opening **195** overlaps the boundary line of the first electrode **710** or the opening **195** may be formed to expose the boundary line of the first electrode **710**.

An organic emission layer **720** is formed in the opening **195** of the pixel definition layer **190**.

The organic emission layer **720** is formed of multiple layers including an emission layer and one or more of a hole injection layer (HIL), a hole transport layer (HTL), an electron transport layer (ETL), and an electron injection layer (EIL).

In the case where the organic emission layer **720** includes all of the aforementioned layers, the HIL may be disposed on

the first electrode **710** that is the anode, and the HTL, the emission layer, the ETL, and the EIL may be sequentially laminated thereon.

A second electrode **730** is formed on the pixel definition layer **190** and the organic emission layer **720**.

The second electrode **730** becomes a cathode of the organic light emitting element LD. Accordingly, the first electrode **710**, the organic emission layer **720**, and the second electrode **730** form the organic light emitting element LD.

The organic light emitting element LD can be of one of a front display type, a rear display type, and a dual-sided display type according to the direction in which the organic light emitting element LD emits light.

In the case of the front display type, the first electrode **710** is formed of a reflective layer and the second electrode **730** is formed of a transfective or transmissive layer. In the case of the rear display type, the first electrode **710** is formed of a transfective layer and the second electrode **730** is formed of a reflective layer. In the case of the dual-sided display type, the first electrode **710** and the second electrode **730** are formed of a transparent layer or a transfective layer.

The reflective layer and the semi-transparent layer are made of at least one of Mg, Ag, Au, Ca, Li, Cr, and Al, or an alloy thereof. The reflective layer and the transfective layer are determined by the thicknesses thereof, and the transfective layer may have a thickness of less than 200 nm. While the transmittance of the reflective layer or transfective layer increases as the thickness thereof decreases, the resistance thereof increases when the layer is excessively thin.

The transmissive layer is made of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), or indium oxide (In_2O_3).

An encapsulation member **260** is formed on the second electrode **730**.

The encapsulation member **260** may be formed in plural by alternately forming at least one organic layer and at least one inorganic layer.

The organic layer is formed of a polymer, and it may be a single layer or a deposition layer including one of polyethylene terephthalate, a polyimide, a polycarbonate, an epoxy, polyethylene, and a polyacrylate. Further, the organic layer can be formed with a polyacrylate, and in detail, it includes a polymerized monomer composition including a diacrylate monomer and triacrylate monomer. A monoacrylate monomer can be included in the monomer composition. A photoinitiator such as TPO can be further included in the monomer composition, but the monomer composition is not limited thereto.

The inorganic layer can be a single layer or a deposition layer including a metal oxide or a metal nitride. In detail, the inorganic layer can include one of SiN_x , Al_2O_3 , SiO_2 , and TiO_2 .

The externally exposed uppermost layer of the encapsulation layer **260** can be formed with an inorganic layer to prevent permeation of vapor into the organic light emitting element LD.

FIG. 11 is an equivalent circuit of one pixel of an OLED display according to an exemplary embodiment of the present invention.

As shown in FIG. 11, one pixel area of an OLED display according to an exemplary embodiment of the present invention includes a plurality of signal lines **121**, **122**, **123**, **124**, **171**, and **172**, a plurality of transistors **T1**, **T2**, **T3**, **T4**,

11

T5, and T6 connected to the plurality of signal lines, a storage capacitor Cst, and an organic light emitting element LD.

The transistors include a driving thin film transistor, a switching thin film transistor, a compensation transistor, an initialization transistor, an operation control transistor, and a light emission control transistor.

For better understanding and ease of description, the driving transistor is referred to as the first transistor T1, the switching transistor is referred to as the second transistor T2, the compensation transistor is referred to as the third transistor T3, the initialization transistor is referred to as the fourth transistor T4, the operation control transistor is referred to as the fifth transistor T5, and the light emission control transistor is referred to as the sixth transistor T6.

The signal lines include a gate line 121 for transferring a scan signal Sn, a prior gate line 122 for transferring a prior scan signal Sn-1 to the fourth transistor T4, a light emission control line 123 for transferring a light emission control signal En to the fifth transistor T5 and the sixth transistor T6, a data line 171 crossing the gate line 121 and transferring a data signal Dm, a driving voltage line 172 for transferring a driving voltage ELVDD and formed almost parallel to the data line 171, and an initialization voltage line 124 for transferring an initialization voltage Vint initializing the first transistor T1.

A first gate electrode G1 of the first transistor T1 is connected to an end Cst1 of the storage capacitor Cst, a first source electrode S1 of the first transistor T1 is connected via the fifth transistor T5 to the driving voltage line 172, and a first drain electrode D1 of the first transistor T1 is electrically connected via the sixth transistor T6 to an anode of the organic light emitting element LD. The first transistor T1 receives the data signal Dm according to a switching operation of the second transistor T2 to supply a driving current Id to the organic light emitting element LD. A second gate electrode G2 of the second transistor T2 is connected to the gate line 121, a second source electrode S2 of the second transistor T2 is connected to the data line 171, and a second drain electrode D2 of the second transistor T2 is connected to the first source electrode S1 of the first transistor T1 and to the driving voltage line 172 via the fifth transistor T5. The second transistor T2 is turned on according to the scan signal Sn transferred through the gate line 121 to perform a switching operation of transferring the data signal Dm transferred to the data line 171 to the first source electrode S1 of the first transistor T1.

A third gate electrode G3 of the third transistor T3 is connected to the gate line 121, and a third source electrode S3 of the third transistor T3 is connected to the first drain electrode D1 of the first transistor T1 and to the anode of the organic light emitting element LD via the sixth transistor T6. A third drain electrode D3 of the third transistor T3 is connected to one end Cst1 of the storage capacitor Cst, a fourth drain electrode D4 of the fourth transistor T4, and the first gate electrode G1 of the first transistor T1. The third transistor T3 is turned on according to the scan signal Sn transmitted through the gate line 121 to connect the gate electrode G1 and the drain electrode D1 of the first transistor T1 to each other, thus performing diode-connection of the first transistor T1.

A fourth gate electrode G4 of the fourth transistor T4 is connected to the prior gate line 122, a fourth source electrode S4 of the fourth transistor T4 is connected to the initialization voltage line 124, and the fourth drain electrode D4 of the fourth transistor T4 is connected to one end Cst1 of the storage capacitor Cst, the third drain electrode D3 of

12

the third transistor T3, and the first gate electrode G1 of the first transistor T1. The fourth transistor T4 is turned on according to the prior scan signal Sn-1 transferred through the prior scan line 122 to transfer the initialization voltage Vint to the gate electrode G1 of the first transistor T1, thus performing an initialization operation for initializing the voltage of the gate electrode G1 of the first transistor T1.

A fifth gate electrode G5 of the fifth transistor T5 is connected to the light emission control line 123, a fifth source electrode S5 of the fifth transistor T5 is connected to the driving voltage line 172, and a fifth drain electrode D5 of the fifth transistor T5 is connected to the first source electrode S1 of the first transistor T1 and the second drain electrode D2 of the second transistor T2.

A sixth gate electrode G6 of the sixth transistor T6 is connected to the light emission control line 123, a sixth source electrode S6 of the sixth transistor T6 is connected to the first drain electrode D1 of the first transistor T1 and the third source electrode S3 of the third transistor T3, and a sixth drain electrode D6 of the sixth transistor T6 is electrically connected to the anode of the organic light emitting element LD. The fifth transistor T5 and the sixth transistor T6 are simultaneously turned on according to the light emission control signal En transferred through the light emission control line 123 to transfer the driving voltage ELVDD to the organic light emitting element LD, thus allowing the driving current Id to flow in the organic light emitting element LD.

The other end Cst2 of the storage capacitor Cst is connected to the driving voltage line 172, and the cathode of the organic light emitting element LD is connected to the common voltage ELVSS. Accordingly, the organic light emitting element LD receives the driving current Id from the driving transistor T1 to emit light, thereby displaying an image.

In this pixel circuit, the first transistor T1 charges a voltage corresponding to the data signal Dm to the storage capacitor Cst according to the scan signal Sn, and a current corresponding to the voltage charged to the storage capacitor Cst is provided to the organic light emitting element LD. In this case, since a threshold voltage of the first transistor T1 may vary as time passes, the third transistor T3 diode-connects the first transistor T1 in response to the scan signal Sn so that the threshold voltage Vth is compensated.

Now, the operation of one pixel circuit of the OLED display according to an exemplary embodiment of the present invention, as shown in FIG. 11, will be described in detail.

First, the prior scan signal Sn-1 of a low level is supplied through the prior gate line 122 during an initialization period. Then, the fourth transistor T4 is turned on corresponding to the prior scan signal Sn-1 of the low level, and the initialization voltage Vint is provided from the initialization voltage line 124 through the fourth transistor T4 to the first gate electrode G1 of the first transistor T1 to initialize the first transistor T1 with the initialization voltage Vint.

Subsequently, the scan signal Sn of the low level is supplied through the gate line 121 during a data programming period. The second transistor T2 and the third transistor T3 are turned on corresponding to the scan signal Sn of the low level.

In this case, the first transistor T1 is diode-connected by the turned-on third transistor T3, and is biased in a forward direction.

A compensation voltage Dm+Vth (Vth is a negative value) obtained by subtracting a threshold voltage Vth of the

13

first transistor T1 from the data signal Dm supplied from the data line 171 is then applied to the first gate electrode G1 of the first transistor T1.

The driving voltage ELVDD and the compensation voltage $Dm+V_{th}$ are applied to both ends Cst1 and Cst2 of the storage capacitor Cst, and a charge corresponding to a difference between voltages at both ends Cst1 and Cst2 is stored in the storage capacitor Cst. Thereafter, the level of the light emission control signal En supplied from the light emission control line 123 during the light emission period is changed from the high level to the low level. The fifth transistor T5 and the sixth transistor T6 are then turned on by the light emission control signal En of the low level during the light emission period.

Subsequently, the driving current Id is generated according to a difference between the voltage of the first gate electrode G1 of the first transistor T1 and the driving voltage ELVDD, and the driving current Id is supplied through the sixth transistor T6 to the organic light emitting element LD. A gate-source voltage Vgs of the first transistor T1 is maintained at $(Dm+V_{th})-ELVDD$ by the storage capacitor Cst during the light emission period, and the driving current Id is proportional to a square of a value obtained by subtracting the threshold voltage from a source-gate voltage, in other words, $(Dm-ELVDD)^2$, according to a current-voltage relationship of the first transistor T1. Accordingly, the driving current Id is determined regardless of the threshold voltage Vth of the first transistor T1.

According to an exemplary embodiment of the present invention, if a misalignment of openings of a mask and electrodes occurs, the area of an emission layer is not reduced and color mixing is prevented, thereby providing an OLED display of high quality and long life.

While the present invention has been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention as defined by the following claims.

What is claimed is:

1. An organic light emitting diode (OLED) display, comprising:

a substrate;

a plurality of thin film transistors formed on the substrate;

a plurality of first electrodes respectively connected to the thin film transistors;

a pixel definition layer formed on the substrate and having a first opening, a second opening, and a third opening respectively exposing first, second, and third first electrodes of the plurality of first electrodes;

an emission layer formed at the first opening, the second opening, and the third opening; and

a second electrode formed on the emission layer, wherein the first opening has a first pair of boundary lines facing each other and a second pair of boundary lines facing each other,

the first pair of boundary lines are coincident with boundary lines of a pair of boundary lines of the first first electrode, and the second pair of boundary lines are positioned within another pair of boundary lines of the first first electrode, and

the first pair of boundary lines are connected with the second pair of boundary lines.

2. The OLED display of claim 1, wherein the second pair of boundary lines of the first opening is positioned apart from another pair of boundary lines of the first first electrode by at least 4 μm .

14

3. The OLED display of claim 1, wherein boundary lines of the second and third openings are respectively positioned within boundary lines of the second and third first electrodes.

4. The OLED display of claim 3, wherein the boundary lines of the second and third openings are positioned apart from the boundary lines of the second and third first electrodes by at least 4 μm .

5. The OLED display of claim 1, wherein:

the emission layer includes a first emission layer, a second emission layer, and a third emission layer respectively positioned on the first, second, and third first electrodes; and

the first emission layer, the second emission layer, and the third emission layer are respectively positioned in the first, second, and third openings.

6. The OLED display of claim 5, wherein the first emission layer, the second emission layer, and the third emission layer emit light of different colors.

7. The OLED display of claim 6, wherein the first emission layer, the second emission layer, and the third emission layer are respectively a blue emission layer, a red emission layer, and a green emission layer.

8. The OLED display of claim 5, wherein a plurality of the first, second and third emission layers form columns and rows, and

the columns include a first column formed of the first emission layers and a second column formed of the second emission layers and the third emission layers.

9. The OLED display of claim 8, wherein the first column and the second column are alternately repeated.

10. The OLED display of claim 9, wherein the second emission layer and the third emission layer are alternately positioned in the second column.

11. An organic light emitting diode (OLED) display, comprising:

a substrate;

a plurality of thin film transistors formed on the substrate;

a plurality of first electrodes respectively connected to the thin film transistors;

a pixel definition layer formed on the substrate and having a first opening, a second opening, and a third opening respectively exposing first, second, and third first electrodes of the plurality of first electrodes;

an emission layer formed in the first opening, the second opening, and the third opening; and

a second electrode formed on the emission layer,

wherein the first opening has a connected boundary line which has a portion coincident with a boundary line of the first first electrode and a portion positioned within the boundary line of the first first electrode, and the second and third openings respectively have a boundary entirely positioned within the boundary of the second and third first electrodes.

12. The OLED display of claim 11, wherein:

the emission layer includes a first emission layer, a second emission layer, and a third emission layer for emitting different colors, and

the first emission layer, the second emission layer, and the third emission layer are respectively positioned in the first, second, and third openings.

13. The OLED display of claim 12, wherein the first emission layer, the second emission layer, and the third emission layer are respectively a blue emission layer, a red emission layer, and a green emission layer.

15

14. The OLED display of claim 12, wherein a plurality of the first, second and third emission layers form columns and rows, and

the columns include a first column formed of the first emission layers, and a second column formed of the second emission layers and the third emission layers. 5

15. The OLED display of claim 14, wherein the first column and the second column are alternately repeated.

16. The OLED display of claim 15, wherein the second emission layer and the third emission layer are alternately positioned in the second column. 10

17. An organic light emitting diode (OLED) display, comprising:

a substrate;

a pixel electrode and formed on the substrate; and 15

a pixel definition layer having an opening exposing the pixel electrode,

wherein the opening has a connected boundary line,

a portion of the connected boundary line is coincident with a boundary line of the pixel electrode, and 20

another portion of the connected boundary line is positioned within the boundary line of the pixel electrode.

* * * * *

16

专利名称(译)	有机发光二极管显示器		
公开(公告)号	US9548341	公开(公告)日	2017-01-17
申请号	US14/257359	申请日	2014-04-21
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SO DONG YOON KIM JI EUN KIM HAN SOO CHUNG YOUNG JUN		
发明人	SO, DONG-YOON KIM, JI-EUN KIM, HAN-SOO CHUNG, YOUNG-JUN		
IPC分类号	H01L27/32 H01L51/52		
CPC分类号	H01L27/3246 H01L27/3276 H01L27/326 H01L27/3216 H01L27/3218 H01L51/5203 H01L2227/323 H01L27/3248 H05B33/26		
审查员(译)	VU , DAVID		
优先权	1020130096837 2013-08-14 KR		
其他公开文献	US20150048322A1		
外部链接	Espacenet USPTO		

摘要(译)

OLED显示器，包括：基板；形成在所述基板上的多个薄膜晶体管；分别连接到所述薄膜晶体管的多个第一电极；像素限定层，形成在所述基板上，并且具有分别暴露所述多个第一电极中的第一，第二和第三电极的第一开口，第二开口和第三开口；发射层，形成在所述第一开口，所述第二开口和所述第三开口处；以及形成在所述发射层上的第二电极，其中所述第一开口具有彼此面对的第一对边界线和彼此面对的第二对边界线，并且所述第一对边界线与一对边界或者位于所述第一第一电极的所述一对边界线的边界线的外侧。

