



US010686019B2

(12) **United States Patent**  
**Lee et al.**

(10) **Patent No.:** **US 10,686,019 B2**  
(45) **Date of Patent:** **Jun. 16, 2020**

(54) **COLOR CONTROL ENCAPSULATION LAYER AND DISPLAY APPARATUS INCLUDING THE SAME**

(71) Applicant: **Samsung Electronics Co., Ltd.**,  
Suwon-si, Gyeonggi-do (KR)  
(72) Inventors: **Sunghun Lee**, Hwaseong-si (KR);  
**Byoungki Choi**, Hwaseong-si (KR);  
**Seungyeon Kwak**, Suwon-si (KR);  
**Jiwhan Kim**, Seoul (KR)

(73) Assignee: **SAMSUNG ELECTRONICS CO., LTD.**, Gyeonggi-Do (KR)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/152,905**

(22) Filed: **Oct. 5, 2018**

(65) **Prior Publication Data**  
US 2019/0157354 A1 May 23, 2019

(30) **Foreign Application Priority Data**  
Nov. 21, 2017 (KR) ..... 10-2017-0155807

(51) **Int. Cl.**  
**H01L 27/32** (2006.01)  
**H01L 51/52** (2006.01)  
**H01L 33/50** (2010.01)

(52) **U.S. Cl.**  
CPC ..... **H01L 27/322** (2013.01); **H01L 27/3211** (2013.01); **H01L 27/3213** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... H01L 33/50; H01L 33/502; H01L 33/504; H01L 51/5256; H01L 2251/5369;  
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,146,355 A \* 9/1992 Prince ..... G02F 1/133617 349/106  
6,125,226 A \* 9/2000 Forrest ..... H01L 51/5271 313/504

(Continued)

FOREIGN PATENT DOCUMENTS

CN 105609656 A 5/2016  
KR 1020160046202 A 4/2016

OTHER PUBLICATIONS

Jones et al., "Barrier Films for Quantum Dot Encapsulation", Sep. 11, 2017, 1-10 [[http://www.aimcal.org/uploads/4/6/6/9/46695933/jones\\_abstract\\_barrier\\_films.pdf](http://www.aimcal.org/uploads/4/6/6/9/46695933/jones_abstract_barrier_films.pdf)].

(Continued)


*Primary Examiner* — Victoria K. Hall

(74) *Attorney, Agent, or Firm* — Cantor Colburn LLP

(57) **ABSTRACT**

A display apparatus includes an organic light-emitting device ("OLED") substrate which generates and emits a first light, and an encapsulation layer to which the emitted first light from the OLED substrate is incident and from which a second light is emitted. The encapsulation layer includes an inorganic material layer and an organic material layer alternately stacked with each other. The organic material layer includes a plurality of color control elements which color-convert the emitted first light incident to the encapsulation layer. The plurality of color control elements may include a first and second color control element including a first and second quantum dot with which a color of the emitted first light incident to the encapsulation layer is converted to a first and second color, respectively.

**20 Claims, 9 Drawing Sheets**



- (52) **U.S. Cl.**  
 CPC ..... *H01L 33/501* (2013.01); *H01L 27/3244* (2013.01); *H01L 51/5256* (2013.01); *H01L 51/5268* (2013.01); *H01L 2251/5369* (2013.01); *H01L 2251/558* (2013.01)
- (58) **Field of Classification Search**  
 CPC ..... H01L 27/14621; H01L 27/322; H01L 27/3211; H01L 27/3213  
 See application file for complete search history.
- (56) **References Cited**
- U.S. PATENT DOCUMENTS
- |                   |         |             |       |               |         |
|-------------------|---------|-------------|-------|---------------|---------|
| 7,342,620 B2 *    | 3/2008  | Huh         | ..... | G02B 5/201    | 349/106 |
| 9,064,822 B2      | 6/2015  | Park et al. |       |               |         |
| 9,239,458 B2 *    | 1/2016  | Yoon        | ..... | G02B 26/02    |         |
| 9,469,080 B2 *    | 10/2016 | Hajjar      | ..... | G02B 5/201    |         |
| 10,192,932 B2 *   | 1/2019  | Steckel     | ..... | H01L 51/502   |         |
| 10,228,586 B2 *   | 3/2019  | Chae        | ..... | H01L 27/322   |         |
| 10,304,813 B2 *   | 5/2019  | Kuo         | ..... | H01L 25/167   |         |
| 10,326,057 B2 *   | 6/2019  | Kim         | ..... | H01L 33/486   |         |
| 10,333,036 B2 *   | 6/2019  | Ulmer       | ..... | H01L 33/502   |         |
| 10,361,259 B2 *   | 7/2019  | Choi        | ..... | G09G 3/3233   |         |
| 10,396,132 B2 *   | 8/2019  | Kim         | ..... | H01L 51/502   |         |
| 10,490,709 B2 *   | 11/2019 | Ko          | ..... | H01L 33/52    |         |
| 2006/0197437 A1 * | 9/2006  | Krummacher  | ..... | B82Y 10/00    | 313/501 |
| 2007/0077349 A1 * | 4/2007  | Newman      | ..... | H01L 51/5212  | 427/66  |
| 2007/0182319 A1 * | 8/2007  | Wei         | ..... | H01L 51/5262  | 313/506 |
| 2008/0169758 A1 * | 7/2008  | Cok         | ..... | H01L 51/5262  | 313/506 |
| 2009/0244448 A1 * | 10/2009 | Chang       | ..... | G02F 1/133514 | 349/106 |
| 2010/0156280 A1 * | 6/2010  | Song        | ..... | H01L 51/5265  | 313/504 |
| 2012/0119239 A1 * | 5/2012  | Kim         | ..... | H01L 25/048   | 257/89  |
| 2013/0120981 A1 * | 5/2013  | Kim         | ..... | F21V 9/08     | 362/231 |
| 2013/0335799 A1 * | 12/2013 | Yoon        | ..... | G02B 26/02    | 359/227 |
| 2014/0009723 A1 * | 1/2014  | Cho         | ..... | H01J 9/205    | 349/65  |
| 2014/0145158 A1 * | 5/2014  | Choi        | ..... | H01L 27/3246  | 257/40  |
| 2014/0183470 A1 * | 7/2014  | Kim         | ..... | H01L 27/3276  | 257/40  |
| 2014/0183471 A1 * | 7/2014  | Heo         | ..... | H01L 27/322   | 257/40  |
| 2014/0191204 A1 * | 7/2014  | Jeong       | ..... | H01L 27/322   | 257/40  |
| 2014/0287543 A1 * | 9/2014  | Son         | ..... | B32B 37/12    | 438/28  |
| 2014/0346473 A1 * | 11/2014 | Park        | ..... | H01L 51/5256  | 257/40  |
| 2015/0085223 A1 * | 3/2015  | Park        | ..... | G02F 1/133603 | 349/65  |
| 2015/0090971 A1 * | 4/2015  | Kim         | ..... | H01L 51/5281  | 257/40  |
| 2015/0228697 A1   | 8/2015  | Liu et al.  |       |               |         |
| 2015/0280169 A1 * | 10/2015 | Choi        | ..... | H01L 51/5237  | 257/72  |
| 2015/0293280 A1 * | 10/2015 | Lee         | ..... | G02B 5/201    | 359/891 |
| 2015/0318506 A1   | 11/2015 | Zhou et al. |       |               |         |
| 2015/0340652 A1 * | 11/2015 | Oh          | ..... | H01L 51/5256  | 257/40  |
| 2016/0005797 A1 * | 1/2016  | Huang       | ..... | H01L 27/3209  | 257/40  |
| 2016/0072098 A1 * | 3/2016  | Lee         | ..... | C09K 11/06    | 257/40  |
| 2016/0091757 A1 * | 3/2016  | Miki        | ..... | G02F 1/133514 | 349/42  |
| 2017/0133357 A1 * | 5/2017  | Kuo         | ..... | H01L 25/167   |         |
| 2017/0162756 A1 * | 6/2017  | Hartlove    | ..... | B01J 13/08    |         |
| 2017/0170241 A1 * | 6/2017  | Huang       | ..... | H01L 27/322   |         |
| 2017/0179438 A1 * | 6/2017  | Xu          | ..... | H01L 27/3213  |         |
| 2018/0019371 A1 * | 1/2018  | Steckel     | ..... | C09K 11/75    |         |
| 2018/0052366 A1   | 2/2018  | Hao et al.  |       |               |         |
| 2018/0122836 A1 * | 5/2018  | Kang        | ..... | H01L 33/08    |         |
| 2018/0156951 A1 * | 6/2018  | Baek        | ..... | G02F 1/133617 |         |
| 2018/0190747 A1 * | 7/2018  | Son         | ..... | G06F 3/1446   |         |
| 2018/0233537 A1 * | 8/2018  | Liu         | ..... | H01L 27/156   |         |
| 2019/0121176 A1 * | 4/2019  | Lee         | ..... | G02F 1/1336   |         |
| 2019/0148458 A1 * | 5/2019  | Kim         | ..... | H01L 51/502   | 257/89  |
| 2019/0237618 A1 * | 8/2019  | Zou         | ..... | H01L 25/0753  |         |
| 2019/0252579 A1 * | 8/2019  | Choi        | ..... | H01L 25/0753  |         |
| 2019/0295996 A1 * | 9/2019  | Park        | ..... | H01L 27/15    |         |
| 2019/0378873 A1 * | 12/2019 | Lee         | ..... | H01L 25/0655  |         |
- OTHER PUBLICATIONS
- Wang et al., "Enhanced moisture barrier performance for ALD-encapsulated OLEDs by introducing an organic protective layer", *Journal of Materials Chemistry C*, vol. 5, 2017, 4107-4024 (<http://pubs.rsc.org/en/content/articlelanding/2017/tc/c7tc00903h#divAbstract>).
- Coe-Sullivan et al., "Tuning the performance of hybrid organic/inorganic quantum dot light-emitting devices", *Org. Electron.*, vol. 4, Issue 2-3 pp. 123-130 (<https://onelab.mit.edu/tuning-performance-hybrid-organic-inorganic-quantum-dot-light-emitting-devices>).
- \* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14

Absorption type CF




FIG. 15

Cut-off filter type




FIG. 16





FIG. 17



**COLOR CONTROL ENCAPSULATION  
LAYER AND DISPLAY APPARATUS  
INCLUDING THE SAME**

CROSS-REFERENCE TO RELATED  
APPLICATION

This application claims priority to Korean Patent Application No. 10-2017-0155807, filed on Nov. 21, 2017, and all the benefits accruing therefrom under 35 U.S.C. § 119, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

Embodiments set forth herein relate to display apparatuses.

2. Description of the Related Art

Organic light-emitting devices (“OLED”) are self-light-emitting type devices having a wide viewing angle, excellent contrast, high response speed, superior characteristics in terms of a driving voltage, luminance, etc. and being capable of generating multiple colors.

An OLED may include an anode, a cathode, and an emission layer (an organic material-including emission layer) interposed between the anode and the cathode. A hole transport region may be located between the anode and the emission layer. An electron transport region may be located between the emission layer and the cathode. Holes injected from the anode may move to the emission layer via the hole transport region. Electrons injected from the cathode may move to the emission layer via the electron transport region. Carriers such as holes and electrons may recombine in the emission layer to produce excitons. Light may be generated as the excitons change from an excited state to a ground state.

Hybrid technologies of applying quantum-dot materials to organic light-emitting device (“OLED”) type displays have drawn attention. Quantum dots are nanometer sized semiconductor crystals. An energy gap of quantum dots may be controlled according to a size and shape of the quantum dots. When a semiconductor material is reduced to a size of nanometers like the quantum dot, unique optical characteristics may be generated due to a quantum mechanics phenomenon. Particularly, the quantum dots have high luminous efficiency and a narrow full width at half maximum (“FWHM”) in a visible-light region, and thus are expected to be a next-generation display material.

SUMMARY

Provided are display apparatuses which have excellent encapsulation properties with regard to an external environment and which may be relatively easily manufactured.

Provided are display apparatuses capable of suppressing color blurring or color mixing.

Provided are display apparatuses in which color conversion elements are applied in an encapsulation layer structure.

Provided are methods of manufacturing the display apparatuses.

Additional features will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

According to an embodiment, a display apparatus includes an organic light-emitting device (“OLED”) substrate which generates and emits a first light, and an encapsulation layer to which the emitted first light from the organic light-emitting device substrate is incident and from which a second light is emitted, the encapsulation layer including an inorganic material layer and an organic material layer alternately stacked with each other. The organic material layer of the encapsulation layer includes a plurality of color control elements which color-convert the emitted first light incident to the encapsulation layer. The plurality of color control elements include a first color control element including a first quantum dot with which a color of the emitted first light incident to the encapsulation layer is converted to a first color, and a second color control element including a second quantum dot with which the color of the emitted first light incident to the encapsulation layer is converted to a second color.

The encapsulation layer may further include a first inorganic material layer, a second inorganic material layer and the organic material layer including the plurality of color control elements between the first and second inorganic material layers.

The first quantum dot of the first color control element may convert the color of the emitted first light incident to the encapsulation layer into red, and the second quantum dot of the second color control element may convert the color of the emitted first light incident to the encapsulation layer into green.

The organic material layer may further include a light-scattering element adjacent along the organic light-emitting device substrate to the plurality of color control elements. The light-scattering element may maintain the color of the emitted first light incident to the encapsulation layer.

The plurality of color control elements may further include a third color control element adjacent along the organic light-emitting device substrate to the first and second color control elements, the third color control element, the third color control element including a third quantum dot with which the color of the emitted first light incident to the encapsulation layer is converted to a third color.

The display apparatus may further include a color filter layer to which the emitted second light from the encapsulation layer is incident.

The display apparatus may further include a plurality of sub-pixel regions at which color light is emitted to display an image. The color filter layer may include respectively corresponding to the plurality of sub-pixel regions: a first color filter which corresponds to the first color control element of the encapsulation layer, a second color filter which corresponds to the second color control element of the encapsulation layer, and a third color filter.

Within the color filter layer to which the emitted second light from the encapsulation layer is incident, the first color filter may be a first cut-off filter which selectively transmits light in a red light wavelength region. The second color filter may be a second cut-off filter which selectively transmits light in a green light wavelength region. The third color filter may be a third cut-off filter which selectively transmits light in a blue light wavelength region.

Within the color filter layer to which the emitted second light from the encapsulation layer is incident, the first color filter may be an absorption type red color filter. The second color filter may be an absorption-type green color filter. The third color filter may be an absorption-type blue color filter.

The OLED substrate may include a first electrode, a second electrode, and an organic emission layer between the

first and second electrodes. The first and second electrodes may be electrically separated from the inorganic material layer of the encapsulation layer.

The organic material layer of the encapsulation layer may include a photocurable organic material and a light-scattering agent.

The organic material layer of the encapsulation layer may have a thickness of about 10 nanometers (nm) to about 10000 nm.

The inorganic material layer of the encapsulation layer may include any one of a metal nitride, a metal oxide, a metal oxynitride, a metal carbide and a combination thereof.

The inorganic material layer of the encapsulation layer may be an insulating layer or a semiconductor layer.

The inorganic material layer of the encapsulation layer may have a thickness of about 10 nm to about 5000 nm.

Within the encapsulation layer, the first and second inorganic material layers may each extend along the organic material layer to dispose ends of the first and second inorganic material layers spaced apart from outer sides of the organic material layer, the first and second inorganic material layers being bonded to each other at the ends thereof.

The OLED substrate may be a blue OLED substrate which emits blue first light, a white OLED substrate which emits white first light, or a cyan OLED substrate which emits cyan first light.

The display apparatus may further include a thin-film transistor (“TFT”) array substrate connected to the OLED substrate to drive the substrate. The TFT array substrate may include a plurality of TFTs connected to pixel regions of the OLED substrate to drive the pixel regions of the substrate.

#### BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other features will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings in which:

FIG. 1 is a cross-sectional view of a display apparatus according to an embodiment;

FIG. 2 is a cross-sectional view of a display apparatus according to another embodiment;

FIG. 3 is a cross-sectional view of a display apparatus according to another embodiment;

FIG. 4 is a cross-sectional view of a display apparatus according to another embodiment;

FIG. 5 is a cross-sectional view of a display apparatus according to another embodiment;

FIG. 6 is a cross-sectional view of a display apparatus according to another embodiment;

FIG. 7 is a detailed cross-sectional view of a structure of a display apparatus, according to an embodiment;

FIG. 8 is a cross-sectional view of a structure of an encapsulation layer applicable to a display apparatus, according to another embodiment;

FIG. 9 is a cross-sectional view of a display apparatus according to another embodiment;

FIG. 10 is a cross-sectional view of a display apparatus according to another embodiment;

FIG. 11 is a graph showing an electroluminescence (“EL”) spectrum of a blue organic light-emitting display device (“OLED”) substrate applicable to a display apparatus according to an embodiment;

FIG. 12 is a graph showing photoluminescence (“PL”) quantum yield (%) according to wavelengths of a color conversion element including a red quantum dot (“QD”) and

a color conversion element including a green QD, applicable to a display apparatus according to an embodiment;

FIG. 13 is a graph showing a variation in transmittance (%) versus wavelengths of a color conversion element including a red QD and a color conversion element including a green QD, applicable to a display apparatus according to an embodiment;

FIG. 14 is a graph showing a variation in transmittance (%) versus wavelength of an absorption-type color filter applicable to a display apparatus according to an embodiment;

FIG. 15 is a graph showing a variation in transmittance (%) versus wavelength of a cut-off-type color filter applicable to a display apparatus according to an embodiment;

FIG. 16 is a graph showing a spectral radiance difference between when a light-scattering agent is applied to blue light and when the light-scattering agent is not applied to blue light; and

FIG. 17 is a graph showing an emission spectrum according to a wavelength of a display apparatus according to an embodiment.

#### DETAILED DESCRIPTION

Various example embodiments will now be described more fully with reference to the accompanying drawings in which example embodiments are shown.

It will be understood that when an element is referred to as being related to another element such as being “connected” or “coupled” to another element, it can be directly connected or coupled to the other element or intervening elements may be present. In contrast, when an element is referred to as being related to another element such as being “directly connected” or “directly coupled” to another element, there are no intervening elements present.

As used herein the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. “At least one” is not to be construed as limiting “a” or “an.” “Or” means “and/or.”

It will be understood that, although the terms “first,” “second,” etc. may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section discussed below could be termed a second element, component, region, layer or section without departing from the teachings of example embodiments.

Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. The device may be otherwise oriented (rotated 90

degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of example embodiments. As used herein, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprise” and/or “comprising,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

Example embodiments are described herein with reference to cross-sectional illustrations that are schematic illustrations of idealized embodiments (and intermediate structures) of example embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, example embodiments should not be construed as limited to the particular shapes of regions illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, an implanted region illustrated as a rectangle will, typically, have rounded or curved features and/or a gradient of implant concentration at its edges rather than a binary change from implanted to non-implanted region. Likewise, a buried region formed by implantation may result in some implantation in the region between the buried region and the surface through which the implantation takes place. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the actual shape of a region of a device and are not intended to limit the scope of example embodiments.

“About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within  $\pm 30\%$ ,  $20\%$ ,  $10\%$  or  $5\%$  of the stated value.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which example embodiments belong. It will be further understood that terms, such as those defined in commonly-used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

Hereinafter, display apparatuses according to embodiments will be described in detail with reference to the accompanying drawings. In the drawings, a width and thickness of each layer or region may be exaggerated for clarity and convenience of explanation. Throughout the detailed description, same reference numerals represent same elements.

FIG. 1 is a cross-sectional view of a display apparatus according to an embodiment.

Referring to FIG. 1, an organic light-emitting device (“OLED”) substrate **100A** may be provided. A multi-layer encapsulation layer **200A** may be located on the OLED substrate **100A**.

The display apparatus and elements thereof may be disposed along first and second directions which cross each other. In FIG. 1, for example, the horizontal direction may represent the first and/or the second direction. A thickness of the display apparatus and element thereof is taken along a third direction which crosses each of the first and second directions. In FIG. 1, for example, the vertical direction represents the thickness (e.g., third) direction. A top or front of the display apparatus may be defined at a side thereof at which light is emitted.

The OLED substrate **100A** may be a light-source OLED. The OLED substrate **100A** may include a first electrode, a second electrode, and an organic emission layer between the first and second electrodes. The first electrode may be an anode and the second electrode may be a cathode, or vice versa. The OLED substrate **100A** may further include an electron transport layer and a hole transport layer, and may additionally include a hole injection layer and an electron injection layer.

The OLED substrate **100A** may be, for example, a blue-OLED substrate emitting blue light, a white-OLED substrate emitting white light, or a cyan-OLED substrate emitting cyan light. However, colors of light emitted from the OLED substrate **100A** are not limited thereto and are variable. In the following description with reference to FIG. 1, the OLED substrate **100A** is a blue-OLED substrate but is merely an example. In an embodiment of manufacturing the OLED substrate **100A**, the OLED substrate **100A** may be formed using an open mask process such that the OLED substrate **100A** has the same structure (a uniform structure) at all locations when viewed from a top view (e.g., along the thickness direction from the top or front), but the open mask process may not be used according to circumstances.

The encapsulation layer **200A** may have a structure in which an inorganic material layer and an organic material layer are alternately stacked with each other at least once. At least one organic material layer of the encapsulation layer **200A** may include color control elements including quantum dots (“QDs”). When one inorganic material layer and one organic material layer together form one encapsulation unit, ‘n’ number of encapsulation units may be provided. Here, ‘n’ may be greater than or equal to 1.

Referring to FIG. 1, for example, the encapsulation layer **200A** may have a structure in which a first inorganic material layer **210**, an organic material layer **220** and a second inorganic material layer **230** are sequentially stacked along the thickness direction of the display apparatus.

The organic material layer **220** may include a plurality of color control elements **20a** and **20b** to control a color of light generated by the OLED substrate **100A**. The color control elements **20a** and **20b** may include a first color control element **20a** including a first QD to realize a first color, and a second color control element **20b** including a second QD to realize a second color. The second color may be different from the first color.

The organic material layer **220** may further include a light-scattering element **21c** located at a side (lateral side) of the color control elements **20a** and **20b**, such as along the first and/or second direction. The light-scattering element **21c** may be a region that does not include a QD, e.g., a non-QD-including region. That is, the light-scattering element **21c** maintains the color of the light emitted from the OLED substrate **100A** and incident to the encapsulation layer **200A**. The organic material layer **220** including the color control elements **20a** and **20b** to which QDs are applied may be sandwiched between the two inorganic material layers **210** and **230**. Thus, a lowermost layer and an

uppermost layer of the encapsulation layer **200A** may be respectively the inorganic material layers **210** and **230**. The light-scattering element **21c** may be provided in plurality within the display apparatus. The color control elements **20a** and **20b** and the light-scattering element **21c** within a same organic material layer **220** are disposed at substantially a same distance as each other from the OLED substrate **100A** along the thickness direction of the display apparatus.

The encapsulation layer **200A** may encapsulate the color control elements **20a** and **20b** therein while encapsulating the OLED substrate **100A** thereunder. Furthermore, the encapsulation layer **200A** may have a color control function since the color control elements **20a** and **20b** are included therein.

The first color control element **20a** may be a red-QD-including layer and may convert a color of light generated by the OLED substrate **100A** into light having a red (R) color. The second color control element **20b** may be a green-QD-including layer and may convert a color of light generated by the OLED substrate **100A** into light having a green (G) color. Thus, the first color control element **20a** may be referred to as a first color converter (or color conversion element), and the second color control element **20b** may be referred to as a second color conversion element. In an embodiment of manufacturing the encapsulation layer **200A**, the color conversion elements may be formed by combining a photocurable organic material, certain QDs and a light-scattering agent. The photocurable organic material may include, for example, a resin material such as a photoresist ("PR") material.

The light-scattering element **21c** may scatter light without changing the color of light generated by the OLED substrate **100A**. Since each of the first and second color control elements **20a** and **20b** may include a light-scattering agent, the light-scattering element **21c** may be provided at a side of the first and second color control elements **20a** and **20b** to achieve color balance. The light-scattering element **21c** may include a photocurable organic material and a light-scattering agent. Here, the photocurable organic material may include a photoresist ("PR") material, and the light-scattering agent may include, for example, titanium oxide (TiO<sub>2</sub>) or the like but embodiments are not limited thereto.

The first QD included in the first color control element **20a** may be a red QD. The second QD included in the second color control element **20b** may be a green QD. Each of the QDs may be a semiconductor particle having a nanometer (nm) sized spherical shape or a shape similar thereto and having a size (e.g., diameter) of about several to several tens of nanometers.

The QD may have a monolithic structure or a core-shell structure. When the QD has the core-shell structure, the QD may have a single-shell structure of a multi-shell structure. In an embodiment, for example, the QD may consist of a core portion (e.g., center portion) including or formed of a first semiconductor and a skin portion (e.g., shell portion) including or formed of a second semiconductor. Here, a material of the core portion (e.g., center portion) may be cadmium selenide (CdSe), cadmium telluride (CdTe), cadmium sulfide (CdS), or the like. A material of the skin portion (e.g., shell portion) may be zinc sulfide (ZnS) or the like. Alternatively, a material of the skin portion (e.g., shell portion) may be a cadmium-free based QD. That is, various materials that do not include cadmium (Cd) may be applied to the QD. However, the above-described materials are merely examples and other various materials may be applied to the QD. In embodiments, for example, the QD may include at least one among a Group II-VI-based semicon-

ductor, a Group III-V-based semiconductor, a Group IV-VI-based semiconductor, and a Group IV-based semiconductor.

The QD has a relatively very small size and may thus exhibit the quantum confinement effect. When a size of a particle is relatively very small, electrons in the particle form a discontinuous energy state due to the outer walls of the particle. As the size of an inner space of the particle decreases, an energy state of the electrons relatively increases and energy band intervals increases. This effect refers to the quantum confinement effect. Due to the quantum confinement effect, when light such as an ultraviolet ray or visible light is incident on the QD, light of various wavelength ranges may be generated.

A wavelength of light generated by the QD may be determined by a size, material and/or structure of the QD. In detail, when light of a wavelength having energy higher than an energy band interval is incident on the QD, the QD absorbs the energy of the light and is thus excited, emits light of a specific wavelength, and changes to a ground state. In this case, when the size of the QD (or the core portion of the QD) is relatively small, light of a relatively short wavelength, e.g., blue or green light, may be generated. When the size of the QD (or the core portion of the QD) is relatively large, light of a relatively long wavelength, e.g., red light, may be generated. Accordingly, light of various colors may be achieved according to the size of the QD (or the core portion of the QD).

A QD particle emitting green light may be referred to as a green-light QD particle (e.g., a green QD particle). A QD particle emitting red light may be referred to as a red-light QD particle (e.g., a red QD particle). In an embodiment, for example, the green-light QD particle (or core portion) may be a particle having a width (e.g., diameter) of about 2 nm to about 3 nm, and the red-light QD particle (or core portion) may be a particle having a width (e.g., diameter) of about 5 nm to about 6 nm. A wavelength of emitted light may be controlled according to a material and structure of the QD, as well as the size (e.g., diameter) of the QD.

A color filter layer **300A** may be further provided on the encapsulation layer **200A**. An upper surface of the color filter layer **300A** may define a light emitting surface of the display apparatus without being limited thereto. The color filter layer **300A** may include first, second and third color filters **30a**, **30b** and **30c** respectively corresponding to a plurality of sub-pixel regions of the display apparatus at which color light is emitted such as to display an image. The first color filter **30a** may correspond to the first color control element **20a**. The second color filter **30b** may correspond to the second color control element **20b**. The third color filter **30c** may correspond to the light-scattering element **21c**.

The first, second and third color filters **30a**, **30b** and **30c** may be absorption type color filters including pigment or dye. The first color filter **30a** may be an absorption type red-color filter (C/F). The second color filter **30b** may be an absorption type green-color filter (C/F). The third color filter **30c** may be an absorption type blue-color filter (C/F). The red-color filter **30a** may selectively transmit light of a red wavelength region and absorb light of the other wavelength regions. The green-color filter **30b** may selectively transmit light of a green wavelength region and absorb light of the other wavelength regions. The blue-color filter **30c** may selectively transmit light of a blue wavelength region and absorb light of the other wavelength regions. By such transmitting and absorbing described above, the first color filter **30a** may filter out undesired light among light incident thereto after passing through the first color control element **20a**. Similarly, the second color filter **30b** may filter out

undesired light among light incident thereto after passing through the second color control element **20b** and the third color filter **30c** may filter out undesired light among light incident thereto after passing through the light-scattering element **21c**. Full RGB colors may be achieved using the color control elements **20a** and **20b** and the color filter layer **300A**. Here, the above-described order or method of the arrangement of RGB sub-pixels are merely an example and may be changed variously.

In the color filter layer **300A**, partitions **35** may be respectively provided between the first color filter **30a** and the second color filter **30b** and between the second color filter **30b** and the third color filter **30c**. The partitions **35** may be a type of black matrices. In an embodiment of manufacturing the color filter layer **300A**, after the partitions **35** are formed, the first to third color filters **30a**, **30b**, and **30c** may be formed in regions defined by the partitions **35**. The partitions **35** may reduce or effectively prevent different colors of light emitted at pixels or sub-pixels from being mixed with each other.

The inorganic material layers **210** and **230** of the encapsulation layer **200A** may include a metal nitride, a metal oxide, a metal oxynitride, a metal carbide, or a combination thereof. In an embodiment, for example, the inorganic material layers **210** and **230** may include a silicon nitride, an aluminum nitride, a zirconium nitride, a titanium nitride, a hafnium nitride, a tantalum nitride, a silicon oxide, an aluminum oxide, a titanium oxide, a tin oxide, a cerium oxide, a silicon oxynitride, or a combination thereof. The inorganic material layers **210** and **230** may be insulating layers or semiconductor layers. The inorganic material layers **210** and **230** may each have a thickness of about 10 nm to about 5000 nm, for example, a thickness of about 50 nm to about 1000 nm, along the thickness direction of the display apparatus. The thickness may be a total thickness and/or maximum thickness of such layer(s). When the thickness of each of the inorganic material layers **210** and **230** satisfies the above-described thickness range, the encapsulation layer **200A** may have a relatively high sealing property to reduce or effectively prevent contamination (e.g., moisture, etc.) from reaching other elements of the encapsulation layer **200A**. However, the material and thickness range of the inorganic material layers **210** and **230** are not limited thereto.

The organic material layer **220** of the encapsulation layer **200A** may include a photocurable organic material. The photocurable organic material may include a photoresist ("PR") material. The organic material layer **220** may include a titanium oxide (TiO<sub>2</sub>) or the like as a light-scattering agent. The organic material layer **220** may planarize a step portion (not shown) formed due to a pixel defining layer of the OLED substrate **100A** and/or may lessen stress caused by the inorganic material layer **210** or **230**. As a basic function, the organic material layer **220** includes the color control elements **20a** and **20b** and may thus have a color control function. The organic material layer **220** may have a thickness of about 10 nm to about 10000 nm, for example, a thickness of about 1000 nm to about 10000 nm. The thickness may be a total thickness and/or maximum thickness of such layer(s). Accordingly, the organic material layer **220** may have a thickness greater than those of the inorganic material layers **210** and **230**. When the thickness of the organic material layer **220** satisfies the above-described thickness range, a planarizing process may be effectively performed using the organic material layer **220**. However, the material and thickness range of the organic material layer **220** are not limited thereto. When there are two or more

organic material layers **220**, the thicknesses thereof may be the same or different. In an embodiment of manufacturing the encapsulation layer **200A**, the organic material layer **220** may be easily formed using a printing process, a photolithographic process, or the like.

In another embodiment, a cut-off filter type color filter may be used instead of one or more of the absorption type color filters **30a**, **30b** and **30c** of FIG. 1. Examples of the cut-off filter type color filters are illustrated in FIG. 2.

Referring to FIG. 2, a color filter layer **310A** may include cut-off filter type first to third color filters **31a**, **31b** and **31c**. The first color filter **31a** may filter out light of a blue wavelength region and light of a green wavelength region among light incident thereto after passing through a first color control element **20a**. The second color filter **31b** may filter out light of a blue wavelength region and light of a red wavelength region among light incident thereto after passing through a second color control element **20b**. The third color filter **31c** may filter out light of a green wavelength region and light of a red wavelength region among light incident thereto after passing through a light-scattering element **21c**. The first color filter **31a** may be referred to as a blue-and-green-cut filter (B,G cut filter). The second color filter **31b** may be referred to as a blue-and-red-cut filter (B,R cut filter). The third color filter **31c** may be referred to as a green-and-red-cut filter (G,R cut filter). In other words, the first color filter **31a** may be a first cut-off filter configured to selectively transmit light of a red wavelength region. The second color filter **31b** may be a second cut-off filter configured to selectively transmit light of a green wavelength region. The third color filter **31c** may be a third cut-off filter configured to selectively transmit light of a blue wavelength region. Color control/filtering characteristics of the display apparatus may be improved owing to the first to third color filters **31a**, **31b** and **31c**.

The cut-off filter type color filters **31a**, **31b** and **31c** may have, for example, a distributed Bragg reflector ("DBR") structure. The DBR structure may be manufactured by repeatedly stacking two material layers (e.g., dielectrics) having different refractive indexes from each other. The DBR structure may be manufactured to transmit or reflect only light of a desired wavelength band by controlling thicknesses of the material layers and a number of times of stacking the material layers, and is applicable to the color filters **31a**, **31b** and/or **31c**. In an embodiment, for example, a SiO<sub>2</sub> layer and a TiO<sub>2</sub> layer may be repeatedly stacked to satisfy a condition of  $\lambda/4$  (here, ' $\lambda$ ' represents a wavelength of light), and a reflectance or transmittance of light of a desired wavelength band may be increased by controlling the thicknesses of these layers and a number of times of stacking the layers. The DBR structure is a well-known structure and is thus not described in detail here. At least one among the first to third color filters **31a**, **31b** and **31c** may have a structure different from the DBR structure, e.g., a relatively high-contrast grating ("HCG") structure. In FIG. 2, components except the color filter layer **310A** may be the same or substantially the same as those of FIG. 1.

In another embodiment, the display apparatus may further include a fourth sub-pixel region, as well as an R-sub-pixel (e.g., first sub-pixel) region, a G-sub-pixel (e.g., second sub-pixel) region and a B-sub-pixel (e.g., third sub-pixel) region. The fourth sub-pixel region may be provided to exhibit a color (e.g., a fourth color) except for colors of red (R), green (G) and blue (B). The color (e.g., the fourth color) may be, for example, white (W) but is not limited thereto. Cases in which the fourth sub-pixel region is further provided are illustrated in FIGS. 3 and 4.

Referring to FIG. 3, similar to FIG. 1, an organic material layer **220a** of an encapsulation layer **200B** may include a first color control element **21a**, a second color control element **21b**, a first light-scattering element **22c** and a second light-scattering element **22d**. A first inorganic material layer **210a** may be provided below the organic material layer **220a** and a second inorganic material layer **230a** may be provided on the organic material layer **220a**. In this case, an OLED substrate **100B** may be a white-OLED substrate which emits a white color light.

A color filter layer **300B** may include first to third color filters **32a**, **32b** and **32c**, and a blank region corresponding to the second light-scattering element **22d**. The blank region may correspond to the fourth sub-pixel region described above, and white (W) color may be generated from the blank region. An upper surface of the color filter layer **300A** at the first through third sub-pixel regions and an upper surface of the encapsulation layer **200B** at the fourth sub-pixel region together may define a light emitting surface of the display apparatus without being limited thereto.

Referring to FIG. 4, similar to FIG. 3, a color filter layer **310B** may include cut-off filter type color filters **33a**, **33b** and **33c**. The color filter layer **310B** may further include a blank region corresponding to the fourth sub-pixel region described above.

In another embodiment, a color conversion element including a QD (a blue QD) may be used instead of the light-scattering element **21c** of FIG. 1. An example of the color conversion element is illustrated in FIG. 5.

Referring to FIG. 5, an organic material layer **221** of an encapsulation layer **201A** may include a third color control element **20c** including a QD instead of the light-scattering element **21c** of FIG. 1. The QD of the third color control element **20c** may be a blue QD. Thus, the third color control element **20c** may convert a color of light generated by an OLED substrate **100A** into blue light. In this case, the OLED substrate **100A** may be a light source generating light of color other than pure blue. The third color control element **20c** including the blue QD may be used according to the type of the OLED substrate **100A**. Although not shown, in the present embodiment, a fourth sub-pixel region may be further provided as shown in FIGS. 3 and 4. Although not shown, in the present embodiment, the cut-off filters **31a**, **31b** and **31c** may be provided as shown in FIG. 2.

According to one or more embodiment of the present disclosure, a display apparatus which has relatively high protective (encapsulation) properties with respect to an external environment and which is relatively easy to manufacture may be provided. Furthermore, a display apparatus capable of suppressing and/or minimizing color blurring or color mixing may be provided.

In manufacturing a conventional display apparatus, since an outgassing phenomenon may occur during a process for forming a QD color conversion layer, in order to apply a QD color conversion layer to a top-emission light-emitting device, the QD color conversion layer may be directly formed by patterning on an OLED device (e.g., at a display portion thereof) encapsulated with a multi-layer thin film or may be formed on a separate glass substrate and thereafter bonded with an OLED device (e.g., at a display portion thereof). However, if the QD color conversion layer is directly formed by patterning on the OLED device (e.g., at the display portion thereof) encapsulated with the multi-layer thin film, a photoluminescence ("PL") property may be deteriorated when the QD color conversion layer is exposed to a general environment. Thus, the QD color conversion layer may be encapsulated by an additional encapsulation

In this case, the OLED device is primarily encapsulated with a multi-layer thin film and is then secondarily encapsulated. Thus, the encapsulation process is relatively complicated. Furthermore, since the distance between the OLED device and the QD color conversion layer is relatively large, color implementation characteristics may be poor. If the QD color conversion layer is formed on the separate glass substrate and subsequently bonded with the OLED device (e.g., at the display portion thereof), two substrates are used and thus manufacturing costs may increase and a manufacturing process may be complicated. Furthermore, the distance between the OLED device and the QD color conversion layer may increase and thus color mixing may occur.

However, according to one or more embodiment of the present disclosure, at least one organic material film, e.g., among the organic material layers **220**, **220a** and **221**, may be provided in the encapsulation layers **200A**, **200B** and **201A** encapsulating the OLED substrates **100A** and **100B**, and the color control elements **20a**, **20b**, **20c**, **21a** and **21b** including QDs may be disposed or formed in the organic material layers **220**, **220a** and **221**. Accordingly, each of the OLED substrates **100A** and **100B** and the color control elements **20a**, **20b**, **20c**, **21a** and **21b** may be encapsulated with one of the encapsulation layers **200A**, **200B** and **201A**. Furthermore, since the distances between the OLED substrates **100A** and **100B** and the color control elements **20a**, **20b**, **20c**, **21a** and **21b** are relatively small, color blurring may be suppressed or minimized. In addition, the distances between the color control elements **20a**, **20b**, **20c**, **21a** and **21b** and the color filter layers **300A**, **300B**, **310A** and **310B** on the color control elements **20a**, **20b**, **20c**, **21a** and **21b** may be maintained to a minimum. Thus, color mixing may be also suppressed or minimized. Accordingly, a display apparatus that has relatively high protective (encapsulation) characteristics, is easy to manufacture, and is capable of suppressing and/or minimizing color blurring or color mixing may be provided.

A display apparatus according to an embodiment may further include a thin-film transistor ("TFT") array substrate having a plurality of TFTs which drive pixel regions (or sub-pixel regions) of the OLED substrates **100A** and **100B**. An example of the display apparatus is illustrated in FIG. 6. FIG. 6 illustrates a case in which a TFT array substrate **10** is applied to the display apparatus of FIG. 1. However, it will be understood that the TFT array substrate **10** in FIG. 6 may be applied to any one of the display apparatus disclosed in FIGS. 1 to 5.

Referring to FIG. 6, a TFT array substrate **10** having a plurality of TFTs (not shown) may be provided, and an OLED substrate **100A** may be provided on the TFT array substrate **10**. The plurality of TFTs of the TFT array substrate **10** may be devices configured to drive pixel regions (or sub-pixel regions) of the OLED substrate **100A**. As such, the plurality of TFTs of the TFT array substrate **10** may be connected to the OLED substrate **100A** and structures within the pixel regions (or sub-pixel region) to drive the pixel regions (or sub-pixel regions) of the OLED substrate **100A**. The driving of the pixel regions (or sub-pixel regions) of the OLED substrate **100A** may control the OLED substrate **100A** to generate and/or emit light to be incident on an encapsulation layer **200A**. The encapsulation layer **200A** may be provided on the OLED substrate **100A** to receive light emitted therefrom, and a color filter layer **300A** may be provided on the encapsulation layer **200A** to receive light emitted therefrom.

FIG. 7 is a detailed cross-sectional view of a structure of a display apparatus according to an embodiment.

Referring to FIG. 7, a TFT array substrate **10** may be provided, and a first electrode layer **110** having a plurality of first electrodes **110a**, **110b** and **110c** may be provided on the TFT array substrate **10**. The plurality of first electrodes **110a**, **110b** and **110c** may be elements patterned to respectively correspond to sub-pixel regions. The plurality of first electrodes **110a**, **110b** and **110c** may be electrically connected to TFT devices of the TFT array substrate **10**. The plurality of first electrodes **110a**, **110b** and **110c** may include or be formed of a transparent electrode material such as an indium tin oxide (“ITO”).

An emission layer (EML) **130** including an organic material-based emission material may be provided on the first electrode layer **110**. A hole transport layer (HTL) **120** may be provided between the EML **130** and the first electrode layer **110**. An electron transport layer (ETL) **140** may be provided on the EML **130**. A second electrode layer **150** may be provided on the ETL **140**. Although not shown, a hole injection layer may be provided between the first electrode layer **110** and the HTL **120**, and an electron injection layer may be provided between the second electrode layer **150** and the ETL **140**. An intermediate material layer **160** may be further provided on the second electrode layer **150**. The intermediate material layer **160** may be transparent and may be formed of an insulating material.

Although the first electrode layer **110** is patterned and the second electrode layer **150** has a non-patterned shape in the present embodiment, the second electrode layer **150** may be patterned into a plurality of electrode elements according to circumstances. Alternatively, the first electrode layer **110** may not be patterned and the second electrode layer **150** may be patterned, or both the first electrode layer **110** and the second electrode layer **150** may be patterned. Furthermore, the EML **130** located between the first electrode layer **110** and the second electrode layer **150** may be patterned into units corresponding to sub-pixels. In this case, all the HTL **120**, the EML **130** and the ETL **140** may be patterned. Although a case in which one emission unit having the HTL **120**, the EML **130** and the ETL **140** is used is illustrated and described above, a plurality of emission units may be used and a charge generation layer may be applied between the plurality of emission units. In other words, an OLED device having a tandem structure may be used. The collection of the first electrode layer **110**, the HTL **120**, the EML **130**, the ETL **140**, the second electrode layer **150** and the intermediate material layer may form a light-emitting substrate which generates and emits light therefrom. In embodiments, the light-emitting substrate illustrated in FIG. 6 may be used as the OLED substrate in any one of the display apparatus disclosed in FIGS. 1 to 6 without being limited thereto.

An encapsulation layer **200A** and a color filter layer **300A** according to an embodiment may be sequentially provided on the intermediate material layer **160**. The first electrode layer **110** and the second electrode layer **150** of an OLED substrate may be electrically separated (e.g., disconnected) from an inorganic material layer **210** of the encapsulation layer **200A**. The encapsulation layer **200A** and the color filter layer **300A** are as described above with reference to FIG. 1 and are thus not redundantly described again here.

Although FIG. 7 illustrates a case in which the TFT array substrate **10** is located below the emission layer **130**, the TFT array substrate **10** may be located above the emission layer **130**. In an embodiment, for example, the TFT array substrate **10** may be located between the EML **130** and the

encapsulation layer **200A**. In addition, components of the display apparatus described above with reference to FIG. 7 may be variously changed.

FIG. 8 is a cross-sectional view of a structure of an encapsulation layer applicable to a display apparatus according to another embodiment.

Referring to FIG. 8, the encapsulation layer may include a first inorganic material layer **215**, a second inorganic material layer **235**, and a first organic material layer **225** located between the first inorganic material layer **215** and the second inorganic material layer **235**. The first inorganic material layer **215** and the second inorganic material layer **235** may be larger in planar size than the first organic material layer **225** and may be bonded to each other at outer side edges of the first organic material layer **225**. That is, the first inorganic material layer **215** and the second inorganic material layer **235** extend further than the side edges of the first organic material layer **225**, to dispose ends of the first inorganic material layer **215** and the second inorganic material layer **235** spaced apart from the side edges of the first organic material layer **225**. Thus, side surfaces of the first organic material layer **225** may be covered with the inorganic material layer **235**. In other words, the first organic material layer **225** may be completely sealed by the first inorganic material layer **215** and the second inorganic material layer **235**.

The first organic material layer **225** may be divided into a plurality of sub-pixel regions, and include color conversion elements including QDs. When the first organic material layer **225** is completely sealed by the inorganic material layers **215** and **235** according to the present embodiment, the protective (e.g., encapsulation) characteristic of the first organic material layer **225** may be more enhanced. That is, permeation of external oxygen or moisture may be reduced or effectively prevented due to the inorganic material layers **215** and **235** sealing the first organic material layer **225** therebetween.

FIG. 9 is a cross-sectional view of a display apparatus according to another embodiment.

Referring to FIG. 9, an encapsulation layer **200C** may be provided on an OLED substrate **100**. The encapsulation layer **200C** may have a structure in which one or more inorganic material layers and one or more organic material layers are alternately and repeatedly stacked, and a plurality of color control elements may be included in at least one of the one or more organic material layers. In an embodiment, for example, the encapsulation layer **200C** may have a structure in which a first inorganic material layer **210b**, a first organic material layer **220b**, a second inorganic material layer **230b**, a second organic material layer **240b** and a third inorganic material layer **250b** are sequentially stacked.

Color control elements **25a** and **25b** including QDs may be included in at least one of the first organic material layer **220b** and the second organic material layer **240b**, e.g., in the first organic material layer **220b**. A light-scattering element **26c** may be further included in the first organic material layer **220b**. Here, the encapsulation layer **200C** having a five-layer structure is illustrated as an example but the number of material layers of the encapsulation layer **200C** may vary. Alternatively, the color control elements **25a** and **25b** and the light-scattering element **26c** may be included in the second organic material layer **240b** rather than the first organic material layer **220b**. In embodiments, where more than one organic material layer is provided, the color control elements may be provided in only one organic material layer, without being limited thereto. In embodiments, where more than one organic material layer is provided, the light-

scattering element **26c** may be provided in a same organic material layer as the color control elements or in a different organic material layer from the color control elements.

FIG. **10** is a cross-sectional view of a display apparatus according to another embodiment. FIG. **10** is a modified example of the display apparatus of FIG. **1**.

Referring to FIG. **10**, a cover layer **350** may be further provided on a color filter layer **300A**. An encapsulation layer **200A** may protect and encapsulate an OLED substrate **100A** and an organic material layer **220**, whereas the cover layer may protect the color filter layer **300A**. An upper surface of the cover layer **350** may define a light emitting surface of the display apparatus without being limited thereto. The cover layer **350** may include or be formed of an inorganic material and may be a transparent insulating layer. When the color filter layer **300A** includes or is formed of an inorganic material, the cover layer **350** may be omitted. The cover layer **350** is applicable to not only the display apparatus of FIG. **1** but also the display apparatuses of FIGS. **2** to **7**.

FIG. **11** is a graph showing an electroluminescence (“EL”) spectrum of a blue-OLED substrate applicable to a display apparatus according to an embodiment. The EL spectrum is illustrated with an intensity in arbitrary units (a.u.) with respect to wavelength in nanometers (nm) for blue light.

Referring to FIG. **11**, blue light is generated from the blue-OLED substrate. However, an OLED substrate applicable to a display apparatus according to an embodiment is not limited to the blue-OLED substrate, and may be various other colored OLED substrates such as a white-OLED substrate, a cyan-OLED substrate, or the like.

FIG. **12** is a graph showing a photoluminescence (“PL”) quantum yield (“QY”) in percent (%) according to wavelengths in nanometers (nm) of a color conversion element including a red-QD and a color conversion element including a green-QD applicable to a display apparatus according to an embodiment.

Referring to FIG. **12**, the color conversion element including the green-QD has a PL quantum yield up to approximately a green wavelength region, and the color conversion element including the red-QD has a PL quantum yield approximately until a red wavelength region. The color conversion element including the red-QD and color conversion element including the green-QD may be respectively applied to the first color control element **20a** and the second color control element **20b** of FIG. **1**.

FIG. **13** is a graph showing a variation in transmittance in percent (%) versus wavelengths in nanometers (nm) of a color conversion element including a red-QD and a color conversion element including a green-QD applicable to a display apparatus according to an embodiment.

Referring to FIG. **13**, the color conversion element including the green-QD has a relatively high transmittance starting from approximately a wavelength corresponding to a green wavelength region, and the color conversion element including the red-QD has a relatively high transmittance starting from approximately a wavelength corresponding to a red wavelength region.

FIG. **14** is a graph showing a variation in a transmittance in percent (%) versus a wavelength in nanometers (nm) of an absorption type color filter applicable to a display apparatus according to an embodiment. The graph of FIG. **14** shows a variation in a transmittance (%) versus a wavelength (nm) of each of an absorption type red-color filter, an absorption type green-color filter and an absorption type Blue-color filter. The absorption type red-color filter, the absorption type green-color filter and the absorption type blue-color filter

may be respectively applied to, for example, the first color filter **30a**, the second color filter **30b**, and the third color filter **30c** of FIG. **1**.

FIG. **15** is a graph showing a variation in a transmittance in percent (%) versus a wavelength in nanometers (nm) of a cut-off type color filter applicable to a display apparatus according to an embodiment. The graph of FIG. **15** shows a variation in a transmittance (%) versus a wavelength (nm) of each of a cut-off type red-color filter, a cut-off type green-color filter and a cut-off type blue-color filter. The cut-off type red-color filter, the cut-off type green-color filter and the cut-off type blue-color filter may be respectively applied to, for example, the first color filter **31a**, the second color filter **31b** and the third color filter **31c** of FIG. **2**.

FIG. **16** is a graph showing a spectral radiance difference between when a light-scattering agent is applied to blue light and when the light-scattering agent is not applied to the blue light. The spectral difference is expressed in watt per steradian per square metre per nanometre ( $W/(m^2 \cdot sr \cdot nm)$ ).

Referring to FIG. **16**, when the light-scattering agent was not applied (“Before light-scattering agent”), light was not appropriately dispersed and thus a plurality of peaks occurred. When the light-scattering agent was applied (“After light-scattering agent”), light was appropriately dispersed and thus one relatively smoothly curved one peak occurred.

FIG. **17** is a graph showing an emission spectrum according to a wavelength of a display apparatus according to an embodiment. The emission spectrum is expressed in watt per steradian per square metre ( $W \cdot sr^{-1} \cdot m^{-2}$ ).

Referring to FIG. **17**, a spectrum (“Red-AF-CF”) of light generated from an OLED substrate (as a light source) after the light passed through a color conversion element including a red-QD corresponds to a red light region, a spectrum (“Green-AF-CF”) of the light after the light passed through a color conversion element including a green-QD corresponds to a green light region, and a spectrum (“Blue”) of light which has passed through a non-color-converting region of an organic material layer such as in a blue pixel region corresponds to a blue light region.

The display apparatuses according to one or more embodiment described above are applicable to various types of electronic devices. For example, the display apparatuses are applicable to relatively small-sized electronic devices such as portable devices or wearable devices, and medium and relatively large-sized electronic devices such as household appliances.

Although many matters have been described above in detail, it should be understood that they are not intended to restrict the scope of the present disclosure and are provided to give examples. For example, it would be apparent to those of ordinary skill in the art that various changes may be made in the structures of and relations among the OLED substrates, the encapsulation layers, the QD color control elements, the color filter layers and the display apparatuses described above with reference to FIGS. **1** to **10**. In an embodiment, for example, a bottom-emission light-emitting device may be used as an OLED substrate instead of a top-emission light-emitting device shown in the figures, and various changes may be made in structures of a QD color control element and/or a color filter layer according to color of light emitted from the OLED substrate. Furthermore, structures according to embodiments or parts thereof are applicable to display apparatuses and other types of devices, e.g., lighting devices. Accordingly, the scope of the present disclosure should be determined not by the embodiments set forth herein but by the technical idea defined in the appended claims.

What is claimed is:

1. A display apparatus comprising:
  - an organic light-emitting device substrate which generates and emits a first light; and
  - an encapsulation layer to which the emitted first light from the organic light-emitting device substrate is incident and from which a second light is emitted, the encapsulation layer comprising:
    - an inorganic material layer, and
    - an organic material layer comprising a plurality of color control elements which color-convert the emitted first light incident to the encapsulation layer, wherein the plurality of color control elements of the organic material layer comprise:
      - a first color control element including a first quantum dot with which a color of the emitted first light incident to the encapsulation layer is converted to a first color, and
      - a second color control element including a second quantum dot with which the color of the emitted first light incident to the encapsulation layer is converted to a second color; and
    - a color filter layer facing the organic light-emitting device substrate with each of the plurality of color control elements of the organic material layer and the inorganic material layer therebetween.
2. The display apparatus of claim 1, wherein within the encapsulation layer,
  - the inorganic material layer is provided in plurality including a first inorganic material layer and a second inorganic material layer, and;
  - the organic material layer comprising the plurality of color control elements is between the first and second inorganic material layers.
3. The display apparatus of claim 2, wherein the color filter layer faces the organic light-emitting device substrate with each of the plurality of color control elements of the organic material layer, the first inorganic material layer and the second inorganic material layer therebetween.
4. The display apparatus of claim 3, further comprising a plurality of sub-pixel regions at which color light is emitted to display an image,
  - wherein the color filter layer comprises respectively corresponding to the plurality of sub-pixel regions:
    - a first color filter which corresponds to the first color control element of the encapsulation layer,
    - a second color filter which corresponds to the second color control element of the encapsulation layer, and
    - a third color filter.
5. The display apparatus of claim 4, wherein within the color filter layer to which the emitted second light from the encapsulation layer is incident,
  - the first color filter is a first cut-off filter which selectively transmits light in a red light wavelength region,
  - the second color filter is a second cut-off filter which selectively transmits light in a green light wavelength region, and
  - the third color filter is a third cut-off filter which selectively transmits light in a blue light wavelength region.
6. The display apparatus of claim 4, wherein within the color filter layer to which the emitted second light from the encapsulation layer is incident,
  - the first color filter is an absorption-type red color filter,
  - the second color filter is an absorption-type green color filter, and
  - the third color filter is an absorption-type blue color filter.

7. The display apparatus of claim 2, wherein within the encapsulation layer, the first and second inorganic material layers each extend along the organic material layer to dispose ends of the first and second inorganic material layers spaced apart from outer sides of the organic material layer, the first and second inorganic material layers being bonded to each other at the ends thereof.

8. The display apparatus of claim 1, wherein the first quantum dot of the first color control element converts the color of the emitted first light incident to the encapsulation layer into red, and the second quantum dot of the second color control element converts the color of the emitted first light incident to the encapsulation layer into green.

9. The display apparatus of claim 1, wherein in a direction along the organic light-emitting device substrate, the organic material layer further comprises a light-scattering element adjacent to the plurality of color control elements, wherein the light-scattering element maintains the color of the emitted first light incident to the encapsulation layer.

10. The display apparatus of claim 1, wherein in a direction along the organic light-emitting device substrate, the plurality of color control elements further comprise a third color control element adjacent to the first and second color control elements, the third color control element including a third quantum dot with which the color of the emitted first light incident to the encapsulation layer is converted to a third color.

11. The display apparatus of claim 1, wherein the organic light-emitting device substrate comprises:
 

- a first electrode;
- a second electrode; and
- an organic emission layer between the first and second electrodes, and

the first and second electrodes are electrically separated from the inorganic material layer of the encapsulation layer.

12. The display apparatus of claim 1, wherein the organic material layer of the encapsulation layer comprises:
 

- a photocurable organic material; and
- a light-scattering agent.

13. The display apparatus of claim 1, wherein the organic material layer of the encapsulation layer has a thickness of about 10 nanometers to about 10000 nanometers.

14. The display apparatus of claim 1, wherein the inorganic material layer of the encapsulation layer comprises any one of a metal nitride, a metal oxide, a metal oxynitride, a metal carbide and a combination thereof.

15. The display apparatus of claim 1, wherein the inorganic material layer of the encapsulation layer comprises an insulating layer or a semiconductor layer.

16. The display apparatus of claim 1, wherein the inorganic material layer of the encapsulation layer has a thickness of about 10 nanometers to about 5000 nanometers.

17. The display apparatus of claim 1, wherein the organic light-emitting device substrate comprises a blue organic light-emitting device substrate which emits blue first light, a white organic light-emitting device substrate which emits white first light, or a cyan organic light-emitting device substrate which emits cyan first light.

18. The display apparatus of claim 1, wherein within the encapsulation layer,
 

- the inorganic material layer and the organic material layer are each provided in plurality,
- the plurality of inorganic material layers are alternately stacked with the plurality of organic material layers, and

each of the plurality of color control elements which color-convert the emitted first light incident to the encapsulation layer is provided in a single one organic material layer among the plurality of organic material layers. 5

**19.** The display apparatus of claim **18**, wherein in a direction along the organic light-emitting device substrate, the single one organic material layer in which the each of the plurality of color control elements are provided comprises a light-scattering element adjacent 10 to the plurality of color control elements, wherein the light-scattering element maintains the color of the emitted first light incident to the encapsulation layer.

**20.** The display apparatus of claim **1**, wherein 15 the color filter layer comprises a plurality of color filters, within the organic material layer, in a direction along the organic light-emitting device substrate, the encapsulation layer further comprises a plurality of light-scattering elements adjacent to the plurality of color control 20 elements,

the color filters of the color filter layer respectively correspond to the plurality of color control elements and to a first light-scattering element among the plurality of light-scattering elements, and 25 within the organic material layer, a second light-scattering element different from the first light-scattering element among the plurality of light-scattering elements extends further than an end of the color filter layer to be exposed from the color filter layer. 30

\* \* \* \* \*

专利名称(译)	色彩控制封装层和包括其的显示装置		
公开(公告)号	<a href="#">US10686019</a>	公开(公告)日	2020-06-16
申请号	US16/152905	申请日	2018-10-05
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD.		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD.		
[标]发明人	LEE SUNGHUN CHOI BYOUNGKI KWAK SEUNGYEON KIM JIWHAN		
发明人	LEE, SUNGHUN CHOI, BYOUNGKI KWAK, SEUNGYEON KIM, JIWHAN		
IPC分类号	H01L27/32 H01L51/52 H01L33/50		
CPC分类号	H01L27/322 H01L27/3213 H01L33/501 H01L27/3211 H01L2251/5369 H01L51/5256 H01L27/3244 H01L51/5268 H01L2251/558		
代理机构(译)	康托科尔伯恩LLP		
优先权	1020170155807 2017-11-21 KR		
其他公开文献	US20190157354A1		
外部链接	<a href="#">Espacenet</a>		

摘要(译)

显示设备包括：有机发光器件 (“ OLED” ) 基板，其产生并发射第一光；以及封装层，从OLED基板发射的第一光入射到该封装层上，并且从该封装层发射第二光。封装层包括彼此交替堆叠的无机材料层和有机材料层。有机材料层包括多个颜色控制元件，其对入射到封装层的发射的第一光进行颜色转换。多个色彩控制元件可以包括第一色彩控制元件和第二色彩控制元件，该第一色彩控制元件和第二色彩控制元件包括第一量子点和第二量子点，利用该第一量子点和第二量子点将入射到封装层的所发射的第一光的颜色分别转换为第一色彩和第二色彩。

