



US 20160204359A1

(19) **United States**

(12) **Patent Application Publication**
LEE et al.

(10) **Pub. No.: US 2016/0204359 A1**
(43) **Pub. Date: Jul. 14, 2016**

(54) **HETEROCYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE COMPRISING SAME**

(30) **Foreign Application Priority Data**

Jul. 29, 2013 (KR) 10-2013-0089869

(71) Applicant: **LG CHEM, LTD.**, Seoul (KR)

Publication Classification

(72) Inventors: **Hoyong LEE**, Daejeon (KR); **Seongmi CHO**, Daejeon (KR); **Kongkyeom KIM**, Daejeon (KR); **Sang Young JEON**, Daejeon (KR); **Minseung CHUN**, Daejeon (KR); **Hyoung Seok KIM**, Daejeon (KR); **Dongheon KIM**, Daejeon (KR)

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07D 401/14 (2006.01)
C07D 403/14 (2006.01)
C09K 11/02 (2006.01)
C09K 11/06 (2006.01)

(73) Assignee: **LG Chem, LTD.**, Seoul (KR)

(52) **U.S. Cl.**
CPC *H01L 51/0072* (2013.01); *C09K 11/025* (2013.01); *C09K 11/06* (2013.01); *H01L 51/0085* (2013.01); *C07D 403/14* (2013.01); *H01L 51/0067* (2013.01); *C07D 401/14* (2013.01); *H01L 51/0052* (2013.01); *H01L 51/5016* (2013.01)

(21) Appl. No.: **14/908,095**


(22) PCT Filed: **Jul. 10, 2014**

(86) PCT No.: **PCT/KR2014/006184**

§ 371 (c)(1),
(2) Date: **Jan. 27, 2016**

(57) **ABSTRACT**

The present specification provides a heterocyclic compound and an organic light emitting device comprising the same.




[Figure 1]

4
3
2
1

[Figure 2]


4
8
7
6
5
2
1

[Figure 3]




Mass spectrum of chemical Formula 1-1

[Figure 4]




Mass spectrum of chemical Formula 1-2

[Figure 5]




Mass spectrum of chemical Formula 1-4

[Figure 6]




Mass spectrum of chemical Formula 1-5

[Figure 7]




Mass spectrum of chemical Formula 1-19

[Figure 8]




Mass spectrum of chemical Formula 1-23

[Figure 9]




Mass spectrum of chemical Formula 1-70

[Figure 10]




Mass spectrum of chemical Formula 1-71

[Figure 11]




Mass spectrum of chemical Formula 1-74

[Figure 12]




Mass spectrum of chemical Formula 1-142

[Figure 13]




Mass spectrum of chemical Formula 1-160

[Figure 14]




Mass spectrum of chemical Formula 1-219

[Figure 15]



Mass spectrum of chemical Formula 1-227

[Figure 16]



Mass spectrum of chemical Formula 1-228

**HETEROCYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
COMPRISING SAME**

[Chemical Formula 1]

TECHNICAL FIELD

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2013-0089869 filed in the Korean Intellectual Property Office on Jul. 29, 2013, the entire contents of which are incorporated herein by reference.

[0002] The present specification relates to a heterocyclic compound and an organic light emitting device comprising the same.

BACKGROUND ART

[0003] In general, an organic light emitting phenomenon means a phenomenon where electric energy is converted into light energy by using an organic material. An organic light emitting device using the organic light emitting phenomenon has a structure generally including an anode, a cathode, and an organic material layer interposed therebetween. Herein, in many cases, the organic material layer has a multilayered structure constituted by different materials in order to increase efficiency and stability of the organic light emitting device, and for example, the organic material layer may be formed of a hole injection layer, a hole transport layer, a light emitting layer, an electron transport layer, an electron injection layer, and the like. In the structure of the organic light emitting device, if a voltage is applied between two electrodes, the holes are injected from the anode to the organic material layer and the electrons are injected from the cathode to the organic material layer, and when the injected holes and electrons meet each other, an exciton is formed, and light is emitted when the exciton falls to a bottom state again.

[0004] There is a continuous demand for developing a novel material for the aforementioned organic light emitting device.


DISCLOSURE

Technical Problem

[0005] The present specification describes a novel heterocyclic compound and an organic light emitting device comprising the same.

Technical Solution

[0006] An exemplary embodiment of the present specification provides a compound represented by the following Chemical Formula 1.



[0007] In Chemical Formula 1,

[0008] L_1 is a direct bond; substituted or unsubstituted phenylene; or a substituted or unsubstituted divalent monocyclic heterocyclic group including one or more of N, O, and S atoms,

[0009] L_2 is a direct bond; a substituted or unsubstituted arylene group; or a substituted or unsubstituted divalent heterocyclic group including one or more of N, O, and S atoms,

[0010] X_1 is N or CR_{11} , X_2 is N or CR_{12} , X_3 is N or CR_{13} ,

[0011] A is hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthioxy group; a substituted or unsubstituted arylthioxy group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted phenyl group; a substituted or unsubstituted biphenyl group; or a substituted or unsubstituted aromatic or aliphatic monocyclic six-membered heterocyclic group including one or more of N, O, and S atoms,

[0012] Ar_1 and Ar_2 are the same as or different from each other, and are each independently hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthioxy group; a substituted or unsubstituted arylthioxy group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted aryl group; a substituted or unsubstituted fluorenyl group; or a substituted or unsubstituted aromatic or aliphatic heterocyclic group including one or more of N, O, and S atoms, but do not include a carbazole group,

[0013] R_1 to R_4 and R_{11} to R_{13} are the same as or different from each other, and are each independently hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthioxy group; a substituted or unsubstituted arylthioxy group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted aryl group; a substituted or unsubstituted fluorenyl group; or a substituted or unsubstituted aromatic or aliphatic heterocyclic group including one or more of N, O, and S atoms.

[0014] a and c are each an integer of 0 to 4, b and d are each an integer of 0 to 3, in the case where a is 2 or more, R_1 s are the same as or different from each other, in the case where b is 2 or more, R_2 s are the same as or different from each other, in the case where c is 2 or more, R_3 s are the same as or different from each other, and in the case where d is 2 or more, R_4 s are the same as or different from each other.

[0015] Another exemplary embodiment of the present specification provides an organic light emitting device including: a first electrode; a second electrode provided to face the first electrode; and one or more organic material layers provided between the first electrode and the second electrode, in which one or more of the organic material layers include the compound of Chemical Formula 1.

Advantageous Effects

[0016] A compound described in the present specification may be used as a material of an organic material layer of an organic light emitting device. The compound according to at least some exemplary embodiments can improve efficiency, and low driving voltage and/or life-span characteristics in the organic light emitting device. Particularly, in the case where the compound described in the present specification is used as a host of a phosphorescent light emitting layer or an electron transport material adjacent to a light emitting layer, it is possible to provide the organic light emitting device having high efficiency and/or a long life-span.

DESCRIPTION OF DRAWINGS

[0017] FIG. 1 illustrates an example of an organic light emitting device including a substrate 1, an anode 2, a light emitting layer 3, and a cathode 4.

[0018] FIG. 2 illustrates an example of an organic light emitting device including a substrate 1, an anode 2, a hole injection layer 5, a hole transport layer 6, a light emitting layer 7, an electron transport layer 8, and a cathode 4.

[0019] FIGS. 3 to 16 illustrate data for confirming synthesis of main compounds.

MODE FOR INVENTION

[0020] Hereinafter, the present specification will be described in more detail.

[0021] An exemplary embodiment of the present specification provides a compound represented by Chemical Formula 1.


[0022] In the present specification, ξ means a bond connected to another substituent group.

[0023] Examples of the substituent groups will be described below, but are not limited thereto.


[0024] In the present specification, the term "substituted or unsubstituted" means that substitution is performed by one or more substituent groups selected from the group consisting of deuterium; a halogen group; a nitrile group; a nitro group; an imide group; an amide group; a hydroxy group; a thiol group; an alkyl group; an alkenyl group; an alkoxy group; a cycloalkyl group; a silyl group; an arylalkenyl group; an aryl group; an aryloxy group; an alkylthioxy group; an arylthioxy group; an alkylsulfoxy group; an arylsulfoxy group; a silyl group; a boron group; a carbazole group; an aryl group; a fluorenyl group; an arylalkyl group; an arylalkenyl group; and a heterocyclic group including one or more of O, N, and S as a heteroatom, or there is no substituent group, or substitution is performed by a substituent group where two or more substituent groups of the exemplified substituent groups are connected or there is no substituent group. For example, the term "substituent group where two or more substituent groups are connected" may be a biphenyl group. That is, the biphenyl group may be an aryl group, or may be interpreted as a substituent group where two phenyl groups are connected.

[0025] In the present specification, examples of a halogen group include fluorine, chlorine, bromine, or iodine.


[0026] In the present specification, the number of carbon atoms of a carbonyl group is not particularly limited but is preferably 1 to 50. Specifically, the carbonyl group may be compounds having the following structures, but is not limited thereto.




[0027] In the present specification, oxygen of an ester group may be substituted by a straight-chained, branched-chained, or cyclic-chained alkyl group having 1 to 25 carbon atoms, or an aryl group having 6 to 25 carbon atoms. Specifically, the ester group may be compounds having the following Structural Formulas, but is not limited thereto.




[0028] In the present specification, the number of carbon atoms of an imide group is not particularly limited but is preferably 1 to 25. Specifically, the imide group may be compounds having the following structures, but is not limited thereto.



[0029] In the present specification, one or two nitrogen atoms of an amide group may be substituted by hydrogen, a straight-chained, branched-chained, or cyclic-chained alkyl group having 1 to 25 carbon atoms, or an aryl group having 6 to 25 carbon atoms. Specifically, the amide group may be compounds having the following Structural Formulas, but is not limited thereto.



-continued



[0030] In the present specification, an alkyl group may be a straight or branched chain, and the number of carbon atoms thereof is not particularly limited but is preferably 1 to 50. Specific examples thereof include methyl, ethyl, propyl, n-propyl, isopropyl, butyl, n-butyl, isobutyl, tert-butyl, sec-butyl, 1-methyl-butyl, 1-ethyl-butyl, pentyl, n-pentyl, isopentyl, neopentyl, tert-pentyl, hexyl, n-hexyl, 1-methylpentyl, 2-methylpentyl, 4-methyl-2-pentyl, 3,3-dimethylbutyl, 2-ethylbutyl, heptyl, n-heptyl, 1-methylhexyl, cyclopentylmethyl, cyclohexylmethyl, octyl, n-octyl, tert-octyl, 1-methylheptyl, 2-ethylhexyl, 2-propylpentyl, n-nonyl, 2,2-dimethylheptyl, 1-ethyl-propyl, 1,1-dimethyl-propyl, isohexyl, 2-methylpentyl, 4-methylhexyl, 5-methylhexyl, and the like, but are not limited thereto.

[0031] In the present specification, a cycloalkyl group is not particularly limited, but the number of carbon atoms thereof is preferably 3 to 60, and specific examples thereof include cyclopropyl, cyclobutyl, cyclopentyl, 3-methylcyclopentyl, 2,3-dimethylcyclopentyl, cyclohexyl, 3-methylcyclohexyl, 4-methylcyclohexyl, 2,3-dimethylcyclohexyl, 3,4,5-trimethylcyclohexyl, 4-tert-butylcyclohexyl, cycloheptyl, cyclooctyl, and the like, but are not limited thereto.

[0032] In the present specification, the alkoxy group may be a straight, branched, or cyclic chain. The number of carbon atoms of the alkoxy group is not particularly limited, but preferably 1 to 20. Specific examples thereof may include methoxy, ethoxy, n-propoxy, isopropoxy, i-propoxy, n-butoxy, isobutoxy, tert-butoxy, sec-butoxy, n-pentyloxy, neopentyloxy, isopentyloxy, n-hexyloxy, 3,3-dimethylbutyloxy, 2-ethylbutyloxy, n-octyloxy, n-nonyloxy, n-decyloxy, benzyloxy, p-methylbenzyloxy, and the like, but are not limited thereto.

[0033] In the present specification, the alkenyl group may be a straight or branched chain, and the number of carbon atoms thereof is not particularly limited but is preferably 2 to 40. Specific examples thereof include vinyl, 1-propenyl, isopropenyl, 1-butenyl, 2-butenyl, 3-butenyl, 1-pentenyl, 2-pentenyl, 3-pentenyl, 3-methyl-1-butenyl, 1,3-butadienyl, allyl, 1-phenylvinyl-1-yl, 2-phenylvinyl-1-yl, 2,2-diphenylvinyl-1-yl, 2-phenyl-2-(naphthyl-1-yl)vinyl-1-yl, 2,2-bis(diphenyl-1-yl)vinyl-1-yl, a stilbenyl group, a styrenyl group, and the like, but are not limited thereto.

[0034] In the present specification, the aryl group may be a monocyclic aryl group or a polycyclic aryl group, and includes the case where an alkyl group having 1 to 25 carbon atoms or an alkoxy group having 1 to 25 carbon atoms is substituted. Further, in the present specification, the aryl group may mean an aromatic cycle.


[0035] In the case where the aryl group is the monocyclic aryl group, the number of carbon atoms is not particularly limited but is preferably 6 to 25. Specific examples of the

monocyclic aryl group may include a phenyl group, a biphenyl group, a terphenyl group, a stilbenyl group, or the like, but are not limited thereto.

[0036] In the case where the aryl group is the polycyclic aryl group, the number of carbon atoms thereof is not particularly limited but is preferably 10 to 24. Specific examples of the polycyclic aryl group may include a naphthyl group, an anthracenyl group, a phenanthryl group, a pyrenyl group, a perylenyl group, a chrysenyl group, a fluorenyl group, and the like, but are not limited thereto.

[0037] In the present specification, the fluorenyl group may be substituted, and two substituent groups may be bonded to each other to form a spiro structure.

[0038] In the case where the fluorenyl group is substituted,



and the like may be formed. However, the structure is not limited thereto.

[0039] In the present specification, specific examples of the silyl group include a trimethylsilyl group, a triethylsilyl group, a t-butyl dimethylsilyl group, a vinyl dimethylsilyl group, a propyl dimethylsilyl group, a triphenylsilyl group, a diphenylsilyl group, a phenylsilyl group, and the like, but are not limited thereto.

[0040] In the present specification, the heterocyclic group is a heterocyclic group including one or more of O, N, and S as a heteroatom, and the number of carbon atoms thereof is not particularly limited, but is preferably 2 to 60. Examples of the heterocyclic group include a thiophene group, a furan group, a pyrrole group, an imidazole group, a triazole group, an oxazol group, an oxadiazol group, a triazol group, a pyridyl group, a bipyridyl group, a pyrimidyl group, a triazine group, a triazole group, an acridyl group, a pyridazine group, a pyrazinyl group, a quinolinyl group, a quinazoline group, a quinoxaliny group, a phthalazinyl group, a pyridopyrimidinyl group, a pyridopyrazinyl group, a pyrazinopyrazinyl group, an isoquinoline group, an indole group, a carbazole group, a benzoxazole group, a benzimidazole group, a benzothiazol group, a benzocarbazole group, a benzothiophene group, a dibenzothiophene group, a benzofuranyl group, a

phenanthroline group, a thiazolyl group, an isoxazolyl group, an oxadiazolyl group, a thiadiazolyl group, a benzothiazolyl group, a phenothiazinyl group, a dibenzofuranyl group, and the like, but are not limited thereto.

[0041] In the present specification, the aryl group of the aryloxy group, the arylthioxy group, and the arylsulfoxy group is the same as the aforementioned examples of the aryl group. Specific examples of the aryloxy group include phenoxy, p-tolyloxy, m-tolyloxy, 3,5-dimethyl-phenoxy, 2,4,6-trimethylphenoxy, p-tert-butylphenoxy, 3-biphenyloxy, 4-biphenyloxy, 1-naphthyloxy, 2-naphthyloxy, 4-methyl-1-naphthyloxy, 5-methyl-2-naphthyloxy, 1-anthryloxy, 2-anthryloxy, 9-anthryloxy, 1-phenanthryloxy, 3-phenanthryloxy, 9-phenanthryloxy, and the like, specific examples of the arylthioxy group include a phenylthioxy group, a 2-methylphenylthioxy group, a 4-tert-butylphenylthioxy group, and the like, and specific examples of the arylsulfoxy group include a benzenesulfoxy group, a p-toluenesulfoxy group, and the like, but the examples are not limited thereto.

[0042] In the present specification, the alkyl group of an alkylthioxy group and an alkylsulfoxy group is the same as the aforementioned examples of the alkyl group. Specific examples of the alkylthioxy group include a methylthioxy group, an ethylthioxy group, a tert-butylthioxy group, a hexylthioxy group, an octylthioxy group, and the like, and specific examples of the alkylsulfoxy group include a methylsulfoxy group, an ethylsulfoxy group, a propylsulfoxy group, a butylsulfoxy group, and the like, but the examples are not limited thereto.

[0043] In the present specification, an arylene group means a matter where two bonding positions exist at the aryl group, that is, a divalent group. Excepting that the groups are each the divalent group, the aforementioned description of the aryl group may be applied.


[0044] In the present specification, a divalent heterocyclic group means a matter where two bonding positions exist at the heterocyclic group, that is, a divalent group. Excepting that the groups are each the divalent group, the aforementioned description of the heterocyclic group may be applied.

[0045] According to the exemplary embodiment of the present specification, A of Chemical Formula 1 is a substituted or unsubstituted phenyl group; a substituted or unsubstituted biphenyl group; or a substituted or unsubstituted aromatic or aliphatic monocyclic six-membered heterocyclic group including one or more of N, O, and S atoms. In the case where the polycycle is positioned at a position A, synthesis is not easy and a molecular weight is excessively increased, and thus a deposition temperature is excessively high, and in this case, processability is not good.

[0046] According to the exemplary embodiment of the present specification, A of Chemical Formula 1 is a substituted or unsubstituted phenyl group; a substituted or unsubstituted biphenyl group; or a substituted or unsubstituted monocyclic six-membered heterocyclic group including N.

[0047] According to the exemplary embodiment of the present specification, Chemical Formula 1 may be represented by the following Chemical Formula 2.

[Chemical Formula 2]



[0048] In Chemical Formula 2,

[0049] Z_1 to Z_5 are the same as or different from each other, and are each independently CR_5 or N, herein, R_5 is the same as definitions of R_1 to R_4 , in the case where at least two of Z_1 to Z_5 are CR_5 , R_5 s are the same as or different from each other, and a residual substituent group is the same as the matter defined in Chemical Formula 1.

[0050] According to the exemplary embodiment of the present specification, A of Chemical Formula 1 is a phenyl group unsubstituted or substituted by an alkyl group, an aryl group, or a heterocyclic group; a biphenyl group unsubstituted or substituted by an alkyl group, an aryl group, or a heterocyclic group; or a monocyclic six-membered heterocyclic group unsubstituted or substituted by an alkyl group, an aryl group, or a heterocyclic group and including one or more of N, O, and S atoms. In the case where the monocycle is positioned at A, since triplet energy is high, the compound of Chemical Formula 1 is suitable as yellowish green, green, and blue phosphorescent hosts.

[0051] According to the exemplary embodiment of the present specification, A of Chemical Formula 1 is a phenyl group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing monocyclic six-membered heterocyclic group; a biphenyl group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing monocyclic six-membered heterocyclic group; or a N-containing monocyclic six-membered heterocyclic group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing monocyclic six-membered heterocyclic group. Herein, the N-containing monocyclic six-membered heterocyclic group may be a monocyclic structure having 1 to 5 nitrogen atoms and preferably 1 to 3 nitrogen atoms, for example, a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group. The alkyl group may be a C_1 to C_6 alkyl group, for example, methyl, ethyl, propyl, butyl, or the like.

[0052] According to the exemplary embodiment of the present specification, A of Chemical Formula 1 is a phenyl

group unsubstituted or substituted by an alkyl group; or a biphenyl group unsubstituted or substituted by an alkyl group.

[0053] According to the exemplary embodiment of the present specification, L_1 of Chemical Formula 1 is substituted or unsubstituted phenylene; or a substituted or unsubstituted divalent monocyclic heterocyclic group including one or more of N, O, and S atoms. In the case where the polycycle is positioned at a position L_1 , synthesis is not easy and a molecular weight is excessively increased, and thus a deposition temperature is excessively high, and in this case, processability is not good. In the case where the monocycle is positioned at L_1 , since triplet energy is high, the compound of Chemical Formula 1 is suitable as yellowish green, green, and blue phosphorescent hosts.

[0054] According to the exemplary embodiment of the present specification, L_1 of Chemical Formula 1 is substituted or unsubstituted phenylene; or a substituted or unsubstituted divalent monocyclic heterocyclic group including N.

[0055] According to the exemplary embodiment of the present specification, L_1 of Chemical Formula 1 is phenylene unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, an aryl group, or a heterocyclic group; or a divalent monocyclic N-containing heterocyclic group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, an aryl group, or a heterocyclic group.

[0056] According to the exemplary embodiment of the present specification, L_1 of Chemical Formula 1 is phenylene unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, a phenyl group, or a N-containing heterocyclic group; or a divalent N-containing monocyclic heterocyclic group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, a phenyl group, or a N-containing heterocyclic group.

[0057] According to the exemplary embodiment of the present specification, L_1 of Chemical Formula 1 is phenylene unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, a phenyl group, or a N-containing monocyclic heterocyclic group; or a divalent N-containing monocyclic heterocyclic group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, a phenyl group, or a N-containing monocyclic heterocyclic group. Herein, the N-containing monocyclic heterocyclic group may be a monocyclic structure having 1 to 5 nitrogen atoms and preferably 1 to 3 nitrogen atoms, for example, a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group. The alkyl group may be a C_1 to C_6 alkyl group, for example, methyl, ethyl, propyl, butyl, or the like.

[0058] According to the exemplary embodiment of the present specification, L_1 of Chemical Formula 1 does not include a carbazole structure.

[0059] According to the exemplary embodiment of the present specification, L_2 of Chemical Formula 1 is a substituted or unsubstituted arylene group; or a substituted or unsubstituted divalent heterocyclic group including one or more of N, O, and S atoms.


[0060] According to the exemplary embodiment of the present specification, L_2 of Chemical Formula 1 is a substituted or unsubstituted monocyclic arylene group; or a substituted or unsubstituted divalent monocyclic heterocyclic group including one or more of N, O, and S atoms.

[0061] According to the exemplary embodiment of the present specification, L_2 of Chemical Formula 1 is a substi-

tuted or unsubstituted monocyclic arylene group; or a substituted or unsubstituted divalent monocyclic N-containing heterocyclic group.

[0062] According to the exemplary embodiment of the present specification, Chemical Formula 1 may be represented by the following Chemical Formula 3.

[Chemical Formula 3]



[0063] In Chemical Formula 3,

[0064] Z_1 to Z_5 are the same as or different from each other, and are each independently CR_5 or N, herein, R_5 is the same as definitions of R_1 to R_4 , in the case where at least two of Z_1 to Z_5 are CR_5 , R_5 s are the same as or different from each other,

[0065] Y_{11} to Y_{15} and Y_{21} to Y_{25} are the same as or different from each other, and are each independently CR_6 or N, herein, R_6 is the same as definitions of R_1 to R_4 , in the case where at least two of Y_{11} to Y_{15} and Y_{21} to Y_{25} are CR_6 , R_6 s are the same as or different from each other, but one of Y_{11} to Y_{15} and one of Y_{21} to Y_{25} are carbon atoms bonded to an adjacent carbazole group, and


[0066] a residual substituent group is the same as the matter defined in Chemical Formula 1.

[0067] According to the exemplary embodiment of the present specification, L_1 and L_2 of Chemical Formula 1 are the same as or different from each other, and are each independently a phenyl group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, or an aryl group; or a monocyclic N-containing heterocyclic group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, or an aryl group.

[0068] According to the exemplary embodiment of the present specification, L_1 and L_2 of Chemical Formula 1 are the same as or different from each other, and are each independently a phenyl group unsubstituted or substituted by a fluorine group, a nitrile group, an alkyl group, or a phenyl group; or a monocyclic N-containing heterocyclic group unsubstituted or substituted by a fluorine group, a nitrile group, an alkyl group, or a phenyl group. Herein, the N-containing heterocyclic group may be a monocyclic structure having 1 to 5 nitrogen atoms and preferably 1 to 3 nitrogen atoms, for example, a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group. The alkyl group may be a C_1 to C_6 alkyl group, for example, methyl, ethyl, propyl, butyl, or the like.

[0069] According to the exemplary embodiment of the present specification, L_1 and L_2 of Chemical Formula 1 are the same as or different from each other, and are each independently a phenyl group unsubstituted or substituted by a fluorine group, a nitrile group, or an alkyl group.

[0070] According to the exemplary embodiment of the present specification, in Chemical Formula 1, L_1 and L_2 may be each represented as below.




[0071] R_6 is hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthioxy group; a substituted or unsubstituted arylthioxy group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted alkylamine group; a substituted or unsubstituted aralkylamine group; a substituted or unsubstituted arylamine group; a substituted or unsubstituted heteroarylamine group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted aryl group; a substituted or unsubstituted fluorenyl group; or a substituted or unsubstituted aromatic or aliphatic heterocyclic group including one or more of N, O, and S atoms,


[0072] f is an integer of 0 to 4, and in the case where f is 2 or more, R_6 s are the same as or different from each other.

[0073] According to one exemplary embodiment of the present specification, in the aforementioned Structural Formulas, R_6 is a halogen group, a nitrile group, an alkyl group, or an aryl group.

[0074] In Chemical Formulas 1 to 3, the Structural Formula



may be selected from the following Structural Formulas.



[0075] According to the exemplary embodiment of the present specification, Ar_1 and Ar_2 are the same as or different from each other, and are a substituted or unsubstituted aryl group; or a substituted or unsubstituted heterocyclic group including one or more of N, O, and S atoms. However, Ar_1 and Ar_2 do not include a carbazole structure. In the case where carbazole is positioned at positions Ar_1 or Ar_2 , synthesis is not easy.

[0076] According to the exemplary embodiment of the present specification, Ar_1 and Ar_2 are the same as or different


from each other, and are each independently an aryl group unsubstituted or substituted by an alkyl group, an aryl group, or a N-containing heterocyclic group; or a substituted or unsubstituted heterocyclic group unsubstituted or substituted by an alkyl group, an aryl group, or a N-containing heterocyclic group and including one or more of N, O, and S atoms. Herein, the N-containing heterocyclic group may be a monocyclic structure having 1 to 5 nitrogen atoms and preferably 1 to 3 nitrogen atoms, for example, a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group. The alkyl group may be a C_1 to C_6 alkyl group, for example, methyl, ethyl, propyl, butyl, or the like.

[0077] According to the exemplary embodiment of the present specification, Ar_1 and Ar_2 are the same as or different from each other, and are each independently a phenyl group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing heterocyclic group; a fluorenyl group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing heterocyclic group; or a N-containing heterocyclic group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing heterocyclic group. Herein, the N-containing heterocyclic group may be a monocyclic structure having 1 to 5 nitrogen atoms and preferably 1 to 3 nitrogen atoms, for example, a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group. The alkyl group may be a C_1 to C_6 alkyl group, for example, methyl, ethyl, propyl, butyl, or the like.

[0078] According to the exemplary embodiment of the present specification, Ar_1 and Ar_2 are the same as or different from each other, and are each independently a phenyl group unsubstituted or substituted by an alkyl group or a phenyl group; or a N-containing monocyclic heterocyclic group unsubstituted or substituted by an alkyl group or a phenyl group. Herein, the N-containing monocyclic heterocyclic group may be a pyridine group, a pyrimidine group, a pyridazine group, a pyrazine group, or a triazine group. The alkyl group may be a C_1 to C_6 alkyl group, for example, methyl, ethyl, propyl, butyl, or the like.

[0079] According to the exemplary embodiment of the present specification, Chemical Formula 1 may be represented by the following Chemical Formula 4.

[Chemical Formula 4]



[0080] In Chemical Formula 4,

[0081] Z_1 to Z_5 are the same as or different from each other, and are each independently CR₅ or N, herein, R₅ is the same as definitions of R₁ to R₄, in the case where at least two of Z_1 to Z_5 are CR₅, R₅s are the same as or different from each other,


[0082] Y_{11} to Y_{15} and Y_{21} to Y_{25} are the same as or different from each other, and are each independently CR₆ or N, herein, R₆ is the same as definitions of R₁ to R₄, in the case where at least two of Y_{11} to Y_{15} and Y_{21} to Y_{25} are CR₆, R₆s are the same as or different from each other, but one of Y_{11} to Y_{15} and one of Y_{21} to Y_{25} are carbon atoms bonded to an adjacent carbazole group,

[0083] X_{11} to X_{15} and X_{21} to X_{25} are the same as or different from each other, and each independently CR₇ or N, herein, R₇ is the same as definitions of R₁ to R₄, in the case where at least two of X_{11} to X_{15} and X_{21} to X_{25} are CR₇, R₇s are the same as or different from each other, and


[0084] a residual substituent group is the same as a matter defined in Chemical Formula 1.

[0085] According to the exemplary embodiment of the present specification, R₁ to R₄ of Chemical Formula 1 are hydrogen.


[0086] According to the exemplary embodiment of the present specification, the compound of Chemical Formula 1 may be represented by the following Structural Formulas.



Chemical Formula 1-1




Chemical Formula 1-2




Chemical Formula 1-3

-continued


Chemical Formula 1-4



Chemical Formula 1-5




Chemical Formula 1-6




-continued


Chemical Formula 1-7



Chemical Formula 1-8




Chemical Formula 1-9




-continued


Chemical Formula 1-10







Chemical Formula 1-11



Chemical Formula 1-12




-continued




-continued


Chemical Formula 1-17



Chemical Formula 1-18




Chemical Formula 1-19




-continued


Chemical Formula 1-20



Chemical Formula 1-21




Chemical Formula 1-22




-continued


Chemical Formula 1-23



Chemical Formula 1-24




Chemical Formula 1-25




-continued


Chemical Formula 1-26



Chemical Formula 1-27




Chemical Formula 1-28




-continued


Chemical Formula 1-29



Chemical Formula 1-30




Chemical Formula 1-31




-continued


Chemical Formula 1-32






Chemical Formula 1-33



Chemical Formula 1-34




-continued




-continued


Chemical Formula 1-38



Chemical Formula 1-39




Chemical Formula 1-40




-continued


Chemical Formula 1-41






Chemical Formula 1-42



Chemical Formula 1-43




-continued




-continued


Chemical Formula 1-47






Chemical Formula 1-48



Chemical Formula 1-49




-continued




-continued


Chemical Formula 1-53



Chemical Formula 1-54




Chemical Formula 1-55




-continued


Chemical Formula 1-56



Chemical Formula 1-57




Chemical Formula 1-58




-continued


Chemical Formula 1-59



Chemical Formula 1-60




Chemical Formula 1-61




-continued


Chemical Formula 1-62



Chemical Formula 1-63




Chemical Formula 1-64




-continued


Chemical Formula 1-65



Chemical Formula 1-66




Chemical Formula 1-67




-continued

Chemical Formula 1-68




Chemical Formula 1-69




-continued

Chemical Formula 1-70




Chemical Formula 1-71




-continued

Chemical Formula 1-72




Chemical Formula 1-73




-continued

Chemical Formula 1-74




Chemical Formula 1-75




-continued

Chemical Formula 1-76




Chemical Formula 1-77




-continued

Chemical Formula 1-78




Chemical Formula 1-79




-continued

Chemical Formula 1-80




Chemical Formula 1-81




-continued

Chemical Formula 1-82




Chemical Formula 1-83




-continued

Chemical Formula 1-84




Chemical Formula 1-85




-continued

Chemical Formula 1-86




Chemical Formula 1-87




-continued

Chemical Formula 1-88




Chemical Formula 1-89




-continued

Chemical Formula 1-90




Chemical Formula 1-91




-continued

Chemical Formula 1-92




Chemical Formula 1-93




-continued

Chemical Formula 1-94




Chemical Formula 1-95




-continued

Chemical Formula 1-96




Chemical Formula 1-97




-continued

Chemical Formula 1-98




Chemical Formula 1-99




-continued

Chemical Formula 1-100




Chemical Formula 1-101




-continued

Chemical Formula 1-102




Chemical Formula 1-103




-continued

Chemical Formula 1-104




Chemical Formula 1-105




-continued

Chemical Formula 1-106




Chemical Formula 1-107




-continued

Chemical Formula 1-108




Chemical Formula 1-109




-continued

Chemical Formula 1-110




Chemical Formula 1-111




-continued

Chemical Formula 1-112




Chemical Formula 1-113




-continued

Chemical Formula 1-114




Chemical Formula 1-115




-continued

Chemical Formula 1-116




Chemical Formula 1-117




-continued

Chemical Formula 1-118




Chemical Formula 1-119




-continued

Chemical Formula 1-120




Chemical Formula 1-121




-continued

Chemical Formula 1-122




Chemical Formula 1-123




-continued

Chemical Formula 1-124




Chemical Formula 1-125




-continued

Chemical Formula 1-126




Chemical Formula 1-127




-continued

Chemical Formula 1-128




Chemical Formula 1-129




-continued

Chemical Formula 1-130




Chemical Formula 1-131




-continued

Chemical Formula 1-132




Chemical Formula 1-133




-continued

Chemical Formula 1-134




Chemical Formula 1-135




-continued

Chemical Formula 1-136




Chemical Formula 1-137




-continued

Chemical Formula 1-138




Chemical Formula 1-139




-continued

Chemical Formula 1-140




Chemical Formula 1-141




-continued

Chemical Formula 1-142




Chemical Formula 1-143




-continued

Chemical Formula 1-144




Chemical Formula 1-145




-continued

Chemical Formula 1-146




Chemical Formula 1-147




-continued

Chemical Formula 1-148




Chemical Formula 1-149




-continued

Chemical Formula 1-150




Chemical Formula 1-151




-continued

Chemical Formula 1-152




Chemical Formula 1-153




-continued

Chemical Formula 1-154




Chemical Formula 1-155




-continued

Chemical Formula 1-156




Chemical Formula 1-157




-continued

Chemical Formula 1-158




Chemical Formula 1-159




-continued

Chemical Formula 1-160




Chemical Formula 1-161




-continued

Chemical Formula 1-162




Chemical Formula 1-163




-continued

Chemical Formula 1-164




Chemical Formula 1-165




-continued

Chemical Formula 1-166




Chemical Formula 1-167




-continued

Chemical Formula 1-168




Chemical Formula 1-169




-continued

Chemical Formula 1-170




Chemical Formula 1-171




-continued

Chemical Formula 1-172




Chemical Formula 1-173




-continued

Chemical Formula 1-174




Chemical Formula 1-175




-continued

Chemical Formula 1-176




Chemical Formula 1-177




-continued

Chemical Formula 1-178




Chemical Formula 1-179




-continued

Chemical Formula 1-182




Chemical Formula 1-183




-continued

Chemical Formula 1-184




Chemical Formula 1-185




-continued

Chemical Formula 1-186




Chemical Formula 1-187




-continued

Chemical Formula 1-188




Chemical Formula 1-189




-continued

Chemical Formula 1-190




Chemical Formula 1-191




-continued

Chemical Formula 1-192




Chemical Formula 1-193




-continued

Chemical Formula 1-194




Chemical Formula 1-195




-continued

Chemical Formula 1-196




Chemical Formula 1-197




-continued

Chemical Formula 1-198




Chemical Formula 1-199




-continued

Chemical Formula 1-200




Chemical Formula 1-201




-continued

Chemical Formula 1-202




Chemical Formula 1-203




-continued

Chemical Formula 1-204




Chemical Formula 1-205




-continued




Chemical Formula 1-206



Chemical Formula 1-207




-continued




-continued


Chemical Formula 1-211



Chemical Formula 1-212




Chemical Formula 1-213




-continued


Chemical Formula 1-214



Chemical Formula 1-215




Chemical Formula 1-216




-continued


Chemical Formula 1-217






Chemical Formula 1-218



Chemical Formula 1-219




-continued




-continued

Chemical Formula 1-223




Chemical Formula 1-224




-continued


Chemical Formula 1-225



Chemical Formula 1-226




Chemical Formula 1-227




-continued


Chemical Formula 1-228



Chemical Formula 1-229




Chemical Formula 1-230




-continued


Chemical Formula 1-231




Chemical Formula 1-232




Chemical Formula 1-233



-continued




[0087] The compounds represented by Chemical Formula 1 may be manufactured based on Preparation Examples as will be described later. According to the exemplary embodiment, the compounds may be manufactured by a method such as the following Reaction Formula 1 or Reaction Formula 2.



-continued

[Reaction Formula 2]



[0088] In Reaction Formula 1, definitions of substituent groups are the same as matters defined in Chemical Formula 1, and X_4 and X_5 are a halogen atom (Br or Cl).

[0089] Further, the present specification provides an organic light emitting device including the compound represented by Chemical Formula 1.

[0090] In the exemplary embodiment of the present specification, there is provided an organic light emitting device including: a first electrode; a second electrode provided to face the first electrode; and one or more organic material layers provided between the first electrode and the second electrode, in which one or more of the organic material layers include the compound of Chemical Formula 1.







[0091] The organic material layer of the organic light emitting device of the present specification may have a single layer structure, or a multilayered structure in which two or more organic material layers are laminated. For example, the organic light emitting device of the present invention may have a structure including a hole injection layer, a hole transport layer, a light emitting layer, an electron transport layer, an electron injection layer, and the like as the organic material layer. However, the structure of the organic light emitting device is not limited thereto, but may include a smaller number of organic layers.











[0092] In the exemplary embodiment of the present specification, the organic material layer includes the hole injection layer or the hole transport layer, and the hole injection layer or the hole transport layer includes the compound of Chemical Formula 1.

[0093] In another exemplary embodiment, the organic material layer includes the light emitting layer, and the light emitting layer includes the compound of Chemical Formula 1. Specifically, the compound of Chemical Formula 1 may be included as a host of a phosphorescent light emitting layer. In the present specification, the phosphorescent light emitting layer may further include a phosphorescent material. It is preferable that the phosphorescent material include a metal complex and the metal complex have a metal atom selected from Ir, Pt, Os, Au, Cu, Re, and Ru and a ligand.






[0094] Preferable specific examples of the metal complex will be described below.

-continued












-continued



-continued





[0095] In the exemplary embodiment of the present specification, the organic material layer includes the electron transport layer or the electron injection layer, and the electron transport layer or the electron injection layer includes the compound of Chemical Formula 1.

[0096] In the exemplary embodiment of the present specification, the electron transport layer, the electron injection layer, or a layer simultaneously performing electron transporting and electron injection includes the compound of Chemical Formula 1.

[0097] In another exemplary embodiment, the organic material layer includes the light emitting layer and the electron transport layer, and the electron transport layer includes the compound of Chemical Formula 1.

[0098] In the exemplary embodiment of the present specification, the organic material layer further includes the hole injection layer or the hole transport layer including a compound including an arylamino group, a carbazole group, or a benzocarbazole group in addition to the organic material layer including the compound of Chemical Formula 1.

[0099] In the exemplary embodiment of the present specification, the organic material layer including the compound of Chemical Formula 1 includes the compound of Chemical Formula 1 as a host, and includes another organic compound, a metal, or a metal compound as a dopant.

[0100] In another exemplary embodiment, the organic light emitting device may be an organic light emitting device having a structure (normal type) where an anode, one or more organic material layers, and a cathode are sequentially laminated on a substrate.

[0101] In another exemplary embodiment, the organic light emitting device may be an organic light emitting device having an inverted direction structure (inverted type) where the cathode, one or more organic material layers, and the anode are sequentially laminated on the substrate.

[0102] For example, the structure of the organic light emitting device according to the exemplary embodiment of the present specification is illustrated in FIGS. 1 and 2.

[0103] FIG. 1 illustrates an example of an organic light emitting device including a substrate 1, an anode 2, a light emitting layer 3, and a cathode 4. In the aforementioned structure, the compound may be included in the light emitting layer.

[0104] FIG. 2 illustrates an example of an organic light emitting device including a substrate 1, an anode 2, a hole injection layer 5, a hole transport layer 6, a light emitting layer 7, an electron transport layer 8, and a cathode 4. In the aforementioned structure, the compound may be included in one or more layers of the hole injection layer, the hole transport layer, the light emitting layer, and the electron transport layer.

[0105] The organic light emitting device of the present specification may be manufactured by materials and methods known in the art, except that one or more of organic material

layers include the compound of the present specification, that is, the compound of Chemical Formula 1.

[0106] In the case where the organic light emitting device includes a plurality of organic material layers, the organic material layers may be formed of the same material or different materials.

[0107] The organic light emitting device of the present specification may be manufactured by materials and methods known in the art, except that one or more of organic material layers include the compound of Chemical Formula 1, that is, the compound represented by Chemical Formula 1.

[0108] For example, the organic light emitting device of the present specification may be manufactured by sequentially laminating the first electrode, the organic material layer, and the second electrode on the substrate. In this case, the organic light emitting device may be manufactured by depositing a metal, metal oxides having conductivity, or an alloy thereof on the substrate by using a PVD (physical vapor deposition) method such as a sputtering method or an e-beam evaporation method to form the anode, forming the organic material layer including the hole injection layer, the hole transport layer, the light emitting layer, and the electron transport layer thereon, and then depositing a material that can be used as the cathode thereon. In addition to this method, the organic light emitting device may be manufactured by sequentially depositing a cathode material, the organic material layer, and an anode material on the substrate.

[0109] Further, the compound of Chemical Formula 1 may be formed as the organic material layer by a vacuum deposition method or a solution coating method when the organic light emitting device is manufactured. Herein, the solution coating method means spin coating, dip coating, doctor blading, inkjet printing, screen printing, a spray method, roll coating, or the like, but is not limited thereto.

[0110] In addition to this method, the organic light emitting device may be manufactured by sequentially depositing a cathode material, an organic material layer, and an anode material on a substrate (International Patent Application Laid-Open No. WO 2003/012890). However, the manufacturing method is not limited thereto.

[0111] In the exemplary embodiment of the present specification, the first electrode is the anode, and the second electrode is the cathode.

[0112] In another exemplary embodiment, the first electrode is the cathode, and the second electrode is the anode.

[0113] It is preferable that the anode material be, in general, a material having a large work function so as to smoothly inject holes into the organic material layer. Specific examples of the anode material that may be used in the present invention include metals such as vanadium, chrome, copper, zinc, and gold, or an alloy thereof; metal oxides such as zinc oxides, indium oxides, indium tin oxides (ITO), and indium zinc oxides (IZO); a combination of metals and oxides, such as ZnO:Al or SnO₂:Sb; conductive polymers such as poly(3-methylthiophene), poly[3,4-(ethylene-1,2-dioxy)thiophene] (PEDOT), polypyrrole, and polyaniline, and the like, but are not limited thereto.

[0114] It is preferable that the cathode material be, in general, a material having a small work function so as to easily inject electrons into the organic material layer. Specific examples of the cathode material include metals such as magnesium, calcium, sodium, potassium, titanium, indium, yttrium, lithium, gadolinium, aluminum, silver, tin, and lead,

or an alloy thereof; a multilayered structure material such as LiF/Al or LiO₂/Al, and the like, but are not limited thereto.

[0115] The hole injection material is a layer injecting the holes from the electrode, and it is preferable that the hole injection material be a compound which has an ability of transporting the holes to have a hole injection effect in the anode and an excellent hole injection effect to the light emitting layer or the light emitting material, prevents movement of an exciton generated in the light emitting layer to the electron injection layer or the electron injection material, and has an excellent thin film forming ability. It is preferable that a HOMO (highest occupied molecular orbital) of the hole injection material be between the work function of the anode material and a HOMO of a peripheral organic material layer. Specific examples of the hole injection material include metal porphyrine, oligothiophene, an arylamine-based organic material, a hexanitrihexaazatriphenylene-based organic material, a quinacridone-based organic material, a perylene-based organic material, anthraquinone, polyaniline, a polythiophene-based conductive polymer, and the like, but are not limited thereto.

[0116] The hole transport layer is a layer receiving the holes from the hole injection layer and transporting the holes to the light emitting layer, and the hole transport material is a material that can receive the holes from the anode or the hole injection layer and transport the holes to the light emitting layer, and a material having large mobility to the holes is suitable. Specific examples thereof include an arylamine-based organic material, a conductive polymer, a block copolymer in which a conjugate portion and a non-conjugate portion are present together, and the like, but are not limited thereto.

[0117] The light emitting material is a material that can receive the holes and the electrons from the hole transport layer and the electron transport layer, respectively, and bond the holes and the electrons to emit light in a visible ray region, and is preferably a material having good quantum efficiency to fluorescence or phosphorescence. Specific examples thereof include a 8-hydroxy-quinoline aluminum complex (Alq₃); a carbazole-based compound; a dimerized styryl compound; BAq; a 10-hydroxybenzoquinoline-metal compound; benzoxazole, benzthiazole, and benzimidazole-based compounds; a poly(p-phenylenevinylene) (PPV)-based polymer; a spiro compound; polyfluorene, lubrene, and the like, but are not limited thereto.

[0118] The light emitting layer may include a host material and a dopant material. Examples of the host material include a condensation aromatic cycle derivative, a heterocycle-containing compound, or the like. Specific examples of the compensation aromatic cycle derivative include an anthracene derivative, a pyrene derivative, a naphthalene derivative, a pentacene derivative, a phenanthrene compound, a fluoranthene compound, and the like, and specific examples of the heterocycle-containing compound include a carbazole derivative, a dibenzofuran derivative, a ladder-type furan compound, a pyrimidine derivative, and the like, but the examples are not limited thereto.

[0119] Examples of the dopant material include an aromatic amine derivative, a styrylamine compound, a boron complex, a fluoranthene compound, a metal complex, and the like. Specifically, the aromatic amine derivative is a compensation aromatic cycle derivative having a substituted or unsubstituted arylamino group, examples thereof include pyrene, anthracene, chrysene, and perflanthene having the

arylamino group, and the like, the styrylamine compound is a compound where at least one arylvinyl group is substituted in substituted or unsubstituted arylamine, and in the styrylamine compound, one or two or more substituent groups selected from the group consisting of an aryl group, a silyl group, an alkyl group, a cycloalkyl group, and an arylamino group are substituted or unsubstituted. Specific examples thereof include styrylamine, styryldiamine, styryltriamine, styryltetramine, and the like, but are not limited thereto. Further, examples of the metal complex include an iridium complex, a platinum complex, and the like, but are not limited thereto.

[0120] The electron transport material is a layer receiving the electrons from the electron injection layer and transporting the electrons to the light emitting layer, the electron transport material is a material that can receive the electrons well from the cathode and transport the electrons to the light emitting layer, and a material having large mobility to the electrons is suitable. Specific examples thereof include an 8-hydroxyquinoline Al complex; a complex including Alq₃; an organic radical compound; a hydroxyflavone-metal complex, and the like, but are not limited thereto. The electron transport layer may be used together with a predetermined desired cathode material as used according to the related art. Particularly, an example of an appropriate cathode material is a general material having the low work function and followed by an aluminum layer or a silver layer. Specific examples thereof include cesium, barium, calcium, ytterbium, and samarium, and each case is followed by the aluminum layer or the silver layer.

[0121] The electron injection layer is a layer injecting the electrons from the electrode, and a compound which has an ability of transporting the electrons, an electron injection effect from the cathode, and an excellent electron injection effect to the light emitting layer or the light emitting material, prevents movement of an exciton generated in the light emitting layer to the hole injection layer, and has an excellent thin film forming ability is preferable. Specific examples thereof include fluorenone, anthraquinodimethane, diphenylquinone, thiopyran dioxide, oxazole, oxadiazole, triazole, imidazole, perylene tetracarboxylic acid, fluorenylidene methane, anthrone, and the like, and derivatives thereof, a metal complex compound, a nitrogen-containing 5-membered cycle derivative, and the like, but are not limited thereto.

[0122] Examples of the metal complex compound include 8-hydroxyquinolinato lithium, bis(8-hydroxyquinolinato) zinc, bis(8-hydroxyquinolinato)copper, bis(8-hydroxyquinolinato)manganese, tris(8-hydroxyquinolinato)aluminum, tris(2-methyl-8-hydroxyquinolinato)aluminum, tris(8-hydroxyquinolinato)gallium, bis(10-hydroxybenzo[h]quinolinato)beryllium, bis(10-hydroxybenzo[h]quinolinato)zinc, bis(2-methyl-8-quinolinato)chlorogallium, bis(2-methyl-8-quinolinato)(o-cresolato)gallium, bis(2-methyl-8-quinolinato)(1-naphtholato)aluminum, bis(2-methyl-8-quinolinato)(2-naphtholato)gallium, and the like, but are not limited thereto.

[0123] The organic light emitting device according to the present specification may be a top emission type, a bottom emission type, or a both-sided emission type according to the used material.

[0124] In the exemplary embodiment of the present specification, the compound of Chemical Formula 1 may be included in an organic solar cell or an organic transistor in addition to the organic light emitting device.


[0125] Manufacturing of the compound represented by Chemical Formula 1 and the organic light emitting device including the same will be described in detail in the following Examples. However, the following Examples are set forth to illustrate the present specification, but the scope of the present specification is not limited thereto.

EXAMPLE

Preparation Example 1







Preparation of Chemical Formula P1

[0126]









[0127] 2-bromocarbazole (10.0 g, 40.6 mmol), 2,4-diphenyl-6-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolane-2-yl)phenyl)-1,3,5-triazine (18.1 g, 41.5 mmol), and potassium carbonate (17.0 g, 123 mmol) were suspended in the mixture of tetrahydrofuran (100 mL) and water (50 mL). After nitrogen was charged, tetrakis(triphenylphosphine)palladium (0.9 g, 0.7 mmol) was applied to the suspension solution. Under nitrogen, the mixture was agitated in the reflux for about 12 hours. After the temperature was lowered to room temperature, the generated solid was filtered. The light yellow solid was precipitated in chloroform, agitated, filtered, and dried to obtain white solid P1 (17.8 g, 92%).







[0128] Compounds P2 to P40 were prepared according to the method of manufacturing compound P1 of Preparation Example 1. The structure, the shape, the yield, and MS thereof are arranged in the following Table.

Preparation Example	Intermediate 1	Intermediate 2	Compound (Px)	Yield (%)	MS [M+H]
Example 2 (P2)				82	474
Example 3 (P3)				90	474







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (P#)	Shape	Yield (%)	MS [M + H]
Preparation Example 4 (P4)				White solid	95	475
Preparation Example 5 (P5)				White solid	93	474







-continued-

Preparation Example	Intermediate 1	Intermediate 2	Compound (Px)	Yield (%)	Shape	MS [M + H]
Example 6 (P6)				88	White solid	474
Example 7 (P7)				85	White solid	476







-continued-

Preparation Example	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Example 8 (P8)				White solid	84	476
Example 9 (P9)				White solid	87	476







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (P#)	Shape	Yield (%)	MS [M + H]
Preparation Example 10 (P10)				White solid	73	500
Preparation Example 11 (P11)				White solid	55	493







-continued-

Preparation Example	Intermediate 1	Intermediate 2	Compound (Px)	Yield (%)	Shape	MS [M + H]
Example 12 (P12)				67	White solid	475
Example 13 (P13)				78	White solid	474







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (P#)	Shape	Yield (%)	MS [M + H]
Preparation Example 14 (P14)				White solid	81	474
Preparation Example 15 (P15)				White solid	88	475







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (P#)	Yield (%)	Shape	MS [M + H]
Example 16 (P16)				91	White solid	474
Example 17 (P17)				95	White solid	474







-continued-

Preparation Example	Intermediate 1	Intermediate 2	Compound (Px)	Yield (%)	Shape	MS [M + H]
Example 18 (P18)				89	White solid	476
Example 19 (P19)				77	White solid	476







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 20 (P20)				White solid	75	476
Preparation Example 21 (P21)				White solid	59	500







-continued-

Preparation Example (Pxx)	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 22 (P22)				White solid	61	493
Preparation Example 23 (P23)				White solid	81	475







-continued-

Preparation Example	Intermediate 1	Intermediate 2	Compound (Px)	Yield (%)	MS [M + H]
Example 24 (P24)				91	474
Example 25 (P25)				90	474







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (Px)	Yield (%)	Shape	MS [M + H]
Preparation Example 26 (P26)				95	White solid	475
Preparation Example 27 (P27)				90	White solid	474







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 28 (P28)				White solid	88	474
Preparation Example 29 (P29)				White solid	77	476







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 30 (P30)				White solid	74	476
Preparation Example 31 (P31)				White solid	89	476







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 32 (P32)				White solid	70	500
Preparation Example 33 (P33)				White solid	59	493







-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 34 (P34)				White solid	60	550
Preparation Example 35 (P35)				White solid	78	550




-continued-

	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 36 (P36)				White solid	56	591
Preparation Example 37 (P37)				White solid	50	503

-continued-

Preparation Example (P#)	Intermediate 1	Intermediate 2	Compound (P#)	Shape	Yield (%)	MS [M + H]
Preparation Example 38 (P38)				White solid	41	477
Preparation Example 39 (P39)				White solid	80	475



-continued

	Intermediate 1	Intermediate 2	Compound (Px)	Shape	Yield (%)	MS [M + H]
Preparation Example 40 (P40)				White solid	41	477


Preparation Example 41

Preparation of Chemical Formula 1-1

[0129]



-continued









[0130] Compound P1 (8.2 g, 17.2 mmol), 3-(3-chlorophenyl)-9-phenyl-9H-carbazole (6.0 g, 16.9 mmol), bis(tri-tert-butylphosphine)palladium (0.1 g, 0.2 mmol), and sodium tertiary-butoxide (2.8 g, 29.1 mmol) were mixed, and refluxed while being agitated in xylene (50 ml) under nitrogen for 6 hours. After the temperature was lowered to room temperature, the generated solid was filtered. The light yellow solid was dissolved by chloroform, magnesium sulfate and acid clay were put thereinto, followed by agitation and then filtration, and distillation was performed under a reduced pressure. Recrystallization was performed by using chloroform and ethyl acetate to obtain Chemical Formula 1-1 (8.8 g, 64%) that was the white solid compound.













[0131] The compounds of Chemical Formulas 1-2 to 1-231 were manufactured according to the method of manufacturing Chemical Formula 1-1 of Preparation Example 41. The structure, the shape, the yield, and MS thereof are arranged in the following Table.

Preparation Example	Intermediate (Px)	Chemical Formula	Yield (%)	MS	
				Shape	[M + H]
Preparation Example 42	P1		66	White solid	792







-continued

Preparation Example	Intermediate 1 (Px)	Intermediate 2	Chemical Formula	Shape	Yield (%)	MS [M + H]
Preparation Example 43 Chemical Formula 1-4	P1			Light yellow solid	81	792
Preparation Example 44 Chemical Formula 1-6	P1			Light yellow solid	79	792
Preparation Example 45 Chemical Formula 1-9	P2			White solid	56	791





-continued

Preparation Example	Chemical Formula	Intermediate 1 (Px)	Intermediate 2	Chemical Formula	Shape	Yield (%)	MS
							[M + H]
Preparation Example 46		P3			White solid	78	791
Preparation Example 47		P34			White solid	85	867
Preparation Example 48		P34			White solid	83	867
Preparation Example 49		P4			Light yellow solid	66	792







-continued

Preparation Example	Chemical Formula	Intermediate (Px)	Chemical Formula	MS		
				Yield (%)	[M + H]	
Preparation Example 50		P4		Light yellow solid	73	792
Preparation Example 51		P5		White solid	66	791
Preparation Example 52		P5		Light yellow solid	70	791





-continued

Preparation Example	Chemical Formula	Yield (%)	MS	
			Shape	[M + H]
Intermediate (Px) 2				
P6 Preparation Example 53 Chemical Formula 1-32		78	White solid	791
P7 Preparation Example 57 Chemical Formula 1-37		68	White solid	793
P7 Preparation Example 58 Chemical Formula 1-40		79	Light yellow solid	793







-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	MS		
				Yield (%)	[M + H]	
P7 Preparation Example 56 Chemical Formula 1-41		Intermediate (Px) 2		White solid	67	793
P8 Preparation Example 57 Chemical Formula 1-46		Intermediate (Px) 2		Light yellow solid	75	793
P9 Preparation Example 58 Chemical Formula 1-53		Intermediate (Px) 2		White solid	71	793





-continued

Preparation Example	Chemical Formula	Intermediate (Px)	Chemical Formula	Yield (%)	MS
					[M + H]
P10 Preparation Example 59 Chemical Formula 1-62		1		70	817
P11 Preparation Example 60 Chemical Formula 1-63		1		82	810







-continued

Preparation Example	Intermediate (Px)	Chemical Formula	Yield (%)	MS
				[M + H]
Preparation Example 61 Chemical Formula 1-69	P1 		Light yellow solid	71 868
Preparation Example 62 Chemical Formula 1-70	P12 		Light yellow solid	67 792
Preparation Example 63 Chemical Formula 1-71	P12 		White solid	61 792







-continued

Preparation Example	Intermediate (Px)	Chemical Formula	Yield (%)	MS
				[M + H]
P12 64 Chemical Formula 1-73			66	792
P12 65 Chemical Formula 1-74			71	792





-continued

Preparation Example	Chemical Formula	Intermediate (Px)	Chemical Formula	Shape	Yield (%)	MS
						[M + H]
P13 Preparation Example 66 Chemical Formula 1-76		1		Light yellow solid	50	791
P14 Preparation Example 67 Chemical Formula 1-80		1		Light yellow solid	49	791
		2				
		2				







-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	Yield (%)	MS
					[M + H]
P15 Preparation Example 68 Chemical Formula 1-92		1 (Px) 2		78	792
				Light yellow solid	
P16 Preparation Example 69 Chemical Formula 1-98				78	791
				Light yellow solid	





-continued

Preparation Example	Intermediate (Px)	Chemical Formula	Yield (%)	MS
				[M + H]
P17 Preparation Example 70 Chemical Formula 1-105			69	791
P18 Preparation Example 71 Chemical Formula 1-109			71	793





-continued

Preparation Example	Intermediate (Px)	Chemical Formula	Shape	Yield (%)	MS
					[M + H]
P19 Chemical Formula 1-105	2		Light yellow solid	61	793
P20 Chemical Formula 1-109	2		Light yellow solid	65	793
					
					
					
					





-continued

Preparation Example	Intermediate (Px)	Chemical Formula	Yield (%)	MS
				[M + H]
P37 Chemical Formula 1-124			62	820
P38 Chemical Formula 1-128			58	794





-continued

Preparation Example	Intermediate (Px)	Chemical Formula	MS		
			Yield (%)	[M + H]	
P21 Chemical Formula 1-131	2		Light yellow solid	81	817
P22 Chemical Formula 1-132	2	  	Light yellow solid	81	810



-continued

Preparation Example	Intermediate (Px)	Chemical Formula	MS		
			Yield (%)	[M + H]	
P23 Preparation Example 78 Chemical Formula 1-142			Light yellow solid	77	792
P24 Preparation Example 79 Chemical Formula 1-147			White solid	71	791





-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	Yield (%)	MS	
					[M + H]	
80	1-150	P25			66 White solid	791
81	1-152	P35			75 White solid	867





-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	Yield (%)	MS
					[M + H]
P26 82 1-160		1	2	89	792
P27 83 1-165		1	2	60	791





-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	Yield (%)	MS		
					[M + H]		
84	1-173	P28			Light yellow solid	78	791
85	1-178	P29			Light yellow solid	69	793





-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	Yield (%)	MS [M + H]
P30 86		1		65	793
P31 87		1		78	793





-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	Yield (%)	MS
					[M + H]
P32 88 1-200		2		81	817 Light yellow solid
P33 89 1-201				77	810 Light yellow solid





-continued

Preparation Example	Intermediate (Px)	Chemical Formula	MS		
			Yield (%)	[M + H]	
P36 Preparation Example 90 Chemical Formula 1-211			Light yellow solid	71	908
P36 Preparation Example 91 Chemical Formula 1-214			Light yellow solid	71	908

-continued

Preparation Example	Chemical Formula	Intermediate	Chemical Formula	Yield (%)	MS
					[M + H]
P1 Preparation Example 92 Chemical Formula 1-219		1 (Px) 2		69 White solid	716
P40 Preparation Example 93 Chemical Formula 1-221		P40		75 Light yellow solid	716

-continued

Preparation Example	Intermediate 1 (Px)	Intermediate 2	Chemical Formula	Shape	Yield (%)	MS
						[M + H]
Preparation Example 94 Chemical Formula 1-227	P40			yellow solid	55	640
Preparation Example 95 Chemical Formula 1-231	P1			White solid	55	793


[0132] FIGS. 3 to 16 illustrate data for confirming synthesis of main compounds.

Experimental Example 1


[0133] The glass substrate on which a thin film of ITO (indium tin oxide) was applied in a thickness of 1,500 Å was put into distilled water having the detergent dissolved therein and washed by the ultrasonic wave. In this case, the used detergent was a product commercially available from Fisher Co. and the distilled water was one which had been twice filtered by using a filter commercially available from Milli-

pore Co. The ITO was washed for 30 minutes, and washing with ultrasonic waves was then repeated twice for 10 minutes by using distilled water. After the washing with distilled water was finished, washing with ultrasonic waves was performed by solvents such as isopropyl alcohol, acetone, and methanol, and the ITO was dried and transported to the plasma washing machine. Further, the substrate was washed by using oxygen plasma for 5 minutes, and then transported to the vacuum deposition machine.

[0134] Hexanitride hexaazatriphenylene (HAT) of the following Chemical Formula was thermally deposited under vacuum in a thicknesses of 500 Å on the ITO transparent electrode thus prepared to form the hole injection layer.



[0135] The NPB (N,N-bis-(1-naphthalenyl)-N,N-bis-phenyl-(1,1-biphenyl)-4,4-diamine) compound having the following structure was thermally deposited under vacuum in a thickness of 400 Å on the hole injection layer to form the hole transport layer.




[0136] Subsequently, the compound of Chemical Formula 1-1 manufactured in Preparation Example 41 was deposited under vacuum in a film thickness of 300 Å with the Ir(ppy)₃ dopant at a concentration of 10% on the hole transport layer to form the light emitting layer.

[0137] The following electron transport material was deposited under vacuum in a thickness of 200 Å on the light emitting layer to form the electron injection and transport layer.

[Electron Transport Material]

[0138]



[0139] Lithium fluoride (LiF) in a thickness of 12 Å and aluminum in a thickness of 2,000 Å were subsequently deposited on the electron injection and transport layer to form the cathode.

[0140] In the aforementioned process, the deposition speed of the organic material was maintained at 0.4 to 0.7 Å/sec, the deposition speed of the lithium fluoride of the cathode was maintained at 0.3 Å/sec, the deposition speed of aluminum was maintained at 2 Å/sec, and the degree of vacuum during the deposition was maintained at 2×10^{-7} to 5×10^{-8} torr.

Experimental Example 2

[0141] The same experiment was performed, except that the compound of Chemical Formula 1-2 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 3

[0142] The same experiment was performed, except that the compound of Chemical Formula 1-4 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 4

[0143] The same experiment was performed, except that the compound of Chemical Formula 1-23 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 5

[0144] The same experiment was performed, except that the compound of Chemical Formula 1-29 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 6

[0145] The same experiment was performed, except that the compound of Chemical Formula 1-40 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 7

[0146] The same experiment was performed, except that the compound of Chemical Formula 1-62 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 8

[0147] The same experiment was performed, except that the compound of Chemical Formula 1-74 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 9

[0148] The same experiment was performed, except that the compound of Chemical Formula 1-98 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 10

[0149] The same experiment was performed, except that the compound of Chemical Formula 1-109 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 11

[0150] The same experiment was performed, except that the compound of Chemical Formula 1-142 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 12

[0151] The same experiment was performed, except that the compound of Chemical Formula 1-152 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 13

[0152] The same experiment was performed, except that the compound of Chemical Formula 1-200 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 14

[0153] The same experiment was performed, except that the compound of Chemical Formula 1-211 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Experimental Example 15

[0154] The same experiment was performed, except that the compound of Chemical Formula 1-219 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.


Experimental Example 16

[0155] The same experiment was performed, except that the compound of Chemical Formula 1-231 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

Comparative Example 1

[0156] The same experiment was performed, except that the following H1 was used instead of the compound of Chemical Formula 1-1 in Experimental Example 1.

H1



[0157] In Experimental Examples 1 to 16 and Comparative Example 1, results of the devices manufactured by using each compound as the light emitting layer are described in Table 1.

TABLE 1

No.	Host	Dopant	Doping concentration (%)	Driving voltage (V) @5,000 cd/m ²	Light emitting efficiency (Cd/A)
Comparative Example 1	H1	Ir(ppy) ₃	10	5.2	36
Experimental Example 1	Chemical Formula 1-1	Ir(ppy) ₃	10	4.7	40
Experimental Example 2	Chemical Formula 1-2	Ir(ppy) ₃	10	4.9	45
Experimental Example 3	Chemical Formula 1-4	Ir(ppy) ₃	10	4.5	44
Experimental Example 4	Chemical Formula 1-23	Ir(ppy) ₃	10	4.4	43
Experimental Example 5	Chemical Formula 1-29	Ir(ppy) ₃	10	4.7	42
Experimental Example 6	Chemical Formula 1-40	Ir(ppy) ₃	10	4.2	48
Experimental Example 7	Chemical Formula 1-62	Ir(ppy) ₃	10	4.3	44
Experimental Example 8	Chemical Formula 1-74	Ir(ppy) ₃	10	4.6	47
Experimental Example 9	Chemical Formula 1-98	Ir(ppy) ₃	10	4.8	46
Experimental Example 10	Chemical Formula 1-109	Ir(ppy) ₃	10	4.7	47
Experimental Example 11	Chemical Formula 1-142	Ir(ppy) ₃	10	4.7	41
Experimental Example 12	Chemical Formula 1-152	Ir(ppy) ₃	10	4.9	47
Experimental Example 13	Chemical Formula 1-200	Ir(ppy) ₃	10	4.4	40
Experimental Example 14	Chemical Formula 1-211	Ir(ppy) ₃	10	4.7	47

TABLE 1-continued

No.	Host	Dopant	Doping concentration (%)	Driving voltage (V) @5,000 cd/m ²	Light emitting efficiency (Cd/A)
Experimental Example 15	Chemical Formula 1-219	Ir(ppy) ₃	10	4.1	49
Experimental Example 16	Chemical Formula 1-231	Ir(ppy) ₃	10	4.2	48


[0158] As confirmed in Table 1, Experimental Examples 1 to 16 show that the compound of the present specification can be used as the host of the green light emitting layer and exhibits the low voltage characteristic and improved efficiency as compared to Comparative Example 1.

EXPLANATION OF REFERENCE NUMERALS AND SYMBOLS

- [0159]** 1: Substrate
[0160] 2: Anode
[0161] 3: Light emitting layer
[0162] 4: Cathode
[0163] 5: Hole injection layer
[0164] 6: Hole transport layer
[0165] 7: Light emitting layer
[0166] 8: Electron transport layer

1. A compound represented by the following Chemical Formula 1:

[Chemical Formula 1]



in Chemical Formula 1,

L₁ is a direct bond; substituted or unsubstituted phenylene; or a substituted or unsubstituted divalent monocyclic heterocyclic group including one or more of N, O, and S atoms,

L₂ is a direct bond; a substituted or unsubstituted arylene group; or a substituted or unsubstituted divalent heterocyclic group including one or more of N, O, and S atoms,

X₁ is N or CR₁₁, X₂ is N or CR₁₂, X₃ is N or CR₁₃,

A is hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthioxy group;


a substituted or unsubstituted arylthioxy group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted phenyl group; a substituted or unsubstituted biphenyl group; or a substituted or unsubstituted aromatic or aliphatic monocyclic six-membered heterocyclic group including one or more of N, O, and S atoms,

Ar₁ and Ar₂ are the same as or different from each other, and are each independently hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthioxy group; a substituted or unsubstituted arylthioxy group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted aryl group; a substituted or unsubstituted fluorenyl group; or a substituted or unsubstituted aromatic or aliphatic heterocyclic group including one or more of N, O, and S atoms, but do not include a carbazole group,

R₁ to R₄ and R₁₁ to R₁₃ are the same as or different from each other, and are each independently hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthioxy group; a substituted or unsubstituted arylthioxy group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted aryl group; a substituted or unsubstituted fluorenyl group; or a substituted or unsubstituted aromatic or aliphatic heterocyclic group including one or more of N, O, and S atoms,

a and c are each an integer of 0 to 4, b and d are each an integer of 0 to 3, in the case where a is 2 or more, R₁s are the same as or different from each other, in the case where b is 2 or more, R₂s are the same as or different from each other, in the case where c is 2 or more, R₃s are the same as or different from each other, and in the case where d is 2 or more, R₄s are the same as or different from each other.

2. The compound of claim 1, wherein Chemical Formula 1 is represented by the following Chemical Formula 2:



in Chemical Formula 2,

Z₁ to Z₅ are the same as or different from each other, and are each independently CR₅ or N, herein, R₅ is the same as definitions of R₁ to R₄, in the case where at least two of Z₁ to Z₅ are CR₅, R₅s are the same as or different from each other, and a residual substituent group is the same as a matter defined in Chemical Formula 1.


3. The compound of claim 1, wherein A is a phenyl group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing monocyclic six-membered heterocyclic group; a biphenyl group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing monocyclic six-membered heterocyclic group; or a N-containing monocyclic heterocyclic group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing monocyclic six-membered heterocyclic group.

4. The compound of claim 1, wherein L₁ is substituted or unsubstituted phenylene; or a substituted or unsubstituted divalent monocyclic heterocyclic group including one or more of N, O, and S atoms.

5. The compound of claim 1, wherein L₂ is a substituted or unsubstituted arylene group; or a substituted or unsubstituted divalent heterocyclic group including one or more of N, O, and S atoms.

6. The compound of claim 1, wherein Chemical Formula 1 is represented by the following Chemical Formula 3:

[Chemical Formula 3]



in Chemical Formula 3,


Z₁ to Z₅ are the same as or different from each other, and are each independently CR₅ or N, herein, R₅ is the same as definitions of R₁ to R₄, in the case where at least two of Z₁ to Z₅ are CR₅, R₅s are the same as or different from each other,


Y₁₁ to Y₁₅ and Y₂₁ to Y₂₅ are the same as or different from each other, and are each independently CR₆ or N, herein, R₆ is the same as definitions of R₁ to R₄, in the case where at least two of Y₁₁ to Y₁₅ and Y₂₁ to Y₂₅ are CR₆, R₆s are the same as or different from each other, but one of Y₁₁ to Y₁₅ and one of Y₂₁ to Y₂₅ are carbon atoms bonded to an adjacent carbazole group, and

a residual substituent group is the same as a matter defined in Chemical Formula 1.

7. The compound of claim 1, wherein L₁ of Chemical Formula 1 is phenylene unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, a phenyl group, or a N-containing monocyclic heterocyclic group; or a divalent N-containing monocyclic heterocyclic group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, a phenyl group, or a N-containing monocyclic heterocyclic group, and L₂ is a phenyl group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, or an aryl group; or a monocyclic N-containing heterocyclic group unsubstituted or substituted by a halogen group, a nitrile group, an alkyl group, or an aryl group.

8. The compound of claim 1, wherein L₁ and L₂ of Chemical Formula 1 are the same as or different from each other, and are each independently selected from the following Structural Formulas:






R_6 is hydrogen; deuterium; a halogen group; a nitrile group; a nitro group; a hydroxy group; a carbonyl group; an ester group; an imide group; an amide group; a substituted or unsubstituted alkyl group; a substituted or


unsubstituted cycloalkyl group; a substituted or unsubstituted alkoxy group; a substituted or unsubstituted aryloxy group; a substituted or unsubstituted alkylthio group; a substituted or unsubstituted arylthio group; a substituted or unsubstituted alkylsulfoxy group; a substituted or unsubstituted arylsulfoxy group; a substituted or unsubstituted alkenyl group; a substituted or unsubstituted silyl group; a substituted or unsubstituted boron group; a substituted or unsubstituted alkylamine group; a substituted or unsubstituted aralkylamine group; a substituted or unsubstituted arylamine group; a substituted or unsubstituted heteroarylamine group; a substituted or unsubstituted arylphosphine group; a substituted or unsubstituted phosphine oxide group; a substituted or unsubstituted aryl group; a substituted or unsubstituted fluorenyl group; or a substituted or unsubstituted aromatic or aliphatic heterocyclic group including one or more of N, O, and S atoms,

f is an integer of 0 to 4, and in the case where f is 2 or more, R_6 s are the same as or different from each other.

9. The compound of claim 1, wherein the Structural Formula




is selected from the following Structural Formulas:



10. The compound of claim 1, wherein Ar_1 and Ar_2 are the same as or different from each other, and are each independently a phenyl group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing heterocyclic group; fluorenyl unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing heterocyclic group; or a N-containing heterocyclic group unsubstituted or substituted by an alkyl group, a phenyl group, or a N-containing heterocyclic group.

11. The compound of claim 1, wherein Chemical Formula 1 is represented by the following Chemical Formula 4:



in Chemical Formula 4,

Z_1 to Z_5 are the same as or different from each other, and are each independently CR_5 or N, herein, R_5 is the same as definitions of R_1 to R_4 , in the case where at least two of Z_1 to Z_5 are CR_5 , R_5 s are the same as or different from each other,


Y_{11} to Y_{15} and Y_{21} to Y_{25} are the same as or different from each other, and are each independently CR_6 or N, herein, R_6 is the same as definitions of R_1 to R_4 , in the case where at least two of Y_{11} to Y_{15} and Y_{21} to Y_{25} are CR_6 , R_6 s are the same as or different from each other, but one

of Y_{11} to Y_{15} and one of Y_{21} to Y_{25} are carbon atoms bonded to an adjacent carbazole group,




X_{11} to X_{15} and X_{21} to X_{25} are the same as or different from each other, and are each independently CR_7 or N, herein, R_7 is the same as definitions of R_1 to R_4 , in the case where at least two of X_{11} to X_{15} and X_{21} to X_{25} are CR_7 , R_7 s are the same as or different from each other, and a residual substituent group is the same as a matter defined in Chemical Formula 1.

12. The compound of claim 1, wherein Chemical Formula 1 is selected from Chemical Formulas of the following Table:

Chemical Formula 1-1




-continued




-continued


Chemical Formula 1-5






Chemical Formula 1-6



Chemical Formula 1-7




-continued




-continued


Chemical Formula 1-11




Chemical Formula 1-12




Chemical Formula 1-13




-continued



Chemical Formula 1-14




Chemical Formula 1-15




Chemical Formula 1-16

-continued


Chemical Formula 1-17



Chemical Formula 1-18




Chemical Formula 1-19




-continued


Chemical Formula 1-20



Chemical Formula 1-21




Chemical Formula 1-22




-continued


Chemical Formula 1-23






Chemical Formula 1-24



Chemical Formula 1-25




-continued




-continued


Chemical Formula 1-29



Chemical Formula 1-30




Chemical Formula 1-31




-continued


Chemical Formula 1-32



Chemical Formula 1-33




Chemical Formula 1-34




-continued


Chemical Formula 1-35






Chemical Formula 1-36



Chemical Formula 1-37




-continued




-continued


Chemical Formula 1-41






Chemical Formula 1-42



Chemical Formula 1-43




-continued




-continued


Chemical Formula 1-47




Chemical Formula 1-48




Chemical Formula 1-49




-continued



Chemical Formula 1-50




Chemical Formula 1-51




Chemical Formula 1-52

-continued


Chemical Formula 1-53



Chemical Formula 1-54




Chemical Formula 1-55




-continued


Chemical Formula 1-56



Chemical Formula 1-57




Chemical Formula 1-58




-continued


Chemical Formula 1-59



Chemical Formula 1-60




Chemical Formula 1-61




-continued


Chemical Formula 1-62



Chemical Formula 1-63




Chemical Formula 1-64




-continued


Chemical Formula 1-65



Chemical Formula 1-66




Chemical Formula 1-67




-continued

Chemical Formula 1-68




Chemical Formula 1-69




-continued

Chemical Formula 1-70




Chemical Formula 1-71




-continued

Chemical Formula 1-72




Chemical Formula 1-73




-continued

Chemical Formula 1-74




Chemical Formula 1-75




-continued

Chemical Formula 1-76




Chemical Formula 1-77




-continued

Chemical Formula 1-78




Chemical Formula 1-79




-continued

Chemical Formula 1-80




Chemical Formula 1-81




-continued

Chemical Formula 1-82




Chemical Formula 1-83




-continued

Chemical Formula 1-84




Chemical Formula 1-85




-continued

Chemical Formula 1-86




Chemical Formula 1-87




-continued

Chemical Formula 1-88




Chemical Formula 1-89




-continued

Chemical Formula 1-90




Chemical Formula 1-91




-continued

Chemical Formula 1-92




Chemical Formula 1-93




-continued

Chemical Formula 1-94




Chemical Formula 1-95




-continued

Chemical Formula 1-96




Chemical Formula 1-97




-continued

Chemical Formula 1-98




Chemical Formula 1-99




-continued

Chemical Formula 1-100




Chemical Formula 1-101




-continued

Chemical Formula 1-102




Chemical Formula 1-103




-continued

Chemical Formula 1-104




Chemical Formula 1-105




-continued

Chemical Formula 1-106




Chemical Formula 1-107




-continued

Chemical Formula 1-108




Chemical Formula 1-109




-continued

Chemical Formula 1-110




Chemical Formula 1-111




-continued

Chemical Formula 1-112




Chemical Formula 1-113




-continued

Chemical Formula 1-114




Chemical Formula 1-115




-continued

Chemical Formula 1-116




Chemical Formula 1-117




-continued

Chemical Formula 1-118




Chemical Formula 1-119




-continued

Chemical Formula 1-120




Chemical Formula 1-121




-continued

Chemical Formula 1-122




Chemical Formula 1-123




-continued

Chemical Formula 1-124




Chemical Formula 1-125




-continued

Chemical Formula 1-126




Chemical Formula 1-127




-continued

Chemical Formula 1-128




Chemical Formula 1-129




-continued

Chemical Formula 1-130




Chemical Formula 1-131




-continued

Chemical Formula 1-132




Chemical Formula 1-133




-continued

Chemical Formula 1-134




Chemical Formula 1-135




-continued

Chemical Formula 1-136




Chemical Formula 1-137




-continued

Chemical Formula 1-138




Chemical Formula 1-139




-continued

Chemical Formula 1-140




Chemical Formula 1-141




-continued

Chemical Formula 1-142




Chemical Formula 1-143




-continued

Chemical Formula 1-144




Chemical Formula 1-145




-continued

Chemical Formula 1-146




Chemical Formula 1-147




-continued

Chemical Formula 1-148




Chemical Formula 1-149




-continued

Chemical Formula 1-150




Chemical Formula 1-151




-continued

Chemical Formula 1-152




Chemical Formula 1-153




-continued

Chemical Formula 1-154




Chemical Formula 1-155




-continued

Chemical Formula 1-156




Chemical Formula 1-157




-continued

Chemical Formula 1-158




Chemical Formula 1-159




-continued

Chemical Formula 1-160




Chemical Formula 1-161




-continued

Chemical Formula 1-162




Chemical Formula 1-163




-continued

Chemical Formula 1-164




Chemical Formula 1-165




-continued

Chemical Formula 1-166




Chemical Formula 1-167




-continued

Chemical Formula 1-168




Chemical Formula 1-169




-continued

Chemical Formula 1-170




Chemical Formula 1-171




-continued

Chemical Formula 1-174




Chemical Formula 1-175




-continued

Chemical Formula 1-176




Chemical Formula 1-177




-continued

Chemical Formula 1-178




Chemical Formula 1-179




-continued

Chemical Formula 1-180




Chemical Formula 1-181




-continued

Chemical Formula 1-182




Chemical Formula 1-183




-continued

Chemical Formula 1-184




Chemical Formula 1-185




-continued

Chemical Formula 1-186




Chemical Formula 1-187




-continued

Chemical Formula 1-188




Chemical Formula 1-189




-continued

Chemical Formula 1-190




Chemical Formula 1-191




-continued

Chemical Formula 1-192




Chemical Formula 1-193




-continued

Chemical Formula 1-194




Chemical Formula 1-195




-continued

Chemical Formula 1-196




Chemical Formula 1-197




-continued

Chemical Formula 1-198




Chemical Formula 1-199




-continued

Chemical Formula 1-200




Chemical Formula 1-201




-continued

Chemical Formula 1-204




Chemical Formula 1-205




-continued

Chemical Formula 1-206




Chemical Formula 1-207




-continued


Chemical Formula 1-208



Chemical Formula 1-209




Chemical Formula 1-210




-continued


Chemical Formula 1-211



Chemical Formula 1-212




Chemical Formula 1-213




-continued


Chemical Formula 1-214



Chemical Formula 1-215




Chemical Formula 1-216




-continued


Chemical Formula 1-217






Chemical Formula 1-218



Chemical Formula 1-219




-continued




-continued

Chemical Formula 1-223




Chemical Formula 1-224




-continued


Chemical Formula 1-225



Chemical Formula 1-226




Chemical Formula 1-227




-continued


Chemical Formula 1-228



Chemical Formula 1-229




Chemical Formula 1-230




-continued


Chemical Formula 1-231




Chemical Formula 1-232



Chemical Formula 1-233



-continued



13. An organic light emitting device comprising:
a first electrode;
a second electrode provided to face the first electrode; and
one or more organic material layers provided between the first electrode and the second electrode,
wherein one or more of the organic material layers include the compound according to claim 1.

14. The organic light emitting device of claim 13, wherein the organic material layer including the compound is a light emitting layer.

15. The organic light emitting device of claim 14, wherein the light emitting layer is a phosphorescent light emitting layer.

16. The organic light emitting device of claim 14, wherein the light emitting layer further includes a phosphorescent material.

* * * * *

专利名称(译)	杂环化合物和包含其的有机发光装置		
公开(公告)号	US20160204359A1	公开(公告)日	2016-07-14
申请号	US14/908095	申请日	2014-07-10
[标]申请(专利权)人(译)	乐金化学股份有限公司		
申请(专利权)人(译)	LG化学有限公司.		
当前申请(专利权)人(译)	LG化学有限公司.		
[标]发明人	LEE HOYONG CHO SEONGMI KIM KONGKYEOM JEON SANG YOUNG CHUN MINSEUNG KIM HYOUNG SEOK KIM DONGHEON		
发明人	LEE, HOYONG CHO, SEONGMI KIM, KONGKYEOM JEON, SANG YOUNG CHUN, MINSEUNG KIM, HYOUNG SEOK KIM, DONGHEON		
IPC分类号	H01L51/00 C07D401/14 C07D403/14 C09K11/02 C09K11/06		
CPC分类号	H01L51/0072 C09K11/025 C09K11/06 H01L51/0085 C07D403/14 C09K2211/185 C07D401/14 H01L51/0052 H01L51/5016 C09K2211/1007 C09K2211/1029 H01L51/0067 C09K2211/1011 C09K2211/1044 C09K2211/1059 H01L51/006		
优先权	1020130089869 2013-07-29 KR		
其他公开文献	US10253016		
外部链接	Espacenet USPTO		

摘要(译)

本说明书提供杂环化合物和包含其的有机发光器件。

