



US008228277B2

(12) **United States Patent**
Yoshida et al.

(10) **Patent No.:** **US 8,228,277 B2**
(45) **Date of Patent:** **Jul. 24, 2012**

(54) **DISPLAY DEVICE**

(75) Inventors: **Yasunori Yoshida**, Kanagawa (JP); **Hajime Kimura**, Kanagawa (JP); **Shinji Maekawa**, Shizuoka (JP); **Osamu Nakamura**, Kanagawa (JP); **Shunpei Yamazaki**, Tokyo (JP)

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd.**, Kanagawa-ken (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/293,762**

(22) Filed: **Nov. 10, 2011**

(65) **Prior Publication Data**

US 2012/0056550 A1 Mar. 8, 2012

Related U.S. Application Data

(63) Continuation of application No. 12/784,063, filed on May 20, 2010, now Pat. No. 8,102,347, which is a continuation of application No. 10/579,987, filed on May 19, 2006, now Pat. No. 7,733,315.

(30) **Foreign Application Priority Data**

Dec. 6, 2004 (JP) 2004-353457

(51) **Int. Cl.**
G09G 3/36 (2006.01)

(52) **U.S. Cl.** **345/90**; 345/100; 345/211; 315/169.1; 315/169.3; 257/207; 438/149

(58) **Field of Classification Search** 345/45, 345/60, 63, 76, 90, 92, 100, 206, 211, 204, 345/212, 214; 315/169.1, 169.3; 257/59, 257/72, E27.113, E27.116, E29.279, 207; 438/149, 157, 164, 459; 445/24

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,468,659 A	8/1984	Ohba et al.
4,937,517 A	6/1990	Kurashima
4,989,062 A	1/1991	Takahashi et al.
5,440,208 A	8/1995	Uskali et al.
5,670,792 A	9/1997	Utsugi et al.
5,831,709 A	11/1998	Song

(Continued)

FOREIGN PATENT DOCUMENTS

EP 0 895 219 A1 2/1999

(Continued)

OTHER PUBLICATIONS

Schenk.H et al., "Polymers for Light Emitting Diodes," Eurodisplay '99 : The 19th International Display Research Conference, Sep. 6, 1999, pp. 33-37.

(Continued)

Primary Examiner — Haiss Philogene



(74) *Attorney, Agent, or Firm* — Nixon Peabody LLP; Jeffrey L. Costellia

(57)

ABSTRACT

The invention provides an active matrix EL display device which can perform a clear multi-gray scale color display. In particular, the invention provides a large active matrix EL display device at low cost by a manufacturing method which can selectively form a pattern. Power supply lines in a pixel portion are arranged in matrix by the manufacturing method which can selectively form a pattern. Further, capacitance between wirings is reduced by providing a longer distance between adjacent wirings by the manufacturing method which can selectively form a pattern.

37 Claims, 35 Drawing Sheets



U.S. PATENT DOCUMENTS

6,058,257 A 5/2000 Nojima
 6,087,885 A 7/2000 Tobita
 6,118,151 A 9/2000 Tsutsu
 6,127,704 A 10/2000 Kim
 6,239,958 B1 5/2001 Kato et al.
 6,348,702 B1 2/2002 Takayama et al.
 6,380,558 B1 4/2002 Yamazaki et al.
 6,421,034 B1 7/2002 Mihara
 6,469,317 B1 10/2002 Yamazaki et al.
 6,475,845 B2 11/2002 Kimura
 6,476,419 B1 11/2002 Yasuda
 6,512,504 B1 1/2003 Yamauchi et al.
 6,518,941 B1 2/2003 Kimura
 6,522,079 B1 2/2003 Yamada
 6,524,895 B2 2/2003 Yamazaki et al.
 6,529,178 B1 3/2003 Kimura
 6,531,713 B1 3/2003 Yamazaki
 6,545,359 B1 4/2003 Ohtani et al.
 6,548,960 B2 4/2003 Inukai
 6,556,177 B1 4/2003 Katayama et al.
 6,580,408 B1 6/2003 Bae et al.
 6,580,409 B1 6/2003 Ito et al.
 6,583,577 B1 6/2003 Choi et al.
 6,593,691 B2 7/2003 Nishi et al.
 6,618,029 B1 9/2003 Ozawa
 6,633,270 B2 10/2003 Hashimoto
 6,682,963 B2 1/2004 Ishikawa
 6,700,330 B2 3/2004 Koyama
 6,714,178 B2 3/2004 Koyama et al.
 6,724,149 B2 4/2004 Komiyama et al.
 6,765,549 B1* 7/2004 Yamazaki et al. 345/80
 6,958,489 B2 10/2005 Kimura
 7,009,345 B2 3/2006 Komiyama et al.
 7,012,290 B2 3/2006 Kimura
 7,029,960 B2 4/2006 Hashimoto et al.
 7,045,861 B2 5/2006 Takayama et al.
 7,109,071 B2 9/2006 Ishikawa
 7,148,630 B2 12/2006 Koyama et al.
 7,192,859 B2 3/2007 Yamazaki et al.
 7,221,337 B1 5/2007 Choi et al.
 7,236,164 B2 6/2007 Kimura
 7,245,297 B2 7/2007 Kimura et al.
 7,397,451 B2 7/2008 Ozawa
 7,408,193 B2 8/2008 Ishikawa
 7,460,094 B2 12/2008 Ozawa
 7,592,652 B2 9/2009 Kimura
 7,619,593 B2* 11/2009 Fish et al. 345/76
 7,642,555 B2 1/2010 Ishikawa
 7,687,808 B2 3/2010 Umezaki
 7,733,315 B2 6/2010 Yoshida et al.
 2001/0022565 A1 9/2001 Kimura
 2001/0048408 A1 12/2001 Koyama et al.
 2002/0011976 A1 1/2002 Hashimoto
 2002/0024493 A1 2/2002 Ozawa et al.
 2003/0047729 A1 3/2003 Hirai et al.
 2003/0151568 A1 8/2003 Ozawa
 2003/0201496 A1 10/2003 Yamazaki et al.
 2004/0108978 A1 6/2004 Matsueda et al.
 2005/0140306 A1 6/2005 Park
 2007/0080917 A1 4/2007 Koyama et al.
 2007/0181945 A1 8/2007 Nakamura
 2008/0158209 A1 7/2008 Ozawa
 2008/0165174 A1 7/2008 Ozawa
 2008/0198152 A1 8/2008 Ozawa
 2008/0290807 A1 11/2008 Matsueda et al.
 2009/0315066 A1 12/2009 Kimura

FOREIGN PATENT DOCUMENTS

EP 0 935 229 A1 8/1999
 EP 0 949 603 A1 10/1999
 EP 1 058 310 A2 12/2000
 EP 1 139 454 A2 10/2001
 EP 1 291 932 A2 3/2003
 EP 1 505 650 A2 2/2005
 EP 1 505 651 A2 2/2005
 EP 1 505 652 A2 2/2005
 EP 2 112 693 A2 10/2009
 JP 57-041694 3/1982
 JP 63-083798 6/1988
 JP 04-031299 3/1992
 JP 04-229529 8/1992
 JP 04-234785 8/1992
 JP 04-250492 9/1992
 JP 05-035207 2/1993
 JP 06-176868 6/1994
 JP 08-129158 5/1996
 JP 08-171081 7/1996
 JP 09-114398 5/1997
 JP 09-260061 10/1997
 JP 09-281928 10/1997
 JP 10-092576 4/1998
 JP 10-247735 9/1998
 JP 10-284690 10/1998
 JP 11-024606 1/1999
 JP 11-073158 3/1999
 JP 11-219133 8/1999
 JP 2000-132133 5/2000
 JP 2000-242196 9/2000
 JP 2001-53287 2/2001
 JP 2001-100654 4/2001
 JP 2001-324958 11/2001
 JP 2002-032037 1/2002
 JP 2002-164354 6/2002
 JP 2003-177682 6/2003
 JP 2004-126439 4/2004
 KR 1999-0018059 3/1999
 KR 1999-0025571 4/1999
 KR 2001-0093076 10/2001
 KR 2005-0065947 6/2005
 WO 98/36407 8/1998
 WO WO-9912150 A1 3/1999
 WO WO 2004/086487 A1 10/2004
 WO WO 2005-048222 A1 5/2005

OTHER PUBLICATIONS

Japanese Office Action (Application No. 2001-140325; J05709) Dated Aug. 24, 2010.
 Shimoda.T et al., "Technology for Active Matrix Light Emitting Polymer Displays," IEDM 99: Technical Digest of International Electron Devices Meeting, 1999, pp. 107-110.
 Kimura.M et al., "Low-Temperature Poly-Si TFT Driven Light-Emitting-Polymer Displays and Digital Gray Scale for Uniformity," IDW '99 : Proceedings of the 6th International Display Workshops, 1999, pp. 171-174.
 Chinese Office Action in Chinese Patent Application No. 200580041540.3 dated May 30, 2008 with English translation.
 Kimura et al. "TFT-LEPD with Image Uniformity by Area Ratio Gray Scale", Euro Display 99, Sep. 6, 1999, pp. 71-74.
 International Search Report for PCT/JP2005/022608 dated Mar. 14, 2006.
 Written Opinion of the International Searching Authority for PCT/JP2005/022608 dated Mar. 14, 2006.
 "Korean Office Action (Applicant No. 2007-7015518. PCTKR08407) Dated Mar. 20, 2012,".

* cited by examiner

Fig. 1




Fig. 2




Fig. 3




FIG. 4




Fig. 5A

Fig. 5B




Fig. 6A




Fig. 6B




Fig. 6C




Fig. 7A




Fig. 7B




Fig. 7C




Fig. 7D




Fig. 8




Fig. 10




Fig. 11




Fig. 12




Fig. 13A




Fig. 13B




Fig. 13C




Fig. 13D




Fig. 14A




Fig. 14B




Fig. 15




Fig. 16A




Fig. 16B




Fig. 17




Fig. 18A




Fig. 18B




Fig. 18C




Fig. 18D




Fig. 19A




Fig. 19B




Fig. 20A




Fig. 20B




Fig. 20C




Fig. 20D




Fig. 21




Fig. 22A




Fig. 22B




Fig. 22C




Fig. 22D




Fig. 23A




Fig. 23B




Fig. 24A




Fig. 24B




Fig. 24C




Fig. 24D




Fig. 25A




Fig. 25B




Fig. 26A




Fig. 26B




Fig. 26C




Fig. 26D




Fig. 27




Fig. 28A




Fig. 28B




Fig. 28C




Fig. 28D




Fig. 29A




Fig. 29B




Fig. 30A




Fig. 30B





Fig. 30C






Fig. 32




Fig. 33




Fig. 34A




Fig. 34B




Fig. 34C




Fig. 35A




Fig. 35B





Fig. 35C



1

DISPLAY DEVICE

This application is a Continuation of U.S. application Ser. No. 12/784,063, filed on May 20, 2010, now U.S. Pat. No. 8,102,347 which is a Continuation of U.S. application Ser. No. 10/579,987, filed on May 19, 2006, now U.S. Pat. No. 7,733,315.

TECHNICAL FIELD

The present invention relates to an electronic display (electro-optic device) in which EL (electroluminescence) elements are formed over a substrate. In particular, the invention relates to a display device using a semiconductor element (element using a semiconductor thin film). Further, the invention relates to an electronic device using an EL display device in a display portion.

BACKGROUND ART

In recent years, a technique to form a thin film transistor (hereinafter referred to as a TFT in this specification) over a substrate has been drastically advanced and developed for an application to an active matrix display device. In particular, a TFT using a polycrystalline semiconductor film such as polysilicon is higher than a conventional TFT using an amorphous semiconductor film such as amorphous silicon in field effect mobility (also referred to as mobility), which enables a fast operation. Accordingly, pixels which are conventionally controlled by a driver circuit outside a substrate can now be controlled by a driver circuit formed over the same substrate as the pixels.

In an active matrix display device using such a polycrystalline semiconductor film, various circuits and elements can be formed over the same substrate. Therefore, there are various advantages such as reduction in manufacturing cost, downsizing of a display device, improvement of yield, and reduction of throughput.

Further, a research on an active matrix EL display device using an EL element as a self-luminous element has been activated. An EL display device is also referred to as an organic EL display (OLED) or an organic light emitting diode (OLED).

An EL element has a structure in which a pair of electrodes (anode and cathode) sandwich an EL layer which normally has a stacked-layer structure. Typically, there is a stacked layer structure of "a hole transporting layer, a light emitting layer, and an electron transporting layer" suggested by Tang et al. at Eastman Kodak Company. This structure has quite high light emitting efficiency and is employed for most EL display devices now being researched and developed.

Besides, a stacked-layer structure of a hole injecting layer, a hole transporting layer, a light emitting layer, and an electron transporting layer or a stacked-layer structure of a hole injecting layer, a hole transporting layer, a light emitting layer, an electron transporting layer, and an electron injecting layer over an anode may be employed as well. The light emitting layer may be doped with a phosphorescence pigment and the like.

In this specification, all layers provided between a cathode and an anode are collectively referred to as an EL layer. Therefore, the hole injecting layer, the hole transporting layer, the light emitting layer, the electron transporting layer, the electron injecting layer and the like are all included in the EL layer.

When a predetermined voltage is applied to an EL layer with the aforementioned structure from the pair of electrodes,

2

carriers are recombined in the light emitting layer and light is emitted. In this specification, when an EL element emits light, it is referred that EL element is driven. Further in this specification, a light emitting element formed of an anode, an EL layer, and a cathode is referred to as an EL element.

It is to be noted in this specification that an EL element may utilize both light emission (phosphorescence) which occurs from a singlet excitation state and light emission (fluorescence) which occurs from a triplet excitation state.

An EL display device may be driven by an analog driving method (analog drive) and a digital driving method (digital drive). First, description is made with reference to FIGS. 1 and 2 on the analog drive of an EL display device.

FIG. 1 shows a structure of a pixel portion 100 of an analog drive EL display device. Gate signal lines (G1 to Gy) each of which is inputted with a selection signal from a gate signal line driver circuit is connected to a gate electrode of a switching TFT 101 of each pixel. One of a source region and a drain region of the switching TFT 101 of each pixel is connected to each of source signal lines (also referred to as a data signal line) (S1 to Sx) which is inputted with an analog video signal and the other is connected to a gate electrode of a driving TFT 104 and a capacitor 108 of each pixel.

One of a source region and a drain region of the driving TFT 104 of each pixel is connected to each of power supply lines (V1 to Vx) and the other is connected to an EL element 106. A potential of each of the power supply lines (V1 to Vx) is referred to as a power source potential. Each of the power supply lines (V1 to Vx) is connected to the capacitor 108 of each pixel.

The EL element 106 has an anode, a cathode, and an EL layer provided between the anode and the cathode. In the case where the anode of the EL element 106 is connected to the source region or the drain region of the driving TFT 104, the anode of the EL element 106 is a pixel electrode while the cathode thereof is a counter electrode. In the case where the cathode of the EL element 106 is connected to the source region or the drain region of the driving TFT 104, the anode of the EL element 106 is a counter electrode while the cathode thereof is a pixel electrode.

In this specification, a potential of a counter electrode is referred to as a counter potential. A power source which applies a counter potential to a counter electrode is referred to as a counter power source. A potential difference between a potential of a pixel electrode and a potential of a counter electrode is an EL driving voltage which is applied to an EL layer.

FIG. 2 shows a timing chart of the EL display device shown in FIG. 1 driven by an analog method. A period from selection of one gate signal line until the selection of a different gate signal line is referred to as one line period (L). A period from a display of one image until a display of a next image corresponds to one frame period (F). In the case of the EL display device of FIG. 1, there are y gate signal lines, therefore, y line periods (L1 to Ly) are provided in one frame period.

The power supply lines V1 to Vx are held at a certain power source potential. The counter potential which is a potential of the counter electrode is also held at a certain potential. The counter potential and the power source potential have a potential difference such that an EL element emits light.

In a first line period (L1), the gate signal line G1 is inputted with a selection signal from a gate signal line driver circuit. Then, analog video signals are sequentially inputted to the source signal lines S1 to Sx. Since all switching TFTs connected to the gate signal line G1 are turned on, the analog

video signals inputted to the source signal lines S1 to Sx are inputted through the switching TFTs to the gate electrodes of the driving TFTs.

The amount of current flowing through a channel forming region of a driving TFT is controlled by a gate voltage thereof.

Here, description is made on an example where a source region of a driving TFT is connected to a power supply line and a drain region thereof is connected to an EL element.

As the source region of the driving TFT is connected to the power supply line, each pixel in a pixel portion is inputted with the same potential. At this time, when an analog signal is inputted to a source signal line, a potential difference between a potential of the signal voltage and a potential of the source region of the driving TFT becomes a gate voltage. A current flowing to an EL element depends on a gate voltage of the driving TFT. Here, luminance of the EL element is in proportion with a current flowing between opposite electrodes of the EL element. In this manner, an EL element emits light depending on a voltage of an analog video signal.

The aforementioned operation is repeated, and when analog video signals are inputted to all the source signal lines (S1 to Sx), the first line period (L1) ends. It is to be noted that the period until the analog video signals are all inputted and a horizontal retrace line period together may be one line period. Then, in a second line period (L2), the gate signal line G2 is inputted with a selection signal. Similarly to the case of the first line period (L1), analog video signals are sequentially inputted to the source signal lines (S1 to Sx).

When the selection signals are inputted to all the gate signal lines (G1 to Gy), all the line periods (L1 to Ly) end. When all the line periods (L1 to Ly) end, one frame period ends. In one frame period, all the pixels perform display to form one image. It is to be noted that all the line periods (L1 to Ly) and a vertical retrace line period together may be one frame period.

As described above, the amount of light emitted by an EL element is controlled by an analog video signal. By controlling the amount of light emission, a gray scale display is performed. This method is a so-called analog driving method, where a gray scale display is performed by changing a voltage of an analog video signal inputted to the source signal line.

Next, description is made on a digital drive of an EL display device. In a digital gray scale method, a gate-source voltage V_g of the driving TFT 104 operates in two stages: either in a region (equal to a light emission start voltage or lower) that no current flows to the EL element 106 or a region (equal to a luminance saturation voltage or higher) that the largest current flows thereto. That is, an EL element either emits light or emits no light.

An EL display mainly employs the digital gray scale method in which variations in characteristics such as a threshold value of a TFT do not easily affect a display. In the case of the digital gray scale method, however, only two gray scale levels can be displayed by itself. Therefore, a plurality of techniques to employ the digital gray scale method in combination with another method are suggested to perform a multi gray scale display.

One of these techniques is a method of using an area gray scale method and the digital gray scale method in combination. The area gray scale method is a method for displaying gray scales by controlling the area of portions which emit light. That is, one pixel is divided into a plurality of subpixels, and the number and the area of subpixels which emit light are controlled to display a gray scale. This method is disadvantageous in that high resolution and multi gray scales display cannot be easily achieved as the number of subpixels cannot

be increased. Non-patent Documents 1, 2, and the like disclose the area gray scale method.

Another method to achieve a multi gray scale display is a method for using a time gray scale method and the digital gray scale method in combination. The time gray scale method is a method for displaying gray scales by utilizing a difference in light emission time. That is, one frame period is divided into a plurality of subframe periods, and gray scales are displayed by controlling the number and length of the subframe periods in which light is emitted (see Patent Document 1).

Non-patent Document 3 discloses the case of using the digital gray scale method, the area gray scale method, and the time gray scale method in combination.

Next, description is made on a constant current drive and a constant voltage drive in the case of displaying gray scales by the digital gray scale method.

The constant current drive is a driving method to operate the driving TFT 104 in a saturation region when the EL element 106 emits light and supply a constant current to all pixels. This driving method is advantageous in that a constant current can be supplied to the EL element 106 even when the EL element 106 deteriorates and $V-I$ characteristics change, which leads to prolong life of an EL display device.

On the other hand, the constant voltage drive is a driving method to operate the driving TFT 104 in a linear region when the EL element 106 emits light and supply a constant voltage to all pixels. This driving method is advantageous in that a constant voltage can be applied to the EL element 106 even when characteristics of the driving TFT 104 vary, which leads to no variations in luminance of pixels and high display quality.

Non-Patent Document 1

Euro Display 99 Late News: P71: "TFT-LEPD with Image Uniformity by Area Ratio Gray Scale"

Non-Patent Document 2

IEDM 99: P107: "Technology for Active Matrix Light Emitting Polymer Displays"

Non-Patent Document 3

IDW'99: P171: "Low-Temperature Poly-Si TFT Driven Light-Emitting-Polymer Displays and Digital Gray Scale for Uniformity"

Patent Document 1

Japanese Patent Laid-open No. 2001-324958

DISCLOSURE OF INVENTION

The invention provides a large and high resolution EL display device with favorable yield which can be manufactured at low cost. In view of this, following problems exist.

First, description is made on problems in the case of using the digital gray scale method and the time gray scale method in combination as a driving method of an EL display device. In the case of using the digital gray scale method and the time gray scale method in combination, one frame period is divided into a plurality of subframe periods and the number and length of the subframe periods in which light is emitted are controlled to display a gray scale. That is, as compared to time which can be spent for displaying one image by the

analog gray scale method, only the subframe number-th part of time can be spent to display one image in the case of using the digital gray scale method and the time gray scale method in combination, which requires a driver circuit to operate at quite a fast speed as compared to the analog gray scale method.

Further, an operating frequency of a driver circuit is limited. If one frame is divided into too many subframes or the resolution is too high, sufficient write time cannot be provided. That is, one of the problems in using the digital gray scale method and the time gray scale method in combination is insufficient write time. In view of this, write time is required to be provided as long as possible.

Next, description is made on a problem in increase of parasitic capacitance. The larger and higher resolution display device has a pixel portion with a longer wiring. Further, the number of wirings to cross the wirings is increased, which leads to increase parasitic capacitance of the wirings in the pixel portion.

When the parasitic capacitance is increased, dullness of waveform of electric signal transmitting through the wiring is increased. The dullness of the waveform prevents accurate transmission of signals and degrades display quality. That is, one of the problems in manufacturing a large and high resolution EL display device is an increase in parasitic capacitance. In view of this, parasitic capacitance is required to be as little as possible.

Next, description is made on a problem in manufacturing at low cost. At present, a TFT and an electronic circuit using a TFT are generally manufactured by stacking various thin films such as a semiconductor, an insulator and a conductor over a substrate and forming a predetermined pattern by a photolithography technique appropriately. The photolithography technique is a technique to transfer a pattern such as a circuit formed of a material which does not transmit light over a light-transmissive plane surface called a photo mask onto a substrate by utilizing light. This technique is widely used in manufacturing steps of a semiconductor integrated circuit and the like.

Manufacturing steps using the photolithography technique require a number of steps such as exposure, development, baking, and peeling even only for a mask pattern formed of a photosensitive organic resin material called a photo resist. Therefore, as the number of photolithography steps increases, manufacturing cost necessarily increases.

Next, description is made on a problem of wiring resistance. First, description is made on the case of using the analog driving method as a driving method of an EL display device.

FIG. 3 is a graph showing characteristics of a driving TFT in a saturation region ($V_{ds} > V_{g} - V_{th}$). Here, V_{ds} is a source-drain voltage, V_g is a gate-source voltage, and V_{th} is a threshold voltage. Reference numeral 301 denotes I_d - V_g characteristics (or an I_d - V_g curve). Here, I_d denotes a drain current. By this graph, the amount of current flowing with any gate voltage can be known.

In the analog driving method, a driving TFT operates in a saturation region and a gate voltage is changed to change a drain current thereof.

An analog video signal inputted through a source signal line to a pixel when a switching TFT is turned on is applied to a gate electrode of a driving TFT. In this manner, a gate voltage of the driving TFT changes. At this time, the drain current is set in accordance with the ratio 1:1 to the gate voltage in accordance with the I_d - V_g characteristics. In this manner, a predetermined drain current is supplied to an EL element in accordance with a voltage of an analog video

signal inputted to a gate electrode of the driving TFT. The EL element emits light with the amount in accordance at the amount of the supplied current.

As described above, the amount of light emission of the EL element is controlled by an analog video signal, by which gray scale display is performed.

Here, a gate voltage of the driving TFT of each pixel changes when a potential of a source region of the driving TFT changes even with the same signal inputted from the source signal line. Here, the potential of the source region of the driving TFT is applied from the power supply line. However, a potential of the power supply line changes depending on a position in the pixel portion due to a potential drop caused by wiring resistance.

Further, in the case where wiring resistance of the power supply line is small, the case where the display device is relatively small, or the case where a current flowing through the power supply line is relatively small, the potential change of the power supply line due to a potential drop caused by wiring resistance does not have so much effect, but has a significant effect besides the above cases, in particular in the case where the display device is relatively large.

In particular, as the display device is larger, there are larger variations in distance from an external input terminal to each power supply line of a pixel portion, therefore, larger variations exist in length of wirings in a power supply line lead portion. Therefore, a change in potential of the power supply line due to a potential drop of the power supply line lead portion becomes large.

The variations in potential of the power supply line due to the aforementioned factors affect luminance of an EL element in each pixel and change display luminance, which cause display unevenness.

Hereinafter, description is made on a specific example of variations in potential of the power supply line.

As shown in FIG. 4, when a white or black box is displayed in a display screen, a phenomenon called a cross talk occurs. This is a phenomenon that a difference in luminance occurs between portions above and below the box and the portions beside the box.

Cross talk is a phenomenon that a different current flows to the driving TFTs 104 in pixels above, below, and beside the box. This difference is caused by the power supply lines V1 and V2 arranged in parallel to the source signal lines S1 and S2.

In the case where a white box is displayed in a portion of a display screen as shown in FIG. 4, the power supply line corresponding to a pixel which displays the white box has a larger potential drop due to wiring resistance as compared to a power supply line which supplies power only to pixels which do not display the white box, because current is supplied to an EL element through a source and drain of a driving TFT in the pixel which displays the white box. Therefore, there are portions above and below the white box which are darker than other pixels which do not display the white box.

Here, in the case where a display screen of a display device is small, the problem did not occur. However, with a larger display screen of the display device, the total amount of current flowing to an EL element increases in proportion with the area of the display screen.

For example, when comparing the total amount of current flowing to the EL element in a display device having a display screen of four inches diagonal and a display device having a display screen of 20 inches diagonal, the latter display screen is 25 times as large as the former, and thus the total amount of current supplied to the EL element is also about 25 times as large.

Accordingly, the aforementioned potential drop is quite a problem in a display device having a large display screen.

For example, provided that the display device having a display screen of 20 inches diagonal has a wiring with a length of 700 mm, a width of 10 mm, and sheet resistance of 0.1 ohm, when a current of 1 A flows, a potential drop of 10 V occurs and a normal display cannot be performed.

Next, description is made on problems of wiring resistance in the case of employing the constant voltage drive with the digital driving method as a driving method of an EL display device.

When the constant voltage drive is employed, a constant voltage is applied to the EL element **106** in each pixel. Therefore, an EL display device capable of displaying an image of quite high quality can be obtained with pixels whose luminance is not affected by variations in characteristics of the driving TFT **104**. However, if wiring resistance is high, it is impossible to satisfy a necessary condition for performing the constant voltage drive, that a constant voltage is supplied to the EL element **106** in each pixel. Description is made on this with reference to FIGS. **5A** and **5B**.

FIG. **5A** shows a panel in which a third of all pixels emit light at the same time. FIG. **5B** shows a panel in which two third of all pixels emit light at the same time.

As different number of pixels emit light at the same time between the FIGS. **5A** and **5B**, different current values are supplied to the power supply lines (V1 to Vx) in a pixel portion when emitting light. Here, if there is wiring resistance in the power supply lines (V1 to Vx) in the pixel portion, a voltage drops in accordance with the amount of current. That is, in FIGS. **5A** and **513** of which current values are different, a voltage applied per pixel is different. When different voltages are applied, luminance of an EL element differs between when displaying as shown in FIG. **5A** and when displaying as shown in FIG. **5B**.

In this manner, when luminance per pixel changes depending on a light emission rate of a displayed image, it adversely affects when displaying gray scales by the time gray scale method. For example, the case of displaying three gray scale levels are displayed continuously for the same period by the panels in FIGS. **5A** and **5B**. At this time, it is supposed that a display region **503** displays a gray scale 0, a display region **504** displays a gray scale 2, and a display region **505** displays a gray scale 1. However, with wiring resistance, the display region **505** displays a gray scale lower than 1 as luminance per pixel of FIG. **5A** is higher than that of FIG. **5B**. In this manner, with wiring resistance, desired gray scale cannot be displayed in the case of performing the constant voltage drive with the digital driving method.

This difference in luminance is larger as wiring resistance of the power supply lines (V1 to Vx) is higher. The larger a display device has a longer power supply line, which makes wiring resistance higher. That is, one of the problems in manufacturing a large and high resolution EL display device is the increase in wiring resistance. In view of this, wiring resistance is required to be as low as possible.

The invention is made in view of the aforementioned problems to provide an active matrix EL display device capable of a clear multi gray scale color display. The invention also provides a high functional electronic device using such an active matrix EL display device.

The invention provides a large and high resolution EL display device with favorable yield which can be manufactured at low cost. In view of this, a configuration of the invention is described below.

A configuration of the invention includes a display device comprising a plurality of source signal lines over an insulat-

ing surface, a plurality of gate signal lines, a plurality of power supply lines in columns, a plurality of power supply lines in rows, and a plurality of pixels arranged in matrix, wherein each of the plurality of pixels includes a switching thin film transistor, a driving thin film transistor, and a light emitting element, wherein each of the plurality of pixels is connected to one of the plurality of power supply lines in columns and one of the plurality of power supply lines in rows, and wherein an insulating thin film is formed in a portion under at least one of the plurality of source signal lines, the plurality of gate signal lines, the plurality of power supply lines in columns, and the plurality of power supply lines in rows.

Another configuration of the invention includes a method for manufacturing a display device comprising the steps of: forming a plurality of source signal lines over an insulating surface, forming a plurality of gate signal lines, forming a plurality of pixels arranged in matrix, and each of said plurality of pixels includes a switching thin film transistor, a driving thin film transistor, and a light emitting element, forming a plurality of power supply lines in columns, forming a plurality of power supply lines in rows, and connecting each of the plurality of pixels to one of the plurality of power supply lines in columns and one of the plurality of power supply lines in rows by a droplet discharging method or a printing method.

Another configuration of the invention includes a method for manufacturing a display device comprising the steps of: forming a source signal line over an insulating surface, forming a gate signal line, forming a power supply line, forming a pixel including a switching thin film transistor, a driving thin film transistor, and a light emitting element, forming an insulating thin film in a portion under at least one of the source signal line, the gate signal line, and the power supply line by a droplet discharging method or a printing method.

In the aforementioned invention, one of the plurality of source signal lines, the plurality of gate signal lines, and the plurality of power supply lines is formed by a sputtering method or a CVD method.

Here, the CVD method includes a plasma CVD method (an RF plasma CVD method, a microwave CVD method, an electron cyclotron resonant CVD method, a thermal filament CVD method and the like), an LPCVD method, and a thermal CVD method.

The invention is a personal computer using the display device in accordance with the aforementioned configuration of the invention.

The invention is a television receiver using the display device in accordance with the aforementioned configuration of the invention.

The invention is a camera such as a video camera using the display device in accordance with the aforementioned configuration of the invention.

The invention is an image reproducing device using the display device in accordance with the aforementioned configuration of the invention.

The invention is a head mounted display using the display device in accordance with the aforementioned configuration of the invention.

The invention is a portable information terminal using the display device in accordance with the aforementioned configuration of the invention.

According to the invention, a large and high resolution EL display device with favorable yield which can be manufactured at low cost can be provided. Further, as sufficient signal write time can be obtained, signals can be accurately inputted to pixels, thereby a clear image can be displayed. Further, as

an effect of wiring resistance can be lessened, image quality defect due to wiring resistance can be reduced.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1 is a diagram showing a pixel circuit of an EL display device.

FIG. 2 is a diagram showing a driving timing of an analog drive.

FIG. 3 is a diagram showing characteristics of a driving TFT.

FIG. 4 is a diagram showing a cross talk by a box display.

FIGS. 5A and 5B are diagrams showing potential effects due to wiring resistance of a power supply line.

FIGS. 6A to 6C are diagrams showing structures to reduce parasitic capacitance between wirings.

FIGS. 7A to 7D are diagrams showing shapes which cause variations in wiring resistance.

FIG. 8 is a diagram showing Embodiment Mode 1 of the invention.

FIG. 9 is a diagram showing Embodiment Mode 2 of the invention.

FIG. 10 is a diagram showing Embodiment Mode 3 of the invention.

FIG. 11 is a diagram showing Embodiment Mode 4 of the invention.

FIG. 12 is a diagram showing Embodiment Mode 5 of the invention.

FIGS. 13A to 13D are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 14A and 14B are views showing a manufacturing method of a display device to which the invention can be applied.

FIG. 15 is a view showing a configuration of a droplet discharging apparatus which can be applied to the invention.

FIG. 16A is a top plan view of a pixel portion of a display device which can be applied to the invention, and FIG. 16B is a circuit diagram thereof.

FIG. 17 is a view showing a display device which can be applied to the invention.

FIGS. 18A to 18D are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 19A and 19B are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 20A to 20D are views showing a manufacturing method of a display device to which the invention can be applied.

FIG. 21 is a view showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 22A to 22D are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 23A and 23B are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 24A to 24D are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 25A and 25B are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 26A to 26D are views showing a manufacturing method of a display device to which the invention can be applied.

FIG. 27 is a view showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 28A to 28D are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 29A and 29B are views showing a manufacturing method of a display device to which the invention can be applied.

FIGS. 30A to 30C are views showing a display device to which the invention can be applied.

FIG. 31 is a top plan view of a panel which is one mode of a semiconductor device to which the invention is applied.

FIG. 32 is a block diagram showing a major configuration of an electronic device of the invention.

FIG. 33 is a view showing an electronic device to which the invention is applied.

FIGS. 34A to 34C are views showing electronic devices to which the invention is applied.

FIGS. 35A to 35C are views showing electronic devices to which the invention is applied.

BEST MODE FOR CARRYING OUT THE INVENTION

Although the invention will be fully described by way of embodiment modes with reference to the accompanying drawings, it is to be understood that various changes and modifications will be apparent to those skilled in the art. Therefore, unless otherwise such changes and modifications depart from the scope of the invention, they should be construed as being included therein. Note that identical portions or portions having the identical function in embodiment modes are denoted by the same reference numerals and detailed descriptions thereof are omitted.

A transistor used for the invention is not exclusively limited to a certain type. It may be a thin film transistor (TFT) using a non-single crystalline semiconductor film represented by amorphous silicon or polycrystalline silicon, a MOS transistor formed by using a semiconductor substrate or an SOI (Silicon On Insulator) substrate, a junction transistor, a bipolar transistor, a transistor using an organic semiconductor, a carbon nanotube, or the like. Furthermore, a substrate on which a transistor is mounted is not exclusively limited to a certain type. It may be a single crystalline substrate, an SOI substrate, a glass substrate, and the like.

Embodiment Mode 1

Description is made with reference to FIGS. 13A to 16B, 8, and 6A to 6C on an embodiment mode of the invention. First, it is one of the objects of the invention to manufacture an EL display device at low cost. In view of this, a TFT is manufactured by reducing the number of photolithography steps.

As a method for reducing the number of photolithography steps, a method for manufacturing a display device is suggested that one or more of patterns required for manufacturing a display panel, such as a conductive layer for forming a wiring layer or an electrode or a mask layer for forming a predetermined pattern is formed by a method which can selectively form a pattern. As the method which can selectively form a pattern, a droplet discharging method (also referred to as an ink-jetting method depending on the system) is suggested which can form a predetermined pattern by selectively discharging droplets of a composition which is blended for a specific purpose. Further, by employing a method for transferring or drawing a pattern, for example a printing method (a method for forming a pattern by screen

printing, offset printing and the like) and the like, cost reduction can be achieved. That is, one of the problems in manufacturing an EL display device at low cost is the large number of photolithography steps. In view of this, the number of photolithography steps is required to be as small as possible, for which the method which can selectively form a pattern is effective.

Therefore, in this embodiment mode, an EL display device is manufactured by the droplet discharging method as one of manufacturing methods of an EL display device which can selectively form a pattern that is described below. Note that this is only an example and this embodiment mode is not limited to this method.

First, description is made with reference to FIGS. 13A to 14B on a manufacturing method of a display device including a channel protective type thin film transistor of which gate electrode, a source or drain wiring are manufactured by a means to improve adhesiveness.

A base film **801** to improve adhesiveness is formed over a substrate **800** as pre-base treatment. The substrate **800** is formed of a glass substrate such as a barium borosilicate glass and aluminoborosilicate glass, a quartz substrate, a silicon substrate, a metal substrate, a stainless substrate, or a plastic substrate with heat resistance to the processing temperature of the step in this embodiment mode. A surface of the substrate **800** may be planarized by polishing by a CMP (Chemical Mechanical Polishing) method and the like. An insulating layer may be formed over the substrate **800**. The insulating layer is formed by a known method such as the CVD method, the plasma CVD method, the sputtering method, or a spin coating method using an oxide material and a nitride material each containing silicon in a single layer or stacked layers. This insulating layer is not necessarily provided, but has an effect to block a contaminant and the like from the substrate **800**. In the case of forming a base layer for preventing contamination from a glass substrate, the base film **801** is formed as pre-treatment for conductive layers **802** and **803** which are formed over the base layer by the droplet discharging method.

FIG. 15 shows one mode of the droplet discharging apparatus used for forming a pattern. Each head **905** of a droplet discharging unit **903** is connected to a control unit **907**. A computer **910** controls the control unit **907**, thereby a programmed pattern can be drawn. A timing to draw may be determined, for example, on the basis of a marker **911** formed on a substrate **900**. Alternatively, a base point may be determined on the basis of the edges of the substrate **900**. This is detected by an image pickup unit **904** such as a CCD, and converted into a digital signal by an image processing unit **909**. The computer **910** recognizes the digital signal and generates a control signal which is sent to the control unit **907**. It is needless to say that data on patterns to be formed over the substrate **900** is stored in a memory medium **908**, on the basis of which a control signal is sent to the control unit **907** and thus each head **905** of the droplet discharging unit **903** can be controlled independently. Using one head can discharge and draw each of a conductive material, an organic material, an inorganic material and the like. In the case of drawing in a wide region such as an interlayer film, the same material can be discharged to be drawn from a plurality of nozzles at the same time to improve throughput. In the case of using a large substrate, the head **905** freely scans over a substrate and freely set a region to draw, thereby a plurality of the same patterns can be drawn over one substrate.

In this embodiment mode, a substance having a photocatalytic function is used as the base film having a function to improve adhesiveness. The photocatalytic substance can be formed by a sol-gel method such as a dip coating method, a

spin coating method, the droplet discharging method, or an ion plating method, an ion beam method, the CVD method, the sputtering method, an RF magnetron sputtering method, a plasma spray method, or an anodic oxidation method. In addition, the photocatalytic substance does not need to have continuity as a film, depending on its formation method. The photocatalytic substance can be formed by mixing and melting a salt of a constituent element, in the case of a photocatalytic substance formed of an oxide semiconductor including a plurality of metals. A solvent may be baked or dried when it is necessary to be removed in the case of forming the photocatalytic substance by an application method such as the dip coating method or the spin coating method. Specifically, it may be heated at a predetermined temperature (for example, 300° C. or higher), preferably, in an atmosphere including oxygen. For example, baking is performed using Ag as a conductive paste in an atmosphere including oxygen and nitrogen, then, an organic material such as a heat curable resin is decomposed. Therefore, Ag without containing an organic material can be obtained. Accordingly, planarity of the surface of Ag can be enhanced.

According to the thermal treatment, the photocatalytic substance can have a predetermined crystalline structure. For example, it has an anatase type or a rutile-anatase mixed type. The anatase type is formed by priority in a low temperature phase. Therefore, the photocatalytic substance may also be heated when it does not have a predetermined crystalline structure. In addition, the photocatalytic substance can be formed a plurality of times to obtain a predetermined film thickness in the case of forming by an application method.

The case of forming TiO_x (typically, TiO_2) crystal having a predetermined crystalline structure by the sputtering method as a photocatalytic substance is described in this embodiment mode. Sputtering is performed using a metal titanium tube as a target and using an argon gas and oxygen. Further, a He gas may be introduced. The atmosphere includes much oxygen and formation pressure is set high to form TiO_x having high photocatalytic activity. It is preferable to form TiO_x while heating a deposition chamber or a substrate provided with an object to be treated.

The thus formed TiO_x has a photocatalytic function even when it is a very thin film (about 1 nm to 1 μm).

Further, it is preferable to form the base film **801** formed of a metal material such as Ti (titanium), W (tungsten), Cr (chromium), Ta (tantalum), Ni (nickel), or Mo (molybdenum), or oxide thereof by the sputtering method, a vapor deposition method, or the like as another pre-base treatment.

The base film **801** may be formed to be 0.01 to 10 nm in thickness. It does not necessarily have a layer structure as long as it is formed quite thin. When a high-melting point metal material is used as the base film, it is preferable to treat a base film exposed on the surface by carrying out one of the following two steps after forming the conductive layers **802** and **803** to be a gate electrode layer.

The first method is a step of insulating the base film **801** which is not overlapped with the conductive layers **802** and **803** and forming an insulating layer. In other words, the base film **801** which is not overlapped with the conductive layers **802** and **803** is oxidized and insulated. When the base film **801** is oxidized and insulated in this manner, it is preferable to form the base film **801** to be 0.01 to 10 nm in thickness, thus, the base film can be easily oxidized. Note that oxidation may be performed by exposure to an oxygen atmosphere or thermal treatment.

The second method is a step of removing the base film **801** by etching using the conductive layers **802** and **803** as masks.

When this step is employed, there is no limitation in the thickness of the base film **801**.

Alternatively, a method for performing plasma treatment onto a formation region (formation face) can be employed as another pre-base treatment. The plasma treatment is performed with air, oxygen, or nitrogen used as a treatment gas, with pressure from several ten Torr to 1000 Torr (133000 Pa), preferably, from 100 Torr (13300 Pa) to 1000 Torr (133000 Pa), more preferably, from 700 Torr (93100 Pa) to 800 Torr (106400 Pa), that is, atmospheric pressure or pressure in proximity of atmospheric pressure, and a pulse voltage is applied with such conditions. At this time, plasma density is set at 1×10^{10} to $1 \times 10^{14} \text{ m}^{-3}$, so that so-called corona discharge or glow discharge is achieved. Surface modification can be performed without material dependence by employing plasma treatment using air, oxygen, or nitrogen as the treatment gas. Accordingly, surface modification can be performed on any material.

As another method, a substance of an organic material functioning as an adhesive may be formed to improve adhesion between a pattern to be formed by the droplet discharging method and a formation region thereof. An organic material (organic resin material) (polyimide or acrylic) or a siloxane may be used. Note that the siloxane is composed of a skeleton formed of the bond of silicon (Si) and oxygen (O), in which an organic group containing at least hydrogen (such as an alkyl group or aromatic hydrocarbon) is included as a substituent. Alternatively, a fluoro group may be used as the substituent. Further alternatively, a fluoro group and an organic group containing at least hydrogen may be used as the substituent.

Subsequently, a composition containing a conductive material is discharged, and the conductive layers **802** and **803** to function as gate electrodes later are formed.

The droplet discharging unit is a collective term for the one having a unit for discharging a droplet such as a nozzle having a discharging opening of a composition or a head provided with one or a plurality of nozzles. A diameter of the nozzle included in the droplet discharging unit is set in the range of 0.02 to 100 μm (favorably, 30 μm or less) and a volume of the composition to be discharged from the nozzle is set in the range of 0.001 to 100 pl (favorably, 10 pl or less). The volume of the composition to be discharged increases in proportion to the diameter of the nozzle. Further, it is preferable that a distance between an object to be treated and the discharging openings of the nozzle be as short as possible in order to drop the droplet on a desired position. The distance is favorably set in the range of about 0.1 to 3 mm (more favorably, 1 mm or less).

As for the composition to be discharged from the discharging opening, a conductive material dissolved or dispersed in a solvent is used. The conductive material corresponds to a fine particle or a dispersant nano-particle of a metal such as Ag, Au, Cu, Ni, Pt, Pd, Ir, Rh, W, or Al, sulfide of a metal such as Cd or Zn, oxide of Fe, Ti, Si, Ge, Zr, or Ba, or silver halide. In addition, it corresponds to indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), organic indium, organotin, zinc oxide, titanium nitride, or the like which is used as a light-transmissive conductive film. However, as for compositions to be discharged from the discharging opening, it is preferable to use any material selected from gold, silver, and copper, which is dissolved or dispersed in a solvent, in consideration of resistivity. It is more preferable to use silver or copper having a low resistance value. When silver or copper is used, a barrier film may be additionally provided as a measure for an impurity. A silicon nitride film or nickel boron (NiB) can be used as the barrier film.

In addition, a particle having a plurality of layers formed by coating the periphery of the conductive material with another conductive material may be used. For example, a particle having a three-layer structure in which copper is coated with nickel boron (NiB) and then silver, and the like may be used. As for such solvents, esters such as butyl acetate and ethyl acetate; alcohols such as isopropyl alcohol and ethyl alcohol; organic solvents such as methyl ethyl ketone and acetone; or the like may be used. The viscosity of the composition is preferably 50 mPa·S (cps) or less. This is because the composition is prevented from drying or the composition is smoothly discharged from the discharging opening. The surface tension of the composition is preferably 40 mN/m or less. Note that the viscosity of the composition and the like may be appropriately adjusted in accordance with a solvent to be used and intended use. For example, the viscosity of a composition in which ITO, organic indium, or organotin is dissolved or dispersed in the solvent is 5 to 50 mPa·S, the viscosity of a composition in which silver is dissolved or dispersed in the solvent is 5 to 20 mPa·S, and the viscosity of a composition in which gold is dissolved or dispersed in the solvent is 10 to 20 mPa·S.

The conductive layer may be formed by stacking a plurality of conductive materials. In addition, the conductive layer may be formed by the droplet discharging method using silver as a conductive material, thereafter, it may be plated with copper or the like. Plating may be performed by electroplating or a chemical (electroless) plating method. Plating may be performed by soaking a substrate surface into a container filled with a solution having a plating material. A solution having a plating material may be applied so that the solution flows over the substrate surface with the substrate placed obliquely (or vertically). When the plating is performed by applying a solution with the substrate placed vertically, there is an advantage in that a process apparatus can be downsized.

The diameter of a particle of the conductive material is preferably as small as possible for preventing clogged nozzles and manufacturing a high-definition pattern, although it depends on the diameter of each nozzle, a desired shape of a pattern, and the like. Preferably, the diameter of the particle of the conductive material is 0.1 μm or less. The composition is formed by a known method such as an electrolyzing method, an atomizing method, or a wet reducing method, and the particle size thereof is typically about from 0.01 to 10 μm . Note that when a gas evaporation method is employed, a nanomolecule protected with a dispersant is as minute as about 7 nm. When each surface of particles is covered with a coating, the nanoparticles do not cohere in the solvent and are uniformly dispersed in the solvent at a room temperature, and show a property similar to that of liquid. Accordingly, it is preferable to use a coating.

When the step of discharging the composition is performed under reduced pressure, the solvent of the composition is evaporated until the discharged composition lands on an object to be treated, and thus, later steps of drying and baking the composition can be both omitted. It is preferable to perform the step under reduced pressure, since an oxide film or the like is not formed on the surface of the conductor. After discharging the composition, either or both steps of drying and baking is/are performed. Each step of drying and baking is a step of thermal treatment. For example, drying is performed for three minutes at 100° C. and baking is performed for from 15 minutes to 30 minutes at a temperature of from 200 to 350° C., each of which has a different purpose, temperature, and period. The steps of drying and baking are performed under normal pressure or reduced pressure by laser light irradiation, rapid thermal annealing, a heating fur-

nance, or the like. Note that the timing of the thermal treatment is not particularly limited. The substrate may be heated in advance to favorably perform the steps of drying and baking. The temperature of the substrate at the time depends on a material of the substrate or the like, but it is typically 100 to 800° C. (preferably, 200 to 350° C.). According to these steps, nanoparticles contact with one another and fusion and welding are accelerated by hardening and shrinking a peripheral resin as well as evaporating the solvent in the composition or chemically removing the dispersant.

A continuous wave or pulsed wave gas laser or solid laser may be used for laser light irradiation. An excimer laser and the like can be given as a gas laser, and a laser using a crystal of YAG or YVO₄ which is doped with Cr, Nd, or the like can be given as a solid laser. Note that it is preferable to use a continuous wave laser in relation to the absorptance of laser light. Moreover, a so-called hybrid laser irradiation method in which a pulsed wave and a continuous wave are used in combination may be used. However, it is preferable that the thermal treatment by laser light irradiation be instantaneously performed within several microseconds to several ten seconds so that the substrate **800** is not damaged, depending on heat resistance of the substrate **800**. Rapid thermal annealing (RTA) is carried out by rapidly raising the temperature and heating for several microseconds to several minutes using an infrared lamp or a halogen lamp emitting light for irradiation with ultraviolet to infrared light in an inert gas atmosphere. Since the treatment is performed instantaneously, only a thin film on a top surface can be substantially heated and a lower layer film is not affected. In other words, even a substrate having low heat resistance such as a plastic substrate is not affected either.

In addition, the aforementioned step of forming the base film **801** is carried out as pre-base treatment for a conductive layer formed by the droplet discharging method, however, this treatment step may be carried out after forming the conductive layer.

Subsequently, a gate insulating layer is formed over the conductive layers **802** and **803** (see FIG. 13A). The gate insulating layer may be formed of a known material such as an oxide or nitride material of silicon, and may be stacked layers or a single layer. For example, it may be stacked layers of three layers of a silicon nitride film, a silicon oxide film, and a silicon nitride film, or may be a single layer of these or a silicon oxynitride film, or stacked layers of two layers. A silicon nitride film is used as an insulating layer **804** and a silicon nitride oxide film is used as a gate insulating layer **805** in this embodiment mode. A silicon nitride film having dense film quality is preferably used. In the case of using silver, copper, or the like for the conductive layer formed by the droplet discharging method, forming a silicon nitride film or a NiB film thereover as a barrier film is effective in preventing an impurity from diffusing and in planarizing the surface. Note that a rare gas element such as argon is preferably included in a reactive gas and is preferably mixed in the insulating film to be formed in order to form a dense insulating film with few gate leak current at a low film-formation temperature.

Subsequently, a conductive layer (also referred to as a first electrode) **806** is formed by selectively discharging a composition containing a conductive material over the gate insulating film (see FIG. 13B). The conductive layer **806** may be formed in a predetermined pattern of a composition containing indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), zinc oxide (ZnO), tin oxide (SnO₂), or the

like and by baking it when light is emitted from the substrate **800** side or when a light-transmissive EL display panel is manufactured.

Preferably, the conductive layer **806** is formed of indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), zinc oxide (ZnO), or the like by the sputtering method. It is more preferable to use indium tin oxide containing silicon oxide formed by the sputtering method using a target in which ITO contains silicon oxide of 2 to 10 wt %. In addition, an oxide conductive material formed using a target obtained by mixing zinc oxide (ZnO) of 2 to 20 wt % to indium oxide containing silicon oxide may be used. A mask layer may be formed by the droplet discharging method and be etched to have a desired pattern after forming the conductive layer (the first electrode) **806** by the sputtering method. In this embodiment mode, the conductive layer **806** is formed of a light-transmissive conductive material by the droplet discharging method. Specifically, it is formed of indium tin oxide or ITSO formed of ITO and silicon oxide. Although not shown, a photocatalytic substance may be formed in a region where the conductive layer **806** is formed, similarly to the case of forming the conductive layers **802** and **803**. The photocatalytic substance can improve adhesiveness and the conductive layer **806** can be formed into a desired pattern to be a thin line. The conductive layer **806** becomes the first electrode which functions as a pixel electrode.

In this embodiment mode, an example of the gate insulating layer formed of three layers of a silicon nitride film, a silicon oxynitride film (silicon oxide film), and a silicon nitride film which are formed of silicon nitride is described. The conductive layer (the first electrode) **806** formed of indium tin oxide containing silicon oxide is preferably formed in close contact with an insulating layer formed of silicon nitride included in the gate insulating layer **805**. Accordingly, a rate at which light generated in an electroluminescent layer is emitted outside can be enhanced.

In addition, a composition containing a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), or Al (aluminum) as its main component can be used when generated light is emitted to an opposite side of the substrate **800** or when a reflective EL display panel is manufactured. As another method, a first electrode layer may be formed by forming a light-transmissive conductive film or a light-reflective conductive film by the sputtering method, forming a mask pattern by the droplet discharging method, and additionally performing an etching process.

The conductive layer (the first electrode) **806** may be polished by a CMP method or by cleaning with a porous body of polyvinyl alcohol so that the surface thereof is planarized. Furthermore, the surface of the conductive layer (the first electrode) **806** may be irradiated with an ultraviolet ray or may be treated with oxygen plasma after polishing by the CMP method.

The semiconductor layer may be formed by a known method (the sputtering method, an LP (Low Pressure) CVD method, the plasma CVD method, or the like). There is no particular limitation in materials of the semiconductor layer, but the semiconductor layer is preferably formed of silicon, a silicon germanium (SiGe) alloy, or the like.

The semiconductor layer is formed of an amorphous semiconductor (typically, hydrogenated amorphous silicon) or a crystalline semiconductor (typically, polysilicon) as a material. Polysilicon includes so-called high-temperature polysilicon which has, as a main material, polycrystalline silicon formed through a process temperature of 800° C. or higher, so-called low-temperature polysilicon which has, as a main material, polycrystalline silicon formed at a process tempera-

ture of 600° C. or lower, crystalline silicon which is crystallized by adding, for example, an element for promoting crystallization, and the like.

Further, as another substance, a semi-amorphous semiconductor or a semiconductor containing a crystal phase in a part of a semiconductor layer can also be used. The semi-amorphous semiconductor means a semiconductor having an intermediate structure of an amorphous structure and a crystalline structure (including a single crystal and a poly-crystal) and having a third state which is stable in terms of free energy, and a crystalline semiconductor having short-range order and lattice distortion. Typically, it is a semiconductor layer containing silicon as a main component with lattice distortion, in which the Raman spectrum is shifted to a lower frequency side than 520 cm⁻¹. Further, hydrogen or halogen of at least 1 atomic % or more is contained therein to terminate a dangling bond. Here, such a semiconductor as described above is referred to as a semi-amorphous semiconductor (hereinafter, referred to as a "SAS"). The SAS is also referred to as a so-called microcrystal semiconductor (typically, microcrystalline silicon).

The SAS can be obtained by performing glow discharge decomposition (plasma CVD) on a silicon source gas. SiH₄ is given as a typical silicon source gas. Si₂H₆, SiH₂Cl₂, SiHCl₃, SiCl₄, SiF₄, or the like can be used as well. Further, GeF₄ or F₂ may be mixed. Formation of the SAS can be facilitated by using the silicon source gas diluted with hydrogen or a mixture of hydrogen and one or more of rare gases selected from helium, argon, krypton, and neon. A dilution ratio of hydrogen to the silicon source gas is, for example, preferably in the range of 2 to 1000 times in terms of a flow ratio. Although formation of the SAS by glow discharge decomposition is preferably performed under reduced pressure, the formation can also be performed by utilizing an electric discharge under atmospheric pressure. Typically, the formation may be performed in the pressure range of 0.1 to 133 Pa. A power supply frequency for generating the glow discharge is in the range of 1 to 120 MHz, preferably, in the range of 13 to 60 MHz. A high-frequency power supply may appropriately be set. A temperature for heating the substrate is preferably 300° C. or less and the temperature in the range of 100 to 200° C. may also be employed. As for impurity elements to be contained mainly at the time of forming a film, an impurity derived from an atmospheric constituent such as oxygen, nitrogen, or carbon is preferably in a concentration of 1×10²⁰ cm⁻³ or less, and particularly, a concentration of oxygen is 5×10¹⁹ cm⁻³ or less, preferably, 1×10¹⁹ cm⁻³ or less. Further, stability of the SAS can be enhanced by promoting the lattice distortion by allowing a rare gas element such as helium, argon, krypton, or neon to be contained, thereby forming a favorable SAS. In addition, an SAS layer formed of a hydrogen-based gas may be stacked over a SAS layer formed of a fluorine-based gas as the semiconductor layer.

When a crystalline semiconductor layer is used as the semiconductor layer, a known method (a laser crystallization method, a thermal crystallization method, a thermal crystallization method using an element promoting crystallization such as nickel, or the like) may be employed as a method for manufacturing the crystalline semiconductor layer. In the case where an element promoting crystallization is not introduced, hydrogen is released until hydrogen concentration contained in an amorphous silicon film becomes 1×10²⁰ atoms/cm³ or less by heating the amorphous silicon film for one hour at a temperature of 500° C. in nitrogen atmosphere before irradiating the amorphous silicon film with laser light. This is because a film is damaged when the amorphous silicon film containing much hydrogen is irradiated with laser light.

There is no particular limitation in a method for introducing a metal element into the amorphous semiconductor layer as long as it is a method capable of making the metal element exist on the surface of or inside the amorphous semiconductor layer. For example, the sputtering method, the CVD method, a plasma treating method (including the plasma CVD method), an adsorption method, or a method for applying a metal salt solution can be employed. Among them, the method using a solution is simple and easy and is useful in terms of easy concentration adjustment of the metal element. It is preferable that an oxide film be formed by UV light irradiation in oxygen atmosphere, a thermal oxidation method, treatment with ozone water or hydrogen peroxide including a hydroxyl radical, or the like in order to improve wettability of the surface of the amorphous semiconductor layer and to spread an aqueous solution over an entire surface of the amorphous semiconductor layer.

In addition, thermal treatment and laser light irradiation may be combined to crystallize the amorphous semiconductor layer. The thermal treatment and/or the laser light irradiation may be independently performed a plurality of times.

An organic semiconductor using an organic material may be used as a semiconductor. A low molecular weight material, a high molecular weight material, or the like is used for the organic semiconductor, and in addition, a material such as an organic pigment, a conductive high molecular weight material can be used.

An amorphous semiconductor is used as the semiconductor in this embodiment mode. A semiconductor layer **807** that is an amorphous semiconductor layer is formed, and an insulating film is formed by, for example, the plasma CVD method and is etched selectively to have a desired shape in a desired region in order to form channel protective films **809** and **810**. At this time, the channel protective films **809** and **810** can be formed by exposing a back of the substrate to light using the gate electrodes as masks. In addition, polyimide, polyvinyl alcohol, or the like may be dropped as the channel protective film by the droplet discharging method. Consequently, the light-exposure step can be omitted. Then, an N-type semiconductor layer **808** is formed using a semiconductor layer having one conductivity, for example, an N-type amorphous semiconductor layer by the plasma CVD method or the like (see FIG. 13C). The semiconductor layer having one conductivity may be formed as required.

A film formed of one or a plurality of inorganic materials (silicon oxide, silicon nitride, silicon oxynitride, silicon nitride oxide, and the like), photosensitive or non-photosensitive organic materials (organic resin materials) (polyimide, acrylic, polyamide, polyimide amide, a resist, benzocyclobutene, and the like), a Low-k material having a low dielectric constant, and the like, or stacked layers of them can be used as the channel protective film. In addition, a material in which a skeletal structure is configured by the bond of silicon (Si) and oxygen (O) and which contains at least hydrogen as a substituent (for example, alkyl group or aromatic hydrocarbon) may be used. Alternatively, a fluoro group may be used as the substituent. Further alternatively, a fluoro group and an organic group containing at least hydrogen may be used as the substituent. A vapor phase growth method such as the plasma CVD method or the thermal CVD method or the sputtering method can be employed as a manufacturing method to use an inorganic material as a channel protective film. In addition, in the case of using an organic material, the droplet discharging method or the printing method (a method for forming a pattern, such as screen printing or offset printing) can be employed. An insulating film, an SOG film, or the like obtained by an application method can be used.

Subsequently, mask layers **811** and **812** formed of an insulator such as a resist or polyimide are formed. Then, the semiconductor layer **807** and the N-type semiconductor layer **808** are simultaneously patterned using the mask layers **811** and **812**.

Then, mask layers **813** and **814** formed of an insulator such as a resist or polyimide are formed by the droplet discharging method (see FIG. 13D). A through-hole **818** is formed in a part of the gate insulating layers **804** and **805** by an etching process using the mask layers **813** and **814**, and a part of the conductive layer **803** which is disposed on a lower layer side thereof and functions as a gate electrode layer is exposed. Either plasma etching (dry etching) or wet etching may be adopted as the etching process. However, plasma etching is suitable to treat a large substrate. A fluorine-based or chlorine-based gas such as CF_4 , NF_3 , Cl_2 , or BCl_3 is used as an etching gas, and an inert gas such as He or Ar may be appropriately added. In addition, a local discharge process can be performed when an atmospheric pressure discharge etching process is applied, and a mask layer is not required to be entirely formed over the substrate.

Conductive layers **815**, **816**, and **817** are formed by discharging a composition containing a conductive material after the mask layers **813** and **814** are removed. Then, the N-type semiconductor is patterned using the conductive layers **815**, **816**, and **817** as masks to form an N-type semiconductor layer (see FIG. 14A). The conductive layers **815**, **816**, and **817** function as wiring layers. Note that the above-mentioned pre-base treatment of selectively forming a photocatalytic substance or the like in a portion where the conductive layers **815**, **816**, and **817** are in contact with the gate insulating layer **805** may be performed before forming the conductive layers **815**, **816**, and **817**, although not shown. Accordingly, the conductive layer can be formed with favorable adhesiveness.

The above-mentioned step of forming the base film may be performed as pre-base treatment for the conductive layer to be formed by the droplet discharging method. In addition, the treatment step may be performed after the conductive layer is formed. Reliability of a display device can be improved since adhesion between the layers is improved in accordance with this step.

The conductive layer **817** functions as a source wiring layer or a drain wiring layer and is formed to be electrically connected to the first electrode formed before. In addition, the conductive layer **816** that is the source wiring layer or the drain wiring layer and the conductive layer **803** that is a gate electrode layer are electrically connected to each other in the through-hole **818** formed in the gate insulating layer **805**. A composition containing a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), or Al (aluminum) as its main component can be used as a conductive material for forming the wiring layer. In addition, light-transmissive indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), organic indium, organotin, zinc oxide, titanium nitride, and the like may be used in combination.

The step of forming the through-hole **818** in a part of the gate insulating layers **804** and **805** may be performed after forming the conductive layers **815**, **816**, and **817**, using the conductive layers **815**, **816**, and **817** as a mask to form the through-hole **818**. Then, a conductive layer is formed in the through-hole **818**, and the conductive layer **816** and the conductive layer **803** that is a gate electrode layer are electrically connected to each other. In this case, there is an advantage in that the steps can be simplified.

Subsequently, an insulating layer **820** to be a partition wall is formed. Although not shown, a protective layer formed of

silicon nitride or silicon nitride oxide may be entirely formed under the insulating layer **820** to cover a thin film transistor. An opening is formed in the insulating layer **820** as shown in FIG. 14B by an etching process after the insulating layer is entirely formed by the spin coating method or a dipping method. The etching process is not necessarily carried out when the insulating layer **820** is formed by the droplet discharging method. When a wide region such as the insulating layer **820** is formed by the droplet discharging method, it is formed by discharging a composition from a plurality of discharging openings of nozzles of a droplet discharge apparatus and by drawing so that a plurality of lines are overlapped with each other. Consequently, a throughput is improved.

The insulating layer **820** is formed to have a through-hole corresponding to a position where a pixel is to be formed in accordance with the conductive layer **806** that is the first electrode. The insulating layer **820** can be formed by using an inorganic insulating material such as silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, or aluminum oxynitride, acrylic acid, methacrylic acid, a derivative of acrylic acid or methacrylic acid, a heat-resistant high molecular weight material such as polyimide, aromatic polyamide, or polybenzimidazole, or inorganic siloxane including a Si—O—Si bond among compounds that contain silicon, oxygen, and hydrogen and that is formed by using a siloxane material as a starting material or an organosiloxane-based insulating material in which hydrogen bonded with silicon is substituted by an organic group such as methyl or phenyl. It is preferable to form the insulating layer **820** by using a photosensitive or non-photosensitive material such as acrylic or polyimide since a side face thereof becomes such a shape that a curvature radius continuously changes and an upper-layer thin film is formed without break.

According to the above-mentioned steps, a TFT substrate for the EL display panel in which a bottom gate type (also referred to as an inversely staggered type) channel protective TFT and the first electrode (first electrode layer) are connected over the substrate **800** is completed.

Moisture adsorbed inside the insulating layer **820** or to a surface thereof is removed by performing thermal treatment at 200° C. under atmospheric pressure before forming an electroluminescent layer **821**. In addition, thermal treatment is performed at a temperature of 200 to 400° C., preferably, 250 to 350° C. under reduced pressure, and the electroluminescent layer **821** is preferably formed by a vacuum vapor deposition method or the droplet discharging method under reduced pressure without being exposed to atmospheric air.

Materials which emit light of red (R), green (G), and blue (B) are selectively formed as the electroluminescent layer **821** by a vapor deposition method or the like using respective vapor-deposition mask. The materials which emit light of red (R), green (G), and blue (B) (a low molecular weight or high molecular weight material, or the like) can be formed by the droplet discharging method similarly to a color filter. This case is preferable since RGB can be separately deposited without using a mask. A conductive layer **822** that is a second electrode is stacked over the electroluminescent layer **821**, and then, a display device having a display function using a light emitting element is completed (see FIG. 14B).

It is effective to provide a passivation film to cover the second electrode, although not shown. The passivation film is formed of an insulating film containing silicon nitride (SiN), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y ; $x>y>0$), silicon nitride oxide (SiN_xO_y ; $x>y>0$), aluminum nitride (AlN), aluminum oxynitride (AlO_xN_y ; $x>y>0$), aluminum nitride oxide (AlN_xO_y ; $x>y>0$) having larger nitrogen content than oxygen content, aluminum oxide, diamond like carbon

(DLC), or a nitrogen-containing carbon film (CN_x), and a single layer or combined stacked layers of the insulating film can be used. For example, stacked layers of a nitrogen-containing carbon film (CN_x) and silicon nitride (SiN), or an organic material can be used, and stacked layers of a high molecular weight material such as a styrene polymer may be used. A siloxane resin may be used as well. Siloxane is composed of a skeleton formed of the bond of silicon (Si) and oxygen (O), in which an organic group containing at least hydrogen (such as an alkyl group or aromatic hydrocarbon) is included as a substituent. Alternatively, a fluoro group may be used as the substituent. Further alternatively, a fluoro group and an organic group containing at least hydrogen may be used as the substituent.

In this case, a film having favorable coverage is preferably used as the passivation film, and it is effective to use a carbon film, specifically, a DLC film. Since the DLC film can be formed at a temperature ranging from a room temperature to nor or lower, it can be easily formed over the electroluminescent layer having low heat resistance. The DLC film can be formed by the plasma CVD method (typically, the RF plasma CVD method, a microwave CVD method, an electron cyclotron resonance (ECR) CVD method, a hot filament CVD method, or the like), a combustion flame method, the sputtering method, an ion beam vapor deposition method, a laser vapor deposition method, or the like. As a reactive gas to be used for film formation, a hydrogen gas and a hydrocarbon gas (for example, CH₄, C₂H₂, C₆H₆, or the like) are used. The gases are ionized by glow discharge, and ions are accelerated to collide against a cathode, to which a negative self-bias is applied, thereby a film is formed. In addition, a CN film may be formed using a C₂H₄ gas and an N₂ gas as a reactive gas. The DLC film has a high blocking effect against oxygen and can suppress oxidation of the electroluminescent layer. Therefore, a problem in that the electroluminescent layer is oxidized can be prevented during the following sealing step.

FIG. 16A is a top plan view of a pixel portion of a display device of this embodiment mode and FIG. 16B shows a circuit diagram thereof. Reference numerals **1001** and **1002** denote TFTs, **1003** denotes a light emitting element, **1004** denotes a capacitor, **1005** denotes a source line, **1006** denotes a gate line, and **1007** denotes a power supply line. The TFT **1001** is a transistor (hereinafter also referred to as a "switching transistor" or a "switching TFT") which controls a connection with the signal line. The TFT **1002** is a transistor (hereinafter also referred to as a "driving transistor" or a "driving TFT") which controls a current flowing to the light emitting element, and the driving TFT is connected in series with the light emitting element. The capacitor **1004** holds source-gate voltage of the TFT **1002** that is the driving TFT.

FIG. 17 is a detailed diagram of the display device of this embodiment mode. A substrate **800** having the switching TFT **1001** and the TFT **1002** that is a driving TFT connected to the light emitting element **1003** is firmly fixed to a sealing substrate **850** by a sealing material **851**. Various signals supplied to each circuit formed over the substrate **800** are supplied from a terminal portion.

A gate wiring layer **860** is formed in the terminal portion in the same step as the conductive layers **802** and **803**. It is needless to say that a photocatalytic substance is formed in a formation region of the gate wiring layer **860** similarly to the conductive layers **802** and **803**. When the photocatalytic substance is formed by the droplet discharging method, adhesion between the gate wiring layer **860** and a formation region of a base can be improved. Etching which exposes the gate wiring layer **860** can be simultaneously performed when the through-hole **818** is formed in the gate insulating layer **805**. A

flexible printed circuit (FPC) **862** can be connected to the gate wiring layer **860** by an anisotropic conductive layer **868**.

Note that the case where the light emitting element **1003** is sealed with the glass substrate is shown in the aforementioned display device. Sealing treatment is treatment for protecting the light emitting element from moisture. Any one of a method for sealing mechanically with a cover material, a method for sealing with a heat curable resin or a UV curable resin, and a method for sealing with a thin film having high barrier property such as metal oxide or nitride is employed. Glass, ceramics, plastic, or metal can be used as the cover material, and the cover material is required to transmit light when light is emitted to the cover material side. The cover material and the substrate over which the light emitting element is formed are attached to each other using a sealing material such as a heat curable resin or an ultraviolet curable resin. A sealed space is formed by curing the resin by thermal treatment or ultraviolet light irradiation treatment. It is also effective to provide a moisture absorbent material typified by barium oxide inside the sealed space. The moisture absorbent material may be provided over the sealing material in contact therewith, or in the periphery of the partition wall so as not to block light from the light emitting element. Furthermore, a space between the cover material and the substrate over which the light emitting element is formed can be filled with a heat curable resin or an ultraviolet curable resin. In this case, it is effective to add a moisture absorbent material typified by barium oxide into the heat curable resin or the ultraviolet curable resin.

As described above, the step can be omitted in this embodiment mode by not applying a light-exposure step utilizing a photo mask. In addition, an EL display panel can be easily manufactured by directly forming various patterns over a substrate by the droplet discharging method even when a glass substrate of the fifth or the following generation having a side of more than 1000 mm is used.

In addition, a highly reliable display device in which adhesiveness and peel resistance are improved can be manufactured.

FIGS. 8, 16A and 16B show circuit diagrams of a whole pixel portion of this embodiment mode. In this embodiment mode, a plurality of source signal lines are provided for one vertical column of pixels. In FIG. 8, description is made on an example where three source signal lines are provided for one vertical column of pixels.

It is to be noted that the number of the source signal lines is not limited to three and may be provided as many as required.

A circuit **854** of each pixel in FIG. 8 is described as a circuit shown in FIGS. 16A and 16B. However, this is only an example and a circuit in each pixel is not limited to the circuits in FIGS. 16A and 16B.

A pixel of row one and column one includes a gate signal line G1, a source signal line S1a which is one of the three source signal lines, a power supply line V1, a switching TFT **1001**, a driving TFT **1002**, an EL element **1003**, and a capacitor **1004**.

A connection between the pixel and circuit is described. The gate signal line G1 is connected to a gate electrode of the switching TFT **1001** and the source signal line S1a which is one of the three source signal lines is connected to a source electrode or a drain electrode of the switching TFT **1001**, the power supply line V1 is connected to a source electrode or a drain electrode of the driving TFT **1002** and one electrode of the capacitor **1004**. The other electrode of the capacitor **1004** is connected to the other of the source electrode and the drain electrode of the switching TFT **1002** and a gate electrode of

23

the driving TFT **1002**. The other of the source electrode and the drain electrode of the driving TFT **1002** is connected to the EL element **1003**.

Further, a pixel of row two and column one includes a gate signal line **G2**, a source signal line **S1b** which is one of the three source signal lines, the power supply line **V1**, the switching TFT **1001**, the driving TFT **1002**, the EL element **1003**, and the capacitor **1004**.

The pixel of row two and column one is different from the pixel of row one and column one in that **G2** is used instead of **G1** and **S1b** is used instead of **S1a**.

A pixel of row three and column one includes a gate signal line **G3**, a source signal line **S1c** which is one of the three signal lines, the power supply line **V1**, the switching TFT **1001**, the driving TFT **1002**, the EL element **1003**, and the capacitor **1004**.

The pixel of row three and column one is different from the pixel of row one and column one in that **G1** is used instead of **G3** and **S1c** is used instead of **S1a**.

Further, in the three pixel columns described above, **G1**, **G2**, and **G3** are electrically connected.

Further, the pixels of column one are the repetition of the aforementioned structure.

Further, the pixels of column two is different from the aforementioned structure in that **V2** is used instead of **V1**, **S2a** is used instead of **S1a**, **S2b** is used instead of **S1b**, and **S2c** is used instead of **S1c**.

Further, the pixels of column n is different from the aforementioned structure in that **Vn** is used instead of **V1**, **Sna** is used instead of **S1a**, **Snb** is used instead of **S1b**, and **Snc** is used instead of **S1c**.

Further, **V1** to **Vn** are all electrically connected to each other.

Next, description is made on how to operate the circuit of FIG. **8**. First, the gate signal lines **G1**, **G2**, and **G3** are turned on at the same time. While the gate signal lines **G1**, **G2**, and **G3** are on, signals are written to the pixels from the source signal lines **S1a**, **S1b**, **S1c**, **Sna**, **Snb**, and **Snc**. Then, gate signal lines **G4**, **G5**, and **G6** are turned on at the same time. While the gate signal lines **G4**, **G5**, and **G6** are on, signals are written to the pixels from the source signal lines **S1a**, **S1b**, **S1c**, ..., **Sna**, **Snb**, and **Snc**. These operations are repeated up to gate signal lines **Gm-2**, **Gm-1**, and **Gm**. The signals for one image can be written by the aforementioned operations.

When operating in this manner that the three gate signal lines operate as one group, therefore, the gate signal line is turned on three times as long as a circuit having only one signal line. That is, the problem that the write time is required to be as long as possible can be resolved.

In the case of connecting as shown in FIG. **8**, however, parasitic capacitance between wirings may increase in some cases.

Accordingly, a process may be devised by utilizing the advantage of the method which can selectively form a pattern in addition to the structure of FIG. **8**. In order to describe this, FIGS. **6A** to **6C** are referred as diagrams showing cross sections along a line **855**.

FIGS. **6A** to **6C** show a process applied to the substrate over which the gate insulating layer **805** is formed in the aforementioned TFT forming steps (FIG. **13A**). There is no semiconductor layer in the cross section **855**, therefore, a conductive layer is normally formed after forming a gate insulating layer **605** (FIG. **6A**). In this embodiment mode, however, a portion of the insulating layer over which the three source signal lines are formed is further selectively formed into a pattern by the droplet discharging method after forming

24

the gate insulating layer **605** (FIG. **6B**). After that, a conductive layer is formed as described above to form a pattern (FIG. **6C**).

By performing such a process, the three source signal lines are formed with and without an insulating layer **606**. In this structure, a distance between wirings is longer than the case with no insulating layer **606**, and thus parasitic capacitance between the wirings can be reduced. That is, the problem that parasitic capacitance is required to be as little as possible can be achieved. Further, in the structure of this embodiment mode, the longer the wiring is, the larger the effect is.

It is to be noted in this embodiment mode that the place, number, shape, and the like of the insulating layer may be freely determined as long as the insulating layer is selectively formed to keep the distance between the wirings of the same layer long. Further, the wiring formed over the insulating layer which is selectively formed is not limited to the source signal line. An insulating layer can be formed as a gate signal line or a power supply line by a similar method and parasitic capacitance can be reduced.

Embodiment Mode 2

Description is made with reference to FIGS. **9**, **16A**, and **16B** on an embodiment mode of the invention.

In FIG. **9**, a circuit **954** in each pixel is described as the circuit shown in FIGS. **16A** and **16B**. However, this is only an example and the circuit in each pixel is not limited to the circuit in FIGS. **16A** and **16B**.

A pixel of row one and column one of the pixel portion includes the gate signal line **G1**, the source signal line **S1**, a power supply line **Vx1**, a power supply line **Vy1**, the switching TFT **1001**, the driving TFT **1002**, the EL element **1003**, and the capacitor **1004**.

Description is made on a connection between the pixel and circuit. The gate signal line **G1** is connected to the gate electrode of the switching TFT **1001**, the source signal line **S1** is connected to the source electrode or the drain electrode of the switching TFT **1001**, the power supply line **Vx1** is connected to the source electrode or the drain electrode of the driving TFT **1002** and one electrode of the capacitor **1004**. The power supply line **Vy1** is connected to the power supply line **Vx1** and the other electrode of the capacitor **1004** is connected to the other of the source electrode or the drain electrode of the switching TFT **1001** and the gate electrode of the driving TFT **1002**. The other of the source electrode or the drain electrode of the driving TFT **1002** is connected to the EL element **1003**.

A pixel of row two and column one of the pixel portion includes the gate signal line **G2**, the source signal line **S1**, the power supply line **Vx1**, the power supply line **Vy2**, the switching TFT **1001**, the driving TFT **1002**, the EL element **1003**, and the capacitor **1004**.

The pixel of row two and column one of the pixel portion is different from the pixel of row one and column one in that **G2** is used instead of **G1** and **Vy2** is used instead of **Vy1**.

Further, a pixel of row m and column one of the pixel portion includes a gate signal line **Gm**, the source signal line **S1**, the power supply line **Vx1**, a power supply line **Vym**, the switching TFT **1001**, the driving TFT **1002**, the EL element **1003**, and the capacitor **1004**.

Further, a pixel of row one and column n of the pixel portion is different from the pixel of row one and column one in that **Sn** is used instead of **S1** and **Vxn** is used instead of **Vx1**.

Further, a pixel of row m and column n of the pixel portion is different from the pixel of row one and column one in that **Sn** is used instead of **S1**, **Vxn** is used instead of **Vx1**, **Gm** is used instead of **G1**, and **Vym** is used instead of **Vy1**.

Further, Vx1 to Vxn and Vy1 to Vyn are all electrically connected to each other.

In this embodiment mode, power supply lines in the pixel portion are not only the wirings (Vx1 to Vxn) provided in parallel with the source signal lines (S1 to Sn) but also provided in a vertical direction or an almost vertical direction (Vy1 to Vym), thereby voltage is supplied from each direction to the source region or the drain region of the driving TFT **1002** of the pixel. The power supply lines provided in a vertical direction or an almost vertical direction (Vy1 to Vym) are connected to the power supply lines (Vx1 to Vxn) per pixel and the power supply lines are arranged in matrix. Accordingly, a current flowing through the EL element **1003** is supplied not only in a direction parallel to the source signal lines (S1 to Sn) but also in the vertical direction. Therefore, one of the problems to be solved in the invention that wiring resistance is required to be as low as possible can be resolved.

As wiring resistance can be low, a cross talk which occurs when an EL display device is driven by the analog driving method is reduced. Further, a gray scale display defect can be reduced which occurs when an EL display device operates by the digital driving method and the constant voltage drive in combination.

However, it is one of the objects of this embodiment to manufacture an EL display device at low cost similarly to Embodiment Mode 1. Therefore, an EL display device may be manufactured through an EL display device manufacturing process by the droplet discharging method which is one of manufacturing methods of an EL display device capable of selectively forming a pattern.

Here, description is made on a problem in employing the droplet discharging method for cost reduction in manufacturing an EL display device.

FIGS. 7A to 7D are top plan views (A and B) and sectional views (C and D) of a conductive layer formed as a wiring by the droplet discharging method. When forming the conductive layer by discharging a composition containing a conductive material, the conductive layer may not be formed in a desired shape at a desired position depending on the characteristics of the conductive material to be discharged, water repellency of the base, an error of the discharged position and the like (see FIGS. 7B and 7D).

Here, resistance of wiring depends on the length of the wiring and the area of the cross section when using the same conductive material. In the case where a desired shape is not obtained as shown in FIGS. 7B and 7D, the resistance of the wiring becomes higher than the designed value. That is, the wiring formed by the droplet discharging method has more variations in wiring resistance as compared to a wiring formed by the photolithography method.

With high wiring resistance, a cross talk occurs in the case of using the analog driving method and a defect occurs in a gray scale display in the case of using the constant voltage drive in the digital driving method as described above. When the wiring resistance varies, display defects of the pixels differ depending on the power supply lines. This can be easily observed as display unevenness.

That is, one of the problems in using the droplet discharging method for cost reduction is the variations in wiring resistance. In view of this, variations in wiring resistance are required to be as little as possible.

Here, description is made in this embodiment mode on that variations in wiring resistance caused by the droplet discharging method can be reduced.

This can be described by considering all wiring resistance is connected in parallel when the power supply lines are arranged in matrix. That is, when the wiring resistance is

connected in parallel, resistance of the power supply line up to a certain pixel depends on the resistance of all the power supply lines and becomes less dependent on the position of resistance which exists in the case of non-matrix arrangement.

That is, according to this embodiment mode, the object that variations in wiring resistance in the case of using the droplet discharging method are required to be as little as possible can be resolved as well as reducing the wiring resistance of the power supply line can be reduced.

It is to be noted in this embodiment mode that wirings are not required to be provided in parallel to each other and may be provided in any directions. Further, the power supply line is not required to be only one in each pixel and may be provided as many as required. Furthermore, the power supply lines are not required to be arranged in matrix in all the pixel portion and may be arranged in matrix in a portion of the pixel portion.

Further, this embodiment mode can be freely implemented in combination with Embodiment Mode 1.

Embodiment Mode 3

Description is made with reference to FIGS. 10, 16A and 16B on an embodiment mode of the invention.

In FIG. 10, a circuit **1054** in each pixel is described as the circuit shown in FIGS. 16A and 16B. However, this is only an example and the circuit in each pixel is not limited to the circuit in FIGS. 16A and 16B.

A pixel of row one and column one of the pixel portion includes the gate signal line G1, the source signal line S1, the power supply line Vx1, a power supply line Vy1R, the switching TFT **1001**, the driving TFT **1002**, the EL element **1003**, and the capacitor **1004**.

Description is made on a connection between the pixel and circuit. The gate signal line G1 is connected to the gate electrode of the switching TFT **1001** and the source signal line S1 is connected to the source electrode or the drain electrode of the switching TFT **1001**. The power supply line Vx1 is connected to the source electrode or the drain electrode of the driving TFT **1002** and one electrode of the capacitor **1004**. The power supply line Vy1R is connected to the power supply line Vx1 and the other electrode of the capacitor **1004** is connected to the other of the source electrode or the drain electrode of the switching TFT **1001** and the gate electrode of the driving TFT **1002**. The other of the source electrode or the drain electrode of the driving **1002** is connected to the EL element **1003**.

Further, a pixel of row two and column one of the pixel portion includes the gate signal line G2, the source signal line S1, the power supply line Vx1, a power supply line Vy2R, the switching TFT **1001**, the driving TFT **1002**, the EL element **1003**, and the capacitor **1004**.

The pixel of row two and column one of the pixel portion is different from the pixel of row one and column one in that G2 is used instead of G1 and Vy2R is used instead of Vy1R.

Further, a pixel of row three and column one of the pixel portion is different from the pixel of row one and column one in that G3 is used instead of G1 and Vy3R is used instead of Vy1R.

Further, the pixels of column one of the pixel portion are the repetition of the structure of the aforementioned three rows.

Further, the pixel of row one and column two of the pixel portion is different from the pixel of row one and column one in that S2 is used instead of S1, Vx2 is used instead of Vx1, and Vy1G is used instead of Vy1R.

Further, the pixel of row two and column two of the pixel portion is different from the pixel of row one and column two in that G2 is used instead of G1 and Vy2G is used instead of Vy1G.

Further, a pixel of row three and column two of the pixel portion is different from the pixel of row one and column two in that G3 is used instead of G1 and Vy3G is used instead of Vy1G.

Further, the pixels of column two are the repetition of the structure of the aforementioned three rows.

Further, the pixel of row one and column three of the pixel portion is different from the pixel of row one and column one in that S3 is used instead of S1, Vx3 is used instead of Vx1, and Vy1B is used instead of Vy1R.

Further, the pixel of row two and column three of the pixel portion is different from the pixel of row one and column three in that G2 is used instead of G1 and Vy2B is used instead of Vy1B.

Further, the pixel of row three and column three of the pixel portion is different from the pixel of row one and column three in that G3 is used instead of G1 and Vy3B is used instead of Vy1B.

Further, the pixels of column three are the repetition of the structure of the aforementioned three rows.

Further, Vy1R to VymR are all electrically connected to each other.

Further, Vy1G to VymG are all electrically connected to each other.

Further, Vy1B to VymB are all electrically connected to each other.

In this embodiment mode, power supply lines of the pixel portion are not only the wirings (Vx1 to Vxn) provided in parallel with the source signal lines (S1 to Sn) but also provided in a vertical direction or an almost vertical direction (Vy1R to VymB), thereby voltage is applied from each direction to the source region or the drain region of the driving TFT 1002 in each pixel of R, G, and B respectively. The power supply lines provided in a vertical direction or an almost vertical direction (Vy1 to Vym) are connected to the power supply lines (Vx1 to Vxn) per pixel of R, G, and B and the power supply lines are arranged, in matrix. Accordingly, a current flowing through the EL element 1003 is supplied not only in a direction parallel to the source signal lines (S1 to Sn) but also in the vertical direction. Therefore, one of the problems to be solved in the invention that wiring resistance is required to be as low as possible can be resolved. Further, different levels of voltage may be applied to R, and B pixels which are connected independently.

As wiring resistance can be low, a cross talk which occurs when an EL display device is driven by the analog driving method is reduced. Further, a gray scale display defect can be reduced which occurs when an EL display device operates by the digital driving method and the constant voltage drive in combination.

However, it is one of the problems to be solved in this embodiment to manufacture an EL display device at low cost similarly to Embodiment Modes 1 and 2. Therefore, an EL display device may be manufactured through an EL display device manufacturing process by the droplet discharging method which is one of manufacturing methods of an EL display device capable of selectively forming a pattern.

In the case of forming wirings by the droplet discharging method, variations occur in wiring resistance as described above. According to this embodiment mode, variations in wiring resistance caused by the droplet discharging method can be reduced.

This can be described by considering all wiring resistance is connected in parallel when the power supply lines are arranged in matrix. That is, when the wiring resistance is connected in parallel, resistance of the power supply line up to a certain pixel depends on the resistance of all the power supply lines and becomes less dependent on the position of resistance which exists in the case of non-matrix arrangement.

That is, according to this embodiment mode, the problem that variations in wiring resistance in the case of using the droplet discharging method are required to be as little as possible can be resolved as well as reducing the wiring resistance of the power supply line can be reduced.

It is to be noted in this embodiment mode that wirings are not required to be provided in parallel to each other and may be provided in any directions. Further, the power supply line is not required to be only one in each pixel and may be provided as many as required. Furthermore, the power supply lines are not required to be arranged in matrix in all the pixel portion and may be arranged in matrix in a portion of the pixel portion.

Further, this embodiment mode can be freely implemented in combination with Embodiment Modes 1 and 2.

Embodiment Mode 4

Description is made with reference to FIGS. 11, 16A and 16B on an embodiment mode of the invention.

In FIG. 11, a circuit 1154 in each circuit is described as the circuit shown in FIGS. 16A and 16B. However, this is only an example and the circuit in each pixel is not limited to the circuit in FIGS. 16A and 16B.

A pixel of row one and column one includes the gate signal line G1, the source signal line S1, the power supply line Vx1, the power supply line Vy1, the switching TFT 1001, the driving TFT 1002, the EL element 1003, and the capacitor 1004.

Description is made on a connection between the pixel and circuit. The gate signal line G1 is connected to the gate electrode of the switching TFT 1001 and the source signal line S1 is connected to the source electrode or the drain electrode of the switching TFT 1001. The power supply line Vx1 is connected to the source electrode or the drain electrode of the driving TFT 1002 and one electrode of the capacitor 1004. The power supply line Vy1 is connected to the power supply line Vx1 and the other electrode of the capacitor 1004 is connected to the other of the source electrode or the drain electrode of the switching TFT 1001 and the gate electrode of the driving TFT 1002. The other of the source electrode or the drain electrode of the driving TFT 1002 is connected to the EL element 1003.

Further, a pixel of row two and column one of the pixel portion is different from the pixel of row one and column one in that G2 is used instead of G1 and may have a configuration in which Vx1 is not connected to another power supply line in order to electrically separate the power supply lines per R, G, and B.

Further, a pixel of row three and column one of the pixel portion is different from the pixel of row one and column one in that G3 is used instead of G1 and may have a configuration in which Vx1 is not connected to another power supply line in order to electrically separate the power supply lines per R, G, and B.

Further, a pixel of row four and column one of the pixel portion is different from the pixel of row one and column one in that G4 is used instead of G1 and Vy4 is used instead of Vy1.

Further, a pixel of row five and column one of the pixel portion is different from the pixel of row four and column one in that G5 is used instead of G4 and may have a configuration in which Vx1 is not connected to another power supply line in order to electrically separate the power supply lines per R, G, and B.

Further, a pixel of row six and column one of the pixel portion is different from the pixel of row four and column one in that G6 is used instead of G4 and may have a configuration in which Vx1 is not connected to another power supply line in order to electrically separate the power supply lines per R, G, and B.

Further, the pixels of column one are the repetition of the structure of the aforementioned three rows.

Further, a pixel of row one and column two of the pixel portion is different from the pixel of row one and column one in that S2 is used instead of S1 and Vx2 is used instead of Vx1 and may have a configuration in which Vx2 is not connected to another power supply line in order to electrically separate the power supply lines per R, G, and B.

Further, a pixel of row two and column two of the pixel portion is different from the pixel of row one and column two in that G2 is used instead of G1 and may have a configuration in which Vx2 is connected to another power supply line Vy2.

Further, a pixel of row three and column two of the pixel portion is different from the pixel of row one and column two in that G3 is used instead of G1 and may have a configuration in which Vx2 is not connected to another power supply line in order to electrically separate the power supply lines per R, G, and B.

Further, the pixels of column two are the repetition of the structure of the aforementioned three rows.

Further, a pixel of row one and column three of the pixel portion is different from the pixel of row one and column one in that S3 is used instead of S1 and Vx3 is used instead of Vx1, and may have a configuration in which Vx3 is not connected to another power supply line in order to electrically separate the power supply lines per R, G, and B.

Further, a pixel of row two and column three is different from the pixel of row one and column three in that G2 is used instead of G1 and has a configuration in which Vx3 is not connected to another power supply line.

Further, a pixel of row three and column three is different from the pixel of row one and column three in that G3 is used instead of G1 and may have a configuration in which Vx3 is not connected to another power supply line Vy3 in order to electrically separate the power supply lines per R, G, and B.

Further, the pixels of column three are the repetition of the structure of the aforementioned three rows.

The rest of the columns in the pixel portion has a configuration in which the configurations of the columns one to three are repeated.

Further, Vx1, Vx4, . . . , Vx(3i-2), Vy1, Vy4, . . . , and Vy(3j-2) are all electrically connected to each other (i and j are natural numbers).

Further, Vx2, Vx5, . . . , Vx(3i-1), Vy2, Vy5, . . . , and Vy(3j-1) are all electrically connected to each other (i and j are natural numbers).

Further, Vx3, Vx6, . . . , Vx(3i), Vy3, Vy6, . . . , and Vy(3j) are all electrically connected to each other (i and j are natural numbers).

In this embodiment mode, power supply lines of the pixel portion are not only the wirings (Vx1 to Vxn) provided in parallel to the source signal lines (S1 to Sn) but also provided in a vertical direction or an almost vertical direction (Vy1 to Vym), thereby voltage is applied from each direction to the source region or the drain region of the driving TFT 1002 of

the pixel of R, G, and B respectively. The power supply lines provided in a vertical direction or an almost vertical direction (Vy1 to Vym) are connected to the power supply lines (Vx1 to Vxn) per pixel of R, G and B and the power supply lines are arranged in matrix. Accordingly, a current flowing through the EL element 1003 is supplied not only in a direction parallel to the source signal lines (S1 to Sn) but also in the vertical direction. Therefore, one of the problems to be solved in the invention that wiring resistance is required to be as low as possible can be resolved. Further, different levels of voltage may be applied to R, G, and B which are connected independently.

Further, as one power supply line is provided in parallel to a gate signal line in each pixel, wiring resistance can be reduced without drastically reducing the aperture ratio and increasing parasitic capacitance between the wirings.

As wiring resistance can be low, a cross talk which occurs when an EL display device drives by the analog driving method is reduced. Further, a gray scale display defect can be reduced which occurs when an EL display device operates by the digital driving method and the constant voltage drive in combination.

However, it is one of the problems to be solved in this embodiment mode to manufacture an EL display device at low cost similarly to Embodiment Modes 1, 2, and 3. Therefore, an EL display device may be manufactured through an EL display device manufacturing process by the droplet discharging method which is one of manufacturing methods of an EL display device which can selectively form a pattern.

In the case of forming wirings by the droplet discharging method, variations occur in wiring resistance as described above. According to this embodiment mode, variations in wiring resistance caused by the droplet discharging method can be reduced.

This can be described by considering all wiring resistance is connected in parallel when the power supply lines are arranged in matrix. That is, when the wiring resistance are connected in parallel, resistance of the power supply line up to a certain pixel depends on the resistance of all the power supply lines and becomes less dependent on the position of resistance which exists in the case of non-matrix arrangement.

That is, according to this embodiment mode, the problem in that variations in wiring resistance in the case of using the droplet discharging method are required to be as little as possible can be resolved as well as reducing the wiring resistance of the power supply line can be reduced.

It is to be noted in this embodiment mode that wirings are not required to be provided in parallel to each other and may be provided in any directions. Further, the power supply line is not required to be only one in each pixel and may be provided as many as required. Furthermore, the power supply lines are not required to be arranged in matrix in the whole pixel portion and may be arranged in matrix in a portion of the pixel portion.

Further, this embodiment mode can be freely implemented in combination with Embodiment Modes 1, 2, and 3.

Embodiment Mode 5

This embodiment mode is a combination of Embodiment Mode 1 and Embodiment Mode 2, 3, or 4. A configuration here is described with reference to FIGS. 12, 16A and 16B.

FIGS. 12 and 16 show circuit diagrams of a whole pixel portion of this embodiment mode. In this embodiment mode, a plurality of source signal lines are provided for one vertical

column of pixels. In FIG. 8, description is made on the case of providing three source signal lines for one vertical column of pixels.

It is to be noted that the number of the source signal lines is not limited to three and may be provided as many as required.

A circuit 1254 of each pixel in FIG. 12 is described as the circuit shown in FIGS. 16A and 16B. However, this is only an example and a circuit in each pixel is not limited to the circuit in FIG. 16.

A pixel of row one and column one includes a gate signal line G1, a source signal line S1a which is one of the three source signal lines, the power supply line Vx1, the switching TFT 1001, the driving TFT 1002, the EL element 1003, and the capacitor 1004.

A connection between the pixel and circuit is described. The gate signal line G1 is connected to a gate electrode of the switching TFT 1001 and the source signal line S1a which is one of the three source signal lines is connected to a source electrode or a drain electrode of the switching TFT 1001, the power supply line Vx1 is connected to the source electrode or the drain electrode of the driving TFT 1002 and one electrode of the capacitor 1004. The power supply line Vy1R is connected to the power supply line Vx1 and the other electrode of the capacitor 1004 is connected to the other of the source electrode or the drain electrode of the switching TFT 1001 and the gate electrode of the driving TFT 1002. The other of the source electrode or the drain electrode of the driving TFT 1002 is connected to the EL element 1003.

Further, a pixel of row two and column one of the pixel portion includes the gate signal line G2, the source signal line S1b which is one of the three source signal lines, the power supply line Vx1, the power supply line Vy2R, the switching TFT 1001, the driving TFT 1002, the EL element 1003, and the capacitor 1004.

A pixel of row two and column one is different from the pixel of row one, and column one in that G2 is used instead of G1, S1b is used instead of S1a, and Vy2R is used instead of Vy1R.

A pixel of row three and column one includes a gate signal line G3, the source signal line S1c which is one of the three signal lines, the power supply line Vx1, the power supply line Vy3R, the switching TFT 1001, the driving TFT 1002, the EL element 1003, and the capacitor 1004.

A pixel of row three and column one is different from the pixel of row one and column one in that G1 is used instead of G3, S1c is used instead of S1a, and Vy3R is used instead of Vy1R.

Further, in the three pixel columns described above, G1, G2, and G3 are electrically connected.

Further, the pixels of column one are the repetition of the aforementioned structure.

Further, the pixels of column two are different from the aforementioned structure in that Vx2 is used instead of Vx1, S2a is used instead of S1a, S2b is used instead of S1b, S2c is used instead of S1c, Vy1G is used instead of Vy1R, Vy2G is used instead of Vy2R, and Vy3G is used instead of Vy3R.

Further, the pixels of column three are different from the aforementioned structure in that Vx3 is used instead of Vx1, S3a is used instead of S1a, S3b is used instead of S1b, S3c is used instead of S1c, VynB is used instead of Vy1R, Vy2B is used instead of Vy2R, and Vy3B is used instead of Vy3R.

Further, the columns of the pixels after the column three are the repetition of the aforementioned structure.

Further, Vy1R to VymR are all electrically connected to each other.

Further, Vy1G to VymG are all electrically connected to each other.

Further, Vy1B to VymB are all electrically connected to each other.

According to this embodiment mode, the problem described in Embodiment Mode 1 in that the write time is required to be taken as long as possible can be resolved. Further, the problem in that parasitic capacitance is required to be as small as possible can be resolved.

Further, according to this embodiment mode, the problem described in Embodiment Mode 2, 3, or 4 in that wiring resistance is required to be as low as possible can be resolved. Further, the problem in that variations in wiring resistance are required to be as little as possible can be resolved.

Further, according to this embodiment mode, an EL display device can be manufactured at low cost as the droplet discharging method is used which can selectively form a pattern.

Embodiment Mode 6

Description is made with reference to FIGS. 18A to 19F on an embodiment mode of the invention. In this embodiment mode, a channel etch type thin film transistor is used as a thin film transistor. Therefore, description on the same portion or the portion having a similar function is omitted here.

A base film 1201 having a function to improve adhesiveness is formed over a substrate 1200 (see FIG. 18A). An insulating layer may be formed over the substrate 1200. This insulating layer is used as a base film and is not necessarily provided, but has an effect to block a contaminant and the like from the substrate 1200. In the case of forming a base layer for preventing contamination from a glass substrate, the base film 801 is formed as pre-treatment for conductive layers 1202 and 1203 which are formed over the base layer by the droplet discharging method.

In this embodiment mode, a substance having a photocatalytic function is used as the base film having a function to improve adhesiveness.

In this embodiment mode, description is made on the case of forming a TiO_x crystal having a predetermined crystalline structure as a photocatalytic substance by the sputtering method. Sputtering is performed by using a metal titanium tube as a target and an argon gas and oxygen. Further, a He gas may be introduced as well. In order to form TiO_x which is highly photocatalytically active, an atmosphere containing a lot of oxygen is used with a rather high pressure. Further, TiO_x is preferably formed while heating a deposition chamber or a substrate over which an object to be treated is formed.

TiO_x formed in this manner formed in this manner has a photocatalytic function even in a quite thin film form.

It is preferable to form the base film 1201 using a metal material such as Ti (titanium), W (tungsten), Cr (chromium), Ta (tantalum), Ni (nickel), and Mo (molybdenum), or oxide thereof by a sputtering method or a vapor deposition method. The base film is formed with a thickness of 0.01 to 10 nm, and does not necessarily have a layer structure as long as it is formed quite thin. In the case of using a high-melting point material as the base film, it is preferable to treat the base film exposed on the surface by carrying out one of the following two steps after forming the conductive layers 1202 and 1203 to be gate electrode layers.

The first method is a step of insulating the base film 1201 which is not overlapped with the conductive layers 1202 and 1203 to form an insulating layer. In other words, the base film 1201 which is not overlapped with the conductive layers 1202 and 1203 is oxidized and insulated. When the base film 1201 is oxidized and insulated in this manner, it is preferable to form the base film 1201 to be 0.01 to 10 nm in thickness, thus,

the base film can be easily oxidized. Note that oxidation may be performed by exposing to an oxygen atmosphere or by thermal treatment.

The second method is a step of removing the base film **1201** by etching using the conductive layers **1202** and **1203** as a mask. When this step is employed, there is no limitation in the thickness of the base film **1201**.

Alternatively, a method of performing plasma treatment on a formation region (formation surface) can be employed as another pre-base treatment. The plasma treatment is performed with air, oxygen, or nitrogen used as a treatment gas, with pressure from several ten Torr to 1000 Torr (133000 Pa), preferably, from 100 Torr (13300 Pa) to 1000 Torr (133000 Pa), more preferably, from 700 Torr (93100 Pa) to 800 Torr (106400 Pa), that is, atmospheric pressure or pressure in proximity of atmospheric pressure, and a pulse voltage is applied with such conditions. At this time, plasma density is set at 1×10^{10} to $1 \times 10^{14} \text{ m}^{-3}$, so that so-called corona discharge or glow discharge is achieved. Surface modification can be performed without material dependence by employing plasma treatment using air, oxygen, or nitrogen as a treatment gas. Accordingly, surface modification can be performed on any material.

As another method, a substance of an organic material functioning as an adhesive may be formed to improve adhesiveness of a pattern to be formed by a droplet discharging method with a formation region thereof. An organic material (organic resin material) (polyimide or acrylic) is composed of a skeleton formed of the bond of silicon (Si) and oxygen (O), in which an organic group containing at least hydrogen (such as an alkyl group or aromatic hydrocarbon) is included as a substituent. Alternatively, a fluoro group may be used as the substituent. Further alternatively, a fluoro group and an organic group containing at least hydrogen may be used as the substituent.

Subsequently, a composition containing a conductive material is discharged, and conductive layers **1202** and **1203** to function as gate electrodes later are formed. These conductive layers **1202** and **1203** are formed by the droplet discharging method. In this embodiment mode, silver is used as a conductive material, but a stack of silver, copper and the like may be used as well. Alternatively, a single layer of copper may be used as well.

In addition, the aforementioned step of forming the base film **1201** is carried out as pre-base treatment for a conductive layer to be formed by using the droplet discharging method, however, this treatment step may be carried out after forming the conductive layer.

Subsequently, a gate insulating film is formed over the conductive layers **1202** and **1203** (see FIG. 18A). The gate insulating film may be formed of a known material such as an oxide or nitride material of silicon, and may be stacked layers or a single layer.

Subsequently, a conductive layer (also referred to as a first electrode) **1206** is formed by selectively discharging a composition containing a conductive material onto the gate insulating film (see FIG. 18B). The conductive layer **1206** may be formed in a predetermined pattern of a composition containing indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), zinc oxide (ZnO), tin oxide (SnO_2), or the like and by baking it when light is emitted from the substrate **1200** side or when a light-transmissive EL display panel is manufactured. Although not shown, a photocatalytic substance may be formed in a region where the conductive layer **1206** is formed similarly to the case of forming the conductive layers **1202** and **1203**. With a photocatalytic substance, adhesiveness is improved and the conductive layer **1206** can be

formed into a desired pattern to be a thin line. This conductive layer **1206** becomes a first electrode which functions as a pixel electrode.

The semiconductor layer may be formed by a known method (the sputtering method, the LPCVD method, the plasma CVD method, or the like). There is no particular limitation in materials of the semiconductor layer, but the semiconductor layer is preferably formed of silicon, a silicon germanium (SiGe) alloy, or the like.

The semiconductor layer formed of an amorphous semiconductor (typically, hydrogenated amorphous silicon), a semi-amorphous semiconductor, a semiconductor of which semiconductor layer partially has a crystal phase, a crystalline semiconductor (typically polysilicon), or an organic semiconductor as a material.

In this embodiment mode, an amorphous semiconductor is used as a semiconductor. A semiconductor layer **1207** is formed and a semiconductor layer having one conductivity, for example an N-type semiconductor layer **1208** is formed by the plasma CVD method and the like (see FIG. 12C). The semiconductor layer having one conductivity may be formed as required.

Subsequently, mask layers **1211** and **1212** each of which is formed of an insulator such as resist and polyimide are formed, and then the semiconductor layer **1207** and the N-type semiconductor layer **1208** are patterned at the same time by using the mask layers **1211** and **1212**.

Subsequently, mask layers **1213** and **1214** formed of an insulator such as resist and polyimide are formed by the droplet discharging method (see FIG. 18D). By using the mask layers **1213** and **1214**, a through hole **1218** is formed in a portion of the gate insulating layers **1204** and **1205** by an etching process, thereby exposing a portion of the conductive layer **1203** which functions as a gate electrode provided on a lower layer side.

After removing the mask layers **1213** and **1214**, conductive layers **1215**, **1216**, and **1217** are formed by discharging a composition containing a conductive material, and the N-type semiconductor layer is patterned with the conductive layers **1215**, **1216**, and **1217** as masks to form an N-type semiconductor layer (see FIG. 19A). It is to be noted that before forming the conductive layers **1215**, **1216**, and **1217**, a photocatalytic substance may be selectively formed in a portion where the conductive layers **1215**, **1216**, and **1217** are in contact with the gate insulating layer **1205**. Accordingly, a conductive layer can be formed with favorable adhesiveness.

The conductive layer **1217** functions as a source wiring layer or a drain wiring layer and is formed to be electrically connected to the conductive layer **1206** as a first electrode formed in advance. The conductive layer **1216** as a source wiring layer or a drain wiring layer and the conductive layer **1203** as a gate electrode layer are electrically connected through the through hole **1218** formed in the gate insulating layer **1205**.

A step of forming the through hole **1218** in a portion of the gate insulating layers **1204** and **1205** may be performed after forming the conductive layers **1215**, **1216**, and **1217** with the conductive layers **1215**, **1216**, and **1217** to be the wiring layers as masks. Then, a conductive layer is formed in the through hole **1218**, and then the conductive layer **1216** and the conductive layer **1203** as a gate electrode layer are electrically connected. In this case, it is advantageous in that the manufacturing steps can be simplified.

Subsequently, an insulating layer **1220** to be a partition wall is formed. An opening is formed in the insulating layer **1220** as shown in FIG. 19B by an etching process after the insulating layer is entirely formed by the spin coating method

or the dipping method. The etching process is not necessarily carried out when the insulating layer **1220** is formed by the droplet discharging method.

The insulating layer **1220** is formed with the through hole having an opening portion provided in accordance with a position where a pixel is formed corresponding to the conductive layer **1206** as the first electrode.

By the aforementioned steps, a TFT substrate in which a bottom gate type (also referred to as an inversely staggered type) channel etch type TFT and the conductive layer **1206** as the first electrode are connected over the substrate **1200** is completed.

By stacking an electroluminescent layer **1221** over the conductive layer **1206** as the first electrode and a conductive layer **1222** thereover, a display device having a display function using a light emitting element is completed (see FIG. **19B**).

As described above, the step can be omitted in this embodiment mode by not applying a light exposure step utilizing a photo mask. In addition, an EL display panel can be easily manufactured by directly forming various patterns over a substrate with a droplet discharging method even when a glass substrate of the fifth or the following generation having a side of more than 1000 mm is used.

Furthermore, a highly reliable display device of which adhesiveness and peeling resistance are improved can be manufactured.

Embodiment Mode 7

Description is made with reference to FIGS. **20A** to **21** on an embodiment mode of the invention. This embodiment mode is different from Embodiment Mode 1 in that a top gate (also referred to as a forward staggered) type thin film transistor is used as a thin film transistor. Accordingly, description on the same portion or a portion having a similar function is omitted.

A base film **1301** having a function to improve adhesiveness is formed over a substrate **1300** (see FIG. **20A**). It is to be noted that an insulating layer may be formed over the substrate **1300**. This insulating layer is not necessarily provided, but has an effect to block a contaminant and the like from the substrate **1300**. In the case of using a forward staggered thin film transistor as in this embodiment mode, a semiconductor layer is in direct contact with a substrate, therefore, a base layer is not required. In the case of forming a base layer for preventing contamination from a glass substrate, the base film **1301** is formed over the base layer by the droplet discharging method as pre-treatment for conductive layers **1315**, **1316**, and **1317** in forming regions thereof.

In this embodiment mode, a substance having a photocatalytic function is used as the base film **1301** having a function to improve adhesiveness.

In this embodiment mode, description is made on the case of forming a TiO_x crystal having a predetermined crystalline structure as a photocatalytic substance by the sputtering method. Sputtering is performed by using a metal titanium tube as a target and an argon gas and oxygen. Further, a He gas may be introduced as well. In order to form TiO_x which is highly photocatalytically active, an atmosphere containing a lot of oxygen is used with a rather high pressure. Further, TiO_x is preferably formed while heating a deposition chamber or a substrate over which an element is formed.

TiO_x formed in this manner has a photocatalytic function even in a quite thin film form.

It is preferable to form a base film **1301** formed of a metal material such as Ti (titanium), W (tungsten), Cr (chromium),

Ta (tantalum), Ni (nickel), and Mo (molybdenum), or oxide thereof. The base film **1301** is to be formed with a thickness of 0.01 to 10 μm , and does not necessarily have a layer structure as long as it is formed quite thin. In the case of using a high-melting point material as the base film, it is preferable to treat the base film exposed on the surface by carrying out one of the following two steps after forming the conductive layers **1315**, **1316**, and **1317** to be source wiring layers or drain wiring layers.

The first method is a step of insulating the base film **1301** which is not overlapped with the conductive layers **1315**, **1316**, and **1317** to form an insulating layer. In other words, the base film **1301** which is not overlapped with the conductive layers **1315**, **1316**, and **1317** is oxidized and insulated. When the base film **1301** is oxidized and insulated in this manner, it is preferable to form the base film **1301** to be 0.01 to 10 nm in thickness, thus, the base film can be easily oxidized. Note that oxidation may be performed by exposing to an oxygen atmosphere or by thermal treatment.

The second method is a step of removing the base film **1301** by etching using the conductive layers **1315**, **1316**, and **1317** which function as source wiring layers or drain wiring layers as masks. When this step is employed, there is no limitation in the thickness of the base film **1301**.

Alternatively, a method for performing plasma treatment on a formation region (formation surface) can be employed as another pre-base treatment. The plasma treatment is performed with air, oxygen, or nitrogen used as a treatment gas, with pressure from several ten Torr to 1000 Torr (133000 Pa), preferably, from 100 Torr (13300 Pa) to 1000 Torr (133000 Pa), more preferably, from 700 Torr (93100 Pa) to 800 Torr (106400 Pa), that is, atmospheric pressure or pressure in proximity of atmospheric pressure, and a pulse voltage is applied under such conditions. At this time, plasma density is set at 1×10^{10} to $1 \times 10^{14} \text{ m}^{-3}$, so that so-called corona discharge or glow discharge is achieved. Surface modification can be performed without material dependence by employing plasma treatment using air, oxygen, or nitrogen as a treatment gas. Accordingly, surface modification can be performed on any material.

As another method, an organic material-based substance which functions as an adhesive may be formed to improve adhesion between a pattern formed by the droplet discharging method and a forming region thereof. An organic material (organic resin material) (polyimide or acrylic) is composed of a skeleton formed of the bond of silicon (Si) and oxygen (O), in which an organic group containing at least hydrogen (such as an alkyl group or aromatic hydrocarbon) is included as a substituent. Alternatively, a fluoro group may be used as the substituent. Further alternatively, a fluoro group and an organic group containing at least hydrogen may be used as the substituent.

Subsequently, a composition containing a conductive material is discharged, and conductive layers **1315**, **1316**, and **1317** to function as source wiring layers or drain wiring layers later are formed. These conductive layers **1315**, **1316**, and **1317** are formed by the droplet discharging method.

As the conductive material used for forming the conductive layers **1315**, **1316**, and **1317**, a composition containing as a main component a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), and Al (aluminum) can be used. In particular, a source wiring layer or a drain wiring layer which are preferably low in resistance are preferably formed by using any one of gold, silver, and copper dissolved or dispersed in a solvent in consideration of resistivity. More preferably, silver and copper which are low resistant are used. As for such solvents, esters such as butyl acetate, alcohols

such as isopropyl alcohol, organic solvents such as acetone, or the like may be used. The surface tension and viscosity are appropriately controlled by controlling the concentration of the solvent and adding a surfactant and the like.

Subsequently, a conductive layer (also referred to as a first electrode) **1306** is formed by selectively discharging a composition containing a conductive material (see FIG. 20A). The conductive layer **1306** may be formed in a predetermined pattern of a composition containing indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), zinc oxide (ZnO), tin oxide (SnO₂), or the like and by baking it when light is to be emitted from the substrate **1300** side or when a light-transmissive EL display panel is to be manufactured. Although not shown, a photocatalytic substance may be formed in a region where the conductive layer **1306** is formed similarly to the case of forming the conductive layers **1315**, **1316**, and **1317**. With a photocatalytic substance, adhesiveness is improved and the conductive layer **1306** can be formed into a thin desired pattern to be a thin line. This conductive layer **1306** becomes a first electrode which functions as a pixel electrode.

The step of forming the base film **1301** described above is performed as pre-base treatment for a conductive layer formed by the droplet discharging method, however, this treatment may be performed after forming the conductive layers **1315**, **1316**, and **1317**. For example, by forming a titanium oxide film and an N-type semiconductor layer thereover though not shown, adhesion between the conductive layer and the N-type semiconductor layer is improved.

After forming the N-type semiconductor layer over the whole surface of the conductive layers **1315**, **1316**, and **1317**, the N-type semiconductor layer provided between the conductive layers **1315** and **1316** and between the conductive layers **1316** and **1317** is removed by etching using mask layers **1311**, **1312**, and **1319** formed of an insulator such as resist and polyimide. A semiconductor layer having one conductivity may be formed as required. Then, a semiconductor layer **1307** formed of an amorphous semiconductor (hereinafter referred to as an AS) or an SAS is formed by a vapor phase method or the sputtering method. In the case of employing the plasma CVD method, the AS is formed by using SiH₄ as a semiconductor material gas or a mixed gas of SiH₄ and H₂. The SAS is formed of a mixed gas in which SiH₄ is diluted with H₂ by 3 to 1000 times. When the SAS is formed of the above kind of gas, the semiconductor layer has favorable crystallinity on a surface side. The SAS is suitable for a top gate type TFT in which the gate electrode is formed in an upper layer of the semiconductor layer.

Subsequently, a gate insulating layer **1305** is formed with a single layer or a stacked-layer structure by the plasma CVD method or the sputtering method. A stack of three layers of an insulating layer formed of silicon nitride, an insulating layer formed of silicon oxide, and an insulating layer formed of silicon nitride is particularly a preferable structure.

Next, gate electrode layers **1302** and **1303** are formed by the droplet discharging method. A composition containing a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), or Al (aluminum), as its main component can be used as a conductive material for forming the gate electrode layers **1302** and **1303**.

The semiconductor layer **1307** and the gate insulating layer **1305** are formed in a position corresponding to the source wiring layers and the drain wiring layers (the conductive layers **1315**, **1316**, and **1317**) using the mask layers **1313** and **1314** formed by the droplet discharging method. In other

words, the semiconductor layer and the gate insulating layer are formed to straddle over the conductive layers **1315** and **1316**.

Subsequently, conductive layers **1330** and **1331** are formed by the droplet discharging method. The conductive layer **1316** and the gate electrode layer **1303**, and the conductive layer **1317** and the conductive layer **1306** as the first electrode are electrically connected to each other.

The source wiring layer or drain wiring layer and the gate electrode layer may be directly connected through the gate electrode layer without using the conductive layer **1330**. In that case, a through-hole is formed in the gate insulating layer **1305** and a part of the conductive layers **1316** and **1317** that are the source wiring or drain wirings is exposed before the gate electrode layers **1302** and **1303** are formed. After that, the gate electrode layers **1302**, **1303** and the conductive layer **1331** are formed by the droplet discharging method. At this time, the gate electrode layer **1303** is a wiring which also serves as the conductive layer **1330**, and is connected to the conductive layer **1316**. Either dry etching or wet etching may be employed for etching, however, plasma etching which is dry etching is more preferable.

Subsequently, an insulating layer **1320** to be a partition wall is formed. Although not shown, a protective layer formed of silicon nitride or silicon nitride oxide may be entirely formed under the insulating layer **1320** to cover a thin film transistor. An opening is formed in the insulating layer **1320** as shown in FIG. 21 by an etching process after the insulating layer is entirely formed by the spin coating method or the dipping method. The etching process is not necessarily carried out when the insulating layer **1320** is formed by the droplet discharging method. When a wide region such as the insulating layer **1320** is formed by the droplet discharging method, a throughput is improved by forming by discharging a composition from a plurality of discharging openings of nozzles in a droplet discharging apparatus and drawing so that a plurality of lines are overlapped with each other.

The insulating layer **1320** is formed to have a through-hole corresponding to a position where a pixel is to be formed in accordance with the conductive layer **1306** as the first electrode.

According to the aforementioned steps, a TFT substrate is completed in which a top gate type (also referred to as an inversely staggered type) TFT and the conductive layer **1306** as the first electrode layer are connected over the substrate **1300**.

Moisture adsorbed in the insulating layer **1320** or to a surface thereof is removed by performing thermal treatment at 200° C. under atmospheric pressure before forming an electroluminescent layer **1321**. In addition, thermal treatment is performed at a temperature of 200 to 400° C., preferably, 250 to 350° C. under reduced pressure, and the electroluminescent layer **1321** is preferably formed by the vacuum vapor deposition method or the droplet discharging method under reduced pressure without being exposed to an atmospheric air.

The electroluminescent layer **1321** and a conductive layer **1322** are stacked over the conductive layer **1306** as the first electrode, and then, a display device having a display function using a light emitting element is completed (see FIG. 21).

As described above, the step can be omitted in this embodiment mode by not applying a light exposure step utilizing a photo mask. In addition, an EL display panel can be easily manufactured by directly forming various patterns over a substrate by the droplet discharging method even when a glass substrate of the fifth or the following generation having a side of more than 1000 mm is used.

Furthermore, a display device of which adhesiveness and peeling resistance are improved and reliability is high can be manufactured.

Embodiment Mode 8

An embodiment mode of the invention is described with reference to FIGS. 22A to 23B. This embodiment mode is different from Embodiment Mode 1 in that a thin film transistor and a first electrode are connected differently. Therefore, description on the same portion or a portion having a similar function is omitted.

A base film **1401** for improving adhesiveness is formed over a substrate **1400** as pre-base treatment. The case of forming TiO_x crystal having a predetermined crystalline structure as a photocatalytic substance by the sputtering method is described in this embodiment mode. Sputtering is performed using a metal titanium tube as a target and using an argon gas and oxygen. Further, a He gas may be introduced. The atmosphere includes much oxygen and formation pressure is set high to form TiO_x having high photocatalytic activity. It is preferable to form TiO_x while heating a deposition chamber or a substrate provided with an object to be treated.

The thus formed TiO_x has a photocatalytic function even when it is a very thin film.

Further, it is preferable to form the base film **1401** formed of a metal material such as Ti (titanium), W (tungsten), Cr (chromium), Ta (tantalum), Ni (nickel), or Mo (molybdenum), or oxide thereof by a sputtering method, a vapor deposition method, or the like as another pre-base treatment. The base film **1401** may be formed to be 0.01 to 10 nm in thickness. It does not necessarily have a layer structure as long as it is formed quite thin. When a high-melting point metal material is used as the base film, it is preferable to treat a base film exposed on the surface by carrying out either of the following two steps after forming conductive layers **1402** and **1403** to be gate electrode layers.

The first method is a step of insulating the base film **1401** which is not overlapped with the conductive layers **1402** and **1403** and forming an insulating layer. In other words, the base film **1401** which is not overlapped with the conductive layers **1402** and **1403** is oxidized and insulated. When the base film **1401** is oxidized and insulated in this manner, it is preferable to form the base film **1401** to be 0.01 to 10 nm in thickness, thus, the base film can be easily oxidized. Note that oxidation may be performed by exposing to an oxygen atmosphere or by thermal treatment.

The second method is a step of removing the base film **1401** by etching using the conductive layers **1402** and **1403** as masks. When this step is employed, there is no limitation in the thickness of the base film **1401**.

Alternatively, a method for performing plasma treatment on a formation region (formation face) can be employed as another pre-base treatment. The plasma treatment is performed with air, oxygen, or nitrogen used as a treatment gas, with pressure from several ten Torr to 1000 Torr (133000 Pa), preferably, from 100 Torr (13300 Pa) to 1000 Torr (133000 Pa), more preferably, from 700 Torr (93100 Pa) to 800 Torr (106400 Pa), that is, atmospheric pressure or pressure in proximity of atmospheric pressure, and a pulse voltage is applied under such conditions. At this time, plasma density is set at 1×10^{10} to $1 \times 10^{14} \text{ m}^{-3}$, so that so-called corona discharge or glow discharge is achieved. Surface modification can be performed without material dependence by employing plasma treatment using air, oxygen, or nitrogen as a treatment gas. Accordingly, surface modification can be performed on any material.

As another method, a substance of an organic material functioning as an adhesive may be formed to improve adhesion between a pattern to be formed by the droplet discharging method and a formation region thereof. An organic material (organic resin material) (polyimide or acrylic) or a material in which a skeletal structure is configured by the bond of silicon (Si) and oxygen (O) and which contains at least hydrogen as a substituent or which contains at least one of fluorine, an alkyl group, and aromatic hydrocarbon as a substituent may be used.

Subsequently, a composition containing a conductive material is discharged, and conductive layers **1402** and **1403** to function as a gate electrode later are formed. These conductive layers **1402** and **1403** are formed by the droplet discharging method. In this embodiment mode, silver is used as a conductive material, but a stack of silver, copper and the like may be used as well. Alternatively, a single layer of copper may be used as well.

In addition, the aforementioned step of forming the base film **1401** is carried out as pre-base treatment for a conductive layer to be formed by the droplet discharging method, however, this treatment step may be carried out after forming the conductive layer.

Subsequently, a gate insulating film is formed over the conductive layers **1402** and **1403** (see FIG. 22A). The gate insulating film may be formed of a known material such as an oxide or nitride material of silicon, and may be stacked layers or a single layer.

The semiconductor layer may be formed by a known method (the sputtering method, the LPCVD method, the plasma CVD method, or the like). There is no particular limitation in materials of the semiconductor layer, but the semiconductor layer is preferably formed of silicon, a silicon germanium (SiGe) alloy, or the like.

The semiconductor layer uses an amorphous semiconductor (typically, hydrogenated amorphous silicon), a semi-amorphous semiconductor, a semiconductor of which semiconductor layer partially has a crystal phase, a crystalline semiconductor (typically polysilicon), or an organic semiconductor as a material.

An amorphous semiconductor is used as the semiconductor in this embodiment mode. A semiconductor layer **1407** is formed and an insulating film is formed by, for example, the plasma CVD method and is selectively etched to have a desired shape in a desired region in order to form channel protective films **1409** and **1410**. In addition, the channel protective film may be formed using polyimide, polyvinyl alcohol, or the like by the droplet discharging method or the printing method (a method which can form a pattern, such as the screen printing method and the offset printing method). Thereafter, a semiconductor layer having one conductivity, for example, an N-type semiconductor layer **1408** is formed by the plasma CVD method or the like. The semiconductor layer having one conductivity may be formed as required.

Subsequently, mask layers **1411** and **1412** formed of an insulator such as a resist or polyimide are formed. Then, the semiconductor layer **1407** and the N-type semiconductor layer **1408** are simultaneously patterned using the mask layers **1411** and **1412**.

Then, mask layers **1413** and **1414** formed of an insulator such as a resist or polyimide are formed by the droplet discharging method (see FIG. 22C). A through-hole **1418** is formed in a part of the gate insulating layers **1404** and **1405** by an etching process using the mask layers **1413** and **1414**, and a part of the conductive layer **1403** which is disposed on a lower layer side thereof and functions as a gate electrode layer is exposed. Either plasma etching (dry etching) or wet etching

may be adopted as the etching process. In addition, a local discharge process can be performed when an atmospheric pressure discharge etching process is applied, and a mask layer does not need to be entirely formed over the substrate.

Conductive layers **1415**, **1416**, and **1417** are formed by discharging a composition containing a conductive material after the mask layers **1413** and **1414** are removed. Then, the N-type semiconductor layer is patterned using the conductive layers **1415**, **1416**, and **1417** as masks (see FIG. 22D). Note that the aforementioned base pre-base treatment to selectively form a photocatalytic substance or the like in a portion where the conductive layers **1415**, **1416**, and **1417** are to be in contact with the gate insulating layer **1405** may be performed before forming the conductive layers **1415**, **1416**, and **1417**, although not shown. Accordingly, the conductive layer can be formed with favorable adhesion with the stacked upper and lower layers.

Further, the conductive layers **1415**, **1416**, and **1417** that are wiring layers are formed to cover the N-type semiconductor layer and the semiconductor layer as shown in FIG. 22D. The semiconductor layer is etched. Therefore, the wiring layer might not be able to cover a steep step and might be disconnected. Therefore, insulating layers **1441**, **1442**, and **1443** are formed to reduce a step, and the step may be smoothed. The insulating layers **1441**, **1442**, and **1443** can be selectively formed without a mask or the like when the droplet discharging method is employed. The step can be smoothed by the insulating layers **1441**, **1442**, and **1443**, and the wiring layer to cover the insulating layers can be formed with favorable coverage without a defect such as break. The insulating layers **1441**, **1442**, and **1443** can be formed of an inorganic insulating material such as silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, or aluminum oxynitride, acrylic acid, methacrylic acid, a derivative of acrylic acid or methacrylic acid, a heat-resistant high molecular weight material such as polyimide, aromatic polyamide, or polybenzimidazole, or inorganic siloxane including a Si—O—Si bond among compounds that contain silicon, oxygen, and hydrogen and that is formed by using a siloxane-based material as a starting material or an organosiloxane-based insulating material in which hydrogen bonded with silicon is substituted by an organic group such as methyl or phenyl.

Subsequently, a conductive layer (also referred to as a first electrode) **1406** is formed by selectively discharging a composition containing a conductive material onto the gate insulating film to be in contact with the conductive layer **1417** which functions as the source wiring layer or a drain wiring layer (see FIG. 23A). The conductive layer **1406** may be formed by forming a predetermined pattern of a composition containing indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), zinc oxide (ZnO), tin oxide (SnO₂), or the like and by baking it when light is emitted from the substrate **1400** side or when a transmissive EL display panel is manufactured. Although not shown, pre-base treatment such as formation of a photocatalytic substance may be performed similarly to the case of forming the conductive layers **1402** and **1403** in a region where the conductive layer **1406** is to be formed. The pre-base treatment can improve adhesiveness and the conductive layer **1406** can be formed into a desired pattern to be a thin line. The conductive layer **1406** becomes the first electrode which functions as a pixel electrode.

In addition, the conductive layer **1416** that is the source wiring layer or the drain wiring layer and the conductive layer **1403** that is the gate electrode layer are electrically connected to each other in the through-hole **1418** formed in the gate

insulating layer **1405**. A composition containing a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), or Al (aluminum) as its main component can be used as a conductive material for forming the wiring layer. In addition, light-transmissive indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), organic indium, organotin, zinc oxide, titanium nitride, and the like may be used in combination.

The through-hole **1418** may be formed after forming the conductive layers **1415**, **1416**, **1417**, and **1406** using the conductive layers **1415**, **1416**, **1417**, and **1406** as masks to form the through-hole **1418**. Then, a conductive layer is formed in the through-hole **1418**, and the conductive layer **1416** and the conductive layer **1403** as the gate electrode layer are electrically connected to each other.

Subsequently, an insulating layer **1420** to be a partition wall is formed. Although not shown, a protective layer formed of silicon nitride or silicon nitride oxide may be entirely formed under the insulating layer **1420** to cover a thin film transistor. An opening is formed in the insulating layer **1420** as shown in FIG. 23B by an etching process after the insulating layer is entirely formed by the spin coating method or the dipping method. The etching process is not necessarily carried out when the insulating layer **1420** is formed by the droplet discharging method. When a wide region such as the insulating layer **1420** is formed by the droplet discharging method, a throughput is improved by forming by discharging a composition from a plurality of discharging openings of nozzles in a droplet discharge apparatus and drawing so that a plurality of lines are overlapped with each other.

The insulating layer **1420** is formed to have a through-hole corresponding to a position where a pixel is to be formed in accordance with the conductive layer **1406** that is the first electrode.

By the aforementioned steps, a TFT substrate is completed in which a bottom gate type (also referred to as an inversely staggered type) channel protective and the conductive layer (the first electrode layer) **1406** are connected over the substrate **1400**.

By stacking an electroluminescent layer **1421** and a conductive layer **1422** over the conductive layer **1406** as the first electrode, a display device having a display function using a light emitting element is completed (see FIG. 23B).

As described above, the step can be omitted in this embodiment mode by not applying a light exposure step utilizing a photo mask. In addition, an EL display panel can be easily manufactured by directly forming various patterns over a substrate by the droplet discharging method even when a glass substrate of the fifth or the following generation having a side of more than 1000 mm is used.

Furthermore, a display device of which adhesiveness and peeling resistance are improved and reliability is high can be manufactured.

Embodiment Mode 9

An embodiment mode of the invention is described with reference to FIGS. 24A to 25B. This embodiment mode is different from Embodiment Mode 6 in that a thin film transistor and a first electrode are connected differently. Therefore, description of the same portion or a portion having a similar function is omitted.

A base film **1501** for improving adhesiveness is formed over a substrate **1500** as pre-base treatment. In this embodiment mode, description is made on the case of forming a TiO_x crystal having a predetermined crystalline structure as a photocatalytic substance by the sputtering method. Sputtering is

performed by using a metal titanium tube as a target and an argon gas and oxygen. Further, a He gas may be introduced as well. In order to form TiO_x which is highly photocatalytically active, an atmosphere containing a lot of oxygen is used with a rather high pressure. Further, TiO_x is preferably formed while heating a deposition chamber or a substrate over which an object to be treated is formed.

TiO_x formed in this manner has a photocatalytic function even in a thin film form.

It is preferable to form a base film **1501** using a metal material such as Ti (titanium), W (tungsten), Cr (chromium), Ta (tantalum), Ni (nickel), and Mo (molybdenum), or oxide thereof. The base film **1501** is to be formed with a thickness of 0.01 to 10 nm, and does not necessarily have a layer structure as long as it is formed quite thin. In the case of using a high-melting point material as the base film, it is preferable to treat the base film exposed on the surface by carrying out one of the following two steps after forming the conductive layers **1502** and **1503** to be gate electrode layers.

The first method is a step of insulating the base film **1501** which is not overlapped with the conductive layers **1502** and **1503** and forming an insulating layer. In other words, the base film **1501** which is not overlapped with the conductive layers **1502** and **1503** is oxidized and insulated. When the base film **1501** is oxidized and insulated in this manner, it is preferable to form the base film **1501** to be 0.01 to 10 nm in thickness, thus, the base film can be easily oxidized. Note that oxidation may be performed by exposing to an oxygen atmosphere or by thermal treatment.

The second method is a step of removing the base film **1501** by etching using the conductive layers **1502** and **1503** as masks. When this step is employed, there is no limitation in the thickness of the base film **1501**.

Alternatively, a method for performing plasma treatment on a formation region (formation surface) can be employed as another pre-base treatment. The plasma treatment is performed with air, oxygen, or nitrogen used as a treatment gas, with pressure from several ten Torr to 1000 Torr (133000 Pa), preferably, from 100 Torr (13300 Pa) to 1000 Torr (133000 Pa), more preferably, from 700 Torr (93100 Pa) to 800 Torr (106400 Pa), that is, atmospheric pressure or pressure in proximity of atmospheric pressure, and a pulse voltage is applied under such conditions. At this time, plasma density is set from 1×10^{10} to $1 \times 10^{11} \text{ m}^{-3}$, so that so-called corona discharge or glow discharge is achieved. Surface modification can be performed without material dependence by employing plasma treatment using air, oxygen, or nitrogen as a treatment gas. Accordingly, surface modification can be performed on any material.

As another method, an organic material-based substance which functions as an adhesive may be formed to improve adhesion between a pattern formed by the droplet discharging method and a forming region thereof. An organic material (organic resin material) (polyimide or acrylic) is composed of a skeleton formed of the bond of silicon (Si) and oxygen (O), in which an organic group containing at least hydrogen (such as an alkyl group or aromatic hydrocarbon) is included as a substituent. Alternatively, a fluoro group may be used as the substituent. Further alternatively, a fluoro group and an organic group containing at least hydrogen may be used as the substituent.

Subsequently, a composition containing a conductive material is discharged, and conductive layers **1502** and **1503** to function as gate electrode layers later are formed. These conductive layers **1502** and **1503** are formed by the droplet discharging method. In this embodiment mode, silver is used

as the conductive material, however, a stack of silver, copper, and the like as well as a single layer of copper may be used.

The step of forming the base film **1501** described above is performed as pre-base treatment for a conductive layer formed by the droplet discharging method, however, this treatment may be performed after forming the conductive layers **1502** and **1503**.

Subsequently, a gate insulating film is formed over the conductive layers **1502** and **1503** (see FIG. 24A). The gate insulating film may be formed of a known material such as an oxide or nitride material of silicon, and may be stacked layers or a single layer.

The semiconductor layer may be formed by a known method (the sputtering method, the LPCVD method, the plasma CVD method, or the like). There is no particular limitation in materials of the semiconductor layer, but the semiconductor layer is preferably formed of silicon, a silicon germanium (SiGe) alloy, or the like.

The semiconductor layer uses an amorphous semiconductor (typically, hydrogenated amorphous silicon), a semi-amorphous semiconductor, a semiconductor of which semiconductor layer partially has a crystal phase, a crystalline semiconductor (typically polysilicon), or an organic semiconductor as a material.

In this embodiment mode, an amorphous semiconductor is used as the semiconductor. A semiconductor layer **1507** is formed, and then a semiconductor layer having one conductivity, for example, an N-type semiconductor layer **1508** is formed by the plasma CVD method or the like. The semiconductor layer having one conductivity may be formed as required.

Subsequently, mask layers **1511** and **1512** formed of an insulating material such as a resist or polyimide are formed. Then, the semiconductor layer **1507** and the N-type semiconductor layer **1508** are simultaneously patterned using the mask layers **1511** and **1512** (see FIG. 24B).

Then, mask layers **1513** and **1514** formed of an insulator such as a resist or polyimide are formed by using the droplet discharging method (see FIG. 24C). A through-hole **1518** is formed in a part of the gate insulating layers **1504** and **1505** by an etching process using the mask layers **1513** and **1514**, and a part of the conductive layer **1503** disposed on a lower layer side thereof and to function as a gate electrode layer is exposed. Either plasma etching (dry etching) or wet etching may be adopted as the etching process. In addition, a local discharge process can be performed when an atmospheric pressure discharge etching process is applied, and a mask layer does not need to be entirely formed over the substrate.

Conductive layers **1515**, **1516**, and **1517** are formed by discharging a composition containing a conductive material after the mask layers **1513** and **1514** are removed. Then, the N-type semiconductor layer is patterned using the conductive layers **1515**, **1516**, and **1517** as masks to form an N-type semiconductor layer (see FIG. 24D). Note that the aforementioned pre-base treatment to selectively form a photocatalytic substance or the like in a portion where the conductive layers **1515**, **1516**, and **1517** are to be in contact with the gate insulating layer **1505** may be performed before forming the conductive layers **1515**, **1516**, and **1517**, although not shown. Accordingly, the conductive layer can be formed with favorable adhesion with the stacked upper and lower layers.

Subsequently, a conductive layer (also referred to as a first electrode) **1506** is formed by selectively discharging a composition containing a conductive material onto the gate insulating film to be in contact with the conductive layer **1517** which functions as the source wiring layer or the drain wiring layer (see FIG. 25A). The conductive layer **1506** may be

formed by forming a predetermined pattern of a composition containing indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), zinc oxide (ZnO), tin oxide (SnO₂), or the like and by baking it when light is to be emitted from the substrate **1500** side or when a light transmissive EL display panel is to be manufactured. Although not shown, pre-base treatment such as formation of a photocatalytic substance may be performed similarly to the case of forming the conductive layers **1502** and **1503** in a region where the conductive layer **1506** is to be formed. The pre-base treatment can improve adhesiveness and the conductive layer **1506** can be formed into a desired pattern to be a thin line. The conductive layer **1506** becomes the first electrode which functions as a pixel electrode.

In addition, the conductive layer **1516** that is the source wiring layer or drain wiring layer and the conductive layer **1503** that is the gate electrode layer are electrically connected to each other in the through-hole **1518** formed in the gate insulating layer **1505**. A composition containing a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), or Al (aluminum) as its main component can be used as a conductive material for forming the conductive layer. In addition, light-transmissive indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), organic indium, organotin, zinc oxide, titanium nitride, and the like may be used in combination.

The step of forming the through-hole **1518** may be performed using the conductive layers **1515**, **1516**, **1517**, and **1506** as masks after forming the conductive layers **1515**, **1516**, **1517**, and **1506**. Then, a conductive layer is formed in the through-hole **1518**, and the conductive layer **1516** and the conductive layer **1503** as the gate electrode layer are electrically connected to each other.

Subsequently, an insulating layer **1520** to be a partition wall is formed. Although not shown, a protective layer formed of silicon nitride or silicon nitride oxide may be entirely formed under the insulating layer **1520** to cover a thin film transistor. An opening is formed in the insulating layer **1520** as shown in FIG. **25B** by an etching process after the insulating layer is entirely formed by the spin coating method or the dipping method. The etching process is not necessarily required when the insulating layer **1520** is formed by the droplet discharging method. When the a wide region such as the insulating layer **1520** is formed by the droplet discharging method, a throughput is improved by forming by discharging a composition from a plurality of discharging openings of nozzles in a droplet discharge apparatus and drawing so that a plurality of lines are overlapped with each other.

The insulating layer **1520** is formed to have a through-hole corresponding to a position where a pixel is to be formed in accordance with the conductive layer **1506** as the first electrode.

By the aforementioned steps, a TFT substrate is completed in which a bottom gate type (also referred to as an inversely staggered type) TFT and the conductive layer (the first electrode layer) **1506** are connected over the substrate **1500**.

By stacking an electroluminescent layer **1521** and a conductive layer **1522** over the conductive layer **1506** as the first electrode, a display device having a display function using a light emitting element is completed (see FIG. **25B**).

As described above, the step can be omitted in this embodiment mode by not applying a light exposure step utilizing a photo mask. In addition, an EL display panel can be easily manufactured by directly forming various patterns over a substrate by the droplet discharging method even when a glass substrate of the fifth or the following generation having a side of more than 1000 mm is used.

Furthermore, a display device of which adhesiveness and peeling resistance are improved and reliability is high can be manufactured.

Embodiment Mode 10

An embodiment mode of the invention is described with reference to FIGS. **26A** to **27**. This embodiment mode is different from Embodiment Mode 7 in that a thin film transistor and a first electrode are connected differently. Therefore, description of the same portion or a portion having a similar function is omitted.

A base film **1601** having a function to improve adhesiveness is formed over a substrate **1600** (see FIG. **26A**). An insulating layer may be formed over the substrate **1600**. This insulating layer is not necessarily provided, but has an effect to block a contaminant and the like from the substrate **1600**. In the case of using a staggered thin film transistor as in this embodiment mode, the base layer is effective since a semiconductor layer is in direct contact with the substrate. In the case of forming the base layer for preventing contamination from a glass substrate, the base film **1601** is formed as pre-treatment in forming regions of the conductive layers **1615**, **1616**, and **1617** by the droplet discharging method.

In this embodiment mode, a substance having a photocatalytic function is used as the base film **1601** having a function to improve adhesiveness.

In this embodiment mode, description is made on the case of forming a TiO_x crystal having a predetermined crystalline structure as a photocatalytic substance by the sputtering method. Sputtering is performed by using a metal titanium tube as a target and an argon gas and oxygen. Further, a He gas may be introduced as well. In order to form TiO_x which is highly photocatalytically active, an atmosphere containing a lot of oxygen is used with a rather high pressure. Further, TiO_x is preferably formed while heating a deposition chamber or a substrate over which an element is formed.

TiO_x formed in this manner has a photocatalytic function even in a thin film form.

It is preferable to form a base film **1601** formed of a metal material such as Ti (titanium), W (tungsten), Cr (chromium), Ta (tantalum), Ni (nickel), and Mo (molybdenum), or oxide thereof. The base film **1601** is to be formed with a thickness of 0.01 to 10 nm, and does not necessarily have a layer structure as long as it is formed quite thin. In the case of using a high-melting point material as the base film, it is preferable to treat the base film exposed on the surface by carrying out one of the following two steps after forming the conductive layers **1615**, **1616**, and **1617** to be source wiring layers or drain wiring layers.

The first method is a step of insulating the base film **1601** which is not overlapped with the conductive layers **1615**, **1616**, and **1617** to be a source wiring layer or a drain wiring layer and forming an insulating layer. In other words, the base film **1601** which is not overlapped with the conductive layers **1615**, **1616**, and **1617** to be a source wiring layer or a drain wiring layer is oxidized and insulated. When the base film **1601** is oxidized and insulated in this manner, it is preferable to form the base film **1601** to be 0.01 to 10 nm in thickness, thus, the base film can be easily oxidized. Note that oxidation may be performed by exposing to an oxygen atmosphere or by thermal treatment.

The second method is a step of removing the base film **1601** by etching using the conductive layers **1615**, **1616**, and **1617** to be source wiring layers or drain wiring layers as masks. When this step is employed, there is no limitation in the thickness of the base film **1601**.

Alternatively, a method for performing plasma treatment on a formation region (formation surface) can be employed as another pre-base treatment. The plasma treatment is performed with air, oxygen, or nitrogen used as a treatment gas, with pressure from several ten Torr to 1000 Torr (133000 Pa), preferably, from 100 Torr (13300 Pa) to 1000 Torr (133000 Pa), more preferably, from 700 Torr (93100 Pa) to 800 Torr (106400 Pa), that is, atmospheric pressure or pressure in proximity of atmospheric pressure, and a pulse voltage is applied under such conditions. At this time, plasma density is set at 1×10^{10} to $1 \times 10^{14} \text{ m}^{-3}$, so that so-called corona discharge or glow discharge is achieved. Surface modification can be performed without material dependence by employing plasma treatment using air, oxygen, or nitrogen as a treatment gas. Accordingly, surface modification can be performed on any material.

As another method, a substance of an organic material functioning as an adhesive may be formed to improve adhesion between a pattern to be formed by the droplet discharging method and a formation region thereof. An organic material (organic resin material) (polyimide or acrylic) or a material in which a skeletal structure is configured by the bond of silicon (Si) and oxygen (O) and which contains at least hydrogen as a substituent or which contains at least one of fluorine, an alkyl group, and aromatic hydrocarbon as a substituent may be used.

Subsequently, a composition containing a conductive material is discharged, and the conductive layers **1615**, **1616**, and **1617** to be source wiring layers or drain wiring layers are formed. These conductive layers **1615**, **1616**, and **1617** are formed by the droplet discharging method.

As the conductive material used for forming the conductive layers **1615**, **1616**, and **1617**, a composition containing as a main component a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), and Al (aluminum) can be used. In particular, a source wiring layer or a drain wiring layer which are preferably low in resistance are preferably formed by using any one of gold, silver, and copper dissolved or dispersed in a solvent in consideration of resistivity. More preferably, silver and copper which are low resistant are used. Further, a particle having a plurality of layers formed by coating the periphery of the conductive material with another conductive material may be used. For example, a particle having a three-layer structure in which the periphery of copper is coated with nickel boron (NiB) and then silver thereover, and the like may be used. As for such solvents, esters such as butyl acetate, alcohols such as isopropyl alcohol, organic solvents such as acetone, or the like may be used. The surface tension and viscosity are appropriately controlled by controlling the concentration of the solvent and adding a surfactant and the like.

The step of forming the base film **1601** described above is performed as pre-base treatment for a conductive layer formed by the droplet discharging method, however, this treatment may be performed after forming the conductive layers **1615**, **1616**, and **1617**. For example, by forming a titanium oxide film and an N-type semiconductor layer thereover though not shown, adhesion between the conductive layer and the N-type semiconductor layer is improved.

After forming the N-type semiconductor layer over the whole surface of the conductive layers **1615**, **1616**, and **1617**, the N-type semiconductor layer provided between the conductive layers **1615** and **1616** and between the conductive layers **1616** and **1617** is removed by etching using mask layers **1611**, **1612**, and **1619** formed of an insulator such as resist and polyimide. A semiconductor layer having one conductivity may be formed as required. Then, a semiconductor

layer **1607** formed of an AS or an SAS is formed by a vapor phase method or the sputtering method. In the case of employing the plasma CVD method, the AS is formed by using SiH_4 as a semiconductor material gas or a mixed gas of SiH_4 and H_2 . The SAS is formed of a mixed gas in which SiH_4 is diluted with H_2 by 3 to 1000 times. When the SAS is formed from the above kind of gas, the semiconductor layer has favorable crystallinity on a surface side thereof. The SAS is suitable for a top gate type TFT in which the gate electrode is formed in an upper layer of the semiconductor layer.

Subsequently, a gate insulating layer **1605** is formed with a single layer or a stacked-layer structure by the plasma CVD method or the sputtering method (see FIG. **26B**). A stack of three layers of an insulating layer formed of silicon nitride, an insulating layer formed of silicon oxide, and an insulating layer formed of silicon nitride is particularly a preferable structure.

Next, conductive layers **1602** and **1603** as the gate electrode layers are formed by the droplet discharging method (see FIG. **26C**). A composition containing a particle of a metal such as Ag (silver), Au (gold), Cu (copper), W (tungsten), or Al (aluminum), as its main component can be used as a conductive material for forming the gate electrode layers **1602** and **1603**.

The semiconductor layer **1607** and the gate insulating layer **1605** are formed in a position corresponding to the source wiring layers and the drain wiring layers (the conductive layers **1615**, **1616**, and **1617**) using the mask layers **1613** and **1614** formed by the droplet discharging method. In other words, the semiconductor layer and the gate insulating layer are formed to straddle over the conductive layers **1615** and **1616**.

Subsequently, conductive layers **1630** and **1631** are formed by the droplet discharging method and electrically connected to the conductive layer **1616** and the conductive layer **1603**.

Subsequently, a conductive layer (also referred to as a first electrode) **1606** is formed by selectively discharging a composition containing a conductive material so as to contact the conductive layer **1631**. Alternatively, the conductive layer **1606** may have a structure to have direct contact with the conductive layer **1617**. The conductive layer **1606** may be formed in a predetermined pattern of a composition containing indium tin oxide (ITO), indium tin oxide containing silicon oxide (ITSO), zinc oxide (ZnO), tin oxide (SnO_2), or the like and by baking it when light is emitted from the substrate **1600** side or when a light-transmissive EL display panel is manufactured. Although not shown, a photocatalytic substance may be formed in a region where the conductive layer **1606** is formed similarly to the case of forming the conductive layers **1615**, **1616**, and **1617**. With a photocatalytic substance, adhesiveness is improved and the conductive layer **1606** can be formed into a thin desired pattern to be a thin line. This conductive layer **1606** becomes a first electrode which functions as a pixel electrode.

The source wiring layer or drain wiring layer and the gate electrode layer may be directly connected through the gate electrode layer without using the conductive layer **1630**. In that case, a through-hole is formed in the gate insulating layer **1605** and a part of the conductive layers **1616** and **1617** that are the source or drain wirings is exposed before the conductive gate electrode layers **1602** and **1603** are formed. After that, the conductive gate electrode layers **1602**, **1603** and the conductive layer **1631** are formed by the droplet discharging method. At this time, the conductive layer **1603** is a wiring which also serves as the conductive layer **1630**, and is connected to the conductive layer **1616**. Either dry etching or wet

etching may be employed for etching, however, plasma etching which is dry etching is more preferable.

Subsequently, an insulating layer **1620** to be a partition wall is formed. Although not shown, a protective layer formed of silicon nitride or silicon nitride oxide may be entirely formed under the insulating layer **1620** to cover a thin film transistor. An opening is formed in the insulating layer **1620** as shown in FIG. **27** by an etching process after the insulating layer is entirely formed by the spin coating method or the dipping method. The etching process is not necessarily carried out when the insulating layer **1620** is formed by the droplet discharging method. When a wide region such as the insulating layer **1620** is formed by the droplet discharging method, a throughput is improved by forming by discharging a composition from a plurality of discharging openings of nozzles in a droplet discharge apparatus and drawing so that a plurality of lines are overlapped with each other.

The insulating layer **1620** is formed to have a through-hole corresponding to a position where a pixel is to be formed in accordance with the conductive layer **1606** as the first electrode.

By the aforementioned steps, a TFT substrate is completed in which a top gate type (also referred to as a staggered type) TFT and the conductive layer **1606** are connected over the substrate **1600**.

Moisture adsorbed in the insulating layer **1620** or to a surface thereof is removed by performing thermal treatment at 200° C. under atmospheric pressure before forming an electroluminescent layer **1621**. In addition, thermal treatment is performed at a temperature of 200 to 400° C., preferably, 250 to 350° C. under reduced pressure, and the electroluminescent layer **1621** is preferably formed by a vacuum vapor deposition method or the droplet discharging method under reduced pressure without being exposed to an atmospheric air.

By stacking an electroluminescent layer **1621** and a conductive layer **1622** over the conductive layer **1606** as the first electrode, a display device having a display function using a light emitting element is completed (see FIG. **27**).

As described above, a step can be omitted in this embodiment mode by not applying a light exposure step utilizing a photo mask. In addition, an EL display panel can be easily manufactured by directly forming various patterns over a substrate by the droplet discharging method even when a glass substrate of the fifth or the following generation having a side of more than 1000 mm is used.

Furthermore, a display device of which adhesiveness and peeling resistance are improved and reliability is high can be manufactured.

Embodiment Mode 11

An embodiment mode of the invention is described with reference to FIGS. **28A** to **29B**. This embodiment mode is different from Embodiment Mode 1 in that the conductive layer **816** as the wiring layer which passes through the gate electrode layer **805** and the conductive layer **803** as the gate electrode layer are connected differently. Therefore, description on the same portion or a portion having a similar function is omitted.

A base film **1701** to improve adhesiveness is formed over a substrate **1700** (see FIG. **28A**). It is to be noted that an insulating layer may be formed over the substrate **1700**.

In this embodiment mode, a substance having a photocatalytic function is used as the base film **1701** having a function to improve adhesiveness.

The case of forming TiO_x crystal having a predetermined crystalline structure by the sputtering method as a photocatalytic substance is described in this embodiment mode. Sputtering is performed using a metal titanium tube as a target and using an argon gas and oxygen. Further, a He gas may be introduced. The atmosphere includes much oxygen and formation pressure is set high to form TiO_x having high photocatalytic activity. It is preferable to form TiO_x while heating a deposition chamber or a substrate provided with an object to be treated.

The thus formed TiO_x has a photocatalytic function even in a quite thin film form.

It is preferable to form a base film **1701** using a metal material such as Ti (titanium), W (tungsten), Cr (chromium), Ta (tantalum), Ni (nickel), and Mo (molybdenum), or oxide thereof by the sputtering method, the vapor deposition method and the like as pre-base treatment. The base film is to be formed with a thickness of 0.01 to 10 nm, and does not necessarily have a layer structure as long as it is formed quite thin. In the case of using a high-melting point material as the base film, it is preferable to treat the base film exposed on the surface by carrying out one of the following two steps after forming the conductive layers **1702** and **1703** to be gate electrode layers.

The first method is a step of insulating the base film **1701** which is not overlapped with the conductive layers **1702** and **1703** and forming an insulating layer. In other words, the base film **1701** which is not overlapped with the conductive layers **1702** and **1703** is oxidized and insulated. When the base film **1701** is oxidized and insulated in this manner, it is preferable to form the base film **1701** to be 0.01 to 10 nm in thickness, thus, the base film can be easily oxidized. Note that oxidation may be performed by exposing to an oxygen atmosphere or by thermal treatment.

The second method is a step of removing the base film **1701** by etching using the conductive layers **1702** and **1703** as masks. When this step is employed, there is no limitation in the thickness of the base film **1701**.

Alternatively, a method for performing plasma treatment on a formation region (formation face) can be employed as another pre-base treatment. The plasma treatment is performed with air, oxygen, or nitrogen used as a treatment gas, with pressure from several ten Torr to 1000 Torr (133000 Pa), preferably, from 100 Torr (13300 Pa) to 1000 Torr (133000 Pa), more preferably, from 700 Torr (93100 Pa) to 800 Torr (106400 Pa), that is, atmospheric pressure or pressure in proximity of atmospheric pressure, and a pulse voltage is applied under such conditions. At this time, plasma density is set at 1×10^{10} to $1 \times 10^{14} \text{ m}^{-3}$, so that so-called corona discharge or glow discharge is achieved. Surface modification can be performed without material dependence by employing plasma treatment using air, oxygen, or nitrogen as a treatment gas. Accordingly, surface modification can be performed on any material.

As another method, a substance of an organic material functioning as an adhesive may be formed to improve adhesion between a pattern to be formed by the droplet discharging method and a formation region thereof. An organic material (organic resin material) (polyimide or acrylic) or a material in which a skeletal structure is configured by the bond of silicon (Si) and oxygen (O) and which contains at least hydrogen as a substituent or which contains at least one of fluorine, an alkyl group, and aromatic hydrocarbon as a substituent may be used.

Subsequently, a composition containing a conductive material is discharged, and the conductive layers **1702** and **1703** to be source wiring layers or drain wiring layers are

formed. These conductive layers **1702** and **1703** are formed by the droplet discharging method.

A conductor **1704** which functions as a pillar is formed by locally discharging a composition containing a conductive material after the conductive layer **1703** is formed. The conductor **1740** is preferably formed to be cylindrical by depositing the discharged composition so that a pattern in a lower layer and a pattern in an upper layer easily make contact with each other when the cylindrical conductor **1740** is used. The conductor **1704** may be formed of the same material as that of the conductive layer **1703** or be formed of a different material. It may be formed by discharging the composition to be stacked.

After the conductive layer **1703** is formed, the aforementioned pre-base treatment may be performed on the conductive layer **1703** to improve the adhesiveness again. Further, it is preferable to perform pre-base treatment similarly, after the conductor **1704** to be a pillar is formed. Layers can have favorable adhesion when pre-base treatment such as forming a photocatalytic substance such as TiO_x is performed.

Subsequently, a gate insulating film is formed over the conductive layers **1702** and **1703** (see FIG. **28A**).

Then, a conductive layer (also referred to as a first electrode) **1706** is formed by selectively discharging a composition containing a conductive material onto the gate insulating film (see FIG. **28B**). Although not shown, a photocatalytic substance may be formed similarly to the case of forming the conductive layers **1702** and **1703** in a region where the conductive layer **1706** is formed. The photocatalytic substance can improve adhesiveness and the conductive layer **1706** can be formed into a desired pattern to be a thin line. The conductive layer **1706** becomes the first electrode to function as a pixel electrode.

An amorphous semiconductor is used as the semiconductor in this embodiment mode. A semiconductor layer **1707** that is an amorphous semiconductor layer is formed, and an insulating film is formed by, for example, the plasma CVD method and is selectively etched to have a desired shape in a desired region in order to form channel protective films **1709** and **1710**. At this time, the channel protective films **1709** and **1710** can be formed by exposing a back of the substrate to light using the gate electrode as a mask. In addition, polyimide, polyvinyl alcohol, or the like may be dropped as the channel protective film by the droplet discharging method. Consequently, an exposure step can be omitted. Thereafter, a semiconductor layer having one conductivity, for example, an N-type semiconductor layer **1708** using an N-type amorphous semiconductor layer is formed by the plasma CVD method or the like (see FIG. **28C**). The semiconductor layer having one conductivity may be formed as required.

Subsequently, mask layers **1711** and **1712** formed of an insulator such as a resist or polyimide are formed, and the semiconductor layer **1707** and the N-type semiconductor layer **1708** are simultaneously patterned using the mask layers **1711** and **1712**.

In this embodiment mode, a conductor to be connected to the conductive layer **1703** which is a gate electrode layer by the conductor **1704** which functions as a pillar passes through the gate electrode layer **1705** and exists on the gate insulating layer **1705**. Therefore, a step of opening a through-hole in the gate insulating layer can be omitted.

Conductive layers **1715**, **1716**, and **1717** are formed by discharging a composition containing a conductive material. Then, the N-type semiconductor layer is patterned using the conductive layers **1715**, **1716**, and **1717** as masks. Note that a photocatalytic substance may be selectively formed in a portion where the conductive layers **1715**, **1716**, and **1717** are in

contact with the gate insulating layer **1705** before forming the conductive layers **1715**, **1716**, and **1717**, although not shown. Accordingly, the conductive layer can be formed with favorable adhesion.

The conductive layer **1717** functions as a source wiring layer or a drain wiring layer and is formed to be electrically connected to the first electrode formed beforehand. The conductive layer **1716** which is a source wiring layer or a drain wiring layer can be electrically connected to the conductive layer **1703** which is the gate electrode layer through the conductor **1704** (see FIG. **29A**). When the insulating layer or the like is left over the conductor **1704** which functions as a pillar, it may be removed by etching or the like.

Subsequently, an insulating layer **1720** to be a partition wall is formed.

The insulating layer **1720** is formed to have a through-hole corresponding to a position where a pixel is to be formed in accordance with the conductive layer **1706** that is the first electrode.

By the above-mentioned steps, a TFT substrate for the EL display panel in which a bottom gate type (also referred to as an inversely staggered type) channel protective TFT and the first electrode (first electrode layer) are connected over the substrate **1700** is completed.

An electroluminescent layer **1721** and a conductive layer **1722** are stacked over the conductive layer **1706** that is the first electrode, and then, a display device having a display function using a light emitting element is completed (see FIG. **29B**).

As described above, the step can be omitted in this embodiment mode by not applying a light exposure step utilizing a photo mask. In addition, an EL display panel can be easily manufactured by directly forming various patterns over a substrate by the droplet discharging method even when a glass substrate of the fifth or the following generation having a side of more than 1000 mm is used.

In addition, a highly reliable display device of which adhesiveness and peel resistance are improved can be manufactured. A connecting method of using a pillar for a through-hole in this embodiment mode can be implemented freely in combination with the above embodiment modes.

Embodiment Mode 12

A thin film transistor can be formed by applying the invention, and a display device can be formed by using the thin film transistor. In the case of using a light emitting element as a display element and using an N-type transistor as a transistor for driving the light emitting element, light emitted from the light emitting element is any one of the bottom emission, top emission, and dual emission. Here, a stacked structure of a light emitting element for any case is described with reference to FIGS. **30A** to **30C**.

A transistor **1851** that is a channel protective thin film transistor formed in Embodiment Mode 1 by applying the invention is used in this embodiment.

First, the case where light is emitted to a substrate **1850** side, that is, the case of bottom emission is described with reference to FIG. **30A**. In this case, a source wiring or a drain wiring **1852** and **1853**, a first electrode **1854**, an electroluminescent layer **1855**, and a second electrode **1856** are sequentially stacked so as to be electrically connected to a transistor **1851**. Next, the case where light is emitted to an opposite side of the substrate **1850**, that is, the case of top emission is described with reference to FIG. **30B**. A source wiring or a drain wiring **1861** and **1862**, a first electrode **1863**, an electroluminescent layer **1864**, and a second electrode **1865** are

sequentially stacked, so as to be electrically connected to the transistor 1851. Even if the first electrode 1863 transmits light, the light is reflected by the wiring 1862 and emitted to the opposite side to the substrate 1850 in the above structure. Note that a light-transmissive material is not required to be used for the first electrode 1863 in this structure. Lastly, the case where light is emitted to the substrate 1850 side and to the opposite side thereto, that is, the case of dual emission is described with reference to FIG. 30C. A source wiring or a drain wiring 1870 and 1871, a first electrode 1872, an electroluminescent layer 1873, and a second electrode 1874 are sequentially stacked so as to be electrically connected to the transistor 1851. At this time, dual emission is realized when both the first electrode 1872 and the second electrode 1874 are formed of a light-transmissive material or formed thin enough to transmit light.

The light emitting element has a structure in which the electroluminescent layer is sandwiched between the first electrode and the second electrode. It is necessary to select materials of the first electrode and the second electrode in consideration of a work function. Both the first electrode and the second electrode can be an anode or a cathode depending on a pixel structure. Since polarity of a driving TFT is an N-channel type in this embodiment mode, the first electrode is preferably a cathode and the second electrode is preferably an anode. When polarity of the driving TFT is a P-channel type, the first electrode is preferably an anode and the second electrode is preferably a cathode.

When the first electrode is an anode, the electroluminescent layer is preferably formed by sequentially stacking an HIL (hole injecting layer), an HTL (hole transporting layer), an EML (light emitting layer), an ETL (electron transporting layer), and an EIL (electron injecting layer) from an anode side. When the first electrode is a cathode, a structure of the electroluminescent layer becomes the reverse. It is preferable to sequentially stack an EIL (electron injecting layer), an ETL (electron transporting layer), an EML (light emitting layer), an HTL (hole transporting layer), an HIL (hole injecting layer), and an anode that is the second electrode from a cathode side. Note that the electroluminescent layer can have a single-layer structure or a combined structure as well as a stacked-layer structure.

Materials showing luminescence of red (R), green (G), and blue (B) may be selectively formed as the electroluminescent layer by the vapor deposition method using respective vapor deposition masks or the like. The materials showing luminescence of red (R), green (G), and blue (B) (such as a low molecular weight or high molecular weight material) can be formed by the droplet discharging method, which is preferable since coloring of RGB can be separately performed in this case without using a mask similarly to a color filter.

In specific, CuPc or PEDOT is used as the HIL, α -NPD is used as the HTL, BCP or Alq₃ is used, as the ETL, BCP:Li or CaF₂ is used, as the EIL, respectively. In addition, Alq₃-doped with a dopant corresponding to respective luminescence colors of R, G and B (DCM or the like in the case of R, and DMQD or the like in the case of G) may be used as the EML, for example.

Note that the electroluminescent layer is not limited to the above material. For example, a hole injecting property can be enhanced by co-evaporating oxide such as molybdenum oxide (MoO_x; x=2 to 3) and α -NPD or rubrene instead of using CuPc or PEDOT. An organic material (including a low molecular weight material or a high molecular weight material) or a composite material of an organic material and an inorganic material can be used as the material of the electroluminescent layer.

In addition, a color filter may be formed on an counter substrate of the substrate 1850, although not shown in FIGS. 30A to 30C. The color filter can be formed by the droplet discharging method, in that case, photoplasma treatment can be performed as the aforementioned pre-base treatment. The color filter can be formed in a desired pattern with favorable adhesion due to the base film of the invention. High-definition display can be performed by using the color filter. This is because the color filter can adjust a broad peak to be sharp in each emission spectrum of RGB.

The case of forming materials showing each luminescence of RGB is described hereinabove, however, full color display can be performed also by forming a material showing luminescence of a single color and using the material with a color filter or a color conversion layer in combination. For example, in the case of forming an electroluminescent layer showing white or orange luminescence, full color display can be performed by separately providing a color filter, a color conversion layer, or a combination of a color filter and a color conversion layer. For example, the color filter or the color conversion layer may be formed over a second substrate (sealing substrate), and then, be attached to the substrate. As described above, the material showing luminescence of a single color, the color filter, and the color conversion layer can all be formed by the droplet discharging method.

It is needless to say that display of single color luminescence may be performed. For example, an area color type display device may be formed by using single color luminescence. A passive matrix display portion is suitable for the area color type which can display mainly text and symbols.

A material having a low work function can be used for the cathode in the above structure, for example, Ca, Al, CaF, MgAg, AlLi, or the like is preferable. The electroluminescent layer may be any one of a single-layer type, a stacked-layer type, and a mixed-layer type having no interface between layers. Any of the following materials can be used: a singlet material, a triplet material, a combined material thereof, an organic material including a low molecular weight material, a high molecular weight material, and an intermediate molecular weight material, an inorganic material typified by molybdenum oxide which is superior in an electron injecting property, and a composite material of an organic material and an inorganic material. The first electrodes 1854, 1863, and 1872 are formed by using a light-transmissive conductive film which transmits light, for example, a light-transmissive conductive film in which indium oxide is mixed with zinc oxide (ZnO) of 2 to 20 wt % as well as ITO or ITSO. Note that plasma treatment in an oxygen atmosphere or heat treatment in a vacuum atmosphere is preferably performed before forming the first electrodes 1854, 1863, and 1872. A partition wall (also referred to as a bank) is formed by using a material containing silicon, an organic material, or a compound material. In addition, a porous film may be used. Note that it is preferable to form the partition wall by using a photosensitive or non-photosensitive material such as acrylic or polyimide, since a side face thereof becomes a shape in which a curvature radius continuously changes and an upper-layer thin film is formed without break. This embodiment mode can be freely implemented in combination with the above embodiment mode.

Embodiment Mode 13

An appearance of a panel that is one mode of a display device to which the invention is applied is described with reference to FIG. 31.

55

In a panel shown in FIG. 31, a driver IC in which a driver circuit is formed around a pixel portion **1951** is mounted by a COG (Chip On Glass) method. It is needless to say that the driver IC may be mounted by a TAB (Tape Automated Bonding) method as well.

A substrate **1950** is fixed to an counter substrate **1953** with a sealing material **1952**. The pixel portion **1951** may utilize an EL element as a display medium. Driver ICs **1955a** and **1955b**, and driver ICs **1957a**, **1957b**, and **1957c** may each be an integrated circuit formed by using a single crystalline semiconductor, or an equivalent formed by using a TFT which is manufactured by using a polycrystalline semiconductor. A signal or power is supplied to the driver ICs **1955a** and **1955b**, and the driver ICs **1957a**, **1957b**, and **1957c** through FPCs **1954a**, **1954b** and **1954c**, and FPCs **1956a** and **1956b**, respectively.

Embodiment Mode 14

An EL TV set can be completed by using a display device formed in accordance with the invention. FIG. 32 is a block diagram showing a main structure of the EL TV set. An EL display panel includes, as a structure as shown in FIG. 31, the case that a scan line driver circuit and a signal line driver circuit are mounted on a pixel portion **1951** and in a periphery thereof by the COG method, that only a pixel portion is formed and the scan line driver circuit and the signal line driver circuit are mounted by the TAB method, and that a TFT is formed using an SAS, a pixel portion and the scan line driver circuit are integrated over a substrate, and the signal line driver circuit is separately mounted as a driver IC, however, any mode may be employed.

Another external circuit may be composed of a video signal amplifier circuit **2005** which amplifies a video signal among signals received by a tuner **2004**, a video signal processing circuit **2006** which converts a signal to be outputted therefrom into a chrominance signal corresponding to each color of red, green, and blue, a control circuit **2007** which converts the video signal so as to be inputted to a driver IC, and the like on an input side of a video signal. The control circuit **2007** outputs a signal to both a scan line side and a signal line side. In the case of digital drive, a signal divider circuit **2008** may be provided on the signal line side, and an input digital signal may be divided into m parts and be supplied.

An audio signal among signals received by the tuner **2004** is transmitted to an audio signal amplifier circuit **2009** and is supplied to a speaker **2013** through an audio signal processing circuit **2010**. A control circuit **2011** receives control data on a receiving station (reception frequency) or volume from an input portion **2012** and transmits the signal to the tuner **2004** and the audio signal processing circuit **2010**.

A TV set can be completed by incorporating an EL module including such external circuits into a housing **2101** as shown in FIG. 33. A display screen **2021** is formed by using an EL display module, and a speaker **2202**, an operating switch **2024**, and the like may be provided as accessory equipment. In this manner, a TV set can be completed in accordance with the invention.

In addition, reflected light of light entering externally may be blocked by using a wave plate and a polarizing plate. A $\lambda/4$ plate or a $\lambda/2$ plate are used as the wave plate, and may be designed to be able to control light. A module has a stacked structure of a TFT element substrate, a light emitting element, a sealing substrate (sealing material), a wave plate (a $\lambda/4$ plate or a $\lambda/2$ plate), and a polarizing plate, and light emitted from a light emitting element passes therethrough and is emitted outside the polarizing plate side. The wave plate and the

56

polarizing plate may be provided on an a side of to which light is emitted. In the case of a dual emission light emitting display device which emits light to both sides, the wave plate and the polarizing plate can be provided on both sides. In addition, an anti-reflective film may be provided outside the polarizing plate. Accordingly, a high definition precise image can be displayed.

A display panel **2102** utilizing an EL element is incorporated in the housing **2101**. Not only can ordinary TV broadcasting be received by a receiver **2105**, but also one-way data communication (from a transmitter to a receiver) or two-way data communication (between a transmitter and a receiver or between receivers) can be achieved by connecting to a communication network with or without a wire through a modem **2104**. The TV set can be operated by a switch incorporated in the housing or a separately provided remote control unit **2106**, and a display portion **2107** showing information to be outputted may be included in the remote control unit.

Further, the TV set may also have a sub screen **2108** formed of a second display panel which displays channels or volume, in addition to a main screen **2103**. The main screen **2103** and the sub screen **2108** may be formed by using an EL display panel. Alternatively, the main screen **2103** may be formed by an EL display panel having an excellent viewing angle and the sub screen **2108** may be formed by using a liquid crystal display panel capable of displaying at low power consumption in the above structure. Further, in the case of giving priority on the low power consumption, the main screen **2103** may be formed by using a liquid crystal display panel, the sub screen **2108** may be formed by using an EL display panel which can blink. A highly reliable display device can be formed by applying the invention even when such a large substrate is used, and a large number of TFTs or electronic parts are used.

It is needless to say that the invention is not limited to a TV set and can be used for various applications particularly for a large display medium such as an information display board in a train station, an airport, or the like, or an advertisement display board on the street as well as a monitor of a personal computer.

Embodiment Mode 15

Various display devices can be manufactured by applying the invention. That is to say, the invention can be applied to various electronic devices in which the display device is incorporated in a display portion.

Such electronic devices can be given as follows: a camera such as a video camera and a digital camera, a projector, a head mounted display (a goggle type display), a car navigation system, a car stereo, a personal computer, a game machine, a portable information terminal (a mobile computer, a cellular phone, an electronic book, or the like), an image reproducing device including a recording medium (specifically, a device capable of reproducing the recording medium such as a Digital Versatile Disc (DVD) and having a display that can display the reproduced image), and the like. Examples thereof are shown in FIGS. 34A to 34C.

FIG. 34A shows a laptop personal computer, which includes a main body **2201**, a housing **2202**, a display portion **2203**, a keyboard **2204**, an external connection port **2205**, a pointing mouse **2206**, and the like. The invention is applied for manufacturing the display portion **2203**. When the invention is applied, a laptop personal computer having a display portion with high display quality can be manufactured at low cost.

57

FIG. 34B shows an image reproducing device (specifically, a DVD reproducing device) including an image display portion, which includes a main body 2301, a housing 2302, a display portion A 2303, a display portion B 2304, a recording medium (a DVD or the like) reading portion 2305, an operation key 2306, a speaker portion 2307, and the like. The display portion A 2303 mainly displays image data, and the display portion B 2304 mainly displays text data. The invention is applied for manufacturing the display portion A 2303 and the display portion B 2304. When the invention is applied, an image reproducing device having an image display portion with high display quality can be manufactured at low cost.

FIG. 34C shows a cellular phone, which includes a main body 2401, an audio output portion 2402, an audio input portion 2403, a display portion 2404, operating switches 2405, an antenna 2406, and the like. When a display device manufactured in accordance with the invention is applied to the display portion 2404, a cellular phone having a display portion with high display quality can be manufactured at low cost.

FIG. 35A shows a video camera which includes a main body 2501, a display portion 2502, a housing 2503, an external connecting port 2504, a remote control receiving portion 2505, an image receiving portion 2506, a battery 2507, an audio input portion 2508, operation keys 2509, an eyepiece portion 2510 and the like. The invention can be applied to the display portion 2502, which is a dual emission light emitting display device. FIGS. 35B and 35C show an image displayed in the display portion 2502. FIG. 35B shows an image being shot, and FIG. 35C shows an image which can be seen from the side of a vehicle being shot. Since the display device of the invention is a light transmissive type and thus an image can be displayed on both sides, the image being shot can be seen from a subject side as well. Therefore, it is also convenient to shoot a picture of oneself. In addition, the invention can be applied to a digital video camera or the like as well as a video camera for which a similar effect can be obtained. By applying the display device manufactured in accordance with the invention to the display portion 2502, a camera such as a video camera and a digital video camera having a display portion with high display quality can be manufactured at low cost. This embodiment can be freely implemented in combination with the above embodiment modes.

The present application is based on Japanese Priority Application No. 2004-353457 filed on Dec. 6, 2004 with the Japan Patent Office, the entire contents of which are hereby incorporated by reference.

What is claimed is:

1. A semiconductor device comprising:
 - a first pixel;
 - a second pixel;
 - a first power supply line electrically connected to the first pixel and the second pixel;
 - a second power supply line that intersects with the first power supply line, wherein the second power supply line is electrically connected to the first power supply line;
 - a first line electrically connected to the first pixel;
 - a second line electrically connected to the second pixel; and
 - a gate signal line driver circuit, wherein a first terminal of the gate signal line driver circuit is electrically connected to the first line and the second line.
2. The semiconductor device according to claim 1, further comprising:
 - a third pixel electrically connected to the first power supply line; and

58

a third line electrically connected to the third pixel, wherein a second terminal of the gate signal line driver circuit is electrically connected to the third line, and wherein the third line is not electrically connected to the first line and the second line at the second terminal.

3. The semiconductor device according to claim 1, wherein the first pixel comprising:

- a first thin film transistor whose gate terminal is electrically connected to the first line;
- a second thin film transistor whose first terminal is electrically connected to the first power supply line;
- a capacitor whose first terminal is electrically connected to the first power supply line; and
- a light emitting element electrically connected to a second terminal of the second thin film transistor.

4. The semiconductor device according to claim 1, wherein the first pixel comprising:

- a first thin film transistor whose gate terminal is electrically connected to the first line;
- a second thin film transistor whose first terminal is electrically connected to the first power supply line, and whose gate terminal is electrically connected to a first terminal of the first thin film transistor;
- a capacitor whose first terminal is electrically connected to the first power supply line, and whose second terminal is electrically connected to the gate terminal of the second thin film transistor; and
- a light emitting element electrically connected to a second terminal of the second thin film transistor, wherein the second terminal of the second thin film transistor is directly connected to the light emitting element, and wherein the second terminal of the capacitor is directly connected to the second terminal of the second thin film transistor.

5. The semiconductor device according to claim 1, further comprising:

- a first source signal line electrically connected to the first pixel; and
- a second source signal line electrically connected to the second pixel.

6. The semiconductor device according to claim 1, wherein the first pixel comprises a thin film transistor, and wherein the thin film transistor comprises a semiconductor layer that comprises polysilicon.

7. A cellular phone comprising the semiconductor device according to claim 1.

8. An electronic book comprising the semiconductor device according to claim 1.

9. A semiconductor device comprising:

- a first pixel;
- a second pixel;
- a third pixel;
- a fourth pixel;
- a first power supply line electrically connected to the first pixel and the second pixel;
- a second power supply line that intersects with the first power supply line, wherein the second power supply line is electrically connected to the first power supply line;
- a third power supply line electrically connected to the third pixel and the fourth pixel, wherein the third power supply line intersects with the second power supply line, and wherein the third power supply line is electrically connected to the second power supply line;
- a first line electrically connected to the first pixel and the third pixel;

59

a second line electrically connected to the second pixel and the fourth pixel; and
 a gate signal line driver circuit, wherein a first terminal of the gate signal line driver circuit is electrically connected to the first line and the second line.

10. The semiconductor device according to claim 9, further comprising:

a fifth pixel electrically connected to the first power supply line; and

a third line electrically connected to the fifth pixel, wherein a second terminal of the gate signal line driver circuit is electrically connected to the third line, and wherein the third line is not electrically connected to the first line and the second line at the second terminal.

11. The semiconductor device according to claim 9, wherein the first pixel, the second pixel, the third pixel, and the fourth pixel are arranged in matrix.

12. The semiconductor device according to claim 9, wherein the first pixel comprising:

a first thin film transistor whose gate terminal is electrically connected to the first line;

a second thin film transistor whose first terminal is electrically connected to the first power supply line;

a capacitor whose first terminal is electrically connected to the first power supply line; and

a light emitting element electrically connected to a second terminal of the second thin film transistor.

13. The semiconductor device according to claim 9, wherein the first pixel comprising:

a first thin film transistor whose gate terminal is electrically connected to the first line;

a second thin film transistor whose first terminal is electrically connected to the first power supply line, and whose gate terminal is electrically connected to a first terminal of the first thin film transistor;

a capacitor whose first terminal is electrically connected to the first power supply line, and whose second terminal is electrically connected to the gate terminal of the second thin film transistor; and

a light emitting element electrically connected to a second terminal of the second thin film transistor,

wherein the second terminal of the second thin film transistor is directly connected to the light emitting element, and

wherein the second terminal of the capacitor is directly connected to the second terminal of the second thin film transistor.

14. The semiconductor device according to claim 9, further comprising:

a first source signal line electrically connected to the first pixel; and

a second source signal line electrically connected to the second pixel.

15. The semiconductor device according to claim 9, wherein the first pixel comprises a thin film transistor, and wherein the thin film transistor comprises a semiconductor layer that comprises polysilicon.

16. A cellular phone comprising the semiconductor device according to claim 9.

17. An electronic hook comprising the semiconductor device according to claim 9.

18. A semiconductor device comprising:

a first pixel;

a second pixel;

a third pixel;

a fourth pixel;

60

a first power supply line electrically connected to the first pixel and the second pixel;

a second power supply line that intersects with the first power supply line, wherein the second power supply line is electrically connected to the first power supply line;

a third power supply line electrically connected to the third pixel and the fourth pixel, wherein the third power supply line intersects with the second power supply line, and wherein the third power supply line is electrically connected to the second power supply line;

a first line electrically connected to the first pixel and the third pixel;

a second line electrically connected to the second pixel and the fourth pixel; and

a gate signal line driver circuit, wherein a first terminal of the gate signal line driver circuit is electrically connected to the first line and the second line,

wherein the first pixel comprises:

a first thin film transistor whose gate terminal is electrically connected to the first line, and whose first terminal is electrically connected to a third line, wherein the third line is electrically connected to a source signal line driver circuit;

a second thin film transistor whose first terminal is electrically connected to the first power supply line;

a capacitor whose first terminal is electrically connected to the first power supply line, and whose second terminal is electrically connected to a second terminal of the first thin film transistor; and

a light emitting element electrically connected to a second terminal of the second thin film transistor.

19. The semiconductor device according to claim 18, further comprising:

a fifth pixel electrically connected to the first power supply line; and

a fourth line electrically connected to the fifth pixel, wherein a second terminal of the gate signal line driver circuit is electrically connected to the fourth line, and wherein the fourth line is not electrically connected to the first line and the second line at the second terminal.

20. The semiconductor device according to claim 18, wherein the first pixel, the second pixel, the third pixel, and the fourth pixel are arranged in matrix.

21. The semiconductor device according to claim 18, wherein the first thin film transistor comprises a semiconductor layer that comprises polysilicon.

22. The semiconductor device according to claim 18, wherein the gate terminal of the second thin film transistor is electrically connected to the second terminal of the first thin film transistor.

23. The semiconductor device according to claim 18, wherein the gate terminal of the second thin film transistor is electrically connected to the second terminal of the capacitor.

24. The semiconductor device according to claim 18, wherein the second terminal of the second thin film transistor is directly connected to the light emitting element.

25. The semiconductor device according to claim 18, wherein the second terminal of the capacitor is directly connected to the second terminal of the first thin film transistor.

26. The semiconductor device according to claim 18, further comprising:

a fourth line electrically connected to the second pixel, wherein the fourth line is electrically connected to the source signal line driver circuit.

27. The semiconductor device according to claim 18, wherein the second pixel comprises:

61

- a third thin film transistor whose gate terminal is electrically connected to the second line, and whose first terminal is electrically connected to a fourth line, wherein the fourth line is electrically connected to the source signal line driver circuit;
- a fourth thin film transistor whose first terminal is electrically connected to the first power supply line;
- a second capacitor whose first terminal is electrically connected to the first power supply line, and whose second terminal is electrically connected to the second terminal of the third thin film transistor; and
- a second light emitting element electrically connected to a second terminal of the fourth thin film transistor.
28. A cellular phone comprising the semiconductor device according to claim 18.
29. An electronic book comprising the semiconductor device according to claim 18.
30. A semiconductor device comprising:
- a plurality of pixels arranged in matrix, the plurality of pixels comprising a first pixel in n-th row and a second pixel in (n+1)-th row, wherein n is an integer larger of 1 or more;
 - a first power supply line electrically connected to the first pixel and the second pixel;
 - a second power supply line that intersects with the first power supply line, wherein the second power supply line is electrically connected to the first power supply line;
 - a first line electrically connected to the first pixel;
 - a second line electrically connected to the second pixel; and
 - a gate signal line driver circuit, wherein a first terminal of the gate signal line driver circuit is electrically connected to the first line and the second line.
31. The semiconductor device according to claim 30, further comprising:
- a third pixel electrically connected to the first power supply line; and
 - a third line electrically connected to the third pixel, wherein a second terminal of the gate signal line driver circuit is electrically connected to the third line, and wherein the third line is not electrically connected to the first line and the second line at the second terminal.
32. The semiconductor device according to claim 30, wherein the first pixel comprising:

62

- a first thin film transistor whose gate terminal is electrically connected to the first line;
 - a second thin film transistor whose first terminal is electrically connected to the first power supply line;
 - a capacitor whose first terminal whose first terminal is electrically connected to the first power supply line; and
 - a light emitting element electrically connected to a second terminal of the second thin film transistor.
33. The semiconductor device according to claim 30, wherein the first pixel comprising:
- a first thin film transistor whose gate terminal is electrically connected to the first line;
 - a second thin film transistor whose first terminal is electrically connected to the first power supply line, and whose gate terminal is electrically connected to a first terminal of the first thin film transistor;
 - a capacitor whose first terminal is electrically connected to the first power supply line, and whose second terminal is electrically connected to the gate terminal of the second thin film transistor; and
 - a light emitting element electrically connected to a second terminal of the second thin film transistor,
- wherein the second terminal of the second thin film transistor is directly connected to the light emitting element, and
- wherein the second terminal of the capacitor is directly connected to the second terminal of the second thin film transistor.
34. The semiconductor device according to claim 30, further comprising:
- a first source signal line electrically connected to the first pixel; and
 - a second source signal line electrically connected to the second pixel.
35. The semiconductor device according to claim 30, wherein the first pixel comprises a thin film transistor, and wherein the thin film transistor comprises a semiconductor layer that comprises polysilicon.
36. A cellular phone comprising the semiconductor device according to claim 30.
37. An electronic book comprising the semiconductor device according to claim 30.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 8,228,277 B2
APPLICATION NO. : 13/293762
DATED : July 24, 2012
INVENTOR(S) : Yasunori Yoshida et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

In the Specification:

Column 2, line 18, "1FT **101**" should read "TFT **101**"

Column 7, line 31, "FIGS. **5A** and **513**" should read "FIGS. **5A** and **5B**"

Column 21, line 19, "nor or lower" should read "100°C or lower"

Column 26, line 47, "driving **1002** is connected" should read "driving TFT **1002** is connected"

Column 27, line 47, "R, and B pixels" should read "R, G, and B pixels"

Column 28, line 7, "ease" should read "case"


Column 33, line 45, "tarried" should read "carried"

Column 42, line 37, "channel protective" should read "channel protective TFT"

In the Claims:

Column 59, claim 17, line 61, "An electronic hook" should read "An electronic book"

Signed and Sealed this
Eighteenth Day of December, 2012

A handwritten signature in black ink, reading "David J. Kappos". The signature is written in a cursive, flowing style with a large initial "D".

David J. Kappos
Director of the United States Patent and Trademark Office

专利名称(译)	显示设备		
公开(公告)号	US8228277	公开(公告)日	2012-07-24
申请号	US13/293762	申请日	2011-11-10
[标]申请(专利权)人(译)	株式会社半导体能源研究所		
申请(专利权)人(译)	半导体能源研究所有限公司.		
当前申请(专利权)人(译)	半导体能源研究所有限公司.		
[标]发明人	YOSHIDA YASUNORI KIMURA HAJIME MAEKAWA SHINJI NAKAMURA OSAMU YAMAZAKI SHUNPEI		
发明人	YOSHIDA, YASUNORI KIMURA, HAJIME MAEKAWA, SHINJI NAKAMURA, OSAMU YAMAZAKI, SHUNPEI		
IPC分类号	G09G3/36		
CPC分类号	H01L21/288 H01L21/76838 H01L27/1292 H01L27/156 H01L27/1285 H01L27/3276 H01L27/3248 G09G3/32 G09G3/36 H01L27/1214 H01L27/124 H01L51/0508		
优先权	2004353457 2004-12-06 JP 10/579987 2006-05-19 US		
其他公开文献	US20120056550A1		
外部链接	Espacenet USPTO		

摘要(译)

本发明提供一种有源矩阵EL显示装置，可以进行清晰的多灰度彩色显示。特别地，本发明通过可以选择性地形成图案的制造方法以低成本提供大型有源矩阵EL显示装置。通过可以选择性地形成图案的制造方法将像素部分中的电源线布置成矩阵。此外，通过可以选择性地形成图案的制造方法在相邻布线之间提供更长的距离来减小布线之间的电容。

