



US009705092B2

(12) **United States Patent**  
**Yamamoto et al.**

(10) **Patent No.:** **US 9,705,092 B2**  
(45) **Date of Patent:** **Jul. 11, 2017**

(54) **PHOSPHORESCENT ORGANIC LIGHT EMITTING DEVICES COMBINED WITH HOLE TRANSPORT MATERIAL HAVING HIGH OPERATING STABILITY**

(75) Inventors: **Hitoshi Yamamoto**, Princeton, NJ (US); **Michael Stewart Weaver**, Princeton, NJ (US); **Norimasa Yokoyama**, Tsukuba (JP); **Makoto Nagaoka**, Tsukuba (JP); **Naoaki Kabasawa**, Tsukuba (JP)

(73) Assignees: **Universal Display Corporation**, Ewing, NJ (US); **Hodogaya Chemical Co., Ltd.**, Tokyo (JP)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 600 days.

(21) Appl. No.: **14/237,142**

(22) PCT Filed: **Aug. 5, 2011**

(86) PCT No.: **PCT/US2011/046736**

§ 371 (c)(1),  
(2), (4) Date: **Mar. 31, 2014**

(87) PCT Pub. No.: **WO2013/022419**

PCT Pub. Date: **Feb. 14, 2013**

(65) **Prior Publication Data**

US 2014/0339518 A1 Nov. 20, 2014

(51) **Int. Cl.**  
**H01L 51/50** (2006.01)  
**H01L 51/00** (2006.01)

(Continued)

(52) **U.S. Cl.**  
CPC ..... **H01L 51/0072** (2013.01); **C09K 11/06** (2013.01); **H01L 51/0054** (2013.01);  
(Continued)

(58) **Field of Classification Search**

None  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2002/0034656 A1\* 3/2002 Thompson ..... C07D 209/86  
428/690

2006/0073357 A1 4/2006 Brunner et al.  
(Continued)

FOREIGN PATENT DOCUMENTS

CN 102850177 1/2013  
EP 1589789 10/2005

(Continued)

OTHER PUBLICATIONS

Search Report issued on Oct. 28, 2015 in corresponding Taiwanese Patent Application No. 101128015.

(Continued)


*Primary Examiner* — Gregory Clark

(74) *Attorney, Agent, or Firm* — Duane Morris LLP

(57) **ABSTRACT**

An improved OLED includes an emitter layer disposed between a cathode and an anode where the emitter layer includes a host material and a phosphorescent emitter material. A first hole transport layer is disposed between the emitter layer and the anode and a second hole transport layer is disposed between the first hole transport layer and the anode. The first hole transport layer includes a first hole transport material that is a carbazole type compound and the second hole transport layer includes a second hole transport material that is different from the first hole transport material. The phosphorescent emitter material includes a phosphorescent organometallic compound that is a heteroleptic compound represented by the formula  $L_2MX$ ,  $LL'MX$ ,  $LL'L''M$ , or  $LMXX'$ , wherein  $L$ ,  $L'$ ,  $L''$ ,  $X$ , and  $X'$  are inequivalent, bidentate ligands and  $M$  is a metal that forms octahedral complexes, wherein  $L$ ,  $L'$ , and  $L''$  are monoan-

(Continued)



ionic inequivalent bidentate ligands coordinated to M through an  $sp^2$  hybridized carbon and a heteroatom.

2010/0237334 A1\* 9/2010 Ma ..... C07D 307/91  
257/40  
2012/0205642 A1\* 8/2012 Yokoyama ..... C07D 209/86  
257/40

**19 Claims, 2 Drawing Sheets**

(51) **Int. Cl.**  
*C09K 11/06* (2006.01)  
*H05B 33/14* (2006.01)

(52) **U.S. Cl.**  
CPC ..... *H01L 51/0059* (2013.01); *H01L 51/0074* (2013.01); *H01L 51/5016* (2013.01); *H01L 51/5064* (2013.01); *H05B 33/14* (2013.01); *C09K 2211/185* (2013.01)

**(56) References Cited**

## U.S. PATENT DOCUMENTS

2007/0231596 A1 10/2007 Spindler et al.

## FOREIGN PATENT DOCUMENTS

JP	8003547	1/1996
KR	20090028943	3/2009
WO	2009/021126	2/2009
WO	2010/027583	3/2010
WO	2010/028151	3/2010
WO	2011/048821	4/2011
WO	2011/048822	4/2011

## OTHER PUBLICATIONS

Yamamoto, H. et al., "High Efficiency and Long-Lived Green Phosphorescent OLEDs," the 16th International Display Workshops, Miyazaki, Japan, Papers OLED1-3, 435 (2009).

\* cited by examiner




FIG. 1




FIG. 2

**PHOSPHORESCENT ORGANIC LIGHT  
EMITTING DEVICES COMBINED WITH  
HOLE TRANSPORT MATERIAL HAVING  
HIGH OPERATING STABILITY**

**FIELD OF THE INVENTION**

The present invention relates to an organic electroluminescent (EL) device such as an organic light emitting device (hereinafter abbreviated as an OLED) and materials capable of being used in such an OLED. In particular, it relates to an OLED which comprises a light emitting layer which emits a green light, and materials for such an OLED.

**BACKGROUND OF THE INVENTION**

OLEDs which comprise an organic thin film layer which includes a light emitting layer located between an anode and a cathode are known in the art. In such devices, emission of light may be obtained from exciton energy, produced by recombination of a hole injected into a light emitting layer with an electron.

OLEDs make use of thin organic films that emit light when voltage is applied across the device. Generally, OLEDs are comprised of several organic layers in which at least one of the layers can be made to electroluminesce by applying a voltage across the device. When a voltage is applied across a device, the cathode effectively reduces the adjacent organic layers (i.e., injects electrons), and the anode effectively oxidizes the adjacent organic layers (i.e., injects holes). Holes and electrons migrate across the device toward their respective oppositely charged electrodes. When a hole and electron meet on the same molecule, recombination is said to occur, and an exciton is formed. Recombination of the hole and electron in luminescent compounds is accompanied by radiative emission, thereby producing electroluminescence.

Depending on the spin states of the hole and electron, the exciton resulting from hole and electron recombination can have either a triplet or singlet spin state. Luminescence from a singlet exciton results in fluorescence, whereas luminescence from a triplet exciton results in phosphorescence. Statistically, for organic materials typically used in OLEDs, one quarter of the excitons are singlets, and the remaining three-quarters are triplets. Electro-phosphorescent OLEDs have been shown to have superior overall device efficiencies as compared with electro-fluorescent OLEDs.

Due to strong spin-orbit coupling that leads to singlet-triplet state mixing, heavy metal complexes often display efficient phosphorescent emission from such triplets at room

temperature. Accordingly, OLEDs comprising such complexes have been shown to have internal quantum efficiencies of more than 75% (Adachi, et al., *Appl. Phys. Lett.*, 2000, 77, 904). Certain organometallic iridium complexes have been reported as having intense phosphorescence (Lamansky, et al., *Inorganic Chemistry*, 2001, 40, 1704), and efficient OLEDs emitting in the green to red spectrum have been prepared with these complexes (Lamansky, et al., *J. Am. Chem. Soc.*, 2001, 123, 4304). OLEDs, as described above, generally provide excellent luminous efficiency, image quality, power consumption and the ability to be incorporated into thin design products such as flat screens, and therefore hold many advantages over prior technology, such as cathode ray devices.

Development of light emitting phosphorescent materials in which light emission is obtained from a triplet exciton resulting in enhanced internal quantum efficiency have lead to OLEDs having greater current efficiency. Such phosphorescent materials may be used as a dopant in a host material which comprises such a light emitting layer.

In a light emitting layer formed by doping with a light emitting material such as a phosphorescent material, excitons can efficiently be produced from a charge injected into a host material. Exciton energy of an exciton produced may be transferred to a dopant, and light emission may be obtained from the dopant at high efficiency. Excitons may be formed either on the host materials or directly on the dopant.

In order to achieve intermolecular energy transfer from a host material to a phosphorescent dopant with high device efficiencies, the excited triplet energy  $Eg(T)$  of the host material must be greater than the  $Eg(T)$  of the phosphorescent dopant. In order to carry out intermolecular energy transfer from a host material to a phosphorescent dopant, the  $Eg(T)$  of the host material has to be larger than the  $Eg(T)$  of the phosphorescent dopant.

PCT Publication No. WO2011/048821 published on Apr. 28, 2011 discloses certain prior art OLED devices, Example 6 and Example 7, in which  $Ir(ppy)_3$  is provided as the electroluminescent dopant and a carbazole type compound is provided as an electron blocking layer between the electro luminescent layer and a hole injection layer. WO2011/048821 also discloses additional prior art OLED devices, Comparative Example 1 and Comparative Example 2, in which the electron blocking layer is omitted for comparison purposes. Table 1 provides the device performance data for the prior art devices Example 6, Example 7, Comparative Example 1 and Comparative Example 2.

TABLE 1

Device #	At 10 mA/cm <sup>2</sup>							
	1931 CIE		Voltage (V)	Luminance (cd/m <sup>2</sup> )	Efficiency (lm/W)	Power		
	x	y				(V)	LE (cd/A)	EQE (%)
Example 6 from WO2011/048821	0.309	0.615	5.77	2604	14.21	4.87	29.26	8.40
Example 7 from WO2011/048821	0.306	0.620	5.68	2943	16.30	4.70	33.60	9.60
Comparative Example 1 from WO2011/048821	0.316	0.612	6.54	1931	9.29	5.89	20.74	5.94

TABLE 1-continued

Device #	At 10 mA/cm <sup>2</sup>							
	1931 CIE		Voltage (V)	Luminance (cd/m <sup>2</sup> )	Efficiency (lm/W)	At 1000 nits		
	x	y				Voltage (V)	LE (cd/A)	EQE (%)
Comparative Example 2 from WO2011/048821	0.312	0.613	5.89	1896	10.23	5.28	20.23	5.76

Despite the recent discoveries of efficient heavy metal phosphors and the resulting advancements in OLED technology, there remains a need for longer device stability. Fabrication of devices that have longer lifetimes will contribute to the development of new OLED based display technologies and help realize the current goals toward full color electronic display on flat surfaces. An improved OLED device that exhibit improved lifetime is disclosed herein along with the host materials, phosphorescent emitter materials and hole transport materials that may be used to construct such OLED.

As used herein, the term “organic” includes polymeric materials as well as small molecule organic materials that may be used to fabricate organic opto-electronic devices. As used herein, “small molecule” refers to any organic material that is not a polymer, i.e., organic material having molecules with a defined molecular weight, and “small molecules” may actually be quite large. Small molecules may include repeat units in some circumstances, e.g. oligomers. For example, using a long chain alkyl group as a substituent does not remove a molecule from the “small molecule” class. Small molecules may also be incorporated into polymers, for example as a pendent group on a polymer backbone or as a part of the backbone. Small molecules may also serve as the core moiety of a dendrimer, which consists of a series of chemical shells built on the core moiety. The core moiety of a dendrimer may be a fluorescent or phosphorescent small molecule emitter. A dendrimer may be a “small molecule,” and it is believed that all dendrimers currently used in the field of OLEDs are small molecules.

As used herein, “top” means furthest away from the substrate, while “bottom” means closest to the substrate. Where a first layer is described as “disposed over” a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is “in contact with” the second layer. For example, a cathode may be described as “disposed over” an anode, even though there are various organic layers in between.

As used herein, “solution processible” means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

A ligand may be referred to as “photoactive” when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as “ancillary” when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter the properties of a photoactive ligand.


As used herein, and as would be generally understood by one skilled in the art, a first “Highest Occupied Molecular Orbital” (HOMO) or “Lowest Unoccupied Molecular Orbital” (LUMO) energy level is “greater than” or “higher

than” a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the LUMO energy level of a material is higher than the HOMO energy level of the same material. A “higher” HOMO or LUMO energy level appears closer to the top of such a diagram than a “lower” HOMO or LUMO energy level.

As used herein, and as would be generally understood by one skilled in the art, a first work function is “greater than” or “higher than” a second work function if the first work function has a higher absolute value. Because work functions are generally measured as negative numbers relative to vacuum level, this means that a “higher” work function is more negative. On a conventional energy level diagram, with the vacuum level at the top, a “higher” work function is illustrated as further away from the vacuum level in the downward direction. Thus, the definitions of HOMO and LUMO energy levels follow a different convention than work functions.

## SUMMARY OF THE INVENTION

According to an embodiment of the present disclosure, an OLED is disclosed. The device comprises an anode, a cathode and a plurality of organic layers sandwiched between them. The plurality of organic layers comprising an emitter layer that can include a host material and a phosphorescent emitter material. The phosphorescent emitter material comprising a phosphorescent organometallic compound that emits phosphorescent radiation from a triplet molecular excited state when a voltage is applied across the emitter layer. The plurality of organic layers further comprises a first hole transport layer disposed between the emitter layer and the anode and a second hole transport layer disposed between the first hole transport layer and the anode. The first hole transport layer comprising a first hole transport material of represented by the following general formula (HTL1)



wherein  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_5$ , and  $R_6$  may be the same or different fluoric atom, chlorine atom, a deuterium atom, a cyano group, a trifluoromethyl group, a nitro group, linear or branched alkyl group (C1-C6), cyclo-alkyl group (C5-C10), linear or branched alkoxy group (C1-C6), cyclo-alkoxy group (C5-C10), substituted or unsubstituted aromatic hydrocarbon group, substituted or unsubstituted aromatic heterocyclic group, substituted or unsubstituted condensed polycyclic aromatic group,

$r_1$ ,  $r_4$ ,  $r_5$ =0, 1, 2, 3, or 4,  
 $r_2$ ,  $r_3$ ,  $r_6$ =0, 1, 2 or 3,  
 $n$ =0 or 1, and

$Ar_1$ ,  $Ar_2$ , and  $Ar_3$  may be the same or different, substituted or unsubstituted aromatic hydrocarbon group, substituted or unsubstituted aromatic heterocyclic group, substituted or unsubstituted condensed polycyclic aromatic group, deuterium substituted aromatic hydrocarbon group, deuterium substituted aromatic heterocyclic group, or deuterium substituted condensed polycyclic aromatic group. The second hole transport layer comprising a second hole transport material that is different from the first hole transport material. The phosphorescent organometallic compound is a heteroleptic compound represented by the formula  $L_2MX$ ,  $LL'MX$ ,  $LL'L'M$ , or  $LMXX'$ , wherein  $L$ ,  $L'$ ,  $L''$ ,  $X$ , and  $X'$  are inequivalent, bidentate ligands and  $M$  is a metal that forms octahedral complexes, wherein  $L$ ,  $L'$ , and  $L''$  are monoanionic inequivalent bidentate ligands coordinated to  $M$  through an  $sp^2$  hybridized carbon and a heteroatom.

The inventors have discovered that the OLED incorporating the teachings of the present disclosure exhibits an unexpectedly substantial improved working lifetime characteristics and improved luminous efficiency.

#### BRIEF DESCRIPTION OF THE DRAWING

FIG. 1 is a schematic drawing showing an outline constitution of one example of the OLED according to one embodiment of the present invention. The drawing is not drawn to scale.

FIG. 2 shows an inverted OLED according to another embodiment of the present disclosure.

#### DETAILED DESCRIPTION


The present disclosure describes an OLED in which a combination of a phosphorescent emitter dopant material, its associated host material, and two hole transport layers each comprising a different hole transport material are utilized to extend the lifetime of the OLED and increase luminous efficiency. Operational stability is a tremendous advantage in OLED displays and lighting applications.

Referring to FIG. 1, an OLED 100 according to an embodiment of the present disclosure is disclosed. The OLED 100 can include a substrate 2, an anode 3, a cathode 11 and a plurality of organic layers 12 sandwiched between them. The plurality of organic layers comprise an emitter layer 7 that can include a host material and a phosphorescent emitter dopant material. In one preferred embodiment, the phosphorescent emitter material comprises a phosphorescent organometallic compound that emits phosphorescent radiation from a triplet molecular excited state when a voltage is applied across the emitter layer 7 via the two electrodes, the anode and the cathode. The device can further comprise a first hole transport layer 6, a second hole transport layer 5, and a hole injection layer 4 disposed between the emitter layer 7 and the anode 3 in an arrangement as shown. The device can further comprise a hole blocking layer 8, electron transport layer 9, and an electron injection layer 10 disposed between the emitter layer 7 and the cathode 11. In another embodiment, an electron blocking layer (not shown) can be provided between the emitter layer 7 and the first hole transport layer 6. The hole blocking layer 8 and the electron blocking layer make it possible to contain electrons and holes in the phosphorescence emitter layer 7 to enhance the production rate of excitons in the phosphorescence emitter layer. The structure illustrated is an example only and the OLED according to the disclosed invention is not limited to the particular structure and can include more layers or fewer layers or different combinations of the layers.

According to one preferred embodiment of the present disclosure the plurality of organic layers 12 comprises the emitter layer 7 that includes a host material and a phosphorescent emitter material. The phosphorescent emitter material comprising a phosphorescent organometallic compound that emits phosphorescent radiation from a triplet molecular excited state when a voltage is applied across the emitter layer. The plurality of organic layers 12 further comprises the first hole transport layer 6 disposed between the emitter layer 7 and the anode 3 and the second hole transport layer 5 disposed between the first hole transport layer 6 and the anode 3.

#### First Hole Transport Material:

The first hole transport layer 6 comprises a first hole transport material of a carbazole type compound represented by the following general formula (HTL1):



wherein  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_5$ , and  $R_6$  may be the same or different fluoric atom, chlorine atom, a deuterium atom, a cyano group, a trifluoromethyl group, a nitro group, linear or branched alkyl group (C1-C6), cyclo-alkyl group (C5-C10), linear or branched alkoxy group (C1-C6), cyclo-alkoxy group (C5-C10), substituted or unsubstituted aromatic

hydrocarbon group, substituted or unsubstituted aromatic heterocyclic group, substituted or unsubstituted condensed polycyclic aromatic group,


$r_1, r_4, r_5 = 0, 1, 2, 3, \text{ or } 4$ ,  
 $r_2, r_3, r_6 = 0, 1, 2 \text{ or } 3$ ,  
 $n = 0 \text{ or } 1$ , and

$\text{Ar}_1, \text{Ar}_2, \text{ and } \text{Ar}_3$  may be the same or different, substituted or unsubstituted aromatic hydrocarbon group, substituted or unsubstituted aromatic heterocyclic group, substituted or


unsubstituted condensed polycyclic aromatic group, deuterium substituted aromatic hydrocarbon group, deuterium substituted aromatic heterocyclic group, or deuterium substituted condensed polycyclic aromatic group. The second hole transport layer **5** comprises a second hole transport material that is different from the first hole transport material.

Examples of compounds having the structure of formula (HTL1) include:


Compound HTL1-1




Compound HTL1-2




Compound HTL1-3



Compound HTL1-4




Compound HTL1-5




-continued


Compound HTL-6



Compound HTL-7




Compound HTL-8




-continued


Compound HTL1-9



Compound HTL1-10




Compound HTL1-11




-continued

Compound HTL1-12



Compound HTL1-13



Synthesis Example 1: Synthesis of 3,6-Bis(9'-phenyl-9H-carbazol-3-yl)-9-phenyl-9H-carbazole  
(Compound HTL1-1)

In a nitrogen atmosphere, 1.6 g of 3,6-Dibromo-9-phenyl-9H-carbazole, 2.4 g of 9-Phenyl-3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-9H-carbazole, 0.23 g of tetrakis(triphenylphosphine) palladium, 6 ml of an aqueous 2 M potassium carbonate solution, 20 ml of toluene and 5 ml of ethanol were added to a reaction vessel, then heated, and stirred under refluxing for 5 hours. After cooling to 40° C., the insoluble materials were removed by filtration, and the filtrate was concentrated under reduced pressure to obtain a crude product. The crude product was purified by recrystallization (solvent: toluene/methanol) to obtain 1.76 g (yield: 60.9%) of 3,6-Bis(9'-phenyl-9H-carbazol-3-yl)-9-phenyl-9H-carbazole (Compound HTL1-1) as a brownish white powder.

The structure of the obtained brownish white powder was identified using NMR. The following 35 hydrogen signals were detected on <sup>1</sup>H-NMR (CDCl<sub>3</sub>). δ (ppm)=8.56 (2H), 8.49 (2H), 8.24-8.26 (2H), 7.79-7.81 (4H), 7.62-7.67 (12H), 7.43-7.55 (11H), 7.30-7.33 (2H).

Synthesis Example 2: Synthesis of 9'-Phenyl-9-[4-(9-phenyl-9H-carbazol-3-yl)-phenyl]-9H,9'H-[3,3']bicarbazolyl (Compound HTL1-5)

In a nitrogen atmosphere, 12.9 g of 9-Phenyl-9H,9'H-[3,3']bicarbazolyl, 13.4 g of 4-Bromoiodobenzene, 0.64 g of copper powder, 8.34 g of potassium carbonate, 0.49 g of sodium hydrogenesulfite and 50 ml of o-dichlorobenzene were added to a reaction vessel, then heated and stirred at 170° C. for 19.5 hours. After cooling to 90° C., 200 ml of toluene were added thereto and insoluble materials were removed by filtration. The filtrate was concentrated under


15

reduced pressure to obtain a crude product, and the crude product was purified by recrystallization with methanol to obtain 17.3 g (yield: 97%) of 9-(4-Bromophenyl-9H,9H-[3,3]bicarbazolyl as a white powder.

In a nitrogen atmosphere, 17.0 g of 9-(4-Bromophenyl-9H,9H-[3,3]bicarbazolyl, 12.3 g of 9-Phenyl-3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-9H-carbazole, 1.74 g of tetrakis(triphenylphosphine) palladium, 23 ml of an aqueous 2 M potassium carbonate solution, 160 ml of toluene and 40 ml of ethanol were added to a reaction vessel, then heated, and stirred under refluxing for 13 hours. After cooling to room temperature, 100 ml of toluene and 150 ml of water were added thereto, followed by stirring, and the

16

wherein  $R_{11}$  and  $R_{12}$  may be the same or different and are independently selected from the group consisting of a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, a phenyl group, a phenyl group having a lower alkyl group or deuterium substituent, and a phenyl group having a deuterium atom or a lower alkoxy group substituent with the proviso at least one of  $R_{11}$  and  $R_{12}$  is a deuterium atom, a normal butyl group, an isobutyl group, a secondary butyl group, a tertiary butyl group, a phenyl group, a phenyl group having a lower alkyl group substituent, or a phenyl group having a lower alkoxy group substituent; and  $R_{13}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom;



organic layer was separated by liquid separation. The organic layer was dried over magnesium sulfate, and then concentrated under reduced pressure to obtain a crude product. The crude product was purified by column chromatography (carrier: silica gel, eluent: n-hexane/toluene) to obtain 10.4 g (yield: 48%) of 9'-Phenyl-9-[4-(9-phenyl-9H-carbazol-3-yl)-phenyl]-9H,9H-[3,3]bicarbazolyl (Compound HTL1-5) as a slightly yellow powder.


The structure of the obtained slightly yellow powder was identified using NMR. The following 35 hydrogen signals were detected on  $^1\text{H-NMR}$  (THF- $d_8$ ).  $\delta$  (ppm)=8.56-8.61 (3H), 8.26-8.30 (3H), 8.04-8.08 (2H), 7.81-7.85 (3H), 7.73-7.76 (2H), 7.64-7.69 (8H), 7.58 (1H), 7.48-7.53 (5H), 7.36-7.44 (5H), 7.25-7.31 (3H).

#### Second Hole Transport Material:


In another embodiment of the present disclosure, the second hole transport material can comprise at least one of the compounds having a formula selected from (HTL2-I) to (HTL2-VI) listed below:

wherein  $R_{21}$ ,  $R_{22}$  and  $R_{23}$  may be the same or different and each represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group, or a phenyl group having a lower alkyl group or a lower alkoxy group as a substituent(s);  $R_{24}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and  $A_1$  represents a group represented by any one of the following structural formulae (a1) to (i1);


(a1)




(b1)




(c1)



(d1)




(HTL2-I) 55




**17**

-continued


**18**

-continued




20 in which  $R_{25}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom;

(HTL2-III)





45 wherein  $R_{31}$ ,  $R_{32}$  and  $R_{33}$  may be the same or different and each represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group, or a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group as a substituent(s);  $R_{34}$   
50 represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and  $A_2$  represents a group represented by any one of the following formulae (j1) to (n1);




(j1)

(k1)




(l1)

(m1)




-continued

(n1)




(HTL2-IV)




wherein R<sub>41</sub> and R<sub>42</sub> may be the same or different and each represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group or a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group as a substituent(s); R<sub>43</sub> represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and A<sub>3</sub> represents a group represented by anyone of the following structural formulae (a2) to (i2);

-continued


(e2)




(a2) 45




(b2) 50



(c2) 55




(d2) 60




65

(f2)




(g2)




**21**

-continued

**22**

-continued

(h2)




(i2)

5


in which  $R_{44}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom;

(HTL2-V)




wherein  $R_{51}$  and  $R_{52}$  may be the same or different and each represent a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group or a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group as a substituent(s);  $R_{53}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and  $A_4$  represents a group represented by anyone of the following structural formulae (j2) to (n2);


(j2)




(k2)




(l2)



(m2)




(n2)



-continued

(HTL2-VI)




where  $R_{61}$  to  $R_{69}$ , which may be the same or different, represent a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted aromatic hydrocarbon group, a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group;  $r_{61}$  to  $r_{69}$ , which may be the same or different, represent 0, 1 or 2.

The terms "lower alkyl group" and "lower alkoxy group" as used herein mean " $C_{1-4}$  alkyl group" and " $C_{1-4}$  alkoxy group," respectively.

The synthesis information for the compounds of the formulae (HTL2-I) to (HTL2-V) and the specific examples of the compounds of formulae (HTL2-I) to (HTL2-V) are provided in U.S. Pat. No. 5,707,747 to Tomiyama et al., the contents of which are incorporated herein by reference.


Examples of compounds having the structure of formula (HTL2-VI) include:




**25**

-continued


Compound-3a

**26**


Compound-4a




Compound-5a



Compound-6a




Compound-7a




**27****28**

-continued


Compound-8a



Compound-9a




Compound-10a




-continued

Compound-11a



Compound-12a



Synthesis Example 1: Synthesis of N,N,N',N'-Tetra-  
kis (biphenyl-4-yl)-4,4'-diaminobiphenyl (Com-  
pound 1a)

A mixture of bis(biphenyl-4-yl)amine 10.0 g (31.1 mmol), 4,4'-Diodobiphenyl 5.28 g (30.0 mmol), anhydrous potassium carbonate 5.39 g (39.0 mmol), copper powder 0.083 g (1.3 mmol), dodecylbenzene 12 ml and xylene 24 ml was stirred and heated. After xylene was evaporated the mixture was reacted at 210-215° C. for 4 hours. Furthermore copper powder 0.083 g (1.3 mmol) was added to the mixture, additional reaction was proceeded for 4.5 hours. After cooling to 90° C., toluene was added to the reaction mixture, and the reaction mixture was cooled to room temperature. The reaction mixture was filtered and washed with water, methanol and toluene. The residue was extracted with hot toluene and toluene solution was concentrated to dry-up in vacuo. The crude product obtained was purified by recrystallization. 7.38 g (yield: 71.7%) of N,N,N',N'-Tetrakis (biphenyl-4-yl)-4,4'-diaminobiphenyl (Compound 1a) was obtained. The melting point was 265° C.

Synthesis Example 2: Synthesis of 4',4"-bis[bis(4-  
biphenyl)amino]-9,9-diphenylfluorene (Compound  
5a)

A mixture of bis(biphenyl-4-yl)amine 20.30 g (63.16 mmol), 9,9-bis(4-iodophenyl)fluorene 15.0 g (26.31 mmol), anhydrous potassium carbonate 10.91 g (78.92 mmol), copper powder 0.17 g (2.63 mmol) and dodecylbenzene 30 ml was stirred and heated at 200° C. for 13 hours under nitrogen gas. The reacting mixture was analyzed by HPLC, it was

<sup>35</sup> confirmed that the monoiodo-compound of intermediates was 1% or less, and assumed a reactive end. Toluene 100 ml was added to the reaction mixture and filtered. A residue was washed with methanol and water. The residue was added in chlorobenzene 2000 ml and heated to 120° C. After cooling to 60° C. the mixture was filtered and the filtrate was concentrated to dry up. The crude product obtained was purified by recrystallization by chlorobenzene for 3 times. The purified product, 4',4"-bis[bis(4-biphenyl)amino]-9,9-diphenylfluorene (Compound 5a) was 17.9 g of gray-white powder. Yield was 71% and melting point was 324-326° C.

Synthesis Example 3: Synthesis of N,N'-Bis[4'-  
(diphenylamino) biphenyl-4-yl]-N,N'-diphenyl-4,4'-  
diaminobiphenyl (Compound 8a)

<sup>50</sup> Acetanilide 20.3 g (0.15 mol), 4,4'-diodobiphenyl 73.1 g (0.18 mol), anhydrous potassium carbonate 22.1 g (0.16 mol), copper powder 2.16 g (0.034 mol) and nitrobenzene 35 ml were mixed. The reaction mixture was stirred for 10 hours at 190-205° C. The reaction mixture was extracted with toluene 200 ml. The insoluble matters were removed by filtration. The filtrate was concentrated to dry-up. The crude product obtained was purified by column chromatography (carrier was silica gel and eluent was 6/1 mixture of toluene and ethyl acetate). 40.2 g (yield: 64.8%) of N-(4'-ido-4-biphenyl)acetanilide was obtained. A melting point of the product was 135.0-136.0° C.

<sup>55</sup> Subsequently, N-(4'-ido-4-biphenyl)acetanilide 13.2 g (0.032 mol), diphenylamine 6.60 g (0.039 mol), anhydrous potassium carbonate 5.53 g (0.040 mol), copper powder 0.45 g (0.007 mol) and nitrobenzene 10 ml were mixed. The

reaction mixture was stirred for 15 hours at 200-212° C. The reaction mixture was extracted with toluene 100 ml. The insoluble matters were removed by filtration. The filtrate was concentrated to dry-up. An oily matter was obtained. The oily matter was dissolved in isoamyl alcohol 60 ml. The material was hydrolyzed with water 1 ml and 85% potassium hydroxide 2.64 g (0.040 mol) at 130° C. The reaction solution was then distilled by steam distillation to remove isoamyl alcohol. The residue was extracted with toluene 250 ml, toluene solution was washed with water and concentrated to dry-up. The crude product obtained was purified by column chromatography (carrier was silica gel and eluent was 1/2 mixture of toluene and n-hexane). 10.5 g (yield: 72.2%) of N,N,N'-triphenyl-4,4'-diaminobiphenyl was obtained. The compound melted at 167.5-168.5° C.

N,N,N'-Triphenyl-4,4'-diaminobiphenyl 8.66 g (0.021 mol), 4,4'-diiodobiphenyl 4.06 g (0.01 mol), anhydrous potassium carbonate 2.90 g (0.021 mol), copper powder 0.32 g (0.005 mol) and nitrobenzene 10 ml were mixed. The reaction mixture was stirred at 195-210° C. for 20 hours. The reaction mixture was extracted with toluene 140 ml. The insoluble matters were removed by filtration. The filtrate was concentrated and a crude product was obtained. n-Hexane 120 ml was added to the crude product to recover a crude crystal. The crude crystal was purified by column chromatography (carrier was silica gel and eluent was 1/2 mixture of toluene and n-hexane). 4.73 g (yield: 48.5%) of N,N'-Bis[4'-(diphenylamino) biphenyl-4-yl]-N,N'-diphenyl-4,4'-diaminobiphenyl (Compound 8a) was obtained. The melting point of the product was 242.5-243.5° C.

The result of elementary analysis on the product was as follows:

The theoretical value: (carbon 88.67%) (hydrogen 5.58%) (nitrogen 5.75%)

Actual measurement value: (carbon 88.75%) (hydrogen 5.70%) (nitrogen 5.68%)

**Synthesis Example 4: Synthesis of 4',4"-Bis[N-(4'-diphenylaminobiphenyl-4-yl)-N-phenyl-amino]-9,9-diphenylfluorene (Compound 12a)**

4',4"-Bis[(4'-phenylaminobiphenyl-4-yl)amino]-9,9-diphenylfluorene 8.4 g (10 mmol), iodobenzene 10.2 g (50 mmol), anhydrous potassium carbonate 8.3 g (60 mmol), copper powder 0.64 g (10 mmol), tridecane 100 ml were mixed and reacted for 10 hours at reflux temperature under nitrogen gas. The reaction mixture was extracted with toluene 120 ml and insoluble matters were removed with filtration. The filtrate was concentrated to dry up and crude product was obtained. The crude product was purified by column chromatography with silica gel. The purified product, 4',4"-Bis[N-(4'-diphenylaminobiphenyl-4-yl)-N-phenyl-amino]-9,9-diphenylfluorene (Compound 12a) was 5.4 g of white powder. Yield was 47% and melting point was 186-220° C.

The chemical structure of the obtained white powder was identified with 13C-NMR. In 13C-NMR, 24 peaks among 26 peaks that correspond to aromatic 84 carbon atoms were 120.03, 122.71, 123.20, 123.97, 124.13, 124.21, 124.41, 125.20, 126.14, 127.16, 127.29, 127.51, 128.12, 128.83, 128.92, 129.13, 134.62, 139.77, 139.94, 145.91, 146.45, 146.58, 147.58, 151.40 ppm and a peak of aliphatic carbon atom in fluorene 9-position was 64.56 ppm.

In addition, the result of elementary analysis on the obtained white powder was as follows:

The theoretical value: (carbon 89.6%) (hydrogen 5.5%) (nitrogen 4.9%)

Actual measurement value: (carbon 89.5%) (hydrogen 5.6%) (nitrogen 4.4%)

The chemical structure of compound-12b was identified from the results of 13C-NMR and the elementary analysis. 5 Emitter Dopant:

Some examples of the phosphorescent organometallic compound of the phosphorescent emitter material are heteroleptic compounds represented by the formula L<sub>2</sub>MX, LL'MX, LL'L"MX, or LMXX', wherein L, L', L", X, and X' are inequivalent, bidentate ligands and M is a metal that forms octahedral complexes, wherein L, L', and L" are monoanionic inequivalent bidentate ligands coordinated to M through an sp<sup>2</sup> hybridized carbon and a heteroatom.

The phosphorescent organometallic compound can also 15 be a compound selected from the group consisting of phosphorescent organometallic platinum compounds, organometallic iridium compounds and organometallic osmium compounds. The phosphorescent organometallic compound can include a carbon-metal bond. The organometallic platinum compounds, iridium compounds and osmium compounds can each include an aromatic ligand.

The phosphorescent organometallic compounds can comprise heteroleptic complexes with extended conjugation on the heterocyclic ring. Examples of such heteroleptic iridium 20 compounds are described in PCT publication No. WO 2010/028151, published on Mar. 11, 2010, the disclosure of which is incorporated herein by reference in its entirety.

In another embodiment of the present disclosure the OLED comprises at least one phosphorescent material in the 25 light emitting layer, wherein the phosphorescent material has a maximum value of 500 nm or more and 720 nm or less in a light emitting wavelength.

**Emitter Host:**

The host material for the emitter layer can be a compound 30 comprising a triphenylene containing benzo-fused thiophene. Triphenylene is a polycyclic hydrocarbon with high triplet energy, yet high [pi]-conjugation and a relatively small energy difference between the first singlet and first triplet levels. This would indicate that triphenylene has 35 relatively easily accessible HOMO and LUMO levels compared to other aromatic compounds with similar triplet energy (e.g., biphenyl). The advantage of using triphenylene and its derivatives as hosts is that it can accommodate red, green and even blue phosphorescent dopants to give high efficiency without energy quenching. Triphenylene hosts may be used to provide high efficiency and stability phosphorescent OLEDs (PHOLEDs). See Kwong and Alleyene, Triphenylene Hosts in Phosphorescent Light Emitting Diodes, 2006, 60 pp, US 2006/0280965 A1. Benzo-fused thiophenes may be used as hole transporting organic conductors. In addition, the triplet energies of benzothiophenes, namely dibenzo[b,d]thiophene (referred to herein as "dibenzo-thiophene"), benzo[b]thiophene and benzo[c]thiophene are relatively high. A combination of benzo-fused thiophenes and triphenylene as hosts in PHOLEDs may be 50 beneficial. More specifically, benzo-fused thiophenes are typically more hole transporting than electron transporting, and triphenylene is more electron transporting than hole transporting. Therefore combining these two moieties in one molecule may offer improved charge balance which may improve device performance in terms of lifetime, efficiency and low voltage. Different chemical linkage of the two moieties can be used to tune the properties of the resulting 55 compound to make it the most appropriate for a particular phosphorescent emitter, device architecture, and/or fabrication process. For example, m-phenylene linkage is expected to result in higher triplet energy and higher solubility

60 65

whereas p-phenylene linkage is expected to result in lower triplet energy and lower solubility.

Similar to the characterization of benzo-fused thiophenes, benzo-fused furans are also typically hole transporting materials having relatively high triplet energy. Examples of benzo-fused furans include benzofuran and dibenzofuran. Therefore, a material containing both triphenylene and benzofuran may be advantageously used as host or hole blocking material in PHOLED. A compound containing both of these two groups may offer improved electron stabilization which may improve device stability and efficiency with low voltage. The properties of the triphenylene containing benzofuran compounds may be tuned as necessary by using different chemical linkages to link the triphenylene and the benzofuran.

The compounds may be substituted with groups that are not necessarily triphenylenes, benzo-fused thiophenes, and benzo-fused furans. Preferably, any group that is used as a substituent of the compound has a triplet energy high enough to maintain the benefit of having triphenylene benzo-fused thiophenes or benzo-fused furans (i.e. the triplet energy of the substituent maintains the high triplet energy of benzo-fused thiophenes, benzo-fused furans and triphenylenes). Examples of such groups that may be used as substituents of the compound may include any unfused substituent independently selected from the group consisting of  $C_nH_{2n+1}$ ,  $OC_nH_{2n+1}$ ,  $OAr_1$ ,  $N(C_nH_{2n+1})_2$ ,  $N(Ar_1)(Ar_2)$ ,  $CH=CH-C_nH_{2n+1}$ ,  $C=CCHC_nH_{2n+1}$ ,  $Ar_1$ ,  $Ar_1-Ar_2$ ,  $C_nH_{2n}-Ar_1$ , or no substitution, wherein  $n$  is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10, and wherein  $Ar_1$  and  $Ar_2$  are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof. The compounds for the host material described herein have a high enough triplet energy to be suitable for use in a device having phosphorescent blue emissive materials.

The substituents of the compounds described herein are unfused such that the substituents are not fused to the triphenylene, benzo-fused furan or benzo-fused thiophene moieties of the compound. The substituents may optionally be inter-fused (i.e. fused to each other).


In addition to improved device stability and efficiency, the materials provided herein may also offer improved film formation in the device as fabricated by both vapor deposition and solution processing methods. In particular, materials offering improved fabrication have a central pyridine ring to which the benzo-fused thiophenylene and triphenylene, or benzofuran and triphenylene, are attached. The improved film formation is believed to be a result of the combination of polar and non-polar rings in the compound.

Examples of triphenylene-containing benzo-fused thiophenes include compounds having the structure of the following formulae (H-I), (H-II), and (H-III):

5  
10  
15  
20  
25  
30  
35

-continued


(H-III)



$R_1$ ,  $R_2$  and  $R_3$  are independently selected from alkyl, alkoxy, amino, alkenyl, alkynyl, aryalkyl, aryl, heteroaryl and hydrogen. Each of  $R_1$ ,  $R_2$  and  $R_3$  may represent multiple substituents. At least one of  $R_1$ ,  $R_2$  and  $R_3$  includes a triphenylene group. The triphenylene group may be linked directly to the structure of formulae (H-I), (H-II) or (H-III), but there may also be a "spacer" in between the triphenylene group and the structure of formulae (H-I), (H-II) or (H-III).


15 Examples of triphenylene-containing benzo-fused thiophenes or benzo-fused furans include compounds having the structure of the following formulae (H-IV), (H-V), and (H-VI):

20




(H-IV)

25




(H-V)

30



(H-VI)

35



40

45

$X$  is S or O. Preferably,  $R_1$ ,  $R_2$  and  $R_3$  are unfused substituents that are independently selected from  $C_nH_{2n+1}$ ,  $OC_nH_{2n+1}$ ,  $OAr_1$ ,  $N(C_nH_{2n+1})_2$ ,  $N(Ar_1)(Ar_2)$ ,  $CH=CH-C_nH_{2n+1}$ ,  $C=CCHC_nH_{2n+1}$ ,  $Ar_1$ ,  $Ar_1-Ar_2$ ,  $C_nH_{2n}-Ar_1$ , or no substitution. Each of  $R_1$ ,  $R_2$  and  $R_3$  may represent mono, di, tri, or tetra substitutions,  $n$  is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10.  $Ar_1$  and  $Ar_2$  are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof. At least one of  $R_1$ ,  $R_2$  and  $R_3$  includes a triphenylene group.

45 Examples of compounds having the structure of the formula (H-I) include:

50



Compound 11'G

(H-I) 55

60


(H-II)

65




35

-continued







36

Compound 12'G




$R_1$  to  $R_n$  represents, independently, mono, di, tri or tetra substitutions selected from alkyl, alkoxy, amino, alkenyl, alkynyl, aryalkyl, aryl and heteroaryl, or no substitution.

Examples of compounds having the structure of the formula (H-IV) include:




where  $X$  is S or O. Preferably,  $X$  is S.  $R_1$  to  $R_n$  are independently selected from the group consisting of  $C_nH_{2n+1}$ ,  $OC_nH_{2n+1}$ ,  $OAr_1$ ,  $N(C_nH_{2n+1})_2$ ,  $N(Ar_1)(Ar_2)$ ,  $CH=CH-C_nH_{2n+1}$ ,  $C=CHC_nH_{2n+1}$ ,  $Ar_1$ ,  $Ar_1-Ar_2$ ,  $C_nH_{2n}-A_{r1}$ , or no substitution. Each of  $R_1$  to  $R_n$  may represent mono, di, tri, or tetra substitutions,  $n$  is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10.  $Ar_1$  and  $Ar_2$  are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof. At least one of  $R_1$ ,  $R_2$ , and  $R_3$  includes a triphenylene group.

Examples of compounds having the structure of the formula (H-II) include:




37

-continued




5



20

25


30



35

40

45



50


55

60


38

-continued


Compound 17'G




10



15



20



30

35

40


50

55

60

where  $R_1$  to  $R_n$  represents, independently, mono, di, tri or tetra substitutions selected from alkyl, alkoxy, amino, alkynyl, alkynyl, aryalkyl, aryl and heteroaryl, or no substitution.

Examples of compounds having the structure of the formula (H-V) include:


**39**

Compound 12G

**40**

-continued

Compound 14G




5

10

15

Compound 12




20

25


30

Compound 14



Compound 13G

Compound 16C




35

40


45

50



Compound 13


Compound 16



55

60


65



41


-continued

Compound 17G




5

Compound 17 15




20

Compound 18G




30

Compound 18



40

Compound 18



45

50

55

where X is S or O. Preferably, X is S. R<sub>1</sub> to R<sub>n</sub> are independently selected from the group consisting of C<sub>n</sub>H<sub>2n+1</sub>, OC<sub>n</sub>H<sub>2n+1</sub>, OAr<sub>1</sub>, N(C<sub>n</sub>H<sub>2n+1</sub>)<sub>2</sub>, N(Ar<sub>1</sub>)(Ar<sub>2</sub>), CH=CH—C<sub>n</sub>H<sub>2n+1</sub>, C=CHC<sub>n</sub>H<sub>2n+1</sub>, Ar<sub>1</sub>, Ar<sub>1</sub>—Ar<sub>2</sub>, C<sub>n</sub>H<sub>2n</sub>—Ar<sub>1</sub>, or no substitution. Each of R<sub>1</sub> to R<sub>n</sub> may represent mono, di, tri, or tetra substitutions, n is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10. Ar<sub>1</sub> and Ar<sub>2</sub> are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof. At least one of R<sub>1</sub>, R<sub>2</sub>, and R<sub>3</sub> includes a triphenylene group.


60

65


Examples of compounds having the structure of the formula (H-III) include:

42


Compound 1'G




Compound 1'




Compound 2'G



Compound 2'




Compound 3'G



**43**


-continued



Compound 3'


**44**

-continued




Compound 5'

Compound 4'G




20




25

Compound 4'




40




45

Compound 6'



55




60

65

Compound 7'G

**45**

-continued




Compound 7'


**46**

-continued

Compound 10'G



Compound 8'G



5

10

15

20

25

30

35

40

45

50

55

60


65

Compound 8'


Compound 15'G

Compound 9'G

Compound 15'




Compound 9'




where  $R_1$  to  $R_n$  represents, independently, mono, di, tri or tetra substitutions selected from alkyl, alkoxy, amino, alkynyl, alkynyl, aryalkyl, aryl and heteroaryl, or no substitution.

Examples of compounds having the structure of the formula (H-VI) include:




Compound 1G      Compound 1




Compound 2G

Compound 2





Compound 3G

Compound 3





Compound 4G

Compound 4



Compound 5G


Compound 5




**49**

-continued

Compound 6G



**50**

Compound 6





Compound 7G

Compound 7





Compound 8G

Compound 8





Compound 9G

Compound 9



Compound 10G


Compound 10




**51**

-continued

Compound 15G



**52**

Compound 15





Compound 19 G

Compound 19





Compound 20 G

Compound 20



Compound 21 G


Compound 21




53

-continued

Compound 22 G





Compound 23 G





54

Compound 22





Compound 23

Compound 23



Compound 24 G

Compound 24



Compound 25 G


Compound 25

**55**


-continued

**56**


Compound 26 G




Compound 24 G




Compound 26




Compound 27 G



Compound 27




Compound 28 G




**57**

-continued

Compound 28



**58**

Compound 29 G





Compound 29


Compound 30 G



Compound 30


Compound 31 G



**59**


-continued

Compound 31


**60**

Compound 32 G


Compound 32




Compound 33 G




Compound 33



Compound 34 G




**61****62**

-continued



Compound 34

Compound 35 G





Compound 35


Compound 36 G



Compound 36


Compound 37 G






-continued

Compound 37




Compound 38 G


Compound 38




Compound 39




Compound 39 G



Compound 39




Compound 40 G


**65**

-continued

Compound 40


**66**

Compound 41 G





Compound 41

Compound 42 G





Compound 42

Compound 43 G




Compound 43

Compound 44 G




-continued

Compound 44





Compound 45 G





Compound 45




Compound 46 G



Compound 46

Compound 47 G





where X is S or O. Preferably, X is S. R<sub>1</sub> to R<sub>n</sub> are independently selected from the group consisting of C<sub>n</sub>H<sub>2n+1</sub>, OC<sub>n</sub>H<sub>2n+1</sub>, OAr<sub>1</sub>, N(C<sub>n</sub>H<sub>2n+1</sub>)<sub>2</sub>, N(Ar<sub>1</sub>)(Ar<sub>2</sub>), CH=CH—C<sub>n</sub>H<sub>2n+1</sub>, C=CHC<sub>n</sub>H<sub>2n+1</sub>, Ar<sub>1</sub>, Ar<sub>1</sub>—Ar<sub>2</sub>, C<sub>n</sub>H<sub>2n</sub>—A<sub>r1</sub>, or no substitution. Each of R<sub>1</sub> to R<sub>n</sub> may represent mono, di, tri, or tetra substitutions. n is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10. Ar<sub>1</sub> and Ar<sub>2</sub> are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof. At least one of R<sub>1</sub>, R<sub>2</sub>, and R<sub>3</sub> includes a triphenylene group.

The synthesis information for the host compounds described above can be found in PCT publication No. WO 2009/021126 published on 12 Feb. 2009 the contents of which are incorporated herein by reference.

## Substrate:

The OLED of the present invention may be prepared on a substrate. The substrate referred to in this case is a substrate for supporting the OLED, and it is preferably a flat substrate in which light in the visible region of about 400 to about 700 nm has a transmittance of at least about 50%.

The substrate may include a glass plate, a polymer plate and the like. In particular, the glass plate may include soda lime glass, barium strontium-containing glass, lead glass, aluminosilicate glass, borosilicate glass, barium borosilicate glass, quartz and the like. The polymer plate may include polycarbonate, acryl, polyethylene terephthalate, polyether sulfide, polysulfone and the like.

## Electrodes:

The anode 3 in the OLED 100 of the present invention assumes the role of injecting holes into the hole injecting

layer, the hole transporting layer or the light emitting layer. Typically the anode has a work function of 4.5 eV or more. Specific examples of a material suitable for use as the anode include indium tin oxide alloy (ITO), tin oxide (NESA), indium zinc oxide, gold, silver, platinum, copper and the like. The anode can be prepared by forming a thin film from electrode substances, such as those discussed above, by a method such as a vapor deposition method, a sputtering method and the like.

When light is emitted from the light emitting layer, the transmittance of light in the visible light region in the anode is preferably larger than 10%. The sheet resistance of the anode is preferably several hundred  $\Omega$ /square or less. The film thickness of the anode is selected, depending on the material, and is typically in the range of from about 10 nm to about 1  $\mu$ m, and preferably from about 10 nm to about 200 nm.

The cathode 11 comprises preferably a material having a small work function for the purpose of injecting an electron into the electron injecting layer, the electron transporting layer or the light emitting layer. Materials suitable for use as the cathode include, but are not limited to indium, aluminum, magnesium, magnesium-indium alloys, magnesium-aluminum alloys, aluminum-lithium alloys, aluminum-scandium-lithium alloys, magnesium-silver alloys and the like. For transparent or top-emitting devices, a TOLED cathode such as disclosed in U.S. Pat. No. 6,548,956 is preferred.

The cathode can be prepared, as is the case with the anode, by forming a thin film by a method such as a vapor deposition method, a sputtering method and the like. Further, an embodiment in which light emission is taken out from a cathode side can be employed as well.

#### Inverted OLED:

FIG. 2 shows an inverted OLED 200 according to another embodiment of the present disclosure. The device includes a substrate 210, a cathode 215 an emitter layer 220, a first hole transport layer 225, a second hole transport layer 230, and an anode 235. Because the most common OLED configuration has a cathode disposed over the anode, and the OLED 200 has cathode 215 disposed under the anode 235, the OLED 200 may be referred to as an inverted OLED. The first hole transport layer 225 and the second hole transport layer 230 are formed of the first and second hole transport materials which are different from each other, as described above in connection with the OLED device embodiment 100.

The simple layered structures of OLED 100 and 200 are provided by way of non-limiting examples and it is understood that embodiments of the invention may be used in connection with a wide variety of other structures. Functional OLEDs may be achieved by combining the various layers described in different ways, or certain layers may be omitted entirely, based on the design, performance, and cost factors. Other layers not specifically described herein may also be included.


In one embodiment, the present invention comprises an OLED which comprises a host material, wherein the triplet energy of the host material is from about 2.0 eV to about 2.8 eV.

#### Examples


The invention will be described in further detail with reference to the following examples and comparative examples. However, the invention is not limited by the following examples.

An experimental green PHOLED Device #1 bearing the structure shown in FIG. 1 was constructed according to the present disclosure as follows. HAT-CN was used to form a 10 nm thick hole injection layer 4. Second hole transport material HTL2-I was used to form a 25 nm thick second hole transport layer 5. First hole transport material HTL1-1 was used to form a 5 nm thick first hole transport layer 6. Green phosphorescent emitter, a heteroleptic organo metallic compound identified below as GD-001, was the emitter dopant (11% doping level) used with the host material identified below as H-001 to form a 30 nm thick emitter layer 7. An undoped layer of the H-001 was used to form a 5 nm thick hole blocking layer 8. Alq<sub>3</sub> was used to form a 40 nm thick electron transport layer 9. LiF was used to form 1 nm thick electron injection layer 11. A 100 nm thick layer of Aluminum formed the cathode 11 and an 80 nm thick layer of ITO formed the anode 3. Table 2 shows the chemical structures of the organic materials used. The green phosphorescent emitter GD-001 is one of the heteroleptic organometallic compounds disclosed in WO2010/028151, specifically the Compound 12 disclosed in WO2010/028151, the disclosure of which is incorporated herein by reference in its entirety. The host material H-001 is one of the triphenylene-containing benzo-fused thiophene compounds disclosed herein, specifically the Compound 2' among the compounds having the general structure H-III.


TABLE 2




---

HTL1-1

HTL2-1



GD-001



H-001





TABLE 2-continued



All organic layers were deposited under high-vacuum conditions ( $1 \times 10^{-7}$  Torr). The green PHOLED was transferred directly from vacuum into an inert environment glove-box, where it was encapsulated using a UV-curable epoxy, and a glass lid with a moisture getter. The PHOLED emission profiles were assumed to be Lambertian, so EQE was calculated from measurements, made with a SpectraScan PR705, of the emission intensity normal to the substrate. The current and voltage measurements were obtained using a Keithley 236 source measure unit.

For performance comparison, Comparative Example PHOLED Device #2 was also constructed. PHOLED Device #2 also was built with two hole transport layers but both layers were built with a single material (the second hole transport material, HTL2-1) resulting in a 30 nm thick layer of HTL2-1. In effect, Device #2 is equivalent to a conventional single hole transport layer configuration. Table 3a shows the performance comparison of the two green PHOLED devices. Device #1 is the PHOLED device built according to the present disclosure and Device #2 is the conventional single hole transport layer device. Table 3b shows a summary of the two devices' construction in terms of the materials used for the hole transporting layers and the emitter layer.

TABLE 3a

Device #	1931 CIE		Voltage (V)	LE (cd/A)	EQE (%)	L <sub>0</sub> (nits)	LT <sub>80%</sub> (hrs)
	x	y					
1	0.320	0.628	5.5	71	20	21612	365
2	0.319	0.629	5.4	66	18	19204	266

TABLE 3b

Device #	Hole Transporting Material 2	Hole Transporting Material 1	Emitter Dopant	Emitter Host
1	arylamine type compound HTL2-I	carbazole type compound HTL1-1	heteroleptic organometallic compound GD-001	triphenylene containing benzo-fused thiophene compound H-001
2	arylamine type compound HTL2-I	None	heteroleptic organometallic compound GD-001	triphenylene containing benzo-fused thiophene compound H-001

As shown in Table 3a, Device #1 exhibited unexpectedly substantially higher luminous efficiency (LE) and external quantum efficiency (EQE) over Device #2. The LE of Device #1 was 71 cd/A at 1,000 nits compared to 66 cd/A

for Device #2. The EQE of Device #1 was 20% at 1,000 nits compared to 18% for Device #2. The substantially superior performance data of Device #1 was unexpected. Particularly, 15 considering that in Device #2, three of the four listed materials are the same as those of Device #1, the degree of performance superiority demonstrated by Device #1 was unexpected.

Additionally, Device #1 also demonstrated an unexpectedly longer LT<sub>80</sub> (the time for the luminance to decrease to 80% of its initial level) at 25° C. than Device #2. For LT<sub>80</sub> 20 measurements, the devices were operated at a constant current of 40 mA/cm<sup>2</sup>, at 25° C. The LT<sub>80</sub> of Device #1 was 365 hrs compared to 266 hours for the Device #2.

25 The device performance data for the prior art devices of WO2011/048821 shown above indicates that the enhanced device lifetimes observed with Device #1 would not be possible for the prior art devices in which the carbazole type compounds are provided in a layer between an emissive layer and a TPD hole transport layer in which the emissive layer's emitter dopant is a homoleptic emitter (Ir(ppy)<sub>3</sub>) rather than the heteroleptic emitters used in Device #1.

30 The substantial improvement in the overall performance observed with Device #1 compared to Device #2 was unexpected, especially when considering the incremental difference in the structure of the devices (i.e. the addition of a thin layer (5 nm) of the compound HTL1-1. Without being bound by a theory, the inventors believe that the enhanced device performance is attributed to the combination of 35 HTL1-1 and HTL2-1 in particular when used with the materials in the emitter layers disclosed herein. For example, in Device #1, The HTL1-1 compound used as a first hole transport layer positioned adjacent to the emitter layer is a polycarbazole type compound whose triplet energy is higher 40 than second hole transport layer material HTL2-I which is a biphenyl arylamine type compound. The provision of a higher triplet energy material next to the emitter layer may reduce quenching of triplet excitons generated in the emitter layer. Additionally, because the HOMO energy of first hole transport layer material HTL1-1 in Device #1 is between

45 that of second hole transport layer material HTL2-I and emitter layer host material H-001, the inventors believe that the HTL1-1 layer assists hole injection from the second hole transporting layer into the emitter layer. Still further, the 50 HTL1-1 layer may also provide an electron blocking function in Device #1 since the LUMO energy of HTL1-1 is higher than that of HTL2-I. With the above three points, the 55 triplet excitons can be well confined in the emitter layer with an overall better charge balance in the whole device.


60 Additionally, the performance data for the Device #1 was compared against the prior art devices disclosed in PCT International Application Publication No. WO2011/048821 A1. Table 3 shows comparative performance data of Example devices 6, 7

65 Unless otherwise specified, any of the layers of the various embodiments of the invention described herein may be deposited by any suitable method. For the organic layers,

preferred methods include thermal evaporation, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, which are incorporated by reference in their entireties, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102 to Forrest et al., which is incorporated by reference in its entirety, and deposition by organic vapor jet printing (OVJP), such as described in U.S. patent application Ser. No. 10/233,470, which is incorporated by reference in its entirety. Other suitable deposition methods include spin coating and other solution based processes. Solution based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition through a mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, which are incorporated by reference in their entireties, and patterning associated with some of the deposition methods such as ink-jet and OVJD. Other methods may also be used. The materials to be deposited may be modified to make them compatible with a particular deposition method. For example, substituents such as alkyl and aryl groups, branched or unbranched, and preferably containing at least 3 carbons, may be used in small molecules to enhance their ability to undergo solution processing. Substituents having 20 carbons or more may be used, and 3-20 carbons is a preferred range. Materials with asymmetric structures may have better solution processibility than those having symmetric structures, because asymmetric materials may have a lower tendency to recrystallize. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing.

What is claimed is:

1. An organic light emitting device comprising an anode, a cathode and a plurality of organic layers sandwiched between them, the plurality of organic layers comprising: an emitter layer comprising a host material and a phosphorescent emitter material, the phosphorescent emitter material comprising a phosphorescent organometallic compound that emits phosphorescent radiation from a triplet molecular excited state when a voltage is applied across the first organic layer; a first hole transport layer disposed between the emitter layer and the anode, the first hole transport layer comprising a first hole transport material represented by the following general formula (HTL1)



wherein R<sub>1</sub>, R<sub>2</sub>, R<sub>3</sub>, R<sub>4</sub>, R<sub>5</sub>, and R<sub>6</sub> may be the same or different fluoric atom, chlorine atom, a deuterium atom, a cyano group, a trifluoromethyl group, a nitro group, linear or branched alkyl group (C1-C6), cyclo-alkyl group (C5-C10), linear or branched alkoxy group (C1-

5 C6), cyclo-alkoxy group (C5-C10), substituted or unsubstituted aromatic hydrocarbon group, substituted or unsubstituted aromatic heterocyclic group, substituted or unsubstituted condensed polycyclic aromatic group,

r<sub>1</sub>, r<sub>4</sub>, r<sub>5</sub>=0, 1, 2, 3, or 4,

r<sub>2</sub>, r<sub>3</sub>, r<sub>6</sub>=0, 1, 2 or 3,

n=0 or 1, and

10 Ar<sub>1</sub>, Ar<sub>2</sub>, and Ar<sub>3</sub> may be the same or different, substituted or unsubstituted aromatic hydrocarbon group, substituted or unsubstituted aromatic heterocyclic group, substituted or unsubstituted condensed polycyclic aromatic group, deuterium substituted aromatic hydrocarbon group, deuterium substituted aromatic heterocyclic group, or deuterium substituted condensed polycyclic aromatic group; and

15 a second hole transport layer disposed between the first hole transport layer and the anode whereby the first hole transport layer is next to the emitter layer between the emitter layer and the second hole transport layer, wherein the second hole transport layer comprising a second hole transport material that is different from the first hole transport material;


20 wherein the first hole transport material has a triplet energy that is higher than that of the second hole transport material; and

25 wherein the phosphorescent organometallic compound is a heteroleptic compound represented by the formula L<sub>2</sub>MX, LL'MX, LL'L'M, or LMXX', wherein L, L', L", X, and X' are inequivalent, bidentate ligands and M is a metal that forms octahedral complexes, wherein L, L', and L" are monoanionic inequivalent bidentate ligands coordinated to M through an sp<sup>2</sup> hybridized carbon and a heteroatom.


30 35 40 45 50 55 60 65 70 75 80 85 90 95 100 105 110 115 120 125 130 135 140 145 150 155 160 165 170 175 180 185 190 195 200 205 210 215 220 225 230 235 240 245 250 255 260 265 270 275 280 285 290 295 300 305 310 315 320 325 330 335 340 345 350 355 360 365 370 375 380 385 390 395 400 405 410 415 420 425 430 435 440 445 450 455 460 465 470 475 480 485 490 495 500 505 510 515 520 525 530 535 540 545 550 555 560 565 570 575 580 585 590 595 600 605 610 615 620 625 630 635 640 645 650 655 660 665 670 675 680 685 690 695 700 705 710 715 720 725 730 735 740 745 750 755 760 765 770 775 780 785 790 795 800 805 810 815 820 825 830 835 840 845 850 855 860 865 870 875 880 885 890 895 900 905 910 915 920 925 930 935 940 945 950 955 960 965 970 975 980 985 990 995 1000 1005 1010 1015 1020 1025 1030 1035 1040 1045 1050 1055 1060 1065 1070 1075 1080 1085 1090 1095 1100 1105 1110 1115 1120 1125 1130 1135 1140 1145 1150 1155 1160 1165 1170 1175 1180 1185 1190 1195 1200 1205 1210 1215 1220 1225 1230 1235 1240 1245 1250 1255 1260 1265 1270 1275 1280 1285 1290 1295 1300 1305 1310 1315 1320 1325 1330 1335 1340 1345 1350 1355 1360 1365 1370 1375 1380 1385 1390 1395 1400 1405 1410 1415 1420 1425 1430 1435 1440 1445 1450 1455 1460 1465 1470 1475 1480 1485 1490 1495 1500 1505 1510 1515 1520 1525 1530 1535 1540 1545 1550 1555 1560 1565 1570 1575 1580 1585 1590 1595 1600 1605 1610 1615 1620 1625 1630 1635 1640 1645 1650 1655 1660 1665 1670 1675 1680 1685 1690 1695 1700 1705 1710 1715 1720 1725 1730 1735 1740 1745 1750 1755 1760 1765 1770 1775 1780 1785 1790 1795 1800 1805 1810 1815 1820 1825 1830 1835 1840 1845 1850 1855 1860 1865 1870 1875 1880 1885 1890 1895 1900 1905 1910 1915 1920 1925 1930 1935 1940 1945 1950 1955 1960 1965 1970 1975 1980 1985 1990 1995 2000 2005 2010 2015 2020 2025 2030 2035 2040 2045 2050 2055 2060 2065 2070 2075 2080 2085 2090 2095 2100 2105 2110 2115 2120 2125 2130 2135 2140 2145 2150 2155 2160 2165 2170 2175 2180 2185 2190 2195 2200 2205 2210 2215 2220 2225 2230 2235 2240 2245 2250 2255 2260 2265 2270 2275 2280 2285 2290 2295 2300 2305 2310 2315 2320 2325 2330 2335 2340 2345 2350 2355 2360 2365 2370 2375 2380 2385 2390 2395 2400 2405 2410 2415 2420 2425 2430 2435 2440 2445 2450 2455 2460 2465 2470 2475 2480 2485 2490 2495 2500 2505 2510 2515 2520 2525 2530 2535 2540 2545 2550 2555 2560 2565 2570 2575 2580 2585 2590 2595 2600 2605 2610 2615 2620 2625 2630 2635 2640 2645 2650 2655 2660 2665 2670 2675 2680 2685 2690 2695 2700 2705 2710 2715 2720 2725 2730 2735 2740 2745 2750 2755 2760 2765 2770 2775 2780 2785 2790 2795 2800 2805 2810 2815 2820 2825 2830 2835 2840 2845 2850 2855 2860 2865 2870 2875 2880 2885 2890 2895 2900 2905 2910 2915 2920 2925 2930 2935 2940 2945 2950 2955 2960 2965 2970 2975 2980 2985 2990 2995 3000 3005 3010 3015 3020 3025 3030 3035 3040 3045 3050 3055 3060 3065 3070 3075 3080 3085 3090 3095 3100 3105 3110 3115 3120 3125 3130 3135 3140 3145 3150 3155 3160 3165 3170 3175 3180 3185 3190 3195 3200 3205 3210 3215 3220 3225 3230 3235 3240 3245 3250 3255 3260 3265 3270 3275 3280 3285 3290 3295 3300 3305 3310 3315 3320 3325 3330 3335 3340 3345 3350 3355 3360 3365 3370 3375 3380 3385 3390 3395 3400 3405 3410 3415 3420 3425 3430 3435 3440 3445 3450 3455 3460 3465 3470 3475 3480 3485 3490 3495 3500 3505 3510 3515 3520 3525 3530 3535 3540 3545 3550 3555 3560 3565 3570 3575 3580 3585 3590 3595 3600 3605 3610 3615 3620 3625 3630 3635 3640 3645 3650 3655 3660 3665 3670 3675 3680 3685 3690 3695 3700 3705 3710 3715 3720 3725 3730 3735 3740 3745 3750 3755 3760 3765 3770 3775 3780 3785 3790 3795 3800 3805 3810 3815 3820 3825 3830 3835 3840 3845 3850 3855 3860 3865 3870 3875 3880 3885 3890 3895 3900 3905 3910 3915 3920 3925 3930 3935 3940 3945 3950 3955 3960 3965 3970 3975 3980 3985 3990 3995 4000 4005 4010 4015 4020 4025 4030 4035 4040 4045 4050 4055 4060 4065 4070 4075 4080 4085 4090 4095 4100 4105 4110 4115 4120 4125 4130 4135 4140 4145 4150 4155 4160 4165 4170 4175 4180 4185 4190 4195 4200 4205 4210 4215 4220 4225 4230 4235 4240 4245 4250 4255 4260 4265 4270 4275 4280 4285 4290 4295 4300 4305 4310 4315 4320 4325 4330 4335 4340 4345 4350 4355 4360 4365 4370 4375 4380 4385 4390 4395 4400 4405 4410 4415 4420 4425 4430 4435 4440 4445 4450 4455 4460 4465 4470 4475 4480 4485 4490 4495 4500 4505 4510 4515 4520 4525 4530 4535 4540 4545 4550 4555 4560 4565 4570 4575 4580 4585 4590 4595 4600 4605 4610 4615 4620 4625 4630 4635 4640 4645 4650 4655 4660 4665 4670 4675 4680 4685 4690 4695 4700 4705 4710 4715 4720 4725 4730 4735 4740 4745 4750 4755 4760 4765 4770 4775 4780 4785 4790 4795 4800 4805 4810 4815 4820 4825 4830 4835 4840 4845 4850 4855 4860 4865 4870 4875 4880 4885 4890 4895 4900 4905 4910 4915 4920 4925 4930 4935 4940 4945 4950 4955 4960 4965 4970 4975 4980 4985 4990 4995 5000 5005 5010 5015 5020 5025 5030 5035 5040 5045 5050 5055 5060 5065 5070 5075 5080 5085 5090 5095 5100 5105 5110 5115 5120 5125 5130 5135 5140 5145 5150 5155 5160 5165 5170 5175 5180 5185 5190 5195 5200 5205 5210 5215 5220 5225 5230 5235 5240 5245 5250 5255 5260 5265 5270 5275 5280 5285 5290 5295 5300 5305 5310 5315 5320 5325 5330 5335 5340 5345 5350 5355 5360 5365 5370 5375 5380 5385 5390 5395 5400 5405 5410 5415 5420 5425 5430 5435 5440 5445 5450 5455 5460 5465 5470 5475 5480 5485 5490 5495 5500 5505 5510 5515 5520 5525 5530 5535 5540 5545 5550 5555 5560 5565 5570 5575 5580 5585 5590 5595 5600 5605 5610 5615 5620 5625 5630 5635 5640 5645 5650 5655 5660 5665 5670 5675 5680 5685 5690 5695 5700 5705 5710 5715 5720 5725 5730 5735 5740 5745 5750 5755 5760 5765 5770 5775 5780 5785 5790 5795 5800 5805 5810 5815 5820 5825 5830 5835 5840 5845 5850 5855 5860 5865 5870 5875 5880 5885 5890 5895 5900 5905 5910 5915 5920 5925 5930 5935 5940 5945 5950 5955 5960 5965 5970 5975 5980 5985 5990 5995 6000 6005 6010 6015 6020 6025 6030 6035 6040 6045 6050 6055 6060 6065 6070 6075 6080 6085 6090 6095 6100 6105 6110 6115 6120 6125 6130 6135 6140 6145 6150 6155 6160 6165 6170 6175 6180 6185 6190 6195 6200 6205 6210 6215 6220 6225 6230 6235 6240 6245 6250 6255 6260 6265 6270 6275 6280 6285 6290 6295 6300 6305 6310 6315 6320 6325 6330 6335 6340 6345 6350 6355 6360 6365 6370 6375 6380 6385 6390 6395 6400 6405 6410 6415 6420 6425 6430 6435 6440 6445 6450 6455 6460 6465 6470 6475 6480 6485 6490 6495 6500 6505 6510 6515 6520 6525 6530 6535 6540 6545 6550 6555 6560 6565 6570 6575 6580 6585 6590 6595 6600 6605 6610 6615 6620 6625 6630 6635 6640 6645 6650 6655 6660 6665 6670 6675 6680 6685 6690 6695 6700 6705 6710 6715 6720 6725 6730 6735 6740 6745 6750 6755 6760 6765 6770 6775 6780 6785 6790 6795 6800 6805 6810 6815 6820 6825 6830 6835 6840 6845 6850 6855 6860 6865 6870 6875 6880 6885 6890 6895 6900 6905 6910 6915 6920 6925 6930 6935 6940 6945 6950 6955 6960 6965 6970 6975 6980 6985 6990 6995 7000 7005 7010 7015 7020 7025 7030 7035 7040 7045 7050 7055 7060 7065 7070 7075 7080 7085 7090 7095 7100 7105 7110 7115 7120 7125 7130 7135 7140 7145 7150 7155 7160 7165 7170 7175 7180 7185 7190 7195 7200 7205 7210 7215 7220 7225 7230 7235 7240 7245 7250 7255 7260 7265 7270 7275 7280 7285 7290 7295 7300 7305 7310 7315 7320 7325 7330 7335 7340 7345 7350 7355 7360 7365 7370 7375 7380 7385 7390 7395 7400 7405 7410 7415 7420 7425 7430 7435 7440 7445 7450 7455 7460 7465 7470 7475 7480 7485 7490 7495 7500 7505 7510 7515 7520 7525 7530 7535 7540 7545 7550 7555 7560 7565 7570 7575 7580 7585 7590 7595 7600 7605 7610 7615 7620 7625 7630 7635 7640 7645 7650 7655 7660 7665 7670 7675 7680 7685 7690 7695 7700 7705 7710 7715 7720 7725 7730 7735 7740 7745 7750 7755 7760 7765 7770 7775 7780 7785 7790 7795 7800 7805 7810 7815 7820 7825 7830 7835 7840 7845 7850 7855 7860 7865 7870 7875 7880 7885 7890 7895 7900 7905 7910 7915 7920 7925 7930 7935 7940 7945 7950 7955 7960 7965 7970 7975 7980 7985 7990 7995 8000 8005 8010 8015 8020 8025 8030 8035 8040 8045 8050 8055 8060 8065 8070 8075 8080 8085 8090 8095 8100 8105 8110 8115 8120 8125 8130 8135 8140 8145 8150 8155 8160 8165 8170 8175 8180 8185 8190 8195 8200 8205 8210 8215 8220 8225 8230 8235 8240 8245 8250 8255 8260 8265 8270 8275 8280 8285 8290 8295 8300 8305 8310 8315 8320 8325 8330 8335 8340 8345 8350 8355 8360 8365 8370 8375 8380 8385 8390 8395 8400 8405 8410 8415 8420 8425 8430 8435 8440 8445 8450 8455 8460 8465 8470 8475 8480 8485 8490 8495 8500 8505 8510 8515 8520 8525 8530 8535 8540 8545 8550 8555 8560 8565 8570 8575 8580 8585 8590 8595 8600 8605 8610 8615 8620 8625 8630 8635 8640 8645 8650 8655 8660 8665 8670 8675 8680 8685 8690 8695 8700 8705 8710 8715 8720 8725 8730 8735 8740 8745 8750 8755 8760 8765 8770 8775 8780 8785 8790 8795 8800 8805 8810 8815 8820 8825 8830 8835 8840 8845 8850 8855 8860 8865 8870 8875 8880 8885 8890 8895 8900 8905 8910 8915 8920 8925 8930 8935 8940 8945 8950 8955 8960 8965 8970 8975 8980 8985 8990 8995 9000 9005 9010 9015 9020 9025 9030 9035 9040 9045 9050 9055 9060 9065 9070 9075 9080 9085 9090 9095 9100 9105 9110 9115 9120 9125 9130 9135 9140 9145 9150 9155 9160 9165 9170 9175 9180 9185 9190 9195 9200 9205 9210 9215 9220 9225 9230 9235 9240 9245 9250 9255 9260 9265 9270 9275 9280 9285 9290 9295 9300 9305 9310 9315 9320 9325 9330 9335 9340 9345 9350 9355 9360 9365 9370 9375 9380 9385 9390 9395 9400 9405 9410 9415 9420 9425 9430 9435 9440 9445 9450 9455 9460 9465 9470 9475 9480 9485 9490 9495 9500 9505 9510 9515 9520 9525 9530 9535 9540 9545 9550 9555 9560 9565 9570 9575 9580 9585 9590 9595 9600 9605 9610 9615 9620 9625 9630 9635 9640 96

wherein  $R_{11}$  and  $R_{12}$  may be the same or different and are independently selected from the group consisting of a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, a phenyl group, a phenyl group having a lower alkyl group or deuterium substituent, 5 and a phenyl group having a deuterium atom or a lower alkoxy group substituent with the proviso at least one of  $R_{11}$  and  $R_{12}$  is a deuterium atom, a normal butyl group, an isobutyl group, a secondary butyl group, a tertiary butyl group, a phenyl group, a phenyl group having a lower alkyl group substituent, or a phenyl group having a lower alkoxy group substituent; and  $R_{13}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom;

-continued



(d1)




(HTL2-II)

wherein  $R_{21}$ ,  $R_{22}$  and  $R_{23}$  may be the same or different and each represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group, or a phenyl group having a lower alkyl group or a lower alkoxy group as a substituent(s); 40  $R_{24}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and

$A_1$  represents a group represented by any one of the 45 following structural formulae (a1) to (i1);

-continued




(e1)




(a1)


50




(f1)



(b1)




(g1)



(c1)

60




(h1)

65

**81**

-continued



5


10

**82**

(i1)

in which  $R_{25}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom;


(HTL2-III)




wherein  $R_{31}$ ,  $R_{32}$  and  $R_{33}$  may be the same or different and each represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group, or a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group as a substituent(s);

$R_{34}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and


$A_2$  represents a group represented by any one of the following formulae (j1) to (n1)




(j1)




(k1)



(l1)




(m1)



(n1)

-continued

(HTL2-IV)



wherein  $R_{41}$  and  $R_{42}$  may be the same or different and each represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group or a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group as a substituent(s);

$R_{43}$  represents a hydrogen atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and

$A_3$  represents a group represented by anyone of the following structural formulae (a2) to (i2)

30

35

40

(a2)

45

(b2)

50

(c2)

55


(d2)

60


65

-continued


(e2)








(f2)




(g2)




(h2)





(i2)


in which  $R_{44}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom;



wherein  $R_{51}$  and  $R_{52}$  may be the same or different and each represent a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted phenyl group or a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group as a substituent(s);


$R_{53}$  represents a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group or a chlorine atom; and

$A_4$  represents a group represented by anyone of the following structural formulae (j2) to (n2)






(j2)

(k2)



(l2)


(m2)



(n2)

-continued

(HTL2-VI)




25

where  $R_{61}$  to  $R_{69}$ , which may be the same or different, represent a hydrogen atom, a deuterium atom, a lower alkyl group, a lower alkoxy group, an unsubstituted aromatic hydrocarbon group, a phenyl group having a deuterium atom, a lower alkyl group or a lower alkoxy group;  $r_{61}$  to  $r_{69}$ , which may be the same or different, represent 0, 1 or 2.


30

7. The organic light emitting device of claim 1, wherein the first hole transport material is selected from the group consisting of:

Compound HTL1-1



Compound HTL1-2




89


90

-continued


### Compound HTL1-3




## Compound HTL1-4



### Compound HTL1-5




### Compound HTL1-6




-continued


Compound HTL-7



Compound HTL-8



Compound HTL-9




93


94

-continued


### Compound HTL1-10



### Compound HTL1-11




### Compound HTL1-12




-continued

Compound HTL1-13



8. The organic light emitting device according to claim 1, wherein the host material is a compound comprising a triphenylene containing benzo-fused thiophene or benzo-fused furan, wherein any substituent in the compound is an unfused substituent independently selected from the group consisting of  $C_nH_{2n+1}$ ,  $OC_nH_{2n+1}$ ,  $OAr_1$ ,  $N(C_nH_{2n+1})_2$ ,  $N(Ar_1)(Ar_2)$ ,  $CH=CH-C_nH_{2n+1}$ ,  $C=CHC_nH_{2n+1}$ ,  $Ar_1$ ,  $Ar_1-Ar_2$ ,  $C_nH_{2n}-Ar_1$ , or no substitution, wherein n is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10, and wherein  $Ar_1$  and  $Ar_2$  are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof.

9. The organic light emitting device according to claim 8, wherein the host material is represented by the structure of formula (H-IV):



wherein X is S or O;

wherein  $R_1$ ,  $R_2$ , and  $R_3$  are unfused substituents independently selected from the group consisting of  $C_nH_{2n+1}$ ,  $OC_nH_{2n+1}$ ,  $OAr_1$ ,  $N(C_nH_{2n+1})_2$ ,  $N(Ar_1)(Ar_2)$ ,  $CH=CH-C_nH_{2n+1}$ ,  $C=CHC_nH_{2n+1}$ ,  $Ar_1$ ,  $Ar_1-Ar_2$ ,  $C_nH_{2n}-Ar_1$ , or no substitution, and wherein each of  $R_1$ ,  $R_2$  and  $R_3$  may represent mono, di, tri, or tetra substitutions;

wherein n is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10;


wherein  $Ar_1$  and  $Ar_2$  are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof; and

wherein at least one of  $R_1$ ,  $R_2$  and  $R_3$  includes a triphenylene group.

10. The organic light emitting device according to claim 9, wherein X is S.

11. The organic light emitting device according to claim 9, wherein X is O.

12. The organic light emitting device according to claim 8, wherein the host material is represented by the structure of formula (H-V):



wherein X is S or O;

wherein  $R_1$ ,  $R_2$ , and  $R_3$  are unfused substituents independently selected from the group consisting of  $C_nH_{2n+1}$ ,  $OC_nH_{2n+1}$ ,  $OAr_1$ ,  $N(C_nH_{2n+1})_2$ ,  $N(Ar_1)(Ar_2)$ ,  $CH=CH-C_nH_{2n+1}$ ,  $C=CHC_nH_{2n+1}$ ,  $Ar_1$ ,  $Ar_1-Ar_2$ ,  $C_nH_{2n}-Ar_1$ , or no substitution, and wherein each of  $R_1$ ,  $R_2$  and  $R_3$  may represent mono, di, tri, or tetra substitutions;

wherein n is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10;


wherein  $Ar_1$  and  $Ar_2$  are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof; and

wherein at least one of  $R_1$ ,  $R_2$  and  $R_3$  includes a triphenylene group.

13. The organic light emitting device according to claim 12, wherein X is S.

14. The organic light emitting device according to claim 12, wherein X is O.

15. The organic light emitting device according to claim 8, wherein the host material is represented by the structure of formula (H-VI):



(H-VI)

wherein X is S or O;

wherein R<sub>1</sub>, R<sub>2</sub>, and R<sub>3</sub> are unfused substituents independently selected from the group consisting C<sub>n</sub>H<sub>2n+1</sub>, OC<sub>n</sub>H<sub>2n+1</sub>, OAr<sub>1</sub>, N(C<sub>n</sub>H<sub>2n+1</sub>)<sub>2</sub>, N(Ar<sub>1</sub>)(Ar<sub>2</sub>), CH=CH—C<sub>n</sub>H<sub>2n+1</sub>, C=CHC<sub>n</sub>H<sub>2n+1</sub>, Ar<sub>1</sub>, Ar<sub>1</sub>—Ar<sub>2</sub>, 5 C<sub>n</sub>H<sub>2n</sub>—Ar<sub>1</sub>, or no substitution, and wherein each of R<sub>1</sub>, R<sub>2</sub> and R<sub>3</sub> may represent mono, di, tri, or tetra substitutions;

wherein n is 1, 2, 3, 4, 5, 6, 7, 8, 9, or 10;

wherein Ar<sub>1</sub> and Ar<sub>2</sub> are independently selected from the 10 group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof; and

wherein at least one of R<sub>1</sub>, R<sub>2</sub> and R<sub>3</sub> includes a triphenylene group. 15

**16.** The organic light emitting device according to claim 15, wherein X is S.

**17.** The organic light emitting device according to claim 15, wherein X is O.

**18.** The organic light emitting device according to claim 1, wherein the first hole transport material has a HOMO energy level that is between that of the second hole transport material and the host material. 20

**19.** The organic light emitting device according to claim 1, wherein the first hole transport material has a LUMO 25 energy level that is higher than that of the second hole transport material.

\* \* \* \* \*

专利名称(译)	磷光有机发光器件与具有高操作稳定性的空穴传输材料相结合		
公开(公告)号	<a href="#">US9705092</a>	公开(公告)日	2017-07-11
申请号	US14/237142	申请日	2011-08-05
[标]申请(专利权)人(译)	山本仁 织女米迦勒斯图尔特 横山典正 长冈MAKOTO KABASAWA NAOAKI		
申请(专利权)人(译)	山本仁 韦弗MICHAEL STEWART 横山典正 长冈，MAKOTO KABASAWA，NAOAKI		
当前申请(专利权)人(译)	通用显示器公司 HODOGAYA化学有限公司.		
[标]发明人	YAMAMOTO HITOSHI WEAVER MICHAEL STEWART YOKOYAMA NORIMASA NAGAOKA MAKOTO KABASAWA NAOAKI		
发明人	YAMAMOTO, HITOSHI WEAVER, MICHAEL STEWART YOKOYAMA, NORIMASA NAGAOKA, MAKOTO KABASAWA, NAOAKI		
IPC分类号	H01L51/50 H01L51/00 H05B33/14 C09K11/06		
CPC分类号	H01L51/0072 C09K11/06 H01L51/0054 H01L51/0059 H01L51/0074 H01L51/5016 H01L51/5064 H05B33/14 C09K2211/185		
代理机构(译)	DUANE MORRIS LLP		
审查员(译)	CLARK, GREGORY		
其他公开文献	US20140339518A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

**摘要(译)**

改进的OLED包括设置在阴极和阳极之间的发射极层，其中发射极层包括主体材料和磷光发射极材料。第一空穴传输层设置在发射极层和阳极之间，第二空穴传输层设置在第一空穴传输层和阳极之间。第一空穴传输层包括作为咔唑类化合物的第一空穴传输材料，第二空穴传输层包括与第一空穴传输材料不同的第二空穴传输材料。磷光发光体材料包括磷光有机金属化合物，其是由式L<sub>2</sub>MX，L<sub>2</sub>MX，L<sub>2</sub>M或LMXX表示的杂配化合物，其中L，L<sup>+</sup>，L<sup>-</sup>，X和X<sup>+</sup>是不等价的双齿配体，M是形成八面体配合物的金属，其中L，L<sup>+</sup>和L<sup>-</sup>是通过sp<sup>2</sup>与M配位的单阴离子不等价二齿配体杂化碳和杂原子。

