



US009768406B2

(12) **United States Patent**
Sun et al.

(10) **Patent No.:** **US 9,768,406 B2**
(45) **Date of Patent:** **Sep. 19, 2017**

(54) **OLED DISPLAY PANEL AND MANUFACTURING METHOD THEREOF, DISPLAY DEVICE AND FILLING METHOD OF FILLING ADHESIVE**

(71) Applicant: **BOE TECHNOLOGY GROUP CO., LTD.**, Beijing (CN)

(72) Inventors: **Zhongyuan Sun**, Beijing (CN);
Kaihong Ma, Beijing (CN)

(73) Assignee: **BOE Technology Group Co., Ltd.**, Beijing (CN)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 49 days.

(21) Appl. No.: **14/429,256**

(22) PCT Filed: **Jul. 17, 2014**

(86) PCT No.: **PCT/CN2014/082410**

§ 371 (c)(1),

(2) Date: **Mar. 18, 2015**

(87) PCT Pub. No.: **WO2015/055029**

PCT Pub. Date: **Apr. 23, 2015**

(65) **Prior Publication Data**

US 2016/0035996 A1 Feb. 4, 2016

(30) **Foreign Application Priority Data**

Oct. 16, 2013 (CN) 2013 1 0485179

(51) **Int. Cl.**

H01L 51/52 (2006.01)

H01L 21/77 (2017.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 51/5246** (2013.01); **H01L 21/77** (2013.01); **H01L 27/3244** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC .. H01L 51/5246; H01L 27/3244; H01L 51/52
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2005/0275792 A1 12/2005 Chen et al.
2008/0296159 A1* 12/2008 Kong C08G 65/18
204/600

(Continued)

FOREIGN PATENT DOCUMENTS

CN 1571598 A 1/2005
CN 1913193 A 2/2007

(Continued)

OTHER PUBLICATIONS

Dec. 30, 2015—(CN)—Second Office Action Appn
201310485179.X with English Tran.

(Continued)


Primary Examiner — Marc Armand

(74) *Attorney, Agent, or Firm* — Banner & Witcoff, Ltd.

(57) **ABSTRACT**

An OLED display panel and a manufacturing method thereof, a display device and a filling method of a filling adhesive are provided. The OLED display panel comprises: a first substrate and a second substrate disposed opposite to each other; a first adhesive dam connected with and located between the first substrate and the second substrate, and provided with at least one opening; a second adhesive dam connected with and located between the first substrate and the second substrate, located outside the first adhesive dam, and forming a sealed cell together with the first substrate and the second substrate; an OLED device located on an inner side of the first adhesive dam and on the first substrate; and a filling adhesive filled in the inner side of the first adhesive dam. With the OLED display panel, the adjusting difficulty of production engineering of the OLED display panel can be reduced.

17 Claims, 3 Drawing Sheets



(51) **Int. Cl.**

H01L 27/32 (2006.01)

H01L 51/56 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/525** (2013.01); **H01L 51/5259**
(2013.01); **H01L 51/56** (2013.01); **H01L**
2227/323 (2013.01); **H01L 2251/533**
(2013.01); **H01L 2251/5315** (2013.01)

FOREIGN PATENT DOCUMENTS

CN	101211962 A	7/2008
CN	101478305 A	7/2009
CN	101867024 A	10/2010
CN	103500755 A	1/2014
CN	203521418 U	4/2014
JP	2002025764 A	1/2002
KR	20030043249 A	6/2003

OTHER PUBLICATIONS

(56)

References Cited

U.S. PATENT DOCUMENTS

2010/0013384 A1*	1/2010	Song	H01L 51/5246 313/504
2010/0045181 A1*	2/2010	Oh	H01L 51/5246 313/512

Oct. 20, 2014—(CN) International Search Report for PCT/CN2014/082410.

Oct. 20, 2014—(CN) Written Opinion for PCT/CN2014/082410—Eng Trans.

Jul. 28, 2015—(CN) First Office Action Appn 201310485179.X with Eng Tran.

* cited by examiner




FIG.1




FIG.2




FIG.3




FIG.4




FIG.5

**OLED DISPLAY PANEL AND
MANUFACTURING METHOD THEREOF,
DISPLAY DEVICE AND FILLING METHOD
OF FILLING ADHESIVE**

The application is a U.S. National Phase Entry of International Application No. PCT/CN2014/082410 filed on Jul. 17, 2014, designating the United States of America and claiming priority to Chinese Patent Application No. 201310485179.X filed on Oct. 16, 2013. The present application claims priority to and the benefit of the above-identified applications and the above-identified applications are incorporated by reference herein in their entirety.

TECHNICAL FIELD

At least one embodiment of the present disclosure relates to an OLED display panel and a manufacturing method, a display device and a filling method of a filling adhesive.

BACKGROUND

OLED (Organic Light-Emitting Diode) display panels have the advantages of thinness, lightness, wide viewing angle, active luminescence, continuous and adjustable color of emitted light, low cost, fast response speed, small energy consumption, low driving voltage, wide working-temperature range, simple production engineering, high luminous efficiency, being usable for flexible display and so on, and have been listed as the next generation display technology having excellent development prospects.

Research shows that, water vapor, oxygen gas and similar components in air have a great effect on the lifetime of the OLED device in an OLED display panel, the reason is as follows. When an OLED device is in operation, electrons need to be injected from a cathode, and this requires the work function of the cathode to be as low as possible. However, the cathode is usually made of aluminum, magnesium, calcium or other metallic material, the chemical property of which is relative active, and which is very prone to react with water vapor and oxygen gas permeated therein; furthermore, water vapor and oxygen gas can also react with a hole transport layer and an electron transport layer in the OLED device; and all of these reactions can cause the failure of the OLED device. Therefore, by means of conducting an effective package for an OLED device so that functional layers of the OLED device are fully separated from water vapor, oxygen gas and similar components in air, the lifetime of the OLED device can be prolonged greatly, and thus the service life of the OLED display panel is prolonged.

At present, method for packaging an OLED device mainly includes: desiccant attaching plus UV adhesive coating, surface packaging, glass frit packaging, thin film packaging and so on. Packaging technology in which an adhesive dam and a filling adhesive are used belongs to the surface packaging. The filling adhesive has a higher transparency, so this packaging technology not only can be used for packaging of bottom-emission devices, but also can be used for packaging of top-emission devices, and is one of the packaging methods having excellent development prospects currently.

As shown in FIG. 1 and FIG. 2, an OLED display panel mainly includes a deposition substrate **19**, an OLED device **16** located on the deposition substrate **19** and a protective layer **17** covering the OLED device **16**, a package substrate **20** located above the deposition substrate **19** and disposed opposite to the deposition substrate **19**, an adhesive dam **21**

forming a sealed cell together with the deposition substrate **19** and the package substrate **20**, and a filling adhesive **18** filled within the sealed cell. The adhesive dam **21** functions as a first barrier for blocking water vapor and oxygen, the filling adhesive **18** functions as a second barrier for blocking water vapor and oxygen, and the protective layer **17** not only has a function of blocking water vapor and oxygen, but also can prevent the filling adhesive **18** from directly contacting the OLED device **16** and thus affecting the operational characteristics of the OLED device **16**.

SUMMARY

At least one embodiment of the present disclosure provides an OLED display panel, a manufacturing method of the OLED display panel, a display device and a filling method of a filling adhesive, so as to reduce the adjusting difficulty of the production engineering of the OLED display panel, and improve the production efficiency of products and the product quality.

An organic light-emitting diode (OLED) display panel provided by at least one embodiment of the disclosure comprises: a first substrate and a second substrate disposed opposite to each other; a first adhesive dam connected with and located between the first substrate and the second substrate, and provided with at least one opening; a second adhesive dam connected with and located between the first substrate and the second substrate and located outside the first adhesive dam, and forming a sealed cell together with the first substrate and the second substrate; an OLED device, located on an inner side of the first adhesive dam and on the first substrate; and a filling adhesive filled in the inner side of the first adhesive dam.

At least one embodiment of the disclosure further provides a display device, which comprises the above-mentioned organic light-emitting diode (OLED) display panel.

At least one embodiment of the disclosure further provides a manufacturing method of an organic light-emitting diode (OLED) display panel, and the method comprises: forming an OLED device on a first substrate; forming a first adhesive dam provided with at least one opening, and a second adhesive dam located outside the first adhesive dam, on a second substrate, with a filling adhesive filled in an inner side of the first adhesive dam; aligning the first substrate and the second substrate, so that the OLED device is located on the inner side of the first adhesive dam and the first substrate is respectively connected to the first adhesive dam and the second adhesive dam; and solidifying the first adhesive dam, the second adhesive dam and the filling adhesive.

At least one embodiment of the disclosure further provides a filling method of a filling adhesive, and the method comprises: forming a first adhesive dam provided with at least one opening and a second adhesive dam located outside the first adhesive dam, on a second substrate; and providing a filling adhesive filled in an inner side of the first adhesive dam.

BRIEF DESCRIPTION OF THE DRAWINGS

In order to illustrate the technical solution of the embodiments of the disclosure more clearly, the drawings of the embodiments will be briefly described below; it is obvious that the drawings as described below are only related to some embodiments of the disclosure, but not limitative of the disclosure.

FIG. 1 is a schematic top view illustrating a structure of an OLED display panel;

FIG. 2 is a structurally, schematically sectional view taken along a direction A-A in FIG. 1;

FIG. 3 is a schematic top view illustrating a structure of an OLED display panel according to an embodiment the disclosure;

FIG. 4 is a structurally, schematically sectional view taken along a direction B-B in FIG. 3; and

FIG. 5 is a flow chart illustrating a manufacturing method of an OLED display panel according to an embodiment of the disclosure.

REFERENCE NUMERALS

11—first substrate	12—second substrate
13—first adhesive dam	14—opening
15—second adhesive dam	16—OLED device
17—protective layer	18—filling adhesive
19—deposition substrate	20—package substrate
21—adhesive dam	

DETAILED DESCRIPTION

In order to make objects, technical details and advantages of the embodiments of the disclosure apparent, hereinafter, the technical solutions of the embodiments of the disclosure will be described in a clearly and fully understandable way in connection with the drawings related to the embodiments of the disclosure. It is obvious that the described embodiments are just a part but not all of the embodiments of the disclosure. Based on the described embodiments of the disclosure, those skilled in the art can obtain other embodiment(s), without any inventive work, which should be within the scope of the disclosure.

The inventor(s) of the present application noted that, in an OLED display panel shown in FIG. 1, a filling adhesive 18 needs to fully fill a sealed cell. If the filling amount is less, a cavity may occur within the sealed cell, and water vapor and oxygen may seep in from the cavity, and thus cause the failure of the OLED device 16. And if the filling amount of the filling adhesive is too much, the adhesive dam 21 can be damaged by overmuch filling adhesive 18, and a protective effect of preventing water vapor and oxygen from penetrating is lost. Therefore, when the filling adhesive 18 is filled, the filling amount of the filling adhesive 18 needs to be controlled accurately. This brings a large adjusting difficulty to the production engineering of the OLED display panel, and affects the production efficiency and the product quality.

In order to reduce the adjusting difficulty of the production engineering of the OLED display panel, and to enhance the production efficiency of products and the product quality, at least one embodiment of the disclosure provides an OLED display panel, a manufacturing method of the OLED display panel, a display device and a filling method of a filling adhesive. In the OLED display panel provided by embodiments of the disclosure, due to the provision of two adhesive dams inside and outside, the filling adhesive only needs to fill up an inner region of the first adhesive dam, and excess filling adhesive may flow out from at least one opening of the first adhesive dam, to fill a gap region between the first adhesive dam and the second adhesive dam. By adopting this design, the filling amount of the filling adhesive may have a larger range of process error. Thus, the adjusting difficulty of production engineering of the OLED display

panel is greatly reduced, and this is helpful for enhancing the production efficiency of products and the product quality.

As shown in FIG. 3 and FIG. 4, an OLED display panel provided by at least one embodiment of the disclosure includes a first substrate 11 and a second substrate 12 disposed opposite to each other; a first adhesive dam 13 provided with at least one opening 14, connected with and located between the first substrate 11 and the second substrate 12; a second adhesive dam 15, connected with and located between the first substrate 11 and the second substrate 12 and located on an outer side of the first adhesive dam 13, and forming a sealed cell together with the first substrate 11 and the second substrate 12; an OLED device 16, located on an inner side of the first adhesive dam 13 and on the first substrate 11; a protective layer 17, covering the OLED device 16 and hermetically connected to the first substrate 11; and a filling adhesive 18 filled in an inner side of the first adhesive dam 13.

In at least one embodiment of the disclosure, according to the processing technique of the OLED display panel, the first substrate 11 is usually called as a deposition substrate, and the second substrate 12 is usually called as a package substrate. For example, the first adhesive dam 13 and the second adhesive dam 15 may adopt the same constituent (for example, the effective component is epoxy resin) and proportion. For example, the filling adhesive 18 may adopt the same constituent as the first adhesive dam 13 and the second adhesive dam 15, but adopt a different proportion, so that the filling adhesive has a certain flowability when the filling adhesive is filled. All of the first adhesive dam 13, the second adhesive dam 15 and the filling adhesive 18 need to be shaped by a curing process. In various examples, the OLED device 16 may be a top-emission OLED device or a bottom-emission OLED device. Embodiments of the disclosure do not limit the type of the OLED device 16. A material of the protective layer 17 may be silicon nitride and/or silicon oxide and so on, so that a good function of blocking water vapor and oxygen can be obtained.

In the OLED display panel shown in FIG. 1, only a circle of adhesive dam is provided, and a sealed cell is constituted by the adhesive dam and first and second substrates, with a filling adhesive filled in the sealed cell. When the filling adhesive is filled, the filling amount of the filling adhesive needs to be controlled accurately, so as to avoid such a case where the filling amount is inadequate and thus a cavity occurs within the sealed cell, or such a case where the filling amount is too much and thus the adhesive dam is damaged. In embodiments of the disclosure, the filling adhesive 18 only needs to fill up an inner region of the first adhesive dam 13, and excess filling adhesive 18 may flow out from at least one opening 14 of the first adhesive dam 13, to fill a gap region between the first adhesive dam 13 and the second adhesive dam 15. By adopting this design, the filling amount of the filling adhesive 18 may have a larger range of process error (at the very most, it can fill up the gap region between the first adhesive dam 13 and the second adhesive dam 15). Thus, the adjusting difficulty of production engineering of the OLED display panel is greatly reduced, and this is helpful for enhancing the production efficiency of products and the product quality.

In various embodiments, the water permeable rate of the second adhesive dam 15 at normal temperature and pressure may be from 10 to 20 g/m² per day (g/m²-d), the water permeable rate of the filling adhesive 18 at normal temperature and pressure may be from 5 to 10 g/m² per day, and the water permeable rate of the protective layer 17 at normal temperature and pressure may be from 10⁻⁴ g/m² per day. A

sealed cell is formed by the second adhesive dam **15** and the first and second substrates **11** and **12**, and the second adhesive dam **15** acts as a first barrier for blocking water vapor and oxygen. The filling adhesive **18** acts as a second barrier for blocking water vapor and oxygen, and the protective layer **17** not only has a function of blocking water vapor and oxygen, but also can prevent the filling adhesive **18** from directly contacting the OLED device **16** and affecting operational characteristics of the OLED device **16**. It is seen that, with the structure of embodiments of the disclosure, functional layers of the OLED device can be separated fully from water vapor, oxygen gas and similar component in air, and the lifetime of the OLED device is prolonged greatly. Thus, the service life of the OLED display panel is prolonged.

The specific shapes of the first adhesive dam **13** and the second adhesive dam **15** are not limitative. In at least one embodiment, the OLED display panel is usually a rectangular screen, so the first adhesive dam **13** and the second adhesive dam **15** may take on the shape of a rectangular frame as a whole. As shown in FIG. 3, in an example, the number of the opening **14** is at least two. It is to be noted that, the specific number of the opening **14** can be designed according to the shape and size of the OLED display panel, material properties of adhesive dams and the filling adhesive, etc. In various examples, the at least two openings **14** may be distributed evenly, and the length of each opening **14** may be from 1 millimeter to 2 millimeters. The length of the opening within the selective range enables excess filling adhesive **18** to flow out smoothly, and cannot causing an overlarge impact on the first adhesive dam **13** to damage the first adhesive dam **13**. Furthermore, that the length of the opening falls within the selective range can also guarantee that the filling adhesive **18** fully fills in an inner region of the first adhesive dam **13**, so as to avoid a filling cavity from occurring in the inner region of the first adhesive dam **13**. Thus, this is helpful for improving the product quality.

As shown in FIG. 3, a gap **b** between the first adhesive dam **13** and the second adhesive dam **15**, for example, may be designed according to the precision of a filling device for the filling adhesive and the size of the OLED display panel. It not only helps to reduce the adjusting difficulty of production engineering, but also favors the optimized design of products and further reduction in the production cost, to design the size of the gap between the first adhesive dam **13** and the second adhesive dam **15** according to the precision of a filling device for the filling adhesive and the size of the OLED display panel.

At least one embodiment of the disclosure provides a display device, and the display device comprises the OLED display panel according to any one of the above-mentioned embodiments. Because the OLED display panel has the above-mentioned effects, the structure of the display device also reduces the adjusting difficulty of production engineering of the display device greatly. This helps to enhance the production efficiency of products and the product quality.

In addition, as shown in FIG. 5, at least one embodiment of the disclosure further provides a manufacturing method of an OLED display panel, which comprises the following steps.

Step **101**, an OLED device is formed on a first substrate, and is covered with a protective layer hermetically connected to the first substrate.

For example, a vacuum evaporation process may be used to form the OLED device on the first substrate. That is, an evaporated material is heated under a certain vacuum condition, and melted (or sublimated) to form vapor composed

of atoms, molecules or atomic groups, and then it accumulates on a surface of a base to form a film, thereby forming a functional layer of the OLED device. The specific process is an existing technology, and details are omitted herein.

For examples, silicon nitride and/or silicon oxide and so on may be chosen as a material of the protective layer. The protective layer may be formed into film by way of chemical vapor deposition.

Step **102**, a first adhesive dam provided with at least one opening and a second adhesive dam located outside the first adhesive dam are formed on a second substrate, and a filling adhesive is filled inside the first adhesive dam.

For example, the first adhesive dam and the second adhesive dam may adopt the same constituent (for example, the effective component is epoxy resin) and proportion. For example, the filling adhesive may adopt the same constituent as the first adhesive dam and the second adhesive dam, but adopt a different proportion so that the filling adhesive has a certain flowability when the filling adhesive is filled. Patterns of the first adhesive dam and the second adhesive dam may be directly formed through a coating process, the filling adhesive may be filled in an inner side of the first adhesive dam through a coating process as well, and the filling amount of the filling adhesive may have a larger range of process error.

Step **103**, the first substrate and the second substrate are aligned, so that the OLED device and the protective layer are located on an inner side of the first adhesive dam, and the first substrate is connected to the first adhesive dam and the second adhesive dam, respectively.

In this step, a pressing process may be used to connect the first substrate and the first and second adhesive dams. After pressing, the first adhesive dam and the second adhesive dam are contracted under the action of an extrusion force, so that their thicknesses are decreased, while redundant part of the filling adhesive flows out from the opening of the first adhesive dam due to the extrusion force acting on it, and fill a gap region between the first adhesive dam and the second adhesive dam.

Step **104**, the first adhesive dam, the second adhesive dam and the filling adhesive are cured. Because the first adhesive dam, the second adhesive dam and the filling adhesive subjected to the step **103** have a certain plasticity, it is necessary for them to be cured. For example, an UV light curing process may be employed.

It is to be noted that, upon manufacture of the OLED display panel, orders of the step **101** and the step **102** can be interchanged, or they are carried out simultaneously. This does not affect the final fabrication and formation of the OLED display panel.

Owing to use of the method, the filling amount of the filling adhesive may have a larger range of process error. Thus, the adjusting difficulty of the production engineering is reduced, and this helps to enhance the production efficiency of products and the product quality.

At least one embodiment of the disclosure further provides a filling method of a filling adhesive. The method comprises: forming a first adhesive dam provided with at least one opening, and a second adhesive dam located outside the first adhesive dam, on a second substrate; and filling a filling adhesive in an inner side of the first adhesive dam.

In an example, the filling method further comprises: placing the first substrate and the second substrate to be opposite to each other, so that the first substrate is connected to the first adhesive dam and the second adhesive dam,

respectively; and solidifying the first adhesive dam, the second adhesive dam and the filling adhesive.

The filling method according to embodiments of the disclosure is suitable for such a sealing environment that requires to be filled with a filling adhesive, especially 5 a filling adhesive, especially a filling adhesive, like an OLED display panel. In the filling method according to embodiments of the disclosure, due to the provision of two circles of adhesive dams inside and outside, the filling adhesive only needs to fill up an inner region of the first adhesive dam, and excess filling adhesive may flow out from at least one opening of the first adhesive dam, to fill a gap region between the first adhesive dam and the second adhesive dam. Owing to the adoption of the design, the filling amount of the filling adhesive can have a larger range of process error. Thus, this greatly reduces the adjusting difficulty in filling the filling adhesive.

Apparently, various modifications and variations to the present disclosure can be made by those skilled in the art without departing from the spirit and scope of the disclosure. In this way, if these modifications and variations of the disclosure fall within the scope of the claims of the disclosure and their equivalents, then the present disclosure is intended to cover these modifications and variations.

This application claims the benefit of Chinese Patent Application No. 201310485179.X, filed on Oct. 16, 2013, which is hereby entirely incorporated by reference.

What is claimed is:

1. An organic light-emitting diode (OLED) display panel, comprising:

a first substrate and a second substrate disposed opposite to each other;

a first adhesive dam, connected with and located between the first substrate and the second substrate, and provided with at least one opening;

a second adhesive dam, connected with and located between the first substrate and the second substrate, and located outside the first adhesive dam, wherein the second adhesive dam, the first substrate and the second substrate form a sealed cell;

an OLED device, located on an inner side of the first adhesive dam and on the first substrate;

a filling adhesive, filled in the inner side of the first adhesive dam; and

a protective layer covering the OLED device and hermetically connected to the first substrate.

2. The OLED display panel claimed as claim 1, wherein there are at least two openings in number, the at least two openings are distributed evenly, and a length of each of the openings is from 1 millimeter to 2 millimeters.

3. The OLED display panel claimed as claim 1, wherein a gap between the first adhesive dam and the second adhesive dam is obtained based on precision of a filling device for the filling adhesive and a size of the OLED display panel.

4. The OLED display panel claimed as claim 1, wherein a water permeable rate of the second adhesive dam at normal temperature and pressure is from 10 to 20 g/m² per day, and a water permeable rate of the filling adhesive at normal temperature and pressure is from 5 to 10 g/m² per day.

5. The OLED display panel claimed as claim 1, wherein the OLED device comprises a top-emission OLED device or a bottom-emission OLED device.

6. The OLED display panel claimed as claim 1, wherein a water permeable rate of the protective layer at normal temperature and pressure is 10⁻⁴ g/m² per day.

7. The OLED display panel claimed as claim 1, wherein a material of the protective layer comprises at least one selected from the group consisting of silicon nitride and silicon oxide.

8. A display device, comprising an organic light-emitting diode (OLED) display panel claimed as claim 1.

9. The OLED display panel claimed as claim 2, wherein a gap between the first adhesive dam and the second adhesive dam is obtained based on precision of a filling device for the filling adhesive and a size of the OLED display panel.

10. The OLED display panel claimed as claim 2, wherein a water permeable rate of the second adhesive dam at normal temperature and pressure is from 10 to 20 g/m² per day, and a water permeable rate of the filling adhesive at normal temperature and pressure is from 5 to 10 g/m² per day.

11. The OLED display panel claimed as claim 2, wherein the OLED device comprises a top-emission OLED device or a bottom-emission OLED device.

12. The OLED display panel claimed as claim 3, wherein a water permeable rate of the second adhesive dam at normal temperature and pressure is from 10 to 20 g/m² per day, and a water permeable rate of the filling adhesive at normal temperature and pressure is from 5 to 10 g/m² per day.

13. The OLED display panel claimed as claim 3, wherein the OLED device comprises a top-emission OLED device or a bottom-emission OLED device.

14. The OLED display panel claimed as claim 4, wherein the OLED device comprises a top-emission OLED device or a bottom-emission OLED device.

15. A manufacturing method of an organic light-emitting diode (OLED) display panel, comprising:

forming an OLED device on a first substrate;

forming a first adhesive dam with at least one opening, and a second adhesive dam located outside the first adhesive dam, on a second substrate, with a filling adhesive filled in an inner side of the first adhesive dam;

aligning the first substrate and the second substrate, wherein the OLED device is located on the inner side of the first adhesive dam, and the first substrate is connected to the first adhesive dam and the second adhesive dam, respectively; and

solidifying the first adhesive dam, the second adhesive dam and the filling adhesive,

the manufacturing method further comprising covering the OLED device with a protective layer which is hermetically connected to the first substrate, wherein the protective layer is located on the inner side of the first adhesive dam.

16. A filling method of a filling adhesive, comprising: forming a first adhesive dam provided with at least one opening, and a second adhesive dam located outside the first adhesive dam, on a second substrate; and

providing a filling adhesive filled in an inner side of the first adhesive dam,

wherein the at least one opening can allow the filling adhesive to communicate between the inner side of the first adhesive dam and an outer side of the first adhesive dam.

17. The filling method of the filling adhesive claimed as claim 16, further comprising:

opposing a first substrate and the second substrate to each other, so that the first substrate is connected to the first adhesive dam and the second adhesive dam, respectively; and

solidifying the first adhesive dam, the second adhesive dam and the filling adhesive.

专利名称(译)	OLED显示面板及其制造方法，显示装置和填充粘合剂的填充方法		
公开(公告)号	US9768406	公开(公告)日	2017-09-19
申请号	US14/429256	申请日	2014-07-17
[标]申请(专利权)人(译)	京东方科技集团股份有限公司		
申请(专利权)人(译)	京东方科技集团股份有限公司.		
当前申请(专利权)人(译)	京东方科技集团股份有限公司.		
[标]发明人	SUN ZHONGYUAN MA KAIHONG		
发明人	SUN, ZHONGYUAN MA, KAIHONG		
IPC分类号	H01L51/52 H01L21/77 H01L27/32 H01L51/56		
CPC分类号	H01L51/5246 H01L21/77 H01L27/3244 H01L51/525 H01L51/5259 H01L51/56 H01L2227/323 H01L2251/533 H01L2251/5315		
代理机构(译)	BANNER & WITCOFF., LTD.		
审查员(译)	阿尔芒, MARC		
优先权	201310485179.X 2013-10-16 CN		
其他公开文献	US20160035996A1		
外部链接	Espacenet USPTO		

摘要(译)

提供一种OLED显示面板及其制造方法，显示装置和填充粘合剂的填充方法。 OLED显示面板包括：第一基板和第二基板，彼此相对设置；第一粘合坝，其与第一基板和第二基板连接并位于第一基板和第二基板之间，并设有至少一个开口；第二粘合坝，位于第一基板和第二基板之间，位于第一基板和第二基板之间，位于第一粘合坝的外侧，与第一基板和第二基板一起形成密封的单元； OLED器件，位于第一粘合剂坝的内侧和第一基板上；填充粘合剂填充在第一粘合剂坝的内侧。利用OLED显示面板，可以降低OLED显示面板的生产工程的调整难度。

