



US010290818B2

(12) **United States Patent**
Park et al.

(10) **Patent No.:** **US 10,290,818 B2**

(45) **Date of Patent:** **May 14, 2019**

(54) **ORGANOMETALLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) Applicants: **Samsung Electronics Co., Ltd.**,
Suwon-si, Gyeonggi-do (KR); **Samsung SDI Co., Ltd.**, Yongin-si, Gyeonggi-do (KR)

(72) Inventors: **Sangho Park**, Anyang-si (KR); **Wook Kim**, Suwon-si (KR); **Changho Noh**, Suwon-si (KR); **Hyejin Bae**, Suwon-si (KR); **Virendra Kumar Rai**, Hwaseong-si (KR); **Satoko Ishibe**, Seongnam-si (KR); **Miyoung Chae**, Suwon-si (KR); **Dmitry Kravchuk**, Hwaseong-si (KR)

(73) Assignees: **SAMSUNG ELECTRONICS CO., LTD.**, Gyeonggi-Do (KR); **SAMSUNG SDI CO., LTD.**, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 282 days.

(21) Appl. No.: **15/064,112**

(22) Filed: **Mar. 8, 2016**

(65) **Prior Publication Data**

US 2017/0110673 A1 Apr. 20, 2017

(30) **Foreign Application Priority Data**

Oct. 14, 2015 (KR) 10-2015-0143371

(51) **Int. Cl.**

H01L 51/00 (2006.01)
C07F 15/00 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 51/0085** (2013.01); **C07F 15/0033** (2013.01); **C09K 11/06** (2013.01); **C09K 2211/185** (2013.01); **H01L 51/5016** (2013.01)

(58) **Field of Classification Search**

CPC H01L 51/0085; H01L 51/5016; C07F 15/0033; C09K 11/06; C09K 2211/185

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,585,573 B2 * 9/2009 Lee C07F 15/0033
252/301.16

9,978,961 B2 * 5/2018 Tsai H01L 51/0085
(Continued)

FOREIGN PATENT DOCUMENTS

JP 2011-256116 A 12/2011
JP 2012-019171 A 1/2012


(Continued)

Primary Examiner — Michael Bernshteyn

(74) *Attorney, Agent, or Firm* — Cantor Colburn LLP

(57) **ABSTRACT**


An organometallic compound represented by Formula 1:



Formula 1

wherein, in Formula 1, L_{11} , M, R_{11} to R_{17} , m, and n are the same as described in the specification.

19 Claims, 3 Drawing Sheets



(51) **Int. Cl.***C09K 11/06* (2006.01)*H01L 51/50* (2006.01)(58) **Field of Classification Search**

USPC 428/690

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2013/0292654 A1 * 11/2013 Matsunaga C09K 11/06
257/402013/0313532 A1 * 11/2013 Watanabe H01L 51/0071
257/40

FOREIGN PATENT DOCUMENTS

JP 2013-243299 A 12/2013

KR 2005-0078472 A 8/2005

KR 2015-0083017 A 7/2015

* cited by examiner

FIG. 1




FIG. 2





FIG. 3



1

ORGANOMETALLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to and the benefit of Korean Patent Application No. 10-2015-0143371, filed on Oct. 14, 2015, in the Korean Intellectual Property Office, the content of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

The present disclosure relate to an organometallic compound and an organic light-emitting device including the same.

2. Description of the Related Art

Organic light-emitting devices (OLEDs) are self-emission devices that have wide viewing angles, high contrast ratios, and short response times. In addition, the OLEDs display excellent brightness, driving voltage, and response speed characteristics, and produce full-color images.

A typical organic light-emitting device includes an anode, a cathode, and an emission layer disposed between the anode and the cathode. A hole transport region may be disposed between the anode and the emission layer, and an electron transport region may be disposed between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons change from an excited state to a ground state, thereby generating light.

Different types of organic light emitting devices are known. However, there still remains a need in OLEDs having low driving voltage, high efficiency, high brightness, and long lifespan.

SUMMARY


Provided are organometallic compounds and organic light-emitting devices including the same.

Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented exemplary embodiments.

According to an aspect of an exemplary embodiment, provided is an organometallic compound represented by Formula 1:

2

Formula 1



In Formula 1,

M is selected from a Period 4 transition metal, a Period 5 transition metal, and a Period 6 transition metal, europium (Eu), terbium (Tb), and thulium (Tm);

R₁₁ to R₁₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁)(Q₂)(Q₃); two adjacent groups selected from R₁₁ to R₁₇ are optionally linked to each other to form a saturated or unsaturated ring;

at least one of R₁₅ and R₁₇ is selected from a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group;

Q₁ to Q₃ are each independently selected from a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, and a substituted or unsubstituted C₁-C₆₀ heteroaryl group;

n is selected from 1, 2, and 3;

L₁₁ is selected from a monodentate ligand and a bidentate ligand;

m is selected from 0, 1, 2, 3, and 4.

According to an aspect of another exemplary embodiment, an organic light-emitting device includes:

a first electrode;

a second electrode; and

an organic layer between the first electrode and the second electrode,

wherein the organic layer including an emission layer, and

wherein the organic layer comprises at least one organometallic compound represented by Formula 1.

The emission layer may include the organometallic compound, the emission layer may further include a host, and the organometallic compound included in the emission layer may act as a dopant.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects will become apparent and more readily appreciated from the following description of the exemplary embodiments, taken in conjunction with the accompanying drawings in which:

FIG. 1 is a schematic cross-sectional view of an organic light-emitting device according to an embodiment;

FIG. 2 shows a lifespan-luminance graph of brightness (percent, %) versus T_{80} comparative lifespan (percent, %) of organic light-emitting devices manufactured according to Comparative Examples 1 and 2, and Examples 1, 2, 3 and 9; and

FIG. 3 is a graph of normalized photoluminescence (PL) intensity versus wavelength (nanometers, nm) showing photoluminescent (PL) spectra of organic light-emitting devices manufactured according to Comparative Examples 1 and 2, and Examples 2 and 3.

DETAILED DESCRIPTION

Reference will now be made in detail to exemplary embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present exemplary embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the exemplary embodiments are merely described below, by referring to the figures, to explain aspects of the present inventive concept. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list

It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

The term “or” means “and/or.” It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do

not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.


Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this general inventive concept belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

“About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

An organometallic compound according to an embodiment is represented by Formula 1:

Formula 1



M in Formula 1 may be selected from a Period 4 transition metal, a Period 5 transition metal, and a Period 6 transition metal, europium (Eu), terbium (Tb), and thulium (Tm).

For example, M in Formula 1 may be selected from iridium (Ir), platinum (Pt), osmium (Os), ruthenium (Ru), rhodium (Rh), palladium (Pd), copper (Cu), silver (Ag), gold (Au), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm), but is not limited thereto.

In various embodiments, M in Formula 1 may be selected from Ir, Pt, Os, Ti, Zr, Hf, Eu, Tb, and Tm, but is not limited thereto.

In various embodiments, M in Formula 1 may be selected from Ir, Pt, and Os, but is not limited thereto.

In various embodiments, M in Formula 1 may be selected from Ir and Pt, but is not limited thereto.

In various embodiments, M in Formula 1 may be Ir, but is not limited thereto.

R₁₁ to R₁₇ in Formula 1 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁)(Q₂)(Q₃);

two adjacent groups selected from R₁₁ to R₁₇ may be optionally linked to each other to form a saturated or unsaturated ring;

at least one of R₁₅ and R₁₇ may be selected from a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group; and

Q₁ to Q₃ may each independently be selected from a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, and a substituted or unsubstituted C₁-C₆₀ heteroaryl group.

For example, R₁₇ in Formula 1 may be selected from a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, but is not limited thereto.

For example, R₁₁ to R₁₇ in Formula 1 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁)(Q₂)(Q₃); two adjacent groups selected from R₁₁ to R₁₇ may be optionally linked to each other to form a saturated or unsaturated ring;

at least one of R₁₅ and R₁₇ may be selected from a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group; and

Q₁ to Q₃ may each independently be selected from a substituted or unsubstituted C₁-C₆₀ alkyl group and a substituted or unsubstituted C₆-C₆₀ aryl group, but is not limited thereto.

In various embodiments, R₁₁ to R₁₇ in Formula 1 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, and a C₁-C₁₀ heterocycloalkyl group;

a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, and a C₁-C₁₀ heterocycloalkyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, and —I;

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, and —Si(Q₁₁)(Q₁₂)(Q₁₃); and

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a C₁-C₂₀ alkyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, and —I;

two adjacent groups selected from R₁₁ to R₁₇ may be optionally linked to each other to form a saturated or unsaturated ring;

at least one of R₁₅ and R₁₇ may be selected from

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, and a naphthyl group; and

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a C₁-C₂₀ alkyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, and —I; and

7

Q_{11} to Q_{13} may each independently be selected from a methyl group, an ethyl group, and a phenyl group, but is not limited thereto.

In various embodiments, R_{11} to R_{17} in Formula 1 may each independently be selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a methoxy group, an ethoxy group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a methoxy group, an ethoxy group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group, each substituted with at least one selected from deuterium and —F;

a phenyl group, a naphthyl group, and a dibenzofuran group;

a phenyl group, a naphthyl group, and a dibenzofuran group, each substituted with at least one selected from deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, a naphthyl group, and —Si(CH₃)₃; and

a phenyl group, a naphthyl group, and a dibenzofuran group, each substituted with at least one selected from a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium and —F;

two adjacent groups selected from R_{11} to R_{17} may be optionally linked to each other to form a saturated or unsaturated ring;

at least one of R_{15} and R_{17} may be selected from

a phenyl group, a naphthyl group, and a dibenzofuran group;

a phenyl group, a naphthyl group, and a dibenzofuran group, each substituted with at least one selected from deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, and a naphthyl group; and


a phenyl group, a naphthyl group, and a dibenzofuran group, each substituted with at least one selected from a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium and —F, but are not limited thereto.

In various embodiments, R_{11} to R_{17} in Formula 1 may each independently be selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an iso-butyl group, a tert-butyl group, a cyclopentyl group, a cyclohexyl group, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, and groups represented by Formulae 5-1 to 5-19;


two adjacent groups selected from R_{11} to R_{17} may be optionally linked to each other to form a saturated or unsaturated ring; and

8


at least one of R_{15} and R_{17} may be selected from groups represented by Formulae 5-1 to 5-19, but they are not limited thereto:




5-1




5-2




5-3




5-4




5-5



5-6











5-7



5-8

9

-continued




10

-continued

5-9

5-17

5




10

5-18


5-10

15



5-11

20



5-19

25

5-12

30

5-13

35

40

5-14

45

5-15

55

5-16

60

65

65

In Formulae 5-1 to 5-19,

* indicates a binding site to an adjacent atom; and


Ph indicates a phenyl group.

In various embodiments, R_{11} to R_{17} in Formula 1 may each independently be selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an iso-butyl group, a tert-butyl group, a cyclopentyl group, a cyclohexyl group, —CD₃, —CF₃, and groups represented by Formulae 5-1 to 5-19;

two adjacent groups selected from R_{11} to R_{17} may be optionally linked to each other to form a saturated or unsaturated ring; and

R_{17} may be selected from groups represented by Formulae 5-1 to 5-19, but they are not limited thereto.

n in Formula 1 indicates the number of ligands represented by



wherein * and * each indicate a binding site to M in Formula 1. n in Formula 1 may be selected from 1, 2, and 3. When n in Formula 1 is 2 or more, the ligands may be identical to or different from each other.

For example, n in Formula 1 may be selected from 2 and 3, but is not limited thereto.

In various embodiments, M in Formula 1 may be Ir, and n may be 3, but is not limited thereto.

In various embodiments, M in Formula 1 may be Ir, and n may be 2, but is not limited thereto.

In various embodiments, M in Formula 1 may be Ir, and n may be 1, but is not limited thereto.

11


In various embodiments, M in Formula 1 may be Pt, and n may be 2, but is not limited thereto.

In various embodiments, M in Formula 1 may be Pt, and n may be 1, but M and n not limited thereto.

L_{11} in Formula 1 may be selected from a monodentate ligand and a bidentate ligand.

For example, L_{11} in Formula 1 may be selected from monodentate ligands, and L_{11} may be selected from I^- , Br^- , Cl^- , sulfide, nitrate, azide, hydroxide, cyanate, isocyanate, thiocyanate, water, acetonitrile, pyridine, ammonia, carbon monoxide, $P(Ph)_3$, $P(Ph)_2CH_3$, $PPh(CH_3)_2$, and $P(CH_3)_3$, but is not limited thereto.

In various embodiments, L_{11} in Formula 1 may be selected from bidentate ligands, and L_{11} may be selected from oxalate, acetylacetonate, picolinic acid, 2-(2-hydroxyphenyl)-pyridine, 2-phenylpyridine, 1,2-bis(diphenylphosphino)ethane, 1,1-bis(diphenylphosphino)methane, glycinate, ethylenediamine, 1,10-phenanthroline, and groups represented by Formulae 3-1 and 3-2, but is not limited thereto:



In Formulae 3-1 and 3-2,

A_{31} and A_{32} may each independently be selected from a C_6-C_{20} carbocyclic group and a C_1-C_{20} heterocyclic group;

X_{31} to X_{34} may each independently be selected from a carbon atom (C) and a nitrogen atom (N);

R_{31} to R_{38} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} , alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{10} cycloalkyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3-C_{10} cycloalkenyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted

12

C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_1-C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-C(=O)(Q_{31})$, $-N(Q_{31})(Q_{32})$, and $-Si(Q_{31})(Q_{32})(Q_{33})$; R_{32} and R_{33} may be optionally linked to each other to form a saturated or unsaturated ring; R_{35} and R_{36} may be optionally linked to each other to form a saturated or unsaturated ring;

b_{34} and b_{38} may each independently be selected from 1, 2, 3, 4, 5, and 6; and

* and *' each indicate a binding site to M in Formula 1.

For example, A_{31} and A_{32} in Formulae 3-1 and 3-2 may each independently be selected from a benzene, a naphthalene, an imidazole, a pyridine, a pyrimidine, a triazine, a quinoline, and an isoquinoline, but they are not limited thereto.

In various embodiments, A_{31} and A_{32} in Formulae 3-1 and 3-2 may be each independently a benzene, but they are not limited thereto.

For example, R_{31} to R_{38} in Formulae 3-1 and 3-2 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a cyano group, a methyl group, an ethyl group, a phenyl group, and a naphthyl group, but they are not limited thereto.



m in Formula 1 indicates the number of groups L_{11} , and may be selected from 0, 1, 2, 3, and 4. When m is 2 or more, groups L_{11} may be identical to or different from each other.

For example, m in Formula 1 may be 0, 1, and 2, but is not limited thereto.

In various embodiments, m in Formula 1 may be selected from 0 and 1, but is not limited thereto.



In various embodiments, m in Formula 1 may be 0, but is not limited thereto.

In various embodiments, the organometallic compound represented by Formula 1 may be selected from compounds represented by Formulae 1-1 to 1-4:



13

-continued




In Formulae 1-1 to 1-4,

A_{11} to A_{13} may each independently be selected from substituted or unsubstituted C_6 - C_{20} carbocyclic groups; and




M , R_{11} to R_{17} , n , L_{11} , and m are the same as described in connection with Formula 1.

For example, A_{11} to A_{13} in Formulae 1-1 to 1-4 may each independently be selected from a cyclopentene, a cyclohexene, and a benzene, but they are not limited thereto.

In various embodiments, the organometallic compound represented by Formula 1 may be selected from compounds represented by Formulae 1-11 to 1-14:

**14**

-continued




In Formulae 1-11 to 1-14,

A_{11} to A_{13} may each independently be selected from a substituted or unsubstituted C_6 - C_{20} carbocyclic group;

M , R_{11} to R_{15} , R_{17} , n , L_{11} , and m are the same as described in connection with Formula 1.


For example, A_{11} to A_{13} in Formulae 1-11 to 1-14 may each independently be selected from a cyclopentene, a cyclohexene, and a benzene, but they are not limited thereto.

In various embodiments, the organometallic compound represented by Formula 1 may be selected from compounds represented by Formulae 1-21 to 1-24:



15

-continued




1-22

5

10

1-23




15

20

1-24

25



30

35


In Formulae 1-21 to 1-24,

M, R₁₂, R₁₅, R₁₇, n, L₁₁, and m are the same as described in connection with Formula 1.

For example, R₁₂, R₁₅, and R₁₇ in Formulae 1-21 to 1-24 may each independently be selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an iso-butyl group, a tert-butyl group, a cyclopentyl group, a cyclohexyl group, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, and a group represented by one of Formulae 5-1 to 5-19; and

at least one of R₁₅ and R₁₇ may be selected from groups represented by Formulae 5-1 to 5-19, but is not limited thereto.

In various embodiments, the organometallic compound represented by Formula 1 may be selected from groups represented by Formulae 1-31 to 1-34:




1-31

60


65

16


-continued



1-32



1-33



1-34


In Formulae 1-31 to 1-34,

M, R₁₂, R₁₇, n, L₁, and m are the same as described in connection with Formula 1.

For example, R₁₂ and R₁₇ in Formulae 1-31 to 1-34 may each independently be selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an iso-butyl group, a tert-butyl group, a cyclopentyl group, a cyclohexyl group, —CD₃, —CF₃, and a group represented by one of Formulae 5-1 to 5-19; and

R₁₇ may be selected from groups represented by Formulae 5-1 to 5-19, but is not limited thereto.






In various embodiments, the organometallic compound represented by Formula 1 may be selected from Compounds BD01 to BD12:



BD01

17

-continued

**18**

-continued

BD02

5

10

BD03

15

20

25

BD04

30

35

BD05

40

45






50

BD06

55

60

65



BD07

BD08


BD09

BD10

BD11

19

-continued




A maximum luminescent wavelength of the organometallic compound may be in a range of 420 nanometers (nm) to 480 nm, for example, 440 nm to 465 nm.

While not wishing to be bound by theory, it is understood that when the maximum luminescent wavelength is 480 nm or lower, an organic light-emitting device emitting blue light may be obtained.

The organometallic compound represented by Formula 1 may necessarily have a substituent having a large steric hindrance, such as an aryl group, in a pyridine ring. While not wishing to be bound by theory, it is understood that due to the inclusion of such a substituent, the organometallic compound may provide high thermal stability. Accordingly, an organic light-emitting device including the organometallic compound represented by Formula 1 may have improved lifespan.

Since the organometallic compound represented by Formula 1 may necessarily have a substituent having a large steric hindrance, such as an aryl group, in a pyridine ring, it is believed that, when the organometallic compound is deposited, aggregation may be suppressed and accordingly, the organometallic compound may be deposited in a uniform ratio with respect to an emission layer, for example, a host. Accordingly, an organic light-emitting device including the organometallic compound represented by Formula 1 may prevent exciton-quenching that occurs due to aggregation, thereby having improved efficiency.

Regarding the organometallic compound represented by Formula 1, like Formula 1', a non-coordinated nitrogen atom may be located in a para-position with respect to a metal atom. The organometallic compound may provide a high quantum yield and a short excited state lifespan.



BD12

5

10

15

20

25

30

35

40

45

Formula 1'

50

55


60

65

20

Due to the presence of the substituent having large steric hindrance, such as an aryl group, of the organometallic compound represented by Formula 1, a torsion strain between ring X1 and ring X2 illustrated in Formula 1" may be substantially reduced. Accordingly, an organic light-emitting device including the organometallic compound represented by Formula 1 may have improved driving voltage, current efficiency, and lifespan characteristics.

Formula 1"



Meanwhile, an organometallic compound that necessarily has —F, for example, bis[2-(4,6-difluorophenyl)pyridinato-C², N]iridium(III)(Flrpic) or tris[2-(4,6-difluorophenyl)pyridinato-C², N]iridium(III) is known to be unstable. However, since the organometallic compound represented by Formula 1 does not necessarily include —F, the organometallic compound may have stability.

A synthesis method for the organometallic compound represented by Formula 1 may be easily understood by one of ordinary skill in the art by referring to Synthesis Example.

Accordingly, the organometallic compound represented by Formula 1 is suitable for use in an organic layer of an organic light-emitting device, for example, a dopant of an emission layer constituting the organic layer. Thus, another aspect provides an organic light-emitting device including:

- a first electrode;
- a second electrode; and
- an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer includes an emission layer, and wherein the organometallic compound is represented by Formula 1.

Due to the inclusion of the organic layer including the organometallic compound represented by Formula 1, an organic light-emitting device having high efficiency, long lifespan and high color purity may be obtained.

The organometallic compound represented by Formula 1 may be used between a pair of electrodes of an organic light-emitting device. For example, the organometallic compound represented by Formula 1 may be included in the emission layer. In this regard, the organometallic compound acts as a dopant, and the emission layer may further include a host. The emission layer may emit red light, green light, or blue light.

The expression that "(an organic layer) includes an organometallic compound" as used herein may include an embodiment in which "(an organic layer) includes identical organometallic compounds represented by Formula 1 and an embodiment in which (an organic layer) includes two or more different organometallic compounds represented by Formula 1.

21

For example, the organic layer may include, as the organometallic compound, only Compound 1. In this regard, Compound 1 may be included in an emission layer of the organic light-emitting device. In some embodiments, the organic layer may include, as the organometallic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may be included in an identical layer (for example, Compound 1 and Compound 2 may all be included in an emission layer).

The first electrode may be an anode, which is a hole injection electrode, and the second electrode may be a cathode, which is an electron injection electrode, or the first electrode may be a cathode, which is an electron injection electrode, or the second electrode may be an anode, which is a hole injection electrode.

For example, the first electrode may be an anode, and the second electrode may be a cathode, and the organic layer may include:

i) a hole transport region that is disposed between the first electrode and the emission layer, wherein the hole transport region includes at least one selected from a hole injection layer, a hole transport layer, and an electron blocking layer, and

ii) an electron transport region that is disposed between the emission layer and the second electrode, wherein the electron transport region includes at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

The term "organic layer" as used herein refers to a single layer and/or a plurality of layers between the first electrode and the second electrode of the organic light-emitting device. The "organic layer" may include, in addition to an organic compound, an organometallic complex including metal.

FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIG. 1. The organic light-emitting device 10 includes a first electrode 11, an organic layer 15, and a second electrode 19, which are sequentially stacked.

A substrate may be additionally disposed below the first electrode 11 or above the second electrode 19. For use as the substrate, any substrate that is used in general organic light-emitting devices may be used, and the substrate may be a glass substrate having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water-resistance, or a transparent plastic substrate.

The first electrode 11 may be formed by depositing or sputtering a material for forming the first electrode 11 on the substrate. The first electrode 11 may be an anode. The material for the first electrode 11 may be selected from materials with a high work function to facilitate hole injection. The first electrode 11 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The material for the first electrode 11 may be an indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), or zinc oxide (ZnO). In some embodiments, the material for the first electrode 11 may be metal, such as magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag).

22

The first electrode 11 may have a single-layer structure or a multi-layer structure including two or more layers. For example, the first electrode 11 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 11 is not limited thereto.

The organic layer 15 is disposed on the first electrode 11.

The organic layer 15 may include a hole transport region, an emission layer, and an electron transport region.

The hole transport region may be disposed between the first electrode 11 and the emission layer.

The hole transport region may include at least one selected from a hole injection layer, a hole transport layer, an electron blocking layer, and a buffer layer.

The hole transport region may include only either a hole injection layer or a hole transport layer. In some embodiments, the hole transport region may have a structure of hole injection layer/hole transport layer or hole injection layer/hole transport layer/electron blocking layer, which are sequentially stacked in this stated order from the first electrode 11.

When the hole transport region includes a hole injection layer (HIL), the hole injection layer may be formed on the first electrode 11 by using any one of various methods, for example, vacuum deposition, spin coating, casting, or Langmuir-Blodgett (LB) deposition.


When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer, and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100 to about 500° C., a vacuum pressure of about 10⁻⁸ to about 10⁻³ torr, and a deposition rate of about 0.01 to about 100 Angstroms per second (Å/sec). However, the deposition conditions are not limited thereto.

When the hole injection layer is formed using spin coating, coating conditions may vary according to the material used to form the hole injection layer, and the structure and thermal properties of the hole injection layer. For example, a coating speed may be from about 2,000 revolutions per minute (rpm) to about 5,000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

Conditions for a hole transport layer and an electron blocking layer may be understood by referring to conditions for forming the hole injection layer.


The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β-NPB, TPD, Spiro-TPD, Spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201 below, and a compound represented by Formula 202 below:

23




24

-continued




25


-continued



methylated NPB




TAPC



HMTPD


Formula 201



26

-continued

Formula 202



Ar₁₀₁ and Ar₁₀₂ in Formula 201 may each independently be selected from

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, and a pentacenylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

xa and xb in Formula 201 may each independently be an integer of 0 to 5, or 0, 1 or 2. For example, xa may be 1 and xb may be 0, but xa and xb are not limited thereto.

R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉, and R₁₂₁ to R₁₂₄ in Formulae 201 and 202 may each independently be selected from

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, and so on), or a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, and so on);

a C₁-C₁₀ alkyl group or a C₁-C₁₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro

27

group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, or a pyrenyl group; or


a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group and a C₁-C₁₀ alkoxy group, but they are not limited thereto.

R₁₀₉ in Formula 201 may be

a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group; and

a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group.

According to an embodiment, the compound represented by Formula 201 may be represented by Formula 201A below, but is not limited thereto:




R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ in Formula 201A may be understood by referring to the description provided herein.


For example, the compound represented by Formula 201, and the compound represented by Formula 202 may include compounds HT1 to HT20 illustrated below, but are not limited thereto.

28


HT1



HT2




HT3




29

-continued


HT4



HT5




HT6

**30**


-continued

HT7




25

HT8



45

HT9




65


31

-continued


HT10



HT11




HT12


**32**

-continued


HT13




HT14



HT15




HT16




33


-continued




HT17



HT18



HT19



HT20

A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes both a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, for example about 100 Å to about 1,500 Å. While not wishing


34

to be bound by theory, it is understood that when the thicknesses of the hole transport region, the hole injection layer and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.


The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

The charge-generation material may be, for example, a p-dopant. The p-dopant may be one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments are not limited thereto. Non-limiting examples of the p-dopant are a quinone derivative, such as tetracyanoquinonodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide; and a cyano group-containing compound, such as Compound HT-D1 or Compound HT-D2 below, but are not limited thereto.


Compound HT-D1



F4-TCNQ



Compound HT-D2



The hole transport region may include a buffer layer.

Also, the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, efficiency of a formed organic light-emitting device may be improved.


Then, an emission layer (EML) may be formed on the hole transport region by vacuum deposition, spin coating,

35


casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer although the deposition or coating conditions may vary according to the material that is used to form the emission layer.

The emission layer may include a host and a dopant.


The host may include at least one selected from CBP, CDBP, TCP, and mCP:




CBP



CDBP



TCP



mCP

When the organic light-emitting device is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. In some embodiments, due to a stack structure including a red emission layer, a green emission layer, and/or a blue emission layer, the emission layer may emit white light.

The emission layer may include the organometallic compound represented by Formula 1 as a dopant.

36

When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 to about 20 parts by weight based on 100 parts by weight of the host, but is not limited thereto.

A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. While not wishing to be bound by theory, it is understood that when the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.


Then, an electron transport region may be disposed on the emission layer.

The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.


For example, the electron transport region may have a structure of hole blocking layer/electron transport layer/electron injection layer or a structure of electron transport layer/electron injection layer, but the structure of the electron transport region is not limited thereto. The electron transport layer may have a single-layered structure or a multi-layer structure including two or more different materials.

Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer which constitute the electron transport region may be understood by referring to the conditions for forming the hole injection layer.

When the electron transport layer includes a hole blocking layer, the hole blocking layer may include, for example, at least one of BCP and Bphen, but may also include other materials.



BCP







Bphen




A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. While not wishing to be bound by theory, it is understood that when the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have excellent hole blocking characteristics without a substantial increase in driving voltage.

The electron transport layer may further include, in addition to the organometallic compound represented by Formula 1, at least one selected from BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ.

37




38




In some embodiments, the electron transport layer may include at least one of ET1 and ET19, but are not limited thereto:

39

-continued


**40**

-continued



41

-continued



ET11

5


10

15


20

42

-continued



ET14




ET12

25

30

35

40



ET15

ET13


45

50


55

60

65




ET16



43

-continued



A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. While not wishing to be bound by

44


theory, it is understood that when the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

Also, the electron transport layer may further include, in addition to the materials described above, a metal-containing material.

The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.


15

ET-D1



20

ET-D2



25

30

The electron transport layer may include an electron injection layer (EIL) that promotes flow of electrons from the second electrode **19** thereinto.

The electron injection layer may include at least one selected from, LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. While not wishing to be bound by theory, it is understood that when the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

ET19

The second electrode **19** is disposed on the organic layer **15**. The second electrode **19** may be a cathode. A material for forming the second electrode **19** may be metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be formed as the material for forming the second electrode **19**. To manufacture a top emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode **19**.

Hereinbefore, the organic light-emitting device has been described with reference to FIG. 1, but is not limited thereto.

A C₁-C₃₀ alkyl group as used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Detailed examples thereof are a methyl group, an ethyl group, a propyl group, an iso-butyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group.

A C₁-C₃₀ alkoxy group as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₃₀ alkyl group). Detailed examples thereof are a methoxy group, an ethoxy group, and an iso-propyloxy group.

A C₂-C₃₀ alkenyl group as used herein refers to a hydrocarbon group formed by introducing at least one carbon double bond in the middle or at the terminal of the C₂-C₃₀ alkyl group. Detailed examples thereof are an ethenyl group, a propenyl group, and a butenyl group.

A C₂-C₆₀ alkynyl group as used herein refers to a hydrocarbon group formed by substituting at least one carbon triple bond in the middle or at the terminal of the C₂-C₃₀ alkyl group. Detailed examples thereof are an ethynyl group and a propynyl group.

A C₃-C₁₀ cycloalkenyl group as used herein refers to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms. Detailed examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group.

A C₁-C₁₀ heterocycloalkyl group as used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, P, and S as a ring-forming atom and 1 to 10 carbon atoms. Detailed examples thereof are a tetrahydrofuran group, and a tetrahydrothiophenyl group.

A C₃-C₁₀ cycloalkenyl group as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof, and which is not aromatic. Detailed examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group.

A C₁-C₁₀ heterocycloalkenyl group as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Examples of the C₁-C₁₀ heterocycloalkenyl group are a 2,3-dihydrofuran group and a 2,3-dihydrothiophenyl group.

A C₆-C₆₀ aryl group as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Detailed examples of the C₆-C₃₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group includes two or more rings, the rings may be fused to each other.

A C₆-C₆₀ aryloxy group as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₆-C₆₀ aryl group), and a detailed example thereof is a phenoxy group.

A C₆-C₆₀ arylthio group as used herein refers to a monovalent group represented by —SA₁₀₁ (wherein A₁₀₁ is the C₆-C₆₀ aryl group), and a detailed example thereof is a phenylthio group.

A C₁-C₆₀ heteroaryl group as used herein refers to a monovalent carbocyclic aromatic system having at least one heteroatom selected from N, O, P, and S as a ring-forming atom and 1 to 60 carbon atoms. Detailed examples of the C₁-C₆₀ heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group includes two or more rings, the rings may be fused to each other.

A monovalent non-aromatic condensed polycyclic group as used herein refers to a monovalent group that has two or more rings condensed to each other, only carbon atoms as a ring forming atom, and which is non-aromatic in the entire

molecular structure. Detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group.

A monovalent non-aromatic condensed heteropolycyclic group as used herein refers to a monovalent group that has two or more rings condensed to each other, has a heteroatom selected from N, O, P, and S, other than carbon atoms, as a ring forming atom, and which is non-aromatic in the entire molecular structure. Detailed example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group.

The C₆-C₂₀ carbocyclic group as used herein refers to an aliphatic or aromatic group having 6 to 20 carbon atoms. Detailed examples of the C₆-C₂₀ carbocyclic group are a cyclohexane, a cyclohexene, a benzene, a naphthalene. When the C₆-C₂₀ carbocyclic group includes two or more rings, the rings may be fused to each other.

The C₁-C₂₀ heterocyclic group as used herein refers to an aliphatic or aromatic group having a heteroatom selected from N, O, P, and S and 1 to 20 carbon atoms. Detailed examples of the C₁-C₂₀ heterocyclic group are a pyrrolidine, a piperidine, tetrahydrofuran, a pyrrole, a furan, and a thiophene. When the C₁-C₂₀ heterocyclic group includes two or more rings, the rings may be fused to each other.

At least one of substituents of the substituted C₁-C₃₀ alkyl group, substituted C₂-C₃₀ alkenyl group, substituted C₂-C₃₀ alkynyl group, substituted C₁-C₃₀ alkoxy group, substituted C₃-C₆₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₃₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₃₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, substituted monovalent non-aromatic condensed heteropolycyclic group, and substituted C₆-C₂₀ carbocyclic group may be selected from

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₃₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, and C₁-C₃₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, and C₁-C₃₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a C₁-C₃₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a C₁-C₃₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy

group, a C₆-C₃₀ arylthio group, a C₁-C₃₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₃₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, and C₁-C₃₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a C₁-C₃₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

For example, at least one of substituents of the substituted C₁-C₃₀ alkyl group, substituted C₂-C₃₀ alkenyl group, substituted C₂-C₃₀ alkynyl group, substituted C₁-C₃₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₃₀ aryl group, substituted C₆-C₃₀ aryloxy group, substituted C₆-C₃₀ arylthio group, substituted C₁-C₃₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, substituted monovalent non-aromatic condensed heteropolycyclic group, and substituted C₆-C₂₀ carbocyclic group may be selected from

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₃₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, and C₁-C₃₀ alkoxy group;

a C₁-C₃₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, and C₁-C₃₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a C₁-C₃₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzoimidazolyl

group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group and an imidazopyridinyl group, each substituted with at least one selected from a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a phthalazinyl group, a quinoxalinyl group, a cinnolinyl group, and a quinazolinyl group; and

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, and an imidazopyridinyl group, each substituted with at least one selected from a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a phthalazinyl group, a quinoxalinyl group, a cinnolinyl group, and a quinazolinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₃₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, and C₁-C₃₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a C₁-C₃₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

49


matic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

When a group containing a specified number of carbon atoms is substituted with any of the groups listed in the preceding paragraph, the number of carbon atoms in the resulting "substituted" group is defined as the sum of the carbon atoms contained in the original (unsubstituted) group and the carbon atoms (if any) contained in the substituent. For example, when the term "substituted C₁-C₃₀ alkyl" refers to a C₁-C₃₀ alkyl group substituted with C₆-C₃₀ aryl group, the total number of carbon atoms in the resulting aryl substituted alkyl group is C₇-C₆₀.

Hereinafter, a compound and an organic light-emitting device including the compound according to one or more embodiments of the present disclosure will be described in more detail with reference to Synthesis Examples and Examples. However, these examples are for illustrative purposes only and are not intended to limit the scope of the present disclosure. The term "B was used instead of A" used in describing Synthesis Examples may refer to a molar equivalent of 'A' being identical to a molar equivalent of 'B'.

EXAMPLES

Synthesis Example 1: Synthesis of Compound BD01



1) Synthesis of Intermediate 01C

Material 01A (63.3 millimoles (mmol)), Material 01B (75.9 mmol), Pd(PPh₃)₄ (3.2 mmol), K₂CO₃ (189.9 mmol), 200 milliliters (mL) of 1,4-dioxane, and 67 mL of distilled water were added to a 1.0 liter (L) reaction container, and the mixed solution was refluxed in a nitrogen atmosphere for 12

50

hours. After the reaction is completed, the resulting solution was cooled to room temperature and was subjected to an extraction process using dichloromethane and distilled water. An organic layer collected therefrom was washed twice with distilled water, dried by using magnesium sulfate (MgSO₄), and then a solvent was removed therefrom. The crude products obtained therefrom were purified by silica gel column chromatography (using ethyl acetate and n-hexane as an eluent), thereby completing the preparation of Intermediate 01C (26.58 mmol).

LC-MS (m/z): 261.23 [M+1]⁺

2) Synthesis of Compound BD01

Ir(COD)₂BF₄ (5.32 mmol), 01C (26.58 mmol), and glycerol were added together to a reaction container, and the mixed solution was refluxed in a nitrogen atmosphere for 12 hours. After the reaction is completed, the resulting solution was cooled to room temperature, and was subjected to an extraction process using dichloromethane and distilled water. An organic layer collected therefrom was washed twice with distilled water, dried by using magnesium sulfate (MgSO₄), and then a solvent was removed therefrom. The crude products obtained therefrom were purified by silica gel column chromatography (using ethyl acetate and n-hexane as an eluent), thereby completing the preparation of Compound BD01 (1.1 mmol, yield: 20%).

MALDI-TOF(m/z): 970.28 [M+1]⁺

Synthesis Example 2: Synthesis of Compound BD02

Compound BD02 (yield: 22%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Initial material 02A shown in Structural Formulae of Intermediates below was used instead of Initial material 01A.

MALDI-TOF(m/z): 1012.57 [M+1]⁺

Synthesis Example 3: Synthesis of Compound BD03

Compound BD03 (yield: 20%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Initial material 03A shown in Structural Formulae of Intermediates below was used instead of Initial material 01A.

MALDI-TOF(m/z): 1138.23 [M+1]⁺

Synthesis Example 4: Synthesis of Compound BD04

Compound BD04 (yield: 18%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Initial material 04A shown in Structural Formulae of Intermediates below was used instead of Initial material 01A.

MALDI-TOF(m/z): 1138.38 [M+1]⁺

Synthesis Example 5: Synthesis of Compound BD05

Compound BD05 (yield: 15%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Initial material 05A shown in Structural Formulae of Intermediates below was used instead of Initial material 01A.

MALDI-TOF(m/z): 1132.87 [M+1]⁺

51

Synthesis Example 6: Synthesis of Compound
BD06

Compound BD06 (yield: 21%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Materials 03A and 06B shown in Structural Formulae of Intermediates below were used instead of Initial materials 01A and 01B, respectively.

MALDI-TOF(m/z): 1180.22 [M+1]⁺

Synthesis Example 7: Synthesis of Compound
BD07

Compound BD07 (yield: 21%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Materials 03A and 07B shown in Structural Formulae of Intermediates below were used instead of Initial materials 01A and 01B, respectively.

MALDI-TOF(m/z): 1306.46 [M+1]⁺

Synthesis Example 8: Synthesis of Compound
BD08

Compound BD08 (yield: 19%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Materials 03A and 08B shown in Structural Formulae of Intermediates below were used instead of Initial materials 01A and 01B, respectively.

MALDI-TOF(m/z): 1306.22 [M+1]⁺

Synthesis Example 9: Synthesis of Compound
BD09

Compound BD09 (yield: 15%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Materials 03A and 09B shown in Structural Formulae of Intermediates below were used instead of Initial materials 01A and 01B, respectively.

MALDI-TOF(m/z): 1366.82 [M+1]⁺

Synthesis Example 10: Synthesis of Compound
BD10

Compound BD10 (yield: 16%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Materials 03A and 10B shown in Structural Formulae of Intermediates below were used instead of Initial materials 01A and 01B, respectively.

MALDI-TOF(m/z): 1366.52 [M+1]⁺

Synthesis Example 11: Synthesis of Compound
BD11

Compound BD11 (yield: 12%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Materials 03A and 11B shown in Structural Formulae of Intermediates below were used instead of Initial materials 01A and 01B, respectively.

MALDI-TOF(m/z): 1408.51 [M+1]⁺


52

Synthesis Example 12: Synthesis of Compound
BD12


Compound BD12 (yield: 13%) was synthesized in the same manner according to Reaction Scheme 1, except that in synthesizing Compound BD01 of Reaction Scheme 1, Materials 03A and 12B shown in Structural Formulae of Intermediates below were used instead of Initial materials 01A and 01B, respectively.

MALDI-TOF(m/z): 1408.26 [M+1]⁺


Structural Formulae of Intermediates




01A




02A




03A



04A




05A



01B

53

-continued



Evaluation Example 1: Evaluation of HOMO, LUMO, and T₁ Energy Levels of Compounds A, B, and BD01 to BD12

According to methods described in Table 1 below, HOMO, LUMO, and T₁ energy levels of Compounds A, B and BD01 to BD12 were evaluated, and results are shown in Table 2 below.


54

TABLE 1

06B	HOMO energy level evaluation	Cyclic voltammetry (CV) (electrolyte: 0.1M Bu ₄ NClO ₄ /solvent: CH ₂ Cl ₂ / electrode: 3 electrode system (working electrode: GC, standard electrode: Ag/AgCl, auxiliary electrode: Pt)) is used to draw a potential (Volts, V) - current (Amperes, A) graph regarding each compound. Based on reduction onset values of the graph, HOMO energy levels for each compound are calculated. Each compound is diluted with CHCl ₃ to a concentration of 1 × 10 ⁻⁵ molar (M), and Shimadzu UV-350 Spectrometer is used to measure UV absorption spectrum of each compound at room temperature. LUMO energy levels for each compound are calculated using optical band gap (E _g) values of the edge of the absorption spectrum. Each compound is diluted with CH ₂ Cl ₂ to a concentration of 10 millimolar (mM), and ISC PC1 Spectrofluorometer equipped with Xenon light is used to measure photoluminescence spectrum of each compound at room temperature. λ _{max} values measured therefrom are converted to electron Volts (eV) values.
5		
07B	LUMO energy level evaluation	
10		
15		
09B	T ₁ energy level evaluation	
20		
25		

TABLE 2

Compound	HOMO (eV)	LUMO (eV)	T ₁ (eV)	λ _{max} (nm)
30 A	-5.75	-2.85	2.79	444
B	-5.52	-2.93	2.59	479
BD01	-5.68	-3.09	2.62	473
BD02	-5.54	-2.98	2.64	469
BD03	-5.52	-2.94	2.65	468
BD04	-5.53	-2.90	2.65	468
11B 35 BD05	-5.42	-2.73	2.66	466
BD06	-5.47	-2.90	2.65	468
BD07	-5.47	-2.95	2.65	468
BD08	-5.57	-2.98	2.65	468
BD09	-5.56	-2.98	2.64	470
BD10	-5.55	-2.96	2.64	469
40 BD11	-5.68	-2.99	2.65	468
BD12	-5.66	-2.99	2.65	468



Referring to Table 2 above, it was confirmed that Compounds BD01 to BD12 had appropriate electric characteristics to be used as a material for manufacturing the organic light-emitting device.

55

Example 1

A glass substrate on which an indium tin oxide (ITO) electrode (i.e., a first electrode or an anode) was formed to a thickness of 1,500 Angstroms (Å) was ultrasonically washed with distilled water. After the washing using distilled water was completed, the glass substrate was ultrasonically washed with a solvent, such as isopropyl alcohol, acetone, and methanol, and dried. The glass substrate was transported to a plasma washing machine to be cleaned using oxygen plasma for 5 minutes, and then, transported to be mounted on a vacuum depositor.

Compound HT3 was vacuum-deposited on the ITO electrode of the glass substrate to form a first hole injection layer (HIL) having a thickness of 3,500 Å, and Compound HT-D1 was vacuum-deposited on the first HIL to form a second HIL having a thickness of 300 Å. Subsequently, TAPC was vacuum-deposited on the second HIL to form an electron blocking layer (EBL) having a thickness of 100 Å, thereby forming a hole transport region.

mCP as a host and Compound BD01 (7 percent by weight (wt %)) as a dopant were co-deposited on the hole transport region to form an emission layer (EML) having a thickness of 300 Å.

Compound ET3 was vacuum-deposited on the EML to form an electron transport layer (ETL) having a thickness of 250 Å, and ET-D1 (Li_q) was deposited on the ETL to form an electron injection layer (EIL) having a thickness of 5 Å. Then, Al was deposited on the EIL to form a second electrode (i.e., a cathode) having a thickness of 1,000 Å, thereby completing the manufacture of an organic light-emitting device.

Example 2

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD02 was used instead of Compound BD01 as the dopant.

Example 3

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD03 was used instead of Compound BD01 as the dopant.

Example 4

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD04 was used instead of Compound BD01 as the dopant.

Example 5

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD05 was used instead of Compound BD01 as the dopant.

Example 6

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD06 was used instead of Compound BD01 as the dopant.

56

Example 7

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD07 was used instead of Compound BD01 as the dopant.

Example 8

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD08 was used instead of Compound BD01 as the dopant.

Example 9

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD09 was used instead of Compound BD01 as the dopant.

Example 10

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD10 was used instead of Compound BD01 as the dopant.

Example 11


An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD11 was used instead of Compound BD01 as the dopant.

Example 12

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound BD12 was used instead of Compound BD01 as the dopant.

Comparative Example 1

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound A was used instead of Compound BD01 as the dopant.




A

57

Comparative Example 2

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the EML, Compound B was used instead of Compound BD01 as the dopant.



Evaluation Example 2: Evaluation of Characteristics of Organic Light-Emitting Device

The organic light-emitting devices of Examples 1 to 12 and Comparative Examples 1 and 2 were evaluated in terms

58

(2) Measurement of Changes in Brightness According to Changes in Voltage

A brightness measuring meter (Minolta Cs-1000A) was used with respect to the manufactured organic light-emitting devices. Accordingly, brightness values thereof were measured when a voltage was increased from 0 V to 10 V.

(3) Measurement of Emission Efficiency

Based on the brightness values measured according to Evaluation Examples 2(1) and 2(2) and a current density and a voltage, current efficiency (candelas per Ampere, cd/A) of the manufactured organic light-emitting devices in the same current density (i.e., 10 milli Amperes per square centimeter (mA/cm²)) was calculated.

(4) Measurement of Lifespan

Each organic light-emitting device was subjected to measure times taken to reduce the brightness values of Evaluation Example 2(2) to 80%. Here, a lifespan at T₈₀ of the organic light-emitting device of Comparative Example 2 was considered as a basis of 100, and accordingly, relative lifespan data at T₈₀ of the organic light-emitting devices of Examples 1 to 12 and Comparative Example 1 is shown in Table 3 below.

(5) Measurement of EL Spectrum and CIE Color Coordinate

CIE coordinates of the manufactured organic light-emitting devices were obtained from EL spectra thereof which was measured by using a brightness measuring meter (Minolta Cs-1000A) at a brightness of 500 candelas per square meter (cd/m²).

TABLE 3

	Host	Dopant	Driving voltage (V)	Current efficiency (cd/A)	Brightness (cd/m ²)	Comparative lifespan at T ₈₀ (%)	Color coordinate	
							CIEx	CIEy
Example 1	mCP	BD01	3.8	34.3	500	185	0.19	0.41
Example 2	mCP	BD02	3.6	36.5	500	230	0.18	0.37
Example 3	mCP	BD03	3.4	37.6	500	325	0.18	0.36
Example 4	mCP	BD04	3.5	37.1	500	305	0.18	0.36
Example 5	mCP	BD05	3.5	35.0	500	300	0.17	0.34
Example 6	mCP	BD08	3.4	37.7	500	335	0.18	0.36
Example 7	mCP	BD07	3.4	37.9	500	340	0.18	0.36
Example 8	mCP	BD08	3.4	37.7	500	300	0.18	0.35
Example 9	mCP	BD09	3.5	38.5	500	375	0.19	0.39
Example 10	mCP	BD10	3.5	38.8	500	360	0.18	0.39
Example 11	mCP	BD11	3.4	36.8	500	300	0.18	0.36
Example 12	mCP	BD12	3.6	35.7	500	290	0.18	0.36
Comparative Example 1	mCP	A	8.9	8.5	500	0.4	0.15	0.13
Comparative Example 2	mCP	B	4.9	24.2	500	100	0.20	0.43

of changes in current density, changes in brightness, emission efficiency, and lifespan. Detailed measurement methods are described below, and results obtained therefrom are shown in Table 3 below. Lifespan data of the organic light-emitting devices of Comparative Examples 1 and 2 and Examples 1, 2, 3, and 9 is shown in FIG. 2. Electroluminescent (EL) spectra of the organic light-emitting devices of Comparative Examples 1 and 2 and Examples 2 and 3 are shown in FIG. 3.

(1) Measurement of Changes in Current Density According to Changes in Voltage

A voltage-current meter (Keithley 2400) was used with respect to the manufactured organic light-emitting device. Here, a voltage was increased from 0 Volts (V) to 10 V while a current flowing in a unit device was measured. Measurement results are obtained by dividing the measured current value by an area of the unit device.

According to Table 3 above, it was confirmed that the organic light-emitting devices of Examples 1 to 12 exhibited significantly improved driving voltage, current efficiency, and lifespan characteristics, compared to those of the organic light-emitting device of Comparative Example 1.

According to Table 3 above, it was also confirmed that the organic light-emitting devices of Examples 1 to 12 exhibited short wavelengths, compared to the organic light-emitting device of Comparative Example 2. It was also confirmed that the organic light-emitting devices of Examples 1 to 12 exhibited significantly improved driving voltage, current efficiency, and lifespan characteristics, compared to those of the organic light-emitting device of Comparative Example 2.

An organometallic compound according to embodiments may have excellent optical characteristics, electric charac-

59


teristics, and thermal stability, and accordingly, an organic light-emitting device including the organometallic compound may have a low driving voltage, high efficiency, long lifespan, and high color purity characteristics.

It should be understood that exemplary embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each exemplary embodiment should typically be considered as available for other similar features or aspects in other exemplary embodiments.

While one or more exemplary embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present inventive concept as defined by the following claims.

What is claimed is:

1. An organometallic compound represented by Formula 1:



Formula 1

wherein, in Formula 1,

M is selected from a Period 4 transition metal, a Period 5 transition metal, and a Period 6 transition metal, EU, Tb, and Tm;

R₁₁ to R₁₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁)(Q₂)(Q₃); two adjacent groups selected from R₁₁ to R₁₆ are optionally linked to each other to form a saturated or unsaturated ring;

R₁₇ is selected from a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group;

60

Q₁ to Q₃ are each independently selected from a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, and a substituted or unsubstituted C₁-C₆₀ heteroaryl group;

n is selected from 1, 2, and 3;

L₁₁ is selected from a monodentate ligand and a bidentate ligand; and

m is selected from 0, 1, 2, 3, and 4.

2. The organometallic compound of claim 1, wherein M is selected from Ir, Pt, Os, Ru, Rh, Pd, Cu, Ag, Au, Ti, Zr, Hf, Eu, Tb, and Tm.

3. The organometallic compound of claim 1, wherein M is selected from Ir and Pt.

4. The organometallic compound of claim 1, wherein M is Ir.

5. The organometallic compound of claim 1, wherein R₁₁ to R₁₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁)(Q₂)(Q₃);

two adjacent groups selected from of R₁₁ to R₁₆ are optionally linked to each other to form a saturated or unsaturated ring;

R₁₇ is selected from a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group; and

Q₁ to Q₃ are each independently selected from a substituted or unsubstituted C₁-C₆₀ alkyl group and a substituted or unsubstituted C₆-C₆₀ aryl group.

6. The organometallic compound of claim 1, wherein R₁₁ to R₁₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, and a C₁-C₁₀ heterocycloalkyl group,

a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, and a C₁-C₁₀ heterocycloalkyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, and —I;

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, and —Si(Q₁₁)(Q₁₂)(Q₁₃); and

61

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a C₁-C₂₀ alkyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, and —I;

two adjacent groups selected from R₁₁ to R₁₆ are optionally linked to each other to form a saturated or unsaturated ring;

R₁₇ is selected from a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, and a naphthyl group; and

a phenyl group, a naphthyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a C₁-C₂₀ alkyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, and —I; and

Q₁₁ to Q₁₃ are each independently selected from a methyl group, an ethyl group, and a phenyl group.

7. The organometallic compound of claim 1, wherein

R₁₁ to R₁₇ are each independently selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a methoxy group, an ethoxy group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a methoxy group, an ethoxy group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group, each substituted with at least one selected from deuterium and —F;

a phenyl group, a naphthyl group, and a dibenzofuranyl group;

a phenyl group, a naphthyl group, and a dibenzofuranyl group, each substituted with at least one selected from deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, a naphthyl group, and —Si(CH₃)₃; and

62

a phenyl group, a naphthyl group, and a dibenzofuranyl group, each substituted with at least one selected from a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium and —F;

two adjacent groups selected from R₁₁ to R₁₆ are optionally linked to each other to form a saturated or unsaturated ring;

R₁₇ is selected from a phenyl group, a naphthyl group, and a dibenzofuranyl group;

a phenyl group, a naphthyl group, and a dibenzofuranyl group, each substituted with at least one selected from deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, and a naphthyl group; and

a phenyl group, a naphthyl group, and a dibenzofuranyl group, each substituted with at least one selected from a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, an n-pentyl group, a phenyl group, and a naphthyl group, each substituted with at least one selected from deuterium and —F.


8. The organometallic compound of claim 1, wherein

R₁₁ to R₁₇ are each independently selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, a cyclopentyl group, a cyclohexyl group, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, and a group represented by one of Formulae 5-1 to 5-19;


two adjacent groups selected from R₁₁ to R₁₆ are optionally linked to each other to form a saturated or unsaturated ring; and

R₁₇ is selected from groups represented by Formulae 5-1 to 5-19:


5-1



5-2











5-3











63

-continued

**64**

-continued



wherein, in Formulae 5-1 to 5-19,

* indicates a binding site to an adjacent atom; and

Ph indicates a phenyl group.


65

9. The organometallic compound of claim 1, wherein


R₁₁ to R₁₇ are each independently selected from hydro-
gen, deuterium, —F, a methyl group, an ethyl group, an
n-propyl group, an iso-propyl group, an iso-butyl
group, a tert-butyl group, a cyclopentyl group, a cyclo-
hexyl group, —CD₃, —CF₃, and a group represented
by one of Formulae 5-1 to 5-19;

two adjacent groups selected from R₁₁ to R₁₆ are option-
ally linked to each other to form a saturated or unsatu-
rated ring; and


R₁₇ is selected from groups represented by Formulae 5-1
to 5-19:




15
5-1




20
5-2




25
5-3




30
5-4



35
5-5



40
5-6




45
5-7


66

-continued


5-8




5-9




5-10




5-11




5-12




5-13



5-14







5-15



60
65

67

-continued




wherein, in Formulae 5-1 to 5-19,

* indicates a binding site to an adjacent atom; and

Ph indicates a phenyl group.


10. The organometallic compound of claim 1, wherein n is selected from 2 and 3.

11. The organometallic compound of claim 1, wherein L_{11} is a ligand represented by one of Formulae 3-1 and 3-2:



68

-continued



wherein, in Formulae 3-1 and 3-2,

A_{31} and A_{32} are each independently selected from a C_6-C_{20} carbocyclic group and a C_1-C_{20} heterocyclic group;

X_{31} to X_{34} are each independently selected from C and N;

R_{31} to R_{38} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{10} cycloalkyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3-C_{60} cycloalkenyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_1-C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —C(=O)(Q_{31}), —N(Q_{31})(Q_{32}), and —Si(Q_{31})(Q_{32})(Q_{33}); R_{32} and R_{33} are optionally linked to each other to form a saturated or unsaturated ring; R_{35} and R_{36} are optionally linked to each other to form a saturated or unsaturated ring;


b_{34} and b_{38} are each independently selected from 1, 2, 3, 4, 5, and 6; and

* and *' each indicate a binding site to M in Formula 1.

12. The organometallic compound of claim 1, wherein m is selected from 0 and 1.

13. The organometallic compound of claim 1, wherein the organometallic compound represented by Formula 1 is represented by groups represented by Formulae 1-1 to 1-4:

69



wherein, in Formulae 1-1 to 1-4,

A₁₁ to A₁₃ are each independently selected from substituted or unsubstituted C₆-C₂₀ carbocyclic groups; and M, R₁₁ to R₁₇, n, L₁₁, and m are the same as described in connection with Formula 1.

14. The organometallic compound of claim 13, wherein A₁₁ to A₁₃ are each independently selected from a cyclopentene, a cyclohexene, and a benzene.

70

15. The organometallic compound of claim 1, wherein the organometallic compound represented by Formula 1 is selected from groups represented by Formulae 1-21 to 1-24:

1-1

5

10

1-2

15

20

25

1-3

30


35

40


1-4

45


50




1-21



1-22



1-23



1-24


wherein, in Formulae 1-21 to 1-24,

M, R₁₂, R₁₅, R₁₇, n, L₁₁, and m are the same as described in connection with Formula 1.

16. The organometallic compound of claim 15, wherein R₁₂ and R₁₅ are each independently selected from hydrogen, deuterium, —F, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an iso-butyl group, a tert-butyl group, a cyclopentyl group, a cyclohexyl group, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, and a group represented by one of Formulae 5-1 to 5-19; and


R₁₇ is selected from groups represented by Formulae 5-1 to 5-19:

71






72

-continued



73

-continued






wherein, in Formulae 5-1 to 5-19,






* indicates a binding site to an adjacent atom; and

Ph indicates a phenyl group.

17. The organometallic compound of claim 1, wherein the organometallic compound represented by Formula 1 is selected from Compounds BD01 to BD12:

**74**

-continued



BD04

BD05

BD06

BD07

BD08

5-17

5

5-18 10

15

5-19

20

25

30

35

BD01

40

BD02

50


BD03

60

65

75

-continued



BD09

5


10

BD10

15

76

-continued



BD12

18. An organic light-emitting device comprising:

a first electrode;

a second electrode; and

an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer comprises an emission layer and at least one organometallic compound of Formula 1 of claim 1.

19. The organic light-emitting device of claim 18, wherein the emission layer comprises the at least one organometallic compound of Formula 1.

* * * * *

专利名称(译)	有机金属化合物和包括其的有机发光器件		
公开(公告)号	US10290818	公开(公告)日	2019-05-14
申请号	US15/064112	申请日	2016-03-08
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD.		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD.		
[标]发明人	PARK SANGHO KIM WOOK NOH CHANGHO BAE HYEJIN RAI VIRENDRA KUMAR ISHIBE SATOKO CHAE MIYOUNG KRAVCHUK DMITRY		
发明人	PARK, SANGHO KIM, WOOK NOH, CHANGHO BAE, HYEJIN RAI, VIRENDRA KUMAR ISHIBE, SATOKO CHAE, MIYOUNG KRAVCHUK, DMITRY		
IPC分类号	H01L51/00 C07F15/00 C09K11/06 H01L51/50		
CPC分类号	H01L51/0085 C07F15/0033 C09K11/06 H01L51/5016 C09K2211/185		
代理机构(译)	康托科尔伯恩LLP		
优先权	1020150143371 2015-10-14 KR		
其他公开文献	US20170110673A1		
外部链接	Espacenet		

摘要(译)

由式1表示的有机金属化合物：其中，在公式1中，L 11，M，R 11至R 17，m和n与说明书中描述的相同。

