



US009324947B2

(12) **United States Patent**
Sato et al.

(10) **Patent No.:** **US 9,324,947 B2**
(45) **Date of Patent:** **Apr. 26, 2016**

(54) **ORGANIC ELECTROLUMINESCENT DISPLAY DEVICE AND METHOD OF MANUFACTURING THE SAME**

(71) Applicant: **Japan Display Inc.**, Tokyo (JP)

(72) Inventors: **Toshihiro Sato**, Tokyo (JP); **Hironori Toyoda**, Tokyo (JP); **Takeshi Ookawara**, Tokyo (JP)

(73) Assignee: **Japan Display Inc.**, Tokyo (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/480,854**

(22) Filed: **Sep. 9, 2014**

(65) **Prior Publication Data**

US 2015/0069361 A1 Mar. 12, 2015

(30) **Foreign Application Priority Data**

Sep. 9, 2013 (JP) 2013-186146
Sep. 9, 2013 (JP) 2013-186175

(51) **Int. Cl.**

H01L 27/32 (2006.01)
H01L 51/00 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/0015** (2013.01); **H01L 27/322** (2013.01); **H01L 27/3246** (2013.01); **H01L 2227/323** (2013.01)

(58) **Field of Classification Search**

CPC H01L 51/0015; H01L 27/322; H01L 2227/323; H01L 27/3246
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2006/0097263 A1 5/2006 Lee et al.
2006/0244368 A1* 11/2006 Nagayama et al. 313/504
2014/0167018 A1* 6/2014 Okumoto et al. 257/40

FOREIGN PATENT DOCUMENTS

JP 2006-140145 A 6/2006
JP 2009-88320 A 4/2009
JP 2010-034143 A 2/2010
JP 2010-212177 A 9/2010
JP 2013-026394 A 2/2013

OTHER PUBLICATIONS

Korean Office Action for corresponding KR Patent Application No. 10-2014-0116718, dated Feb. 1, 2016.

* cited by examiner

Primary Examiner — Roy Potter

Assistant Examiner — Paul Patton

(74) *Attorney, Agent, or Firm* — Typha IP LLC

(57) **ABSTRACT**

A substrate on which a plurality of pixel electrodes are disposed is prepared. An organic electroluminescent film 22 is formed with the inclusion of a common layer that continuously covers the plural pixel electrodes. A common electrode is formed on the organic electroluminescent film. The common layer is irradiated with an energy ray above areas between the respective adjacent pixel electrodes with the avoidance of irradiation above the plural pixel electrodes. An electric conductivity of the common layer is reduced above the areas between the respective adjacent pixel electrodes, by irradiation of the energy ray. With this configuration, a current leakage can be prevented between the adjacent pixels.

18 Claims, 18 Drawing Sheets




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17





FIG. 18



ORGANIC ELECTROLUMINESCENT DISPLAY DEVICE AND METHOD OF MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

The present application claims priorities from Japanese application JP2013-186146 filed on Sep. 9, 2013, and Japanese application JP2013-186175 filed on Sep. 9, 2013, the contents of which are hereby incorporated by reference into this application.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an organic electroluminescent display device and a method of manufacturing the display device.

2. Description of the Related Art

An organic electroluminescent display device has a structure in which an organic film is sandwiched between an anode and a cathode. Normally, plural organic films are laminated on each other, and include a light emitting layer as one layer. In order to obtain light emission of one color (for example, white) in plural pixels, the organic film forming the light emitting layer is wholly continuously disposed. Alternatively, in order to obtain light emission of plural colors in the plural pixels, the organic film forming the light emitting layer is separated for each of the pixels, but the organic film forming a hole injection layer, an electron injection layer, a hole transport layer, or an electron transport layer is continuously disposed. Even in any case, at least one organic film is continuously disposed over the adjacent pixels.

SUMMARY OF THE INVENTION

In the display device of high quality, the adjacent pixels come closer to each other with the miniaturization of the pixels. For that reason, a current may leak from an electrode of any pixel to adjacent pixels through the continuous organic film. There arises such a problem that the current leakage causes the adjacent pixels to emit light.

JP 2009-88320 A discloses a method of preventing a current leakage. However, the method relates to the prevention of a current leakage between an anode and a cathode in one pixel, which is different from a problem to be solved by the present invention. Also, JP 2010-212177 A and JP 2006-140145 A disclose that a surface of a partition (or an insulating film) is roughened, but fail to disclose an organic film formed on the partition. Therefore, there is no solution to the problem on the current leakage.

An object of the present invention is to prevent a current leakage between the adjacent pixels.

(1) According to the present invention, there is provided a method of manufacturing an organic electroluminescent display device, including the steps of: preparing a substrate on which a plurality of pixel electrodes are disposed; forming an organic electroluminescent film with the inclusion of a common layer that continuously covers the plurality of pixel electrodes; forming a common electrode on the organic electroluminescent film; and irradiating the common layer with an energy ray above areas between the respective adjacent pixel electrodes with the avoidance of irradiation above the organic electroluminescent film, in which an electric conductivity of the common layer is reduced above the areas between the respective adjacent pixel electrodes, by irradiation of the

energy ray. According to the present invention, since the electric conductivity of the common layer of the organic electroluminescent film becomes lower above the areas between the respective adjacent pixel electrodes, the current leakage between the adjacent pixels can be prevented.

(2) The method of manufacturing an organic electroluminescent display device according to the item (1), may further include the step of: forming an insulating layer in the areas between the respective adjacent pixel electrodes so as to rest on ends of the respective pixel electrodes, in which the organic electroluminescent film may be formed to rest on the insulating layer.

(3) In the method of manufacturing an organic electroluminescent display device according to the item (1) or (2), the common layer may be irradiated with the energy ray before forming the common electrode.

(4) In the method of manufacturing an organic electroluminescent display device according to the item (1) or (2), the energy ray may be allowed to pass through the common electrode, and applied to the common layer after forming the common electrode.

(5) The method of manufacturing an organic electroluminescent display device according to the item (1) or (2) may further include the step of forming a sealing film on the common electrode, in which the energy ray may be allowed to pass through the sealing film and the common electrode, and applied to the common layer after forming the sealing film.

(6) In the method of manufacturing an organic electroluminescent display device according to any one of the items (1) to (5), the energy ray may be applied through a mask, and the mask may have a pattern that allows the energy ray to pass above the areas between the respective adjacent pixel electrodes with the avoidance of the energy ray from passing therethrough above the plurality of pixel electrodes.

(7) The method of manufacturing an organic electroluminescent display device according to any one of the items (1) to (5) may further include the step of forming a mask layer that prevents the energy ray from passing therethrough above the organic electroluminescent film, in which the energy ray may be applied through a pattern of the mask layer, and the pattern of the mask layer may allow the energy ray to pass above the areas between the respective adjacent pixel electrodes with the avoidance of the energy ray from passing therethrough above the plurality of pixel electrodes.

(8) According to the present invention, there is provided an organic electroluminescent display device, including: a substrate; a plurality of pixel electrodes that are disposed on the substrate; an organic electroluminescent film that is disposed on the substrate with the inclusion of a common layer which continuously covers the plurality of pixel electrodes; and a common electrode that is disposed on the organic electroluminescent film, in which the common layer has low conductive portions lower in electric conductivity than portions above the plurality of pixel electrodes, above the areas between the respective adjacent pixel electrodes. According to the present invention, since the common layer of the organic electroluminescent film is lower in electric conductivity above the areas between the respective adjacent pixel electrodes, the current leakage between the adjacent pixel electrodes can be prevented.

(9) According to the present invention, there is provided an organic electroluminescent display device, including: a substrate; a plurality of pixel electrodes that are disposed on the substrate; an insulating layer that is disposed in areas between the respective adjacent pixel electrodes so as to rest on ends of the respective pixel electrodes; an organic electroluminescent film that is disposed on the substrate with the inclusion of a

common layer which continuously covers the plurality of pixel electrodes, and the insulating layer; and a common electrode that is disposed over the organic electroluminescent film, in which the insulating layer has an upper surface with a concavo-convex shape having a plurality of concave portions and a plurality of convex portions, in which the common layer includes an upper portion that rests on the respective convex portions of the concavo-convex shape, and a lower portion that rests on the respective concave portions thereof, and in which the upper portion and the lower portion are offset vertically from each other, and at least parts of the upper portion and the lower portion in a thickness direction are discontinuous from each other, and a thickness of the common layer is partially thinned to increase an electric resistance. According to the present invention, the thickness of the common layer is partially thinned to increase the electric resistance above the areas between the respective adjacent pixel electrodes. With the above configuration, a current can be prevented from passing through the common layer, and being leaked between the adjacent pixel electrodes.

(10) In the organic electroluminescent display device according to the item (9), the respective parts of the upper portion and the lower portion in the thickness direction may be continuous to each other.

(11) In the organic electroluminescent display device according to the item (9), the upper portion and the lower portion may be separated from each other.

(12) In the organic electroluminescent display device according to any one of the items (9) to (11), bottom surfaces of the plurality of concave portions may be arrayed along one plane, and upper surfaces of the plurality of convex portions may be arrayed along another plane.

(13) In the organic electroluminescent display device according to any one of the items (9) to (11), bottom surfaces of the plurality of concave portions may be arrayed along one convex curve, and upper surfaces of the plurality of convex portions may be arrayed along another convex curve.

(14) In the organic electroluminescent display device according to any one of the items (9) to (13), the plurality of pixel electrodes may be arrayed in a longitudinal direction and a lateral direction, a planar shape of the respective pixel electrodes may be elongated in one direction with a long axis and a short axis, respective short sides along the short axis may be adjacent to each other in the pixel electrodes adjacent to each other in the longitudinal direction, respective long sides along the long axis may be adjacent to each other in the pixel electrodes adjacent to each other in the lateral direction, and the plurality of concave portions and the plurality of convex portions in the insulating layer may be formed in areas between the adjacent long sides with the avoidance of areas between the adjacent short sides.

(15) According to the present invention, there is provided a method of manufacturing an organic electroluminescent display device, including the steps of: preparing a substrate on which a plurality of pixel electrodes are disposed; forming an insulating layer in areas between the respective adjacent pixel electrodes so as to rest on ends of the respective pixel electrodes; forming an organic electroluminescent film on the substrate with the inclusion of a common layer that continuously covers the plurality of pixel electrodes and the insulating layer; and forming a common electrode on the organic electroluminescent film, in which the insulating layer has an upper surface with a concavo-convex shape having a plurality of concave portions and a plurality of convex portions, in which the common layer includes an upper portion that rests on the respective convex portions of the concavo-convex shape, and a lower portion that rests on the respective concave

portions thereof, and in which the upper portion and the lower portion are offset vertically from each other, and at least parts of the upper portion and the lower portion in a thickness direction are discontinuous from each other, and a thickness of the common layer is partially thinned to increase an electric resistance. According to the present invention, the thickness of the common layer is partially thinned above the areas between the respective adjacent pixel electrodes to increase the electric resistance. With the above configuration, a current can be prevented from passing through the common layer, and being leaked between the adjacent pixel electrodes.

(16) In the method of manufacturing an organic electroluminescent display device according to the item (15), the step of forming the insulating layer having the upper surface with the concavo-convex shape may include the steps of: providing an insulating material; and giving the concavo-convex shape to the insulating material by nanoimprint.

(17) In the method of manufacturing an organic electroluminescent display device according to the item (16), the step of forming the insulating layer having the upper surface with the concavo-convex shape may include the steps of: providing the insulating material to cover the plurality of pixel electrodes; and partially removing the insulating material from above at least a center portion of the respective pixel electrodes after the step of giving the concavo-convex shape.

(18) In the method of manufacturing an organic electroluminescent display device according to the item (17), the step of partially removing the insulating material may be conducted by at least one of photolithography and dry etching.

(19) In the method of manufacturing an organic electroluminescent display device according to the item (17), the insulating material may be recessed and thinned, by the nanoimprint, above at least the center portion of the respective pixel electrodes in the step of giving the concavo-convex shape.

(20) In the method of manufacturing an organic electroluminescent display device according to the item (19), the step of partially removing the insulating material may be conducted by dry etching.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view of an organic electroluminescent display device according to a first embodiment of the present invention;

FIG. 2 is a schematic cross-sectional view taken along a line II-II of the organic electroluminescent display device illustrated in FIG. 1;

FIG. 3 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the first embodiment;

FIG. 4 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 1 of the first embodiment;

FIG. 5 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 2 of the first embodiment;

FIG. 6 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 3 of the first embodiment;

FIG. 7 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 4 of the first embodiment;

FIG. 8 is a perspective view of an organic electroluminescent display device according to a second embodiment of the present invention;

FIG. 9 is a schematic cross-sectional view taken along a line IX-IX of the organic electroluminescent display device illustrated in FIG. 8;

FIG. 10 is a plan view illustrating an array of plural pixel electrodes;

FIG. 11 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the second embodiment of the present invention;

FIG. 12 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the second embodiment of the present invention;

FIG. 13 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the second embodiment of the present invention;

FIG. 14 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the second embodiment of the present invention;

FIG. 15 is a cross-sectional view of an organic electroluminescent display device according to a third embodiment of the present invention;

FIG. 16 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the third embodiment of the present invention;

FIG. 17 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the third embodiment of the present invention; and

FIG. 18 is a diagram illustrating a modification of the third embodiment.

DETAILED DESCRIPTION OF THE INVENTION

Hereinafter embodiments of the present invention will be described with reference to the accompanying drawings. FIG. 1 is a perspective view of an organic electroluminescent display device according to a first embodiment of the present invention. FIG. 2 is a schematic cross-sectional view taken along a line II-II of the organic electroluminescent display device illustrated in FIG. 1.

As illustrated in FIG. 1, the organic electroluminescent display device includes a first substrate 10 having an optical transparency made of glass or the like. The first substrate 10 has an image display area for image display. An integrated circuit chip 12 for driving an element for displaying an image is mounted on the first substrate 10. A flexible wiring substrate 14 is connected to the first substrate 10 for electric connection with an external.

As illustrated in FIG. 2, a circuit layer 16 is disposed on the first substrate 10. The circuit layer 16 includes lines, thin film transistors, and an insulating film not shown. Plural pixel electrodes 18 are disposed on the first substrate 10 (on the circuit layer 16 in the example of FIG. 2). The pixel electrodes 18 are anodes. An insulating layer 20 is disposed in areas between the respective adjacent pixel electrodes 18 so as to rest on ends of the respective pixel electrodes 18. The insulating layer 20 is configured to surround peripheral portions of the respective pixel electrodes 18.

An organic electroluminescent film 22 is disposed over the first substrate 10. The organic electroluminescent film 22 is configured to rest on the plural pixel electrodes 18 and the insulating layer 20. The organic electroluminescent film 22 is formed of plural layers although not shown, includes at least a light emitting layer, and also includes at least one layer of an electron transport layer, a hole transport layer, an electron injection layer, and a hole injection layer. The light emitting layer is configured to emit only light of one color (for example, white).

The organic electroluminescent film 22 includes a common layer 24 that continuously covers the plural pixel electrodes 18. In the example of FIG. 2, the overall organic electroluminescent film 22 is formed of the common layer 24. Alternatively, at least one layer (except for at least one layer) of the organic electroluminescent film 22 including the plural layers is the common layer 24 (for example, the electron injection layer), and the remaining layers including at least one layer may be cut for each of the pixel electrodes 18. In the organic electroluminescent film with a tandem structure including two or more light emitting layers, a charge generation layer for supplying electrons and holes which is arranged between the respective adjacent light emitting layers may be configured by the common layer.

The common layer 24 has low conductive portions 26 lower in electric conductivity than portions above the plural pixel electrodes 18, above the areas between the respective adjacent pixel electrodes 18. The provision of the low conductive portions 26 makes it difficult that carriers (electrons or holes) flow in a spread direction of the common layer 24. Since the low conductive portions 26 are disposed over the insulating layer 20, the carriers are prevented from flowing in the spread direction of the common layer 24 above the insulating layer 20. On the contrary, in portions of the common layer 24 above the plural pixel electrodes 18 (portions except for the low conductive portions 26), a current flows in the thickness direction and the spread direction of the common layer 24.

A common electrode 28 is disposed on the organic electroluminescent film 22. The common electrode 28 is a cathode. A voltage is applied to the pixel electrodes 18 and the common electrode 28 to inject holes and electrons into the organic electroluminescent film 22 from the pixel electrodes 18 and the common electrode 28. The injected holes and electrons are coupled with each other in the light emitting layer to emit light. Since the insulating layer 20 is interposed between the ends of the respective pixel electrodes 18 and the common electrode 28, short-circuiting is prevented between the respective pixel electrodes 18 and the common electrode 28.

According to this embodiment, since the common layer 24 of the organic electroluminescent film 22 is lower in the electric conductivity above the areas between the respective pixel electrodes 18, the current leakage can be prevented between the adjacent pixels. Therefore, pixels adjacent to a pixel into which a current flows emit no light.

A sealing film 42 is disposed on the common electrode 28. The sealing film 42 seals the organic electroluminescent film 22 so as to block moisture. A filter layer 38 is disposed on the sealing film 42.

A second substrate 30 is arranged to face the first substrate 10 with a gap. A color filter layer 32 is disposed on a surface of the second substrate 30 on the first substrate 10 side. The color filter layer 32 includes a black matrix 34 and a colored layer 36. Since the light emitting layer (not shown) of the above-mentioned organic electroluminescent film 22 emits a single color (for example, white), the provision of the color filter layer 32 enables full color display in this embodiment. When the organic electroluminescent film 22 includes plural light emitting layers that emit respective different colors (for example, red, green, and blue), the light emitting layer emits the light of plural colors, thereby making the colored layer 36 unnecessary. The filter layer 38 is disposed between the first substrate 10 and the second substrate 30.

FIG. 3 is a diagram illustrating a method of manufacturing the organic electroluminescent display device according to the first embodiment of the present invention.

In this embodiment, the first substrate **10** on which the plural pixel electrodes **18** are disposed is prepared. The insulating layer **20** is formed in the areas between the respective adjacent pixel electrodes **18** so as to rest on the ends of the respective pixel electrodes **18**. The organic electroluminescent film **22** is formed with the inclusion of the common layer **24** that continuously covers the plural pixel electrodes **18**. The organic electroluminescent film **22** is formed to rest on the insulating layer **20**. The organic electroluminescent film **22** is formed by vapor deposition or sputtering.

Then, the common layer **24** is irradiated with an energy ray (ultraviolet ray, electron ray, infrared ray, etc.). The energy ray is applied above the areas (insulating layer **20**) between the respective adjacent pixel electrodes **18** with the avoidance of upsides of the plural pixel electrodes **18**. With the irradiation of the energy ray, the electric conductivity of the common layer **24** is reduced above the areas between the respective adjacent pixel electrodes **18**. As a result, the low conductive portions **26** are formed in the common layer **24**.

The energy ray is applied through a mask **40**. The mask **40** has a pattern having ribs and openings. The pattern prevents the energy ray energy ray from passing therethrough above the plural pixel electrodes **18**, and allows the energy ray to pass above the areas between the respective adjacent pixel electrodes **18**. Alternatively, the mask **40** is unnecessary if laser scanning using a laser beam is applied.

Subsequently, as illustrated in FIG. 2, the common electrode **28** is formed on the organic electroluminescent film **22**. The common electrode **28** is formed after the common layer **24** has been irradiated with the energy ray. Since the energy ray is applied before the formation of the common electrode **28**, a loss of irradiation energy is low.

According to this embodiment, since the common layer **24** of the organic electroluminescent film **22** becomes low in the electric conductivity above the areas between the respective adjacent pixel electrodes **18**, the current leakage can be prevented between the respective adjacent pixels.

FIG. 4 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 1 of the first embodiment of the present invention. In this example, the common layer **24** is irradiated with the energy ray after the common electrode **28** has been formed. The energy ray is allowed to pass through the common electrode **28**.

FIG. 5 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 2 of the first embodiment of the present invention. In this example, the sealing film **42** is formed on the common electrode **28**. Then, after the sealing film **42** has been formed, the energy ray is allowed to pass through the sealing film **42** and the common electrode **28**, and applied to the common layer **24**. With this configuration, the sealing film **42** can prevent the incorporation of foreign matter.

FIG. 6 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 3 of the first embodiment of the present invention. In this example, the sealing film **42** is formed on the common electrode **28**, and a mask layer **44** is formed on the sealing film **42** (above the organic electroluminescent film **22**). The mask layer **44** is made of, for example, titanium oxide, and made of a material that prevents the energy ray from passing therethrough. The energy ray is applied through a pattern of the mask layer **44**. The pattern of the mask layer **44** prevents the energy ray from passing therethrough above the plural pixel electrodes **18**, and allows the energy ray to pass above the areas between the respective adjacent pixel electrodes **18**.

FIG. 7 is a diagram illustrating a method of manufacturing an organic electroluminescent display device according to a modification 4 of the first embodiment of the present invention. In this example, the mask layer **44** is formed on the common electrode **28** (above the organic electroluminescent film **22**), and the sealing film **42** is formed on the mask layer **44**. The mask layer **44** is made of, for example, titanium oxide, and prevents the energy ray to pass therethrough. The energy ray is applied through the sealing film **42** and the mask layer **44**. The pattern of the mask layer **44** prevents the energy ray from passing therethrough above the plural pixel electrodes **18**, and allows the energy ray to pass therethrough above the areas between the respective adjacent pixel electrodes **18**.

FIG. 8 is a perspective view of an organic electroluminescent display device according to a second embodiment of the present invention. FIG. 9 is a schematic cross-sectional view taken along a line IX-IX of the organic electroluminescent display device illustrated in FIG. 8.

As illustrated in FIG. 8, the organic electroluminescent display device includes a first substrate **110** having an optical transparency made of glass or the like. The first substrate **110** has an image display area for image display. An integrated circuit chip **112** for driving an element for displaying an image is mounted on the first substrate **110**. A flexible wiring substrate **114** is connected to the first substrate **110** for electric connection with an external.

As illustrated in FIG. 9, a circuit layer **116** is disposed on the first substrate **110**. The circuit layer **116** includes lines, thin film transistors, an insulating film and the like not shown. Plural pixel electrodes **118** are disposed on the first substrate **110** (on the circuit layer **116** in the example of FIG. 9). The pixel electrodes **118** are anodes.

FIG. 10 is a plan view illustrating an array of the plural pixel electrode **118**. The plural pixel electrodes **118** are arrayed in a longitudinal direction and a lateral direction. A planar shape of the respective pixel electrodes **118** is elongated in one direction with a long axis and a short axis. In the pixel electrodes **118** adjacent to each other in the longitudinal direction, the respective short sides are adjacent to each other along the short axis. In the pixel electrodes **118** adjacent to each other in the lateral direction, the respective long sides are adjacent to each other along the long axis. The pixel electrodes **118** are electrically connected to lines not shown of the circuit layer **116** by contacts **120**.

As illustrated in FIG. 9, an insulating layer **122** is disposed in the areas between the respective adjacent pixel electrodes **118** so as to rest on ends of the respective pixel electrodes **118**. The insulating layer **122** is configured to surround the peripheries of the respective pixel electrodes **118**. In other words, the insulating layer **122** has openings **122a** that expose the center portions of the pixel electrodes **118** (refer to FIG. 10).

The insulating layer **122** has an upper surface with a concavo-convex shape having plural concave portions **124** and plural convex portions **126**. The concavo-convex shape is formed on a convex curve. Therefore, bottom surfaces of the plural concave portions **124** are arrayed along one convex curve, and upper surfaces of the plural convex portions **126** are arrayed along another convex curve. As illustrated in FIG. 10, the plural concave portions **124** and the plural convex portions **126** of the insulating layer **122** are formed in areas **128** between the respective adjacent long sides with the avoidance of areas between the respective adjacent short sides.

An organic electroluminescent film **130** is disposed over the first substrate **110**. The organic electroluminescent film **130** is configured to rest on the plural pixel electrodes **118** and

the insulating layer 122. The organic electroluminescent film 130 is formed of plural layers although not shown, includes at least a light emitting layer, and also includes at least one layer of an electron transport layer, a hole transport layer, an electron injection layer, and a hole injection layer. The light emitting layer is configured to emit only light of one color (for example, white).

The organic electroluminescent film 130 includes a common layer 132 that continuously covers the plural pixel electrodes 118 and the insulating layer 122. In the example of FIG. 9, the overall organic electroluminescent film 130 is formed of the common layer 132. Alternatively, at least one layer (except for at least one layer) of the organic electroluminescent film 130 including the plural layers is the common layer 132 (for example, the electron injection layer), and the remaining layers including at least one layer may be cut for each of the pixel electrodes 118. In the organic electroluminescent film 130 with a tandem structure including two or more light emitting layers, a charge generation layer for supplying electrons and holes which is arranged between the respective adjacent light emitting layers may be configured by the common layer 132.

The common layer 132 includes an upper portion 134 that rests on the respective convex portions 126 of the concavo-convex shape of the insulating layer 122, and a lower portion 136 that rests on the respective concave portions 124 thereof. The upper portion 134 and the lower portion 136 are offset vertically from each other. Parts of the upper portion 134 and the lower portion 136 in the thickness direction thereof are continuous in the lateral direction, but at least parts of the upper portion 134 and the lower portion 136 in the thickness direction thereof are discontinuous from each other in the lateral direction, to thereby form steps. With the formation of the upper portion 134 and the lower portion 136, the thickness of the common layer 132 is partially thinned to increase an electric resistance of the common layer 132.

A common electrode 138 is disposed on the organic electroluminescent film 130. The common electrode 138 is a cathode. A voltage is applied to the pixel electrodes 118 and the common electrode 138 to inject holes and electrons into the organic electroluminescent film 130 from the pixel electrodes 118 and the common electrode 138. The injected holes and electrons are coupled with each other in the light emitting layer to emit light. Since the insulating layer 122 is interposed between the ends of the pixel electrodes 118 and the common electrode 138, the short-circuiting between the pixel electrodes 118 and the common electrode 138 is prevented.

According to this embodiment, the thickness of the common layer 132 is partially thinned above the areas between the respective adjacent pixel electrodes 118 to increase the electric resistance. With this configuration, a current can be prevented from being leaked between the respective adjacent pixels through the common layer 132.

A sealing film 140 is disposed on the common electrode 138. The sealing film 140 seals the organic electroluminescent film 130 so as to block moisture. A filter layer 142 is disposed on the sealing film 140.

A second substrate 144 is arranged to face the first substrate 110 with a gap. A color filter layer 146 is disposed on a surface of the second substrate 144 on the first substrate 110 side. The color filter layer 146 includes a black matrix 148 and a colored layer 150. Since the light emitting layer (not shown) of the above-mentioned organic electroluminescent film 130 emits a single color (for example, white), the provision of the color filter layer 146 enables full color display in this embodiment. When the organic electroluminescent film 130 includes plural light emitting layers that emit respective different col-

ors (for example, red, green, and blue), the light emitting layer emits the light of plural colors, thereby making the colored layer 150 unnecessary. The filter layer 142 is disposed between the first substrate 110 and the second substrate 144.

FIGS. 11 to 14 are diagrams illustrating a method of manufacturing the organic electroluminescent display device according to the second embodiment of the present invention.

As illustrated in FIG. 11, the first substrate 110 on which the plural pixel electrodes 118 are disposed is prepared, and an insulating material 152 is disposed to cover the plural pixel electrodes 118.

As illustrated in FIG. 12, the insulating material 152 is formed into a concavo-convex shape. For example, the concavo-convex shape is given the insulating material 152 by nanoimprint. In detail, a nanostamper 154 having fine irregularities is pushed against the insulating material 152 to transfer a pattern of the nanostamper 154. In thermal nanoimprint, the insulating material 152 is a thermoplastic resin, and the irregularities of the nanostamper 154 are pressed and transferred to the resin softened by heating to a glass transition temperature or higher.

As illustrated in FIG. 13, the insulating material 152 is partially removed from above at least a center portion of the respective pixel electrodes 118. The partial removal of the insulating material 152 is conducted by at least one of photolithography and dry etching. With the application of the photolithography, as illustrated in FIG. 13, an upper surface of the remaining insulating material 152 is formed into a convex curve shape. In this way, the insulating layer 122 is formed in the areas between the respective adjacent pixel electrodes 118 so as to rest on the ends of the respective pixel electrodes 118. The insulating layer 122 has the upper surface with the concavo-convex shape having the plural concave portions 124 and the plural convex portions 126.

As illustrated in FIG. 14, the organic electroluminescent film 130 is formed over the first substrate 110 with the inclusion of the common layer 132 that continuously covers the plural pixel electrodes 118 and the insulating layer 122. Since the organic electroluminescent film 130 is formed by vapor deposition, the organic electroluminescent film 130 is shaped according to an underlying surface shape. In detail, the above-mentioned common layer 132 is formed with the provision of the upper portion 134 resting on the respective plural convex portions 126 of the concavo-convex shape of the insulating layer 122, and the lower portion 136 resting on the respective plural concave portions 124 thereof. The upper portion 134 and the lower portion 136 are offset vertically from each other. At least parts of the upper portion 134 and the lower portion 136 in the thickness direction thereof are discontinuous from each other in the thickness direction. The common electrode 138 is formed on the organic electroluminescent film 130.

According to this embodiment, the thickness of the common layer 132 is partially thinned above the areas between the respective adjacent pixel electrodes 118 to increase the electric resistance. With this configuration, a current can be prevented from being leaked between the respective adjacent pixels through the common layer 132.

FIG. 15 is a cross-sectional view of an organic electroluminescent display device according to a third embodiment of the present invention. In this embodiment, a concavo-convex shape of an insulating layer 222 is formed on a plane. That is, bottom surfaces of plural concave portions 224 are arrayed along one plane, and upper surfaces of plural convex portions 226 are arrayed along another plane. Plural sealing films 240 (a first sealing film 256, a second sealing film 258, and a third sealing film 260) are disposed on a common electrode 238.

The sealing films **240** seal an organic electroluminescent film **230** to block moisture. The other configurations correspond to the contents described in the above embodiments.

FIGS. **16** and **17** are diagrams illustrating a method of manufacturing the organic electroluminescent display device according to the third embodiment of the present invention.

As illustrated in FIG. **16**, a concavo-convex shape is given an insulating material **252** formed to cover plural pixel electrodes **218** by nanoimprint. In detail, a nanostamper **254** having fine irregularities is pushed against the insulating material **252** to transfer a pattern of the nanostamper **254**. In optical nanoimprint, the insulating material **252** is a photocurable resin, and the irregularities of the nanostamper **254** are pressed and transferred to the resin, and the resin is irradiated with ultraviolet rays, and cured.

Also, the insulating material **252** is recessed and thinned above at least the center portion of the respective pixel electrodes **218** by nanoimprint. In detail, the nanostamper **254** has protrusion areas corresponding to positions at which the insulating material **252** is recessed. The nanostamper **254** has irregularities in the relatively recessed areas.

Then, the insulating material **252** is partially removed from above at least a center portion of the respective pixel electrodes **218** (refer to FIG. **15**). The partial removal of the insulating material **252** is conducted by dry etching.

As illustrated in FIG. **17**, the organic electroluminescent film **230** is formed. As illustrated in FIG. **15**, the common electrode **238** is formed on the organic electroluminescent film **230** to form the plural sealing films **240** (the first sealing film **256**, the second sealing film **258**, and the third sealing film **260**). The subsequent processes correspond to the contents described in the second embodiment.

FIG. **18** is a diagram illustrating a modification of the third embodiment. Also, in this example, a common layer **332** of an organic electroluminescent film **330** has an upper portion **334** that rests on convex portions **326** of an insulating layer **322**, and a lower portion **336** that rests on a concave portion **324**. However, the upper portion **334** and the lower portion **336** are separated from each other. That is, the upper portion **334** and the lower portion **336** are offset vertically from each other, and the overall portion of the upper portion **334** and the lower portion **336** in the thickness direction is discontinuous from each other. If the common layer **332** is thinly formed, the upper portion **334** and the lower portion **336** are separated from each other.

While there have been described what are at present considered to be certain embodiments of the invention, it will be understood that various modifications may be made thereto, and it is intended that the appended claims cover all such modifications as fall within the true spirit and scope of the invention.

What is claimed is:

1. A method of manufacturing an organic electroluminescent display device, comprising the steps of:

- preparing a substrate on which a plurality of pixel electrodes are disposed;
- forming an insulating layer in the areas between the respective adjacent pixel electrodes so as to rest on ends of the respective pixel electrodes,
- forming an organic electroluminescent film to rest on the insulating layer, with the inclusion of a common layer that continuously covers the plurality of pixel electrodes;
- forming a common electrode on the organic electroluminescent film; and

irradiating the common layer with an energy ray above the areas between the respective adjacent pixel electrodes with the avoidance of irradiation above the organic electroluminescent film,

wherein an electric conductivity of the common layer is reduced above the areas between the respective adjacent pixel electrodes, by irradiation of the energy ray.

2. The method of manufacturing an organic electroluminescent display device according to claim **1**, wherein the common layer is irradiated with the energy ray before forming the common electrode.

3. The method of manufacturing an organic electroluminescent display device according to claim **1**, wherein the energy ray is allowed to pass through the common electrode, and applied to the common layer after forming the common electrode.

4. The method of manufacturing an organic electroluminescent display device according to claim **1**, further comprising the step of forming a sealing film on the common electrode,

wherein the energy ray is allowed to pass through the sealing film and the common electrode, and applied to the common layer after forming the sealing film.

5. The method of manufacturing an organic electroluminescent display device according to claim **1**, wherein the energy ray is applied through a mask, and wherein the mask has a pattern that allows the energy ray to pass above the areas between the respective adjacent pixel electrodes with the avoidance of the energy ray from passing therethrough above the plurality of pixel electrodes.

6. The method of manufacturing an organic electroluminescent display device according to claim **1**, further comprising the step of forming a mask layer that prevents the energy ray from passing therethrough above the organic electroluminescent film,

wherein the energy ray is applied through a pattern of the mask layer, and

wherein the pattern of the mask layer allows the energy ray to pass therethrough above the areas between the respective adjacent pixel electrodes with the avoidance of the energy ray from passing therethrough above the plurality of pixel electrodes.

7. An organic electroluminescent display device, comprising:

- a substrate;
 - a plurality of pixel electrodes that are disposed on the substrate;
 - an insulating layer that is disposed in areas between the respective adjacent pixel electrodes so as to rest on ends of the respective pixel electrodes;
 - an organic electroluminescent film that is disposed on the substrate with the inclusion of a common layer which continuously covers the plurality of pixel electrodes, and the insulating layer; and
 - a common electrode that is disposed over the organic electroluminescent film,
- wherein the insulating layer has an upper surface with a concavo-convex shape having a plurality of concave portions and a plurality of convex portions,
- wherein the common layer includes an upper portion that rests on the respective convex portions of the concavo-convex shape, and a lower portion that rests on the respective concave portions thereof, and
- wherein the upper portion and the lower portion are offset vertically from each other, and at least parts of the upper portion and the lower portion in a thickness direction are

13

discontinuous from each other, and a thickness of the common layer is partially thinned to increase an electric resistance.

8. The organic electroluminescent display device according to claim 7, 5
 wherein the respective parts of the upper portion and the lower portion in the thickness direction are continuous to each other.

9. The organic electroluminescent display device according to claim 7, 10
 wherein the upper portion and the lower portion are separated from each other.

10. The organic electroluminescent display device according to claim 7, 15
 wherein bottom surfaces of the plurality of concave portions are arrayed along one plane, and wherein upper surfaces of the plurality of convex portions are arrayed along another plane.

11. The organic electroluminescent display device according to claim 7, 20
 wherein bottom surfaces of the plurality of concave portions are arrayed along one convex curve, and wherein upper surfaces of the plurality of convex portions are arrayed along another convex curve.

12. The organic electroluminescent display device according to claim 7, 25
 wherein the plurality of pixel electrodes are arrayed in a longitudinal direction and a lateral direction, wherein a planar shape of the respective pixel electrodes is elongated in one direction with a long axis and a short axis, 30
 wherein in the pixel electrodes adjacent to each other in the longitudinal direction, respective short sides along the short axis are adjacent to each other, wherein in the pixel electrodes adjacent to each other in the lateral direction, respective long sides along the long axis are adjacent to each other, and 35
 wherein the plurality of concave portions and the plurality of convex portions in the insulating layer are formed in areas between the adjacent long sides with the avoidance of areas between the adjacent short sides. 40

13. A method of manufacturing an organic electroluminescent display device, comprising the steps of: 45
 preparing a substrate on which a plurality of pixel electrodes are disposed;
 forming an insulating layer in areas between the respective adjacent pixel electrodes so as to rest on ends of the respective pixel electrodes;
 forming an organic electroluminescent film on the substrate with the inclusion of a common layer that continuously covers the plurality of pixel electrodes and the insulating layer; and 50

14

forming a common electrode on the organic electroluminescent film,
 wherein the insulating layer has an upper surface with a concavo-convex shape having a plurality of concave portions and a plurality of convex portions,
 wherein the common layer includes an upper portion that rests on the respective convex portions of the concavo-convex shape, and a lower portion that rests on the respective concave portions thereof, and 10
 wherein the upper portion and the lower portion are offset vertically from each other, and at least parts of the upper portion and the lower portion in a thickness direction are discontinuous from each other, and a thickness of the common layer is partially thinned to increase an electric resistance.

14. The method of manufacturing an organic electroluminescent display device according to claim 13, 15
 wherein the step of forming the insulating layer having the upper surface with the concavo-convex shape comprises the steps of:
 providing an insulating material; and
 giving the concavo-convex shape to the insulating material by nanoimprint.

15. The method of manufacturing an organic electroluminescent display device according to claim 14, 20
 wherein the step of forming the insulating layer having the upper surface with the concavo-convex shape comprises the steps of:
 providing the insulating material to cover the plurality of pixel electrodes; and
 partially removing the insulating material from above at least a center portion of the respective pixel electrodes after the step of giving the concavo-convex shape. 25

16. The method of manufacturing an organic electroluminescent display device according to claim 15, 30
 wherein the step of partially removing the insulating material is conducted by at least one of photolithography and dry etching.

17. The method of manufacturing an organic electroluminescent display device according to claim 15, 35
 wherein in the step of giving the concavo-convex shape, the insulating material is recessed and thinned above at least the center portion of the respective pixel electrodes.

18. The method of manufacturing an organic electroluminescent display device according to claim 17, 40
 wherein the step of partially removing the insulating material is conducted by dry etching. 45

* * * * *

专利名称(译)	有机电致发光显示装置及其制造方法		
公开(公告)号	US9324947	公开(公告)日	2016-04-26
申请号	US14/480854	申请日	2014-09-09
[标]申请(专利权)人(译)	株式会社日本显示器		
申请(专利权)人(译)	日本展示INC.		
当前申请(专利权)人(译)	日本展示INC.		
[标]发明人	SATO TOSHIHIRO TOYODA HIRONORI OOKAWARA TAKESHI		
发明人	SATO, TOSHIHIRO TOYODA, HIRONORI OOKAWARA, TAKESHI		
IPC分类号	H01L27/32 H01L51/00		
CPC分类号	H01L51/0015 H01L27/3246 H01L2227/323 H01L27/322 H01L27/3279 H01L51/5243		
审查员(译)	波特, ROY		
助理审查员(译)	巴顿PAUL		
优先权	2013186146 2013-09-09 JP 2013186175 2013-09-09 JP		
其他公开文献	US20150069361A1		
外部链接	Espacenet USPTO		

摘要(译)

准备其上设置多个像素电极的基板。形成有机电致发光膜 22，其包括连续覆盖多个像素电极的公共层。在有机电致发光膜上形成公共电极。在各个相邻像素电极之间的区域上方用能量射线照射公共层，同时避免在多个像素电极上方照射。通过能量射线的照射，公共层的电导率在各个相邻像素电极之间的区域上方减小。利用这种配置，可以防止相邻像素之间的电流泄漏。

