



US010411189B2

(12) **United States Patent**
Kong et al.

(10) **Patent No.:** **US 10,411,189 B2**
(45) **Date of Patent:** **Sep. 10, 2019**

(54) **DISPLAY PANEL HAVING CATHODE CONNECTED TO AUXILIARY ELECTRODE THROUGH CONDUCTIVE SPACERS AND MANUFACTURING METHOD THEREOF, AND DISPLAY DEVICE**

(58) **Field of Classification Search**
CPC H01L 51/0024; H01L 51/5228
See application file for complete search history.

(71) Applicant: **BOE TECHNOLOGY GROUP CO., LTD.**, Beijing (CN)

(56) **References Cited**

(72) Inventors: **Xiangyong Kong**, Beijing (CN);
Dongfang Wang, Beijing (CN)

U.S. PATENT DOCUMENTS

(73) Assignee: **BOE TECHNOLOGY GROUP CO., LTD.**, Beijing (CN)

2004/0031959 A1 2/2004 Park et al.
2004/0185604 A1* 9/2004 Park H01L 27/12
438/149

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(Continued)

FOREIGN PATENT DOCUMENTS

CN 1543269 A 11/2004
CN 1691846 A 11/2005

(Continued)

(21) Appl. No.: **14/422,271**

OTHER PUBLICATIONS

(22) PCT Filed: **Jul. 15, 2014**

2nd Office Action issued in Chinese application No. 201310557149.5 dated Dec. 29, 2015.

(86) PCT No.: **PCT/CN2014/082240**

(Continued)

§ 371 (c)(1),

(2) Date: **Feb. 18, 2015**

Primary Examiner — Kevin Parendo

(87) PCT Pub. No.: **WO2015/067066**

(74) *Attorney, Agent, or Firm* — Nath, Goldberg & Meyer; Joshua B. Goldberg; Daniel Bissing

PCT Pub. Date: **May 14, 2015**

(65) **Prior Publication Data**

US 2016/0035980 A1 Feb. 4, 2016

(30) **Foreign Application Priority Data**

Nov. 11, 2013 (CN) 2013 1 0557149

(51) **Int. Cl.**

H01L 51/00 (2006.01)

H01L 51/52 (2006.01)

(Continued)

(52) **U.S. Cl.**


CPC **H01L 51/0024** (2013.01); **H01L 51/0023** (2013.01); **H01L 51/5036** (2013.01);

(Continued)

(57) **ABSTRACT**

The invention provides a display panel and a manufacturing method thereof, and a display device, belongs to the field of display device manufacturing technology, which can solve the following problem in the existing display device: when light transmits the cathode layer which is thin, has high resistance and thus poor conductivity, the display effect is nonuniform. The display panel of the invention comprises a first substrate and a second substrate which are assembled, wherein the second substrate is provided with an organic electroluminescent device thereon, an anode layer of the organic electroluminescent device is away from the first substrate and an cathode layer thereof is close to the first substrate; and the cathode layer is electrically connected to an auxiliary electrode on a light entering surface of the first

(Continued)



substrate through a plurality of conductive spacers spaced at certain intervals, wherein the cathode layer is a transparent electrode layer.

12 Claims, 3 Drawing Sheets

2005/0140287	A1	6/2005	Ko	
2005/0212413	A1	9/2005	Matsuura et al.	
2007/0108899	A1 *	5/2007	Jung H01L 27/3276 313/506
2010/0097295	A1 *	4/2010	Kwak H01L 27/322 345/32

FOREIGN PATENT DOCUMENTS

CN	1967864	A	5/2007
CN	101728419	A	6/2010
CN	103545345	A	1/2014
KR	20050024033	A	3/2005
WO	2013062059	A1	5/2013

OTHER PUBLICATIONS

Notification of the First Office Action dated Jul. 15, 2015 corresponding to Chinese application No. 201310557149.5.
 Written Opinion of the International Searching Authority dated Oct. 21, 2014 corresponding to International application No. PCT/CN2014/082240.
 PCT International Search Report for Application No. PCT/CN2014/082240.

* cited by examiner

- (51) **Int. Cl.**
H01L 51/50 (2006.01)
H01L 51/56 (2006.01)
H01L 27/32 (2006.01)
- (52) **U.S. Cl.**
 CPC *H01L 51/525* (2013.01); *H01L 51/5218* (2013.01); *H01L 51/5228* (2013.01); *H01L 51/5234* (2013.01); *H01L 51/5271* (2013.01); *H01L 51/56* (2013.01); *H01L 27/322* (2013.01); *H01L 2251/5315* (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

2004/0227459	A1	11/2004	Imura
2005/0051776	A1 *	3/2005	Miyagi G09G 3/3233 257/72




Fig. 1
(Prior Art)




Fig. 2




Fig. 3




Fig. 4




Fig. 5

**DISPLAY PANEL HAVING CATHODE
CONNECTED TO AUXILIARY ELECTRODE
THROUGH CONDUCTIVE SPACERS AND
MANUFACTURING METHOD THEREOF,
AND DISPLAY DEVICE**

This is a National Phase Application filed under 35 U.S.C. 371 as a national stage of PCT/CN2014/082240, filed Jul. 15, 2014, an application claiming the benefit to Chinese Application No. 201310557149.5, filed Nov. 11, 2013; the content of each of which is hereby incorporated by reference in its entirety.

FIELD OF THE INVENTION

The present invention relates to the field of the display device manufacturing technology, and particular to a display panel and a manufacturing method thereof, and a display device.

BACKGROUND OF THE INVENTION

In recent years, the display technology has been developed rapidly, and especially the organic electroluminescent device (OLED) display technology has been developed rapidly. Currently, there are mainly two kinds of technologies for colorizing large-sized white organic electroluminescent devices (WOLEDs), one of which is to form a display panel by directly manufacturing color filter patterns on a second substrate (COA, color filter on array), and the other of which is to form a display panel by assembling a first substrate and a second substrate, and providing spacers arranged spaced at certain intervals between the first substrate and the second substrate, wherein the spacers are used to support the first substrate and the second substrate.

As shown in FIG. 1, for a display panel consisting of a second substrate **102** and a first substrate **101**, the first substrate **101** includes black matrixes **108**, color filter patterns **109** of various colors provided above the black matrixes **108**, and a planarization layer **110** provided above the black matrixes **108** and the color filter patterns **109** of various colors; a drain of a thin film transistor **103** on the second substrate **102** is electrically connected to an anode layer **104** of an organic electroluminescent device, the anode layer **104** is provided at one side close to the second substrate **102**, a cathode layer **106** of the organic electroluminescent device is provided at one side away from the second substrate **102**, a light emitting layer **105** is provided between the anode layer **104** and the cathode layer **106**, and a plurality of organic electroluminescent devices are provided on the second substrate **102**, the anode layers **104** of the organic electroluminescent devices are controlled by different thin film transistors **103** respectively, all of the cathode layers **106** are connected together, spacers **107** supports the first substrate **101** and the second substrate **102** therebetween, at this time, light emitted from the organic electroluminescent devices transmits the cathode layer **106**, that is to say, the organic electroluminescent device is of a top-emitting type, the cathode layer **106** is commonly made of conductive material such as silver (Ag) and aluminium (Al), light transmission of which is low, thus it is required to select very thin conductive material so that light may transmit. It should be noted that, after the first substrate **101** and the second substrate **102** are manufactured separately, the first substrate **101** and the second substrate **102** are assembled to form a display panel, wherein the spacers **106** may be formed on the first substrate **101** or on the second substrate **102**.

The inventor finds that, in the organic electroluminescent device of top-emitting type adopted in the above display panel, the cathode layer **106** is thin due to requirement on transmittance, resulting in the fact that the cathode layer **106** has large resistance, and poor conductivity, therefore the light emitting performance of the organic electroluminescent device is poor, and the display effect is nonuniform.

SUMMARY OF THE INVENTION

In view of the above disadvantages existing in the current display panel, the technical problem to be solved by the present invention is to provide a display panel and a manufacturing method thereof, and a display device, which can enhance the conductivity of the cathode layer.

A solution adopted to solve the above problem is a display panel, which comprises: a first substrate and a second substrate which are assembled, wherein the second substrate is provided with an organic electroluminescent device thereon, an anode layer of the organic electroluminescent device is away from the first substrate and a cathode layer thereof is closed to the first substrate; and the cathode layer of the organic electroluminescent device is electrically connected to an auxiliary electrode on a light entering surface of the first substrate through a plurality of conductive spacers spaced at certain intervals, and the cathode layer is a transparent electrode layer.

The auxiliary electrode is added into the display panel and is connected to the cathode layer through the conductive spacers, enhancing the conductivity of the cathode layer, and thus enhancing the light emitting performance of the organic electroluminescent device.

Preferably, the auxiliary electrode has a resistance smaller than that of the cathode layer of the organic electroluminescent device.

Preferably, the spacer is made of any one of polyacetylene, PPV (Poly-(P-phenylenevinyle)), polythiophene, poly p-phenylene, polypyrrole, polyaniline, poly(3,4-ethylenedioxythiophene) or combination thereof.

Preferably, the conductive spacers are provided on the first substrate or the second substrate.

Preferably, the conductive spacer includes a first conductive spacer and a second conductive spacer which are connected to each other; the first conductive spacer is provided on the first substrate and the second conductive spacer is provided on the second substrate, or the first conductive spacer is provided on the second substrate and the second conductive spacer is provided on the first substrate.

Preferably, a surface area of an end of the first conductive spacer towards the second conductive spacer is smaller than that of an end of the second conductive spacer towards the first conductive spacer, or the surface area of an end of the first conductive spacer towards the second conductive spacer is larger than that of an end of the second conductive spacer towards the first conductive spacer.

Preferably, the auxiliary electrode is a plate-shaped auxiliary electrode which is transparent and conductive.

Further preferably, the plate-shaped auxiliary electrode is made of any one of indium tin oxide, indium gallium zinc oxide, and indium zinc oxide.

Preferably, the auxiliary electrode is a grid-shaped auxiliary electrode and provided in a non-display region.

Further preferably, the grid-shaped auxiliary electrode is made of any one of aluminium (Al), molybdenum (Mo), copper (Cu), silver (Ag), chrome (Cr) and gold (Au) or combination thereof.

Preferably, a reflective layer is provided below the anode layer of the organic electroluminescent device, and the reflective layer is used to reflect light emitted from the organic electroluminescent device to the cathode layer of the organic electroluminescent device.

Preferably, the organic electroluminescent device is an organic electroluminescent device emitting white light.

Further preferably, the first substrate is provided with red filter patterns, green filter patterns and blue filter patterns spaced at certain intervals thereon.

Preferably, the organic electroluminescent device includes an organic electroluminescent device emitting red light, green light or blue light.

A solution adopted to solve the above problem in the invention is a manufacturing method of a display panel, which comprises steps of:

forming a pattern including an auxiliary electrode on a light entering surface of a first substrate by a patterning process;

forming a pattern including conductive spacers on the auxiliary electrode by a patterning process; and

assembling the first substrate and a second substrate, so that the auxiliary electrode is electrically connected to a cathode layer of an organic electroluminescent device through the conductive spacers, wherein the cathode layer is a transparent electrode layer.

A solution adopted to solve the above problem in the invention is manufacturing method of a display panel, which comprises steps of:

forming a pattern including an auxiliary electrode on a light entering surface of a first substrate by a patterning process, and forming a pattern including conductive spacers on a cathode layer of a second substrate at positions corresponding to the auxiliary electrode by a patterning process; and

assembling the first substrate and a second substrate, so that the auxiliary electrode is electrically connected to the cathode layer of an organic electroluminescent device through the conductive spacers, wherein the cathode layer is a transparent electrode layer.

A solution adopted to solve the above problem in the invention is a manufacturing method of a display panel, which comprises steps of:

forming a pattern including an auxiliary electrode on a light entering surface of a first substrate by a patterning process, forming a pattern including first conductive spacers on the auxiliary electrode by a patterning process, and forming a pattern including second conductive spacers on a cathode layer of a second substrate at positions corresponding to the first conductive spacers by a patterning process; and

assembling the first substrate and the second substrate, so that the auxiliary electrode is electrically connected to the cathode layer of an organic electroluminescent device through the first conductive spacers and the second conductive spacers, wherein the cathode layer is a transparent electrode layer.

A solution adopted to solve the above problem in the invention is a display device comprising the above display panel.

Since the display device in the invention comprises the above display panel, it has better display effect.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a structural diagram of a display panel in the prior art;

FIG. 2 is a structural diagram of a display panel according to embodiment 1 of the invention;

FIG. 3 a top view of an auxiliary electrode, which is a grid-shaped auxiliary electrode, of the display panel according to embodiment 1 of the invention;

FIG. 4 is another structural diagram of a display panel according to embodiment 1 of the invention; and

FIG. 5 is a structural diagram of a display panel manufactured by a manufacturing method of a display panel according to embodiment 4 of the invention.

Reference signs: **101** first substrate; **102** second substrate; **103** thin film transistor; **104** pixel electrode layer (anode layer); **105** light emitting layer; **106** cathode layer; **107** (conductive) spacer; **1071** first conductive spacer; **1072** second conductive spacer; **108** black matrix; **109** color filter pattern; **110** planarization layer; **111** (plate/grid-shaped) auxiliary electrode.

DETAILED DESCRIPTION OF EMBODIMENTS

In order to make persons skilled in the art better understand the solutions of the invention, the invention will be described below in detail in conjunction with drawings and embodiments.

Embodiment 1

As shown in FIGS. 2, 3, 4 and 5, the present embodiment provides a display panel, which comprises a first substrate **101** and a second substrate **102** which are assembled, the second substrate **102** is provided with organic electroluminescent devices thereon, an anode layer **104** of the organic electroluminescent device is away from the first substrate **101** and a cathode layer **106** thereof is close to the first substrate **101**; and the cathode layer **106** of the organic electroluminescent device is electrically connected to an auxiliary electrode **111** on a light entering surface of the first substrate **101** through a plurality of conductive spacers **107** spaced at certain intervals, wherein the cathode layer **106** is a transparent electrode layer.

The second substrate **102** of the display panel of the embodiment includes a plurality of organic electroluminescent devices, an anode layer **104** of each of the organic electroluminescent devices is separately controlled by a separated thin film transistor **103**, cathode layers **106** of all of the organic electroluminescent devices are connected together, and the light entering surface of the first substrate **101** is provided with the auxiliary electrode **111**, which is electrically connected to the cathode layers **106** of the organic electroluminescent devices through the conductive spacers **107** so as to improve the conductivity of the cathode layers **106**, and thus improve the luminance uniformity of the display panel.

Preferably, the auxiliary electrode **111** has a resistance smaller than that of the cathode layer **106** of the organic electroluminescent device, thus an IR drop of the cathode layer **106** may be prevented or decreased, the conductivity of the cathode layer **106** is enhanced due to the auxiliary electrode, and thus the luminance uniformity of the display panel may be improved.

The conductive spacer **107** is preferably made of any one of polyacetylene, PPV, polythiophene, poly p-phenylene, polypyrrole, polyaniline, poly(3,4-ethylenedioxythiophene) or combination thereof. Of course, the invention is not limited thereto. The conductive spacer **107** may be made of any other material, so long as it is conductive and plays a supporting role.

The conductive spacer **107** may be of an integrated structure, and may be provided on the first substrate **101** or the second substrate **102** for supporting the first substrate **101** and the second substrate **102** when assembled. The conductive spacer **107** may preferably include, as shown in FIG. **5**, a first conductive spacer **1071** and a second conductive spacer **1072** which are connected to each other, for example, the first conductive spacer **1071** is provided on the first substrate **101**, and the second conductive spacer **1072** is provided on the second substrate **102**, and a surface area of an end of the first conductive spacer **1071** towards the second conductive spacer **1072** is smaller than that of an end of the second conductive spacer **1072** towards the first conductive spacer **1071**. At this time, compared to the integrated conductive spacer **107**, the height of the first conductive spacer **1071** or the second conductive spacer **1072** is relatively small, therefore, the first conductive spacer **1071** and the second conductive spacer **1072** are easily manufactured, and since the surface area of an end of the first conductive spacer **1071** towards the second conductive spacer **1072** is smaller than that of an end of the second conductive spacer **1072** towards the first conductive spacer **1071**, the first substrate **101** and the second substrate **102** are assembled more stably. It should be noted that, it is possible to make the surface area of an end of the first conductive spacer **1071** towards the second conductive spacer **1072** be larger than that of an end of the second conductive spacer **1072** towards the first conductive spacer **1071**, and it can be easily conceived that the stability of the assemblage of the first substrate **101** and the second substrate **102** with the support of the first conductive spacer **1071** and the second conductive spacer **1072** can be ensured, so long as one of surface areas of contacting surfaces of the first conductive spacer **1071** and the second conductive spacer **1072** is made be larger than the other one.

The auxiliary electrode **111** is preferably a plate-shaped auxiliary electrode **111** which is transparent and conductive. The plate-shaped auxiliary electrode **111** is made of any one of indium tin oxide, indium gallium zinc oxide, and indium zinc oxide, and of course, other transparent materials are also possible.

As shown in FIG. **3**, the auxiliary electrode **111** is preferably a grid-shaped auxiliary electrode and provided in a non-display region (that is, regions corresponding to the black matrixes **108** on the first substrate **101**), and may be preferably made of any one of Al, Mo, Cu, Ag, Cr and Au or combination thereof. Of course, any other conductive material with low resistance is possible, and the thickness of the auxiliary electrode **111** is in a range of 50-300 nm. At this time, the grid-shaped auxiliary electrode **111** is preferably made of opaque conductive material, and in this case, it is possible that no black matrix **108** is provided on the first substrate **101**, and the grid-shaped auxiliary electrode **111** acts as the black matrix **108**, the resistance of the material of the grid-shaped auxiliary electrode **111** is lower than that of the cathode, which may improve the conductivity of the cathode layer **106**. Of course, bar-shaped auxiliary electrodes **111** are also possible and provided in the non-display region, and all of the bar-shaped auxiliary electrodes may be electrically connected to each other through at least one connection stripe.

Preferably, a reflective layer is provided below the anode layer **104** of the organic electroluminescent device, and the reflective layer is used to reflect light emitted from the organic electroluminescent device to the cathode layer **106** of the organic electroluminescent device. Specifically, the reflective layer may be provided on the anode layer **104** of

the organic electroluminescent device at a side away from the first substrate **101**, but position of the reflective layer is not limited thereto. The reflective layer may be made of a reflective material, such as Ag and Al. Since light frequently transmits the anode layer **104**, by adding the reflective layer, light incident onto the anode layer **104** may be reflected to the cathode layer side, and outgoes from the cathode layer **106** of the organic electroluminescent device, therefore, utilization of the emergent light of the organic electroluminescent device may be increased, and in a case of other conditions being the same, power consumption of the organic electroluminescent device may be reduced.

Preferably, the organic electroluminescent device is an organic electroluminescent device emitting white light. As to the white light-emitting organic electroluminescent device, patterns **109** of red filter, green filter and blue filter are provided on the first substrate **101** at a side close to the second substrate **102**, and of course, the organic electroluminescent device may preferably be an organic electroluminescent device emitting red light, green light or blue light.

It should be noted that, in the above description of the present embodiment, in order to better understand the invention, description is made by taking the first substrate **101** being a color filter substrate and the second substrate **102** being an array substrate as an example. However, the invention is not limited thereto, for example, the organic electroluminescent device may be a colorized organic electroluminescent device, which can emit red light, green light or blue light, at this time, it is unnecessary to manufacture the color filter patterns **109**, and the first substrate **101** may be a transparent substrate and assembled with the second substrate **102** to form a display panel.

Embodiment 2

The present embodiment provides a manufacturing method of a display panel, which comprises following steps:

Step 1, forming a pattern including an auxiliary electrode **111** on a light entering surface of a first substrate **101** by a patterning process.

Step 2, forming a pattern including conductive spacers **107** on the auxiliary electrode **111** by a patterning process; and

Step 3, assembling the first substrate **101** and a second substrate **102**, so that the auxiliary electrode **111** is electrically connected to cathode layers **106** of organic electroluminescent devices through the conductive spacers **107**, wherein the cathode layer **106** is a transparent electrode layer.

Specifically, first, black matrixes (BM) are formed on a first base by coating, exposure, development and baking processes and the like, red (R), green (G) and blue (B) color filter patterns **109** are formed above the black matrixes **108** respectively by coating, exposure, development and baking processes and the like, then a planarization layer **110** is coated, and a layer of metal or metal oxide is deposited on the planarization layer **110** by sputtering, Plasma Enhanced Chemical Vapor Deposition (PECVD) method, evaporation or the like and then a patterning process is performed thereon to form a pattern including the auxiliary electrode **111**, and conductive spacers **107** are formed above the auxiliary electrode **111** by a patterning process. In a case of the auxiliary electrode **111** being made of a transparent material, it may be plate-shaped or of other shape. In a case of the auxiliary electrode **111** being made of an opaque material, in order to enable light to transmit, the auxiliary electrode **111** is preferably grid-shaped and provided in a

non-display region so as to ensure light emitted from the organic electroluminescent devices may transmit the first substrate **101**, at this time, it is possible that no black matrix **108** is provided on the first substrate **101**. Of course, it is also possible that the auxiliary electrode **111** may be formed as bar-shaped auxiliary electrodes, and all of the bar-shaped auxiliary electrodes are electrically connected together through at least one connection stripe.

The plate-shaped auxiliary electrode **111** is made of any one of indium tin oxide, indium gallium zinc oxide, and indium zinc oxide, or may be made of other transparent conductive material. The grid-shaped auxiliary electrode **111** may be made of any one of aluminium (Al), molybdenum (Mo), copper (Cu), silver (Ag), chrome (Cr) and gold (Au) or combination thereof, of course, material of the plate-shaped auxiliary electrode is not limited thereto, other opaque conductive materials are possible, and the plate-shaped auxiliary electrode may have a thickness of 50-300 nm.

The conductive spacer **107** may be made of a conductive organic material, such as polyacetylene, PPV (Poly-(P-phenylenevinyle)), PTH (polythiophenes), PPP (poly p-phenylene), PPy (polypyrroles), PANI (polyaniline), PEDOT (poly(3,4-ethylenedioxythiophene)) or combination thereof.

Next, a gate is formed on a second base by sputtering, exposure, development, etching, peeling off processes and the like, a gate insulation layer is formed above the gate by a plasma enhanced chemical vapor deposition method and the like, an active layer of oxide semiconductor is formed above the gate insulation layer by sputtering, exposure, development, etching, peeling off processes and the like, an etch stopper layer (ESL) is formed above the active layer by sputtering, exposure, development, etching, peeling off processes and the like, a drain and a source are formed above the etch stopper layer by sputtering, exposure, development, etching, peeling off processes and the like so that the drain and the source are connected to the active layer of oxide semiconductor through contact vias passing through the etch stopper layer, a passivation protection layer is formed above the drain and the source, a pixel electrode layer **104** is formed above the passivation protection layer so that the pixel electrode layer **104** is connected to the drain through a via passing through the passivation protection layer, a pixel defining layer (PDL) is formed above the pixel electrode layer **104** which is the anode layer **104** of the organic electroluminescent device, and a light emitting layer **105** and a cathode layer **106** required for the light emitting layer **105** are evaporated on the pixel electrode layer **104**.

The gate may be of a single-layered structure or a multilayered composite laminated structure made of one or more of molybdenum (Mo), alloy of molybdenum and niobium (MoNb), aluminum (Al), alloy of aluminum and neodymium (AlNd), titanium (Ti) and copper (Cu), and preferably is of a single-layered structure or a multilayered composite laminated structure made of Mo, Al or alloy containing Mo and Al. Thickness of the gate is 100 nm~500 nm.

In the present embodiment, the gate insulation layer may be a multilayered composite film made of one or two of silicon oxide (SiOx), silicon nitride (SiNx), hafnium oxide (HfOx), silicon nitrogen oxide (SiON) and aluminum oxide (AlOx), and, and thickness thereof is controlled to be about 100-600 nm and adjustable as desired.

The active layer of oxide semiconductor may be a thin film made of elements including Indium (In), gallium (Ga), zinc (Zn), oxygen (O), stannum (Sn) etc. and is formed by sputtering, wherein the thin film must be made of oxygen

element and two or more of the above elements, such as indium gallium zinc oxide (IGZO), indium zinc oxide (IZO), indium tin oxide (InSnO), indium gallium stannum oxide (InGaSnO) and the like. The active layer of oxide semiconductor is preferably made of IGZO and IZO, and thickness thereof is preferably 10-100 nm.

The etch stopper layer may be made of a material, such as SiOx, SiNx, HfOx, SiON, AlOx etc. and may be a multilayered film made of two or three of the above materials.

The source and the drain may be a single-layered structure or a multilayered composite laminated structure made of one or more of Mo, MoNb, Al, AlNd, Ti and Cu, and preferably is of a single-layered film or a multilayered composite film made of Mo, Al or alloy containing Mo and Al.

The passivation protection layer may be made of one of SiOx, SiNx, HfOx, SiON, AlOx and organ materials or combination thereof.

The pixel electrode layer **104**, i.e., the anode layer **104** of the organic electroluminescent device, may be made of ITO (indium tin oxide), of course it also may be made of other transparent conductive material. Since the pixel electrode layer **104** is transparent, it is necessary to provide a reflective layer under the anode layer **104** to reflect light emitted from the organic electroluminescent device to the cathode layer **106** side, and the reflective layer may be made of a reflective metal material such as Ag.

The pixel defining layer may be an organic insulating layer with lower moisture and has photosensitive property similar to that of the common photoresist.

The light emitting layer **105** is made of an organ material, which is determined as desired.

The cathode layer **106** may be made of a metal material with low work function, such as Al or Ag, and is thin enough to enable light to transmit.

Finally, the resultant first substrate **101** and the resultant second substrate **102** are encapsulated to form a display panel.

It should be noted that, there is no sequencing for manufacturing the first substrate **101** and manufacturing the auxiliary electrode **111** and the conductive spacers **107** on the first substrate **101**, and manufacturing the second substrate **102** (including the thin film transistors **103** and the organic electroluminescent devices thereon), the above description is just an example, and it is also possible to first manufacture the second substrate **102**, then manufacture the first substrate **101** and manufacture the auxiliary electrode **111** and the conductive spacers **107** on the first substrate **101**.

In the display panel manufactured by the manufacturing method provided by the present embodiment, the cathode layer **106** thereof is connected to the auxiliary electrode **111** through the conductive spacers **107**, and the conductivity of the cathode layer **106** is improved significantly, and thus the luminance uniformity of the display panel is improved.

It should be noted that, in the present embodiment, the first substrate **101** is a color filter substrate, and the second substrate **102** is an array substrate, but the invention is not limited thereto. For example, when the manufactured organic electroluminescent device is a colorized organic electroluminescent device which may emit red light, green light or blue light, it is unnecessary to manufacture color filter patterns **109**, and at this time, the first substrate **101** may be a transparent substrate, and a display panel may be formed by assembling the first substrate **101** and the second substrate **102**. The above structures may be set as desired.

Embodiment 3

The present embodiment provides a manufacturing method of a display panel, which comprises following steps:

Step 1, forming a pattern including an auxiliary electrode on a light entering surface of a first substrate **101** by a patterning process.

Step 2, forming a pattern including conductive spacers **107** on a cathode layer **106** of a second substrate **102** at positions corresponding to the auxiliary electrode **111** by a patterning process.

Step 3, assembling the first substrate **101** and a second substrate **102**, so that the auxiliary electrode **111** is electrically connected to the cathode layer **106** of the organic electroluminescent device through the conductive spacers **107**, wherein the cathode layer **106** is a transparent electrode layer.

It should be noted that, the sequence of the step 1 and the step 2 may be reversed, that is to say, it is also possible to form the conductive spacers **107** on the cathode layer **106** of the second substrate **102** first, then form the auxiliary electrode **111** on a light entering surface of a first substrate **101** at positions corresponding to the conductive spacers **107**.

In the manufacturing method of a display panel provide by the present embodiment, the conductive spacers **107** are provided on the second substrate **102**, other procedures are the same as those in the manufacturing method of a display panel provide by the embodiment 1, and will not be repeatedly described herein.

In the display panel manufactured by the manufacturing method provided by the present embodiment, the cathode layer thereof is connected to the auxiliary electrode **111** through the conductive spacers **107**, the conductivity of the cathode layer **106** is improved remarkably, and thus the luminance uniformity of the display panel is improved.

Embodiment 4

As shown in FIG. 5, the present embodiment provides a manufacturing method of a display panel, which comprises following steps.

Step 1, forming a pattern including an auxiliary electrode on a light entering surface of a first substrate **101** by a patterning process, and forming a pattern including first conductive spacers **1071** on the auxiliary electrode **111** by a patterning process.

Step 2, forming a pattern including second conductive spacers **1072** on a cathode layer **106** of a second substrate **102** at positions corresponding to the first conductive spacers **1071** by a patterning process.

Step 3, assembling the first substrate **101** and a second substrate **102**, so that the auxiliary electrode **111** is electrically connected to the cathode layers **106** of the organic electroluminescent device through the first conductive spacers **1071** and the second conductive spacers **1072**, wherein the cathode layer **106** is a transparent electrode layer. A display panel as shown in FIG. 5 is obtained.

It should be noted that, the sequence of the step 1 and the step 2 may be reversed, that is to say, it is also possible to form the second conductive spacers **1072** on the second substrate **102** first, and then form the first conductive spacers **1071** above the auxiliary electrode **111** on the light entering surface of the first substrate **101** at positions corresponding to the second conductive spacers **1072**.

In the manufacturing method of a display panel provide by the present embodiment, the conductive spacer **107** is divided into a first conductive spacer **1071** and a second conductive spacer **1072**, which are manufactured on the first substrate **101** and the second substrate **102** respectively, at this time, compared to the height of the conductive spacer

107 in the embodiment 1 or 2, the height of the first conductive spacer **1071** or the second conductive spacer **1072** in the present embodiment is lower, thus the first conductive spacer **1071** and the second conductive spacer **1072** are easy to be manufactured. One of the first conductive spacer **1071** and the second conductive spacer **1072** is wider than the other one, that is, the surface area of an end of one of the first conductive spacer **1071** and the second conductive spacer **1072** towards the other one of the first conductive spacer **1071** and the second conductive spacer **1072** is larger than that of an end of the other one towards the one, so that the first substrate **101** and the second substrate **102** are assembled more stably. Other manufacturing procedures of the manufacturing method of the present embodiment are the same as those in the embodiment 1, and will not be repeatedly described herein. Of course, in the present embodiment, the first conductive spacer **1071** and the second conductive spacer **1072** may also be manufactured on the first substrate **101** and the second substrate **102** respectively, and manufacturing procedures thereof are the same as the above case in the present embodiment, and will not be repeatedly described herein.

In the display panel manufactured by the manufacturing method provided by the present embodiment, the cathode layer **106** thereof is connected to the auxiliary electrode **111** through the first conductive spacers **1071** and the second conductive spacers **1072**, the conductivity of the cathode layer **106** is improved significantly, and thus the luminance uniformity of the display panel is improved.

Embodiment 5

The present embodiment provides a display device comprising the display panel of the embodiment 1. The display device may be any product or component with display function, such as a mobile phone, a tablet computer, a TV, a display, a notebook computer, a digital image frame, a navigator.

In the display device comprising the display panel of the embodiment 1, the cathode layer thereof is connected to the auxiliary electrode **111** through the conductive spacers **107**, the conductivity of the cathode layer **106** is improved significantly, the luminance uniformity of the display panel is improved, and thus the display effect of the display device is excellent.

Of course, the display device of the present embodiment may further comprise other conventional structures, such as a power supply unit, a display driving unit and the like.

It should be understood that, the above embodiments are only exemplary embodiments employed to illustrate the principle of the invention, and the invention is not limited thereto. Persons skilled in the art can make various modifications and improvements without departing from the principle and substance of the invention, and these modifications and improvements should be considered to be within the protection scope of the invention.

The invention claimed is:

1. A display panel comprising a first substrate and a second substrate which are assembled, wherein

the second substrate is provided with an organic electroluminescent device thereon, an anode layer of the organic electroluminescent device is away from the first substrate and a cathode layer thereof is closer to the first substrate than is the anode layer;

the cathode layer of the organic electroluminescent device is electrically connected to an auxiliary electrode on a light entering surface of the first substrate through a

11

plurality of conductive spacers, the plurality of conductive spacers are spaced apart from each other, and the cathode layer is a transparent electrode layer; and the auxiliary electrode has a resistance smaller than that of the cathode layer of the organic electroluminescent device;

wherein the auxiliary electrode is a plate-shaped auxiliary electrode which is transparent and conductive, and a thickness of the auxiliary electrode is in a range of 50-300 nm.

2. The display panel of claim 1, wherein the conductive spacers are made of any one of polyacetylene, PPV, polythiophene, poly p-phenylene, polypyrrole, polyaniline, poly(3,4-ethylenedioxythiophene) or combination thereof.

3. The display panel of claim 1, wherein the conductive spacers are provided on the first substrate or the second substrate.

4. The display panel of claim 1, wherein a reflective layer is provided below the anode layer of the organic electroluminescent device, and the reflective layer is used to reflect light emitted from the organic electroluminescent device to the cathode layer of the organic electroluminescent device.

5. The display panel of claim 1, wherein the organic electroluminescent device is an organic electroluminescent device emitting white light.

6. The display panel of claim 5, wherein the first substrate is provided with red filter patterns, green filter patterns and blue filter patterns spaced thereon.

12

7. The display panel of claim 1, wherein the organic electroluminescent device includes an organic electroluminescent device emitting red light, green light or blue light.

8. A display device comprising the display panel of claim 1.

9. The display panel of claim 1, wherein the conductive spacers include a first conductive spacer and a second conductive spacer which are connected to each other; and

the first conductive spacer is provided on the first substrate and the second conductive spacer is provided on the second substrate, or the first conductive spacer is provided on the second substrate and the second conductive spacer is provided on the first substrate.

10. The display panel of claim 9, wherein a surface area of an end of the first conductive spacer facing the second conductive spacer is smaller than that of an end of the second conductive spacer facing the first conductive spacer.

11. The display panel of claim 9, wherein a surface area of an end of the first conductive spacer facing the second conductive spacer is larger than that of an end of the second conductive spacer facing the first conductive spacer.

12. The display panel of claim 9, wherein the plate-shaped auxiliary electrode is made of any one of indium tin oxide, indium gallium zinc oxide, and indium zinc oxide.

* * * * *

专利名称(译)	具有通过导电隔离物连接到辅助电极的阴极的显示面板及其制造方法和显示装置		
公开(公告)号	US10411189	公开(公告)日	2019-09-10
申请号	US14/422271	申请日	2014-07-15
[标]申请(专利权)人(译)	京东方科技集团股份有限公司		
申请(专利权)人(译)	京东方科技集团股份有限公司.		
当前申请(专利权)人(译)	京东方科技集团股份有限公司.		
[标]发明人	KONG XIANGYONG WANG DONGFANG		
发明人	KONG, XIANGYONG WANG, DONGFANG		
IPC分类号	H01L51/00 H01L51/56 H01L27/32 H01L51/50 H01L51/52		
CPC分类号	H01L51/5234 H01L51/5271 H01L51/56 H01L51/5228 H01L51/0024 H01L51/0023 H01L51/5036 H01L51/525 H01L51/5218 H01L27/322 H01L2251/5315		
优先权	201310557149.5 2013-11-11 CN		
其他公开文献	US20160035980A1		
外部链接	Espacenet		

摘要(译)

本发明提供一种显示面板及其制造方法和显示装置，属于显示装置制造技术领域，可以解决现有显示装置中的以下问题：当光线透过薄的阴极层时，电阻高，导电性差，显示效果不均匀。本发明的显示面板包括组装的第一基板和第二基板，其中第二基板上设置有有机电致发光器件，有机电致发光器件的阳极层远离第一基板及其阴极层靠近第一个基板；阴极层通过以一定间隔隔开的多个导电垫片电连接到第一基板的位于表面上的辅助电极，其中阴极层是透明电极层。

